Chemical Science

EDGE ARTICLE



View Article Online View Journal | View Issue

Check for updates

Cite this: Chem. Sci., 2025, 16, 1271

All publication charges for this article have been paid for by the Royal Society of Chemistry

Structural characterization of surface immobilized platinum hydrides by sensitivity-enhanced ¹⁹⁵Pt solid state NMR spectroscopy and DFT calculations[†]

Benjamin A. Atterberry, (1) ‡^{ab} Erik J. Wimmer, (1) ‡^c Sina Klostermann,^c Wolfgang Frey,^c Johannes Kästner, (1) ^c Deven P. Estes (1) *^c and Aaron J. Rossini (1) *^{ab}

Supported single-site platinum hydride compounds are promising heterogeneous catalysts for organic transformations. Few methods exist to describe the structures of single-site Pt catalysts with atomic resolution because of their disordered structures and low Pt loadings. Here, we study the compounds formed when bis(tri-tert-butylphosphino)platinum, Pt(P^tBu₃)₂, is supported on dehydroxylated SiO₂ or SiO₂-Al₂O₃. First, we obtain magic angle spinning (MAS) ¹H, ³¹P and ¹⁹⁵Pt ssNMR spectra of four model Pt phosphine compounds with oxidation states of 0 or +2 and coordination numbers between 2 and 4. These compounds are analogs of potential structures present in the supported compounds. MAS ¹⁹⁵Pt ssNMR spectra were obtained using ³¹P{¹⁹⁵Pt} sideband selective J-resolved and J-HMQC experiments. The measured ¹H and ³¹P chemical shifts, ${}^{31}P - {}^{195}Pt$ J-couplings and ${}^{195}Pt$ chemical shift (CS) tensors are shown to be diagnostic of oxidation state and coordination number. Room temperature ¹H ssNMR spectra of Pt(P^tBu₃)₂ supported on SiO₂ or SiO₂-Al₂O₃ show diagnostic hydride NMR signals, suggesting that Pt(P^tBu₃)₂ undergoes oxidative addition, resulting in surface hydrides and Pt-oxygen bonds to the support surface. MAS dynamic nuclear polarization (DNP) enables ³¹P(¹⁹⁵Pt) correlation NMR experiments on the supported compounds. These experiments enable the measurement of the ³¹P-¹⁹⁵Pt J-coupling constants and ¹⁹⁵Pt CS tensors. Combined NMR and DFT analyses suggest that the primary surface platinum species are $[HPt(P^tBu_3)_2OSi]$ on SiO₂ and $[HPt(P^tBu_3)_2]^+[Si-O^--AI]$ on SiO₂-Al₂O₃. The Pt-oxygen bond length is dependent on the support and estimated as 2.1–2.3 Å and 2.7–3.0 Å for SiO₂ and SiO₂-Al₂O₃, respectively.

Received 23rd September 2024 Accepted 20th November 2024

DOI: 10.1039/d4sc06450j

Introduction

Single-site or single-atom platinum catalysts find widespread application in industrial processes such as fuel production, automotive catalytic converters for emissions control, hydrogenation reactions, hydrosilylation and other organic reactions.¹⁻⁶ One such notable class are the platinum hydride catalysts, renowned for their exceptional catalytic performance in cycloisomerization, isomerization and hydroformylation reactions.⁷⁻⁹ However, Pt and Pd catalysts often suffer from a significant drawback in homogeneous catalysis: deactivation through

^bUS DOE Ames National Laboratory, Ames, Iowa, 50011, USA

dimerization.¹⁰⁻¹² To overcome this limitation, heterogeneous catalysts can be used because they prevent dimerization and enable the reusability of the platinum hydride.¹³ Heterogeneous catalysts can be synthesized *via* surface organometallic chemistry (SOMC), which involves immobilizing well-defined metal complexes on metal oxide surfaces.¹⁴⁻¹⁸ In SOMC, metal oxide samples undergo controlled dehydroxylation at high temperature and high vacuum, resulting in a surface covered with a controlled density of chemically similar OH groups. These OH groups serve as ligands for organometallic complexes, typically achieved through protonolysis reactions where a basic ligand deprotonates the OH group. This process forms a new M–O bond directly to the surface while releasing HX.¹⁹

Recently, some of the authors of this paper utilized surface OH groups on Brønsted acidic supports like $SiO_2-Al_2O_3$ to immobilize $Pt(PR_3)_2$ complexes.¹³ Through solid-state nuclear magnetic resonance (ssNMR) spectroscopy, infrared spectroscopy (IR), and X-ray absorption spectroscopy (XAS) characterization, we discovered that the immobilization occurred *via* the apparent oxidative addition of OH groups to the Pt(0) center in the precursor, resulting in Pt(II)–H species with a new Pt–O bond

[&]quot;Iowa State University, Department of Chemistry, Ames, IA, 50011, USA. E-mail: arossini@iastate.edu; deven.estes@itc.uni-stuttgart.de

^cUniversity of Stuttgart, Department of Chemistry, Stuttgart, Baden-Württemberg, 70569, Germany

[†] Electronic supplementary information (ESI) available: Additional SIMPSON simulation results and solid-state NMR spectra. CCDC 2339745-2339747. For ESI and crystallographic data in CIF or other electronic format see DOI: https://doi.org/10.1039/d4sc06450j

[‡] These authors contributed equally.

to the surface. This finding is quite rare, with only two known examples reported in the literature so far.^{13,20} The Pt–O bond length (2.01 Å) measured by EXAFS in our study was indicative of a four-coordinate Pt–H with a slightly elongated Pt–O bond.²¹ However, the Pt–H ¹H chemical shift (-36 ppm) and J_{Pt-H} (2400 Hz) values were more consistent with formation of cationic three-coordinate Pt–H, such as [($^{t}Bu_{3}P)_{2}Pt-H$]⁺. Based on these observations, we proposed that the structure on the surface lies somewhere between three- and four-coordinate, where the nature of the Pt–O bond is something in between a true Pt–O bond and an ion pair. Thus, additional experimental methods are needed to characterize the structure of these surface species.

¹⁹⁵Pt ssNMR spectroscopy is potentially an appealing method to investigate the structure of surface-supported platinum organometallics. Essential information about the chemical and electronic environments of Pt centers in catalysts are encoded in the 195Pt chemical shift (CS) tensor, which is sensitive to the bonding character and symmetry of the neighboring ligands.²²⁻³² However, ¹⁹⁵Pt NMR experiments in the solid-state are often challenging because Pt compounds often exhibit a large 195Pt chemical shift anisotropy (CSA) on the order of several thousand parts-per-million (ppm), especially for $Pt(\pi)$ complexes, which typically adopt a square planar geometry.23,33,34 Several notable methods have been proposed to expedite the measurement of ¹⁹⁵Pt ssNMR spectra and CS tensors. Schurko and coworkers have incorporated Wideband Uniform Rate Smooth Truncation (WURST) pulses35,36 and broadband adiabatic inversion cross-polarization (BRAIN-CP)37 into Carr-Purcell-Meiboom-Gill (CPMG)38 sequences that allow static ¹⁹⁵Pt ssNMR spectra to be acquired with increased sensitivity on molecular complexes. Unfortunately, it is timeconsuming to study single-site Pt catalysts using these methods because they have low Pt loadings (<5 wt%). To address this challenge, dynamic nuclear polarization surface enhanced NMR spectroscopy (DNP SENS) has been used to increase the sensitivity of static37,39 and magic angle spinning (MAS)^{27,40} ¹⁹⁵Pt ssNMR experiments. We have also previously shown that a sensitive spy nucleus like ¹H, ³¹P, or ¹³C can be used to enable acquisition of wideline ¹⁹⁵Pt ssNMR spectra, including for detection of surface species.^{27,41,42} Further gains in sensitivity have been achieved by combining indirect detection MAS experiments with DNP SENS. Most indirect detection ssNMR experiments have used MAS frequencies >25 kHz, while slower MAS frequencies less than 12.5 kHz have not been employed yet.27

In this work, we use room temperature fast MAS ${}^{1}H{}^{195}Pt$ and ${}^{1}H{}^{-31}P{}^{195}Pt$ *J*-resolved and *J*-HMQC experiments to investigate four different molecular bis(tri-*tert*-butylphosphino) platinum compounds (Fig. 1). These compounds feature Pt in oxidation states of 0 and +2 and some of the compounds have coordinated hydrides. We then use slow MAS (12.5 kHz) cryogenic DNP SENS ${}^{1}H{}^{-31}P{}^{195}Pt$ *J*-resolved experiments to study two low Pt wt% (1.9 and 2 wt%) single-site catalysts. By comparing the ${}^{1}H$, ${}^{31}P$, and ${}^{195}Pt$ ssNMR spectra of two-, three-, and four-coordinate Pt model complexes (1–4) with those of the surface complexes, we were able to gain insights into the nature of the Pt–O bond on the surface. These methods, combined with



Fig. 1 (A) Graphical summary of the characterization of molecular and surface-supported Pt complexes. (B) Molecular structures and X-ray crystal structures are shown for $Pt(P^tBu_3)_2$ (1), $HPt(P^tBu_3)_2Cl$ (2),⁴³ [$HPt(P^tBu_3)_2]BF_4$ (3), and $[HPt(P^tBu_3)_2NCCH_3]BF_4$ (4). (C) Hypothesized structures are shown for the supported single-site Pt complexes discussed in this work. The Pt loadings in the supported single-site materials were 2 wt% (1/SiO₂-Al₂O₃) and 1.9 wt% (1/SBA-15).

DFT calculations, offer a blueprint of the electronic and coordination spheres of the molecular and surface-supported complexes. Overall, these experiments allow us to put forward evidence-based structural models of surface-supported platinum hydride compounds.

Results & discussion

Overview

First, we applied ssNMR spectroscopy to molecular platinum hydride and phosphine compounds (Fig. 1). These compounds

serve as analogs for different surface species that could be present when supporting bis(tri-*tert*-butylphosphino)platinum (1) on SBA-15 or SiO₂–Al₂O₃. For each molecular compound, we measured the ¹H, ³¹P, and ¹⁹⁵Pt isotropic chemical shifts, ¹⁹⁵Pt anisotropic chemical shift tensor parameters, and ³¹P–¹⁹⁵Pt and ¹H–¹⁹⁵Pt *J*-couplings (when possible). These measured NMR parameters are diagnostic of the Pt oxidation state and coordination environment. These NMR parameters are also reproduced with DFT calculations. In the last part of the paper, we use DNP-enhanced ³¹P detected ssNMR experiments to study the immobilized platinum phosphine compounds supported on SBA-15 and on SiO₂–Al₂O₃. Comparison of experimental and calculated ¹⁹⁵Pt CS tensor parameters and hydride ¹H chemical shifts are used to elucidate structural models for the surface species formed on the two different supports.

¹H, ³¹P and ¹⁹⁵Pt ssNMR experiments on molecular complexes

We begin with a study of the molecular platinum phosphine compounds, 1–4. Fig. 2A shows the ³¹P CPMAS NMR spectrum and a rotor-synchronized ³¹P{¹⁹⁵Pt} *J*-HMQC spectrum of 1. The 1D ³¹P CPMAS NMR spectrum shows two satellites that arise from a *J*-coupling of 4407 Hz between ¹⁹⁵Pt and ³¹P. In the 2D *J*-HMQC spectrum, only the satellite peaks are visible. The ³¹P {¹⁹⁵Pt} *J*-HMQC was recorded with the *t*₁-increment set to a rotor period (40 µs), corresponding to the indirect dimension spectral width being equal to the MAS frequency (25 kHz). Rotor

synchronization of the indirect dimension maximizes sensitivity of the 2D experiments because all the spinning sidebands will be aliased onto a single peak. From the 2D ³¹P{¹⁹⁵Pt} J-HMQC spectrum, we can determine the offset of a single ¹⁹⁵Pt spinning sideband, which was -605492 Hz from the reference ¹⁹⁵Pt frequency in this case. Once we know the offset of a single sideband, we can then perform sideband selective $1D^{31}P_{1}^{195}Pt_{2}$ J-HMQC or J-resolved NMR experiments that enable us to map out the intensity of each spinning sideband that makes up the entire ¹⁹⁵Pt MAS ssNMR spectrum (Fig. 2B and C).^{41,42} The sideband selective NMR experiments use ¹⁹⁵Pt selective long (SL) pulses that have durations of one rotor cycle or longer and RF fields less than 50 kHz.44 Each line represents the measured intensity or dephasing of the ³¹P NMR signal at the indicated ¹⁹⁵Pt offset. Note that sideband selective experiments also require the RF-field strength of the pulses to be accurately calibrated because using an RF field 10 kHz higher-thanoptimal will result in an NMR spectrum that does not accurately reconstruct the MAS ¹⁹⁵Pt ssNMR spectrum.⁴²

Fig. 2B and C show experimental ${}^{1}H{-}^{31}P{}^{195}Pt$ *J*-HMQC and *J*-resolved sideband selective NMR spectra of 1 obtained with 80 μ s ${}^{195}Pt$ saturation pulses, with RF fields of 5 kHz and 9 kHz RF for *J*-HMQC and *J*-resolved, respectively. 42 In both cases, the sideband selective spectra match closely with the overlaid ideal MAS ${}^{195}Pt$ ssNMR spectrum. The NMR spectra shown in Fig. 2B and C were obtained in 3 hours and 45 minutes, respectively.



Fig. 2 Graphical illustration of implementing a sideband selective experiment for compound **1**. (A) 1D ${}^{1}H^{-31}P$ CPMAS spectrum overlaid on the rotor-synchronized ${}^{1}H^{-31}P$ { $}^{195}Pt$ } J-HMQC spectrum. Reconstructed ${}^{195}Pt$ ssNMR spectra obtained using (B) sideband selective ${}^{1}H^{-31}P$ { $}^{195}Pt$ } J-HMQC and (C) ${}^{1}H^{-31}P$ { $}^{195}Pt$ } J-resolved experiments (black lines). The intensities of the sidebands are compared to the SIMPSON-calculated ideal ${}^{195}Pt$ MAS NMR spectrum (blue lines). All NMR experiments were performed with a 25 kHz MAS frequency and a magnetic field of 9.4 T. The ${}^{195}Pt$ saturation pulses were 80 μ s in duration with RF fields of 5 kHz and 9 kHz RF for J-HMQC and J-resolved, respectively.



Fig. 3 195 Pt ssNMR spectra reconstructed using 31 P(195 Pt) *J*-resolved (left) and 31 P(195 Pt) *J*-HMQC (right) sideband selective experiments along with SIMPSON fits for structures 1, 2, and 4. 1 H(195 Pt) *J*-resolved and *J*-HMQC experiments are shown for 3. Sideband selective experiments and SIMPSON fits are colored black and pink, respectively. The chemical shift (CS) tensors from the SIMPSON fits are given with the Herzfeld–Berger convention.⁴⁵ Error bars are overlaid on the most intense spinning sidebands.

Fig. 3 shows ³¹P{¹⁹⁵Pt} *J*-resolved and *J*-HMQC sideband selective experiments for **1**, **2**, and **4** obtained with a 25 kHz MAS frequency. For **3**, ¹H{¹⁹⁵Pt} *J*-resolved and *J*-HMQC sideband selective experiments were performed at 50 kHz MAS. ¹H spin echo and ¹H-³¹P CPMAS NMR spectra for complexes **1**-4 are shown in Fig. S1.† Overall, Fig. 3 illustrates that we can quickly and accurately measure the ¹⁹⁵Pt ssNMR spectra of Pt–phosphine

or hydride compounds. Below, we discuss trends in the measured ¹⁹⁵Pt, ¹H and ³¹P chemical shifts and *J*-coupling constants.

The clear identification of oxidation state and coordination sphere symmetry can be achieved by analyzing the trends in the ¹⁹⁵Pt CS tensors. Comparing the ¹⁹⁵Pt isotropic shifts reveals that complex **1** with an oxidation state of Pt(0) gives rise to the most negative shift (-6450 ppm) and complexes **2–4** with Pt(II) have more positive shifts (-4200 ppm to -5000 ppm). This observation is consistent with the results obtained from ¹⁹⁵Pt solution NMR experiments.46-48 The second parameter that gives insight about geometry at the Pt atoms is the span (Ω) . As shown in Fig. 3, Ω is much larger for the three-coordinate complex (3, ca. 5750 ppm) in comparison to the fourcoordinate complexes (2, 4, ca. 2500 ppm). Although, we caution that the Ω is also sensitive to the electronic nature of the ligands, with stronger donors leading to smaller Ω .⁴¹ The last parameter to discuss would be the asymmetry parameter of the CS tensor (κ). For the four-coordinate compounds, κ is close to -1, indicating the presence of a mirror plane (or C_2 symmetric or higher rotational axis) and the requirement for two of the three parameters in the CS tensor to be the same. Similarly, the three- and two-coordinate compounds exhibit a κ close to +1. The transition from $\kappa = -1$ to $\kappa = +1$ can be attributed to shifts in the electronic configuration due to differences in the coordination number (less electron donation perpendicular to the P-Pt-P axis), consequently altering the energies of the d orbitals and thus the positions of the corresponding tensor components. The ¹⁹⁵Pt CS tensor parameters provide a reliable means of determining the oxidation state or coordination environment of an unknown complex.

In addition, the ³¹P and ¹H ssNMR spectra are diagnostic of the Pt oxidation state. Specifically, a three-coordinate Pt–H complex exhibits a characteristic hydride chemical shift in the ¹H NMR shift at *ca.* –38 ppm, whereas the four-coordinate complexes display shifts around –19 ppm (Fig. S1†). We also observed that the ³¹P shift for **1** is centered at 100 ppm (Pt⁰) and **2–4** have ³¹P shifts around 70–80 ppm (Pt^{II}). Finally, the ³¹P–¹⁹⁵Pt *J*-couplings could be directly measured based on the difference in frequencies of the satellite peaks in the ³¹P NMR spectra, except for **4**, for which we used a *J*-resolved evolution curve to measure the *J*-coupling (Fig. S2†). For complex **1**, a sizeable ³¹P–¹⁹⁵Pt *J*-coupling is observed (¹*J*(³¹P–¹⁹⁵Pt) = 4407 Hz), which is typical of Pt⁰ compounds.⁴⁹ But for complexes **2–4**, ¹*J*(³¹P–¹⁹⁵Pt *J*) decreases to ~2500 to ~3000 Hz. The ¹H–¹⁹⁵Pt *J*- couplings for complexes 2–4 were also measured and ${}^{1}J({}^{1}H-{}^{195}Pt)$ is ~1000 Hz for 4-coordinate complexes (2 & 4) and 2630 Hz for the 3-coordinate complex (3). These characteristic chemical shifts and coupling constants supply valuable information that can aid in the investigation of surface-supported samples. The root mean square error plots for the numerical fits of the ${}^{31}P{}^{195}Pt$ *J*-resolved and *J*-HMQC sideband selective experiments on 1–4 are shown in Fig. S3.†

DFT calculations of NMR observables

Modern computational chemistry methods can accurately predict CS tensors^{50,51} and *J*-couplings^{52,53} for heavy nuclei such as ¹⁹⁵Pt. We geometrically optimized the H-atom positions in the X-ray crystal structures of complexes **1–4** using DFT calculations in CASTEP⁵⁴ and then used molecular DFT calculations in the Amsterdam Modeling Suite⁵⁵ along with a hybrid density functional^{56,57} to predict the NMR parameters. Overall, the calculated and experimental ¹H, ³¹P and ¹⁹⁵Pt NMR parameters are in good agreement for complexes **1**, **2**, and **4** (Table 1 and Fig. 4).

While calculating the CS tensors with optimized H atom positions and crystallographic coordinates for heavy atoms (crystal structures for 2-4 are shown in Fig. S13-S15 and Tables S3-S5[†]) worked well for complexes 1, 2, and 4, the agreement for complex 3 was less than satisfactory. As for 1, 2, and 4 we calculated the ¹⁹⁵Pt CS tensor using the single crystal X-ray diffraction structure (with DFT optimization of the H atom positions). This calculation gave a predicted ¹⁹⁵Pt NMR spectrum with $\delta_{iso} = -3717$ ppm, $\Omega = 7325$ ppm, and $\kappa = -0.10$, which was significantly different from the experimental spectrum that we measured for 3 ($\delta_{iso} = -4214$ ppm, $\Omega = 5798$ ppm, and $\kappa = 0.78$) (Fig. 5, bottom). Examination of the experimental ¹H and ³¹P NMR spectra shows that the complex has not decomposed before measurement (signals for Pt-H and of the $P^{t}Bu_{3}$ groups are correct, Table 1 and Fig. S1[†]). However, we have observed that the crystal lattice of 3 is not stable over long time periods due to slow loss of the dichloromethane solvents

Table 1	Experimental ar	nd calculated	chemical	shifts and	spin-spin	couplinas
	Export interitor at at		0110111001	0111100 01110	00000	000.00.00

Compound	Pt oxidation state	Geometry	Method	$\begin{array}{l} Hydride \\ \delta_{iso} \left({}^{1}H \right) \\ (ppm) \end{array}$	$\delta_{iso} \left({}^{31}P \right)$ (ppm)	¹ J (³¹ P- ¹⁹⁵ Pt) (Hz)	¹ J (¹ H- ¹⁹⁵ Pt) (Hz)	¹⁹⁵ Pt δ _{iso} (ppm)	¹⁹⁵ Pt Ω (ppm)	¹⁹⁵ Ρt κ
1	+0	Linear	Experiment	_	100	4407	_	-6450	5313	0.95
			X-ray structure	_	100	5226	_	-6392	5272	0.99
2	+2	Square planar	Experiment	-19	76	3025	1100	-4764	2424	-0.88
			X-ray structure	-17	81	3386	1071	-4716	2078	-0.81
3	+2	T-shaped	Experiment	-38	88	2624	2630	-4214	5798	0.78
		-	X-ray structure	-35	92	3088	3117	-3717	7325	-0.10
			One trans	-27	62, 34	2114	2355	-4154	5168	-0.17
			Two orthogonal	-32	62, 47	3031	4278	-3188	7109	0.33
4	+2	Square planar	Experiment	-19	95, 78	2793	1030	-4969	2559	-0.83
			X-ray structure	-15	90, 66	2822, 3049	1114	-4885	2019	-0.67
1/SiO ₂ -Al ₂ O ₃	+2	Square planar/	Experiment	-35	82	2433	2400	-4841	5680	-0.6
		T-shaped	Optimized structure	-32	85	3434	1882	-4385	6314	-0.3
1/SBA-15	+2	Square planar/	Experiment (hydride)	-26	72	2908	1034	-4441	4080	0.0
		T-shaped	Experiment (C-H activated)	-	52	—	_	-3541	7980	0.0
			Optimized Structure	-26	99	3315	1213	-4484	3775	-0.8



Fig. 4 Simulated ¹⁹⁵Pt static ssNMR spectra for compounds **1**, **2**, and **4**. Black lines show the spectra simulated using ¹⁹⁵Pt CS tensors measured with the MAS ssNMR experiments and solid blue patterns correspond to DFT calculated ¹⁹⁵Pt CS tensors.

of crystallization from the crystal lattice (Fig. S4[†]). Indeed, placing the crystals under vacuum even for short periods results in reduced crystallinity. We theorized that the local structure of 3 could change upon loss of the solvents of crystallization to give a different coordination environment - changing the CS tensor. One commonly observed interaction in similar T-shaped cationic Pt phosphine complexes is the formation of C-H agostic interactions, which is notably absent from the crystal structure of complex 3.58-62 Indeed, DFT calculations showed that optimization of the methyl positions resulted in a new structure, 3(trans), which features a C-H agostic interaction in the position *trans* to the hydride ligand is *ca.* 4.5 kcal mol⁻¹ more stable than the structure with no agostic interactions (3(Xray)). The optimized structure of 3(trans) showed a Pt-C distance of 2.77 Å and a \angle H–Pt–C = 157.30°, both of which are typical for such complexes.⁶³ We therefore calculated the ¹⁹⁵Pt NMR parameters of 3(trans) and found that the agreement with our experimental observations was now significantly better (δ_{iso} = -4154 ppm, Ω = 5168 ppm, and κ = -0.17). It is evident that if methyl groups participate in secondary bonding there is a change two of the principal components of the ¹⁹⁵Pt CS tensor $(\delta_{11} \text{ and } \delta_{22})$ but not δ_{33} . Still, the agreement between the calculated NMR parameters of 3(trans) and the experimental spectrum of **3** is not perfect. The δ_{22} tensor component shows the largest deviation, as demonstrated by the very different κ value for 3(trans). We also examined another model, 3(ortho),



Fig. 5 Comparison of the ¹⁹⁵Pt ssNMR spectrum for complex **3** and the DFT-calculated ¹⁹⁵Pt NMR spectra for different structural models. Calculations were performed with the single crystal X-ray diffraction structure (bottom), a modified structure featuring one agostic interaction between Pt and a methyl group C–H bond that was oriented *trans* to the platinum hydride bond (middle), and two Pt methyl C–H agostic interactions orthogonal to the platinum hydride bond (top). A green dashed line indicates an agostic interaction.

having agostic interactions in the apical position (orthogonal to the H-Pt-P plane). This led to a structure with two agostic interactions perpendicular to the T-shaped coordination structure and had an energy that is *ca.* 40 kcal mol⁻¹ higher than **3**(*trans*). The NMR parameters of this species were also quite different than the experimental spectrum. Calculations predict a large ¹H-¹⁹⁵Pt *J*-coupling for **3**(*ortho*) (3031 Hz), which is much larger than what is predicted for **3**(*trans*) (2114 Hz) and what is observed experimentally (2630 Hz). The ³¹P and ¹H spectra predicted for 3(trans) also match the experimental spectrum better than what is seen for the other two models. However, we only see one chemically equivalent peak for the P^{*t*}Bu₃ groups in **3**, rather than the two inequivalent signals predicted for **3**(*trans*). Therefore, we hypothesize that the experimental spectrum of **3** can be explained by formation of a *trans*-agostic interaction upon loss of solvated dichloromethane from the crystal lattice. The observed chemical equivalency of the P atoms of the two phosphines of **3** could be the result of rapid exchange between methyl groups in the agostic position.

In summary, NMR experiments on complexes 1–4 illustrate how ¹⁹⁵Pt CS tensors can be measured and related back to the structural features and Pt oxidation states of the compounds. The ³¹P and ¹H chemical shifts and ³¹P–¹⁹⁵Pt *J*-coupling constants also provide valuable structural information. Using relativistic DFT calculations it is possible to accurately reproduce the NMR observables. With these capabilities in hand, we now turn to the structural characterization of surface-supported platinum phosphine compounds.

ssNMR experiments on surface-supported complexes

We sought to understand the chemical structure of the surfacesupported complexes $1/SiO_2-Al_2O_3$ and 1/SBA-15. The surface immobilized complexes were synthesized by reacting a solution of 1 at room temperature with either $SiO_2-Al_2O_3$ or SBA-15 for 18 hours, as we reported previously.¹³ ³¹P CPMAS NMR spectra show that the results of the immobilization are highly dependent on the level of dehydroxylation of the material (Fig. 6).

We immobilized 1 on SiO₂-Al₂O₃ that had not been dehydroxylated, as well as material dehydroxylated at 200 °C and at 500 °C. When the material had not been dehydroxylated, a major peak at 53.7 ppm corresponding to the protonated phosphine $HP^{t}Bu_{3}^{+}$ and a minor peak at 79.9 ppm corresponding to the four coordinate hydrated complex $[HPt(P^tBu_3)_2(OH_2)]^+$ were observed.^{64,65} Additionally, two other minor peaks can be seen at 70 ppm and 24 ppm that have been more difficult to assign. Four coordinate platinum hydrides are known to activate the C-H bonds of ligated P^tBu₃ at relatively mild conditions to give the cyclometallated Pt complexes and loss of H2 (vide infra).11 We did not observe formation of tri-tertbutylphosphine oxide (66.5 ppm)⁶⁶ in any of the grafted samples. However, the chemical shift of tri-tert-butylphosphine oxide can vary considerably due to hydrogen bonding to surface Brønsted and Lewis acid sites.67-71

The rate of C–H activation is highly dependent on the identity of the fourth ligand. For four-coordinated Pt complexes, the metalation rate decreases in the order I > Br > Cl > O₂CCF₃ \approx NO₃, with the *trans*–I complex undergoing cyclometallation in less than 24 hours.¹¹ In contrast, for three-coordinated complexes with non-coordinating anions (*e.g.* BF₄⁻), no cyclometallation is observed (Scheme 1).⁶⁴ While the mechanism of the C–H activation in these cases is not completely clear, there seems to be a relationship between the rate of cyclometallation and the *trans*-influence of the fourth ligand, which matches the trend observed above. The signals of cyclometallated complexes



Fig. 6 Room temperature ³¹P CPMAS ssNMR spectra of **1/SBA-15** (green) and **1/SiO₂-Al₂O₃** made with SiO₂-Al₂O₃ had not been dehydroxylated (red), dehydroxylated at $T_d = 200$ °C (purple), and dehydroxylated at $T_d = 500$ °C (blue).

of the type $[Pt(-CH_2CMe_2P'Bu_2)(P'Bu_3)]^+$ in the ³¹P NMR spectrum also vary depending on the identity of the counterion/ fourth ligand. The resonance corresponding to coordinated P'Bu₃ falls between 70 and 59 ppm while the cyclometallated phosphine can have values between 25 and -16 ppm. Thus, the observed NMR signals at 70 and 24 ppm in $1/SiO_2-Al_2O_3$ dehydroxylated at room temperature could be consistent with cyclometallation after the initial preparation (*vide infra*).^{11,72} However, upon dehydroxylation of the surface at temperatures up to 500 °C, all of these signals give way to a complex with spectral signals similar to that of three coordinate 3 (δ^{31}_{P} =



Scheme 1 C–H activation and formation of cyclometallated Pt species on silica surfaces (top) and non-activated 3-coordinated Pt–H on SiO_2 –Al₂O₃ surfaces (bottom).

84.7 ppm, $\delta_{Pt-H} = -35$ ppm), which becomes the main species on the surface dehydroxylated at 500 °C. Degradation over time was observed towards forming more protonated phosphine, with only small amounts of C-H activation. Therefore, our subsequent analysis focused on **1/SiO₂-Al₂O₃** prepared with SiO₂-Al₂O₃ that was dehydroxylated at 500 °C. Since we mostly observe the four-coordinate [HPt(P^tBu₃)₂(OH₂)]⁺ complex on the surface of partly hydroxylated supports, this would explain its propensity for undergoing slow cyclometallation, which is not observed in the three-coordinate $[HPt(P'Bu_3)_2]^+$ species formed on the dehydroxylated surfaces.

Interestingly, regardless of the dehydroxylation temperature, only one species forms for **1/SBA-15** indicated by the presence of a ³¹P NMR signal at 80 ppm. However, over time, we also



Fig. 7 (A) Room temperature MAS ¹H spin echo NMR spectra of $1/SiO_2-Al_2O_3$ (left) and 1/SBA-15 (right). (B) DNP-enhanced ³¹P{¹⁹⁵Pt} *J*-resolved control (*S*₀), dephasing (*S*) and difference (*S*₀ – *S*) spectra. Spectra were obtained with CPMG detection and co-addition of the spin echoes in the time domain. Spectra were acquired with a 0.32 ms *J*-evolution time (spin echo duration). A higher resolution DNP-enhanced ³¹P CPMAS spin echo spectrum is overlaid. (C) ³¹P{¹⁹⁵Pt} *J*-evolution plots. Black circles and pink lines correspond to experimental data points and least-squares fit, respectively. (D) Plot of ³¹P{¹⁹⁵Pt} *J*-resolved signal dephasing as a function of ¹⁹⁵Pt offset. The black lines with data markers correspond to experiments on complexes $1/SiO_2-Al_2O_3$ and 1/SBA-15, and the pink line is the SIMPSON fit of the experiment on complex $1/SiO_2-Al_2O_3$ ($\delta_{iso} = -4841$ ppm, $\Omega = 5680$ ppm, $\kappa = -0.6$). The green and blue lines are the SIMPSON fits for site 1 ($\delta_{iso} = -4441$ ppm, $\Omega = 4080$ ppm, $\kappa = 0.0$) and site 2 ($\delta_{iso} = -3541$ ppm, $\Omega = 7980$ ppm, $\kappa = 0.0$), respectively, of 1/SBA-15.

observed C–H activation, which might be accelerated under reduced pressure when the compounds are stored in sealed tubes under vacuum (see Fig. S6–S8†); two additional ³¹P peaks are visible at 56 and 24 ppm in the DNP-enhanced ³¹P ssNMR spectrum of **1/SBA-15**. These chemical shifts are consistent with the literature-reported C–H activated Pt(P^tBu₃)₂ complex.⁷²

We used a combination of room temperature 25 kHz MAS frequency and 100 K DNP SENS NMR experiments (12.5 kHz MAS frequency) to assess the Pt coordination sphere of 1/SiO₂-Al₂O₃ and 1/SBA-15. Due to the low concentration of the phosphine compounds on the surface, DNP was used to boost the sensitivity of the ³¹P{¹⁹⁵Pt} J-resolved NMR experiments. Fig. 7A shows ¹H spin echo NMR spectra of 1/SiO₂-Al₂O₃ and 1/SBA-15 recorded with a 25 kHz MAS frequency. Both materials show negatively shifted ¹H NMR signals attributed to hydride protons. The chemical shifts of the hydride peaks are -35 ppm for 1/SiO₂-Al₂O₃ and -26 ppm for 1/SBA-15. The hydride ¹H NMR signals also show splittings attributable to ¹H-¹⁹⁵Pt spinspin couplings (2.6 and 1.7 kHz for 1/SiO₂-Al₂O₃ and 1/SBA-15, respectively). For $1/SiO_2$ -Al₂O₃ we confirmed that the satellite peaks dephase in a ${}^{1}H{}^{195}Pt{}$ J-resolved experiment (Fig. S5[†]), which confirms the presence of platinum hydrides in these supported compounds. A ¹H{¹⁹⁵Pt} J-resolved experiment was not conducted for 1/SBA-15 due to the poorer ¹H signal-to-noise.

We performed control room temperature ³¹P ssNMR experiments on samples of **1/SBA-15** and **1/SiO₂-Al₂O₃** impregnated with TEMPO solutions (Fig. S6–S7†). We observed decreased ³¹P NMR sensitivity but no degradation towards C-H activated or other complexes. Therefore, the degradation to C-H activated species likely occurred while the samples were held under vacuum in sealed storage tubes for the weeks it took to ship the samples from Germany to the USA to perform DNP experiments. Exposure to the biradical does appear to cause some degradation to phosphine oxide and protonated phosphine decomposition products (*vide infra*). However, under the conditions needed for DNP enough of the Pt-H species are present for to measure the ¹⁹⁵Pt ssNMR spectra.

Fig. 7B shows DNP-enhanced ³¹P{¹⁹⁵Pt} J-resolved control (S_0) , dephasing (S), and difference $(S_0 - S)$ spectra. The ³¹P NMR spectrum of 1/SiO₂-Al₂O₃ shows the same peak at 82 ppm due to the $[HPt(P^tBu_3)_2]$ fragment, along with new peaks at 71 ppm (OP^tBu_3) and 57 ppm $(HP(^tBu_{3^+}))^{.65,73}$ These new peaks were due to partial decomposition from the DNP biradical solution (Fig. S7-S8[†]). The ³¹P NMR of 1/SBA-15 shows the expected signal of the $[HPt(P^tBu_3)_2]$ fragment at 72 ppm along with new signals at 52, 25, and 4 ppm. The ³¹P-¹⁹⁵Pt J-couplings of both of the Pt–H species were measured to be 2433 and 2908 Hz for 1/SiO₂-Al₂O₃ and 1/SBA-15, respectively, which are close to the expected value of ca. 2500-3000 Hz for a ³¹P-¹⁹⁵Pt(II) bond. The ³¹P NMR signals at 52 and 25 ppm (with close to 1 : 1 ratio) can be assigned as the C-H activated $\left[\kappa^{2} - Bu_{2}P(CMe_{2}CH_{2})\right]$ $Pt(P^{t}Bu_{3})]^{+}$ complex based on the similarity to NMR spectra of known cyclometallated Pt complexes.72 While the exact nature of the decomposition peak at 4 ppm on 1/SBA-15 is at this point unclear, this is consistent with higher oxidation of the phosphine (e.g. to phosphites or phosphonates) upon reaction with TEKPol.⁷⁴ Peak fits of the ¹H-³¹P CPMAS spectra for 1/SiO₂-

 Al_2O_3 and 1/SBA-15 are shown in Fig. S9 and Table S1.[†] These fits demonstrate that while the Pt–H is still the most prominent species in $1/SiO_2-Al_2O_3$ (*ca.* 60%), the decomposition of 1/SBA-15 is significantly greater, showing that the proportion of Pt–H to C–H activated species are both *ca.* 30% of the total phosphorus.⁷²

Lastly, we performed variable ¹⁹⁵Pt offset ³¹P{¹⁹⁵Pt} *J*-resolved experiments to measure the ¹⁹⁵Pt CS tensor. These experiments were challenging for a number of reasons. First, the ¹⁹⁵Pt spinning sidebands are likely broadened by several kilohertz, meaning that at the MAS frequency of 12.5 kHz achievable in the DNP setup the sidebands will likely be overlapped with one another. Consequently, the dephasing profiles will roughly trace out the MAS spectrum sideband pattern, but it is not possible to measure sideband positions or isotropic ¹⁹⁵Pt chemical shifts with high precision. Second, we also had to use ¹⁹⁵Pt saturation pulses with durations of 120 µs and 35 kHz RF fields to induce enough dephasing in the ³¹P{¹⁹⁵Pt} J-resolved experiments (Fig. S10[†]). The use of these pulse conditions causes distortions of the dephasing profile, making it challenging to accurately determine δ_{22} or κ . Finally, under DNP conditions, the ³¹P signals suffered from inhomogeneous broadening on the order of a few kHz, reducing NMR sensitivity. To overcome the inhomogeneous broadening, a ³¹P CPMG echo train detection was used in the ³¹P {¹⁹⁵Pt} *J*-resolved experiment (Fig. S11†).

Fig. 7D shows the ¹⁹⁵Pt NMR spectra reconstructed from the ³¹P{¹⁹⁵Pt} J-resolved experiments for both 1/SiO₂-Al₂O₃ and 1/ SBA-15 along with SIMPSON-simulated fits. For the 1/SiO₂-Al₂O₃, where the Pt-H is the primary surface species, the ¹⁹⁵Pt NMR signature matches closely with complexes 2-4 (δ_{iso} = -4841 ppm, $\Omega = 5680$ ppm, $\kappa = -0.6$). The spectrum of 1/SBA-15 is somewhat more complicated and had to be fit to two Pt sites, one with a small CSA (site 1: $\delta_{iso} = -4441$ ppm, $\Omega = 4080$ ppm, κ = 0.0) and the other with a large CSA (site 2: $\delta_{iso} = -3541$ ppm, Ω = 7980 ppm, $\kappa = 0.0$). We note that for both site 1 and site 2, there is large uncertainty in the fit of κ , so it is set equal to 0.0 (Fig. S12[†]). The spectrum of site 1 was obtained by monitoring the dephasing of the spikelets in the ³¹P CPMG spectrum centered around 90 ppm (mainly from Pt-H surface complexes) while the spectrum of site 2 is from the lower frequency spikelets around 50 ppm (mainly from C-H activated complex). Hence, we believe that site 1 is the Pt hydride and site 2 is the C-H activated species (Fig. S9 and S11[†]). Dephasing of the ³¹P resonance from the cyclometallated phosphine at 25 ppm was not observed due to a lower *J*-coupling constant ($J_{Pt-P} \approx 2000 \text{ Hz}$) in comparison to Pt–H complexes ($J_{\text{Pt–P}} \approx 3000 \text{ Hz}$).

DFT modeling of surface-supported complexes

To understand the nature of the Pt–O bonds of the surface supported platinum hydrides, we created nine DFT structural models for **1/SBA-15** (Fig. 8) and six for **1/SiO₂–Al₂O₃** (Fig. 9) with varying Pt–O bond lengths. For these calculations, $[HPt(P^tBu_3)_2]^+$ fragments were ligated by $[(MeO)_3Al-O-Si(OMe)_3]^-$ or $[OSi(OMe)_3]^-$ (structural analogs of the SiO₂–Al₂O₃ and SBA-15 surface oxygen atoms, respectively) and were geometrically optimized by DFT, then the NMR parameters were calculated.



Fig. 8 (Top left) Possible structural models of **1/SBA-15** used for DFT calculations. The Pt–O bond lengths are indicated. (Top right) Comparison of DFT calculated ¹⁹⁵Pt static lineshapes for each model and experimental ¹⁹⁵Pt static lineshape for **1/SBA-15**. Green bars that are 600 ppm wide are shown at δ_{11} and δ_{33} to show the approximate combined error based upon fits of experimental dephasing profiles and standard deviation of DFT calculations. Green bars are not shown for δ_{22} due to the large uncertainty in the skew (κ). (Lower panel) Comparison of experimental (black) and calculated hydride ¹H chemical shifts (pink).

However, these model ligands do not have the same steric and electronic behavior as the true surface sites. Therefore, we subsequently geometrically optimized the same structure with constrained Pt-O bond lengths and calculated their NMR parameters. The Pt-O bond length was successively increased from the DFT calculated equilibrium distances for each model ligand in order to see the effect of lengthening the Pt-O bond on the NMR spectra and more accurately predict the true Pt-O bond length. We also carried out the same calculations for Pt(0)complexes coordinating to either surface OH or anionic surface sites using the same surface model ligands. Table S2[†] contains a detailed list of the DFT-calculated hydride ¹H and ³¹P chemical shifts, and the ¹H-¹⁹⁵Pt and ³¹P-¹⁹⁵Pt J-couplings for all structural models. The ³¹P chemical shifts and ³¹P-¹⁹⁵Pt J-couplings will not be discussed further because they change little between the structural models. The ¹H-¹⁹⁵Pt *J*-couplings differ by several hundred Hertz for each model, but due to the poor signal-tonoise in the room temperature ¹H spin echo spectra (Fig. 7A),

it was difficult to accurately measure the ${}^{1}H^{-195}Pt$ *J*-couplings, so they will not be discussed either. Based on our calculations, the ${}^{195}Pt$ CS tensors and ${}^{1}H$ chemical shift of the hydride provide crucial structural information about the surface supported complexes.

Fig. 8 shows the comparison of the experimental ¹⁹⁵Pt static lineshape to the calculated lineshapes of the model structures as well as the calculated hydride chemical shifts for **1/SBA-15**. We note that there is large uncertainty in the least-squares fit of κ/δ_{22} for **1/SBA-15**, so it is not considered here. The calculations predict that the ¹⁹⁵Pt CSA increases as the Pt–O distance increases past the calculated equilibrium distance of 2.131 Å. This prediction is consistent with our experiments that showed the three-coordinate complex **3** has a much larger CSA than either of the four-coordinate complexes **2** or **4**. The hydride shift also becomes more negative as the Pt–O distance increases (–23 ppm for model **III** and –37 ppm for model **IX**). The least squares fit of the ¹⁹⁵Pt CSA indicates that the calculated ¹⁹⁵Pt



Fig. 9 (Top left) Possible structural models of $1/SiO_2-Al_2O_3$ used for DFT calculations. The Pt–O bond lengths are indicated. (Top right) Comparison of DFT calculated ¹⁹⁵Pt static lineshapes for each model and experimental ¹⁹⁵Pt static lineshape for $1/SiO_2-Al_2O_3$. Green bars that are 600 ppm wide are shown at δ_{11} , δ_{22} , and δ_{33} to show the approximate combined error based upon fits of experimental dephasing profiles and standard deviation of DFT calculations. (Lower panel) Comparison of experimental (black) and calculated hydride ¹H chemical shifts (pink).

lineshape of model **III** matches most closely with the experimental spectrum, while the hydride ¹H chemical shift matches best with model **IV**. Therefore, we conclude the surface supported Pt–H complex present in **1/SBA-15** most likely has Pt–O distances between 2.1 Å and 2.3 Å.

The DFT structural models for $1/SiO_2-Al_2O_3$ are shown in Fig. 9. DFT calculations predicted an equilibrium Pt–O bond length of 2.383 Å. The comparison of the experimental ¹⁹⁵Pt static lineshape to the calculated lineshapes of the model structures as well as the calculated hydride chemical shifts are shown. DFT calculations predict similar trends between the Pt–O bond length and the ¹⁹⁵Pt CSA and hydride ¹H chemical shift as was seen above for **1/SBA-15**. The least squares fit of the ¹⁹⁵Pt CSA indicates that the ¹⁹⁵Pt lineshape of model **XIV** matches best with the experimental spectrum, and the hydride chemical shift. We therefore conclude that the Pt–O distance is likely between 2.7 and 3.0 Å for **1/SiO₂-Al₂O₃**.

Our experimental observations and DFT calculations demonstrate a few key differences between the Pt–H complexes on the different supports. Previous NMR and FTIR studies suggest that ca. 90% of surface Si-OH groups on SiO₂-Al₂O₃ neighbor nearby Al lewis acid sites, explaining the enhanced acidity of SiO₂-Al₂O₃ as compared to SiO₂.⁷⁵⁻⁷⁹ This higher acidity of leads to a higher Pt loading per unit surface area on SiO₂-Al₂O₃ by making the thermodynamics of the O-H oxidative addition to Pt more favorable. Consequently, the Pt loadings on SBA-15 and SiO₂-Al₂O₃ are similar, despite SBA-15 having a much larger surface area than SiO₂-Al₂O₃. Consistent with this finding, the IR spectra of SiO₂-Al₂O₃ before and after immobilization of 1 shows a decrease in the intensity of $v_{\rm OH}$ by about half (Fig. S16[†]). In contrast, the intensity of $v_{\rm OH}$ on SBA-15 shows a smaller intensity change after immobilization of 1, suggesting that only a small percentage of isolated Si-OH groups react with 1 (Fig. S17[†]). In addition, we expect that the increased acidity of the OH groups on SiO2-Al2O3 leads to longer Pt-O bond distances than for 1/SBA-15. This is because the higher acidity of the [Al-OH-Si] groups makes [Al-O-Si]⁻ more weakly coordinating than [Si-O]⁻, leading to longer Pt-O bond lengths on SiO₂-Al₂O₃. Longer Pt-O distances on SiO₂-Al₂O₃ also correlate with the propensity for the complexes to undergo C-H activation of the ^tBu groups, which is dependent



Fig. 10 Summary of structural information for supported compounds. Major surface sites after dehydroxylation at 500 °C on the respective metal oxide before reaction with 1. When 1 is supported on SBA-15 two different Pt surface species are formed: a bisphosphine hydride and a CH-activated phosphine complex. Calculations of the ¹⁹⁵Pt CSA suggest that the Pt–O bond length is between 2.1 to 2.3 Å for the bisphosphine hydride. When 1 is supported on SiO₂–Al₂O₃ a bisphosphine hydride is the major surface species. The Pt–O bond length is between 2.7 and 3.0 Å.

on the *trans*-influence of the X-type ligand (*vide supra*).¹¹ This fact explains why **1/SiO₂-Al₂O₃** shows no C-H activation while **1/ SBA-15** does undergo cyclometallation (Scheme 1).

We previously measured a Pt–O distance of 2.01(3) Å *via* Pt L3 edge EXAFS of $1/SiO_2-Al_2O_3$, which is seemingly at odds with our results here.¹³ However, given that the complex undergoes C–H activation, it may be that the 2.01(3) Å bond distance actually corresponded to the Pt–C bond of the cyclometallated complex, which formed either during shipment of the sample under high vacuum or (more likely) in the X-ray beam of the XAS measurements. This explanation is supported by the experimental Pt–C bond length of *ca.* 2.06 Å of a similar cyclometallated Pt(P^tBu₃) complex.⁷² This result highlights the need for complementary characterization strategies such as NMR spectroscopy and EXAFS in order to arrive at a clear understanding of surface structure.

Conclusions

In conclusion, this study demonstrates that sideband selective experiments with selective long pulses can be used for the rapid reconstruction of ¹⁹⁵Pt ssNMR spectra of supported platinum hydrides on different metal oxides (SiO₂ and SiO₂/Al₂O, ~2 Pt wt% loading). With ¹H{¹⁹⁵Pt} and ¹H-³¹P{¹⁹⁵Pt} *J*-resolved and *J*-HMQC experiments it was possible to rapidly measure ¹⁹⁵Pt ssNMR spectra of the molecular complexes **1–4**. The ¹H, ³¹P and ¹⁹⁵Pt NMR fingerprints provide direct insight into the oxidation state and coordination environment of the molecular complexes. With this information it was possible to probe the structure of surface species formed by supporting **1** on SBA-15 or SiO₂–Al₂O₃.

Monitoring the ³¹P signal dephasing as a function of ¹⁹⁵Pt offset in *J*-resolved experiments allowed for the determination of the ¹⁹⁵Pt CS tensor of the surface Pt species in $1/SiO_2-Al_2O_3$ and 1/SBA-15. Numerical fits of ¹H-³¹P{¹⁹⁵Pt} *J*-resolved curves

also allowed the accurate determination of ³¹P-¹⁹⁵Pt J-coupling constants in the supported complexes (2433 Hz and 2908 Hz for 1/SiO₂-Al₂O₃ and 1/SBA-15, respectively). These values align closely with the expected value of approximately 2500 Hz for a ³¹P-¹⁹⁵Pt(II) bond. Comparing experimental and DFT calculated NMR parameters suggested that the bond distance between Pt and O for 1/SiO2-Al2O3 was about 2.7 Å. This distance does not correspond to that of a typical covalent bond, which is around 2 Å, indicating the presence of a 3-coordinated complex on the surface of 1/SiO2-Al2O3 (Fig. 10). Several additional data, including the hydride ¹H NMR signal at -36 ppm, the ¹⁹⁵Pt CSA, and the ³¹P-¹⁹⁵Pt J-coupling constants, show the characteristic features of a 3-coordinate complex. Room temperature ³¹P ssNMR spectra indicate the presence of two surface species on 1/SBA-15, one of which is a 4-coordinated bisphosphine hydride complex with a Pt-O bond length between 2.1 Å to 2.3 Å and a proton shift of -27 ppm (Fig. 10). The other species is a decomposition product, which was assigned to a cyclometallated compound, formed by C-H activation. The use of sideband selective ¹⁹⁵Pt ssNMR experiments allowed the differentiation of two platinum species.

Overall, the combination of experimental and computational techniques presented in this paper offers a comprehensive characterization of these surface-supported Pt complexes. The knowledge gained from this study contributes to the understanding of the coordination geometry, Pt oxidation states, and electronic environments of these complexes. This knowledge can guide the design and optimization of heterogeneous catalysts based on supported Pt species, facilitating the development of efficient catalytic systems for various chemical transformations.

Experimental section

General

All air- and moisture-sensitive materials were manipulated under an atmosphere of oxygen-free dry argon using a MBraun glovebox and standard schlenkline techniques.⁸⁰ Spectrograde acetone was stored over molecular sieve (3 A) 24 h prior to use. Dichloromethane and pentane were used directly form the SPS and dry benzene was used as bought from Sigma Aldrich (anhydrous benzene, 99.99%). *Materials*: bis(tri-*tert*-butylphosphine)platinum(0) **1** and the platinum hydrides **2–4** were synthesized according to an adapted literature procedures.⁶⁴

Preparation of complex 2: trans-PtHCl[P(^tBu)₃]₂

To a stirred solution of Pt(0)(P^tBu₃)₂ 1 (650 mg, 1.1 mmol) in toluene, HCl dissolved in toluene (2 eq., 0.2 mmL, 12 M) was added slowly. It was stirred for 20 minutes and dried under vacuum and crystallized from *n*-pentane to give a white powder (570 mg, 0.9 mmol, 83%). ¹H NMR (400 MHz, benzene-*d*₆): δ = 1.58–1.51 (m, 54H), -19.20 (tt, *J*_{H-Pt} = 1072 Hz, *J*_{H-P} 12.9 Hz, ¹H) ppm. ³¹P NMR (162 MHz, benzene-*d*₆): δ = 75.69 (t, *J*_{P-Pt} = 2951 Hz).

Edge Article

Preparation of complex 3: trans-PtH[P(^tBu)₃]₂ BF₄

Complex 2 (450 mg, 0.7 mmol) was dissolved in dry acetone (3 mL) and AgBF₄ (137.70 mg, 0.7 mmol) dissolved in acetone (2 mL) was added slowly. The precipitate AgCl was filtered off and the filtrate was dried under vacuum. After precipitation from CH₂Cl₂/*n*-pentane a bright yellow powder was obtained (230 mg, 0.33 mmol, 50%). It was crystalized from CH₂Cl₂/*n*-pentane. ¹H NMR (400 MHz, chloroform-*d*) δ 1.29–1.15 (m, 54H), -35.63 (t, $J_{\text{H-Pt}} = 2638$ Hz, ¹H) ppm. ³¹P NMR (162 MHz, chloroform-*d*): $\delta = 85.58$ ppm (t, $J_{\text{P-Pt}} = 2625$) ppm.

Preparation of complex 4: trans-PtH[CH₃CN][P(^tBu)₃]₂ BF₄

3 was dissolved in CH₂Cl₂ and an excess of CH₃CN (>1 eq.) was added. The solution was dried under vacuum and a white powder was yield quantitatively. It was crystalized from CH₂Cl₂/ *n*-pentane. ¹H NMR (400 MHz, CDCl₃): $\delta = 1.48-1.37$ (m, 54H), -19.20 (t, *J*_{H-Pt} = 1049 Hz, *J*_{H-P} = 12.4 Hz, 1H) ppm. ³¹P NMR (162 MHz, chloroform-*d*): $\delta = 80.07$ (t, *J*_{P-Pt} = 2810) ppm.

Preparation of 1/SBA-15

The reaction of **1** with SBA-15 was done using the double-Schlenk technique. A solution of **1** (30 mg, 0.058 mmol) in toluene (3 mL) was frozen in one finger of the double Schlenk. The other finger was filled with SBA-15 (dehydroxylated at 500 ° C, 500 mg). The Schlenk was evacuated and under static vacuum the solution was unfrozen and added to the powder. The reaction was stirred for 20 h at room temperature. The mixture was filtered and washed with *n*-pentane (3 × 5 mL) before dried under high vacuum (10⁻⁵ mbar). An off-white powder was obtained (loading: 0.1 mmol g⁻¹, determined by ICP-OES). Following synthesis, room temperature MAS ¹H ssNMR spectra were acquired with an MAS frequency of 7 kHz. The ¹H ssNMR spectrum showed a diagnostic hydride ¹H NMR signal at -26.6 ppm and a ¹H-¹⁹⁵Pt *J*-coupling of 1034 Hz.

Preparation of 1/SiO₂-Al₂O₃

A solution of **1** (30 mg, 0.058 mmol) in pentane (1 mL) was added to suspension of $SiO_2-Al_2O_3$ (dehydroxylated at 500 °C) in pentane (2 mL). After 20 h stirring at room temperature the mixture was filtered and washed with *n*-pentane (3 × 5 mL) before drying under high vacuum (10⁻⁵ mbar). An off-white powder was obtained (loading: 0.1 mmol g⁻¹, determined by ICP-OES). Following synthesis, a room temperature ¹H MAS ssNMR spectrum was acquired with a 10 kHz MAS frequency. The 1H ssNMR spectrum showed a diagnostic hydride ¹H NMR signal at -36.3 ppm and a ¹H-¹⁹⁵Pt *J*-coupling of 2510 Hz.

Room temperature solid-state NMR experiments

All experiments were performed with a 9.4 T wide bore magnet equipped with a Bruker Avance III HD console. Chemical shifts were indirectly referenced to adamantane using the ¹H shift at 1.82 with respect to TMS in CDCl₃ ppm using the IUPACrecommended chemical shift convention.⁸¹ The probe was not retuned for any sideband selective experiment. The ¹⁹⁵Pt RF field was calibrated using the Bloch–Siegert shift method.⁸² The RF field strength of the ¹⁹⁵Pt saturation pulses for the sideband selective experiments varied depending on the MAS frequency and the saturation pulse length that was used. Numerical simulations suggest that the optimal RF fields are within a few kilohertz of those that were used experimentally (Fig. S18 and Table S6†).

DNP-SENS solid-state NMR experiments

All experiments were performed with a wide bore 9.4 T/263 GHz DNP spectrometer⁸³ equipped with a Bruker Avance III HD console. Chemical shifts were indirectly referenced to the ¹³C chemical shift of tetrakis(trimethylsilyl)silane at 2.75 ppm (with respect to TMS ($\delta(^{1}H) = 0$ ppm) in 98% CDCl₃). The ¹⁹⁵Pt RF field was calibrated by scaling the ¹³C $\pi/2$ pulse length, which was calibrated directly on tetrakis(trimethylsilyl)silane by nutating the pulse length.

Room temperature ¹H{¹⁹⁵Pt} experiments

Complex 3 was packed into a 1.3 mm zirconia rotor in a glovebox then spun with nitrogen gas. A 1.3 mm Bruker HX probe and a MAS frequency of 50 kHz was used. Before experiments began, the magic angle was precisely calibrated by minimizing the splitting in the ²H NMR spectrum of deuterated oxalic acid.⁸⁴ ¹H 90 and 180° pulse used durations of 2.5 and 5 µs, respectively. A ¹H{¹⁹⁵Pt}2D *J*-HMQC with a rotor-synchronized t_1 -evolution period and hyper-complex states-TPPI acquisition⁸⁵ was done to determine the exact frequency of a ¹⁹⁵Pt spinning sideband so that sideband selective experiments could be performed. The sideband selective experiments were performed with 32 scans, 1.55 s recycle delay (1.3 × T_1), 0.4 ms *J*evolution period (¹*J*(¹H-¹⁹⁵Pt) = ~2500 Hz), and 31 sub-spectra. 60 µs SL pulses with an 8 kHz and 6 kHz RF field were employed for *J*-resolved and *J*-HMQC, respectively.

Room temperature ¹H-³¹P{¹⁹⁵Pt} experiments on 1

Complex 1 was packed into a 2.5 mm zirconia rotor in a glovebox then spun with nitrogen gas. A Bruker 2.5 mm HXY probe configured in ¹H-³¹P-¹⁹⁵Pt mode and a MAS frequency of 25 kHz were used. Before experiments began, the magic angle was precisely calibrated by maximizing the intensity of the second spinning sideband of the ⁷⁹Br spectrum of KBr.^{86 1}H 90 and 180° pulse used durations of 2.5 and 5 μ s, respectively. The ¹H \rightarrow ³¹P CP contact time was set to 2.5 ms and optimal ¹H and ³¹P spinlock RF powers of 105 and 70 kHz, respectively, were used; the ¹H RF power was ramped from 90 to 100%. A $^{1}H-^{31}P\{^{195}Pt\}$ 2D J-HMQC experiment with a rotor-synchronized t_1 -evolution period and hyper-complex states-TPPI acquisition⁸⁵ was used to determine the exact frequency of a ¹⁹⁵Pt spinning sideband so that sideband selective experiments could be performed. Sideband selective experiments used 80 μ s SL ¹⁹⁵Pt pulses with a 6 kHz RF field or 5 kHz RF field for J-resolved and J-HMQC, respectively. 128 scans and 512 scans were acquired for Jresolved and J-HMQC, respectively The recycle delay was 0.66 s $(1.3 \times T_1)$, the *J*-evolution period was 0.22 ms $({}^{1}J({}^{31}P-{}^{195}Pt) =$ 4400 Hz), and 31 sub-spectra were acquired. 100 kHz ¹H SPINAL-64 decoupling was applied during the J-evolution

periods and signal acquisition.⁸⁷ The same ³¹P CP conditions and ¹H decoupling conditions were used for room temperature ssNMR experiments on compound 2–4.

Room temperature ${}^{1}H-{}^{31}P{}^{195}Pt}$ experiments on 2

Sideband selective experiments used 120 μ s SL pulses with 7 kHz and 4 kHz RF fields for *J*-resolved and *J*-HMQC, respectively. The recycle delay was 1.17 s (1.3 \times *T*₁), the *J*-evolution period was 0.22 ms (¹*J*(³¹P⁻¹⁹⁵Pt) = ~3000 Hz), and 56 subspectra were acquired. 32 scans were acquired at each ¹⁹⁵Pt offset.

Room temperature ¹H{¹⁹⁵Pt} experiments on 3

Sideband selective experiments used 60 µs SL pulses with 8 kHz and 6 kHz RF fields for *J*-resolved and *J*-HMQC, respectively. The recycle delay was 1.55 s ($1.3 \times T_1$), the *J*-evolution period was 0.4 ms (${}^{1}J({}^{31}P-{}^{195}Pt) = \sim 2500$ Hz), and 31 sub-spectra were acquired. 32 scans were acquired at each ${}^{195}Pt$ offset.

Room temperature ${}^{1}H-{}^{31}P{}^{195}Pt}$ experiments on 4

Sideband selective experiments used 80 μ s SL pulses with 7 kHz and 5 kHz RF for *J*-resolved and *J*-HMQC, respectively. The recycle delay was 1.43 s (1.3 \times *T*₁), the *J*-evolution period was 0.16 ms (¹*J*(³¹P-¹⁹⁵Pt) = ~6250 Hz), which was not optimal, and 66 sub-spectra were acquired. 64 scans were acquired at each ¹⁹⁵Pt offset. A CPMG echo train was added at the end of the sideband selective pulse sequences for detection to increase sensitivity.

DNP-SENS $^1H-^{31}P\{^{195}Pt\}$ experiments on $1/SiO_2-Al_2O_3$ and 1/SBA-15

The DNP samples of 1/SiO₂-Al₂O₃ and 1/SBA-15 were prepared in a glovebox and impregnated with a solution of 10 mM TEK-Pol⁸⁸ in 1,1,2,2 tetrachloroethane (TCE) via the incipient wetness method and packed into a 3.2 mm sapphire rotor. The rotor was then inserted into a low-temperature Bruker 3.2 mm HXY MAS DNP probe configured in ¹H-³¹P-¹⁹⁵Pt mode which was precooled to 100 K, then spun with an MAS frequency of 12.5 kHz. The ${}^{1}\text{H} \rightarrow {}^{31}\text{P}$ CP contact time was set to 2 ms and optimal ¹H and ³¹P spinlock RF powers of 40 and 72 kHz, respectively, were used; the ¹H RF power was ramped from 90 to 100%. ${}^{1}H-{}^{31}P{}^{195}Pt{}$ J-resolved experiments to measure ³¹P-¹⁹⁵Pt J-couplings were performed with a WURST-80 (ref. 35) saturation pulse on ¹⁹⁵Pt. The WURST-80 pulse was 25 µs duration, used a RF field of ca. 120 kHz, and swept over a total frequency range of 1.25 MHz. The WURST pulse was found to give superior dephasing as compared to a rectangular pulse. 100 kHz ¹H SPINAL-64 decoupling was applied during the J-evolution periods and signal acquisition.87 For 195Pt variable offset ¹H-³¹P{¹⁹⁵Pt} J-resolved experiments rectangular ¹⁹⁵Pt saturation pulses that were 120 μ s (1.5 $\times \tau_r$) in duration were used with an RF field of 35 kHz. The ¹⁹⁵Pt saturation pulse offset was incremented in steps of 25 kHz while retuning the ¹⁹⁵Pt channel on the probe every 250 kHz; 69 sub-spectra were acquired. The total echo duration was set to 0.32 ms which is approximately

the inverse of the ³¹P–¹⁹⁵Pt *J*-coupling. For all experiments, the recycle delay was 2.21 s for 1/SiO₂–Al₂O₃ and 4.43 s for 1/SBA-15. 128 scans were acquired at each ¹⁹⁵Pt offset.

Room temperature ssNMR experiments on $1/SiO_2$ -Al₂O₃ and 1/SBA-15

1/SiO₂-Al₂O₃ and 1/SBA-15 were packed into 2.5 mm zirconia rotors inside of a glovebox and then spun with nitrogen gas. A Bruker 2.5 mm HX probe configured in double mode was used. The ¹H spin echo ($\pi/2-\tau-\pi-\tau$) spectra were acquired with a (1.3 × *T*₁) recycle delay (2 s for 1/SiO₂-Al₂O₃ and 1.42 s for 1/SBA-15). The ¹H spectra were acquired with 4096 and 16 384 scans for 1/SiO₂-Al₂O₃ and 1/SBA-15, respectively.

Numerical SIMPSON simulations

Numerical simulations were performed using SIMPSON v4.2.1.⁸⁹⁻⁹¹ The SIMPSON input codes are provided with the archived data. All pulses in the files were of finite duration, except the ¹H and ³¹P $\pi/2$ pulses, which were ideal. The rep320 crystal file was used for all simulations. The number of gamma angles was set to 13. The heat maps in the ESI† were constructed using MATLAB_R2021B. The 1D spectra were processed with Python using Microsoft Visual Studio Code as the interpreter.

DFT calculations

For complexes 1–4, hydrogen atom coordinates were geometrically optimized in CASTEP⁵⁴ using the PBE-GGA functional,⁹² TS dispersion correction scheme,⁹³ and ultra-soft pseudopotentials.^{94,95} The coordinates for the models of $1/SiO_2$ – Al_2O_3 and 1/SBA-15 were geometrically optimized with AMS 2021. All NMR calculations were performed using AMS 2021 with the hybrid PBE0 functional^{56,57} and a Slater-type basis set of triple- ζ with two polarization functions.⁵⁵ Relativistic effects were treated by zero order regular approximation (ZORA)^{96–99} with spin–orbit relativity level.

Data availability

The data that support the findings of this study are openly available at https://doi.org/10.5281/zenodo.12773732 or https:// zenodo.org/records/12773732. Data includes experimental NMR datasets and pulse programs (TopSpin format), SIMPSON simulation files and AMS 2021 files. Solution NMR spectra of molecular compounds, 1D ¹H and ³¹P MAS NMR spectra, crystallographic data and infrared spectra are available at https://doi.org/10.18419/darus-4580.

Author contributions

B. A. A. performed solid-state NMR experiments, performed DFT calculations and analyzed data. E. J. W. synthesized compounds, characterized them by standard techniques and assisted with solid-state NMR experiments. S. K. and J. K. performed DFT calculations. W. F. obtained single-crystal X-ray structures of compounds. A. J. R. and D. P. E. directed and

oversaw all research. The manuscript was written through the contributions of all authors.

Conflicts of interest

There are no conflicts of interest to declare.

Acknowledgements

B. A. A. and A. J. R. were supported by the National Science Foundation under grant no. CBET-1916809. This work was also funded by the Deutsche Forschungsgemeinschaft (DFG, German Research Foundation). Project number 358283783-SFB 1333/2.

References

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

ven Access Article. Published on 20 November 2024. Downloaded on 6/17/2025 11:04:43 AM.

- 1 X. Cui, K. Junge, X. Dai, C. Kreyenschulte, M.-M. Pohl, S. Wohlrab, F. Shi, A. Brückner and M. Beller, *ACS Cent. Sci.*, 2017, **3**, 580–585.
- 2 Z. Xiang, W. Li, F. Liu, F. Tan, F. Han, X. Wang, C. Shao, M. Xu, W. Liu and X. Yang, *Electrochem. Commun.*, 2021, 127, 107039.
- 3 P. Bourges, S. Lunati and G. Mabilon, in *Studies in Surface Science and Catalysis*, Elsevier, 1998, vol. 116, pp. 213–222.
- 4 J. Hou, M. Yang, C. Ke, G. Wei, C. Priest, Z. Qiao, G. Wu and J. Zhang, *EnergyChem*, 2020, **2**, 100023.
- 5 A. V. Da Rosa, in *Fundamentals of Renewable Energy Processes*, Elsevier/AP, Amsterdam, 3rd edn, 2013.
- 6 J. Kijenski and P. Winiarek, in *Studies in Surface Science and Catalysis*, Elsevier, 2000, vol. 143, pp. 787–794.
- 7 M. Gomez, G. Muller, D. Sainz, J. Sales and X. Solans, *Organometallics*, 1991, **10**, 4036–4045.
- 8 L. Charruault, V. Michelet, R. Taras, S. Gladiali and J.-P. Genêt, *Chem. Commun.*, 2004, 850–851.
- 9 A. B. Permin and V. S. Petrosyan, *Appl. Organomet. Chem.*, 1990, 4, 329–333.
- 10 D. Gregson, J. A. K. Howard, M. Murray and J. L. Spencer, J. Chem. Soc., Chem. Commun., 1981, 716–717.
- 11 R. G. Goel, W. O. Ogini and R. C. Srivastava, *Organometallics*, 1982, **1**, 819–824.
- 12 T. Yoshida, T. Yamagata, T. H. Tulip, J. A. Ibers and S. Otsuka, J. Am. Chem. Soc., 1978, **100**, 2063–2073.
- 13 S. Maier, S. P. Cronin, M.-A. Vu Dinh, Z. Li, M. Dyballa, M. Nowakowski, M. Bauer and D. P. Estes, *Organometallics*, 2021, 40, 1751–1757.
- 14 P. J. Ayare, S. A. Gregory, R. J. Key, A. E. Short, J. G. Tillou, J. D. Sitter, T. Yom, D. W. Goodlett, D.-C. Lee, F. M. Alamgir, M. D. Losego and A. K. Vannucci, *Green Chem.*, 2021, 23, 9523–9533.
- 15 S. L. Wegener, T. J. Marks and P. C. Stair, Acc. Chem. Res., 2012, 45, 206-214.
- 16 J. D. A. Pelletier and J.-M. Basset, Acc. Chem. Res., 2016, 49, 664–677.
- 17 M. K. Samantaray, E. Pump, A. Bendjeriou-Sedjerari, V. D'Elia, J. D. A. Pelletier, M. Guidotti, R. Psaro and J.-M. Basset, *Chem. Soc. Rev.*, 2018, 47, 8403–8437.

- 18 C. Copéret, M. Chabanas, R. Petroff Saint-Arroman and J. Basset, Angew. Chem., Int. Ed., 2003, 42, 156–181.
- C. Copéret, A. Comas-Vives, M. P. Conley, D. P. Estes,
 A. Fedorov, V. Mougel, H. Nagae, F. Núñez-Zarur and
 P. A. Zhizhko, *Chem. Rev.*, 2016, **116**, 323–421.
- 20 A. W. Kaplan and R. G. Bergman, *Organometallics*, 1998, **17**, 5072–5085.
- 21 P. Laurent, L. Veyre, C. Thieuleux, S. Donet and C. Copéret, *Dalton Trans.*, 2013, **42**, 238–248.
- 22 E. J. W. Austin, P. J. Barrie and R. J. H. Clark, *J. Chem. Soc., Chem. Commun.*, 1993, 1404–1405.
- 23 B. E. G. Lucier, A. R. Reidel and R. W. Schurko, *Can. J. Chem.*, 2011, **89**, 919–937.
- 24 B. E. G. Lucier, K. E. Johnston, W. Xu, J. C. Hanson, S. D. Senanayake, S. Yao, M. W. Bourassa, M. Srebro, J. Autschbach and R. W. Schurko, *J. Am. Chem. Soc.*, 2014, 136, 1333–1351.
- 25 T. Kobayashi, F. A. Perras, T. W. Goh, T. L. Metz, W. Huang and M. Pruski, *J. Phys. Chem. Lett.*, 2016, 7, 2322–2327.
- 26 M. Soorholtz, L. C. Jones, D. Samuelis, C. Weidenthaler, R. J. White, M.-M. Titirici, D. A. Cullen, T. Zimmermann, M. Antonietti, J. Maier, R. Palkovits, B. F. Chmelka and F. Schüth, ACS Catal., 2016, 6, 2332–2340.
- 27 Z. Wang, L. A. Völker, T. C. Robinson, N. Kaeffer, G. Menzildjian, R. Jabbour, A. Venkatesh, D. Gajan, A. J. Rossini, C. Copéret and A. Lesage, *J. Am. Chem. Soc.*, 2022, 144, 21530–21543.
- 28 S. Todisco, G. Saielli, V. Gallo, M. Latronico, A. Rizzuti and P. Mastrorilli, *Dalton Trans.*, 2018, 47, 8884–8891.
- 29 G. J. Rees, S. T. Orr, L. O. Barrett, J. M. Fisher, J. Houghton, G. H. Spikes, B. R. C. Theobald, D. Thompsett, M. E. Smith and J. V. Hanna, *Phys. Chem. Chem. Phys.*, 2013, 15, 17195.
- 30 C. D. Makowka, C. P. Slichter and J. H. Sinfelt, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1985, 31, 5663–5679.
- 31 C. P. Slichter, Surf. Sci., 1981, 106, 382-396.
- 32 S. W. Sparks and P. D. Ellis, *J. Am. Chem. Soc.*, 1986, **108**, 3215–3218.
- 33 M. J. Jaroszewicz, A. R. Altenhof, R. W. Schurko and L. Frydman, *J. Am. Chem. Soc.*, 2021, **143**, 19778–19784.
- 34 T. Pawlak, M. L. Munzarová, L. Pazderski and R. Marek, J. Chem. Theory Comput., 2011, 7, 3909–3923.
- 35 L. A. O'Dell and R. W. Schurko, *Chem. Phys. Lett.*, 2008, **464**, 97–102.
- 36 A. W. MacGregor, L. A. O'Dell and R. W. Schurko, J. Magn. Reson., 2011, 208, 103–113.
- 37 K. J. Harris, A. Lupulescu, B. E. G. Lucier, L. Frydman and R. W. Schurko, *J. Magn. Reson.*, 2012, **224**, 38–47.
- 38 I. Hung, A. J. Rossini and R. W. Schurko, *J. Phys. Chem. A*, 2004, **108**, 7112–7120.
- J. Camacho-Bunquin, M. Ferrandon, H. Sohn, D. Yang,
 C. Liu, P. A. Ignacio-de Leon, F. A. Perras, M. Pruski,
 P. C. Stair and M. Delferro, *J. Am. Chem. Soc.*, 2018, 140, 3940–3951.
- 40 Y. Ishizaka, N. Arai, K. Matsumoto, H. Nagashima, K. Takeuchi, N. Fukaya, H. Yasuda, K. Sato and J. Choi, *Chem.-Eur. J.*, 2021, 27, 12069–12077.

- 41 A. Venkatesh, D. Gioffrè, B. A. Atterberry, L. Rochlitz,
 S. L. Carnahan, Z. Wang, G. Menzildjian, A. Lesage,
 C. Copéret and A. J. Rossini, *J. Am. Chem. Soc.*, 2022, 144, 13511–13525.
- 42 B. A. Atterberry, E. Wimmer, D. P. Estes and A. J. Rossini, *J. Magn. Reson.*, 2023, **352**, 107457.
- 43 E. Prack, C. A. O'Keefe, J. K. Moore, A. Lai, A. J. Lough, P. M. Macdonald, M. S. Conradi, R. W. Schurko and U. Fekl, *J. Am. Chem. Soc.*, 2015, 137, 13464–13467.
- 44 P. Paluch, A. G. M. Rankin, J. Trébosc, O. Lafon and J.-P. Amoureux, *Solid State Nucl. Magn. Reson.*, 2019, **100**, 11–25.
- 45 J. Herzfeld and A. E. Berger, *J. Chem. Phys.*, 1980, 73, 6021–6030.
- 46 F. D. Rochon and A. Morneau, *Magn. Reson. Chem.*, 1991, **29**, 120–126.
- 47 S. J. S. Kerrison and P. J. Sadler, *Inorg. Chim. Acta*, 1985, **104**, 197–201.
- 48 L. Schwartsburd, R. Cohen, L. Konstantinovski and D. Milstein, *Angew. Chem.*, 2008, **120**, 3659–3662.
- 49 B. M. Still, P. G. A. Kumar, J. R. Aldrich-Wright and W. S. Price, *Chem. Soc. Rev.*, 2007, 36, 665–686.
- 50 M. Sterzel and J. Autschbach, *Inorg. Chem.*, 2006, 45, 3316–3324.
- 51 J. Autschbach and S. Zheng, *Magn. Reson. Chem.*, 2008, 46, S45–S55.
- 52 A. V. Buevich, J. Saurí, T. Parella, N. De Tommasi, G. Bifulco,
 R. T. Williamson and G. E. Martin, *Chem. Commun.*, 2019,
 55, 5781–5784.
- 53 J. S. Fabián, J. M. García De La Vega and E. San Fabián, J. Chem. Theory Comput., 2014, 10, 4938-4949.
- 54 S. J. Clark, M. D. Segall, C. J. Pickard, P. J. Hasnip, M. I. J. Probert, K. Refson and M. C. Payne, *Z. Kristallogr.*, 2005, **220**, 567–570.
- 55 G. Te Velde, F. M. Bickelhaupt, E. J. Baerends, C. Fonseca Guerra, S. J. A. Van Gisbergen, J. G. Snijders and T. Ziegler, *J. Comput. Chem.*, 2001, 22, 931–967.
- 56 S. Grimme, J. Comput. Chem., 2004, 25, 1463-1473.
- 57 M. Ernzerhof and G. E. Scuseria, *J. Chem. Phys.*, 1999, **110**, 5029–5036.
- 58 J. Campos, L. Ortega-Moreno, S. Conejero, R. Peloso, J. López-Serrano, C. Maya and E. Carmona, *Chem.-Eur. J.*, 2015, **21**, 8883-8896.
- 59 H. Braunschweig, K. Radacki and K. Uttinger, *Chem.–Eur. J.*, 2008, **14**, 7858–7866.
- 60 W. Baratta, S. Stoccoro, A. Doppiu, E. Herdtweck, A. Zucca and P. Rigo, *Angew. Chem., Int. Ed.*, 2003, **42**, 105–109.
- 61 N. Carr, L. Mole, A. G. Orpen and J. L. Spencer, *J. Chem. Soc.*, *Dalton Trans.*, 1992, 2653–2662.
- 62 M. J. Ingleson, M. F. Mahon and A. S. Weller, *Chem. Commun.*, 2004, 2398–2399.
- 63 M. A. Ortuño, P. Vidossich, G. Ujaque, S. Conejero and A. Lledós, *Dalton Trans.*, 2013, **42**, 12165.
- 64 R. G. Goel and R. C. Srivastava, *Can. J. Chem.*, 1983, **61**, 1352–1359.
- 65 J. Rodriguez, D. B. Culver and M. P. Conley, *J. Am. Chem. Soc.*, 2019, **141**, 1484–1488.

- 66 A. Bowden, S. J. Coles, M. B. Pitak and A. W. G. Platt, *Inorg. Chem.*, 2012, **51**, 4379–4389.
- 67 M. Dyballa, Energy Fuels, 2023, 37, 18517-18559.
- 68 P. E. M. Siegbahn and R. H. Crabtree, J. Am. Chem. Soc., 1996, 118, 4442–4450.
- 69 T. M. Gilbert, I. Hristov and T. Ziegler, *Organometallics*, 2001, 20, 1183–1189.
- 70 S. Niu and M. B. Hall, J. Am. Chem. Soc., 1998, **120**, 6169–6170.
- 71 B. L. Simms and J. A. Ibers, *J. Organomet. Chem.*, 1987, **330**, 279–289.
- 72 T. Troadec, S. Tan, C. J. Wedge, J. P. Rourke, P. R. Unwin and A. B. Chaplin, *Angew. Chem., Int. Ed.*, 2016, 55, 3754– 3757.
- 73 S. J. Coles, S. J. Fieldhouse, W. T. Klooster and A. W. G. Platt, *Polyhedron*, 2019, **161**, 346–351.
- 74 S. E. Maier, T. Nagel, M. Turan, E. Kaya, W. Frey, M. Dyballa and D. P. Estes, *Organometallics*, 2024, **43**, 233–241.
- 75 G. Crépeau, V. Montouillout, A. Vimont, L. Mariey, T. Cseri and F. Maugé, *J. Phys. Chem. B*, 2006, **110**, 15172–15185.
- 76 W. Daniell, U. Schubert, R. Glöckler, A. Meyer, K. Noweck and H. Knözinger, *Appl. Catal.*, *A*, 2000, **196**, 247–260.
- 77 F. Rascón, R. Wischert and C. Copéret, *Chem. Sci.*, 2011, 2, 1449.
- 78 W. S. Salvia, T. Y. Zhao, P. Chatterjee, W. Huang and F. A. Perras, *Chem. Commun.*, 2023, **59**, 13962–13965.
- 79 F. A. Perras, Z. Wang, T. Kobayashi, A. Baiker, J. Huang and M. Pruski, *Phys. Chem. Chem. Phys.*, 2019, 21, 19529– 19537.
- 80 D. F. Shriver and M. A. Drezdzon, *The Manipulation of Air-Sensitive Compounds*, Wiley, New York, 2nd edn, 1986.
- 81 R. K. Harris, E. D. Becker, S. M. Cabral De Menezes, R. Goodfellow and P. Granger, *Pure Appl. Chem.*, 2001, 73, 1795–1818.
- 82 I. Hung, P. Gor'kov and Z. Gan, J. Magn. Reson., 2020, 310, 106636.
- 83 M. Rosay, L. Tometich, S. Pawsey, R. Bader, R. Schauwecker, M. Blank, P. M. Borchard, S. R. Cauffman, K. L. Felch, R. T. Weber, R. J. Temkin, R. G. Griffin and W. E. Maas, *Phys. Chem. Chem. Phys.*, 2010, **12**, 5850.
- 84 S. Antonijevic and G. Bodenhausen, Angew. Chem., Int. Ed., 2005, 44, 2935–2938.
- 85 D. Marion, M. Ikura, R. Tschudin and A. Bax, *J. Magn. Reson.*, 1989, **85**, 393–399.
- 86 J. S. Frye and G. E. Maciel, J. Magn. Reson., 1982, 48, 125-131.
- 87 B. M. Fung, A. K. Khitrin and K. Ermolaev, J. Magn. Reson., 2000, 142, 97–101.
- 88 A. Zagdoun, G. Casano, O. Ouari, M. Schwarzwälder, A. J. Rossini, F. Aussenac, M. Yulikov, G. Jeschke, C. Copéret, A. Lesage, P. Tordo and L. Emsley, *J. Am. Chem. Soc.*, 2013, **135**, 12790–12797.
- 89 Z. Tošner, R. Andersen, B. Stevensson, M. Edén, N. C. Nielsen and T. Vosegaard, J. Magn. Reson., 2014, 246, 79–93.
- 90 M. Bak, J. T. Rasmussen and N. C. Nielsen, J. Magn. Reson., 2000, 147, 296–330.

- 91 Z. Tošner, T. Vosegaard, C. Kehlet, N. Khaneja, S. J. Glaser and N. C. Nielsen, *J. Magn. Reson.*, 2009, **197**, 120–134.
- 92 J. P. Perdew, K. Burke and M. Ernzerhof, *Phys. Rev. Lett.*, 1996, 77, 3865–3868.
- 93 A. Tkatchenko and M. Scheffler, *Phys. Rev. Lett.*, 2009, **102**, 073005.
- 94 D. Vanderbilt, Phys. Rev. B: Condens. Matter Mater. Phys., 1990, 41, 7892-7895.
- 95 J. R. Yates, C. J. Pickard and F. Mauri, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2007, **76**, 024401.
- 96 E. Van Lenthe, A. Ehlers and E.-J. Baerends, *J. Chem. Phys.*, 1999, **110**, 8943–8953.
- 97 E. V. Lenthe, E. J. Baerends and J. G. Snijders, J. Chem. Phys., 1993, 99, 4597–4610.
- 98 E. Van Lenthe, R. Van Leeuwen, E. J. Baerends and J. G. Snijders, *Int. J. Quantum Chem.*, 1996, **57**, 281–293.
- 99 E. Van Lenthe, J. G. Snijders and E. J. Baerends, J. Chem. Phys., 1996, 105, 6505–6516.