

Cite this: *J. Mater. Chem. A*, 2023, 11, 2836

# Heteroatomic interface engineering of an octahedron $VSe_2$ - $ZrO_2$ /C/MXene composite derived from a MXene-MOF hybrid as a superior-performance anode for lithium-ion batteries†

Hanbin Li,<sup>a</sup> Jinliang Li,<sup>b</sup> Liang Ma,<sup>\*bc</sup> Xinlu Zhang,<sup>d</sup> Junfeng Li,<sup>e</sup> Jiabao Li,<sup>f</sup> Ting Lu<sup>a</sup> and Likun Pan<sup>g</sup>

As a promising electrode material with tremendous specific capacity, vanadium diselenide ( $VSe_2$ ) has recently attracted renewed attention. However, the application of  $VSe_2$  is still hindered by the difficulty in its synthesis and nature of volume expansion. In this work, we developed a practical solvothermal method and *in situ* selenization process to obtain the  $VSe_2$ - $ZrO_2$ /C/MXene composite from the MXene-metal-organic framework (MOF) hybrid precursor. During the synthesis process,  $V_2CT_x$  is converted to  $VSe_2$ /MXene, which firmly anchors on the porous carbon derived from UiO-66 with the assistance of another derivative  $ZrO_2$  via chemical bonding. Remarkably, benefitting from the practical cooperation between  $VSe_2$ /MXene,  $ZrO_2$  and porous carbon,  $VSe_2$ - $ZrO_2$ /C/MXene displays an outstanding lithium storage performance with an enduring capacity rise from 461.2 to 1238.5 mA h  $g^{-1}$  at 100 mA  $g^{-1}$  after a short recession during cycling, which is investigated in detail as a "negative fading" phenomenon. Even at the high current density of 1.0 A  $g^{-1}$ , the composite still presents a high reversible capacity of 430 mA h  $g^{-1}$  after 1000 cycles, highlighting its superior cycling stability. The application potential of the  $VSe_2$ - $ZrO_2$ /C/MXene anode for LIBs has also been evaluated by assembling full cells. The strategy in this work inspires the construction design of novel selenide-based electrode materials for high-performance lithium-ion batteries.

Received 20th November 2022  
Accepted 4th January 2023

DOI: 10.1039/d2ta09043k

rsc.li/materials-a

## Introduction

As an anticipant medium to realize energy conservation and emission reduction, rechargeable lithium-ion batteries (LIBs) have drawn wide attention in portable electronics, vehicle

industry, and intelligent devices due to their ultra-high energy density, stability, and safety.<sup>1-4</sup> Nevertheless, the intensifying global energy crisis as well as the eco-friendly ethic/policy demands urge a profound revolution of LIBs. Regarded as the primary commercial anode, graphite is restricted by a low theoretical capacity of 372 mA h  $g^{-1}$ ,<sup>5</sup> which is inadequate for the ever-increasing electric-driving requirements.<sup>6-9</sup> Because of this situation, numerous studies have been devoted to the exploration of battery materials pursuing higher performance.

Among a series of anode species, transition-metal selenides (TMSes) have captured much research attention in recent years as an emerging material for lithium-ion storage due to their excellent charge transfer properties.<sup>10-12</sup> Additionally, TMSes exhibit brilliant volumetric capacity and rapid electron migration rate, stemming from high conductivity ( $1 \times 10^{-5}$  S  $m^{-1}$ ) and low electronegativity (2.4) of selenium during the full lithiation process.<sup>13,14</sup> Zhang *et al.* used Cu-BTC as sacrificial templates to fabricate a  $Cu_{1.8}Se@C$  decahedron through the co-precipitation process, which delivered a capacity of 824.4 mA h  $g^{-1}$  after 200 cycles at 100 mA  $g^{-1}$ .<sup>15</sup> Zhu *et al.* proposed ZnSe nanoparticle-embedded N-doped carbon nanocubes in a similar process, which displayed a high reversible capacity of 1166.6 mA h  $g^{-1}$  after 500 cycles at 0.5 A  $g^{-1}$ .<sup>16</sup>

<sup>a</sup>Shanghai Key Laboratory of Magnetic Resonance, School of Physics and Electronic Science, East China Normal University, Shanghai, 200241, China. E-mail: lkpan@phy.ecnu.edu.cn

<sup>b</sup>Siyuan Laboratory, Guangdong Provincial Key Laboratory of Nanophotonic Manipulation, Guangdong Provincial Engineering Technology Research Center of Vacuum Coating Technologies and New Materials, Department of Physics, Jinan University, Guangzhou, Guangdong, 510632, China. E-mail: lijianliang@email.jnu.edu.cn; maliang2415@jnu.edu.cn

<sup>c</sup>School of Chemistry, Guangzhou Key Laboratory of Materials for Energy Conversion and Storage, South China Normal University, Guangzhou, 510006, China

<sup>d</sup>Key Laboratory for Liquid-Solid Structural Evolution & Processing of Materials (Ministry of Education), Research Center for Carbon Nanomaterials, School of Materials Science and Engineering, Shandong University, Jinan, 250061, China

<sup>e</sup>College of Logistics Engineering, Shanghai Maritime University, Shanghai, 201306, China

<sup>f</sup>School of Chemistry and Chemical Engineering, Yangzhou University, Yangzhou, Jiangsu, 225002, China

† Electronic supplementary information (ESI) available. See DOI: <https://doi.org/10.1039/d2ta09043k>

Among various TMSes,  $VSe_2$  with excellent electrochemical activity stands out for its high lithium-ion storage performance because of its light molecular mass and multi-electron transfer mechanism.<sup>17</sup> Nevertheless, the preparation difficulty and insufficient capacity hinder the application of  $VSe_2$  in the energy storage field. For instance, among the traditional methods of  $VSe_2$  synthesis, chemical vapor deposition is capable of synthesizing high crystalline quality  $VSe_2$ ,<sup>18</sup> but requires a high synthesis temperature (up to 900 °C), which makes the synthesis process complex and highly energy intensive.<sup>19</sup> Therefore, it is necessary to develop methods with relatively simple synthesis processes, such as hydrothermal selenidation or surface annealing treatment selenidation. Wang *et al.* developed  $VSe_2$ /graphene *via* a hydrothermal route using  $NH_4VO_3$  and  $SeO_2$ , which showed a reversible discharge capacity of 632 mA h  $g^{-1}$  at 100 mA  $g^{-1}$  during 60 cycles.<sup>20</sup> Unfortunately, the reported lithium storage capacity is not enough for practical applications. Currently, MXenes, 2D layer transition metal carbonitrides/carbides with regulable physical and chemical properties have attracted much attention in energy storage fields<sup>21–23</sup> because of their open structure, internal conductivity<sup>24,25</sup> as well as terrific hydrophilicity endowing an abundance of active sites for ion storage and rapid charge transfer.<sup>26,27</sup> Moreover, MXenes have been demonstrated as good sacrificial precursors for synthesizing numerous nanomaterials or their hybrids,<sup>3,28</sup> where the incompletely converted MXenes can also act as a conductive support in these hybrids.<sup>29</sup> The Sha group successfully constructed  $VSe_2@V_2CT_x$  by surface selenization strategy. In this way, the surface metal atoms on MXene supplied a metal source for TMSe, and the layer structure preserved the nanoplates from restacking concurrently. The obtained  $VSe_2@V_2CT_x$  delivered an excellent capacity of 158.1 mA h  $g^{-1}$  at 2.0 A  $g^{-1}$  after 600 cycles for aqueous zinc-ion batteries.<sup>30</sup> Inspired by this encouraging work, the selenization of  $V_2CT_x$  can be a promising strategy for synthesizing stable  $VSe_2$ .

Volume expansion and cycling have been widely reported to result in structural deterioration and even pulverization, remaining a critical challenge for TMSes.<sup>31,32</sup> It is of great necessity to figure out advanced tactics to improve the cycling stability of selenide electrodes. It is well known that  $ZrO_2$  is a viable material not only for its high dielectric constant, but also for its structural protection role in mitigating capacity fading.<sup>33</sup> Thus, introducing  $ZrO_2$  into TMSes is deemed to effectively solve the attenuation issue.<sup>34</sup> Yao *et al.* found that the modified amorphous  $ZrO_2$  coating on  $LiCoO_2$  particles could improve the capacity retention to 82.5% after 100 cycles.<sup>35</sup> Additionally, coupling with hollow/porous carbonaceous constructions,<sup>36–38</sup> such as carbon aerogels, carbon nanotubes, carbon cages, and carbon nanofibers, as buffer materials is another rational strategy to relieve the volumetric strain.<sup>28,39–43</sup> In particular, porous carbon derived from metal–organic frameworks (MOFs) can control the morphology and realize a high specific surface area, which provides sufficient active sites, shortens the pathways for lithium-ion transfer, improves the electrolyte infusion and enhances the electrical conductivity.<sup>44–47</sup> Yang *et al.* synthesized a Ni–Co–Se@C bundle-

like micro/nanostructure hybrid with bimetallic MOF as the precursor using a surfactant-assisted co-precipitation approach, which remarkably modified the rate performance with a capacity of 493 mA h  $g^{-1}$  at 8 A  $g^{-1}$  in LIBs.<sup>48</sup> Jin *et al.* encapsulated ZnSe and CoSe in N-doped carbon polyhedra interconnecting with CNTs through *in situ* pyrolysis and selenization procedure, and the acquired LIBs anode established a capacity of 873 mA h  $g^{-1}$  after 500 cycles at 0.5 A  $g^{-1}$ .<sup>49</sup> Given the above, incorporating  $ZrO_2$  and porous carbon together into MXene-derived  $VSe_2$  (or  $VSe_2$ /MXene) should be a feasible method to synergistically enhance its energy storage ability. Fortunately, UiO-66 can act as a sacrificial precursor to produce both  $ZrO_2$  and porous carbon with effective integration. However, up to now, the exploration of UiO-66 and its derivatives in LIBs is quite limited, much less for the design of the hybrid material containing  $VSe_2$ ,  $ZrO_2$  and porous carbon.

Herein, we propose a heteroatomic interface engineering of octahedron  $VSe_2$ - $ZrO_2$ /C/MXene composite derived from the MXene-MOF hybrid *via* a two-step method. In the unique structure,  $V_2CT_x$ -derived  $VSe_2$ /MXene contributed to a high reversible capacity, and the  $ZrO_2$ -assisted  $VSe_2$  firmly anchoring on the octahedron carbon greatly improved the electrochemical stability, while the MOF-derived porous carbon suppressed the volumetric changes and enhanced the lithium-ion transport dynamics. Consequently,  $VSe_2$ - $ZrO_2$ /C/MXene demonstrates a high reversible capacity reaching 1238.5 mA h  $g^{-1}$  at 100 mA  $g^{-1}$ , and superior cycling stability with a capacity of 430 mA h  $g^{-1}$  even after 1000 cycles at 1.0 A  $g^{-1}$ . Furthermore, we assembled a full cell by coupling  $LiFePO_4$  as the cathode and  $VSe_2$ - $ZrO_2$ /C/MXene as the anode. This work could be regarded as a significant motivation for application exploration.

## Experimental

For the etching process, 2.0 g  $V_2AlC$  powder was slowly added into 40 mL HF (40%) solution for 1 h. The mixture was kept stirring for 5 days at a temperature of 35 °C to remove  $Al^{3+}$ . After that, the black residue was washed with deionized water by centrifugation until the pH of the supernatant reached  $\sim 7$ . Subsequently, the residue was transferred to a vacuum freeze dryer for drying to obtain  $V_2CT_x$ .

The composite was synthesized *via* the typical hydrothermal method. First, 0.9 mmol  $H_2BDC$  and 0.9 mmol  $ZrCl_4$  were dissolved in 60 mL DMF with 150 mg  $V_2CT_x$  under ultrasonic treatment. Then, 6 mL glacial acetic acid was dropwise injected into the above-mixed solution under ultrasound for 0.5 h. Subsequently, the mixed solution was transferred into a Teflon-lined stainless-steel autoclave for hydrothermal treatment at 120 °C for 16 h. The obtained black precipitate was washed by DMF and dried in a vacuum oven at 60 °C to attain the precursor of UiO-66/ $V_2CT_x$ . UiO-66 was prepared in the same way, except for adding  $V_2CT_x$  in the precursor. The as-prepared UiO-66/ $V_2CT_x$  precursor and Se powder were placed in two fused quartz boats with a dosage ratio of 1 : 20, and then calcinated at 600 °C for 2 h in nitrogen flow, which is denoted as  $VSe_2$ - $ZrO_2$ /C/MXene. The corresponding synthesis schematic diagram is generalized in Fig. 1a. For comparison, Se- $ZrO_2$ /C and  $VSe_2$ /




Fig. 1 (a) Schematic of the preparation of  $VSe_2-ZrO_2/C/MXene$ . FESEM images of (b)  $Se-ZrO_2/C$ , (c)  $VSe_2/MXene$  and (d and e)  $VSe_2-ZrO_2/C/MXene$ . (f) TEM (inset: HRTEM and corresponding IFFT image), and (g) EDS elemental mapping images of  $VSe_2-ZrO_2/C/MXene$ .

$MXene$  were obtained at the same selenization condition by directly heating  $UiO-66$  and  $V_2CT_x$   $MXene$ . Detailed characterizations and electrochemical tests are shown in ESI.†

## Results and discussion

The morphologies of the samples were revealed in field-emission scanning electron microscopy (FESEM). As observed from Fig. S1a,† the original  $UiO-66$  exhibits an octahedron configuration with an even size of  $0.8\ \mu m$ , while  $V_2CT_x$  shows a typical corrugated structure of  $MXene$  (Fig. S1b†).<sup>50</sup> Fig. 1b and S2a† show the FESEM and transmission electron microscopy (TEM) images of  $Se-ZrO_2/C$ , which present the well-defined octahedral structure, except for slight size shrinkage owing to thermal contraction.<sup>51</sup> The  $V_2CT_x$  layers turn into irregular stacking of  $VSe_2/MXene$  with thicker flakes after selenization (Fig. 1c and S2b†). Fig. 1d and e demonstrates the retainability of the architecture after selenization of  $UiO-66/V_2CT_x$  to form  $VSe_2-ZrO_2/C/MXene$ . According to the morphology changes of different precursors (Fig. S1, S2† and 1), a relative non-uniform octahedral structure with a rough surface can be detected, which should be derived from the selenization process. A little flake also can be observed in Fig. 1d, caused by the collapse of octahedral structures during the selenization process. In this case, the auxetic specific surface area can supply more active sites and abundant Li-ion transfer paths to improve the reaction kinetics.<sup>52</sup> Fig. 1f shows the TEM image of the  $VSe_2-ZrO_2/C/MXene$  composite, demonstrating an interlink between flakes and octahedrons. The inset is the high-resolution transmission electron microscopy (HRTEM) and the corresponding inverse fast Fourier transform (IFFT) images of  $VSe_2-ZrO_2/C/MXene$ . Lattice fringes with spacings of  $0.29\ nm$  and  $0.27\ nm$  are observed, corresponding to the (101) planes of tetragonal  $ZrO_2$  (JCPDS 88-1007) and the (011) planes of hexagonal  $VSe_2$  (JCPDS 89-1641), respectively, implying the migration of V and *in situ* growth of  $VSe_2$ . The  $MXene$  is too rare to be found in HRTEM. A uniform

distribution of V, Zr, Se, C, and O elements is observed from energy dispersive spectroscopy (EDS) elemental mapping images in Fig. 1g. The V signal is found in the region of octahedrons, further verifying the transform of  $V_2CT_x$  to  $VSe_2$  on carbon. Therefore, the tiny particles on the rough surface of the octahedron are  $VSe_2$ . The above tests confirm the existence of each component in  $VSe_2-ZrO_2/C/MXene$ . The contents of V, Zr, and Se are 15.7%, 18.2%, and 38.2%, respectively, determined by inductively coupled plasma-atomic emission spectrometry (ICP-AES). As a result, we can calculate the mass ratios of  $VSe_2$  and  $ZrO_2$  to be 50.53% and 24.55%, respectively. The remaining 24.92% should be porous carbon and a small number of  $MXene$ .

Fig. 2a and b and S3† present the samples' X-ray diffraction (XRD) patterns. The XRD pattern of  $UiO-66$  in Fig. S3a† is in line with the previous report.<sup>53</sup> The sharp peak at  $7.3^\circ$  is characteristic of the typical  $UiO-66$  diffraction peak. As seen from Fig. S3b,† the new peak that appears at  $9.3^\circ$  after etching treatment can be assigned to the (002) peak for  $V_2CT_x$ , indicating the removal of the Al layer. The complex pattern of  $UiO-66/V_2CT_x$  in Fig. S3c† incorporates the diffraction peaks of both  $UiO-66$  and  $V_2CT_x$ , suggesting their successful integration. After selenization, the diffraction pattern of  $Se-ZrO_2/C$  in Fig. 2a is in agreement with the standard  $ZrO_2$  peaks at  $30.25^\circ$ ,  $50.4^\circ$ , and  $60.2^\circ$  that are ascribed to the (101), (112) and (211) planes, respectively, while the diffraction peaks of  $VSe_2/MXene$  at  $14.6^\circ$ ,  $34.1^\circ$  and  $42.9^\circ$  match well with the (001), (011) and (102) planes of  $VSe_2$ , respectively. Notably, the peaks at  $41.3^\circ$  and  $55.2^\circ$  indicate the existence of residual  $V_2CT_x$ , which should be helpful in improving the conductivity of  $VSe_2$ . Similar peaks detected in the pattern of  $VSe_2-ZrO_2/C/MXene$  in Fig. 2b with those for  $Se-ZrO_2/C$  and  $VSe_2/MXene$  can be rationalized as their co-existence in  $VSe_2-ZrO_2/C/MXene$ . In addition, the broad peak at around  $22^\circ$  belongs to amorphous carbon in the hybrid.<sup>54</sup>




Fig. 2 XRD patterns of (a)  $VSe_2/MXene$  and  $Se-ZrO_2/C$ , (b)  $VSe_2-ZrO_2/C/MXene$ . (c) Nitrogen adsorption–desorption isotherms and (d) pore size distributions of  $VSe_2-ZrO_2/C/MXene$ ,  $VSe_2/MXene$  and  $Se-ZrO_2/C$ .

Table 1 Specific surface areas, pore volumes, and mean pore diameters of  $V_2CT_x$ ,  $Se-ZrO_2/C$ ,  $VSe_2/MXene$  and  $VSe_2-ZrO_2/C/MXene$ 

Sample	Specific surface area ( $m^2 g^{-1}$ )	Pore volume ( $cm^3 g^{-1}$ )	Mean pore diameter (nm)
$V_2CT_x$	88.2	0.173	3.063
$Se-ZrO_2/C$	329.0	0.196	3.422
$VSe_2/MXene$	132.7	0.176	3.059
$VSe_2-ZrO_2/C/MXene$	218.7	0.368	3.410

$N_2$  adsorption-desorption isotherms were conducted to investigate the specific surface area and pore nature based on the Brunauer-Emmett-Teller (BET) and Barrett-Joyner-Halenda (BJH) methods, respectively. All of the sample plots are in accordance with the type-IV hysteresis curve in Fig. 2c. The apparent hysteresis loop at a relative pressure range  $P/P_0$  of 0.2–0.8 and pore size distributions (Fig. 2d) indicate mesoporous constructions in these samples. The abundance of mesopores not only contributes to the specific surface area, but also provides more reaction sites. This type of pore structure will provide a site for the formation of the Li-cluster, which contributes to the high capacity of the composite, especially after activation. Furthermore, the hierarchical porous structure constructs abundant 3D channels to facilitate ion transport. The details of the specific surface areas, pore volumes, and mean pore diameters of  $V_2CT_x$ ,  $Se-ZrO_2/C$ ,  $VSe_2/MXene$ , and  $VSe_2-ZrO_2/C/MXene$  are summarized in Table 1. The specific surface area of  $VSe_2-ZrO_2/C/MXene$  is calculated to be  $218.7 m^2 g^{-1}$ , which is higher than that of  $VSe_2/MXene$ . Such an enhancement of the specific surface area relies on the carbon matrix from the MOF precursor. Furthermore,  $VSe_2-ZrO_2/C/MXene$  displays the largest pore volume among all of the samples due to its unique multi-component architecture. This structural improvement of the MOF-MXene hybrid intuitively explains the enhancement mechanism related to the ample ion storage, facile ion/charge diffusion, and void space for volume variation.<sup>55,56</sup> Fig. S4† shows the nitrogen adsorption-desorption isotherms and pore size distributions of the pure  $V_2CT_x$ .

The chemical states of  $VSe_2/MXene$ ,  $Se-ZrO_2/C$ , and  $VSe_2-ZrO_2/C/MXene$  were disclosed by X-ray photoelectron spectroscopy (XPS) analysis. Fig. 3a shows the XPS survey spectra and Table S1† demonstrates the atomic concentration (at%) of the elements for  $Se-ZrO_2/C$ ,  $VSe_2/MXene$  and  $VSe_2-ZrO_2/C/MXene$ . The results confirm the existence of Zr, V, Se, C, N and O in  $VSe_2-ZrO_2/C/MXene$ , which is consistent with the elemental mapping results. As shown in the high-resolution Zr 3d spectrum (Fig. 3b), the peaks centered at 184.3 eV and 181.9 eV originate from the Zr  $3d_{3/2}$  and Zr  $3d_{5/2}$  orbitals of  $Zr^{4+}$ .<sup>57</sup> Compared to  $Se-ZrO_2/C$ , a slight shift to higher binding energy for Zr 3d in  $VSe_2-ZrO_2/C/MXene$  can be detected, indicating the formation of strong chemical binding between  $VSe_2$  and  $ZrO_2$ . Fig. 3c presents the V 2p spectrum of  $VSe_2/MXene$  and  $VSe_2-ZrO_2/C/MXene$ . Three pairs of peaks at 524.9/517.0 eV, 523.4/516.6 eV, and 521.0/512.4 eV can be deconvoluted, representing the V  $2p_{1/2}$  and V  $2p_{3/2}$  orbitals of the  $V^{4+}$ ,  $V^{3+}$  and  $V^{2+}$  states, respectively.<sup>30</sup> The XPS V 2p peak shape becomes less metallic after introducing  $ZrO_2$ , which is mainly manifested as a higher

binding energy shift and increased asymmetric shape at the high binding energy side.<sup>58</sup> The Se 3d spectrum in Fig. 3d shows that the peaks observed at 55.9 eV and 53.1 eV are attributed to Se  $3d_{3/2}$  and Se  $3d_{5/2}$  orbitals, respectively. These two peaks appear at the relatively low binding energy position because of the weakened metal-Se bond in  $VSe_2/MXene$ .<sup>59</sup> Another peak at 58.9 eV is derived from the formation of  $SeO_x$  on the surface of the composite.<sup>60</sup> The increased atomic ratio of  $V^{4+}$  and  $V^{3+}$  at the high binding energy side and the change of the Se 3d orbital intensities reflect the partial electronic transfer upon the influence of  $ZrO_2$ .<sup>61</sup> Moreover, the presence of defects in the samples was investigated by electron paramagnetic resonance (EPR). From the spectra in Fig. S5,† the signal at g factor of 2.00 can be assigned to the amorphous MOF-derived carbon,<sup>62</sup> which is detected in  $Se-ZrO_2/C$  and  $VSe_2-ZrO_2/C/MXene$ . Accordingly, an additional signal at g factor of 1.97 originates from the paramagnetic  $V^{4+}$ .<sup>63,64</sup> The significant defect-related signal indicates the existence of abundant active sites in  $VSe_2-ZrO_2/C/MXene$ . Notably, more active nodes for lithium storage are favorable to coulombic efficiency because of the increased capacity and faster ion transport.<sup>65,66</sup>

Thermogravimetric analysis (TGA) from atmospheric temperature to 800 °C was tested in a nitrogen atmosphere to investigate the residue of free Se in these electrode materials. As previously reported, the Se is sublimated at around 400 °C in  $N_2$ .<sup>67</sup> It can be observed in Fig. S6† that except for the release of




Fig. 3 (a) Survey, (b) Zr 3d, (c) V 2p and (d) Se 3d XPS spectra of  $Se-ZrO_2/C$ ,  $VSe_2/MXene$  and  $VSe_2-ZrO_2/C/MXene$ .

adsorbed or bonded water before 200 °C, the slight weight loss of 3.8% for Se-ZrO<sub>2</sub>/C results from the sublimation of the free Se, indicating that there is no residue of free Se in these samples. Notably, compared with Se-ZrO<sub>2</sub>/C, VSe<sub>2</sub>/MXene and VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene exhibit much more significant weight loss after 400 °C, which should be ascribed to the fact that the unstable V<sup>4+</sup> is prone to be converted into the V<sup>3+</sup> or V<sup>5+</sup> species.<sup>19</sup>

The electrochemical performances of the samples were evaluated in half cells. As depicted in Fig. 4a and S7a and b,<sup>†</sup> the cyclic voltammetry (CV) curves gradually overlap from cycle to cycle, which is typical for Se-based materials.<sup>68–70</sup> In the initial cathodic scan of VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene, two broad peaks from 0.9 to 0.01 V can be recorded, attributed to certain side reactions, including the electrolyte decomposition along with the generation of the solid-state electrolyte interface (SEI) layer.<sup>71</sup> During the intercalation of lithium ions, the cathodic peaks centered at 1.9 V and 1.4 V can be assigned to the formation of Li<sub>x</sub>VSe<sub>2</sub> (eqn. (1))<sup>71</sup> and intermediate product Li<sub>2</sub>Se<sub>n</sub> ( $n \geq 4$ ) (eqn. (2)),<sup>67</sup> respectively. Another reduction peak at 0.5 V can be attributed to the conversion reaction to V and Li<sub>2</sub>Se (eqn. (3)).<sup>71</sup> In the subsequent curves, two intercalation peaks shift slightly to lower voltage due to the polarization and merge into a wide-ranging peak at ~1.3 V, which could be certified by the decreased capacity in the first few cycles in Fig. 4b. This phenomenon for the deviation of CV curves is common for TMDs.<sup>72,73</sup> During the initial anodic scan, the peaks at 1.9 V and

2.2 V are associated with delithiation to gain the intermediate product Li<sub>x</sub>VSe<sub>2</sub> (eqn. (4)) and fully charged product VSe<sub>2</sub> (eqn. (5))<sup>19</sup> and Se (eqn. (6)).<sup>74</sup> It is noticed that from the subsequent cycles, two anodic peaks remain at the original position with weakened intensity, resulting from the irreversible formation of the SEI layer. The CV curves of Se-ZrO<sub>2</sub>/C and VSe<sub>2</sub>/MXene show the corresponding redox peaks. Notably, the reduction peaks for VSe<sub>2</sub>/MXene are not obvious at 1.8 V, demonstrating weaker insertion of lithium ions. The phenomenon should be ascribed to its low specific surface area and small pore volume, which leads to stiff lithium-ion insertion and poor storage site. According to the above electrochemical reaction analysis, we suggest the reaction process of the VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene electrode for LIBs as below:

The discharge reactions:



The charge reactions:






Fig. 4 (a) CV curves at 0.2 mV s<sup>-1</sup>, and (b) galvanostatic charge/discharge profiles of VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene (inset shows the magnified images for charge/discharge curves at the range of 0.2–0.8 V and 1.0–2.5 V). (c) Cycling performances and corresponding coulombic efficiencies of Se-ZrO<sub>2</sub>/C, VSe<sub>2</sub>/MXene, and VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene at 100 mA g<sup>-1</sup>. (d) Long-term cyclabilities at 1.0 A g<sup>-1</sup> and (e) rate performances of Se-ZrO<sub>2</sub>/C, VSe<sub>2</sub>/MXene and VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene.




Fig. 4b and S7c and d† show the galvanostatic charge/discharge (GCD) profiles of the electrodes. Several distinct voltage plateaus at ~2.0 V, 1.4 V, and 0.9 V can be detected in the initial discharge curve, which is in good agreement with the CV curves. The current measurement of the state of charge (SOC) of the battery is currently still a difficult point. Thus, for the linear discharge curve of the anode, we suggest that this behavior may provide an opportunity to accurately measure the SOC of the battery. During the charging process, the plateau is of negligible change. It can be observed that the initial charge/discharge capacities of  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$ ,  $\text{Se-ZrO}_2/\text{C}$  and  $\text{VSe}_2/\text{MXene}$  are 508/1094.4  $\text{mA h g}^{-1}$ , 315.4/598.3  $\text{mA h g}^{-1}$  and 381/562.6  $\text{mA h g}^{-1}$ , respectively, giving the coulombic efficiencies of 46.42%, 52.71% and 67.72%, respectively. The initial fading irreversible capacity is mainly related to the formation of the SEI layer. For the porous material, the high pore volume and a larger surface area offer abundant contact sites between the electrolyte and electrode, which leads to the polarization and lower coulombic efficiency.<sup>75,76</sup> On the other side, the reversible capacity of  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  surpasses those of  $\text{Se-ZrO}_2/\text{C}$  and  $\text{VSe}_2/\text{MXene}$  to a large extent, illustrating that the architecture of  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  is more conducive to the storage of lithium ions. With the cycling proceeding, the reversible capacity of  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  manifests a continuous elevation derived from the activation of the electrode after a transitory deterioration in the first ten cycles. The details are elaborated in Fig. 4c. Surprisingly, the specific capacity of  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  becomes stable up to 1238.5  $\text{mA h g}^{-1}$  after 200 cycles. Compared to  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$ ,  $\text{Se-ZrO}_2/\text{C}$  achieves stable cycling performance with a specific capacity of 298  $\text{mA h g}^{-1}$ , while  $\text{VSe}_2/\text{MXene}$  only presents a specific capacity of 128.2  $\text{mA h g}^{-1}$  after 100 cycles. The visual insight of the morphology change after cycling by FESEM is presented in Fig. S8.† As depicted, the obtained  $\text{VSe}_2/\text{MXene}$  flakes become one giant bulk, and  $\text{Se-ZrO}_2/\text{C}$  is subjected to severe structural damage on account of the mechanical strains in repeated cycling. Fortunately, the  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  composite retains the octahedral shape, ensuring its outstanding cyclic and structural stability. All of the samples retain stable coulombic efficiencies close to 100% after ten cycles, as shown in Fig. 4c. The continuous activation is also reflected by the long-term cycling performance in Fig. 4d. The capacity of  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  continues to increase until 200 cycles.  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  delivers excellent cycling performance even over 1000 cycles at 1.0  $\text{A g}^{-1}$ , achieving a high capacity retention of nearly 100%. The reversible capacity can be maintained at 430  $\text{mA h g}^{-1}$  after 1000 cycles, which is superior to  $\text{Se-ZrO}_2/\text{C}$  (265  $\text{mA h g}^{-1}$ ) and  $\text{VSe}_2/\text{MXene}$  (105  $\text{mA h g}^{-1}$ ). It can be detected that the electrode underwent complex activation during cycling, which is common in anodes.<sup>48,77-79</sup> Furthermore, the activation behavior depends on many factors, such as the mechanical stress and volume change rate at different current densities.<sup>80</sup> This fading-reactivation phenomenon is probably driven by the delayed soaking of electrolytes into porous carbon and the gradual establishment of the SEI layer.<sup>81-83</sup> Small

inorganic species in the composite can also induce the enhancement.<sup>84</sup> The Li-cluster in porous carbon material can also provide extra ultra-high capacity.<sup>85,86</sup> The increasing capacity of the anode does not cause a capacity decay of the battery. However, we suggest that the increased capacity of the composite can couple with some capacity attenuation anode materials, including Si, Sn, Sb, and Bi, to achieve capacity complementarity.<sup>87-90</sup> This behavior should provide an opportunity to settle the capacity-fading situation.

Fig. 4e shows the rate performances of  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$ ,  $\text{Se-ZrO}_2/\text{C}$  and  $\text{VSe}_2/\text{MXene}$ . The reversible specific capacities of  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  are 427.8, 385.1, 335.3, 288.9 and 225.9  $\text{mA h g}^{-1}$  at the current density of 0.1, 0.2, 0.5, 1.0 and 2.0  $\text{A g}^{-1}$ , respectively. Even at a high current density of 5.0  $\text{A g}^{-1}$ ,  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  still exhibits excellent cyclability. The gratifying stability demonstrates that the multi-hole carbon matrix derived from the MOF structure can act as a flexible buffering to relieve volume variety and suppress electrode pulverization at high current density. With the recovery of the current density to 0.1  $\text{A g}^{-1}$ , a reversible capacity of 612.2  $\text{mA h g}^{-1}$  can be obtained, indicating the excellent reversibility of the  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  electrode. The versatile rate performance is to a great extent attributed to the inimitable structural construction. Expressly, the multi-channel carbon derived from the MOF precursor not only guarantees the architectural integrity during the charge/discharge process, but also provides ample reaction sites for lithium ions. Furthermore,  $\text{ZrO}_2$  chemically bonds with  $\text{VSe}_2$  to assist it in anchoring firmly on carbon. By contrast,  $\text{Se-ZrO}_2/\text{C}$  and  $\text{VSe}_2/\text{MXene}$  establish much lower reversible capacities than  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$ . Thereinto,  $\text{Se-ZrO}_2/\text{C}$  presents higher capacities of 243.5, 213.4, 120.9, 68.0, 30.3 and 9.3  $\text{mA h g}^{-1}$  than  $\text{VSe}_2/\text{MXene}$  at 0.1, 0.2, 0.5, 1.0, 2.0 and 5.0  $\text{A g}^{-1}$ , respectively, which further proves that the introduction of  $\text{ZrO}_2$  is beneficial to better stability for lithium-ion storage. The relative growth of reversible capacity for these selenide samples indicates the different extent of the activation process.<sup>71,75,91</sup> To the best of our knowledge, our prepared  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  exhibits the best electrochemical properties among the similar type of LIBs anode materials reported in the literature in terms of the reversible capacity, cycling stability, and rate capability, as shown in Table S2†, highlighting the promising application of  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  in LIBs.

The evaluation of the electrochemical performance of anode materials is not only the capacity, but also its voltage plateau. Therefore, we adopted a concept of relative energy density ( $E_R$ ).<sup>92,93</sup> We compared our anode with meso-carbon microbeads to evaluate the electrochemical performance of anode materials more accurately and conveniently. The corresponding equations are as follows:

$$E_R = \Delta U Q \quad (7)$$

$$\Delta U = -P_K - V_A \quad (8)$$

$$V_A = \int U dQ/Q \quad (9)$$




Fig. 5 Typical legends for the determination of the relative energy density ( $E_R$ ) of (a) discharge  $E_R$  and (b) charge  $E_R$ . (c) Discharge  $E_R$  of  $VSe_2-ZrO_2/C/MXene$  and meso-carbon microbeads.

In the equations,  $Q$ ,  $P_K$  and  $V_A$  represent the specific capacity, electrode potential of Li ( $-3.04$  V vs.  $Li/Li^+$ ) and average voltage, respectively. Fig. 5a and b present the determination of these parameters. According to the calculation from the above equations, Fig. 5c shows that the electrode presents an initial discharge  $E_R$  of  $2715.616$  W h  $kg^{-1}$ , and maintains the discharge  $E_R$  of  $2171.12$  W h  $kg^{-1}$  after 100 cycles at  $100$  mA  $g^{-1}$ . Compared with Fig. S9b and c,† it was found that the  $E_R$  of  $VSe_2-ZrO_2/C/MXene$  is relatively higher than the conventional carbon material. Fig. S9a† is the cycling performance of meso-carbon microbeads.

To better understand the electrochemical reaction along with cycling and prove the above-mentioned phase transformation, the *ex situ* XRD measurement of the  $VSe_2-ZrO_2/C/MXene$  electrode was carried out. Fig. 6a records the charge/discharge curve of the  $VSe_2-ZrO_2/C/MXene$  electrode after 250 cycles, and Fig. 6b shows the corresponding XRD patterns during the different insertion/extraction states. It was found that the (101) peak of  $ZrO_2$  presents the left shift, suggesting a lattice expansion in the Li-ion insertion process to form

$Li_xVSe_2$ , whereas the lattice regresses after delithiation. In the discharge process, the peak of the (011) lattice plane becomes broader and the intensity weakens. After discharging to  $0.05$  V, the new characteristic peaks of metal V and  $Li_2Se$  appear. These changes indicate the occurrence of a partial conversion reaction wherein  $Li_xVSe_2$  is converted to  $Li_2Se$  and metal V.  $Li_2Se$  and metal V reversibly disappear in the charge process. A similar result was obtained from *ex situ* Raman spectra, as shown in Fig. S10.† The peaks at  $\sim 1351$  and  $1590$   $cm^{-1}$  can be characterized as the D and G bands of amorphous carbon, respectively.<sup>94</sup> The vague peak at around  $640$   $cm^{-1}$  confirms the existence of  $ZrO_2$  with low crystallinity.<sup>95</sup> Specifically, two broad peaks at  $\sim 280$  and  $406$   $cm^{-1}$  are assigned to the  $E_{2g}$  in-plane vibration mode and  $A_{1g}$  out-of-plane vibration mode of  $VSe_2$ , respectively.<sup>71</sup> These two characteristic peaks broadened, and the intensities tended to vanish during the discharging process, which suggests the intercalation of lithium ions and conversion reaction of  $VSe_2$ . In the charging process, the intensities of the  $VSe_2$  peaks gradually recovered. The appearance of a peak located at around  $1087$   $cm^{-1}$  is due to the symmetric stretching vibrations of  $Li_2CO_3$ ,<sup>96,97</sup> which indicates certain side reactions. Additionally, the electrochemical impedance spectroscopy (EIS) plots during the 40th cycle in the activation process were measured at different charge/discharge states, namely, open-circuit voltage (OCV),  $0.8$  V and  $0.05$  V (discharging),  $1.8$  V and  $3.0$  V (charging). As presented in Fig. 6c, the large  $R_{ct}$  (charge transfer resistance) value of  $155$   $\Omega$  in the OCV state decreases to  $143$   $\Omega$  after discharging to  $0.8$  V. It further decreases to  $55.5$   $\Omega$  when discharging to  $0.05$  V, which can be attributed to the activation process as a result of enhanced infiltration of the electrolyte into the electrode.<sup>98</sup> The semicircle at high frequency nearly vanishes at the delithiation state of  $3.0$  V, indicating the partial decomposition of the SEI layer at this stage. Fig. S11† records the TEM images of  $VSe_2-ZrO_2/C/MXene$  after discharging down to  $0.05$  V and fully charging to  $3.0$  V. The thickness of the SEI layer is approximately  $880$  nm at  $0.05$  V in Fig. S11a.† Hereafter, the electrode undergoing reconversion only preserves a thin SEI layer in Fig. S11b,† which further proves the decomposition of the SEI layer. We also compared the EIS plots of  $VSe_2-ZrO_2/C/MXene$ ,  $Se-ZrO_2/C$  and  $VSe_2/MXene$  cells after 100 cycles, as shown in Fig. 6d. The corresponding equivalent circuit model is shown in the inset. The fitted  $R_{ct}$  values of  $Se-ZrO_2/C$ ,  $VSe_2/MXene$  and  $VSe_2-ZrO_2/C/MXene$  are  $9.67$ ,  $38.6$ , and  $13.2$   $\Omega$ , respectively. The decreased impedance of  $VSe_2-ZrO_2/C/MXene$  indicates that the conductive carbon plays an essential role in kinetic behavior. Given that the value of the second semicircle is caused by the charge transfer resistance, the small  $R_{ct}$  unveils the surface layer's low resistance, which greatly facilitates the electron transport.<sup>99</sup> To further confirm the increase of ionic conductivity in the battery, we calculated the lithium-ion diffusion coefficients ( $D_{Li}$ ) according to the EIS results. The corresponding equation is as follows:

$$D_{Li} = \frac{R^2 T^2}{2S^2 n^4 F^4 C^2 \sigma^2} \quad (10)$$




Fig. 6 (a) Discharge/charge curve and corresponding voltage positions of  $VSe_2-ZrO_2/C/MXene$ . (b) *Ex situ* XRD characterizations of the corresponding potential states. (c) EIS plots of  $VSe_2-ZrO_2/C/MXene$  at various states in the 40th cycle at  $100$  mA  $g^{-1}$ . (d) Nyquist plots of  $Se-ZrO_2/C$ ,  $VSe_2/MXene$  and  $VSe_2-ZrO_2/C/MXene$  after 100 cycles at  $100$  mA  $g^{-1}$  (inset: corresponding equivalent circuit model). (e) Fitted lines of  $Z'$  versus  $\omega^{-1/2}$  at low frequency for  $VSe_2-ZrO_2/C/MXene$ .

where  $D_{\text{Li}}$  represents the diffusion coefficient of lithium ions,  $S$  stands for the surface area of the electrode/electrolyte and  $n$  is the number of electrons participating in the electrode reactions.  $R$ ,  $T$  and  $F$  are the gas constant, absolute temperature, and Faraday constant, respectively.  $C$  is the concentration of lithium ions. Warburg factor  $\sigma$  can be calculated from  $Z' - \omega^{-1/2}$  fitted line in the low-frequency region, as shown in Fig. 6e. The  $\sigma$  values for Se-ZrO<sub>2</sub>/C, VSe<sub>2</sub>/MXene and VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene are 68.3, 244.1 and 64.2  $\Omega \text{ s}^{-1/2}$ , respectively. Hence, the  $D_{\text{Li}}$  value of the VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene electrode is about 14 times higher than that of the obtained VSe<sub>2</sub>/MXene electrode, which means that the derivative of UiO-66 tremendously accelerates the lithium-ion diffusion.

Based on the above results, we find a very interesting phenomenon wherein the abnormal charge storage behavior observed in the cycling performance is in contrast with capacity fading in VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene. The behavior has been referred to as “negative fading” in previous works.<sup>100,101</sup> Despite the extensive observations on this subject, its origin has not been identified by far for the reason of complex reactions, involving bulk materials, interface and electrolyte constituents.<sup>100,102</sup> To study the internal mechanism of the capacity increase, a series of tests for cells after cycles were thoroughly explored for comparison. Fig. S12b† shows the capacity difference between the 100th cycle ( $C_{100}$ ) and the 10th cycle ( $C_{10}$ ), and its calculated differential  $\text{vs. voltage } d(C_{100}-C_{10})/dV$ . We suggest that the “negative fading” results from the capacity enhancement in the low potential region.<sup>103</sup> The sharp differential peaks at around

0.7 V and 2.0 V can be attributed to the discharge plateaus in Fig. S12a.† When fully discharging to  $\sim 0.01$  V, the capacity difference increases to 463.1  $\text{mA h g}^{-1}$ . The exceeding reversible capacity for the 100th cycle reveals prominent “negative fading”.

The capacity of the composite should be attributed to the synergistic effect, including the insertion reaction in carbon and MXene, conversion reaction in VSe<sub>2</sub>, adsorption of Li on the surface of the composite, and the formation of Li-cluster in the space of the composite. To further understand the kinetic behavior, CV curves at different scan rates from 0.2 to 2.0  $\text{mV s}^{-1}$  were measured (Fig. 7a). Especially, the CV curves with the same shapes illustrate the excellent reversibility for Li-ion storage of VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene. As the two vital mechanisms, the capacitive contribution mainly comprises the adsorption of Li on the surface and the formation of a Li-cluster in the space of the composite, and the diffusion-controlled contributions from the insertion reaction in carbon and MXene, and conversion reaction in VSe<sub>2</sub>.<sup>104</sup> The relationship between the scan rate ( $v$ ) and current ( $i$ ) can be summarized as eqn (8):

$$i = av^b \quad (11)$$

Eqn (8) can be converted to eqn (9):

$$\log(i) = \log(a) + b \log(v) \quad (12)$$




Fig. 7 (a and e) CV curves of the as-prepared VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene and after cycling for 250 cycles at different scan rates. (b and f) Linear relationship between  $\log(i)$  and  $\log(v)$  at different voltages for the as-prepared VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene and after cycling for 250 cycles. (c and g) Separation of capacitive and diffusion-controlled contribution areas at 0.4  $\text{mV s}^{-1}$  for the as-prepared VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene and after cycling for 250 cycles. (d and h) Ratios of capacitive and diffusion-controlled contributions at different scan rates for the as-prepared VSe<sub>2</sub>-ZrO<sub>2</sub>/C/MXene and after cycling for 250 cycles.



where the coefficients  $a$  and  $b$  are regulatable,  $i$  is the corresponding current and  $v$  is the scan rate. Particularly, if  $b$  is close to 1, the capacitive behavior dominates. Otherwise, the diffusion-controlled dominates when  $b$  approaches 0.5. In Fig. 7b, the  $b$  values are fitted as 0.77, 0.94, 0.79, 0.74, 0.50, 0.61, and 0.99 at the potentials of 0.01, 0.3, 0.6, 0.9, 1.2, 1.8 and 3.0 V, respectively, demonstrating the cooperative control of both storage mechanisms.

The specific contribution ratios for capacitive and diffusion-controlled behaviors can be quantified by eqn (10):

$$i(V) = k_1 v + k_2 v^{1/2} \quad (13)$$

where  $i(V)$  is the current density at a fixed potential, and  $k_1 v$  and  $k_2 v^{1/2}$  are the respective contributions of the capacitive effect and diffusion process. Fig. 7c displays the fitting curves for the contribution ratio at  $0.4 \text{ mV s}^{-1}$ . As shown in Fig. 7d, the capacitive/diffusion contributions are 22.8%/77.2%, 33.7%/66.3%, 41.3%/58.7%, 44.8%/55.2%, 47.2%/52.8%, 51.8%/48.2% and 54.0%/46.0% at the scan rates of 0.2, 0.4, 0.6, 0.8, 1.0, 1.5 and  $2.0 \text{ mV s}^{-1}$ , respectively. The capacitive contribution grows with increasing scan rates. As elucidated in the pioneering work, it facilitates the lithium-ion storage in the electrode surface that expedites the ion transfer,<sup>3</sup> benefitting the rate performance. These results indicate that the common effect of capacitive and diffusion contributions constituted the capacity of our composite.

To fully explain the evolution of the lithium-ion storage performance, the XPS analysis, CV curves and EIS plots for the cells after 250 cycles were performed. As shown in Fig. S13,† the changes in XPS can be found on the V and Se elements, indicating that the fading-reativation phenomenon is mainly caused by  $\text{VSe}_2$  in the composite. Fig. 7e displays the CV curves at different sweep rates of  $0.2$ – $2.0 \text{ mV s}^{-1}$ . The linear relationship between  $\log(i)$  and  $\log(v)$  in Fig. 7f reflects the fitted  $b$  values of 0.63, 0.73, 0.53, 0.71, 0.83, 0.73, and 0.91. The variations of the  $b$  values indicate the change of dominating mechanism. We also calculated the diffusion-controlled contribution of  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$ , as shown in Fig. 7g and h. An enhanced diffusion behavior was observed. The diffusion mechanism of the batteries mainly contributes to the Li-ion insertion or conversion reaction. These continuous behaviors will lead to the continuous change of the material structure, resulting in the occurrence of the fading-reativation phenomenon. The Nyquist plots for the  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  anode are also displayed after different cycles in Fig. S14.† The resistance continuously decreases during the activation process, demonstrating the facile reaction kinetics. Even after 200 cycles, the  $R_{\text{ct}}$  value of  $105 \Omega$  is still smaller than the original value of  $155 \Omega$ , further supporting the improved capacity activation during cycling. The above evidence explains the enhancement phenomenon in negative fading.

To confirm the applicability of the  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  electrode, the  $\text{LiFePO}_4\|\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  ( $\text{LFP}\|\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$ ) full cells were assembled. It should be noted that the anodes were pre-lithiated at  $2 \text{ A g}^{-1}$  for five cycles in half cells to achieve rapid activation. Based on the cycle performance




Fig. 8 (a) Half-cell charge–discharge profiles of LFP and  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  electrodes at  $100 \text{ mA g}^{-1}$ . (b) Galvanostatic charge/discharge profiles and (c) cycling performances for  $\text{LFP}\|\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  full cell at  $100 \text{ mA g}^{-1}$ . (d) Rate performances and (e) Nyquist plot for  $\text{LFP}\|\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  full cell (inset: equivalent electrical circuit model).

of commercial  $\text{LiFePO}_4$  and  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  in Fig. 8a, the mass loading of  $\text{LiFePO}_4$  should be 2.5 times of that of  $\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$ , achieving an anode/cathode capacity ratio of  $\sim 1.1$ . Fig. 8b depicts the galvanostatic charge/discharge curves of the  $\text{LFP}\|\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  full cell in the 1st, 2nd, 15th and 20th cycles. It can be seen that the full cell exhibits a clearly extended platform. Benefitting from the pre-lithiation before assembly, the initial coulombic efficiency reaches 90.2%, indicating that the effective replenishment of lithium to anode can offset the irreversible lithium loss during the formation of the SEI layer in the initial cycle.<sup>105,106</sup> From Fig. 8c and d, the reversible capacity for the  $\text{LFP}\|\text{VSe}_2\text{-ZrO}_2/\text{C}/\text{MXene}$  full cell retains  $113.2 \text{ mA h g}^{-1}$  after 100 cycles at  $100 \text{ mA g}^{-1}$  and good rate capability is manifested with a capacity of  $71 \text{ mA h g}^{-1}$  at  $500 \text{ mA g}^{-1}$ , demonstrating a successful operation of the full cell. In addition, the EIS test of the full cell is provided to evaluate the reaction dynamics in Fig. 8e. A small  $R_{\text{ct}}$  of  $113 \Omega$  can be obtained, indicating that our electrode in the full cell also presents an excellent electron transfer characteristic.

The mechanism schematic is summarized in Fig. 9.  $\text{VSe}_2$  provides the capacity, while the remaining MXene can enhance the conductivity of the hybrid. The derived carbon and  $\text{ZrO}_2$  play a significant role in Li-ion storage. The  $\text{ZrO}_2$  in the abundant channel can act like steel to reinforce the carbon structure during repeated lithiation/delithiation. Moreover, it assists the anchoring of  $\text{VSe}_2$ . It may also help the accommodation of Li



Fig. 9 Schematic of  $VSe_2-ZrO_2/C/MXene$  for the Li-ion storage mechanism.

cluster for storage to provide extra ultra-high capacity.<sup>85,86</sup> As shown in Fig. S15,<sup>†</sup> without the participation of  $ZrO_2$  and porous carbon,  $VSe_2/MXene$  suffers during the repeated cycles, which leads to degenerative performance.

## Conclusions

To summarize, after a simple solvothermal method and *in situ* selenization,  $V_2CT_x$ -derived  $VSe_2/MXene$  was incorporated with UiO-66-derived  $ZrO_2$  and porous carbon. Due to the synergistic effect of electrochemically active  $VSe_2/MXene$ , stable  $ZrO_2$  and conductive porous carbon matrix in lithium-ion kinetics, the constructed  $VSe_2-ZrO_2/C/MXene$  composite shows an excellent reversible specific capacity of  $1238.5 \text{ mA h g}^{-1}$  at  $100 \text{ mA g}^{-1}$  with a “negative fading” behavior and a superior rate capability with a capacity retention of 143%. In addition,  $VSe_2-ZrO_2/C/MXene$  manifests a long-term cycling stability with a capacity of  $430 \text{ mA h g}^{-1}$  after 1000 cycles at  $1.0 \text{ A g}^{-1}$ . The LFP|| $VSe_2-ZrO_2/C/MXene$  full cell retains  $113.2 \text{ mA h g}^{-1}$  after 100 cycles at  $100 \text{ mA g}^{-1}$ , and remains stable even at  $500 \text{ mA g}^{-1}$ . This new attempt should guide future investigations on MOF/MXene-derived selenide electrode materials in energy storage exploration.

## Conflicts of interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

## Acknowledgements

Financial support from the Shanghai Domestic Science and Technology Cooperation Project (21015801000), the Fundamental Research Funds for the Central Universities (21621406), the Science and Technology Program of Guangzhou, China (202102020737), the Shenzhen Science and Technology Program (JCYJ20200109113606007) is gratefully acknowledged.

## Notes and references

1 Y. Li, R. Wang, Z. Guo, Z. Xiao, H. Wang, X. Luo and H. Zhang, *J. Mater. Chem. A*, 2019, 7, 25227–25246.

- J. Li, J. Yu, I. S. Amiinu, J. Zhang, J. Sheng, Z. Kou, Z. Wang, Q. Yu, L. Mai and S. Mu, *J. Mater. Chem. A*, 2017, 5, 18509–18517.
- X. Zhang, J. Li, J. Li, L. Han, T. Lu, X. Zhang, G. Zhu and L. Pan, *Chem. Eng. J.*, 2020, 385, 123394.
- Y. Zhang, J. Li, H. Li, H. Shi, Z. Gong, T. Lu and L. Pan, *J. Colloid Interface Sci.*, 2022, 607, 145–152.
- Y. Zhao, L. P. Wang, M. T. Sougrati, Z. Feng, Y. Leconte, A. Fisher, M. Srinivasan and Z. Xu, *Adv. Energy Mater.*, 2017, 7, 1601424.
- X. Cai, W. Yi, J. Chen, L. Lu, B. Sun, Y. Ni, S. A. T. Redfern, H. Wang, Z. Chen and Y. Chen, *J. Mater. Chem. A*, 2022, 10, 6551–6559.
- H. Hou, L. Shao, Y. Zhang, G. Zou, J. Chen and X. Ji, *Adv. Sci.*, 2017, 4, 1600243.
- F. Wang, B. Wang, J. Li, B. Wang, Y. Zhou, D. Wang, H. Liu and S. Dou, *ACS Nano*, 2021, 15, 2197–2218.
- Y. Zhang, X. Yuan, T. Lu, Z. Gong, L. Pan and S. Guo, *J. Colloid Interface Sci.*, 2021, 585, 347–354.
- Z. Wei, L. Wang, M. Zhuo, W. Ni, H. Wang and J. Ma, *J. Mater. Chem. A*, 2018, 6, 12185–12214.
- J. Li, W. Liu, C. Chen, X. Zhao, Z. Qiu, H. Xu, F. Sheng, Q. Hu, Y. Zheng, M. Lin, S. J. Pennycook, C. Su and J. Lu, *J. Mater. Chem. A*, 2019, 7, 23958–23963.
- X. Hu, X. Liu, K. Chen, G. Wang and H. Wang, *J. Mater. Chem. A*, 2019, 7, 11016–11037.
- S.-K. Park, J. K. Kim and Y. C. Kang, *Chem. Eng. J.*, 2017, 328, 546–555.
- P. Ge, C. Zhang, H. Hou, B. Wu, L. Zhou, S. Li, T. Wu, J. Hu, L. Mai and X. Ji, *Nano Energy*, 2018, 48, 617–629.
- J. Xiao, H. Liu, J. Huang, Y. Lu and L. Zhang, *Appl. Surf. Sci.*, 2020, 526, 146746.
- L. Zhu, Z. Wang, L. Wang, L. Xie, J. Li and X. Cao, *Chem. Eng. J.*, 2019, 364, 503–513.
- C. Yang, J. Feng, F. Lv, J. Zhou, C. Lin, K. Wang, Y. Zhang, Y. Yang, W. Wang, J. Li and S. Guo, *Adv. Mater.*, 2018, 30, 1800036.
- Z. Zhang, J. Niu, P. Yang, Y. Gong, Q. Ji, J. Shi, Q. Fang, S. Jiang, H. Li, X. Zhou, L. Gu, X. Wu and Y. Zhang, *Adv. Mater.*, 2017, 29, 1702359.
- F. Ming, H. Liang, Y. Lei, W. Zhang and H. N. Alshareef, *Nano Energy*, 2018, 53, 11–16.
- Y. Wang, B. Qian, H. Li, L. Liu, L. Chen and H. Jiang, *Mater. Lett.*, 2015, 141, 35–38.
- J. Li, D. Yan, S. Hou, Y. Li, T. Lu, Y. Yao and L. Pan, *J. Mater. Chem. A*, 2018, 6, 1234–1243.
- L. Wan, Y. Tang, L. Chen, K. Wang, J. Zhang, Y. Gao, J. Y. Lee, T. Lu, X. Xu, J. Li, Y. Zheng and L. Pan, *Chem. Eng. J.*, 2021, 410, 128349.
- C. Cui, R. Dai, C. Zhang, B. Fan and X. Wang, *J. Mater. Chem. A*, 2022, 10, 15474–15484.
- A. Lipatov, M. Alhabeib, M. R. Lukatskaya, A. Boson, Y. Gogotsi and A. Sinitskii, *Adv. Electron. Mater.*, 2016, 2, 1600255.
- Y. Yu, Z. Guo, Q. Peng, J. Zhou and Z. Sun, *J. Mater. Chem. A*, 2019, 7, 12145–12153.

- 26 M. K. Aslam, Y. Niu and M. Xu, *Adv. Energy Mater.*, 2021, **11**, 2000681.
- 27 Y. Zhang, J. Li, Z. Gong, J. Xie, T. Lu and L. Pan, *J. Colloid Interface Sci.*, 2021, **587**, 489–498.
- 28 L. Wan, D. H. C. Chua, H. Sun, L. Chen, K. Wang, T. Lu and L. Pan, *J. Colloid Interface Sci.*, 2021, **588**, 147–156.
- 29 Z. Chen, X. Xu, Z. Ding, K. Wang, X. Sun, T. Lu, M. Konarova, M. Eguchi, J. G. Shapter, L. Pan and Y. Yamauchi, *Chem. Eng. J.*, 2021, **407**, 127148.
- 30 D. Sha, C. Lu, W. He, J. Ding, H. Zhang, Z. Bao, X. Cao, J. Fan, Y. Dou, L. Pan and Z. Sun, *ACS Nano*, 2022, **16**, 2711–2720.
- 31 Z. Ali, T. Zhang, M. Asif, L. Zhao, Y. Yu and Y. Hou, *Mater. Today*, 2020, **35**, 131–167.
- 32 Z. Ye, Y. Jiang, L. Li, F. Wu and R. Chen, *Adv. Mater.*, 2021, **33**, 2101204.
- 33 J. Ahn, E. K. Jang, S. Yoon, S.-J. Lee, S.-J. Sung, D.-H. Kim and K. Y. Cho, *Appl. Surf. Sci.*, 2019, **484**, 701–709.
- 34 J. Cho, Y. J. Kim, T.-J. Kim and B. Park, *Angew. Chem., Int. Ed.*, 2001, **40**, 3367–3369.
- 35 L. Yao, F. Liang, J. Jin, B. V. R. Chowdari, J. Yang and Z. Wen, *Chem. Eng. J.*, 2020, **389**, 124403.
- 36 C. Yang, D. Liu, S. Huang and W. Lei, *Energy Storage Mater.*, 2020, **28**, 393–400.
- 37 J. H. Park, H. J. Lee, J. Y. Cho, S. Jeong, H. Y. Kim, J. H. Kim, S. H. Seo, H. J. Jeong, S. Y. Jeong, G.-W. Lee and J. T. Han, *ACS Appl. Mater. Interfaces*, 2020, **12**, 1322–1329.
- 38 X.-h. Zhou, K.-m. Su, W.-m. Kang, B.-w. Cheng, Z.-h. Li and Z. Jiang, *Chem. Eng. J.*, 2020, **397**, 125271.
- 39 J. Li, L. Han, X. Zhang, H. Sun, X. Liu, T. Lu, Y. Yao and L. Pan, *Chem. Eng. J.*, 2021, **406**, 126873.
- 40 J. Li, J. Li, Z. Ding, X. Zhang, Y. Li, T. Lu, Y. Yao, W. Mai and L. Pan, *Chem. Eng. J.*, 2019, **378**, 122108.
- 41 Z. Ding, X. Xu, J. Li, Y. Li, K. Wang, T. Lu, M. S. A. Hossain, M. A. Amin, S. Zhang, L. Pan and Y. Yamauchi, *Chem. Eng. J.*, 2022, **430**, 133161.
- 42 J. Wang, H. Wang, F. Li, S. Xie, G. Xu, Y. She, M. K. H. Leung and T. Liu, *J. Mater. Chem. A*, 2019, **7**, 3024–3030.
- 43 Y. Zhang, S. Li, L. Cheng, Y. Li, X. Ren, P. Zhang, L. Sun and H. Y. Yang, *J. Mater. Chem. A*, 2021, **9**, 3388–3397.
- 44 J. Li, L. Han, X. Zhang, G. Zhu, T. Chen, T. Lu and L. Pan, *Chem. Eng. J.*, 2019, **370**, 800–809.
- 45 J. Li, D. Yan, T. Lu, Y. Yao and L. Pan, *Chem. Eng. J.*, 2017, **325**, 14–24.
- 46 Q. Cheng and X. Yu, *J. Mater. Chem. A*, 2021, **9**, 11381–11396.
- 47 K. Liu, C. Li, L. Yan, M. Fan, Y. Wu, X. Meng and T. Ma, *J. Mater. Chem. A*, 2021, **9**, 27234–27251.
- 48 T. Yang, Y. Liu, D. Yang, B. Deng, Z. Huang, C. D. Ling, H. Liu, G. Wang, Z. Guo and R. Zheng, *Energy Storage Mater.*, 2019, **17**, 374–384.
- 49 J. Jin, Y. Zheng, L. B. Kong, N. Srikanth, Q. Yan and K. Zhou, *J. Mater. Chem. A*, 2018, **6**, 15710–15717.
- 50 C. Liu, Y. Bai, W. Li, F. Yang, G. Zhang and H. Pang, *Angew. Chem., Int. Ed.*, 2022, **61**, e202116282.
- 51 F. Chen, S. Zhang, B. Ma, Y. Xiong, H. Luo, Y. Cheng, X. Li, X. Wang and R. Gong, *Chem. Eng. J.*, 2022, **431**, 134007.
- 52 H. Zou, B. He, P. Kuang, J. Yu and K. Fan, *ACS Appl. Mater. Interfaces*, 2018, **10**, 22311–22319.
- 53 Y. Jiang, G. Cheng, Y. Li, Z. He, J. Zhu, W. Meng, L. Dai and L. Wang, *Chem. Eng. J.*, 2021, **415**, 129014.
- 54 Z. Wang, S. Wang, A. Wang, X. Liu, J. Chen, Q. Zeng, L. Zhang, W. Liu and L. Zhang, *J. Mater. Chem. A*, 2018, **6**, 17227–17234.
- 55 T. Li, Y. Bai, Y. Wang, H. Xu and H. Jin, *Coord. Chem. Rev.*, 2020, **410**, 213221.
- 56 Y. Zhang, Z. Mu, J. Lai, Y. Chao, Y. Yang, P. Zhou, Y. Li, W. Yang, Z. Xia and S. Guo, *ACS Nano*, 2019, **13**, 2167–2175.
- 57 R. J. Toh, Z. Sofer and M. Pumera, *J. Mater. Chem. A*, 2016, **4**, 18322–18334.
- 58 W. Zhang, L. Zhang, P. K. J. Wong, J. Yuan, G. Vinai, P. Torelli, G. van der Laan, Y. P. Feng and A. T. S. Wee, *ACS Nano*, 2019, **13**, 8997–9004.
- 59 Y. Bai, H. Zhang, B. Xiang, X. Liang, J. Hao, C. Zhu and L. Yan, *ACS Appl. Mater. Interfaces*, 2021, **13**, 23230–23238.
- 60 Z. Liu, C. Zhang, H. Liu and L. Feng, *Appl. Catal., B*, 2020, **276**, 119165.
- 61 L. Kang, C. Huang, J. Zhang, M. Zhang, N. Zhang, S. Liu, Y. Ye, C. Luo, Z. Gong, C. Wang, X. Zhou, X. Wu and S. C. Jun, *Chem. Eng. J.*, 2020, **390**, 124643.
- 62 R. Daiyan, X. Tan, R. Chen, W. H. Saputera, H. A. Tahini, E. Lovell, Y. H. Ng, S. C. Smith, L. Dai, X. Lu and R. Amal, *ACS Energy Lett.*, 2018, **3**, 2292–2298.
- 63 G. Che, D. Wang, C. Wang, F. Yu, D. Li, N. Suzuki, C. Terashima, A. Fujishima, Y. Liu and X. Zhang, *Chem. Eng. J.*, 2020, **397**, 125381.
- 64 Z. Chen, N. Mi, L. Huang, W. Wang, C. Li, Y. Teng and C. Gu, *Sci. Total Environ.*, 2022, **808**, 152083.
- 65 R. Xue, N. Liu, L. Bao, L. Chen, Y. Su, Y. Lu, J. Dong, S. Chen and F. Wu, *J. Energy Chem.*, 2020, **50**, 378–386.
- 66 Y. Tian, Y. An and J. Feng, *ACS Appl. Mater. Interfaces*, 2019, **11**, 10004–10011.
- 67 P. Xue, Y. Zhai, N. Wang, Y. Zhang, Z. Lu, Y. Liu, Z. Bai, B. Han, G. Zou and S. Dou, *Chem. Eng. J.*, 2020, **392**, 123676.
- 68 X. Yang, S. Wang, D. Y. W. Yu and A. L. Rogach, *Nano Energy*, 2019, **58**, 392–398.
- 69 J. Li, J. Zhao, R. Tang, Q. Chen, Z. Niu, M. Li, C. Guo, J. Su and L. Zhang, *J. Power Sources*, 2020, **449**, 227517.
- 70 J. Jin, Y. Zheng, L. B. Kong, N. Srikanth, Q. Yan and K. Zhou, *J. Mater. Chem. A*, 2018, **6**, 15710–15717.
- 71 Q. Jiang, J. Wang, Y. Jiang, L. Li, X. Cao and M. Cao, *Nanoscale*, 2020, **12**, 8858–8866.
- 72 Y. Liu, Y. Fang, Z. Zhao, C. Yuan and X. W. Lou, *Adv. Energy Mater.*, 2019, **9**, 1803052.
- 73 M. Wan, R. Zeng, K. Chen, G. Liu, W. Chen, L. Wang, N. Zhang, L. Xue, W. Zhang and Y. Huang, *Energy Storage Mater.*, 2018, **10**, 114–121.
- 74 H. Ye, Y.-X. Yin, S.-F. Zhang and Y.-G. Guo, *J. Mater. Chem. A*, 2014, **2**, 13293–13298.
- 75 H. Wang, X. Wang, Q. Li, H. Li, J. Xu, X. Li, H. Zhao, Y. Tang, G. Zhao, H. Li, H. Zhao and S. Li, *ACS Appl. Mater. Interfaces*, 2018, **10**, 38862–38871.
- 76 D. Zhao, J. Qin, L. Zheng and M. Cao, *Chem. Mater.*, 2016, **28**, 4180–4190.

- 77 Q. Yi, M. Du, B. Shen, J. Ji, C. Dong, M. Xing and J. Zhang, *Sci. Bull.*, 2020, **65**, 233–242.
- 78 J. Yan, C. Gao, S. Qi, Z. Jiang, L. R. Jensen, H. Zhan, Y. Zhang and Y. Yue, *Nano Energy*, 2022, **103**, 107779.
- 79 T. Yang, M. Fang, J. Liu, D. Yang, Y. Liang, J. Zhong, Y.-J. Yuan, Y. Zhang, X. Liu, R. Zheng, K. Davey, J. Zhang and Z. Guo, *Adv. Funct. Mater.*, 2022, **32**, 2205880.
- 80 H. Sun, G. Xin, T. Hu, M. Yu, D. Shao, X. Sun and J. Lian, *Nat. Commun.*, 2014, **5**, 4526.
- 81 H. Wu, G. Yu, L. Pan, N. Liu, M. T. McDowell, Z. Bao and Y. Cui, *Nat. Commun.*, 2013, **4**, 1943.
- 82 X. Huang, H. Yu, J. Chen, Z. Lu, R. Yazami and H. H. Hng, *Adv. Mater. Technol.*, 2014, **26**, 1296–1303.
- 83 C. Huan, X. Zhao, X. Xiao, Y. Lu, S. Qi, Y. Zhan, L. Zhang and G. Xu, *J. Alloys Compd.*, 2019, **776**, 568–574.
- 84 H. Song, L. Shen, J. Wang and C. Wang, *Nano Energy*, 2017, **34**, 47–57.
- 85 F. Wang, L. Mao, X. Wei and J. Mao, *Chem. Eng. J.*, 2022, **450**, 138235.
- 86 S. Huang, J. Yang, L. Ma, J. Ding, X. Wang, C. Peng, B. Zhao, M. Cao, J. Zheng, X.-X. Zhang and J. Chen, *Adv. Sci.*, 2021, **8**, 2101584.
- 87 S. Liang, Y.-J. Cheng, J. Zhu, Y. Xia and P. Müller-Buschbaum, *Small Methods*, 2020, **4**, 2000218.
- 88 A. N. Preman, H. Lee, J. Yoo, I. T. Kim, T. Saito and S.-k. Ahn, *J. Mater. Chem. A*, 2020, **8**, 25548–25570.
- 89 W.-J. Zhang, *J. Power Sources*, 2011, **196**, 13–24.
- 90 C.-M. Park, J.-H. Kim, H. Kim and H.-J. Sohn, *Chem. Soc. Rev.*, 2010, **39**, 3115–3141.
- 91 R. Wu, D. P. Wang, X. Rui, B. Liu, K. Zhou, A. W. K. Law, Q. Yan, J. Wei and Z. Chen, *Adv. Mater.*, 2015, **27**, 3038–3044.
- 92 X. Li, J. Li, L. Ma, C. Yu, Z. Ji, L. Pan and W. Mai, *Energy Environ. Mater.*, 2022, **5**, 458–469.
- 93 M. Kim, J. F. S. Fernando, Z. Li, A. Alowasheer, A. Ashok, R. Xin, D. Martin, A. Kumar Nanjundan, D. V. Golberg, Y. Yamauchi, N. Amiralian and J. Li, *Chem. Eng. J.*, 2022, **445**, 136344.
- 94 D. Wu, Z. Yao, X. Sun, X. Liu, L. Liu, R. Zhang and C. Wang, *Chem. Eng. J.*, 2022, **429**, 132449.
- 95 A. Cabañas, J. A. Darr, E. Lester and M. Poliakoff, *J. Mater. Chem.*, 2001, **11**, 561–568.
- 96 P. Pasierb, S. Komornicki, M. Rokita and M. Rekas, *J. Mol. Struct.*, 2001, **596**, 151–156.
- 97 A. Halder, H.-H. Wang, K. C. Lau, R. S. Assary, J. Lu, S. Vajda, K. Amine and L. A. Curtiss, *ACS Energy Lett.*, 2018, **3**, 1105–1109.
- 98 Y. Yi, X. Du, Z. Zhao, Y. Liu, H. Guan, X. Liu, X. Pei, S. Zhang and D. Li, *ACS Nano*, 2022, **16**, 7772–7782.
- 99 X. Li, L. Qiao, D. Li, X. Wang, W. Xie and D. He, *J. Mater. Chem. A*, 2013, **1**, 6400–6406.
- 100 H. Kim, W. Choi, J. Yoon, J. H. Um, W. Lee, J. Kim, J. Cabana and W.-S. Yoon, *Chem. Rev.*, 2020, **120**, 6934–6976.
- 101 Y. S. Choi, W. Choi, W.-S. Yoon and J. M. Kim, *ACS Nano*, 2022, **16**, 631–642.
- 102 T. Kim, K. Ho Kim, W. Lee, W. Choi, H. Park, H. Kim, J. Yoon, Y. S. Choi, J. Lee, J. M. Kim and W.-S. Yoon, *Appl. Surf. Sci.*, 2022, **575**, 151744.
- 103 A. Ponrouch and M. R. Palacin, *J. Power Sources*, 2012, **212**, 233–246.
- 104 J. Zhu, D. Wang, D. Chen, B. Song, Y. Li, F. Liu and J. Chen, *J. Alloys Compd.*, 2020, **848**, 156593.
- 105 D. Sun, L. Zhao, Z. Xiao, K. Zhao, R. Lin, H. Song, X. Zhang, X. Ma, C. Peng, X. Huang, X. Li, J. Gao and C. Xu, *J. Energy Chem.*, 2022, **74**, 100–110.
- 106 L. Ma, Z. Li, J. Li, Y. Dai, C. Qian, Y. Zhu, H. Wang, K. N. Hui, L. Pan, M. A. Amin, Y. Yamauchi and W. Mai, *J. Mater. Chem. A*, 2021, **9**, 25445–25452.