RSC Advances



View Article Online

View Journal | View Issue

PAPER



Cite this: RSC Adv., 2017, 7, 5610

Received 3rd October 2016 Accepted 8th November 2016

DOI: 10.1039/c6ra24692c

www.rsc.org/advances

Introduction 1.

Polymorphism is the ability of a given material to exist in more than one form, that is, to have different crystal structures and properties, while maintaining the same chemical composition. Polymorphism is a key property that enables researchers to investigate different structures depending on external conditions, such as temperature, pressure, type of field (electric, magnetic, etc.), synthetic procedure, and mode and duration of the material processing, *i.e.*, the enhancement of a particular phase modification, out of all possible polymorphic phases, depends on the thermodynamic and kinetic factors. Research on the synthesis of metastable material phases has been fueled by studies where it has been found that these phases exhibit unexplored physical and chemical properties that are distinct from the properties of their thermodynamically stable counterparts.¹⁻⁵ However, these studies have been incomplete due to the propensity of the metastable phases to transform into more stable phases. In addition, the challenge to develop facile

Uncovering the metastable γ -Ag₂WO₄ phase: a joint experimental and theoretical study[†]

Roman Alvarez Roca,*^a Pablo S. Lemos,^a Lourdes Gracia,^b Juan Andrés^b and Elson Longo^a

The synthesis of metastable solid phases is a pivotal starting point for innovative materials research. Here, we report the synthesis by means of a precipitation method of the metastable cubic γ -Ag₂WO₄ phase under ambient conditions. Different experimental techniques such as X-ray diffraction (XRD) with Rietveld refinement, field emission scanning electron microscopy (FE-SEM), micro-Raman/ultravioletvisible (UV-vis) diffuse reflectance, photoluminescence spectroscopies, and differential scanning calorimetry (DSC) were employed. To complement the experimental data, the geometry, morphology, vibrational and electronic structure of γ -Ag₂WO₄ were characterized and evaluated using first-principles quantum mechanical calculations at the density functional theory (DFT) level. A theoretical model based on the Wulff construction was introduced to explain the possible crystal morphologies of the faceted crystals, which were obtained by tuning the surface chemistry of the crystals, and are related to their relative stability. Both the experimental and theoretical data revealed the presence of (100), (110), and (111) facets with low surface energies in the γ -Ag₂WO₄ crystals. When the surface energy value of the (111) surface was lowered, the experimental morphologies of the as-synthesized samples were similar to the theoretically obtained shapes. From the analysis of the experimental and calculated Raman spectra, PL emissions, and the density of states, we can assume that γ -Ag₂WO₄ is primarily formed by both distorted clusters: [WO₄] tetrahedra and, distorted in a lesser extent, [AqO₆] octahedra.

> methods for the synthesis of metastable materials remains.6,7 Thus, it would be highly desirable to investigate metastable material phases in a manner similar to that adopted for the thermodynamically stable ones, so as to put both on a comparable footing.

> Silver tungstate (Ag_2WO_4) -based materials constitute a particularly intensively researched family of inorganic compounds because of their particular crystal and electronic structures.8-12 In response to their extensive range of innovative properties and practical applications, a plethora of experimental works have been published on the synthesis and properties of Ag₂WO₄-based materials,¹³⁻²⁶ and on their applications in photocatalysis,^{17,19,20,25} catalysis,^{14,18} photoluminescence,^{9,13,15} sensors,²² and as antibacterial agents.^{21,23,26} Ag₂WO₄ exhibits stunningly complex polymorphism,²⁷ and its understanding has evoked recent interest due to both fundamental scientific and technological aspects. Apart from the orthorhombic and thermodynamically stable α -Ag₂WO₄ phase, β - and γ -phases have also been identified with hexagonal and cubic structures, respectively.27 In addition, it has been well established that these β - and γ -phases are metastable phases that can be transformed into the α -phase when heated.

> To date, different synthesis methods have been reported in the literature to obtain Ag₂WO₄ metastable phases.²⁷⁻³³ In particular, β-Ag₂WO₄ was successfully prepared by a precipitation

BΥ-NC

^aCDMF-UFSCar-Universidade Federal de São Carlos, P.O. Box 676, CEP, 13565-905 São Carlos, SP, Brazil

^bDepartment of Analytical and Physical Chemistry, University Jaume I (UJI), Castelló 12071, Spain. E-mail: andres@qfa.uji.es

[†] Electronic supplementary information (ESI) available. See DOI: 10.1039/c6ra24692c

Paper

method using a surfactant-assisted route in the presence of polymethacrylic acid (PMAA),28 acrylamide (AM),26 or polyvinylpyrrolidone (PVP).29 The transformation from the metastable β -phase to the thermodynamically stable α -phase was inhibited by the surfactant. Without the addition of any surfactants, other conditions (such as temperature and pH) can serve as inhibitors to prevent this phase transformation. For example, a metastable β -Ag₂WO₄ phase, which coexisted with a weak amount of α-phase, was obtained using a co-precipitation method at pH 4;³¹ in addition, the synthesis of pure β -Ag₂WO₄ at low temperatures has also been reported.³⁰ Recently, our research group reported the synthesis of β-Ag₂WO₄ microcrystals by simple³⁴ and drop-wise precipitation³⁵ methods. Moreover, Gupta et al. presented a new strategy for synthesizing hexagonal metastable β -Ag₂WO₄ at room temperature through the use of aliovalent Eu^{3+} dopants (to induced the orthorhombic (α -Ag₂WO₄) to hexagonal (β -Ag₂WO₄) phase transition) along with the coprecipitation method.³⁶ Less is known about the Y-Ag₂WO₄ phase due to its scarcity and complex synthesis, and practically no attempt has been reported regarding the formation of a pure,metastable γ -Ag₂WO₄.^{27,32,33} Thus, the transfer of all the preceding experiments to the corresponding cubic phase is most rewarding with respect to elucidating the common properties and differences between the α - and β -Ag₂WO₄ modifications.

The simultaneous use of theoretical calculations alongside experiments has been a significant aid for the interpretation and assignment of complex spectra. This combination has previously been applied to the investigation of complex materials such as β -Ag₂WO₄,³⁵ Ag₂CrO₄,³⁷ and Ag₄V₂O₇ (ref. 38) crystals. To the best of our knowledge, combination of theoretical and experimental studies on the structure of γ -Ag₂WO₄ crystals is inexistent. This encouraged us to investigate the geometry, cluster coordination, and electronic structure of γ -Ag₂WO₄ crystals.

Herein, for the first time, the facile synthesis and characterization of the metastable cubic γ -Ag₂WO₄ phase is reported. Different experimental techniques such as X-ray diffraction (XRD) with Rietveld refinement, field emission scanning electron microscopy (FE-SEM), micro-Raman/ultraviolet-visible (UV-vis) diffuse reflectance, photoluminescence (PL) spectroscopies, and differential scanning calorimetry have been employed. In addition, the geometry, electronic structure, morphology, and optical properties of the γ -Ag₂WO₄ phase were investigated with firstprinciples quantum mechanical calculations at the density functional theory (DFT) level, and the theoretical results were compared with the experimental data. The calculations helped us to interpret and understand the physical mechanisms that drive the experimental results. The remainder of this paper is organized as follows: Section 2 describes the experimental procedure and computational details; Section 3 contains the results and discussion; and Section 4 provides a summary of this study and the concluding remarks.

2. Experimental

2.1 Material synthesis

High-purity silver nitrate (AgNO₃; 99.8% purity, Sigma-Aldrich) and sodium tungstate (Na₂WO₄ \cdot 2H₂O; 99.0% purity, Sigma-

Aldrich) were obtained from commercial sources and used as received. The γ -Ag₂WO₄ phase was obtained by simultaneous addition of 1.13 g (6.66 mmol) of AgNO₃ and 1.10 g (3.33 mmol) of Na₂WO₄ · 2H₂O in 20 mL of deionized water. The reaction was performed under low temperature conditions (0–5 °C) and under continuous stirring. In order to have a better understanding of the process of formation of the γ -Ag₂WO₄ particles, the reaction progress was checked in two moments: one portion was extracted of the reaction after 10 min and then the precipitate was collected; and the second portion was allowed to react for another 10 min, for a total 20 min reaction time. Subsequently, the two portions were washed several times with acetone and dried at 50 °C.

2.2 Characterization

In order to determine the crystal phase, X-ray diffraction (XRD) measurements were carried out using a D/max-2000/PC X-ray powder diffractometer (Rigaku) with Cu Ka radiation at a scanning speed of 2° min⁻¹. The XRD accelerating voltage and emission current were 40 kV and 30 mA, respectively. The microstructure and surface characteristics were investigated using an FE-SEM Inspect F50 (FEI Company, Hillsboro, OR) apparatus operated at 10 kV. High-resolution Raman spectra were recorded with a He-Ne laser at 632.81 nm (model CCD DU420AOE325) operating at 25-1000 cm⁻¹, keeping its maximum output power at 6 mW. The transformation of the material during its heat treatment was studied by differential scanning calorimetry (DSC) using an STA 409/429 Netzsch instrument at a rate of 10 °C min⁻¹ from 25 to 700 °C. UV-vis diffuse reflectance spectra measurements were carried out using a Varian spectrophotometer (model Cary 5G) at the 100-800 nm wavelength analysis range. Photoluminescence emission spectra were recorded on a Monospec 27 monochromator (Thermal Jarrel Ash) coupled to an R446 (Hamamatsu Photonics) photomultiplier, and a krypton-ion laser (Coherent Innova 90K; $\lambda = 350$ nm), over a wavelength range of 350– 850 nm.

2.3 Computational details

Calculations on the periodic γ -Ag₂WO₄ structure were performed with the CRYSTAL14 software package.39 For the calculations, tungsten was described by a large-core ECP, derived by Hay and Wadt, and modified by Cora et al.,40 while the silver and oxygen centers were described using HAYWSC-311d31G and O (6-31d1G) basis sets, respectively, which were taken from the Crystal website.41 The screened-Coulomb HSE06 (ref. 42 and 43) range-separated hybrid functional was used to obtain accurate band gaps of the computed structures. The diagonalization of the Fock matrix was performed at adequate kpoint grids in the reciprocal space. The thresholds controlling the accuracy of the Coulomb and exchange integrals calculations were set to 10^{-8} and 10^{-14} , and the mixing percent of the Fock/Kohn-Sham matrices was set to 40% (IPMIX keyword).39 The band structure and the density of states (DOS) projected on the atoms and orbitals of bulk \gamma-Ag2WO4 were constructed along the appropriate high-symmetry directions of the

corresponding irreducible Brillouin zone. To confirm the character of local minima on the potential energy of the surfaces, vibrational frequency calculations were carried out to ensure that only positive frequencies corresponded to minima for the studied ordered and disordered structural models.

The disordered models were generated by creating Ag or W atom dislocations from their initial coordinates in the ordered and most stable structure. The following displacements were explored: (i) 0.05 to 0.20 Å in the *z*-coordinate of the Ag atom; (ii) 0.05 to 0.20 Å in the *z*-coordinate of the W atom; and (iii) 0.05 to 0.20 Å in the *z*-coordinate of the Ag and W atoms. These displacements were considered for 25% and 50% of all Ag or W atoms.

Stoichiometric slabs for the (100), (110) and (111) surfaces of the cubic γ -Ag₂WO₄ structure were modeled, and the surface energy value, E_{surf} , which is defined as the energy per unit area required to form the surface relative to the bulk, was calculated as follows:

$$E_{\rm surf} = \frac{E_{\rm slab} - nE_{\rm bulk}}{2A} \tag{1}$$

where E_{slab} is the total energy of the 2D slab, nE_{bulk} is the energy of the corresponding amount of bulk Ag₂WO₄ units, and *A* represents the surface area, which is created on each side of the 2D slab and is repeated periodically. After the corresponding thickness optimization process and convergence tests, slab models consisting of four molecular units were obtained for the (100) and (111) surfaces, while six molecular units were used for the (110) surface. In addition, different slab terminations have been taken into account in order to find the E_{surf} values.

The equilibrium shape of a crystal can be calculated using the classic Wulff construction, which minimizes the total surface free energy at a fixed volume, and provides a simple relationship between the E_{surf} of the (*hkl*) plane and its distance in the normal direction from the center of the crystallite. This strategy can be used to correlate the theoretical and experimental morphologies for α and β phases of Ag₂WO₄ system.^{44,45}

3. Results and discussion

3.1 XRD

The X-ray diffraction pattern of the Ag₂WO₄ sample is shown in Fig. 1. From the analysis of the peak positions and their relative intensities, we confirmed that the as-synthetized samples, with a lattice parameter of a = 9.335 Å, were consistent with the standard powder diffraction pattern of γ -Ag₂WO₄ (JCPDS file no. 861157). This lattice parameter value is in agreement with those of other isomorphous spinel compounds such as Na₂WO₄ with a = 9.13 Å,³² Ag₂MOO₄ with a = 9.26 Å (ref. 46) and a = 9.25 Å,⁴⁷ Na₂MOO₄ with a = 9.108 Å,⁴⁸ and Ag₂WO₄ with a = 9.35 Å.²⁷ To confirm the γ -Ag₂WO₄ structure, the d_{hkl} and the respective relative intensity for the associate peak were compared with other reported data from similar structures as shown in Table S1 of the (ESI†).

The theoretical calculations of γ -Ag₂WO₄ yielded a lattice parameter of 9.3045 Å, which is in agreement with the experimental value obtained, and a simple fully cubic symmetry. The



Fig. 1 XRD pattern of γ -Ag₂WO₄ with its respective Miller index.

conventional cell for this spinel structure contains 8 formula units where the W atoms occupy the tetrahedral 8a sites, the Ag atoms reside at the octahedral 16d position, and the O atoms stay at the 32e positions in the $Fd\bar{3}m$ space group, as depicted in Fig. 2. As reported by our group for α - and β -phases, the [AgO_y] and [WO_z] clusters are the common building blocks in the polyhedral representation of each unit cell.^{9,15,34,45} However, difference between *y* and *z* subscripts are revealed for each structure.

3.2 FE-SEM

Different magnification FE-SEM micrographs of samples with synthesis times of 10 and 20 min are shown in Fig. 3, where the morphological evolution of the γ -Ag₂WO₄ particles can be seen. The images display a broad grain size distribution, at around 2–4 μ m, and nearly spherical shapes. For the reaction time of 10 min, some small nanocrystals with a cuboid structure are visible on the large microcrystal surfaces that have not diffused into the interior. The samples corresponding to 20 min reaction time had the most microparticles with irregular or approximately spherical structures, although some faceted particles can be observed. Furthermore, a decrease in the number of



Fig. 2 A polyhedral representation of the γ -Ag₂WO₄ unit cell. Depicted are the local coordination of the Ag and W atoms corresponding to the octahedral [AgO₆] and tetrahedral [WO₄] clusters, respectively.



Fig. 3 FE-SEM micrographs at different magnifications for the different times of synthesis.

nanoparticles on the surface can be perceived. These nanoparticles are observed to be rod-shaped. Although our group had previously reported this rod-like morphology in the α -Ag₂WO₄ phase,^{9,12,15} traces of this phase were not detected for the experimental techniques used in this work. For both reaction times, the presence of nanoparticles on the surface of the microparticles can be explained by the incomplete diffusion of these small particles into the larger γ -Ag₂WO₄ particles. This behavior suggests that an Ostwald-ripening mechanism takes place, where, when the growth kinetics are fast, bigger crystals grow at the expense of smaller nanocrystals.

To shed light on the morphology of the γ -Ag₂WO₄ phase, a theoretical analysis was performed. According to the theoretical calculations, the order of stability of the γ -Ag₂WO₄ surfaces is (110) < (100) < (111). Slab models with thickness of 9.1 Å, 9.6 Å and 9.3 Å were constructed for the (100), (110) and



Fig. 4 Slab models constructed for (a) (100), (b) (110) and (c) (111) surfaces.

(111) surfaces, respectively. These surfaces are depicted in Fig. 4, where the most exposed Ag atoms in all surfaces are three-coordinated. The most exposed W atoms form $[WO_4]$

clusters as in the bulk. Other non-symmetric slab models constructed for the (100), (110) and (111) surfaces are presented in Fig. S1 of ESI,† which present lower stability.



Fig. 5 (a) Theoretical morphology map for γ -Ag₂WO₄ crystals (the surface energy units are given in J m⁻²) and (b) experimental FE-SEM images of faceted γ -Ag₂WO₄ microcrystals. The computationally simulated crystal shapes are included for comparison purposes.

Paper

From the Wulff construction, it is derived that the surfaces with the lowest surface energies control the crystal morphology.⁴⁹ The ideal morphology of γ -Ag₂WO₄ is a cube dominated by the surface (100). However, it is possible to modify this ideal morphology by tuning the surface energies of the different facets using the Wulff construction.⁴⁹⁻⁵¹ An analysis of the theoretical results showed that when the relative stability of the facets changes (increases or decreases), more than one type of facet will appear in the resulting morphology. We followed a model recently developed by our research group,44,45 based on the Wulff construction, which can be used to explicitly predict the evolution of morphologies in different environments. The map of the crystal morphologies is displayed in Fig. 5a. The analysis of the theoretical results indicates that the most stable surface is the (110) followed by the (100), which form the ideal morphology (shown in the upper part of Fig. 5a). When the relative stability of the (110) and (100) facets decreased, more than one type of facet appeared in the resulting morphology. A rhombic dodecahedron (picture 1.1 of Fig. 5a) was obtained from the ideal morphology passing through picture 1, as the surface energy of the (110) facet decreased to 0.88 J m⁻²; while a cube was produced when the surface energy of the (100) facet decreased to 0.82 J m^{-2} (see morphology 2.1). When the surface energy of the (111) facet decreased to 1.30 J m⁻², morphology 3 was obtained, and a subsequent decrease in the surface energy value for the (111) facet rendered the 3.1, 3.2 and 3.3 morphologies (see Fig. 5a). Finally, an octahedron was achieved when the surface energy of the (111) facet decreased to 0.72 J m^{-2} (morphology 4). The experimental FE-SEM image displayed in Fig. 5b was the best well-faceted sighting to use for comparison. A good agreement between the experimental and theoretical morphologies was obtained when the surface energy values of the (111) facet was 1.20 or 1.15 J m⁻². These surface energy values generated 3.1 or 3.2 morphologies, respectively. In the neck region: the particle diverted from the suggested theoretical morphology due to the neck formed with other particles. Thus, variations in the ratio between surface energy values affect the related morphologies, and can be used to obtain correlations with the experimental results. We have reported well-faceted rod-like elongated particles as typical morphology for α - and β -Ag₂WO₄ microcrystals. For these two polymorphs, a narrow range of values, between 0.2–1.4 J $\mathrm{m^{-2}}$ and 0.08–1.16 J m⁻², for α -⁵² and β -,⁴⁵ respectively, were calculated for the surface energy values. In comparison, the present work displays: (i) bigger values, 1.17-1.96 J m⁻²; and (ii) not-faceted shape for γ -Ag₂WO₄. A possible relationship between value and range of surface energy with the metastability is under review for future works.

3.3 Differential scanning calorimetry

The γ -Ag₂WO₄ thermograms are shown in Fig. 6. The DSC curve clearly shows three processes. At lower temperatures, the exothermic peak at 184 °C is linked to the γ - α phase transition. Two endothermic peaks at higher temperatures can be observed, abroad peak at 500 °C and a sharp peak at 603 °C, which can be associated to the probable decomposition of the Ag₂WO₄ and a melting process, respectively. Only the last process is reversible.

View Article Online RSC Advances



Fig. 6 DSC curves of γ -Ag₂WO₄.

3.4 Raman spectra

Raman spectroscopy is one of the most suitable methods for investigating and characterizing the structure and symmetry of solids, particularly the degree of short-range structural order, and it also provides the degree of structural order–disorder in bonds between atoms in the materials.⁵³ Fig. 7a shows the



Fig. 7 (a) The micro-Raman spectra of γ -Ag₂WO₄, the inset shows the wavelength range at a lower intensity band. (b) Theoretical stretching modes in the 580–940 cm⁻¹ range related to the structural rearrangement provoked by the displacement of 50% of the W atoms.

Raman spectra of γ -Ag₂WO₄ crystals, where 10 active modes are observed. An analysis of the results rendered the presence of an intense absorption band at 912 cm⁻¹, which did not appear in the other Ag₂WO₄ phases, as well as active modes at around 880 and 853 cm⁻¹. These bands, as well as others with lower intensities at 658 and 530 cm⁻¹, can be assigned to the W–O stretching bonds, and are usually present in any tungstate sample. Torsional motions of the [WO₄] clusters appeared at 361 and 342 cm⁻¹.

In order to better understand the structural arrangement and vibrational behavior of the γ -Ag₂WO₄ crystals, computational calculations were carried out. The theoretical active Raman modes (Table S2 of the ESI†) can be organized into two groups. For the ordered structure, the first group goes to 380 cm⁻¹ and is composed of the internal vibrations of the symmetric and asymmetric bending of the tetrahedral [WO₄] clusters. In the second group, at higher frequencies, there are only two modes, which correspond to the asymmetric and symmetric stretching of the [WO₄] clusters at ~672 cm⁻¹ and ~905 cm⁻¹, respectively.

Another interesting aspect observed in the Raman spectra is the significant increase of the bandwidth modes, which suggests that some disorder was present due to the weakening of some interatomic interactions. Disorder is used here in its most general sense, namely, any perturbations that disrupt the ideal or ordered crystal. At the time, the emphasis was on the description of the disordered crystal and these disorders were considered to be perturbations. The experimentally observed absorption peaks in the 750–850 cm⁻¹ range, depending on the structural distortion related to a displacement of Ag or W atoms, can be assigned to modes obtained by theoretical calculations. This kind of behavior was also associated with a tighter arrangement of ions in the unit cell. Therefore, it is important to mention that γ -Ag₂WO₄ is formed by two groups of distorted polyhedral (octahedral [AgO₆] and tetrahedral [WO₄] clusters). Hence, we assume that tungstate groups are



Fig. 8 Comparison between the relative positions of the theoretical and experimental Raman-active modes.

partially disordered, giving rise to the large bandwidth increase observed.

From all displacements explored, we have considered those that agree well with the experimental results, such as the displacement of 50% of the 0.10 Å W atoms in the z-coordinate, as listed in Table S2.† The displacement of 50% of the W atoms generated the higher mode at 936.8 cm^{-1} corresponding to the symmetric stretching of only the distorted clusters (half of the $[WO_4]$ clusters), while the mode at 899.9 cm⁻¹ refers to the symmetric stretching of the ordered clusters. As previously mentioned, the modes that appeared at 779.2 cm^{-1} , 651.1 cm^{-1} and 589.5 cm⁻¹ are related to the asymmetric stretching of the distorted [WO₄] clusters, while the modes in the range 686-693 cm⁻¹ are associated to the asymmetric stretching of the ordered clusters. Stretching modes in the range 580–940 cm^{-1} are depicted in Fig. 7b. It is worth noting that the stretching motion of the [WO₄] clusters is not affected by the displacement of any percentage of Ag atoms, and therefore it is not appropriate to explain the observed experimental modes in the 750-850 cm⁻¹ range. The relative positions of the theoretical and experimental Raman-active modes are displayed in Fig. 8, where it can be observed that there is good agreement between the experimental and calculated. However, the calculated frequencies are slightly overestimated (except for both bending of disordered



Fig. 9 PL spectra of γ -Ag₂WO₄ microcrystals.



Fig. 10 UV-vis spectra of γ -Ag₂WO₄ metastable.



Fig. 11 Band structure and DOS projected on $\gamma\text{-}Ag_2WO_4$ atoms.

structure, A_1 mode, and stretching of both ordered, F_{2g} mode, and disordered structures, B_1 , B_2 and A_1 modes) compared to experimental data. Hence, we assume that: (i) tungstate groups are partially disordered, giving rise to the large bandwidth increase in the Raman spectra, and (ii) these disordered tungstate groups are present in larger quantities than the disordered silver groups.

3.5 PL spectra

PL emission spectra are dependent on the electronic structure of the material at hand, and they are a powerful probe for structural short and medium range order–disorder effects, such as clusters in the lattice. In Fig. 9, a prominent PL emission band is clearly seen with a maximum emission at 449 nm. This emission peak in the blue region is typically related to distorted [WO₆] octahedral in the α - and β -Ag₂WO₄ crystals.^{9,15,35,45} However, in our samples, it can be related to distorted [WO₄] tetrahedral. For the α -Ag₂WO₄ phase, another diffused emission in the red region, from 620 to 640 nm, can be attributed to the [AgO_y] clusters.^{9,15} In our samples, any red peak obtained was an indication that the [AgO₆] clusters were less prone to be distorted. This result is in agreement with the Raman spectroscopy results.

3.6 UV spectra

The determination of the optical band gap was obtained by combining Tauc's equation⁵⁴ with the method proposed by Kubelka and Munk-Aussig,⁵⁵ which is based on the transformation of diffuse-reflectance measurements, see ESI.† Tauc's equation is the following,

$$\alpha h\nu = A(h\nu - E_{\rm gap})^n \tag{2}$$

where E_{gap} is the optical energy gap, α is the optical absorption coefficient, $h\nu$ is the photon energy, A is a constant, and n is

a constant associated with different kinds of electronic transitions (n = 0.5 for a direct allowed and n = 2 for an indirect allowed). The band gap energy was estimated from the modified Kubelka–Munk equation, see ESI.† Fig. 10 shows the UV-visible diffuse reflectance spectra for γ -Ag₂WO₄. According to literature, the optical absorption spectrum in the silver tungstate family exhibits direct electronic transitions between the valence and conduction bands;^{9,13,56} therefore, in this work a n = 0.5value was used in eqn (2). The band gap energy, estimated from the intercept of the tangent to the plot, was 3.21 eV.

For the theoretical band gap, we report an indirect band gap value of 4.37 eV from Γ to W (see Fig. 11), which serves as a guide to understand band gap trends, but does not directly correspond to the physically measured quantity. The difference between the experimental and theoretical band gap values can be associated to the short and medium-range distortions on the [AgO₆] and [WO₄] clusters. An analysis of the DOS projected on the atoms renders that the conduction band (CB) is mainly attributed to W atoms, while the valence band (VB) is mainly formed by O and Ag atoms. An analysis of the DOS projected on the orbitals shows that the top of the VB is formed by the hybridization of Ag 4d and O 2p orbitals, while the bottom of the CB is mainly formed by the hybridization of W 5d and O 2p orbitals.

The value of this difference, 1.16 eV, is bigger than the difference between experimental and theoretical values reported by our group for α - and β -, ~0.40 and 0.40 eV, respectively.^{15,45,52} This agree with the suggestion that γ -Ag₂WO₄ is the polymorph more susceptible to be disordered.

4. Conclusions

The behavior of metastable phases is of substantial scientific and technological interest. The polymorphism of Ag_2WO_4 is a puzzling and important problem. In this work, metastable γ -Ag₂WO₄ crystals were prepared by the precipitation method, and an in-depth physicochemical characterization of these structures was successfully performed. The theoretical models and results, along with our experimental data, allowed us to analyze the structural, morphological, vibrational, and optical properties of the γ -Ag₂WO₄ phase.

Ordered and disordered models to describe the crystal structure are considered. Disordered [WO₄] tetrahedral clusters were key to reproduce the linewidth of the bands appearing in the Raman spectra, while a prominent PL emission band with maximum emission in the blue region was related to these distorted [WO₄] tetrahedra. In addition, it was found that Y-Ag₂WO₄ has an indirect band gap, and the calculated positions of the valence and conduction bands showed the presence of [WO₄] tetrahedral and [AgO₆] octahedral clusters. These distortions can facilitate the separation and migration of electron and hole pairs, they can improve the photocatalytic performance of γ -Ag₂WO₄, and they could be the source of the metastable character of this phase. The experimental morphologies of the as-synthesized samples are similar to the theoretically obtained shapes when the surface energy values for the (111) surface was decreased.

Finally, we point out how the combination of experimental techniques with theory is the first step to better understand the chemistry of the less-common γ -Ag₂WO₄ polymorph. Therefore, this study illustrates the potential of this joint strategy, which helps to open a promising path toward fundamental information regarding the geometry, cluster coordination, and electronic structure of γ -Ag₂WO₄ crystals. The availability of a facile method to prepare γ -Ag₂WO₄ is expected to catalyze further empirical studies on the elusive and little-studied γ -phase because of its varied potential applications.

Acknowledgements

This work was financially supported by the following Brazilian research funding institutions: Fundação de Amparo à Pesquisa do Estado de São Paulo (FAPESP; 2012/14004-5 and 2013/07296-2), Conselho Nacional de Desenvolvimento Científico e Tecnológico (CNPq; 479644/2012-8, 350711/2012-7, 304531/2013-8 and 151136/2013-0). Coordenação de Aperfeiçoamento de Pessoal de Nível Superior (CAPES). J. A. acknowledges also the financial support of the Spanish research funding projects: PrometeoII/2014/022 and ACOMP/ 2014/270 and ACOMP72015/1202 projects (Generalitat-Valenciana), Ministerio de Economia y Competitividad (CTQ2015-652017-P) and Programa de Cooperación Cientifíca con Iberoamerica (Brasil) of Ministerio de Educación (PHBP14-00020). J. A. acknowledges to Ministerio de Economia y Competitividad, "Salvador Madariaga" program, PRX15/ 00261. L. G. acknowledges Banco Santander (Becas Iberoamérica: Jóvenes profesores e investigadores). We also acknowledge the Servei Informática, Universitat Jaume I for a generous allotment of computer time.

- 1 C. C. Chen, A. B. Herhold, C. S. Johnson and A. P. Alivisatos, Size dependence of structural metastability in semiconductor nanocrystals, *Science*, 1997, **276**, 398–401.
- 2 M. Jansen, I. V. Pentin and J. C. Schoen, A Universal Representation of the States of Chemical Matter Including Metastable Configurations in Phase Diagrams, *Angew. Chem., Int. Ed.*, 2012, **51**, 132–135.
- 3 S. Shukla, S. Seal, R. Vij, S. Bandyopadhyay and Z. Rahman, Effect of nanocrystallite morphology on the metastable tetragonal phase stabilization in zirconia, *Nano Lett.*, 2002, **2**, 989–993.
- 4 U. Schubert and N. Hüsing, *Synthesis of Inorganic Materials*, Wiley-VCH Weinheim, 2012.
- 5 C. G. Levi, Metastability and microstructure evolution in the synthesis of inorganics from precursors, *Acta Mater.*, 1998, 46, 787–800.
- 6 J. F. Liu, Q. H. Li, T. H. Wang, D. P. Yu and Y. D. Li, Metastable vanadium dioxide nanobelts: Hydrothermal synthesis, electrical transport, and magnetic properties, *Angew. Chem., Int. Ed.*, 2004, **43**, 5048–5052.
- 7 J. Lu, P. F. Qi, Y. Y. Peng, Z. Y. Meng, Z. P. Yang, W. C. Yu and Y. T. Qian, Metastable MnS crystallites through solvothermal synthesis, *Chem. Mater.*, 2001, **13**, 2169–2172.
- 8 J. Andrés, L. Gracia, P. Gonzalez-Navarrete, V. M. Longo, W. Avansi Jr, D. P. Volanti, M. M. Ferrer, P. S. Lemos, F. A. L. Porta, A. C. Hernandes and E. Longo, Structural and electronic analysis of the atomic scale nucleation of Ag on α -Ag₂WO₄ induced by electron irradiation, *Sci. Rep.*, 2014, 5, 5391.
- 9 L. S. Cavalcante, M. A. P. Almeida, W. Avansi, R. L. Tranquilin, E. Longo, N. C. Batista, V. R. Mastelaro and M. S. Li, Cluster Coordination and Photoluminescence Properties of α -Ag₂WO₄ Microcrystals, *Inorg. Chem.*, 2012, **51**, 10675–10687.
- 10 X. J. Cui, S. H. Yu, L. L. Li, L. Biao, H. B. Li, M. S. Mo and X. M. Liu, Selective synthesis and characterization of single-crystal silver molybdate/tungstate nanowires by a hydrothermal process, *Chem.-Eur. J.*, 2004, **10**, 218–223.
- 11 Z. Lin, J. Li, Z. Zheng, J. Yan, P. Liu, C. Wang and G. Yang, Electronic Reconstruction of α-Ag₂WO₄ Nanorods for Visible-Light Photocatalysis, ACS Nano, 2015, 9, 7256–7265.
- 12 E. Longo, L. S. Cavalcante, D. P. Volanti, A. F. Gouveia, V. M. Longo, J. A. Varela, M. O. Orlandi and J. Andres, Direct *in situ* observation of the electron-driven synthesis of Ag filaments on α-Ag₂WO₄ crystals, *Sci. Rep.*, 2013, 3, 1676.
- 13 L. S. Cavalcante, V. M. Longo, J. C. Sczancoski, M. A. P. Almeida, A. A. Batista, J. A. Varela, M. O. Orlandi, E. Longo and M. S. Li, Electronic structure, growth mechanism and photoluminescence of CaWO₄ crystals, *CrystEngComm*, 2012, 14, 853–868.
- 14 C.-X. Guo, B. Yu, J.-N. Xie and L.-N. He, Silver tungstate: a single-component bifunctional catalyst for carboxylation of terminal alkynes with CO_2 in ambient conditions, *Green Chem.*, 2015, **17**, 474–479.

- 15 E. Longo, D. P. Volanti, V. M. Longo, L. Gracia,
 I. C. Nogueira, M. A. P. Almeida, A. N. Pinheiro,
 M. M. Ferrer, L. S. Cavalcante and J. Andres, Toward an Understanding of the Growth of Ag Filaments on α-Ag₂WO₄ and Their Photoluminescent Properties: A Combined Experimental and Theoretical Study, *J. Phys. Chem. C*, 2014, **118**, 1229–1239.
- 16 E. Longo, W. Avansi Jr, J. Bettini, J. Andres and L. Gracia, *In situ* Transmission Electron Microscopy observation of Ag nanocrystal evolution by surfactant free electron-driven synthesis, *Sci. Rep.*, 2016, **6**, 21498.
- 17 J. W. Tang and J. H. Ye, Correlation of crystal structures and electronic structures and photocatalytic properties of the Wcontaining oxides, *J. Mater. Chem.*, 2005, **15**(39), 4246–4251.
- 18 M. Vafaeezadeh and M. M. Hashemi, One pot oxidative cleavage of cyclohexene to adipic acid using silver tungstate nano-rods in a Bronsted acidic ionic liquid, *RSC Adv.*, 2015, 5, 31298–31302.
- 19 J. T.-W. Wang, J. M. Ball, E. M. Barea, A. Abate, J. A. Alexander-Webber, J. Huang, M. Saliba, I. Mora-Sero, J. Bisquert, H. J. Snaith and R. J. Nicholas, Low-Temperature Processed Electron Collection Layers of Graphene/TiO₂ Nanocomposites in Thin Film Perovskite Solar Cells, *Nano Lett.*, 2013, 14, 724–730.
- 20 R. Zhang, H. Cui, X. Yang, H. Tang, H. Liu and Y. Li, Facile hydrothermal synthesis and photocatalytic activity of rodlike nanosized silver tungstate, *Micro Nano Lett.*, 2012, 7, 1285–1288.
- 21 X. Sang, P. Wang, L. Ai, Y. Li and J. Bu, Preparation of fine Ag₂WO₄ antibacterial powders and its application in the sanitary ceramics, *Adv. Mater. Res.*, 2011, **284–286**, 1321–1325.
- 22 L. F. da Silva, A. C. Catto, W. Avansi Jr, L. S. Cavalcante, J. Andres, K. Aguir, V. R. Mastelaro and E. Longo, A novel ozone gas sensor based on one-dimensional (1D) α -Ag₂WO₄ nanostructures, *Nanoscale*, 2014, **6**, 4058–4062.
- 23 V. M. Longo, C. C. De Foggi, M. M. Ferrer, A. F. Gouveia, R. S. Andre, W. Avansi, C. E. Vergani, A. L. Machado, J. Andres, L. S. Cavalcante, A. C. Hernandes and E. Longo, Potentiated Electron Transference in α -Ag₂WO₄ Microcrystals with Ag Nanofilaments as Microbial Agent, *J. Phys. Chem. A*, 2014, **118**, 5769–5778.
- 24 W. d. S. Pereira, J. Andres, L. Gracia, M. A. San-Miguel, E. Z. da Silva, E. Longo and V. M. Longo, Elucidating the real-time Ag nanoparticle growth on α -Ag₂WO₄ during electron beam irradiation: experimental evidence and theoretical insights, *Phys. Chem. Chem. Phys.*, 2015, **17**, 5352–5359.
- 25 D. Xu, B. Cheng, J. Zhang, W. Wang, J. Yu and W. Ho, Photocatalytic activity of Ag_2MO_4 (M = Cr, Mo, W) photocatalysts, *J. Mater. Chem. A*, 2015, **3**, 20153–20166.
- 26 X.-Y. Zhang, J.-D. Wang, J.-K. Liu, X.-H. Yang and Y. Lu, Construction of silver tungstate multilevel sphere clusters by controlling the energy distribution on the crystal surface, *CrystEngComm*, 2015, **17**, 1129–1138.

- 27 A. J. van den Berg and C. A. H. Juffermans, The polymorphism of silver tungstate Ag₂WO₄, *J. Appl. Crystallogr.*, 1982, **15**, 114–116.
- 28 X. Wang, C. Fu, P. Wang, H. Yu and J. Yu, Hierarchically porous metastable beta-Ag₂WO₄ hollow nanospheres: controlled synthesis and high photocatalytic activity, *Nanotechnology*, 2013, 24, 165602–165609.
- 29 J. Li, C. Yu, C. Zheng, A. Etogo, Y. Xie, Y. Zhong and Y. Hu, Facile formation of Ag_2WO_4/AgX (X = Cl, Br, I) hybrid nanorods with enhanced visible-light-driven photoelectrochemical properties, *Mater. Res. Bull.*, 2015, **61**, 315–320.
- 30 H. Chen and Y. Xu, Photoactivity and stability of Ag₂WO₄ for organic degradation in aqueous suspensions, *Appl. Surf. Sci.*, 2014, **319**, 319–323.
- 31 Y. V. B. De Santana, J. E. C. Gomes, L. Matos, G. H. Cruvinel,
 A. Perrin, C. Perrin, J. Andres, J. A. Varela and E. Longo,
 Silver Molybdate and Silver Tungstate Nanocomposites
 with Enhanced Photoluminescence, *Nanomater. Nanotechnol.*, 2014, 4, 1–10.
- 32 P. H. Bottelberghs, E. Everts and G. H. J. Broers, Phase-Diagram and High Ionic-Conductivity of System Na₂WO₄-Ag₂WO₄, *Mater. Res. Bull.*, 1976, **11**, 263–268.
- 33 T. Takahashi, S. Ikeda and O. Yamamoto, Solid-State Ionics New High Ionic Conductivity Solid Electrolyte Ag₆I₄WO₄ and Use of This Compound in a Solid-Electrolyte Cell, *J. Electrochem. Soc.*, 1973, **120**, 647–651.
- 34 R. A. Roca, P. S. Lemos, J. Andrés and E. Longo, Formation of Ag nanoparticles on metastable β -Ag₂WO₄ microcrystals induced by electron irradiation, *Chem. Phys. Lett.*, 2016, **644**, 68–72.
- 35 P. S. Lemos, A. Altomare, A. F. Gouveia, I. C. Nogueira, L. Gracia, R. Llusar, J. Andrés, E. Longo and L. S. Cavalcante, Synthesis and characterization of metastable β-Ag₂WO₄: an experimental and theoretical approach, *Dalton Trans.*, 2016, **45**, 1185–1191.
- 36 S. K. Gupta, K. Sudarshan, P. S. Ghosh, S. Mukherjee and R. M. Kadam, Doping Induced Room Temperature Stabilization of Metastable β -Ag₂WO₄ and Origin of Visible Emission in α and β -Ag₂WO₄: Low Temperature Photoluminescence Studies, *J. Phys. Chem. C*, 2016, **120**, 7265–7276.
- 37 G. S. Silva, M. T. Fabbro, L. Gracia, L. P. S. d. Santos,
 J. Andrés, E. Condorcillo, H. Beltrán-Mir and E. Longo,
 Theoretical and Experimental Insight on Ag₂CrO₄
 Microcrystals: Synthesis, Characterization and
 Photoluminescence Properties, *Inorg. Chem.*, 2016, 55, 8961–8970.
- 38 R. C. d. Oliveira, L. Gracia, M. Assis, M. S. Li, J. Andrés, E. Longo and L. S. Cavalcante, Disclosing the electronic structure and optical properties of Ag₄V₂O₇ crystals: Experimental and theoretical Insights, *CrystEngComm*, 2016, 18, 6303–6326.
- 39 R. Dovesi, V. R. Saunders, C. Roetti, R. Orlando,C. M. Zicovich-Wilson, F. Pascale, B. Civalleri, K. Doll,N. M. Harrison, I. J. Bush, P. D'Arco, M. Llunel, M. Causà

Paper

and Y. Noël, *CRYSTAL14 User's Manual*, Theoretical Chemistry Group: University of Turin, Italy, 2014.

- 40 F. Cora, A. Patel, N. M. Harrison, R. Dovesi and C. R. A. Catlow, An *ab initio* Hartree–Fock study of the cubic and tetragonal phases of bulk tungsten trioxide, *J. Am. Chem. Soc.*, 1996, **118**, 12174–12182.
- 41 Crystal, http://www.crystal.unito.it/basis-sets.php.
- 42 J. Heyd, G. E. Scuseria and M. Ernzerhof, Hybrid functionals based on a screened Coulomb potential, *J. Chem. Phys.*, 2003, **118**, 8207–8215.
- 43 A. V. Krukau, O. A. Vydrov, A. F. Izmaylov and G. E. Scuseria, Influence of the exchange screening parameter on the performance of screened hybrid functionals, *J. Chem. Phys.*, 2006, **125**, 224106.
- 44 J. Andrés, L. Gracia, A. F. Gouveia, M. M. Ferrer and E. Longo, Effects of surface stability on the morphological transformation of metals and metal oxides as investigated by first-principles calculations, *Nanotechnology*, 2015, **26**, 405703–405713.
- 45 R. A. Roca, A. F. Gouveia, P. S. Lemos, L. Gracia, J. Andrés and E. Longo, Formation of Ag Nanoparticles on β-Ag₂WO₄ through Electron Beam Irradiation: A Synergetic Computational and Experimental Study, *Inorg. Chem.*, 2016, **55**, 8661–8671.
- 46 J. Donohue and W. Shand, The Determination of the Interatomic Distances in Silver Molybdate, Ag₂MoO₄, J. Am. Chem. Soc., 1947, 69, 222–223.
- 47 L. Cheng, Q. Shao, M. Shao, X. Wei and Z. Wu, Photoswitches of One-Dimensional Ag_2MO_4 (M = Cr, Mo, and W), *J. Phys. Chem. C*, 2009, **113**, 1764–1768.

- 48 K. G. Bramnik and H. Ehrenberg, Study of the Na₂O–MoO₃ system. Na₆Mo₁₁O₃₆ a new oxide with anatase-related structure, and the crystal structures of Na₂MoO₄, *Z. Anorg. Allg. Chem.*, 2004, **630**, 1336–1341.
- 49 G. Wulff, On the question of speed of growth and dissolution of crystal surfaces, *Z. Kristallogr.*, 1901, **34**, 449–530.
- 50 J. W. Gibbs, On the equilibrium of heterogeneous substances, *Trans. Conn. Acad. Arts Sci.*, 1878, **3**, 343–524.
- 51 C. Herring, Some Theorems on the Free Energies of Crystal Surfaces, *Phys. Rev.*, 1951, **82**, 87–93.
- 52 R. A. Roca, J. C. Sczancoski, I. C. Nogueira, M. T. Fabbro, H. C. Alves, L. Gracia, L. P. S. Santos, C. P. de Sousa, J. Andrés, G. E. Luz Jr, E. Longo and L. S. Cavalcante, Facet-dependent photocatalytic and antibacterial properties of α -Ag₂WO₄ crystals: combining experimental data and theoretical insights, *Catal. Sci. Technol.*, 2015, 5, 4091–4105.
- 53 J. R. Ferraro, K. Nakamoto and C. W. Brown., *Introductory Raman Spectroscopy*, Academic Press, Amsterdam, 2nd edn, 2003.
- 54 J. Tauc, Optical Properties and Electronic Structure of Amorphous, *Mater. Res. Bull.*, 1968, **3**, 37–46.
- 55 P. Kubelka and F. Munk, Ein Beitrag Zur Optik Der Farbanstriche, *Z. Med. Phys.*, 1931, **12**, 593–601.
- 56 D. Y. Kim, S. H. Im and O. O. Park, Synthesis of Tetrahexahedral Gold Nanocrystals with High-Index Facets, *Cryst. Growth Des.*, 2010, **10**, 3321–3323.