# RSC Advances



# PAPER

Cite this: RSC Adv., 2017, 7, 31401

Received 21st March 2017 Accepted 12th June 2017 DOI: 10.1039/c7ra03318d rsc.li/rsc-advances

### 1. Introduction

During the coming decades the world will be challenged to replace a major part of its use of oil based feedstocks for the production of new commodity chemicals and fuels. A nonpetrochemical technology platform requires synthesis of nextgeneration as well as existing functional organic materials from sustainable intermediates. In this context, particular attention is now given to the use of renewable biomass in the chemical industry, where lignocellulosic biomass and nonedible resources have the potential to provide direct access to valuable chemicals.<sup>1-3</sup> Ideally, this would employ continuous processes, inexpensive catalysts, and preferentially allow retro fitting of existing industrial processes.

5-(Hydroxymethyl)furfural (HMF) can be obtained from carbohydrate biomass, i.e. lignocellulosic biomass, in particular from the dehydration of C-6 carbohydrates (for example p-glucose and pfructose – constituent lignocellulosic biomass monomers), using homogeneous and heterogeneous acid catalysts.<sup>4-6</sup> HMF is considered one of the most promising platform chemicals in the biorefinery, providing access to a wide range of alternative polymerbuilding blocks.<sup>7-9</sup> Among the furanic intermediates that are highly

# Towards sustainable hydrogenation of 5- (hydroxymethyl)furfural: a two-stage continuous process in aqueous media over RANEY® catalysts

Sérgio Lima[,](http://orcid.org/0000-0001-5442-4683) <sup>D</sup> David Chadwic[k](http://orcid.org/0000-0002-0110-6080) D and Klaus Hellgard[t](http://orcid.org/0000-0002-4630-1015) D<sup>\*</sup>

The hydrogenation of 5-(hydroxymethyl)furfural (HMF) to 2,5-bis(hydroxymethyl)tetrahydrofuran (DHMTHF) in aqueous media under relatively mild reaction conditions has been investigated over heterogeneous RANEY® Cu and Ni catalysts using a continuous-flow hydrogenation reactor. These RANEY® catalysts were selected following a screening of several catalysts including precious metals supported on carbon for the hydrogenation of HMF. A single-stage versus a two-stage process for the hydrogenation of HMF into DHMTHF, i.e. via 2,5-dihydroxymethylfuran (DHMF) has been evaluated. The best result with an average selectivity of 98% for DHMTHF was obtained using a two-stage process; RANEY® Cu was used as a catalyst for the highly selective hydrogenation of HMF to DHMF (92 mol%) in the first stage and this product was used without further purification for in a second-stage selective hydrogenation of DHMF into DHMTHF using RANEY® Ni as a catalyst. The influence of the HMF concentration in the feeding solution  $(1-3 \text{ wt})$ , flow rate  $(0.05-0.25 \text{ mL min}^{-1})$  and total pressure  $(20-$ 90 bar) were investigated for the first-stage hydrogenation of HMF into DHMF over RANEY® Cu. HMF was found to exert an inhibiting effect on the conversion due to strong adsorption. The RANEY® Ni catalyst used in the second stage gradually deactivated. A procedure for in situ regeneration of the partially deactivated RANEY® Ni catalyst using acetic acid washing was investigated with limited success. PAPER<br>
Concert for updates<br>
Concert in the second state of the conditional of the second interest in the s

attractive as alternative renewable polymer-building blocks are the HMF-based di-ols 2,5-dihydroxymethylfuran (DHMF) and 2,5 bis(hydroxymethyl)tetrahydrofuran (DHMTHF). DHMF is considered an analogue of  $m/p$ -benzenedimethanol, which is currently used for the production of phenolic and aromatic resins, homopolymers, polyesters and polyurethanes, and can be obtained by the selective hydrogenation of HMF, *i.e.* reductive hydrogenation of the carbonyl group (see Scheme  $1(1)$ ).<sup>10</sup> DHMTHF is considered an analogue of 1,3/1,4-cyclohexanedimethanol currently used for polyester production and can find several applications, for example as a solvent or an intermediate for pharmaceuticals production. It can be obtained by total hydrogenation of HMF shown in Scheme 1. In principle, DHMTHF can be converted to 1,6-hexanediol (1,6HD) by ring opening and hydrogenolysis or hydrodeoxygenation, which opens a route to the industrial production of polyamines such as nylon-6.3,10,11

Several studies have been reported concerning the catalytic hydrogenation of HMF to DHMF using metal-based heterogeneous catalysts especially over various metals such as Au, Cu, Ni, Pt, Pd, Ir, Ru – for example bimetallic nickel and iron supported on carbon nanotubes catalyst or copper supported in  $\gamma$ alumina.<sup>10</sup>–<sup>22</sup> The choice of catalysts and reaction conditions governs the product distribution.<sup>10</sup>–<sup>22</sup> Various organic solvents including 1,4-dioxane, ethanol, 1-propanol or organic solvent– water biphasic mixtures such as *n*-butanol/water, THF/water or toluene/water have been used in those reported studies.<sup>10-22</sup>

Department of Chemical Engineering, Imperial College London, South Kensington Campus, London, SW7 2AZ, UK. E-mail: k.hellgardt@imperial.ac.uk; Tel: +44 (0)20 759 45577



Scheme 1 Schematic reductive hydrogenation and hydrogenolysis/hydrodeoxygenation of HMF. HMF: 5-hydroxymethylfurfural, DHMF: 2,5 dihydroxymethylfuran, 5-MF: 5-methylfurfural, DMF: dimethylfurfural, DMTHF: 2,5-dimethyltetrahydrofuran, DHMTHF: 2,5-bis(hydroxymethyl) tetrahydrofuran, 1,2,6-HT: 1,2,6-hexanetriol.

DHMF selectivities and HMF conversions higher than 96% using 1 wt% Pt on MCM-41 (Pt/MCM-41), gold sub-nano clusters supported on alumina  $(Au/Al_2O_3)$  or  $ReO_x$  modified  $SiO_2$ supported metal catalysts with iridium (Ir–ReO<sub>x</sub>/SiO<sub>2</sub>) as catalysts have been reported at temperatures between 30 and 110  $^{\circ}$ C and pressures of  $6.9$  to  $65$  bar after  $2-6$  hours using water as monophasic solvent system.<sup>18</sup>–<sup>22</sup>

A considerable number of studies have been reported for the synthesis of DHMTHF from HMF.11,22,23,23–<sup>30</sup> Due to the relatively stable furan ring, typically harsher conditions are required  $(i.e.$ higher pressure and temperatures) compared to the reduction of the aldehyde group of HMF to form DHMF.<sup>23</sup> Common materials investigated as heterogeneous catalysts include nonnoble and noble metals, especially bifunctional catalysts derived from hydrotalcite-like compounds, bimetallic catalysts supported on silica as Ni-Pd/SiO<sub>2</sub> and Pd-Ir/SiO<sub>2</sub> and RANEY®type metal catalysts (Co, Cu, Ni) and others using different monophasic organic solvents.11,17,22–26,28

RANEY®-type metals (Cu, Co and Ni) have been investigated as catalyst for total hydrogenation of HMF using 1,4-dioxane as solvent by Kong et  $al.^{25}$  Among the RANEY®-type metals, RANEY® Ni was revealed to be the most selective with a 96% DHMTHF selectivity at full conversion, at 100 $\degree$ C and 15 bar of  $H_2$  after 15 h of reaction.<sup>25</sup> RANEY® Ni has also been successfully used to catalyse the hydrogenation of HMF into DHMTHF in other solvents such as methanol or ethanol with yields higher than 95%.<sup>11,26</sup> The best result was reported by Connolly et al. using methanol as solvent, achieving 99% selectivity to DHMTHF and over 95% HMF conversion under relatively mild reaction conditions, 60 °C under 4.8 bar of  $H_2$  after 4 h of batch operation.<sup>26</sup>

All the above research has been conducted in batch reactors. To our knowledge only three papers have addressed the synthesis of DHMF or DHMTHF using heterogeneous catalytic continuous hydrogenation of HMF, although indirectly, despite the potential advantages of catalytic continuous-flow hydrogenation for large-scale industrial production compared with batch reactor processes.<sup>31-39</sup> The catalysts studied include bifunctional oxides with Brønsted or Lewis acidy such as  $\gamma$ -Al<sub>2</sub>O<sub>3</sub>, ZrO<sub>2</sub>, TiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>/SBA-15, ZrO<sub>2</sub>/SBA-15, TiO<sub>2</sub>/SBA-15, H-BEA, Sn-BEA ZrO<sub>2</sub>, and supported metals such as  $Fe<sub>2</sub>O<sub>3</sub>$ -supported Pd, and Ni, Pd, and Cu supported on  $\gamma$ -alumina.<sup>31-39</sup> Tucker et al. proposed a tandem catalytic approach to

continuous production of DHMTHF from fructose, in which fructose is first dehydrated to HMF, then HMF is hydrogenated to DHMTHF.<sup>40</sup> A certain amount of DHMTHF is recovered as product, while the remainder is recycled to serve as the cosolvent in the dehydration reaction.<sup>40</sup> However, no catalytic results were reported by the authors using a flow hydrogenation reactor.<sup>40</sup>

In this paper we report the selective catalytic synthesis of DHMTHF from HMF using a continuous hydrogenation reactor system. A single-stage process to DHMTHF and a two-stage process via the selective synthesis of the intermediate DHMF have been investigated. These studies have been performed in aqueous media at the relatively mild conditions of 90 $\degree$ C and 90 bar H<sub>2</sub>. The performance of heterogeneous RANEY® Cu and Ni catalysts has been compared with common supported precious metal catalysts. The catalysts were in the form of commercial CatCart® supplied by ThalesNano Inc. RANEY® catalysts have the advantage of being inexpensive compared to precious metal catalysts. We show that the two-stage process using RANEY® Cu in the first stage and RANEY® Ni in the second stage is the most efficient system for selective synthesis of DHMTHF from HMF at the mild conditions used. A pathway for in situ regeneration of RANEY® Ni catalyst is also proposed in this paper. PSC Advances<br>
Property on  $\frac{1}{2}$  Published on 19 June 2017. The performance of 19 June 2017. The performance of the state of th

### 2. Experimental section

5-(Hydroxymethyl)furfural was purchased from Sigma-Aldrich and used as received without further purification. For the catalytic reactions a fixed-bed bench-top continuous-flow hydrogenation reactor, H-CUBE® model HC 2, developed by ThalesNano Inc. (Budapest, Hungary) was used.35,36 Commercial pre-packed heterogeneous catalyst cartridges (CatCat®) of 4 mm inner diameter and 30 mm length (tubular) filled with ca. 140 mg of catalyst (particle size of  $50-400 \mu m$ ) were used. The general protocol was as follows: the CatCart® was placed vertically in the H-Cube system cartridge holder and rinsed with degassed, deionised water followed by activation by pretreatment with water saturated with hydrogen through the CatCart® by an HPLC-pump (flow rate of 0.25 mL min $^{-1}$ ) for 30 min at the selected temperature and pressure, usually 90 bar. The catalytic reaction was performed by feeding a continuous flow of the substrate solution saturated with hydrogen. The performance of the selected CatCart® was evaluated by analysing the liquid samples collected on an hourly basis after the start of the experimental run feeding the substrate solution. Steady state was reached after 1 h of time on stream. The average conversions and product selectivities were calculated, for example over the period of 1–8 h, by averaging the point conversions and selectivities obtained from the liquid samples collected at each hour interval from 1 to 8 h time-on-stream (7 points). The product solutions were analysed by a GC (Hewlett-Packard HP 6890 series) equipped with a 30 m StabilWAX(R)-DA column (30 m length,  $0.32$  mm internal diameter, and  $0.5 \mu m$  film thickness) and a flame ionization detector (FID), injection volume 0.5 µL, inlet temperature 250 °C, detector temperature 250 °C, and a split ratio 1 : 5. The initial column temperature was 50  $\degree$ C (5 min) with a temperature rise of 10  $^{\circ}$ C min<sup>-1</sup> and final temperature was  $240^{\circ}$ C. Nitrogen was used as the carrier gas. Each peak of the GC chromatogram was properly integrated and the actual concentration of each product was obtained from a precalibrated plot of peak area against concentrations. Phenol was used as internal standard. Conversion, selectivities and yields were calculated with the following eqn (eqn  $(1)-(3)$ ):

$$
Conversion (\%) = \frac{\text{mole HMF inlet} - \text{mole HMF outlet}}{\text{mole HMF inlet}} \times 100
$$
\n(1)

$$
Selectivity (%) = \frac{mole product}{mole HMF inlet - mole HMF outlet} \times 100
$$
\n(2)

$$
Yield \text{ (%)} = \frac{\text{mole product}}{\text{mole HMF inlet}} \times 100 \tag{3}
$$

Inductively coupled plasma atomic emission spectroscopy (ICP-AES) analyses were performed using a ICP-OES spectrometer Perkin-Elmer Optima 2000 DV ICP.

### 3. Results and discussion

The reaction network for the catalytic hydrogenation of HMF is given in Scheme 1. The reactions of interest in the present study are HMF to DHMF (reaction 1) and DHMF to DHMTHF (reaction 2). The hydrogenolysis/hydrodeoxygenation of HMF to 5 methylfurfural (5-MF), and the further conversion of DMF, DHMF and DHMTHF to dimethylfurfural (DMF), 2,5-dimethyltetrahydrofuran (DMTHF) among others are herein referred to as giving rise to by-products.

The present catalytic hydrogenation results were obtained in aqueous media using heterogeneous pre-packed catalyst cartridges in a continuous-flow hydrogenation bench-top reactor (H-Cube) as noted above, where molecular hydrogen was generated *in situ* by the electrolysis of water and continuously mixed into the flowing aqueous solution of feed, for example HMF.

#### 3.1 Single-stage catalytic hydrogenation of HMF

The single-stage hydrogenation of HMF to DHMTHF was investigated using a range of commercially available cartridge

catalysts. These included precious metals supported on carbon and  $SiO<sub>2</sub>$ , heterogeneous RANEY® catalysts (Ni, Cu), and Ni/  $SiO_2$ –Al<sub>2</sub>O<sub>3</sub>, 5% Rh/Al<sub>2</sub>O<sub>3</sub> as CatCart® catalysts. The reactions were performed using aqueous solutions of 1 wt% HMF as feeding solution (feed flow rate of 0.05 mL  $min^{-1}$ ) under mild reaction condition (90 $\degree$ C, 90 bar H<sub>2</sub>) and a liquid hourly space velocity (LHSV) of 7.95  $\rm h^{-1}$ , calculated considering the internal cartridge volume  $= 3.77 \times 10^{-7}$  m<sup>3</sup>, equivalent to a mean liquid residence time for this feed flow rate of 4.16 min based on the average dead volume for 30 mm filled CatCart =  $0.208$  mL (value provided by ThalesNano). The conversion of HMF to DHMF, DHMTHF or by-products using Darco® CatCart® (carbon black) as blank at these conditions was negligible after 8 h on stream.

The average conversion and product selectivity for the studied catalysts are given in Table 1. The average conversion of HMF was in range of 70–100% for most of the catalysts, with the exception of  $Ni/SiO<sub>2</sub>-Al<sub>2</sub>O<sub>3</sub>$ , 5% Ru/C (Table 1, entry 1 and 4). In general, the catalysts investigated exhibited poor selectivity for the single-stage synthesis of DHMTHF. Average selectivity from 1–8 h on stream was less than 20% for DHMTHF, showing that these catalysts are not effective for a continuous single-stage synthesis of DHMTHF from HMF in aqueous solution under the reaction conditions investigated. The mass balance are not closed for most of catalysts investigated, except for  $Ni/SiO<sub>2</sub>-Al<sub>2</sub>O<sub>3</sub>$  and  $Rh/Al<sub>2</sub>O<sub>3</sub>$ , which can be consequence of either formation of insoluble by-products and/or because not all by-products formed were detected by the GC-FID analysis. RANEY® Ni catalyst gave a 13% average selectivity to DHMTHF which corresponded to an average productivity of 0.2 mmol $_{\text{DHMTHF}}$ .gcatalyst<sup>-1</sup> h<sup>-1</sup> after 8 h of operation. Nevertheless, RANEY® Cu as catalyst (Table 1, entry 3) showed a stable average selectivity to DHMF of 84% at and an average HMF conversion of 94%. This result suggested that a two-stage continuous process might prove attractive. Paper<br>
Secretaries are procedured on an hourly hasts after the sam of the standpath. These included precises are not<br>
standard standard standard standard standard standard standard standard in the standard standard on the

#### 3.2 Two-stages catalytic hydrogenation of HMF

3.2.1 First-stage reaction: catalytic hydrogenation of HMF into DHMF over RANEY® Cu. The hydrogenation of HMF to DHMF over the RANEY® Cu catalyst was explored in more detail with regard to use in a possible first stage. The catalyst proved to exhibit exceptional activity and selectivity toward DHMF over 24 h on stream at 90 $^{\circ}$ C and 90 bar pressure, with an average conversion of 94% and 92% selectivity, Fig. 1. The average selectivity obtained over 24 h (92%) is slightly higher than that observed over 8 h on stream (84%), mainly due to the higher consistency (*i.e.* less fluctuation) of calculated selectivities over a longer period of time on stream. The DHMF moles formed per mole of Cu (RANEY® Cu: 91 wt% Cu), *i.e.* the turnover number (TON), was low, 2.4 after 24 h of time on stream due to the low concentrations used. Operating for longer periods of time would increase product/catalyst ratio, although this depends on catalyst stability over extended periods of operation. By-products from over-hydrogenation or hydrogenolysis/hydrodeoxygenation of DHMF (e.g. DMF) were not observed using RANEY® Cu as catalyst. ICP-OES analyses of the recovered solutions after 24 h of on-stream operation showed that no measurable Cu or Al leaching occurred.

Table 1 Performance of commercial catalysts (CatCart®) in the catalytic hydrogenation reaction of HMF and selected bio-products at 90 °C and 90 bar

Entry	Catalyst	Conv. $^{b}$ (%)	Bio-products selectivity <sup>b,c</sup> (%)					
			<b>DMF</b>	5-MF	<b>DMTHF</b>	<b>DHMF</b>	<b>DHMTHF</b>	Total yield <sup><math>d</math></sup> (%)
1	$Ni/SiO2-Al2O3$	52		2(1)		93 (48)	5(3)	52
2	RANEY® Ni	100		3(3)		60(60)	13(13)	76
3	RANEY <sup>®</sup> Cu	94		9(8)		84 (79)		87
4	5% Ru/C	100		$\overline{\phantom{0}}$	4(4)	27(27)	18 (18)	49
5	4.5% Ru 0.5% Pd/C	96		4(4)	7(7)	30 (30)	6(6)	45
6	1% Pt/SiO <sub>2</sub>	69		5(3)		78 (54)		57
7	10% Pt/C	99	1(1)	10(10)	3(3)	44 (44)	1(1)	58
8	5% Pd/SiO <sub>2</sub>	100		2(2)	4(4)	17(17)	16(16)	39
9	10% Pd/C	100			21(21)		17(17)	38
10	5% $Rh/Al_2O_3$	74		5(4)	7(5)	81(60)	7(5)	74
	hour from 1 h to 8 h of time on-stream (7 points). The steady state was reached after 1 h of time on stream. <sup>c</sup> In brackets is provided the yield. $d$ Total yield was calculated as the sum of the yields for the identified by-products.			yields were calculated by averaging the moles of HMF or bio-products obtained from the GC-FID analysis of the liquid samples collected at each				
100								
80								conversions reported in Fig. 2(a) are not limited by thermody- namic equilibrium based on the temperature and pressure dependence of the thermodynamic equilibrium constant for the
							hydrogenation of HMF to DHMF as previously reported. <sup>45,46</sup>	
			$-$ HMF conversion					
60			$\sim$ DHMF selectivity					
								The influence of the flow rate on the hydrogenation of HMF at a concentration of 1 wt% was investigated in the range of 0.05-0.25 mL min <sup>-1</sup> (LHSV: 7.95-39.78 h <sup>-1</sup> ) at 90 °C and 90 bar
							by using the RANEY® Cu as catalyst (Fig. 2(b)). As the flow rate	
	40							
							increases in the range of 0.05–0.25 mL min <sup><math>-1</math></sup> the conversion of	
							HMF decreases, as expected. An excellent linear correlation $(R^2)$	
20							$= 0.99$ ) was observed, being consistent with a zero-order kinetic	
Conversion & Selectivity (mol.%)								
							regime in the concentration of HMF. In a similar way, the	
	0						hydrogenation reaction of furfural to furfuryl alcohol in the liquid-phase, was reported to be negative first-order to zero-	



Fig. 1 Conversion of HMF into DHMF over RANEY® Cu catalyst. Reaction conditions: flow rate of 0.05 mL min<sup>-1</sup>, 1 wt% HMF in water, 90 bar, 90 °C.

The effect of total pressure of the system on the HMF conversion to DHMF was investigated in range of 20–100 bar over the RANEY® Cu catalyst at 90  $^{\circ}$ C, Fig. 2(a). Each point in the plot corresponds to an average value obtained after 8 h of on-stream operation. An excellent linear correlation ( $R^2 = 0.99$ ) for the reaction activity was observed up to 70 bar (flow rate: 0.05 mL min<sup>-1</sup>, 90 °C, 1 wt% HMF), showing that the hydrogenation of HMF is strongly dependent on the hydrogen concentration up to this pressure (Fig. 2(a)), due to the limiting stoichiometric hydrogen availability up to this pressure (mole fraction of hydrogen per moles of HMF in aqueous phase  $= 0.74$ at 70 bar and 0.96 at 90 bar).<sup>41,42</sup> Similar results were reported by Tukacs et al. for the hydrogenation of levulinic acid to  $\gamma$ -valerolactone using Ru/C® and butyl-bis-(m-sulfonated-phenyl) phosphine ligand as co-catalyst in aqueous media.<sup>43</sup> The

The influence of the flow rate on the hydrogenation of HMF at a concentration of 1 wt% was investigated in the range of 0.05–0.25 mL  $\text{min}^{-1}$  (LHSV: 7.95–39.78  $\text{h}^{-1}$ ) at 90 °C and 90 bar by using the RANEY® Cu as catalyst (Fig.  $2(b)$ ). As the flow rate increases in the range of 0.05–0.25 mL  $min^{-1}$  the conversion of HMF decreases, as expected. An excellent linear correlation  $(R^2)$  $(0.99)$  was observed, being consistent with a zero-order kinetic regime in the concentration of HMF. In a similar way, the hydrogenation reaction of furfural to furfuryl alcohol in the liquid-phase, was reported to be negative first-order to zeroorder in furfural concentration (0.025–0.1 M), and close to first-order with respect to hydrogen pressure, in the temperature range of 50-90  $^{\circ}$ C.<sup>46</sup> However, closer to first-order dependence was observed with respect to both HMF and hydrogen, reported for the hydrogenation of HMF to DHMF in aqueous media in the concentration range 0.05–0.3 M and temperature range 40–70 °C, over  $Ru/C.<sup>21</sup>$ 

The influence of the HMF concentration in the feeding solution was also investigated. Fig. 2(c) shows the results for the hydrogenation of HMF to DHMF with feed concentrations in the range of 1–3 wt% (*i.e.* from 8.2 to 24.7 mM) at 90 °C and 90 bar total pressure over RANEY® Cu. As the concentration of HMF increases from 1 to 3 wt%, the conversion of HMF decreases, as expected due to strong adsorption of HMF, and matches the observed flow rate dependence. Interestingly, in the range of HMF concentrations investigated, the selectivity to DHMF (average ca. 92%) did not change significantly with the increase of the HMF concentration in the feeding aqueous solutions.

3.2.2 Second-stage reaction: catalytic hydrogenation of DHMF to DHMTHF over RANEY® Ni. RANEY® Ni as catalyst for the hydrogenation of DHMF to DHMTHF as a second stage in



Fig. 2 Effect of: (a) total pressure (flow rate: 0.050 mL min<sup>-1</sup>, 1 wt% HMF), (b) feed flow rate (pressure: 90 bar, 1 wt% HMF in water) and (c) concentration of substrate (flow rate: 0.05 mL min $^{-1}$ , pressure: 90 bar) on the HMF hydrogenation to DHMF in the presence of RANEY® Cu at 90 °C in aqueous media. Each point correspond to an average after 8 h of time on stream.

Pressure (bar)

the hydrogenation of HMF to DHMTHF has been investigated. The product aqueous solutions collected over 24 h of operation at the outlet of the reactor obtained from the experimental runs performed using RANEY® Cu as catalyst (and 1 wt% HMF aqueous solution, feeding flow rate of 0.05 mL min<sup>-1</sup> at 90 °C

and 90 bar of total pressure) were used after have been mixed, without further purification as feeding solution for the secondstage catalytic experiments over RANEY® Ni.

The RANEY® Ni catalyst exhibited exceptional selectivity toward DHMTHF, with an average selectivity of 98% and a high productivity = 19 mmol $_{\text{DHMTHF}}$ .  $g_{\text{catalyst}}^{-1}$  h<sup>-1</sup> after 15 h of operation, Fig. 3. Measurement of the amount of leaching gave 4.9 ppm of Ni and 0.023 ppm of Al in the product liquid corresponding to the total mass of Ni and Al leached after 15 h of operation of 0.18 wt% and <0.01 wt% respectively, based on the initial specified composition of RANEY® Ni alloy  $(85 \text{ wt}\%)$ Ni min., 12 wt% Al max.) and 140 mg of catalyst filled in the cartridge. Other two well-known hydrogenating catalysts, 10% Pd/C and 5% Rh/C were also investigated as catalysts for the selective hydrogenation of DHMF to DHMTHF in aqueous phase under the same operation reaction conditions (temperature, pressure and feeding flow rate). An average DHMTHF selectivity less than 5% was observed for 10% Pd/C after 8 h of time on stream and 5% Rh/C catalyst completely deactivated after 2 h (result not shown). When RANEY® Ni was used as catalyst for the single-stage conversion of HMF into DHMTHF (Table 1, entry 2) an average selectivity of only 13% was obtained after 8 h of time on stream.

The effect of hydrogen pressure on the DHMF conversion into DHMTHF was also investigated in the range of 20–90 bar using RANEY® Ni at 90  $^{\circ}$ C, Fig. 4. The hydrogenation is not limited by thermodynamic equilibrium at these conditions.<sup>44,45</sup> As can be observed, the highest catalytic performance (conversion and selectivity) for the conversion of DHMF to DHMTHF (Scheme 1(2)) was reached at the same operation pressure as the first-stage reaction, *i.e.* 90 bar, which is convenient from a process stand point.

While the selectivity did not change significantly over the operating time investigated, shown in Fig. 3, the DHMF conversion gradually decreased over time. After 32 h of operation (result not



Fig. 3 Conversion of DHMF into DHMTHF over RANEY® Ni catalyst. Reaction conditions: flow rate of 0.05 mL min<sup>-1</sup>, 90 bar, 90 °C. Feed solution: aqueous solution of DHMF (molar ratio DHMF/HMF  $= 0.92$ ) obtained from the catalytic experiment using RANEY® Cu (first-stage reaction) under the similar operation conditions.



Fig. 4 Effect of total pressure on the hydrogenation of DHMF into DHMTHF over RANEY® Ni (reaction conditions: flow rate of 0.050 mL min $^{-1}$ , 1 wt% HMF in water, 90 °C). Feed solution: aqueous solution of DHMF (molar ratio DHMF/HMF  $= 0.92$ ) from the catalytic reaction using RANEY® Cu as catalyst under similar operation conditions. Each point correspond to an average after 8 h of time on stream.

shown), the conversion decreased to ca. 71% of the initial value. Stability of catalyst performance is of extreme importance in industrial processing. From previous studies the main reasons for deactivation of RANEY®-type catalysts are considered to be: (1) loss of active Ni surface by sintering; (2) leaching of Ni and promoter metal into the acidic and chelating reaction mixture. However, the negligible Ni and Al leaching measured after 15 h of operation suggests that the observed deactivation of RANEY® Ni may not be a result of loss of metal and/or promoter species; (3) poisoning of the active Ni surface by organic species principally produced by side reactions.<sup>47</sup> Hoffer et al. showed that RANEY®-type Ni catalysts used in hydrogenation of aqueous solutions of p-glucose can be effectively regenerated by a hydrogen treatment at temperatures



Fig. 5 Conversion of DHMF into DHMTHF over RANEY® Ni in aqueous media. Comparison of DHMF conversion after the CatCart® have been regenerated/washed (after regeneration) and after the same CatCart® have been regenerated for second time (after regeneration for the second time).

higher than 120  $\degree$ C after a very severe washing procedure.<sup>47</sup> In order to recover the RANEY® Ni activity we used a procedure based on early literature reported by Hauschild et al. to perform the regeneration in situ, i.e. without unpacking the catalyst from the cartridge.<sup>48</sup> The spent RANEY® Ni cartridge was flushed in situ with a degassed, alcoholic solution of acetic acid (acetic acid in methanol/water) saturated with hydrogen (generated in situ by electrolysis of water) at a flow rate of 1 mL min<sup>-1</sup> at 40 °C and 50 bar for 2 h, followed by washing the CatCart® with deionised water saturated with hydrogen for another 3 h under the same conditions.

The activity of catalyst treated according to the above procedure was not comparable to the activity of the fresh catalyst, even after repeating the severe washing procedure two times, as shown in Fig. 5. These results show that regeneration of RANEY® Ni was achieved with only limited success. Harsher conditions than those that can be achieved in the H-Cube hydrogenation reactor, for example higher temperature under hydrogen, might be needed to effectively regenerate the Ni surface after being washed.<sup>47</sup>

### 4. Conclusions

DHMTHF was obtained efficiently from the hydrogenation of HMF in aqueous media using a continuous two-stage catalytic process *via* DHMF under relatively mild reaction conditions, 90  $^{\circ}$ C at 90 bar. An average selectivity of 98% was achieved using different nonnoble catalysts in each stage: RANEY® Cu to hydrogenate HMF to DHMF and RANEY® Ni to hydrogenate DHMF to DHMTHF under the same reaction conditions (productivity  $= 19$  mmol<sub>DHMTHF</sub>.  $g_{\text{catalyst}}^{-1}$  h<sup>-1</sup> after 15 h of operation). This approach was shown to be preferable to a single-stage process using RANEY® Ni catalyst where only 13% average selectivity to DHMTHF was obtained (average productivity = 0.2 mmol<sub>DHMTHF</sub>.g<sub>catalyst</sub><sup>-1</sup> h<sup>-1</sup> after 8 h of operation). The first-stage hydrogenation of HMF to DHMF over the RANEY® Cu catalyst proved to give stable performance, but the RANEY® Ni in the second stage gradually deactivated while maintaining high selectivity to DHMTHF. Negligible Ni and Al leaching occurred over 15 h of operation, suggesting that the observed decrease of activity over time-on-stream might be a result of either poisoning of the active Ni surface by organic species or due to irreversible oxidation of the active Ni surface species. Regeneration of the RANEY® Ni catalyst by washing the spent catalyst with an alcoholic aqueous solution of acetic acid in the presence of hydrogen had only a partial success. The conditions for the regeneration are limited by the H-Cube which would not necessarily apply to an industrial process.

The two-stage approach described here can be an important contribution to the development of sustainable catalytic routes to DHMTHF production, where continuous hydrogenation is required for large-scale production of this high value intermediate for polymer manufacture.

### Acknowledgements

This work was financially supported by EPSRC(UK) under grant EP/K014749/1.

### References

- 1 G. W. Huber, S. Iborra and A. Corma, Chem. Rev., 2006, 106(9), 4044–4098.
- 2 J. N. Chheda, G. W. Huber and J. A. Dumesic, Angew. Chem., Int. Ed., 2007, 46(38), 7164–7184.
- 3 G. Berndes and J. Hansson, Energy Policy, 2007, 35(12), 5965– 5979.
- 4 P. K. Rout, A. D. Nannaware, O. Prakash, A. Kalra and R. Rajasekharan, Chem. Eng. Sci., 2016, 142, 318–346.
- 5 A. Chinnappan, C. Baskar and H. Kim, RSC Adv., 2016, 6, 63991–64002.
- 6 I. Agirrezabal-Telleria, I. Gandarias and P. L. Arias, Catal. Today, 2014, 234, 42–58.
- 7 L. Hu, G. Zhao, W. Hao, X. Tang, Y. Sun, L. Lin and S. Liu, RSC Adv., 2012, 2, 11184–11206.
- 8 K. Yan and A. Chen, Fuel, 2014, 115, 101–108.
- 9 Y. Román-Leshkov, J. N. Chheda and J. A. Dumesic, Science, 2006, 321, 1933–1938.
- 10 I. Delidovich, P. J. C. Hausoul, L. Deng, R. Pfützenreuter, M. Rose and R. Palkovits, Chem. Rev., 2016, 116, 1540–1599.
- 11 T. Buntara, S. Noel, P. H. Phua, I. Melián-Cabrera, J. G. de Vries and H. J. Heeres, Angew. Chem., Int. Ed., 2011, 50, 7083–7087.
- 12 Y. Zhu, X. Kong, H. Zheng, G. Ding, Y. Zhu and Y.-W. Li, Catal. Sci. Technol., 2015, 5, 4208–4217.
- 13 G. C. A. Luijkx, N. P. M. Huck, F. van Rantwijk, L. Maat and H. van Bekkum, Heterocycles, 2009, 77, 1037–1044.
- 14 A. J. Kumalaputri, G. Bottari, P. M. Erne, H. J. Heeres and K. Barta, ChemSusChem, 2014, 7, 2266–2275.
- 15 L. Yu, L. He, J. Chen, J. Zheng, L. Ye, H. Lin and Y. Yuan, ChemCatChem, 2015, 7, 1701–1707.
- 16 Y. Liu, M. A. Mellmer, D. M. Alonso and J. A. Dumesic, ChemSusChem, 2015, 8, 3983–3986.
- 17 R. Alamillo, M. Tucker, M. Chia, Y. Pagán-Torres and J. A. Dumesic, Green Chem., 2012, 14, 1413–1419.
- 18 M. Chatterjee, T. Ishizaka and H. Kawanami, Green Chem., 2014, 16, 4734–4739.
- 19 M. Tamura, K. Tokonami, Y. Nakagawa and K. Tomishige, Chem. Commun., 2013, 49, 7034–7036.
- 20 J. Ohyama, A. Esaki, Y. Yamamoto, S. Arai and A. Satsuma, RSC Adv., 2013, 2, 1033–1036.
- 21 A. B. Jain and P. D. Vaidya, Int. J. Chem. Kinet., 2016, 48, 318– 328.
- 22 A. J. Sanborn and P. D. Bloom, US Pat. number 7393963 B2, 2008.
- 23 K. Weissermel and H.-J. Arpe, Industrielle Organische Chemie, VCH, Weinheim, 4th edn, 1994.
- 24 X. Kong, R. Zheng, Y. Zhu, G. Ding, Y. Zhu and Y.-W. Li, Green Chem., 2015, 17, 2504–2515.
- 25 X. Kong, Y. Zhu, H. Zheng, F. Dong, Y. Zhu and Y.-W. Li, RSC Adv., 2014, 4, 60467–60472.
- 26 T. J. Connolly, J. L. Considine, Z. Ding, B. Fordatz, M. N. Jennings, M. F. MacEwan, K. M. McCoy, D. W. Place,

A. Sharma and K. Sutherland, Org. Process Res. Dev., 2010, 14, 459–465.

- 27 J. Chen, R. Liu, Y. Guo, L. Chen and H. Gao, ACS Catal., 2015, 5, 722–733.
- 28 S. Yao, X. Wang, Y. Jiang, F. Wu, X. Chen and X. Mu, ACS Sustainable Chem. Eng., 2014, 2, 173–180.
- 29 Y. Nakagawa and K. Tomishige, Catal. Commun., 2010, 12, 154–156.
- 30 Y. Nakagawa, K. Takada, M. Tamura and K. Tomishige, ACS Catal., 2014, 4, 2718–2726.
- 31 J. Luo, J. Yu, R. J. Gorte, E. Mahmoud, D. G. Vlachos and M. A. Smith, Catal. Sci. Technol., 2014, 4, 3074–3081.
- 32 D. Scholz, C. Aellig and I. Hermans, ChemSusChem, 2014, 7, 268–275.
- 33 D. P. Duarte, R. Martínez and L. J. Hoyos, Ind. Eng. Chem. Res., 2016, 55, 54–63.
- 34 B. Xiao, M. Zheng, X. Li, J. Pang, R. Sun, H. Wang, X. Pang, A. Wang, X. Wang and T. Zhang, Green Chem., 2016, 18, 2175–2184.
- 35 N. G. Anderson, Org. Process Res. Dev., 2012, 16, 852–869.
- 36 R. Jones, L. Gödörházy, N. Varga, D. Szalay, L. Ürge and F. Darvas, J. Comb. Chem., 2006, 8, 110–116.
- 37 E. A. Artiukha, A. L. Nuzhdin, G. A. Bukhtiyarova, Y. S. Zaytsev, P. E. Plyusnin, Y. V. Shubin and V. I. Bukhtiyarov, Catal. Sci. Technol., 2015, 5, 4741–4745. Paper<br> **Commons Access Article is article.** A common and K. Sulterial, Org. Paper Access Articles. 2017. A common and K. Common and K. Common and K. Commons A. Downloaded on Windows Commons C. Paper Articles. 2017. A creat
	- 38 M. C. Bryan, D. Wernick, C. D. Hein, J. V. Petersen, J. W. Eschelbach and E. M. Doherty, Beilstein J. Org. Chem., 2011, 7, 1141–1149.
	- 39 P. J. Cossar, L. Hizartzidis, M. I. Simone, A. McCluskey and C. P. Gordon, Org. Biomol. Chem., 2015, 13, 7119–7130.
	- 40 M. Tucker, H. R. Alamillo, A. J. Crisci, G. M. Gonzalez, S. L. Scott and J. A. Dumesic, ACS Sustainable Chem. Eng., 2013, 1, 554–560.
	- 41 E. L. Stephan, N. S. Hatfield, R. S. Peoples and H. A. H. Pray, USAEC Report BMI-1067, Battelle Memorial Institute, Columbus, Ohio, 1956.
	- 42 H. A. Pray, C. E. Schweickert and B. H. Minnich, Ind. Eng. Chem., 1952, 44(5), 1146–1151.
	- 43 J. M. Tukacs, R. V. Jones, F. Darvas, G. Dibó, G. Lezsák and L. T. Mika, RSC Adv., 2013, 3, 16283–16287.
	- 44 R. S. Assary, P. C. Redfern, J. R. Hammond, J. Greeley and L. A. Curtiss, Chem. Phys. Lett., 2010, 497, 123–128.
	- 45 S. P. Verevkin, V. N. Emel'yanenko, E. N. Stepurko, R. V. Ralys and D. H. Zaitsau, Ind. Eng. Chem. Res., 2009, 48, 10087–10093.
	- 46 H. Rojas, J. J. Martínez and P. Reyes, *Dyna*, 2010, 163, 151-159.
	- 47 B. W. Hoffer, E. Crezee, F. Devred, P. R. M. Mooijman, W. G. Sloof, P. J. Kooyman, A. D. van Langeveld, F. Kapteijn and J. A. Moulijn, Appl. Catal., A, 2003, 253, 437–452.
	- 48 U. Hauschild and H. Nicolaus, US Pat. number 3165478 A, 1965.