# **RSC Advances**



View Article Online

View Journal | View Issue

# PAPER

Check for updates

Cite this: RSC Adv., 2017, 7, 27354

# 3D nanostructured WO<sub>3</sub>/BiVO<sub>4</sub> heterojunction derived from *Papilio paris* for efficient water splitting<sup>†</sup>

Chao Yin, 💿 Shenmin Zhu 💿 \* and Di Zhang \*

We report on a novel butterfly wing-like WO<sub>3</sub>/BiVO<sub>4</sub> heterojunction for photocatalytic water splitting, in which BiVO<sub>4</sub> is the primary visible light-absorber and WO<sub>3</sub> acts as an electron conductor. The heterojunction, which is prepared by a one-step sol-gel method, achieves high light absorption and charge separation efficiencies, even without a sacrificial agent, and produces a photocatalytic O<sub>2</sub> evolution of 20  $\mu$ mol h<sup>-1</sup> mg<sup>-1</sup> under visible light irradiation ( $\lambda > 420$  nm) and an incident photon-to-current conversion efficiency of ~10% at 380–450 nm, both at a potential of 1.23 V *versus* RHE. Compared to planar WO<sub>3</sub>/BiVO<sub>4</sub> heterojunction, the 3D nanostructured WO<sub>3</sub>/BiVO<sub>4</sub> heterojunction shows significantly improved photocatalytic performance due to the quasi-honeycomb structure inherited from the *Papilio paris* and the efficient separation of the photogenerated charge at the WO<sub>3</sub>/BiVO<sub>4</sub> interface. Synthesis details are discussed, with heterojunction morphologies and structures characterized by field emission scanning electron microscopy and X-ray diffraction.

Received 26th March 2017 Accepted 5th May 2017

DOI: 10.1039/c7ra03491a

rsc.li/rsc-advances

# Introduction

Photocatalytic water splitting into H<sub>2</sub> and O<sub>2</sub> using semiconductors is a very attractive and desirable way to meet the global energy challenge and solve environmental issues.<sup>1,2</sup> Although several semiconductor materials show photocatalytic activity, most of them have limited utility due to the high charge carrier recombination<sup>3</sup> and wide band gaps, which make them only active under UV light irradiation, and UV light represents merely 4-5% of the solar spectrum energy lies.<sup>4</sup> A range of attempts have been made to improve light absorption and charge separation efficiencies, including impurity doping,5-7 loading co-catalysts,<sup>8,9</sup> and the introduction of nanoscale porosity.<sup>10,11</sup> Moreover, photocatalytic performance has also been improved by the formation of heterojunctions, which couple a large band gap semiconductor with a small band gap semiconductor. Heterojunctions have a more negative conduction band (CB) level, and the CB electrons can be injected from the small band gap semiconductor into the large band gap semiconductor, promising that the heterojunction can be more efficient than a single semiconductor system.<sup>12</sup>

Monoclinic BiVO<sub>4</sub> (mBiVO<sub>4</sub>) has become the top performer among all metal oxide photocatalysts under visible light owing to its relatively small band-gap energy (2.4 eV).<sup>13</sup> BiVO<sub>4</sub> based heterostructures with other desirable semiconductors including ZnO,<sup>14</sup> WO<sub>3</sub>,<sup>12,15-19</sup> nanowires of Fe<sub>2</sub>O<sub>3</sub> (ref. 20) and others<sup>21-24</sup> have been shown to promote the separation of electron-hole pairs and anti-photocorrosion. Among the latest state-of-the-art BiVO<sub>4</sub>-based heterojunctions, the highest efficiency was achieved by a W doped WO<sub>3</sub>/BiVO<sub>4</sub> core/shell nanowire photoanode, synthesized on an FTO without an added catalyst, which produced a photocurrent of 3.1 mA cm<sup>-2</sup> under simulated sunlight and an incident photon-to-current conversion efficiency of ~60% at 300–450 nm, both at a potential of 1.23 V *versus* RHE.<sup>12</sup> However, the cumbersome process and difficulty in controlling the nanomorphology of the photoanode create obstacles in its practical use.

As a matter of fact, nature offers an astonishing variety of materials with exquisite 3D hierarchical structures, which cannot be easily synthesized using available nanotechnology to date. 3D hierarchical structures from nature often display an efficient light-harvesting capacity, particularly in the region of visible light, and the abundant biogenic elements endowed from biological systems can be preserved and incorporated into the final biotemplated materials to reduce the bandgap of photocatalysts,25 leading to a new way to obtain efficient photocatalysts. Recently, we reported that a C-doped BiVO<sub>4</sub> photocatalyst with fine 3D hierarchical structures templated from Papilio paris butterfly wings fabricated by a novel one-step solgel and templating method enables simultaneous control of crystal phase, nanomorphology, and element carbon doping in a single process.<sup>26</sup> The improved photocatalytic performance was attributed to the synergetic effect of the unique morphology and doping control. We have also reported that the sequence of

State Key Laboratory of Metal Matrix Composites, Shanghai Jiao Tong University, 800 Dongchuan Road, Shanghai, 200240, P. R. China. E-mail: smzhu@sjtu.edu.cn; zhangdi@sjtu.edu.cn; Fax: +86-21-34202749; Tel: +86-21-34203927

<sup>†</sup> Electronic supplementary information (ESI) available. See DOI: 10.1039/c7ra03491a

ceramic WO<sub>3</sub> butterfly wings was also inherited from *Papilio* paris.<sup>27</sup> We verified that the quasi-honeycomb structure adapted from *Papilio paris* can help WO<sub>3</sub> harvest visible light more efficiently and boost charge transport. Nevertheless, the efficiency of these photocatalysts is not sufficient due to the still limited charge separation efficiencies. Hence heterojunction nano-architectures coupled with the unique structures are expected to result in the highest photocatalytic activity.

In this study, we fabricate a novel 3D nanostructured  $WO_3/BiVO_4$  heterojunction derived from *Papilio paris* for photocatalytic water splitting, in which  $BiVO_4$  is the primary visible light-absorber and  $WO_3$  acts as an electron conductor. The heterojunction, which is prepared by a one-step sol–gel method, achieves the highest light absorption and charge separation efficiencies among  $BiVO_4$ -based powder composites, even without a sacrificial agent. In the following, we will describe the synthesis and characterization of the present  $WO_3/BiVO_4$  heterojunction in detail and explain the origin of the improved photocatalytic performance.

### Experimental

#### Materials

Butterfly wing biotemplates were purchased from Shanghai Natural Wild-Insect Kingdom Co., Ltd. Analytical grade reagents such as phosphotungstic acid 44-hydrate  $(H_3PO_{40}W_{12})$ , bismuth nitrate  $(Bi(NO_3)_3 \cdot 5H_2O)$ , ammonium metavanadate  $(NH_4VO_3)$ , ethanol, acetic acid, nitric acid, and tetramethylammonium hydroxide (TMAH) were purchased from Sino-pharm Reagent Chemical Co., Ltd.

#### Synthesis

In a typical synthesis, first, Papilio paris butterfly wings, as biological templates, were air dried before use. The biological samples were pretreated by a mixture solution of acetic acid and ethanol for 6 h at room temperature and then washed with deionized water and air-dried for 24 h. The pretreated samples were carefully dipped into 20 wt% of phosphotungstic acid 44hydrate (H<sub>3</sub>PO<sub>40</sub>W<sub>12</sub>) in ethanol solution and kept at 36 °C for 6 h, denoted as WO<sub>3</sub>BWs.<sup>27</sup> Then, WO<sub>3</sub>/BiVO<sub>4</sub> heterojunction was achieved by a one-step sol-gel method and a two-step solgel method. In the one-step sol-gel process, WO3BWs were washed with ethanol and dried overnight under vacuum at 60 °C and dipped into the BiVO<sub>4</sub> sol-gel solution<sup>26</sup> and kept at 36  $^{\circ}$ C for 12 h. Finally, the samples were calcined in air at 500  $^{\circ}$ C with a constant heating rate of 1 °C min<sup>-1</sup> to format the crystal and remove the organic templates (WO3/BiVO4BWs). The synthesis process is illustrated in Scheme 1. For comparison, WO<sub>3</sub>/BiVO<sub>4</sub>BWs (two-step) were prepared by WO<sub>3</sub>BWs, which were first calcined in N2 atmosphere at 800 °C to crystallize the WO3 and dipped into the BiVO4 sol-gel solution at last.

#### Photocatalytic activity test

The photocatalytic activities of the samples were evaluated by the amount of oxygen split from water (Labsolar-H<sub>2</sub>, Perfect Light, China) under visible light. Portions of the solid samples



Scheme 1 The synthesis process of replication of butterfly wing in  ${\rm WO}_3/{\rm BiVO}_4{\rm BWs}.$ 

(10 mg) were introduced into a spectroscopic quartz probe cell, and the measurements were taken at room temperature under visible light irradiation from a 300 W Xe lamp (PLS-SXE300/ 300UV, Perfect Light, China) equipped with a cutoff filter L42. The visible light intensity is about 10 mA. The evolved gases were analyzed by gas chromatography with a thermal conductivity detector (GC7890II, Tianmei, Shanghai; N<sub>2</sub> carrier gas).

The electrodes were prepared according to the method from Kudo. Photoelectrochemical properties were evaluated with a three-electrode cell consisting of the prepared electrodes, a Pt electrode, and a saturated Ag/AgCl electrode as the working, counter, and reference electrodes, respectively. The working electrode was irradiated from the FTO side with visible-light through a cutoff filter (L42). The incident photon-to-photocurrent efficiency (IPCE) was calculated as follows:

 $[IPCE/\%] = 1240 \times [photocurrent density/\mu A cm<sup>-2</sup>]/$ ([wavelength/nm] × [photo flux/Wm<sup>-2</sup>])

#### Characterizations

The synthesized samples were examined by X-ray diffraction (XRD) on a D-max/2550 (Rigaku) X-ray diffractometer system operating at 1600 W power (40 kV, 40 mA) with Cu K $\alpha$  radiation ( $\lambda = 0.15406$  nm), at a scan rate of 4° min<sup>-1</sup> and a step size of 0.050° in 2 $\theta$ . The morphologies and microstructures of the samples were characterized using a FEI QUANTA TEG 250 scanning electron microscope (SEM) and a JEOL2011 transmission electron microscope (TEM). TEM specimens were

prepared by dispersing the synthesized samples in pure ethanol, and the powder was picked up by copper grids. UV-Visible (UV-Vis) diffuse reflectance spectra of all the samples were recorded using a PerkinElmer UV-Vis-NIR spectrophotometer (750S) in the spectral range of 200–800 nm, and Raman scattering measurements were obtained in back scattering geometry on a Via<sup>+</sup> Reflex from 150–1000 cm<sup>-1</sup>.

## Results and discussion

BiVO<sub>4</sub> has a narrow band gap (2.4 eV), and its conduction band is more negative than that of WO<sub>3</sub>. Therefore coupling with photocorrosion resistant WO<sub>3</sub>, WO<sub>3</sub>/BiVO<sub>4</sub> heterojunctions<sup>15-19</sup> could be suitable for efficient photocatalytic water splitting under visible irradiation; see Fig. 1e. The quasi-honeycomb structure of *Papilio paris* butterfly wings is shown in Fig. S1,† which can absorb visible light to an utmost degree with over 95% absorption rate.<sup>28</sup> The morphologies of WO<sub>3</sub>BWs, WO<sub>3</sub>/ BiVO<sub>4</sub>BWs (two-step) and WO<sub>3</sub>/BiVO<sub>4</sub>BWs are shown in Fig. 1ac. The quasi-honeycomb and three-layer structures of the scales can clearly be seen in the three samples. Compared with the original butterfly wing, the replicas show a 20% shrinkage for both WO<sub>3</sub>/BiVO<sub>4</sub>BWs (two-step) and WO<sub>3</sub>/BiVO<sub>4</sub>BWs after calcination (Fig. 1b and c). The scales, neatly arranged on the surface of the structure of the Papilio paris butterfly wings, were completely retained by WO<sub>3</sub> (Fig. 1a). The parallel ridges of the scales and nanoscale ribs were retained in the WO<sub>3</sub>/BiVO<sub>4</sub>BWs, indicating an extremely fine duplication of the original scale structures using the one-step sol-gel method (Fig. 1c), and the high-resolution TEM (HRTEM) images provide the 150 nm average pore diameter (Fig. 1d). However, the further finer and elaborate architectures in the ribs of the WO3/BiVO4BWs (twostep) disappear (Fig. 1b) because of the significant grain growth of WO<sub>3</sub> particles when the calcination temperature reaches 800 °C, suggesting a poor photocatalytic performance.

Fig. 2a shows X-ray diffraction patterns of WO<sub>3</sub>BWs, BiVO<sub>4</sub>-BWs, and WO<sub>3</sub>/BiVO<sub>4</sub>BWs. In the WO<sub>3</sub>BWs, the peaks of 23.3, 23.8, and 24.6° are observed corresponding to (002), (020), and (200) planes for the monoclinic phase of WO<sub>3</sub> (JCPDS 43-1035), which is known to show the highest photocatalytic effect compared to other crystal phases.<sup>29,30</sup> Compared with monoclinic WO<sub>3</sub>, several new peaks appeared on the XRD spectra, and they could be indexed as other  $W_xO_y$  phases, such as WO<sub>2.9</sub> and  $W_{18}O_{49}$ . This means that the bio-template resulted in multiple



Fig. 2 XRD patterns of (a) WO<sub>3</sub>BWs, BiVO<sub>4</sub>BWs, and WO<sub>3</sub>/BiVO<sub>4</sub>BWs.
(b) Magnified peaks of (120) planes in the range of 2θ from 28° to 30°.



Fig. 1 The 3D nanostructured WO<sub>3</sub>/BiVO<sub>4</sub>BWs. (a–c) Scanning electron microscope (SEM) of WO<sub>3</sub>BWs, WO<sub>3</sub>/BiVO<sub>4</sub>BWs (two-step) and WO<sub>3</sub>/BiVO<sub>4</sub>BWs. (d) Transmission electron microscope (TEM) images of the WO<sub>3</sub>/BiVO<sub>4</sub>BWs (150 nm average pore diameter). The BiVO<sub>4</sub> consists of a single layer of densely packed nanoparticles. (e) Structural schematic and energy band diagram of the butterfly wing WO<sub>3</sub>/BiVO<sub>4</sub>BWs and type-II staggered heterojunction, in which charges generated in both the BiVO<sub>4</sub> outside and WO<sub>3</sub> inside can contribute to water oxidation. The band edges and water oxidation and reduction potentials are plotted on the reversible hydrogen electrode (RHE) scale.

#### Paper

tungsten oxide phases in the replicas. For bare BiVO<sub>4</sub>BWs, the main peaks can be indexed as (110), (011), (121), (040), (200) and (002) planes, which can represent the monoclinic BiVO<sub>4</sub> (JCPDS 14-0688) without any impurity phase, illustrating that the biotemplate has been removed completely by calcination at 500 °C. In the case of WO<sub>3</sub>/BiVO<sub>4</sub>BWs, monoclinic WO<sub>3</sub> and BiVO<sub>4</sub> are the only phases detected in XRD measurements (Fig. 2a), demonstrating that a novel 3D nanostructured WO<sub>3</sub>/BiVO<sub>4</sub> heterojunction derived from *Papilio paris* with pure and high crystallinity can be achieved by the one-step sol-gel method mentioned before. As a result, the average grain size of the samples, calculated *via* the Scherrer formula, are 15.3, 27.2 and 30.5 nm, corresponding to WO<sub>3</sub>/BiVO<sub>4</sub>BWs (two-step) shows 48.5 nm.

Fig. 2b exhibits a magnified view of (121) peaks, which show  $0.318^{\circ}$  shifts to lower angles in the WO<sub>3</sub>/BiVO<sub>4</sub>BWs, compared with the BiVO<sub>4</sub>BWs. Pratap M. Rao *et al.* in 2014 have reported that W<sup>6+</sup> dopes into BiVO<sub>4</sub> by substituting for V<sup>5+</sup> and acts as an electron donor in the WO<sub>3</sub>/BiVO<sub>4</sub> core/shell nanowire photo-anode.<sup>12</sup> This shifting may be ascribed to lattice expansion due to the slight portion of W atoms incorporating from WO<sub>3</sub>. These XRD results indicate that little W atoms have been well inserted into V sites of the host BiVO<sub>4</sub> lattice, induces lattice expansion without forming any segregated impurity phase.<sup>12</sup> It has been known that impurity doping may form new bonds to promote the electron-hole separation efficiency.<sup>6</sup> Therefore, the WO<sub>3</sub>/BiVO<sub>4</sub>BWs are expected to show enhanced photocatalytic performance.

Moreover, Fig. 3 presents the Raman spectra of the WO<sub>3</sub>BWs, BiVO<sub>4</sub>BWs, and WO<sub>3</sub>/BiVO<sub>4</sub>BWs in the 150–1000 cm<sup>-1</sup> region. The bands at 827, 723, 367, 324, 210 and 128 cm<sup>-1</sup> in the BiVO<sub>4</sub>BWs correspond to the typical vibrations of monoclinic BiVO<sub>4</sub>. The band at 827 is assigned to the typical symmetric V–O stretching mode,<sup>31</sup> and the one with a weak shoulder at about 712 cm<sup>-1</sup> assigned to the antisymmetric V–O stretching mode, whereas those at 367 and 324 cm<sup>-1</sup> are attributed to the typical symmetric and antisymmetric bending modes of the vanadate anion.<sup>32,33</sup> Raman vibrations centered at 135, 214, 708 and 785 cm<sup>-1</sup>, characteristic of pure WO<sub>3</sub>, are also detected in the



Fig. 3 Raman spectra of WO<sub>3</sub>BWs, BiVO<sub>4</sub>BWs, and WO<sub>3</sub>/BiVO<sub>4</sub>BWs.

 $WO_3BWs$ . The bands at 708 and 785 cm<sup>-1</sup> are identified as the O–W–O bending and stretching mode, respectively.<sup>32</sup>

AS seen from Fig. 3, in the case of WO<sub>3</sub>/BiVO<sub>4</sub>BWs, it is clear that a shift of the Raman band to the lower wavenumber, from 827 to 810 cm<sup>-1</sup> assigned to symmetric V-O bond stretching mode, reveals that the average lone-range symmetry of the VO<sub>4</sub> tetrahedral becomes less regular. The blue-shift is due to the Wdoping effect where W has been inserted into the V sites of the BiVO<sub>4</sub> lattice to form the W-O bond, which has the bond length shorter than that of the V–O bond. Furthermore, the band at 785 cm<sup>-1</sup> attributed to O-W-O bonds is broad and shifted to 810 cm<sup>-1</sup> in WO<sub>3</sub>/BiVO<sub>4</sub>BWs, probably due to the formation of the WO<sub>3</sub>/BiVO<sub>4</sub> heterojunction structures, which generate a new W-O-V bond,33 consistent with XRD results. It has been reported that formation of new bonds can promote electron-hole separation efficiency of photocatalysts. It would be expected that WO<sub>3</sub>/BiVO<sub>4</sub>BWs should perform the best in the photocatalytic O2 production experiments.

To investigate the optical absorption properties of the samples, UV/Vis spectroscopy was conducted, and the results are shown in Fig. 4. Light absorption of the bare WO<sub>3</sub>BWs starts at around 475 nm in correspondence with its band gap energy. For the bare BiVO<sub>4</sub>BWs, the onset of light absorption is around 520 nm, again corresponding to its band gap energy. In the WO<sub>3</sub>/BiVO<sub>4</sub>BWs, the main absorption edge has a red-shift of more than 20 nm compared with pure BiVO<sub>4</sub>BWs. It indicates that the band-gap energy of the samples is affected by the quasihoneycomb structure of Papilio paris butterfly wing, and the quasi-honeycomb structure can enhance visible light absorption, which has been reported by us before.26 Moreover, compared with BiVO4BWs and WO3BWs, WO3/BiVO4BWs exhibits an increased photoabsorption at wavelengths between 200 nm and 480 nm, which is probably due to the formation of the heterojunction structure. The optical band-gap energies of the three samples are estimated from the absorption spectra using the following relationship:

$$\alpha h\nu = A(h\nu - E_{\rm g})^n$$



Fig. 4 UV-Vis absorbance spectra of WO\_3BWs, BiVO\_4BWs, and WO\_3/ BiVO\_4BWs.

where  $E_{\rm g}$  is the band-gap energy of allowed transitions (eV), *h* is Planck's constant (6.626 × 10<sup>-34</sup> J s),  $\alpha$  and  $\nu$  are the absorption coefficient and light frequency, respectively, and *A* is a constant. The band gap energy for BiVO<sub>4</sub>BWs is measured to be about 2.4 eV, which is smaller than that of WO<sub>3</sub>/BiVO<sub>4</sub>BWs (2.46 eV) and WO<sub>3</sub>BWs (2.69 eV). Thus, the absorption range of the WO<sub>3</sub>BWs is enhanced by coupling of BiVO<sub>4</sub> having a smaller band gap energy. Thus, the band-gap energy of the samples is affected by the quasi-honeycomb structure of *Papilio paris* butterfly wings and the heterojunction coupled by WO<sub>3</sub> and BiVO<sub>4</sub>. The small difference in band gap has a significant influence on the photocatalytic performance, which will be discussed later with the results of oxygen production from water splitting.

We further measure photocurrents of WO<sub>3</sub>BWs, BiVO<sub>4</sub>BWs, and WO<sub>3</sub>/BiVO<sub>4</sub>BWs by depositing each material on ITO electrodes. A fast and strong photocurrent response is observed for each switch-on/off event in both WO<sub>3</sub>/BiVO<sub>4</sub>BWs and BiVO<sub>4</sub>-BWs-deposited electrodes under visible light (Fig. 5a). Under



**Fig. 5** (a) Photocurrent responses of WO<sub>3</sub>BWs, BiVO<sub>4</sub>BWs, and WO<sub>3</sub>/ BiVO<sub>4</sub>BWs under visible light irradiation ( $\lambda > 420$  nm). (b) Incident photon to current conversion efficiency (IPCE) of the WO<sub>3</sub>BWs, BiVO<sub>4</sub>BWs, and WO<sub>3</sub>/BiVO<sub>4</sub>BWs. The IPCE was measured at 1.23 V (vs. Ag/AgCl) under 0.5 M Na<sub>2</sub>SO<sub>4</sub> solution. The three-electrode cell consists of a prepared electrode, a Pt electrode, and a saturated Ag/ AgCl electrode as the working, counter, and reference electrodes, respectively. The working electrode was irradiated from the FTO side with visible-light through a cutoff filter (L42).

visible light irradiation ( $\lambda > 420$  nm), the photocurrent of WO<sub>3</sub>/ BiVO<sub>4</sub>BWs electrode (2.5  $\mu$ A) is approximately 5 times higher than that of the BiVO<sub>4</sub>BWs electrode (0.5  $\mu$ A), which indicates that the separation efficiency of photo-induced electrons and holes is improved significantly through the electronic interaction between BiVO<sub>4</sub> and WO<sub>3</sub>, as expected from the results in Fig. 5a. In contrast, no photocurrent is recorded for WO<sub>3</sub>BWs under visible light irradiation, which implies no photocatalytic O<sub>2</sub> evolution from water splitting under visible light gap.

The incident photon-to-photocurrent efficiency (IPCE) spectra of WO<sub>3</sub>BWs, BiVO<sub>4</sub>BWs, and WO<sub>3</sub>/BiVO<sub>4</sub>BWs are shown in Fig. 5b, in which the electrodes are measured at 1.23 V (*vs.* Ag/ AgCl) in 0.5 M Na<sub>2</sub>SO<sub>4</sub> using monochromatic light controlled with band pass filters. The IPCE is defined by the following equation:

 $[IPCE/\%] = 1240 \times [photocurrent density/\mu A cm<sup>-2</sup>]/$ ([wavelength/nm] × [photo flux/Wm<sup>-2</sup>])

The WO<sub>3</sub>BWs shows rising IPCE from 480 nm and the BiVO<sub>4</sub>BWs from 540 nm, in agreement with their band gap energies. The WO<sub>3</sub>/BiVO<sub>4</sub>BWs also shows the onset of IPCE at 540 nm similar to BiVO<sub>4</sub>BWs. Moreover, the WO<sub>3</sub>/BiVO<sub>4</sub>BWs electrode performs at an excellent anodic photocurrent with 10.8% of an IPCE at 400 nm at 1.23 V vs. Ag/AgCl, whereas the trivial IPCE of WO<sub>3</sub>BWs at 0.3% (at 380 nm) and BiVO<sub>4</sub>BWs at 0.7% (at 400 nm) is observed. Despite the range of light absorption of BiVO<sub>4</sub>BWs being larger than WO<sub>3</sub>/BiVO<sub>4</sub>BWs, the photoactivity was much less because of poor charge transfer characteristics as evidenced by the photocurrents study discussed above. Because WO3 cannot absorb light with wavelength between 500 and 540 nm, the IPCE in this range for WO<sub>3</sub>/ BiVO<sub>4</sub>BWs originates from the absorption by the BiVO<sub>4</sub> layers. However, unlike bare BiVO<sub>4</sub>, the WO<sub>3</sub>/BiVO<sub>4</sub> heterojunction can utilize light at 500-540 nm for water oxidation because the good charge transfer characteristic at the interface induces rapid transfer of photoelectrons formed in BiVO<sub>4</sub> to WO<sub>3</sub>. One order of magnitude enhancement in photoconversion efficiency indicates that WO3/BiVO4BWs may result in the best photocatalytic activity.

On the basis of the above results, the photocatalytic activities of the samples were tested for  $O_2$  evolution from water splitting under visible light range. Fig. 6 shows the amount of evolved  $O_2$ by solar light from boiled water. The amount of evolved  $O_2$  from aqueous solution after 1 h from the WO<sub>3</sub>/BiVO<sub>4</sub>BWs is *ca.* 200 µmol, which is 5 times as much as that of the BiVO<sub>4</sub>BWs (*ca.* 42 µmol), the highest photocatalytic  $O_2$  evolution among all the tested samples. The total evolved  $O_2$  after 5 h from the WO<sub>3</sub>/ BiVO<sub>4</sub>BWs is *ca.* 950 µmol, which is more than 7.6 times that of the BiVO<sub>4</sub>BWs (*ca.* 125 µmol). On the contrary, WO<sub>3</sub>/BiVO<sub>4</sub>BWs (two-step) shows *ca.* 35 µmol (Fig. S2, ESI†) and WO<sub>3</sub>BWs produces no oxygen under visible light irradiation. The results suggest that the WO<sub>3</sub>/BiVO<sub>4</sub>BWs performs the best photocatalytic activities, compared with other hierarchical porous photocatalysts from bio-templates that we have reported Paper



**Fig. 6** Photocatalytic O<sub>2</sub> evolution of WO<sub>3</sub>BWs, BiVO<sub>4</sub>BWs, and WO<sub>3</sub>/ BiVO<sub>4</sub>BWs under visible light irradiation ( $\lambda > 420$  nm). The amount is kept the same for all the samples.

before.<sup>26,27</sup> This result shows that the  $WO_3/BiVO_4BWs$  are stable and indeed oxidize water into  $O_2$ .

From all the results presented above, a possible mechanism for photocatalytic  $O_2$  evolution from water splitting by the  $WO_3$ / BiVO\_4BWs has been proposed and illustrated in Fig. 7. We attribute the significantly enhanced photocatalytic performance of  $WO_3$ /BiVO\_4BWs under visible light to more absorption of visible light as well as more efficient transfer of photogenerated electrons. The unique quasi-honeycomb structure allows more visible light waves to penetrate deep inside the photocatalyst, thus improving the light absorption capability and the formation of heterojunctions which enhances the separation of photogenerated electron-hole pairs and thus reduces charge



Fig. 7 Depiction of the energy diagram of the WO<sub>3</sub>/BiVO<sub>4</sub> heterojunction (at pH 7) and electron transport process. Suggested mechanism for the photocatalytic O<sub>2</sub> evolution by WO<sub>3</sub>/BiVO<sub>4</sub>BWs under visible-light. The conduction band of WO<sub>3</sub> and BiVO<sub>4</sub> are -0.52, and 0.05 eV, respectively. Electrons from BiVO<sub>4</sub> flow to the conduction band of WO<sub>3</sub>. Valence electrons of BiVO<sub>4</sub> are excited to the conduction band state by absorbing visible light, which can convert oxygen molecules in the solution to singlet oxygen.

recombination rate as evidenced by the photocurrent responses analysis.

According to the literature, for a WO<sub>3</sub> film in Na<sub>2</sub>SO<sub>4</sub>, a flatband potential of  $V_{\rm fb} = 0.15$  V (*vs.* SCE) was reported by Patil,<sup>34</sup> while the  $V_{\rm fb}$  of BiVO<sub>4</sub> was reported as -0.62 V (*vs.* SCE) by Sayama<sup>35</sup> and Li<sup>36</sup>. It is generally known that the bottoms of the conduction bands in several n-type semiconductors are more negative by 0.1 V than the flat band potential.<sup>37</sup> In the photocatalytic oxygen evolution process (Fig. 7), illumination photons create electron-hole pairs in the WO<sub>3</sub>/BiVO<sub>4</sub>BWs at the solid/ solution interface. These electron-hole pairs separate and reach the photocatalyst surface by diffusion. Owing to the positive conduction band position (>0 eV *vs.* NHE at pH = 7), only the reaction of holes with water to produce O<sub>2</sub> can occur spontaneously (eqn (2)).

$$h\nu \xrightarrow{\text{BiVO}_4} e^- + h^+$$
 (1)

$$2\mathrm{H}_{2}\mathrm{O} + 4\mathrm{h}^{+} \to 4\mathrm{H}^{+} + \mathrm{O}_{2} \tag{2}$$

With the bottom of the BiVO<sub>4</sub> conduction band more positive than that of WO<sub>3</sub>, it is favorable for the electrons to travel from the BiVO<sub>4</sub> conduction band to WO<sub>3</sub>. Hence, electrons generated in the BiVO<sub>4</sub> will first travel radially inward to the WO<sub>3</sub> in the WO<sub>3</sub>/BiVO<sub>4</sub>BWs, and then travel to the current collector through WO<sub>3</sub>, in turn suppressing electron-hole recombination. Although BiVO<sub>4</sub> absorbs a larger fraction of solar light than WO<sub>3</sub> due to its narrower band gap as shown in Fig. 4, electrons and holes formed in BiVO<sub>4</sub> are not fully utilized for water decomposition reaction because its poor transfer characteristics lead to recombination. However, the holes can migrate to the semiconductor/electrolyte interface either directly or after transfer from WO<sub>3</sub> to BiVO<sub>4</sub>. The reduced recombination naturally induces photoactivity enhancement.

## Conclusions

In summary, a novel 3D nanostructured WO<sub>3</sub>/BiVO<sub>4</sub> heterojunction derived from Papilio paris for photocatalytic water splitting is fabricated by a one-step sol-gel method. The quasihoneycomb structure of the original butterfly wings is kept perfectly in the heterojunction. The photocurrents of WO<sub>3</sub>/ BiVO<sub>4</sub>BWs (2.5  $\mu$ A) is approximately 5 times higher than that of a BiVO<sub>4</sub>BWs (0.5 µA), and an incident photon-to-current conversion efficiency of ~10% at 380-450 nm (1.23 V versus RHE), indicating a higher product of light absorption and charge separation efficiencies. The WO3/BiVO4BWs, in which BiVO<sub>4</sub> is the primary visible light-absorber and WO<sub>3</sub> acts as an electron conductor, achieved an excellent photocatalytic O2 evolution of 20 µmol h<sup>-1</sup> mg<sup>-1</sup> under visible light irradiation, which is 5 times higher than BiVO<sub>4</sub>BWs, even without a sacrificial agent. The enhanced photocatalytic performance is attributed to not only the unique quasi-honeycomb structure with an efficient visible light-harvesting capacity, but also to improved separation efficiency of photo-induced electrons and holes through the electronic interaction in the WO<sub>3</sub>/BiVO<sub>4</sub> heterojunction. These promising results open new possibilities in the design of highly photoactive heterojunction photocatalysts inherited from bio-templates for water-splitting systems.

# Acknowledgements

The authors gratefully acknowledge financial support for this research from the Morgan Crucible Company, the National Science Foundation of China (No. 51072117, 51171110), the National Basic Research Program of China (973 Program, 2012CB619600), the Shanghai Science and Technology Committee (0JC1407600). We also thank the Shanghai Jiao Tong University (SJTU) Instrument Analysis Center.

# Notes and references

- 1 A. Kudo and Y. Miseki, Chem. Soc. Rev., 2009, 38, 253-278.
- 2 M. G. Walter, E. L. Warren, J. R. McKone, S. W. Boettcher, Q. Mi, E. A. Santori and N. S. Lewis, *Chem. Rev.*, 2010, **110**, 6446.
- 3 H. P. Maruska and A. K. Ghosh, *Sol. Energy Mater.*, 1979, 1, 411–429.
- 4 P. V. Kamat, Chem. Rev., 1993, 93, 267-300.
- 5 W. J. Jo, J. W. Jang, K. J. Kong, H. J. Kang, J. Y. Kim, H. Jun, K. P. S. Parmar and J. S. Lee, *Angew. Chem., Int. Ed.*, 2012, **51**, 1–6.
- 6 W. J. Luo, Z. S. Yang, Z. Li, J. Zhang, J. Liu, Z. Zhao, Z. Wang, S. Yan, T. Yu and Z. Zou, *Energy Environ. Sci.*, 2011, 4, 4046– 4051.
- 7 S. K. Pilli, T. E. Furtak, L. D. Brown, T. G. Deutsch, J. A. Turner and A. M. Herring, *Energy Environ. Sci.*, 2011, 4, 5028–5034.
- 8 F. Lin, D. G. Wang, Z. X. Jiang, Y. Ma, J. Li, R. Li and C. Li, *Energy Environ. Sci.*, 2012, 5, 6400-6406.
- 9 J. A. Seabold and K. S. Choi, J. Am. Chem. Soc., 2012, 134, 2186-2192.
- 10 R. G. Li, F. X. Zhang, D. G. Wang, J. X. Yang, M. R. Li, J. Zhu, X. Zhou, H. X. Han and C. Li, *Nat. Commun.*, 2013, 4, 1–7.
- 11 L. Chen, Q. Zhang, R. Huang, S. F. Yin, S. L. Luo and C. T. Au, *Dalton Trans.*, 2012, **41**, 9513–9518.
- 12 P. M. Rao, L. Cai, C. Liu, I. S. Cho, C. H. Lee, J. M. Weisse, P. Yang and X. Zheng, *Nano Lett.*, 2014, 14, 1099–1105.
- 13 A. Kudo, K. Omori and H. Kato, *J. Am. Chem. Soc.*, 1999, **121**, 11459–11467.
- 14 T. W. Kim and K. S. Choi, Science, 2014, 343, 990-994.
- 15 W. J. Luo, Z. S. Yang, Z. Li, J. Zhang, J. Liu, Z. Zhao, Z. Wang, S. Yan, T. Yu and Z. Zou, *Energy Environ. Sci.*, 2011, 4, 4046– 4051.

- 16 S. J. A. Moniz, J. Zhu and J. W. Tang, *Adv. Energy Mater.*, 2014, 4, 1301590.
- 17 R. Saito, Y. Miseki and K. Sayama, *Chem. Commun.*, 2012, **48**, 3833–3835.
- 18 S. J. Hong, S. Lee, J. S. Jang and J. S. Lee, *Energy Environ. Sci.*, 2011, 4, 1781–1787.
- 19 K. Zhang, X. J. Shi, J. K. Kim and J. H. Park, *Phys. Chem. Chem. Phys.*, 2012, 14, 11119–11124.
- 20 J. Su, L. Guo, N. Bao and C. A. Grimes, *Nano Lett.*, 2011, **11**, 1928–1933.
- 21 Y. Hou, F. Zuo, A. Dagg and P. Feng, *Nano Lett.*, 2012, 12, 6464-6473.
- 22 A. Iwase, Y. H. Ng, Y. Ishiguro, A. Kudo and R. Amal, J. Am. Chem. Soc., 2011, 133, 11054–11057.
- 23 F. F. Abdi, L. Han, A. H. M. Smets, M. Zeman, B. Dam and R. vande Krol, *Nat. Commun.*, 2013, **4**, 2195.
- 24 X. Lin, Y. S. Wang, J. Zheng, C. Liu, Y. Yang and G. B. Che, *Dalton Trans.*, 2015, **44**, 19185–19193.
- 25 C. J. Li, S. P. Wang, T. Wang, Y. J. Wei, P. Zhang and J. L. Gong, *Small*, 2014, **10**, 2783–2790.
- 26 C. Yin, S. M. Zhu, Z. X. Chen, W. Zhang, J. J. Gua and D. Zhang, J. Mater. Chem. A, 2013, 1, 8367–8378.
- 27 C. Yin, S. M. Zhu, F. Yao, J. J. Gu, W. Zhang, Z. X. Chen and D. Zhang, *J. Nanopart. Res.*, 2013, 15, 1812–1823.
- 28 P. Vukusic, J. R. Sambles and C. R. Lawrence, *Proc. R. Soc. B*, 2004, **271**, 237–239.
- 29 U. M. García-Pérez, S. Sepúlveda-Guzmán and A. Martínez-de la Cruz, *Solid State Sci.*, 2012, 14, 293–298.
- 30 J. Kenneth, M. Donald and K. S. Choi, *Energy Environ. Sci.*, 2012, 5, 8553–8557.
- 31 H. Liu, R. Nakamur and N. Yoshihiro, J. Electrochem. Soc., 2005, 152, 856–861.
- 32 G. S. Li, D. Q. Zhang and J. C. Yu, *Chem. Mater.*, 2008, 20, 3983–3992.
- 33 D. Wang, H. Jiang, X. Zong, Q. Xu, Y. Ma, G. Li and C. Li, *Chem.-Eur. J.*, 2011, 17, 1275–1282.
- 34 P. S. Patil and P. R. Patil, Bull. Mater. Sci., 1996, 19, 651-656.
- 35 K. Sayama, A. Nomura, T. Arai, T. Sugita, R. Abe, M. Yanagida, T. Oi, Y. Iwasaki, Y. Abe and H. J. Sugihara, *J. Phys. Chem. B*, 2006, **110**, 11352–11360.
- 36 M. Li, Z. L. Hao and L. Guo, *Int. J. Hydrogen Energy*, 2010, 35, 7127–7133.
- 37 Y. Matsumoto, K. Omae, I. Watanabe and E. J. Sato, J. Electrochem. Soc., 1986, 133, 711–716.