



Cite this: *RSC Adv.*, 2017, 7, 47251

# Role of porosity and polarity of nanoporous carbon spheres in adsorption applications†

Hee Soo Kim,<sup>a</sup> Seunghun Lee,<sup>a</sup> Dong Kwan Kim,<sup>a</sup> Yong-Woo Lee<sup>\*ab</sup>  
 and Won Cheol Yoo<sup>id</sup> <sup>\*ab</sup>

The role of porosity (pore size distribution (PSD) and specific surface area (SSA)) and polarity (N-doping) of carbonaceous materials for selective separation of CH<sub>4</sub> over N<sub>2</sub> and adsorption of heavy metal ions are presented herein. Two different carbons (resorcinol-formaldehyde carbon (RFC) and highly N-doped melanin carbon (MC)) with different N-doping levels are utilized and further activated by hot CO<sub>2</sub> treatment to finely control PSD and SSA. For CH<sub>4</sub> adsorption, the accumulated ultramicropore (<1 nm) volume of both carbons is strongly correlated with CH<sub>4</sub> adsorption regardless of surface polarity of carbons ( $R^2 = 0.94$ ). This is probably due to the high polarizability and nonpolar nature of CH<sub>4</sub>. Carbons with the highest ultramicropore volumes (RFC\_C60 and MC\_C55) show ultrahigh CH<sub>4</sub> uptake capacities of 2.64 and 2.41 mmol g<sup>-1</sup> at 273 K under 1 bar, respectively; these carbons also have superb CH<sub>4</sub> over N<sub>2</sub> selectivity of 6.8 and 7.4 obtained at 298 K, respectively. RFC\_C60 and MC\_C55 present excellent CH<sub>4</sub> adsorption capacities and selectivities for CH<sub>4</sub> over N<sub>2</sub>, which are comparable with the best values reported from various porous materials. In addition, heavy metal ion (Fe<sup>2+</sup>, Sb<sup>3+</sup>, and Sb<sup>5+</sup>) adsorption was achieved to identify the importance of SSA and the polarity of carbons. The SSA of RFC samples is highly correlated with Fe<sup>2+</sup> metal ion adsorption capacity ( $R^2 = 0.98$ ). Conversely, highly N-doped MC series are located on the upper region of the plotted line of RFC samples due to their basic nature, which is caused by high loading of N-doping within the carbon framework. Furthermore, RFC\_C60 and MC\_C55 samples with similar porosity but different N-doping levels are utilized for selective adsorption of Sb<sup>3+</sup> over Sb<sup>5+</sup>. The more basic MC\_C55 has higher selectivity of 3.3 compared to that of its less basic counterpart (2.0), strongly inferring that carbon polarity is involved in metal ion adsorption. Distinct correlations between carbon porosity and polarity, adsorption capacity for CH<sub>4</sub>, ultrahigh selectivity for CH<sub>4</sub> over N<sub>2</sub>, adsorption capacity, and selectivity of metal ions are exclusively elucidated here, providing design principles of nanoporous carbonaceous materials for specific adsorption applications.

Received 24th August 2017  
 Accepted 2nd October 2017

DOI: 10.1039/c7ra09360h

rsc.li/rsc-advances

## 1. Introduction

Carbonaceous materials are highly porous, lightweight, chemically and physically stable, and relatively cheap, making them suitable for numerous applications. Carbons have been intensively utilized as sorbents for gas molecules and metal ions because of textural features such as controllable PSD, high SSA, and surface polarity associated with heteroatom doping within the graphitic framework. Textural features and polarity should be judiciously considered when applying carbon materials for specific adsorption applications.

Several porous materials have been implemented for adsorption-based separation of CH<sub>4</sub> over N<sub>2</sub>, including silica

gels,<sup>1</sup> activated carbons,<sup>2-4</sup> zeolites,<sup>5,6</sup> Metal-Organic Frameworks (MOFs),<sup>7-10</sup> and microporous organic polymers (MOPs).<sup>11</sup> For example, ultramicropores (<1 nm) have a pivotal role in CH<sub>4</sub> adsorption and adsorption-based separation of CH<sub>4</sub> over N<sub>2</sub>. The effective separation of CH<sub>4</sub> over N<sub>2</sub> is needed for unconventional natural gases (UCNs), such as landfill gas and shale gas,<sup>7,8,12</sup> which inevitably contain impurities such as CO<sub>2</sub> and N<sub>2</sub>. These UCNs need to be upgraded to meet pipeline quality (typically >90% methane).<sup>13</sup> Although adsorption-based separation of CH<sub>4</sub> over N<sub>2</sub> is an effective process for removing N<sub>2</sub> from UCN, the process is difficult due to the similar sizes and nonpolar nature of CH<sub>4</sub> and N<sub>2</sub>. Therefore, adsorbents that are highly selective for CH<sub>4</sub> over N<sub>2</sub> are needed. Largely developed ultramicropore and moderate adsorbent polarizability have shown improved adsorption selectivity for CH<sub>4</sub> over N<sub>2</sub> (ref. 7 and 14-19) in equilibrium separation. The higher polarizability of CH<sub>4</sub> (2.59 Å<sup>3</sup>) over N<sub>2</sub> (1.74 Å<sup>3</sup>) mainly accounts for the higher adsorption of CH<sub>4</sub> over N<sub>2</sub> within ultramicropores.<sup>7,14-19</sup> A

<sup>a</sup>Department of Applied Chemistry, Hanyang University, Ansan 15588, Republic of Korea. E-mail: yongwoolee@hanyang.ac.kr; wcyoo@hanyang.ac.kr

<sup>b</sup>Department of Chemical and Molecular Engineering, Hanyang University, Ansan 15588, Republic of Korea

† Electronic supplementary information (ESI) available. See DOI: 10.1039/c7ra09360h



similar trend of CO<sub>2</sub> over N<sub>2</sub> is due to the higher polarizability of CO<sub>2</sub> (2.91 Å<sup>3</sup>).<sup>20–24</sup>

Recently, MOFs with a 1-D micro-channel have shown outstanding adsorption-based selectivity up to 8.34 at 298 K.<sup>7</sup> Hyper-cross-linked heterocyclic MOPs also presented high adsorption-based selectivity of 8.0 at 273 K and 7.6 at 298 K.<sup>11</sup> However, the adsorption capacities of these MOFs and MOPs at 1 bar with the above temperatures are less than 1 mmol g<sup>-1</sup>, which is not sufficient for practical purposes.

Recent reports on carbonaceous materials have shown promising adsorption capacity of CH<sub>4</sub> at ambient conditions. El-Kaderi *et al.* synthesized N-doped porous carbons activated by KOH with outstanding CH<sub>4</sub> uptake capacity of 2.7 mmol g<sup>-1</sup> at 273 K and 1.7 mmol g<sup>-1</sup> at 298 K.<sup>25</sup> The Qiu group reported KOH activated carbons derived from a porous aromatic framework with high CH<sub>4</sub> adsorption capacity of 2.4 mmol g<sup>-1</sup> at 273 K.<sup>19</sup> Both research groups reported carbons with ultrahigh CH<sub>4</sub> uptake at ambient conditions and ultramicropores developed by a judicious KOH activation process as the key component.

On the other hand, contamination of water by heavy metal ions is a serious issue for health and environmental reasons due to their toxic and nonbiodegradable properties.<sup>26–30</sup> For example, antimony (Sb) has been widely utilized in numerous industrial areas, such as production of batteries, ceramics, chemicals, and flame retardants.<sup>31–35</sup> Antimony species are highly toxic compounds known as high priority pollutants determined by the USEPA and EU, by which the maximum permissible concentrations for Sb species in drinking water are 6 and 5 µg l<sup>-1</sup>, respectively.<sup>33,35</sup> In environmental species, antimony is mainly found in two oxidation states of Sb<sup>3+</sup> and Sb<sup>5+</sup>. Most oxygenated systems contain predominately Sb<sup>5+</sup> formed as Sb(OH)6<sup>-</sup>.<sup>32,33</sup> Sb<sup>3+</sup> mainly formed as Sb(OH)<sub>3</sub> is almost ten times more toxic than Sb<sup>5+</sup>.<sup>31,33,36</sup>

Among various methods for removing heavy metal ions, an adsorption-based removal process is the most widely utilized due to its effectiveness and economic benefits.<sup>26,27,29,30</sup> In general, large SSA and basic surface functionality of adsorbents forming complexes with metal ions are needed for effective removal of metal ions from aqueous solutions.<sup>26–30</sup> As efficient adsorbents for metal ion adsorption, carbonaceous materials have been widely implemented due to the aforementioned features.<sup>27,29,30</sup>

Herein, the role of porosity (*i.e.*, PSA and SSA) and polarity (*i.e.*, N-doping) of carbonaceous materials for adsorption applications are presented. Different precursors of resorcinol-formaldehyde (RF) and highly N-containing dopamine are utilized to prepare RFC and highly N-doped MC spheres that are further activated by hot CO<sub>2</sub> treatment to finely control PSD, SSA, and pore volume. The importance of carbon ultramicroporosity is revealed in that CH<sub>4</sub> adsorption and adsorption-based selective separation of CH<sub>4</sub> over N<sub>2</sub> are strongly correlated with accumulated pore volumes of 0.7 nm and 1 nm of both carbons regardless of surface polarity. This result is ascribed to the high polarizability and nonpolar nature of CH<sub>4</sub>. Carbons with highest ultramicropore volumes show ultrahigh CH<sub>4</sub> uptake capacities and superb selectivity for CH<sub>4</sub>

over N<sub>2</sub>, comparable with the best results from MOFs, MOPs, zeolites, and carbonaceous materials.

In addition, adsorption of heavy metal ions (Fe<sup>2+</sup>, Sb<sup>3+</sup>, and Sb<sup>5+</sup>) is achieved to reveal the role of SSA and polarity of carbons. The SSAs of the RFC series are highly correlated with Fe<sup>2+</sup> adsorption capacity ( $R^2 = 0.98$ ). Conversely, MC samples are located in the upper region of the plotted line for RFC samples due to their basic nature caused by high loading of N-doping within a carbon framework. Furthermore, RFC\_C60 and MC\_C55 with similar porosity but different N-doping levels are utilized for selective adsorption of Sb<sup>3+</sup> over Sb<sup>5+</sup>. The more basic MC\_C55 has higher selectivity, indicating the role of carbon surface polarity. The structure–property relationship of carbons for adsorption of gas molecules and heavy metal ions is elucidated herein along with design principles of nanoporous carbonaceous materials for use in specific adsorption applications.

## 2. Experimental section

### 2.1 Reagents and chemicals

Resorcinol (Junsei), formaldehyde (38%, Amresco), dopamine hydrochloride (Sigma Aldrich), and ammonia solution (28%, Daejung) were used for synthetic carbons. Iron(III) nitrate hexahydrate (99%, Sigma Aldrich), potassium antimonyl tartrate hemihydrate (99.5%, Daejung), potassium hexahydroantimonate (99%, Sigma Aldrich), and pH 5 buffer solution (98%, Daejung) were used for metal ion adsorption experiments. High purity gas was used for all adsorption experiments (N<sub>2</sub>: 99.999%, CH<sub>4</sub>: 99.95%).

### 2.2 Synthesis of RFP, MP and RFC, MC samples

To synthesize resorcinol-formaldehyde polymers (RFP), resorcinol (0.14 g) and formaldehyde (0.16 g, 28%) were mixed with a solution containing (200 ml) deionized water (H<sub>2</sub>O) and aqueous ammonia (0.7 g, 28% NH<sub>4</sub>OH). After stirring for 24 h at room temperature, the reaction mixture was moved to an oven and was subsequently heated for 24 h at 90 °C without stirring. Solid product was recovered by centrifugation and was washed several times with deionized water.

To synthesize melanin polymers (MP), 1.08 g of dopamine hydrochloride was dissolved in 280 ml of deionized water and 80 ml of ethanol. Under vigorous stirring, 1 ml of aqueous ammonia solution (28% NH<sub>3</sub> (aq.)) was added to a dopamine hydrochloride solution at room temperature. After stirring for 12 hours, melanin-like nanoparticles were retrieved by centrifugation and were washed with deionized water and ethanol several times.

To obtain carbon samples, RFP was heated from ambient temperature to 800 °C under a N<sub>2</sub> atmosphere over 3 h at a heating rate of 4.3 °C per min, and then denoted as RFC. In the melanin polymer carbonization process, MP samples underwent carbonization at 800 °C (N<sub>2</sub> atmosphere over 3 h at a heating rate of 4.3 °C per min). These carbon samples were denoted as MC.



### 2.3 CO<sub>2</sub> activation process

CO<sub>2</sub> activation was performed using 250 mg of carbon samples. The samples were placed in an alumina boat in a quartz tube in the isothermal zone of a tubular furnace that was purged with flowing nitrogen. The samples were heated to 900 °C (heating rate 30 °C per min) under inert conditions (N<sub>2</sub>), followed by changing the gas flux to CO<sub>2</sub> (1000 cc per min) for various times (e.g., 60, 120, 250, and 380 min). CO<sub>2</sub> activated carbon samples were denoted as RFC\_CX and MC\_CX, where X is CO<sub>2</sub> activation time.

### 2.4 Adsorption measurements for Fe<sup>2+</sup> ion and calculation of adsorption capacity using Langmuir method

A stock solution of Fe ions was prepared by dissolving Fe(NO<sub>3</sub>)<sub>2</sub>·6H<sub>2</sub>O in deionized pH 5 buffer solution at 2.1 mM (410 ppm). Different carbon samples (10 mg) were added to 10 ml of pH 5 buffer solution, and the mixture was stirred for various amounts of time (e.g., 30, 60, 120, 360, and 720 min). Next, an aliquot of the sample was removed and centrifuged to separate the solid and liquid. Finally, the concentration of metal ion in the supernatant was analyzed by UV-vis spectrometry. The calibration curve of the different concentrations of Fe<sup>2+</sup> and UV-vis results for carbon samples are in the Fig. S1.† The adsorption capacity of adsorbent at equilibrium was calculated by the following equation:

$$q_e = \frac{(C_0 - C_e)V}{W}$$

where  $q_e$  is equilibrium adsorption capacity of adsorbent in mg g<sup>-1</sup>,  $C_0$  is initial concentration in mg l<sup>-1</sup>,  $C_e$  is equilibrium concentration of Fe ion in mg l<sup>-1</sup>,  $V$  is volume in l of Fe ion solution, and  $W$  is weight in g of adsorbent (carbon sample).

The isotherm data were correlated with Langmuir models. A Langmuir isotherm is based on monolayer sorption of metal ion on the surface of adsorbent and is described by the following equation:

$$q_e = \frac{q_m C_e b}{1 + C_e b}$$

where  $q_e$  is adsorption capacity of adsorbent in mg g<sup>-1</sup> and  $C_e$  is concentration of metal ion in mg l<sup>-1</sup> at equilibrium. The  $q_m$  is maximum adsorption capacity of the metal monolayer in mg g<sup>-1</sup>, and  $b$  is a constant that refers to the bonding energy of adsorption in l mg<sup>-1</sup>. According to the Langmuir isotherm model, the metal ion adsorption process occurs at specific homogeneous sites on the adsorbent surface with monolayer formation. This model is used to estimate the maximum adsorption capacity<sup>37</sup> ( $q_m$ ).

### 2.5 Adsorption measurements for Sb<sup>3+</sup> and Sb<sup>5+</sup> ions and capacity

To make Sb(III) 1000 ppm solutions, potassium antimonyl tartrate hemihydrate (1.38 g) was mixed with a solution containing (500 ml) deionized water (H<sub>2</sub>O). To make Sb(V) 1000 ppm solutions, potassium hexahydroxoantimonate (1.08 g) was mixed with a solution containing (500 ml) deionized

water (H<sub>2</sub>O). And the two solutions were mixed 1 : 1 and serially diluted to the target concentration (50, 500 ppb). An aqueous solution (30 ml) with a suitable concentration of Sb ions was shaken with a suitable amount of adsorbent at 20 °C for a definite period. Acid (hydrochloric acid) and base (potassium hydroxide) solutions were added to adjust pH, which was measured with a digital pH meter. After removing the adsorbent by centrifugation, the concentrations of anions remaining in the supernatant were determined by anodic stripping voltammetry (PDV 6000 plus, Modern Water, UK) to determine each Sb ion (Sb<sup>3+</sup> and Sb<sup>5+</sup>) and inductive coupled plasma mass spectroscopy (NexION 300X, Perkin Elmer, USA) to determine total Sb ions. The adsorption isotherms were studied with varying initial concentrations of Sb ions at a fixed dose of adsorbent (10 mg). The adsorption density, given as μmol-Sb/g adsorbent, was calculated from the residual concentrations of Sb ions, known initial concentrations of Sb ions (μM), and amount of adsorbent used (g).

### 2.6 Calculation of Henry's law selectivity

Selectivity is calculated using the ratio of Henry's law constants, which is estimated from the initial slopes of CH<sub>4</sub> ( $I_{CH_4}$ ) and N<sub>2</sub> ( $I_{N_2}$ ) adsorption isotherms (0–0.1 bar):

$$S = \frac{I_{CH_4}}{I_{N_2}}$$

### 2.7 Töth isotherm calculation for carbon samples

The Töth model was applied to all of CH<sub>4</sub> and N<sub>2</sub> adsorption isotherms of activated carbon samples. The Töth isotherm equation can be expressed:

$$q = \frac{q_m K_i p}{[1 + (K_i p)^n]^{1/n}}$$

where  $q$  and  $q_m$  are the absolute amount adsorbed and the maximum amount adsorbed capacity.  $K_i$  is the adsorption constant, related to the adsorption energy and the affinity of gas molecules.  $n$  is an exponent related to the heterogeneity of the adsorbent surface.

### 2.8 Characterizations

Low temperature nitrogen adsorption–desorption isotherms were measured at –196 °C on an adsorption volumetric analyzer BEL MAX manufactured by BEL, Inc (Japan). CH<sub>4</sub> and N<sub>2</sub> adsorption isotherms were located at 0 °C and 25 °C on the adsorption volumetric analyzer (BEL MINI). All samples were degassed at 200 °C for 12 h under static vacuum before adsorption measurements. Specific surface area was determined by the Brunauer–Emmett–Teller (BET) method from nitrogen adsorption isotherms in the relative pressure range of 0.05–0.20. Total pore volume ( $V_t$ ) was estimated from the amount of gas adsorbed at relative pressure  $P/P_0 = 0.99$ . PSD and accumulated pore volume of RFC and MC samples were calculated from adsorption branches of nitrogen sorption isotherms using the NLDFT (nonlocal density functional theory)



method for slit-like pores available in BEL master software from BEL Inc. The volume of pores below 0.7, 1, and 2 nm were calculated on the basis of accumulated pore volumes. Isothermic heat of adsorption ( $Q_{st}$ ) was calculated using the Clausius–Clapeyron equation. Surface functional groups of carbon samples were determined by recording FTIR spectra on a Varian Corporation (USA) Varian Scimitar 1000 FT-IR. Scanning electron microscopy (SEM) images were obtained with a HITACHI S-4800 microscope with accelerating voltage of 15.0 kV. Elemental analyses (EA) were obtained using FLASH EA1112. TEM images were recorded on a transmission electron microscope (JEM-2100F). UV-vis spectrometer data was recorded by Optizen 2120UV (MECASYS Inc.). The pH value was obtained from is inoLab\_IDS Multi 9420 and ICP results was recorded from NexION 300X (Perkin elmer Inc). The zeta potential results were obtained from EPELS-Z1 (Otsuka Inc).

### 3. Results and discussion

#### 3.1 Synthesis of carbon spheres and their textural features

Two carbon spheres (RFC and MC) with different N-containing levels are chosen to elucidate the role of porosity and polarity of carbon spheres for  $\text{CH}_4$  adsorption, adsorption-based separation of  $\text{CH}_4$  over  $\text{N}_2$ , and heavy metal ion adsorption. First, Monodisperse RFP spheres with size of  $548 \pm 23$  nm are synthesized by the modified sol–gel method reported elsewhere<sup>38,39</sup> (Fig. 1a). RF precursor is polymerized under water-ethanol mixture as a solvent with  $\text{NH}_3$  catalyst for 24 h and is subsequently aged for 24 h at  $100^\circ\text{C}$ . It was revealed that  $\text{NH}_3$  acts as a base catalyst as well as a nitrogen additive, resulting in polymer spheres with nitrogen content less than 2.8 wt% (Table 1).<sup>38</sup> Conversely, dopamine is chosen as a precursor to synthesize highly N-containing polymer spheres. Dopamine precursor is cross-linked *via* spontaneous oxidation under basic ammonia solution with  $\text{O}_2$ ,<sup>40</sup> resulting in melanin-like polymer (MP)

spheres with size of  $393 \pm 21$  nm and N-content of 19.2 wt% (Fig. 2a and Table 1). Both carbons are subsequently carbonized at  $800^\circ\text{C}$  and denoted as RFC and MC. The RFC sphere is reduced to  $440 \pm 21$  nm, probably due to radial shrinkage during carbonization (Fig. 1b).<sup>38,40–43</sup> To control PSD and SSA, hot  $\text{CO}_2$  treatment at  $900^\circ\text{C}$  is carried out for RFC spheres, denoted as RFC\_C50, C120, C250, and C380, respectively, where C indicates  $\text{CO}_2$  activation time. According to SEM investigation (Fig. 1c–f), the sizes of  $\text{CO}_2$ -activated RFC spheres (RFC\_C50, C120, C250, and C380) are reduced to  $400 \pm 20$ ,  $358 \pm 19$ ,  $301 \pm 18$ , and  $256 \pm 27$  nm, respectively, which is attributed to carbon loss during the activation process ( $\text{CO}_2(\text{g}) + \text{C}(\text{s}) \rightarrow 2\text{CO}(\text{g})$ ).<sup>39,41–43</sup> Such carbon loss is also identified under TEM investigation, in which the highly porous nature of the RFC\_C380 sphere compared to the RFC sphere is observed (Fig. 3a and b). A similar shrinkage trend is observed for MC reduced to  $162 \pm 17$  nm, and the sizes of  $\text{CO}_2$ -activated MC spheres of MC\_C55 and C125 are  $130 \pm 18$  and  $108 \pm 18$  nm, respectively (Fig. 2b–d). Successful  $\text{CO}_2$  activation for MC\_C125 with a highly porous nature compared to MC is also identified under TEM investigation (Fig. 3c and d).

The textural features of RFC and MC series were analyzed by nitrogen sorption isotherm measurements. As-prepared RFC shows intrinsic microporosity of a type I isotherm (Fig. 4a). As  $\text{CO}_2$  activation prolongs, the amount adsorbed at low relative pressure abruptly increases, indicating the development of microporosity (Fig. 4a). Features of type IV isotherms appeared for RFC\_C250 and C380, in which more carbon loss with longer activation treatment generates larger mesopores (Fig. 4a).<sup>39,41–43</sup> According to PSD analysis determined by the NLDFT model, sharp increases in ultramicropores centered around 0.6–0.7 nm are identified for RFC\_C60 and C120 samples, strongly suggesting that relative fine-tuning of ultramicropores is possible for carbonaceous materials with  $\text{CO}_2$  activation (Fig. 4b). SSAs




Fig. 1 SEM image of RFP (a), RFC (b), RFC\_C60 (c), RFC\_C120 (d), RFC\_C250 (e) and RFC\_C380 (f).



**Table 1** Textural properties, CH<sub>4</sub>, N<sub>2</sub> uptake capacities with Q<sub>st</sub> values, N contents, Fe ion adsorption capacities, and Sb<sup>3+</sup>/Sb<sup>5+</sup> selectivity for RFC and MC samples

Sample	Pore volume (cm <sup>3</sup> g <sup>-1</sup> )				BET surface area <sup>c</sup> (m <sup>2</sup> g <sup>-1</sup> )	N (wt%)	CH <sub>4</sub> adsorption (273 K/298 K) (mmol g <sup>-1</sup> )	Selectivity (CH <sub>4</sub> /N <sub>2</sub> ) (273 K/298 K)	Q <sub>st</sub> CH <sub>4</sub> [kJ mol <sup>-1</sup> ]	Q <sub>st</sub> N <sub>2</sub> [kJ mol <sup>-1</sup> ]	Fe <sup>2+</sup> adsorption (q <sub>m</sub> ) (mg g <sup>-1</sup> )	Selectivity (Sb <sup>3+</sup> /Sb <sup>5+</sup> ) (500 ppb) at pH 5
	0.7 <sup>a</sup> nm	1 <sup>a</sup> nm	2 <sup>a</sup> nm	Total <sup>b</sup>								
RFC	0.11	0.22	0.28	0.38	628	1.61	1.83/1.26	3.8/4.2	18.2	5.1	16	—
RFC_C60	0.67	0.9	0.91	0.88	1649	1.55	2.64/1.75	5.7/6.8	21.8	5.7	33	2.0
RFC_C120	0.5	0.71	1.23	1.25	2688	1.34	2.26/1.50	4.9/5.3	20.3	6.1	61	—
RFC_C250	—	—	—	1.61	3572	1.1	—	—	—	—	72	—
RFC_C380	—	—	—	2.4	3958	0.8	—	—	—	—	101	—
MC	0.17	0.24	0.28	0.35	561	11.7	1.78/0.93	4.7/5.3	16.1	4.9	21	—
MC_C55	0.58	0.81	0.88	0.86	1550	5.9	2.41/1.62	6.1/7.4	20.2	5.4	42	3.3
MC_C125	0.43	0.65	1.2	1.23	2544	2.4	2.15/1.39	5.7/6.0	18.9	6.0	70	—

<sup>a</sup> Accumulated pore volume obtained from NLDFT method. <sup>b</sup> Measured at P/P<sub>0</sub> = 0.99. <sup>c</sup> Obtained from BET method.

obtained from the BET method for RFC samples (RFC, RFC\_C60, C120, C250, and C380) increased from 628 to 1649, 2688, 3572, and 3958 m<sup>2</sup> g<sup>-1</sup>, respectively, indicating the power of this activation process (Table 1). In addition, a similar pattern was observed for MC samples (MC, MC\_C55 and C125). There was a sharp increase in the amount adsorbed at a relative pressure, with abrupt development of ultramicropores around 0.6–0.7 nm and large increases in SSAs from 561 to 1550 and 2544 m<sup>2</sup> g<sup>-1</sup>, respectively (Fig. 4c and d, and Table 1).

The nitrogen contents of RFC series (RFC, RFC\_C60, C120, 250, and C380) are 1.61, 1.55, 1.34, 1.1, and 0.8 wt% (Table 1), respectively, indicating a gradual decrease in nitrogen content that is probably due to the less stabilized nature of nitrogen species during activation.<sup>38</sup> In contrast, the nitrogen contents of MC series (MC, MC\_C55, and C125) are 11.7, 5.9, and 2.4 wt%, definitely showing higher nitrogen content than the RFC series (Table 1). There are huge nitrogen content differences of 1.55 and 5.9 wt% for RFC\_C60 and MC\_C55, respectively. Considering the similar textural features, SSA, and PSD of both carbons, a polarity issue derived from N-doping could be of interest in specific adsorption applications. FR-IR measurements (Fig. 5 and Table S1<sup>†</sup>) identify the development of several peaks indicating nitrogen species within the carbon framework: 1260 cm<sup>-1</sup> for out of plane mode of pyrrole ring, 1389 cm<sup>-1</sup> for C–N stretching, and 1405 cm<sup>-1</sup> for vibration peak of N=O.

According to the zeta potential measurements for all carbon samples, it is identified that as prolonged CO<sub>2</sub>-activation process, the zetapotential values slightly and gradually changes from –14 mV (RFC) to –7 mV (RFC\_C380) in the Fig. S2.<sup>†</sup> This is probably that hot CO<sub>2</sub> treatment at 900 °C, relatively less stable N moiety is more damaged and disappeared easily, eventually reducing the surface polarity of the carbons with prolonged CO<sub>2</sub>-activation, which also identified from the N contents obtained from EA analysis in the Table 1. Similarly, the zetapotential values from –26, –22, and –19 mV were identified for MC and MC\_C55 and C125 samples, respectively (Fig. S2<sup>†</sup>), confirming the disappearance of N content along prolonged CO<sub>2</sub>-activation process, in which the decrease of N content is also observed from EA analysis (Table 1).

### 3.2 Adsorption-based separation of CH<sub>4</sub> over N<sub>2</sub>: role of ultramicroposity

CH<sub>4</sub> adsorption isotherms for RFC samples (RFC, RFC\_C60, and C120) and MC samples (MC, MC\_C55, and C125) are measured at 273 K and 298 K (Fig. 6 and S3<sup>†</sup>). The CH<sub>4</sub> uptake capacities of RFC samples (RFC, RFC\_C60, and C120) at 273 K (1 bar) are 1.83, 2.64, and 2.26 mmol g<sup>-1</sup>, respectively; those of MC samples are 1.78, 2.41, and 2.15 mmol g<sup>-1</sup>, respectively (Fig. 6a and b and Table 1). CH<sub>4</sub> adsorption capacities of 2.64 mmol g<sup>-1</sup> for RFC\_C60 and 2.41 mmol g<sup>-1</sup> for MC\_C60 at 273 K (1 bar) are ranked among the highest CH<sub>4</sub> uptake capacities from MOFs, MOPs, and carbonaceous materials (Table 2). In addition, CH<sub>4</sub> adsorption capacities of RFC samples (RFC, RFC\_C60, and C120) and MC samples (MC, MC\_C55, and C125) at 298 K (1 bar) are 1.26, 1.75, and 1.50, and 0.93, 1.62, and 1.39 mmol g<sup>-1</sup>, respectively, demonstrating the ultrahigh CH<sub>4</sub> adsorption






Fig. 2 SEM images of MP (a), MC (b), MC\_C55 (c), and MC\_C125 (d).

ability of both carbons (Fig. S3,† Tables 1 and 2). Strong correlation is observed between the accumulated ultramicropore volumes (<0.7 nm and <1 nm) for both RFC and MC series and CH<sub>4</sub> adsorption capacities (Fig. 6c and d). Both carbons (RFC\_C60 and MC\_C55) with higher accumulated ultramicropore volumes present the highest CH<sub>4</sub> uptake capacities compared to others, strongly suggesting how to effectively enhance adsorption capacity within ultramicropores for small CH<sub>4</sub> molecules (3.80 Å).<sup>2,37</sup>

N<sub>2</sub> adsorption isotherms for RFC and MC series are measured at 273 K and 298 K (Fig. 6a and b, S3a and b and S4d and e†). Unlike CH<sub>4</sub> adsorption, which is well correlated with ultramicropore volumes, N<sub>2</sub> adsorption is well correlated with the SSA ( $R^2 = 0.95$ ) of both carbon samples (Fig. 6f and S3f†). There is no relationship between surface polarity and N<sub>2</sub> loading levels, which is probably ascribed to the moderate polarity of the carbon surface and small quadrupole moment of




Fig. 4 Nitrogen isotherm of RFC (a) and MC (c) samples at 77 K. Pore size distribution of RFC (b) and MC (d) samples by NLDFT method.

N<sub>2</sub> ( $-4.72 \times 10^{-40} \text{ cm}^2$ ). The  $Q_{st}$  values for RFC\_C60 and MC\_C55 are 5.7 and 5.4 kJ mol<sup>-1</sup>, respectively. Considering the nitrogen content of both carbons, 1.55 and 5.9 wt%, respectively, the polarity effect for N<sub>2</sub> adsorption does not exist for either carbon series (Table 1).

All the CH<sub>4</sub> and N<sub>2</sub> isotherms were well fitted to Töth model (Fig. 6a and b and S3a and b†) and the parameters of the fitting are presented in Table S2.† The Töth model is a semi-empirical expression that effectively describes many systems with sub-monolayer coverage and presents correct behavior at both the low and high pressure ends, reducing deviation errors between experimental data and calculated values of adsorption equilibrium.<sup>44–49</sup> It is noteworthy that the parameter  $n$  presents the system heterogeneity.<sup>22,44–49</sup> If the heterogeneity parameter  $n$  becomes unity, it is identical to the Langmuir model presenting homogeneous surface; in contrast, if this parameter is lower than unity, the more heterogeneous system is expected.<sup>44–46</sup> According to the heterogeneity parameters of CH<sub>4</sub> on the carbon samples (Table S2†), the values are in the range 0.5–0.67,




Fig. 3 TEM images of RFC (a), RFC\_C380 (b), MC (c), and MC\_C125 (d).




Fig. 5 FT-IR spectra of RFC\_C60 and MC\_C55.






Fig. 6 CH<sub>4</sub> and N<sub>2</sub> isotherm of RFC (a) and MC (b) samples at 273 K (red line is Töth isotherm fitting). Distribution of pore volumes between pores of less than 0.7 nm (black), less than 1 nm (red), and less than 2 nm (blue) of RFC (c) and MC (d) samples at 273 K. Relationship plot of CH<sub>4</sub> adsorption capacities with respect to accumulated ultramicropore volume of 0.7 nm (e) and relationship plot of N<sub>2</sub> adsorption capacities with respect to BET surface area (f) of RFC and MC samples at 273 K.

inferring that the surface heterogeneity of carbon surfaces strongly favors CH<sub>4</sub> adsorption.<sup>4,46,47</sup> Since the carbon samples with highest CH<sub>4</sub> uptake present lowest *n* values (0.5–0.52 for RFC\_C60 and 0.51–0.54 for MC\_C55), it turns out that the role ultramicroporosity is pivotal to enhance the CH<sub>4</sub> uptake capacity. On the other hands, the values of heterogeneity parameters of N<sub>2</sub> on the carbon samples (Table S2†) are closed to unity, suggesting the less interaction between N<sub>2</sub> and the carbon surface.

The isosteric heat of adsorption (*Q<sub>st</sub>*) values of carbon samples also suggest the same trend (Table 1). Therefore, the development of ultramicropores is pivotal to enhance CH<sub>4</sub> adsorption capacity at equilibrium adsorption under ambient conditions. To further elucidate the importance of ultramicropores for CH<sub>4</sub> adsorption, CH<sub>4</sub> adsorption capacities of

both carbon samples are plotted with respect to accumulated ultramicropore volume (<0.7 nm and <1 nm) (Fig. 6e and S4a†).

Good correlation ( $R^2 = 0.94$ ) is obtained for accumulated ultramicropore volumes. In contrast, no correlation is obtained for accumulated pore volume up to 2 nm and SSA (Fig. S4b and c†), strongly indicating the importance of ultramicropore development. Such high correlation also indicates that polarity derived from N-doping on the carbon surface is not related to CH<sub>4</sub> adsorption due to the nonpolar nature of CH<sub>4</sub>.<sup>1,2,17</sup>

The adsorption-based selectivities of CH<sub>4</sub> over N<sub>2</sub> for RFC and MC samples at 273 K and 298 K are calculated using the ratio of Henry's law constants derived from single gas isotherms (Tables 1 and S3†).

The selectivity trend at 298 K for RFC samples (RFC, RFC\_C60, and C120) and MC samples (MC, MC\_C55, and C125)



Table 2 Comparison of CH<sub>4</sub> adsorption and CH<sub>4</sub>/N<sub>2</sub> selectivity of various absorbents measured at 273 K and 298 K

Sample	CH <sub>4</sub> adsorption 273 K/298 K (1 bar, mmol g <sup>-1</sup> )	Selectivity 273 K/298 K (CH <sub>4</sub> /N <sub>2</sub> )	Reference
[Ni <sub>3</sub> (HCOO) <sub>6</sub> ]/MOF	—/0.791	—/6.02	Ref. 1
[Cu(INA) <sub>2</sub> ]/MOF	—/0.827	—/8.34	Ref. 1
Ni formate/MOF	—/0.75	—/6.1	Ref. 2
AC G2X7/carbon	1.9/1.3	6.17/4.38	Ref. 3
MAC/carbon	—/0.98	—/3	Ref. 4
K-PAF-600/carbon	2.4/-	—	Ref. 10
sOMC/carbon	0.9/1.3	3.8/3.7	Ref. 17
BPL calgon/carbon	—/0.8	—/5.0	Ref. 18
Poly(vinylidene chloride)-based carbon/carbon	—/1.8	—	Ref. 19
Hb/zeolite	0.8/0.6 (303 K)	—/2 (303 K)	Ref. 20
Nab/zeolite	0.6/0.4 (303 K)	—/1.75 (303 K)	Ref. 20
DBT/porous polymer	1.1/0.9	8.0/7.6	Ref. 21
Basolite A 100/MOF	1.12/0.71	4.8/3.7	Ref. 22
Cu(Me-4py-trz-ia)/MOF	1.8/1.5	4.6/4.2	Ref. 22
MOF-505/MOF	1.39/-	—	Ref. 23
CPC550/carbon	2.7/1.7	—	Ref. 25
RFC_C60	2.64/1.75	5.7/6.8	In this work
MC_C55	2.41/1.62	6.1/7.4	In this work

is very similar to the CH<sub>4</sub> uptake capacities, which are 4.2, 6.8, and 5.3, and 5.3, 7.4, and 6.0, respectively. A similar trend is also observed for selectivities measured at 273 K (Table 1). Higher CH<sub>4</sub> adsorption capacity due to the development of more ultramicropores results in higher CH<sub>4</sub> over N<sub>2</sub> selectivity, suggesting that differences in CH<sub>4</sub> adsorption capacities between carbons is more sensitive than differences in N<sub>2</sub> adsorption.

This result is further identified as a difference in Henry's constants (Table S3<sup>†</sup>). The development of ultramicropores is not only helpful for enhanced CH<sub>4</sub> adsorption but also for high selectivity of separating CH<sub>4</sub> over N<sub>2</sub>. With its higher polarizability value, CH<sub>4</sub> is more sensitively adsorbed within ultramicropores rather than the less polarizable N<sub>2</sub>.<sup>1,2,17</sup> Ideal adsorption selectivities of 6.8 for RFC\_C60 and 7.4 for MC\_C55 at 298 K are ones of the highest values comparable with those of MOFs, MOPs, and carbonaceous materials (Table 2). With combining the superb CH<sub>4</sub> uptake capacities, such ultrahigh selectivities of CO<sub>2</sub>-activated RFC and MC carbons are highly desirable for adsorption-based UCN upgrading.

### 3.3 Adsorption of heavy metal ions: role of SSA and polarity

In attempts to elucidate the role of SSA and polarity of carbons, adsorption of heavy metal ions (Fe<sup>2+</sup>, Sb<sup>3+</sup>, and Sb<sup>5+</sup>) is carried out using aqueous solutions at pH 5 under ambient condition. First, Fe<sup>2+</sup> adsorption equilibrium isotherms for RFC samples (RFC, RFC\_C60, C120, C250, and C380) and MC samples (MC, MC\_C55, and C120) are measured as functions of time (Fig. 7a and b). The carbon samples of RFC, RFC\_C60 and C120, MC, and MC\_C55 reach adsorption equilibrium in less than 2 h. Conversely, RFC\_C250, C380, and MC\_C125 require more than 6 h for adsorption saturation, strongly indicating the relationship of adsorption capacity and porosity. Then, equilibrium isotherms are fitted with the Langmuir isotherm model<sup>26–30</sup> (detailed parameters are explained in the Experimental section).

Obtained  $q_m$  values from RFC samples are plotted with respect to SSA (Fig. 7c). A good relationship ( $R^2 = 0.97$ ) between the  $q_m$  values and SSAs of RFC samples is identified, as has been reported in the literature.<sup>49–53</sup> Thus, the superb  $q_m$  value (101 mg g<sup>-1</sup>) for RFC\_C390 is attributed to ultrahigh SSA of 3958 m<sup>2</sup> g<sup>-1</sup> derived from a prolonged CO<sub>2</sub> activation process. When the  $q_m$




Fig. 7 Equilibrium isotherms of Fe ion adsorption of RFC (a) and MC (b) samples. Relationship plot of Fe ion adsorption capacities with respect to BET surface area (c).








Fig. 8 Selectivity of Sb<sup>3+</sup>/Sb<sup>5+</sup> using RFC\_C60 (a) and MC\_C55 (b) at 50 and 500 ppb in pH 5 buffer solution. (Inset number in figure is Sb<sup>3+</sup>/Sb<sup>5+</sup> selectivity).

values of MC samples are compared with those of RFC samples, they are located on the upper region of the plotted line, indicating a good correlation of the  $q_m$  values of RFC samples with SSA (Fig. 7c). According to nitrogen content and FT-IR analyses, surface polarity caused by N-doping is attributed to higher adsorption capacity of Fe<sup>2+</sup> under ambient conditions.

Another adsorption experiment that evaluates the polarity effect of carbons for selective adsorption of Sb<sup>3+</sup> over Sb<sup>5+</sup> is also performed. The selective adsorption experiment for Sb<sup>3+</sup> over Sb<sup>5+</sup> is achieved using RFC\_C60 and MC\_C55 samples with similar SSAs but different nitrogen contents (Table 1). Equimolar amounts of 50 and 500 ppb of two Sb species are adsorbed on RFC\_C60 and MC\_C55 samples at pH 5. The adsorption capacities with associated selectivities for Sb<sup>3+</sup> over Sb<sup>5+</sup> of RFC\_C60 and MC\_C55 on different concentrations are plotted in Fig. 8a and b, respectively. The adsorption capacities for Sb<sup>3+</sup> are very similar for both carbons, whereas the adsorption capacity trend for Sb<sup>5+</sup> is quite different.

MC\_C55 adsorbs substantially less Sb<sup>5+</sup> than RFC\_C60. Considering the charge characters of Sb species, Sb<sup>3+</sup> (neutral charge as Sb(OH)<sub>3</sub>) and Sb<sup>5+</sup> (negative charge as Sb(OH)<sub>6</sub><sup>-</sup>), the different adsorption trends for Sb<sup>5+</sup> are ascribed to the more basic MC\_C55 preferentially adsorbing less negatively charged Sb<sup>5+</sup> under the specific conditions. Therefore, the higher selectivity of MC\_C55 compared to RFC\_C60 of up to 3.3 for Sb<sup>3+</sup> over Sb<sup>5+</sup> is accomplished. This result indicates the role of polarity in selective adsorption of metal ions.

## 4. Conclusions

The role of porosity and polarity of carbonaceous materials for selective separation of CH<sub>4</sub> over N<sub>2</sub>, adsorption of heavy metal ions, and selective adsorption of Sb species were elucidated using synthesized carbon spheres with different N-doping levels. Hot CO<sub>2</sub> treatment allows fine-control of the PSA and SSA of RFC and highly N-doped MC samples. The development of ultramicropores is highly desirable for enhanced CH<sub>4</sub> uptake regardless of the surface polarity of carbons, which eventually

results in ultrahigh selectivity for CH<sub>4</sub> over N<sub>2</sub>. The CH<sub>4</sub> adsorption capacities of the most developed ultramicropores of RFC\_C60 and MC\_C55 are 2.64 and 2.41 mmol g<sup>-1</sup> at 273 K (1 bar), respectively, and these carbons also have superb selectivities of CH<sub>4</sub> over N<sub>2</sub> of 6.8 and 7.1 at 298 K, respectively, which are ones of the best values for CH<sub>4</sub> adsorbents. In addition, Fe<sup>2+</sup> ion is more adsorbed on carbons with higher SSAs. N-doped MC samples present higher adsorption capacities over RFC samples. Higher selective adsorption for Sb<sup>3+</sup> over Sb<sup>5+</sup> is accomplished for the basic MC\_C55 sample, strongly suggesting that the choice of carbon surface polarity is important for selective metal ion adsorption. Distinct correlations between porosity and polarity of carbons, adsorption capacities for CH<sub>4</sub>, ultrahigh selectivity for CH<sub>4</sub> over N<sub>2</sub>, and metal ions are exclusively elucidated. The results provide design principles for nanoporous carbonaceous materials and use in specific adsorption applications.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

The authors thank Prof. H. Chun regarding CH<sub>4</sub> adsorption. This work was supported by the Korea Environmental Industry and Technology Institute (KEITI, No. 2016000200005).

## References

- 1 J. A. Delgado, M. A. Uguina, J. L. Sotelo and B. Ruiz, *Sep. Purif. Technol.*, 2006, **50**, 192–203.
- 2 B. Yuan, X. Wu, Y. Chen, J. Huang, H. Luo and S. Deng, *Environ. Sci. Technol.*, 2013, **47**, 5474–5480.
- 3 M. S. A. Baksh, R. T. Yang and D. D. L. Chung, *Carbon*, 1989, **27**, 931–934.
- 4 J. Cai, J. Qi, C. Yang and X. Zhao, *ACS Appl. Mater. Interfaces*, 2014, **6**, 3703–3711.
- 5 X. Xu, X. Zhao, L. Sun and X. Liu, *J. Nat. Gas Chem.*, 2008, **17**, 391–396.



- 6 N. K. Jensen, T. E. Rufford, G. Watson, D. K. Zhang, K. I. Chan and E. F. May, *J. Chem. Eng. Data*, 2011, **57**, 106–113.
- 7 J. Hu, T. Sun, X. Liu, Y. Guo and S. Wang, *RSC Adv.*, 2016, **6**, 64039–64046.
- 8 X. Ren, T. Sun, J. Hu and S. Wang, *Microporous Mesoporous Mater.*, 2014, **186**, 137–145.
- 9 J. Möllmer, M. Lange, A. Möller, C. Patzschke, K. Stein, D. Lässig, J. Lincke, R. Gläser, H. Krautscheid and R. Staudt, *J. Mater. Chem.*, 2012, **22**, 10274–10286.
- 10 Y.-X. Hu, S.-C. Xiang, W.-W. Zhang, Z.-X. Zhang, L. Wang, J.-F. Bai and B. Chen, *Chem. Commun.*, 2009, 7551–7553.
- 11 M. Saleh, H. M. Lee, K. C. Kemp and K. S. Kim, *ACS Appl. Mater. Interfaces*, 2014, **6**, 7325–7333.
- 12 A. Olajossy, A. Gawdzik, Z. Budner and J. Dula, *Chem. Eng. Res. Des.*, 2003, **81**, 474–482.
- 13 H. Yi, F. Li, P. Ning, X. Tang, J. Peng, Y. Li and H. Deng, *Chem. Eng. J.*, 2013, **215**, 635–664.
- 14 R. T. Yang, *Adsorbents: fundamentals and applications*, John Wiley & Sons, 2003.
- 15 R. T. Yang, *Gas separation by adsorption processes*, Butterworth-Heinemann, 2013.
- 16 D. M. Ruthven, *Chem. Eng. Technol.*, 2011, **83**, 44–52.
- 17 S. Ma and H.-C. Zhou, *Chem. Commun.*, 2010, **46**, 44–53.
- 18 D. Lässig, J. Lincke, J. Moellmer, C. Reichenbach, A. Moeller, R. Gläser, G. Kalies, K. A. Cychosz, M. Thommes and R. Staudt, *Angew. Chem., Int. Ed.*, 2011, **50**, 10344–10348.
- 19 Y. Li, T. Ben, B. Zhang, Y. Fu and S. Qiu, *Sci. Rep.*, 2013, **3**, 2420–2425.
- 20 L. Bastin, P. S. Bárcia, E. J. Hurtado, J. A. Silva, A. E. Rodrigues and B. Chen, *J. Phys. Chem. C*, 2008, **112**, 1575–1581.
- 21 B. Liu and B. Smit, *Langmuir*, 2009, **25**, 5918–5926.
- 22 Y. Zhu, H. Long and W. Zhang, *Chem. Mater.*, 2013, **25**, 1630–1635.
- 23 B. Liu and B. Smit, *J. Phys. Chem. C*, 2010, **114**, 8515–8522.
- 24 E. Haldoupis, S. Nair and D. S. Sholl, *J. Am. Chem. Soc.*, 2012, **134**, 4313–4323.
- 25 B. Ashourirad, A. K. Sekizkardes, S. Altarawneh and H. M. El-Kaderi, *Chem. Mater.*, 2015, **27**, 1349–1358.
- 26 X. Luo, X. Lei, N. Cai, X. Xie, Y. Xue and F. Yu, *ACS Sustainable Chem. Eng.*, 2016, **4**, 3960–3969.
- 27 B. Yang, C. Yu, Q. Yu, X. Zhang, Z. Li and L. Lei, *RSC Adv.*, 2015, **5**, 7182–7191.
- 28 X. Li, H. Zhou, W. Wu, S. Wei, Y. Xu and Y. Kuang, *J. Colloid Interface Sci.*, 2015, **448**, 389–397.
- 29 G.-X. Yang and H. Jiang, *Water Res.*, 2014, **48**, 396–405.
- 30 Z. Zhang, Z. Dong, Y. Dai, S. Xiao, X. Cao, Y. Liu, W. Guo, M. Luo and Z. Le, *RSC Adv.*, 2016, **6**, 102462–102471.
- 31 K. Simeonidis, V. Papadopoulou, S. Tresintsi, E. Kokkinos, I. A. Katsoyiannis, A. I. Zouboulis and M. Mitrakas, *Sustainability*, 2017, **9**, 238.
- 32 X. Guo, Z. Wu, M. He, X. Meng, X. Jin, N. Qiu and J. Zhang, *J. Hazard. Mater.*, 2014, **276**, 339–345.
- 33 A. Sarı, G. N. R. Şahinoğlu and M. Tüzen, *Ind. Eng. Chem. Res.*, 2012, **51**, 6877–6886.
- 34 U. EPA, US Environmental Protection Agency, Washington, DC, EPA, 2006.
- 35 S. Risica and S. Grande, *RAPPORTI ISTISAN*, 2000.
- 36 M. Krachler, H. Emons and J. Zheng, *Trends Anal. Chem.*, 2001, **20**, 79–90.
- 37 L. Nemes and L. Bulgariu, *Open Chem.*, 2016, **14**, 175–187.
- 38 J. Liu, S. Z. Qiao, H. Liu, J. Chen, A. Orpe, D. Zhao and G. Q. M. Lu, *Angew. Chem., Int. Ed.*, 2011, **50**, 5947–5951.
- 39 H. S. Kim, M. S. Kang and W. C. Yoo, *J. Phys. Chem. C*, 2015, **119**, 28512.
- 40 K.-Y. Ju, Y. Lee, S. Lee, S. B. Park and J.-K. Lee, *Biomacromolecules*, 2011, **12**, 625–632.
- 41 N. P. Wickramaratne and M. Jaroniec, *ACS Appl. Mater. Interfaces*, 2013, **5**, 1849–1855.
- 42 M. Kim, H. S. Kim, S. J. Yoo, W. C. Yoo and Y.-E. Sung, *J. Mater. Chem. A*, 2017, **5**, 4199–4206.
- 43 N. P. Wickramaratne, J. Xu, M. Wang, L. Zhu, L. Dai and M. Jaroniec, *Chem. Mater.*, 2014, **26**, 2820–2828.
- 44 D. D. Do, *Adsorption Analysis: Equilibria and Kinetics: (With CD Containing Computer Matlab Programs)*, World Scientific, 1998.
- 45 S. Loh, K. A. Rahman, A. Chakraborty, B. B. Saha, Y. S. Choo, B. C. Khoo and K. C. Ng, *J. Chem. Eng. Data*, 2010, **55**, 2840–2847.
- 46 D. P. Vargas, L. Giraldo and J. C. Moreno-Pirajan, *Int. J. Mol. Sci.*, 2012, **13**, 8388–8397.
- 47 A. P. Terzyk, J. Chatlas, P. A. Gauden, G. Rychlicki and P. Kowalczyk, *J. Colloid Interface Sci.*, 2003, **266**, 473–476.
- 48 D. Park, Y. Moon, H. Kim, H. Ahn and C. Lee, *Adsorption*, 2014, **20**, 631–647.
- 49 Y. Ying, A. M. Ribeiro, L. Ping, J. G. Yu and A. E. Rodrigues, *Ind. Eng. Chem. Res.*, 2014, **53**, 16840–16850.
- 50 K. Kadirvelu and C. Namasivayam, *Adv. Environ. Res.*, 2003, **7**, 471–478.
- 51 M. Prasad, S. Saxena and S. Amritphale, *Ind. Eng. Chem. Res.*, 2002, **41**, 105–111.
- 52 I. E. M. Carpio, J. D. Mangadlao, H. N. Nguyen, R. C. Advincula and D. F. Rodrigues, *Carbon*, 2014, **77**, 289–301.
- 53 M. Myglovets, O. Poddubnaya, O. Sevastyanova, M. E. Lindström, B. Gawdzik, M. Sobiesiak, M. Tsyba, V. Sapsay, D. Klymchuk and A. Puziy, *Carbon*, 2014, **80**, 771–783.

