



CrossMark  
click for updates

Cite this: *RSC Adv.*, 2017, 7, 13877

## Correction: DBU-catalyzed biobased poly(ethylene 2,5-furandicarboxylate) polyester with rapid melt crystallization: synthesis, crystallization kinetics and melting behavior

Jiaping Wu,<sup>a</sup> Hongzhou Xie,<sup>a</sup> Linbo Wu,<sup>\*a</sup> Bo-Geng Li<sup>a</sup> and Philippe Dubois<sup>\*bc</sup>

DOI: 10.1039/c7ra90035j

www.rsc.org/advances

Correction for 'DBU-catalyzed biobased poly(ethylene 2,5-furandicarboxylate) polyester with rapid melt crystallization: synthesis, crystallization kinetics and melting behavior' by Jiaping Wu *et al.*, *RSC Adv.*, 2016, 6, 101578–101586.

The authors regret that the chemical structure in Fig. 1 is incorrect. The corrected figure, in which CH–OH bonds have been corrected to C=O bonds, tetrahydrofuran rings have been corrected to furan rings, and a missed carbonyl oxygen atom was added, is presented herein.




Fig. 1 <sup>1</sup>H NMR spectrum (400 MHz, d<sub>1</sub>-TFA, 25 °C) of PEF (sample no. 5 in Table 1). The spin side bands are marked as "x".<sup>43</sup>

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

<sup>a</sup>State Key Laboratory of Chemical Engineering at ZJU, College of Chemical and Biological Engineering, Zhejiang University, Hangzhou 310027, China. E-mail: wulinbo@zju.edu.cn; Fax: +86-571-87952631; Tel: +86-571-87952631

<sup>b</sup>Laboratory of Polymeric and Composite Materials (LPCM), Center of Innovation and Research in Materials and Polymers (CIRMAP), University of Mons, Mons 7000, Belgium. E-mail: philippe.dubois@umons.ac.be

<sup>c</sup>Materials Research and Technology Department (MRT), Luxembourg Institute of Science and Technology (LIST), 41 rue du Brill, L-4422 Belvaux, Luxembourg

