## **RSC Advances**



View Article Online

View Journal | View Issue

## CORRECTION

Check for updates

Cite this: RSC Adv., 2017, 7, 39096

## Correction: A versatile strategy to fabricate MOFs/carbon material integrations and their derivatives for enhanced electrocatalysis

Xiao Ma,<sup>ab</sup> Xue Zhao,<sup>ab</sup> Jian Sun,<sup>a</sup> Dehui Li<sup>ab</sup> and Xiurong Yang<sup>\*a</sup>

DOI: 10.1039/c7ra90085f www.rsc.org/advances

Correction for 'A versatile strategy to fabricate MOFs/carbon material integrations and their derivatives for enhanced electrocatalysis' by Xiao Ma *et al., RSC Adv.,* 2016, **6**, 7728–7735.

The authors regret that the XPS fitting results of Fig. S9 in the ESI of the original article were not adequate. The corrected re-fitted curves (Fig. S9) and corresponding assignments and content of different types of C (Table S1) are shown below. These results do not affect the original conclusions of this paper.



Fig. S9 High-resolution C 1s spectra of (a) ZIF-8-900 and (b) ZPC-1/1-900.

Table S1	The content of different types of N and CtblS1fna	
Tuble 51	The content of uncreated gpcs of N and cloublynd	

Catalyst		•••								
	N1	N2	N3	N (total)	C1	C2	C3	C4	C5	C (total)
ZPC-1/1-800	2.89	1.02	1.05	4.96	43.15	26.29	4.54	5.74	4.22	83.94
ZPC-1/1-900	1.61	0.97	1.40	3.98	48.58	15.70	11.01	9.66	4.75	89.7
ZPC-1/1-1000	0.68	0.50	0.53	1.7	35.40	27.54	13.95	9.01	6.20	92.09

*tblS1fna* N1: pyridinic-N, N2: pyrrolic-N and N3: quaternary-N; C1: sp<sup>2</sup> C, C2: sp<sup>3</sup> C, C3: C–N or C–O, C4: carbonyl C=O and C5: amide N–C=O or carboxylic COOR.

The ESI for the original article has been correspondingly updated. This replaces the version originally published on 19<sup>th</sup> January 2016.

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

"State Key Laboratory of Electroanalytical Chemistry, Changchun Institute of Applied Chemistry, Chinese Academy of Sciences, Changchun 130022, Jilin, China. E-mail: xryang@ ciac.ac.cn

<sup>b</sup>University of the Chinese Academy of Sciences, Beijing 100049, China