RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2018, 8, 12138

Microstructure, friction and corrosion resistance properties of a Ni–Co–Al₂O₃ composite coating

Zong-wei Jia, 📴 Wan-chang Sun,* Fang Guo, Ya-ru Dong and Xiao-jia Liu

Ni-Co-Al₂O₃ composite coatings were prepared by pulsed electrodeposition and electrophoresiselectrodeposition on aluminum alloy. The content of Al₂O₃ particles of the Ni-Co-Al₂O₃ composite coating prepared by electrophoresis-electrodeposition was significantly higher than the composite coating prepared by pulsed electrodeposition. The composite coating prepared by electrophoresiselectrodeposition exhibited a better anti-wear performance than that prepared by pulsed electrodeposition. The morphology, composition and microstructure of the composite coatings were determined by means of X-ray diffractometer (XRD) and scanning electron microscopy (SEM). The hardness and friction properties of the samples were tested on the microhardness tester and the friction and wear loss tester respectively.

Received 24th January 2018 Accepted 13th March 2018

DOI: 10.1039/c8ra00722e

rsc.li/rsc-advances

1. Introduction

Aluminum alloys have a wide range of applications in the aerospace, transportation and electronic packaging industries, due to their light weight, high specific strength, good ductility, high thermal conductivity, and low coefficient of thermal expansion. However, their use is limited, due to their low hardness, poor wear and corrosion resistance.¹⁻⁴ The study of the surface hardness, wear resistance and corrosion resistance of aluminum alloys has become a focus and hotspot of research. Among the many surface modification technologies, electrode-position is considered one of the most important and cost-effective industrial technologies, because it has the advantages of simple technology, cheap equipment, scalability and so on.^{5,6}

The composite coating has a higher hardness, better wear resistance and corrosion resistance. Therefore, it has wide application prospect. Numerous studies have shown that the hard ceramic particles such as (Al₂O₃, SiC, Cr₂O₃, TiO₂, WC, diamond) could significantly enhance the mechanical properties and corrosion resistance of the composite coating.⁷⁻¹¹ In addition, the content of ceramic particles also affects the performance of the composite coating. In general, the ceramic particles will refine the surface structure of the coating, and they will be uniformly distributed in the coating, which plays a vital role on the properties of the composite coatings.¹² In recent years, since electrophoresis has drawn great attention in the preparation of ceramic materials and coatings, it enables a large number of ceramic particles to be uniformly deposited on the

surface of a substrate, which achieves a combination of different materials.¹³⁻¹⁵ In this paper, the same Ni–Co–Al₂O₃ composite coatings were prepared by different processes (pulsed electrodeposition and electrophoresis–electrodeposition). The content of alumina particles in the composite coating prepared by electrophoresis–electrodeposition is much higher than that of pulsed electrodeposition. The results show that the composite coating prepared by electrophoresis–electrodeposition has more excellent performance in hardness, wear resistance and corrosion resistance than the traditional pulsed electrodeposition composite coating.

2. Experimental details

2.1 Pulse electrodeposition progress

The substrates are LY12 aluminum alloy with size 15 mm \times 15 mm \times 10 mm, and the average particle size of the alumina particles (α -Al₂O₃, 99.99% in purity, ST-NANO, China) is 150 nm. The substrate was polished with 2000# abrasive paper and washed in alkaline solution to remove surface oil and then washed in acidic medium to remove the oxide on the surface of magnesium alloy. After each step, the substrates were washed with distilled water. Then the samples were treated in bath which the temperature is 60 °C and the pH value is 3.0–6.0 for 50 min to obtain deposition coating and the concentration of aluminum oxide is 10 g L⁻¹. The deposition voltage was 1.55–1.75 V. The composition of bath was listed in the Table 1.

2.2 Electrophoresis-electrodeposition progress

The sample pretreatment is the same as described above. The sample is placed in an electrophoresis solution of ethanol as a dispersant which the temperature is 55 °C for 300 s to make the Al_2O particles electrophoresised to the sample surface, and

College of Materials Science and Engineering, Xi'an University of Science and Technology, Xi'an, Shaanxi 710054, P.R.China. E-mail: sunwanchang@tsinghua.org. cn; Tel: +86-29-85587373

Table 1 Solution composition

Reagent	Value	Factory	Purity
NiSO ₄	300 g L^{-1}	JHD	>98.5%
NiCl	100 g L^{-1}	JHD	>98%
$CoSO_4$	20 g L^{-1}	JHD	>99.5%
Al_2O_3	10 g L^{-1}	ST-NANO	99.99%

the composition of the electrophoresis solution are listed in Table 2. The deposition voltage was 60–90 V. Then, the samples were treated in the bath which the composition is same to Table 1 and the experimental conditions is the same to pulse electrodeposition progress.

2.3 Characterizations

The cross-sectional and surface morphology of the composite coatings were investigated using scanning electron microscopy (SEM, JSM-6390A, JEOL Ltd., Tokyo, Japan) with an integrated EDS system. The phase structures of the composite coatings were analyzed by X-ray diffraction (XRD-7000; Shimadzu, Tokyo, Japan) with a CuKa radiation. The microindentation hardness of the coatings was measured on the cross-section by a microindentation hardness tester (EM-1500L; Shanghai Everone, Shanghai, China). The load and loading time were 200 gf and 15 seconds. The polarization curves of the samples were determined by CHI760D electrochemical system. The samples were completely immersed in 3.5% NaCl solution for 25 minutes. The friction coefficient of the composite coating was measured using a friction and wear tester (HT-1000; Lanzhou Zhongkai, Lanzhou, China). The test was carried out with disc speed at 560 rpm, using a bearing GCr15 ball (6 mm in diameter) under a load of 5 N for 10 minutes.

Results and discussion

3.1 Morphology observation and EDS analysis of Ni-Co-Al₂O₃ composite coatings

The morphology of the composite coating prepared by electrophoresis–electrodeposition and pulsed electrodeposition is shown in Fig. 1. Fig. 1(a) shows that the cross-sectional morphology of Ni–Co–Al₂O₃ composite coatings by pulsed electrodeposition. The gray area on the left side is the aluminum alloy matrix, the middle gray and narrow area is the Ni–Co primer layer, and the gray area of the right side is Ni–Co– Al₂O₃ composite coating. As can be seen from the Fig. 1(a), the Al₂O₃ particles are uniformly dispersed in the Ni–Co matrix. The binding of the coating with the substrate is well, without particle agglomeration. Fig. 1(b) shows the surface morphology

Table 2	Composition	of electrolytic bath
		· · · · · · · · · · · · · · · · · · ·

Reagent	Value	Factory	Purity
Al_2O_3	$10~{ m g~L^{-1}} \\ 5~{ m g~L^{-1}}$	ST-NANO	99.99%
MgCl ₂ ·H ₂ O		Xi'an Chemical Reagent Factory	>98.0%

of the Ni-Co-Al₂O₃ composite coating by pulsed electrodeposition. As shown in Fig. 1(b), the cell structure is homogeneously distributed and is dense. There are no obvious defects and impurities on the coating surface. Fig. 1(c) shows the crosssectional morphology of the Ni-Co-Al₂O₃ composite coating prepared by electrophoresis-electrodeposition. In Fig. 1(c), the left side is Ni-Co-Al₂O₃ composite coating, the middle area is the Ni-Co, and the right side is the aluminum alloy matrix. It is obvious from the left composite coating that a large amount of Al₂O₃ particles are distributed in the Ni-Co matrix and the content is higher than that of the previous process. The thickness of the composite coating is uniform. There are no other defects on the coating surface. The surface morphology of the electrophoresis-electrodeposition composite coating is shown in Fig. 1(d). The surface of the Ni-Co-Al₂O₃ composite coating is slightly rugged. Because a lot of the Al₂O₃ particles are deposited on the aluminum alloy substrate, the Ni-Co alloy of pulse electrodeposition could not fully fill clearance between the Al₂O₃ particles. In addition, the growth of the Ni–Co matrix on substrate deposited nano-Al2O3 particles could be disturbed and limited.

It can be seen clearly from Fig. 1(a) and (c) that the content of Al₂O₃ particles of the Ni-Co-Al₂O₃ composite coating (c) prepared by electrophoresis-electrodeposition is higher than the composite coating (a) prepared by pulsed electrodeposition. During pulsed electrodeposition, the Al_2O_3 particles are deposited on aluminum alloy substrate in an embedded manner with the Ni-Co matrix. Because of the influence of stirring and Al₂O₃ particles own gravitation, the number of Al₂O₃ particles co-deposited onto the surface of the cathode sample is less. Some of the Al₂O₃ particles are deposited on the cathode sample, but it is not well combined with the matrix and may be returned to the bath again under the action of stirring. Therefore, the content of Al₂O₃ particles in the Ni-Co-Al₂O₃ composite coating prepared by pulsed electrodeposition is lower than Ni-Co-Al2O3 composite coating prepared electrophoresis-electrodeposition.

Fig. 2 describes the EDS patterns of the Ni–Co–Al₂O₃ composite coating prepared by the two processes. Fig. 2 (b) and (d) show that composite coating contains nickel, cobalt, oxygen, aluminum four elements. The result of energy spectrum analysis of composite coating prepared by pulse electrodeposition is shown in Fig. 2(a) and Table 3. As shown in Table 3, the mass fraction of aluminum element is 15.07% and the mass fraction of oxygen is 9.76% in composite coating prepared by electrophoresis–electrodeposition is shown in Fig. 2(c) and Table 4, as shown in Table 4, the mass fraction of aluminum element is 26.53% and the mass fraction of oxygen is 18.6% in composite coating. Therefore, the content of alumina particles in the composite coating prepared by electrodeposition is much higher than that of pulsed electrodeposition.

The elemental mapping of Ni–Co–Al₂O₃ composite coating by the two processes is shown in Fig. 3. Fig. 3 (a)–(c) show elemental mapping of the Ni–Co–Al₂O₃ composite coating prepared by pulse electrodeposition. Fig. 3 (a)–(c) display the elemental distributions of aluminum, cobalt and nickel

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.



ig. 1 SEM micrographs of Ni-Co-Al₂O₃ composite coating by two different processes.

respectively. Fig. 3 (d)–(f) show elemental mappings of the Ni– Co–Al₂O₃ composite coating prepared by electrophoresis–electrodeposition. Fig. 3 (d)–(f) display the elemental distributions of aluminum, cobalt and nickel respectively. It can be seen from Fig. 3(a) and (b) that the aluminum elements are evenly distributed in the layer, meaning that the Al₂O₃ particles are uniformly dispersed in the layer. Comparing Fig. 3(a) with Fig. 3(d), it can be seen that the content of aluminum in the Fig. 3(d) is significantly higher than in Fig. 3(a). This means that the content of the Al₂O₃ particles in the composite coating prepared by electrophoresis–electrodeposition is higher than that of the Al₂O₃ particles in the composite coating by pulse electrodeposition. These conclusions are consistent with those described above.

3.2 Composition of Ni-Co-Al₂O₃ composite coatings

The X-ray diffraction patterns of the Ni–Co–Al₂O₃ composite coating prepared by the two processes are shown in Fig. 4. Fig. 4(a) shows the X-ray diffraction spectrum of the composite coating prepared by pulsed electrodeposited. The peaks of $2\theta = 44.507^{\circ}$, 51.846° and 76.37 in the spectrum could clearly show the characteristic peaks of Ni and the diffraction peak is very sharp. The characteristic peaks of Al₂O₃ are also found at $2\theta = 29.359^{\circ}$, 35.164, 38.155° , 68.212° . The results show that the peak value of alumina in the composite coating prepared by

electrophoresis–electrodeposition is higher, which indicates that the content of Al₂O₃ particles in the Ni–Co–Al₂O₃ composite coating is higher.

3.3 Microhardness of the Ni-Co-Al₂O₃ composite coatings

Fig. 5 displays the microhardness of the Ni-Co-Al₂O₃ composite coating prepared by the electrophoresis-electrodeposition and the pulsed electrodeposition. In order to clearly show the difference of microhardness of different coatings, firstly, a layer of Ni-Co coating was prepared by pulsed electrodeposition on the aluminum alloy substrate for 5 min. Then Ni-Co-Al₂O₃ coating was prepared by pulsed electrodeposition for 15 min on Ni-Co coating. The third step was to prepare a layer of nano-Al₂O₃ particles on Ni-Co-Al2O3 coating by means of electrophoretic deposition for 200 s. The nano-Al2O3 particles are easily separated from Ni-Co-Al2O3 coating, so the Ni-Co coating was electrodeposited on it for 10 min. The nano-Al2O3 particles with weak binding force were tightly coated with Ni-Co matrix coating, which with good binding force and high content of nano-Al₂O₃ particles. Fig. 4(a) shows the microhardness of aluminum alloy matrix, the Ni-Co-Al₂O₃ composite coating prepared by pulsed electrodeposition and the Ni-Co-Al2O3 composite coating prepared by electrophoresis-electrodeposition. From Fig. 5(a), it can be seen that the indentation of the coating is smaller than that of the substrate, and the indentation has the following



Fig. 2 EDS micrographs of Ni-Co-Al₂O₃ composite coating by two different processes.

tendency: aluminum alloy > pulsed electrodeposition Ni–Co– Al₂O₃ composite coating > electrophoresis–electrodeposition Ni– Co–Al₂O₃ composite coating, so Ni–Co–Al₂O₃ composite coating

Table 3 Energy spectrum analysis of Ni–Co–Al $_2O_3$ composite coatings by pulse electrodeposition

Element	(keV)	Mass%	Error%	Atom%	Κ
ОК	0.525	9.76	0.05	24.92	12.8574
Al K	1.486	15.07	0.08	22.82	8.7701
Co K	6.924	18.8	0.43	13.03	19.1025
Ni K	7.471	56.37	0.55	39.23	59.2699
Total		100		100	

Table 4 Energy spectrum analysis of Ni–Co–Al $_2O_3$ composite coating by electrophoresis–electrodeposition

Element	(keV)	Mass%	Error%	Atom%	Κ
ОК	0.525	18.6	0.06	37.75	24.8301
Al K	1.486	26.53	0.09	31.93	17.5833
Co K	6.924	13.26	0.55	7.31	13.5675
Ni K	7.471	41.62	0.71	23.02	44.0191
Total		100		100	

prepared by electrophoresis–electrodeposition composite process has better hardness. Fig. 5(b) shows the hardness values of the aluminum alloy matrix, the composite coating prepared by pulsed electrodeposition and the composite coating prepared by electrophoresis–electrodeposition. The microhardness of the Ni– Co–Al₂O₃ composite coating prepared by the electrophoresis– electrodeposition is about 550 HV, which is significantly higher than that of the pulsed electrodeposition composite coating and the aluminum alloy matrix.

The hardness of Ni–Co–Al₂O₃ composite coating prepared by electrophoresis–electrodeposition is improved significantly, mainly due to fine grain strengthening and dispersion strengthening mechanism. The fine grain metals at room temperature have higher strength, hardness than coarse grain metals. Because the grain is fine, the grain boundary is twists, which is more unfavorable to the expansion of the dislocation. The content of Al₂O₃ particles of Ni–Co–Al₂O₃ composite coating is higher, and the coated surface grains are finer.^{16,17} On the basis of a large number of experiments, a general expression Hall–Petch formula between grain size and metal strength was established

$$\sigma_{\rm y} = \sigma_0 + K d^{-n} \tag{3.1}$$



Fig. 3 Elemental mappings of Ni–Co–Al₂O₃ composite coating by two different processes.

where σ_y is the flow stress, σ_0 is the lattice friction, *d* is the grain diameter, *K* is the constant (positive) associated with the material, and the index *n* is always 0.5.

Dispersion strengthening stressed that the second phase with fine particles evenly distributed in the grain of the solid solution, which make the alloyed plasticity, toughness decreased slightly and strength, hardness improved. The Al₂O₃ particles with high hardness as the second phase of solid particles embedded in the composite coating, and they prevent the movement of the dislocation and lattice deformation. According to the relationship between the dislocation bending stress and the radius of curvature (the following formula 3.2).¹⁸

The smaller the particle, the higher the particle content, the smaller the spacing between the particles and the particles make the dislocation bending shear stress large and the dispersion enhancement more obvious. The Ni–Co–Al₂O₃ composite coating prepared by electrodeposition–electrodeposition contains a large amount of nano-sized alumina particles, which makes the hardness of the composite coating greatly improved under the condition of high dispersion.

$$\tau = \frac{G_{\rm b}}{2R} = \frac{G_{\rm b}}{\lambda} \tag{3.2}$$



Fig. 4 XRD patterns of Ni-Co-Al₂O₃composite coating by two different processes: (a) pulse-electrodeposition; (b) electrophoresiselectrodeposition.

where τ is the shear stress, *G* is the shear elastic modulus, *R* is the misalignment bending radius, and λ is the particle spacing.

3.4 Tribological behaviors of the Ni–Co–Al $_2O_3$ composite coatings

The friction coefficient of the Ni-Co-Al₂O₃ composite coating prepared by the two processes is shown in Fig. 6. Fig. 6 shows that the friction coefficient of the coating prepared by pulsed electrodeposition is lower than that of the composite coating prepared by electrophoresis-electrodeposition at the beginning of the experiment. With the increase of the experimental time, the friction coefficient of the composite coating prepared by pulsed electrodeposition began to be higher than that of the composite coating prepared by electrophoresis-electrodeposition and was always higher than that of the latter. The reason is that the content of Al₂O₃ particles in the composite coating prepared by electrophoresis-electrodeposition process is higher than that of the composite coating prepared by pulsed electrodeposition. There is a layer of convex alumina particles on the surface of the composite coating prepared by electrophoresiselectrodeposition. In the initial experiment, the alumina

particles are easy to fall off so that the friction coefficient is high. With the surface particles grinded, because the composite coating prepared by electrophoresis–electrodeposition has high hardness and deformation resistance, the friction coefficient changes more slowly. When the friction coefficient reaches about 0.45, the friction coefficient is almost unchanged.

Fig. 7 shows wear loss of Ni–Co–Al₂O₃ composite coatings prepared by electrophoresis–electrodeposition and pulse electrodeposition with the change of time. The Fig. 7 presents that the wear loss of composite coating compared by electrophoresis–electrodeposition is lower than that of composite coating compared by pulse electrodeposition. As the composite coating compared by the electrophoresis–electrodeposition has a higher content of Al₂O₃ particles, the alumina particles as the second phase is homogeneously dispersion in the composite coating, which make composite coating has high hardness and strong deformation resistance.

The wear scars of Ni–Co–Al₂O₃ composite coatings prepared by two kinds of process conditions under the same friction conditions are shown in Fig. 8. Fig. 8(a) shows the wear scars of Ni–Co–Al₂O₃ composite coating prepared by pulsed



Fig. 5 The micro-hardness of Ni–Co–Al₂O₃ composite coating by two different processes: (a) the creasing of two composite coatings under the same pressure, (b) the microhardness of two composite coatings.



Fig. 6 Friction coefficient of Ni–Co–Al₂O₃ composite coatings by two different processes.



Fig. 7 Wear loss of Ni–Co–Al $_2O_3$ composite coatings with two different processes.

electrodeposition. Fig. 8(b) shows the wear scars of Ni–Co–Al₂O₃ composite coating prepared by electrophoresis–electrodeposition. From Fig. 8(a), it can be seen that some of the area of the

coating has been stripped from the substrate and shows a significant grain wear characteristics. From Fig. 8(b), it can be seen that wear surface is relatively smooth, shallow furrow and dose not appear peeling phenomenon, which perform the grain wear characteristics also.

The wear resistance of the composite coating is related to the phase structure and composition of the surface. The coating with high strength and high hardness has good wear resistance. As for the Ni–Co–Al₂O₃ composite coating, the Ni–Co matrix belongs to matrix metal of high hardness, and the nano-Al₂O₃ particles as the second enhanced phase has a high hardness. During the process of wear and tear, the Ni–Co–Al₂O₃ composite coating prepared by electrophoresis–electrodeposition did not appear obvious furrow, peeling and other characteristics.¹⁹

3.5 Corrosion resistance of the Ni–Co–Al₂O₃ composite coatings

Fig. 9 shows the polarization curves (Tafel curves) of Ni-Co-Al₂O₃ composite coatings prepared for two different processes, in 3.5 wt% NaCl solution. Fig. 8 shows that the self-corrosion potential of Ni-Co-Al₂O₃ composite coating prepared by electrophoresis-electrodeposition is +0.065 V, and the selfcorrosion potential of Ni-Co-Al2O3 composite coating prepared by pulsed electrodeposition is -0.114 V. It can be described that the corrosion resistance of Ni-Co-Al₂O₃ composite coating prepared by electrophoresis-electrodeposition is better than that of Ni-Co-Al₂O₃ composite coating prepared by pulsed electrodeposition. The Al₂O₃ particles are inert ceramic particles which are not conductive itself, so they play a role in the shield of composite coating and it will reduce the size of the corrosion current. With increasing of Al₂O₃ particles, this phenomenon is more obvious. The Al₂O₃ particles hinder the free crystallization of the matrix metal so that the preferential orientation of the single crystal plane occurs in the process of electrical crystallization and the surface potential of the composite coating tends to be homogenization. The microchemical uniformity of coating is more excellent, which makes the driving force of the micro-battery of composite coating reduced in the corrosive environment. Therefore corrosion



Fig. 8 Worn scars of Ni-Co-Al₂O₃ composite coatings by two processes: (a) pulse electrodeposition, (b) electrophoresis-electrodeposition.



Fig. 9 The Tafel polarization curves of Ni–Co–Al $_2O_3$ composite coatings by two different processes.

resistance of the composite coating is enhanced. Furthermore, during the growth of the composite coating, the Al_2O_3 particles make the nucleation rate increasing and the growth rate inhibited.²⁰ This dense composite structure is very useful in suppressing the corrosion dissolution of composite coating.²¹

4. Conclusions

(1) The content of Al_2O_3 particles of Ni–Co– Al_2O_3 composite coating prepared by electrophoresis–electrodeposition is higher than that prepared by pulsed electrodeposition.

(2) The hardness of Ni–Co–Al₂O₃ composite coating prepared by electrophoresis–electrodeposition is higher than that the composite coating prepared by pulse electrodeposition. What is more, the composite coating prepared by electrophoresis–electrodeposition exhibited more excellent wear resistance and low coefficient than the composite coating prepared by pulsed electrodeposition.

(3) The composite coating prepared by electrophoresiselectrodeposition with high Al_2O_3 content has good corrosion resistance. The Al_2O_3 particles could improve the corrosion resistance of the composite coating.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The work was supported by the National Natural Science Foundation of China (50172023) and the Shaanxi Industrial Science and Technology Research (2014K08-09).

References

- 1 H. Gül, F. Kılıç, S. Aslan, A. Alp and H. Akbulut, *Wear*, 2009, **267**, 976–990.
- 2 C. S. Kumar, S. M. Mayanna, K. N. Mahendra, A. K. Sharma and R. U. Rani, *Appl. Surf. Sci.*, 1999, **151**, 280–286.
- 3 A. Hakimizad, K. Raeissi and F. Ashrafizadeh, *Surf. Coat. Technol.*, 2012, **206**, 2438–2445.
- 4 J. Yuan, J. Wang, K. Zhang, et al., RSC Adv., 2017, 7(46), 28909–28917.
- 5 R. K. Saha and T. I. Khan, *Surf. Coat. Technol.*, 2010, 205, 890–895.
- 6 M. Sajjadnejad, A. Mozafari, H. Omidvar and M. Javanbakht, *Appl. Surf. Sci.*, 2014, **300**, 1–7.
- 7 L. Chen, L. Wang, Z. Zeng and T. Xu, *Surf. Coat. Technol.*, 2006, **201**, 599–605.
- 8 L. M. Chang, M. Z. An, H. F. Guo and S. Y. Shi, *Appl. Surf. Sci.*, 2006, **253**, 2132–2137.
- 9 K. H. Hou and Y. C. Chen, *Appl. Surf. Sci.*, 2011, 257, 6340-6346.
- 10 G. Wu, N. Li, D. Zhou and K. Mitsuo, Surf. Coat. Technol., 2004, 176, 157–164.
- 11 S. L. Kuo, Y. C. Chen, M. D. Ger and W. H. Hwu, *Mater. Chem. Phys.*, 2004, **86**, 5–10.
- 12 B. Bakhit and A. Akbari, *Surf. Coat. Technol.*, 2012, **206**, 4964–4975.
- 13 S. Kishida, D. Y. Ju, H. He and Y. Li, *J. Environ. Sci.*, 2009, 21(suppl. 1), S112–S115.
- 14 G. Song, G. Xu, Y. Quan, Q. Yuan and P. A. Davies, *Surf. Coat. Technol.*, 2016, **286**, 268–278.
- 15 E. G. Kalinina, A. A. Efimov and A. P. Safronov, *Inorg. Mater.*, 2016, **52**, 1301–1306.
- 16 E. BełtowskaLehman, A. Góral and P. Indyka, Arch. Metall. Mater., 2011, 56, 919–931.
- 17 S. Mirzamohammadi, H. Khorsand, M. Aliofkhazraei and D. V. Shtansky, *Tribol. Int.*, 2017, **11**7, 68–77.
- 18 A. F. Zimmerman, D. G. Clark, K. T. Aust and U. Erb, *Mater. Lett.*, 2002, **52**, 85–90.
- 19 H. Sharifi, K. Ostovan, M. Tayebi and A. Rajaee, *Tribol. Int.*, 2017, **116**, 244–255.
- 20 L. Benea, P. L. Bonora, A. Borello, S. Martelli, F. O. Wenger,
 P. Ponthiaux, et al., J. Electrochem. Soc., 2001, 148(7), C461.
- 21 B. Szczygieł and M. Kołodziej, *Electrochim. Acta*, 2005, 50, 4188–4195.

Paper