RSC Advances

PAPER

Cite this: RSC Adv., 2018, 8, 29840

Highly efficient one-step microwave-assisted synthesis of structurally diverse bis-substituted α amino acid derived diimides†

We report herein a facile and widely applicable microwave-assisted protocol for the synthesis of symmetrical diimides based on three structurally distinct aromatic dianhydrides: pyromellitic (PMA), biphenyl-tetracarboxylic acid (BPDA) and benzophenone-tetracarboxylic (BTDA) and five natural amino acids (Phe, Tyr, Ile, Lys, Cys). Fifteen symmetrical diimides with different structural characteristics

Marcin Konopka,^{†ab} Gr[z](http://orcid.org/0000-0002-6177-358X)egorz Markiewicz^{†ab} and Artur R. Stefankiewicz D^{*ab}

containing a variety of functional groups can be produced with high yields and on a large scale.

Received 9th July 2018 Accepted 16th August 2018

DOI: 10.1039/c8ra05835k

rsc.li/rsc-advances

Introduction

Symmetrical diimides have found a wide spectrum of uses in the last decade.¹ The vast majority of these materials have structures based on naphthalene diimide (NDI) or perylene bisimide (PBI) cores.^{1,2} Both systems have constituted essential components of numerous non-covalent polymers^{3,4} and selfassembled supramolecular architectures,5,6 and have been used in DNA complexation⁷⁻⁹ and biomolecular recognition.^{10,11} Currently, there is an increased interest in this class of compounds, especially those bearing unique functional substituents and containing alternative central diimide cores, due to their significant application potential in materials chemistry and receptors in supramolecular chemistry.¹²–¹⁴ Despite the widely reported synthetic methodologies for the preparation of NDI and PBI derivatives, the literature protocols concerning compounds that are alternatives to them are scant. PAPER
 (A) Check for updates
 EVALUATION CONTINUMERTY (THE CONTROVERTIES)

Concentrates and a synthesis of structurally diverse bis-substituted comes and the synthesis of structurally diverse bis-substituted comes and

It has been previously shown that α -amino acid derived NDIs can be obtained in high yields by microwave assisted synthesis.15,16 Although the protocols developed have considerably improved the preparation of these molecules in terms of time and ease of workup, the studies were devoted to a single group of diimides only i.e. NDIs, leaving the others to be synthesised by classical synthesis which was found to be dependent in an ill understood manner on the particular choice of dianhydride and amine. Thus, the synthesis of this important group of molecules is still associated with time-consuming and complicated protocols often leading to contaminated products

in low yields.¹⁷⁻¹⁹ In addition, purification of these molecules is usually very difficult because of their generally low solubility and tendency to form undefined polymeric materials. For these reasons, the development of an accessible methodology based on microwave-assisted synthesis of non-NDI/PBI diimides in short reaction times, with easy work up and in high yields is greatly desirable from the viewpoints of both synthesis and the application potential of these molecules.

YAL SOCIETY
CHEMISTRY

Here, we describe a one-step process for microwave assisted synthesis of symmetrical a-amino acid derived diimides based on three structurally distinct aromatic cores namely, pyromellitic dianhydride (PMA),²⁰ biphenyl-tetracarboxylic acid dianhydride (BPDA)²¹ and benzophenone-tetracarboxylic acid dianhydride $(BTDA)^{22}$ (Scheme 1). We chose these anhydrides due to their potential to deliver diimides with properties different to those of NDIs and PBIs. The PMA little core was found as an interesting platform for designing n-channel transistor semiconductors based on pyromellitic diimides.²³ BPDA introduces a free rotation axis in the center of diimide

R = side chain of: L-Phe, L-Tyr, L-Ile, Ns-Boc-L-Lys, STr-L-Cys

Scheme 1 General synthetic method for the microwave assisted preparation of symmetrical diimides from three distinct dianhydrides and a-amino acids.

[&]quot;Faculty of Chemistry, Adam Mickiewicz University, Umultowska 89b, 61-614 Poznań, Poland. E-mail: ars@amu.edu.pl

b Center for Advanced Technologies, Adam Mickiewicz University, Umultowska 89c, 61- 614 Poznań, Poland

[†] Electronic supplementary information (ESI) available: ¹H and ¹³C NMR spectra. See DOI: 10.1039/c8ra05835k

[‡] These authors contributed equally to this work.

molecule and this offers a means to engender of new class of symmetrical diimides with greater conformational lability. BTDA has a ketone group in the center of molecule which offers prospects for further modification or provision of an attachment point for coupling of two or more diimide molecules into larger systems.²⁴ Use of well-known reversible reactions like imine formation, reductive amination or formation of hemithioacetals was seen as a pathway to further variations. All three aromatic platforms were functionalized with five different amino acids: L-phenylalanine, L-tyrosine, L-isoleucine, Nε-Boc-Llysine and S-Tr-L-cysteine. These were selected as structurally diverse species providing a stringent test of the sensitivity of our methods to the presence of several functional groups. We have prepared fifteen diimides, nine of them new, in very high yields independent of the reaction scale, and without evidence of racemization at the chiral centers.

Results and discussion

General synthetic methodology

The enantiomerically pure diimides were synthesized as shown in Scheme 1. The reactions were conducted in pressureresistant glass vessels with a total volume of \sim 10 mL, designed for CEM microwave ovens and closed with silicone/ PTFE caps.

The optimal scale for these reactions was to use 0.5 mmol of an anhydride, 1.0 mmol of amino acid, and \sim 2 mmol of base, which is equal to less than 1 g of total material load. We found that higher loadings led to significant contamination with thermal decomposition products. The reaction mixtures were irradiated for 10 min at 140 \degree C using full microwave power (300 W) for the temperature ramping $(\sim 30 \text{ s})$ followed by short pulses $(20-40 W)$ to maintain the scheduled conditions. After cooling to room temperature, the reaction mixtures were poured into hydrochloric acid (1.0 mol \times dm⁻³), the solid product was filtered off, washed with deionized water and dried in high vacuum for 12 h. This procedure turned out to be sufficient to obtain the desired products with high spectroscopic and analytical purity (See Experimental section for details).

Method optimisation

We found that the procedure originally presented by Pantos et al.^{15,16} for naphthalene diimides (NDI), which utilizes DMF as a solvent and triethylamine $(Et₃N)$ as a base catalyst, could also

be used for the systems described here but the use of these reagents is associated with certain difficulties. Although DMF is perfectly suited for conducting nucleophilic reactions under microwave conditions, due to its high dipole moment and low vapor pressure, as well as its stability under microwave conditions, very often its residues are problematic during reaction work-up and purification of the products. $Et₃N$, due to its very high volatility, generates high pressures $(0.5-1.0 \text{ MPa})$ in the closed reaction systems, which limits its application only to expensive high-pressure reactors with fixed volume and synthesis scales. To facilitate reaction work-up and be able to carry out reaction on the larger scales at atmospheric pressure, we therefore investigated modification of this procedure. The reaction between PMA and L-phenylalanine was chosen as a model for the optimization of the synthetic methodology. These reagents give the diimide, PMI-Phe, in the form of very fine powder requiring only a simple water wash during workup. Two different solvents, N,N-dimethylformamide (DMF) and acetonitrile (MeCN), and three bases: triethylamine ($Et₃N$), 4-(dimethylamino)pyridine) (DMAP), and 1,4-diazabicyclo[2.2.2] octane (DABCO) were selected for the test reactions. Paper

New York on 23 August 2018. The second of the second online to the second on the second on the second on the second on the second of the second o

The outcomes of the reactions performed under the different conditions are shown in Table 1. The highest yield (\approx 87%) was observed when DMF and DMAP were employed as solvent and base, respectively. Despite the fact that MeCN slightly reduces the reaction yields (down to \approx 79% and \approx 63% for the DABCO and DMAP, respectively), it is an interesting alternative for DMF, especially when fully aliphatic amino acids are used (see ahead). Complete removal of DMF from the products was possible through a combination of several water rinses, ultrasonic irradiation and pumping in vacuum, but in some cases, it was a very time-consuming process. The previously proposed pre-evaporation of the DMF^{15,16} from the reaction mixtures seems to be helpful but it does not solve the trace contamination problem. What we have now found is that the use of acetonitrile instead of DMF greatly facilitates the work-up, and significantly improves the separation and drying processes.

The poorest results were obtained when DMF/DABCO and $MeCN/Et_3N$ pairs were employed. While the first pair is inefficient and gives contaminated products, the second generates high overpressure, which is problematic even for a dedicated microwave reactor. On the basis of these initial observations, we decided to synthesize the entire series of symmetrically functionalised diimides using the DMF/DMAP pair, since this gave the highest yield for the model reaction. As shown in Table 2, all

 a Reactions were carried out on 0.5 mmol of dianhydride, 1.0 mmol of amino acid, 2.0 mmol of base and 5 mL of the solvent. b Excluding temperature ramping. ^c Each reaction was repeated 3-times, giving isolation yields in the ranges shown.

Table 2 List of synthesized symmetrical diimides with structures and abbreviations

	Entry Dianhydride acid	Amino	Product ^a			Reaction Abbreviation time ^b (min)	Reaction temp. $(^{\circ}C)$ Yield ^c $(\%)$	
13	BTDA	L-Ile	HOO	COOH	BTDI-Ile	10	140	79
14	BTDA	S-Tr-L-Cys	Ph ₃ CS	COOH SCPh	BTDI-Cys	10	140	90
15	BTDA	$N\epsilon$ -Boc-L-Lys		COOH	BTDI-Lys	10	140	70
	ramping. ^c Yield of isolated product.		a Reactions were carried out on 0.5 mmol of dianhydride, 1.0 mmol of amino acid and 2.0 mmol of DMAP in 5 mL of DMF. b Excluding temperature					
			fifteen different diimides were obtained in high yields and purities, indicating the broad utility of the procedure and thus	conducted at high temperature. ²⁵ In the present case, due to the presence of two chiral centers, it is possible to generate three				
			that it should be useful for the synthesis of any desired diimide.	products with LL, DD and DL configurations. However, the high				
			We have not found any marked dependence on the structure of the substrates used and consider that the minor variations in	symmetry of signals in the ¹ H NMR spectra, namely single set of resonances for α -CH and β -CH ₂ protons implies that the applied				
			yield are probably due to differences in solvation. In Fig. 1 we	methodology leads to the formation of enantiomerically pure				
			present the stacked ¹ H-NMR spectra of molecules PMI-Phe	products. The only noticeable but obvious difference between				
			(blue), BPDI-Phe (green), BTDI-Phe (red) with L-phenylalanine	the three spectra is the distribution of aromatic signals from				
			and three structurally different dianhydrides. Signals due to the	central aromatic cores.				
			α -CH and β-CH ₂ protons of the amino acid residue appear at essentially identical positions (\approx 5.2 and 3.4 ppm, respectively).	To further confirm this, we performed the test reaction between PMA dianhydride and racemic tyrosine. Indeed as ex-				
			Importantly, it was previously found that racemization of	pected, the use of the substrate in its racemic form has led to				
			amino acid may occur when the fusion with anhydride is	a mixture of diastereomeric products whose presence was				

 a Reactions were carried out on 0.5 mmol of dianhydride, 1.0 mmol of amino acid and 2.0 mmol of DMAP in 5 mL of DMF. b Excluding temperature ramping. ^c Yield of isolated product.

Fig. 1 $^{-1}$ H NMR (300 MHz, DMSO- d_6) spectra of PMI-Phe (blue), BPDI (green), BTDI-Phe (red). Peaks description: α -CH (2H), β -CH₂ (4H) and Ph-H (10H) stands from L-phenylalanine moieties.

To further confirm this, we performed the test reaction between PMA dianhydride and racemic tyrosine. Indeed as expected, the use of the substrate in its racemic form has led to a mixture of diastereomeric products whose presence was manifested by the multiplication of all resonances in the ¹H NMR spectrum, in contrast to the fully symmetrical spectrum observed when chirally pure amino acids were used (Fig. 2).

Large scale synthesis

The synthesis of symmetrical diimides is usually the first step in the synthesis of functionalized monomers used in selfassembled systems such as dynamers,²⁶ so relatively large quantities of these precursors are often required. Therefore, we investigated whether the method above might be applied in reaction at a larger scale while maintaining the high yields and purities obtained in test reactions.

The high scale reactions were performed using 10.0 mmol of appropriate amino acid, and 5.0 mmol of dianhydride. The nonpressurized DMF/DMAP system was found to be well suited for the open vessel conditions. Reactions were conducted in a standard 100 mL round-bottom flask with an air-cooled condenser to provide reflux. Using the standard reaction times (10 min) the expected products were obtained in essentially identical yields compared to that observed in low scale under pressurized conditions. We were able to obtain up to 5 g

Fig. 2 $^{-1}$ H NMR (300 MHz, DMSO- d_6) spectra of the products isolated after reaction of PMA dianhydride with chirally pure L-tyrosine (top) and racemic tyrosine (bottom).

of pure diimide in one large-scale batch and use it for further modification. The MeCN/DABCO system was also found to be useful in open-vessel reactions but due to the low boiling point of acetonitrile (82 \degree C), it was necessary to extend the reaction time up to 20 minutes in order to obtain yields comparable to that obtained under high pressure. The results of six large scale syntheses are shown in Table 3.

By conducting reactions at lower temperature $(82 \degree C, 10 \text{ min})$ in the MeCN/DABCO mixture we were able to observe reaction intermediates, among which the most interesting are monosubstitution products that are essential in the synthesis of unsymmetrical bis-substituted compounds. Unfortunately, despite the utilisation of both thermodynamic and stoichiometric control, we were not able to isolate them using methodology presented in this work, as their high solubility in all range of solvents prevents their effective precipitation from reaction mixtures. Although it was possible to separate the monosubstituted products by reverse phase HPLC methods, we believe that easier and more efficient synthetic and isolation protocols may be developed which will open the way for the desymmetrisation of the presented diimides in the future.

Experimental

General considerations

All chemicals and solvents were purchased from commercial sources and used as received. NMR solvents were purchased

from Deutero GmbH (Germany). NMR spectra were acquired on Bruker Fourier 300 spectrometer equipped with 1H/13C 5 mm probe, at 298 K and were referenced on solvent residual peaks. Mass spectra were recorded on Bruker Impact HD Q-TOF spectrometer in negative ion mode. Elemental analyses were obtained using an Elemental Analyser Vario EL III. Samples were dried for 12 h under high vacuum prior to analysis. The microwave assisted reactions were performed on CEM Discover SP oven.

General method for the synthesis of symmetrical diimides

A representative example is that of the PMA and L-phenylalanine reaction. L-Phenylalanine (165.2 mg, 1.0 mmol), PMA (109.0 mg, 0.5 mmol) and DMAP (244.0 mg, 2.0 mmol) were placed in a glass vessel and suspended in 5 mL of dry DMF. The mixture was sonicated until complete dissolution had occurred. The vessel was sealed with a silicon cap and placed in a microwave oven. The mixture was heated at 140 °C for 10 min. After cooling, the mixture was poured into 50 mL of hydrochloric acid $(1 \text{ mol} \times \text{dm}^{-3})$. The precipitate was filtered off and washed with 200 mL of water to remove residual DMF. The solid residue was dried under high vacuum. Yield: 223 mg (87%) of PMI-Phe.

General method for the large-scale synthesis of symmetrical diimides

A representative example again is that of the PMA/L-phenylalanine reaction. PMA (1.09 g, 5.0 mmol), L-phenylalanine (1.65 g, 10.0 mmol) and DMAP (2.44 g, 20.0 mmol) were placed in 100 mL round-bottom flask and dissolved in 50 mL of dry DMF. The solution was heated in the microwave oven at 180 W for 10 min under open vessel conditions with an air condenser. The resulting solution was concentrated to a 10 mL volume on a rotary evaporator before being mixed with 200 mL of hydrochloric acid (1 mol \times dm⁻³). The white precipitate was filtered off, washed with 500 mL of water and dried under high vacuum. Yield 2.12 g (83%) of PMI-Phe.

PMI-Phe. ¹H NMR (300 MHz, DMSO- d_6) δ 13.47 (s, 2H), 8.22 $(s, 2H), 7.23-7.07$ (m, 10H), 5.16 (dd, $J = 11.3, 4.8$ Hz, 2H), 3.50 $(dd, J = 14.1, 4.8$ Hz, 2H), 3.39-3.24 (m, 2H). ¹³C NMR (75 MHz, DMSO-d₆) δ 169.61, 165.18, 137.11, 136.24, 128.75, 128.40, 126.66, 118.51, 53.60, 33.92. ESI-MS: m/z calculated for: [M – H ^{$-$} 511.1147, found: 511.1153. Elemental analysis calcd $%$ for

 a Reactions were carried out on 5.0 mmol of dianhydride, 10.0 mmol of amino acid and 20.0 mmol of base in 50 mL of given solvent. b At constant microwave power = 180 W. $c \pm 5$ °C maintained at constant power. ^d Boiling point of the solvent. ^e Yield of isolated product.

 $C_{28}H_{20}N_2O_8$: C 65.62, H 3.93, N 5.47; found: C 65.75, H 3.82, N 5.52.

PMI-Tyr. ¹H NMR (300 MHz, DMSO- d_6) δ 13.40 (s, 2H), 9.15 $(s, 2H), 8.22 (s, 2H), 6.92 (d, J = 8.0 Hz, 4H), 6.53 (d, J = 7.9 Hz,$ 4H), 5.05 (dd, $J = 11.6$, 4.8 Hz, 2H), 3.43-3.29 (m, 2H), 3.25-3.13 (m, 2H). ¹³C NMR (75 MHz, DMSO-d₆) δ 169.69, 165.21, 155.89, 136.26, 129.70, 127.05, 118.48, 115.23, 53.97, 33.07. ESI-MS: m/z calculated for: $[M - H]$ ⁻ 543.1045, found: 543.1048. Elemental analysis calcd (%) for $C_{28}H_{20}N_2O_{10}$: C 61.77, H 3.70, N 5.15; found: C 61.72, H 3.73, N 5.11.

PMI-Ile. ¹H NMR (300 MHz, DMSO- d_6) δ 13.16 (s, 2H), 8.33 (s, 2H), 4.60 (d, $J = 7.8$ Hz, 2H), 2.45-2.31 (m, 2H), 1.50 (ddd, $J =$ 13.4, 7.6, 3.6 Hz, 2H), 1.06 (d, $J = 6.7$ Hz, 6H), 1.03–0.92 (m, 2H), 0.81 (t, $J = 7.3$ Hz, 6H). ¹³C NMR (75 MHz, DMSO- d_6) δ 169.46, 165.80, 136.54, 118.44, 57.02, 34.05, 25.28, 16.66, 10.93. ESI-MS: m/z calculated for: $[M - H]$ ⁻ 443.1460, found: 443.1461. Elemental analysis calcd (%) for $C_{22}H_{24}N_2O_8$: C 59.46, H 5.44, N 6.30; found: C 59.34, H 5.48, N 6.34.

PMI-Lys. 1 H NMR (300 MHz, DMSO- d_{6}) δ 13.27 (s, 2H), 8.32 $(s, 2H)$, 6.71 (t, J = 5.7 Hz, 2H), 4.80 (dd, J = 7.7 Hz, 2H), 2.84 (q, J $= 6.4$ Hz, 4H), 2.14–2.05 (m, 4H), 1.40–1.21 (m, 26H). ¹³C NMR (75 MHz, DMSO- d_6) δ 170.15, 165.66, 155.55, 136.67, 118.31, 77.27, 52.34, 28.99, 28.18, 27.71, 23.06. ESI-MS: m/z calculated for: $[M - H]$ ⁻ 673.2726, found: 673.2737. Elemental analysis calcd (%) for $C_{32}H_{42}N_4O_{12}$: C 56.97, H 6.27, N 8.30; found: C 57.13, H 6.25, N 8.40.

PMI-Cys. 1 H NMR (600 MHz, DMSO- d_{6}) δ 13.66 (s, 2H), 8.38– 8.27 (m, 2H), 7.30–7.26 (m, 32H), 4.59 (ddp, $J = 14.2$, 9.2, 4.8 Hz, 2H), 3.11–3.03 (m, 2H), 3.01–2.94 (m, 2H). 13C NMR (151 MHz, DMSO) δ 168.52, 165.02, 143.75, 136.42, 129.03, 128.31, 128.12, 126.22, 66.66, 55.82, 39.52, 30.37. ESI-MS: m/z calculated for: [M $-H$ ⁻ 907.2153, found: 907.2158. Elemental analysis calcd $(\%)$ for $C_{54}H_{40}N_2O_8S_2$: C 71.35, H 4.44, N 3.08; found: C 71.44, H 4.73, N 3.11.

BPDI-Phe. ¹H NMR (300 MHz, DMSO- d_6) δ 13.38 (s, 2H), 8.31–8.18 (m, 4H), 7.94 (d, $J = 8.2$ Hz, 2H), 7.22–7.08 (m, 10H), 5.15 (dd, $J = 11.6$, 4.8 Hz, 2H), 3.50 (dd, $J = 14.1$, 4.9 Hz, 2H), 3.42–3.35 (m, 2H). ¹³C NMR (75 MHz, DMSO- d_6) δ 170.04, 166.68, 144.64, 137.30, 134.14, 131.70, 130.46, 128.74, 128.37, 126.61, 124.05, 122.61, 53.11, 33.96. ESI-MS: m/z calculated for: $[M - H]$ ⁻ 587.1460, found: 587.1465. Elemental analysis calcd (%) for $C_{34}H_{24}N_2O_8$: C 69.38, H 4.11, N 4.76; found: C 69.42, H 4.27, N 4.82.

BPDI-Tyr. 1 H NMR (300 MHz, DMSO- d_{6}) δ 13.32 (s, 2H), 9.15 $(s, 2H)$, 8.29-8.16 (m, 4H), 7.97-7.93 (m, 2H), 6.94 (d, $J = 8.1$ Hz, 4H), 6.55 (d, $J = 8.1$ Hz, 4H), 5.05 (dd, $J = 11.6$, 4.9 Hz, 2H), 3.37 $(dd, J = 14.2, 4.9$ Hz, 2H), 3.25 $(dd, J = 14.2, 11.7$ Hz, 2H). ¹³C NMR (75 MHz, DMSO) δ 170.16, 166.77, 155.89, 144.68, 134.14, 131.77, 130.53, 129.71, 127.27, 124.06, 122.62, 115.23, 53.44, 33.14. ESI-MS: m/z calculated for: $[M - H]$ ⁻ 619.1358, found: 619.1359. Elemental analysis calcd $(\%)$ for $C_{34}H_{24}N_2O_{10}$: C 65.81, H, 3.90, N 4.51; found: C 65.77, H 4.03, N 4.62.

BPDI-Ile. 1 H NMR (300 MHz, DMSO- $d_{6})$ δ 13.07 (s, 2H), 8.33 $(d, J = 8.3 \text{ Hz}, 4\text{H}), 8.05 (d, J = 7.8 \text{ Hz}, 2\text{H}), 4.55 (d, J = 8.1 \text{ Hz},$ 2H), 2.39 (t, $J = 8.3$ Hz, 2H), 1.49 (ddd, $J = 13.5, 7.5, 3.5$ Hz, 2H), 1.07 (d, $J = 6.7$ Hz, 6H), 1.04-0.94 (m, 2H), 0.81 (t, $J = 7.3$ Hz, 6H). ¹³C NMR (75 MHz, DMSO- d_6) δ 169.87, 167.13, 144.77,

134.09, 132.05, 130.78, 124.19, 122.63, 56.56, 33.94, 16.85, 10.87. ESI-MS: m/z calculated for: $[M - H]$ ⁻ 519.1773, found: 519.1764. Elemental analysis calcd (%) for $C_{28}H_{28}N_2O_8$: C 64.61, H 5.42, N 5.38; found: C 64.67, H 5.73, N 5.31.

BPDI-Lys. ¹H NMR (300 MHz, DMSO- d_6) δ 13.19 (s, 2H), 8.33 $(d, J = 7.3 \text{ Hz}, 4\text{H}), 8.04 (d, J = 8.0 \text{ Hz}, 2\text{H}), 6.74 (d, J = 6.2 \text{ Hz},$ 2H), 4.76 (t, $J = 7.8$ Hz, 2H), 2.86 (q, $J = 6.2$ Hz, 4H), 2.20-2.02 $(m, 4H)$, 1.30 (s, 26H). ¹³C NMR (75 MHz, DMSO) δ 170.53, 167.04, 155.56, 144.70, 133.98, 132.21, 130.93, 124.15, 122.52, 77.27, 51.91, 29.02, 28.97, 28.20, 27.80, 23.16. ESI-MS: m/z calculated for: $[M - H]$ ⁻ 749.3039, found: 749.3042. Elemental analysis calcd (%) for $C_{38}H_{46}N_4O_{12}$: C 60.79, H 6.18, N 7.46; found: C 60.73, H 6.23, N 7.51.

BPDI-Cys. ¹H NMR (600 MHz, DMSO- d_6) δ 8.33 (dd, *J* = 24.6, 16.7 Hz, 4H), 8.04 (d, $J = 7.7$ Hz, 2H), 7.28–7.20 (m, 30H), 4.56 $(dd, J = 11.4, 4.5 Hz, 2H$, 3.09 $(t, J = 12.9 Hz, 2H)$, 2.91 $(dd, J =$ 13.1, 4.3 Hz, 2H). ¹³C NMR (151 MHz, DMSO) δ 168.86, 166.50, 143.97, 143.76, 129.02, 128.32, 128.10, 127.76, 127.50, 126.88, 126.22, 66.50, 55.77, 39.52, 30.59. ESI-MS: m/z calculated for: [M $-H$ ^{$-$} 983.2466, found: 983.2485. Elemental analysis calcd $(\%)$ for $C_{60}H_{44}N_2O_8S_2$: C 73.15, H 4.50, N 2.84; found: C 73.24, H 4.63, N 2.89. Paper

C₂11₂M₂O_pc C.65.62, 11.392, N.31₂(11.302, 11.342, N.312, 12.459, 132.62, 132.454, 132.63, 23.53, 23.45

(5, 241), 82.25, 234), 8-22 (d., 42), 423-45 (d., 42), 0.31

(5, 241), 82.25, 234), 8-22 (d., 42), 4

BTDI-Phe. ¹H NMR (300 MHz, DMSO- d_6) δ 13.49 (s, 2H), 8.24–8.10 (m, 3H), 8.06–7.97 (m, 3H), 7.18 (d, $J = 4.2$ Hz, 10H), 5.18 (dd, $J = 11.6$, 4.8 Hz, 2H), 3.51 (dd, $J = 14.1$, 5.0 Hz, 2H), 3.35 (dd, $J = 14.0$, 11.5 Hz, 3H). ¹³C NMR (75 MHz, DMSO- d_6) d 193.05, 169.86, 166.28, 141.85, 137.22, 136.35, 133.59, 130.86, 128.73, 128.38, 126.64, 124.05, 123.85, 53.28, 33.94. ESI-MS: m/z calculated for: $[M - H]$ ⁻ 615.1409, found: 615.1413. Elemental analysis calcd (%) for $C_{35}H_{24}N_{2}O_{9}$: C 68.18, H 3.92, N 4.54; found: C 68.33, H 3.83, N 4.61.

BTDI-Tyr. 1 H NMR (300 MHz, DMSO- d_{6}) δ 13.43 (s, 2H), 9.17 $(s, 2H)$, 8.19–8.00 (m, 6H), 6.94 (d, $J = 8.2$ Hz, 4H), 6.56 (d, $J =$ 8.5 Hz, 4H), 5.08 (dd, $J = 11.5$, 4.9 Hz, 2H), 3.38 (dd, $J = 14.2$, 4.9 Hz, 2H), 3.24 (dd, $J = 14.2$, 11.6 Hz, 2H). ¹³C NMR (75 MHz, DMSO-d6) d 193.09, 169.98, 166.34, 155.89, 141.86, 136.39, 133.67, 130.94, 129.69, 127.16, 124.07, 123.85, 115.23, 53.61, 33.10. ESI-MS: m/z calculated for: $[M - H]$ ⁻ 647.1307, found: 647.1309. Elemental analysis calcd (%) for $C_{35}H_{24}N_2O_{11}$: C 64.82, H 3.73, N 4.32; found: C 64.87, H 3.93, N 4.26.

BTDI-Ile. ¹H NMR (300 MHz, DMSO- d_6) δ 13.12 (s, 2H), 8.26– 8.09 (m, 6H), 4.57 (d, $J = 8.0$ Hz, 2H), 2.47–2.30 (m, 2H), 1.62– 1.38 (m, 2H), 1.07 (d, $J = 6.7$ Hz, 6H), 1.02-0.86 (m, 2H), 0.81 (t, J $= 7.3$ Hz, 6H). ¹³C NMR (75 MHz, DMSO- d_6) δ 193.30, 169.68, 166.75, 141.86, 136.24, 134.03, 131.26, 124.13, 123.93, 56.74, 33.99, 25.33, 16.75, 10.91. ESI-MS: m/z calculated for: $[M - H]$ ⁻ 547.1722, found: 547.1725. Elemental analysis calcd (%) for $C_{29}H_{28}N_{2}O_{9}$: C 63.50, H 5.15, N 5.11; found: C 63.57, H 5.25, N 5.24.

BTDI-Lys. 1 H NMR (300 MHz, DMSO- d_{6}) δ 13.22 (s, 2H), 8.27– 7.97 (m, 6H), 6.73 (t, $J = 5.9$ Hz, 2H), 4.77 (t, $J = 7.7$ Hz, 2H), 2.86 $(dd, J = 12.5, 6.3 Hz, 4H, 2.09 (t, J = 7.9 Hz, 4H), 1.48-1.11 (m,$ 26H). ¹³C NMR (75 MHz, DMSO- d_6) δ 193.31, 170.38, 166.66, 155.57, 141.81, 136.17, 134.20, 131.41, 124.02, 123.92, 77.31, 52.10, 29.02, 28.22, 27.80, 27.73, 23.14. ESI-MS: m/z calculated for: $[M - H]$ ⁻ 777.2989, found: 777.3006. Elemental analysis calcd (%) for $C_{39}H_{46}N_4O_{13}$: C 60.15, H 5.95, N 7.19; found: C 60.32, H 6.13, N 7.27.

BTDI-Cys. ¹H NMR (600 MHz, DMSO- d_6) δ 13.57 (s, 2H), 8.27– 8.20 (m, 3H), 8.17-8.09 (m, 3H), 7.29 (dd, $J = 9.2$, 5.9 Hz, 30H), 4.62 (dd, $J = 11.0$, 5.0 Hz, 2H), 3.15–3.08 (m, 2H), 2.98 (dd, $J =$ 14.1, 5.0 Hz, 2H). 13C NMR (151 MHz, DMSO) d 193.14, 168.78, 166.10, 143.96, 143.77, 129.07, 129.05, 128.33, 128.13, 127.81, 127.51, 126.92, 126.23, 66.66, 55.85, 30.46. ESI-MS: m/z calculated for: $[M - H]^-$ 1011.2415, found: 1011.2435. Elemental analysis calcd (%) for $C_{61}H_{44}N_2O_9S_2$: C 72.32, H 4.38, N 2.77; found: C 72.51, H 4.51, N 2.71.

Conclusions

In conclusion, the use of microwave heating and an appropriate choice of solvent/base pair provide an efficient means of preparing a diverse family of symmetrical diimides based on three structurally distinct aromatic cores and five different amino acids. The developed methodology shows that the syntheses are equally efficient under pressure (small scale) or in open vessels (large scale). The reactions proceed without racemization at α -centre and led to enantiomerically clean products. Short reaction times and facile workup make the developed protocol extremely useful, the present work having provided a library of functionalised diimides with a variety of possible applications. **BSC Articles:** Published on 23 August 2018. Downloaded on 23 August 2018. Downloaded on 24 August 2018. Downloaded on 23 August 2018. Downloaded the CALIFORNIA CREATIVE COMMON Access Articles. The CALIFORNIA CREATIVE COM

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

We thank the Polish National Centre for Research and Development (LIDER 024/391/L-5/13/NCBR/2014) and Polish National Science Centre (UMO-2017/25/N/ST5/00451) for funding.

Notes and references

- 1 M. Al Kobaisi, S. V. Bhosale, K. Latham, A. M. Raynor and S. V. Bhosale, Chem. Rev., 2016, 116, 11685–11796.
- 2 M. J. Robb, B. Newton, B. P. Fors and C. J. Hawker, J. Org. Chem., 2014, 79, 6360–6365.
- 3 T. Seki, S. Yagai, T. Karatsu and A. Kitamura, J. Org. Chem., 2008, 73, 3328–3335.
- 4 F. Fennel, J. Gershberg, M. Stolte and F. Würthner, Phys. Chem. Chem. Phys., 2018, 20, 7612–7620.
- 5 M. A. Squillaci, G. Markiewicz, A. Walczak, A. Ciesielski, A. R. Stefankiewicz and P. Samorì, Chem. Commun., 2017, 53, 9713–9716.
- 6 A. R. Stefankiewicz, E. Tamanini, G. D. Pantos¸ and J. K. Sanders, Angew. Chem., Int. Ed., 2011, 50, 5725–5728.
- 7 V. L. Malinovskii, D. Wenger and R. Haner, Chem. Soc. Rev., 2010, 39, 410–422.
- 8 D. Gorl, X. Zhang and F. Würthner, Angew. Chem., Int. Ed., 2012, 51, 6328–6348.
- 9 J. Gershberg, M. Radić Stojković, M. Skugor, S. Tomić, H. Rehm Thomas, S. Rehm, R. Saha-Möller Chantu, I. Piantanida and F. Würthner, Chem.-Eur. J., 2015, 21, 7886–7895.
- 10 R. E. Dawson, A. Hennig, D. P. Weimann, D. Emery, V. Ravikumar, J. Montenegro, T. Takeuchi, S. Gabutti, M. Mayor, J. Mareda, C. A. Schalley and S. Matile, Nat. Chem., 2010, 2, 533–538.
- 11 M. Safont-Sempere Marina, P. Osswald, K. Radacki and F. Würthner, Chem.-Eur. J., 2010, 16, 7380-7384.
- 12 D.-J. Liaw, F.-C. Chang, J.-H. Liu, K.-L. Wang, K. Faghihi, S.-H. Huang, K.-R. Lee and J.-Y. Lai, Polym. Degrad. Stab., 2007, 92, 323–329.
- 13 X. Cao, A. Gao, H. Lv, H. Lan, Q. Cheng and N. Zhao, RSC Adv., 2015, 5, 48500–48505.
- 14 Q. Zheng, J. Huang, A. Sarjeant and H. E. Katz, J. Am. Chem. Soc., 2008, 130, 14410–14411.
- 15 P. Pengo, G. D. Pantos, S. Otto and J. K. Sanders, J. Org. Chem., 2006, 71, 7063–7066.
- 16 K. Tambara, N. Ponnuswamy, G. Hennrich and G. D. Pantos¸, J. Org. Chem., 2011, 76, 3338–3347.
- 17 H. Toiserkani and M. Rafiaee, Bull. Chem. Soc. Jpn., 2013, 86, 289–295.
- 18 A. Feyzi, K. Faghihi, A. Raeisi, M. Koushki and M. Farahani, J. Chil. Chem. Soc., 2013, 58, 1884–1887.
- 19 K. A. Murphy, A. S. Zebertavage, B. E. Kiliman and D. A. Shipp, J. Polym. Sci., Part A: Polym. Chem., 2013, 51, 4637–4642.
- 20 B. K. Manukian, P. Niklaus and H. Ehrsam, Helv. Chim. Acta, 1969, 52, 1259–1273.
- 21 H. Iataaki and H. Yoshimoto, J. Org. Chem., 1973, 38, 76–79.
- 22 N. Finch, C. W. Gemenden and B. P. Korzun, J. Org. Chem., 1976, 41, 2509–2514.
- 23 Q. Zheng, J. Huang, A. Sarjeant and H. E. Katz, J. Am. Chem. Soc., 2008, 130, 14410–14411.
- 24 T. Abdinejad, M. R. Zamanloo, T. Alizadeh and N. O. Mahmoodi, Dyes Pigm., 2017, 146, 203–209.
- 25 J. C. Sheehan, D. W. Chapman and R. W. Roth, J. Am. Chem. Soc., 1952, 74, 3822–3825.
- 26 N. Roy, B. Bruchmann and J. M. Lehn, Chem. Soc. Rev., 2015, 44, 3786–3807.