RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2018, 8, 41994

Defect mediated mechanism in undoped, Cu and Zn-doped TiO₂ nanocrystals for tailoring the band gap and magnetic properties[†]

V. R. Akshay,^{ab} B. Arun,^{ab} Shubhra Dash,^c Ajit K. Patra,^c Guruprasad Mandal,^d Geeta R. Mutta, [©] Anupama Chanda [©] *^f and M. Vasundhara^{*ab}

Oxide based dilute magnetic semiconductor materials have been of great interest over the years due to their potential use in spintronic devices. However, the variations in the magnetic behavior of the materials have raised concerns regarding the origin of ferromagnetic properties which still needs to be explored. Manipulation of magnetic behavior in oxide based dilute magnetic semiconductors has become a challenge due to the interplay of intrinsic defects present in the material. TiO₂ nanocrystals have been studied largely due to their challenging optical and magnetic properties. The present investigation studies in detail the structural, morphological, optical and magnetic behavior of nonmagnetic element (Cu and Zn) doped TiO₂, synthesized via a simple sol-gel technique. X-ray diffraction patterns and Raman spectra confirm the anatase phase and high resolution transmission electron microscopic results clearly indicate the formation of highly crystalline nanocrystals in all the samples with particle size ranging from 5-15 nm. Energy dispersive X-ray fluorescence spectroscopic studies reveal the compositional homogeneity of all the investigated samples. The presence of functional groups and molecular interactions were identified by Fourier transform infrared spectroscopy. Optical properties were studied through UV-visible and photoluminescence spectroscopy from which a significant reduction in band gap in Cu-doped TiO₂ nanocrystals was found. X-ray photoelectron spectra confirm the presence of Ti³⁺, Cu²⁺, Cu⁺ and Zn²⁺ in Cu and Zn-doped TiO₂ samples. The concept of bound magnetic polarons associated with the vacancy defects at both Ti, Cu, Zn and oxygen sites is used to explain the induced weak ferromagnetic behavior in undoped, Cu and Zn-doped TiO₂ at room temperature. The overlapping of bound magnetic polarons could be the source of ferromagnetism irrespective of the non-magnetic nature of the dopant ion. The concentration of bound magnetic polarons is estimated using a Langevin fit and a detailed understanding of the variation of defect mediated magnetic properties is established with the help of PL analysis. A significant reduction in bandgap along with enhanced magnetization observed in the Cu-doped TiO₂ material makes it suitable as a potential candidate for spintronics and magneto-optics applications. Room temperature magnetic properties of the Zn doped sample show a diamagnetic tail which is explained based on the defect centers and oxidation states of dopant ions present in the sample which is further verified with the help of XPS results.

Received 31st August 2018 Accepted 24th November 2018

DOI: 10.1039/c8ra07287f

rsc.li/rsc-advances

^aMaterials Science and Technology Division, CSIR-National Institute for Interdisciplinary Science and Technology, Trivandrum-695 019, India. E-mail: mvas@niist.res.in; anupamamatsc@gmail.com

^bAcademy of Scientific and Innovative Research (AcSIR), CSIR, Trivandrum, India ^cDepartment of Physics, Central University of Rajasthan, India

^dCentre for Rural and Cryogenic Technologies, Jadavpur University, Kolkata-700032, India

^eNano-Materials Laboratory, School of Engineering and Physical Sciences, Heriot Watt University, Edinburgh EH14 4AS, UK

† Electronic supplementary information (ESI) available. See DOI: 10.1039/c8ra07287f

Introduction

 TiO_2 is a wide-band-gap semiconductor, the nanocrystals of which find a large number of practical applications such as in dilute magnetic semiconductors (DMS),¹ photo-catalysts,² lithium-ion batteries³ and photo-electrochemical solar energy conversion.⁴⁻⁶ In the past decade, much attention has been focused on TiO_2 specifically due to its interesting optical and electronic properties, non-toxicity, low cost, and high stability. The synthesis conditions, modification of nanostructured TiO_2 and tailoring of the band gap have long been the core area of research which has drawn great attention. TiO_2 can be treated as a multifunctional material but due to its wide band gap it can

Department of Physics, Dr Hari Singh Gour Central University, Sagar, Madhya Pradesh, India

absorb only UV radiation and the total solar spectrum cannot be useful for practical purposes. Hence, the optoelectronics application requires tailoring of its energy band gap which can be obtained by suitable doping with appropriate dopants.

Transition metal (TM) elements can successfully induce changes in the band gap and reports suggest that substitutional doping can alter the optical and magnetic properties of TiO₂ nanocrystals.7-13 In general, nanosized semiconductor materials like TiO₂ usually contain a large number of surface oxygen vacancies because of both surface and size effects. The oxygen vacancies strongly affect the electronic states, which modify the optical and magnetic properties.14-17 Therefore, the impact of oxygen vacancies on the material properties is considered to be a crucial factor for various applications. Further, depending on the type of TM ion dopant, TiO₂ nanocrystals exhibit different optical and magnetic properties, which can be ferromagnetic (FM), paramagnetic (PM), superparamagnetic (SPM) or diamagnetic. It is expected that due to self purification mechanism, successful doping of nanocrystals will be a tedious job and distribution of dopant ions will be more near the surface than the core of the nanocrystals.¹⁸⁻²⁰ It is well reported that doping with magnetic transition elements such as Fe, Co and Ni can induce ferromagnetism in TiO₂.

TiO₂ has also been studied largely as a DMS material for spintronics and magneto-optic devices²¹⁻²³ due to its good optical transmission in UV-visible as well as in the near-infrared region. Our recent report well explains the magnetic properties of Co doped TiO_2 in which it is suggested that Co doped TiO_2 could be a potential candidate for DMS applications.²⁴ The concept of DMS lies with the introduction of magnetic impurities to replace a small fraction of cations in the semiconductor host lattice. For practical applications of DMS based spintronics devices room temperature ferromagnetism (RTFM) is essential and the ferromagnetism should be intrinsic. The discovery of RTFM in Co-doped anatase TiO2 and ZnO23-26 invited worldwide attention on oxide-based DMS for spintronics devices. In particular, TiO₂ has been given much importance due to its multifunctional applications, as an excellent photocatalyst as well as magneto-optic devices. Even though a good amount of work has been reported on TiO₂ based DMS, the origin of RTFM in TiO₂ is still under controversy. These controversies are due to the existence of intrinsic defects like oxygen vacancies or Ti interstitials or extrinsic contributions arising from magnetic clusters due to TM doping.24,27-35 It is interesting to note that RTFM has been even reported in un-doped and non-magnetic impurities doped TiO₂ and other oxides^{36,37} which suggests the importance of defects in creating ferromagnetic ordering.

The structural and optical properties of TiO_2 nanocrystals doped with different TM elements like Fe, Co, Ni, Cu, Mn, *etc.* and their influence on the magnetic properties and interaction of these doped ions with defects such as oxygen vacancies present in the TiO_2 lattice have been reported.^{1,24,38-42} Recently, few reports have suggested that successful incorporation of metal ions into the host lattice can induce a red shift in the band gap of TiO_2 material and create oxygen vacancies which contribute towards FM.⁴³ Our recent report suggests that Co doping in TiO_2 can induce FM, which could be due to the combined effect of inherent magnetism present in the doped element and oxygen vacancies present in doped TiO2.24 Very few studies have reported about the origin of magnetic behavior of non magnetic transition element doped TiO₂ and the formation of both TM ion site vacancies and oxygen site vacancies. In the present study, we have investigated in detail the structural, morphological, optical and magnetic properties of undoped, Cu and Zn doped TiO₂ nanocrystals synthesized by a simple and cost effective sol-gel technique. A significant reduction in bandgap in Cu-doped TiO2 as well as a narrowing of bandgap in Zn-doped TiO₂ is obtained. The magnetic behavior of undoped, Cu and Zn doped TiO₂ material has been explained based on bound magnetic polaron (BMP) model. The present work is focused on the study of the formation of Cu and Zn-doped TiO₂ nanocrystals with defects associated with Ti and O site which ultimately decides the optical and magnetic behavior of these materials.

Experimental

Undoped, Cu (3%) and Zn (3%) doped TiO₂ nanocrystals were synthesized by a simple sol-gel technique where titanium butoxide and corresponding metal nitrates were used as the Ti and metal ion precursors respectively. The synthesis approach enables the formation of stable anatase phase of all the studied samples and hence after named as T-P, T-Cu and T-Zn for undoped, Cu-doped and Zn-doped samples respectively. The resultant sol-gel materials were calcined at 400 °C for 3.5 h in a muffle furnace under ambient air atmosphere. Their structure and phase purity were studied by X-ray diffraction (XRD) at room temperature using PANalytical X'Pert Pro diffractometer with Cu-Ka radiation. The crystal structure of anatase TiO2 was generated using Vesta software. Micro-Raman spectroscopy was performed using Horiba Jobin Yvon LabRAM HR 800 micro-Raman spectrometer using 1800 grooves mm^{-1} grating, with the spectral resolution of 2 cm^{-1} . All the experiments were performed using the excitation wavelength of 405 nm. The particle size and morphology were studied using High Resolution-Transmission Electron Microscopy (HR-TEM, FEI Tecnai F20, operated at 300 kV). Again, to confirm the elemental composition, an energy dispersive X-ray Fluorescence Spectrometry (ED-XRFS) study was carried out using PANalytical Epsilon 3 and further confirmed by Inductive Coupled Plasma -Mass Spectroscopy (ICP-MS, Thermofisher Scientific, Model iCAP-RQ-ICPMS). Functional group identification of the prepared nanocrystals was investigated by Fourier Transform-Infrared (FT-IR) spectra using a Bruker FT-IR spectrometer. The UV-visible spectra of the samples were recorded by a Shimadzu UV 2401 PC spectrophotometer and the emission spectra were obtained from a spectrofluorometer (Cary Eclipse, Varian). The X-ray photoelectron spectroscopy (XPS) study was carried out on powder samples at room temperature using a PHY 5000 Versa Probe II, ULVAC-PHI, Inc instrument. Al Ka was used as the X-ray source and pressure in the XPS chamber during the measurements was 5×10^{-10} mbar. The binding energies were corrected by taking C 1s as reference energy (C 1s = 284.60 eV). A wide scan was collected to ensure that no

foreign material was present on the sample surface. The highresolution scans of Ti 2p, Cu 2p and Zn 2p regions were collected. Curve fitting to the XPS spectrum was done using MultiPak Spectrum:ESCA. Background subtraction was done using the Shirley method. Room temperature magnetic studies were performed using vibrating sample magnetometer (VSM) attached to the physical property measurement system, Quantum Design Inc., (USA).

Results and discussion

Fig. 1 shows the Rietveld refinement patterns of the T-P, T-Cu and T-Zn nanocrystals. All the samples were found to crystallize in the tetragonal anatase phase of TiO₂ and match well with the JCPDS card no: 89-4921.44,45 Fig. S1 (given in ESI†) shows the indexed XRD patterns along with peak shift associated with each sample. No diffraction peaks related to Cu and Zn can be seen in the XRD pattern of T-Cu and T-Zn. The shifting of the highest intense (101) peak as well as change in full width at half maximum (FWHM) in T-Cu and T-Zn XRD patterns indicate the incorporation of Cu and Zn in the host lattice. The crystallite size calculated from XRD analysis for T-P, T-Cu and T-Zn are 12.10 nm, 13.31 nm and 11.27 nm respectively. Rietveld refinement was carried out by varying 16 parameters such as background parameters, unit cell, shape and isotropic thermal parameters, and oxygen occupancy using the Fullprof-98 program. The refined parameters of T-P, T-Cu and T-Zn are depicted in Table 1.

The Rietveld refinement indicates the incorporation of Cu and Zn ions in the sol-gel derived TiO₂ matrix. As a representative of the series, the anatase crystal structure of TiO₂ derived using Vesta software is depicted in Fig. S2.[†] To further confirm the phase and crystallinity of T-P, T-Cu and T-Zn nanocrystals, Raman spectra were taken and are shown in Fig. 2. Raman spectrum of T-P nanocrystals exhibits peaks which are located at around 144, 196, 398, 520 and 640 cm⁻¹. These peaks correspond to the lattice vibration of $E_g(1)$, $E_g(2)$, $B_{1g}(1)$, A_{1g} + B_{1g} (2), and E_{g} (3) modes of anatase TiO₂ respectively.⁴⁶⁻⁴⁸ Raman spectra of T-Cu and T-Zn show typical spectra of anatase TiO₂. Furthermore, there is no Cu or Zn related Raman peaks in doped TiO₂ samples. The absence of the characteristic Cu and Zn vibration modes in the Raman spectra reveals that there is no segregation of Cu or Zn in TiO₂ nanocrystals. These results

clearly suggest the solid solution formation in T-P, T-Cu and T-Zn samples, which is consistent with the XRD analysis.

The absence of any other mode related to Cu, Zn, CuO, ZnO, Cu-Ti or Zn-Ti species within the detection limit of Raman spectra of doped samples indicates that the doped elements might have gone to the substitutional site replacing Ti in TiO₂. The ionic size of Cu^{2+} (0.73 Å) is larger than that of Ti^{4+} (0.64 Å) and hence substitution of Cu on Ti site will distort the lattice structure. Also due to the charge difference between Ti⁴⁺ and Cu²⁺, substitution of Cu will generate oxygen vacancies in the lattice to maintain charge neutrality. It is very clear that the phonon confinement and non-stoichiometry due to defects associated with the system could induce disorders in the lattice leading to the shifting and broadening of Raman lines.48 Hence, it is believed that defects like oxygen vacancy in the material strongly affect the Raman modes. In our study, the most intense E_{g} (1) Raman mode at 144 cm⁻¹ shows blue shifting and slight broadening with doping (Fig. 2(b)). XRD and TEM (discussed later) results show the crystallite size in the nanoscale range. So, both the phonon confinement and disorder in the host lattice induced due to the incorporation of Cu, Zn atoms/ions creating defects like oxygen vacancies in TiO₂ have caused the shifting and broadening of the Raman peaks.49-51

Detailed TEM micrographs showing the morphology of all the samples are given in Fig. 3. Interestingly, the morphology is highly dependent on synthesis conditions, which assisted the formation of nanocrystals with an average particle size of about 12 nm in T-P which further agrees well with the crystallite size estimated from the XRD results. It is reported that sol-gel route facilitates the formation of nanostructures.52,53 Cu substitution into the Ti site could result in lattice expansion due to larger ionic size of Cu and hence an increase in particle size is also expected as mentioned in the crystallite size calculation from XRD analysis. TEM results of T-Cu indicate the formation of nanocrystals having higher particle size (13 nm) than T-P sample (12 nm). Interestingly, T-Zn sample shows a decrease in particle size (11 nm) which also agrees well with the crystallite size calculated from XRD results. Previous reports suggest the reduction in particle size of TiO2 upon Zn doping.54 The T-P sample shows an average particle size of 12 nm and T-Zn samples show an average size of 11 nm suggesting that Zn doping has significantly decreased the size distribution of nanocrystals. Fig. 3(d-f) demonstrate the high resolution TEM



Fig. 1 Rietveld refinement of XRD patterns of (a) T-P (b) T-Cu and (c) T-Zn nanocrystals

Compound	T-P	T-Cu	T-Zn		
Phase		Anatase			
Crystal structure	Tetragonal				
Space group	I41/amd				
Lattice parameters					
a (Å)	3.7901	3.7932	3.7940		
<i>c</i> (Å)	9.4923	9.5016	9.5162		
Volume $(Å)^3$	136.35 136.71 13				
Residual parameters					
R _p	4.56	3.98	3.38		
R _{wp}	5.77	5.33	4.55		
χ^{2}	1.89	1.94	1.83		

images of T-P, T-Cu and T-Zn samples respectively. The high resolution TEM images show clear lattice fringes without any distortion in TiO₂ and (Cu, Zn) nanocrystals indicating the high crystallinity of the nanocrystals. The estimated interplanar spacing of adjacent lattice fringes of T-P corresponds to the (101) and (004) planes of anatase TiO_2 which are shown in Fig. 3(d). Similarly, (101), (004) and (200) planes of T-Cu are represented in Fig. 3(e) and high resolution TEM images and FFT suggest the crystalline nature and quality of the prepared samples. Further Fig. 3(f) demonstrates the (101) and (004) planes of T-Zn sample and the interplanar spacing obtained in each case are in accordance with the XRD patterns (Fig. 1). Fig. 3(g-i) represent the selected area diffraction patterns (SAED) of the T-P, T-Cu and T-Zn samples respectively which suggest the polycrystalline nature of all the samples and T-Cu shows an enhanced crystallinity among the three samples, which again corroborates with high resolution TEM images and lattice fringes as discussed earlier.

To investigate on the elemental compositions, an ED-XRF analysis was carried out on all the samples. The stoichiometries of all the studied compounds were found by ED-XRF analysis. Chemical compositions of T-P, T-Cu and T-Zn are given in Table 2. The undoped TiO_2 is dominated with 99.97% TiO_2 which clearly shows the presence of TiO2 alone and the slight mismatch could be covered within the limit of experimental error. It is

evident that the ratios of Ti : Cu and Ti : Zn are very much close to the nominal compositions for T-Cu and T-Zn respectively. It is worthwhile to note that the ratio of Ti : (Cu, Zn) were also found to be the same as that of the expected single phase composition within the limits of experimental error. Further, the elemental composition and accuracy are verified using ICP-MS analysis and the results are shown in Table 3.

FT-IR spectroscopy technique gives information about the functional groups, inter and intra-molecular interactions and the molecular geometry of the compound. FT-IR spectra of all the samples were taken at room temperature to identify the various functional groups and vibrational bands present in the samples which are shown in Fig. 4. Different bands observed in FT-IR spectra of T-P, T-Cu and T-Zn nanocrystals are summarized in Table S1.[†] Among the different bands that appear in the spectra, the broad band around 3500 cm^{-1} corresponds to the stretching vibration of OH groups and could be due to the OH group associated with the Ti atoms, i.e., Ti-OH. The narrow band around 1650 cm⁻¹ is well known for the characteristic bending vibrations of H-O-H. However, the peak close to 1400 cm⁻¹ has been ascribed to C-O stretching bond present in the precursor material as discussed earlier. This peak might have arisen as a result of the organic radical from Ti-butoxide which is adsorbed in the nanocrystals. The presence of organic components in studied samples are clearly observed from TEM images shown in Fig. 5, in which the amorphous regions have been shown which suggest the existence of organic residues along with crystalline TiO₂ nanocrystals. The FFT corresponding to different regions are also clearly demonstrated in Fig. 5. The band centered at nearly 550 cm^{-1} are due to bonding among metal and oxygen, *i.e.*, metal-oxygen bonds of (Ti-O) in undoped, (Ti-O, Cu-O) and (Ti-O, Zn-O) in Cu and Zn doped TiO₂ nanocrystals.^{55,56} Furthermore, no peak corresponding to any other oxide phases of doped elements appeared in the spectra. It reveals that doped metal ions are introduced into the Ti framework. This result corroborates with the results of XRD, TEM and ED-XRFS as mentioned earlier.

Fig. 6(a) shows the UV-visible absorption spectra of all the samples. The optical absorption of all the samples was obtained from the diffuse reflectance spectra using Kubelka-Munk equation. The Cu and Zn doped TiO2 nanocrystals show



Fig. 2 Raman spectra of (a) T-P, T-Cu and T-Zn samples (b) Raman peak shift of E_a (1) mode associated with T-P, T-Cu and T-Zn samples.



Fig. 3 (a-c) TEM images of T-P, T-Cu and T-Zn showing the formation of nanocrystals with histogram showing particle size distribution in the inset (d-f) HR-TEM images showing lattice fringes with FFT shown in the inset and (g-i) SAED patterns of samples.

a regular shift of the absorption edge towards longer wavelengths due to incorporation of Cu and Zn in TiO_2 . The undoped TiO_2 sample shows an optical absorption near 375 nm, which is ascribed due to the electronic transition between valence and conduction band. A slight shift in optical absorption edge is observed for T-Zn which is around 385 nm whereas a clear red shift is observed for T-Cu towards longer wavelength. It is clear from XRD and TEM analysis that particle size is decreased with Zn doping and previous reports suggest that the red shift of the absorption edge cannot be due to quantum

confinement effect.⁵⁷ New energy bands are created within the band gap of TiO_2 due to these metal ion doping. The transition from valence band to intra-band energy levels or from these intermediate levels to the conduction band can cause the red shift of the absorption edge of TiO_2 . This red shift can be taken as an evidence for the incorporation of doped metal ions into the TiO_2 lattice. The band gap (obtained from Tauc's plot) observed for T-P, T-Cu and T-Zn are 3.16 eV, 2.38 eV and 3.05 eV

Table 2	2 ED-XRFS data obtained for T-P, T-Cu and T-Zn					
Compou	ınd	Percentage of elemental oxide				
T-P		99.97% TiO ₂				
T-Cu		97.10% TiO ₂ + 2.90% CuO				
T-Zn		97.03% TiO ₂ + 2.97% ZnO				

Table	3	ICP-MS	analysis	of	Τ-Р,	T-Cu	and	T-Zn	to	confirm	the
eleme	nta	Il concen	tration								

Material	Molar ratio of TM/Ti (TM = Cu, Zn)	Actual composition
T-P	0	TiO ₂
T-Cu	0.032	Ti _{0.97} Cu _{0.03} O ₂
T-Zn	0.034	Ti _{0.97} Cu _{0.03} O ₂



Fig. 4 FT-IR spectra of T-P, T-Cu and T-Zn samples.

respectively which are illustrated in Fig. 6(b). The decrease in band gap for T-Cu and T-Zn is due to the incorporation of metal ions into host crystal lattice. The red shift in bandgap due to Cu and Zn doping can be due to sp–d exchange interactions between the band electrons and the localized d-electrons of Cu^{2+} and Zn^{2+} ions substituting Ti^{4+} ions. The s–d and p–d exchange interactions give rise to downward shifting of conduction band edge and upward shifting of valence band edge resulting in narrowing of bandgap. The interaction of

these metal ions with the conduction band electrons could have shifted the valence band by lowering the conduction band which results in the reduction of band gap for the doped $\rm TiO_2$ nanocrystals.

PL spectra provides information regarding structural matters, defects in the crystal lattice and trap states of the material which decides the electronic structure of materials. Thus PL spectra recorded for all the samples are shown in Fig. 7(a). The deconvoluted PL spectra of T-P, T-Cu and T-Zn are represented in Fig. 7(b), (c) and (d) respectively, from which strong emission peaks are observed in the range 370-600 nm. The emission peak observed around 390 nm is due to the near band edge emission of host TiO2. The emission peaks located in between 400-450 nm have arisen as a result of self-trapped excitons (STE), oxygen vacancies, surface defects, etc.⁵⁸⁻⁶¹ The STE arises when a trapped electron captures a hole in TiO_2 , more clearly, the recombination occurs through oxygen vacancies present in the system. Since oxygen vacancies are intrinsic defects in TiO2 and Cu/Zn doping also creates oxygen vacancies due to the substitution of Cu⁺/Cu²⁺/Zn²⁺ on Ti⁴⁺, the emissions around 400-450 nm are probably due to STE.58-61 The emission peak at 490 nm appears as a result of charge transition from Ti³⁺ to TiO₆²⁻ linked with oxygen vacancies⁶² and the peak at nearly 520 nm may have appeared due to the F⁺-center formation.^{63,64} The hydroxyl (OH) species as observed in the FTIR spectra as well as confirmed from XPS analysis (which are discussed in the coming sections), can create an acceptor level just above the valence band and contributes for the observed emission near 600 nm.14 It is expected that the presence of oxygen deficiency in



Fig. 5 TEM images and corresponding FFT patterns of T-P (a and b) T-Cu (c and d) and T-Zn (e and f) showing the coexistence of both amorphous and crystalline regions.



Fig. 6 (a) UV-visible spectra of T-P, T-Cu and T-Zn samples and (b) corresponding Tauc's plot.

small amounts cannot be ruled out in the air annealing process and hence the multiple oxidation states of Ti is expected in the system which is discussed in detail in the later sections.

The magnetic properties of undoped, Cu-doped and Zndoped TiO₂ nanocrystals were studied by VSM. The M-H measurements on all the samples were performed by varying the magnetic field from -90 kOe to +90kOe at room temperature. The *M*-*H* curves obtained for all the samples are shown in

Fig. 8(a) from which a PM behavior is observed for T-P and T-Cu whereas a diamagnetic tail is noticed for T-Zn. However, it is interesting to note that the M-H loops show weak FM in T-P and T-Cu sample (Fig. 8(b) and (c)) at lower fields. There is a slight increase in the magnetic moment in T-Cu sample. The inset in Fig. 8(b) shows the M-H plot (zoomed) at lower field of T-P sample at 300 K which gives coercivity (H_c) of 305 Oe. There is a similar observation for T-Cu sample as shown in inset of



Fig. 7 PL spectra of (a) T-P, T-Cu and T-Zn samples (b) deconvoluted PL spectra of T-P, (c) T-Cu and (d) T-Zn.

Fig. 8(c) from which H_c of 120 Oe is noticed. It can be interpreted that different oxidation states of both Ti and Cu might have induced weak FM in the case of T-Cu sample. Hence, the electronic contribution from Cu⁺ and Cu²⁺ could have played crucial role in determining the magnetism of the T-Cu material. The contribution from either Ti³⁺/Cu²⁺ cannot be disregarded in T-P and T-Cu samples, due to which weak FM might have observed at lower fields. RTFM is generally observed when magnetic impurities are introduced into the host lattice due to the FM behavior of the magnetic impurities. Interestingly, very few reports have suggested the observation of PM and FM behavior due to the presence of non-magnetic impurities which could be mainly due to the charge carriers trapped by oxygen vacancies.²⁷⁻³⁵ Some reports⁶⁵ have demonstrated the suppression of FM in TiO₂ even in the presence of magnetic impurities resulting in PM or antiferromagnetic (AFM) behavior due to the presence of secondary phases associated with the reported samples. In the present study, XRD and Raman analysis eliminate the presence of any other secondary phases like Cu or Cu related oxides in the case of T-Cu sample. It is interesting to note that undoped TiO2 exhibits weak RTFM which may have arisen due to intrinsic defects such as Ti site vacancies, oxygen vacancies, Ti³⁺ ions or Ti interstitials.

This observation on the RTFM in nonmagnetic DMS materials such as TiO₂ based system reveals that magnetic properties may not be completely depending on the magnetic ions, but may be mediated effectively by the point defects such as oxygen vacancies or host lattice vacancies. Thus, point defects mediated FM is termed as 'd0 ferromagnetism' which is commonly noticed in nanostructures having high surface area to volume ratio and exhibiting notable surface defects.66,67 Hence, the size and morphology of nanostructures can strongly determine the observed FM, which is so crucial in studying the defect-related FM. The occurrence of intrinsic magnetic moment in TiO₂ nanoparticles can be explained by the magnetic interactions caused by the isolated magnetic moments arising as a result of partially filled electron shells due to imperfections at the surface and inter surface ultimately leading to the surface magnetic moments in nonmagnetic TiO₂ material. Hence, it can be assumed that surface defect states of TiO₂ nanoparticles could be responsible for the intrinsic origin of the macroscopic d0 FM in TiO₂ nanostructures.

The presence of FM in both T-P and T-Cu and an increase in magnetic moment in T-Cu indicate that magnetism can be enhanced due to Cu-doping which may have created more vacancies/Ti³⁺ ions which is well in accordance with the PL results. But in the case of Zn-doped samples although magnetization is observed at lower fields as shown in Fig. 8(d), but an



Fig. 8 Room temperature M-H curves of (a) T-P, T-Cu and T-Zn nanocrystals, (b) T-P, (c) T-Cu and (d) diamagnetic behavior of T-Zn, insets in (b)–(d) show the M-H plots (zoomed) at lower field.

absence of clear PM/FM behavior indicates that long range FM ordering has been lost in the sample, which can be due to the interaction of oxygen vacancies/Zn²⁺ ions with Zn ions inhibiting FM/PM. Although, the T-Zn sample exhibits a diamagnetic behavior at higher magnetic fields, a positive response to the magnetic field well below 1 Tesla is observed (as shown in the inset of Fig. 8(d)). The observation of weak FM at lower magnetic fields might be due to the presence of oxygen vacancy defects and Ti/Zn site defects. A very weak FM observed at lower fields could be attributed to the d0 mechanism as explained above. This could lead to the formation of bound magnetic polarons (BMPs) similar to undoped and Cu-doped samples where small particle size could induce single domain in the system. Raman, UVvisible and XPS analysis indicate the presence of defects like Ti/ Cu/Zn site vacancies or oxygen vacancies in T-P, T-Cu, T-Zn samples. The presence of these deficiencies in both undoped and Cu, Zn doped samples may have been obtained due to the synthesis conditions, surface defects especially arising when nanostructuring due to particle size reduction and these vacancy defects are responsible for variation in the magnetic behavior observed in undoped and doped samples of TiO2.68 A perfect diamagnetism is absent in Zn-doped sample as shown in Fig. 8(d) and a diamagnetic tail is observed which is due to the effect of surface defects and oxygen vacancy defects even though stable Zn²⁺ and Ti⁴⁺exist in the T-Zn sample.

In order to have a detailed understanding of the relationship between magnetic properties and oxidation states of Ti, Cu, Zn and oxygen, XPS spectra have been recorded for all the samples and are shown in Fig. 9-11. Fig. 9(a) shows the wide scan spectra of undoped TiO₂. Elemental scan of Ti in undoped sample is shown in Fig. 9(b). The binding energies of Ti $2p_{3/2}$ and Ti 2p1/2 for the undoped sample are 458.09 eV and 463.76 eV, which are consistent with that of Ti^{4+} . The small peaks at 457.31 eV and 461.10 eV confirm the presence of Ti³⁺ which indicate the existence of both Ti³⁺ and Ti⁴⁺ in the T-P sample.⁶⁹ Hence, the peaks corresponding to the binding energy of both Ti³⁺ and Ti⁴⁺ ions were observed,⁷⁰ which suggests the delocalization of electrons between oxygen vacancies and Ti³⁺ ions on the surface. The O 1s spectra of undoped sample is shown in Fig. 9(c) and the deconvoluted O 1s peak gives three peaks at 529.43 eV, 529.81 eV and 531.41 eV which are ascribed to surface oxygen, probably in the form of surface hydroxyl groups and Ti-O-Ti group.71,72

The XPS wide scan of T-Cu is represented in Fig. 10(a), which indicates the presence of Cu with the appearance of Cu 2p peak.69 The elemental scans of Ti, Cu and O are shown in Fig. 10(b), (c) and (d) respectively. The peaks at 457.51 eV and 463.94 eV correspond to the presence of Ti³⁺ and at 458.97 eV and 464.72 eV corresponds to Ti⁴⁺ ions.⁶⁹ Hence, the presence of both Ti³⁺ and Ti⁴⁺ is confirmed in Cu doped samples. The binding energy of 931.64 eV and 933.45 eV of Cu 2p_{3/2} suggest the presence of Cu⁺ and Cu²⁺ in the present system^{69,73} rather than metallic Cu^{74,75} and hence Ti³⁺/Ti⁴⁺/Cu⁺/Cu²⁺ interactions are possible in the Cu doped system. A slight shift in the peak position of O1s spectra was observed in Cu doped sample in comparison to the undoped sample indicating a change in the surface environments of Cu doped sample. The O 1s spectra of Cu doped sample show a red shift at 531.49, 532.10 and 533.33 eV respectively, which indicates a lesser contribution from the Ti³⁺–O bonds.⁷⁶ The contribution of surface oxygen is significantly more in T-Cu in comparison to undoped T-P as shown in Fig. 10(d).

The appearance of Zn 3s and Zn 3p peaks in the wide scan of T-Zn sample indicates the presence of Zn in T-Zn sample which is represented in Fig. 11(a). The detailed elemental scans of Ti, Zn and O are depicted in Fig. 11(b), (c) and (d) respectively. The peaks corresponding to 458.69 and 464.48 eV represent the Ti $2p_{3/2}$ and Ti $2p_{1/2}$ states which suggest that Ti exists as Ti⁴⁺ in T-Zn sample as shown in Fig. 11(b) where peaks corresponding to Ti³⁺ are completely absent. In the elemental scan of Zn, two peaks of Zn 2p spectrum corresponding to Zn $2p_{3/2}$ and Zn $2p_{1/2}$ electronic states of Zn(II) with binding energies of 1021.99 eV and 1045.08 eV are observed which are clearly shown in Fig. 11(c). Hence, it is confirmed that Zn is bivalent in T-Zn. Therefore, it is well understood that Zn²⁺ exist mainly in ZnO clusters dispersed on TiO2 surface and this could be the reason for perfect diamagnetism exhibited by T-Zn as shown in Fig. 8(d). The O 1s spectra of T-Zn sample is shown in Fig. 11(d) and after deconvolution, the O 1s peak of the sample is split into three peaks at 529.89, 530.01 and 531.58 eV. The behavior of O 1s spectra of T-Zn is almost similar to T-P and slight peak shift observed among T-P, T-Cu and T-Zn could be due to the different surface oxygen contributions present in the respective samples. The intense peak at about 529.89 eV arises due to the oxygen in the TiO₂ crystal lattice (O_L) , while the other oxygen peaks are the outcome of Ti-O/Zn-O bonds (OTi⁴⁺/OZn²⁺,



Fig. 9 XPS spectra of T-P sample (a) wide scan of T-P (b) Ti 2p and (c) O 1s.



Fig. 10 XPS spectra of T-Cu sample (a) wide scan showing the presence of Cu (b) Ti 2p and (c) Cu 2p (d) O 1s spectra along with deconvolution.

530.01 eV) and the hydroxyl group (OH, 531.58 eV) respectively as shown in Fig. 11(d).

In the present study, we have attempted to investigate the influence of TM ion site vacancies and oxygen vacancies on the magnetic behavior of the TiO₂ material due to the incorporation of non-magnetic elements in TiO₂. The origin of RTFM observed for the undoped sample (inset of Fig. 8(b)) has been mainly attributed to the particle size effect, defect concentration and Ti oxidation states. It has been observed that the reduction of particle size has a strong influence on the magnetic properties of nanostructured TiO₂ material. The observed results suggest that the nanocrystalline material form in such a way that larger particles would be preferentially doped over the smaller particles. As the grain size further decreases, the surface area to volume ratio increases and the contribution from the grain boundary defects increases. Thus the inside of the nanocrystalline compound has magnetic properties same as that of the bulk counterpart while the amorphous outer layer is magnetically disordered due to more crystallographic defects and oxygen vacancies. Thus, due to the high disordered state of the outer region, the net magnetic moment of this amorphous region is zero, which in turn reduces the magnetization of the nanocrystalline compound compared to that of bulk counterpart. There is a strong exchange coupling taking place between the inner region and outer region of the nanocrystalline

compound. The magnetically disordered state in the outer layer has a surface anisotropy contribution towards the effective anisotropy of the nanocrystalline compound. The effect of the surface anisotropy increases with a decrease in crystallite size. Thus the broken symmetry due to the grain surface effects has a strong influence on the magnetic properties of nanocrystalline materials. The variation of magnetic moment and coercivity with particle size has been plotted and is shown in Fig. S3.[†] One of the theoretical report suggest that a weak FM component in Ti can exist as a result of oxygen vacancy even without the presence of any secondary phases or magnetic impurities present at the Ti site.77 Even though there is a weak FM behavior, a considerable magnetic moment may not be observed with the generation of oxygen vacancy interaction with the trapped electrons in TiO2 material.78 Depending on the magnetic interactions present between the Ti³⁺/Ti⁴⁺ ions and Ti³⁺ interaction with oxygen site vacancies, magnetic interactions such as diamagnetism, AFM, ferrimagnetism or FM could be liable to occur in undoped TiO₂ system. The charge redistribution associated with the oxygen vacancies can decide the magnetic properties of TiO2 material, which is reflected in the controversial results obtained in different TiO2 based systems.77,78 Oxygen vacancy is associated with the formation of F-centres and the interaction of these leads to the change in magnetic behavior of the material due to the trapping of



Fig. 11 XPS spectra of T-Zn sample (a) wide scan showing the presence of Zn (b) Ti 2p and (c) Zn 2p and (d) O 1s spectra along with the deconvolution.

electrons and charge redistribution occurring on the surface of TiO₂. When such an electron trapping occurs on the surface of TiO₂, it results in the formation of an F-centre and an electron interacting with the F-centre could play with the nearby localized Ti⁴⁺ and subsequently, conversion of Ti⁴⁺ ions to Ti³⁺ ions occurs, leading to the formation of an F⁺-centre.¹⁴ The formation of Ti³⁺ is confirmed from the XPS analysis and F⁺ defect centers are observed from the PL analysis as discussed in the previous section. Bound magnetic polarons (BMPs) may be generated as a result of localization of electrons in the F⁺-centre and could develop magnetism by ordering the electron spin associated with Ti³⁺ (3d¹) located around oxygen vacancies. In the case of undoped TiO₂ sample, s-d exchange interaction associated with the 1s¹ electron spin of the F⁺-centre and the 3d¹ electron spin originating from Ti³⁺ ions could easily favor a long-range FM ordering which is reflected in the magnetic measurements. Another possible way to get the FM behavior in undoped sample is the O 2p orbitals that arise from Ti site vacancy rather than the Ti 3d orbitals and oxygen vacancies. Hence, the intensity of d0 magnetism in the undoped TiO₂ nanostructures is determined by the population of Ti site vacancy at surface and or edge regions. To control the RTFM in undoped TiO₂ nanostructures, in general, factors towards surface defect state and defect density is to be manipulated. From these observations, the best strategy to promote RTFM in undoped TiO₂ for spintronics related applications is to stabilize enough Ti vacancies near the surface in TiO2 nanostructures by

maintaining the crystalline quality of the material. Hence, a combined effect among the surface defects, Ti site vacancy and oxygen vacancy is ultimately leading to the electrons trapped at the defect sites leading to the BMP formation and ultimately deciding the magnetic behavior of undoped TiO₂ nanostructures. The interaction will be much stronger if the dopant ion contributes some 3d electrons which is exactly happening between the F⁺-centre and Cu²⁺ ions to generate more number of BMPs, hence along with the s-d interaction mentioned above, another interaction in Cu-doped TiO2 could arise among the F⁺-centers and 3d⁹ electron spin of Cu²⁺ ions leading to FM ordering and enhanced magnetic moment. Previous reports suggest the formation of a $1s^2$ state with the doubly occupied F-centers, which leads to a weak AFM interaction.79 It is clear from these discussions that the ability of a system to generate more number of BMPs either due to Ti³⁺ or Cu^{2+} ions with the F⁺-centre or both together, where an orbital overlapping with the unpaired 3d¹ electron of Ti³⁺ ions or the unpaired 3d9 electron of Cu2+ ions is responsible for the observed RTFM which has happened in the present case, i.e., in T-Cu sample. Here, the concept of mixed valence ions also holds good along with the concept of surface defects and hence the possible role of charge transfer FM can also be used to explain the RTFM.^{80,81} The room temperature *M*-*H* loop at lower fields show a weak FM behavior in T-Zn, which further corroborates the PL results and the formation of defect centers and surface free electrons inherently present in the TiO₂ system is crucial in

determining the magnetic behavior in the T-Zn sample. Rather than the oxygen vacancies, O 2p orbitals resulting from Ti/Zn site vacancy could be favorable for the magnetic response of T-Zn at lower fields. However, the diamagnetic tail observed at higher fields indicates the presence of Ti⁴⁺ and Zn²⁺ in T-Zn sample which is in agreement with the XPS results. BMP fitting on undoped and Cu, Zn doped samples was carried out to investigate the impact of oxygen vacancy and non-magnetic ion concentrations. The fitting has been carried out on the recorded *M versus H* data to the BMP model as explained in the previous report.^{82,83} According to this model, the measured magnetization can be fitted using the following relation;

$$M = M_0 L(x) + \chi_{\rm m} H. \tag{1}$$

In the above mentioned equation, the first term accounts for BMP contribution and the second term is associated with the PM matrix contribution. The value of M_0 can be represented as the product of N and m_s , where N is the number of BMPs involved (per cm³) and m_s is the effective spontaneous magnetic moment per BMP. The Langevin function, L(x) is defined as L(x)= $\operatorname{coth}(x) - 1/x$ where $x = m_{\text{eff}}H/k_{\beta}T$. The term m_{eff} is the true spontaneous magnetic moment per BMP and it can be approximated to m_s . The parameters M_0 , m_{eff} and χ_m are the variables in the fitting process. The experimental and fitted data to estimate the BMP concentration for both undoped and Cu, Zn doped samples are represented in Fig. 12(a), (b) and (c) respectively and it can be observed that the fitted data are very well in accordance with the experimental data. The obtained parameters are represented in Fig. 12(d) from which the BMP concentration is found to be highest in T-Cu sample due to which the magnetic moment is more in comparison to T-P or T-Zn which is corroborated with the size *versus* moment plot shown in Fig. S3.[†]

In order to have a clear understanding regarding the spin interactions in these samples, a schematic representation is developed based on the results of XPS analysis which is depicted in Fig. 13. As per the earlier discussions, the presence of Ti^{3+} is suggested in undoped T-P sample along with Ti4+. The ratio of Ti³⁺ to Ti⁴⁺ is considerably small as shown in Fig. 9(b). Still, this small fraction of Ti³⁺ could have unpaired electrons in the 3d state as shown in Fig. 13 and it can interact with the oxygen vacancy centers associated with the T-P sample as discussed previously. In the case of T-Cu, Cu²⁺ can be considered to be magnetic with one free electron and defect centers on the surface of TiO₂ system locally traps the electrons, ultimately leading to the formation of an F-centre where one of the electrons associated with the F-centre will have a tendency to interact with the adjacent localized Ti⁴⁺ and convert Ti⁴⁺ ions to Ti³⁺ ions, resulting in the formation of an F⁺-centre. This mechanism can be well corroborated with the magnetic measurements also. But in the case of Zn-doped samples, Zn^{2+} is the most stable oxidation state which is diamagnetic in nature and the formation of both Ti³⁺ and F⁺-centre will be hindered here ultimately leading to the



Fig. 12 BMP fitting employed to estimate the concentration of magnetic polarons of (a) T-P and (b) T-Cu (c) T-Zn and (d) parameters obtained from langevin-fit for T-P, T-Cu and T-Zn.



Fig. 13 Schematic showing the spin state interactions of valence shell electrons in T-P, T-Cu and T-Zn.



Fig. 14 Schematic showing the BMP interactions in (a) T-P, (b) T-Cu and (c) absence of BMP formation in T-Zn

diamagnetic tail like behavior of the sample. The formation of Fcenters and F⁺-centers will be facilitated due to the trapped electrons in these defect sites. The F⁺-center formation ultimately leads to the formation of BMPs, which favors the FM interaction. The room temperature *M*–*H* loop at lower fields shows a weak RTFM which further corroborates the PL results and the formation of defect centers and 3d¹ interaction of Ti^{3+}/Cu^{2+} plays a crucial role in generating the magnetic response in the undoped and Cu-doped sample.

A similar behavior is observed for T-Zn also especially at lower magnetic fields, whereas at higher fields, *i.e.*, above 10 000 Oe, the magnetic contribution from Ti^{4+} and Zn^{2+} magnetic contribution is dominated and ultimately diamagnetic tails are observed and hence the ratio of Ti^{3+}/Ti^{4+} is crucial in determining the magnetic behavior in both undoped and doped samples. The previous discussions suggest the absence of expected perfect diamagnetism in T-Zn due to the defects associated with the system and the XPS results illustrate the presence of Ti^{4+} and Zn^{2+} in the T-Zn system, where there is no unpaired electrons at all to contribute towards a long range FM as shown in Fig. 13 and 14.

Conclusion

Structural, optical and magnetic properties of sol-gel derived undoped, Cu and Zn doped TiO2 nanocrystals have been investigated. X-ray diffraction and Raman spectroscopy confirm the formation of anatase TiO₂ phase and detailed morphological and structural analysis using high resolution transmission electron microscopy reveals the nanocrystal formation for both undoped and (Cu, Zn) doped TiO2. The UV absorption spectra illustrates a red shift in the absorption edge for the doped samples indicating the successful incorporation of doped ions into the TiO₂ lattice. Cu doped TiO₂ shows a large shift in the absorption edge giving rise a significant reduction in bandgap which favors the visible light photoactivity. The electronic transitions from conduction band to valence band, radiative recombination of self-trapped excitons and the information regarding the defect centers are explained using PL spectra. The undoped and Cu doped samples show a positive slope of magnetization up to a field of 9 tesla and the magnetic moment is more prominently enhanced in Cu-doped TiO₂ than undoped TiO₂. A significant reduction in bandgap along with enhanced

magnetization makes Cu-doped TiO_2 a suitable candidate material for future spintronic and magneto-optic applications. A diamagnetic tail is observed for Zn-doped TiO_2 in the magnetic field ranging from 1 tesla to 9 tesla and a perfect diamagnetism is not observed in Zn doped TiO_2 due to the defect centers which is well explained using the BMP model and detailed XPS analysis.

Conflicts of interest

There are no conflicts of interest to declare.

Acknowledgements

The authors would like to acknowledge the financial support received from Council of Scientific and Industrial Research (CSIR), Govt. of India. V. R. Akshay and B. Arun are thankful to Council of Scientific and Industrial Research (CSIR), Government of India for granting the Senior Research Fellowship and also thankful to Academy of Scientific and Innovative Research (AcSIR), CSIR. The authors would also like to thank Department of Science and Technology, sponsored project GAP 232339 for partially supporting this work.

References

- 1 B. Santara, B. Pal and P. K. Giri, J. Appl. Phys., 2011, 110, 114322.
- 2 J. Schneider, M. Matsuoka, M. Takeuchi, J. Zhang, Y. Horiuchi, M. Anpo and D. W. Bahnemann, *Chem. Rev.*, 2014, **114**(19), 9919–9986.
- 3 J. Wei, Adv. Mater. Res., 2013, 750-752, 301-306.
- 4 Y. Tang, C. Lee, J. Xu, Z. Liu, Z. Chen, Z. He, Y. Cao, G. Yuan, H. Song, L. Chen, L. Luo, H. Cheng, W. Zhang, I. Bello and S. Lee, *ACS Nano*, 2010, 4(6), 3482–3488.
- 5 I. Gur, N. A. Fromer, M. L. Geier and A. P. Alivisatos, *Science*, 2005, **310**, 462–465.
- 6 Y. Cong, J. Zhang, F. Chen, M. Anpo and D. He, *J. Phys. Chem. C*, 2007, **111**, 10618–10623.
- 7 Z. Y. Zhao, Z. S. Li and Z. G. Zou, *ChemPhysChem*, 2012, 13, 3836.
- 8 X. H. Yu, T. J. Hou, X. H. Sun and Y. Y. Li, *ChemPhysChem*, 2012, **13**, 1514.
- 9 H. M. Weng, X. P. Yang, J. M. Dong, H. Mizuseki, M. Kawasaki and Y. Kawazoe, *Phys. Rev. B*, 2004, **69**, 125219.
- 10 X. S. Du, Q. X. Li, H. B. Su and J. L. Yang, *Phys. Rev. B*, 2006, 74, 233201.
- 11 L. H. Gan, C. C. Wu, Y. Tan, B. Chi, J. Pu and L. Jian, *J. Alloys Compd.*, 2014, 585, 729.
- 12 Y. Li, Y. Yue, Z.-Q. Que, M. Zhang and M. Guo, *Int. J. Miner.*, *Metall. Mater.*, 2013, **20**, 1012.
- 13 M. Pal, U. Pal, J. M. Gracia, Y. Jiménez and F. PérezRodriguez, *Nanoscale Res. Lett.*, 2012, 7, 1–12.
- 14 B. Santara, P. K. Giri, K. Imakita and M. Fujii, *Nanoscale*, 2013, 5, 5476–5488.
- 15 H.-Y. Lee, S. J. Clark and J. Robertson, *Phys. Rev. B*, 2012, **86**, 075209.

- 16 S. Na-Phattalung, M. F. Smith, K. Kim, M.-H. Du, S.-H. Wei, S. B. Zhang and S. Limpijumnong, *Phys. Rev. B*, 2006, 73, 125205.
- 17 B. Santara, P. K. Giri, K. Imakita and M. Fujii, *J. Phys. Chem. C*, 2013, **117**, 23402–23411.
- 18 D. J. Norris, A. L. Efros and S. C. Erwin, *Science*, 2008, 319, 1776–1779.
- 19 Y. C. Cao, Science, 2011, 332, 48-49.
- 20 R. A. Abram, G. J. Rees and B. L. H. Wilson, *Adv. Phys.*, 1978, 27, 799–892.
- 21 S. A. Wolf, D. D. Awschalom, R. A. Buhrman, J. M. Daughton, S. Von Molnar, M. L. Roukes, A. Y. Chtchelkanova and D. M. Treger, *Science*, 2001, **294**, 1488.
- 22 H. Ohno, Science, 1998, 281, 951.
- 23 Y. Matsumoto, M. Murakami, T. Shono, T. Hasegawa,T. Fukumra, M. Kawasaki, P. Ahmet, T. Chikyow,S. Koshihara and H. Koinuma, *Science*, 2001, 291, 854.
- 24 A. Chanda, K. Rout, M. Vasundhara, S. R. Joshi and J. Singh, *RSC Adv.*, 2018, **8**, 10939–10947.
- 25 T. Dietl, H. Ohno, F. Matsukura, J. Cibert and D. Ferrand, *Science*, 2000, 287, 1019.
- 26 A. Chanda, S. Gupta, M. Vasundhara, S. R. Joshi, G. R. Mutta and J. Singh, *RSC Adv.*, 2017, 7, 50527–50536.
- 27 M. Parras, A. Varela, R. C. Gil, K. Boulahya, A. Hernando and J. M. G. Calbet, *J. Phys. Chem. Lett.*, 2013, 4, 2171.
- 28 J. Y. Zheng, S. H. Bao, Y. H. Lv and P. Jin, ACS Appl. Mater. Interfaces, 2014, 6, 22243.
- 29 S. Wang, L. Pan, J. J. Wang, W. Mi, J. J. Zou, L. Wang and X. Zhang, *J. Am. Chem. Soc.*, 2015, 137, 2975.
- 30 K. Karthik, S. Kesava Pandian, K. Suresh Kumar and N. Victor Jaya, *Appl. Surf. Sci.*, 2010, **256**, 4757.
- 31 N. H. Hong, J. Sakai, N. Poirot and V. Brize, *Phys. Rev. B*, 2006, **73**, 132404.
- 32 S. D. Yoon, Y. Chen, A. Yang, T. L. Goodrich, X. Zuo, D. A. Arena, K. Zeimer, C. Vittoria and V. G. Harris, *J. Phys.: Condens. Matter*, 2006, 18, L355.
- 33 D. Kim, J. Hong, Y. R. Park and K. J. Kim, J. Phys.: Condens. Matter, 2009, 21, 195405.
- 34 J.-Y. Kim, J.-H. Park, B.-G. Park, H.-J. Noh, S.-J. Oh, J. S. Yang, D.-H. Kim, S. D. Bu, T. W. Noh, H.-J. Lin, H.-H. Hsieh and C. T. Chen, *Phys. Rev. Lett.*, 2003, **90**, 017401.
- 35 J. Xu, S. Shi, L. Li, X. Zhang, Y. Wang, X. Chen, J. Wang, L. Lv,
 F. Zhang and W. Zhong, *J. Appl. Phys.*, 2010, **107**, 053910.
- 36 N. H. Hong, J. Sakai, N. Poirot and V. Brize, *Phys. Rev. B*, 2006, **73**, 132404.
- 37 M. Venkatesan, C. B. Fitzgerald and J. M. D. Coey, *Nature*, 2004, **430**, 630.
- 38 B. Prajapati, S. Kumar, M. Kumar, S. Chatterjee and A. K. Ghosh, J. Mater. Chem. C, 2017, 5, 4257–4267.
- 39 B. Parveen, M. ul-Hassan, Z. Khalid, S. Riaz and S. Naseem, *J. Appl. Res. Technol.*, 2017, **15**, 132–139.
- 40 B. Choudhury, S. Paul, G. A. Ahmed and A. Choudhury, *Mater. Res. Express*, 2015, **2**, 096104.
- 41 B. Choudhury and A. Choudhury, *Curr. Appl. Phys.*, 2013, **13**, 1025–1031.
- 42 B. Choudhury, M. Dey and A. Choudhury, *Int. Nano Lett.*, 2013, 3, 25.

- 43 S. A. Ahmed, J. Magn. Magn. Mater., 2017, 442, 152-157.
- 44 J. Yu, T. Ma and S. Liu, *Phys. Chem. Chem. Phys.*, 2011, 13, 3491.
- 45 Q.-H. Zhang, W.-D. Han, Y.-J. Hong and J.-G. Yu, *Catal. Today*, 2009, **148**, 335.
- 46 T. Ohsaka, F. Izumi and Y. Fujiki, *J. Raman Spectrosc.*, 1978, 7, 321–324.
- 47 D. Berdani, P. P. Lottice and A. Montenero, *J. Mater. Sci.*, 2000, **35**, 4301–4305.
- 48 H. A. Szymanski, *Raman Spectroscopy: Theory and Practice*, Plenum press, New York, 1967.
- 49 W. F. Zhang, Y. L. He, M. S. Zhang, Z. Yin and Q. Chen, *J. Phys. D: Appl. Phys.*, 2000, 33, 912.
- 50 H. C. Choi, Y. M. Jung and S. B. Kim, *Vib. Spectrosc.*, 2005, 37, 33–38.
- 51 L. H. Liang, C. M. Shen, X. P. Chen, W. M. Liu and H. J. Gao, *J. Phys.: Condens. Matter*, 2004, **16**, 267.
- 52 A. Ali, E. Yassitepe, I. Ruzybayev, S. I. Shah and A. S. Bhatti, *J. Appl. Phys.*, 2012, **112**, 113505.
- 53 A. Punnoose, J. Hays, V. ShutthanandanV and V. Gopal, *Appl. Phys. Lett.*, 2004, **85**, 155.
- 54 M. Ahamed, M. A. M. Khan, M. J. Akhtar, H. A. Alhadlaq and A. Alshamsan, *Sci. Rep.*, 2016, 6, 30196.
- 55 M. Cernea, C. Valsangiacom, R. Trusca and F. Vasiliu, J. Optoelectron. Adv. Mater., 2007, 9, 2648–2652.
- 56 Z. Li, B. Hou, Y. Xu, D. Wu and Y. Sun, J. Colloid Interface Sci., 2005, 288, 149–154.
- 57 A. Bouaine, N. Brihi, G. Schmerber, C. Ulhaq-Bouillet, S. Colis and A. Dinia, *J. Phys. Chem. C*, 2007, **111**(7), 2924– 2928.
- 58 K. Nagaveni, M. S. Hegde and G. Madras, J. Phys. Chem. B, 2004, **108**, 20204–20212.
- 59 K. Das, S. N. Sharma, K. Mahesh and S. K. De, *J. Phys. Chem. C*, 2009, **113**, 14783–14792.
- 60 W. Y. Wu, Y. M. Chang and J. M. Ting, *Cryst. Growth Des.*, 2010, **10**, 1646.
- 61 R. Sanjines, H. Tang, H. Berger, F. Gozzo, G. Margaritondo and F. Lévy, *J. Appl. Phys.*, 1994, 75, 2945.
- 62 J. Liu, J. Li, A. Sedhain, J. Lin and H. Jiang, J. Phys. Chem. C, 2008, 112, 17127–17132.

- 63 Y. Lei, L. Zhang, G. Meng, G. Li, X. Zhang, C. Liang, W. Chen and S. Wang, *Appl. Phys. Lett.*, 2001, **78**, 1125–1127.
- 64 N. Serpone, J. Phys. Chem. B, 2006, 110, 24287-24293.
- 65 L.-T. Tseng, X. Luo, T. T. Tan, S. Li and J. Yi, *Nanoscale Res. Lett.*, 2014, **9**, 673.
- 66 B. Qi, S. Ólafsson and H. P. Gíslason, *Prog. Mater. Sci.*, 2017, 90, 45–74.
- 67 J. M. D. Coey, Solid State Sci., 2005, 7, 660-667.
- 68 L. A. Errico, M. Rentería and M. Weissmann, *Phys. Rev. B:* Condens. Matter Mater. Phys., 2005, 72(1-8), 184425.
- 69 http://srdata.nist.gov/xps.
- 70 J. C. Huo, Nanoscale, 2014, 6, 9078-9084.
- 71 H. Jensena, A. Solovieva, Z. S. Li and E. G. Sogaard, *Appl. Surf. Sci.*, 2005, 246, 239–249.
- 72 M. Xing and B. Tian, Chem. Commun., 2011, 47, 4947-4949.
- 73 I. Nakai, Y. Sugitani, K. Nagashima and Y. Niwa, J. Inorg. Nucl. Chem., 1978, 40(5), 789–791.
- 74 B. R. Strohmeier, D. E. Levden, R. ScottField and D. M. Hercules, J. Catal., 1985, 94(2), 514–530.
- 75 B. Sudakshina, B. Arun, K. Devi Chandrasekhar, H. D. Yang and M. Vasundhara, *Phys. B*, 2018, 539(15), 14–20.
- 76 Z. Wang, C. Yang, T. Lin, H. Yin, P. Chen, D. Wan, F. Xu,
 F. Huang, J. Lin, X. Xie and M. Jiang, *Adv. Funct. Mater.*, 2013, 23, 5444–5450.
- 77 D. Kim, J. Hong, Y. R. Park and K. J. Kim, J. Phys.: Condens. Matter, 2009, 21, 195405.
- 78 S. K. Pandey and R. J. Choudhary, J. Phys.: Condens. Matter, 2011, 23, 276005.
- 79 J. M. D. Coey, M. Venkatesan and C. B. Fitzgerald, *Nat. Mater.*, 2005, 4, 173–179.
- 80 D. Y. Inamdar, A. D. Lad, A. K. Pathak, I. Dubenko, N. Ali and S. Mahamuni, *J. Phys. Chem. C*, 2010, **114**, 1451–1459.
- 81 J. J. Beltrán, C. A. Barrero and A. Punnoose, J. Phys. Chem. C, 2016, 129(16), 8969–8978.
- 82 C. Chiorescu, J. L. Cohin and J. J. Neumeier, *Phys. Rev. B*, 2007, **76**, 020404(R).
- 83 G. Madhu, K. Maniammal and V. Biju, *Phys. Chem. Chem. Phys.*, 2016, 18, 12135–12148.