Chemical Science

EDGE ARTICLE

Check for updates

Cite this: Chem. Sci., 2018, 9, 2147

Received 21st November 2017 Accepted 5th January 2018

DOI: 10.1039/c7sc04997h

rsc.li/chemical-science

Impact of ambient gases on the mechanism of [Cs₈Nb₆O₁₉]-promoted nerve-agent decomposition[†]‡

Alexey L. Kaledin,^a Darren M. Driscoll, ^b Diego Troya,^b Daniel L. Collins-Wildman,^c Craig L. Hill, ^b *^c John R. Morris*^b and Djamaladdin G. Musaev *^{ab}

The impact of ambient gas molecules (X), NO₂, CO₂ and SO₂ on the structure, stability and decontamination activity of Cs₈Nb₆O₁₉ polyoxometalate was studied computationally and experimentally. It was found that Cs₈Nb₆O₁₉ absorbs these molecules more strongly than it adsorbs water and Sarin (GB) and that these interactions hinder nerve agent decontamination. The impacts of diamagnetic CO2 and SO2 molecules on polyoxoniobate Cs₈Nb₆O₁₉ were fundamentally different from that of NO₂ radical. At ambient temperatures, weak coordination of the first NO_2 radical to $Cs_8Nb_6O_{19}$ conferred partial radical character on the polyoxoniobate and promoted stronger coordination of the second NO₂ adsorbent to form a stable diamagnetic $Cs_8Nb_6O_{19}/(NO_2)_2$ species. Moreover, at low temperatures, NO_2 radicals formed stable dinitrogen tetraoxide (N_2O_4) that weakly interacted with $Cs_8Nb_6O_{19}$. It was found that both in the absence and presence of ambient gas molecules, GB decontamination by the Cs₈Nb₆O₁₉ species proceeds via general base hydrolysis involving: (a) the adsorption of water and the nerve agent on $Cs_8Nb_6O_{19}/(X)$, (b) concerted hydrolysis of a water molecule on a basic oxygen atom of the polyoxoniobate and nucleophilic addition of the nascent OH group to the phosphorus center of Sarin, and (c) rapid reorganization of the formed pentacoordinated-phosphorus intermediate, followed by dissociation of either HF or isopropanol and formation of POM-bound isopropyl methyl phosphonic acid (i-MPA) or methyl phosphonofluoridic acid (MPFA), respectively. The presence of the ambient gas molecules increases the energy of the intermediate stationary points relative to the asymptote of the reactants and slightly increases the hydrolysis barrier. These changes closely correlate with the Cs₈Nb₆O₁₉-X complexation energy. The most energetically stable intermediates of the GB hydrolysis and decontamination reaction were found to be Cs₈Nb₆O₁₉/X-MPFA-(i-POH) and Cs₈Nb₆O₁₉/X-(i-MPA)-HF both in the absence and presence of ambient gas molecules. The high stability of these intermediates is due to, in part, the strong hydrogen bonding between the adsorbates and the protonated [Cs₈Nb₆O₁₉/ X/H]⁺-core. Desorption of HF or/and (i-POH) and regeneration of the catalyst required deprotonation of the [Cs₈Nb₆O₁₉/X/H]⁺-core and protonation of the phosphonic acids i-MPA and MPFA. This catalyst regeneration is shown to be a highly endothermic process, which is the rate-limiting step of the GB hydrolysis and decontamination reaction both in the absence and presence of ambient gas molecules.

°C. L. Emerson Center for Scientific Computation and Department of Chemistry, Emory University, Atlanta, Georgia, 30322, USA. E-mail: dmusaev@emory.edu

^bDepartment of Chemistry, Virginia Tech, Blacksburg, Virginia, 24061, USA. E-mail: imorris@vt.edu

Department of Chemistry, Emory University, Atlanta, Georgia, 30322, USA. E-mail: chill@emory.edu

† Dedicated to the memory of Prof. Keiji Morokuma.

[‡] Electronic supplementary information (ESI) available: (1) The calculated transition states, intermediates and products of the GB hydrolysis and their important geometry parameters (in Å) for X = SO₂, (2) the calculated adsorption energies (in kcal mol⁻¹) of NO₂ radicals to Cs₈Nb₆O₁₉, (3) Cartesian coordinates for all reported structures in xyz format. (structure.xyz). See DOI: 10.1039/c7sc04997h

Introduction

The design of materials that can rapidly, fully, and catalytically decontaminate chemical warfare agents (CWAs) and other toxic compounds is an increasingly active area of research and one that presents some questions in fundamental chemistry.¹⁻⁵ As suggested by enzymatic chemistry, some of the most effective strategies for CWA destruction involve catalyzed hydrolysis reactions.⁴ Specifically, it is well established that the P–X bonds (X = F, CN, SR, *etc.*) of organophosphorus (OP) nerve agents rapidly inactivate acetylcholinesterase (a serine hydrolase), the enzyme that facilitates hydrolysis of the neurotransmitter acetylcholine in the nervous system. This inactivation occurs through rapid nucleophilic addition and irreversible binding of



View Article Online

View Journal | View Issue

Chemical Science

the serine OH to the phosphorus atom of the nerve agent. Thus, an atomistic/molecular level understanding of the hydrolysis of OP compounds by nucleophilic addition and other processes may lead to the development of more effective materials and catalysts for nerve agent decontamination. Ongoing research efforts have identified several organic and inorganic materials, including metal–organic frameworks (MOFs, especially UiO-66, NU-1000 and MOF-808),^{5–10} polyoxometalates (POMs),^{11–14} MOF/POM hybrid materials,^{15,16} zirconium hydroxide,¹⁷ zeolites,¹⁸ and organic polymers,¹⁹ as effective OP hydrolysis materials.

Recently, the use of POMs to catalyze nerve agent decontamination has attracted wide attention, in part because POMs are molecular representations of metal oxides and are thus far more amenable than the latter to extensive synthetic compositional alteration and characterization at the molecular level.^{20,21} Polyoxoniobates (PONbs), including $[Nb_6O_{19}]^{8-}$, are effective OP nerve agent hydrolysis compounds because their high negative charge densities (negative charge per polyanion oxygen) render them highly basic and nucleophilic. Thus, it is not surprising that the synthesis and in-depth analysis of the structures and reactivities of various (alkali and organic) salts of PONbs continue to be the focus of extensive studies.^{22,23} These studies show that the structures and, consequently, the catalytic activities of these materials for nerve agent decontamination depend on many factors, including (but not limited to) the nature of the counter-cation, the pH of the solution, the aggregate state (powder or solid-state material) of the catalyst, the real-time environmental conditions, and the nature and concentration of ambient gas molecules.

Earlier research on Lindqvist hexaniobate alkali salts $(M_8Nb_6O_{19}, M = Li, K, Cs)$ reported rapid hydrolysis of the OP agent Sarin (GB, propan-2-yl methylphosphonofluoridate, see Scheme 1) both in aqueous solution and at the gas–surface interface.¹¹ Small-angle X-ray scattering (SAXS) measurements showed aggregation of the OP compounds on the polyoxoniobate (PONb), which led to the suggestion that the reaction follows a general base hydrolysis mechanism.¹² Our subsequent computational study on the mechanism of decomposition of GB by a Cs-salt of PONb, Cs₈Nb₆O₁₉ (or CsPONb), confirmed the general base hydrolysis mechanism of this reaction at the gas–surface interface.²⁴



Scheme 1 Schematics of: (a) the mechanism of Sarin (GB) hydrolysis (reported in ref. 24) promoted by the $Cs_8Nb_6O_{19}$ polyoxoniobate and (b) the $Cs_8Nb_6O_{19}$ polyoxoniobate.

Briefly, we have found that GB degradation by $Cs_8Nb_6O_{19}$ includes the following elementary steps (see Scheme 1): (a) the adsorption of water and the nerve agent on the Cs₈Nb₆O₁₉ species, (b) concerted dissociation of the adsorbed water molecule on a basic oxygen atom of the polyoxoniobate and nucleophilic addition of the nascent OH group to the phosphorus center of the nerve agent, (c) rapid reorganization of the resulting pentacoordinated phosphorus intermediate by dissociation of either HF or isopropanol, and formation of POMbound isopropyl methyl phosphonic acid (i-MPA) or methyl phosphonofluoridic acid (MPFA), respectively. The calculations showed that the phosphonic acids i-MPA and MPFA are strongly bound to the protonated $[Cs_8Nb_6O_{19}H]^+$ -core through hydrogen bonds and electrostatic interactions with the Cs counter-ions, suggesting that full catalyst regeneration may require additional treatment and depends on the nature of the countercations as well as the real-time (ambient) experimental conditions.

Although PONb catalysts have been shown to react with CWAs, the chemistry has yet to be characterized in the presence of ambient gases (for example, NO₂, CO₂ and SO₂), which may affect the stabilities, structural motifs, and activities of the PONb catalysts. Because this issue is vital to the application of PONbs as decontamination catalysts in real conditions, this paper probes the impact of the common battlefield contamination activity of the exemplary PONb species $Cs_8Nb_6O_{19}$. This study addresses in depth the effects of these ambient gases on the structures of the catalysts and the base hydrolysis mechanism for Sarin degradation using density functional theory (DFT) calculations and infrared (IR) spectroscopy.

Results and discussion

A. Structure of $Cs_8Nb_6O_{19}$ in the presence of gaseous CO_2 , NO_2 and SO_2

Here, we divide our discussion into two subsections. First, we discuss the interaction of diamagnetic CO_2 and SO_2 molecules with $Cs_8Nb_6O_{19}$; then, we present our findings on the interactions between NO_2 radical and $Cs_8Nb_6O_{19}$.

A1. Structure of $Cs_8Nb_6O_{19}$ in the presence of gaseous CO_2 and SO_2 . Our calculations reveal that $Cs_8Nb_6O_{19}$ very strongly binds the ambient gas molecules CO_2 and SO_2 at various (terminal O^t and/or bridging O^µ) sites to form $Cs_8Nb_6O_{19}/X$ adducts. As reported in Table 1, where we present the calculated adsorption energies, there is a clear preference of adsorption of both CO_2 and SO_2 at the terminal oxygen site rather than at the bridging oxygen site. Indeed, the calculated enthalpies and free energies of adsorption (presented as $\Delta H/\Delta G$) of $Cs_8Nb_6O_{19} + X \rightarrow Cs_8Nb_6O_{19}/X$ upon coordination of X to the O^t and O^µ sites are -29.0/-23.2 and -16.7/-10.8 kcal mol⁻¹ for $X = CO_2$ and -47.6/-40.3 and -34.1/-26.6 kcal mol⁻¹ for $X = SO_2$, respectively.

The factors that impact the strength of the $Cs_8Nb_6O_{19}/X$ bonding and site-preference of absorption were analyzed by investigating the resulting geometries of these complexes. From Fig. 1, where we present the most important geometries of the

Table 1 Adsorption energies (total electronic *E*, enthalpy *H* and Gibbs free energy *G* in kcal mol⁻¹) defined as energy differences of the complex $Cs_8Nb_6O_{19}/X$ and its two separated fragments, $Cs_8Nb_6O_{19} + X$, where $X = CO_2$, NO_2 and SO_2 , as shown in the leftmost column. The superscripts "t" and " μ " indicate the position where the molecule is adsorbed on $Cs_8Nb_6O_{19}$; Cs^N indicates NO_2 adsorption to two Cs counter-cations in a symmetric manner

	ΔE	ΔH	ΔG
$O^{t}: Cs_{8}Nb_{6}O_{19} + CO_{2}$	-29.1	-29.0	-23.2
$O^{\mu}: Cs_8Nb_6O_{19} + CO_2$	-16.8	-16.7	-10.8
$O^{t}: Cs_8Nb_6O_{19} + SO_2$	-48.2	-47.6	-40.3
$O^{\mu}: Cs_8Nb_6O_{19} + SO_2$	-34.7	-34.1	-26.6
Cs^{N} : $Cs_{8}Nb_{6}O_{19} + NO_{2}$	-21.7	-22.2	-22.1
$O^{t}: Cs_8Nb_6O_{19} + NO_2$	-18.8	-18.7	-13.9
Cs^{N} and O^{t} : $Cs_{8}Nb_{6}O_{19} + 2NO_{2}$	-77.4	-74.6	-58.0
$Cs_8Nb_6O_{19}/CO_2(O^t) + H_2O$	-24.2	-22.4	-11.9
$Cs_8Nb_6O_{19}/SO_2(O^t) + H_2O$	-22.7	-21.0	-9.7
$Cs_8Nb_6O_{19} + H_2O$	-24.6	-23.6	-17.3
$Cs_8Nb_6O_{19}/H_2O + GB$	-18.8	-17.4	-4.2
$Cs_8Nb_6O_{19}/H_2O/CO_2(O^t) + GB$	-18.0	-17.4	-2.4
$Cs_8Nb_6O_{19}/H_2O/SO_2(O^t) + GB$	-17.4	-16.4	-3.7

 $Cs_8Nb_6O_{19}/X(O^t)$ and $Cs_8Nb_6O_{19}/X(O^{\mu})$ isomeric species for $X = CO_2$ and SO_2 (for full geometries of these species, see the ESI[‡]), we make the following conclusions:

(a) The CO₂ molecule in Cs₈Nb₆O₁₉/CO₂(O^t) is bound to Cs₈Nb₆O₁₉ *via* multiple interactions, including two (C=O)_{CO₂}... Cs interactions and one C-O^t interaction. The long calculated bond distances for the Cs-O¹, Cs-O² and Cs-C interactions (3.23, 3.25 and 3.28 Å, respectively) indicate they are relatively weak. In contrast, the C-O^t interaction is stronger, with a bond distance of 1.39 Å. As a result of this strong interaction, the Nb-O^t distance is elongated from 1.80 Å to 2.02 Å (see Fig. 1). Thus, while the interactions with the Cs cations provide additional stability to the complex Cs₈Nb₆O₁₉/CO₂(O^t), the primary

 $\begin{array}{c} 3.23 \\ 3.28 \\ 5^{\circ} \\ 3.28 \\ 0^{\circ} \\ 3.28 \\ 0^{\circ} \\ 0^{$

S-O^µ = 1.79

 $S = 0^2 = 1.51$

 $O^1 = 1.51$

Fig. 1 Adsorption of the ambient gas molecules CO_2 and SO_2 on $Cs_8Nb_6O_{19}$ at the O^t sites (left) and bridging sites (right) with their important geometry parameters (in Å).

CsoPONb1/SO

 $-0^1 = 1.52$

 $O^2 = 1.52$

interaction occurs between the C atom of CO_2 and the terminal oxygen atom of $Cs_8Nb_6O_{19}$.

In the $Cs_8Nb_6O_{19}/CO_2(O^{\mu})$ isomer, where CO_2 interacts with a bridging oxygen, the C–O^{μ} bond distance is longer (calculated to be 1.44 Å) than the C–O^t bond distance in $Cs_8Nb_6O_{19}/CO_2(O^t)$, while the Cs–O¹ and Cs–O² interactions are slightly stronger (based on the calculated Cs–O¹ and Cs–O² distances). The above presented geometry parameters of $Cs_8Nb_6O_{19}/CO_2(O^t)$ and $Cs_8PONb/CO_2(O^{\mu})$ not only explain the calculated energy difference between these species, but are also consistent with the amounts of charge transfer from $Cs_8Nb_6O_{19}$ to CO_2 : in the $Cs_8Nb_6O_{19}/CO_2(O^t)$ and $Cs_8Nb_6O_{19}/CO_2(O^{\mu})$ complexes, almost 0.8 |e| and 0.4 |e| negative charge is transferred from $Cs_8Nb_6O_{19}$ to CO_2 , respectively. Furthermore, the putative CO_3 -group in $Cs_8Nb_6O_{19}/CO_2(O^t)$ has a total negative charge of 1.52 |e|.

The strong coordination of CO₂ to Cs₈Nb₆O₁₉ is also supported by IR spectroscopic studies, where the adsorption of CO₂ onto Cs₈Nb₆O₁₉ was investigated by recording the infrared spectra before, during, and after exposure of Cs₈Nb₆O₁₉ to a constant flux of CO₂. Upon adsorption of CO₂ on Cs₈Nb₆O₁₉, three prominent features appeared in the infrared spectrum (Fig. 2, i) at 1659 cm^{-1} , 1290 cm^{-1} and 1229 cm^{-1} . Interestingly, we observed no feature in the infrared spectrum around 2300 cm⁻¹, which would be associated with a linear CO₂ molecule bound to the POM surface. The 1229 cm⁻¹ and 1290 cm⁻¹ bands are consistent with the IR-inactive symmetric stretch from the gas-phase (ν_1 (C–O)), which becomes IR active upon binding to the POM. The 1659 cm^{-1} band is likely related to the antisymmetric v_3 (C–O) stretch of CO₂/CO₃ (occurs at 2349 cm⁻¹ in the gas-phase²⁵ and significantly redshifts upon adsorption). The presence of both the v_1 and v_3 bands in the infrared spectrum indicates a bent structure of the adsorbate at the surface. Upon evacuation of CO_2 from the chamber, the 1229 cm⁻¹ spectroscopic feature diminishes, indicating that this band corresponds to the vibrational motion of weakly bound CO₂ species on the surface (Fig. 2, ii); however, the two other features (1659 and 1290 cm^{-1}) persist until annealing the Cs₈Nb₆O₁₉ sample at 423 K (Fig. 2, iii). The elevated



Fig. 2 Infrared spectra recorded during and after the adsorption of CO₂ onto Cs₈Nb₆O₁₉ at 300 K. (i) Adsorption of 100 mTorr of CO₂. (ii) After CO₂ evacuation. (iii) After CO₂ evacuation and thermal treatment at 423 K.

O^t - site

temperature required to fully remove the CO_2 suggests that the molecules responsible for these infrared bands are strongly bound to $Cs_8Nb_6O_{19}$. The experimentally observed IR features are in full agreement with the DFT calculations (harmonic, unscaled). Indeed, the two prominent IR active features at 1290 and 1659 cm⁻¹, which are ascribed to the bending and asymmetric CO stretch motions of a bent CO_2 molecule, are calculated to be 1316 and 1317 cm⁻¹ (for the bend) and 1702 and 1719 cm⁻¹ (for the asymmetric stretch) in $Cs_8Nb_6O_{19}/CO_2(O^{\mu})$, respectively. Thus, the above presented experimental and computational analysis shows that a large fraction of the surface, the molecule adopts a bent geometry, which activates the ν_1 vibrational motion toward absorption of infrared radiation.

(b) The geometric features of $Cs_8Nb_6O_{19}/SO_2(O^t)$ and $Cs_8Nb_6O_{19}/SO_2(O^{\mu})$ adducts are similar to those of their CO_2 analogs: among the interactions, the strongest are the S–O^t and S–O^µ interactions, with 1.70 and 1.79 Å bond distances, respectively. These geometry parameters are consistent with the greater stability of the $Cs_8Nb_6O_{19}/SO_2(O^t)$ isomer. Furthermore, comparison of the calculated $Cs_8Nb_6O_{19}$ –X binding energies shows that SO_2 interacts with $Cs_8Nb_6O_{19}$ –X binding energies shows that SO_2 interacts with $Cs_8Nb_6O_{19}$ much more strongly, by nearly a factor of two, than CO_2 . However, both molecules clearly persist on the POM at ambient and well above ambient temperatures.

Further calculations showed that single $Cs_8Nb_6O_{19}$ species can bind several CO_2 and SO_2 molecules. As seen in Table 2, where we have summarized the adsorption energies as a function of the number of molecules adsorbed at the six O^t sites, there is a pronounced monotonic convergence of the electronic and enthalpy binding energies up to n = 6. The free energies, on the other hand, reveal thermodynamic instability for CO_2 adsorption at larger values of n, suggesting that only the $Cs_8Nb_6O_{19}/(CO_2)_n$ species with $n \le 4$ are viable. The $Cs_8Nb_6O_{19}/(SO_2)_n$ species may still be stable for n > 6.

A2. Structure of $Cs_8Nb_6O_{19}$ in the presence of NO_2 radicals. As one might expect, the interaction of $Cs_8Nb_6O_{19}$ with NO_2 radicals is conceptually different than those discussed above for the diamagnetic CO_2 and SO_2 molecules. Indeed, at first, in the

Table 2 Adsorption of n(X) (X = CO₂ and SO₂ and n = 1 to 6) on Cs₈Nb₆O₁₉ at its O^t-sites, reported as incremental $\Delta Z_{n,n-1}$ (Cs₈Nb₆O₁₉/X) = Z_n (Cs₈Nb₆O₁₉/X) – Z_{n-1} (Cs₈Nb₆O₁₉/X) – Z(X) energies (where Z = E, H or G) (in kcal mol⁻¹)

n	$X = CO_2$			$X = SO_2$		
	Z = E	Z = H	Z = G	Z = E	Z = H	Z = G
1	-29.1	-29.0	-23.2	-48.2	-47.6	-40.3
2	-22.9	-21.8	-11.2	-43.3	-42.4	-27.6
3	-19.6	-18.9	-9.6	-38.8	-37.1	-27.3
4	-13.3	-12.5	-0.7	-34.2	-32.9	-19.8
5	-7.3	-6.6	4.4	-26.9	-25.9	-14.9
6	-2.2	-2.0	6.9	-29.0	-27.9	-16.9

gas-phase and at low temperatures, NO_2 radicals are in equilibrium with dinitrogen tetraoxide, N_2O_4 , while higher temperatures shift the equilibrium towards nitrogen dioxide.²⁶

The calculations show that N₂O₄ is planar, with an N-N bond distance of 1.85 Å, which is significantly longer than the average N-N single bond length of 1.45 Å; this species has a dimerization energy of $\Delta E/\Delta H/\Delta G = 19.8/17.3/5.6$ kcal mol⁻¹. Unlike NO_{2} , $N_{2}O_{4}$ is diamagnetic and coordinates to the $Cs_{8}Nb_{6}O_{19}$ catalyst (see Fig. 3) with a Cs8Nb6O19-N2O4 interaction energy of $\Delta E/\Delta H/\Delta G = -25.3/-25.3/-18.5$ kcal mol⁻¹. Secondly, as shown in Table 1 and Fig. 3, the "free" NO₂ radical (at ambient temperature) can interact with polyoxoniobate to form the [Cs₈Nb₆O₁₉]/NO₂ adduct. This adduct exists in two energetically stable isomeric forms, Cs8Nb6O19/NO2(Ot) and Cs8Nb6O19/ $NO_2(Cs^N)$; the most favorable form is $Cs_8Nb_6O_{19}/NO_2(Cs^N)$, where the N atom of NO2 interacts with two Cs centers (with Cs^{1} -N and Cs^{2} -N distances of 3.42 and 3.44 Å). To our surprise, these Cs-N interactions lead to electron transfer from $Cs_8Nb_6O_{19}$ to NO₂ in $Cs_8Nb_6O_{19}/NO_2(Cs^N)$, as evidenced by population analysis: the calculated Mulliken spin/charge is $NO_2(Cs^N) = 0.34/-0.65 |e|$. Thus, as a result of these interactions, almost 0.65 |e| charge is transferred from Cs₈Nb₆O₁₉ to NO₂; and, consequently, the Cs₈Nb₆O₁₉ unit develops partial radical character. Further analysis shows that most of the unpaired spin of Cs8Nb6O19 is located on the internal OIN-center $(\sim 0.24 |e|)$ and the bridging O^{μ} $(\sim 0.14 |e|)$ located close to the Cs atoms coordinated to NO₂, while the remaining spin is delocalized on all other atoms of the polyoxoniobate. Similarly, but to a lesser extent, $NO_2(O^t)$ has a 0.67/-0.41 |e| spin/charge distribution in the Cs₈Nb₆O₁₉/NO₂(O^t) isomer. The calculated $Cs_8Nb_6O_{19}$ -NO₂ binding energies are $\Delta H/\Delta G = -22.2/-22.1$ and -18.7/-13.9 kcal mol⁻¹ in Cs₈Nb₆O₁₉/NO₂(Cs^N) and $Cs_8Nb_6O_{19}/NO_2(O^t)$, respectively.



Fig. 3 The calculated most energetically stable structures of NO₂ and N₂O₄ adsorbed on Cs₈Nb₆O₁₉, with their important geometry parameters (in Å).

Consequently, the acquired partial radical character of $Cs_8Nb_6O_{19}$ in the $Cs_8Nb_6O_{19}/NO_2(Cs^N)$ complex significantly increases its NO2-affinity, enabling strong coordination of another (second) NO2 radical to the Ot-site of polyoxoniobate and formation of the most thermodynamically favorable Cs₈Nb₆O₁₉/ $[NO_2(Cs^N)NO_2(O^t)]$ singlet species. The calculated energy of the reaction $Cs_8Nb_6O_{19}/NO_2(Cs^N) + NO_2 \rightarrow Cs_8Nb_6O_{19}/[NO_2(Cs^N)]$ $NO_2(O^t)$] is $\Delta E/\Delta H/\Delta G = -55.8/-52.4/-35.9$ kcal mol⁻¹, while the energy of the $Cs_8Nb_6O_{19}/NO_2(O^t) + NO_2 \rightarrow Cs_8Nb_6O_{19}/NO_2(O^t)$ $[NO_2(Cs^N)NO_2(O^t)]$ reaction is $\Delta E/\Delta H/\Delta G = -63.8/-61.5/$ -52.8 kcal mol⁻¹ (see ESI^{\ddagger} for more details). Thus, removal of NO₂(O^t) and/or NO₂(Cs^N) from Cs₈Nb₆O₁₉/[NO₂(Cs^N)NO₂(O^t)] with two NO₂-adsorbates requires greater energy than removing them from Cs₈Nb₆O₁₉/NO₂(O^t) and/or Cs₈Nb₆O₁₉/NO₂(Cs^N). The overall energy of the reaction $Cs_8Nb_6O_{19} + 2NO_2 \rightarrow Cs_8Nb_6O_{19}$ $[NO_2(Cs^N)NO_2(O^t)]$ is $\Delta E/\Delta H/\Delta G = -77.4/-74.6/-58.0$ kcal mol⁻¹ (see Table 1). To summarize, a relatively weak coordination of the first NO₂ radical to Cs₈Nb₆O₁₉ at the Cs sites promotes stronger coordination of the second NO₂ molecule at the O^t site of $Cs_8Nb_6O_{19}$. As a result, the coordination of the NO₂ radicals to Cs₈Nb₆O₁₉ is substantially stronger than that of CO₂, yet slightly weaker than that of one SO₂ molecule.

The reported highly stable $Cs_8Nb_6O_{19}/[NO_2(Cs^N)NO_2(O^t)]$ complex with two NO₂ fragments can also be formed *via* N–N bond activation of the coordinated N₂O₄ molecule by the polyoxometalate catalyst. The former pathway (*i.e.* stepwise addition of two NO₂ radicals to polyoxoniobate) may be valid at ambient temperature, while the latter process may occur at low temperature. In this paper, we did not study the N–N activation barrier; however, we found that the complex $Cs_8Nb_6O_{19}/$ $[NO_2(Cs^N)NO_2(O^t)]$ (see Fig. 3) lies significantly lower in energy than the $Cs_8Nb_6O_{19} + N_2O_4$ dissociation limit, by $\Delta E/\Delta H/\Delta G =$ 57.6/57.3/52.4 kcal mol⁻¹, and $\Delta E/\Delta H/\Delta G =$ 37.8/40.0/46.8 kcal mol⁻¹ lower than the $Cs_8Nb_6O_{19}/N_2O_4$ intermediate.

In order to better understand the factors impacting the strength of the Cs₈Nb₆O₁₉/NO₂ interaction, we also analyzed the geometry of the complex Cs₈Nb₆O₁₉/[NO₂(Cs^N)NO₂(O^t)]. As seen in Fig. 3, where we present the most important geometries of the Cs₈Nb₆O₁₉/NO₂(O^t), Cs₈Nb₆O₁₉/NO₂(Cs^N) and Cs₈Nb₆O₁₉/[NO₂(Cs^N)NO₂(O^t)] species (for full geometries of these species, see the ESI[‡]), in Cs₈Nb₆O₁₉/[NO₂(Cs^N)NO₂(O^t)], the Nb–O^t bond is elongated to 2.47 Å; concurrently, the Nb–O^{IN} bonds (which are 2.34, 2.44 and 2.02 Å in these complexes, respectively) and N–O^t bonds (which are 1.28 and 2.25 Å in Cs₈Nb₆O₁₉/[NO₂(Cs^N)NO₂(O^t)] and Cs₈Nb₆O₁₉/NO₂(O^t), respectively) are formed. As a result, the complex Cs₈Nb₆O₁₉/[NO₂(Cs^N)NO₂(O^t)] has one NO₃^{-ô} fragment (δ = 0.4) and one NO₂^{-ô} fragment (δ = 0.94) coordinated to the Cs-cations.

Above, we have shown that: (1) at ambient temperatures, a relatively weak coordination of the first NO_2 radical to $Cs_8Nb_6O_{19}$ confers partial radical character on the polyoxoniobate and promotes a stronger coordination of the second NO_2 radical to form a stable diamagnetic $Cs_8Nb_6O_{19}/[NO_2(Cs^N) NO_2(O^t)]$ complex, and (2) at low temperatures, coordination of a weakly stable N_2O_4 molecule to $Cs_8Nb_6O_{19}/[NO_2(Cs^N) NO_2(O^t)]$ complex. Regardless of the formation mechanisms, in

 $Cs_8Nb_6O_{19}/[NO_2(Cs^N)NO_2(O^t)]$, the coordination of the NO_2 radical positioned at O^t to $Cs_8Nb_6O_{19}$ is substantially stronger than that of CO_2 , yet is slightly weaker than that of one SO_2 molecule.

These conclusions from our computations are fully supported by experiments. As with CO₂, the adsorption of NO₂ onto Cs₈Nb₆O₁₉ was probed with the use of infrared spectroscopy. Fig. 4 shows spectra for the interaction between NO₂ and Cs₈Nb₆O₁₉. The adsorption of NO₂ on the surface resulted in two infrared vibrational features - one at 1668 cm⁻¹ and another at 1240 cm^{-1} (Fig. 4, i). These features are attributed to adsorbate N-O stretches as opposed to POM motions, which appear below 1000 cm⁻¹. Analysis of the calculated $[Cs_8Nb_6O_{19}]$ -NO₂ complexes suggests that the 1668 cm⁻¹ feature is likely due to an asymmetric NO stretch originating from the Cs₈Nb₆O₁₉/N₂O₄ complex, which the calculations (unscaled) show to be at 1813 cm^{-1} . For the other NO₂ complexes, the highest frequency NO stretch is found below 1600 cm⁻¹, *i.e.* at a lower frequency relative to the experimental peak. Taking into account the usual anharmonic correction, these modes will be found to be even further redshifted to lower frequencies. However, if we consider that the calculated asymmetric (strongly IR active) NO stretch of a free NO2 radical is 1752 cm⁻¹, and the known experimental value²⁵ is 1618 cm⁻¹, the resulting frequency scale factor of 0.92 brings the asymmetric NO stretch of the Cs₈Nb₆O₁₉/N₂O₄ complex to exactly 1668 cm⁻¹. Moreover, if the measured 1668 and 1240 cm⁻ peaks originate from the same thermal mixture of diamagnetic complexes, we expect that the 1240 cm⁻¹ peak, which persists at higher temperatures (Fig. 4, iii), is due to the Cs₈Nb₆O₁₉/ $[NO_2(Cs^N)NO_2(O^t)]$ complex, which is much more stable to thermal perturbation than Cs8Nb6O19/N2O4. The latter immediately transforms to Cs₈Nb₆O₁₉/[NO₂(Cs^N)NO₂(O^t)] upon N-N activation by heating. Indeed, there is a group of IR-active NO stretching motions in the Cs₈Nb₆O₁₉/[NO₂(Cs^N)NO₂(O^t)] complex in the 1346 to 1361 cm^{-1} (1238 to 1252 cm^{-1} scaled) region, which captures the measured 1240 cm^{-1} peak.



Fig. 4 Infrared spectra recorded during and after the adsorption of NO₂ onto $Cs_8Nb_6O_{19}$ at 300 K. (i) Adsorption of 35 mTorr of NO₂. (ii) After NO₂ evacuation. (iii) After NO₂ evacuation and thermal treatment at 423 K.

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Thus, we present two spectra (shown in Fig. 5); one corresponds to low temperature, Fig. 5(A), which is the sum of $Cs_8Nb_6O_{19}/N_2O_4$ and $Cs_8Nb_6O_{19}/[NO_2(Cs^N)NO_2(O^t)]$, and one corresponds to high temperature, Fig. 5(B), which is pure $Cs_8Nb_6O_{19}/[NO_2(Cs^N)NO_2(O^t)]$. The frequency axis is scaled by the same factor of 0.92. The calculation is consistent with experiments with regard to the disappearance of the 1668 cm⁻¹ peak and the persistence of the 1240 cm⁻¹ peak. However, the peak at 1470 cm⁻¹ (after scaling) in the calculated spectra, which is attributed to a local NO stretch of the NO₃ unit in $Cs_8Nb_6O_{19}/[NO_2(Cs^N)NO_2(O^t)]$, is absent in the room-temperature experiments. This suggests that the formation of NO₃ requires a significant amount of thermal energy.

Furthermore, experiments clearly show that NO₂ is strongly bound to the POM, *i.e.* the 1240 cm⁻¹ peak is present even after gas phase evacuation (Fig. 4, ii) and upon heating the POM to 423 K (Fig. 4, iii). In fact, thermal treatment up to 600 K was required to fully desorb the species, *i.e.* to remove NO₂ radicals. This suggests that NO₂ binds more strongly to the POM than CO₂, which is consistent with the computational data for the Cs₈Nb₆O₁₉/[NO₂(Cs^N)NO₂(O^t)] complex presented above (see Table 1 and the ESI[‡]).

Thus, the data presented above show that in the presence of ambient gas molecules of CO_2 , NO_2 and SO_2 , $Cs_8Nb_6O_{19}$ will absorb these molecules more strongly than the water and GB molecules required for hydrolysis of Sarin (see Table 1). This is expected to impact the hydrolysis of Sarin by $Cs_8Nb_6O_{19}$ in the following two ways: first, because the ambient gas molecules coordinate to catalytically active O^t-centers, they block these catalytically active centers, hindering water and Sarin coordination, and may alter the previously reported mechanism of Sarin hydrolysis by $Cs_8Nb_6O_{19}$. Second, the interaction of an ambient gas molecule with $Cs_8Nb_6O_{19}$ may change the electronic properties of the polyoxoniobate: this is expected to only impact the calculated energetics of the Sarin hydrolysis and to not significantly change the nature of the previously reported intermediates and transition state structures.



Fig. 5 The calculated harmonic IR spectra (all in the NO stretch region), scaled by 0.92, of (A) the sum of the $Cs_8Nb_6O_{19}/N_2O_4$ and $Cs_8Nb_6O_{19}/[NO_2(Cs^N)NO_2(O^t)]$ species; (B) the pure $Cs_8Nb_6O_{19}/[NO_2(Cs^N)NO_2(O^t)]$ species.

Below, we test the first hypothesis by (a) studying the full potential energy surfaces of GB hydrolysis by $Cs_8Nb_6O_{19}/X$, where $X = CO_2$ and SO_2 , and (b) comparing these new findings with our previous results on the same reaction in the absence of ambient gas molecules. For the sake of simplicity, we discuss in detail only the reaction mechanism (as well as the structures of the pre-reaction complexes, intermediates, transition states and products) for $X = CO_2$ and compare these findings with those (previously reported) in the absence of ambient gas molecules. In addition, we briefly discuss, where appropriate, our findings for $X = SO_2$ (full potential energy surfaces are available in the ESI^+_2). The reactivities of the NO_2 and other radical species coordinated to $Cs_8Nb_6O_{19}$ will be reported elsewhere.

B. Hydrolysis of Sarin by $Cs_8Nb_6O_{19}/X$ species (where $X = CO_2$ and SO_2)

As we have shown previously²⁴ and have briefly discussed above (see Scheme 1), Sarin hydrolysis by $Cs_8Nb_6O_{19}$ is a multistep process, with coordination of a water molecule to the catalyst as the first step. The calculations (see Table 1) show that coordination of H₂O to $Cs_8Nb_6O_{19}$ to form $Cs_8Nb_6O_{19}/H_2O$ is exothermic/exergonic by (presented as $\Delta H/\Delta G$) 23.6/ 17.3 kcal mol⁻¹. In $Cs_8Nb_6O_{19}/H_2O$, the two hydrogens of the water molecule interact with one bridging (O^µ) and one terminal (O^t) oxygen atom of the polyoxometalate.

Water molecule coordination to the adduct formed when CO_2 (or SO_2) binds to the O^t-center of $Cs_8Nb_6O_{19}$ is a few kcal mol⁻¹ less than that for "free" $Cs_8Nb_6O_{19}$; the energies are -22.4/-11.9and -21.0/-9.7 kcal mol⁻¹ for $X = CO_2$ and SO_2 , respectively. This effect is more pronounced for the $Cs_8Nb_6O_{19}/SO_2$ adduct than for $Cs_8Nb_6O_{19}/CO_2$. Furthermore, as seen in Fig. 6, the water coordination motif in $Cs_8Nb_6O_{19}/CO_2/H_2O$ is different from that in $Cs_8Nb_6O_{19}/H_2O$: because CO_2 occupies the O^t-position in $Cs_8Nb_6O_{19}/CO_2$, the H_2O molecule is H-bonded to one bridging (O^{μ}) and one CO (O¹) oxygen atom (instead of O^t). The calculated $O^{\mu}-H^1$ and O^1-H^2 bond distances are 1.76 and 1.85 Å, respectively.

Following the formation of the $Cs_8Nb_6O_{19}/X/H_2O$ complex, the addition of Sarin to this intermediate occurs. Previously, we examined several approaches of Sarin to $Cs_8Nb_6O_{19}$ and found that nerve agent decomposition occurs when Sarin approaches the hydrated $Cs_8Nb_6O_{19}$ segment with its $O(sp^2)$ and $O(sp^3)$ atoms (labeled in Fig. 6 and below as O^5 and O^4 , respectively).²⁴ The additional stabilization of the complex arises from the longrange $O^4...Cs^3$ ionic interaction. Thus, for the purposes of modeling the decomposition of Sarin in the presence of carbon and sulfur dioxide, it is sufficient to examine the most energetically favorable pathway, similar to that previously reported for the case with no ambient gas molecules. In keeping with the previously established shorthand notation, the pre-reaction complex of this reaction pathway is labeled as R–F_X.

The present calculations show that the coordination of Sarin (GB) to $Cs_8Nb_6O_{19}/X/H_2O$ is exothermic by -18.0/-2.4 and -17.4/-3.8 kcal mol⁻¹ for $X = CO_2$ and SO_2 , respectively. Inspection of the structure of the $Cs_8Nb_6O_{19}/X/H_2O/GB$, R–F_X, intermediate reveals a non-covalently bonded [Cs₈Nb₆O₁₉/CO₂/H₂O]–GB complex. For example, as seen in Fig. 6, in contrast to

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.



Fig. 6 Calculated pre-reaction complexes, transition states and products of GB hydrolysis by $Cs_8Nb_6O_{19}/CO_2$ (*i.e.* the reaction $Cs_8Nb_6O_{19}/CO_2$ + H_2O + GB \rightarrow R-F_CO₂ \rightarrow TS-F_CO₂ \rightarrow P5-F_CO₂) and their important geometry parameters (in Å). Similar structures for X = SO₂ are presented in the ESI.[‡]

the coordination of GB to $Cs_8Nb_6O_{19}/H_2O$, in $Cs_8Nb_6O_{19}/CO_2/H_2O/GB$, the nerve agent is coordinated to one of the Cs centers of the $Cs_8Nb_6O_{19}$ -core with its $P=O^4$ double bond. Several H-bonds also exist between the GB ligand and the $[Cs_8Nb_6O_{19}/CO_2/H_2O]$ -fragment. In this complex, the calculated Cs^3-O^4 bond distance is 3.13 Å and the nascent $P-O^3(OH_2)$ bond distance is 3.12 Å.

In the next step, hydrolysis of the coordinated water molecule occurs between the coordinated gas molecule X, the bridging oxygen (O^{μ}) of the Cs₈Nb₆O₁₉-core and the phosphorus center of Sarin. The transition state associated with this process, TS-F_CO₂, is shown in Fig. 6 (for TS-F_SO₂, see the ESI[‡]). As seen in this figure, at TS-F_CO₂, the breaking O³-H¹ bond of the water molecule is elongated to 1.16 Å, and the forming O^{μ}-H¹ bond distance becomes 1.25 Å. In addition, Nb¹-O^{μ} and Nb²-O^{μ} bonds are slightly elongated and the Cs³-O⁴ bond is slightly shortened. Importantly, the Cs³-center of the Cs₈Nb₆O₁₉ core also interacts with the oxygen (O³) of water and provides additional support for hydrolysis. Here, the other coordinates of interest are the P-O³(H₂O) bond and the P-F bond.

As seen in Fig. 6, P–O³(H₂O) undergoes a major reduction from 3.12 Å in R-F_CO₂ to 1.96 Å in TS-F_CO₂. Its P-F counterpart, located *trans* to the water-activated molecule, extends from the typical single bond in R-F_CO₂, with an increase from 1.62 Å to 1.71 Å in TS-F_CO₂. Similar geometry changes at the hydrolysis transition state were observed for X = SO₂ (see the ESI[‡]). As seen in Fig. 7, the calculated $\Delta E/\Delta G$ barrier heights relative to R-F_X are 7.8/7.5 and 8.4/8.8 kcal mol⁻¹ for $X = CO_2$ and SO_2 , respectively. These values are slightly larger than the values of 6.8/6.1 kcal mol⁻¹ calculated for the reaction in the absence of these ambient gas molecules; this suggests that common battlefield contaminants may impair the hydrolytic decomposition of nerve agents under operational conditions.

The hydrolysis product is a pentacoordinated-phosphorus complex P5-F_X with a trigonal bipyramidal structure around the central phosphorus atom. In our previous paper, we showed that this intermediate exhibits multiple isomeric forms.²⁴ Here, we discuss only the energetically most favorable form, which is directly connected to the transition state TS-F_X. For example,



Fig. 7 Potential energy profile of the hydrolysis of Sarin (GB) by $Cs_8Nb_6O_{19}$ and $Cs_8Nb_6O_{19}/X(O^t)$, where $X = CO_2$ or SO_2 . ΔE and ΔG are the changes in the electronic and Gibbs free energies and are calculated relative to the reactants $Cs_8Nb_6O_{19}/X(O^t) + H_2O + GB$.

as seen in Fig. 6, the formed P–O³ bond in P5-F_CO₂ contracts to 1.79 Å, while its P-F counterpart, located *trans* to the activated water molecule, extends to 1.76 Å. The broken O³–H¹ bond is elongated to 1.64 Å and the Nb¹–O^µ and Nb²–O^µ bonds are elongated to 2.20 and 2.13 Å, respectively. Concurrently, the Cs³–O³ bond of 3.11 Å is formed to provide additional stabilization to the pentacoordinated-phosphorus complex, similar to that previously reported in P5-F.²⁴ Based on the calculated Mulliken charge distribution, the resulting P5-F_X complexes can be labeled as a [(GBOH⁻)–(Cs₈Nb₆O₁₉H/X)⁺] ion-pair system.

As shown in Fig. 7, the hydrolysis of Sarin, *i.e.* the reaction $Cs_8Nb_6O_{19}/X + H_2O + GB \rightarrow R-F_X \rightarrow TS-F_X \rightarrow P5-F_X$ for X = none, CO_2 or SO_2 , is exergonic by -50.1/-27.9, -38.8/-11.1 and -40.5/-14.7 kcal mol⁻¹ (presented as $\Delta H/\Delta G$) and proceeds over energy barriers of 6.8/6.1, 7.5/7.5 and 8.4/8.8 kcal mol⁻¹ (calculated relative to the pre-reaction intermediate R-F X), respectively. The reaction $R-F_X \rightarrow TS-F_X \rightarrow P5-F_X$ is exothermic for X = none and SO₂ by 6.8/6.4 and 0.4/ 1.2 kcal mol $^{-1}$, respectively, but is endothermic by 3.4/ 3.2 kcal mol⁻¹ for $X = CO_2$. These energy values allow us to conclude that the presence of ambient gas molecules increases the energies of the stationary points relative to the asymptote of the reactants. This is likely the result of a different charge distribution on Cs₈Nb₆O₁₉/X relative to Cs₈Nb₆O₁₉, where X acquires a net negative charge of 0.8 to 0.7 |e|, as we showed above. Furthermore, X coordinates to the O^t reactive center and disables its hydrolytic activity. The presence of ambient gases increases the hydrolysis barrier by 1.0 to 2.5 kcal mol⁻¹, and this change in the energy barrier is closely associated with the Cs₈Nb₆O₁₉-X complexation energy: the stronger the Cs₈Nb₆O₁₉-X bond, the higher the barrier for Sarin hydrolysis.

C. Pentacoordinated P5-F_X intermediate dissociation

Once the pentacoordinated P5-F_X species is formed, the reaction can proceed along several paths, as discussed in our previous paper.24 In order to evaluate the role of the catalyst in the course of the reaction, as above, here we discuss in detail only those pathways that directly involve the catalyst. These are the HF and isopropanol elimination and, ultimately, desorption pathways. The accompanying products of these paths are isopropyl methyl phosphonic acid (i-MPA) and methyl phosphonofluoridic acid (MPFA), respectively. It is evident that in order to form HF or isopropanol, protonation of the fluoride or oxygen centers of the isopropoxy ligand is required. Furthermore, in order to facilitate regeneration of the catalyst, the ultimate proton source should be the $O^{\mu}H^{1}$ -group of the $[Cs_8Nb_6O_{19}H/X]^+$ cation. However, these processes are expected to be very complex and may proceed via multiple mechanisms. One of these processes could involve any surrounding water molecules, which are expected to be present in real experimental conditions. In this mechanism, a water molecule located close to the fluoride or oxygen atoms of the iopropoxy ligand is expected to donate its proton to these groups (to form HF and/or isopropanol, respectively) and compensate by removing the proton from the O^µH¹-group of the catalyst via a H-bonding network. This process depends on multiple factors (including, but not limited to, the concentration of water in the system and the reaction temperature) and was not studied in this paper.

Another possible mechanism of HF and/or isopropanol formation is direct removal of the proton from the O^µH¹-group of the catalyst by the fluoride and/or isopropoxide ligands, respectively. As shown previously for the Cs₈Nb₆O₁₉ catalyst (i.e., in the absence of ambient gas molecules),²⁴ these processes occur with very small energy barriers which have no contribution to the overall outcome of the decontamination reaction but lead to the most energetically stable intermediates, Cs₈Nb₆O₁₉-(i-MPA)-HF and Cs₈Nb₆O₁₉-(MPFA)-(i-POH), respectively (see Fig. 8). Here, we performed an extensive search to locate the transition states TS2-F HF X and TS2-F (i-POH) X that lead to either HF and i-MPA or isopropanol (i-POH) and MPFA from the most stable pentacoordinated intermediate P5-F X (where X = CO_2 or SO_2). Ultimately, we were able to locate only the TS2-F_(i-POH)_X transition state (see Fig. 8). The search for the HF formation transition state TS2-F HF X was unsuccessful and always led to either the Cs₈Nb₆O₁₉/X-(i-MPA)-HF intermediate, its derivative $F^- \cdots H^+ \cdots O^{\mu}$ intermediate, or the pre-reaction complex P5-F_X. For example, in Fig. 8, we present the intermediates, transition states and products involved in pentacoordinated P5-F CO2 intermediate dissociation alone, with their important geometry parameters (for those of $X = SO_2$, see the ESI[‡]). The relative energies of these species, calculated from the P5-F_X pre-reaction complex, are given in Fig. 9.

As seen in Fig. 8, at the transition state TS2-F_(i-POH)_CO₂ associated with the formation of i-POH and MPFA, the activated P-O⁵(Osp²) bond extends to 2.19 Å from 1.68 Å in P5-F_CO₂, with simultaneous formation of a double H-bond network $(O^5-H^1 = 1.63 \text{ Å and } O^1-H^2 = 1.57 \text{ Å})$ as a precursor to the



Fig. 8 The calculated transition states, intermediates and products of the dissociation of pentacoordinated P5-F_CO₂ (*i.e.* reactions: P5-F_CO₂ \rightarrow Cs₈Nb₆O₁₉/CO₂-(MPFA)-(i-POH) \rightarrow Cs₈Nb₆O₁₉/CO₂ + MPFAH + (i-POH) and P5-F_X \rightarrow Cs₈Nb₆O₁₉/CO₂-(MPA)-HF \rightarrow Cs₈Nb₆O₁₉/CO₂ + MPAH + HF) with their important geometry parameters (in Å). Similar structures for X = SO₂ are presented in the ESI.‡



Fig. 9 Potential energy profiles of the decomposition reaction of pentacoordinated-phosphorus intermediate P5-F_X, where X = CO₂ and SO₂ (*i.e.* reactions: P5-F_X \rightarrow Cs₈Nb₆O₁₉/X-(MPFA)-(i-POH) \rightarrow Cs₈Nb₆O₁₉/X + MPFAH + (i-POH) and P5-F_X \rightarrow Cs₈Nb₆O₁₉/X + (MPA)-HF \rightarrow Cs₈Nb₆O₁₉/X + MPAH + HF). ΔE and ΔG are the changes in the electronic and Gibbs free energies and are calculated relative to the reactants Cs₈Nb₆O₁₉/X(O^t) + H₂O + GB.

charge-preserving double proton transfer. In other words, as the proton of the $O^{\mu}H^{1}$ -group moves to Sarin, the proton on the $PO^{3}H^{1}$ group of Sarin migrates back to the $Cs_{8}Nb_{6}O_{19}/X$ -core to form $[HXO^{t}]^{q}$, where $X = CO_{2}$. As a result, the formed P– $O^{3}(H_{2}O)$ bond is shortened from 1.79 Å in P5-F_CO₂ to 1.61 Å in the transition state.

As seen in Fig. 9, the calculated energy barriers from P5-F_X are 7.0/7.6, 5.4/5.4 and 3.6/6.5 kcal mol⁻¹ for X = none, CO₂ and SO₂. Thus, the presence of these gas molecules in the reaction mixture slightly reduces the pentacoordinated P5-F_X intermediate dissociation barrier (by 2 to 4 kcal mol⁻¹). Furthermore, the changes in the i-POH and MPFA formation energy barriers correlate with the Cs₈Nb₆O₁₉-X complexation energy: the stronger the Cs₈Nb₆O₁₉-X bond, the smaller the i-POH and MPFA formation energy barriers.

Comparison of the calculated energetics for the dissociation of the pentacoordinated intermediate with those for hydrolysis (*i.e.* formation of the pentacoordinated intermediate) show that, in general, the hydrolysis step is a rate-determining step for all reported species, and the presence of ambient gas molecules increases this energy barrier only slightly, by 2 to 4 kcal mol⁻¹. Furthermore, the height of this rate-determining energy barrier correlates with the $Cs_8Nb_6O_{19}$ -X complexation energy: the stronger the $Cs_8Nb_6O_{19}$ -X bond, the more difficult the hydrolysis of GB by the $Cs_8Nb_6O_{19}$ catalyst.

D. Catalyst regeneration

Thus, the facile dissociation of the P5_F_X species, as reported previously for P5_F, yields HF and i-MPA and/or i-POH and MPFA products. All these species are initially bound to $Cs_8Nb_6O_{19}$, as shown in Fig. 8 for X = CO_2 and the ESI‡ for X = SO_2 . For example, in the $Cs_8Nb_6O_{19}/CO_2$ -(i-MPA)-HF complex, the (i-MPA)-fragment forms a hydrogen bond with the O^{μ} and OH-unit of the HOCOO^t fragment, respectively. The HF molecule, on the other hand, in the presence of an X molecule,

prefers to form an $[F^-\cdots H^+]$ ion-pair prior to dissociation. Similarly, in the $Cs_8Nb_6O_{19}/CO_2$ -(MPFA)-(i-POH) complex, the (i-POH) molecule and MPFA-fragment are hydrogen bonded to another O^t atom and the OH-unit of the HOCOO^t fragment, respectively: the calculated H^1-O^6 and O^3-H^2 bond distances are 1.73 and 1.67 Å, respectively. In addition, there are electrostatic interactions between the O center of the isopropanol molecule and two Cs cations of the $Cs_8Nb_6O_{19}/CO_2$ core, with Cs^1-O^5 and Cs^3-O^5 bond distances of 3.19 Å and 3.31 Å, respectively. The formed P–O³ fragment also interacts with the Cs^1 -center, with a Cs^1-O^3 distance of 3.16 Å.

As seen in Fig. 9, the formed $Cs_8Nb_6O_{19}/X$ -MPFA-(i-POH) is the energetically lowest structure on the potential energy surface of the entire GB hydrolysis and decontamination reaction by $Cs_8Nb_6O_{19}$ both in the absence and presence of ambient gas molecules. The intermediate $Cs_8Nb_6O_{19}/X$ -(i-MPA)-HF is found to be only slightly higher in energy. As we mentioned previously,²⁴ the high stability of these intermediates is due in part to the strong hydrogen bonds between the adsorbates and the $Cs_8Nb_6O_{19}/X$ -core; however, it is also due to the additional stabilizing interactions between the Cs counter-ions and the electronegative atoms of the nerve-agent fragments.

Desorption of HF and isopropanol from $Cs_8Nb_6O_{19}/X$ -(i-MPA)-HF and $Cs_8Nb_6O_{19}/X$ -MPFA-(i-POH) requires 15.2/12.7 and 20.0/ 5.3 kcal mol⁻¹ energy, respectively, for X = CO₂. Dissociation of HF and isopropanol only slightly modifies the geometries of the products $Cs_8Nb_6O_{19}/X$ -(i-MPA) and $Cs_8Nb_6O_{19}/X$ -MPFA fragments (for example, see Fig. 8 for X = CO₂) compared with the $Cs_8Nb_6O_{19}/X$ -(i-MPA)-HF and $Cs_8Nb_6O_{19}/X$ -MPFA-(i-POH) adducts; therefore, this will not be discussed in detail.

However, both i-MPA in Cs₈Nb₆O₁₉/X-(i-MPA) and MPFA in Cs₈Nb₆O₁₉/X-MPFA are strongly bound to the protonated $[Cs_8Nb_6O_{19}/X]H^+$ -core. Thus, regeneration of the catalyst requires deprotonation of the [Cs8Nb6O19/X]H+-core and protonation of the phosphonic acids i-MPA and MPFA. This step of the reaction, which forms a final decontaminated form of the GB and re-generated catalyst, is found to be highly endothermic/endergonic, *i.e.* 6.4/6.5 and 2.8/1.9 kcal mol⁻¹ for i-MPAH and MPFAH formation, respectively. Overall, the last steps of the reaction, *i.e.* the reactions Cs₈Nb₆O₁₉/X-(i-MPA)-HF \rightarrow Cs₈Nb₆O₁₉/X + HF + (i-MPAH) and Cs₈Nb₆O₁₉/X-MPFA-(i-POH) \rightarrow Cs₈Nb₆O₁₉/X + (i-POH) + MPFAH, are highly prohibitive and require energies of 80.3/60.2 (X = none), 64.4/36.3 (X = CO_2), and 66.0/39.4 (X = SO_2) kcal mol⁻¹ and 81.0/60.4 (X = none), 71.2/43.6 (X = CO₂), and 63.3/36.4 (X = SO₂) kcal mol⁻¹. respectively. Furthermore, deprotonation of the $[Cs_8Nb_6O_{19}/X]$ H⁺-core and protonation of the phosphonic acids i-MPA and MPFA is expected to be very complex and may proceed via several pathways depending on the reaction conditions. One of these may involve any surrounding water molecules, in real experimental conditions, via a concerted protonationdeprotonation mechanism involving the hydrogen-bonded water-based network. However, this process depends on multiple factors (including, but not limited to, the concentration of water in the system and the reaction temperature) and was not studied in this paper. We also failed to locate a transition state associated with the direct deprotonation of $[{\rm Cs_8Nb_6O_{19}/X}]{\rm H^+}$ and protonation of the phosphonic acids because of the high stability of the corresponding pre-reaction complexes ${\rm Cs_8Nb_6O_{19}/X}\text{-}(i\text{-}MPA)$ and ${\rm Cs_8Nb_6O_{19}/X}\text{-}MPFA$. The solution to this issue requires special comprehensive experimental and computational studies, which are in progress.

Conclusions

This paper, for the first time, addresses the impact of environmentally-significant ambient gas molecules, NO_2 , CO_2 and SO_2 , on the structure, stability and decontamination activity of a basic polyoxometalate species. Specifically, $Cs_8Nb_6O_{19}$ in the presence of these gases has been studied in depth by complementary computational and experimental approaches. It was found that:

(1) $Cs_8Nb_6O_{19}$ absorbs ambient gas molecules of $X = CO_2$, NO_2 and SO_2 more strongly than it absorbs water or Sarin (GB) molecules. The calculated $Cs_8Nb_6O_{19}$ -X binding energy follows the trend for ΔG (X = CO₂) < ΔG (NO₂) < ΔG (SO₂).

(2) The impacts of the diamagnetic CO_2 and SO_2 molecules on polyoxoniobate $Cs_8Nb_6O_{19}$ are fundamentally different than that of the NO₂ radical. At ambient temperatures, weak coordination of the first NO₂ radical to $Cs_8Nb_6O_{19}$ confers partial radical character on the polyoxoniobate and promotes a stronger coordination of the second NO₂ radical to form a stable diamagnetic $Cs_8Nb_6O_{19}/(NO_2)_2$ species; meanwhile, at low temperatures, NO₂ radicals form weakly stable dinitrogen tetraoxide (N₂O₄), which interacts weakly with $Cs_8Nb_6O_{19}$.

(3) Similar to the case without ambient gas molecules, reported previously,²⁴ in the presence of X, GB hydrolysis by $Cs_8Nb_6O_{19}/X$ proceeds *via* general base hydrolysis involving: (a) adsorption of water and the nerve agent on the $Cs_8Nb_6O_{19}/X$ catalyst, (b) concerted hydrolysis of the adsorbed water molecule on a basic oxygen atom of the polyoxoniobate and nucleophilic addition of the nascent OH group to the phosphorus center of the nerve agent, (c) rapid reorganization of the resulting pentacoordinated-phosphorus intermediate followed by dissociation of either HF or isopropanol with formation of POM-bound isopropyl methyl phosphonic acid (i-MPA) or methyl phosphonofluoridic acid (MPFA), respectively.

(4) $Cs_8Nb_6O_{19}$ adsorbs ambient gas molecules X at its basic O^t (or O^{μ}) reactive centers, which shields them from involvement in the base hydrolysis. As a result, one of the O centers of the coordinated ambient gas molecule becomes an active hydrolysis center. This increases the energies of the stationary points relative to the asymptote of the reactants and increases the hydrolysis barrier. These changes are closely correlated with the $Cs_8Nb_6O_{19}$ -X complexation energy; the stronger the $Cs_8Nb_6O_{19}$ -X bond, the higher the barrier for Sarin hydrolysis.

(5) The most energetically stable products of the GB hydrolysis and decontamination reaction are $Cs_8Nb_6O_{19}/X$ -MPFA-(i-POH) and $Cs_8Nb_6O_{19}/X$ -(i-MPA)-HF both in the absence and presence of ambient gas molecules. The high stability of these intermediates is due in part to the strong hydrogen bonds between the adsorbates and the protonated $[Cs_8Nb_6O_{19}/X/H]^+$ -core and to interactions between the Cs counterions and the electronegative atoms of the adsorbates.

(6) Desorption of HF or/and (i-POH) and regeneration of the catalyst requires deprotonation of the $[Cs_8Nb_6O_{19}/X/H]^+$ -core with protonation of the phosphonic acids i-MPA and MPFA. Regeneration of the catalyst is a highly endergonic process and is the rate-limiting step for GB hydrolytic decontamination, both in the absence and presence of ambient gas molecules.

Notes

A. Computational and experimental procedures

A1. Computational methodology. A major computational challenge in the present work is to properly describe the noncovalent interactions involving the various ions in the systems studied: the Cs^+ counter-cations, $[Nb_6O_{19}]^{8-}$ with its large negative charge, and the H⁺ and OH⁻ ions resulting from heterolytic water dissociation. These interactions are expected to be well described by the M06-L density functional,²⁷ a pure density functional designed for transition metal bonding and non-covalent interactions. Therefore, all presented calculations have been carried out with the M06-L density functional, as implemented in the Gaussian09 code.28 In these calculations, we used the 6-31++G(d,p) basis set for the elements S, P, F, O, C, H and the Lanl2dz basis set with corresponding Hay-Wadt effective core potentials for Nb and Cs, as implemented in Gaussian09. The sets of diffuse functions (++) were added specifically to obtain proper descriptions of the diffuse charge densities and long-range interactions. All reported stationary points were confirmed to have either all real frequencies (minima) or one imaginary frequency (transition states). The latter were further verified to connect the corresponding minima by IRC calculations. All reported enthalpy and Gibbs free energies were computed at a temperature of 298.15 K and 1 atm pressure.

A2. Experimental methodology. The synthesis of $Cs_8Nb_6-O_{19}\cdot 14H_2O$ followed a known literature procedure. A solution of cesium hydroxide (14.6 g, 50% by weight) was heated to 90 °C in an Erlenmeyer flask. 5 g of hydrous, amorphous niobium oxide was added in small portions, with full dissolution of each portion before addition of the subsequent portion. Evaporative crystallization yielded giant hexagonal crystals.

Infrared spectroscopic experiments were performed in a stainless-steel high-vacuum chamber with a base pressure of $\sim 1 \times 10^{-8}$ Torr. The Cs₈Nb₆O₁₉ sample was pressed, as a 7 mm diameter disk, into a tungsten grid, which was then clamped onto a sample mount coupled to a precision manipulator. An empty region of the grid was used to monitor the gas phase species in the chamber and was also employed as a background for surface adsorption and desorption studies. The grid was resistively heated, and the temperature was monitored via a K-type thermocouple spot-welded adjacent to the sample. A PID controller mediated the sample temperature to within ± 1 K. Details of the vacuum chamber and sample mount can be found in a previous publication.²⁹ An FTIR spectrometer (Thermo, Nicolet, Nexus 470 FTIR) with an external liquid-N2-cooled MCT-A detector and a spectral resolution of 2 cm⁻¹ was used for collection of the infrared spectra.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This material is based upon work supported by the U. S. Army Research Laboratory and the U. S. Army Research Office under grant number W911NF-15-2-0107. The authors are grateful for the support of the Defence Threat Reduction Agency. The authors gratefully acknowledge NSF MRI-R2 grant (CHE-0958205 for D. G. M.) and the use of the resources of the Cherry Emerson Center for Scientific Computation.

Notes and references

- 1 (*a*) F. M. Raushel, *Nature*, 2011, **469**, 310; (*b*) M. Enserink, *Science*, 2013, **341**, 1050; (*c*) M. B. D. Nikitin, P. K. Kerr and A. Feickert, *Syria's Chemical Weapons: Issues for Congress*, 2013, report # R42848.
- 2 (a) N. Sharma and R. Kakkar, Adv. Mater. Lett., 2013, 4, 508;
 (b) N. Munro, Environ. Health Perspect., 1994, 102, 18; (c)
 W. W. George, in Nanoscale Materials in Chemistry: Environmental Applications, American Chemical Society, 2010, vol. 1045, pp. 125–136.
- 3 R. H. Pastel and E. C. Ritchie, in *Psychological Responses to the New Terrorism: A NATO-Russia Dialogue*, IOS Press, Amsterdam, 2005, pp. 9–24.
- 4 (a) Y. J. Yang, K. Kim, O. G. Tsay, D. A. Atwood and D. G. Churchill, *Chem. Rev.*, 2015, 115, PR1; (b) Y. C. Yang, J. A. Baker and J. R. Ward, *Chem. Rev.*, 1992, 92, 1729.
- 5 J. B. DeCoste and G. W. Peterson, *Chem. Rev.*, 2014, **114**, 5695.
- 6 S. Y. Moon, G. W. Wagner, J. E. Mondloch, G. W. Peterson, J. B. DeCoste, J. T. Hupp and O. K. Farha, *Inorg. Chem.*, 2015, 54, 10829.
- 7 Y. Liu, S. Y. Moon, J. T. Hupp and O. K. Farha, ACS Nano, 2015, 9, 12358.
- 8 J. E. Mondloch, M. J. Katz, W. C. Isley, P. Ghosh, P. L. Liao, W. Bury, G. W. Wagner, M. G. Hall, J. B. DeCoste, G. W. Peterson, R. Q. Snurr, C. J. Cramer, J. T. Hupp and O. K. Farha, *Nat. Mater.*, 2015, 14, 512.
- 9 M. J. Katz, J. E. Mondloch, R. K. Totten, J. K. Park, S. T. Nguyen, O. K. Farha and J. T. Hupp, *Angew. Chem.*, *Int. Ed.*, 2014, 53, 497.
- 10 R. Gaillac, P. Pullumbi, K. A. Beyer, K. W. Chapman, D. A. Keen, T. D. Bennett and F.-X. Coudert, *Nat. Mater.*, 2017, **16**, 1149–1154.
- 11 M. K. Kinnan, W. R. Creasy, L. B. Fullmer, H. L. Schreuder-Gibson and M. Nyman, *Eur. J. Inorg. Chem.*, 2014, 2014, 2361.
- 12 W. Guo, H. Lv, K. P. Sullivan, W. O. Gordon, A. Balboa, G. W. Wagner, D. G. Musaev, J. Bacsa and C. L. Hill, *Angew. Chem., Int. Ed.*, 2016, 55, 7403.
- 13 (a) D. M. Mizrahi, S. Saphier and I. Columbus, J. Hazard. Mater., 2010, 179, 495; (b) N. M. Okun, J. C. Tarr, D. A. Hilleshiem, L. Zhang, K. I. Hardcastle and C. L. Hill, J. Mol. Catal. A: Chem., 2006, 246, 11; (c) N. M. Okun,

T. M. Anderson and C. L. Hill, *J. Mol. Catal. A: Chem.*, 2003, **197**, 283; (*d*) F. Carniato, C. Bisio, R. Psaro, L. Marchese and M. Guidotti, *Angew. Chem., Int. Ed.*, 2014, 53, 10095.

- 14 As an example for computational studies of the POMs see:
 (a) J. M. Poblet, X. Lopez and C. Bo, *Chem. Soc. Rev.*, 2003,
 32, 297; (b) P. Miro, J. M. Poblet, J. B. Avalos and C. Bo, *Can. J. Biochem.*, 2009, 87, 1296; (c) C. Bo and J. M. Poblet, *Isr. J. Chem.*, 2011, 51, 228; (d) X. Lopez, P. Miro,
 J. J. Carbo, A. Rodriguez-Fortea, C. Bo and J. M. Poblet, *Theor. Chem. Acc.*, 2011, 128, 393; (e) X. Lopez, J. J. Carbo,
 C. Bo and J. M. Poblet, *Chem. Soc. Rev.*, 2012, 41, 7537; (f)
 B. Matt, X. Xiang, A. L. Kaledin, N. N. Han, J. Moussa,
 H. Amouri, S. Alves, C. L. Hill, T. Q. Lian, D. G. Musaev,
 G. Izzet and A. Proust, *Chem. Sci.*, 2013, 4, 1737; (g)
 A. E. Kuznetsov, Y. V. Geletii, C. L. Hill, K. Morokuma and
 D. C. Musaev, *J. Am. Chem. Soc.*, 2009, 131, 6844.
- 15 J. Song, Z. Luo, D. K. Britt, H. Furukawa, O. M. Yaghi,
 K. I. Hardcastle and C. L. Hill, *J. Am. Chem. Soc.*, 2011, 133, 16839.
- 16 F. J. Ma, S. X. Liu, C. Y. Sun, D. D. Liang, G. J. Ren, F. Wei, Y. G. Chen and Z. M. Su, *J. Am. Chem. Soc.*, 2011, 133, 4178.
- 17 T. J. Bandosz, M. Laskoski, J. Mahle, G. Mogilevsky,G. W. Peterson, J. A. Rossin and G. W. Wagner, *J. Phys. Chem. C*, 2012, **116**, 11606.
- 18 S. W. Yang, D. C. Doetschman, J. T. Schulte, J. B. Sarnbur, C. W. Kanyi and J. D. Fox, *Microporous Mesoporous Mater.*, 2006, 92, 56.
- 19 L. Bromberg, H. Schreuder-Gibson, W. R. Creasy, D. J. McGarvey, R. A. Fry and T. A. Hatton, *Ind. Eng. Chem. Res.*, 2009, 48, 1650.
- 20 (a) M. K. Kinnan, W. R. Creasy, L. B. Fullmer, H. L. Schreuder-Gibson and M. Nyman, *Eur. J. Inorg. Chem.*, 2014, 2014, 2361; (b) F.-J. Ma, S.-X. Liu, C.-Y. Sun, D.-D. Liang, G.-J. Ren, F. Wei, Y.-G. Chen and Z.-M. Su, *J. Am. Chem. Soc.*, 2011, 133, 4178; (c) D. M. Mizrahi, S. Saphier and I. Columbus, *J. Hazard. Mater.*, 2010, 179, 495–499; (d) N. M. Okun, J. C. Tarr, D. A. Hilleshiem, L. Zhang, K. I. Hardcastle and C. L. Hill, *J. Mol. Catal. A: Chem.*, 2006, 246, 11; (e) N. M. Okun, T. M. Anderson and C. L. Hill, *J. Mol. Catal. A: Chem.*, 2003, 197, 283; (f) F. Carniato, C. Bisio, R. Psaro, L. Marchese and M. Guidotti, *Angew. Chem., Int. Ed.*, 2014, 53, 10095.
- 21 (a) T. Yamase and M. T. Pope, in Nanostructure Science and Technology, ed. D. J. Lockwood, Kluwer Academic/Plenum Publishers, New York, vol. 2, 2002; (b) M. T. Pope, in Comprehensive Coordination Chemistry II: From Biology to Nanotechnology, ed. A. G. Wedd, Elsevier Ltd., Oxford, UK, 2004, vol. 4, pp. 635–678; (c) H. N. Miras, J. Yan, D.-L. Long and L. Cronin, Chem. Soc. Rev., 2012, 41, 7403; (d) H. Lv, Y. V. Geletii, C. Zhao, J. W. Vickers, G. Zhu, Z. Luo, J. Song, T. Lian, D. G. Musaev and C. L. Hill, Chem. Soc. Rev., 2012, 41, 7572.
- 22 (a) M. R. Antonio, M. Nyman and T. M. Anderson, Angew. Chem., Int. Ed., 2009, 121, 6252; (b) M. Nyman, T. M. Alam,
 F. Bonhomme, M. A. Rodriguez, C. S. Frazer and
 M. E. Welk, J. Cluster Sci., 2006, 17, 197; (c) M. Nyman,

Dalton Trans., 2011, **40**, 8049; (d) E. M. Villa, C. A. Ohlin, E. Balogh, T. M. Anderson, M. D. Nyman and W. H. Casey, *Angew. Chem., Int. Ed.*, 2008, **47**, 4844; (e) E. Balogh, T. M. Anderson, J. R. Rustad, M. Nyman and W. H. Casey, *Inorg. Chem.*, 2007, **46**, 7032.

- 23 M. Nyman, F. Bonhomme, T. M. Alam, M. A. Rodriguez,
 B. R. Cherry, J. L. Krumhansl, T. M. Nenoff and
 A. M. Sattler, *Science*, 2002, 297, 996.
- 24 R. C. Chapleski Jr, D. G. Musaev, C. L. Hill and D. Troya, J. *Phys. Chem. C*, 2016, **120**, 16822.
- 25 T. Shimanouchi, *Tables of molecular vibrational frequencies*, National Bureau of Standards, U.S. Govt. Print. Off., Washington, 1972.
- 26 (a) H. A. Bent, *Inorg. Chem.*, 1963, 2, 747; (b) E. Wiberg,
 N. Wiberg and A. F. Holleman, *Inorganic Chemistry*,
 Academic Press, San Diego, 2001, ISBN 0-12-352651-5.
- 27 Y. Zhao and D. G. Truhlar, J. Chem. Phys., 2006, 125, 194101.
- 28 M. J. Frisch, G. W. Trucks, H. B. Schlegel, G. E. Scuseria, M. A. Robb, J. R. Cheeseman, G. Scalmani, V. Barone,
- B. Mennucci, G. A. Petersson, H. Nakatsuji, M. Caricato, X. Li, H. P Hratchian, A. F. Izmaylov, J. Bloino, G. Zheng, J. L. Sonnenberg, M. Hada, M. Ehara, K. Toyota, R. Fukuda, J. Hasegawa, M. Ishida, T. Nakajima, Y. Honda, O. Kitao, H. Nakai, T. Vreven, J. A. Montgomery Jr, J. E. Peralta, F. ß. Ogliaro, M. J. Bearpark, J. Heyd, E. N. Brothers, K. N. Kudin, V. N. Staroverov, R. Kobayashi, J. Normand, K. Raghavachari, A. P. Rendell, J. C. Burant, S. S. Iyengar, J. Tomasi, M. Cossi, N. Rega, N. J. Millam, M. Klene, J. E. Knox, J. B. Cross, V. Bakken, C. Adamo, J. Jaramillo, R. Gomperts, R. E. Stratmann, O. Yazyev, A. J. Austin, R. Cammi, C. Pomelli, J. W. Ochterski, R. L. Martin, K. Morokuma, V. G. Zakrzewski, G. A. Voth, P. Salvador, J. J. Dannenberg, A. Dapprich, A. D. Daniels, ñ. n. Farkas, J. B. Foresman, J. V. Ortiz, J. Cioslowski and D. J. Fox, Gaussian, Inc.: Wallingford, CT, USA, 2009.
- 29 P. Basu, T. H. Ballinger and J. T. Yates, *Rev. Sci. Instrum.*, 1988, **59**, 1321.