RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2019, 9, 6299

Received 17th November 2018 Accepted 15th February 2019

DOI: 10.1039/c8ra09476d

rsc li/rsc-advances

1. Introduction

In recent years, various types of nanoparticles (NPs) have been investigated as potential magnetic resonance imaging (MRI) contrast agents. At the nanoscale, there is a higher probability to observe particles that constitute a single magnetic domain, this resulting in superparamagnetic behaviour. In fact, superparamagnetism is assumed to be the most favourable condition for solid-state contrast agents, as the uniform directionality of the field will maximize the magnetization strength. To achieve this maximal magnetic moment, the particle must remain below a certain size threshold (upwards from which a multidomain regime occurs).¹ Superparamagnetism is marked by the absence of remnant magnetization after removal of external fields. When applied to NPs, this property promotes colloidal stability and, most importantly, avoids aggregation (which is key for NPs used in biomedical applications).² However, with size reduction (and the associated increase in surface-to-volume unintended phenomena become ratio), some more

Cobalt ferrite supported on reduced graphene oxide as a T_2 contrast agent for magnetic resonance imaging⁺

Amira Alazmi, 💿 *ad Venkatesh Singaravelu, ^b Nitin M. Batra, a Jasmin Smajic, 回 a Mram Alyami,^c Niveen M. Khashab⁽⁰⁾ and Pedro M. F. J. Costa⁽⁰⁾*^a

Nanoscaled spinel-structured ferrites bear promise as next-generation contrast agents for magnetic resonance imaging. However, the small size of the particles commonly leads to colloidal instability under physiological conditions. To circumvent this problem, supports onto which the dispersed nanoparticles can be anchored have been proposed. Amongst these, flakes of graphene have shown interesting performance but it remains unknown if and how their surface texture and chemistry affect the magnetic properties and relaxation time (T_2) of the ferrite nanoparticles. Here, it is shown that the type of graphene oxide (GO) precursor, used to make composites of cobalt ferrite (CoFe₂O₄) and reduced GO, influences greatly not just the T_2 but also the average size, dispersion and magnetic behaviour of the grafted nanoparticles. Accordingly, and without compromising biocompatibility, a judicious choice of the initial GO precursor can result in the doubling of the proton relaxivity rate in this system.

> pronounced. These can deleteriously affect the superparamagnetic response of a nanoparticle and include agglomeration, spin-glass-like behaviour, non-collinear spins and spin canting.2,3

> Spinel ferrite compounds MFe_2O_4 (M = Mn, Co, Ni, Fe, etc.) are a class of metal oxide materials that offer a broad spectrum of applications.^{4,5} In particular, cobalt ferrite (CoFe₂O₄) NPs have been studied as signal enhancement agents in MRI because of their large Curie temperature, moderate saturation magnetization and notable magneto-crystalline anisotropy.6,7 Recently, nanocomposites that consist of GO mixed with CoFe₂O₄ NPs were reported.^{8,9} The GO substrate not only anchors the NPs (avoiding aggregation and/or sedimentation) but also has a fairly biocompatible surface.8

> Although GO is a valid supporting matrix, it is chemically reactive (because of the profusion of grafted functional groups). Under physiological conditions, this could represent a liability (e.g. risk of early deactivation). On the other hand, its counterpart, the reduced graphene oxide (rGO), retains the flaky layered structure of GO and is more inert. To the best of our knowledge, there are no reports regarding the proton relaxivity value obtained in CoFe₂O₄-rGO composites. Herein, it is described how the MRI contrast is changed when the oxide loading and the type of graphene are varied in composites of cobalt ferrite nanoparticles grafted to rGO. To do this, the morphology, structure, chemistry, magnetic properties and cytotoxicity of two sets of rGO composites with CoFe₂O₄ loadings comprised between 5-30 wt% were considered.

[&]quot;King Abdullah University of Science and Technology (KAUST), Physical Science and Engineering Division, Thuwal 23955-6900, Saudi Arabia. E-mail: amirh.aalazmy@ kaust.edu.sa; pedro.dacosta@kaust.edu.sa

^bKing Abdullah University of Science and Technology (KAUST), Core Labs, Thuwal, 23955-6900, Saudi Arabia

Smart Hybrid Materials (SHMs) Laboratory, Advanced Membranes and Porous Materials Center, King Abdullah University of Science and Technology, Thuwal 23955-6900, Kingdom of Saudi Arabia

^dUniversity of Hafr Al Batin, University Colleges at Nairiyah, Nairiyah, Saudi Arabia DOI: [†] Electronic supplementary information (ESI) available. See 10.1039/c8ra09476d

2. Experimental

2.1 Synthesis of the GO precursor

The GO was prepared from graphite powder (Alfa Aesar, $<50 \mu$ m) through one of two commonly used chemical processes: the Hummers' (HGO)¹⁰ or the so-called improved Hummers' (IGO)¹¹ method. The hydrothermally reduced GOs were prepared as follows: 100 mg of HGO (or IGO) powder was dispersed in 40 mL of deionized water and stirred for 24 h to form an aqueous dispersion. The mixture was then transferred to a 50 mL Teflon-lined stainless steel autoclave, which was placed in an oven at 180 °C for 24 h. The product was collected, centrifuged and washed several times with deionized water and freeze-dried under reduced pressure (0.133 mbar) for 24 h in a Labconco Free Zone system. The rGO prepared by the Hummers' method is hereafter designated as rHGO, and that prepared by the improved Hummers' method is designated as rIGO.

2.2 Synthesis of the CoFe₂O₄-rGO composites

CoFe₂O₄-rGO composites with metal oxide loadings of 0, 5, 10, 16 and 30 wt% were prepared by a hydrothermal method using water as a solvent. In a typical synthesis procedure, 100 g of HGO (or IGO) was dispersed in 30 mL of water with sonication for 12 h. Stoichiometric amounts of Co(NO₃)₂·6H₂O (Sigma-Aldrich) and Fe(NO₃)₃·9H₂O (Sigma-Aldrich) were added to the GO aqueous dispersion, followed by stirring at room temperature. The pH of the reaction mixture was adjusted to 10 by adding the needed volume of a $NH_3 \cdot H_2O$ solution. The mixture was then transferred to a 50 mL Teflon-lined stainless steel autoclave and kept in an oven at 180 °C for 24 h. The product was collected, centrifuged, washed several times with deionized water and freeze-dried under reduced pressure (0.133 mbar) for 24 h. For reference, pure CoFe₂O₄ NPs were synthesized as follows: 0.5 g of Co(NO₃)₂·6H₂O and 1.37 g of Fe(NO₃)₃·9H₂O were dissolved in 30 mL of water. The pH of the reaction mixture was subsequently adjusted to 10 by adding the needed volume of a $NH_3 \cdot H_2O$ solution. The mixture was then transferred to a 50 mL Teflon-lined stainless steel autoclave and kept in an oven at 180 °C for 24 h. The product was collected, centrifuged, washed several times with deionized water and freeze-dried under reduced pressure (0.133 mbar) for 24 h.

3. Measurements

3.1 Characterization techniques

All composite materials were characterized by X-ray powder diffraction (XRD; Bruker, D8 Advance) with Cu K α radiation (λ_{av} = 1.5418 Å). The morphology and size of the carbonaceous flakes and metal oxide NPs were examined by transmission electron microscopy (TEM; Thermo Fisher Scientific Tecnai BioTwin, 120 keV). SEM micrographs of the powder samples were acquired with a Quanta FEG scanning electron microscope (Thermo Fisher Scientific) operated at 5 kV. Energy-dispersive Xray spectroscopy (EDS) was performed using an EDS Genesis detector (EDAX Inc.). The Fourier transform infrared (FTIR) spectral analyses were carried out with a Thermo Scientific

spectrometer (Nicolet iS10). Raman studies were performed using a WITec Alpha 300 RA spectrometer employing an excitation wavelength of 488 nm. X-ray photoelectron spectroscopy (XPS) studies were carried out in a Kratos Axis Ultra DLD spectrometer equipped with a monochromatic Al Ka X-ray source ($h\nu = 1486.6$ eV) operating at 150 W, a multi-channel plate and delay line detector under a vacuum of $\sim 10^{-9}$ mbar. The survey and high-resolution XPS spectra were collected at fixed analyzer pass energies of 160 eV and 20 eV, respectively. Samples were mounted in floating mode in order to avoid differential charging. Zeta (ζ)-potential analyses were performed using a Malvern Zetasizer Nano ZS instrument. The magnetic properties of the composites were characterized using a superconducting quantum interference device (SQUID)vibrating sample magnetometer (VSM) system (Quantum Design USA) equipped with a highly sensitive (10^{-8} emu) sensor. The magnetization measurements were carried out on powder samples using straw holders by varying the magnetic field from -3 T to +3 T. For the magnetic resonance imaging (MRI) studies, different concentrations of the composites were dispersed in 2% agarose (w/v) gels, whereas a blank gel was used as a reference. The T_2 relaxivity of water protons in the presence of the as-synthesized composites was measured using a Bruker 500SWB spectrometer integrating a superwide-bore 11.7 T magnet resonating at 500 MHz. The relaxivity r_2 is the slope of the line fitted to the $1/T_2$ concentrations (C) plot, which is related to T_2 through eqn (1):

$$\frac{1}{T_2} = \frac{1}{T_2^\circ} + r_2 C \tag{1}$$

where *C* is the contrast agent concentration, T_2 is the observed relaxation time in the presence of the CoFe₂O₄ nanostructures, and T_2° is the relaxation time in the absence of the contrast agent. From eqn (1), T_2 is revealed as a concentrationdependent term. However, r_2 is a concentration-independent term. In fact, a contrast agent with a large r_2 value can shorten the T_2 substantially with a smaller concentration increment. The relaxivity values (r_2) of the water protons were calculated using eqn (1). The Fe concentrations were obtained from inductively coupled plasma optical emission spectrometry (ICP-OES) using a Varian 720-ES spectrometer. Typically, 10 mg of sample powder was mixed in 4 mL of concentrated HNO₃ and 1 mL of H₂O₂ (30%). Subsequently, this mixture was placed in closed Teflon vessels and digested for 40 min with the assistance of microwaves (1000 W, 200 °C).

3.2 In vitro cytotoxicity

HeLa cells were seeded in 96-well plates (6 \times 10³ cells per well) in 100 µL of a Dulbecco's modified Eagle's medium (DMEM) supplemented with 10% foetal bovine serum (FBS) and 1% penicillin–streptomycin at 37 °C in a 5% CO₂ humidified atmosphere for 24 h. After cell attachment, the cells were washed with Dulbecco's phosphate buffer solution (PBS) and incubated at different concentrations (5, 10, 20, 25 and 50 µg mL⁻¹) of rIGO, rHGO, 30 wt% CoFe₂O₄–rHGO and 30 wt% CoFe₂O₄–rIGO in the DMEM for 24 h at 37 °C. The culture

Paper

medium was then discarded, the Cell Counting Kit-8 (CCK)-8 solution was added into the wells, and the plate was incubated for an additional 4 h in darkness. The absorbance values were measured at 450 nm using a microplate spectrophotometer (xMark[™] Microplate Absorbance Spectrophotometer).

4. Results and discussion

4.1 Structural and chemical characterization

First, the shape, size, composition and structure of the spinelstructured ferrite NPs and their respective composites were analysed. A tableau of representative TEM micrographs for the entire set of synthesized materials is shown in Fig. 1. The micrographs of the CoFe₂O₄-rGO composites (Fig. 1a–h) show 5–13 nm NPs distributed randomly on the surface and at the edges of the rGO sheets. In all cases, the presence of C, O, Fe and Co was confirmed by EDS analysis (Fig. SI1⁺). Additionally, the bulk Fe content of each sample was measured with ICP-OES. As expected, the concentration of iron increased as a function of particle loading in the composites, attaining a maximum for the 30 wt% CoFe₂O₄-rIGO (Table SI1[†]). Throughout the set of composites, the morphologies of the substrate sheets (rGO) are similar but the size of the NPs (CoFe₂O₄) differs. The bar charts showing the size distribution were constructed from the statistical analysis of TEM images, with the number of NPs counted exceeding 100. The average particle size (D_{av}) and corresponding standard deviation (σ) are also presented in Fig. 1 and Table SI2.[†] Generally, the CoFe₂O₄ particles grafted onto the flakes grew as the loading concentration increased (from 5 to 30 wt%); this growth occurred irrespective of the type of GO precursor employed. However, for equivalent loadings, the average particle size was smaller in the rHGO composites than



Fig. 1 (a–d) TEM images (inset: NPs size distribution histogram and average size) of the $CoFe_2O_4$ -rHGO composites with 5, 10, 16 and 30 wt% CoFe₂O₄, respectively; (e–h) TEM images (inset: NPs size distribution histogram and average size) of the $CoFe_2O_4$ -rlGO composites with 5, 10, 16 and 30 wt% CoFe₂O₄, respectively; (i) TEM image (inset: NPs size distribution histogram and average size) of the pure CoFe₂O₄ NPs.



Fig. 2 XRD patterns for: (a) $CoFe_2O_4$, rHGO and $CoFe_2O_4$ -rHGO composites with 5, 10, 16 and 30 wt% $CoFe_2O_4$; (b) $CoFe_2O_4$, rIGO and $CoFe_2O_4$ -rIGO composites with 5, 10, 16 and 30 wt% $CoFe_2O_4$.

in the rIGO ones. Following the analysis of oxygen content by XPS (Fig. SI2†), a possible explanation is that the sheets of the IGO precursor contain a greater number of oxygenated groups¹¹⁻¹³ that, upon the reduction reaction, produce a larger amount of gaseous species (more on this later in the text). Higher pressures in the autoclave favour both an increase in the nucleation rate and faster growth kinetics of the $CoFe_2O_4$ NPs.¹⁴ Altogether, as the optimal loading and resulting particle size are concerned, it can be stated that it is not just the metal oxide precursor that is used.

The XRD patterns of the NPs, pure rGOs and their respective composites are presented in Fig. 2. The diffractogram of the CoFe₂O₄ NPs confirms the expected cubic spinel phase (space group 227 or $Fd\bar{3}m$, ICDD card 03-0864). The patterns of the rHGO (Fig. 2a) and rIGO (Fig. 2b) also follow the general profile for these materials.^{15,16} Interestingly, in the case of the composites, the diffractograms of the rHGOs are dominated by the peaks of the carbonaceous matrix, whereas the rIGOs go through an inversion from sheets to particles, upwards from 16 wt% loadings. In fact, for the maximum loading tested (30 wt%), the rIGO peak at $2\theta \approx 25^{\circ}$ becomes overshadowed by those of the grafted NPs (which are similar, in shape and intensity ratios, to the peaks of the standalone NPs). This result concurs with the more localized TEM observations and extends them to the bulk powder. Effectively, the 30 wt% CoFe₂O₄-rIGO composite is the one with the highest loading efficiency and contains NPs whose crystallinity and size match those of the standalone NPs.

To confirm the successful synthesis of the $CoFe_2O_4$ NPs and the structural constancy of the rGOs in the composites, Raman spectra were acquired for all of the samples (Fig. 3). In the spectrum of the standalone particles, a set of bands between 100 cm^{-1} and 750 cm^{-1} were observed, identified as the characteristic peaks of the $CoFe_2O_4$ spinel structure; specifically, the $A_{1g} + E_g + 3T_{2g}$ resonant modes.¹⁷ The spectra of the rGOs had similar profiles, showing the expected D and G bands of disordered carbon. The intensity ratio between these bands differed slightly, with the rIGO showing a more preponderant D band. Likewise, in the spectra of all of the $CoFe_2O_4$ -rGO composites, the D and G bands of the support dominated, with the peaks of the NPs noticeable only in the samples with 30 wt% loading. Interestingly, the frequencies of the D (1328 cm⁻¹) and G (1598 cm⁻¹) bands do not change with loading or type of rGO. However, when inspecting the set of spectra for rHGO, we observed that their intensity ratio changed from the parent flakes to the composites. This change could be due to the hydrothermal synthesis conditions, which may induce additional exfoliation and expose more defects in the graphene lattice.¹¹⁻¹³ Altogether, no visible differences were observed in the Raman spectra of the composites derived from HGO or IGO.

Infrared spectroscopy was used to verify the integrity of the NPs and to identify major variations in the chemical moieties attached to the carbonaceous sheets. As shown in Fig. 4, all of the FTIR spectra (CoFe2O4 NPs included) exhibited a broad peak at approximately 3435 cm⁻¹. This peak corresponds to the -OH stretching vibration, a fingerprint for surface-adsorbed water.18 In the spectrum of the standalone CoFe₂O₄ NPs, the peak at 583 cm⁻¹ is a spectral fingerprint derived from the Fe(Co)-O stretching vibration (it is also observed, at the same frequency, in the spectrum of bulk CoFe₂O₄).¹⁹⁻²² The spectra of the two rGOs are similar. The peak located at \sim 1711 cm⁻¹ is attributed to the C=O stretching vibration,²³ whereas the broad peak at \sim 1564 cm⁻¹ likely originates from the bending vibrations of adsorbed water molecules and the skeletal C=C vibrations of non-oxidized graphitic domains.²⁴⁻²⁷ The peaks at 1222 cm⁻¹ and 1037 cm⁻¹ could belong to the asymmetrical and symmetrical C-O aromatic stretching vibrations of epoxy groups, respectively (the latter could also be derived from a C-N stretch).19,28 A comparison of the two sets of composites reveals that the IR spectral signature is mostly independent of the rGO used. Nonetheless, these results, whilst indicating a bulk-level similarity in the main types of organic moieties grafted onto the carbonaceous sheets, do not preclude variations in surface



Fig. 3 Raman spectra for: (a) rHGO, CoFe₂O₄ and CoFe₂O₄-rHGO composites with 5, 10, 16 and 30 wt% CoFe₂O₄, respectively; (b) rIGO, CoFe₂O₄ and CoFe₂O₄-rIGO composites with 5, 10, 16 and 30 wt% CoFe₂O₄, respectively.

chemistry such as concentration and dispersion of the moieties, as previously shown.¹² Interestingly, for the two 30 wt% rGO composites, the C=O stretching vibration is suppressed, whereas the NPs signature peak becomes quite prominent.

Taken together, the TEM and XRD analyses show clear trends in the composite samples as the density and size of NPs differed with the type of rGO. However, the vibrational spectroscopy studies (Raman and FTIR) did not identify variations as a function of the rGO used. In these circumstances, the concentration, dispersion and sterical availability of grafted functional groups such as hydroxyl, epoxy, and carboxylic acid groups (which are commonly found on the surface and edges of GO sheets)27,29,30 are the main reason for the observed variations. This explanation concurs with our previous observation of a greater degree of surface oxidation and specific surface area for the rIGO powder.12 With respect to the suppression of the C=O mode in the composites with the highest $CoFe_2O_4$ loading (cf. FTIR spectra), these organic moieties can plausibly act as preferential anchor sites to nucleate the NPs. One possible mechanism is the formation of carboxylate anions (due to the addition of aqueous NH3 to adjust the pH to 10) which localizes the negative charge needed to trap the divalent transition metal ion, Co²⁺.^{19,29} With prolonged exposure to heat, the greater concentration of organic moieties at the rIGO surface results in more ammonium that boils and contributes to pressure buildup in the autoclave. This increase in pressure favours the kinetics of spinel formation explaining the faster growth rates and larger average size of the NPs in the rIGO composites.

4.2 Magnetic properties

Surface and finite-size effects play a key role in the magnetic properties of NPs.^{31,32} Given that a direct correlation of magnetization and particle size has been reported in several ferrite systems,³³⁻³⁵ establishing this effect for the present composites is important. The magnetic properties of the standalone CoFe2O4 NPs, the rGOs and the CoFe2O4-rGO composites were studied at room temperature using magnetic field strengths in the range from $-30\,000$ Oe to $30\,000$ Oe (Fig. 5 and SI3[†]). The field-dependent magnetization hysteresis (M vs. H) measurements show that the standalone NPs are ferromagnetic (Fig. 5a). The saturation magnetization (M_s) is approximately 56 emu g^{-1} , which agrees well with the value reported in the literature.³⁶ By contrast, the blank rGOs are diamagnetic (Fig. SI4[†]). With respect to the various CoFe₂O₄-rGO composites, and in addition to the curves in Fig. 5b and c, the magnetization at 30 000 Oe $(M_{H=30\ 000\ Oe})$ and coercivity (H_c) are summarized in Table SI3.[†] On the whole, the $M_{\rm H=30\ 000\ Oe}$ and H_c values obtained for the CoFe₂O₄-rIGO composites were consistently higher than those for the corresponding rHGOs. Furthermore, most of the composites showed negligible remanence (M_r) and H_c , implying a superparamagnetic response. The exceptions were the CoFe2O4-rIGO powders with the two highest ferrite loadings. For these samples, ferromagnetism was identified, along with relatively large H_c values of 87 Oe and 97 Oe for the 16 wt% and 30 wt% loadings, respectively. Finally, the combined results for the field-dependent magnetization and the average ferrite particle size in each composite confirm the

6



Fig. 4 FTIR spectra for: (a) rHGO, $CoFe_2O_4$ and $CoFe_2O_4$ -rHGO composites with 5, 10, 16 and 30 wt% $CoFe_2O_4$; (b) rIGO, $CoFe_2O_4$ and $CoFe_2O_4$ -rIGO composites with 5, 10, 16 and 30 wt% $CoFe_2O_4$.

aforementioned magnetization-size correlation for the two rGO sets (Fig. SI5[†]).

To further understand the correlation of magnetization to particle size/loading and to explain the superparamagnetic-toferromagnetic transition observed in the $CoFe_2O_4$ -rIGO composites, temperature-dependent magnetization data were acquired under zero-field-cooled (ZFC) and field-cooled (FC) conditions (Fig. 6). Initially, each sample was cooled under a nominal zero field to 5 K. Then, a 1 kOe field was applied. The magnetization data (ZFC) were collected as the sample was warmed to 300 K, and the FC data were collected as the sample was cooled to 5 K (at 1 kOe). A substantial separation between the ZFC and FC curves was observed for the composite samples. The peak in the ZFC curve (Fig. 6a) denotes the average blocking temperature ($T_{\rm B}$). In the case of the rHGO composites (Fig. 6a-d), the $T_{\rm B}$ value increases linearly with CoFe₂O₄ loading (71 K, 105 K, 133 K and 215 K for the 5 wt%, 10 wt%, 16 wt% and 30 wt%, respectively) but remains well below room temperature. For the rIGO composites (Fig. 6e–h), the $T_{\rm B}$ increases from the sample with 5 wt% (135 K) to the sample with 10 wt% loading (179 K). However, at higher loadings, the blocking disappears and the ZFC-FC curves resemble that of the standalone CoFe₂O₄ NPs (Fig. 6i). Overall, when comparing the $T_{\rm B}$ obtained (where applicable) with the loadings and the average size of NPs



Fig. 5 Field-dependent magnetic hysteresis loops for: (a) pure $CoFe_2O_4$ NPs, (b) $CoFe_2O_4$ -rHGO composites and (c) $CoFe_2O_4$ -rHGO composites, measured at room temperature.

0C) BY-NC





Fig. 6 The ZFC-FC curves for the rHGO (panels a-d) and rIGO (panels e-h) composites with increased loading of CoFe₂O₄. Reference data for the pure CoFe₂O₄ powder are shown in panel (i). The average blocking temperature (T_B), which is the peak of the ZFC curve, is indicated by an arrow in panel (a).



Fig. 7 Plot correlating the $CoFe_2O_4$ loading with the average particle size and respective magnetization at 30 000 Oe for the two rGOs studied.

in the two sets of rGO composites, a linear correlation is inferred between $T_{\rm B}$ and the size of the CoFe₂O₄ particles.

The critical size for the single-to-multidomain magnetic transition of a nanoparticle (r_0) can be calculated by $r_0 = (6k_BT_B/C_B)$

 $(K)^{1/3}$, where $k_{\rm B}$ is the Boltzmann constant, $T_{\rm B}$ is the maximum blocking temperature, and K is the anisotropy constant. For CoFe₂O₄, the reported critical size is \sim 10 nm.³⁷ The ZFC-FC curves in Fig. 6 show that the critical size was not attained for the rHGO composites because a $T_{\rm B}$ is still observed for the highest loading (30 wt%). This behaviour contrasts to that of the rIGO composites, where a critical size of 9.4 nm was identified for the 16 wt% loading (cf. absence of a $T_{\rm B}$). Conceivably, the true r_0 may be smaller because no loadings in the interval 10-16 wt% (7.5-9.4 nm) were tested. Irrespective of the exact value for the critical particle size, the threshold for the transition from a single-domain to a multi-domain structure is a function of the CoFe₂O₄ loading and the type of rGO used, being surpassed only for two of the CoFe₂O₄-rIGO powders (Fig. 7). These results explain the superparamagnetic-to-ferromagnetic transition observed in the set of rIGO composites.

4.3 Magnetic resonance imaging

Superparamagnetic and ferromagnetic particles have been reported to similarly influence MRI contrast enhancement.³⁸ Given the aforementioned observations (where both responses were observed), the T_2 -weighted magnetic resonance (MR) signal intensity of the standalone NPs and the two sets of composites were analysed. Different concentrations (0.0 to 0.2



Fig. 8 T₂-weighted MRI images for: (a) CoFe₂O₄-rHGO composites, (b) CoFe₂O₄-rIGO composites and (c) pure CoFe₂O₄, at different Fe concentrations.

mM) of these samples in agarose gel were studied at room temperature. The T_2 -weighted images in Fig. 8 clearly show that the MRI signal intensity is related to the concentration of iron, irrespective of the type of sample (darker images correspond to a decrease in the T_2 -weighted MR signal intensity). However, the contrast enhancement effect is particularly strong for the composites. Given the previously established correlation between the loading and average size of NPs, it is clear that the MR signal is dependent on the size of the NPs in the CoFe₂O₄rGO composites.

Proton relaxivity (r_2) values were obtained from the slope of the line fitted to the $1/T_2$ versus Fe concentration plot (Fig. 9). The r_2 value of the standalone CoFe₂O₄ NPs was 112.4 mM⁻¹ $\rm S^{-1}.$ For the CoFe₂O₄–rHGO composites, the r_2 values were 8.8 mM^{-1} S⁻¹ (5 wt% CoFe₂O₄ loading), 16.7 mM⁻¹ S⁻¹ (10 wt%), 33.7 mM⁻¹ S⁻¹ (16 wt%) and 55.6 mM⁻¹ S⁻¹ (30 wt%). The r_2 values of the CoFe₂O₄-rIGO composites were 17.4 mM⁻¹ S⁻¹ (5 wt%), 21.4 mM⁻¹ S⁻¹ (10 wt%), 43.6 mM⁻¹ S⁻¹ (16 wt%) and 102.1 mM⁻¹ S⁻¹ (30 wt%). The rIGO composites consistently showed higher r_2 values than the corresponding rHGO composites. These results demonstrate that the r_2 values depend not only on the CoFe₂O₄ loading but also on the type of GO precursor selected. Remarkably, the r_2 of the 30 wt% CoFe₂O₄-rIGO composite is almost that of the standalone NPs. This result indicates that similar MRI contrast enhancement can be obtained despite the lower mass of ferrite present in the composite (1.7 mmole for the standalone CoFe₂O₄ against 0.55 mmole used to make the 30 wt% CoFe₂O₄-rIGO composite). Also of note, this r_2 value is comparable to those of Fe-based commercial contrast agents such as Feridex® and Resovist® (see Table SI4[†] for a literature comparison of proton relaxivity values and corresponding particle sizes). Finally, to ensure that



Fig. 9 Plot of the T_2 relaxation rate $r_2(1/T_2)$ for: (a) pure CoFe₂O₄, (b) CoFe₂O₄-rHGO composites and (c) CoFe₂O₄-rIGO composites, suspended in aqueous solution at different Fe concentrations.

(00)



Fig. 10 (a) Plot of the relaxivity coefficient r₂ vs. M_s, *i.e.*, magnetic saturation. (b) Plot of the relaxivity coefficient vs. magnetic nanostructure size.

the composites had a negative T_2 -type of response, the $1/T_1$ values were plotted as a function of different concentrations of Fe (Fig. SI6†). Irrespective of considering the standalone or the composite samples, the r_1 relaxivity is negligible (and practically constant) when compared to r_2 .

Because loading and particle size are related in the CoFe2O4rGO composites, a plot was constructed to show how the r_2 values differ with size of the NPs (Fig. 10a). For both sets, a direct correlation is observed (*i.e.*, r_2 increases with increasing particle size), which corroborates previous claims.^{39,40} This size dependence is speculated to originate from surface spin anisotropy, a phenomenon that is more pronounced for smaller particles (due to the larger surface-area-to-volume ratios).41 Comparing the saturation magnetization (M_s) results obtained from the field-dependent magnetization measurements with the r_2 values of the composites is also informative. Similar to previously reported behaviours,⁴² higher M_s values lead to more pronounced proton relaxivity (Fig. 10b). Taken together, the r_2 is related to the M_s which, in turn, is affected by the size of the $CoFe_2O_4$ particles (that grow larger in the rIGO). The optimization of proton relaxivity (r_2) is therefore also a function of the GO precursor.

4.4 In vitro cytotoxicity

It is known that surface charge and the aggregation state of nanomaterials critically influence their in vitro cytotoxicity. Prior to the cell viability studies, the integrity of the composite materials in solution was tested. As shown in Table SI5,† the zeta (ζ)-potentials of the 30 wt% CoFe₂O₄-rHGO and 30 wt% CoFe₂O₄-rIGO composites were negative, with absolute values ranging from 30-40 mV. These figures imply a moderate to good stability of the dispersions, the rIGO composites having a slightly better dispersion degree. As per the high-resolution O1s XPS peak analysis (Fig. SI2[†]), this may be explained by the higher content of oxygen in the rIGO sample when compared to the rHGO one. Also from Table SI5,[†] note that the samples maintain similar ζ-potentials in aqueous phosphate buffered saline (PBS) for 24 h. To further estimate the aging behavior of these two composites in a PBS solution, visual inspection of settling over 24 h, and at room temperature, was carried out. At a concentration of 70 μ g mL⁻¹, the two samples showed excellent colloidal dispersity and stability (Fig. SI7[†]). We attribute this to their highly negative surface charge (electrostatic stabilization), which is consistent with the ζ -potentials



Fig. 11 Viability of HeLa cells in different concentrations of: (a) rHGO/rIGO and (b) CoFe₂O₄-rHGO/CoFe₂O₄-rIGO.

measurements (Table SI5[†]). Adding to this, the microscopical inspection of the composites, after 24 h in the physiologic solution, did not reveal noticeable changes to the materials from their initial state (Fig. SI8[†]).

Safety and toxicity are major concerns when considering the deployment of new MRI contrast agents. To evaluate the *in vitro* cytotoxicity of the rGOs and their composites with the highest $CoFe_2O_4$ loading (30 wt%), the viability of cells exposed to these materials was investigated using CCK-8 assays on HeLa cell lines. As shown in Fig. 11a, increasing the rGO concentration resulted in an overall decrease of cell viability. However, no statistically meaningful difference was observed between the two types of rGO used. Similar observations were made for the composite samples (Fig. 11b). It is noteworthy that the $CoFe_2O_4$ -rGO composites showed 80% cell viability at a concentration of 50 µg mL⁻¹. This corroborates the low cytotoxicity expected for these hybrid systems.

5. Conclusions

 $CoFe_2O_4$ -rGO composites were prepared to enhance the contrast and proton relaxivity coefficient for MRI. The effect of using different GO precursors bearing various concentrations of $CoFe_2O_4$ was studied. The type of GO and the loading of ferrite NPs play significant roles in tailoring the average particle size and magnetic properties of the composites. The 30 wt% $CoFe_2O_4$ -rIGO sample showed the highest proton relaxivity value (102.1 mM⁻¹ S⁻¹) amongst all of the investigated composites. In fact, some of the properties measured were similar in magnitude and manner to those of the standalone NPs despite the smaller mass of $CoFe_2O_4$ present in the composites.

Conflicts of interest

There are no conflicts of interest to declare.

Acknowledgements

We are thankful for the financial support from KAUST (BAS/1/ 1346-01-01 and URF/1/3001-01-01). The technical support from the Core Labs at KAUST is appreciated. The TOC figure was created by Heno Hwang, scientific illustrator at KAUST.

References

- 1 A. G. Kolhatkar, A. C. Jamison, D. Litvinov, R. C. Willson and T. R. Lee, Tuning the magnetic properties of nanoparticles, *Int. J. Mol. Sci.*, 2013, **14**(8), 15977–16009.
- 2 C. Sun, J. S. H. Lee and M. Zhang, Magnetic nanoparticles in MR imaging and drug delivery, *Adv. Drug Delivery Rev.*, 2008, **60**(11), 1252–1265.
- 3 A. H. Lu, E. e. L. Salabas and F. Schüth, Magnetic nanoparticles: synthesis, protection, functionalization, and application, *Angew. Chem., Int. Ed.*, 2007, **46**(8), 1222–1244.
- 4 V. Georgiadou, C. Kokotidou, B. Le Droumaguet, B. Carbonnier, T. Choli-Papadopoulou and C. Dendrinou-

Samara, Oleylamine as a beneficial agent for the synthesis of CoFe2O4 nanoparticles with potential biomedical uses, *Dalton Trans.*, 2014, **43**(17), 6377–6388.

- 5 K.-H. Choi, K. C. Nam, L. Malkinski, E. H. Choi, J.-S. Jung and B. J. Park, Size-Dependent Photodynamic Anticancer Activity of Biocompatible Multifunctional Magnetic Submicron Particles in Prostate Cancer Cells, *Molecules*, 2016, 21(9), 1187.
- 6 S. Amiri and H. Shokrollahi, The role of cobalt ferrite magnetic nanoparticles in medical science, *Mater. Sci. Eng.*, *C*, 2013, 33(1), 1–8.
- 7 E. Mendonça, M. A. Tenório, S. Mecena, B. Zucolotto, L. Silva, C. Jesus, C. Meneses and J. Duque, Intrinsic dependence of the magnetic properties of CoFe2O4 nanoparticles prepared via chemical methods with addition of chelating agents, *J. Magn. Magn. Mater.*, 2015, 395, 345–349.
- 8 G. Wang, Y. Ma, Z. Wei and M. Qi, Development of multifunctional cobalt ferrite/graphene oxide nanocomposites for magnetic resonance imaging and controlled drug delivery, *Chem. Eng. J.*, 2016, **289**, 150–160.
- 9 N. Venkatesha, R. Ashwini, P. Poojar, S. Geethanath and C. Srivastava, High Value of Proton Relaxivity Achieved by Graphene Oxide-Cobalt Ferrite Nanoparticle Composite: A Potential Contrast Agent in Magnetic Resonance Imaging, *J. Indian Inst. Sci.*, 2014, **94**(4), 415–422.
- 10 N. A. Kumar, H.-J. Choi, Y. R. Shin, D. W. Chang, L. Dai and J.-B. Baek, Polyaniline-grafted reduced graphene oxide for efficient electrochemical supercapacitors, *ACS Nano*, 2012, 6(2), 1715–1723.
- 11 D. C. Marcano, D. V. Kosynkin, J. M. Berlin, A. Sinitskii, Z. Sun, A. Slesarev, L. B. Alemany, W. Lu and J. M. Tour, Improved Synthesis of Graphene Oxide, *ACS Nano*, 2010, 4(8), 4806–4814.
- 12 S. Rasul, A. Alazmi, K. Jaouen, M. N. Hedhili and P. Costa, Rational design of reduced graphene oxide for superior performance of supercapacitor electrodes, *Carbon*, 2017, 111, 774–781.
- 13 A. Alazmi, O. El Tall, M. N. Hedhili and P. M. Costa, The impact of surface chemistry and texture on the CO2 uptake capacity of graphene oxide, *Inorg. Chim. Acta*, 2018, **482**, 470–477.
- 14 M. Y. Rafique, L. Pan, M. Z. Iqbal and L. Yang, Influence of NaBH4 on the size, composition, and magnetic properties of CoFe2O4 nanoparticles synthesized by hydrothermal method, *J. Nanopart. Res.*, 2012, **14**(10), 1189.
- 15 A. Alazmi, S. Rasul, S. P. Patole and P. M. Costa, Comparative study of synthesis and reduction methods for graphene oxide, *Polyhedron*, 2016, **116**, 153–161.
- 16 A. Alazmi, O. El Tall, S. Rasul, M. N. Hedhili, S. P. Patole and P. M. Costa, A process to enhance the specific surface area and capacitance of hydrothermally reduced graphene oxide, *Nanoscale*, 2016, **8**(41), 17782–17787.
- 17 P. R. Kumar, P. Kollu, C. Santhosh, K. Eswara Varaprasada Rao, D. K. Kim and A. N. Grace, Enhanced properties of porous CoFe2O4-reduced graphene oxide composites with

alginate binders for Li-ion battery applications, *New J. Chem.*, 2014, **38**(8), 3654–3661.

- 18 Z. Wang, X. Zhang, Y. Li, Z. Liu and Z. Hao, Synthesis of graphene–NiFe2O4 nanocomposites and their electrochemical capacitive behavior, *J. Mater. Chem. A*, 2013, 1(21), 6393.
- 19 P. He, K. Yang, W. Wang, F. Dong, L. Du and Y. Deng, Reduced graphene oxide-CoFe2O4 composites for supercapacitor electrode, *Russ. J. Electrochem.*, 2013, **49**(4), 359–364.
- 20 X. Lu, L. Yang, X. Bian, D. Chao and C. Wang, Rapid, Microwave-Assisted, and One-Pot Synthesis of Magnetic Palladium–CoFe2O4–Graphene Composite Nanosheets and Their Applications as Recyclable Catalysts, *Part. Part. Syst. Charact.*, 2014, **31**(2), 245–251.
- 21 Z. Song, W. Ran and F. Wei, One-step approach for the synthesis of CoFe2O4@ rGO core-shell nanocomposites as efficient adsorbent for removal of organic pollutants, *Water Sci. Technol.*, 2017, **75**(2), 397–405.
- 22 R. D. Waldron, Infrared Spectra of Ferrites, *Phys. Rev.*, 1955, **99**(6), 1727–1735.
- 23 M. Naebe, J. Wang, A. Amini, H. Khayyam, N. Hameed, L. H. Li, Y. Chen and B. Fox, Mechanical Property and Structure of Covalent Functionalised Graphene/Epoxy Nanocomposites, *Sci. Rep.*, 2014, **4**, 4375.
- 24 Z. Ji, X. Shen, Y. Song and G. Zhu, In situ synthesis of graphene/cobalt nanocomposites and their magnetic properties, *Mater. Sci. Eng.*, *B*, 2011, **176**(9), 711–715.
- 25 Y. Xu, H. Bai, G. Lu, C. Li and G. Shi, Flexible Graphene Films via the Filtration of Water-Soluble Noncovalent Functionalized Graphene Sheets, *J. Am. Chem. Soc.*, 2008, **130**(18), 5856–5857.
- 26 C. Galande, A. D. Mohite, A. V. Naumov, W. Gao, L. Ci, A. Ajayan, H. Gao, A. Srivastava, R. B. Weisman and P. M. Ajayan, Quasi-Molecular Fluorescence from Graphene Oxide, *Sci. Rep.*, 2011, 1, 85.
- 27 B. Shatabda, M. Ramaprasad, S. Moni Baskey, S. Shyamal Kumar and C. Dipankar, Anomalous enhancement in the magnetoconductance of graphene/CoFe 2 O 4 composite due to spin-orbit coupling, *J. Phys. D: Appl. Phys.*, 2015, 48(43), 435002.
- 28 S. Park, K.-S. Lee, G. Bozoklu, W. Cai, S. T. Nguyen and R. S. Ruoff, Graphene Oxide Papers Modified by Divalent Ions—Enhancing Mechanical Properties via Chemical Cross-Linking, ACS Nano, 2008, 2(3), 572–578.
- 29 S. Chen, J. Zhu, X. Wu, Q. Han and X. Wang, Graphene Oxide–MnO2 Nanocomposites for Supercapacitors, *ACS Nano*, 2010, 4(5), 2822–2830.

- 30 C. Xu, X. Wang, J. Zhu, X. Yang and L. Lu, Deposition of Co3O4nanoparticles onto exfoliated graphite oxide sheets, *J. Mater. Chem.*, 2008, 18(46), 5625–5629.
- 31 J. M. D. Coey, Noncollinear spin arrangement in ultrafine ferrimagnetic crystallites, *Phys. Rev. Lett.*, 1971, 27(17), 1140.
- 32 B. Martinez, A. Roig, X. Obradors, E. Molins, A. Rouanet and C. Monty, Magnetic properties of γ -Fe2O3 nanoparticles obtained by vaporization condensation in a solar furnace, *J. Appl. Phys.*, 1996, **79**(5), 2580–2586.
- 33 J. Chen, C. Sorensen, K. Klabunde, G. Hadjipanayis, E. Devlin and A. Kostikas, Size-dependent magnetic properties of MnFe2O4 fine particles synthesized by coprecipitation, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1996, 54(13), 9288.
- 34 K. V. Shafi, A. Gedanken, R. Prozorov and J. Balogh, Sonochemical preparation and size-dependent properties of nanostructured CoFe2O4 particles, *Chem. Mater.*, 1998, 10(11), 3445–3450.
- 35 A. Morr and K. Haneda, Magnetic structure of small NiFe2O4 particles, *J. Appl. Phys.*, 1981, **52**(3), 2496–2498.
- 36 H. M. Joshi, Y. P. Lin, M. Aslam, P. V. Prasad, E. A. Schultz-Sikma, R. Edelman, T. Meade and V. P. Dravid, Effects of Shape and Size of Cobalt Ferrite Nanostructures on Their MRI Contrast and Thermal Activation, *J. Phys. Chem. C*, 2009, **113**(41), 17761–17767.
- 37 M. Colombo, S. Carregal-Romero, M. F. Casula, L. Gutiérrez, M. P. Morales, I. B. Böhm, J. T. Heverhagen, D. Prosperi and W. J. Parak, Biological applications of magnetic nanoparticles, *Chem. Soc. Rev.*, 2012, 41(11), 4306–4334.
- 38 C. Rümenapp, B. Gleich and A. Haase, Magnetic Nanoparticles in Magnetic Resonance Imaging and Diagnostics, *Pharm. Res.*, 2012, 29(5), 1165–1179.
- 39 H. M. Joshi, Y. P. Lin, M. Aslam, P. Prasad, E. A. Schultz-Sikma, R. Edelman, T. Meade and V. P. Dravid, Effects of shape and size of cobalt ferrite nanostructures on their MRI contrast and thermal activation, *J. Phys. Chem. C*, 2009, **113**(41), 17761–17767.
- 40 Y.-w. Jun, Y.-M. Huh, J.-s. Choi, J.-H. Lee, H.-T. Song, K. Kim, S. Yoon, K.-S. Kim, J.-S. Shin, J.-S. Suh and J. Cheon, Nanoscale Size Effect of Magnetic Nanocrystals and Their Utilization for Cancer Diagnosis via Magnetic Resonance Imaging, J. Am. Chem. Soc., 2005, 127(16), 5732–5733.
- 41 F. Liu, S. Laurent, A. Roch, L. V. Elst and R. N. Muller, Sizecontrolled synthesis of CoFe2O4 nanoparticles potential contrast agent for MRI and investigation on their sizedependent magnetic properties, *J. Nanomater.*, 2013, **2013**, 127.
- 42 Y.-w. Jun, J.-w. Seo and J. Cheon, Nanoscaling Laws of Magnetic Nanoparticles and Their Applicabilities in Biomedical Sciences, *Acc. Chem. Res.*, 2008, 41(2), 179–189.