RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2019, 9, 6152

Received 13th December 2018 Accepted 22nd January 2019

DOI: 10.1039/c8ra10238d

rsc.li/rsc-advances

1 Introduction

Titanium dioxide (TiO₂) is a conventional photocatalyst widely used for the degradation of organic pollutants in wastewater, because of its powerful oxidizing power, high benefit-to-cost ratio, nontoxicity, and its extended stability against photoand chemical corrosion.¹ However, TiO₂ can be activated only under UV-light irradiation due to its wide bandgap ($E_g = 3.2 \text{ eV}$ for anatase TiO₂), which might hinder its practical application.² To improve the utilization of solar light, a lot of researchers have shown that doping TiO₂ with non-metal elements such as C, N, F, S and B could be an effective strategy.³⁻⁷ In order to further achieve photocatalytic activity, co-doping TiO₂ with two or three non-metal elements has attracted much attention, such as N-F,^{5,8} N-B,⁹ C-N,¹⁰ S-N,^{11,12} S, N and C,^{3,13} and so on. Density functional theory (DFT) calculations have shown that the doping S, N elements could lower the band gap of TiO₂ effectively.14 Our previous work12 also proved that a S-N co-doped anatase nanosized TiO₂ photocatalyst exhibited a high activity for the decomposition of methyl orange under both UV-light and Vis-light irradiation comparing to S-doped TiO2 and undoped TiO₂ due to the synergetic effects induced by N and S co-doping.

Preparation of S–N co-doped CoFe₂O₄@rGO@TiO₂ nanoparticles and their superior UV-Vis light photocatalytic activities

Fengyu Wei, 匝 * Hui Wang, Wei Ran, Tao Liu and Xueting Liu

A S–N co-doped CoFe₂O₄@rGO@TiO₂ (CFGT-S/N) nanocomposite was successfully synthesized via a facile vapor-thermal method. XRD, XPS, FT-IR and FETEM results confirmed that N and S were codoped into the lattice of TiO₂. Photocatalytic tests indicated that CFGT-S/N exhibited excellent UV-Vis photocatalytic activity for decompositions of different organic dyes, including methyl orange (MO), rhodamine B (RhB) and methylene blue (MB). Particularly, the photocatalytic degradation rate of MO was about 33% higher than that when using P25 under visible light irradiation. The higher UV-Vis light photocatalytic activity of CFGT-S/N can be attributed to the synergetic effects of the strong absorption of visible light, the narrow band gap, improved separation of photo-generated electron/hole pairs, and the enhancement of the enrichment of pollutant dye molecules by S, N co-doping, CoFe₂O₄ and rGO. Moreover, this photocatalyst was superparamagnetic, which enables it to be easily recovered by an external magnetic field, and maintained stable photocatalytic efficiency over five cycles. Hence, CFGT-S/ N with its highly efficient, recoverable and stable photocatalytic properties shows great potential for environmental treatment.

> In recent years, graphene has attracted much attention because it is an ideal electron acceptor for nanocomposites during the photocatalytic process, which can slow the recombination of photoexcited electron–hole pairs, increasing the charge transfer rate of electrons.^{15,16} What is more, the high surface area of graphene based on nanocomposites can provide more active sites to adsorb reactant molecules. Many researchers have indicated that graphene–TiO₂ hybrid materials exhibited enhanced photoactivity over bare TiO₂ during decomposition of organic dyes in water.^{17–19}

> Although the photocatalytic performance of graphene-TiO₂ nanocomposites has improved, separation and recycling is still a major bottleneck for their application. To solve the separation of the catalyst, a method to integrate graphene-TiO₂ with magnetic nanocomposites, such as Fe₃O₄,^{17,20} CoFe₂O₄,²¹ ZnFe₂O₄,²² and so on, was proposed, which enables recycling and removal of the magnetic particles by an external magnetic field. Wherein, cobalt ferrite (CoFe₂O₄) with a spinel crystallographic structure and a narrow band-gap exhibited a superior magnetic behavior and visible light response.^{21,23-25} But these TiO₂ and magnetic nanoparticles loaded on the surface of graphene sheets may have the defects of detachment and could not effectively prevent photodissolution and recombination of electron-hole pairs, which decreases their photocatalytic activity.^{26,27} Recently, Yang et al.²⁸ synthesized a ternary nanocomposite with TiO₂ nanoparticles anchored on reduced graphene oxide (rGO)-encapsulated Fe₃O₄ spheres (Fe₃O₄@rGO@TiO₂) by an electrostatic layer-by-layer method.

Anhui Province Key Laboratory of Advanced Catalytic Materials and Reaction Engineering, School of Chemistry and Chemical Engineering, Hefei University of Technology, Hefei 230009, P. R. China. E-mail: weifyliuj@hfut.edu.cn; Fax: +86 551 62901548; Tel: +86 551 62901548

The results showed that the three components of Fe_3O_4 rGO@TiO₂ possessed synergistic effect, and the catalyst exhibited enhancing catalytic activity for the degradation of MB. However, its preparation was more complicated, and visible light activity was high only in the presence of H_2O_2 .

Recently, our group has prepared a magnetic $CoFe_2O_4$ (a)rGO core-shell nanocomposite as an efficient adsorbent for removal of organic pollutants, which had excellent adsorption properties and selectivity.²⁹ On this basis, we provided a facile and feasible way to synthesize S and N co-doped CoFe₂O₄(a)rGO(a)TiO₂ composites, which possessed excellent photocatalytic activity under both ultraviolet and visible light irradiation. Physical and chemical characterizations of catalysts were conducted, and the photocatalytic activity was evaluated in the photocatalytic degradation of organic dyes. This work may be helpful for preparing novel UV-light and Vislight photocatalysts with good performance and recoverable ability.

2 Experimental

2.1 Materials and chemicals

Graphite powder, ethylene glycol (EG), polyethylene 2000 (PEG 2000), anhydrous ferric chloride (FeCl₃), cobalt(π) chloride hexahydrate (CoCl₂·6H₂O), sodium acetate (NaAc), tetrabutyltitanate (TBOT), thiourea, methylene blue, methylene orange, rhodamine B and other reagents were purchased from Sinopharm Group Chemical Reagent Co (China). All chemicals used were analytical grade and were used without further purification.

2.2 Preparation of the S, N co-doped CoFe₂O₄@rGO@TiO₂ nanocomposite

Graphene oxide was prepared by a modified Hummers method.³⁰ The preparation of the binary core-shell composites CoFe₂O₄@rGO (CFG) using a one-step hydrothermal method has been reported by our laboratory.29 The S-N codoped CoFe2O4@rGO@TiO2 nanocomposite was synthesized via the vapor-thermal method20 with minor modifications. Briefly, 0.8 mL of TBOT and 60 mg of thiourea were added into 10 mL ethanol, and then the beaker was placed in an ultrasonic bath to completely dissolve the resulting mixture. After that, 50 mg of the as-prepared CFG was added into the above clear solution with the help of ultrasound for two hours, and then the suspension was transferred into a 25 mL beaker, which was placed into a 100 mL stainless steel autoclave with a Teflon-liner filled with de-ionized water. The autoclave was heated to 180 °C and kept for 36 h. During the reaction, the de-ionized water vaporized and led to TBOT hydrolysis. At the end of the reaction, the autoclave was cooled to ambient temperature, and the precipitate obtained was repeatedly washed with de-ionized water and ethanol, and then dried at 60 °C in a vacuum oven for 8 h. Furthermore, undoped CoFe2O4@rGO@TiO2 (CFGT) was synthesized as above without thiourea.

2.3 Characterization

X-ray powder diffraction (XRD) was used to characterize the phase structures and particle sizes of the as-prepared samples, using a Rigaku D/max 2500 pc X-ray diffractometer with Cu Ka radiation ($\lambda = 1.54056$ Å) at a scan rate of 0.02° s⁻¹. The morphology and structure of the catalysts were examined by field emission transmission electron microscopy (HRTEM, JEM-2100F, Japan). Fourier transform infrared (FT-IR) spectra on KBr pellets of the samples were recorded on a PE-100 FT-IR spectrometer at a resolution of 4 cm⁻¹. Diffuse reflectance spectra (DRS) of samples were obtained using a Varian Cary 5000 spectrometer equipped with a Cary Labsphere DRA-CA-301 DR accessory. Photocurrent density was measured by a CHI electrochemical analyzer (CHI 660e, China) in a standard three-electrode configuration, with the working electrode (an effective area of 2 cm²), a platinum foil as the counter electrode, and a saturated calomel electrode (SCE) as the reference electrode. Na₂SO₄ (0.01 M) was used as the electrolyte. X-ray photoelectron spectroscopy (XPS) was conducted with an ESCALAB250 (Vacuum Generators) spectrometer using monochromatized Al K X-rays (150 W). The magnetic properties of the samples were determined by a vibrating sample magnetometer (VSM, Lake Shore 7410, USA) at a temperature of 300 K.

2.4 Photocatalytic experiments

The photocatalytic performance of the as-prepared samples was evaluated by measuring the decomposition of a 5 mg L^{-1} organic dyes aqueous solution. UV-light photocatalytic experiments were carried out in a homemade jacketed reactor with a 25 W low-pressure mercury lamp as the UV-light source, and the light intensity was 80 μ W cm⁻². 0.18 g of the as-prepared sample was dispersed in 900 mL of the aqueous dye solution. The Vis-light photocatalytic experiments were carried out in a 250 mL jacketed reactor under a 300 W Xe lamp with a filter to remove light of wavelengths below 420 nm as the Vis-light source, and the light intensity is 240 mW cm⁻². 0.08 g of the as-prepared sample was dispersed in 100 mL of the aqueous dye solution. Prior to photocatalytic experiments, the catalysts were settled in suspension for 30 min in the dark for the adsorption equilibrium. The concentration of the organic dye solution was quantified by a Shimadzu UV-2550 (Japan) spectrophotometer at the maximum absorption wavelength of different dyes (λ_{max} $(MO) = 464 \text{ nm}, \lambda_{max} (MB) = 663 \text{ nm and } \lambda_{max} (RhB) = 554 \text{ nm}).$ To evaluate the photocatalyst stability, CFGT-S/N were magnetically separated, washed, dried, and reused for the next cycle under the same conditions. The used CFGT-S/N after five cycles was named CFGT-S/N-5. The quenching tests of the active species for the photoreaction were carried out by using different scavengers. The photocatalytic reaction rate constants (k) used the pseudo-first-order model as expressed as eqn (1)

$$\ln(C/C_0) = -kt \tag{1}$$

where C and C_0 were the actual and initial concentrations of the MO solution, respectively, and k was the apparent reaction rate

constant. To ensure the accuracy of the experiment, each experiment was carried out three times.

3 Results and discussion

3.1 XRD analysis and FT-IR measurements

The XRD patterns of CFG, CFGT, CFGT-S/N and CFGT-S/N-5 are shown in Fig. 1(a). It can be easily found that the diffraction peaks of CFG at $2\theta = 30.0^{\circ}$, 35.4° , 43.5° , 57.2° and 62.7° matched the reflections of (220), (311), (400), (511) and (440), respectively, corresponding to the cubic spinel structure of CoFe₂O₄ (JCPDS #79-1744).³¹ No apparent diffraction peaks of GO were observed. This was because the crystal growth of CoFe₂O₄ between the interlayer of GO destroyed the regular layer stacking, leading to the exfoliation of GO and the disappearance of the (001) diffraction peak during the hydrothermal reaction.³² After coating with a TiO₂ layer, a new crystalline phase of anatase TiO₂ (JCPDS #21-1272) occurred in the CFGT. However, the diffraction peaks of CoFe₂O₄ were weakened, which suggested that most of the CoFe2O4 NPs were coated with a TiO₂ layer. For the co-doped TiO₂ NPs (CFGT-S/N), the main diffraction peak at $2\theta = 35.4^{\circ}$ of CoFe₂O₄ almost disappeared, suggesting that its saturation magnetization may be decreased. The unit cell volumes of CFGT and CFGT-S/N determined by the Debye-Scherrer equation were 0.1317 and 0.1359 nm³, which indicated that S and N had been successfully co-doped into the TiO₂ lattice.^{8,33} It was noted that the diffraction pattern of CFGT-S/N-5 was almost same as that of CFGT-S/N, which showed that the catalyst possessed a good stability.

In addition, the chemical bonding of the sulfur and nitrogen complexes on the surface of TiO_2 was examined by FT-IR measurements. Fig. 1(b) presented the FT-IR spectra of the samples ranging from 4000 to 400 cm⁻¹. For the CFG NPs, the band was observed in the range 600–500 cm⁻¹, and was indexed to the intrinsic stretching vibrations of the metal at the octahedral site Co–O and Fe–O in CoFe₂O₄. The absorption bands at 1230 cm⁻¹ and 1076 cm⁻¹ were associated with the epoxy C–O and alkoxy C–O groups of GO, respectively.^{16,32} The peak at

1627 cm⁻¹ corresponded to the O–H bending of the adsorbed water molecules, whereas the broad absorption bands at 3400 cm⁻¹ resulted from the O–H stretch region. It can be clearly seen that the main characteristic peaks of the CFG NPs appeared in the spectra of the CFGT NPs and CFGT-S/N NPs, but the GO characteristic peaks were weakened. The absorption bands below 1000 cm⁻¹ can be assigned to the Ti–O–Ti vibration.⁴ Ammonium ions produced by the dissociation of thiourea were also found in the titania prepared using thiourea as shown by a peak at 1403 cm⁻¹ attributable to the deformation mode of ammonium ions.¹² The peak at 1124 cm⁻¹ was assigned to the Ti–O–S vibration.¹³ The above results confirmed that S and N were successfully implanted in the structure of TiO₂.

3.2 UV-Vis DRS spectra analysis

To further investigate the optical properties of the prepared catalysts, the UV-Vis DRS spectra were recorded (Fig. 2). As shown in Fig. 2(a), P25 mainly responded to the ultraviolet region. However, the absorption of TiO2-SN (T-SN) in the visible light region was significantly increased due to co-doping with N and S elements.14,42,46 CoFe2O4 (CF) had broad and obvious absorption ranging in a wide region from 300 to 800 nm owing to its narrow bandgap.^{21,23-25,34} CFG NPs showed a stronger light absorption than CF, implying that the introduction of rGO can enhance the visible light absorption.17,25,36 Compared with CFG, the absorption intensity of CFGT decreased slightly, which can be attributed to the mixing effect of the two semiconductors introducing defect levels.35 Furthermore, it was found that CFT showed a relatively lower absorption in the visible light region (550-800 nm) than CFGT. After co-doping, the absorption of CFGT-S/N in the visible region improved, hence enhancing the photocatalytic activity.12,37 The plots of the transformed Kubelka-Munck function versus the energy of light were shown in Fig. 2(b). The band gap values of P25, T-SN, CF, CFG, CFT, CFGT and CFGT-S/N were 3.29, 3.08, 1.55, 1.45, 2.33, 2.21 and 2.15 eV, respectively. The results indicated that S, N co-doping,



Fig. 1 (a) XRD patterns of CFG, CFGT, CFGT-S/N and CFGT-S/N-5; (b) FT-IR spectra of CFG, CFGT, CFGT-S/N.

Paper



Fig. 2 (a) Diffuse reflectance spectra (DRS); (b) plots of transferred Kubelka-Munk vs. the energy of the light absorbed by the samples.

CoFe₂O₄ and rGO can enhance the visible light absorption of CFGT-S/N.

3.3 Morphology and structure analysis

The morphological structure of CFGT-S/N was further verified by FETEM observation. As can be seen in the inset of Fig. 3(a), binary CFG nanoparticles with a core-shell structure can be observed. After TiO₂-S/N coating, CFGT-S/N nanocomposites had a spherical morphology and their grain sizes were 160– 220 nm in diameter. From the HRTEM image of the CFGT-S/N hybrid (Fig. 3(b)), two different lattices were observed with *d* spaces of 2.54 and 3.50 Å, corresponding to the (311) plane of CoFe₂O₄ and the (101) plane of anatase TiO₂, respectively, which were quite similar to the literature values.³⁸ In addition, the EDS mapping images clearly showed that Ti, O, C, Fe, Co, S, and N elements were uniformly distributed in the CFGT-S/N sample, further confirming the presence of CoFe₂O₄, TiO₂, rGO, and the elements S and N (Fig. 3(d–j)).

3.4 XPS analysis

In order to determine the surface chemical compositions, XPS analysis was carried out. As shown in Fig. 4(a), CFGT contained Fe, Co, C, Ti and O, while CFGT-S/N not only contained Fe, Co, C, Ti, and O, but also S and N, which indicated that S and N had been co-doped into the CFGT-S/N hybrids. As shown in Fig. 4(b), the XPS spectrum of Fe 2p depicted two main broad peaks, 710.9 eV for Fe $2p_{3/2}$ and 724.0 eV for Fe $2p_{1/2}$, and a small peak at 714.3 eV for Fe $2p_{3/2}$, which could be due to the contributions from Fe³⁺ ions. From Fig. 4(c), the peaks of 779.0 eV, 781.0 eV and 794.2 eV were associated with Co2+ ions.21,39 The C 1s highresolution spectrum was curve-fitted in Fig. 4(d). The peaks at 284.7, 285.8, 286.9 and 288.6 eV were assigned to C=C/C-C, C-OH, C-O and HO-C=O, respectively.²⁵ For the S 2p XPS spectrum in Fig. 4(e), the characteristic peak in the range of 160-163 eV could be ascribed to the formation of Ti-S bond. It can be deduced that the S^{2-} ions replaced the O^{2-} ions in the lattice of TiO₂, making it produce a lattice distortion due to a large ionic radius difference between S^{2-} (0.184 nm) and O^{2-} (0.140 nm).^{12,33}

The peak at 168.8 eV was related to the S^{6+} of SO_4^{2-} ions, assigned to the SO₄²⁻ ions adsorbed on the surface of CFGT-S/N.⁴¹ The XPS spectra of the N 1s region are shown in Fig. 4(f). The peak at 400.3 eV was attributed to interstitial nitrogen atoms as Ti-O-N structural characteristic.^{10,13} From Fig. 4(g), the Ti 2p XPS spectrum of CFGT-S/N appeared two peaks at 459.2 and 465.0 eV, assigned to Ti $2p_{3/2}$ and Ti $2p_{1/2}$, respectively,^{22,40} a little lower than those of CFGT (459.5 and 465.1 eV), which could be attributed to partial of oxygen in the lattice of TiO₂ replaced by low electronegativity S anions, subsequently leading to the increase of the charge density of Ti atoms, and then decreasing binding energy of Ti 2p.42 This consequence further approved the formation of Ti-S bond. In addition, there is a shift of the O 1s peak by 0.1 eV toward low energy in CFGT-S/N (Fig. 4(h)), indicating the existence of concomitant oxygen deficiencies, which resulted in increased outer electron density of O and, consequently, decreased binding energy.43,50 The result of XPS was in good agreement with FT-IR.

3.5 Magnetic characterization

To evaluate the magnetic separation capacity, the magnetic hysteresis loops of CFG, CFGT and CFGT-S/N nanoparticles were measured at room temperature, as shown in Fig. 5. The saturation magnetization (Ms) values of the CFG, CFGT and CFGT-S/N were 32.74, 2.95 and 1.73 emu g⁻¹, respectively. It can be found that the non-magnetic coating TiO₂ layer affected the magnetic properties of the CoFe₂O₄ particles.^{20,23} Fortunately, the maximum saturation magnetization of 1.73 emu g⁻¹ was strong enough to separate CFGT-S/N from solution with the help of an external magnetic force. The magnetic separability was tested by placing a magnet near a glass bottle. The black product was rapidly attracted toward the magneti n a short period (the inset of Fig. 5), demonstrating the high magnetic sensitivity of the CFGT-S/N nanocomposites.

3.6 Photocatalytic activities

3.6.1 Photodegradation of MO. The photocatalytic activities of CFT, CFGT, CFGT-S/N, P25, and $CoFe_2O_4$ were tested



Fig. 3 (a) and (c) FETEM and (b) HRTEM images of CFGT-S/N; EDS elemental mapping images of the corresponding area: (d) Fe; (e) Co; (f) Ti; (g) O; (h) C; (i) N; and (j) S.

using the degradation of MO under UV- and Vis-light irradiation and the results were displayed in Fig. 6. From Fig. 6(a), it can be seen that CF displayed poor UV-light photocatalytic activity and P25 exhibited the highest photocatalytic activity. For CFT, MO degradation rate was only 74% within 150 min, while for CFGT, 100% of MO was degraded due to the rGO acting as an acceptor of the electrons generated in the TiO₂ particles, suppressing the recombination of charges.²⁶ After S, N co-doping, CFGT-S/N exhibited an improved photocatalytic activity compared to CFGT, and it took around 120 min to decompose MO completely. Furthermore, Fig. 6(b) illustrates that the photocatalytic reaction rate constants (k) onto CF, CFT, CFGT, CFGT-S/N and P25, were in turn 0.0009, 0.0081, 0.0133, 0.0192 and 0.1014 min^{-1} . Due to the lower content of TiO₂ in CFGT-S/N at the same dosage of catalysts, its rate constant k was lower than that of P25. As shown in Fig. 6(c), almost no degradation of MO over bare CF and CFT was observed under visible light irradiation. Although CFGT exerted facile MO adsorption, it displayed less photocatalytic activity. Notably, CFGT-S/N exhibited better catalytic activity, and the degradation rate of MO reached 100% within 6 h. For P25, only 72% of MO was removed within 6 h. It can be seen from Fig. 6(d), the k of CF, CFT, CFGT, CFGT-S/N and P25 was 0, 0, 0.0003, 0.0052 and 0.0039 min⁻¹, respectively. The k of CFGT-S/N was 33% higher than that of P25 under visible light irradiation. It indicated that the prepared CFGT-S/N displayed an excellent photocatalytic activity no matter which light source (UV or Vis) was used.

3.6.2 Photodegradation of various dyes. The photodegradation of the different organic dyes on CFGT-S/N was further studied under UV- and Vis-light irradiation. Two kinds of anionic dyes (RhB and MB) were selected as other pollutants. To confirm whether dyes were not photodegraded by itself, a blank test was also carried out. As shown in Fig. 7(a), CFGT-S/ N exhibited excellent UV-light photocatalytic activity, and it only



Fig. 4 (a) XPS survey spectra of CFGT and CFGT-S/N; high-resolution spectra of (b) Fe 2p, (c) Co 2p, (d) C 1s, (e) S 2p and (f) N 1s of CFGT-S/N; and high-resolution spectra of (g) Ti 2p and (h) O 1s of CFGT and CFGT-S/N.



Fig. 5 VSM magnetization curves of CFG, CFGT and CFGT-S/N. The inset shows the separation of CFGT-S/N from aqueous solution under an external magnetic field.

took 120 min to decompose various pollutants molecules completely. Under Vis-light illumination, the photocatalytic degradation rates of pollutants were still lower than those under UV-light illumination as shown in Fig. 7(b). Overall, the CFGT-S/ N showed no selectivity to photocatalytic degradation for most organic pollutants, which was of great importance to practical applications.

3.6.3 Cycling photodegradation of MO. As a recyclable photocatalyst, high stability and facile separation of catalysts were also important for the photocatalytic nanomaterial in water remediation.⁴ Recycling photocatalytic experiments of CFGT-S/N were conducted, and the results are represented in Fig. 8(a and b). After five cycles, the degradation rates of MO were 96% and 92% of that for the first cycle under UV- and Vislight illumination, respectively. This result implied that the asprepared catalysts had an excellent chemical stability and could be recycled in the organic dyestuff wastewater purification.

3.7 Photocatalytic mechanism

To better understand the separation efficiency of the photogenerated electrons and holes of CFGT-S/N, we investigated its photoinduced charge transfer properties.⁵ Fig. 9(a) shows the photocurrent density variations of the P25, CFG, CFT, CFGT and CFGT-S/N electrodes with measured potential in Na₂SO₄ solution. The dark current densities in all cases can be negligible. Upon irradiation, a significant increase in the photocurrent density was observed throughout the potential window at the CFGT-S/N electrode. The saturated photocurrent density of the CFGT-S/N electrode was about 0.71 μ A cm⁻², higher than those of the CFGT (0.08 μ A cm⁻²), CFT (0.05 μ A cm⁻²), CFG (0.05 μ A cm⁻²) and P25 (0.06 μ A cm⁻²) electrodes by a factor of 11.8, 14.2, 14.2 and 8.9, respectively. This demonstrated that the separation rate of photo-generated electrons and holes increased because of the co-doping of S and N in the TiO₂ network.

Furthermore, to verify the role of the reactive species under UV-Vis light irradiation over CFGT-S/N, different scavengers were employed in this study. They were benzoquinone (0.1 mM BQ) for the superoxide radical (O2'-), tert-butyl alcohol (0.1 mM TBA) for the hydroxyl radical (·OH), AgNO₃ (0.01 mM) for photogenerated electrons (e⁻) and disodium ethylenediaminetetraacetate (0.1 mM EDTA) for photo-generated holes (h⁺).^{3,4} As shown in Fig. 9(b), upon the addition of BQ and EDTA, the degradation rates were greatly suppressed to 23% and 48%, respectively. After the addition of AgNO₃, the photodegradation rate of MO decreased from 100% to 68%, indicating that e⁻ was definitely produced and transferred from TiO2-SN to rGO in the photocatalytic reaction, which was consistent with the literature reports.47,50 Besides, a significant change was observed in the presence of TBA, displaying that ·OH as an oxidation species was also indeed photogenerated on catalyst surfaces. The results suggested that O_2 , h^+ , e^- and $\cdot OH$ were the main active species in the MO photocatalytic oxidation process.

On the basis of the above experimental results, a possible photocatalytic mechanism for CFGT-S/N under UV-Vis irradiation was proposed and is illustrated in Scheme 1. Upon UV-Vis irradiation, $CoFe_2O_4$ (1.55 eV) with a narrow bandgap energy



Fig. 6 Photodegradation of MO on CF, P25, CFT, CFGT and CFGT-S/N under (a) UV- and (c) Vis-light irradiation; (b) and (d) first-order kinetics rate curves.

could be easily excited from the valence band (VB) to the conduction band (CB), inducing the generation of electron–hole pairs (eqn (2)).^{24,25,44,45} Notably, the introduction of $CoFe_2O_4$ with superparamagnetic behavior was conducive to catalyst recycling.^{23,25} For TiO₂, the co-doping of nitrogen and sulfur into the TiO₂ lattice led to the formation of mid-gap energy levels such as N 2p and S 2p between the valence band (VB) of O 2p and the conduction band (CB) of Ti 3d and narrowed the bandgap energy to 3.08 eV, thereby TiO₂-S/N can be excited easily by the

photons (eqn (3)).^{42,46,52,53} The photoinduced electrons (e⁻) from TiO₂-S/N can be quickly transferred to the huge π - π network of rGO due to their excellent electron accepting and transporting properties,^{36,47} and then rGO (e⁻) reacted with dissolved O₂ to generate O₂^{•-} radicals (eqn (4) and (5)). This process can restrain effectively the electron-hole recombination on TiO₂-S/N.^{48,49} The photoinduced holes (h⁺) remaining in the VB of TiO₂-SN can directly degrade MO, and can also be captured by H₂O to form •OH radicals (eqn (6)).^{45,46,50} Moreover, the h⁺ on the VB of



Fig. 7 Photodegradation of various dyes in the presence of CFGT-S/N under (a) UV- and (b) Vis-light irradiation.







Fig. 9 (a) Photocurrent density of P25, CFG, CFT, CFGT and CFGT-S/N; and (b) photocatalytic activities of CFGT-S/N hybrid in the presence of different scavengers under UV-Vis light irradiation (reaction conditions: $[MO] = 5 \text{ mg } L^{-1}$, $[catalyst] = 0.20 \text{ g } L^{-1}$).



Scheme 1 The possible photocatalytic mechanism on the CFGT-S/N nanocomposite.

 TiO_2 -S/N can be transferred to the VB of $CoFe_2O_4$ due to the lower potential energy of the VB of $CoFe_2O_4$, which can facilitate efficiently interface charge separation and hamper carrier

recombination.^{44,51} As a result, these highly reactive oxygen species (ROS, such as O_2^{*-} , h^+ and $\cdot OH$) can effectively degrade MO adsorbed on CFGT-SN (eqn (7)). According to the above analysis, the relevant reactions on the surface of nanocomposite can be expressed as follows:

$$CoFe_2O_4 + hv \rightarrow CoFe_2O_4 (h^+ + e^-)$$
(2)

$$TiO_2-S/N + hv \rightarrow TiO_2-S/N (h^+ + e^-)$$
(3)

$$e^- + rGO \rightarrow rGO (e^-)$$
 (4)

$$rGO(e^{-}) + O_2 \rightarrow O_2^{\cdot -}$$
(5)

$$h^+ + H_2 O \rightarrow H^+ + \cdot O H \tag{6}$$

$$MO + ROS \rightarrow CO_2 + H_2O \tag{7}$$

4 Conclusions

In summary, we have presented a simple and controllable way to synthesise magnetically separable S, N co-doped

Paper

 $CoFe_2O_4$ @rGO@TiO_2 composites, which has not been reported before. This method can efficiently dope sulfur and nitrogen elements into the lattice of TiO_2. The results showed that CFGT-S/N exhibited excellent photocatalytic activity no matter which light source (UV or Vis) was used. The high activity of CFGT-S/N was ascribed to a synergetic consequence of several beneficial effects, such as the efficient separation of photoinduced electron-hole pairs and the improvement in UV-Vis absorption. Furthermore, the presence of $CoFe_2O_4$ in the hybrid helped the catalyst particles to acquire ferromagnetic properties, and they were easily separated from the catalytic solution. Therefore, the synthesized CFGT-S/N can be used as a composite photocatalyst for the elimination of organic pollutants from waste water.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The authors gratefully acknowledge financial support from the National Natural Science Foundation of China (No. 51372062).

References

- J. Schneider, M. Matsuoka, M. Takeuchi, J. L. Zhang, Y. Horiuchi, M. Anpo and D. W. Bahnemann, Understanding TiO₂ photocatalysis: mechanisms and materials, *Chem. Rev.*, 2014, **114**(19), 9919–9986.
- 2 M. Liu, R. Inde, M. Nishikawa, X. Q. Qiu, D. Atarashi, E. Sakai, Y. Nosaka, K. Hashimoto and M. Miyauchi, Enhanced photoactivity with nanocluster-grafted titanium dioxide photocatalysts, *ACS Nano*, 2014, **8**(7), 7229–7238.
- 3 C. Burda and X. Chen, The electronic origin of the visiblelight absorption properties of C-, N- and S-doped TiO₂ nanomaterials, *J. Am. Chem. Soc.*, 2008, **130**(15), 5018–5019.
- 4 Y. J. Yao, J. C. Qin, H. Chen, F. Y. Wei, X. T. Liu, J. L. Wang and S. B. Wang, One-pot approach for synthesis of Ndoped $TiO_2/ZnFe_2O_4$ hybrid as an efficient photocatalyst for degradation of aqueous organic pollutants, *J. Hazard. Mater.*, 2015, **291**, 28–37.
- 5 F. Y. Wei, T. Liu, F. Z. Zhou, W. Ran, Y. J. Yao, H. Wang and P. H. Wang, Magnetic recoverable F-N Co-doped ZnFe₂O₄/C/ TiO₂ nanocomposites with UV-Vis light photocatalytic activity, *Environ. Eng. Sci.*, 2018, **35**, 37–45.
- 6 T. Ohno, M. Akiyoshi, T. Umebayashi, K. Asai, T. Mitsui and M. Matsumura, Preparation of S-doped TiO_2 photocatalysts and their photocatalytic activities under visible light, *Appl. Catal.*, A, 2004, **265**(1), 115–121.
- 7 Y. M. Wu, M. Y. Xing, J. L. Zhang and F. Chen, Effective visible light-active boron and carbon modified TiO₂ photocatalyst for degradation of organic pollutant, *Appl. Catal.*, *B*, 2010, **97**, 182–189.
- 8 M. Behpour, R. Foulady-Dehaghi and N. Mir, Considering photocatalytic activity of N/F/S-doped TiO_2 thin films in degradation of textile waste under visible and sunlight irradiation, *Sol. Energy*, 2017, **158**, 636–643.

- 9 S. In, A. Orlov, R. Berg, F. García, S. Pedrosa-Jimenez, M. S. Tikhov, D. S. Wright and R. M. Lambert, Effective visible light-activated B-doped and B,N-codoped TiO₂ photocatalysts, *J. Am. Chem. Soc.*, 2007, **129**(45), 13790– 13791.
- 10 X. P. Wang and T. Lim, Solvothermal synthesis of C-N codoped TiO₂ and photocatalytic evaluation for bisphenol a degradation using a visible-light irradiated LED photoreactor, *Appl. Catal.*, *B*, 2010, **100**, 355–364.
- 11 N. C. Birben, C. S. Uyguner-Demirel, S. Sen-Kavurmaci, Y. Y. Gurkan, N. Turkten, Z. Cinar and M. Bekbolet, Comparative evaluation of anion doped photocatalysts on the mineralization and decolorization of natural organic matter, *Catal. Today*, 2015, 240, 125–131.
- 12 F. Y. Wei, L. S. Ni and P. Cui, Preparation and characterization of N-S-codoped TiO₂ photocatalyst and its photocatalytic activity, *J. Hazard. Mater.*, 2008, **156**, 135–140.
- 13 G. Zhang, C. Z. Yong, M. Nadagouda, C. Han, K. O'Shea, S. M. El-Sheikh, A. A. Ismail and D. D. Dionysiou, Visible light-sensitized S, N and C co-doped polymorphic TiO₂ for photocatalytic destruction of microcystin-LR, *Appl. Catal.*, *B*, 2014, **144**(1), 614–621.
- 14 W. W. Zhao, F. H. Tian, X. B. Wang, L. H. Zhao, L. H. Xia and C. B. Liu, Theoretical study on S-, N-doped anatase TiO₂: the visible-light-driven photocatalysts, *Journal of Computational Science & Engineering*, 2013, 4, 170–177.
- 15 Q. Y. He, H. G. Sudibya, Z. Y. Yin, S. X. Wu, H. Li, F. Boey, W. Huang, P. Chen and H. Huang, Centimeter-long and large-scale micropatterns of reduced graphene oxide films: fabrication and sensing applications, *ACS Nano*, 2010, 4, 3201–3208.
- 16 D. Y. Liang, C. Cui, H. H. Hu, Y. P. Wang, S. Xu, B. L. Ying, P. G. Li, B. Q. Lu and H. L. Shen, One-step hydrothermal synthesis of anatase TiO₂/reduced graphene oxide nanocomposites with enhanced photocatalytic activity, *J. Alloys Compd.*, 2014, 582, 236–240.
- 17 Z. Q. Li, H. L. Wang, L. Y. Zi, J. J. Zhang and Y. S. Zhang, Preparation and photocatalytic performance of magnetic TiO₂-Fe₃O₄/graphene (RGO) composites under Vis-light irradiation, *Ceram. Int.*, 2015, **41**, 10634–10643.
- 18 H. Liu, X. N. Dong, X. C. Wang, C. C. Sun, J. Q. Li and Z. F. Zhu, A green and direct synthesis of graphene oxide encapsulated TiO_2 core/shell structures with enhanced photoactivity, *Chem. Eng. J.*, 2013, **230**, 279–285.
- 19 H. Kim, G. Moon and M. Damian, Solar photoconversion using Graphene/TiO₂ composites: nanographene shell on TiO₂ core versus TiO₂ nanoparticles on graphene sheet, *J. Phys. Chem. C*, 2012, **116**, 1535–1543.
- 20 P. C. Ma, W. Jiang, F. H. Wang, F. S. Li, P. Shen, M. D. Chen, Y. J. Wang, J. Liu and P. Y. Li, Synthesis and photocatalytic property of Fe₃O₄@TiO₂ core/shell nanoparticles supported by reduced graphene oxide sheets, *J. Alloys Compd.*, 2013, 578, 501–506.
- 21 V. K. Gupta, T. Eren, N. Atar, M. L. Yole, C. Parlak and H. Karimi-Maleh, CoFe₂O₄@TiO₂ decorated reduced graphene oxide nanocomposite for photocatalytic degradation of chlorpyrifos, *J. Mol. Liq.*, 2015, **208**, 122–129.

- 22 J. T. Feng, Y. C. Wang, Y. H. Hou and L. C. Li, Tunable design of yolk-shell ZnFe₂O₄@RGO@TiO₂ microspheres for enhanced high-frequency microwave absorption, *Inorg. Chem. Front.*, 2017, **4**, 935–945.
- 23 S. M. Moosavi, P. Molla-Abbasi and Z. Haji-Aghajani, Photo-catalyst CoFe₂O₄-TiO₂: application in photo-degradation of organic dyes and magnetic nanocomposite preparation, *J. Mater. Sci.: Mater. Electron.*, 2016, 27, 4879–4886.
- 24 P. Sathishkumar, R. V. Mangalaraja, S. Anandan and M. Ashokkumar, CoFe₂O₄/TiO₂, nanocatalysts for the photocatalytic degradation of reactive red 120 in aqueous solutions in the presence and absence of electron acceptors, *Chem. Eng. J.*, 2013, **220**, 302–310.
- 25 J. W. Sun, Y. S. Fu, P. Xiong, X. Q. Sun, B. H. Xu and X. Wang, A magnetically separable P25/CoFe₂O₄/graphene catalyst with enhanced adsorption capacity and visible-light-driven photocatalytic activity, *RSC Adv.*, 2013, **3**, 22490–22497.
- 26 Y. Lin, Z. G. Geng, H. B. Cai, L. Ma, J. Chen, J. Zeng, N. Pan and X. P. Wang, Ternary graphene– TiO_2 – Fe_3O_4 nanocomposite as a recollectable photocatalyst with enhanced durability, *Eur. J. Inorg. Chem.*, 2012, **28**, 4439– 4444.
- 27 S. M. Li, B. Wang, J. H. Liu and M. Yu, In situ one-step synthesis of CoFe₂O₄/graphene nanocomposites as high performance anode for lithium-ion batteries, *Electrochim. Acta*, 2014, **129**, 33–39.
- 28 X. L. Yang, W. Chen, J. F. Huang, Y. Zhou, Y. H. Zhu and C. Z. Li, Rapid degradation of methylene blue in a novel heterogeneous Fe₃O₄@rGO@TiO₂-catalyzed photo-fenton system, *Sci. Rep.*, 2015, 5, 10632–10642.
- 29 Z. J. Song, W. Ran and F. Y. Wei, One-step approach for the synthesis of CoFe₂O₄@rGO core-shell nanocomposites as efficient absorbent for removal of organic pollutants, *Water Sci. Technol.*, 2017, **75**, 397–405.
- 30 D. C. Marcano, D. V. Kosynkin, J. M. Berlin, A. Sinitskii, Z. Z. Sun, A. Slesarev, L. B. Alemany, W. Lu and J. M. Tour, Improved synthesis of graphene oxide, *ACS Nano*, 2010, 4, 4806–4814.
- 31 Y. J. Yao, Z. H. Yang, D. W. Zhang, W. H. Peng, H. Q. Sun and S. Wang, Magnetic CoFe₂O₄-graphene hybrids: facile synthesis, characterization, and catalytic properties, *Ind. Eng. Chem. Res.*, 2012, **51**, 6044–6051.
- 32 L. Gan, S. M. Shang, C. W. M. Yuen, S. X. Jiang and E. L. Hu, Hydrothermal synthesis of magnetic CoFe₂O₄/graphene nanocomposites with improved photocatalytic activity, *Appl. Surf. Sci.*, 2015, **351**, 140–147.
- 33 D. Ma, Y. J. Xin, M. C. Gao and J. Wu, Fabrication and photocatalytic properties of cationic and anionic S-doped TiO₂ nanofibers by electrospinning, *Appl. Catal.*, *B*, 2014, 147, 49–57.
- 34 M. H. Habibi and J. Parhizkar, Cobalt ferrite nano-composite coated on glass by doctor blade method for photo-catalytic degradation of an azo textile dye reactive red 4: XRD, FESEM and DRS investigations, *Spectrochim. Acta, Part A*, 2015, **150**, 879–885.
- 35 P. P. Hankare, R. P. Patil, A. V. Jadhav, K. M. Garadkar and R. Sasikala, Enhanced photocatalytic degradation of

methyl red and thymol blue using titania-alumina-zinc ferrite nanocomposite, *Appl. Catal., B*, 2011, **107**, 333-339.

- 36 G. Y. He, J. J. Ding, J. G. Zhang, Q. L. Hao and H. Q. Chen, One-step ball-milling preparation of highly photocatalytic active CoFe₂O₄-reduced graphene oxide heterojunctions for organic dye removal, *Ind. Eng. Chem. Res.*, 2015, 54, 2862– 2867.
- 37 M. Behpour and V. Atouf, Study of the photocatalytic activity of nanocrystalline S, N-codoped TiO₂ thin films and powders under visible and sun light irradiation, *Appl. Surf. Sci.*, 2012, 258(17), 6595–6601.
- 38 W. Li, J. P. Yang, Z. X. Wu, J. X. Wang, B. Li, S. S. Feng, Y. H. Deng, F. Zhang and D. Y. Zhao, A versatile kineticscontrolled coating method to construct uniform porous TiO₂ shells for multifunctional core-shell structures, *J. Am. Chem. Soc.*, 2012, **134**, 11864–11867.
- 39 Z. P. Zhou, Y. Zhang, Z. Y. Wang, W. Wei, W. F. Tang, J. Shi and R. Xiong, Electronic structure studies of the spinel $CoFe_2O_4$ by X-ray photoelectron spectroscopy, *Appl. Surf. Sci.*, 2008, **254**, 6972–6975.
- 40 Y. Min, G. Q. He, R. B. Li, W. Zhao, Y. C. Chen and Y. G. Zhang, Doping nitrogen anion enhanced photocatalytic activity on TiO₂ hybridized with graphene composite under solar light, *Sep. Purif. Technol.*, 2013, **106**, 97–104.
- 41 C. Han, M. Pelaez, V. Likodimos, A. G. Kontos, P. Falaras,
 K. Shea and D. D. Dionysiou, Innovative visible lightactivated sulfur doped TiO₂ films for water treatment, *Appl. Catal.*, *B*, 2011, **107**, 77–87.
- 42 D. Li, Z. P. Xing, X. J. Yu and X. W. Cheng, One-step hydrothermal synthesis of C-N-S-tridoped TiO₂-based nanosheets photoelectrode for enhanced photoelectrocatalytic performance and mechanism, *Electrochim. Acta*, 2015, **170**, 182–190.
- 43 R. Huo, J. Y. Yang, Y. Q. Liu, H. F. Liu, X. Li and Y. H. Xu, Preparation of W and N, S co-doped titanium dioxide with enhanced photocatalytic activity under visible light irradiation, *Mater. Res. Bull.*, 2016, **76**, 72–78.
- 44 C. Haw, W. Chiu, S. A. Rahman, P. Khiew, S. Radiman, R. A. Shukor, M. A. A. Hamid and N. Ghazali, The design of new magnetic-photocatalyst nanocomposites (CoFe₂O₄-TiO₂) as smart nanomaterials for recyclable-photocatalysis applications, *New J. Chem.*, 2016, **40**, 1124–1136.
- 45 P. Xiong, L. J. Wang, X. Q. Sun, B. H. Xu and X. Wang, Ternary titania-cobalt ferrite-polyaniline nanocomposite: a magnetically recyclable hybrid for adsorption and photodegradation of dyes under visible light, *Ind. Eng. Chem. Res.*, 2013, **52**, 10105–10113.
- 46 A. Brindha and T. Sivakumar, Visible active N, S co-doped TiO₂/graphene photocatalysts for the degradation of hazardous dyes, *J. Photochem. Photobiol.*, *A*, 2017, **340**, 146–156.
- 47 Q. W. Huang, S. Q. Tian, D. W. Zeng, X. X. Wang, W. L. Song, Y. Y. Li, W. Xiao and C. S. Xie, Enhanced photocatalytic activity of chemically bonded TiO₂/graphene composites based on the effective interfacial charge transfer through the C–Ti bond, *ACS Catal.*, 2013, 3(7), 1477–1485.

- 48 P. Wang, J. Wang, T. S. Ming, X. F. Wang, H. G. Yu, J. G. Yu, Y. G. Wang and M. Lei, Dye-sensitization-induced visiblelight reduction of graphene oxide for the enhanced TiO₂ photocatalytic performance, ACS Appl. Mater. Interfaces, 2013, 5(8), 2924.
- 49 H. Zhang, X. J. Lv, Y. M. Li, Y. Wang and J. H. Li, P25graphene composite as a high performance photocatalyst, *ACS Nano*, 2010, 4(1), 380–386.
- 50 W. Qian, P. A. Greaney, S. Fowler, S. K. Chiu, A. M. Gafoth and J. Jiao, Low-temperature titrogen doping in ammonia solution for production of N-doped TiO₂-hybridized graphene as a highly efficient photocatalyst for water treatment, *ACS Sustainable Chem. Eng.*, 2014, 2(7), 1802– 1810.
- 51 C. J. Leng, J. H. Wei, Z. Y. Liu, R. Xiong, C. X. Pan and J. Shi, Facile synthesis of PANI-modified CoFe₂O₄-TiO₂, hierarchical flower-like nanoarchitectures with high photocatalytic activity, *J. Nanopart. Res.*, 2013, **15**(5), 1–11.
- 52 C. Di Valentin, G. Pacchioni, A. Selloni, S. Livraghi and E. Giamello, Characterization of paramagnetic species in N-doped TiO₂ powders by EPR spectroscopy and DFT calculations, *J. Phys. Chem. B*, 2005, **109**(23), 11414–11419.
- 53 S. Pany, B. Naik, S. Martha and K. Parida, Plasmon induced nano Au particle decorated over S,N-modified TiO₂ for exceptional photocatalytic hydrogen evolution under visible light, ACS Appl. Mater. Interfaces, 2014, 6(2), 839–846.