RSC Advances

PAPER

Cite this: RSC Adv., 2019, 9, 10081

Received 27th January 2019 Accepted 13th March 2019

DOI: 10.1039/c9ra00719a

rsc.li/rsc-advances

1. Introduction

Bone defects are a common clinical condition. When a bone defect reaches 1.5 times the diameter of the long bone, the bone defect cannot heal and needs to be repaired.¹ Artificial bone material is one of the common bone repair materials, which can effectively avoid the immune rejection caused by autologous bone or allogeneic bone transplantation.² Polyetheretherketone (PEEK) is a rigid semi-crystalline polymer with the advantages of corrosion resistance, wear resistance, high strength, high stiffness, creep resistance and fatigue strength. Meanwhile, it will not cause tissue rejection reactions. Due to a low swelling rate and good self-lubrication, PEEK has potential to be bone implant material matrix.³ Compared with metal implants, PEEK is more compatible with bone mechanical properties,^{4,5} but the biological inertness of PEEK has led to its limitations.⁶⁻⁹ Hydroxyapatite (HAP) is one of the main inorganic components in bone.¹⁰ Shucong Yu¹¹ dispersed different levels of HAP in PEEK and found that HAP can effectively improve the biocompatibility of PEEK. On this basis, KL Wong et al .¹² prepared a HAP/PEEK composite containing niobium to enhance its biocompatibility. Wang L^{13} prepared a fluorine-containing

Preparation and biocompatibility of $Fe_{50}Ni_{50}p/$ HAP/PEEK biocomposites with weak magnetic properties

Dengyu Liu, ^{Da} Zhenghou Zhu, *a Jia Zhou, *b Hui Zhao, b Jie Chen, a Ruru Bai, a Q ianying Lin^a and Manikandan Alagarsamy^c

Hydroxyapatite (HAP)/polyetheretherketone (PEEK) composites are widely used in the new generation of bone implant materials. The use of weak magnetic fields can promote the biocompatibility of PEEK materials. In this paper, Fe₅₀Ni₅₀ alloy nanopowders and Fe₅₀Ni₅₀/HAP/PEEK composites were prepared by liquid phase chemical reduction and liquid phase mixing. The prepared $Fe_{50}Ni_{50}$ alloy nanopowders have a particle size of about 100 nm and good chemical activity and magnetic properties. The saturation magnetization (M_s) of the Fe₅₀Ni₅₀ alloy powders is 70 emu g⁻¹. Fe₅₀Ni₅₀ nano-powders in Fe₅₀Ni₅₀/ HAP/PEEK composites are uniformly distributed in the matrix in the form of individual particles, achieving nano-level dispersion. With the increase of Fe₅₀Ni₅₀ alloy powders content, the magnetic properties of the composites are significantly enhanced. The biocompatibility of $Fe_{50}Ni_{50}/HAP/PEEK$ composites is significantly better than that of PEEK and HAP/PEEK materials. The 2% Fe₅₀Ni₅₀/HAP/PEEK composite has the best comprehensive performance, and its biocompatibility is good. The contact angle is only 55.85°. The M_s reaches 1.5 emu g⁻¹ and the hardness reaches 42 HBa. PAPER
 (A) Check for undates
 (A) Check for undates
 EVALUATELY

Check for undates
 EVALUATELY
 EVALUATELY
 **CHEAR DEPREM biocomposites with weak magnetic

properties

Properties

Dengyu Liu ^O² Zhenghou Zhu,**

nHAP/PEEK composite with good biocompatibility and antibacterial properties in vitro.

Another research hotspot for improving the biocompatibility of PEEK is the use of weak magnetic fields to promote biocompatibility.¹⁴–¹⁹ Current research shows that magnetic field can effectively promote bone growth, accelerate fracture healing, and treat bone nonunion.²⁰⁻²³ Yan²⁴ studied the effect of static magnetic field (SMF) on the bone formation of rat femur by a tapered rod made of magnetized and unmagnetized samarium cobalt. The results show that the local magnetic field can locally increase the density of bone tissue. Richard Leesungbok²⁵ found that acidified titanium-containing titanium implants can induce bone formation around the implant more quickly.

The introduction of the magnetic nanopowders into the artificial bone material not only preserves the structural role of the artificial bone in the human body, but also introduces a magnetic field to further enhance the bone repairing ability. At present, the most magnetic nanopowders used in clinical practice is $Fe₃O₄$.²⁶ $Fe₃O₄$ is a paramagnetic material with weak magnetic properties. As a composite reinforcement, it usually needs to add more amount, which will seriously affect the mechanical properties and color of the matrix. $Fe₃O₄$ has strong oxidizing properties and is easily reduced in the human body, which affects biocompatibility.

Compared with $Fe₃O₄$, the nano FeNi alloy powders has strong magnetic properties, which can reduce the amount of addition in the composite material, and has less influence on its

a School of Materials Science & Engineering, Nanchang University, Nanchang 330031, China. E-mail: z00708@sina.com

^bInstitute of Space Science and Technology, Nanchang University, Nanchang 330031, China. E-mail: 303248527@qq.com

c Nanchang University School of Medicine, Nanchang 330031, China

mechanical properties and appearance. At the same time, FeNi powders overcomes the poor magnetic properties of the elemental powders such as pure Fe powders and pure Ni powders.

In this study, nano FeNi alloy powders with better magnetic properties was used to replace $Fe₃O₄$ powders, which can reduce the amount of magnetic powders added and have less influence on the mechanical properties of the matrix.

FeNi alloy nanopowders mainly have two typical components: $Fe₅₀Ni₅₀$ and $Fe₂₀Ni₈₀$. The low cost $Fe₅₀Ni₅₀$ alloy powders was selected in this paper. At present, methods for preparing FeNi alloy nanopowders include vacuum condensation method, physical pulverization method, mechanical ball milling method, etc., but the products obtained by physical methods have low purity and uneven particle size.²⁷ In this paper, the $Fe₅₀Ni₅₀$ alloy nanopowders was prepared by liquid phase chemical reduction method, then the $Fe_{50}Ni_{50}$ powder was compounded into HAP and PEEK powders by liquid phase blending method, and then the sample was prepared by compression molding.

2. Material and methods

2.1 Preparation of $Fe_{50}Ni_{50}$ nanopowders and $Fe_{50}Ni_{50}/HAP/$ PEEK composite

Fe₅₀Ni₅₀ nanopowders were prepared by liquid phase chemical reduction. A certain amount of NiSO₄ (Jinchuan Group Co., Ltd, CP) and FeSO₄ (Xilong Chemical Co., Ltd, AR) were dissolved in deionized water, and after thorough stirring, NaOH (Damao chemical reagent factory in Tianjin, AR) was added to form a Fe(OH)₂ + Ni(OH)₂ precursor. Heated to 85 °C, added N₂H₄ (Damao chemical reagent factory in Tianjin, AR) and stirred for 40 minutes, the color of the solution gradually grayed from green, and finally turned black, while generating a lot of irritating gas, indicating that the product of the first step was gradually reduced to $Fe₅₀Ni₅₀$ nanopowders (black precipitate). After magnetic separation and repeated extraction with absolute ethanol, a suspension of $Fe₅₀Ni₅₀$ nanopowders in absolute ethanol was obtained.²⁸ Slowly added 20 wt% HAP (Xian Season Biotechnology Co., Ltd.), 80 wt% PEEK (Victrex® Manufacturing Ltd.) powders to the suspension, continue stirring until the powders was evenly mixed, and heated to 90 \degree C to remove anhydrous ethanol. $Fe_{50}Ni_{50}/HAP/PEEK$ composite powders was obtained.

The composite powders were heated to 375 \degree C in a mold and held at 15 MPa for 30 min to prepare a bulk composite sample. The sample types were PEEK, 20 wt% HAP/PEEK, 2% $Fe_{50}Ni_{50}/$ 20 wt% HAP/PEEK, 5% $Fe_{50}Ni_{50}/20$ wt% HAP/PEEK.

All the samples were uniformly polished with metallographic sandpaper, ultrasonically treated in an ethanol solution for 30 min, and dried at 70 °C.

2.2 Performance characterization

2.2.1 Characterization of $Fe_{50}Ni_{50}$ powders and composite powders. The phase structure of $Fe_{50}Ni_{50}$ alloy was analyzed by German Bruker-ax D8 ADVANCE X-ray diffraction analyzer $(XRD, CuK\alpha)$. The test conditions were as follows: tube voltage was 40 kV, current was 40 mA, and step size was 0.02° . At the same time, the microscopic morphology analysis and distribution of the powders were observed using a high-resolution scanning electron microscope JSM-6701F (Japan Electronics).

2.2.2 Electrochemical activity test of $Fe_{50}Ni_{50}$ powders. The prepared $Fe₅₀Ni₅₀$ powders was uniformly mixed with conductive carbon black and polyvinylidene fluoride (PVDF) in a ratio of 80 : 10 : 10, and ground in an anhydrous ethanol atmosphere for two hours to prepare a slurry. The slurry was applied to a 20 mm \times 10 mm nickel mesh, and the solvent was removed by drying to form an electrode. The electrochemical performance of $Fe_{50}Ni_{50}$ powders was tested by a three-electrode system using an electrochemical workstation (Shanghai Chenhua CHI760E). Among them, a platinum electrode was used as an auxiliary electrode, Hg/HgO was used as a reference electrode, and a 1 M KOH solution was used as an electrolyte. The cyclic voltammetry (CV) test has a voltage range of 0–0.75 V and a sampling interval of 0.001 V. BSC Advances

Incelaring inporties and appearance. At the same time, FeNT exacts at N₁, tries uses Colliders are properties (and the published on 2018) and the same in the published on 2018. The same of the same of the

2.2.3 Contact angle measurements. The contact angles were measured by a JC2000A CA system at 20 \degree C. Prior to these measurements, all the samples were vacuum dried and kept in a desiccator.

2.2.4 Biocompatibility. To study the biocompatibility of the samples (the ability of the bone implant material to integrate the surrounding bones), samples of different compositions were soaked in simulated body fluids (SBF). The SBF solution has the same ion species and concentration as human plasma, and the in vitro biocompatibility of the sample was characterized by studying the apatite formed on the surface of the sample in SBF solution. However, $Fe₅₀Ni₅₀$ powders is not easy to obtain nanostructures. In this paper, nanoscale powders were prepared by a relatively simple liquid phase chemical reduction method.

Analytically pure NaCl (Xilong Chemical Co., Ltd, AR, NaHCO₃), KCl (Xilong Chemical Co., Ltd, AR), K₂HPO₄·3H₂O (Xilong Chemical Co., Ltd, AR), MgCl·6H₂O (Fengchuan Chemical Reagent Technology Co., Ltd, AR), HCl (Xilong Chemical Co., Ltd, AR), CaCl₂ (Shanghai Yanchen Chemical Industry Co., Ltd, AR), $Naso₄$ (Damao chemical reagent factory in Tianjin, AR) and Tris (Sinopharm Chemical Reagent Co., Ltd) were dissolved in deionized water to buffer the solution to 7.4, and the volume was adjusted to 1 L. Simulated body fluids (SBF) were produced.²⁹ Table 1 compares the prepared SBF solution

Table 1 Comparison between SBF solution and human plasma ion concentration

Blood plasma $(mmol^{-1})$	SBF (mmol ⁻¹)
142.0	142.0
5.0	5.0
1.5	1.5
2.5	2.5
103.0	147.8
27.0	4.2
1.0	1.0
0.5	0.5

Paper RSC Advances

with human blood ion concentration, and the pH range of blood plasma is 7.2–7.4. The samples were each immersed in an appropriate amount of SBF solution and the temperature was maintained at 36.5 \degree C. The SBF solution was changed every two days. After 7 days, the sample was taken out and washed with deionized water and then air-dried. The in vitro biocompatibility of the material was evaluated by scanning the surface topography and analyzing the surface Ca and P contents with a JSM 6701F field emission scanning electron microscope (SEM) with an energy spectrometer.

2.2.5 Mechanical properties. The mechanical properties of the samples were tested using a CMT series microcomputer controlled electronic tensile testing machine (China Shenzhen New Sansi Material Testing Co., Ltd.). A tensile stress–strain curve was obtained by setting the stretching rate to 2 mm min^{-1} to record the breaking strength. The Barcol hardness of the composite was measured using a Barcol hardness tester (GYZJ-934-1).

2.2.6 Magnetic performance characterization. The hysteresis loop of pure $Fe_{50}Ni_{50}$ powders, HAP/PEEK containing 2% Fe₅₀Ni₅₀ powders and HAP/PEEK material containing 5% $Fe₅₀Ni₅₀$ powders was tested by the American Quantum Design PPMS-9 physical property test system. The sweep speed was 100 Oe s^{-1} and the test temperature was 300 K.

3. Results and discussion

3.1 X-ray and SEM characterization results of $Fe_{50}Ni_{50}$ powders

The powders composition of nano FeNi alloy mainly includes $Fe_{50}Ni_{50}$ and $Fe_{20}Ni_{80}$. In this paper, $Fe_{50}Ni_{50}$ alloy nanopowders were prepared by liquid phase reduction method. The reaction equation is

$$
2FeSO4 + N2H4 + 4NaOH \rightarrow 2Fe4 + N2†+ 4H2O + 2Na2SO4
$$
 (1)

$$
2NiSO4 + N2H4 + 4NaOH \rightarrow 2Ni\downarrow + N2\uparrow
$$

+ 4H₂O + 2Na₂SO₄ (2)

Due to difference of Gibbs free energy value $(G$ value) in the reduction reaction of Fe^{2+} and Ni^{2+} , the preparation of alloy nanopowders must be completed by a two-step process by adjusting the reaction rate and the concentration of the

Fig. 1 Schematic diagram of reaction.

Fig. 3 SEM image of $Fe₅₀Ni₅₀$ powders.

reactant. First, the reaction rate and the Fe^{2+}/Ni^{2+} concentration ratio was adjusted, and the Ni nucleus was formed. Then, the reduction reaction was synchronized by adjusting the reaction rate. Fe²⁺ and Ni²⁺ were simultaneously deposited on the crystal nucleus to form an alloy after reduction. The schematic diagram of the reaction principle is shown in Fig. 1.

Fig. 5 Dispersion of $Fe₅₀Ni₅₀$ powders in matrix after molding.

Fig. 2 showed the XRD diagram of $Fe₅₀Ni₅₀$ powders obtained by liquid phase chemical reduction, in which 1 was the corresponding peak of $Fe₅₀Ni₅₀$ and 2 was the corresponding peak of

Fig. 4 Mixing of Fe₅₀Ni₅₀ powders in HAP/PEEK powders before molding.

Fe₂O₃. Due to the excess Fe²⁺ in the reactant, Fe atom cladding layer was mainly formed in the later stage of the reaction. With low G value of $Fe₂O₃$, Fe atom on the surface layer was oxidized to form $Fe₂O₃$ in the air. Fig. 3 was a SEM photograph of a Fe₅₀Ni₅₀ powders, in which the particle diameter was about 100 nm, reaching the nanometer scale and having a high surface energy.

Fig. 4 and 5 were SEM images of composite powders and composites respectively. The nanoscale $Fe₅₀Ni₅₀$ powders in

the composite powders were dispersed in the surface cracks of HAP powders with large particle size, forming a stable complex. After the composite powders was pressed at high temperature, the $Fe₅₀Ni₅₀$ powders flowed with the PEEK matrix and redistributes to become the composite material. In the composite materials, the $Fe₅₀Ni₅₀$ nanometer powders were uniformly distributed in the matrix in the form of a single particle, reaching the nano-scale dispersion level.

Fig. 7 The water contact angle (degrees) of PEEK, HAP/PEEK composites, FeNi/HAP/PEEK composites

Fig. 8 SEM images of the surface of (a) PEEK, (b) HAP/PEEK composite, (c) 2% Fe₅₀Ni₅₀/HA/PEEK composite and (d) 5% Fe₅₀Ni₅₀/HA/PEEK composite after 7 days of immersion in SBF solution.

3.2 Electrochemical activity of $Fe₅₀Ni₅₀$ powders

The high chemical activity of $Fe₅₀Ni₅₀$ powders was beneficial to improve the biocompatibility of the composite. Through repeated experiments, the scanning speed was chosen to be

0.1 V s^{-1} . It could be seen from Fig. 6 that the CV curve has obvious and symmetric oxidation peaks and reduction peaks, indicating that the electrodes have a certain reversibility. At the high scanning speed of 0.1 V s^{-1} , there were still obvious

Fig. 9 Energy spectrum diagram of (a) PEEK, (b) HAP/PEEK composite, (c) 2% Fe₅₀Ni₅₀/HAP/PEEK composite and (d) 5% Fe₅₀Ni₅₀/HAP/PEEK composite after 7 days of immersion in SBF solution.

Fig. 10 The formation of apatite.

Fig. 11 The dependency of strain to failure on $Fe₅₀Ni₅₀%$ in the HAP/ PEEK composites

oxidation peaks and reduction peaks, and the peak current of the oxidation peak reached 0.0457 A, indicating that the electrochemical activity of $Fe₅₀Ni₅₀$ is very high.

3.3 Contact angle studies

The contact angle of the biocomposite can reflect the wetting properties of the material,^{30–33} while the wetting performance is directly related to the wear of the material surface. The results of contact angle studies are shown in Fig. 7. The four materials are all hydrophilic materials. The contact angles of PEEK and HAP/ PEEK are 75.21° and 75.88°, respectively. After adding 2% and 5% FeNi powder, the contact angle of the composite is reduced to 55.85° and 50.54° , respectively. According to Fig. 6, FeNi powder has good electrochemical properties and surface energy. FeNi enables the surface of biological composites to have a higher surface free energy, which increases the surface tension difference with the liquid, thus improving the material's wettability and reducing wear.

3.4 Biocompatibility evaluation

In Fig. 8a–d were SEM images of PEEK, HAP/PEEK, 2% Fe₅₀Ni₅₀/ HAP/PEEK, and 5% Fe₅₀Ni₅₀/HAP/PEEK samples immersed in SBF solution for 7 days. After SBF solution immersion, no significant changes in the surface of PEEK. P and Ca elements are also not found in Fig. 9a, with only a few impurities reflecting the biological inertness of the PEEK material. The surface of HAP/PEEK was formed with micron crystal shape, and it was found that these crystals are separated from each other by high magnification and did not form into continuous sheets. The composition of these crystals was determined to be apatite by combining the P and Ca ratios in Fig. 9 energy spectrometer. Continuous layer structure with certain thickness

Fig. 12 The Hardness of PEEK, HAP/PEEK composites, FeNi/HAP/PEEK composites.

was formed on the surface of 2% $Fe_{50}Ni_{50}/HAP/PEEK$ and 5% $Fe_{50}Ni_{50}/HAP/PEEK$ samples. Meanwhile, granular $Fe_{50}Ni_{50}$ powder particles and rod-like apatite could be clearly seen on both samples. Among them, the crystal particle size on the surface of 5% $Fe_{50}Ni_{50}/HAP/PEEK$ samples was the largest. With the introduction of the HAP, the PEEK surface contains a large number of Ca^{2+} , which can induce a nuclear growth of the phosphorite crystals. As a result of electrostatic action, $\mathrm{HPO_4}^{2-},$ OH^- and Ca^{2+} in SBF solution will continuously accumulate on the material surface to form apatite crystals.³⁴ Fig. 10 shows the physical model of apatite formation on the composite surface. The introduction of HAP can improve the biocompatibility of PEEK.¹⁰ FeNi powder will not interfere with the production of apatite crystals on PEEK surface, but will also increase the electrochemical activity of the materials and promote the formation of crystallization process.

3.5 Mechanical performance evaluation

Fig. 11 reflected the tensile properties of the composite after the $Fe₅₀Ni₅₀$ powders was composited into HAP/PEEK. Due to the HAP powders composite material in PEEK, the elongation of HAP/PEEK material decreased greatly and the material was brittle. In Fig. 11, the tensile curve of HAP/PEEK material was linear under slight strain, the material was in elastic deformation stage, the material fracture was brittle fracture, and the breaking strength was 43.02 MPa. After compounding $Fe_{50}Ni_{50}$ powders in HAP/PEEK material, the elongation of the composite material was improved due to the pinning effect of the powders on microcracks. However, due to the small particle size of $Fe₅₀Ni₅₀$ nanopowders, its microcracking effect was small. When the powders content was small, the tensile curve of the composite was not significant. Fig. 11 showed that when the $Fe₅₀Ni₅₀$ nanopowders content was 2%, the effect of the powders on the overall tensile curve of the composite was not significant. When the content of $Fe_{50}Ni_{50}$ nanopowders was 5%, the elongation of the composite was significantly improved. When the elongation was 0.08%, the stress values of HAP/PEEK, 2% $Fe_{50}Ni_{50}/HAP/PEEK$ and 5% $Fe_{50}Ni_{50}/HAP/PEEK$ were 43.02 MPa, 41.85 MPa and 35.89 MPa, respectively. **PSC Advances**
 $\frac{1}{2}$ **CR** $\frac{1}{2}$

For bone implant materials, it is desirable that the material has a certain hardness to protect the artificial bone from being easily damaged when subjected to physical external forces. Fig. 12 reflected the change in hardness properties of composites after $Fe_{50}Ni_{50}$ powders was compounded into HAP/PEEK. Compared with the tensile properties, the $Fe₅₀Ni₅₀$ powders had a significant effect on the hardness of the composite. The hardness of HAP/PEEK, 2% Fe₅₀Ni₅₀/HAP/PEEK and 5% $Fe₅₀Ni₅₀/HAP/PEEK$ were 30.8 HBa, 41.8 HBa and 38.8 HBa, respectively.

Fig. 13 was a hysteresis loop of the nano $Fe_{50}Ni_{50}$ soft magnetic alloy powders prepared at room temperature. The abscissa was the applied magnetic field strength and the ordinate was the magnetization. Fig. 14 was the hysteresis loop of nano $Fe₃O₄$ powders prepared by Yan Wei at room temperature.³⁵ Among them, the saturation magnetizations of the four powders a, b, c, and d were 50.61, 61.36, 56.05, 55.43 emu $\rm g^{-1}$, respectively. As can be seen from Fig. 13, the M_s of the Fe₅₀Ni₅₀ powders was 70 emu $\rm g^{-1}$, which was significantly higher than that of the Fe₃O₄ powders. The hysteresis loop of the $Fe_{50}Ni_{50}$ powders with better magnetic properties added to the HAP/PEEK composite was shown in Fig. 15. The magnetic properties of the composite material with 5% content were better than those of the composite material with 2% content. According to the percolation theory studied by Ruru Bai, the magnetically permeable powders formed a pathway as shown in Fig. 16 in the matrix. With the increase of the content of magnetically permeable Paper

Access Article on 2019. This vasca algorithm and the internal on 2019 and the common content of the common content of the common c

Fig. 15 Room temperature hysteresis loop of HAP/PEEK composite with 2% Fe $_{50}$ Ni₅₀ powders and 5% Fe $_{50}$ Ni₅₀ powders.

Fig. 16 Magnetically permeable powders forms a pathway in the resin matrix.¹⁸

powders, the composite material would experience the nonmagnetic permeability zone, the magnetic permeability seepage zone and the magnetic permeability saturation zone.³⁶ The composite magnetic powders prepared in this paper had a small amount of magnetic powders, and the spacing between the powders was large, and it was difficult to form a passage between the powders, so the magnetic permeability was still small. However, the M_s of 2% Fe₅₀Ni₅₀/HAP/PEEK and 5% $Fe_{50}Ni_{50}/HAP/PEEK$ materials reached 1.5 emu g^{-1} and 3 emu $\rm g^{-1},$ respectively, with weak magnetic properties.

4. Conclusion

 $Fe_{50}Ni_{50}$ alloy nanopowders and $Fe_{50}Ni_{50}/HAP/PEEK$ composites were prepared by liquid phase chemical reduction method and liquid phase mixing method. The prepared $Fe₅₀Ni₅₀$ alloy nanopowders had a particle size of about 100 nm and had good chemical activity and magnetic properties. The M_s of Fe₅₀Ni₅₀ alloy powders was 70 emu g^{-1} , which was significantly higher than that of Fe₃O₄ powders. Fe₅₀Ni₅₀ nanopowders in Fe₅₀Ni₅₀/ HAP/PEEK composites were uniformly distributed in the matrix in the form of individual particles, achieving nano-level dispersion. With the increase of $Fe₅₀Ni₅₀$ alloy powders content, the magnetic properties of the composites are significantly enhanced. The M_s of 2% Fe₅₀Ni₅₀/HAP/PEEK and 5% $Fe₅₀Ni₅₀/HAP/PEEK$ materials reached 1.5 emu $g⁻¹$ and 3 emu $\rm g^{-1},$ respectively, with weak magnetic properties.

The biocompatibility of $Fe_{50}Ni_{50}/HAP/PEEK$ composites was significantly better than that of PEEK and HAP/PEEK materials. The elongation and hardness of composites were improved due to the pinning and dispersion strengthening effects of $Fe_{50}Ni_{50}$ powders on microcracks. The 2% Fe₅₀Ni₅₀/HAP/PEEK composite had the best comprehensive performance, and its biocompatibility was good. The contact angle was only 55.85°. The M_s reached 1.5 emu g^{-1} and the hardness reached 42 HBa.

Conflicts of interest

There are no conflicts to declare.

References

- 1 J. P. Schmitz and J. O. Hollinger, Clin. Orthop. Relat. Res., 1986, 299–308.
- 2 T. W. Bauer and G. F. Muschler, Clin. Orthop. Relat. Res., 2000, 10–27.
- 3 S. M. Kurtz and J. N. Devine, Biomaterials, 2007, 28, 4845– 4869.
- 4 D. J. Jaekel, D. W. MacDonald and S. M. Kurtz, J. Mech. Behav. Biomed. Mater., 2011, 4, 1275–1282.
- 5 M. F. Arif, S. Kumar, K. M. Varadarajan and W. J. Cantwell, Mater. Des., 2018, 146, 249–259.
- 6 C. H. Rivard, S. Rhalmi and C. Coillard, J. Biomed. Mater. Res., 2002, 62, 488–498.
- 7 N. Sheiko, P. Kekicheff, P. Marie, M. Schmutz, L. Jacomine and F. Perrin-Schmitt, Appl. Surf. Sci., 2016, 389, 651–665.
- 8 N. J. Hallab, Q. B. Bao and T. Brown, Eur. Spine J., 2013, 22, 2740–2751.
- 9 K. B. Sagomonyants, M. L. Jarman-Smith, J. N. Devine, M. S. Aronow and G. A. Gronowicz, Biomaterials, 2008, 29, 1563–1572.
- 10 H. Zhou and J. Lee, Acta Biomater., 2011, 7, 2769–2781.
- 11 S. C. Yu, K. P. Hariram, R. Kumar, P. Cheang and K. K. Aik, Biomaterials, 2005, 26, 2343–2352.
- 12 K. L. Wong, C. T. Wong, W. C. Liu, H. B. Pan, M. K. Fong, W. M. Lam, W. L. Cheung, W. M. Tang, K. Y. Chiu, K. D. K. Luk and W. W. Lu, Biomaterials, 2009, 30, 3810– 3817.
- 13 L. X. Wang, S. He, X. M. Wu, S. S. Liang, Z. L. Mu, J. Wei, F. Deng, Y. Deng and S. C. Wei, Biomaterials, 2014, 35, 6758–6775.
- 14 S. Guba, B. Horvath and I. Szalai, J. Magn. Magn. Mater., 2017, 444, 173–177.
- 15 F. Crippa, T. L. Moore, M. Mortato, C. Geers, L. Haeni, A. M. Hirt, B. Rothen-Rutishauser and A. Petri-Fink, J. Magn. Magn. Mater., 2017, 427, 212–219.
- 16 D. E. Igartua, P. L. Azcona, C. S. Martinez, S. D. V. Alonso, V. L. Lassalle and M. J. Prieto, Toxicol. Appl. Pharmacol., 2018, 358, 23–34.
- 17 J. H. Huang, W. Liu, Y. J. Liang, L. Li, L. Duan, J. L. Chen, F. Y. Zhu, Y. X. Lai, W. M. Zhu, W. You, Z. F. Jia, J. Y. Xiong and D. P. Wang, Mater. Sci. Eng., C, 2018, 87, 70–77. Open Access Articles. Published on 2019. Article 2019. Downloaded on 2019. This article is like the set of the s
	- 18 P. Bury, J. Kudelcik, S. Hardon, M. Kubovcikova, M. Timko and P. Kopcansky, Phys. Procedia, 2015, 75, 1029–1034.
	- 19 A. Sunny, K. S. A. Kumar, V. Karunakaran, M. Aathira, G. R. Mutta, K. K. Maiti, V. R. Reddy and M. Vasundhara, Nano-Struct. Nano-Objects, 2018, 16, 69–76.
	- 20 S. Yamaguchi-Sekino, T. Kira, M. Sekino and M. Akahane, Bioelectromagnetics, 2019, 40, 16–26.
- 21 Y. Xia, J. Sun, L. Zhao, F. Zhang, X. J. Liang, Y. Guo, M. D. Weir, M. A. Reynolds, N. Gu and H. H. K. Xu, Biomaterials, 2018, 183, 151–170.
- 22 T. Calcagnotto, M. M. B. Schwengber, C. C. De Antoni, D. L. de Oliveira, T. M. Vago and J. Guilinelli, Ann. Maxillofac. Surg., 2017, 7, 18–24.
- 23 J. Zhang, C. Ding, L. Ren, Y. Zhou and P. Shang, Prog. Biophys. Mol. Biol., 2014, 114, 146–152.
- 24 Q. C. Yan, N. Tomita and Y. Ikada, Med. Eng. Phys, 1998, 20, 397–402.
- 25 R. Leesungbok, S. J. Ahn, S. W. Lee, G. H. Park, J. S. Kang and J. J. Choi, J. Oral Implantol., 2013, 39, 248–255.
- 26 A. Ali, H. Zafar, M. Zia, I. Ul Haq, A. R. Phull, J. S. Ali and A. Hussain, Nanotechnol., Sci. Appl., 2016, 9, 49–67.
- 27 V. L. Kurichenko, D. Y. Karpenkov, A. Y. Karpenkov, M. B. Lyakhova and V. V. Khovaylo, J. Magn. Magn. Mater., 2019, 470, 33–37.
- 28 Z. H. Zhu, H. Zhao and H. Song, Mater. Chem. Phys., 2016, 172, 173–178.
- 29 T. Kokubo and H. Takadama, Biomaterials, 2006, 27, 2907– 2915.
- 30 B. Yang, S. Q. Zhang, S. S. Li, H. F. Yao, W. N. Li and J. H. Hou, Adv. Mater., 2019, 31, 1804657.
- 31 D. P. Suhas, T. M. Aminabhavi and A. V. Raghu, Appl. Clay Sci., 2014, 101, 419–429.
- 32 D. P. Suhas, T. M. Aminabhavi and A. V. Raghu, Polym. Eng. Sci., 2014, 54, 1774–1782.
- 33 D. P. Suhas, T. M. Aminabhavi, H. M. Jeong and A. V. Raghu, RSC Adv., 2015, 5, 100984–100995.
- 34 D. N. Mohd, A. A. R. Hussein, K. M. R. Abdul and S. Syafiqah, Ann. Anat., 2018, 220, 29–37.
- 35 Y. Wei, B. Han, X. Y. Hu, Y. H. Lin, X. Z. Wang and X. L. Deng, Procedia Eng., 2012, 27, 632–637.
- 36 R. R. Bai, Z. H. Zhu, H. Zhao, S. H. Mao and Q. Zhong, J. Magn. Magn. Mater., 2017, 433, 285–291.