

Showcasing research from Dr. Xiang Zhu's group at State Key Laboratory for Oxo Synthesis and Selective Oxidation, Suzhou Research Institute of Lanzhou Institute of Chemical Physics, China, and Dr. Yong Chen's group at Key Laboratory of Photochemical Conversion and Optoelectronic Materials, Technical Institute of Physics and Chemistry, China

Achieving an exceptionally high loading of isolated cobalt single atoms on a porous carbon matrix for efficient visible-light-driven photocatalytic hydrogen production

A new *in situ* preparation strategy that enables the synthesis of isolated cobalt (Co) single atoms (SAs) with an exceptionally high metal loading, up to 5.9 wt%, has been developed. Due to the successful electron transfer from carbon nitride to isolated Co SAs, high-performance photocatalytic H_2 production using Co SAs as a co-catalyst was achieved.

ROYAL SOCIETY | Celebrating
OF CHEMISTRY | IYPT 2019

As featured in:

See Xiang Zhu, Lin He, Yong Chen, Sheng Dai *et al.*, *Chem. Sci.*, 2019, **10**, 2585.

rsc.li/chemical-science

Chemical Science

EDGE ARTICLE

Cite this: Chem. Sci., 2019, 10, 2585

C All publication charges for this article have been paid for by the Royal Society of Chemistry

Received 11th December 2018 Accepted 15th January 2019

DOI: 10.1039/c8sc05540h

rsc.li/chemical-science

Introduction

Single-atom catalysts (SACs) have attracted extensive attention as a new scientific frontier, effectively bridging the fields of heterogeneous and homogeneous catalysis.¹⁻⁵ Composed of isolated metal atoms dispersed on a support, SACs display distinctly different catalytic behavior to metal nanoparticles

‡ These two authors contributed equally.

Achieving an exceptionally high loading of isolated cobalt single atoms on a porous carbon matrix for efficient visible-light-driven photocatalytic hydrogen production†

Rui Shi[,](http://orcid.org/0000-0002-3973-4998) \sharp ^a Chengcheng Tian, \sharp ^b Xiang Zhu, D^{*bcd} Cheng-Yun Peng,^a Bingbao Mei,^e Li[n](http://orcid.org/0000-0001-6689-8923) He, \mathbf{D}^{*c} Xian-Long Du,^e Zheng Jiang,^e Yong Chen \mathbf{D}^{*a} and Sheng Dai \mathbf{D}^{*b}

Single-atom catalysts (SACs) have shown great potential in a wide variety of chemical reactions and become the most active new frontier in catalysis due to the maximum efficiency of metal atom use. The key obstacle in preparing SAs lies in the development of appropriate supports that can avoid aggregation or sintering during synthetic procedures. As such, achieving high loadings of isolated SAs is nontrivial and challenging. Conventional methods usually afford the formation of SAs with extremely low loadings (less than 1.5 wt%). In this work, a new in situ preparation strategy that enables the synthesis of isolated cobalt (Co) SAs with an exceptionally high metal loading, up to 5.9 wt%, is developed. The approach is based on a simple one-step pyrolysis of a nitrogen-enriched molecular carbon precursor (1,4,5,8,9,12 hexaazatriphenylene hexacarbonitrile) and CoCl₂. Furthermore, due to the successful electron transfer from carbon nitride to the isolated Co SAs, we demonstrate a high-performance photocatalytic H_2 production using Co SAs as a co-catalyst, and the evolution rate is measured to be 1180 μ mol g⁻¹ h⁻¹. We anticipate that this new study will inspire the discovery of more isolated SACs with high metal loadings, evidently advancing the development of this emerging type of advanced catalysts. EDGE ARTICLE
 (A) Check for undees **Consult School School**

(NPs) while simultaneously maximizing the metal efficiency.⁶⁻⁸ As such, they offer great potential for achieving superior catalytic activity and selectivity, particularly for systems based on noble metals.9,10 However, it has been well documented that the surface free energy of metals increases signicantly with decreasing particle size, promoting aggregation or sintering during synthetic procedures.11,12 As such, conventional synthetic approaches generally afford the formation of isolated SAs with extremely low metal loadings (less than 1.5 wt%) since small loadings can help to avoid aggregation and prevent the formation of metal nanocrystals. This has signicantly impeded the development of SACs on account of the limited studies of their macroscopic properties.13–¹⁷ Therefore, while the synthesis of uniform and stable SACs with high metal loadings is highly desired, it nevertheless remains a great challenge in this field.

Herein, we report a new in situ synthesis approach for the preparation of isolated cobalt (Co) SAs with a significantly large metal loading and further demonstrate their application as an efficient co-catalyst for visible-light-driven photocatalytic H_2 evolution. Photocatalytic hydrogen $(H₂)$ evolution from water splitting represents one of the promising methods for effectively storing renewable solar energy in the chemical form and has attracted tremendous attention.¹⁸⁻²¹ Loading a co-catalyst is highly required in many systems, where the co-catalyst could promote efficient charge separation from the semiconductor to

a Key Laboratory of Photochemical Conversion and Optoelectronic Materials, HKU-CAS Joint Laboratory on New Materials, Technical Institute of Physics and Chemistry, Chinese Academy of Sciences, Beijing 100190, China. E-mail: chenyong@mail.ipc.ac. cn

b Chemical Sciences Division, Oak Ridge National Laboratory, Oak Ridge, TN 37831, USA. E-mail: dais@ornl.gov

c State Key Laboratory for Oxo Synthesis and Selective Oxidation, Suzhou Research Institute of Lanzhou Institute of Chemical Physics, Chinese Academy of Sciences, Lanzhou, 730000, China. E-mail: helin@licp.cas.cn

d Department of Chemistry, Texas A&M University, College Station, Texas 77843, USA. E-mail: zhuxiang.ecust@gmail.com; xiang@licp.cas.cn

e Shanghai Synchrotron Radiation Facility, Shanghai Institute of Applied Physics, Chinese Academy of Sciences, Shanghai 201204, China

[†] Electronic supplementary information (ESI) available: Characterization details, XPS studies, XRD patterns, Raman spectra, N_2 adsorption-desorption curves, UV-vis diffuse reflectance images, durability tests, HAADF-STEM images, Mott–Schottky plots in the dark at frequencies of 2000 and 3000 Hz, Scheme S1 and lifetimes of TIRA decays under 420 nm and 600 nm irradiation, respectively. See DOI: 10.1039/c8sc05540h

Chemical Science Edge Article

the co-catalyst's surface.²²⁻²⁶ Although great progress has been achieved, the synthesis of SACs, especially non-noble metal SACs, for photocatalytic H_2 evolution remains rare.²⁷⁻³⁰ The key to our success lies in a simple one-step pyrolysis of a nitrogenenriched molecular carbon precursor (1,4,5,8,9,12-hexaazatriphenylene hexacarbonitrile) and $CoCl₂$, whereas isolated Co SAs were synthesized and immobilized on a porous nitrogendoped carbon support. The loading of Co SAs was as high as 5.9 wt%. Based on the successful electron transfer from the photosensitizer $g - C_3N_4$ (ref. 31 and 32) to Co SAs, a highperformance photocatalytic H_2 production was achieved, suggesting promising catalysis applications of this new material.

Experimental

Preparation of $g - C_3N_4$

The photosensitizer $g - C_3N_4$ was prepared through a typical thermal polymerization procedure.²⁷ In a typical process, 5 g of urea was put into an alumina crucible and heated to 823 K for 4 h under an air atmosphere. The resultant yellow powder was washed with deionized water and ethanol, and then dried.

Preparation of Co–N–C

A mixture of 1,4,5,8,9,12-hexaazatriphenylene hexacarbonitrile (HAT-6CN, 116 mg) and anhydrous $CoCl₂$ (392 mg) (molar ratio: 1 : 10) was added into a quartz ampoule inside a glove box. The ampoule was then evacuated, vacuum-sealed, and then heated at 450 °C for 20 h and 600 °C for another 20 h. The heating rate is 5 $^{\circ}$ C min $^{-1}$. The obtained black powder was subsequently ground and washed thoroughly with dilute 2 M HCl, water, acetone and dichloromethane. The desired product was dried in an oven at 80 \degree C.

Different contents of $CoCl₂$ (1 : 15, 1 : 20, 1 : 30, molar ratio) were used towards the synthesis of Co–N–C with a diverse Co loading.

Metal free N–C was prepared in the absence of $CoCl₂$ using the above pyrolysis method.

Preparation of Co–N–C/g-C₃N₄ composites

The hybrid materials were prepared as follows: Co–N–C and $g - C_3N_4$ were mixed with a certain mass ratio and ground in an agate mortar for about 20 min.

Photoelectrochemical analysis

The electrochemical properties were obtained on a CHI 660E electrochemical work station (Chenhua Instrument, Shanghai, China) with a conventional three-electrode system. A working electrode was prepared as follows: 1 mg of the sample and 50 uL of Nafion (5% solution) were dispersed in 1 mL $CH₃CH₂OH$ by at least 2 h sonication to prepare a homogeneous catalyst colloid. Then, $100 \mu L$ of the above suspension was deposited onto 1×2 cm² indium tin oxide (ITO) glass, and then dried at room temperature for 48 h to obtain working electrodes. The prepared electrodes, a platinum flake and an Ag/AgCl (saturated KCl) electrode were used as the working, counter and reference electrodes, respectively. A 0.1 M $Na₂SO₄$ solution was employed as the electrolyte. Mott–Schottky plots were obtained under direct current potential polarization at different frequencies (2000, 3000 Hz) and at the potential range from -0.6 V to 0.4 V. Electrochemical impedance spectroscopy (EIS) was performed at an applied potential of 0.01 V versus Ag/AgCl over the frequency range of 1 MHz to 0.1 Hz.

Photocatalytic measurement

Photocatalytic H_2 evolution experiments were carried out in a 15 mL quartz tube sealed with a silicone rubber septum. In a typical photocatalytic experiment, 2 mg of the samples were suspended in an aqueous solution containing sacrificial electron donors (5 mL, 10 vol%). The system was deoxygenated with Ar for 30 min to remove the air before irradiation. A LED light source (12 W, $\lambda = 420 \pm 10$ nm) was used as the irradiation light source. The quantities of the H_2 evolution were measured using a gas chromatograph (GC-2014C, Shimadzu, with Ar as the carrier gas), which was equipped with a 5 Å molecular sieve column (3 mm \times 2 mm) and a thermal-conductivity detector. The detection of isotope D_2 is exactly the same as that of H_2 , except that the carrier gas is replaced by H_2 . The apparent quantum efficiency (AQE) was calculated according to the equation below: Operation Science (i.e., the spin of the

$$
AQE = 2 \times N_{\rm H_2}/N_{\rm P} \times 100\%,
$$

where N_{H_2} and N_{P} refer to the moles of H_2 evolved and total moles of photons absorbed by the photocatalyst, respectively.

Results and discussion

To illustrate this approach, the preparation route is shown in Scheme 1. 1,4,5,8,9,12-hexaazatriphenylene hexacarbonitrile (HAT-6CN), a nitrogen (N)-enriched molecular carbon monomer, was rationally synthesized and employed for the construction of our desired porous carbon matrix. The metal– support interaction has been proven to play a crucial role in stabilizing metal SACs. Doping rich N-based sites into carbon architectures provides a facile means to enhance this interaction, as a way to stabilize isolated metal SAs, such as $Co-N₄$ and Ni–N4.33–³⁷ Previously, we reported the successful synthesis of a N-enriched porous triazine-linked framework based on the $ZnCl₂$ -promoted ionothermal polymerization of an analogue motif, 3,7,11-trimethoxy-2,6,10-tricyano-1,4,5,8,9,12-hexaazatriphenylene (HAT-3CN, Scheme $S1\dagger$).³⁸ We hypothesized that this new type of N-doped material derived from the HAT ring

Scheme 1 Synthesis route and proposed structure for isolated Co single atoms.

could be employed as a novel support for the immobilization of SAs, for example, Co SAs. In this regard, $CoCl₂$ was used as a surrogate for $ZnCl₂$. It has been well documented that pyrolyzing aromatic ortho dinitriles at a high temperature in the presence of metal salts, like $ZnCl₂$ and $CuCl₂$, affords the formation of phthalocyanine-linked frameworks based on the condensation reaction of nitrile groups.39,40 In this context, HAT-6CN and $CoCl₂$ (1 : 10, molar ratio) were first sealed in a quartz ampoule and then pyrolyzed at 450 $^{\circ}$ C for 20 h and 600 C for another 20 h, as a way to create abundant N-doped sites inside the carbon matrix. The obtained crude material was thoroughly washed with a diluted acid solution to remove impurities. Synthetic details are presented in the experimental section.

As expected, elemental analysis indicates an extremely high N content of 21.8 wt% within the resulting material Co–N–C. Pyridinic N (398.6 eV), Co–N (399.1 eV) and pyrrolic N (400.2 eV) were observed (Fig. S1†), respectively.⁴¹ These attractive Ndoped sites may serve as anchors to stabilize Co species. To confirm this, the structure of $Co-N-C$ was first examined by Xray diffraction (XRD), and we did not obtain any diffraction peaks associated with large Co species (Fig. S2†), suggesting that the sizes of Co species within the architecture of Co–N–C are extremely small, potentially in terms of small nanoclusters or even single atoms. The observed broad peak originates from the partially graphitized structure of Co–N–C. Both the D band and graphitic G band were clearly observed in its Raman spectra (Fig. S3†). Additionally, as shown in the Co 2p XPS spectrum (Fig. S1†), the binding energies at 781.0 and 796.2 eV are assigned to Co $3p_{1/2}$ (Co²⁺) and Co $3p_{3/2}$ (Co²⁺), respectively, indicating the existence of Co–N moieties.⁴² The atomic ratio of C and N was estimated to be 1 : 0.24 by energy dispersive X-ray spectroscopy analysis (Fig. S4†), which is basically consistent with the results of elemental analysis. Elemental mapping results, as depicted in Fig. S5,† clearly indicate the existence of Co, N and C elements in the sample.

To get a better understanding of these Co species, we then performed aberration corrected high-angle annular dark-field scanning transmission electron microscopy (HAADF-STEM). As anticipated, abundant Co SAs were clearly observed (Fig. 1b), further supporting the XRD results. X-ray absorption spectra (XAS) measurements were then carried out, aiming to identify their structures. The difference in the intensity and the position in the Co K-edge X-ray absorption near-edge structure (XANES) spectra of Co–N–C and standard Co foil implies that the Co species are in different environments (Fig. 1d).⁴² The Co extended XAFS (EXAFS) spectra (Fig. 1e and f) were therefore collected to determine their local structures. In comparison with those of Co foil, the absence of a peak at $ca. 2.1 \text{ Å}$, ascribed to the Co–Co bond (Fig. 1e), suggests that Co species within Co– N–C are not metallic Co. Instead, the new peak at ca . 1.4 \AA (Fig. 1f) indicates that the Co species are coordinated with nitrogen atoms, thus implying that the Co–N coordination may account for the successful stabilization of these Co SAs.⁴³ The coordination number for isolated Co centers is also quantified by least-squares EXAFS curve-fitting analysis (Fig. S6 and Table $S1\dagger$). The fitting results demonstrated that the coordination

Fig. 1 TEM (a and c) and HAADF-STEM (b) images of Co–N–C. Normalized Co K-edge XANES spectra of Co–N–C in reference to Co foil (d). (b) k3-weighted Fourier-transform Co K-edge EXAFS spectra of Co foil (e) and Co–N–C (f), respectively.

number of Co centers in the first coordination sphere of Co-N-C is close to 4 at a distance of 1.46 \AA based on the absorptionbackscattering pair of Co–N. For standard Co foil, the coordination number of the Co atom in the first coordination sphere is 12 at a distance of 2.21 \AA based on the absorption-backscattering pair of Co–Co. The difference in coordination environments of the Co atom between Co–N–C and Co foil further excludes the formation of Co-Co bands and confirms the presence of the $CoN₄$ configuration. Taken together, HAADF-STEM and XANES as well as XRD results clearly confirm the successful synthesis of isolated Co SAs on this new HAT-derived nitrogen-rich carbon support.

The content of Co SAs was subsequently detected by inductively coupled plasma atomic emission spectroscopy (ICP-AES). Surprisingly, an extremely high loading of 4.2 wt% of Co was determined, suggesting that this new simple *in situ* preparation approach is a unique method that enables the synthesis of SAs with a large metal loading. Furthermore, as determined using the N_2 adsorption–desorption isotherms at 77 K, Co–N–C exhibits an attractive porous nature with a high Brunauer– Emmett–Teller (BET) surface area of 268 m² g⁻¹ (Fig. S7†), suggesting promising catalysis applications.

Inspired by the above success, we examined the photocatalytic H₂ production, using polymeric $g-C_3N_4$ as a photosensitizer and Co–N–C as a co-catalyst. Triethanolamine (TEOA) was employed as a sacrificial agent. As shown in the UV-vis studies (Fig. S8†), pristine g- C_3N_4 exhibits an absorption edge at

440 nm and a corresponding band gap of ca. 2.8 eV. A slight bathochromic shift of the photoabsorption edge was observed for the $Co-N-C/g-C_3N_4$ composite, where the absorption intensity was gradually enhanced with the increase of the loading of Co–N–C. This result is similar to those of previouslydeveloped metal phosphide and sulfide co-catalysts.⁴⁴ As shown in Fig. 2a, pristine $g - C_3N_4$ exhibits weak photocatalytic activity, suggesting a fast recombination of photogenerated charges.⁴⁵ In our work, $g - C_3N_4$ was synthesized through a typical thermal polymerization of urea, which exhibits photocatalytic activity with a H₂ evolution of 22 µmol g^{-1} h⁻¹ under LED visible light irradiation (12 W, $\lambda = 420 \pm 10$ nm). This performance is lower than that of other $g - C_3N_4$ materials in the literature. We reasoned that the difference in the light source may account for this decrease since a light source higher than 300 W is widely used (ESI Table S3†). Co–N–C/g-C₃N₄ with 35 wt% content of Co–N–C, shows the highest H_2 evolution rate, up to 920.0 µmol $\rm g^{-1}$ h $^{-1}$, which is *ca*. 41 fold higher than that of pristine g-C₃N₄, despite the fact that the photocatalytic activity of Co–N–C alone is very low. A further increase in the Co–N–C loading results in a decrease of photocatalytic performance because excess Co–N– C may shield the incident light. As a result, $Co-N-C/g-C_3N_4$ with 35 wt% content of Co–N–C was used as the optimized material for the following studies.

The sacrificial reagent effect on the photocatalytic performance was then examined. Triethylamine (TEA) and methanol $(CH₃OH)$ were investigated. Fig. 2b summarizes the results and indicates that the sacrificial reagent plays an important role in achieving high-performance catalytic activity on Co–N–C/g- C_3N_4 . The use of TEOA affords the best photocatalytic H₂ production. In addition, negligible H_2 can be detected when the sacrificial reagent and light are absent, suggesting that the generation of H_2 is driven by the photocatalytic process. Theoretically, the electronic band structures of $g-C_3N_4$ are suitable for visible-light-driven overall water splitting. However, enormous studies have demonstrated that $g - C_3N_4$ suffers from rapid recombination of photogenerated carriers. To solve this problem, electron sacrificial agents have been frequently added into the reaction system to consume the photogenerated holes, thereby increasing the survival time of photogenerated electrons. The long-lived photogenerated electrons are able to reach the surface active sites to initiate the photocatalytic redox reaction. Electron sacrificial reagents are used to achieve H_2

Fig. 2 (a) Photocatalytic H₂ evolution rate for various contents of Co– N–C/g-C3N4 composites from 10 vol% TEOA aqueous solution (b) comparison of photo-generating H_2 under different conditions.

evolution in most research studies, although very few literature studies have reported that $g - C_3N_4$ can exhibit the overall water splitting reaction, as shown in ESI Table S3.† The controlled metal-free N-doped carbon sample (N–C), which was prepared in the absence of $CoCl₂$, shows very poor catalytic activity, indicating that Co SAs are intrinsic active sites. To confirm whether the as-generated H_2 is from water or TEOA, a reference evaluation using a pure TEOA solvent instead of the TEOA aqueous solution (10% in volume) was performed (Fig. S9†). As expected, there was almost no H_2 evolution when TEOA alone was used, suggesting that water was the source of H_2 during the photocatalytic reaction. To get a better understanding, an isotopic experiment was further conducted. When H_2O was replaced with D_2O , D_2 was detected using He gas as the GC carrier.⁴⁶ The results demonstrate that a negative GC signal for D_2 gas was detected, but H₂ was not generated at all (Fig. S10†). Taken together, it thus can be concluded that H_2 evaluated from the photocatalytic reaction originates from the splitting of water, not TEOA. Furthermore, EIS-MS spectroscopy was employed to monitor the possible oxidation products of TEOA during photocatalytic H_2 evolution (Fig. S11†). No additional peaks of the corresponding oxidation products of TEOA, such as aldehyde and carboxylic acid, were observed, suggesting that TEOA is degraded into fragmented molecules after accepting the photogenerated holes. A durability test was subsequently performed. As shown in Fig. S12, \dagger the rate of H₂ production exhibits a slight decrease after five runs. The XRD pattern of the recovered Co–N–C/g-C₃N₄ is consistent with that of the asprepared sample (Fig. S13†). Moreover, ICP-AES results show that the content of the Co atom is only slightly reduced from 4.2% to 4.0%, where the change in the value is within the measurement error. HAADF-STEM of $Co-N-C/g-C_3N_4$ after the durability test was also examined. As expected, isolated Co SAs were clearly observed (Fig. S14†), further supporting the highperformance of catalytic stability on $Co-N-C/g-C_3N_4$. Openical Science

Atto mand a corresponding band gap of cs. 2.4 eV. A slight couldnot in one treatment should be a strength on the published on 16 January 2019. The results are computed under the second value of Costs, 20

> The synergistic effect between $g - C_3N_4$ and Co–N–C may account for the obtained enhancement of the photocatalytic H_2 evolution. To confirm this, photoluminescence (PL) emission spectroscopy, electrochemical impedance spectroscopy (EIS) and transient IR absorption spectroscopy (TIRA) were carried out to determine the electron transfer between $g-C_3N_4$ and Co-N–C. As shown in Fig. 3a, one main emission peak, attributed to the band to band recombination, appears at about 450 nm for pure g- C_3N_4 .⁴⁷ As the intensity of the emission peak is correlated with the recombination rate of photogenerated electrons and holes, it can be found that the signal intensities of **Co–N–C**/g- C_3N_4 composites are greatly inhibited, implying that the photogenerated electron–hole pairs have a better separation at the interface between $Co-N-C$ and $g-C_3N_4$.^{48,49} Moreover, an inter-
facial transition of charge carriers in $Co \ N C/C C N$ is also facial transition of charge carriers in $Co-N-C/g-C_3N_4$ is also supported by the EIS results (Fig. 3b). The semicircle diameter in the Nyquist plots of $Co-N-C/g-C_3N_4$ is smaller than that of g- C_3N_4 . A smaller arc radius of the EIS Nyquist plot suggests an effective separation of the photogenerated electron–hole pairs and fast interfacial charge transfer, which are in good accordance with the PL results.

Fig. 3 (a) PL spectra excited at 420 nm for the $Co-N-C$, g-C₃N₄ and Co–N–C/g-C₃N₄ composite, (b) EIS spectroscopy of g-C₃N₄ and Co– N–C/g-C3N4, (c) TIRA spectra of Co–N–C, g-C3N4, and Co–N–C/g- C_3N_4 excited at 600 nm, and (d) TIRA spectra of $Co-N-C$, g- C_3N_4 and $Co-N-C/g-C_3N_4$ excited at 420 nm. (e) Schematic of photogenerated charge transfer in the $Co-N-C/g-C_3N_4$ composite under visible light irradiation.

TIRA measurements are therefore performed to determine the direction of electron transfer. The time profiles of transient absorption are studied under 420 and 600 nm visible-light irradiation, respectively. For 600 nm irradiation, no photogenerated electron signals are detected for $g - C_3N_4$ (Fig. 3c). The time profiles of Co–N–C and Co–N–C/g-C₃N₄ could be fitted by two-exponential functions, and their lifetimes are summarized in Table S2.† Based on the calculated equation, the average lifetime of Co–N–C is only 3.9 ps. Comparing with Co–N–C, no significant change was observed for that of $Co-N-C/g-C_3N_4$ (4.4) ps), suggesting that photogenerated electrons cannot be transferred from Co–N–C to g -C₃N₄. When 420 nm excitation was employed, photogenerated electrons could be produced in g- C_3N_4 , and its average lifetime was 723.9 ps (Fig. 3d). Meanwhile, the lifetime of Co–N–C is still only 3.2 ps, which is about twohundredth of that of $g - C_3N_4$. Owing to the ultra-short lifetime of photogenerated electrons in Co–N–C, the absorption signal of photogenerated electrons in the $Co-N-C/g-C_3N_4$ composite mostly originated from the exited g-C $_3$ N $_4$.²⁴ Compared to pure g- C_3N_4 , the average lifetime of Co–N–C/g-C₃N₄ is significantly decreased and is only 3.4 ps. Hence, the loading of Co–N–C greatly decreases the decay lifetime of $g - C_3N_4$. This effect is attributed to an additional decay channel that is opened through electron transfer from $g-C_3N_4$ to the Co atom in

Co–N–C.^{50,51} Based on the PL, EIS and TIRA results, it can be
concluded that under 420 nm irrediction, there is an electron concluded that under 420 nm irradiation, there is an electron transfer between $g - C_3N_4$ and Co–N–C, and the direction of electron transfer is from $g - C_3N_4$ to Co–N–C.

In an effort to get a deeper insight into the transfer of photogenerated electrons from $g - C_3N_4$ to Co–N–C and determine the energy levels, we then examined the flat potentials of both samples. As displayed in Fig. S15,† the positive slopes of Mott– Schottky plots indicate that both $Co-N-C$ and $g-C_3N_4$ possess ntype semiconductor characteristics. For n-type semiconductors, it has been reported that the conduction bands (CBs) are normally $0.1-0.2$ eV deeper than the flatband potential.⁵² As such, the difference between the CB and the flat potential value is set to be 0.1 eV. The CB potentials of $Co-N-C$ and $g-C_3N_4$ were calculated to be -1.14 and -1.42 V (vs. SCE), respectively. Consequently, Co–N–C has a suitable redox potential for accepting the photoinduced electrons from $g - C_3N_4$. A possible photocatalytic mechanism was thus proposed and is shown in Fig. 3e. When $g - C_3N_4$ is modified by the co-catalyst Co–N–C, the photogenerated electrons in $g - C_3N_4$ will be transferred to isolated Co atoms in Co–N–C on account of the difference in the CB position. Then, the electrons will accumulate on Co atoms and participate in H_2 evolution. The electron sacrificial agent will be oxidized by photogenerated holes on the valence band (VB) of $g-C_3N_4$. Therefore, an effective photogenerated charge carrier separation can be achieved, resulting in the enhanced photocatalytic H_2 production.

Based on the aforementioned results, we further attempted the in situ synthesis to achieve a higher loading of Co SAs by simply increasing the use of $CoCl₂$. Significantly, the Co SA loading can be enhanced to 5.9 wt% when 1 : 30 molar ratio of HAT-6CN and $CoCl₂$ was employed (Fig. 4a). The HAADF-STEM

Fig. 4 (a) The synthesis of Co SAs by varying the molar ratio of HAT-6CN and CoCl₂ (from $1:10$ to $1:30$); (b) the H₂ evolution rate of Co-N–C with various Co loadings; (c) XRD patterns of Co–N–Cs prepared by varying the molar ratios and (d) HAADF-STEM image of Co–N–C with 5.9 wt% Co SACs [HAT-6CN : $CoCl_2 = 1 : 30$]

result successfully confirms the rich abundance of isolated Co SAs on the carbon matrix (Fig. 4d). As a result, the H_2 evolution rate was improved from 920.0 µmol g^{-1} h⁻¹ (4.2 wt% Co) to 1180 µmol g^{-1} h⁻¹ (Fig. 4b). A negligible difference in the H₂ evolution rate was obtained for the samples with 5.6 and 5.9 wt% Co loading. We further calculated the AQE determination at 420 nm for Co–N–C with 5.6 wt% of Co SACs. The AQE value for H_2 evolution in 4 h was calculated to be 2.53%. In the meantime, the calculated turnover frequency (TOF) for single Co atom active sites reaches 3.6 h^{-1} . A comparison of the stateof-art performance of other SACs and $g - C_3N_4$ materials is shown in the Tables S3 and S4.† The photocatalytic activity of H_2 evolution of Co–N–C is better than that of most composites reported in the literature. We reasoned that there could be two factors affecting the photocatalytic performance of our Co SACs. One is the loading of Co SACs, the other is the degree of graphitization of our support. The former can improve the number of catalytic active sites, and the latter may promote the transfer rate of photogenerated electrons. As the loading of Co SACs increases, more N-doped sites within the support need to be served as anchors to stabilize Co atoms, which may affect the delocalization π bond of the support. As a result, there could be a threshold for the effect of Co loading on the photocatalytic performance. As shown in Fig. 4a and b, the difference in photocatalytic activity of Co SACs is not signicant when the Co loading is over 5.6 wt%. Openical Science

State Online discussions Article. Published on 16 January 2019. Download access Form and the same are proported under the same and the same are the same and the same are the same and the same and the sam

Conclusions

In summary, a new in situ synthesis strategy was successfully developed for the preparation of isolated Co SAs with extremely high metal loadings. A simple one-step pyrolysis of a N-enriched molecular carbon monomer (1,4,5,8,9,12-hexaazatriphenylene hexacarbonitrile) and CoCl₂ affords the generation isolated Co SAs on a porous carbon support with high loadings, up to 5.9 wt%. Furthermore, based on the successful electron transfer from the photosensitizer graphitic carbon nitride to isolated Co SAs, the resulting new material shows a high catalytic activity for visible-light-driven photocatalytic H_2 production with an evolution rate of 1180 μ mol $\rm{g^{-1}\,h^{-1}}.$ We anticipate that this new study could advance the development of new SACs with high metal loadings for catalysis applications.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

We thank the financial support from the Strategic Priority Research Program of the Chinese Academy of Sciences (XDB17000000) and National Natural Science Foundation of China (21773275). SD was supported by the Division of Chemical Sciences, Geosciences, and Biosciences, Office of Basic Energy Sciences, US Department of Energy. Y. C. acknowledges the financial support from the K. C. Wong Education Foundation and CAS-Croucher Funding Scheme for Joint Laboratories.

X. Z. thanks the start-up financial support from the Chinese Academy of Sciences. L. H. was supported by Foundation research project of Jiangsu Province (BK20171242), and National Natural Science Foundation of China (91645118).

Notes and references

- 1 L. Liu and A. Corma, Chem. Rev., 2018, 118, 4981–5079.
- 2 X.-F. Yang, A. Wang, B. Qiao, J. Li, J. Liu and T. Zhang, Acc. Chem. Res., 2013, 46, 1740–1748.
- 3 J. Liu, ACS Catal., 2017, 7, 34–59.
- 4 L. Nie, D. Mei, H. Xiong, B. Peng, Z. Ren, X. I. P. Hernandez, A. DeLaRiva, M. Wang, M. H. Engelhard, L. Kovarik, A. K. Datye and Y. Wang, Science, 2017, 358, 1419–1423.
- 5 M. Flytzani-Stephanopoulos and B. C. Gates, Annu. Rev. Chem. Biomol. Eng., 2012, 3, 545–574.
- 6 H. Zhang, W. Zhou, T. Chen, B. Guan, Z. Li and X. Lou, Energy Environ. Sci., 2018, 11, 1980–1984.
- 7 H. Zhang, P. An, W. Zhou, B. Guan, P. Zhang, J. Dong and X. Lou, Sci. Adv., 2018, eaao6657.
- 8 H. Zhang, L. Yu, T. Chen, W. Zhou and X. Lou, Adv. Funct. Mater., 2018, 28, 1807086.
- 9 J. Jones, H. Xiong, A. T. DeLaRiva, E. J. Peterson, H. Pham, S. R. Challa, G. Qi, S. Oh, M. H. Wiebenga, X. I. Pereira Hernández, Y. Wang and A. K. Datye, Science, 2016, 353, 150–154.
- 10 B. Qiao, A. Wang, X. Yang, L. F. Allard, Z. Jiang, Y. Cui, J. Liu, J. Li and T. Zhang, Nat. Chem., 2011, 3, 634–641.
- 11 A. Corma, P. Concepción, M. Boronat, M. J. Sabater, J. Navas, M. J. Yacaman, E. Larios, A. Posadas, M. A. López-Quintela, D. Buceta, E. Mendoza, G. Guilera and A. Mayoral, Nat. Chem., 2013, 5, 775–781.
- 12 K. Ding, A. Gulec, A. M. Johnson, N. M. Schweitzer, G. D. Stucky, L. D. Marks and P. C. Stair, Science, 2015, 350, 189–192.
- 13 H. Li, L. Wang, Y. Dai, Z. Pu, Z. Lao, Y. Chen, M. Wang, X. Zheng, J. Zhu, W. Zhang, R. Si, C. Ma and J. Zeng, Nat. Nanotechnol., 2018, 13, 411.
- 14 P. Liu, Y. Zhao, R. Qin, S. Mo, G. Chen, L. Gu, D. M. Chevrier, P. Zhang, Q. Guo, D. Zang, B. Wu, G. Fu and N. Zheng, Science, 2016, 352, 797–800.
- 15 P. Yin, T. Yao, Y. Wu, L. Zheng, Y. Lin, W. Liu, H. Ju, J. Zhu, X. Hong, Z. Deng, G. Zhou, S. Wei and Y. Li, Angew. Chem., Int. Ed., 2016, 55, 10800–10805.
- 16 Y. Chen, S. Ji, C. Chen, Q. Peng, D. Wang and Y. Li, Joule, 2018, 2, 1242–1264.
- 17 A. Wang, J. Li and T. Zhang, Nat. Rev. Chem., 2018, 2, 65–81.
- 18 T. Hisatomi, J. Kubota and K. Domen, Chem. Soc. Rev., 2014, 43, 7520–7535.
- 19 N. S. Lewis, Science, 2016, 351, aad5117.
- 20 J. Ran, J. Zhang, J. Yu, M. Jaroniec and S. Z. Qiao, Chem. Soc. Rev., 2014, 43, 7787–7812.
- 21 H. Wang, L. Zhang, Z. Chen, J. Hu, S. Li, Z. Wang, J. Liu and X. Wang, Chem. Soc. Rev., 2014, 43, 5234–5244.
- 22 A. Indra, P. W. Menezes, K. Kailasam, D. Hollmann, M. Schroder, A. Thomas, A. Bruckner and M. Driess, Chem. Commun., 2016, 52, 104–107.
- 23 A. Indra, A. Acharjya, P. W. Menezes, C. Merschjann, D. Hollmann, M. Schwarze, M. Aktas, A. Friedrich, S. Lochbrunner, A. Thomas and M. Driess, Angew. Chem., Int. Ed., 2017, 56, 1653–1657.
- 24 M. Zhu, S. Kim, L. Mao, M. Fujitsuka, J. Zhang, X. Wang and T. Majima, J. Am. Chem. Soc., 2017, 139, 13234–13242.
- 25 J. Ran, B. Zhu and S. Z. Qiao, Angew. Chem., Int. Ed., 2017, 56, 10373–10377.
- 26 F. Wen and C. Li, Acc. Chem. Res., 2013, 46, 2355–2364.
- 27 Y. Cao, S. Chen, Q. Luo, H. Yan, Y. Lin, W. Liu, L. Cao, J. Lu, J. Yang, T. Yao and S. Wei, Angew. Chem., Int. Ed., 2017, 56, 12191–12196.
- 28 X. Li, W. Bi, L. Zhang, S. Tao, W. Chu, Q. Zhang, Y. Luo, C. Wu and Y. Xie, Adv. Mater., 2016, 28, 2427–2431.
- 29 J. Xing, J. F. Chen, Y. H. Li, W. T. Yuan, Y. Zhou, L. R. Zheng, H. F. Wang, P. Hu, Y. Wang, H. J. Zhao, Y. Wang and H. G. Yang, Chem.–Eur. J., 2014, 20, 2088.
- 30 X. Fang, Q. Shang, Y. Wang, L. Jiao, T. Yao, Y. Li, Q. Zhang, Y. Luo and H. L. Jiang, Adv. Mater., 2018, 30, 1705112.
- 31 X. Wang, K. Maeda, A. Thomas, K. Takanabe, G. Xin, J. Carlsson, K. Domen and M. Antonietti, Nat. Mater., 2009, 8, 76–80.
- 32 S. Cao, J. Low, J. Yu and M. Jaroniec, Adv. Mater., 2015, 27, 2150–2176.
- 33 X. Wang, Z. Chen, X. Zhao, T. Yao, W. Chen, R. You, C. Zhao, G. Wu, J. Wang, W. Huang, J. Yang, X. Hong, S. Wei, Y. Wu and Y. Li, Angew. Chem., Int. Ed., 2018, 57, 1944–1948.
- 34 K. Jiang, S. Siahrostami, T. Zheng, Y. Hu, S. Hwang, E. Stavitski, Y. Peng, J. Dynes, M. Gangisetty, D. Su, K. Attenkofer and H. Wang, Energy Environ. Sci., 2018, 11, 893.
- 35 C. Zhao, X. Dai, T. Yao, W. Chen, X. Wang, J. Wang, J. Yang, S. Wei, Y. Wu and Y. Li, J. Am. Chem. Soc., 2017, ¹³⁹, 8078– 8081.
- 36 X. Li, W. Bi, M. Chen, Y. Sun, H. Ju, W. Yan, J. Zhu, X. Wu, W. Chu, C. Wu and Y. Xie, J. Am. Chem. Soc., 2017, 139, 14889–14892.
- 37 A. Han, W. Chen, S. Zhang, M. Zhang, Y. Han, J. Zhang, S. Ji, L. Zheng, Y. Wang, L. Gu, C. Chen, Q. Peng, D. Wang and Y. Li, Adv. Mater., 2018, 30, 1706508.
- 38 X. Zhu, C. Tian, G. M. Veith, C. W. Abney, J. Dehaudt and S. Dai, J. Am. Chem. Soc., 2016, 138, 11497–11500.
- 39 J. Deng, B. Wang, Y. Shi, Q. Song, A. Wang, L. Hao, B. Luo, X. Li, Z. Wang, F. Wang and L. J. Zhi, Macromol. Chem. Phys., 2012, 213, 1051–1059.
- 40 P. Kuhn, A. Thomas and M. Antonietti, Macromolecules, 2009, 42, 319–326.
- 41 X. Zhu, T. Jin, C. Tian, C. Lu, X. Liu, M. Zeng, X. Zhuang, S. Yang, L. He, H. Liu and S. Dai, Adv. Mater., 2017, 29, 1704091.
- 42 H. Fei, J. Dong, M. J. Arellano-Jiménez, G. Ye, N. Dong Kim, E. L. G. Samuel, Z. Peng, Z. Zhu, F. Qin, J. Bao, M. J. Yacaman, P. M. Ajayan, D. Chen and J. M. Tour, Nat. Commun., 2015, 6, 8668. Edge Article

2014. A change, P. W. Mensca, C. Merselakon, 37 A Han, W. Chen, S. Zhang, X. Han, Zhang, S. Han, 2019. A change of the studients are the studients of the studients are the studients of the studients are the
	- 43 C. Gao, S. Chen, Y. Wang, J. Wang, X. Zheng, J. Zhu, L. Song, W. Zhang and Y. Xiong, Adv. Mater., 2018, 30, 1704624.
	- 44 X. Zong, H. Yan, G. Wu, G. Ma, F. Wen, L. Wang and C. Li, J. Am. Chem. Soc., 2008, 130, 7176–7177.
	- 45 X. Wang, S. Blechert and M. Antonietti, ACS Catal., 2012, 2, 1596–1606.
	- 46 S. Cao, Y. Chen, C. Hou, X. Lv and W. Fu, J. Mater. Chem. A, 2015, 3, 6096–6101.
	- 47 L. Ge and C. Han, Appl. Catal., B, 2012, 117–118, 268–274.
	- 48 F. Dong, Z. Zhao, T. Xiong, Z. Ni, W. Zhang, Y. Sun and W.-K. Ho, ACS Appl. Mater. Interfaces, 2013, 5, 11392–11401.
	- 49 Q. Xu, C. Jiang, B. Cheng and J. Yu, Dalton Trans., 2017, 46, 10611–10619.
	- 50 C. Li, Y. Du, D. Wang, S. Yin, W. Tu, Z. Chen, M. Kraft, G. Chen and R. Xu, Adv. Funct. Mater., 2017, 27, 1604328.
	- 51 R. Shi, H. F. Ye, F. Liang, Z. Wang, K. Li, Y. Weng, Z. Lin, W. F. Fu, C. M. Che and Y. Chen, Adv. Mater., 2018, 30, 1705941.
	- 52 D. Liu, J. Wang, X. Bai, R. Zong and Y. Zhu, Adv. Mater., 2016, 28, 7284–7290.