RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2020, 10, 18841

Received 18th February 2020 Accepted 10th May 2020 DOI: 10.1039/d0ra01573c

rsc.li/rsc-advances

1. Introduction

Volatile organic compounds sensors are used in a wide range of applications such as in human breath analyzers¹, and food and fruit ripening monitoring devices. Many studies have recently been devoted to the development of selective and organic vapor sensitive sensors. Among the sensors developed nowadays, we can cite metal oxides including single oxide or multi-oxide structures such as LaFeO₃,² ZnCo₂O₄,³ CuFe₂O₄/Fe₂O₃,⁴ ZnO,⁵⁻⁷ SnO₂ decorated SiO₂.⁸ The literature review for the latest achievements has shown some very promising results. Recently, metal sulfides have been studied as a new sensitive class for vapor detection. It has been shown that cadmium sulfide (CdS) films are more sensitive to ethanol than Cadmium Oxide (CdO).⁹ Nevertheless, these materials are considered toxic. It is therefore important to develop non-toxic films such as Indium Sulfide In₂S₃. Various techniques such as spray pyrolysis,^{10,11}

Thickness effect on VOC sensing properties of sprayed In₂S₃ films

R. Souissi,^{ab} N. Bouguila, ^{(b) *c} B. Bouricha,^b C. Vázquez-Vázquez, ^{(b) d} M. Bendahan^e and A. Labidi^{bf}

This work reports the thickness effect on the sensing performances of \ln_2S_3 material for some Volatile Organic Compounds (VOCs). \ln_2S_3 films were deposited on glass substrates by the spray pyrolysis technique. Different samples were prepared *via* changing the spray time in the range of 10–90 min. The film thickness varies from 0.8 µm to 6.1 µm. The X-ray diffraction results demonstrate that the \ln_2S_3 films are polycrystalline in nature and exhibit a cubic structure. Additionally, Scanning Electron Microscopy (SEM) and 3D profilometry examinations show that the surface roughness increases with the rising spray time. On the other hand, the oxygen adsorption *versus* working temperature was investigated. Sensing measurements with ethanol, methanol and acetone gases were carried out by a dynamic control of the current passing through the sensitive layers. The best sensitivity was obtained for the film matching a 70 min deposit time. An understanding of the detection mechanism based on the oxidation reaction between reduced vapors and chemisorbed oxygen was confirmed. The selectivity of the sensor was analyzed for several volatile organic compounds (VOCs).

> hydrothermal,¹² ultrasonic dispersion,¹³ Chemical Bath Deposition (CBD),¹⁴ physical vapor deposition,¹⁵ *etc.*, have been used to prepare In_2S_3 . The spray pyrolysis method has been chosen in this work. Indeed, this method, which is both simple and not expensive for the deposition of large area thin films, does not require high quality targets or vacuum and is a facile way to dope material by adding a doping element to the spray solution.¹⁶ The physical properties of the obtained In_2S_3 films depend on synthesis parameters such as deposit time, substrate temperature and spray solution flow rate.^{17,18}

> In₂S₃ is an n-type semiconductor of group III–VI with a wide energy band gap ranging from 2 to 3 eV.¹⁷⁻¹⁹ It can exist in four allotropic crystal structures as a function of temperature and pressure.²⁰ At room temperature and atmospheric pressure, In₂S₃ has been found to crystallize into the defective spinel structure β -In₂S₃, which is a stable phase and presents many sulfur vacancies V_S (donor), indium vacancies V_{In} (acceptor), and indium interstitials I_{In} (donor) in the unit cell.²⁰

> This material shows interesting optoelectronic and semiconductor sensitization properties which allow it to be used as a buffer layer in solar cells,^{21,22} a heterojunction in photovoltaic electric generators,^{23,24} biological imaging sensors²⁵ and a photodetector.^{26–28} More recently, Cai *et al.*²⁹ have demonstrated that In_2S_3 hierarchical microspheres are good candidates for fabricating practical cataluminescence ammonium sulfide sensor. In our earlier paper,³⁰ we reported the use of β -In₂S₃ thin films deposited by the spray pyrolysis technology as an ethanol sensor. We showed that the In₂S₃ layers had a fairly good sensitivity to ethanol. The optimal operating temperature

^aTunis University, Ecole Nationale Supérieure d'ingénieurs de Tunis (ENSIT), Tunisia ^bCarthage University, Laboratoire des Matériaux, Molécules et Applications IPEST, BP 51, La Marsa 2070, Tunis, Tunisia

^cGabès University, Laboratoire de Physique des Matériaux et des Nanomatériaux appliqué à l'environnement, Faculté des Sciences de Gabès, Cité Erriadh, Zrig, 6072 Gabès, Tunisia. E-mail: bouguila.nour@gmail.com

^dLaboratory of Magnetism and Nanotechnology (NANOMAG), Department of Physical Chemistry, Faculty of Chemistry, Universidade de Santiago de Compostela, 15782 Santiago de Compostela, Spain

^eAix Marseille Univ, Université de Toulon, CNRS, IM2NP, Marseille, France

^fDepartment of Physics, College of Science and Arts at Ar-Rass, Qassim University, P.O. Box 1162, Buraydah 52571, Saudi Arabia

was found to be 350 $^{\circ}$ C, the best response to 500 ppm ethanol concentration was 1.7 and the response/recovery times were about 150 s. These results are encouraging to deepen the study for enhancing sensing performances by acting on the synthesis parameters.

The aim of the present study is to investigate the influence of the thickness of sprayed In_2S_3 films on the organic vaporsensing properties. We discuss also in this paper how the oxygen adsorption/desorption phenomenon impacts the detection mechanism of the analyzed gas. The detection properties were generally deduced from DC measurements which provide information in the general sensor behavior.

2. Experimental details

2.1. Films preparation

In₂S₃ films were deposited by the spray pyrolysis technique. Glass substrates were cleaned in ethanol and rinsed in deionised water. An aqueous solution was made by a mix of Indium Chloride (InCl₃) and Thiourea (SC(NH₂)₂) with a ratio of S : In = 2. The solution was sprayed at a flow rate of 2 mL min⁻¹ onto 1 cm × 1 cm glass substrates at 340 °C within an accuracy of ± 5 °C. Nitrogen was used as a carrier gas and the flow rate was kept constant at 6 L min⁻¹. The deposit time was varied in the range of 10–90 min. The In₂S₃ formation results from a global endothermic reaction governed by the following equation:^{14,18}

$$2InCl_3 + 3SC(NH_2)_2 + 6H_2O \rightarrow In_2S_3 + 3CO_2 + 6NH_4Cl \quad (1)$$

Finally, two rectangular Au electrodes of 5 mm long and 2 mm apart are deposited on the film surface using the thermal evaporation technique under high vacuum.

2.2. Films characterization

X-ray diffraction (XRD) analyses of the films were performed using monochromatic CuK α_1 radiation (1.54056 Å) (Bruker D8 Advance diffractometer). Topography images and surface roughness were obtained with a non-contact 3D optical profilometer (Sensofar S Neox) in a white-light vertical scanning interferometry (VSI) mode and using a CFI60-2 Nikon objective lens (10x EPI, numerical aperture 0.3 and working distance 17.5 mm). The surface morphology and the chemical analysis were studied by means of scanning electron microscopy (SEM) using a Zeiss Ultra PLUS microscope endowed with an electron dispersive spectrometer (EDS).

2.3. Experimental set-up for VOC detection

To investigate gas sensing response, the In_2S_3 films were tested using the experimental set-up shown in Fig. 1.

The global gas circuit has two sub-circuits. The first is used to test the organic vapor generated using two mass-flow controllers D_1 and D_2 which are used to set the dry air flow rate and the organic vapor concentration. The dry air from flow controller D_1 is charged with vapor through a dilution bath containing a pure organic solvent. This latter is maintained at a fixed temperature in order to adjust the saturation vapor



Fig. 1 Experimental set-up for gas detection.

partial pressure. This flow is mixed with the second flow of dry air coming from the second flow controller D₂. By varying d_1 and d_2 ($d_1 + d_2$ were kept constant at 1 L min⁻¹), diverse concentrations of organic vapor can be obtained and computed using the formula:^{30,31}

$$[C](ppm) = \left(\frac{xd_1}{(1+x)d_1 + d_2}\right) \times 10^6$$
(2)

where *x* is the molar fraction of the vapor in the bottomed flask at T_{vap} , given by:

$$x = \frac{P_{\text{vap}}}{P_{\text{atm}}} \tag{3}$$

with P_{vap} the partial pressure of the vapor at a specified temperature T_{vap} , and P_{atm} the atmospheric pressure.

The total flow charged with organic vapor has been blown on the sensor for 5 min. Then the test chamber has been purged with dry air for 15 min.

A second sub-circuit is used to check oxygen adsorption/ desorption phenomenon. Since the test chamber is dynamic, the gases are controlled at 1 L min⁻¹ flow rate. Nitrogen (0% oxygen atmosphere) is sent along the third arm D₃. Firstly, the flow loaded with dry air (20% oxygen atmosphere) was sent along the second arm D₂ and blown directly on the sensor for 5 min. Then, it was removed from the test chamber by switching the gas flow to nitrogen for 15 min.

Samples were polarized at 0.5 V. The measurements of direct current intensity have been done in real time using a (HP 4140B) Source/Picoammeter. The electrical contact on the sensor is ensured by gold tip tungsten electrodes. Measurements were done at different operating temperatures ranging from 150 °C to 425 °C. The sensor is heated by a halogen lamp which is powered by a stabilized generator and controlled by an (HP 34401A) Multimeter regulator that allows to set the temperature of the semiconductor by measuring the resistance across the RTD PT100 platinum probe that will be converted into a temperature value.

In order to compare the responses of In_2S_3 sensors we will use the following formula of sensing response:^{30,31}

$$Response = R_a/R_g \tag{4}$$

where $R_{\rm a}$ and $R_{\rm g}$ represent respectively the sensor resistance value in air and in a sample gas.

3. Results and discussion

3.1. Characterization

3.1.1 Thickness and structure. The double weight method was used to measure In_2S_3 film thicknesses (*d*) for varying deposit time and calculated by using the relation:

$$d = \frac{m}{\rho S} \tag{5}$$

where *m* is the deposited film mass, ρ is the density of the material in the bulk form ($\rho = 4.613 \text{ g cm}^{-3}$ matching with the standard file of JCPDS 25-390) and *S* is the effective area on which the film was deposited.

The obtained values of thicknesses for all samples are illustrated in Table 1 and show that thickness increases from $0.8 \,\mu\text{m}$ to $6.1 \,\mu\text{m}$ by rising deposit time in the range 10–90 min.

The X-ray diffraction patterns of the In_2S_3 layers obtained for different thicknesses are shown in Fig. 2.

These patterns indicate that all films were polycrystalline and can be closely indexed to pure β -In₂S₃ phase with a simple cubic structure matching with the standard file of JCPDS 32-0456. The preferred orientation observed in the pattern for all samples is (400). The intensity of the diffraction main peak

Table 1 Thickness, data evaluated from X-ray diffraction pattern and roughness profile parameters of $\mbox{In}_2 S_3$ films

Spray time (min)	Thickness (µm)	D (nm)	$\delta~(10^{10}~{ m lines}$ per cm $^{-2})$	$R_{\rm q}$ (nm)	R _{sk}
10	0.8	39.1	6.5	141	-0.35
30	2.3	43.1	5.2	207	-0.27
50	3.2	51.7	3.7	223	-0.22
70	4.8	52.1	3.7	501	0.93
90	6.1	41.3	5.8	1150	0.43



Fig. 2 XRD patterns of sprayed In₂S₃ films.

becomes more intense with the increase of spray time. Such behavior can be explained by the increase of film thickness and the increased ability of atoms to orient in proper equilibrium sites giving more preferentially oriented films.

The main peak was used to determine the crystallite size using Lorentzian fits and Scherrer's formula:³²

$$D = \frac{0.9\lambda}{\beta\cos\theta} \tag{6}$$

where λ denotes the wavelength of X-ray, θ represents the Bragg angle and β the full width at half maximum (FWHM) in radians.

Likewise, the imperfection in the films can be quantified by computing the dislocation density (δ) which is defined as the length of dislocation lines per unit volume of the crystal. For the (400) peak, it was calculated using the Williamson–Smallman relation:³³

$$\delta = \frac{1}{D^2} \tag{7}$$

The interplanar *d*-spacing (d_{hkl}) for In₂S₃ nanoparticles was calculated using Bragg's eqn (8). The lattice parameter (*a*) associated with d_{hkl} and Miller indices (h,k,l) are calculated *via* the theoretical eqn (9) and (10) as well:³²

$$d_{hkl} = \frac{\lambda}{2\sin\theta} \tag{8}$$

$$\frac{1}{d_{hkl}^2} = \frac{h^2 + k^2 + l^2}{a^2} \tag{9}$$

$$a = 4d_{400}$$
 (10)

The calculated lattice parameter reveals a constant value a = 10.7 Å, while crystallite size and dislocation density of films are presented in Table 1.

It can be seen that the change in thickness affects the density of native imperfections which modify the structural quality of the films. In fact, a maximum of the crystallite size (D = 52 nm) and a minimum of the defect δ ($\delta = 3.7 \times 10^{10}$ lines per cm⁻²) is located around a thickness of 4.8 µm reflecting the best crystallinity of the deposit in this condition.

3.1.2 Topography and morphology. Surface topography is an important surface property and it affects the performance of products at its application fields. Topography of prepared layers was performed by using optical profilometer.

Fig. 3 presents 2D surface measurement of In_2S_3 samples over a scanned area of 1 mm². In this case we arbitrarily amplify the *z* axis and we also know the altitudes using a color palette that allows appreciating the local variations of the heights. Here the variations of the relief are also amplified and the represented surfaces would appear flat. The surface roughness of films seems to change from one layer to another with a changing thickness.

The parameters (prefix) *R* calculated on the roughness profile are defined in a handful of international standards Geometric Product Specifications (GPS) – Surface Texture: Profile Method

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.





This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence. Open Access Article. Published on 18 May 2020. Downloaded on 7/13/2025 5:40:49 AM.

Fig. 3 Topography images of In₂S₃ films.

(ISO 4287:1997). Some parameters calculated on segments of the profile (the base lengths) and averaged over several segments are presented in Table 1. These results are evaluated from measurements in three different areas of each sample and from five profiles for each area.

 $R_{\rm q}$, root mean squared roughness, is the standard deviation of the height distribution over the evaluation length. We can note from Table 1 that $R_{\rm q}$ increases eventually with increasing thickness by rising spray time and shows high values for samples matching thicknesses of 4.8 µm and 6.1 µm.

 $R_{\rm sk}$, asymmetry of the profile: asymmetry of the distribution of the heights, defined on the length of evaluation. This

parameter is important because it gives information on the morphology of the surface state. A positive value of $R_{\rm sk}$ (thicknesses of 4.8 µm and 6.1 µm) corresponds to a surface having peaks and protuberances above the surface, and thus a distribution shifts towards the lowest points, while a negative value (thicknesses of 0.8 µm, 2.3 µm and 3.2 µm) corresponds to a plateau surface with scratches or deep pores, and a shifted distribution towards the highest points.

The morphological study by SEM shows in Fig. 4 the microscopic appearance of the surface layers for different thicknesses.





Fig. 4 SEM images of sprayed In₂S₃ films.

The films were well covered, homogeneous, dense and continuous. We can note that the thickness effect is reflected on the film surface morphologies. SEM images reveal a granular layer for the sample corresponding to the thickness of 4.8 μ m, whereas the layers are smooth for the others thicknesses. In

Table 2EDS results of In_2S_3 thin films								
Thickness (µm)	S (at%)	In (at%)	S/In					
0.8	31.60	23.68	1.33					
2.3	37.83	30.15	1.25					
3.2	37.98	29.90	1.27					
4.8	36.92	29.07	1.27					
6.1	35.74	28.92	1.24					

addition to this, big granules/chunks are observed at the figure for 0.8 μ m, 2.3 μ m, and 4.8 μ m thicknesses. Such observation may be a result of a small deviation from the stoichiometric composition in starting a solution that yields a very strong influence on the microstructure and the surface morphology of the films. This behavior was the subject of previous reports on films such as In₂S₃ (ref. 34) and CuInS₂.³⁵ We can also note a rougher layer surface with cracks at the higher thickness of 6.1 μ m identifying a beginning of crystallinity degradation.

3.1.3 Chemical analysis. The use of EDS made chemical elements' identification possible in the obtained thin layers. We report in Table 2 the counting of the atomic percentage of the main elements in the films.

RSC Advances

These results are evaluated from measurements in four different areas of each sample. The S/In molar ratio remains constant for all the samples with an average value of 1.27. This order of magnitude is less than the stoichiometric ratio (S/In = 1.5) of the In₂S₃ material. This indicates that the prepared In₂S₃ material contains defective sulfur positions.

3.2 VOCs sensing properties

3.2.1 Response. First, all the sensors elaborated with several thicknesses in the range 0.8–6.1 μ m were tested to 4000 ppm of methanol, ethanol and acetone gas at an operating temperature of 350 °C. The choice of such temperature is based on our previous publication.³⁰ This is the optimal temperature for an ethanol detection by In₂S₃ films matching a thickness around 2 μ m. As we will see in the following section, the optimal temperature can be shifted by the film thickness or the gas nature while remaining in the vicinity of 350 °C. We think that this value allows a significant response comparison. Fig. 5 illustrates dynamic responses during the alternating exposure to target gas and dry air. For each sensor, three response and recovery curves are shown.

We note that for all the prepared sensors, during the exposure to target gas, the response increases quickly to an equilibrium value and then returns to the baseline when dry air is reinjected in the test chamber. This behavior is consistent with the sensing mechanism of n-type semiconductors. It is also observed that the response plot obtained is affected by the change of thickness. A possible explanation is that samples have different specific surface areas. In the case of smooth layers and low roughness ($d = 0.8 \ \mu m$, $d = 2.3 \ \mu m$, $d = 3.2 \ \mu m/$ root mean squared roughness of 141 nm, 207 nm and 223 nm, respectively) the gas interaction is only taking place at the geometric surface. In the case of granular layer and high roughness ($d = 4.8 \ \mu m$, $R_q = 501 \ nm$), the gas interaction can therefore take place at the surface of individual grains and at grain–grain boundaries.³⁶ So, such sensor presents a higher



Fig. 5 Dynamic response of In_2S_3 films to 4000 ppm of methanol, ethanol and acetone at 350 °C for thickness varying from 0.8 μ m to 6.1 μ m.



Fig. 6 Response and recovery times of In_2S_3 films to 4000 ppm of methanol, ethanol and acetone at 350 °C.

specific surface area involving abundant active adsorption sites which improve the gas response. This result confirms the proposal to improve the response by changing microstructure and morphology of sensors.³⁷ In the case of sample ($d = 6.1 \mu$ m, $R_q = 1150$ nm) cracks increase the electric potential barriers, reduce the current and diminish the sensing response. Indeed, the increase in resistance is related to the number of cracks in the semiconductor layer which depends on the applied deformation and the thickness of the film.³⁸ Despite the fact that the



Fig. 7 Dynamic response of In_2S_3 sensors with different thicknesses to various concentrations of methanol, ethanol and acetone at the operating temperature of 350 °C.



Fig. 8 (a) Resistance change of In_2S_3 film with time upon altering exposure to dry air and nitrogen at operating temperature ranging from 150 °C to 400 °C, (b) response of In_2S_3 film to oxygen as a function of operating temperature.

cracks can be the gas trapping path, it is also very possible that they cause an electrical rupture of these areas. We think that the active surface which describes the resistance decreases enormously with these cracks because they prevent the electrical contribution of a certain volume of material and therefore reduce the response of the sensor.

3.2.2 Rapidity. In a second stage, we investigated the time deposition effect on the sensing rapidity of In₂S₃ thin films. The response time τ_{res} is defined as the time required for the sensor to reach 90% of the sensor response, and the recovery time $\tau_{\rm rec}$ as that needed to reach 10% of the initial resistance baseline after the analyst gas has been purged. Fig. 6 shows the comparison of samples with respect to their response time, tested by the vapors of methanol, ethanol and acetone with 4000 ppm concentration and 350 °C operating temperature. We note that the sensor prepared with thickness $d = 4.8 \ \mu m$ presents the faster response. Also, the shortest response time corresponds to ethanol gas for all samples (e.g. τ_{res} (ethanol) = 33 s). In addition to this, Fig. 6 illustrates the evaluation of recovery times which show a similar evolution-like response time. We have checked that the sensor matching the thickness of 4.8 μ m has also the shortest recovery time (e.g. τ_{rec} (ethanol) =

138 s). Therefore, the performance of In_2S_3 sensors evaluated by response and rapidity reveals that the sample matching the thickness of 4.8 μ m presents the best results.

3.2.3 Reproducibility. Reproducibility was investigated by exposing In_2S_3 sensors with different thicknesses to a variety of VOCs. Fig. 7 shows the dynamic response of sensors to various concentrations of methanol, ethanol and acetone ranging from 2000 ppm to 10 000 ppm, 1000 ppm to 5000 ppm and 4000 ppm to 20 000 ppm respectively at the operating temperature of 350 °C. For each sensor, the sensor's response has an obvious increasing relationship with VOCs concentration, demonstrating that the sensor can offer more surface active sites and adsorb more VOCs molecules. Moreover, the sensor's response is affected by the layer's thickness and the best response was performed with the thickness matching 4.8 µm. This fact reflects the reproducibility of the results detailed previously.

3.2.4 Gas sensing mechanism. In the following part, we propose to study the sensing mechanism and selectivity for some volatile organic compounds. We focused on the In_2S_3 sample corresponding to the 4.2 µm thickness.

3.2.4.1 Oxygen adsorption/desorption. Here, the adsorption and desorption of oxygen on a polycrystalline indium sulfide



Fig. 9 (a) Resistance evolution of In_2S_3 sensor upon exposure to 4000 ppm concentration of various organic vapors at operating temperatures in the range: 250–400 °C, (b) sensing response of In_2S_3 sensor vs. working temperature towards various organic vapors.



Fig. 10 (a) Dynamic response of In_2S_3 sensor to various organic vapor concentrations at 350 °C, (b) experimental and power fit of sensing response of In_2S_3 sensor as a function of organic vapor concentration at 350 °C.

thin layers have been experimentally demonstrated by performing alternating exposure to nitrogen and dry air at a working temperature ranging from 150 °C to 400 °C. Fig. 8(a) shows that resistance increases when dry air is introduced in the test chamber and decreases after its evacuation by nitrogen for an operating temperature higher than 200 °C.

In fact, under dry air an adsorption phenomenon occurs. Ho et al.³⁹ reported that because of sulfur vacancies and indium interstitials defects, the β -In₂S₃ crystal can form easily surface oxidation states of β -In₂S_{3-3x}O_{3x} in ambient air (or O₂) by chemical reaction of In–O. So, we think that the interaction of atmospheric oxygen with the surface of In₂S₃ forms a layer of charged oxygen species, which traps electrons from the bulk of the material. The electrons trapped for this process are removed from the conduction band and are confined on the surface.³⁶ Consequently, a space charge layer is formed. The presence of negative surface charges leads to a band bending defined by potential barrier eV_s at the surface. This restricts the electron flow and decreases the conductivity. On the other hand, under nitrogen, the resistance decreases reflecting the oxygen desorption phenomenon.

In this context, the study of the oxygen sensing response *versus* the operating temperature was illustrated in Fig. 8(b). The response increases by increasing the working temperature up to 350 °C and decreases above this temperature. This fact could be interpreted as a competition between the rates of oxygen adsorption and desorption, which is shown in the Lennard-Jones⁴⁰ equation:

$$\frac{\mathrm{d}\theta}{\mathrm{d}t} = k_{\mathrm{ads}} \,\mathrm{e}^{-\frac{\Delta E_{\mathrm{A}}}{kT}} - k_{\mathrm{des}} \,\mathrm{e}^{-\frac{(\Delta E_{\mathrm{A}} + \Delta H)}{kT}} \tag{11}$$

where k_{ads} and k_{des} are respectively the rate constants for adsorption and desorption reactions, ΔE_A the activate energy of chemisorption, ΔH the heat of adsorption and θ is the fraction of available surface sites covered.

3.2.4.2 Operating temperature effect. Fig. 9(a) demonstrates the resistance change during an alternating exposure to dry air and organic vapor (methanol, ethanol and acetone) at 4000 ppm concentration. Measurements were made at different operating

temperatures in the range of 250–425 $^{\circ}$ C. The counting of these results is shown in Fig. 9(b).

The evolution of the response *versus* the working temperature follows also Lennard-Jones equation and shows an optimal temperature for each gas. It clearly shows a direct correlation between oxygen adsorption and reducing gas detection. Indeed, responses to oxygen and reducing gases present a similar evolution and a neighboring optimal temperature.

The increase in operating temperature before the optimum value improves the oxygen adsorption and hence the VOCs response. On the other hand, desorption of all oxygen ionic species previously adsorbed occurs at high temperatures, which explains the response decrease to reducing gases beyond the optimum value.

We note that optimal temperature for ethanol and acetone is 365 °C, whereas it is shifted to 385 °C for methanol gas. Similarly, such a trend has been studied by Bejaoui *et al.*⁴¹ They proposed a model simulating the interaction between sensors and reducing gases. They showed that the increase of the activation energy following a change of gas causes a shift of the optimal temperature towards a higher value. We also remarked



Fig. 11 Detection mechanism of organic vapor by In₂S₃ sensor.



Fig. 12 Selectivity of In_2S_3 sensor ($d = 4.8 \ \mu m$).

that ethanol response (16.2) is higher than the acetone one (6.3) at the same optimal temperature. This could be explained by the ethanol and the acetone molecules' size difference. Indeed, the surface cover rate is higher for the smaller molecules of ethanol.

3.2.4.3 Gas concentration effect. In order to identify ionosorbed oxygen species, measurements were conducted on the In_2S_3 sensor at a working temperature of 350 °C by varying the concentration of methanol, ethanol and acetone. The transient current during cycles (air/reducing gas/air) is shown in Fig. 10(a). The fitting of the response (S_{gas}) versus gas concentration (C_{gas}) obtained in Fig. 10(b) shows a power law:

$$S_{\rm gas} = C te \left[C_{\rm gas} \right]^{\gamma} \tag{12}$$

where $\gamma \approx 1/3$ for the three analyzed gases. This typical value locates mainly O^{2-} ionosorbed oxygen on the material surface according to the metal oxide gas detection model proposed by Barsan and Weimar.³⁶

Thus, ionization equations of adsorbed oxygen can be written as follows:

$$O_{2(gas)} \to O_{2(ads)} \tag{13}$$

$$O_{2(ads)} + 4e^- \rightarrow 2O_{(ads)}^{2-}$$
 (14)

In the same context, when the material is exposed to reducing gases, the organic molecules are oxidized by oxygen species O^{2-} and simultaneously the electrons are fed back into sensing body, the potential barrier is reduced and the conductivity increases. This mechanism can be expressed as follows:

For methanol:
$$CH_3OH_{(ads)} + O_{(ads)}^{2^-} \rightarrow H_2CO_{(gas)} + H_2O + 2e^-$$
 (15)

For ethanol:
$$C_2H_5OH_{(ads)} + O_{(ads)}^{2-} \rightarrow CH_3CHO_{(gas)} + H_2O + 2e^-$$
 (16)

For acetone:
$$CH_3COCH_{3(ads)} + 8O_{(ads)}^{2-} \rightarrow 3CO_{2(gas)} + 3H_2O_{(gas)} + 16e^-$$
 (17)

So, oxygen plays the main element in reducing gas sensing response as detailed by the mechanism presented in Fig. 11.

3.2.5 Selectivity. The efficiency of a sensor to respond to a certain gas in the presence of other gases is called selectivity. Fig. 12 shows the dynamic response of an In_2S_3 film (d = 4.8 μ m) to seven VOCs at a 500 ppm concentration and a working temperature of 350 °C. This figure reveals that the relatively high responses are obtained with isopropanol (10.5) and ethanol (9.5). The middle response is observed with butan-1-ol (5.8) and toluene (4.5). Lastly, weak responses correspond to methanol (2.9), acetone (3.3) and chlorobenzene (1.5) vapors. Therefore, we can't expect for the time being that our sensor can be selective. However, it is possible to analyze the different responses through a mathematical technique known as principal component analysis (PCA).42 This latter is a method of graphical data analysis which consists in finding the directions of space which best represents the correlations between the chosen variables of the measure.43 This study is being planned for a future publication.

A comparison of the developed sensor response to those of previously published indium oxide sensors is reported in Table 3. The results show that the ethanol detection response of indium sulfide In_2S_3 -based sensor in the present work is not high but can be improved by enhancing gas adsorption or promoting specific chemical reactions *via* catalytic or electronic effects using bulk dopants and by the addition of metallic clusters or oxide catalysts.⁴⁴⁻⁴⁶

Table 3 Sensing response of the developed indium sulfide sensor compared with previously published indium oxide sensors

Material	Ethanol concentration (ppm)	Response	$\tau_{\rm res}/\tau_{\rm rec}~(s)$	$T_{\mathrm{opt}} \left(^{\circ} \mathrm{C}\right)$	Reference
In_2S_3	500	9.5	23/75	350	This work
In ₂ S ₃	500	1.7	150/155	350	30
In_2O_3	50	5	40/38	300	47
3% Ag-doped In ₂ O ₃	50	30	32/140	300	47
In ₂ O ₃ /Au NRs	500	320	/	400	48
In ₂ O ₃ hierarchical architecture	100	1.5	/	260	49
In ₂ O ₃ microcubes	500	55	/	210	50
Ce-doped In ₂ O ₃	100	27.8	/	240	51
Pb-doped In ₂ O ₃	100	32.5	2.2/0.7	250	52

4. Conclusion

In₂S₃ films were deposited on glass substrates by spray pyrolysis technique. Film thickness increases from 0.8 µm to 6.1 µm by increasing deposit time from 10 min to 90 min. XRD diffraction analysis reveals the formation of cubic ®-In₂S₃ pure phase with (400) preferred orientation. The crystallite size varies in the narrow 39-52 nm range. The EDS measurements indicate that the S/In molar ratio remains constant for all the samples with an average value of 1.27. The morphological study by SEM shows that films were well covered, homogeneous and dense. The parameter R_{q} calculated from the roughness profile increases eventually with increasing thickness. Thus, the In₂S₃ sample matching the thickness of 4.8 µm combine high roughness and best crystallinity. Such results were correlated with its best sensing properties. We have fairly improved the In2S3 sensor performances compared to that mentioned in the previous publication.³⁰ The response to 500 ppm ethanol at 350 °C is enhanced from 1.7 to 9.5. The response time and recovery time are improved from 150 s/155 s to 23 s/75 s respectively. The optimal working temperature is found to be around 385 °C for methanol and 365 °C for both ethanol and acetone. Besides, oxygen adsorption versus working temperature were put forth and the sensing mechanism of the In₂S₃ semiconductor was explained on the bases of the reaction between the reducing vapors with the chemisorbed oxygen ions O^{2-} . Nevertheless, these results revealing the potential of β -In₂S₃ in gas detection are encouraging for deepening the study in order to improve sensing properties and to test other gasses.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by Tunisian Ministry of Higher Education and Scientific Research, Spanish Ministry of Science and Innovation – FEDER Funds (MODENA Project CTQ2016-79461-R) and Fundación Ramón Areces (Spain, Project CIVP18A3940). NANOMAG group belongs to Galician Competitive Research Group ED431C-2017/22, programme co-funded by FEDER, and AEMAT Strategic Partnership (ED431E-2018/ 08, Xunta de Galicia, Spain). The authors are grateful to Dr N. Ihzaz (High Institute of Applied Sciences and Technology, Gabes University, Tunisia) for useful discussions.

References

- 1 B. Lawson, K. Aguir, T. Fiorido, V. Martini-Laithier, R. Bouchakour, S. Burtey, Ch. Reynard-Carette and M. Bendahan, Skin alcohol perspiration measurements using MOX sensors, *Sens. Actuators, B*, 2019, **280**, 306–312.
- 2 Q. Rong, Y. Zhang, T. Lv, K. Shen, B. Zi, Z. Zhu, J. Zhang and Q. Liu, Highly selective and sensitive methanol gas sensor

based on molecular imprinted silver doped $LaFeO_3$ coreshell and cage Structures, *Nanotechnology*, 2018, **29**, 145503–145511.

- 3 Y. Xiong, Z. Zhu, D. Ding, W. Lu and Q. Xue, Multi-shelled ZnCo₂O₄ yolk-shell spheres for high-performance acetone gas sensor, *Appl. Surf. Sci.*, 2018, **443**, 114–121.
- 4 X. Li, D. Lu, C. Shao, G. Lu, X. Li and Y. Liu, Hollow CuFe₂O₄/ α -Fe₂O₃ composite with ultrathin porous shell for acetone detection at ppb levels, *Sens. Actuators, B*, 2018, 258, 436–446.
- 5 O. Lupan, V. Postica, J. Gröttrup, A. K. Mishra, N. H. de Leeuw, J. F. C. Carreira, J. Rodrigues, N. Ben Sedrine, M. R. Correia, T. Monteiro, V. Cretu, I. Tiginyanu, D. Smazna, Y. K. Mishra and R. Adelung, Hybridization of zinc oxide tetrapods for selective gas sensing applications, *ACS Appl. Mater. Interfaces*, 2017, 9(4), 4084–4099.
- 6 E. Wongrat, N. Chanlek, C. Chueaiarrom, W. Thupthimchun, B. Samransuksamer and S. Choopun, Acetone gas sensors based on ZnO nanostructures dectorated with Pt and Nb, *Ceram. Int.*, 2017, **43**, 557–566.
- 7 L. Zhu, Y. Li and Z. Wen, Hydrothermal synthesis of hierarchical flower-like ZnO nanostructure and its enhanced ethanol gas-sensing properties, *Appl. Surf. Sci.*, 2018, 427, 281–287.
- 8 M. Asgari, F. H. Saboor, Y. Mortazavi and A. K. Khodadadi, SnO₂ decorated SiO₂ chemical sensors: enhanced sensing performance toward ethanol and acetone, *Mater. Sci. Semicond. Process.*, 2018, **68**, 87–96.
- 9 A. Gaiardo, B. Fabbri, V. Guidi, P. Bellutti, A. Giberti, S. Gherardi, L. Vanzetti, C. Malagù and G. Zonta, Metal Sulfides as Sensing Materials for Chemoresistive Gas Sensors, *Sensors*, 2016, **16**, 296–314.
- 10 T. T. John, M. Mathew, C. S. Kartha, K. P. Vijayakumar, T. Abe and Y. Kashiwaba, CuInS₂/In₂S₃ thin film solar cell using spray pyrolysis technique having 9.5% efficiency, *Sol. Energy Mater. Sol. Cells*, 2005, **89**, 27–36.
- 11 M. Kraini, N. Bouguila, I. Halidou, A. Timoumi and S. Alaya, Properties of In_2O_3 films obtained by thermal oxidation of sprayed In_2S_3 , *Mater. Sci. Semicond. Process.*, 2013, **16**, 1388–1396.
- 12 P. G. S. Abadi, M. S. Niasari and F. Davar, Hydrothermal synthesis, characterization and optical properties of 3D flower like indium sulfide nanostructures, *Superlattices Microstruct.*, 2013, **53**, 76–88.
- 13 Z. Li, X. Tao, Z. Wu, P. Zhang and Z. Zhang, Preparation of In_2S_3 nanoparticle by ultrasonic dispersion and its tribology property, *Ultrason. Sonochem.*, 2009, **16**, 221–225.
- 14 B. Asenjo, C. Sanz, C. Guillén, A. M. Chaparro, M. T. Gutiérrez and J. Herrero, Indium sulfide buffer layers deposited by dry and wet methods, *Thin Solid Films*, 2007, 515, 6041–6044.
- 15 A. Timoumi, H. Bouzouita, M. Kanzari and B. Rezig, Fabrication and characterization of In_2S_3 thin films deposited by thermal evaporation technique, *Thin Solid Films*, 2005, **480**, 124–128.
- 16 B. Tiss, M. Erouel, N. Bouguila, M. Kraini and K. Khirouni, Effect of silver doping on structural and optical properties

of In₂S₃ thin films fabricated by chemical pyrolysis, *J. Alloys Compd.*, 2019, 771, 60–66.

- 17 N. Bouguila, M. Kraini, I. Halidou, E. Lacaze, H. Bouchriha and H. Bouzouita, Thickness effect on properties of sprayed In_2S_3 films for photovoltaic applications, *J. Electron. Mater.*, 2016, **45**, 829–838.
- 18 N. Bouguila, M. Kraini, A. Timoumi, I. Halidou, C. Vázquez-Vázquez, M. A. López Quintela and S. Alaya, Substrate temperature effect on properties of sprayed In₂S₃ films, *J. Mater. Sci.: Mater. Electron.*, 2015, 26, 7639–7648.
- 19 T. Schulmeyer, A. Klein, R. Kneiese and M. Powalla, Band offset at the CuGaSe₂/In₂S₃ heterointerface, *Appl. Phys. Lett.*, 2004, 85, 961–963.
- 20 R. Diehl and R. Nitsche, Vapour growth of three In₂S₃ modifications by iodine transport, *J. Cryst. Growth*, 1975, 28, 306.
- 21 J. Sterner, J. Malmstrom and L. Stolt, Study on ALD In₂S₃/ Cu(In,Ga)Se₂ interface formation, *Prog. Photovoltaics*, 2005, 13, 179.
- 22 S. Buecheler, D. Corica, D. Guettler, A. Chirila, R. Verma, U. Muller, T. P. Niesen, J. Palm and A. N. Tiwari, Ultrasonically sprayed indium sulfide buffer layers for Cu(In,Ga)(S,Se)₂ thin-film solar cells, *Thin Solid Films*, 2009, **517**, 2312–2315.
- 23 E. Dalas and L. Kobotiatis, Primary solid-state batteries constructed from copper and indium sulphides, *J. Mater. Sci.*, 1993, **28**, 6595.
- 24 Yu-J. Hsiao, C.-H. Lu, L.-W. Ji, T.-H. Meen, Y.-L. Chen and H.-P. Chi, Characterization of photovoltaics with In₂S₃ nanoflakes/p-Si heterojunction, *Nanoscale Res. Lett.*, 2014, 9, 32–38.
- 25 D. K. Nagesha, X. Liang, A. A. Mamedov, G. Gainer, M. A. Eastman, M. Giersig, J. J. Song, T. Ni and N. A. Kotov, In₂S₃ Nanocolloids with Excitonic Emission: In₂S₃ vs. CdS Comparative Study of Optical and Structural Characteristics, *J. Phys. Chem. B*, 2001, **105**, 7490.
- 26 B. Hemanth Kumar and M. C. Santhosh Kumar, Indium sulfide based metal-semiconductor-metal ultravioletvisible photodetector, *Sens. Actuators, A*, 2019, **299**, 111643.
- 27 R. A. Ismail, N. F. Habubi and M. M. Abbod, Preparation of high-sensitivity In₂S₃/Si heterojunction photodetector by chemical spray pyrolysis, *Opt. Quantum Electron.*, 2016, **48**, 455–468.
- 28 S. Ghosh, M. Saha, V. D. Ashok, A. Chatterjee and S. K. De, Excitation dependent multicolor emission and photoconductivity of Mn, Cu doped In_2S_3 monodisperse quantum dots, *Nanotechnology*, 2016, 27, 155708–155724.
- 29 P. Cai, H. Song and Y. Lva, Hierarchical spheres In₂S₃-based cataluminescence sensor for ammonium sulfide, *Microchem. J.*, 2018, 138, 116–121.
- 30 R. Souissi, N. Bouguila and A. Labidi, Ethanol sensing properties of sprayed ®-In₂S₃ thin films, *Sens. Actuators, B*, 2018, **261**, 522–530.
- 31 A. Labidi, E. Gillet, R. Delamare, M. Maaref and K. Aguir, Ethanol and ozone sensing characteristics of WO₃ based

sensors activated by Au and Pd, Sens. Actuators, B, 2006, 120, 338-345.

- 32 B. D. Cullity, *Elements of X-ray Diffraction*, Addison-Wesley, Reading, MA, 1978, Library of Congress Catalog Card No. 77-73950, ISBN 0-201-01174-3.
- 33 V. Bilgin, S. Kose, F. Atay and I. Akyuz, The effect of substrate temperature on the structural and some physical properties of ultrasonically sprayed CdS films, *Mater. Chem. Phys.*, 2005, 94, 103–108.
- 34 N. Revathi, P. Prathap and K. T. Ramakrishna Reddy, Synthesis and physical behavior of In₂S₃ films, *Appl. Surf. Sci.*, 2008, **254**, 5291–5298.
- 35 M. Krunks, O. Bijakina, T. Varema, V. Mikli and E. Mellikov, Structural and optical properties of sprayed CuInS₂ films, *Thin Solid Films*, 1999, **338**, 125–130.
- 36 N. Barsan and U. Weimar, Conduction model of metal oxide gas sensors, *J. Electroceram.*, 2001, 7, 143–167.
- 37 A. Dey, Semiconductor metal oxide gas sensors: a review, *Mater. Sci. Eng., B*, 2018, 229, 206–217.
- 38 D. R. Cairns, R. P. Witte, D. K. Sparacin, S. M. Sachsman, D. C. Paine, Gr. P. Crawford and R. R. Newton, Electric resistance dependent on the stress of indium oxide doped with tin on polymeric substrates, *Appl. Phys. Lett.*, 2000, 76(11), 1425.
- 39 C. Ho, M. Lin, Y. Wang and Y. Huang, Synthesis of In_2S_3 and Ga_2S_3 crystals for oxygen sensing and UV photo-detection, *Sens. Actuators, A*, 2016, **245**, 119–126.
- 40 A. Labidi, C. Jacolin, M. Bendahan, A. Abdelghani, J. Guérin,
 K. Aguir and M. Maaref, Impedance spectroscopy on WO₃ gas sensor, *Sens. Actuators, B*, 2005, **106**, 713–718.
- 41 A. Bejaoui, J. Guerin and K. Aguir, Modeling of a p-type resistive gas sensor in the presence of a reducing gas, *Sens. Actuators, B*, 2013, **181**, 340–347.
- 42 X. Vanden Eynde and P. Bertrand, ToF-SIMS quantification of polystyrene spectra based on principal component analysis (PCA), *Surf. Interface Anal.*, 1997, **25**, 878–888.
- 43 M. Penza, G. Cassano and F. Tortorella, Gas recognition by activated WO₃ thin film sensors array, *Sens. Actuators, B*, 2001, **81**, 115–121.
- 44 L. Liu, P. Song, Z. Yang and Q. Wang, Ultra-fast responding C_2H_5OH sensors based on hierarchical assembly of SnO_2 nanorods on cube-like α -Fe₂O₃, *J. Mater. Sci.: Mater. Electron.*, 2018, **29**(7), 5446–5453.
- 45 P. Tyagi, A. Sharma, M. Tomar and V. Gupta, Metal oxide catalyst assisted SnO₂ thin film based SO₂ gas sensor, *Sens. Actuators, B*, 2016, **224**, 282–289.
- 46 D. Hohl, The role of noble metals in the chemistry of solidstate gas sensors, *Sens. Actuators, B*, 1990, **1**, 158–165.
- 47 K. Anand, J. Kaur, R. C. Singh and R. Thangaraj, Preparation and characterization of Ag-doped In₂O₃ nanoparticles gas Sensor, *Chem. Phys. Lett.*, 2017, **682**, 140–146.
- 48 R. Xing, L. Xu, J. Song, C. Zhou, Q. Li, D. Liu and H. W. Song, Preparation and gas sensing properties of In_2O_3/Au nanorods for detection of volatile organic compounds in exhaled breath, *Sci. Rep.*, 2015, 5, 10717–10730.
- 49 S. Wang, J. Cao, W. Cui, L. Fan, X. Li and D. Li, Oxygen vacancies and grain boundaries potential barriers

modulation facilitated formaldehyde gas sensing performances for In_2O_3 hierarchical architectures, *Sens. Actuators, B*, 2018, 255, 159–165.

- 50 X. Zhou, F. Qu, B. Zhang, C. Jiang and M. Yang, Facile synthesis of In_2O_3 microcubes with exposed {100} facets as gas sensing material for selective detection of ethanol vapor, *Mater. Lett.*, 2017, **209**, 618–621.
- 51 X. Liu, L. Jiang, X. Jiang, X. Tian, X. Sun, Y. Wang, W. He, P. Hou, X. Deng and X. Xu, Synthesis of Ce-doped In₂O₃ nanostructure for gas sensor applications, *Appl. Surf. Sci.*, 2018, **428**, 478–484.
- 52 A. Montazeri and F. Jamali-Sheini, Enhanced Ethanol Gas-Sensing Performance of Pb-Doped In₂O₃ Nanostructures Prepared by Sonochemical Method, *Sens. Actuators, B*, 2017, 242, 778–791.