Materials Advances

PAPER

Check for updates

Cite this: Mater. Adv., 2021, **2**, 1050

Received 24th November 2020, Accepted 28th December 2020

DOI: 10.1039/d0ma00920b

rsc.li/materials-advances

Introduction

The linear alpha olefins (LAOs), linear hydrocarbons with a C=C bond at the terminal position, are chemical intermediates that are attractive for use in detergents, specialty chemicals, synthetic oils, premium synthetic lubricants and plasticizers, as well as in copolymers.¹⁻⁴ To date, ethylene oligomerization for homogeneous transition-metal catalysis has been a significant process for LAO production.^{5,6} For example, more than 1 Mt of alpha olefins per year are produced using the Shell Higher Olefin Process (SHOP), which was discovered in 1968.^{7,8} On the other hand, promising LAO production methods based on carbon monoxide (CO) and carbon dioxide (CO₂) hydrogenation reactions are rarely reported due to the delicate processing

34129, Korea. E-mail: bhkim@kier.re.kr; Tel: +82-42-860-3218



Jin Hee Lee,‡^a Hack-Keun Lee, 🗓 ‡^a Kwangsoo Kim,^{bc} Geun Bae Rhim,^d Min Hye Youn,^d Heondo Jeong,^d Jong Hyeok Park, ^o^c Dong Hyun Chun,*^d Byung-Hyun Kim^b*^b and Ji Chan Park^{*}

 C_5-C_{13} linear alpha(α) olefins (LAOs) are high-value-added chemicals acknowledged by industry. However, using catalysts to elevate the activity and selectivity of LAOs remains a major challenge for Fischer-Tropsch synthesis (FTS). Recently, researchers on catalyst design have reported enhanced LAO production via FTS, but a more detailed understanding of the electron interactions between the active particles and hydrocarbon products is still needed. In the present paper, we report theoretical and experimental results of a potassium (K)-promotion effect on an optimized iron-carbide nanocatalyst (i.e. a carbon-encapsulated iron-carbide nanoparticle supported on nitrogen-doped porous carbon: Fe₅C₂@C/NPC). The K-doped Fe₅C₂@C/NPC nanocatalyst shows excellent catalytic performance with a high CO conversion of up to 96.7% at 78 h time-on-stream, C_5-C_{13} LAO selectivity of 16.5% and productivity of 5.9 CH₂ μ mol g_{cat}^{-1} s⁻¹, compared to those of the K-free Fe₅C₂@C/NPC catalyst. The computer simulation model also supports the positive effects of the catalyst with a small amount of K (ca. 1 wt%, K/Fe = 0.05) in the FTS reaction, which well-matched the experimental results.

> conditions and complicated catalyst properties. These are made worse by insufficient understanding of their performance.⁹⁻¹²

ROYAL SOCIETY

OF CHEMISTRY

View Article Online

Using the high-temperature Fischer–Tropsch synthesis (HT-FTS) process, which is normally conducted at temperatures of 300-350 °C using an iron-based catalyst, hydrocarbons with carbon chains in the gasoline (C5-C12) range and C2-C4 olefins have been obtained selectively.¹³⁻¹⁸ However, exquisite control of the catalysts and processes is needed to achieve the desired LAO products and this remains a major challenge.

To increase olefin production, potassium (a representative alkali metal) has been widely used as an additive in HT-FTS.¹⁹⁻²³ It can donate electrons to active iron surfaces and increase catalyst basicity, leading to the enhanced performance of the catalyst. For instance, Guo et al. reported bio-promoted ironcarbide catalysts with K, as an efficient catalyst for converting CO2 to LAOs. This combination suppressed the secondary hydrogenation of alkenes on active surfaces.²⁴ Recently, the Tsubaki group reported a bimetallic FeCo catalyst with Y-zeolite for the selective production of LAOs by CO₂ hydrogenation.²⁵ Although some iron-based catalysts with alkali promoters have been reported for LAO production, research using computational simulation to interpret their roles in catalysis is still insufficient.²⁶⁻²⁹

For more efficient production of high value-added hydrocarbons in HT-FTS, active and thermally stable nanocatalysts such as Fe@C core-shells and Fe@graphene with a high Fe

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence. Open Access Article. Published on 28 December 2020. Downloaded on 7/28/2025 6:18:11 AM.

^a Clean Fuel Laboratory, Korea Institute of Energy Research, 152 Gajeong-Ro,

Daejeon, 34129, Korea. E-mail: jcpark@kier.re.kr; Tel: +82-42-860-3605 ^b Platform Technology Laboratory, Korea Institute of Energy Research, Daejeon,

^c Department of Chemical and Biomolecular Engineering, Yonsei University, 50 Yonsei-ro, Seoul, 03722, Korea

^d Carbon Conversion Laboratory, Korea Institute of Energy Research, 152 Gajeong-Ro, Daejeon, 34129, Korea. E-mail: cdhsl@kier.re.kr; Tel: +82-42-860-3071

[†] Electronic supplementary information (ESI) available. See DOI: 10.1039/ d0ma00920b

[‡] These authors contributed equally to this work.

Paper

In our previously published work, we reported a new active and stable Fe₅C₂(a)C catalyst supported on a structure of N-doped carbon as an optimum catalyst for HT-FTS.³⁴ In addition, we have found that the appropriate K-doping ratios (K/Fe atomic ratio) at the K-doped χ -Fe₅C₂/charcoal catalysts are in the range of 0.050-0.075.29 From the investigation of the K-promotion effect on the catalyst based on computer simulation, we prepared K-promoted, carbon-encapsulated ironcarbide nanoparticles supported on a nitrogen-doped porous carbon nanostructure (K-Fe5C2@C/NPC). It showed a higher CO conversion rate and better selectivity for linear alpha olefins (LAOs) than those of the K-free Fe₅C₂@C/NPC catalyst. Furthermore, the initial induction period during the FTS reaction using the catalyst with small amounts of K was significantly reduced, resulting in an increase of overall liquid hydrocarbon productivity, including that of LAOs. The catalyst showed a high C_5-C_{13} LAO productivity of 5.9 CH₂ µmol g_{cat}^{-1} s⁻¹, which is \sim 1.5 times higher than that of the K-free Fe₅C₂@C/NPC catalyst $(4.0 \text{ CH}_2 \mu\text{mol g_{cat}}^{-1} \text{ s}^{-1})$ as well as good thermal stability for the HT-FTS reaction carried out at 340 °C and 1.5 MPa for 78 h.

Experimental

Chemicals

Iron(m) acetylacetonate (Fe($C_5H_7O_2$)₃, Aldrich, \geq 99.9%), urea (CH₄N₂O) (Aldrich, 99.0–100.5%), potassium carbonate (K₂CO₃, Aldrich, \geq 98.0%) and ethanol (C₂H₅OH, J.T. Baker, 99.9%) were used without further purification.

Computational details

The plane-wave-based spin-polarized density functional theory (DFT) calculations implemented in the Vienna Ab initio Simulation Package (VASP)³⁵⁻³⁸ were performed to investigate the K-promotion effect on the atomic/electronic structures and adsorption properties of Fe5C2 nanoparticles. The vdW-DF2 functional proposed by Langreth and Lundqvist et al. was used to describe the exchange correlation energy as implemented in the VASP by Klimeš et al.³⁹⁻⁴² The projector augmented wave (PAW)^{43, 44} method was used to describe the interactions between the core and valence electrons. The Kohn-Sham single-electron wave function was expanded by plane-wave basis sets with a cut-off energy of 500 eV. The convergence criteria for the electronic energy and geometry optimization were set at 10^{-5} eV and 0.02 eV Å⁻¹, respectively. The Brillouin zone was sampled at the Γ -point in all the DFT calculations. First-principles molecular dynamics simulations were employed to generate a reliable nanoparticle model structure. A Fe₅C₂ nanoparticle structure was prepared by cutting a single crystalline Hägg iron carbide (Fe₅C₂) structure while maintaining the stoichiometry. Then, the structure was annealed by ramping the temperature from 0 to 1800 K for 100 fs followed by equilibration at 1800 K for 1 ps. The final structure was obtained by ensemble average from the last 500 snapshots during equilibration. The Fe₅C₂ nanoparticle structure was then quenched to 0 K for 100 ps and relaxed by geometry optimization until the maximal force acting on each atom became less than 0.02 eV Å⁻¹. For a K-doped Fe₅C₂ nanoparticle structure, the location of two K atoms was chosen as the energetically most-stable configuration among the eight cases considered (see Fig. S1, ESI⁺).

Synthesis of the K-Fe₅C₂@C/NPC nanocatalyst

The synthesis of the K-free Fe₅C₂@C/NPC nanocatalyst was described in detail in our previous publication.³⁴ Briefly, 0.5 g of $Fe(C_5H_7O_2)_3$ (1.4 mmol) and 2.5 g of CH_4N_2O (41.6 mmol) were mixed to uniformity by grinding in a mortar for 5 min. The powder mixture was transferred to alumina boats in a tube-type furnace. The mixture was then heated to 700 °C at a ramping rate of 5.6 $^{\circ}$ C min⁻¹ under a N₂ flow (200 mL min⁻¹) and then maintained at the same temperature for 2 h. After this, serial thermal treatments were carried out under a H₂ flow (200 mL min⁻¹) for 4 h at 350 $^{\circ}$ C, followed by a CO flow $(200 \text{ mL min}^{-1})$ for 4 h at 350 °C. Finally, the resulting black powder was cooled to room temperature and then submerged in 30 mL of ethanol under a flow of N_2 (500 mL min⁻¹). The powder immersed in 30 mL of ethanol was simply separated using a magnet and then dried in a vacuum oven. For the preparation of the K-doped Fe5C2@C/NPC nanocatalyst, the incipient wetness method was used to merge a K additive with the dried Fe5C2@C/NPC nanocatalyst powder. A solution of aqueous K₂CO₃ in distilled water (1 mL, 0.024 M) was used. After impregnation with the K solution, the K-incorporated sample was transferred to an alumina boat in a tube-type furnace and then slowly heated at a ramping rate of 2.7 $^{\circ}$ C min⁻¹ to 350 $^{\circ}$ C under a CO flow (200 mL min⁻¹). The sample was allowed to remain at 350 K for 4 h under a continuous CO flow. After the thermal treatment, the resulting black powder was cooled to room temperature and then submerged in ethanol under a N₂ flow to prevent rapid surface oxidation. The K-Fe₅C₂@C/NPC nanocatalyst powders were simply separated by magnetic force and then completely dried in a vacuum oven at 50 °C.

High-temperature Fischer-Tropsch synthesis reaction

The reaction tests were performed in a fixed-bed stainless-steel reactor tube with an inner diameter of 5 mm. Some (0.1 g) of the catalyst sample were diluted with glass beads (425-600 μm, 2.9 g) to prevent hot-spot generation during the severe exothermic reaction. Before the reaction, the catalyst was reduced in situ under atmospheric pressure by passing a flow of CO (40 mL min⁻¹) over it at 350 °C for 4 h. After reduction, the reaction tests were carried out at 340 °C and 1.5 MPa for 78 h using reactant gas (H2/CO = 1.0 and gas hourly space velocity (GHSV) = 42 NL $g_{cat}^{-1} h^{-1}$). The composition of the outlet gases was analysed using a gas chromatograph (Agilent, 3000 Micro GC) equipped with a thermal conductivity detector (TCD) and flame ionization detector (FID). The flow rates of the outlet gases were measured using a wet-gas flow meter (Shinagawa Co.). After the reaction, the solid hydrocarbon products were collected in a hot trap (240 °C) and the liquid hydrocarbon products and water were collected in a cold trap

(-3 °C). The isolated solid (wax) and liquid (oil) products were analysed using an offline gas chromatograph (Agilent, 6890 N) and the simulated distillation method (ASTM D2887). Detailed hydrocarbon analysis (DHA) of C₅-C₁₃ LAOs (wt%) in the liquid oil sample was performed using ultra-high-resolution capillary gas chromatography and ASTM D6730.

Characterization

Transmission electron microscopy (TEM) images and highangle annular dark-field scanning transmission electron microscopy (HAADF-STEM) images were obtained using a Talos F200X operated at 200 kV. Energy-dispersive X-ray spectroscopy (EDS) elemental analysis and a mapping process were performed using a higher efficiency detection system (Super X: 4 windowless SDD EDS system). The X-ray diffraction (XRD) patterns of the samples were recorded on a high-power powder X-ray diffractometer (Rigaku D/MAX-2500, 18 kW). The N₂ sorption isotherms were measured at 77 K with a TriStar II 3020 surface area analyser. Before the measurement, the samples were degassed in a vacuum at 573 K for 4 h. X-ray photoelectron spectroscopy (XPS) was carried out using a K-alpha (TM) with a micro-focused monochromator X-ray source (Thermo VG Scientific, Inc.). The Fe loading amount was measured using inductively coupled plasma optical emission spectrometry (ICP-OES, Thermo Scientific iCAP 6300) and the content of K was determined using ICP-OES (Agilent 5110). The N content in the sample was measured using an oxygen-nitrogen-hydrogen analyser (ONH-2000, ELTRA GmbH). Raman analysis was performed using a Raman microscope (Horiba LabRAM HR Evolution Visible_NIR) with a 514 nm laser.

Results and discussion

Synthesis of the K-doped Fe₅C₂@C/NPC nanocatalyst

The K-Fe₅C₂@C/NPC nanocatalyst was prepared through a sequential thermal treatment and the incipient wetness method (Scheme 1). First, the mixed compound prepared by



Scheme 1 Brief synthetic scheme of the K-Fe₅C₂@C/NPC nanocatalyst.

physically grinding Fe(C₅H₇O₂)₃ (iron precursor) and CH₄N₂O (nitrogen-doped carbon source) was transformed by thermal treatment under N₂ gas at 700 °C, H₂ gas at 350 °C and a CO atmosphere at 350 °C to achieve the desired phases (Fe₃C by the initial N₂ treatment, Fe by the sequential H₂ treatment, and Fe₅C₂ by the sequential CO treatment). After the serial thermal treatment, a K-free Fe₅C₂@C/NPC nanocatalyst was obtained. Next, to obtain the K-Fe₅C₂@C/NPC nanocatalyst, aqueous K solution using the K₂CO₃ salt as a K source was used to impregnate the Fe₅C₂@C/NPC nanocatalyst powders. This was followed by the performance of additional CO treatment at 350 °C. In the catalyst, the K-doped Fe₅C₂ nanoparticles were well dispersed on the carbon structure.

The transmission electron microscopy (TEM) images show the overall structures for the K-free and K-doped $Fe_5C_2@C/NPC$ nanocatalyst (Fig. 1a and b, respectively). The average particle size was 17.2 nm for K-free $Fe_5C_2@C/NPC$ and 17.4 nm for K-Fe₅C₂@C/NPC, as determined by measuring 200 particles in the



Fig. 1 TEM images of (a) K-free Fe₅C₂@C/NPC and (b) K-Fe₅C₂@C/NPC, (c) HAADF-STEM image and (d-f) elemental mapping images (green: Fe, red: K, cyan: N), and (g) HR-TEM image with the corresponding Fourier-transform pattern (inset of g) of the K-Fe₅C₂@C/NPC nanocatalyst. (h) XRD spectra of the K-free and K-doped Fe₅C₂@C/NPC nanocatalysts. The bars represent 100 nm (a and b), 50 nm (c-f) and 3 nm (g), respectively.

View Article Online **Materials Advances**

TEM images (Fig. S2, ESI[†]). The high-angle annular dark-field scanning transmission electron microscopy (HAADF-STEM) image clearly shows Fe5C2 nanoparticles as relatively bright spots originating from the Fe atoms (Fig. 1c). The elemental mappings of iron (green), potassium (red) and nitrogen (cyan) also indicate the uniform distribution of each component (Fig. 1d-f). The HRTEM image shows spherical K-Fe₅C₂ nanoparticles encapsulated within carbon shells (Fig. 1g). The carbon shells which encapsulate the nanoparticles originated from the carbonized product of urea during the initial calcination process under nitrogen gas. The lattice distance between neighbouring fringes (0.205 nm) and the corresponding Fourier-transform (FT) patterns, demonstrated the formation of iron-carbide crystals that matched the (510) planes of Hägg iron-carbide (Fe_5C_2).

The X-ray diffraction (XRD) spectra of the K-free and K-doped Fe₅C₂@C/NPC nanocatalysts show that both kinds of iron carbide particles well-matched with the Fe5C2 phase (Fig. 1f, JCPDS No. 36-1248; space group, C2/c). The broad diffraction peak near $2\theta = 25^{\circ}$ corresponds to the (002) plane of amorphous carbon. There was no difference between K-Fe₅C₂@C/NPC and K-free Fe₅C₂@C/NPC nanocatalysts. Using the Debye-Scherrer equation on the basis of peak broadening of the (020) reflection, the average crystal size of the Fe_5C_2 nanoparticles was calculated to be 17.2 nm for K-free Fe₅C₂(a)C/ NPC and 17.5 nm for the K-doped Fe₅C₂@C/NPC nanocatalyst. These results suggest that the K-doping in the catalyst caused no significant change in either the size or phase of the crystals.

To investigate the chemical structure and elemental surface state of Fe and N in the K-free and K-doped Fe₅C₂@C/NPC nanocatalysts, X-ray photoelectron spectroscopy (XPS) analysis was performed. The XPS spectra of the energy region of the Fe band exhibited assigned peaks from iron carbide (Fe(0)) at 706-707 eV and from iron-oxides (Fe(2+) and Fe(3+)) at 710-711 eV (Fig. 2a). Partial oxidation of the active iron-carbide nanoparticles occurs due to exposure to the atmosphere during the sampling processes. In the XPS spectrum, the K-doped Fe₅C₂ nanoparticles showed less intense peaks in the binding-energy ranges. Potassium can effectively stabilize the reduced iron surface against oxidation, as reported elsewhere.45 Because neighbouring K was more easily oxidized than Fe₅C₂, iron oxidation was suppressed. At the core-level the XPS spectrum of N 1s, two split peaks corresponding to pyridinic N at 400.6 eV and pyrrolic N at 398.4 eV were observed in both K-free and K-doped Fe₅C₂(a)C/ NPC nanocatalysts (Fig. 2b).

To evaluate the crystallinity and structure of the porous carbon framework of the K-Fe₅C₂@C/NPC nanocatalyst, Raman spectroscopy was performed (Fig. 2c). The G band near 1580 cm⁻¹ is characteristic of the vibration of sp²bonded carbon atoms in a 2D hexagonal lattice (E_{2g} mode). The strong peak at around 1350 cm^{-1} , called the D band, was ascribed to the dangling bonds of the in-plane terminations of disordered graphite. The second-order 2D band in the range of 2500–3000 $\rm cm^{-1}$ is typical of graphitic $\rm sp^2$ materials. The N-doped porous carbon demonstrated a high I_D/I_G value (~ 1.0) , suggesting the presence of many disordered sites in the carbon matrix.



Fig. 2 XPS spectra in the energy regions of (a) Fe 2p and (b) N 1s of the K-free Fe₅C₂@C/NPC and K-Fe₅C₂@C/NPC nanocatalysts and (c) Raman spectrum of the K-Fe₅C₂@C/NPC nanocatalyst.

The Brunauer-Emmett-Teller (BET) surface area and the porosity in the samples were investigated by N₂ sorption measurements (Fig. 3a). The K-Fe5C2@C/NPC nanocatalyst exhibited type IV adsorption-desorption hysteresis. The BET surface area and the pore volume measured were found to be 284.0 m² g⁻¹ and 0.22 cm³ g⁻¹, respectively. The pore size, calculated by the Barrett-Joyner-Halenda (BJH) method on the desorption branch, was observed to be 3.7 nm (Fig. 3b). From the results of inductively coupled plasma optical emission spectroscopy (ICP-OES), the Fe and K contents were found to be 33.7 and 1.3 wt%, respectively. The total N content in the Fe5C2@C/NPC sample was determined to be 5.0% using a nitrogen analyser (OHN-2000).

High-temperature Fischer-Tropsch synthesis (HT-FTS)

The reaction test with the K-Fe₅C₂@C/NPC nanocatalyst was performed at 1.5 MPa, 340 $^{\circ}$ C and a H₂/CO ratio = 1, under the high gas hourly space velocity (GHSV) conditions of 42 NL g_{cat}^{-1} h⁻¹. The CO conversion and selectivity of the catalysts were measured

Paper

Paper



Fig. 3 (a) N_2 sorption isotherms and (b) pore size distribution diagram of the K-Fe₅C@C/NPC nanocatalyst.

for 72 h over time-on-stream (TOS) by gas chromatography (GC) of the outlet gases containing the unreacted CO, H₂, CH₄, C₂–C₄ hydrocarbons and CO₂. Liquid oil and solid wax recovered in a cold trap and a hot trap, respectively, were further analysed using simulated distillation (SIMDIS). The K-free Fe₅C₂@C/NPC nanocatalyst was also used under the same reaction conditions for comparison with the K-doped Fe₅C₂@C/NPC nanocatalyst.

In HT-FTS, the reactions for paraffin and olefin hydrocarbon-product formation and the water-gas shift (WGS) reaction occur as indicated below:

$$n\text{CO} + (2n+1)\text{H}_2 \rightarrow \text{C}_n\text{H}_{2n+2} \text{ (paraffins)} + n\text{H}_2\text{O}$$
(1)

 $nCO + 2nH_2 \rightarrow C_nH_{2n} \text{ (olefins)} + nH_2O$ (2)

$$CO + H_2O \leftrightarrow CO_2 + H_2$$
 (3)

The K-Fe₅C₂@C/NPC nanocatalyst exhibited very high CO conversion even under high GHSV conditions of 42 NL g_{cat}^{-1} h⁻¹ (Fig. 4a). The CO conversion in the K-free Fe₅C₂@C/NPC catalyst gradually increased until ~78 h from 63.5% at TOS = 12 h to 96.0% at TOS = 78 h. On the other hand, the K-Fe₅C₂@C/NPC nanocatalyst showed much more rapidly stabilized CO conversions of 72.3% at TOS = 12 h and 92.5% at TOS = 18 h, finally reaching 96.7% at TOS = 78 h (Fig. 4b). The selectivity data of the K-doped Fe₅C₂@C/NPC nanocatalyst at TOS = 78 h were calculated to be CO₂ (39.4%), CH₄ (9.6%), C₂-C₄ (15.2%) and C₅₊ (35.8%) (Fig. 4c). These values are comparable to those of the K-free Fe₅C₂@C/NPC nanocatalyst (CO₂: 41.2%, CH₄: 10.2%, C₂-C₄: 15.1%, C₅₊: 33.5%) (Fig. 4d).



Fig. 4 (a and b) CO conversion and (c and d) Hydrocarbon product selectivity graph (a and c: K-Fe₅C₂@C/NPC nanocatalysts; b and d: K-free Fe₅C₂@C/NPC nanocatalysts). The reaction tests were conducted at 340 °C, 1.5 MPa, GHSV = 42 NL g_{cat}⁻¹ h⁻¹ and a H₂: CO ratio of 1. The total CO conversion is the sum of the CO conversion to hydrocarbons (CO to HC) and the CO conversion to CO₂ (CO to CO₂).

The activities of the catalysts were monitored as the iron-timeyield (FTY, *i.e.* the number of CO moles converted to hydrocarbons per gram of iron per second) over TOS (Fig. 5a). The K-Fe₅C₂@C/NPC nanocatalyst showed much faster stabilization behaviour, with a rapid increase of the FTY values (up to 4.4×10^{-4} mol_{CO} g_{Fe}⁻¹ s⁻¹), than did the K-free Fe₅C₂@C/NPC nanocatalyst. The FTY value of the K-Fe₅C₂@C/NPC nanocatalyst. The FTY value of the K-Fe₅C₂@C/NPC nanocatalyst was very high relative to the results reported previously for K-doped Fe catalysts (Table S1, ESI†). From the results, it was confirmed that the K added to the Fe₅C₂ particles contributes to the activation of the catalyst and increases the reactivity.

To determine the hydrocarbon product distributions and specific hydrocarbon productivity, the detailed composition of the liquid and solid hydrocarbons was determined by ASTM D2887 (Fig. 5b). The K-Fe₅C₂@C/NPC nanocatalyst showed higher C₂-C₄ olefins (16.7%) and diesel range C₁₃-C₁₈ hydrocarbons (4.4%), compared to K-free Fe₅C₂@C/NPC (Fig. 5c). The trend toward heavier hydrocarbons with this catalyst was also observed in relation to the chain-growth probability (α value) of the hydrocarbons. This was determined using the Anderson-Schulz-Flory (ASF) chain-growth mechanism in the following equation, where W_n is the weight fraction of hydrocarbons with carbon number *n* (Fig. 5d):

$$\log(W_n/n) = \log(\ln^2 \alpha) + n \log \alpha$$

Paper



80

40 45

C19+

40 45

Fig. 5 (a) FT activity, (b) total syncrude (C₅₊ hydrocarbons) distribution graphs, (c) Total hydrocarbon product distribution, and (d) ASF plots of C_{5+} hydrocarbons and chain-growth probability.

The α value of the hydrocarbons by K-free Fe₅C₂@C/NPC was calculated to be 0.7952, using the slope of the graph fitted to the linear regression at C5-C43. On the other hand, K-free



Fig. 6 (a) Specific hydrocarbon productivity and (b) $C_5 - C_{13}$ LAO selectivity and (c) productivity of K-free ${\rm Fe}_5{\rm C}_2@{\rm C/NPC}$ and ${\rm K-Fe}_5{\rm C}_2@{\rm C/NPC}$ nanocatalysts

Fe₅C₂@C/NPC showed two α values ($\alpha_1 = 0.7317$ at C₅-C₁₈ and $\alpha_2 = 0.8502$ at C₁₉-C₄₃) which are attributed to the K-lean sites and K-rich sites of the catalyst, respectively.

The total hydrocarbon (HC) product yield (grams of hydrocarbons generated per gram of iron per second) was measured after 78 h on-stream of the reaction (Fig. 6a). The K-Fe₅C₂@C/ NPC nanocatalyst shows a higher hydrocarbon product yield (5.48 $g_{HC} g_{cat}^{-1} h^{-1}$), than that of the K-free Fe₅C₂@C/NPC nanocatalyst (5.05 $g_{HC} g_{cat}^{-1} h^{-1}$). The yields using the former were calculated using the sum of the specific product yields [CH₄ (1.57), C₂–C₄ paraffins (1.06), C₂–C₄ olefins (0.91), C₅–C₁₂ (1.58), C_{13} - C_{18} (0.24) and C_{19+} (0.12) g_{HC} g_{cat}^{-1} h^{-1}]. The detailed yield values of each hydrocarbon product for the K-free Fe₅C₂@C/NPC nanocatalyst were CH₄ (1.41), C₂-C₄



Fig. 7 Geometry optimized structure of (a) K-free Fe_5C_2 and (b) K doped Fe_5C_2 nanoparticles. Dark orange, grey and purple balls indicate Fe, C and K atoms, respectively. (c) Bader charge difference and (d) differential charge density between K-free and K-Fe₅C₂ nanoparticles. The isosurface level was set to 0.003 e bohr⁻³. Yellow and cyan colors in the isosurface represent charge accumulation and depletion, respectively.

paraffins (0.98), C_2 - C_4 olefins (0.80), C_5 - C_{12} (1.54), C_{13} - C_{18} (0.21), and C_{19+} (0.11) $g_{HC} g_{cat}^{-1} h^{-1}$.

The specific C_5 - C_{13} LAO content in the liquid oil sample recovered after the HT-FTS reactions was obtained by detailed hydrocarbon analysis. The K-Fe5C2@C/NPC nanocatalyst also showed higher selectivity for C₅-C₁₃ LAOs (16.5 wt%), which is the sum of C₅ LAO (4.7 wt%), C₆ LAO (4.4 wt%), C₇ (3.2 wt%), C₈ LAO (1.8 wt%), C₉ LAO (1.1 wt%), C₁₀ LAO (0.6 wt%), C₁₁ LAO (0.4 wt%), C_{12} LAO (0.3 wt%), and C_{13} LAO (0.2 wt%), compared to the K-free Fe₅C₂@C/NPC nanocatalyst (12.5 wt%) (Fig. 6b). The C₅-C₁₃ LAO productivity data (the number of CH₂ micromoles assigned to LAOs per gram of catalyst per second) of reactions with K-free Fe5C2@C/NPC and K-Fe5C2@C/NPC nanocatalysts were also calculated, based on the C5-C13 LAO contents obtained (Fig. 6c). The K-Fe₅C₂@C/NPC nanocatalyst showed $\sim\!1.5$ times higher total C5–C13 LAO productivity (5.9 CH2 μmol g_{cat}^{-1} s⁻¹) than that of the K-free Fe₅C₂@C/NPC nanocatalyst (4.0 CH₂ μ mol g_{cat}⁻¹ s⁻¹).

After 78 h of the HT-FTS reaction, the recovered K-Fe₅C₂@C/NPC nanocatalyst showed high stability, maintaining its original structure without particle aggregation, as a result of the carbon shells protecting the Fe₅C₂ particles (Fig. S3, ESI†).

Theoretical investigation of the K-promotion effect

To elucidate the origin of the enhanced LAO selectivity, spinpolarized DFT calculations and subsequent charge density analyses were performed for the K-free Fe_5C_2 and K-Fe₅C₂ nanoparticles (Fig. 7a and b). Both Bader charge and differential charge density analyses revealed that K adsorption on the Fe_5C_2 nanoparticles promotes active electron transfer from K to the

Table 1 Calculated adsorption energy of C_5-C_8 olefins on the K-free ${\sf Fe}_5C_2$ and ${\sf K}\text{-}{\sf Fe}_5C_2$ nanoparticles

	Adsorption energy (eV)			
System	$\overline{C_5H_{10}}$	C_6H_{12}	C_7H_{14}	C_8H_{16}
K-free Fe ₅ C ₂ K-Fe ₅ C ₂	$-1.30 \\ -0.81$	$-1.59 \\ -1.01$	$-1.35 \\ -0.55$	$-1.72 \\ -1.15$

adjacent Fe atoms and that these Fe atoms become less positively charged (Fig. 7c and d). The active electron transfer and charge state of the substrate metal atoms have been demonstrated to play an important role in determining the adsorption strength between olefins and metal atoms *via* π -complexation. In such cases, the metal atoms with more positive charges enhance olefin adsorption.^{46–50} Thus, the olefin adsorption calculations on the K-free Fe₅C₂ and K-Fe₅C₂ nanoparticles were performed (Fig. S4, ESI†) and the adsorption energy was calculated using the following equation:

$$E_{ads} = E_{(olefin/nanoparticle)} - [E_{(olefin)} + E_{(nanoparticle)}]$$

where $E_{\text{(olefin)}}$, $E_{\text{(nanoparticle)}}$ and $E_{\text{(olefin/nanoparticle)}}$ are the total energy of an isolated olefin molecule, the K-free nanoparticle or K-Fe₅C₂ nanoparticle and the system after adsorption, respectively. The adsorption site was chosen to be the Fe atom adjacent to K indicated by an arrow in Fig. 7a and b. The calculated adsorption energies of C₅–C₈ olefins on the K-free Fe₅C₂ and K-Fe₅C₂ nanoparticles are summarized (Table 1). It was clearly observed that the adsorption energy of olefins on the K-Fe₅C₂ nanoparticles becomes weaker than that on K-free Fe₅C₂ nanoparticles, which is attributed to electron accumulation on the Fe atoms. Therefore, we postulate that K doping of Fe₅C₂ nanoparticles promotes facile dissociation of C₅–C₈ olefins *via* lowering of the chemisorption energy.

Conclusions

K-doped Fe₅C₂@C/NPC nanocatalyst, bearing highly active and stable Fe_5C_2 nanoparticles (~17 nm) encapsulated within carbon shells, were prepared via subsequent thermal treatment under the flows of N₂, H₂ and CO followed by K impregnation. From computational simulations, it appears that Fe_5C_2 particles with a small amount of K (~ 1 wt%, K/Fe = 0.05) exhibit facile C_5 - C_8 olefin dissociation via lowering of the chemisorption energy. The K-doped Fe5C2@C/NPC showed high FT activity and CO conversion (~97%), as well as good selectivity for C5-C13 LAOs with excellent stability. The K promotion led to facile CO adsorption and dissociation, which increased the basicity of the active Fe₅C₂ surface. The appropriate electronic state derived from the K-doped Fe5C2 nanoparticles resulted in enhanced selectivity for C5-C13 LAOs along with control of the hydrogenation and desorption rates. In addition, the high load of active Fe (\sim 34 wt%) with its uniform dispersion on the nitrogen-doped porous carbon support also contributed to enhanced activity and productivity in HT-FTS. With its enhanced CO conversion, reduced induction period and increased

selectivity for C₅–C₁₃ LAOs, it is anticipated that the K-doped $Fe_5C_2@C/NPC$ nanocatalyst could optimize the sustainable production of valuable LAOs from HT-FTS.

Author contributions

Jin Hee Lee: FTS experiment and drafting; Hack-Keun Lee: data curation and drafting; Kwangsoo Kim: DFT calculation; Geun Bae Rhim: data curation; Min Hye Youn: investigation; Heon-Do Jeong: visualization; Jong Hyeok Park: visualization; Dong Hyun Chun: conceptualization and editing; Byung-Hyun Kim: computer simulation and writing; Ji Chan Park: conceptualization, methodology and writing.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was conducted within the framework of a research and development program of the Korea Institute of Energy Research (C0-2419-02) and funded by the National Research Foundation of Korea (NRF) grant funded by the Korea government (No. 2019R1A2C2086827). This work was also supported by the National Supercomputing Center with supercomputing resources including technical support (KSC-2019-CRE-0202).

Notes and references

- 1 M. Chen, W. Lu, H. Zhu, L. Gong, Z. Zhao and Y. Ding, *Ind. Eng. Chem. Res.*, 2020, **59**, 4388.
- 2 A. Gollwitzer, T. Dietel, W. P. Kretschemer and R. Kempe, *Nat. Commun.*, 2017, **8**, 1226.
- 3 A. Chatterjee, S. H. H. Eliasson, K. W. Törnroos and V. R. Jensen, *ACS Catal.*, 2016, **6**, 7784.
- 4 Y. Kim, H. B. Im, U. H. Jung, J. C. Park, M. H. Youn, H.-D. Jeong, D.-W. Lee, G. B. Rhim, D. H. Chun, K. B. Lee and K. Y. Koo, *Fuel*, 2019, **256**, 115957.
- 5 G. P. Belov and P. E. Matkovsky, *Petroleum Chem.*, 2010, **50**, 283.
- 6 B. L. Small and M. Brookhart, J. Am. Chem. Soc., 1998, 120, 7143.
- 7 W. Keim, Angew. Chem., Int. Ed., 2013, 52, 12492.
- 8 J. Zheng, J. Cai, F. Jiang, Y. Xu and X. Liu, *Catal. Sci. Technol.*, 2017, 7, 4736.
- 9 M. K. Khan, P. Butolia, H. Jo, M. Irshad, D. Han, K.-W. Nam and J. Kim, *ACS Catal.*, 2020, **10**, 10325.
- 10 J. Wang, Y. Xu, G. Ma, J. Lin, H. Wang, C. Zhang and M. Ding, *Appl. Mater. Interfaces*, 2018, **10**, 43578.
- 11 S. L. Soled, E. Iglesia, S. Miseo, B. A. DeRites and R. A. Fiato, *Top. Catal.*, 1995, **2**, 193.
- 12 S. Yang, S. Lee, S. C. Kang, S. J. Han, K.-W. Jun, K.-W. Lee and Y. T. Kim, *RSC Adv.*, 2019, **9**, 14176.
- 13 Q. Zhang, J. Kang and Y. Wang, *ChemCatChem*, 2010, 2, 1030.

- 14 H. M. T. Galvis, J. H. Bitter, C. B. Khare, M. Ruitenbeek, A. I. Dugulan and K. P. de Jong, *Science*, 2012, 335, 835.
- 15 S. O. Moussa, L. S. Panchakarla, M. Q. Ho and M. S. El-Shall, *ACS Catal.*, 2014, 4, 535.
- 16 S. Jang, S. W. Kang, D. H. Chun, H.-T. Lee, J.-I. Yang, H. Jung, H.-D. Jeong, K. M. Nam and J. C. Park, *New J. Chem.*, 2017, **41**, 2756.
- 17 V. V. Ordomsky, B. Legras, K. Cheng, S. Paul and A. Y. Khodakov, *Catal. Sci. Technol.*, 2015, **5**, 1433.
- 18 S. W. Kang, K. H. Kim, D. H. Chun, J.-I. Yang, H.-T. Lee, H. Jung, J. T. Lim, S. H. Jang, C. S. Kim, C. W. Lee, S. H. Joo, J. W. Han and J. C. Park, *J. Catal.*, 2017, **349**, 66–74.
- 19 Z. Tian, C. Wang, J. Yue, X. Zhang and L. Ma, *Catal. Sci. Technol.*, 2019, **9**, 2728.
- 20 F. Jiang, M. Zhang, B. Liu, Y. Xu and X. Liu, *Catal. Sci. Technol.*, 2017, 7, 1245.
- 21 P. A. Chernavskii, V. O. Kazak, G. V. Pankina, Y. D. Perfiliev, T. Li, M. Virginie and A. Y. Khodakov, *Catal. Sci. Technol.*, 2017, 7, 2325.
- 22 Y. Cheng, J. Lin, K. Xu, H. Wang, X. Yao, Y. Pei, S. Yan, M. Qiao and B. Zong, ACS Catal., 2016, 6, 389.
- 23 W. N. Hoc, Y. Zhang, R. J. O'brien, M. Luo and B. H. Davis, *Appl. Catal.*, *A*, 2002, **236**, 77.
- 24 L. Guo, J. Sun, X. Ji, J. Wei, Z. Wen, R. Yao, H. Xu and Q. Ge, *Nat. Commun.*, 2018, 1, 11.
- 25 L. Guo, Y. Cui, H. Li, Y. Fang, R. Prasert, J. Wu, G. Yang,
 Y. Yoneyama and N. Tsubaki, *Catal. Commun.*, 2019,
 130, 105759.
- 26 J. Xie, J. Yang, A. I. Dugulan, A. Holmen, D. Chen, K. P. de Jong and M. J. Louwerse, ACS Catal., 2016, 6, 3147.
- 27 C.-F. Huo, B.-S. Wu, P. Gao, Y. Yang, Y.-W. Li and H. Jiao, Angew. Chem., Int. Ed., 2011, 50, 7403.
- 28 J. C. Park, S. Jang, G. B. Rhim, J. H. Lee, H. Choi, H.-D. Jeong, M. H. Youn, D.-W. Lee, K. Y. Koo, S. W. Kang, J.-I. Yang, H.-T. Lee, H. Jung, C. S. Kim and D. H. Chun, *Appl. Catal.*, *A*, 2018, **564**, 190.
- 29 J. C. Park, S. C. Yeo, D. H. Chun, J. T. Lim, J.-I. Yang, H.-T. Lee, S. Hong, H. M. Lee, C. S. Kim and H. Jung, *J. Mater. Chem. A*, 2014, 2, 14371.
- 30 V. P. Sanots, T. A. Wenzendonk, J. J. D. Jaén, A. I. Dugulan, M. A. Nasalevich, H.-U. Islam, A. Chojecki, S. Sartipi, X. Sun, A. A. Hakeem, A. C. J. Koeken, M. Ruitenbeek, T. Davidian, G. R. Meima, G. Sankar, F. Kapteijn, M. Makkee and J. Gascon, *Nat. Commun.*, 2015, 6, 6451.
- 31 L. O. Arteta, M. J. V. Romero, T. Wezendonk, F. Kaptein and J. Gascon, *Catal. Sci. Technol.*, 2018, 8, 210.
- 32 S. Y. Hong, D. H. Chun, J.-I. Yang, H. Jung, H.-T. Lee, S. Hong, S. H. Jang, J. T. Lim, C. S. Kim and J. C. Park, *Nanoscale*, 2015, 7, 16616.
- 33 H.-K. Lee, J. H. Lee, J. H. Seo, D. H. Chun, S. W. Kang,
 D. W. Lee, J.-I. Yang, G. B. Rhim, M. H. Youn, H.-D. Jung,
 H. Jung and J. C. Park, *J. Catal.*, 2019, 378, 289.
- 34 J. H. Lee, H.-K. Lee, D. H. Chun, H. Choi, G. B. Rhim,
 M. H. Youn, H. Jeong, S. W. Kang, J.-I. Yang, H. Jung,
 C. S. Kim and J. C. Park, *Nano Res.*, 2019, **12**, 2568.
- 35 G. Kresse and J. Hafner, Phys. Rev. B: Condens. Matter Mater. Phys., 1993, 47, 558.

- 36 G. Kresse and J. Hafner, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1994, **49**, 14251.
- 37 G. Kresse and J. Furthmüller, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1996, **54**, 11169.
- 38 G. Kresse and J. Furthmüller, Comput. Mater. Sci., 1996, 6, 15.
- 39 M. Dion, H. Rydberg, E. Schröder, D. C. Langreth and
- B. I. Lundqvist, Phys. Rev. Lett., 2004, 92, 246401.
- 40 G. Román-Pérez and J. M. Soler, *Phys. Rev. Lett.*, 2009, **103**, 096102.
- 41 K. Lee, E. D. Murray, L. Kong, B. I. Lundqvist and D. C. Langreth, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2010, 82, 081101.
- 42 J. Klimeš, D. R. Bowler and A. Michaelides, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2011, 83, 195131.

- 43 P. E. Blöchl, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1994, 50, 17953.
- 44 G. Kresse and D. Joubert, Phys. Rev. B: Condens. Matter Mater. Phys., 1999, 59, 1758.
- 45 J. Gaube and H.-F. Klein, Appl. Catal., A, 2008, 350, 126.
- 46 J. P. Chen and R. T. Yang, Langmuir, 1995, 11, 3450.
- 47 H. Y. Huang, J. Padin and R. T. Yang, J. Phys. Chem. B, 1999, 103, 3206.
- 48 S. W. Kang, K. Char and Y. S. Kang, *Chem. Mater.*, 2008, **20**, 1308.
- 49 R. Faiz and K. Li, Chem. Eng. Sci., 2012, 73, 261.
- 50 Y. Eum, B. S. Kim, I. S. Chae, G. H. Moon, S. C. Park, J. Jang and Y. S. Kang, *Macromol. Res.*, 2020, **28**, 1026.