Volume 3 Number 7 7 April 2021 Pages 1779-2106

Nanoscale Advances

rsc.li/nanoscale-advances



ISSN 2516-0230



COMMUNICATION Yasukazu Kobayashi *et al.* Porous intermetallic Ni₂XAI (X = Ti or Zr) nanoparticles prepared from oxide precursors



Nanoscale Advances

COMMUNICATION

Check for updates

Cite this: Nanoscale Adv., 2021, 3, 1901

Porous intermetallic Ni₂XAl (X = Ti or Zr) nanoparticles prepared from oxide precursors \dagger

Yasukazu Kobayashi, 🕩 *a Shohei Tada 🕩 b and Ryuji Kikuchi 🕩 c

Received 19th January 2021 Accepted 17th February 2021

DOI: 10.1039/d1na00047k

rsc.li/nanoscale-advances

Porous intermetallic Ni₂XAl (X = Ti or Zr) nanoparticles with small crystallite sizes (24–34 nm) and high Brunauer–Emmett–Teller (BET) surface areas (10–71 m² g⁻¹) were prepared from oxide precursors by a chemical route. CaH₂ acted as a template to form the porous morphologies and assisted the reduction.

Heusler intermetallic compounds have attracted interest because of their applications in magnets, semiconductors, and thermoelectric materials.¹⁻³ They are denoted as XYZ (half-Heusler structure) or X₂YZ (full-Heusler structure), where X and Y are transition metals, and Z is a p-block metal. Some Heusler compounds such as Co2MnGe and Ni2TiAl have shown catalytic activities in hydrogenation and oxidation.4-6 Their catalytic activities can be tuned by substitution (e.g., X_2YZ_{1-x} - Z'_{x}), allowing for fine adjustments of the electronic state (ligand effect) and atomic arrangement (ensemble effect) on the surface where heterogeneous catalytic reactions occur. However, difficulty in obtaining Heusler intermetallic powders with high surface areas hinders their practical application as catalysts. preparing high-surface-area intermetallics, Commonly, including early transition metals such as La, Y, Ti, and Zr, is challenging because of the strong oxygen affinities of these metals.⁷⁻⁹ Therefore, they have been prepared by physical approaches in oxygen- and moisture-free conditions. Zr_{0.5}-Hf_{0.5}CoSb_{0.8}Sn_{0.2},¹⁰ Hf_{0.75}Zr_{0.25}NiSn_{0.99}Sb_{0.01},¹¹ and MCo_{1-x}Fe_x- $Sn_{\nu}Sb_{1-\nu}~(M~=~Ti,~Zr,~and~Hf)^{12}$ have been prepared by mechanical ball milling. Vapor deposition-based approaches have been used to prepare Fe₃Si¹³ and Co₃Si.¹⁴ However, these

methods are not practical for applications,^{15–17} whereas the chemical approach is more scalable but challenging. Chemical preparation of some Heusler nanoparticles, such as Fe₃Si¹⁸ and Co₂FeAl,^{19–23} has been reported, but chemically prepared Heusler nanoparticles involving early transition metals have not been reported. Besides, although multicomponent alloys with early transition metals have been studied, such as high-entropy PtPdRhRuCe for ammonia oxidation²⁴ and high-entropy CoFe-LaNiPt for electrocatalytic water splitting,²⁵ it is necessary to develop simple and versatile techniques for the preparation of nano-sized multicomponent alloys involving hard-to-reduce metals.

Previously, we have reported the preparation of high-surfacearea intermetallic nanoparticles, Ni₃Al (13-27 m² g⁻¹)^{26,27} and NiAl $(94-114 \text{ m}^2 \text{ g}^{-1})$,^{27,28} by a chemical route. NiAl oxide precursors, NiO and NiAl₂O₄, were reduced to form porous intermetallic nanostructures in a molten LiCl-CaH₂ system. In the molten LiCl at 600 °C, CaH₂ works as a reducing as well as dehydration agent. Although pure Al tends to react with oxygen, molten LiCl prevents oxide formation and promotes the formation of NiAl and Ni₃Al at 600 °C. The obtained intermetallic nanoparticles had high surface areas attributed to porous structures formed by CaO and CaH2, which acted as a template. The proposed preparation method was then applied to various intermetallic nanoparticles, such as YNi₂Si₂, LaNi₂Si₂,²⁹ Pt₂Y,³⁰ and NiZn.31 In this study, we prepared high-surface-area Heusler nanoparticles comprising early transition metals. Ni2TiAl was selected because of its catalytic applications in steam reforming of methanol,6 whereas Ni2ZrAl was prepared to demonstrate the versatility of the method. This is the first report on the chemical preparation of Heusler nanoparticles involving early transition metals. Finally, the prepared nanoparticles were used for CO₂ activation to evaluate their catalytic performances.

Intermetallic Ni₂XAl (X = Ti or Zr) nanoparticles were prepared by reducing oxide precursors in a LiCl–CaH₂ mixture at 600 °C.²⁶⁻³¹ First, Ni(NO₃)₂·6H₂O, X material (TiCl₄ or ZrO(NO₃)₂·2H₂O), Al(NO₃)₃·9H₂O, and glycine were dissolved in distilled water in a molar ratio of Ni/X/Al/glycine = 2/1/1/4.8.



View Article Online

View Journal | View Issue

Nanoscale Adv., 2021, 3, 1901-1905 | 1901

[&]quot;Interdisciplinary Research Center for Catalytic Chemistry, National Institute of Advanced Industrial Science and Technology (AIST), 1-1-1 Higashi, Tsukuba, Ibaraki 305-8565, Japan. E-mail: yasu-kobayashi@aist.go.jp

^bDepartment of Materials Science and Engineering, Ibaraki University, 4-12-1 Nakanarusawacho, Hitachi, Ibaraki 316-8511, Japan

^cDepartment of Chemical System Engineering, The University of Tokyo, 7-3-1 Hongo, Bunkyo-ku, Tokyo 113-8656, Japan

[†] Electronic supplementary information (ESI) available. See DOI: 10.1039/d1na00047k

The solution was then dried at 110 °C overnight, and the dried powder was finally heated at 500 °C in the air for 2 h to obtain the oxide precursor Ni₂TiAl(Pre) or Ni₂ZrAl(Pre). The oxide precursor CaH₂ and LiCl were next mixed in a mortar in a weight ratio of precursor/CaH₂/LiCl = 0.2/0.4/0.2. The mixed powder was then loaded in a stainless-steel reactor and heated at 600 °C for 2 h under Ar. Finally, the treated precursor was crushed in a mortar and rinsed with 0.1 M NH₄Cl aqueous solution and distilled water, and the final powder, Ni₂TiAl(RDT) or Ni₂ZrAl(RDT), was obtained. Characterization and catalytic tests are described in ESI.†

Fig. 1 shows the X-ray diffraction (XRD) patterns of Ni₂-TiAl(Pre) and Ni₂TiAl(RDT). For Ni₂TiAl(Pre), the peaks were assigned to NiO and Al₂O₃. Titanium-based oxides were not observed. Next, the precursor was reduced by the chemical approach, where the oxide precursor was reduced in a LiCl-CaH₂ system at 600 °C. For the reduced powder of Ni₂TiAl(RDT), the XRD peaks were mostly assigned to the intermetallic Ni₂TiAl phase. The crystallite size of Ni₂TiAl was estimated as 24 nm from the Scherrer equation (Table S1[†]).

The morphology of Ni₂TiAl(RDT) was then investigated by Scanning Electron Microscope (SEM) (Fig. 2 and S1-S3†) and (Scanning) Transmission Electron Microscope ((S)TEM) (Fig. 3 and S4-S8[†]) with energy-dispersive X-ray spectroscopy (EDS) analysis. Small particles of <100 nm interconnected to form porous structures. Moiré fringes indicate good crystallinity. Molar ratios of Ni, Ti, and Al in Ni2TiAl(RDT) calculated by SEM and TEM-EDS were consistent with the stoichiometric ratio of the intermetallic Ni₂TiAl phase. On the elemental mappings, Ni, Ti, and Al are distributed evenly, and their positions are overlapped, indicating the homogeneity of the Ni₂TiAl phase. Molar ratios of oxygen were relatively high in SEM and TEM-EDS, and the high-angle annular dark-field (HAADF)-STEM images show a high concentration of oxygen on the sample surface (Fig. 3, S7 and S8[†]). Because Ti and Al are readily oxidized in comparison with Ni, the sample surface was covered by titanium and aluminum oxides although they were not identified by XRD. Impurities such as Ca, Cl, and Li were not detected in Ni₂-TiAl(RDT), except for oxygen. Therefore, rinsing with NH₄Cl



Fig. 1 XRD patterns of an oxide precursor of $Ni_2TiAl(Pre)$ and the reduced sample of $Ni_2TiAl(RDT)$.



removed these element-related species, such as CaO, CaH_2 , $CaCl_2$, LiCl, and so on.

The surface area and porosity of Ni₂TiAl(RDT) were examined by nitrogen adsorption/desorption. Fig. 4 shows the isotherm curves and the corresponding pore size distribution. The physical values calculated from the curves are summarized in Table S1.† Ni₂TiAl(RDT) showed large nitrogen adsorption indicated by a high BET surface area (71 m² g⁻¹). Small hysteresis was observed between the adsorption and desorption



Fig. 3 HAADF-STEM images of Ni₂TiAl(RDT) and its elemental analysis.



Fig. 4 (a) Adsorption and desorption isotherms of nitrogen and (b) pore size distribution of $Ni_2TiAl(RDT)$.

curves, and a porous structure was suggested by a Barrett-Joyner-Halenda (BJH) method with mesopore sizes of <10 nm. A similar pore size distribution was observed in our previous reports for mesoporous NiAl,27,28 indicating that calcium species such as CaH₂ and CaO worked as a template in molten LiCl. Table S2[†] summarizes BET surface areas and preparation methods of reported nickel-based aluminides. The BET surface area of Ni₂TiAl powder prepared by arc melting is very small $(0.13 \text{ m}^2 \text{ g}^{-1})$. Thus, the Ni₂TiAl powder prepared in this study had more than two orders of magnitude BET surface area compared to that prepared by arc melting. In addition, the reported BET surface areas of nickel aluminides prepared by physical and chemical methods are 15–27 m² g⁻¹. Our method provided remarkably high BET surface areas because of the porous structures. Enhanced catalyst durability and stable activity in ordered nanoporous alloys have been suggested due to their superior mechanical strength.³² Thus the prepared porous intermetallic nanoparticles could be promising catalysts from the practical point of view.

Next, surface states of Ni₂TiAl(RDT) and the Ar⁺-etched sample, denoted by Ni₂TiAl(RDT)-etch, were analyzed by X-ray Photoelectron Spectroscopy (XPS) measurements. Fig. 5 shows the XPS spectra corresponding to Ni $2p_{3/2}$, Ti $2p_{3/2}$, Al 2p, and Ni

3p. In Fig. 5(a), the Ni 2p_{3/2} spectrum of Ni₂TiAl(RDT) had a peak at 856.1 eV (ref. 33) assigned to Ni³⁺. It is noteworthy that the spectrum of Ni2TiAl(RDT)-etch had an intense peak of metallic Ni at 852.8 eV (ref. 34) (Fig. 5(c)), where an intense peak of metallic Ni was also observed at 66.1 eV.35 In Fig. 5(b), the Ti 2p_{3/2} spectrum of Ni₂TiAl(RDT) had a peak at 459.6 eV of Ti⁴⁺, whereas the spectrum of Ni2TiAl(RDT)-etch was separated into four peaks: Ti⁰, Ti²⁺, Ti³⁺, and Ti⁴⁺.^{36,37} The results suggest that the etching treatment partially removed the titanium oxide layer. In Fig. 5(c), the Al 2p spectrum of Ni₂TiAl(RDT) had a peak at 74.8 eV corresponding to AlO_{x} , ^{38,39} confirming the formation of the surface oxide layer. The spectrum of Ni₂TiAl(RDT)-etch had a clear peak corresponding to metallic Al at 72.3 eV.38,39 These results for Ni₂TiAl(RDT) indicate the presence of the surface oxide layer, consistent with the results of STEM observations. Importantly, the oxide layer was thin enough to be mostly removed by etching, and the existence of Ni-Ti-Al alloy, which could be an intermetallic Ni₂TiAl phase, below the oxide layer was confirmed by XPS measurements. Thus, porous Ni₂-TiAl nanoparticles are suitable to be used in catalytic applications.

Next, Ni₂ZrAl(RDT) was prepared and characterized similarly to Ni₂TiAl(RDT) to demonstrate the versatility of the method (Fig. S9–S17 and Table S1†). The Ni₂ZrAl phase was obtained with a crystallite size of 34.4 nm and a BET surface area of 10.3 $m^2 g^{-1}$. Impurities such as NiAl, Ni₁₀Zr₇, and NiZr were observed, resulting in the lower surface area of Ni₂ZrAl(RDT) compared with that of Ni₂TiAl(RDT).

Finally, the catalytic performances of the prepared intermetallic compounds were evaluated in CO₂ activation. The results are shown in Fig. 6. To evaluate the intrinsic catalytic performances, we calculated the turnover frequency (TOF) (Tables S3 and S4[†]). The TOF for CO₂ activation, TOF(CO₂), was in the order of Ni₂ZrAl(RDT) > NiAl > Ni₂TiAl(RDT) at 400 °C, indicating that Ni₂ZrAl(RDT) activated CO₂ more than did NiAl. In a lower reaction temperature range, TOF(CO₂) and TOF(CH₄) were in the order of NiAl > Ni₂ZrAl(RDT) > Ni₂TiAl(RDT). These trends indicated that the substitution of half of Al with Ti and Zr in NiAl harmed the CO₂ activation for methane formation. The order of apparent activation energies (*E*_a) was given as



Fig. 5 XPS spectra of (a) Ni 2p_{3/2}, (b) Ti 2p_{3/2}, and (c) Al 2p and Ni 3p for Ni₂TiAl(RDT) and Ni₂TiAl(RDT)-etch with references of Ni powder, TiO₂, and Al₂O₃.



Fig. 6 (a) TOF for CO₂ activation and (b) TOF for CH₄ production as functions of reaction temperature, and (c) the Arrhenius plots for NiAl, Ni₂TiAl(RDT), and Ni₂ZrAl(RDT).

 $Ni_2ZrAl(RDT)$ (104 kJ mol⁻¹) > NiAl (65 kJ mol⁻¹) > Ni₂TiAl(RDT) (61 kJ mol⁻¹). $Ni_2ZrAl(RDT)$ gave a high Ea value close to 99 kJ mol⁻¹ of the CeO₂-supported Ni catalyst.⁴⁰ On the other hand, NiAl and Ni₂TiAl(RDT) showed low Ea values similar to 70 kJ mol⁻¹ of the sponge Ni catalyst.⁴⁰ Thus, the active sites on NiAl and Ni₂TiAl(RDT) could be in the same state as that of sponge Ni to catalyze CO₂ activation, suggesting that the nonsupported metallic catalysts could decrease the energy barrier for CO₂ activation.

Conclusions

Porous intermetallic Ni₂XAl (X = Ti or Zr) nanoparticles were prepared using CaH₂ as a reducing agent in molten LiCl at 600 °C. The obtained BET surface areas were two orders of magnitude higher than those of powder samples prepared by arc melting. The versatility of our method allows for the preparation of porous intermetallic aluminide nanoparticles. The prepared Ni₂ZrAl showed a higher TOF(CO₂) at 400 °C than NiAl, whereas the Ni₂TiAl activated CO₂ with a lower activation energy than a reported supported catalyst. These findings suggested a potential advantageous application of the prepared nanoparticles in CO₂ activation.

Author contributions

YK carried out the experiments including synthesis and characterization. YK also conceptualized the project and supervised the research work. ST performed the experiments for XPS analysis and catalytic activity evaluation. RK discussed the results, helped to prepare the manuscript. All authors carried out the required revisions.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The Center for Instrumental Analysis at Ibaraki University is acknowledged.

Notes and references

- 1 F. Casper, T. Graf, S. Chadov, B. Balke and C. Felser, *Semicond. Sci. Technol.*, 2012, 27, 063001.
- 2 J.-W. G. Bos and R. A. Downie, J. Phys.: Condens. Matter, 2014, 26, 433201.
- 3 M. Yin, J. Hasier and P. Nash, J. Mater. Sci., 2016, 51, 50.
- 4 T. Kojima, S. Kameoka and A.-P. Tsai, *ACS Omega*, 2017, 2, 147.
- 5 T. Kojima, S. Kameoka, S. Fujii, S. Ueda and A.-P. Tsai, *Sci. Adv.*, 2018, **4**, eaat6063.
- 6 T. Kojima, S. Kameoka and A.-P. Tsai, *ACS Omega*, 2019, 4, 21666.
- 7 M. Armbrüster, R. Schlögl and Y. Grin, *Sci. Technol. Adv. Mater.*, 2014, **15**, 034803.
- 8 S. Furukawa and T. Komatsu, ACS Catal., 2017, 7, 735.
- 9 Y. Gong, J. Wu, M. Kitano, J. Wang, T.-N. Ye, J. Li, Y. Kobayashi, K. Kishida, H. Abe, Y. Niwa, H. Yang, T. Tada and H. Hosono, *Nat. Catal.*, 2018, **1**, 178.
- 10 X. Yan, G. Joshi, W. Liu, Y. Lan, H. Wang, S. Lee, J. W. Simonson, S. J. Poon, T. M. Tritt, G. Chen and Z. F. Ren, *Nano Lett.*, 2011, 11, 556.
- 11 G. Joshi, X. Yan, H. Wang, W. Liu, G. Chen and Z. Ren, *Adv. Energy Mater.*, 2011, **1**, 643.
- 12 C. Wang, J. Meyer, N. Teichert, A. Auge, E. Rausch, B. Balke, A. Hütten, G. H. Fecher and C. Felser, *J. Vac. Sci. Technol., B: Nanotechnol. Microelectron.: Mater., Process., Meas., Phenom.*, 2014, **32**, 020802.
- 13 Y. Jing, Y. Xu and J.-P. Wang, *J. Appl. Phys.*, 2009, **105**, 07B520.
- 14 K. Seo, S. Lee, H. Yoon, J. K. S. K. Varadwaj, Y. Jo, M.-H. Jung, J. Kim and B. Kim, *ACS Nano*, 2009, 3, 1145.

- 15 T. Ogawa, Y. Kobayashi, H. Mizoguchi, M. Kitano, H. Abe, T. Tada, Y. Toda, Y. Niwa and H. Hosono, *J. Phys. Chem. C*, 2018, **122**, 10468.
- 16 Y. Lu, J. Li, T.-N. Ye, Y. Kobayashi, M. Sasase, M. Kitano and H. Hosono, *ACS Catal.*, 2018, **8**, 11054.
- 17 T.-N. Ye, Y. Lu, Y. Kobayashi, J. Li, S.-W. Park, M. Sasase, M. Kitano and H. Hosono, *J. Phys. Chem. C*, 2020, **124**, 28589.
- 18 N. Dahal and V. Chikan, Chem. Mater., 2010, 22, 2892.
- 19 J. H. Du, Y. L. Zuo, Z. Wang, J. H. Ma and L. Xi, J. Mater. Sci. Technol., 2013, 29, 245.
- 20 C. H. Wang, Y. Z. Guo, F. Casper, B. Balke, G. H. Fecher, C. Felser and Y. Hwu, *Appl. Phys. Lett.*, 2010, **97**, 103106.
- 21 C. Wang, L. Basit, Y. Khalavka, Y. Guo, F. Casper, T. Gasi, V. Ksenofontov, B. Balke, G. H. Fecher, C. Sönnichsen, Y.-K. Hwu, J.-J. Lee and C. Felser, *Chem. Mater.*, 2010, 22, 6575.
- 22 C. Wang, F. Casper, Y. Guo, T. Gasi, V. Ksenofontov, B. Balke, G. H. Fecher, C. Felser, Y.-K. Hwu and J.-J. Lee, *J. Appl. Phys.*, 2012, **112**, 124314.
- 23 C. Wang, F. Casper, T. Gasi, V. Ksenofontov, B. Balke,
 G. H. Fecher, C. Felser, Y.-K. Hwu and J.-J. Lee, *J. Phys. D: Appl. Phys.*, 2012, 45, 295001.
- 24 Y. Yao, Z. Huang, P. Xie, S. D. Lacey, R. J. Jacob, H. Xie, F. Chen, A. Nie, T. Pu, M. Rehwoldt, D. Yu, M. R. Zachariah, C. Wang, R. Shahbazian-Yassar, J. Li and L. Hu, *Science*, 2018, 359, 1489.
- 25 M. W. Glasscott, A. D. Pendergast, S. Goines, A. R. Bishop, A. T. Hoang, C. Renault and J. E. Dick, *Nat. Commun.*, 2019, **10**, 2650.

- 26 Y. Kobayashi, Chem. Lett., 2019, 48, 1496.
- 27 Y. Kobayashi, S. Tada and R. Kikuchi, J. Chem. Eng. Jpn., 2020, 53, 562.
- 28 Y. Kobayashi, S. Tada and R. Kikuchi, *Chem. Lett.*, 2020, **49**, 341.
- 29 Y. Kobayashi, S. Tada and R. Kikuchi, *Mater. Trans.*, 2020, **61**, 1037.
- 30 Y. Kobayashi, S. Tada and R. Kikuchi, *Mater. Adv.*, 2020, 1, 2202.
- 31 Y. Kobayashi, M. Sohmiya, S. Tada and R. Kikuchi, *J. Jpn. Pet. Inst.*, 2020, **63**, 380.
- 32 J. Li, Y. Zhang, C. Tian, H. Zhou, G. Hu and R. Xia, Microporous Mesoporous Mater., 2020, 295, 109955.
- 33 A. Liu, G. Liu, H. Zhu, B. Shin, E. Fortunato, R. Martins and F. Shan, *Appl. Phys. Lett.*, 2016, **108**, 233506.
- 34 A. P. Grosvenor, M. C. Biesinger, R. St, C. Smart and N. S. McIntyre, *Surf. Sci.*, 2006, 600, 1771.
- 35 A. N. Mansour, Surf. Sci. Spectra, 1994, 3, 211.
- 36 V. Maurice, G. Despert, S. Zanna, P. Josso, M.-P. Bacos and P. Marcus, *Acta Mater.*, 2007, **55**, 3315.
- 37 T. Hanawa, J. Periodontal Implant Sci., 2011, 41, 263.
- 38 Q. Liu, H. Qin, J. A. Boscoboinik and G. Zhou, *Langmuir*, 2016, **32**, 11414.
- 39 Y. Xu, M. Demura and T. Hirano, *Appl. Surf. Sci.*, 2008, **254**, 5413.
- 40 S. Tada, S. Ikeda, N. Shimoda, T. Honma, M. Takahashi, A. Nariyuki and S. Satokawa, *Int. J. Hydrogen Energy*, 2017, 42, 30126.