# **RSC** Advances



View Article Online

View Journal | View Issue

## PAPER

Check for updates

Cite this: RSC Adv., 2021, 11, 10941

MoS<sub>2</sub>/polyaniline/functionalized carbon cloth electrode materials for excellent supercapacitor performance

Yanfang Wang,<sup>a</sup> Xinrong Lv,<sup>a</sup> Suyan Zou,<sup>a</sup> Xiaoyun Lin<sup>®</sup> and Yongnian Ni<sup>®</sup>

In this study, molybdenum disulfide (MoS<sub>2</sub>), polyaniline (PANI) and their composite (MoS<sub>2</sub>/PANI) were facilely prepared *via* a liquid-phase method and *in situ* polymerization. An MoS<sub>2</sub>/PANI/functionalized carbon cloth (MoS<sub>2</sub>/PANI/FCC) was facilely constructed by a drop-casting method. MoS<sub>2</sub>/PANI-10/FCC displays remarkable electrochemical performances, and its specific capacitances varied from 452.25 to 355.5 F g<sup>-1</sup> at current densities ranging from 0.2 to 4 A g<sup>-1</sup>, which were higher than those of MoS<sub>2</sub>/CC (from 56.525 to 7.5 F g<sup>-1</sup>) and pure PANI/CC (319.5 to 248.5 F g<sup>-1</sup>), respectively. More importantly, the MoS<sub>2</sub>-10/PANI/FCC electrode has a long cycling life, and a capacity retention of 87% was obtained after 1000 cycles at a large current density of 10 A g<sup>-1</sup>. Moreover, the MoS<sub>2</sub>/PANI-10/FCC-based symmetric supercapacitor also exhibits excellent rate performance and good cycling stability. The specific capacitance based on the total mass of the two electrodes is 72.8 F g<sup>-1</sup> at a current density of 0.2 A g<sup>-1</sup> and the capacitance retention of 85% is obtained after 1000 cycles.

Received 26th October 2020 Accepted 18th February 2021

DOI: 10.1039/d0ra09126j

rsc.li/rsc-advances

### 1. Introduction

Supercapacitors (SCs) are important storage devices due to the high power density and high energy density than fuel cells/ batteries and traditional capacitors,<sup>1,2</sup> and have received considerable attention from scientists in recent years. The capacitive property of SCs is influenced by assembled technology, electrolyte, electrode materials *etc.*, the most important factor of which is electrode materials.<sup>3</sup> Therefore, it is very important to develop new electrode materials with high specific capacitance, good rate capability and high cycling stability.

SCs are classified into two types depending on their charge storage mechanism: electrical double layer capacitors (EDLCs) and pseudocapacitors. In general, pseudocapacitors are produced by the fast reversible faradic transitions of active materials and can yield higher specific capacitance than EDLCs.<sup>4-6</sup>

Common pseudocapacitors materials include metal hydroxides,<sup>6-7</sup> transition metal compounds,<sup>8-11</sup> and conductive polymers.<sup>12,13</sup> Among these materials, polyaniline, a typical conductive polymer film, is widely used in supercapacitor electrode materials with high theoretical capacitance, good conductivity, and low cost.<sup>14,15</sup> However, two major defects are found in PANI pseudocapacitive materials, including low practical capacitance and poor cycle stability.<sup>16,17</sup> In addition, PANI

electrode materials tend to cause a loss and unstable structural stability during the charge–discharge processes, resulting in poor supercapacitor performances, because the redox sites of the polymer backbone are not adequately stable and can be destroyed within a limited number of charge–discharge cycles. Therefore, numerous researchers focus on the architectural design of the multicomponent electrode materials to solve the above-mentioned problems. Many researchers have reported the use of two-dimensional nanosheets as the substrates for growing different nanosized PANI.<sup>18–20</sup>

Molybdenum disulfide ( $MoS_2$ ) nanosheet, a typical layered transition-metal sulfide, has attracted considerable attention as a supercapacitor electrode owing to its attractive properties such as high theoretical specific capacitance and good cycling stability.<sup>21-23</sup> However, poor electrical conductivity for  $MoS_2$ limits its practical electrochemical performances. Studies have reported that the  $MoS_2$  and PANI composite is endowed with a synergistic effect and can overcome the above-mentioned deficiencies of  $MoS_2$  and improve its electrochemical performances.<sup>24,25</sup> Furthermore, an electrode substrate is also an important factor to affect the rate capability and power density of supercapacitors.

In this study, a  $MoS_2$ /polyaniline/functionalized carbon cloth electrode ( $MoS_2$ /PANI/FCC) was constructed for applications in supercapacitors.  $MoS_2$  nanosheet and PANI were synthesized by a liquid-phase method, and the  $MoS_2$ /PANI nanocomposite was prepared *via in situ* polymerization. The  $MoS_2$ /PANI/FCC electrode delivers the enhanced specific capacitance and excellent cycle stability.

<sup>&</sup>quot;College of Chemistry, Nanchang University, Nanchang 330031, China. E-mail: linxiaoyun@ncu.edu.cn; Fax: +86 791 83969500; Tel: +86 791 83969500

<sup>&</sup>lt;sup>b</sup>Jiangxi Province Key Laboratory of Modern Analytical Science, Nanchang University, Nanchang 330031, China

## 2. Experimental

#### 2.1 Materials

Aniline (analytical grade),  $Na_2MoO_4 \cdot H_2O$  (100 g, 99.95%), Lcysteine (analytical grade) and ammonium persulfate (APS) were purchased from Beijing Chemical Reagent Co., China, and used without further purification. A carbon cloth was obtained from Taiwan Carbon Energy Technology Co., Ltd.

#### 2.2 Instruments and equipment

Electrochemical experiments (cyclic voltammetry (CV) and galvanostatic charge–discharge (GCD)) were performed on a CHI660A (Shanghai Chenhua Co., Ltd.) electrochemical workstation in conjunction with a standard three-electrode system. The working electrode was a  $MoS_2$ -10/PANI/FCC, the auxiliary electrode was a conductive electrode, and the reference electrode was an Ag/AgCl electrode.

Electrochemical impedance spectroscopy (EIS) was performed in a 1.0 mol  $L^{-1}$  H<sub>2</sub>SO<sub>4</sub> electrolyte solution, using an alternating current voltage of 10 mV, within the frequency range of 0.01–10<sup>4</sup> Hz on Instruments of AUTOLAB (PGSTAT302N, Metrohm, Switzerland) electrochemical workstation.

Transmission electron microscopy (TEM) images were recorded to characterize the morphology of  $MoS_2$  and  $MoS_2$ – PANI nanomaterials with the use of a FEI Tecnai G2 F20 (Thermo Fisher Scientific – CN).

Scanning electron microscopy (SEM) images were obtained using a SU8010 instrument (Hitachi Co. Ltd., Japan).

The X-ray diffraction experiment was carried out on a Bede D1 System (Bede, UK) using Cu K<sub> $\alpha$ </sub> radiation (l = 1.5406), with a Bragg angle range of 10°–70°.

#### 2.3 Preparation of MoS<sub>2</sub> nanosheets

 $MoS_2$  was prepared in a typical process: 0.25 g  $Na_2MoO_4 \cdot 2H_2O$  was dissolved in 25 mL deionized water and the pH value was adjusted to 6.5 with 0.1 mol L<sup>-1</sup> HCl. Then, 0.5 g L-cysteine and 50 mL deionized water were added to the above mixture solution. After ultra-sonication for 10 min, the mixture was transferred into a 100 mL Teflon-lined stainless steel autoclave and was held at 200 °C for 36 h. After the above solution was cooled to room temperature naturally, the MoS<sub>2</sub> composites were collected *via* centrifugation, washed with ultrapure water and ethanol for several times sufficiently and then dried in a vacuum at 60 °C for 12 h. Finally, the MoS<sub>2</sub> nanosheets were obtained.

#### 2.4 Preparation of MoS<sub>2</sub>/PANI

PANI was synthesized according to the following method: 0.92 mL aniline, 20 mL of 1 mol  $L^{-1}$  HCl and 10 mL ethanol were dispersed into 50 mL deionized water in an ice bath (0–5 °C) with magnetic stirring. After stirring for 10 min, 10 mL 1 mol  $L^{-1}$  (NH<sub>4</sub>)<sub>2</sub>S<sub>2</sub>O<sub>8</sub> was added into the above mixture drop by drop, and then stirred in an ice bath for 12 h. The obtained precipitates of PANI were washed deionized water and ethanol

for several times and dried in a vacuum at 60  $^{\circ}$ C for 12 h. The dark green powder of PANI was finally obtained.

Typically,  $MOS_2/PANI$  composites were prepared by *in situ* polymerization induced by a  $MOS_2$  substrate. In a typical synthesis, 0.1 g of  $MOS_2$  was dispersed in 30 mL of 1 mol L<sup>-1</sup> HCl by ultrasonication, and then, the mixture was placed in an ice bath. Subsequently, the fabrication process is the same as that for the preparation of the above-mentioned PANI. On the other hand, by changing the amount of  $MOS_2$  during the polymerization process,  $MOS_2/PANI$  hybrid materials with different amounts of  $MOS_2$  and controllable morphologies were prepared using the same process, which were denoted as  $MOS_2/PANI-x$ , where *x* is the mass percentage of  $MOS_2$  in the hybrid materials (x = 2, 5, 10, 15 and 38).

#### 2.5 Preparation of MoS<sub>2</sub>/FCC, PANI/FCC or MoS<sub>2</sub>/PANI/FCC

The construction process of the working electrode is as follows: first, a carbon cloth (CC) was cut into appropriate size  $(1 \times 2)$  $cm^2$ ), and a few pieces of CC were fully immersed in 2.0 mol  $L^{-1}$ H<sub>2</sub>SO<sub>4</sub>, and the cyclic voltammetry (CV) test was carried out at the potential range from -0.8 V to 2.0 V at 100 mV s<sup>-1</sup>. The asprepared functionalized CC (FCC) was fully washed with ultrapure water and dried in a vacuum at 80 °C. Second, the active materials (MoS2, PANI or MoS2/PANI) (80 wt%), acetylene black (10 wt%) and polytetrafluoroethylene (PTFE, 10 wt%) were mixed, and *n*-methyl pyrrolidone was used to homogenize the mixture. An appropriate mixture (about 3 g after drying) was evenly applied on the functionalized carbon cloth (FCC)  $(1 \times 2)$ cm<sup>2</sup>), and then dried in a vacuum oven for 12 h. Finally, MoS<sub>2</sub>/ FCC, PANI/FCC or MoS<sub>2</sub>/PANI/FCC was soaked in an electrolyte for 12 h for activation. The schematic of the construction process for the MoS<sub>2</sub>/PANI/FCC electrode is shown in Scheme 1.

#### 2.6 Experimental procedure

The crystal structures of the as-synthesized samples were investigated *via* X-ray diffraction (XRD) (Bruker D8 advance) with Cu-K $\alpha$  radiation ( $\lambda = 1.54178$ ). The morphology characterization of the as-synthesized samples was investigated *via* field-emission scanning electron microscopy (FESEM, SU8010) and transmission electron microscopy (TEM, FEI Tecnai G2 F20).

The electrochemical tests were carried out on a threeelectrode system in a 1.0 M H<sub>2</sub>SO<sub>4</sub> aqueous electrolyte, and  $MoS_2/FCC$ , PANI/FCC or  $MoS_2/PANI/FCC$ , Ag/AgCl electrode and conductivity electrode were used as the working electrode, reference electrode and counter electrode, respectively. The electrochemical measurements of the electrode materials were characterized *via* cyclic voltammetry (CV) and galvanostatic charge–discharge (GCD) in the CHI660A electrochemical workstation (Shanghai Chenhua Co., Ltd). CV tests were performed between -0.2 V and 0.6 V (*vs.* Ag/AgCl) at different scan rates. GCD was carried out in the potential range of -0.2 V and 0.6 V (Ag/AgCl) at different current densities of 0.2, 0.5, 1, 1.5, 2 and 4 A g<sup>-1</sup>. Electrochemical impedance spectroscopy (EIS) measurements were also carried out in the frequency range from 100 kHz to 0.1 Hz at an open circuit potential in the



Scheme 1 The construction process of MoS<sub>2</sub>/PANI-10/FCC.

Autolab (PGSTAT302N, Metrohm, Switzerland). All the electrochemical experiments were carried out at room temperature.

The specific capacitance  $(C_s)$  of the electrode material was calculated according to the following equation:

$$C_{\rm s} = I \times \Delta t / (\Delta V \times m) \tag{1}$$

$$E = C_{\rm s} \times \Delta V^2 / 2 \times 3.6 \tag{2}$$

 $P = (3600E)/\Delta t \tag{3}$ 

where *I*,  $\Delta t$ ,  $\Delta V$ , *m*, *E* and *P* denote discharge current (A), discharge time (s), voltage change during the discharge process (V), weight of active materials (g), energy density (W h kg<sup>-1</sup>) and power density (kW kg<sup>-1</sup>), respectively.

### 3. Results and discussion

#### 3.1 Characterization of MoS<sub>2</sub>, PANI and MoS<sub>2</sub>/PANI-10

Fig. 1 shows the crystal characteristics of  $MOS_2$ , PANI and  $MOS_2$ / PANI-10. All the diffraction peaks (14.3°, 32.6° and 58.3°) in both samples can be assigned to hexagonal  $MOS_2$ , respectively.<sup>23</sup> For the pure PANI sample, its XRD pattern includes three peaks at approximately 14.1°, 20.5° and 25.5°, which are attributable to PANI (011), (020) and (200) planes, respectively, suggesting that PANI existed in the form of emeraldine salt.<sup>26</sup> In addition,



Fig. 1 XRD patterns of MoS<sub>2</sub>, PANI and MoS<sub>2</sub>/PANI.

transmission electron microscopy (TEM) (Fig. 2). Fig. 2A and 2D show the SEM images of MoS2 and MoS2/PANI-10, and it can be seen that the precursor MoS<sub>2</sub> had a lamellar structure with an uneven layer assembled surface (Fig. 2A). Fig. 2D shows that the layer PANI nanosheet was grown on the surface of the MoS<sub>2</sub> nanowire arrays. TEM images of MoS2 and MoS2/PANI-10 are shown in Fig. 2B and E. From Fig. 2B, the as-prepared MoS<sub>2</sub> was layered, but there is a stacking phenomenon in different MoS<sub>2</sub> materials. When MoS<sub>2</sub>/PANI-10 was tested, more serious stacking phenomenon was observed and formed a disordered nano-structure (Fig. 2E), which coincided with the SEM image of MoS<sub>2</sub>/PANI-10. From the lattice fringes of the high-resolution TEM (HRTEM) image MoS<sub>2</sub> (Fig. 1C) and MoS<sub>2</sub>/PANI-10 (Fig. 1F), lattice spacing between adjacent planes for MoS<sub>2</sub> and MoS<sub>2</sub>/PANI-10 was measured 0.62 nm and 0.92 nm, respectively. An interplanar spacing of 0.62 nm corresponded to the (002) plane of MoS<sub>2</sub> nanosheets, and interplanar spacing of 0.92 nm was observed in MoS<sub>2</sub>/PANI-10, indicating that amorphous PANI anchored onto the surface of the MoS<sub>2</sub> nanosheet to form a loose structure, which is desirable for supercapacitor application because both surfaces containing thin PANI wafers are effective in contributing pseudocapacitance to the total energy storage.

these three peaks of MoS2 are also observed in the MoS2/PANI-

10 composite materials and the diffraction peak intensity of the

Fig. 3 shows that the uniform distribution of C, N, Mo and S elements of MoS<sub>2</sub>/PANI-10 can be seen in the elemental mapping images, which indicated that PANI was grown on the surface of MoS<sub>2</sub> nanomaterials successfully.

In order to further analyze the composition of  $MoS_2/PANI-10$ , XPS characterization was used to obtain more information. Fig. 4A shows the full-band scanning image of  $MoS_2/PANI-10$ , and it can be seen that  $MoS_2/PANI-10$  is composed of Mo, S, C, N and O elements. It was explained that the elements of Mo and S originated from  $MoS_2$  nanosheet, C and N elements came from PANI, and O element may have generated by the Mo's



Fig. 2 FESEM, TEM, and HRTEM images of MoS<sub>2</sub> (A–C), MoS<sub>2</sub>/PANI-10 (D–F).

REDOX reaction during the hydrothermal reaction. These results were consistent with the elemental mapping images of the MoS<sub>2</sub>/PANI-10 in Fig. 3. It can be seen from the XPS spectra image of C 1s (Fig. 4B) that three peaks at the binding energies of 283.5, 284.5 and 285.5 eV correspond to the following functional groups of C–C, C–N, and C–O, respectively. Two peaks

of N 1s (Fig. 4C) at the binding energies of 398.8 and 399.65 eV were bound up with the corresponding functional groups for C=N- and -NH-, respectively. Fig. 4D is the XPS spectrogram of Mo 3d, and two peaks at the binding energies of 230 and 231.5 eV are attributed to  $Mo^{4+} 3d_{5/2}$  and  $Mo^{4+} 3d_{3/2}$ , respectively. Also, a peak at 235.4 eV in the XPS spectrogram of Mo 3d



Fig. 3 Elemental mapping images of MoS<sub>2</sub>/PANI-10.



Fig. 4 The XPS spectra image of the MoS<sub>2</sub>-PANI full spectrum (A), C 1s (B), N 1s (C), Mo 3d (D), S 2p (E).

was observed, which was mainly caused by  $Mo^{6+} 3d_{3/2}$ , indicating that there existed a reactant- $Na_2MoO_4 \cdot 2H_2O$ . In addition, from Fig. 4F, the S 2p spectrogram included two peaks of 167.8 eV (S  $2p_{3/2}$ ) and 169 eV (S  $2p_{1/2}$ ). Compared with the reported literatures,<sup>28-30</sup> there was a significant shift in the peak position of S 2p for  $MoS_2$ , which may be caused by the oxidation process of  $MoS_2$ . Furthermore, according to the Mo, S, C and N peak area results, the quantitative percentage of Mo, S, C and N can be calculated to be 7.20%, 4.13%, 71.6% and 18.9%, respectively. As the peak area ratio for  $Mo^{6+}/Mo^{4+}$  was estimated to be 1 : 3 according to Fig. 4D, the quantitative percentage of  $Mo^{4+}$  and S was 5.4% and 4.13%; that is to say, the ratio of  $Mo^{4+}$  and  $S^{2-}$  are close to 1/2.28 or ~1/2. So, and Mo element mainly existed in the form of  $MoS_2$ .

## 3.2 Electrochemical properties for MoS<sub>2</sub>/FCC, PANI/FCC and MoS<sub>2</sub>/PANI-*x*/FCC

To explore their potential application in energy storage devices, the electrochemical properties of  $MoS_2/FCC$ , PANI/FCC and  $MoS_2/PANI$ -*x*/FCC were investigated *via* cyclic voltammetry (CV) and galvanostatic charge–discharge (GCD) tests in a threeelectrode system in 1 M H<sub>2</sub>SO<sub>4</sub> electrolyte. At a scan rate of





Fig. 5 CV profiles at 5 mV s<sup>-1</sup> (A) and galvanostatic charge–discharge curves at 0.5 A g<sup>-1</sup> (B) of MoS<sub>2</sub>/FCC, PANI/FCC and MoS<sub>2</sub>/PANI/FCC with different amounts of MoS<sub>2</sub> in the 1 M H<sub>2</sub>SO<sub>4</sub> electrolyte. (C) Charge–discharge curves of MoS<sub>2</sub>/PANI-10/FCC at a current densities of 0.2, 0.5, 1, 1.5, 2 and 4 A g<sup>-1</sup>. (D) CV cures of MoS<sub>2</sub>/PANI-10/FCC tested in the 1 M H<sub>2</sub>SO<sub>4</sub> electrolyte at different scan rates of 5, 10, 20, 30, 50 and 100 mV s<sup>-1</sup>.

5 mV s<sup>-1</sup>, the CV curves of MoS<sub>2</sub>/FCC, PANI/FCC and MoS<sub>2</sub>/ PANI-x/FCC are shown in Fig. 5A. The CV profile of MoS<sub>2</sub>/FCC revealed the typical CV curve of the electric double-layer capacitor (EDLC) within the potential window of -0.2-0.6 V (vs. Ag/AgCl). The capacitance characteristics for PANI/FCC and MoS<sub>2</sub>/PANI-*x*/FCC were different from that of EDLC. For PANI/ FCC, a pair of distinct redox peaks was observed corresponding to the typical pseudocapacitive characteristic, which was ascribed to the transformation between the leucoemeraldine (LB) and emeraldine salt (ES) states of PANI. According to the ref. 31, the redox and conductive mechanisms of PANI could be deduced (Scheme 2). Compared with PANI/FCC and MoS<sub>2</sub>/FCC, the resultant MoS<sub>2</sub>/PANI-x/FCC possessed both pseudocapacitance and EDLC capacitance with significantly increased current densities and expanded the integral area of the CV curves, which resulted in a distinctly higher electrochemical capacitance than that of bare PANI/FCC and MoS<sub>2</sub>/FCC. The results could be due to the synergistic effects between PANI and MoS<sub>2</sub>, which facilitated charge carriers to transfer back and forth from MoS<sub>2</sub> nanosheet edges to inside and outside of PANI.<sup>16,26</sup> In addition, MoS<sub>2</sub>/PANI-x/FCC (MoS<sub>2</sub>/PANI-2/FCC, MoS<sub>2</sub>/PANI-5/FCC, MoS<sub>2</sub>/PANI-10/FCC, MoS<sub>2</sub>/PANI-15/FCC and MoS<sub>2</sub>/PANI-38/FCC) were tested by CV, and MoS<sub>2</sub>/PANI-10/FCC showed drastically enhanced current response, indicating that only a moderate amount ratio of PANI to  $MoS_2$  can obtain the desirable capacitance.

Furthermore, the GCD curves of  $MoS_2/FCC$ , PANI/FCC and  $MoS_2/PANI$ -x/FCC are shown in Fig. 5B, which were measured at a constant current density of 0.2 A g<sup>-1</sup> with voltage between -0.2 and 0.6 V. The results indicated that the capacitance of



Scheme 2 The possible redox and conductive mechanism of PANI.

#### Paper

 $MoS_2/FCC$  and PANI/FCC were 56.53 and 319.5 F g<sup>-1</sup>, respectively. A maximum capacitance (452.25 F g<sup>-1</sup>) was obtained when the amount of  $MoS_2$  was 10% ( $MoS_2/PANI-10/FCC$ ). When the amount of  $MoS_2$  increased to 15% and reduced to 5%, the capacitances of the  $MoS_2/PANI-15/FCC$  and  $MoS_2/PANI-5/FCC$  were calculated to be 428.6 F g<sup>-1</sup> and 392.3 F g<sup>-1</sup>, respectively. However, when the amount of  $MoS_2$  was 38% and 2%, and the capacitance of  $MoS_2/PANI-38/FCC$  and  $MoS_2/PANI-2/FCC$  reduced to 189.7 F g<sup>-1</sup> and 252.6 F g; this could be because  $MoS_2/PANI-10/FCC$  had a higher electronic conductivity than other components due to the uniform dispersion of PANI on the surface of the  $MoS_2$  sheet, which enhanced the charge transfer and facilitated the redox reactivity of PANI.

Fig. 5C shows the CVs of  $MoS_2/PANI-10/FCC$  at different scan rates. From Fig. 5C, a couple of obvious redox peaks can be observed, and the redox peak currents of  $MoS_2/PANI-10/FCC$ increased significantly and maintained the peak shape of CV with the increase in the scan rate from 5 mV s<sup>-1</sup> to 100 mV s<sup>-1</sup>, indicating extraordinary fast charge–discharge property. Moreover, it was noted that the anodic and cathodic peak potentials of  $MoS_2/PANI-10/FCC$  shifted positively and negatively with the increase in the scan rate from 5 mV s<sup>-1</sup> to 100 mV s<sup>-1</sup>, respectively, which showed that  $MoS_2/PANI-10/FCC$  possessed high-rate charge or discharge properties. The specific capacitance values of  $MoS_2/PANI-10/FCC$  decreased with the increase in the scan rates by calculation. This may be because the migration of ions in the electrolyte was limited at high scan rates.

Furthermore, the GCD curves of  $MoS_2/PANI-10/FCC$  (Fig. 5D) displayed a pair of charge and discharge plateaus due to the synergistic effects between PANI and  $MoS_2$  to the total capacitance of composites.  $MoS_2/PANI-10/FCC$  showed the specific capacitances of 452.3, 409.4, 393.8, 382, 374, 355.5 F g<sup>-1</sup> at current densities of 0.2, 0.5, 1.0, 1.5, 2.0, 4.0 A g<sup>-1</sup>, respectively, indicating an excellent rate capability.

The corresponding specific capacitances for MoS<sub>2</sub>/CC, PANI/ CC and MoS<sub>2</sub>/PANI-10/FCC at current densities of 0.2, 0.5, 1.0, 1.5, 2.0, 4.0 A  $g^{-1}$  are plotted in Fig. 6A. It can be seen that the specific capacitances for MoS<sub>2</sub>/PANI-10/FCC varied from 452.25 to 355.5 F  $g^{-1}$  at current densities from 0.2 to 4 A  $g^{-1}$ , which are higher than those of  $MoS_2/CC$  (from 56.53 to 7.5 F g<sup>-1</sup>) and pure PANI/CC (319.5 to 248.5 F  $g^{-1}$ ), respectively. Moreover, when the current densities were varied from 0.2 to 4.0 A  $g^{-1}$ , the capacitance retention of MoS<sub>2</sub>/PANI-10/FCC was 79%, which was also better than that of MoS<sub>2</sub> (13%) and PANI (77%). These results indicate that MoS<sub>2</sub>/PANI-10/FCC possessed an excellent rate capability compared with pure MoS2/FCC and PANI/FCC. The remarkable rate performance could be mainly because the layer MoS<sub>2</sub> not only acted as an active electrode material in the electrochemical reaction but also as a framework to provide more paths for the insertion and extraction of ions within PANI.



Fig. 6 Capacitance retention (A), Nyquist plots measured at the frequency range from 100 kHz to 0.01 Hz (inset, the close-up view of the high-frequency region) (B), and cycling performances at 50 mV s<sup>-1</sup> (C), of MoS<sub>2</sub>/FCC, PANI/FCC and MoS<sub>2</sub>/PANI-10/FCC in the 1 M H<sub>2</sub>SO<sub>4</sub> electrolyte.

Table 1 Results of other reported electrode materials based on MoS<sub>2</sub> in comparison with the electrode material in this study

Cs	Cyclic stability	Ref.
$353.2 \text{ F g}^{-1} (0.6 \text{ A g}^{-1})$	63% (700 cycles)	32
333.5 F $g^{-1}$ (1 A $g^{-1}$ )	81.8% (7000 cycles)	33
400 F $g^{-1}$ (0.8 A $g^{-1}$ )	84% (500 cycles)	34
390 F $g^{-1}$ (0.8 A $g^{-1}$ )	86% (1000 cycles)	35
393.8 $F g^{-1}$ (1.0 $A g^{-1}$ )	87% (1000 cycles)	This work
	$C_{\rm s}$ 353.2 F g <sup>-1</sup> (0.6 A g <sup>-1</sup> ) 333.5 F g <sup>-1</sup> (1 A g <sup>-1</sup> ) 400 F g <sup>-1</sup> (0.8 A g <sup>-1</sup> ) 390 F g <sup>-1</sup> (0.8 A g <sup>-1</sup> ) 393.8 F g <sup>-1</sup> (1.0 A g <sup>-1</sup> )	$C_{\rm s}$ Cyclic stability           353.2 F g <sup>-1</sup> (0.6 A g <sup>-1</sup> )         63% (700 cycles)           333.5 F g <sup>-1</sup> (1 A g <sup>-1</sup> )         81.8% (7000 cycles)           400 F g <sup>-1</sup> (0.8 A g <sup>-1</sup> )         84% (500 cycles)           390 F g <sup>-1</sup> (0.8 A g <sup>-1</sup> )         86% (1000 cycles)           393.8 F g <sup>-1</sup> (1.0 A g <sup>-1</sup> )         87% (1000 cycles)

The Nyquist plots for  $MoS_2/FCC$ , PANI/FCC and  $MoS_2/PANI-10/FCC$  are shown in Fig. 6B, and the plots are composed of a straight line at the lower frequency region and a semicircle at the higher frequency region. In general, the electron-transfer resistance ( $R_{et}$ ) corresponds to the semicircular portion at higher frequencies, and its diameter is equal to the  $R_{et}$ . The  $R_{ets}$ for  $MoS_2/FCC$ , PANI/FCC and  $MoS_2/PANI-10/FCC$  were calculated to be 2.02  $\Omega$ , 1.42  $\Omega$  and 1.19  $\Omega$ , respectively, indicating that  $MoS_2/PANI-10/FCC$  had good conductivity, which endowed  $MoS_2/PANI-10/CC$  with remarkable rate performance and high capacitance behavior.

Fig. 6C shows the cycle performance of  $MoS_2/FCC$ , PANI/FCC and  $MoS_2/PANI-10/FCC$  over 1000 charge–discharge cycles under 5.0 A g<sup>-1</sup>. It was found that  $MoS_2/FCC$  maintained a bad charge–discharge performance, and the capacitance retention is 29% after 1000 cycles, and the capacity retention of 82% was obtained after 1000 cycles at the PANI/FCC. Furthermore,  $MoS_2/PANI-10/FCC$  delivers a high capacitance retention of 87% after 1000 cycles. The improved stability was mainly ascribed to a gradual access of electrolyte ions to the active sites of the electrode surface due to the layer structure, in which the layer structure provides a space between PANI and effectively accommodate the mechanical deformation caused by the shrinking of the nano-structures during the long-term charge-discharge processes.  $MoS_2/PANI-10/FCC$  showed excellent electrochemical properties, and the results compared with others is shown in Table 1.<sup>32–35</sup>

To further investigate the capacitive performance of  $MoS_2/PANI-10/FCC$ , it is employed to assemble a symmetric SC with 1 M  $H_2SO_4$  as the electrolyte over a voltage window of 0–0.7 V.



Fig. 7 (A) Curves of the symmetric SC at different scan rates of 5, 10, 20, 30, 50 and 100 mV s<sup>-1</sup>. (B) Charge–discharge curves of the symmetric SC at current densities of 0.2, 0.5, 1, 1.5, 2 and 10 A g<sup>-1</sup>. (C) Cycling performance at 1.5 A g<sup>-1</sup>.

Fig. 7 shows a series of supercapacitive measuring techniques. As expected, the redox peaks of CV profiles are maintained over a wide range of scan rates (Fig. 7A). Moreover, the charge-discharge curves keep the same shape, and their discharge counterparts show no obvious IR drops even at high current densities (Fig. 7B), demonstrating the excellent rate performance of the device. The specific capacitance based on the total mass of the two electrodes is 73 F g<sup>-1</sup> at a current density of  $0.2 \text{ A g}^{-1}$ , corresponding to  $292 \text{ F g}^{-1}$  for a single electrode when multiplying by a coefficient of 4, which complies with the test method as described by Ruoff *et al.* <sup>36</sup> Moreover, the cycle performance of the MoS<sub>2</sub>/PANI-10/FCC-based symmetric SC is tested by a charge-discharge technique at a current density of  $1.5 \text{ A g}^{-1}$ , and the capacitance retention is 85% after 1000 cycles (Fig. 7C).

## 4. Conclusions

In this study, MoS<sub>2</sub> nanosheet and PANI were synthesized by a liquid-phase method, and an MoS<sub>2</sub>/PANI nanocomposite was prepared via in situ polymerization. The MoS<sub>2</sub>/PANI nanocomposite possessed excellent physicochemical properties, such as large specific surface area, excellent conductivity and pseudocapacitive characteristic. Based on these, CC with a rich carbon element was functionalized and was used as the collecting fluid. Then, the MoS<sub>2</sub>/PANI/FCC electrode was constructed to investigate its electrochemical properties. MoS<sub>2</sub>/ PANI-10/FCC showed specific capacitances of 452.3, 409.4, 393.8, 382, 374, 355.5 F  $g^{-1}$  at current densities of 0.2, 0.5, 1.0, 1.5, 2.0, 4.0 A  $g^{-1}$ , respectively. Moreover, the stability of the composite electrode reached 87% after 1000 cycles. This study indicates that MoS<sub>2</sub>/PANI-10/FCC was an excellent electrochemical energy storage material, and can be applied in the field of energy storage devices.

## Conflicts of interest

Xiaoyun Lin declares that he has no conflict of interest. Yangfang Wang declares that she has no conflict of interest. Xinrong Lv declares that she has no conflict of interest. Yongnian Ni declares that he has no conflict of interest.

## Acknowledgements

The authors gratefully acknowledge the financial support of this study by the National Natural Science Foundation of China (NSFC-31860468) and the Science and Technology Innovation Platform Project of Jiangxi Province (No. 20192BCD40001).

## References

- 1 C. Zhong, Y. D. Deng, W. B. Hu, J. L. Qiao, L. Zhang and J. J. Zhang, *Chem. Soc. Rev.*, 2015, 44, 7484–7539.
- 2 C. Z. Wu, X. L. Lu, L. L. Peng, K. Xu, X. Peng, J. L. Huang,
   G. H. Yu and Y. Xie, *Nat. Commun.*, 2013, 4, 2431–2437.
- 3 K. Y. Xie and B. Q. Wei, Adv. Mater., 2014, 26, 3592-3617.

- 4 A. Ehsani, A. A. Heidari and H. M. Shiri, *Chem. Rec.*, 2019, **19**, 908–926.
- 5 L. Liu, H. P. Zhao and Y. Lei, Small Methods, 2019, 3, 1800341.
- 6 J. M. Goncalves, M. L. da Silva, H. E. Toma, L. Angnes,
  P. R. Martins and K. Araki, *J. Mater. Chem. A*, 2020, 8, 10534–10570.
- 7 Y. L. Li, J. J. Zhou, M. K. Wu, C. Chen, K. Tao, F. Y. Yi and L. Han, *Inorg. Chem.*, 2018, **57**, 6202–6205.
- 8 W. J. Ma, S. H. Chen, S. Y. Yang, W. P. Chen, W. Weng, Y. H. Cheng and M. F. Zhu, *Carbon*, 2017, **113**, 151–158.
- 9 L. L. Chai, L. J. Zhang, X. Wang, Z. J. Ma, T. T. Li, H. Li, Y. Hu, J. J. Qian and S. M. Huang, *Electrochim. Acta*, 2019, **321**, 134680.
- 10 H. W. Li, T. T. Li, J. J. Qian, Y. Mei and Y. Q. Zheng, *Int. J. Hydrogen Energy*, 2020, **45**, 14640–14647.
- 11 B. Ding and X. L. Wu, J. Alloys Compd., 2020, 842, 155838.
- 12 R. Holze, Polymers, 2020, 12, 1835.
- 13 H. J. Tang, J. Y. Wang, H. J. Yin, H. J. Zhao, D. Wang and Z. Y. Tang, *Adv. Mater.*, 2015, **27**, 1117–1123.
- S. Liu, J. Zhang, R. Dong, P. Gordiichuk, T. Zhang, X. Zhang,
   Y. Mai, F. Liu, A. Herrmann and X. Feng, *Angew. Chem., Int. Ed.*, 2016, 55, 12516–12521.
- 15 S. H. Liu, P. Gordiichuk, Z. S. Wu, Z. Y. Liu, W. Wei, M. Wagner, N. Mohamed-Noriega, D. Q. Wu, Y. Y. Mai, A. Herrmann, K. Müllen and X. L. Feng, *Nat. Commun.*, 2015, 6, 8817–8826.
- 16 L. J. Ren, G. N. Zhang, J. Lei, D. W. Hu, S. M. Dou, H. X. Gu, H. Q. Li and X. B. Zhang, *J. Alloys Compd.*, 2019, **798**, 227– 234.
- 17 Q. Wang, J. Yan, Z. J. Fan, T. Wei, M. L. Zhang and X. Y. Jing, J. Power Sources, 2014, 247, 197–203.
- 18 G. Anjli, S. Silki, D. Jasvir, L. Sushma, S. M. Anup, T. Rahul, P. Rajesh, S. Kuldeep and O. Anil, ACS Appl. Energy Mater., 2020, 3, 6434–6446.
- 19 C. C. Wang, Y. Yang, R. J. Li, D. T. Wu, Y. Qin and Y. Kong, *Chem. Commun.*, 2020, **56**, 4003-4006.
- 20 W. J. Luo, L. Zhang, W. Q. Wang, L. H. Ouyang and X. Xue, *Energy Technol.*, 2019, 7, 1900522.
- 21 L. J. Cao, S. B. Yang and W. Gao, Small, 2013, 9, 2905–2910.
- A. Castellanos-Gomez, R. Van Leeuwen, M. Buscema,
  H. S. J. van der Zant, C. A. Steele and W. J. Venstra, *Adv. Mater.*, 2013, 25, 6719–6723.
- 23 Y. Mei, T. T. Li, J. J. Qian, H. W. Li, M. Wu and Y. Q. Zheng, *Chem. Commun.*, 2020, **56**, 13393–13396.
- 24 R. Zeng, Z. C. Li, L. B. Li, Y. Z. Li, J. Huang, Y. B. Xiao, K. Yuan and Y. W. Chen, *ACS Sustainable Chem. Eng.*, 2019, 7, 11540– 11549.
- 25 J. Chao, L. C. Yang, H. Y. Zhang, J. W. Liu, R. Z. Hu and M. Zhu, *J. Power Sources*, 2020, 450, 227680.
- 26 L. J. Ren, G. N. Zhang, Z. Yan, L. P. Kang, H. Xu, F. Shi, Z. B. Lei and Z. H. Liu, ACS Appl. Mater. Interfaces, 2015, 7, 28294–28302.
- 27 K. Wang, X. Zhang, C. Li, H. Zhang, X. Sun, N. Xu and Y. Ma, J. Mater. Chem. A, 2014, 2, 19726–19732.
- 28 L. J. Ren, G. N. Zhang, D. W. Hu, S. M. Dou, H. X. Gu, H. Q. Li and X. B. Zhang, *J. Alloys Compd.*, 2019, **798**, 227–234.

- 29 H. Ma, Z. G. Shen and S. Ben, *J. Colloid Interface Sci.*, 2018, 517, 204–212.
- 30 W. L. Zhang, D. G. Jiang, X. X. Wang, B. N. Hao, Y. D. Liu and J. Q. Liu, *J. Phys. Chem. C*, 2017, **121**, 4989–4998.
- 31 G. E. Wnek, Synth. Met., 1986, 15, 213-218.
- 32 J. Y. Li, R. Wu and X. C. Yang, Phys. E, 2020, 118, 113951.
- 33 F. P. Wang, J. Ma and K. L. Zhou, *Mater. Chem. Phys.*, 2020, 244, 122215.
- 34 M. Kim, Y. K. Kim, J. Kim, S. Cho, G. Lee and J. Jang, *RSC Adv.*, 2016, **6**, 27460–27465.
- 35 J. Wang, Z. C. Wu and K. H. Hu, *J. Alloys Compd.*, 2015, **619**, 38–43.
- 36 M. D. Stoller and R. S. Ruoff, *Energy Environ. Sci.*, 2010, 3, 1294–1301.