RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2021, 11, 13624

Received 30th January 2021 Accepted 28th March 2021

DOI: 10.1039/d1ra00812a

rsc.li/rsc-advances

1. Introduction

The use of photoelectrochemistry (PEC) has received increased attention in biosensor development because of its low background noise, low cost, small size, and high sensitivity.^{1,2} However, most photoanodes are restricted by material factor limitations, such as narrow light absorption range, low charge separation, and low transfer efficiency. Therefore, the photogenerated electron mobility and biocompatibility of materials are important in constructing PEC electrodes.³ Photogenerated electrons and holes produced in wide band gap semiconductors, such as TiO₂ and ZnO, were unstable and

Enhancing the performance of photoelectrochemical glucose sensor *via* the electron cloud bridge of Au in SrTiO₃/PDA electrodes[†]

Yadong Wang,^a Jinxin Ma,^a Nan Zhang,^a Delun Chen,^a Jinchun Tu,^b Yang Cao,^{ac} Qiang Wu,^b ^{*b} Xiaolin Zhang^{*c} and Wanjun Hao^{*a}

Developing photoelectrochemical biosensors *via* efficient photogenerated-charge separation remains a challenging task in biomolecular detection. In this study, we utilised a simple approach for constructing an efficient photoactive organic–inorganic heterojunction interface composed of $SrTiO_3$ with high photocatalytic activity and polydopamine (PDA) with high biocompatibility and electrical conductivity. Gold nanoparticles with dense electron cloud properties were introduced as a bridge between $SrTiO_3$ and PDA ($SrTiO_3/Au/PDA$). The Au bridge allowed the PDA to uniformly and tightly attach on the surface of $SrTiO_3$ electrodes and also provided a separate transmission channel for electrons from PDA to $SrTiO_3$. The rapidly transmitted electrons were captured by a signal-acquisition system, thereby improving the photocurrent signal output. The 3D hollowed out $SrTiO_3/Au/PDA$ biosensor manufactured herein was used for glucose detection. The biosensor achieved ultrahigh sensitivities reaching 23.7 μ A mM⁻¹ cm⁻², an extended linear range (1–20 mM), and a low detection limit (0.012 mM). The excellent results of glucose analysis in serum samples further confirmed the feasibility of the biosensor in clinical applications. In summary, the proposed strategy allowed for the use of an electronic cloud bridge in the construction of glucose biosensors with satisfactory performances, which is promising for the future fabrication of high-performance biosensors.

recombine rapidly, which results in low PEC performance.⁴ Therefore, a rapid photoelectron transfer path must be designed and the Fermi energy level of photoelectrodes should be optimized to effectively improve the photoelectrochemical performance of sensors.⁵

SrTiO₃ with a perovskite structure has a higher conduction band position than TiO_2 , indicating that $SrTiO_3$ has a smaller energy band shift and promotes the transfer of photogenerated electrons better. Thus, $SrTiO_3$ (5-8 cm² V⁻¹ s⁻¹) has a higher electron mobility than TiO₂ (0.1–4.0 cm² V⁻¹ s⁻¹).⁶ Therefore, SrTiO₃ is more suitable to photocatalysis than TiO₂.⁷ However, SrTiO₃, as a single semiconductor, easily recombines with photogenetic carriers. In addition, the biocompatibility of biosensors is unsatisfactory.8-10 Thus, improving the biocompatibility of biosensors is a direction worthy of research.11 Polydopamine (PDA) is a synthetic biomimetic material that has excellent biocompatibility and a stable semiconducting polymer.12 In PEC sensors, PDA plays an important role in immobilizing enzymes and transferring photoelectrons.13 Therefore, the low biocompatibility and inefficient charge separation of SrTiO₃ can be effectively resolved by combining it with PDA.¹⁴ However, the complex inorganic-organic interface is not conducive to the transmission of photogenerated electrons. For

[&]quot;Key Laboratory of Advanced Materials of Tropical Island Resources, State Key Laboratory of Marine Resource Utilization in South China Sea, Hainan University, Haikou 570228, P. R. China. E-mail: hwj8899@163.com

^bSchool of Tropical Medicine and Laboratory Medicine, Key Laboratory of Emergency and Trauma of Ministry of Education, Research Unit of Island Emergency Medicine, Chinese Academy of Medical Sciences (No. 2019RU013), Hainan Medical University, Haikou, 571199, P. R. China. E-mail: wuqiang001001@aliyun.com

^cKey Laboratory of Child Cognition & Behavior Development of Hainan Province, Qiongtai Normal University, Haikou 571127, P. R. China. E-mail: xlzhang0812@ gmail.com

[†] Electronic supplementary information (ESI) available. See DOI: 10.1039/d1ra00812a

Paper

example, a high interface barrier will cause the photogenerated electrons to recombine.¹⁵ Thus, the electronic architectural problem between SrTiO₃ and PDA must be resolved.

A low-impedance interface constructed between SrTiO₃ and PDA can remarkably improve the transmission efficiency of novel inorganic-organic interfaces. Similarly, Colin Tyznik et al.¹⁶ improved the charge separation efficiency by constructing a heterojunction between metal-halide perovskite and organic semiconductor. Constructing a conductive channel between platinum nanoparticles and graphitic carbon can improve the charge-separation ability of the material.¹⁷ This report inspired us to build an electronic cloud bridge to adjust the electronic structure of inorganic-organic interfaces. Noble metal nanoparticles, such as Au and Ag, with high-density electron cloud characteristics can realize effective routes for interface electron transfer.18 A promising strategy is to directly inject electrons through the strong coupling between nanogold and the unsaturated bond on semiconductor surface.19 Another approach is the traditional two-step electron transfer in which free electrons are generated by light excitation and then injected into the semiconductor.²⁰ Therefore, noble metal nanoparticles are more suitable candidates for creating a single electron transmission channel between interfaces by establishing electronic cloud bridges. This approach is expected to address the problem of electron transport and separation between inorganic and organic semiconductors.

In this work, we designed a 3D hollowed out SrTiO₃/Au/PDA photoelectrode *via* hydrothermal *in situ* growth, microwave-assisted synthesis, and photopolymerization methods. This photoelectrode efficiently separated photogenerated charges. The assembly strategy provided an independent electron transport channel for a complex inorganic–organic interface *via* Au nanoparticles and effectively achieved charge separation. This biosensor was applied in glucose detection.

2. Experimental section

2.1. Materials

A Ti wire mesh (60 mesh, 0.14 mm wire diameter, and 0.28 mm mesh width) was acquired from Kangwei Metal Wire Mesh Products Co., Ltd (Hebei China). The reagents including strontium hydroxide octahydrate (Sr(OH)₂·8H₂O, 99.5%), chloroauric acid (HAuCl₄), ethylene glycol (EG), ammonia fluoride (NH₄F), dopamine hydrochloride (DA) were purchased from Shanghai Macklin Biochemical Co., Ltd, and 1, 2-propanediol were purchased from Beijing Chemical Reagent Factory, and were analytical grade and were used as received without further purification. Tetrabutylammonium hydroxide (TBAH, 25 wt%) were purchased from Aladdin Industrial Co., Ltd. Glucose oxidase (GOx) (EC 1.1.3.4, 5 kU mg⁻¹ from Aspergillus niger) was purchased from Sangon Biotech. Phosphate buffer saline (PBS) was prepared by mixing NaH₂PO₄ and Na₂HPO₄ to adjust the pH. All aqueous solutions were prepared using deionized water (DI) with a resistivity of 18.2 M Ω cm.

2.2. Synthesis of 3D hollowed out TiO₂

The titanium dioxide precursor adopted herein was prepared following a previously described method.²¹ At first, a small piece of titanium mesh (20 mm × 10 mm) was treated in a washing solution (volume ratio HF : HNO₃ : H₂O = 1 : 4 : 5) for 10 s. The titanium mesh was separated *via* ultrasonic treatment in isopropanol, acetone, and deionized water for 20 min. At room temperature, the titanium mesh was used as the working electrode, whereas the titanium foil was utilized as the counter electrode for anodizing. The mesh and foil were treated at the constant voltage of 20 V for 90 min. The system reaction solution consisted of 0.3 g of NH₄F, 2 mL of water, and 88 mL of ethylene glycol. The sample was annealed in muffle furnace with a heating rate of 2 °C per minute, and stayed 400 °C for 3 h.

2.3. Synthesis of 3D hollowed out SrTiO₃

The as-synthesized 3D hollowed out TiO_2 was used as the template for synthesizing 3D hollowed out $SrTiO_3$ *via* the hydrothermal *in situ* growth method. During the typical synthesis, the 3D hollowed out TiO_2 was immersed in a Teflon-sealed stainless steel autoclave loaded with solutions of $Sr(OH)_2 \cdot 8H_2O$ (1 mmol) in 17 mL of deionized water, 2 mL of 1,2-propanediol, and 2 mL of tetrabutylammonium hydroxide solution (TBAH, 25 wt%) and then heated at 180 °C for 12 h. The obtained samples were washed three times with 0.1 M HCl solution and deionized water and then dried at 50 °C for 30 min.

2.4. Synthesis of 3D hollowed out SrTiO₃/PDA

The PDA on the SrTiO₃ electrode surface was UV photopolymerized by immersing the electrode in a stirred PBS (pH = 6.0) containing 10 mM DA for 4 h. These steps were repeated on the other electrode side. Finally, the electrode was rinsed with deionized water and then dried at 50 °C for 30 min.

2.5. Synthesis of 3D hollowed out SrTiO₃/Au/PDA

SrTiO₃/Au electrodes were prepared *via* microwave-assisted polyol heating. First, a mixed solution was prepared in an Erlenmeyer flask containing 30 mL of ethylene glycol, 3 mL of deionized water, and 2 mL of HAuCl₄ (0.5 mg mL⁻¹). The mixture was stirred well for 10 min. The strontium titanate substrate was then microwave-digested in this mixed solution for 1 min and finally rinsed with ethanol and H₂O. SrTiO₃/Au/ PDA electrodes were prepared by loading the PDA with the SrTiO₃/Au electrodes following the method outlined above.

2.6. Immobilization of glucose oxidase

The 3D hollowed out SrTiO₃/Au/PDA electrodes were placed in a 4 °C environment for 30 min in advance. Subsequently, 5 μ L of GOx solution (PBS pH = 7.4) was evenly dispersed on the electrode surface, and then the electrodes were dried at 4 °C for 24 h. These steps were repeated for the other electrode side.

2.7. PEC measurements

The electrochemical investigations and biosignal conversions were performed using an electrochemical workstation (CHI Instruments, Chenhua CHI 660E, Shanghai, China) with a 500 W xenon lamp (Beijing Zhongjiao Jinyuan Technology Co., Ltd, China). The test system was used with a three-electrode system (a Pt sheet was used as the counter electrode and saturated Ag/AgCl was used as the reference electrode, bias of 0.4 V, PBS pH = 7.4). During the measurement, the electrode was subjected to an optical density of 100 mW cm⁻².

2.8. Characterization

Powder X-ray diffraction (XRD) patterns were recorded on a Panaltical X'Pert-pro MPD X-ray power diffractometer using Cu K α radiation ($\lambda = 1.54056$ Å). Field-emission scanning electron microscopy (FEI Nano SEM 430) was used to acquire SEM images. Transmission electron microscope (TEM) was performed on JEOL JEM-2100F electron microscope operated at 200 kV. X-ray photoelectron spectroscopy (XPS) spectra were recorded using an ESCALAB 250 Xi XPS system of Thermo Scientific, where the base pressure in analysis chamber was 1.5 $\times 10^{-9}$ mbar and the X-ray spot was 500 µm. UV-Vis diffuse reflection absorption spectra of the samples were obtained by a Varian Cary 5000 UV-Vis spectrometer equipped with an integrating sphere accessory and BaSO₄ as a reference material.

3. Results and discussion

3.1. Design guidelines and microstructure of the electrodes

The typical procedure for synthesizing the PEC sensor is presented in Scheme 1. The 3D hollowed out TiO₂ nanowire clusters were first obtained via Ti mesh anodization because the 3D hollow Ti mesh structure has a low steric hindrance for biological reactions.^{21,22} Scanning electron microscopy (SEM) revealed a highly ordered array of nanowire clusters in the synthesized TiO_2 (Fig. 1(a)). Moreover, a single unit presented a bird's nest-like nanowire cluster structure. This particular structure provided convenient conditions for complete SrTiO₃ conversion (Fig. 1(a)). The synthesized TiO₂ nanowire cluster array was hydrothermally converted to a SrTiO₃ nanostructure. As shown in Fig. 1(c), the synthesized SrTiO₃ had highly ordered nanoarrays similar to the morphology of the TiO₂ precursor. At high magnifications, SrTiO₃ cubes were observed to have piled up into hills. In alkaline environments, Sr²⁺ can chemically react with TiO₂ to generate SrTiO₃ via dissolution-precipitation. In this process, the nanowire TiO₂ was first dissolved around the titanium mesh to form a liquid phase $(Ti(OH)_n^{(n-4)-})$ and then participated in the nucleation and ion-mediated growth of SrTiO₃. At this point, in situ SrTiO₃ growth had been completed. The growth mechanism can be expressed by the following reactions (eqn (1) and (2)):²³

 $\text{TiO}_2(s) + (n-4)\text{OH}^-(aq) + 2\text{H}_2\text{O}(l) \rightarrow \text{Ti}(\text{OH})_n^{(n-4)-}(aq) \ (n = 4-6),$ (1)

 $Ti(OH)_n^{(n-4)-}(aq) + Sr^{2+}(aq) + (6-n)OH^{-}(aq) \rightarrow SrTiO_3(s) + 3H_2O(l).$ (2)

Subsequently, PDA with high biocompatibility was loaded onto the surface of the synthesized SrTiO₃ via photoliterature, photopolymerization. According to the polymerization is the effective method for preparation of PDA. Firstly, the photopolymerization method can functionalize many flat, curved, and even irregular substrates.²⁴ Secondly, no catalyst is needed in the polymerization process.²⁵ Thirdly, robust and well-defined polymer brushes can be directly transplanted onto various surfaces.^{26,27} As shown in Fig. 1(d), PDA was randomly distributed on the surface of SrTiO₃ nanoarrays, and its adhesion on the surface was evidently poor. PDA was anchored on the surface of SrTiO₃ nanoarrays after being loaded with gold via microwave-assisted polyol heating (Fig. 1(b)). The distribution of PDA after adding gold was more uniform than that in samples without gold. This uniform distribution makes better contact between the PDA and the substrate, which is conducive to enhancing the transmission of photogenerated electrons.28 Hence, the problem of uneven PDA distribution was resolved by adding gold. As shown in the enlarged schematic of nanoarray monomers in Scheme 1, PDA was tightly arranged on the surface when gold was added. By contrast, the arrangement was loose when gold was not added. This is due to the extremely high surface energy of gold promoted the close integration of PDA and SrTiO3.29,30 In addition, the high-density electron cloud on the gold surface provided a high-speed bridge for photogenerated electrons to quickly transfer to the electrode.

Transmission electron microscopy (TEM) revealed that the SrTiO₃/Au/PDA composite had uniformly sized approximately 20 nm in size (Fig. 1(f)). The composition of the composite was characterized via HRTEM (Fig. 1(e)), EDX (Fig. S1 in ESI⁺), and mapping (Fig. 1(g)). As shown in Fig. 1(g), the SrTiO₃/Au/PDA had a uniform distribution of Ti, Sr, O, N, and Au, thereby confirming the formation of SrTiO₃, Au, and PDA. Moreover, Ti (17.23%), Sr (12.71%), O (57.79%), N (11.52%), and Au (0.72%) elements were found in the SrTiO₃/Au/PDA composite (Fig. S1 in ESI[†]), indicating that the SrTiO₃ substrate formed and Au and PDA were uniformly loaded onto its surface. The SrTiO₃/Au/ PDA composite material had some clear lattice fringes (Fig. 1(e)), including lattice fringes of 0.273, 0.39, and 0.233 nm, corresponding to the $SrTiO_3(110)$, $SrTiO_3(100)$, and Au(111)planes, respectively. Amorphous regions were clearly observed around these lattice fringes, corresponding to PDA. According to HRTEM images (Fig. S2 in ESI[†]), the SrTiO₃/Au/PDA composite had a richer amorphous region than the SrTiO₃/ PDA composite. This result also demonstrated that Au made the PDA to uniformly distribute in SrTiO₃ nanoarrays.

3.2. Characterization of the electrodes

The composition of the material was further analyzed *via* X-ray diffraction (XRD). First, the diffraction peaks of titanium dioxide were characterized (Fig. S3 in ESI[†]). All diffraction peaks

Paper



Scheme 1 Process of preparing the 3D hollowed out SrTiO₃/Au/PDA PEC sensor and schematic of its microscopic appearance

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence Dpen Access Article. Published on 13 April 2021. Downloaded on 7/19/2025 5:24:07 AM

detected were matched to typical TiO₂ in the anatase phase (JCPDS: 21-1272)³¹ and pure Ti phase (JCPDS: 44-1294),³² indicating that the synthesized precursor was pure anatase TiO₂. Subsequently, the prepared strontium titanate material and its composite with gold and PDA were tested (Fig. 2(a)). The diffraction peaks of the prepared strontium titanate perfectly matched the pure phases of SrTiO₃ phase (JCPDS: 035-0743)⁶ and Ti phase. No other diffraction peaks were found, especially the diffraction peak of TiO2. The XRD of the composite material loaded with amorphous PDA was not different from that of SrTiO₃, suggesting that the crystal structure of SrTiO₃ was not affected by PDA. Finally, the diffraction peaks of Au (JCPDS: 04-0784)¹⁸ could not be clearly analyzed via XRD because their peaks were weak and close to those of Ti. The elemental states of all prepared materials were tracked via X-ray photoelectron spectroscopy (XPS). As shown in Fig. 2(b), SrTiO₃ only contained Sr, Ti, and O elements, SrTiO₃/PDA only contained Sr, Ti, O, and N elements, and SrTiO₃/Au/PDA only contained Sr, Ti, O, N, and Au elements. This result also proved that the SrTiO₃/Au/ PDA composite was successfully and accurately prepared. The binding energy for Sr 3d peaks (Fig. 2(c)) distributed at 132.9 and 134.5 eV were matched to Sr 3d_{5/2} and Sr 3d_{3/2}, respectively, corresponding to Sr²⁺.4 The peaks located at 485.15 and 463.95 eV attributed to Ti $2p_{3/2}$ and $2p_{1/2}$, respectively, matched the binding energy of Ti⁴⁺ (Fig. 2(d)).³³ In addition, the prepared SrTiO₃/PDA and SrTiO₃/Au/PDA material had slight shifts in the peaks of Sr 3d and Ti 2p. These shifts were attributed to the influence of Au and PDA on the electronic state of SrTiO₃. The N 1s spectra (Fig. 2(e)) could be separated into four peaks at 398.7 (==N-), 399.9 (-NH-), 400.7 $(-NH_2)$, and 401.8 eV $(-NH_3^+)$.³⁴ The high-resolution spectra of C 1s is shown in Fig. S4 (ESI[†]). The peaks centered at 284.8 \pm 0.1 eV, 286.1 \pm 0.3 eV and 288.9 \pm 0.1 eV could be assigned to the benzene, C-O or C-N and O-C= O, respectively.35,36 From their percentages in the samples (Table S1 in ESI[†]), it can be seen that, in comparison with

SrTiO₃/Au (28.57%), the relative contents of C–O or C–N in SrTiO₃/Au/PDA (62.60%) obviously increased. This result also confirmed that the PDA was successfully fixed to the electrode. The detection of these amine functional groups indicated that the PDA layer was successfully loaded onto the surface of the 3D hollowed out SrTiO₃. The peaks of Au 4f were concentrated at the binding energies of 83.9 and 87.6 eV, corresponding to Au 4f_{7/2} and 4f_{5/2}, respectively (Fig. 2(f)). In addition, the peak of Au 4f_{7/2} slightly shifted from the standard value of Au element. This shift was attributed to the interaction of Au with SrTiO₃ and PDA. These results confirmed that the 3D hollowed out SrTiO₃/Au/PDA composite was successfully synthesized.

3.3. Electrochemical measurement of the electrodes

The successful implementation of the gold electronic cloud bridge design was confirmed in a series of analyses (Fig. 3). UVvis diffuse reflectance spectra are important and powerful indicators of the optical characteristics of materials. The lightabsorption capacity of the prepared SrTiO₃, SrTiO₃/PDA, and SrTiO₃/Au/PDA materials was investigated via UV-vis diffuse reflectance spectra (Fig. 3(a)). SrTiO₃/Au/PDA had the strongest light absorption in both ultraviolet and visible light regions. SrTiO₃/PDA had the second strongest light absorption. This result indicated that SrTiO₃/Au/PDA had the best photodynamic performance. This excellent performance was attributed to the enhancement of PDA load on the surface of SrTiO₃ upon the addition of gold nanoparticles and the successful construction of the gold electronic cloud bridge. Changes in the band gap of the samples were calculated via the Tauc plot method by using the following equation:

$$(\alpha h\nu)^{1/2} = A(h\nu - E_g), \qquad (3)$$

where α is absorbance index, *h* is Planck constant, *v* is frequency, *A* is a constant, and *E*_g is semiconductor band gap. In



Fig. 1 SEM images of (a) TiO₂, (b) SrTiO₃/Au/PDA, (c) SrTiO₃, and (d) SrTiO₃/PDA. (e) HRTEM image of SrTiO₃/Au/PDA. (f) TEM image of SrTiO₃/ Au/PDA. (g) Mapping of SrTiO₃/Au/PDA (from left to right: Sr, Ti, O, N, and Au).

this study, absorbance was used as a parameter to replace α . The relationship between $(\alpha h\nu)^{1/2}$ and $h\nu$ is depicted in Fig. 3(b). The band gap evidently decreased from SrTiO₃ (3.245 eV) and SrTiO₃/PDA (3.240 eV) to SrTiO₃/Au/PDA (3.220 eV) possibly because of the coupling of semiconductor energy levels. In general, this decrease in band gap is helpful in improving the performance of PEC sensors.

The efficiency of surface charge transfer was evaluated *via* the EIS test method. As shown in Fig. 3(c), in this model, R_s represent the solution resistance, and R_{ct} represent the charge transfer resistance at the semiconductor/electrolyte interface. Notably, compared with pristine SrTiO₃ (12 705 Ω) and SrTiO₃/PDA (10 439 Ω), the value of R_{ct} (5917 Ω) for SrTiO₃/Au/PDA is dramatically decreased, which means the charge transfer resistance inside the SrTiO₃/Au/PDA electrode is much smaller than that of SrTiO₃ and SrTiO₃/PDA. The above results demonstrate that the coating of Au can accelerate the interfacial transfer and separation of charge carriers of SrTiO₃/Au/PDA. The ability of SrTiO₃/Au/PDA to efficiently transfer

photogenerated electrons proved the existence of the gold electronic cloud bridge. The PEC performance of the prepared materials was evaluated by observing time-dependent current under on and off light switching. In Fig. 3(d), SrTiO₃/Au/PDA had the highest light-absorption performance and the highest charge-separation efficiency, resulting in the highest photo-current value. Moreover, the photocurrent value of SrTiO₃/Au/PDA further increased because of the contribution of Au (Fig. S5 in ESI[†]). This result also confirmed that the gold electronic cloud bridge was successfully constructed between SrTiO₃ and PDA.

The electronic lifetime and carrier density ($N_{\rm D}$) of the materials were characterized *via* open-circuit potential (OCP) and Mott–Schottky plots, respectively, to understand further how the performance and electronic properties of PEC were improved. According to the results of OCP tests, electronic lifetime was calculated using eqn (4):³⁷



Fig. 2 (a) XRD of SrTiO₃, SrTiO₃/PDA, and SrTiO₃/Au/PDA. (b) Full-range XPS spectra of SrTiO₃, SrTiO₃/PDA, and SrTiO₃/Au/PDA. (c-f) Amplification local XPS of Sr, Ti, N, and Au.

$$\tau = \frac{KT}{e} \left(\frac{\mathrm{d}V_{\mathrm{OC}}}{\mathrm{d}t} \right)^{-1},\tag{4}$$

The Mott–Schottky equation (eqn (5)) supported the carrier density $(N_{\rm D})$ calculated by the Mott–Schottky plots:³⁷

$$\frac{1}{C^2} = \frac{2}{N_{\rm D}e\varepsilon_0} \left[(U_{\rm S} - U_{\rm F}) - \frac{KT}{e} \right],\tag{5}$$

where τ is the potential dependent photoelectron lifetime, *k* is Boltzmann's constant, *T* is temperature, *e* is the charge of a single electron, and V_{oc} is the open-circuit voltage at time *t*. SrTiO₃/Au/PDA evidently had the longest electron lifetime that greatly contributed to its photoelectric performance (Fig. 3(e)).

where *C* is the space charge capacitance in the semiconductor, $N_{\rm D}$ is the electron carrier density, *e* is the elemental charge value, ε_0 is the permittivity of the vacuum, ε is the relative permittivity of the semiconductor, $U_{\rm S}$ is the applied potential, *T*



Fig. 3 SrTiO₃, SrTiO₃/PDA, and SrTiO₃/Au/PDA PEC sensors. (a) UV-vis absorption spectra. (b) Plots of $(\alpha h\nu)^{1/2}$ and $h\nu$. (c) EIS Nyquist plots at 0.4 V vs. Ag/AgCl under light radiation in 0.1 M PBS (pH = 7.4). (d) Photocurrent response. (e) Open-circuit potential plots. (f) Mott–Schottky plots.



Fig. 4 3D hollowed out $SrTiO_3/Au/PDA/GOX$ PEC sensor. (a) Photocurrent responses at different glucose concentrations (0–20 mM) in 0.1 M PBS (pH = 7.4). (b) Calibration curve of glucose concentration and photocurrent density. (c) Stability detection curve in 0.1 M PBS (pH = 7.4) at 20 mM of glucose. (d) Histogram of the results of anti-interference analysis (3 mM Glu and 0.3 mM each of AA, NaCl, DA, Suc, and UA).

is temperature, and k is the Boltzmann constant. Among all samples, SrTiO₃/Au/PDA had the largest carrier density (Fig. 3(f)). The increase in electrical conductivity during the material recombination process was confirmed by the substantial enhancement in carrier density that accelerated the transfer of photogenerated electrons. In general, SrTiO₃/Au/PDA exhibited extremely high charge separation efficiency that directly benefitted from the successful construction of the gold electronic cloud bridge.

3.4. Sensing measurements of the biosensors

Owing to the excellent performance of PEC under light radiation, the 3D hollowed out SrTiO₃/Au/PDA material was selected as the primary photoelectrode material for PEC sensing detection. The performance of the biosensor in PEC detection was evaluated. GOx was selected as the representative enzyme for detecting glucose concentration. Sensitivity, linear range, and limit of detection (LOD) are important indicators of sensor performance. The ability of the SrTiO₃/Au/PDA photoelectrode to detect different glucose concentrations was examined (Fig. 4). Results showed that photocurrent gradually increased as glucose concentration increased (Fig. 4(a)). This trend arose because of the strong reducing FADH₂ (Flavine adenine dinucleotide, reduced), which was produced during glucose oxidation. Moreover, FADH₂ consumed the photogenerated holes in the photoelectrode and assisted in enhancing the photocurrent. The calibration curve of photocurrent and glucose concentration was analyzed (Fig. 4(b)). Results confirmed the excellent

20

UA

Table 1 Comparison of the biosensors constructed in previous works and the biosensors developed in this study in terms of several performance indicators

PEC sensors	Linear range (mM)	LOD (mM)	Sensitivity (μA m M^{-1} cm $^{-2}$)	Ref.
R/A-TiO ₂ @GOx	1-20	0.019	5.71	41
ITO/TiO ₂ -MoS ₂ -GOx	0.1-10	0.015	0.81	42
FTO/Fe ₂ O ₃ -NB-PDA-GDH	0-2	0.025	7.36	43
GOx/CdTe	0.1-11	0.04	_	44
a-MoS _x /RGO/ITO	0.15-16	0.098	_	45
3D hollowed out SrTiO ₃ /PDA	0-20	0.017	8.9	This work
3D hollowed out SrTiO ₃ /Au/PDA	0-20	0.012	23.7	This work



Scheme 2 (a) Modification of GOx on the 3D hollowed out SrTiO₃/Au/PDA. (b) Mechanism by which gold accelerates photogenerated electron transfer.

biosensing performance of the 3D hollowed out $SrTiO_3/Au/PDA$ (Fig. 4). The biosensor had wide linear range of 1–20 mM, a high sensitivity of 23.7 μ A mM⁻¹ cm⁻², and a low LOD of 0.012 mM (S/N = 3).

The base material (3D hollowed out SrTiO₃/PDA) was used for glucose detection to confirm its excellent PEC performance objectively. All test methods and conditions for the 3D hollowed out SrTiO₃/PDA PEC sensor were exactly the same as those for the 3D hollowed out SrTiO₃/Au/PDA PEC sensor. The results of the comparison of these sensors, including photoelectric performance curves and calibration curves, are exhibited in Fig. S6 (ESI[†]). Although the 3D hollowed out SrTiO₃/PDA PEC sensor had the same linear detection range as the 3D hollowed out SrTiO₃/Au/PDA PEC sensor, its sensitivity was only 37.55% of that of the 3D hollowed out SrTiO₃/Au/PDA PEC sensor. The excellent PEC performance of the 3D hollowed out SrTiO₃/Au/ PDA PEC sensor was attributed to the contribution of Au to electron transfer. In addition, the influence of PDA on the performance of PEC sensors is also explored. As shown in Fig. S7 (ESI[†]), the thickness of PDA of SrTiO₃/Au/PDA is about 3 nm, while the thickness of PDA of SrTiO₃/Au/PDA (excessive PDA) is 8-10 nm, and the distribution is uneven. Subsequently, SrTiO₃/Au/GOx and SrTiO₃/Au/PDA (excess PDA)/GOx PEC sensors were used for glucose detection. The performance of PEC sensors SrTiO₃/Au/GOx and SrTiO₃/Au/PDA (excess PDA)/ GOx for glucose detection was evaluated (Fig. S8 in ESI[†]). The results show that the sensitivity of SrTiO₃/Au/GOx and SrTiO₃/ Au/PDA (excess PDA)/GOx to glucose detection is 43.04% and 33.80% of the sensitivity of SrTiO₃/Au/PDA/GOx, respectively. Therefore, it can be concluded that PDA greatly improves the glucose detection performance of the sensor, which is attributed to the fact that PDA provided an excellent biocompatible environment for enzymes. Furthermore, the promotion of charge separation and transfer had a very positive effect on sensitivity. Therefore, the gold electron cloud bridge played an extremely important role in sensitivity improvement.

The stability of the 3D hollowed out SrTiO₃/Au/PDA as a PEC biosensor was tested in nine cycles of intermittent light radiation in a solution with 20 mM of glucose. After nine cycles, the photocurrent of the 3D hollowed out SrTiO₃/Au/PDA/GOx biosensor had 99.85% of its initial value, which shows remarkable stability in a short time. To monitor the long-term

stability of the biosensor, we performed 20 mM glucose measurement every 1 day (stored at 4 °C for the rest of the time). As shown in Fig. S9 (ESI[†]), the photocurrent of the 3D hollowed out SrTiO₃/Au/PDA/GOx biosensor had an initial value of 99.44% after 10 days. Results showed that the PEC biosensor had excellent stability (Fig. 4(c)), confirming that PDA provided a good biocompatible environment for the enzyme that greatly enhanced the enzyme catalytic activity. The specificity of electrodes in biological testing is critical to detection results. Hence, several interfering substances, such as ascorbic acid (AA), sodium chloride (NaCl), dopamine (DA), sucrose (Suc), and uric acid (UA), were individually added after glucose (Glu). The PEC biosensor exhibited excellent anti-interference ability (Fig. 4(d)). In addition, the sensing mechanism of glucose is described in the ESI.[†] Compared with the biosensor developed in a previous work (Table 1), the PEC biosensor developed herein had better and satisfactory results in terms of sensitivity and linear range.

The detection ability of the 3D hollowed out SrTiO₃/Au/PDA/ GOx sensor was tested by analyzing glucose concentration in human serum samples. Five human serum samples with known blood glucose concentrations were obtained at The First Affiliated Hospital of Hainan Medical University. Subsequently, the human serum samples were diluted 50 times with 0.1 M PBS. The glucose concentration of these samples was measured using the 3D hollowed out SrTiO₃/Au/PDA/GOx PEC sensor. Results showed that the concentration detected by the sensor was consistent with the known glucose concentration (Table S2 in ESI[†]). Moreover, the serum detection recovery rate ranged from 98.487% and 100.831%, which was within the acceptable range (Table S2 in ESI[†]). This result supported the claim that the 3D hollowed out SrTiO₃/Au/PDA PEC sensor constructed herein can be used in detecting glucose concentrations in actual human blood samples.

3.5. Sensing mechanism of the 3D hollowed out SrTiO₃/Au/ PDA/GOx biosensor

As shown in Scheme 2, the path of the 3D hollowed out $SrTiO_3/Au/PDA$ PEC sensor modified by GOx and the gold electron cloud bridge accelerated the transfer mechanism of photogenerated electrons. In Scheme 2(a), GOx was tightly wrapped in the PDA layer of the PEC sensor. Therefore, the highly

biologically active PDA created an efficient catalytic environment for GOx. In Scheme 2(b), when light radiation reached a certain intensity, the PDA molecule changed from the ground state to the excited state because a transition behavior of π - π *. Afterward, the electrons at the excited state transitioned from the highest occupied molecular orbital of PDA to the lowest unoccupied molecular orbital (LUMO) with a high energy level. The excited electrons enriched in LUMO thermodynamically transferred to the conduction band (CB) of SrTiO₃ because the LUMO of PDA was about -1.468 eV (vs. NHE)³⁸ and the CB of SrTiO₃ was approximately -0.8 eV (vs. NHE).³⁹ The transfer of photogenerated electrons induced the photogenerated holes to transfer in the opposite direction and finally annihilated by glucose oxidation.⁴⁰ In this process, sensitivity can be effectively improved by accelerating the transfer of photogenerated electrons. Therefore, elemental gold with extremely dense electron clouds has an indispensable role in the rapid transfer of photogenerated electrons. As an electronic bridge, gold provides a fast channel for the transfer of photogenerated electrons and promotes the separation and transfer of photogenerated thereby substantially improving the photocharges. electrochemical performance of the 3D hollowed out SrTiO₃/Au/ PDA.

4. Conclusion

A 3D hollowed out SrTiO₃/Au/PDA composite material was successfully manufactured in this study. This material was characterized *via* SEM, XPS, XRD, TEM, EDX, mapping, UV-vis spectroscopy. The construction of the gold electronic cloud bridge at the SrTiO₃–PDA interface endowed the 3D hollowed out SrTiO₃/Au/PDA with excellent photoelectrochemical performance and efficient charge separation ability. As a novel type of PEC biosensor, the performance of the 3D hollowed out SrTiO₃/Au/PDA/GOx electrode in glucose detection was tested. This electrode had a low LOD of 0.012 mM and an ultrahigh sensitivity of 23.7 μ A mM⁻¹ cm⁻² within a wide linear range of 1–20 mM. In short, the biosensor exhibited extremely high sensitivity. The results provide a novel idea for designing efficient photocatalytic devices.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This research was financially supported by the National Natural Science Foundation of China (no. 51762012, 81860373, 51862006 and 82060386), the Finance Science and Technology Project of Hainan Province (no. ZDYF2019161 and 2019RC221), CAMS Innovation Fund for Medical Sciences (no. 2019-I2M-5-023), Central government for local science and technology (no. ZY2019HN0909), Key Laboratory Open Project Fund of Emergency and Trauma of Ministry of Education (no. KLET-202008).

References

- 1 L. Y. Ge, R. Hou, Y. Cao, J. C. Tu and Q. Wu, Photoelectrochemical enzymatic sensor for glucose based on Au@C/TiO₂ nanorod arrays, *RSC Adv.*, 2020, **10**(72), 44225–44231.
- 2 T. Hou, L. F. Zhang, X. Z. Sun and F. Li, Biphasic photoelectrochemical sensing strategy based on *in situ* formation of CdS quantum dots for highly sensitive detection of acetylcholinesterase activity and inhibition, *Biosens. Bioelectron.*, 2016, **75**, 359–364.
- 3 A. Devadoss, P. Sudhagar, C. Terashima, K. Nakata and A. Fujishima, Photoelectrochemical biosensors: New insights into promising photoelectrodes and signal amplification strategies, *J. Photochem. Photobiol.*, *C*, 2015, **24**, 43–63.
- 4 T. Xian, H. Yang, L. J. Di and J. F. Dai, Enhanced photocatalytic activity of $SrTiO_3$ particles by surface decoration with Ag nanoparticles for dye degradation, *Phys. Scr.*, 2015, **90**(5), 7.
- 5 L. P. Wang, Y. Meng, C. X. Zhang, H. B. Xiao, Y. L. Li, Y. M. Tan and Q. J. Xie, Improving Photovoltaic and Enzymatic Sensing Performance by Coupling a Core-Shell Au Nanorod@TiO₂ Heterostructure with the Bioinspired L-DOPA Polymer, ACS Appl. Mater. Interfaces, 2019, **11**(9), 9394–9404.
- 6 A. Bera, K. W. Wu, A. Sheikh, E. Alarousu, O. F. Mohammed and T. Wu, Perovskite Oxide SrTiO₃ as an Efficient Electron Transporter for Hybrid Perovskite Solar Cells, *J. Phys. Chem. C*, 2014, **118**(49), 28494–28501.
- 7 A. Naldoni, U. Guler, Z. X. Wang, M. Marelli, F. Malara,
 X. G. Meng, L. V. Besteiro, A. O. Govorov, A. V. Kildishev,
 A. Boltasseva and V. M. Shalaev, Broadband Hot-Electron
 Collection for Solar Water Splitting with Plasmonic
 Titanium Nitride, *Adv. Opt. Mater.*, 2017, 5(15), 11.
- 8 Z. She, Y. Nie, H. Zhong, L. Liu, S. Yu and Y. Li, Effect of surface deformation on biocompatibility of biomedical alloys, *Mater. Sci. Eng.*, *C*, 2021, **119**, 111636.
- 9 Y. Onuki, U. Bhardwaj, F. Papadimitrakopoulos and D. J. Burgess, A Review of the Biocompatibility of Implantable Devices: Current Challenges to Overcome Foreign Body Response, *J. Diabetes Sci. Technol.*, 2008, 2(6), 1003–1015.
- 10 D. F. Williams, There is no such thing as a biocompatible material, *Biomaterials*, 2014, **35**(38), 10009–10014.
- 11 H. Dai, Y. H. Zhong, X. Y. Wu, R. X. Hu, L. Wang, Y. C. Zhang, G. K. Fan, X. Y. Hu, J. Li and Z. J. Yang, Synthesis of perovskite-type SrTiO₃ nanoparticles for sensitive electrochemical biosensing applications, *J. Electroanal. Chem.*, 2018, **810**, 95–99.
- 12 W. Xu, W. Yang, H. Guo, L. Ge, J. Tu and C. Zhen, Constructing a TiO₂/PDA core/shell nanorod array electrode as a highly sensitive and stable photoelectrochemical glucose biosensor, *RSC Adv.*, 2020, **10**(17), 10017–10022.

- 13 H. Lee, S. M. Dellatore, W. M. Miller and P. B. Messersmith, Mussel-inspired surface chemistry for multifunctional coatings, *Science*, 2007, **318**(5849), 426–430.
- 14 H. J. Nam, B. Kim, M. J. Ko, M. Jin, J. M. Kim and D. Y. Jung, A New Mussel-Inspired Polydopamine Sensitizer for Dye-Sensitized Solar Cells: Controlled Synthesis and Charge Transfer, *Chem.-Eur. J.*, 2012, **18**(44), 14000–14007.
- 15 L. Romaner, G. Heimel, J.-L. Bredas, A. Gerlach, F. Schreiber, R. L. Johnson, J. Zegenhagen, S. Duhm, N. Koch and E. Zojer, Impact of bidirectional charge transfer and molecular distortions on the electronic structure of a metal-organic interface, *Phys. Rev. Lett.*, 2007, **99**(25), 256801.
- 16 C. Tyznik, J. Lee, J. Sorli, X. Liu, E. K. Holland, C. S. Day, J. E. Anthony, Y.-L. Loo, Z. V. Vardeny and O. D. Jurchescu, Photocurrent in Metal-Halide Perovskite/Organic Semiconductor Heterostructures: Impact of Microstructure on Charge Generation Efficiency, ACS Appl. Mater. Interfaces, 2021, 13(8), 10231–10238.
- 17 X. Shi, W. Wang, X. R. Miao, F. Tian, Z. W. Xu, N. Li and M. L. Jing, Constructing Conductive Channels between Platinum Nanoparticles and Graphitic Carbon Nitride by Gamma Irradiation for an Enhanced Oxygen Reduction Reaction, *ACS Appl. Mater. Interfaces*, 2020, **12**(41), 46095– 46106.
- 18 N. Arjona, G. Trejo, J. Ledesma-Garcia, L. G. Arriaga and M. Guerra-Balcazar, An electrokinetic-combined electrochemical study of the glucose electro-oxidation reaction: effect of gold surface energy, *RSC Adv.*, 2016, 6(19), 15630–15638.
- 19 R. Long and O. V. Prezhdo, Instantaneous Generation of Charge-Separated State on TiO₂ Surface Sensitized with Plasmonic Nanoparticles, *J. Am. Chem. Soc.*, 2014, **136**(11), 4343–4354.
- 20 Z. S. Zhang, L. H. Liu, W. H. Fang, R. Long, M. V. Tokina and O. V. Prezhdo, Plasmon-Mediated Electron Injection from Au Nanorods into MoS₂: Traditional *versus* Photoexcitation Mechanism, *Chem*, 2018, 4(5), 1112–1127.
- 21 W. Yang, X. Wang, W. Hao, Q. Wu, J. Peng, J. Tu and Y. Cao, 3D hollow-out TiO_2 nanowire cluster/GOx as an ultrasensitive photoelectrochemical glucose biosensor, *J. Mater. Chem. B*, 2020, **8**(11), 2363–2370.
- 22 T. Hou, N. N. Xu, W. X. Wang, L. Ge and F. Li, Truly Immobilization-Free Diffusivity-Mediated Photoelectrochemical Biosensing Strategy for Facile and Highly Sensitive MicroRNA Assay, *Anal. Chem.*, 2018, **90**(15), 9591–9597.
- 23 Y. Z. Wei, J. Y. Wang, R. B. Yu, J. W. Wan and D. Wang, Constructing SrTiO₃-TiO₂ Heterogeneous Hollow Multishelled Structures for Enhanced Solar Water Splitting, *Angew. Chem., Int. Ed.*, 2019, 58(5), 1422–1426.
- 24 J. Chen, P. Xiao, J. C. Gu, D. Han, J. W. Zhang, A. H. Sun, W. Q. Wang and T. Chen, A smart hybrid system of Au nanoparticle immobilized PDMAEMA brushes for thermally adjustable catalysis, *Chem. Commun.*, 2014, 50(10), 1212–1214.
- 25 M. Steenackers, A. Kuller, S. Stoycheva, M. Grunze and R. Jordan, Structured and Gradient Polymer Brushes from

Biphenylthiol Self-Assembled Monolayers by Self-Initiated Photografting and Photopolymerization (SIPGP), *Langmuir*, 2009, **25**(4), 2225–2231.

- 26 I. Amin, M. Steenackers, N. Zhang, R. Schubel, A. Beyer,
 A. Golzhauser and R. Jordan, Patterned Polymer Carpets, Small, 2011, 7(5), 683–687.
- 27 P. Xiao, J. C. Gu, J. Chen, J. W. Zhang, R. B. Xing, Y. C. Han, J. Fu, W. Q. Wang and T. Chen, Micro-contact printing of graphene oxide nanosheets for fabricating patterned polymer brushes, *Chem. Commun.*, 2014, **50**(54), 7103–7106.
- 28 W. C. Ye, H. Huang, W. W. Yang, X. Wang, C. L. Ren, Q. S. Hu, Y. M. Li and B. Ren, Ultrathin polydopamine film coated gold nanoparticles: a sensitive, uniform, and stable SHINERS substrate for detection of benzotriazole, *Analyst*, 2017, 142(18), 3459–3467.
- 29 W. Xu, J. Jia, T. Wang, C. Li, B. He, J. Zong, Y. Wang, H. J. Fan, H. Xu, Y. Feng and H. Chen, Continuous Tuning of Au-Cu₂O Janus Nanostructures for Efficient Charge Separation, *Angew. Chem., Int. Ed.*, 2020, **59**(49), 22246– 22251.
- 30 T. Chen, M. Yang, X. Wang, L. H. Tan and H. Chen, Controlled assembly of eccentrically encapsulated gold nanoparticles, *J. Am. Chem. Soc.*, 2008, **130**(36), 11858–11859.
- K. Woan, G. Pyrgiotakis and W. Sigmund, Photocatalytic Carbon-Nanotube-TiO₂ Composites, *Adv. Mater.*, 2009, 21(21), 2233–2239.
- 32 Y. Horiuchi, T. Toyao, M. Saito, K. Mochizuki, M. Iwata, H. Higashimura, M. Anpo and M. Matsuoka, Visible-Light-Promoted Photocatalytic Hydrogen Production by Using an Amino-Functionalized Ti(IV) Metal-Organic Framework, *J. Phys. Chem. C*, 2012, **116**(39), 20848–20853.
- 33 W. K. Yang, W. Xu, N. Zhang, X. Y. Lai, J. Peng, Y. Cao and J. C. Tu, TiO_2 nanotubes modified with polydopamine and graphene quantum dots as a photochemical biosensor for the ultrasensitive detection of glucose, *J. Mater. Sci.*, 2020, 55(14), 6105–6117.
- 34 H. Mao, J. C. Liang, H. F. Zhang, Q. Pei, D. L. Liu, S. Y. Wu, Y. Zhang and X. M. Song, Poly(ionic liquids) functionalized polypyrrole/graphene oxide nanosheets for electrochemical sensor to detect dopamine in the presence of ascorbic acid, *Biosens. Bioelectron.*, 2015, **70**, 289–298.
- 35 D. T. Sun, L. Peng, W. S. Reeder, S. M. Moosavi, D. Tiana, D. K. Britt, E. Oveisi and W. L. Queen, Rapid, Selective Heavy Metal Removal from Water by a Metal–Organic Framework/Polydopamine Composite, ACS Cent. Sci., 2018, 4(3), 349–356.
- 36 F. Zhang, H. Zhang, R. Chen, Q. Liu, J. Liu, C. Wang, Z. Sun and J. Wang, Mussel-inspired antifouling magnetic activated carbon for uranium recovery from simulated seawater, *J. Colloid Interface Sci.*, 2019, **534**, 172–182.
- 37 Y. M. Xin, Z. Z. Li and Z. H. Zhang, Photoelectrochemical aptasensor for the sensitive and selective detection of kanamycin based on Au nanoparticle functionalized self-doped TiO_2 nanotube arrays, *Chem. Commun.*, 2015, **51**(85), 15498–15501.
- 38 F. Yu, S. G. Chen, Y. Chen, H. M. Li, L. Yang, Y. Y. Chen and Y. S. Yin, Experimental and theoretical analysis of

polymerization reaction process on the polydopamine membranes and its corrosion protection properties for 304 Stainless Steel, *J. Mol. Struct.*, 2010, **982**(1–3), 152–161.

- 39 X. Zhou, J. Y. Shi and C. Li, Effect of Metal Doping on Electronic Structure and Visible Light Absorption of SrTiO₃ and NaTaO₃ (Metal = Mn, Fe, and Co), *J. Phys. Chem. C*, 2011, 115(16), 8305–8311.
- 40 W. K. Yang, W. Xu, Y. D. Wang, D. L. Chen, X. H. Wang, Y. Cao, Q. Wu, J. C. Tu and C. Zhen, Photoelectrochemical Glucose Biosensor Based on the Heterogeneous Facets of Nanocrystalline TiO₂/Au/Glucose Oxidase Films, *ACS Appl. Nano Mater.*, 2020, 3(3), 2723–2732.
- 41 B. D. Yan, Y. Zhuang, Y. L. Jiang, W. Xu, Y. J. Chen, J. C. Tu, X. H. Wang and Q. Wu, Enhanced photoelectrochemical biosensing performance from rutile nanorod/anatase nanowire junction array, *Appl. Surf. Sci.*, 2018, **458**, 382–388.
- 42 X. Q. Liu, X. H. Huo, P. P. Liu, Y. F. Tang, J. Xu, X. H. Liu andY. M. Zhou, Assembly of MoS₂ nanosheet-TiO₂ nanorod

heterostructure as sensor scaffold for photoelectrochemical biosensing, *Electrochim. Acta*, 2017, **242**, 327–336.

- 43 S. Selvarajan, N. R. Alluri, A. Chandrasekhar and S. J. Kim, BaTiO₃ nanoparticles as biomaterial film for self-powered glucose sensor application, *Sens. Actuators, B*, 2016, 234, 395-403.
- 44 W. J. Wang, L. Bao, J. P. Lei, W. W. Tu and H. X. Ju, Visible light induced photoelectrochemical biosensing based on oxygen-sensitive quantum dots, *Anal. Chim. Acta*, 2012, **744**, 33–38.
- 45 M. X. Shang, H. Qi, C. C. Du, H. Huang, S. Y. Wu, J. L. Zhang and W. B. Song, One-step electrodeposition of high-quality amorphous molybdenum sulfide/RGO photoanode for visible-light sensitive photoelectrochemical biosensing, *Sens. Actuators, B*, 2018, **266**, 71–79.