# **RSC** Advances



View Article Online

View Journal | View Issue

# PAPER

Check for updates

Cite this: RSC Adv., 2021, 11, 13556

Received 26th February 2021 Accepted 6th April 2021

DOI: 10.1039/d1ra01558c

rsc.li/rsc-advances

## 1. Introduction

The demand for energy-efficient smart windows utilizing thermochromic materials is constantly increasing due to their potential to dramatically reduce the energy consumption of the buildings by modulating the transmission of light and heat.<sup>3-7</sup> Vanadium dioxide (VO<sub>2</sub>) has been widely investigated for smart windows because of its excellent thermochromic properties.<sup>8-10</sup> In particular, monoclinic M-phase VO<sub>2</sub> undergoes a metal-toinsulator transition (MIT) at a critical temperature of ~68 °C.<sup>12-14</sup> The monoclinic crystal structure of VO<sub>2</sub> displays infrared transparent below the critical temperature while in a rutile crystal structure it is infrared-reflective above the critical temperature accompanied by abrupt changes in the electrical, magnetic, and optical properties.<sup>1,16-18</sup> Due to this special MIT property, monoclinic M-phase VO<sub>2</sub> is a promising candidate for

# 3D mesoporous structure assembled from monoclinic M-phase VO<sub>2</sub> nanoflakes with enhanced thermochromic performance†

Liboro Hundito Molloro, 💿 \*ab Shouqin Tain, 💿 a Neway Belachew, 💿 b Kwadwo Asare Owusu<sup>c</sup> and Xiujian Zhao 💿 \*a

Monoclinic M-phase VO<sub>2</sub> is a promising candidate for thermochromic materials due to its abrupt change in the near infrared (NIR) transmittance along with the metal-to-insulator transition (MIT) at a critical temperature ~68 °C. However, low luminous transmittance ( $T_{lum}$ ), poor solar energy modulation ability ( $\Delta T_{sol}$ ), and high phase transition temperature ( $T_c$ ) can limit the application of VO<sub>2</sub> for smart windows. To overcome these limitations, 3D mesoporous structure can be employed in VO<sub>2</sub> films. Herein, 3D mesoporous structure can be employed in VO<sub>2</sub> films. Herein, 3D mesoporous structures assembled from monoclinic M-phase VO<sub>2</sub> nanoflakes with a pore size of about 2–10 nm were synthesized by a hydrothermal method using *Ensete ventricosum* fiber (EF) as a template followed by calcination at 450 °C. The prepared film exhibited excellent thermochromic performance with balanced  $T_{lum} = 67.3\%$ ,  $\Delta T_{sol} = 12.5\%$ , and lowering  $T_c$  to 63.15 °C. This is because the 3D mesoporous structure can offer the uniform dispersion of VO<sub>2</sub> nanoflakes in the film to enhance  $T_{lum}$ , ensure sufficient VO<sub>2</sub> nanoflakes in the film for high  $\Delta T_{sol}$  and lower  $T_c$ . Therefore, this work can provide a green approach to synthesize 3D mesoporous structures assembled from monoclinic M-phase VO<sub>2</sub> nanoflakes and promote their application in smart windows.

the thermochromic smart window.23,24 However, low luminous transmittance  $(T_{\text{lum}})$ , which is not higher than ~40%,<sup>16,27</sup> poor solar energy modulation ability ( $\Delta T_{sol}$ ), which is usually less than 10%<sup>16,27</sup> and high phase transition temperature ( $T_c$ ) ~68 °C, which should be lowered to room temperature,1,13,20 limits the application of  $VO_2$  in smart windows. Up to the present, various attempts have been made to overcome these limitations,13,31 including introducing pores,29,30,32 structural modification,2,35 designing 2D nanoarchitecture,<sup>7,33,34</sup> core-shell,<sup>24</sup> multilayer stack design,36 doping,1,20 composite15,22,26 and film thickness optimization.<sup>37</sup> Optical calculation confirms that incorporation of VO<sub>2</sub> in another dielectric material could increase  $T_{lum}$  and  $\Delta T_{sol}$ .<sup>27,38</sup> The simulation conducted by Taylor et al.39 and the sample prepared by Qian et al.35 as structural modification can enhance  $T_{\rm lum}$  and  $\Delta T_{\rm sol}$ . Guo et al.<sup>28</sup> fabricated flexible VO<sub>2</sub>-based thermochromic films by dispersing the VO<sub>2</sub> powders in a polymer matrix. The  $T_{\text{lum}}$  and  $\Delta T_{\text{sol}}$  of these flexible films reached 54.26% and 12.34%, respectively. Cao et al.29 used the freeze-drying method to prepare VO<sub>2</sub> film with nanoporous structure, and the film showed the best  $T_{\text{lum}} = 50\%$  and  $\Delta T_{\text{sol}} = 14.7\%$ . Therefore, structurally modified VO2 nanoparticles distributed in another dielectric matrix can offer high value of  $T_{lum}$  and  $\Delta T_{sol.}$ 

Inspired by this concept, 3D architecture with mesopores are introduced in the monoclinic M-phase  $VO_2$  films. Liu *et al.* fabricated ordered M-phase  $VO_2$  honeycomb structures with a complex hierarchy by a template-free surface patterning method.<sup>2</sup> The ordered M-phase  $VO_2$  honeycomb structure film

<sup>&</sup>lt;sup>a</sup>State Key Laboratory of Silicate Materials for Architectures, Wuhan University of Technology (WUT), No. 122, Luoshi Road, Wuhan 430070, P. R. China. E-mail: liborotg@yahoo.com; opluse@whut.edu.cn

<sup>&</sup>lt;sup>b</sup>Department of Chemistry, Debre Berhan University, P.O. Box 445, Debre Berhan, Ethiopia

<sup>&</sup>lt;sup>c</sup>State Key Laboratory of Advanced Technology for Materials Synthesis and Processing, Wuhan University of Technology (WUT), No. 122, Luoshi Road, Wuhan 430070, P. R. China

 $<sup>\</sup>dagger$  Electronic supplementary information (ESI) available: Detail characterization reports of V\_2O\_5, and M-phase VO\_2 synthesised at 200 °C. See DOI: 10.1039/d1ra01558c

#### Paper

exhibited a high  $T_{\rm lum}$  of 95.4%. However, the solar energy modulation ability was only 5.5%. Ke *et al.*<sup>34</sup> reported 2D patterned M-phase VO<sub>2</sub> nanonet films with controlled periodicity. The film exhibited a high  $\Delta T_{\rm sol}$  of 13.2%. However, the value of  $T_{\rm lum}$  was only 46.1%. In this regard, it is a great challenge to introduce surface modification with a desirable architecture in VO<sub>2</sub> film to obtain excellent performance with balanced  $T_{\rm lum}$  and  $\Delta T_{\rm sol}$ . Most reported works of literature are focused either on surface modification<sup>29,30</sup> or designing 2D nanoarchitectures.<sup>7,34</sup> However, the effect of 3D mesoporous structures assembled by VO<sub>2</sub> nanoflakes based thermochromic films has not been reported so far. Therefore, it is of great importance to investigate the effect of microstructure on 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes on the thermochromic properties of VO<sub>2</sub> films.

Herein, we have prepared 3D mesoporous structures assembled by monoclinic M-phase  $VO_2$  nanoflakes using a facile hydrothermal method followed by calcination in the presence of *Ensete ventricosum* fiber (EF) as a template. The crystal structure, morphology, shape, composition and pore size distribution of the synthesised materials were investigated by powder XRD, SEM/EDS, TEM, XPS and BET. The film prepared from the synthesised materials were investigated for thermochromic smart window applications.

#### 2. Experiments and characterization

# 2.1. Preparation of 3D mesoporous structures assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes

All reagents were of the analytical grade and were used without further purification. In a typical synthesis, 0.63 g (0.0034 mol) of vanadium pentoxide (V<sub>2</sub>O<sub>5</sub>) and 1.2859 g (0.0102 mol) of oxalic acid  $(H_2C_2O_4 \cdot 2H_2O)$  were dissolved in 30 ml of deionized water. The suspension was stirred constantly in a water bath kettle at 80 °C until the color of the solution changed to blue. Then 30 ml of ethylene glycol was added to increase the viscosity of the solution. As the acidic solution degrades EF, ammonia was added to adjust the pH to  $\sim$ 7. The solution and 0.5 g of EF were transferred to a 100 ml Teflon-lined stainless-steel autoclave. The autoclave was maintained at a temperature of 180 °C for 20 h and then cooled to room temperature naturally. The black product with EF was separated and washed with water and ethanol, and then dried in air at 80  $^\circ\mathrm{C}$  for 24 h. To remove the template and to obtain the 3D porous structure, the product was calcined at 450 °C for 1 h at a heating rate of 5 °C min<sup>-1</sup>. During the calcination, VO2 nanoflakes were oxidized to yellow 3D mesoporous structure assembled by V<sub>2</sub>O<sub>5</sub> nanoflakes. Finally, the obtained 0.4 g 3D mesoporous structure assembled by V2O5 nanoflakes and 0.2 g NH4HCO4 were placed in a vacuum tube furnace for annealing at 550 °C for 30 min. Ammonia gas produced from the decomposition of NH<sub>4</sub>HCO<sub>4</sub> reduced the 3D mesoporous structure assembled by V<sub>2</sub>O<sub>5</sub> nanoflakes to 3D mesoporous structure assembled by monoclinic M-phase VO2 nanoflakes. For comparison, monoclinic M-phase VO2 was also synthesized under similar conditions without EF S1 (ESI).†

#### 2.2. Preparation of thermochromic films

The obtained 0.5 g 3D mesoporous structure assembled by, monoclinic M-phase VO<sub>2</sub> nanoflakes were dispersed in ethanol that contained an appropriate amount of PVP (0.25 g) for subsequent ball milling and sonication to ensure well mixing. After centrifugation, this suspension was then uniformly cast onto a fused silica glass substrate ( $25 \text{ mm} \times 25 \text{ mm} \times 1 \text{ mm}$ ) by spin-coating at the speed of 500 rpm for 15 s and then 1500 rpm for 30 s. Finally, the ethanol was removed by drying at 80 °C for 5 min to get the film of 3D mesoporous structure assembled by M-phase VO<sub>2</sub> nanoflakes based composite.

#### 2.3. Characterizations

X-ray diffraction (XRD, D8DISCOVER, Cu K $\alpha$ 1 = 0.154056 nm as the source of radiation, output power 3 kW) was employed to determine the crystal phase of obtained samples. A field emission scanning electron microscopy (FE-SEM, JSM-7500F, JEOL, Japan) and a Hitachi S4800 electron microscope operating at 15 kV were employed to observe the morphology of the nanoflakes and films. Transition electron microscopy (TEM) images were recorded with a (TEM, FEG, Talos F200S, Thermo Fisher, USA) microscope operated at 200 kV. The BET analyzer (ASAP 2020) was used to measure the pore size distribution and the specific surface area with nitrogen as an adsorbate, and the pore size distribution was calculated by the Brunauer-Emmett-Teller (BET) method. The compositions of the powder nanoflakes were detected by X-ray photoelectron spectroscopy (XPS, ESCALAB 250Xi). The phase transition properties were detected by differential scanning calorimeter (DSC, DSC8500, American PE). The thermochromic performance of the films was measured from 300 to 2500 nm by UV-vis-NIR spectrophotometer (UV-3600) equipped with temperature controlling unit at 20 °C and 90 °C, respectively. The integral luminous transmittance ( $T_{lum}$ , 380–780 nm) and solar transmittance ( $T_{sol}$ , 300– 2500 nm) were calculated based on the measured spectra using the following expression:40

$$T_{\rm lum/sol} = \int \varphi_{\rm lum/sol}(\lambda) T(\lambda) d\lambda / \int \varphi_{\rm lum/sol}(\lambda) d\lambda$$

where  $T(\lambda)$  denotes the transmittance at the wavelength  $\lambda$ ,  $\varphi_{\text{lum}}(\lambda)$  is the standard luminous efficiency function for the photopic vision of human eyes,  $\varphi_{\text{sol}}(\lambda)$  is the solar spectral irradiance for the air mass 1.5 corresponding to the sun standing 37° above the horizon. The solar energy modulation ability  $(\Delta T_{\text{sol}})$  is defined as:  $\Delta T_{\text{sol}} = T_{\text{sol}} (20 \text{ °C}) - T_{\text{sol}} (90 \text{ °C})$ .

#### Results and discussion

# 3.1. Structure and composition of 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes

Scheme 1 shows the synthesis root and surface morphology of 3D mesoporous structure assembled by monoclinic M-phase  $VO_2$  nanoflakes. The well-mixed precursor solution was added into Teflon-lined stainless-steel autoclave containing EF for the hydrothermal process for adsorption. The negative surface charge from carboxyl (COO<sup>-</sup>) and other hydrophilic functional



Scheme 1 Schematic illustration of the whole process for synthesis of the 3D mesoporous structure assembled by monoclinic M-phase  $VO_2$  nanoflakes.

groups on the fiber surface facilitate the favorable adsorption of the vanadyl complex.41 EF can greatly increase solid-liquid interface so that the nucleation occurs easily on the surface42 and then grew into nanoflakes layer by layer interaction with keeping a similar morphology to that of raw EF. In the second step, 3D mesoporous structure assembled by V<sub>2</sub>O<sub>5</sub> nanoflakes were produced after calcination of the adsorbed fiber at 450  $^\circ\mathrm{C}$ in the presence of air to remove the EF template, the results are described in detail in Fig. S2 (ESI).<sup>†</sup> In this step, VO<sub>2</sub> nanoflakes were converted into a 3D mesoporous structure assembled by V<sub>2</sub>O<sub>5</sub> nanoflakes because of the oxidation reaction. The 3D structure and pore formation are directed by EF during the calcination process. Lastly, post-annealing in reducing ammonia atmosphere produced from the decomposition of NH<sub>4</sub>HCO<sub>4</sub> yields a 3D mesoporous structure assembled by Mphase VO<sub>2</sub> nanoflakes.

To investigate the effect of the hydrothermal temperature on the structure and pore size, M-phase VO<sub>2</sub> nanoflakes were synthesised at 160 °C, 180 °C and 200 °C. However, at 160 °C, the experiment failed. The phenomena suggest that temperature is low to facilitate the adsorption and subsequent growth of the nucleus in the surface of EF. The hydrothermal temperature of 200 °C was effective but relatively high energy cost. The obtained result for 200 °C is presented in Fig. S2 (ESI).† As a result, 180 °C is found to be optimum to carry out the experiment.

The crystal structure and phase composition of samples were measured by XRD (Fig. 1). The diffraction peaks of VO<sub>2</sub> samples synthesised with and without a template was found to be well fitted to the standard XRD pattern of a monoclinic M-phase VO<sub>2</sub> phase (space group: $P2_1/c$ , (no. 14) JCPDS No. 44-252) and no peaks of any other vanadium oxide phases or impurities are detected. There is no obvious difference in diffraction patterns of the two samples, suggesting that *Ensete ventricosum* fiber (EF) template has no effect on the phase structure of samples. Moreover, the peak intensity of (011) plane of 3D mesoporous structure assembled by M-phase VO<sub>2</sub> nanoflakes is relatively stronger and narrower than that of the monoclinic M-phase VO<sub>2</sub> nanorods, indicating a higher crystallinity in the monoclinic Mphase VO<sub>2</sub> nanoflakes.

The morphology of 3D mesoporous structure assembled by monoclinic M-phase VO2 were investigated through SEM and TEM. As shown in Fig. 2(a) and (b), a 3D mesoporous structure assembled by monoclinic M-phase VO2 exhibits a porous structure composed of uniform nanoflakes with a diameter of  $\sim$ 90 nm, hundreds of nanometers length and  $\sim$ 20 nm thickness. Interestingly, the VO<sub>2</sub> product is 3D mesoporous structure assembled by monoclinic M-phase VO2 nanoflakes with many pores. The TEM image of the 3D mesoporous structure assembled by monoclinic M-phase  $VO_2$  nanoflakes Fig. 2(c), shows the stacks of nanoflakes with many small pores (2-10 nm in the diameter) and some other pores in the range of 10-50 nm in diameter between nanoflakes. This is in good agreement with the morphology observed in the SEM images in Fig. 2(a) and (b). The high-resolution TEM (HRTEM) image Fig. 2(d) taken from the edge of a single nanoflakes Fig. 2(c), shows clear lattice fringes with interplanar d-spacing of 0.32 nm, which is corresponding to the (011) lattice plane of monoclinic M-phase VO<sub>2</sub>. This is consistent with the XRD results, indicating high



Fig. 1 XRD patterns of 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes and monoclinic M-phase VO<sub>2</sub> nanorods (initially prepared at the hydrothermal reaction temperature of 180 °C) obtained by annealing  $V_2O_5$  at 550 °C for 30 min in ammonia atmosphere and VO<sub>2</sub>(B) in vacuum, respectively.



Fig. 2 (a) and (b) SEM at different magnification, (c) TEM and (d) HRTEM images of 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes.



Fig. 3 HAADF image (a) and elemental mapping of V (b) and O (c) of obtained 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes.

crystallinity for 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes.

High-angle annular dark-field (HAADF) scanning transmission electron microscopy (STEM) and energy-dispersive spectroscopy (EDS) elemental mapping were used to investigate the chemical analysis of 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes (Fig. 3). The HAADF image of obtained 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes in Fig. 3(a), shows a 3D uniform stack flakes providing high surface area and mesoporosity. The uniform distribution is also confirmed by EDS recorded from various regions of 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes in Fig. 3(b) and (c). The elemental mapping of constituting elements V and O in Fig. 3(b) and (c) demonstrate a well-defined compositional profile of the 3D mesoporous structure assembled by M-phase VO<sub>2</sub> nanoflakes.

The oxidation state of vanadium in the obtained 3D mesoporous structure assembled by monoclinic M-phase  $VO_2$ nanoflakes was examined by X-ray photoelectron spectroscopy (XPS) and the results are shown in Fig. 4. The fully scanned survey spectra show the presence of only V and O, and no other elements exist in Fig. 4(a). The C1s peak (284.6 eV) in the survey is used as a reference. Fig. 4(b) shows the high-resolution XPS spectra of V2p and O1s peaks as well as their deconvolution which can be fitted by applying a Shirley function with software



**Fig. 4** (a) XPS survey spectrum and (b) high resolution XPS spectrum for V2p and O1s of 3D mesoporous monoclinic M-phase VO<sub>2</sub> nanoflakes, and pore size distribution curves and N2 adsorption–desorption curves of (c) 3D mesoporous monoclinic M-phase VO<sub>2</sub> nanoflakes, and (d) monoclinic M-phase VO<sub>2</sub> nanorods.



Fig. 5 (a) Low- and (b) high-magnification SEM, (c) TEM and (d) HRTEM images of monoclinic M-phase VO<sub>2</sub> nanorod.

XPS peak 4.1. The V2p<sub>3/2</sub> peak can be deconvoluted into two peaks, which correspond to V<sup>5+</sup> and V<sup>4+</sup>, with the binding energy of 517.6 and 516.4 eV, respectively.<sup>43</sup> The O1s centered at 530.4 eV can be assigned to the O<sup>2-</sup> in the V–O.<sup>44</sup> The presence of V<sup>5+</sup> ion could be attributed to the partial oxidation of the nanoflakes powder exposed in the air.<sup>43</sup> Besides, the energy bandgap between V2p<sub>3/2</sub> and O1s of V<sup>5+</sup> and V<sup>4+</sup> are 12.8 and 14.0 eV, respectively, which are in good agreement with reported values of 12.8 and 14.16 eV.<sup>44,45</sup>

BET characterization was carried out to further investigate the porous structure of the synthesized 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes. As it is shown in Fig. 4(c), the  $N_2$  absorption-desorption isotherm belongs to type IV isotherm with H2 hysteresis loop,46 which arises from the presence of relatively uniform pore network and ink-bottle shaped pores.<sup>47</sup> With this isotherm type, capillary condensation at lower adsorbate pressure as well as sharp capillary condensation at higher pressure takes place, indicating that there are abundant mesopores in the 3D mesoporous structure assembled by monoclinic M-phase VO2 nanoflakes.48 From the pore size distribution curve in the inset of Fig. 4(c), the typical pore size is in the range of 2-10 nm. Furthermore, the total porosity of a material can be categorized into three main groups based on pore size. By IUPAC definition, micropores have pore diameters less than 2 nm, mesopores have pore sizes between 2 and 50 nm, and macropores have



Scheme 2 Schematic illustration of the process used for preparation of 3D mesoporous structure assembled by monoclinic M-phase  $VO_2$  nanoflakes based composite film.

Paper



Fig. 6 (a) The surface (the inset shows the photograph of film on the glass), (b) the cross-section SEM images, (c) O element distribution and (d) V element distribution of the 3D mesoporous structure assembled by monoclinic M-phase  $VO_2$  nanoflakes based film.

pore sizes larger than 50 nm.<sup>49</sup> The BET surface area and average mean pore size were 42.7 m<sup>2</sup> g<sup>-1</sup> and 7.8 nm, respectively. Which confirms the mesoporosity of 3D mesoporous structure assembled by M-phase VO<sub>2</sub> nanoflakes.

The pore size distribution curves and N<sub>2</sub> adsorptiondesorption curves of M-phase VO<sub>2</sub> synthesized in the absence of template (monoclinic M-phase VO<sub>2</sub> nanorod) are shown in Fig. 4(d). It can be seen that the adsorption isotherm displays type IV behavior with H2 hysteresis loop.<sup>46</sup> From the pore size distribution curve in the inset of Fig. 4(d), the typical pore size is in the range of 2–10 nm. The BET surface area and average mean pore size of nanorods are 19.8 m<sup>2</sup> g<sup>-1</sup> and 5.8 nm, respectively. It is believed that mesopores are mainly distributed in M-phase VO<sub>2</sub> nanorods, which is consistent with TEM results in Fig. 5(c).

The morphology and microstructure of the monoclinic Mphase VO<sub>2</sub> nanorods were also observed by SEM and TEM, as shown in Fig. 5. The SEM images Fig. 5(a) and (b) reveal that the monoclinic M-phase VO<sub>2</sub> nanorods are randomly oriented with an average diameter of ~120 nm. Besides, the nanorods are loosely interconnected with open spaces existing between them, suggesting the formation of small pores. The TEM image Fig. 5(c) unambiguously reveals that the nanorods are interconnected with each other to form their inner space, which is in good agreement with the SEM observations. Fig. 5(d) shows the HRTEM image of monoclinic M-phase VO<sub>2</sub> nanorods taken from the edge of a single nanorod in Fig. 5(c), the d-spacing of lattice fringe is 0.32 nm, which match well with the (011) lattice plane of monoclinic M-phase VO<sub>2</sub>. This is consistent with the XRD results in Fig. 1.

#### 3.2. The thermochromic characteristics of the films

To investigate the thermochromic properties of thin films, the 3D mesoporous structure assembled by monoclinic M-phase  $VO_2$  nanoflakes were dispersed in ethanol that contained PVP and the suspension was uniformly cast onto a float glass substrate by spin-coating as shown in Scheme 2. It can be seen from Fig. 6(a), the films are transparent, homogeneous and light brownish-yellow in color. The thickness of the film is about 1.1  $\mu$ m Fig. 6(b), which is smaller than that of reported



Fig. 7 Transmittance spectra of films at 20 °C and 90 °C for (a) 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes, (b) M-phase VO<sub>2</sub> nanorods, (c) comparison of 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes and monoclinic M-phase VO<sub>2</sub> nanoflakes, and (d) transmittance spectra of 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes films at different temperatures.

#### Paper

composite films,<sup>1,26</sup> and possesses a high visible light transmittance. To enhance the thermochromic property of the thin film, uniform dispersion of the particles in to the deposited film have crucial effect.<sup>1</sup> Therefore, the uniform distribution of V and O in the 3D mesoporous structure assembled by M-phase VO<sub>2</sub> nanoflakes films have been observed by EDS elemental mapping Fig. 6(c) and (d). The figures show the V and O elements are uniformly distributed in the film without agglomeration, indicating a homogeneous dispersion of 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes in the film.

To further investigate the thermochromic properties of thin films, the UV-vis-NIR transmittance spectra were conducted at different temperatures (Fig. 7). As it is shown in Fig. 7(a), the 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes based composite film exhibited excellent optical properties as compared to that of monoclinic M-phase VO<sub>2</sub> nanorod Fig. 7(b). The calculated optical properties ( $T_{\rm lum}$  and  $\Delta T_{\rm sol}$ ) are summarized and compared with previous reports in Table 1.

The 3D structure and mesoporosity show great effects on the optical properties. The  $T_{lum}$  and  $\Delta T_{sol}$  of 3D mesoporous structure assembled by monoclinic M-phase VO2 nanoflakes films are 67.3% and 12.5% while that of M-phase VO<sub>2</sub> nanorods are 53.2% and 10%, respectively. This is because the 3D structure and porosity offer the better dispersion of flakes with PVP during film preparation (Scheme 2) and thereby enhance thermochromic properties. The high luminous transmittance is crucial for smart window<sup>2</sup> and attributed to the 3D structure and mesoporosity of nanoflakes. The 3D mesoporous structure assembled by monoclinic M-phase VO2 nanoflakes also enables the film to contain enough VO<sub>2</sub> for high solar modulation.<sup>32</sup> From this, the 3D structure and mesoporosity of nanoflakes play a great role in regulating the visible light transmittance and solar modulation ability. The optical properties of M-phase VO<sub>2</sub> nanorod film is also good as compared with previous reports. This is because the loosely interconnected nanorods form small pores without the presence of EF. Fig. 7(c) shows the visible transmittance of 3D mesoporous structure assembled by

monoclinic M-phase VO<sub>2</sub> nanoflakes is higher than M-phase VO<sub>2</sub> nanorods. Fig. 7(d) shows transmittance spectra of 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes films at different temperatures in which a critical temperature ( $T_c$ ) exists between 60 °C and 70 °C. The 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes based composite film exhibit much higher balanced  $T_{lum}$  and  $\Delta T_{sol}$  values than<sup>20,22,28,33</sup> and slightly lower values than that of.<sup>15</sup> The 3D mesoporous structure assembled by M-phase VO<sub>2</sub> nanoflakes based composite film also exhibits higher  $T_{lum}$  and slightly lower  $\Delta T_{sol}$  values.<sup>1,26,29</sup> The ordered monoclinic M-phase VO<sub>2</sub> honeycomb films<sup>2</sup> exhibited higher  $T_{lum}$  but  $\Delta T_{sol}$  was too low. In this regards, 3D mesoporous structure assembled by M-phase VO<sub>2</sub> nanoflakes based composite film exhibited higher  $T_{lum}$  but  $\Delta T_{sol}$  was too low. In this regards, 3D mesoporous structure assembled by M-phase VO<sub>2</sub> nanoflakes based composite film exhibited higher  $T_{lum}$  but  $\Delta T_{sol}$  was too low. In this regards, 3D mesoporous structure assembled by M-phase VO<sub>2</sub> nanoflakes based composite film

# 3.3. Metal-to-insulator transition properties of 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes

The metal-to-insulator transition properties of 3D mesoporous structure assembled by M-phase  $VO_2$  nanoflakes and



Fig. 8 DSC curves of 3D mesoporous structure assembled by monoclinic M-phase  $VO_2$  nanoflakes and monoclinic M-phase  $VO_2$  nanorods.

**Table 1** Comparison between this work and previously reported high luminous transmittance ( $T_{lum}$ ) and solar energy modulation ability ( $\Delta T_{sol}$ ) of VO<sub>2</sub> films

System	$(T_{lum})$ %	$(\Delta T_{ m sol})\%$	Reference
$V_x W_{1-x} O_2(M)$ (a) SiO <sub>2</sub> NP based films	50.6	14.7	1
VO <sub>2</sub> /NLETS hybrid films	73.4	18.2	15
Zr/W-codoped VO <sub>2</sub> NP based films	58.4	12.3	20
$VO_2(M)$ NP based films	62.1	12.4	22
Fine crystalline VO <sub>2</sub> NP based films	45.6	22.0	26
Flexible VO <sub>2</sub> NP based films	54.26	12.34	28
Nanoporous M-phase VO <sub>2</sub> thin films	50.6	14.7	29
Mesoporous SiO <sub>2</sub> /VO <sub>2</sub> films	80.0	10.2	30
Ordered M-phase VO <sub>2</sub> honeycomb films	95.4	5.5	2
$2D VO_2/TiO_2$ nanonet films	64.46	11.82	33
2D patterned M-phase VO <sub>2</sub> nanonet films	46.1	13.2	34
M-phase VO <sub>2</sub> nanorods films	53.2	10	This work
3D mesoporous structure assembled by monoclinic M-phase VO <sub>2</sub> nanoflakes film	67.3	12.5	This work

Table 2 Comparison of phase transition temperature for heating and cooling cycles of 3D mesoporous structure assembled by M-phase VO<sub>2</sub> nanoflakes with previously reported different morphologies

M-phase VO <sub>2</sub> morphology	$T_{\rm c,h}$	$T_{\rm c,c}$	$T_{\rm c}$	$\Delta T$	Reference
Ordered honevcomb	81	59	70	22	2
Star-shaped nanoparticles	68.6	55.2	61.9	13.4	11
Cucumber-like shape	67.5	57.9	62.7	9.6	19
Nanorings	68.75	59.77	64.26	8.98	21
Belt with a rectangular cross-section	66	57	61.5	9	25
Nanobelts	68.9	62.44	65.67	6.46	11
Nanorods	68.2	59.6	63.9	8.6	This work
3D assembled by nanoflakes	66.6	59.7	63.15	6.9	This work

monoclinic M-phase VO2 nanorod was determined by differential scanning calorimeter (DSC). As shown in Fig. 8, both DSC curves exhibit a clear endothermic peak and an exothermic peak corresponding to a reversible phase transition between M-phase and R-phase. The endothermic transition temperature  $(T_{c,h})$ during heating cycles was observed at 66.6 °C and an exothermic transition temperature  $(T_{c,c})$  during cooling cycles was observed at 59.7 °C for 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes. So, the phase transition temperature of 63.15 °C is calculated by  $T_{\rm c} = (T_{\rm c,h} + T_{\rm c,c})/2^{37}$ which is lower than 63.9 °C for M-phase VO<sub>2</sub> nanorods, ordered honeycomb,<sup>2</sup> nanorings,<sup>21</sup> nanobelts<sup>11</sup> and 68 °C for the bulk. The hysteresis width ( $\Delta T = T_{c,h} - T_{c,c}$ ) of 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes is 6.9 °C, which is much lower than previously reported values<sup>2,11,19,21,25</sup> and also lower than that of M-phase VO<sub>2</sub> nanorod 8.6 °C, but slightly higher than that of nanobelts.<sup>11</sup> This reduction of T<sub>c</sub> by 3D mesoporous structure assembled by Mphase VO<sub>2</sub> nanoflakes is due to the uniform dispersion of VO<sub>2</sub>. Table 2 summarizes phase transition temperature for heating and cooling cycles of M-phase VO2 with different morphologies. However to get a further reduction of  $T_c$  modification of morphology,<sup>50</sup> size,<sup>51</sup> defect,<sup>52</sup> interfacial effect,<sup>11</sup> Stress,<sup>52</sup> and phase purity<sup>53</sup> have been reported. Particularly doping of metals such as W,54-57 Mo,57,58 and Nb57,58 were reported for the reduction of  $T_{\rm c}$ . Hence, synthesis materials with optimum  $T_{\text{lum}}$ ,  $T_{\text{sol}}$ , and  $T_{\text{c}}$  values for practical thermochromic applications are required.

### 4. Conclusion

In conclusion, 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes with pore size of about 2–10 nm were synthesized by a facile hydrothermal method at temperature of 180 °C using *Ensete ventricosum* fiber (EF) as a template. The EF facilitates the 3D structure and pore formation in the VO<sub>2</sub> nanoflakes and thus enhances thermochromic properties. The composite film obtained from 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes with PVP exhibited excellent thermochromic properties: a high luminous transmittance ( $T_{lum} = 67.3\%$ ) and high solar modulation efficiency ( $\Delta T_{sol} = 12.5\%$ ), as well as a low phase transition temperature of ( $T_c = 63.15$  °C) which is lower than bulk (68 °C). In comparison, the M-phase VO<sub>2</sub> nanorod film exhibits inferior luminous transmittance and solar modulation efficiency as well as a relatively high phase transition temperature. The excellent thermochromic properties of 3D mesoporous structure assembled by M-phase VO<sub>2</sub> nanoflakes film compared with M-phase VO<sub>2</sub> nanorods as well as previous reports is to attributed to 3D structure and mesoporosity. Besides, the 3D mesoporous structure assembled by monoclinic M-phase VO<sub>2</sub> nanoflakes possesses a comparatively lower  $T_c$  and a narrower thermal hysteresis width compared with other monoclinic M-phase VO<sub>2</sub> materials. Therefore, this green route opens the path for synthesis of 3D structure in VO<sub>2</sub> and its application in smart windows.

# Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This work was supported by the 111 project (B18038) and the National Natural Science Foundation of China (Grant No. 51772229 and 51461135004). We also thank the Analytical and Testing Center of WUT for the help with carrying out XRD, TEM, and FESEM analyses.

## References

- 1 J. Zhu, Y. Zhou, B. Wang, J. Zheng, S. Ji, H. Yao, H. Luo and P. Jin, *ACS Appl. Mater. Interfaces*, 2015, 7, 27796–27803.
- 2 M. Liu, B. Su, Y. V. Kaneti, Z. Chen, Y. Tang, Y. Yuan, Y. Gao, L. Jiang, X. Jiang and A. Yu, *ACS Nano*, 2016, **11**, 407–415.
- 3 D. Cao, C. Xu, W. Lu, C. Qin and S. Cheng, *Sol. RRL*, 2018, 2, 1870163.
- 4 D. Ge, E. Lee, L. Yang, Y. Cho, M. Li, D. S. Gianola and S. Yang, *Adv. Mater.*, 2015, 27, 2489–2495.
- 5 C. Sol, J. Schläfer, I. P. Parkin and I. Papakonstantinou, *Sci. Rep.*, 2018, **8**, 13249.
- 6 Q. Hao, W. Li, H. Xu, J. Wang, Y. Yin, H. Wang, L. Ma, F. Ma,
   X. Jiang and O. G. Schmidt, *Adv. Mater.*, 2018, 30, 1705421.
- 7 Y. Ke, I. Balin, N. Wang, Q. Lu, A. I. Y. Tok, T. J. White, S. Magdassi, I. Abdulhalim and Y. Long, *ACS Appl. Mater. Interfaces*, 2016, **8**, 33112–33120.
- 8 E. Strelcov, A. V. Davydov, U. Lanke, C. Watts and A. Kolmakov, *ACS Nano*, 2011, 5, 3373–3384.

- 9 A. Hendaoui, N. Émond, S. Dorval, M. Chaker and E. Haddad, Sol. Energy Mater. Sol. Cells, 2013, 117, 494–498.
- 10 S. Wang, K. A. Owusu, L. Mai, Y. Ke, Y. Zhou, P. Hu, S. Magdassi and Y. Long, *Appl. Energy*, 2018, **211**, 200–217.
- 11 L. Zhong, M. Li, H. Wang, Y. Luo, J. Pan and G. Li, CrystEngComm, 2015, 17, 5614-5619.
- 12 H. Kim, Y. Kim, K. S. Kim, H. Y. Jeong, A.-R. Jang, S. H. Han, D. H. Yoon, K. S. Suh, H. S. Shin and T. Kim, *ACS Nano*, 2013, 7, 5769–5776.
- 13 S. Wang, M. Liu, L. Kong, Y. Long, X. Jiang and A. Yu, Prog. Mater. Sci., 2016, 81, 1–54.
- 14 Y. Ke, C. Zhou, Y. Zhou, S. Wang, S. H. Chan and Y. Long, *Adv. Funct. Mater.*, 2018, 28, 1800113.
- 15 J. Zhu, A. Huang, H. Ma, Y. Chen, S. Zhang, S. Ji, S. Bao and P. Jin, *New J. Chem.*, 2017, **41**, 830–835.
- 16 Y. Gao, H. Luo, Z. Zhang, L. Kang, Z. Chen, J. Du, M. Kanehira and C. Cao, *Nano Energy*, 2012, 1, 221–246.
- 17 M. E. Warwick and R. Binions, J. Mater. Chem. A, 2014, 2, 3275–3292.
- 18 C. Yin, R. Zhang, G. Qian, Q. Fu, C. Li, M. Wang, C. Zhu, L. Wang, S. Yuan and X. Zhao, *Appl. Phys. Lett.*, 2017, **110**, 172404.
- 19 Z. Song, L. Zhang, F. Xia, N. A. Webster, J. Song, B. Liu, H. Luo and Y. Gao, *Inorg. Chem. Front.*, 2016, 3, 1035–1042.
- 20 N. Shen, S. Chen, Z. Chen, X. Liu, C. Cao, B. Dong, H. Luo, J. Liu and Y. Gao, *J. Mater. Chem. A*, 2014, 2, 15087–15093.
- 21 M. Li, F. Kong, Y. Zhang and G. Li, *CrystEngComm*, 2011, 13, 2204–2207.
- 22 H. Zhang, X. Xiao, X. Lu, G. Chai, Y. Sun, Y. Zhan and G. Xu, *J. Alloys Compd.*, 2015, **636**, 106–112.
- 23 M. Kamalisarvestani, R. Saidur, S. Mekhilef and F. Javadi, *Renewable Sustainable Energy Rev.*, 2013, **26**, 353–364.
- 24 Y. Chen, X. Zeng, J. Zhu, R. Li, H. Yao, X. Cao, S. Ji and P. Jin, *ACS Appl. Mater. Interfaces*, 2017, **9**, 27784–27791.
- 25 Y. Zhang, Y. Huang, J. Zhang, W. Wu, F. Niu, Y. Zhong, X. Liu, X. Liu and C. Huang, *Mater. Res. Bull.*, 2012, 47, 1978–1986.
- 26 Z. Chen, Y. Gao, L. Kang, C. Cao, S. Chen and H. Luo, J. Mater. Chem. A, 2014, 2, 2718–2727.
- 27 L. Kang, Y. Gao, H. Luo, Z. Chen, J. Du and Z. Zhang, ACS Appl. Mater. Interfaces, 2011, 3, 135–138.
- 28 D. Guo, C. Ling, C. Wang, D. Wang, J. Li, Z. Zhao, Z. Wang, Y. Zhao, J. Zhang and H. Jin, ACS Appl. Mater. Interfaces, 2018, 10, 28627–28634.
- 29 X. Cao, N. Wang, J. Y. Law, S. C. J. Loo, S. Magdassi and Y. Long, *Langmuir*, 2014, **30**, 1710–1715.
- 30 J. Zhang, J. Wang, C. Yang, H. Jia, X. Cui, S. Zhao and Y. Xu, Sol. Energy Mater. Sol. Cells, 2017, 162, 134–141.
- 31 F. Xu, X. Cao, H. Luo and P. Jin, *J. Mater. Chem. C*, 2018, 6, 1903–1919.
- 32 S. Wu, S. Tian, B. Liu, H. Tao, X. Zhao, R. Palgrave, G. Sankar and I. Parkin, *Sol. Energy Mater. Sol. Cells*, 2018, **176**, 427– 434.
- 33 D. Guo, Z. Zhao, J. Li, J. Zhang, R. Zhang, Z. Wang, P. Chen, Y. Zhao, Z. Chen and H. Jin, *Cryst. Growth Des.*, 2017, 17, 5838–5844.

- 34 Y. Ke, X. Wen, D. Zhao, R. Che, Q. Xiong and Y. Long, ACS Nano, 2017, 11, 7542–7551.
- 35 X. Qian, N. Wang, Y. Li, J. Zhang, Z. Xu and Y. Long, Langmuir, 2014, **30**, 10766–10771.
- 36 T. Chang, X. Cao, L. R. Dedon, S. Long, A. Huang, Z. Shao, N. Li, H. Luo and P. Jin, *Nano Energy*, 2018, 44, 256–264.
- 37 J. Zhang, H. Tian, L. Hao, X. Jin, C. Yang, J. Wang, X. Cui,
  C. Wang, C. Zhang and C. Zhang, *J. Mater. Chem. C*, 2016,
  4, 5281–5288.
- 38 K. Laaksonen, S.-Y. Li, S. Puisto, N. Rostedt, T. Ala-Nissila, C.-G. Granqvist, R. Nieminen and G. A. Niklasson, Sol. Energy Mater. Sol. Cells, 2014, 130, 132–137.
- 39 A. Taylor, I. Parkin, N. Noor, C. Tummeltshammer, M. S. Brown and I. Papakonstantinou, *Opt. Express*, 2013, 21, A750–A764.
- 40 Q. Lu, C. Liu, N. Wang, S. Magdassi, D. Mandler and Y. Long, J. Mater. Chem. C, 2016, 4, 8385–8391.
- 41 R. Purbia, R. Borah and S. Paria, *Inorg. Chem.*, 2017, 56, 10107–10116.
- 42 J. Huang, N. Matsunaga, K. Shimanoe, N. Yamazoe and T. Kunitake, *Chem. Mater.*, 2005, **17**, 3513–3518.
- 43 S. Liang, Q. Shi, H. Zhu, B. Peng and W. Huang, ACS Omega, 2016, 1, 1139–1148.
- 44 G. Silversmit, D. Depla, H. Poelman, G. B. Marin and R. De Gryse, *J. Electron Spectrosc. Relat. Phenom.*, 2004, **135**, 167–175.
- 45 M. Wan, B. Liu, S. Wang, L. Hu, Y. He, H. Tao and X. Zhao, *J. Alloys Compd.*, 2017, **706**, 289–296.
- 46 M. Chen, Y. Zhang, Y. Liu, Q. Wang, J. Zheng and C. Meng, ACS Appl. Energy Mater., 2018, 1, 5527–5538.
- 47 J. Li, X. Liu, W. Zhan, Y. Guo, Y. Guo and G. Lu, *Catal. Sci. Technol.*, 2016, 6, 897–907.
- 48 Y. Zhang, X. Liu and J. Huang, ACS Appl. Mater. Interfaces, 2011, 3, 3272–3275.
- 49 J. V. D. Perez, E. T. Nadres, H. N. Nguyen, M. L. P. Dalida and D. F. Rodrigues, *RSC Adv.*, 2017, 7, 18480–18490.
- 50 S. R. Popuri, A. Artemenko, C. Labrugere, M. Miclau, A. Villesuzanne and M. Pollet, *J. Solid State Chem.*, 2014, 213, 79–86.
- 51 M. Wang, Z. Cui, Y. Xue and R. Zhang, *Cryst. Growth Des.*, 2018, **18**, 4220–4225.
- 52 M. Li, X. Wu, L. Li, Y. Wang, D. Li, J. Pan, S. Li, L. Sun and G. Li, *J. Mater. Chem. A*, 2014, **2**, 4520–4523.
- 53 E. U. Donev, R. Lopez, L. C. Feldman and R. F. Haglund Jr, *Nano Lett.*, 2009, 9, 702–706.
- 54 Y. Liu, H. Tao, X. Chu, M. Wan, J. Bao and X. Zhao, *J. Non. Cryst. Solids*, 2014, **383**, 116–120.
- 55 Z. Liang, L. Zhao, W. Meng, C. Zhong, S. Wei, B. Dong, Z. Xu, L. Wan and S. Wang, *J. Alloys Compd.*, 2017, **694**, 124–131.
- 56 V. Martínez-Landeros, N. Hernandez-Como, G. Gutierrez-Heredia, M. A. Quevedo-López and F. Aguirre-Tostado, *Thin Solid Films*, 2019, 682, 24–28.
- 57 C. Batista, R. M. Ribeiro and V. Teixeira, *Nanoscale Res. Lett.*, 2011, 6, 1–7.
- 58 T. D. Manning, I. P. Parkin, C. Blackman and U. Qureshi, J. Mater. Chem., 2005, 15, 4560–4566.

Paper