

CORRECTION

[View Article Online](#)
[View Journal](#) | [View Issue](#)

Cite this: *RSC Adv.*, 2021, 11, 36587

DOI: 10.1039/d1ra90166d

rsc.li/rsc-advances

Correction: The corrosion behaviors of multilayer diamond-like carbon coatings: influence of deposition periods and corrosive medium

Mingjun Cui,^{ac} Jibin Pu,^b Guangan Zhang,^a Liping Wang^{*ab} and Qunji Xue^{*ab}

Correction for 'The corrosion behaviors of multilayer diamond-like carbon coatings: influence of deposition periods and corrosive medium' by Mingjun Cui *et al.*, *RSC Adv.*, 2016, 6, 28570–28578, DOI: 10.1039/C6RA05527C.

The authors regret that an incorrect version of Fig. 3 was included in the original article. The correct version of Fig. 3 is shown below.




Fig. 3 SEM images of surface morphology of multilayer DLC coatings. (a) 5 deposition periods, (b) 12 deposition periods, (c) 15 deposition periods, (d) 20 deposition periods.

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

^aState Key Laboratory of Solid Lubrication, Lanzhou Institute of Chemical Physics, Chinese Academy of Sciences, Lanzhou 730000, China. E-mail: lpwang@licp.cas.cn; qjxue@lzb.ac.cn; Fax: +86 931 4968163; Tel: +86 931 4968080

^bKey Laboratory of Marine Materials and Related Technologies, Ningbo Institute of Materials Technology and Engineering, Chinese Academy of Sciences, Ningbo 315201, China

^cUniversity of Chinese Academy of Sciences, Beijing 100039, China

