Chemical Science

EDGE ARTICLE

Check for updates

Cite this: Chem. Sci., 2021, 12, 4981

All publication charges for this article have been paid for by the Royal Society of Chemistry

Received 8th January 2021 Accepted 19th February 2021

DOI: 10.1039/d1sc00127b

rsc.li/chemical-science

Introduction

Polymer networks can be obtained by covalent interconnection of discrete metal-organic assemblies (macrocycles or cages) with organic linkers.^{1,2} Two main synthetic strategies have been explored in this context: (a) the post-synthetic cross-linking of assemblies featuring reactive sites/groups in their periphery,³⁻⁷ and (b) the utilization of polymer-linked ligands during the selfassembly process.8-11 The incorporation of metal-based assemblies into polymer networks can lead to materials with interesting properties. For example, a hydrogel containing tetranuclear Fe cages was found to display sorption properties, which reflect the host-guest chemistry of the Fe cage.8 Similarly, by cross-linking of porous Rh cages, it was possible to obtain materials with permanent porosity.3 The utilization of cages as nodes in polymer networks is also interesting in terms of network topology, because cage junctions can act as highly connected nodes.11 Another noteworthy feature of metal-based junctions is the fact that they can be altered or cleaved with appropriate stimuli.⁸⁻¹⁰ Light is a particularly interesting stimulus, because it allows remote manipulation with high spatial and temporal control.12 First studies about light-induced modifications of cage-containing polymer networks were recently published by Johnson and co-workers. They have shown that networks containing Cu₂₄L₂₄-type cages can be cleaved by photochemical reduction of the Cu(II) centers to Cu(I), resulting in a gel-sol transition.9 The inverse process could be induced by re-oxidation with O_2 . Furthermore, they have reported a system, where irradiation allows converting macrocyclic Pd₃L₆ junctions reversibly into Pd₂₄L₄₈ cage junctions.10 The light sensitivity was achieved by using polymeric

Institut des Sciences et Ingénierie Chimiques, École Polytechnique Fédérale de Lausanne (EPFL), 1015 Lausanne, Switzerland. E-mail: kay.severin@epfl.ch

© 2021 The Author(s). Published by the Royal Society of Chemistry

Light-induced assembly and disassembly of polymers with Pd_nL_{2n} -type network junctions[†]

Ru-Jin Li, Cristian Pezzato, D Cesare Berton D and Kay Severin *

Polymers containing Pd_nL_{2n} complexes as network junctions were obtained by reaction of poly(ethylene glycol)-linked N-donor ligands with Pd^{2+} . The addition of a metastable state photoacid renders the networks light sensitive, and gel-sol transitions can be achieved by irradiation with light. The inverse process, a light-induced sol-gel transition, was realized by using a molecularly defined Pd complex as an acid-sensitive reservoir for Pd^{2+} . Upon irradiation, Pd^{2+} ions are released, allowing the formation of an acid-resistant polymer network. Both the gel-sol and the sol-gel transitions are reversed in the dark.

ligands containing photochromic dithienylethene groups. Below, we describe a new approach for rendering Pd-based polymer networks photosensitive. Importantly, our approach allows both the light-induced destruction of polymer networks and the light-induced formation of polymer networks without accumulation of 'chemical waste'.¹³

Results and discussion

The study described herein was inspired by our recent observation¹⁴ that the assembly of certain metal–organic cages can be controlled with light if the merocyanine-based photoacid **PAH**¹⁵ (Scheme 1) is added to the mixture.

Upon irradiation with blue light, **PAH** undergoes a ringclosure reaction, liberating a proton.¹⁶ The increased acidity can lead to the disassembly of metal–organic cages if they contain acid-sensitive metal–ligand bonds. Importantly, cages containing more basic ligands display an increased susceptibility for an acid-induced cleavage.¹⁷ In the dark, the process is reversed, and metal–ligand interactions are re-established.

In order to investigate if a photoacid can be used to control the assembly and disassembly of cage- and macrocycle-



Scheme 1 The photoacid PAH allows controlling the assembly of metal-organic cages.

ROYAL SOCIETY

OF CHEMISTRY

[†] Electronic supplementary information (ESI) available: Containing synthetic procedures and experimental details. See DOI: 10.1039/d1sc00127b

Chemical Science

containing polymer networks, we have prepared the tetratopic N-donor ligands L1–L4 (Scheme 2). All ligands feature a poly(ethylene glycol) spacer with an average molecular weight of M_n = 4600. The design of these ligands was inspired by work of Johnson and co-workers, who have used structural analogues of L2 and L3 for the assembly of networks with Pd₂L₄ and Pd₁₂L₂₄ cage junctions.^{11b,c} Ligand L1 features additional alkynyl spacers, which renders the terminal 3-pyridyl group less basic than the pyridyl groups of L2 and L3. Ligand L4, on the other hand, shows more basic imidazolyl donor groups (for details, see the ESI†).

The geometry of the terminal pyridyl groups of L1 favors the formation of Pd_2L_4 -type metal–organic cages.¹⁸ Upon mixing of $[Pd(CH_3CN)_4](BF_4)_2$ (1 equiv.) with L1 (1 equiv.) in acetonitrile, an opaque gel was immediately obtained. The mixture was then tempered at 70 °C for 4 h to ensure the formation of a polymer network (P1) with intact Pd_2L_4 junctions. The gels P2–P4 were prepared in an analogous fashion. Based on literature reports^{19–21} and our own control experiments (see the ESI†), we expected the presence of Pd_2L_4 links with some $Pd_2L_3X_2$ defects^{22,23} for P2, $Pd_{12}L_{24}$ cage junctions for P3, and a mixture of macrocyclic Pd_3L_6 and Pd_4L_8 junctions for P4.

The polymers **P1–P4** were characterized by NMR spectroscopy, scanning electron microscopy (SEM), and rheology measurements (for details, see ESI†). Selected data are depicted in Fig. 1. The ¹H magic angle spinning (MAS) NMR spectrum of **P1** shows six broad signals in the aromatic region, which are shifted downfield with respect to those of **L1** (Fig. 1a). It was possible to obtain a standard solution-based ¹H NMR spectrum of **P1** when the reaction between **L1** and [Pd(CH₃CN)₄](BF₄)₂ was performed under dilute conditions. The resulting spectrum was similar to what was obtained for the gel by MAS NMR. The SEM image of dried **P1** shows a three-dimensional cross-linked structure (Fig. 1b). Rheology measurements were used to assess the mechanical properties of **P1–P4**. The storage modulus (*G*') increases in the order **P2** < **P1** < **P3** < **P4**. Two factors are expected to contribute to the observed differences:



Scheme 2 Polymers P1–P4 with Pd_nL_{2n} -type network junctions are formed upon mixture of the N-donor ligands L1–L4 with $[Pd(CH_3-CN)_4](BF_4)_2$ in CH₃CN.



Fig. 1 (a) Aromatic region of the ¹H NMR spectra (400 MHz, CD₃CN) of L1 (bottom), P1 in dilute solution (middle), and ¹H MAS NMR spectrum of gel P1 (top); (b) SEM image of P1; (c) rheology data for P1–P4.

the cross-link density,^{10,11} and the strength of the metal–ligand bond. The latter is related to the basicity of the ligands. An alternative measure for the donor strengths of a ligand is the Huynh Electronic Parameter (HEP).²⁴ We have determined the HEP parameter for close analogues of **L1–L4** (lacking the polymer linker), and the data confirmed that the relative donor capability of the ligands is in line with the ligand basicity (see the ESI†). The high G' value observed for **P4** is probably a reflection of the strong Pd–N bonds in the Pd₃L₆ and Pd₄L₈ assemblies. On the other hand, the donor strength of the ligand can be compensated by other factors (*e.g.* anion effects),²³ as evidenced by the higher G' value of **P1** when compared to what is found for **P2**.

The acid sensitivity of **P1–P4** was examined with trifluoroacetic acid (TFA). After addition of TFA (4 equiv. per N-donor group) and heating at 70 °C for 1 h, a gel–sol transition was observed for **P2–P4**, but not for **P1**. The higher acid resistance of **P1** is likely related to the low basicity of **L1**. Having established that acid-induced gel–sol transitions are possible, we subsequently performed test experiments with photoacid **PAH**. Unfortunately, **PAH** was not sufficiently soluble in CH₃CN to perform photoswitching experiments. Therefore, we have prepared the new photoacid **PAH**'(BF₄) featuring a neutral –(CH₂)₂–OH side chain instead of the anionic –(CH₂)₃–SO₃⁻ side chain of **PAH** (Fig. 2a). **PAH**'(BF₄) turned out to be soluble in CH₃CN.

An excess of **PAH**'(BF₄) was added to the respective gel (≥ 2 equiv. per donor group), and the mixture was homogenized by agitation with a vortex mixer. When the samples were irradiated with blue light (456 nm) for 1 h, we observed a similar behavior as for TFA additions: all gels were transformed to solutions except **P1**. The gel–sol transition could be reversed by heating the solutions in the dark for 2 h. The cycle was repeated another 4 times without noticeable difference in behavior.



Fig. 2 (a) Structure of the photoacid PAH'(BF₄), and (b) reversible gelsol transition of the polymer networks P2–P4. Polymer P1 contains acid-resistant network junctions, and is therefore not affected by light.

The results obtained with **PAH**'(BF₄) showed that it is possible to use a photoacid for the light-triggered disassembly of polymers with Pd_nL_{2n} network junctions. Next, we set out to explore a more challenging task: the acid-induced assembly of Pd-based networks. In view of the good acid resistance of **P1**, we hypothesized that it might be possible to achieve the assembly of **P1** from **L1** and Pd^{2+} under acidic conditions. The prerequisite would be a source of Pd, which would liberate Pd^{2+} only under acidic conditions.

Previously, we had shown that metalloligand L5 (Fig. 3) forms hexanuclear Pd complexes of the formula $[Pd_6(L5)_{12}]^{12^+,2^5}$ The two pyridyl groups of L5 are highly basic, rendering the Pd assembly sensitive to acid.¹⁴ Consequently, $[Pd_6(L5)_{12}]^{12+}$ represents a reservoir for Pd²⁺, with metal ions being released under acidic conditions.

When a mixture of L1 (1 equiv.), L5 (2 equiv.) and $[Pd(CH_3-CN)_4](BF_4)_2$ (1 equiv.) in CD₃CN was equilibrated at 70 °C for 3 h, a dark red solution was obtained. Inspection of this solution by NMR spectroscopy revealed the formation $[Pd_6(L5)_{12}]^{12+}$ along



Fig. 3 Light-induced assembly of the Pd-based polymer network P1 is achieved by irradiation of a mixture of L1, $[Pd_6(L5)_{12}]^{12+}$, and PAH'(BF₄). The hexanuclear complex $[Pd_6(L5)_{12}]^{12+}$ acts as an acid-sensitive reservoir for Pd²⁺, enabling the formation of P1 under acidic conditions. The sol-gel transition can be reversed by heating the sample in the dark.

with 'free' polymer ligand L1. The preferential complexation of L5 over L1 can be explained by the higher donor strength of the former. When TFA (2 equiv. per total N-donor groups) was added, the mixture gradually converted to a gel when annealed at 70 °C for 2 h.

Next, we have performed a similar experiment using photoacid **PAH**'(BF₄) instead of TFA. After irradiation of the sample with blue light at 50 °C for 11 h, we observed the formation of a gel (Fig. 3). The network could be cleaved by keeping the sample in the dark at 70 °C for 7 h. A light induced sol-gel transition followed by a heat-induced gel-sol transition cycle could be repeated 4 times without noticeable difference.

Conclusions

To conclude, we have demonstrated that the photoacid $PAH'(BF_4)$ can be used for the light-controlled assembly and disassembly of Pd-based polymers networks. Light-induced gelsol transitions were achieved by using acid-sensitive Pd_nL_{2n} network junctions. For realizing the inverse process, the lightinduced formation of a metallogel, we have employed a hexanuclear Pd cage as an acid-sensitive reservoir for Pd²⁺. The relative basicity of the polymeric N-donor ligand is a key parameter for both processes, because the ligand basicity controls the acid-sensitivity of the polymer network. Another important factor is the pH range, which can be accessed with the photoacid. The metastable state acidity of $PAH'(BF_4)$ is suited to cleave Pd-N bonds. In principle, it should be possible to use photoacids for the light-controlled cleavage of other types of metal-ligand assemblies. However, it might be necessary to use - or develop - photoacids with different properties in order to achieve a reversible cleavage of the respective metal-ligand bond. Investigations in this direction are ongoing in our laboratory.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The work was supported by the Swiss National Science Foundation (SNSF "Ambizione" PZ00P2_180008), and by the École Polytechnique Fédérale de Lausanne (EPFL). We thank Dr Daniel Ortiz for measuring mass spectra and Dr Claudia Avalos for help with MAS NMR spectroscopy measurements.

References

- (a) P. Sutar and T. K. Maji, *Dalton Trans.*, 2020, **49**, 7658–7672; (b) V. J. Pastore and T. R. Cook, *Chem. Mater.*, 2020, **32**, 3680–3700; (c) Y. Gu, J. Zhao and J. A. Johnson, *Angew. Chem., Int. Ed.*, 2020, **59**, 5022–5049; (d) K. C. Bentz and S. M. Cohen, *Angew. Chem., Int. Ed.*, 2018, **57**, 14992–15001.
- 2 The interconnection of metal-based macrocycles and cages *via* non-covalent interactions has also been explored. For reviews, see: (*a*) B. Li, T. He, Y. Fan, X. Yuan, H. Qiu and

Chemical Science

S. Yin, *Chem. Commun.*, 2019, **55**, 8036–8059; (b) Y. Sun, C. Chen and P. J. Stang, *Acc. Chem. Res.*, 2019, **52**, 802–817; (c) L. J. Chen and H. B. Yang, *Acc. Chem. Res.*, 2018, **51**, 2699–2710; (d) S. Datta, M. L. Saha and P. J. Stang, *Acc. Chem. Res.*, 2018, **51**, 2047–2063.

- 3 (a) A. Legrand, G. A. Craig, M. Bonneau, S. Minami, K. Urayama and S. Furukawa, *Chem. Sci.*, 2019, 10, 10833– 10842; (b) A. Carné-Sánchez, G. A. Craig, P. Larpent, V. Guillerm, K. Urayama, D. Maspoch and S. Furukawa, *Angew. Chem., Int. Ed.*, 2019, 58, 6347–6350; (c) A. Carné-Sánchez, G. A. Craig, P. Larpent, T. Hirose, M. Higuchi, S. Kitagawa, K. Matsuda, K. Urayama and S. Furukawa, *Nat. Commun.*, 2018, 9, 1–8.
- 4 G. Lal, M. Derakhshandeh, F. Akhtar, D. M. Spasyuk, J.-B. Lin, M. Trifkovic and G. K. H. Shimizu, *J. Am. Chem. Soc.*, 2019, **141**, 1045–1053.
- 5 J. Liu, W. Duan, J. Song, X. Guo, Z. Wang, X. Shi, J. Liang, J. Wang, P. Cheng, Y. Chen, M. J. Zawarotko and Z. Zhang, *J. Am. Chem. Soc.*, 2019, **141**, 12064–12070.
- 6 X.-Y. Xie, F. Wu, X. Liu, W.-Q. Tao, Y. Jiang, X.-Q. Liu and L.-B. Sun, *Chem. Commun.*, 2019, 55, 6177–6180.
- 7 S.-Q. Deng, D.-M. Li, X.-J. Mo, Y.-L. Miao, S.-L. Cai, J. Fan, W.-G. Zhang and S.-R. Zheng, *ChemPlusChem*, 2020, DOI: 10.1002/cplu.202000570.
- 8 J. A. Foster, R. M. Parker, A. M. Belenguer, N. Kishi, S. Sutton,
 C. Abell and J. R. Nitschke, *J. Am. Chem. Soc.*, 2015, 137, 9722–9729.
- 9 N. J. Oldenhuis, K. P. Qin, S. Wang, H. Z. Ye, E. A. Alt, A. P. Willard, T. Van Voorhis, S. L. Craig and J. A. Johnson, *Angew. Chem., Int. Ed.*, 2020, **59**, 2784–2792.
- 10 Y. Gu, E. A. Alt, H. Wang, X. Li, A. P. Willard and J. A. Johnson, *Nature*, 2018, **560**, 65–69.
- 11 (a) Y. Wang, Y. Gu, E. G. Keeler, J. V. Park, R. G. Griffin and J. A. Johnson, Angew. Chem., Int. Ed., 2017, 56, 188–192; (b) A. V. Zhukhovitskiy, M. Zhong, E. G. Keeler, V. K. Michaelis, J. E. P. Sun, M. J. A. Hore, D. J. Pochan, R. G. Griffin, A. P. Willard and J. A. Johnson, Nat. Chem., 2016, 8, 33–41; (c) A. V. Zhukhovitskiy, J. Zhao, M. Zhong, E. G. Keeler, E. A. Alt, P. Teichen, R. G. Griffin, M. J. A. Hore, A. P. Willard and J. A. Johnson, Macromolecules, 2016, 49, 6896–6902.

- 12 (a) L. Li, J. M. Scheiger and P. A. Levkin, Adv. Mater., 2019, 31, 1807333; (b) Q. Zhang, D.-H. Qu and H. Tian, Adv. Opt. Mater., 2019, 7, 1–18; (c) E. R. Draper and D. J. Adams, Chem. Commun., 2016, 52, 8196–8206; (d) G. L. Fiore, S. J. Rowan and C. Weder, Chem. Soc. Rev., 2013, 42, 7278–7288.
- 13 M. Weißenfels, J. Gemena and R. Klajn, *Chem*, 2021, 7, 23–27.
- 14 S. M. Jansze, G. Cecot and K. Severin, *Chem. Sci.*, 2018, 9, 4253–4257.
- 15 (a) Y. Liao, Acc. Chem. Res., 2017, 50, 1956–1964; (b) Z. Shi,
 P. Peng, D. Strohecker and Y. Liao, J. Am. Chem. Soc., 2011,
 133, 14699–14703.
- 16 For a detailed mechanistic investigation of this process, see:
 C. Berton, D. M. Busiello, S. Zamuner, E. Solari, R. Scopelliti,
 F. Fadaei-Tirani, K. Severin and C. Pezzato, *Chem. Sci.*, 2020,
 11, 8547–8468.
- 17 S. M. Jansze and K. Severin, *J. Am. Chem. Soc.*, 2019, **141**, 815–819.
- 18 D. P. August, G. S. Nichol and P. J. Lusby, Angew. Chem. Int. Ed., 2016, 55, 15022–15026.
- 19 Y. Wang, M. Zhong, J. V. Park, A. V. Zhukhovitskiy, W. Shi and J. A. Johnson, *J. Am. Chem. Soc.*, 2016, **138**, 10708–10715.
- 20 M. Tominaga, K. Suzuki, M. Kawano, T. Kusukawa, T. Ozeki, S. Sakamoto, K. Yamaguchi and M. Fujita, *Angew. Chem., Int. Ed.*, 2004, 43, 5621–5625.
- 21 D. Samanta and P. S. Mukherjee, *Chem. Eur. J.*, 2014, **20**, 12483–12492.
- 22 B. Chen, J. J. Holstein, S. Horiuchi, W. G. Hiller and G. H. Clever, J. Am. Chem. Soc., 2019, 141, 8907–8913.
- 23 Apparently, the formation of Pd₂L₄ links is compromised when using [Pd(CH₃CN)₄](BF)₂ instead of Pd(NO₃)₂ (see ref. 11*b*). For anion effects during the formation of Pd₂L₄ complexes, see: T. Tateishi, S. Takahashi, A. Okazawa, V. Martî-Centelles, J. Wang, T. Kojima, P. J. Lusby, H. Sato and S. Hiraoka, *J. Am. Chem. Soc.*, 2019, **141**, 19669–19676.
- 24 Q. Teng and H. V. Huynh, Dalton Trans., 2017, 46, 614-627.
- 25 M. D. Wise, J. J. Holstein, P. Pattison, C. Besnard, E. Solari, R. Scopelliti, G. Bricogne and K. Severin, *Chem. Sci.*, 2015, 6, 1004–1010.