# **RSC** Advances



View Article Online

View Journal | View Issue

# PAPER

Check for updates

Cite this: RSC Adv., 2022, 12, 9883

Received 28th January 2022 Accepted 6th March 2022

DOI: 10.1039/d2ra00595f

rsc.li/rsc-advances

## Introduction

Solar energy is a renewable and clean energy source that can be used in the field of solar cells. In the early years, perovskites were considered to be one of the most promising solar cell materials.<sup>1</sup> Three-dimensional (3D) lead halide perovskites have been innovatively applied in the field of solar cells with power conversion efficiency (PCE) up to 25.6%.<sup>2</sup> The high PCE of 3D lead halide perovskites is because of their excellent photoelectric properties, such as high carrier mobility, large light absorption coefficient, long carrier diffusion length and strong photoluminescence.<sup>3,4</sup> Although the three-dimensional lead halide perovskites have great photoelectric properties, their instability in air limits their widespread use for

# Optoelectronic properties and interfacial interactions of two-dimensional $Cs_2PbX_4-MSe_2$ (M = Mo, W) heterostructures

Ying Jie Chen,<sup>ab</sup> Xue Li,<sup>b</sup> Bao Nan Jia,<sup>b</sup> Chao Dong,<sup>b</sup> Xiao Ning Guan, <sup>b</sup> \*<sup>bd</sup> Xin Zhao<sup>a</sup> and Li Hong Han\*<sup>abc</sup>

Constructing 2D inorganic perovskites and TMDs heterostructures is an effective method to design stable and high-performance perovskites optoelectronic applications. Here, we investigate the optoelectronic properties and interfacial interactions of  $Cs_2PbX_4-MSe_2$  (X = Cl, Br, I; M = Mo, W) heterostructures using first-principles calculations. Firstly, six Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> interfaces remain stable in energy. With the halogen varying from Cl to I, the interlayer distances of Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures increase rapidly. The CBM and VBM of monolayer  $Cs_2PbX_4$  are all higher than that of monolayer MSe<sub>2</sub> and the charges transfer from Cs<sub>2</sub>PbX<sub>4</sub> interfaces to MSe<sub>2</sub> interfaces when they contact. Both Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures are type-II heterostructures, which can drive the photogenerated electrons and holes to move in opposite directions. What's more, Cs<sub>2</sub>PbCl<sub>4</sub>-MoSe<sub>2</sub> heterostructures exhibit the highest charge transport efficiency among Cs<sub>2</sub>PbX<sub>4</sub>-MoSe<sub>2</sub> heterostructures because Cs<sub>2</sub>PbCl<sub>4</sub>-MoSe<sub>2</sub> heterostructures have the lowest exciton binding energies among Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures. In addition, the optical absorptions of all heterostructures are significantly higher than the corresponding Cs<sub>2</sub>PbX<sub>4</sub> monolayers and MSe<sub>2</sub> monolayers. The construction of Cs<sub>2</sub>PbX<sub>4</sub>-MoSe<sub>2</sub> heterostructures is beneficial for improving the photoelectric performance of two-dimensional perovskite devices. Lastly, we found that the Cs<sub>2</sub>PbI<sub>4</sub>-WSe<sub>2</sub> heterostructure has the largest PCE (18%) among Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures. The Cs<sub>2</sub>PbCl<sub>4</sub>-MoSe<sub>2</sub> heterostructure exhibits great potential application in photodetector devices and the Cs<sub>2</sub>Pbl<sub>4</sub>-WSe<sub>2</sub> heterostructure has great potential application in solar cells.

> commercialization.<sup>5,6</sup> In recent years, two-dimensional (2D) inorganic halide perovskites with good moisture resistance and stability have attracted attention for optoelectronic applications.7 Currently, many theoretical studies and experiments on 2D perovskites have been conducted. For example, Ding et al. reported that the number of layers would affect the optical absorption and transport properties of 2D perovskite Cs2PbI4.8 In addition, Bala et al. also revealed the same laws that the band gap and optical properties of 2D  $Cs_{n+1}Pb_nX_{3n+1}$  (X = Cl, Br, I) perovskite vary with layer number.9 In experiments, Song et al. fabricated 2D CsPbBr3 nanosheets and used them to produce high-performance photodetectors.10 These studies found that the bandgaps of 2D monolayer lead halide perovskites are larger than 3D lead halide perovskites, which lead to lower electric properties, optical absorption and low performance of optoelectronic applications.

> Fortunately, two-dimensional monolayer lead halide perovskites have a wide range of photoelectric properties adjustable by replacing halogens, changing layers, and working with other two-dimensional materials. In particular, the halide perovskites grown in the other 2D materials provides excellent ability to further adjust band gaps, transport properties, charge carrier dynamics, chemical stability and optical light absorption.<sup>11</sup>

<sup>&</sup>quot;State Key Laboratory of High Power Semiconductor Lasers, Changchun University of Science and Technology, Changchun 130013, China

<sup>&</sup>lt;sup>b</sup>State Key Laboratory of Information Photonics and Optical Communications, Beijing University of Posts and Telecommunications, Beijing 100876, China

<sup>&</sup>lt;sup>c</sup>School of Electronic Engineering, Beijing University of Posts and Telecommunications, Beijing 100876, China. E-mail: hanlhstar@bupt.edu.cn

<sup>&</sup>lt;sup>d</sup>School of Information and Communication Engineering, Beijing University of Posts and Telecommunications, Beijing 100876, China. E-mail: guanxiaoning@bupt.edu.cn

Therefore, a great deal of scientific researches of 2D halide perovskites and 2D materials interface engineering have been carried to achieve low-cost, high efficiency, stable heterostructures photoelectric devices. For instance, He et al. theoretically studied the effects of different terminals of heterojunctions and found that CsPbI<sub>3</sub>/MoS<sub>2</sub> heterostructure had higher electric performances than CsPbI<sub>3</sub>/WS<sub>2</sub>.<sup>12</sup> The WS<sub>2</sub>-CsPbBr<sub>3</sub> heterostructure was applied to perovskite solar cells (PSCs), which significantly improved PSCs stability under constant light and humidity (80%) attack over.13 While, the PCE of WS2-CsPbBr3 PSCs is only 10.65%.13 Recently, inverted perovskite solar cells with WS<sub>2</sub> interlayers had increased PCE up to 21.1%.14 As we can see, 2D lead halide perovskites applying for PSCs have high stability and can effectively improve PCE by coordinating with two-dimensional transition metal dichalcogenides (TMDs) such as WS<sub>2</sub>, MoS<sub>2</sub> and so on.

MoSe<sub>2</sub> and WSe<sub>2</sub> as conventional materials of TMDs are widely used in interface engineering in experiments to improve optoelectronic properties of 2D organic halide perovskites. In experiments, Lu et al. fabricated a high-Performance WSe<sub>2</sub>-CH<sub>3</sub>NH<sub>3</sub>PbI<sub>3</sub> perovskite photodetector.<sup>15</sup> MoSe<sub>2</sub>-CsPbBr<sub>3</sub> Mixed van der Waals nanohybrids shown higher photocurrent than pure CsPbBr3 nanocrystals.16 Lee et al. found photoluminescence (PL) quenching occurred after the hybridization of perovskites with MoSe<sub>2</sub> and WSe<sub>2</sub> layers, which reflects the charge-transfer effect.17 The PCE of PEDOT:PSS perovskite solar cells with WSe2-mediated and without WSe2-mediated is 16.3% and 13.8%, respectively.18 These experiments observed the construction of TMDs and perovskite heterostructures can effectively improve the optoelectronic properties of halide perovskites. However, interface electronic transfer and band alignment of Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures are not studied theoretically. It's worth revealing the effect of halide elements and  $MSe_2$  (M = Mo, W) on  $Cs_2PbX_4$ -MSe<sub>2</sub> heterostructures, which can promote the development of 2D inorganic halide perovskite and TMDs optoelectronic applications.

Herein, we constructed the 2D inorganic halide perovskite  $Cs_2PbX_4$  (X = Cl, Br, I) and monolayer MSe<sub>2</sub> heterostructures and discussed their stability, photoelectric properties and charge transfer mechanism through first-principles calculations. We studied electronic structures of the heterostructures with different halide elements and analysed the band alignment type for comparison. Next, we explore the charge transfers mechanism by calculating charge density difference. Finally, optical absorption coefficients of monolayer MSe<sub>2</sub>, Cs<sub>2</sub>PbX<sub>4</sub> and heterostructures  $Cs_2PbX_4$ -MSe<sub>2</sub> were calculated. Our results will be helpful to improve the application performance of twodimensional lead halide perovskite and TMDs heterostructures.

### Computational details

All the density functional theory calculations were performed with the Vienna Ab initial Simulation Package (VASP) code.<sup>19,20</sup> The projector-augmented wave (PAW) method was referred to electron–ion interactions.<sup>21</sup> The structure-relaxation, interface binding energy and optoelectronic properties were computed by Perdew, Burke and Ernzerhof's (PBE) exchange correlation function within the generalized gradient approximation (GGA) formalism.<sup>22-26</sup> The band gaps of monolayer perovskites and TMDs were further corrected using the screened Heyd–Scuseria–Ernzerhof (HSE) hybrid density functional with the spin–orbital coupling (SOC). The plane wave basis set with a cutoff energy of 450 eV. The convergence criteria were  $1 \times 10^{-4}$  eV for the self-consistent field energy and 0.01 eV Å<sup>-1</sup> for the residual forces on each atom, respectively. A vacuum of 20 Å was considered along *z* direction to avoid artificial interlayer interactions.  $3 \times 6 \times 1$  *k*-sampling generated by the Monkhorst–Pack scheme for the Brillouin zone was adopted. The zero damping DFT-D3 method of Gimme is used to account for correcting the van der Waals interaction of Heterostructure.

The interface binding energy is calculated by the following formula:

$$E_{\rm b} = (E_{\rm heter.} - E_{\rm Cs,PbX_4} - E_{\rm MSe_2})/A \tag{1}$$

where *A* represents the interfacial area of  $Cs_2PbX_4$ -MSe<sub>2</sub> heterostructures,  $E_{heter.}$ ,  $E_{Cs_2PbX_4}$ ,  $E_{MSe_2}$  are the total energy of heterostructures  $Cs_2PbX_4$ -MSe<sub>2</sub>, monolayer  $Cs_2PbX_4$  and MSe<sub>2</sub>, respectively.

The plane-averaged charge density difference  $\Delta \rho$  is calculated as the followed equation:

$$\Delta \rho(z) = \rho_{\text{heter.}} - \rho_{\text{Cs}_2\text{PbX}_4} - \rho_{\text{MSe}_2} \tag{2}$$

where  $\rho_{\text{heter.}}$ ,  $\rho_{\text{Cs}_2\text{PbX}_4}$  and  $\rho_{\text{MSe}_2}$  correspond to the planeaveraged charge density of heterojunctions Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub>, monolayer Cs<sub>2</sub>PbX<sub>4</sub> and MSe<sub>2</sub>, respectively.

The 2D Mott-Wananier (MW) exciton binding energy  $(E_{eb})$  equation is calculated as the followed equation:

$$E_{\rm eb} = 4 \frac{13.6\mu_{\rm ex}}{m_0 \varepsilon^2} \text{eV}$$
(3)

where  $\mu_{\rm ex}$  is the effective exciton mass ( $\mu_{\rm ex} = m_{\rm e}m_{\rm h}/(m_{\rm e} + m_{\rm h})$ ),  $m_0$  is the electron mass, and  $\varepsilon$  is the static dielectric constant. The effective masses of electron ( $m_{\rm e}$ ) and hole ( $m_{\rm h}$ ) are determined by the curvature of the energy band extremum.

The optical absorption coefficients are obtained from dielectric function, as the followed equation represented:

$$\alpha(\omega) = \left(\sqrt{2}\right) \omega \left[ \sqrt{\varepsilon_1(\omega)^2 + \varepsilon_2(\omega)^2} - \varepsilon_1(\omega)^2 \right]^{1/2}$$
(4)

$$\varepsilon(\omega) = \varepsilon_1(\omega) + i\varepsilon_2(\omega) \tag{5}$$

where  $\alpha$ ,  $\omega$  correspond to the optical absorption coefficient, the angular frequency and the dielectric function  $\varepsilon(\omega)$  contains real part  $\varepsilon_1(\omega)$  and imaginary part  $\varepsilon_2(\omega)$ .

## Results and discussion

In recent years, the 2D inorganic perovskites  $Cs_2PbX_4$  (X = Cl, Br, I) and monolayers  $MSe_2$  (M = Mo, W) have been successfully synthesized, which attracted much attention due to its highly stable structures.<sup>7,27,28</sup> The unit cell of  $Cs_2PbX_4$  perovskites belongs to cubic system and the optimized lattice parameters of

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.

#### Paper

monolayer Cs<sub>2</sub>PbCl<sub>4</sub>, Cs<sub>2</sub>PbBr<sub>4</sub>, Cs<sub>2</sub>PbI<sub>4</sub> is 5.64 Å, 5.91 Å and 6.30 Å, respectively.<sup>29</sup> [CsI]<sup>0</sup> interface exhibits more strongly charge transferring than [PbI<sub>2</sub>]<sup>0</sup>.<sup>30</sup> Therefore the [CsI]<sup>0</sup> plane of the monolayer Cs<sub>2</sub>PbX<sub>4</sub> is used to form the heterojunctions. The optimized lattice parameters of monolayer MoSe<sub>2</sub>, WSe<sub>2</sub> are 3.32 Å.<sup>31-33</sup> To minimize the lattice mismatch between the stacking blocks, the supercell of new Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures are built by  $3 \times 1$  cubic phases Cs<sub>2</sub>PbCl<sub>4</sub> and  $5 \times \sqrt{3}$  MSe<sub>2</sub>,  $\sqrt{8} \times 2$  cubic phases Cs<sub>2</sub>PbBr<sub>4</sub> and  $5 \times \sqrt{13}$  MSe<sub>2</sub>, and  $\sqrt{8} \times \sqrt{2}$  cubic phases Cs<sub>2</sub>PbI<sub>4</sub> and  $\sqrt{31} \times \sqrt{7}$  MSe<sub>2</sub>, respectively, as seen in Fig. 1 (Table 1).

The lattice mismatches of Cs<sub>2</sub>PbCl<sub>4</sub>-MoSe<sub>2</sub>, Cs<sub>2</sub>PbBr<sub>4</sub>-MoSe<sub>2</sub>, Cs<sub>2</sub>PbI<sub>4</sub>-MoSe<sub>2</sub>, Cs<sub>2</sub>PbCl<sub>4</sub>-WSe<sub>2</sub>, Cs<sub>2</sub>PbBr<sub>4</sub>-WSe<sub>2</sub> and Cs<sub>2</sub>PbI<sub>4</sub>-WSe<sub>2</sub> heterostructures are less than 1.10%, 0.62%, 1.79%, 1.02%, 0.65% and 1.82%. The optimized vertical interlayer distances of Cs<sub>2</sub>PbCl<sub>4</sub>-MoSe<sub>2</sub>, Cs<sub>2</sub>PbBr<sub>4</sub>-MoSe<sub>2</sub>, Cs<sub>2</sub>PbI<sub>4</sub>-MoSe<sub>2</sub>, Cs<sub>2</sub>PbCl<sub>4</sub>-WSe<sub>2</sub>, Cs<sub>2</sub>PbBr<sub>4</sub>-WSe<sub>2</sub> and Cs<sub>2</sub>PbI<sub>4</sub>-WSe<sub>2</sub> interfaces are 3.07, 3.12, 3.16, 2.90, 3.18 and 3.30 Å, respectively, which increase gradually with the halogen varying from Cl to I. Interface binding energy of Cs<sub>2</sub>PbCl<sub>4</sub>-MoSe<sub>2</sub>, Cs<sub>2</sub>PbBr<sub>4</sub>-MoSe<sub>2</sub> and Cs2PbI4-MoSe2, Cs2PbCl4-WSe2, Cs2PbBr4-WSe2 and Cs<sub>2</sub>PbI<sub>4</sub>-WSe<sub>2</sub> interfaces is -16.73, -16.28 and -16.12, -17.09, -17.52 and -15.56 meV Å<sup>-2</sup>, respectively. The small interface binding energy and the interlayer distance ranging from 2.9 Å to 3.3 Å indicate that 2D Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures are formed by vdW contact.<sup>33</sup> These  $E_{\rm b}$  values are comparable to  $E_{\rm b}$ of InSe/GaSe ( $-18.25 \text{ meV } \text{\AA}^{-2}$ ), suggesting that Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures are stable in energy.<sup>34</sup> ln addition, MoSe<sub>2</sub>-CsPbBr<sub>3</sub> Mixed van der Waals nanohybrids also have been fabricated in experiments (Table 2).16

In order to study the band structures of  $Cs_2PbX_4$ -MSe<sub>2</sub> heterostructures, the band structures of 2D perovskites  $Cs_2PbX_4$ , monolayer WSe<sub>2</sub> and monolayer MoSe<sub>2</sub> were calculated by different functionals, including PBE, PBE with SOC (PBE + SOC), HSE, and HSE with SOC (HSE + SOC) functionals. Monolayer MoSe<sub>2</sub> and monolayer WSe<sub>2</sub> show a direct band gap of 1.45 eV and 1.56 eV using PBE functional. Monolayer



Fig. 1 Top and side views of relaxed  $Cs_2PbX_4-MSe_2$  (M = Mo, W) heterostructures. (a and b)  $Cs_2PbCl_4-MSe_2$  heterostructure. (c and d)  $Cs_2PbBr_4-MSe_2$  heterostructure. (e and f)  $Cs_2PbI_4-MSe_2$  heterostructure.

Cs<sub>2</sub>PbCl<sub>4</sub>, Cs<sub>2</sub>PbBr<sub>4</sub> and Cs<sub>2</sub>PbI<sub>4</sub> possess a direct bandgap of 2.59 eV, 2.18 eV and 1.84 eV using PBE functional. We find that the bandgaps of Cs<sub>2</sub>PbX<sub>4</sub> computed via PBE and HSE + SOC functionals are in good agreements with experiments and other theoretical results.<sup>9,10,27,28,35-38</sup> The band gap calculated by HSE is larger than PBE and the band gap calculated by PBE + SOC is smaller than PBE. In addition, the band gap of MSe<sub>2</sub> calculated by HSE + SOC is larger than the related experimental data.<sup>27,28</sup> This is because the HSE functional usually overcorrects slightly the band gap of an intrinsic semiconductor.39 Thus, in order to accurately and closely study the contact characteristics of Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures, PBE is employed in the following heterostructures section. When monolayers Cs<sub>2</sub>PbX<sub>4</sub> and  $MSe_2$  (M = Mo, W) are contacted to make up  $Cs_2PbX_4$ -MSe<sub>2</sub> heterostructures, the electronic structures of Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures are shown in Fig. 2. The Cs<sub>2</sub>PbCl<sub>4</sub>-MoSe<sub>2</sub>, Cs<sub>2</sub>PbBr<sub>4</sub>-MoSe<sub>2</sub>, Cs<sub>2</sub>PbI<sub>4</sub>-MoSe<sub>2</sub>, Cs<sub>2</sub>PbCl<sub>4</sub>-WSe<sub>2</sub>, Cs<sub>2</sub>PbBr<sub>4</sub>-WSe<sub>2</sub> and Cs<sub>2</sub>PbI<sub>4</sub>-WSe<sub>2</sub> heterostructures have an indirect bandgap with the value of 1.30 eV, 1.48 eV, 1.54 eV, 1.33 eV, 1.67 eV and 1.53 eV, which approach optimal bandgap (1.34 eV) for solar cells.40 Moreover, the conduction band minimum (CBM) of Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures are dominated by the MSe<sub>2</sub> layer and the valence band maximum (VBM) of Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures are dominated by Cs<sub>2</sub>PbX<sub>4</sub> part.

The analysis of energy level arrangement is of great significance to further study interface properties of Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures. The vacuum energy level  $(E_v)$  is set to zero in the precontact state and the Fermi level  $(E_f)$  is set to zero in the contact state. In precontact state, the CBM and VBM of monolayer Cs<sub>2</sub>PbX<sub>4</sub> are both higher than that of monolayer MSe<sub>2</sub> and both Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> are type-II heterostructures, as seen in Fig. 3(a). The electrons will diffuse from monolayers Cs<sub>2</sub>PbX<sub>4</sub> to monolayers MSe<sub>2</sub> and the holes will move from monolayers MSe<sub>2</sub> monolayer to monolayers s<sub>2</sub>PbX<sub>4</sub> when they contact. Correspondingly, the holes accumulate in Cs<sub>2</sub>PbX<sub>4</sub> monolayers and the electrons accumulate in MSe<sub>2</sub> monolayers. Moreover, the difference between the vacuum level and the Fermi level is defined as the work function.31 The work function is the internal dynamics of electron flow. The computed work functions of monolayers Cs<sub>2</sub>PbCl<sub>4</sub>, Cs<sub>2</sub>PbBr<sub>4</sub>, Cs<sub>2</sub>PbI<sub>4</sub>, MoSe<sub>2</sub> and WSe<sub>2</sub> are 4.08 eV, 4.21 eV, 4.30 eV, 4.83 eV and 4.51 eV, respectively. The heterostructures are mainly related to the work function after contact. In order to maintain Fermi levels at the same level after contact, the Fermi level of all Cs<sub>2</sub>PbX<sub>4</sub> perovskites moved down and the Fermi level of monolayer MSe2 moved up after they contact each other.

The energy level diagram of  $Cs_2PbX_4$ -MSe<sub>2</sub> heterostructures in contact states is given in Fig. 3(b). The  $Cs_2PbX_4$ -MSe<sub>2</sub> heterostructures are type-II heterostructures, which can drive the photogenerated holes and electrons to move in opposite directions, resulting in spatial separation of holes and electrons on different sides of heterostructures.<sup>33</sup> Thus,  $Cs_2PbX_4$ -MSe<sub>2</sub> heterostructures are beneficial for improving the photoelectric conversion efficiency of  $Cs_2PbX_4$ -MSe<sub>2</sub> optoelectronic applications. In these type-II heterostructures, the differences between the VBM of their components (valence band offset,  $\Delta \nu$ ) are crucial for hole blocking and the differences between the CBM **Table 1** Optimized lattice parameters (a and b) and expanded cell lattice parameters ( $a_1$  and  $b_1$ ), lattice mismatch, interlayer distance  $\Delta Z$  and interface binding energy  $E_b$  of the relaxed Cs<sub>2</sub>PbX<sub>4</sub>–WSe<sub>2</sub> heterostructures

Heterostructures	<i>a</i> (Å)	<i>b</i> (Å)	$a_1$ (Å)	$b_1$ (Å)	Mismatch (%)	$\Delta Z$ (Å)	$E_{\rm b}  ({ m meV}  { m \AA}^{-2})$
Cs <sub>2</sub> PbCl <sub>4</sub> -MoSe <sub>2</sub>	16.51	5.66	16.75	5.69	1.10%	3.09	-16.73
Cs <sub>2</sub> PbBr <sub>4</sub> -MoSe <sub>2</sub>	16.35	11.81	16.65	11.89	0.62%	3.12	-16.28
Cs <sub>2</sub> PbBr <sub>4</sub> -MoSe <sub>2</sub>	18.22	8.66	18.14	8.84	1.79%	3.16	-16.12
Cs <sub>2</sub> PbBr <sub>4</sub> -WSe <sub>2</sub>	16.41	5.67	16.75	5.69	1.02%	2.90	-17.09
Cs <sub>2</sub> PbBr <sub>4</sub> -WSe <sub>2</sub>	16.35	11.81	16.65	11.89	0.65%	3.18	-17.52
$Cs_2PbBr_4$ -WSe_2	18.21	8.66	18.20	8.67	1.82%	3.30	-15.56

Table 2 The bandgaps of monolayer  $\mathsf{Cs}_2\mathsf{PbX}_4,\ \mathsf{MoSe}_2$  and  $\mathsf{WSe}_2$  by different calculation method

$Cs_2PbCl_4$	$Cs_2PbBr_4$	$Cs_2PbI_4$	MoSe <sub>2</sub>	WSe <sub>2</sub>
2.59	2.18	1.84	1.45	1.56
3.58	2.91	2.57	2.10	2.03
1.84	1.46	1.09	1.37	1.33
2.78	2.14	1.78	1.89	1.93
3.01	2.32	1.86	1.48	1.60
	Cs <sub>2</sub> PbCl <sub>4</sub> 2.59 3.58 1.84 2.78 3.01	Cs2PbCl4         Cs2PbBr4           2.59         2.18           3.58         2.91           1.84         1.46           2.78         2.14           3.01         2.32	$\begin{array}{c cccc} Cs_2PbCl_4 & Cs_2PbBr_4 & Cs_2PbI_4 \\ \hline 2.59 & 2.18 & 1.84 \\ 3.58 & 2.91 & 2.57 \\ 1.84 & 1.46 & 1.09 \\ 2.78 & 2.14 & 1.78 \\ 3.01 & 2.32 & 1.86 \\ \hline \end{array}$	$\begin{array}{c cccc} Cs_2PbCl_4 & Cs_2PbBr_4 & Cs_2PbI_4 & MoSe_2 \\ \hline 2.59 & 2.18 & 1.84 & 1.45 \\ 3.58 & 2.91 & 2.57 & 2.10 \\ 1.84 & 1.46 & 1.09 & 1.37 \\ 2.78 & 2.14 & 1.78 & 1.89 \\ 3.01 & 2.32 & 1.86 & 1.48 \\ \hline \end{array}$

of their components (conduction band offset,  $\Delta c$ ) are crucial for electron transport. The large  $\Delta v$  promotes hole extraction from TMDs layers to perovskite layers and the large  $\Delta c$  allows free electrons to move from perovskite to TMDs layers. It is shown that Cs<sub>2</sub>PbCl<sub>4</sub>–MSe<sub>2</sub> heterostructure have the largest  $\Delta c$  and  $\Delta v$ among Cs<sub>2</sub>PbX<sub>4</sub>–MSe<sub>2</sub> heterostructures.<sup>12</sup> Thus, the Cs<sub>2</sub>PbCl<sub>4</sub>– MoSe<sub>2</sub>, and Cs<sub>2</sub>PbCl<sub>4</sub>–WSe<sub>2</sub> heterostructures may have the largest charge transport power and are more conducive to reducing the dark current. In addition, Cs<sub>2</sub>PbX<sub>4</sub>–MoSe<sub>2</sub> heterostructures have lager  $\Delta c$  and  $\Delta v$  than Cs<sub>2</sub>PbX<sub>4</sub>-WSe<sub>2</sub> heterostructures.

In addition, the Mott–Wananier theory has been used to approximate exciton binding energies in the vdW heterostructures.<sup>41</sup> Table 3 lists the carrier masses and MW exciton binding energy of Cs<sub>2</sub>PbX<sub>4</sub>–MSe<sub>2</sub> heterostructures. The lower exciton binding energies usually facilitate the splitting of excitons into free charge carriers.<sup>34</sup> It is shown that Cs<sub>2</sub>PbCl<sub>4</sub>–MoSe<sub>2</sub> heterostructures exhibit the lowest exciton binding energies among Cs<sub>2</sub>PbX<sub>4</sub>–MoSe<sub>2</sub> heterostructures. Therefore, Cs<sub>2</sub>PbCl<sub>4</sub>– MoSe<sub>2</sub> heterostructures can effectively promotes the separation of excitons and exhibit the highest charge transport efficiency among Cs<sub>2</sub>PbX<sub>4</sub>–MSe<sub>2</sub> heterostructures.

To clearly investigate the recombination rates of electronhole pairs and transfer of charges between the Cs<sub>2</sub>PbX<sub>4</sub> monolayers and MSe<sub>2</sub> monolayers across the interfaces, the planeaveraged charge density difference  $\Delta \rho$  are calculated, as shown in Fig. 4. The results demonstrate that the holes mainly accumulated at the Cs<sub>2</sub>PbX<sub>4</sub> interfaces and the charges accumulated at MSe<sub>2</sub> interfaces. Additionally, the charges transfer



Fig. 2 Band structures of  $Cs_2PbX_4-MSe_2$  heterostructures (a) X = Cl, M = Mo; (b) X = Br, M = Mo; (c) X = I, M = Mo; (d) X = Cl, M = W; (e) X = Br, M = W; (f) X = I, M = W. The red and blue lines correspond to  $Cs_2PbX_4$  and  $MSe_2$ , respectively.



Fig. 3 Energy level graphs of the monolayer  $MSe_2$  and  $Cs_2PbX_4$  in the precontact (a) and contact (b). Blue and gray rectangles represent the monolayer  $Cs_2PbX_4$  and  $MSe_2$ . The bottom and top of rectangles correspond to VBM and CBM, respectively.

**Table 3** Carrier effective masses ( $m_{er}$ ,  $m_{hr}$ , and  $\mu_{ex}$ ), static dielectric constant ( $\varepsilon$ ) and MW excitonic binding energies ( $E_{eb}$ )

Heterostructures	$m_{\rm e}(m_0)$	$m_{\rm h}\left(m_0\right)$	$\mu_{\rm ex}\left(m_0\right)$	ε	$E_{\rm eb}$ (eV)
Cs <sub>2</sub> PbCl <sub>4</sub> -MoSe <sub>2</sub>	1.16	0.28	0.23	5.34	0.43
Cs <sub>2</sub> PbBr <sub>4</sub> -MoSe <sub>2</sub>	0.79	0.71	0.37	5.44	0.68
Cs <sub>2</sub> PbI <sub>4</sub> -MoSe <sub>2</sub>	1.39	0.67	0.45	5.24	1.00
Cs <sub>2</sub> PbCl <sub>4</sub> -WSe <sub>2</sub>	1.46	0.27	0.23	4.95	0.50
Cs <sub>2</sub> PbBr <sub>4</sub> -WSe <sub>2</sub>	0.75	0.66	0.35	5.08	0.74
Cs <sub>2</sub> PbI <sub>4</sub> -WSe <sub>2</sub>	1.03	0.61	0.38	5.26	0.76

from  $Cs_2PbX_4$  interfaces to  $MSe_2$  interfaces while the holes move in the opposite direction. The direction of charge transfer is consistent with that of band alignment analysis, which shown type-II heterostructures are benefited to the separation of electrons and holes. What's more, detail charge transfers among interlayer spacing are used to quantitatively evaluate charge transferring of heterostructures. The Cs<sub>2</sub>PbCl<sub>4</sub>–MoSe<sub>2</sub>, Cs<sub>2</sub>PbBr<sub>4</sub>–MoSe<sub>2</sub>, Cs<sub>2</sub>PbI<sub>4</sub>–MoSe<sub>2</sub>, Cs<sub>2</sub>PbCl<sub>4</sub>–WSe<sub>2</sub>, Cs<sub>2</sub>PbBr<sub>4</sub>–WSe<sub>2</sub> and Cs<sub>2</sub>PbI<sub>4</sub>–WSe<sub>2</sub> heterostructures have charge transfers among interlayer spacing with the values of 0.18, 0.15, 0.16, 0.16, 0.10 and 0.14 × 10<sup>-3</sup>e. We find that the Cs<sub>2</sub>PbCl<sub>4</sub>–MSe<sub>2</sub> heterostructures have the highest charge transfers in the six Cs<sub>2</sub>PbX<sub>4</sub>–MSe<sub>2</sub> heterostructures among interlayer spacing. In addition, Cs<sub>2</sub>PbX<sub>4</sub>–MSe<sub>2</sub> heterostructures have larger charge transfers than Cs<sub>2</sub>PbX<sub>4</sub>–WSe<sub>2</sub> heterostructures. It is because



Fig. 4 The planar-averaged differential charge density  $\Delta \rho(z)$  of Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures: (a and d) X = Cl; (b and e) X = Br; (c and f) X = I. Red and blue represent electron depletion and accumulation.



Fig. 5 Optical absorption coefficients of (a and d)  $Cs_2PbCl_4-MSe_2$ , (b and e)  $Cs_2PbBr_4-MSe_2$ , and (c and f)  $Cs_2PbI_4-MSe_2$  heterostructures. The blue, black and red lines represent optical absorption spectrum of heterostructures, monolayer  $MSe_2$  and  $Cs_2PbX_4$ , respectively.

 $Cs_2PbX_4\text{-}MoSe_2$  heterostructures have smaller exciton binding energies than  $Cs_2PbX_4\text{-}WSe_2$  heterostructures.

Except for the electronic structures and charge redistributions of heterostructures, the optical properties in vdW heterostructures have important effects on the performance of perovskite optoelectronic devices.<sup>42</sup> In order to further study the optical properties of  $Cs_2PbX_4$ -MSe<sub>2</sub> heterostructures, the optical absorption coefficients were calculated, as shown in Fig. 5. The optical absorption coefficients of MSe<sub>2</sub> monolayers are higher than those of  $Cs_2PbX_4$  monolayers. The optical absorption coefficients of all heterostructures are significantly higher than those of corresponding  $Cs_2PbX_4$  monolayers and  $MSe_2$  monolayers. This is because the bandgaps of  $2D Cs_2PbX_4$ - $MSe_2$  heterostructures are smaller than the bandgaps of  $Cs_2PbX_4$ - $MSe_2$  heterostructures approach optimal bandgap (1.34 eV) for solar cells.<sup>40</sup> Thus, the construction of  $Cs_2PbX_4$ - $MSe_2$  heterostructures is beneficial to improve the light absorption of optoelectronic devices.

In addition, the light absorption of  $Cs_2PbX_4$ -MoSe<sub>2</sub> heterostructures is only slightly greater than that of  $Cs_2PbX_4$ -WSe<sub>2</sub> in the visible region because the light absorption of MoSe<sub>2</sub> is slightly greater than that of WSe<sub>2</sub> in the visible region. The light absorption coefficients of  $Cs_2PbX_4$  increase rapidly in the visible



Fig. 6 Contour plot showing the calculated PCE of  $Cs_2PbX_4$ -MSe<sub>2</sub> heterostructures according to the  $Cs_2PbX_4$  donor band gap and conduction band offset  $\Delta c$ .

region with the halogen varying from Cl to I. The light absorption coefficients of  $Cs_2PbX4-MSe_2$  heterostructures increase rapidly in the visible region with the halogen varying from Cl to I. Therefore, the  $Cs_2PbI_4-MSe_2$  heterostructure has great potential application in solar cells among  $Cs_2PbX_4-MSe_2$  heterostructures.

In order to explore the application of Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures in solar cells, we further calculated the power conversion efficiency of Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures. The PCE depends on the donor band gap and conduction band offset.43,44 The PCE of Cs2PbX4-MSe2 heterostructures with type-II alignment is shown in Fig. 6 as a contour plot where the xand y-axes are the donor band gap and conduction band offset, respectively. The PCE of Cs2PbI4-MoSe2, Cs2PbI4-WSe2 and Cs<sub>2</sub>PbBr<sub>4</sub>-WSe<sub>2</sub> heterostructures is 13%, 18% and 10%, which is greater than 10%. Three heterostructures can be used in solar cells.  $Cs_2PbI_4$ -WSe<sub>2</sub> heterostructure has the largest PCE (18%) among Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures. The PCE of Cs<sub>2</sub>PbI<sub>4</sub>-WSe<sub>2</sub> heterostructure is larger than that of WS<sub>2</sub>/CsPbBr<sub>3</sub> PSCs (10.65%) and WSe<sub>2</sub>-mediated PSCs (16.3%).<sup>13,18</sup> With the halogen varying from Cl to I, the PCE of Cs<sub>2</sub>PbX<sub>4</sub>-WSe<sub>2</sub> heterostructures increase rapidly. The PCE variation trend is consistent with the absorption coefficients of Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures varying from Cl to I. In addition, the PCE of Cs<sub>2</sub>PbX<sub>4</sub>-WSe<sub>2</sub> heterostructures is larger than the PCE of Cs<sub>2</sub>PbX<sub>4</sub>-MoSe<sub>2</sub> heterostructures. This is mainly because  $Cs_2PbX_4$ -WSe<sub>2</sub> heterostructures have smaller  $\Delta c$  than  $Cs_2PbX_4$ -MoSe<sub>2</sub> heterostructures. Therefore, Cs<sub>2</sub>PbI<sub>4</sub>-WSe<sub>2</sub> heterostructure has great potential application in solar cells.

# Conclusions

In summary, we have systematically studied the structural, stability, charge transfer and optoelectronic properties of 2D perovskite Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures with different halide elements based on density functional calculations. All these six heterostructures are stable in energy and the interlayer distances increase gradually with the halogen varying from Cl to I. Electronic structures show Cs<sub>2</sub>PbX<sub>4</sub>-MSe<sub>2</sub> heterostructures belongs to type-II energy level shifts with narrower optical gap than monolayers Cs<sub>2</sub>PbX<sub>4</sub>. In addition, the Cs<sub>2</sub>PbCl<sub>4</sub>-MoSe<sub>2</sub>, and Cs<sub>2</sub>PbCl<sub>4</sub>-WSe<sub>2</sub> heterostructures may have the largest charge transport power due to their larger band offset, which is beneficial to reduce dark current and improve open circuit voltage. Cs2PbCl4-MoSe2 heterostructures can effectively promotes the separation of excitons and exhibit the highest charge transport efficiency among Cs2PbX4-MSe2 heterostructures due to their lowest exciton binding energies. Cs<sub>2</sub>-PbCl<sub>4</sub>-MoSe<sub>2</sub> heterostructure has the potential to be applied in photodetectors. Next, the charges transfer from Cs<sub>2</sub>PbX<sub>4</sub> interfaces to MSe<sub>2</sub> interfaces while the holes move in the opposite direction. The holes mainly accumulated at the Cs<sub>2</sub>PbX<sub>4</sub> interfaces and the charges accumulated at MSe2 interfaces. Cs2PbX4-MoSe<sub>2</sub> heterostructures have larger charge transfers than Cs<sub>2</sub>PbX<sub>4</sub>-WSe<sub>2</sub> heterostructures. Finally, optical absorptions of six heterostructures are significantly higher than the corresponding Cs<sub>2</sub>PbX<sub>4</sub> monolayers and MSe<sub>2</sub> monolayers. The PCE of  $Cs_2PbX_4$ -WSe<sub>2</sub> heterostructures is larger than the PCE of  $Cs_2PbX_4$ -MoSe<sub>2</sub> heterostructures.  $Cs_2PbI_4$ -WSe<sub>2</sub> heterostructure has the largest PCE (18%) among  $Cs_2PbX_4$ -MSe<sub>2</sub> heterostructures. In conclusion,  $Cs_2PbCl_4$ -MoSe<sub>2</sub> heterostructure exhibits great potential application in photodetectors devices and  $Cs_2PbI_4$ -WSe<sub>2</sub> heterostructure has great potential application in solar cells. Our findings provide insight into of  $Cs_2PbX_4$ -MSe<sub>2</sub> heterostructures can effectively improve the performance of perovskite optoelectronic devices.

# Conflicts of interest

There are no conflicts to declare.

# Acknowledgements

This work is supported by the Fund of State Key Laboratory of IPOC(BUPT) (no. IPOC2019ZZ04) and the Open-Foundation of Key Laboratory of Laser Device Technology, China North Industries Group Corporation Limited (Grant No. KLLDT202103). We thank for the helpful discussion with Prof. Pengfei Guan and the computational support from the Beijing Computational Science Research Center (CSRC). We also acknowledge the computation supported by High-performance Computing Platform of BUPT.

# Notes and references

- 1 A. T. Barrows, A. J. Pearson, C. K. Kwak, A. D. F. Dunbar, A. R. Buckley and D. G. Lidzey, *Energy Environ. Sci.*, 2014, 7, 2944–2950.
- 2 K. Xiao, R. Lin, Q. Han, Y. Hou, Z. Qin, H. T. Nguyen, J. Wen, M. Wei, V. Yeddu, M. I. Saidaminov, Y. Gao, X. Luo, Y. Wang, H. Gao, C. Zhang, J. Xu, J. Zhu, E. H. Sargent and H. Tan, *Nat. Energy*, 2020, 5, 870–880.
- 3 I. L. Braly, D. W. deQilettes, L. M. Pazos-Outon, S. Burke, M. E. Ziffer, D. S. Ginger and H. W. Hillhouse, *Nat. Photonics*, 2018, **12**, 355–361.
- 4 M. M. Lee, J. Teuscher, T. Miyasaka, T. N. Murakami and H. J. Snaith, *Science*, 2012, **338**, 643–647.
- 5 J. H. Noh, S. H. Im, J. H. Heo, T. N. Mandal and S. I. Seok, *Nano Lett.*, 2013, **13**, 1764–1769.
- 6 Y.-Y. Zhang, S. Chen, P. Xu, H. Xiang, X.-G. Gong, A. Walsh and S.-H. Wei, *Chin. Phys. Lett.*, 2018, **35**, 036104.
- 7 S. Chen and G. Shi, Adv. Mater., 2017, 29, 1605448.
- 8 Y. F. Ding, Q. Q. Zhao, Z. L. Yu, Y. Q. Zhao, B. Liu, P. B. He, H. Zhou, K. L. Li, S. F. Yin and M. Q. Cai, *J. Mater. Chem. C*, 2019, 7, 7433–7441.
- 9 A. Bala, A. K. Deb and V. Kumar, *J. Phys. Chem. C*, 2018, **122**, 7464–7473.
- 10 J. Song, L. Xu, J. Li, J. Xue, Y. Dong, X. Li and H. Zeng, Adv. Mater., 2016, 28, 4861–4869.
- 11 E. Shi, Y. Gao, B. P. Finkenauer, A. Akriti, A. H. Coffey and L. Dou, *Chem. Soc. Rev.*, 2018, 47, 6046–6072.
- 12 J. He, J. Su, Z. Lin, S. Zhang, Y. Qin, J. Zhang, J. Chang and Y. Hao, *J. Phys. Chem. C*, 2019, **123**, 7158–7165.

- 13 Q. W. Zhou, J. L. Duan, X. Y. Yang, Y. Y. Duan and Q. W. Tang, Angew. Chem., Int. Ed., 2020, 132, 22181–22185.
- 14 J. P. Cao, G. Q. Tang, P. You, T. Y. Wang, F. Y. Zheng, J. Zhao and F. Yan, *Adv. Funct. Mater.*, 2020, **30**, 2002358.
- 15 Hybrid Bilayer WSe<sub>2</sub>-CH<sub>3</sub>NH<sub>3</sub>PbI<sub>3</sub> Organolead Halide Perovskite as a High-Performance Photodetector.
- 16 S. Hassan, P. Basera, S. Bera, M. Mittal, S. K. Ray, S. Bhattacharya and S. Sapra, ACS Appl. Mater. Interfaces, 2020, 12, 7217–7325.
- 17 S.-H. Lee, J. Y. Kim, S. Choi, Y. Lee, K.-S. Lee, J. Kim and J. Joo, *ACS Appl. Mater. Interfaces*, 2020, **12**, 25159–25167.
- 18 Y. Choi, S. Jung, N. K. Oh, J. Lee, J. Seo, U. Kim, D. Koo and H. Park, Enhanced charge transport via metallic 1T phase transition metal dichalcogenides-mediated hole transport layer engineering for perovskite solar cells, *Chemnanomat*, 2019, 5, 1050–1058.
- 19 G. Kresse and D. Joubert, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1999, **59**, 1758–1775.
- 20 J. P. Perdew, K. Burke and M. Ernzerhof, *Phys. Rev. Lett.*, 1996, 77, 3865–3868.
- 21 P. E. Blochl, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1994, 50, 17953–17979.
- 22 B. Jia, P. Zhu, S. Sun, L. Han, G. Liu, Y. Wang, G.-D. Peng and P. Lu, *IEEE J. Sel. Top. Quantum Electron.*, 2019, **26**, 1–6.
- 23 S. Lin, J. C. Liu, W. Z. Li, D. Wang, Y. Huang, C. Jia, Z. W. Li,
  H. Y. Wang, J. N. Song, Z. L. Liu, K. Huang, D. Zu, M. Lei,
  B. Hong and H. Wu, *Nano Lett.*, 2019, 19, 6853–6861.
- 24 J. C. Xu, K. Bi, R. Zhang, Y. N. Hao, C. W. Lan, M.-M. Klaus,
  X. J. Zhai, Z. D. Zhang and S. G. H, *Research*, 2019, 2019, 9686213.
- 25 X. N. Guan, R. Zhang, B. N. Jia, L. Y. Wu, B. Zhou, L. Fan, G. Liu, Y. Wang, P. F. Lu and G. D. Peng, *J. Non-Cryst. Solids*, 2020, **550**, 120388.
- 26 P. F. Lu, J. Sichuan Norm. Univ., Nat. Sci., 2020, 43, 1-20.
- 27 X. Wang, Y. Gong, G. Shi, W. L. Chow, K. Keyshar, G. Ye,
  R. Vajtai, J. Lou, Z. Liu, E. Ringe, B. K. Tay and
  P. M. Ajayan, ACS Nano, 2014, 8, 5125–5131.

- 28 J.-K. Huang, J. Pu, C.-L. Hsu, M.-H. Chiu, Z.-Y. Juang, Y.-H. Chang, W.-H. Chang, Y. Iwasa, T. Takenobu and L.-J. Li, ACS Nano, 2014, 8(1), 923–930.
- 29 J.-H. Yang, Q. Yuan and B. I. Yakobson, J. Phys. Chem. C, 2016, 120, 24682–24687.
- 30 Y.-Q. Zhao, Y. Xu, D.-F. Zou, J.-N. Wang, G.-F. Xie, B. Liu, M.-Q. Cai and S.-L. Jiang, *J. Phys.: Condens. Matter*, 2020, 32, 195501.
- 31 Y. Ding, Y. Wang, J. Ni, L. Shi, S. Shi and W. Tang, *Phys. Chem. Chem. Phys.*, 2011, **13**, 15546–15553.
- 32 Y. Zhang, Y. Zhao, Y. Xu and L. He, *Solid State Commun.*, 2021, **327**, 114233.
- 33 B. Liu, M. Long, M.-Q. Cai and J. Yang, *J. Phys. Chem. Lett.*, 2018, **327**, 114233.
- 34 J. H. Chen, X. J. He, B. S. Sa, J. Zhou, C. Xu, C. L. Wen and Z. M. Sun, *Nanoscale*, 2019, **11**, 6431–6444.
- 35 P. Zhu, H. Zhao, X. Li, Y. Zu, L. Wu, C. Chen and G. Liu, *Phys. E*, 2021, **134**, 114908.
- 36 A. Molina-Sanchez, ACS Appl. Energy Mater., 2018, 1, 6361–6367.
- 37 Z. Zheng, X. X. Wang, Y. W. Shen, Z. Y. Luo, L. G. Li, L. Gan,
  Y. Ma, H. Q. Li, A. L. Pan and T. Y. Zhai, *Adv. Opt. Mater.*,
  2018, 6, 1800879.
- 38 P. B. Gui, H. Zhou, F. Yao, Z. H. Song, B. R. Li and G. J. Fang, Small, 2019, 15, 1902618.
- 39 R. J. Sutton, M. R. Filip, A. A. Haghighirad, N. Sakai, B. Wenger, F. Giustino and H. J. Snaith, ACS Energy Lett., 2018, 3, 1787–1794.
- 40 S. Ruhle, Sol. Energy, 2016, 130, 139-147.
- 41 P. Wang, Y. X. Zong, H. Liu, H. Y. Wen, H. X. Deng,
  Z. M. Wei, H. B. Wu and J. B. Xia, *J. Phys. Chem. C*, 2020,
  214, 23832–23838.
- 42 W. J. Yin, J. H. Yang, J. Kang, Y. Yan and S. H. Wei, *J. Mater. Chem. A*, 2015, **3**, 8926–8942.
- 43 M. C. Scharber, D. Wuhlbacher, M. Koppe, P. Denk, C. Waldauf, A. J. Heeger and C. L. Brabec, *Adv. Mater.*, 2006, 18, 189.
- 44 M. Bernardi, M. Palummo and J. C. Grossman, *ACS Nano*, 2012, **6**, 10082–10089.