RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2022, 12, 26277

Mono- and dinuclear zirconocene(IV) amide complexes for the catalytic dehydropolymerisation of phenylsilane[†]

Kevin Lindenau, Anke Spannenberg, Fabian Reiß 🗅 * and Torsten Beweries 🕩 *

The dehydropolymerisation of phenylsilane is investigated using group 4 metallocene amide complexes as catalysts. The dinuclear zirconocene amide complex $Cp_2Zr(NMe_2)(\mu-Me_3SiC_3SiMe_3)Zr(NMe_2)Cp_2$ (2) ($Cp = \eta^5$ -cyclopentadienyl) shows high activity in dehydrocoupling reactions, producing polyphenylsilanes with molecular weights ranging from 200 to 3000 g mol⁻¹ and linear-to-cyclic product ratios of up to 80 : 20. Likewise, different ratios of oligomers and polymers with different tacticities could be described. *Ansa*-zirconocene amide complexes possessing the ebthi (ebthi = 1,2-ethylene-1,1'-bis(η^5 -tetrahydroindenyl)) ligand systems were prepared and evaluated for catalytic dehydropolymerisation in comparison to the dinuclear catalyst system.

Received 8th August 2022 Accepted 8th September 2022

DOI: 10.1039/d2ra04955d

rsc.li/rsc-advances

Introduction

The catalytic formation of Si-Si bonds to produce inorganicorganic polymers and hybrid materials has been intensively studied since the 1980s.1-5 The special properties of polysilanes such as σ electron delocalisation have led to the application of these materials for the development of new ceramics, semiconductors and nonlinear optical materials.⁴ For converting silane-based monomers several different approaches are feasible.6-9 Catalytic dehydrocoupling of hydrosilanes represents an atom-efficient method compared to the Wurtz coupling that produces stoichiometric amounts of salts as waste products and shows a poor functional-group-tolerance.^{10,11} Early investigations focused on group 4 metallocene-based catalysts, although complexes of later transition metals were also studied and showed comparable catalytic performance in some cases.12-18 The main advantages are generally good yields (>90%), the possibility for ligand variation and postpolymerisation functionalisation.^{1,19,20} It should however be noted that typically low molecular weight polymers with illdefined tacticity and poor linear-to-cyclic ratios are obtained.¹ However, the utility of this approach for the construction of Si rich polymers containing poly(cyclosilane) units was recently demonstrated by Klausen and co-workers.^{21,22} For group 4 metallocene catalysis, experimental parameters like concentracatalyst deactivation pathways, tion effects, optimal

metallocene substitution patterns, and the pressure dependence on molecular weight, were studied in great detail in the past, mainly by the groups of Corey, Harrod and Tilley.12-14 The dehydropolymerisation of the primary silane PhSiH₃ using the system Cp₂ZrCl₂/n-BuLi was well-studied in the past, giving >99% polysilane with a mass distribution of $M_{\rm p}/M_{\rm w} = 3200/$ 1600 g mol⁻¹ and a ratio of linear/cyclic products of 65/35.²³⁻²⁶ These systems require the use of strong base for activation of the precatalyst. Formation of oligomers and polymers was described to occur via σ bond metathesis for group 4 metals.²⁷⁻²⁹ An alternative approach could be the use of well-defined highly reactive species such as metallocene alkyne complexes, silyl, alkyl, or amide complexes.27,30-33 In the area of dehydropolymerisation of PhSiH₃, only a handful of zirconium amide complexes were described as catalysts.34-36 Corey et al. have reported the mononuclear complex $Cp_2Zr(NMe_2)_2$ (1) as catalyst for the dehydropolymerisation of phenylsilanes (Scheme 1).34

Modification of the cyclopentadienyl scaffold is a common approach in group 4 metallocene chemistry, to synthesise



Scheme 1 Catalytic dehydropolymerisation of $PhSiH_3$ using different zirconocene amide complexes.

Leibniz-Institut für Katalyse e.V., Albert-Einstein-Str. 29a, 18059 Rostock, Germany. E-mail: fabian.reiss@catalysis.de; torsten.beweries@catalysis.de

[†] Electronic supplementary information (ESI) available: Experimental, crystallographic and spectroscopic details, SEC analysis, and catalytic data. CCDC 2181386 and 2181387. For ESI and crystallographic data in CIF or other electronic format see https://doi.org/10.1039/d2ra04955d

optically active compounds or polymers with well-defined tacticity.³⁷⁻³⁹ Ansa-zirconocene amide complexes have been reported by Jordan *et al.*, who demonstrated the selective synthesis of $[rac/meso-(ebi)Zr(NMe_2)_2]$ (ebi = 1,2-ethylene-1,1'bis(η^5 -indenyl)) by amine elimination.^{40,41} Likewise, this route furnishes other zirconocene amide complexes with an indenyl ligand system.^{42,43} Such complexes are used for a wide range of applications in asymmetric catalysis.⁴⁴ Jordan *et al.* described the polymerisation of propene by using $[rac-(ebi)Zr(NMe_2)_2]$ and $[rac-(sbi)Zr(NMe_2)_2]$ (sbi = dimethylsilyl-1,1'-bis(η^5 -indenyl))) with additional MAO activation.⁴⁵ The group showed that amide complexes are significantly less active compared to the chloriderelated systems.⁴⁵ Kim *et al.* described the formation of various cationic zirconocene species by using $[rac-(ebi)Zr(NMe_2)_2]$ as catalyst for polymerisation of propene.^{46,47}

Recently, our group synthesised a set of dinuclear zirconocene complexes, including the amide species $Cp_2Zr(NMe_2)(\mu-Me_3SiC_3SiMe_3)Zr(NMe_2)Cp_2$ (2) (Scheme 1) which exhibited high activity in the dehydrocoupling of $H_3B\cdot NMe_2H$.^{48–50} Dinuclear cooperative reactivity of both metal centers was discussed as an important mechanistic feature. Intrigued by the high activity of this complex at room temperature, we aimed at the study of this species for related dehydrocoupling reactions such as the well-known dehydropolymerisation of PhSiH₃. In this contribution, we describe the application of 2 as catalyst for the dehydropolymerisation to mononuclear complexes. Furthermore, the synthesis of a series of previously unknown *ansa*-zirconocene amide complexes is described, as well as the application of these complexes as single-component catalysts.

Results and discussion

Synthesis and characterisation of ansa-zirconocene amides

Based on the previously reported reaction conditions for the preparation of the dinuclear amide complex 2,⁴⁸ we carried out the reaction of [*rac*-(ebthi)ZrCl₂] (ebthi = 1,2-ethylene-1,1'-bis(η^5 -tetrahydroindenyl)) with two equivalents of LiNMe₂ in a similar fashion (Scheme 2). Formation of one main compound that shows three characteristic resonances in the ¹H NMR spectrum in 2 : 2 : 12 ratio (δ 6.08, 5.31 and 2.97 ppm, Fig. S4†) was observed. A single crystal X-ray diffraction (SC-XRD) analysis using crystals that were obtained from toluene at -78 °C



Scheme 2 Synthesis of ansa-zirconocene amide complexes.



Fig. 1 Molecular structures of complexes *rac-3* and *meso-4*. Selected bond lengths and angles **3**: Zr1–N1 2.1074(13), Zr1–N2 2.1065(13), Ct1–Zr1 2.284, Ct2–Zr1 2.286 [Å]; N1–Zr1–N2 95.09(5), Ct1–Zr1–Ct2 121.14, C_{ind1}–C_{et1}–C_{et2}–C_{ind2}–40.78(19)°. **4** Zr1–Cl1 2.4772(8), Zr1–N1 2.064(3), Ct1–Zr1 2.232, Ct2–Zr1 2.275 [Å]; N1–Zr1–Cl1 96.78(8), Ct1–Zr1–Ct2 123.55, C_{ind1}–C_{et1}–C_{et2}–C_{ind2}–46.2(4)°. Thermal ellipsoids correspond to 30% probability. Hydrogen atoms are omitted for clarity.⁵¹

confirms the assignment as $[rac-(ebthi)Zr(NMe_2)_2]$ (*rac-3*) (Fig. 1). ¹³C NMR analysis shows all typical resonances of the ebthi ligand system and a resonance at δ 48.5 ppm for the NMe₂ ligand which is in line with the value of δ 51.6 ppm found for complex 2 (Fig. S5†).

We next investigated the reaction of the *meso* isomer [*meso*-(ebthi)ZrCl₂] with two equivalents of LiNMe₂ in Et₂O at room temperature, aiming at the synthesis of a related bis(amide) complex. To our surprise, only one of the chloride ligands was replaced under these conditions, as evidenced by the ¹H NMR analysis, which shows resonances at δ 6.06, 5.38 and 2.82 ppm in a ratio of 2 : 2 : 6 (Fig. S12†). 2D NMR analysis revealed that all signals show correlation, confirming the presence of a single new species (Fig. S14 and S15†). Crystals of the highly air and moisture sensitive compound suitable for an SC-XRD analysis were obtained from benzene solution at room temperature and confirm the proposed structure of [*meso*-(ebthi)Zr(Cl)(NMe₂)] (*meso*-4) (Fig. 1).

We next varied the reaction conditions to investigate the direct synthesis of a meso-(ebthi) bis(amide) complex. By varying the temperature to 60 °C in Et₂O formation of bis(amide) compound meso-3 could be observed along with three new resonances at δ 3.01, 2.97 and 2.93 ppm in a ratio of 6 : 12 : 6. As the resonance at δ 2.97 ppm resembles that of the *rac*-(ebthi) complex rac-3 isomerisation of the metallocene scaffold is possible. Addition of further four equivalents of LiNMe2 results in full conversion of *meso-4* to furnish the desired bis(amide) complex [meso-(ebthi)Zr(NMe2)2] meso-3 in 80% NMR yield along with the rac-(ebthi) bis(amide) rac-3 (Fig. S7[†]). To optimise the synthesis conditions of meso-3 and to avoid the formation of rac-3, we next investigated the influence of different solvents. In aprotic non-coordinating solvents at -40 °C, the reaction was rather unselective and only mixtures containing both isomers could be obtained (Fig. S7[†]). In benzene, only a complex reaction mixture resulted, from which only a dark yellow oil could be isolated (Fig. S8†). Use of pentane for work up did not result in the formation of defined products

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Paper

(Fig. S9[†]). During work up in toluene with subsequent crystallisation from toluene/CH2Cl2 at -78 °C only the isomeric mixture could be isolated which converts to the racemic complex rac-3 as the main product at room temperature (Fig. S7[†]). Every route to separate the meso complex meso-3 only leads to the formation of the thermodynamically preferred rac complex *rac-3* ($\Delta_{\rm R} H^{\theta}(meso vs. rac) = -18.5$, $\Delta_{\rm R} G^{\theta}(meso vs. rac) =$ -14.8 kJ mol⁻¹)⁵² probably *via* ring-slippage of an indenvl unit.53 To investigate the steric hindrance in the meso compared to the rac ligand system a buried volume analysis was performed.54,55 The spheric sterical hindrance map shows that the global sterical demand is identical for meso-3 (buried volume $V_{\rm bur} = 54.9\%$) as for *rac-3* ($V_{\rm bur} = 55.0\%$, see ESI[†]). If the analysed space is decomposed into four equally sized quadrants (NE/SE/SW/NW), the main differences between the two ligand systems become apparent, as expected. The distribution of the space requirement values of $V_{\text{bur,quad.}} = 47.1/62.9/47.1/62.9$ (rac-3) and 45.2/47.4/63.0/64.1 (*meso-3*) agree with C_2 and C_3 symmetries of the metallocene scaffolds. Theoretically, meso-4 could exist in two isomeric forms that differ in the position of the chloride and amide ligands relative to the metallocene unit (N_{in}-Cl_{out} and N_{out}-Cl_{in}). As expected, the space requirement analysis of the two quadrants facing away from the metallocene pocket clearly shows the larger space requirement of the amide ligand which can be satisfied in the case of formation of the $N_{out}\text{-}Cl_{in}$ isomer $[N_{out}\text{:}~V_{bur(NE/SE)}\,=\,42.6/$ 44.8%, Clout: Vbur(NE/SE) 38.2/38.4%, see ESI†]. This was confirmed experimentally as only the thermodynamically preferred isomer N_{out} -Cl_{in} ($\Delta_R H^{\theta}(N_{in}$ -Cl_{out} vs. N_{out} -Cl_{in}) = -33.8, $\Delta_{\rm R}G^{\theta}({\rm N}_{\rm in}-{\rm Cl}_{\rm out} \ \nu s. \ {\rm N}_{\rm out}-{\rm Cl}_{\rm in}) = -32.9 \ {\rm kJ} \ {\rm mol}^{-1})$ is present in the crystal. In consequence the chloride ligand in meso-4 is sterically protected in the meso-(ebthi) pocket which explains the necessity of higher temperatures and larger amounts of LiNMe2 for formation of complex meso-3. Notably, attempts to prepare a dinuclear zirconocene amide complex from [(meso-(ebthi)ZrCl)₂(µ-Me₃SiC₃SiMe₃)]⁵⁶ also led to formation of the mononuclear complex meso-3 in low yield (Fig. S6[†]).

We next examined the selective formation of the mixed chloride/amide complex [*rac*-(ebthi)Zr(Cl)(NMe₂)] *rac*-4 by addition of one equivalent of LiNMe₂ to [*rac*-(ebthi)ZrCl₂] in Et₂O at room temperature. Selective formation of five new resonances at δ 6.16, 6.09, 5.54, 5.12 and 2.87 ppm in a 1:1:1:1:6 ratio suggests the formation of the desired mono(amide) species (Fig. S10†). ¹³C NMR analysis shows the characteristic amide resonance at δ 48.4 ppm (Fig. S11†). However, it was difficult to separate complex *rac*-4 from simultaneously formed bis(amide) *rac*-3 (9:1 ratio, Fig. S10†).

Catalytic dehydropolymerisation of PhSiH₃

Catalytic studies using complex 2. The dehydropolymerisation of PhSiH₃ (1.85 mmol) was studied using 0.2 mol% of dinuclear complex 2 without solvent at room temperature in an open reaction vessel with pressure compensation and volumetric monitoring of the reaction system (Scheme 1).⁵⁷ The colour of the reaction mixture changed from bright yellow to



Fig. 2 Volumetric curves of dehydropolymerisation of $PhSiH_3$ using complex 2. Conditions: room temperature, no solvent, 1.85 mmol $PhSiH_3$. The inset shows the induction period that was detected in all catalytic runs (units were removed for clarity and are identical to the full plot).

dark yellow after addition of PhSiH₃ and a glassy yellow solid was obtained at maximum conversion of the substrate after 3 h (Fig. 2). According to the amount of evolved hydrogen no full conversion of PhSiH₃ could be achieved $(n(H_2)/n_0(PhSiH_3)) =$ 0.90). Variation of the catalyst concentration showed that a similar degree of conversion was observed at 0.1 mol%. To our surprise, catalytic runs with 0.4 mol% of 2 gave much lower conversion and the reactions were considerably slower. Reactions of 2 with four equivalents of PhSiH₃ suggest a complete deactivation and no reaction could be observed under these conditions (Fig. S42[†]). In all cases an induction period was observed when using 2 (Fig. 2). This behaviour contrasts with dehydropolymerisation reactions of silanes using the mononuclear 1 where no induction period was observed and the conversion increased with higher catalyst concentrations (Fig. S52[†]). Differences in the activation and/or reaction mechanism must thus be assumed when going from the mononuclear (1) to the dinuclear precatalyst (2). Initial monomerisation of 2 could play a role, however, we have no experimental evidence for this activation step. In fact, cleavage of 2 should result in formation of the alkyne Me₃SiCH₂C₂SiMe₃, which was not observed by ¹H NMR spectroscopy.

Control experiments showed that an open reaction setup with pressure compensation and continuous stirring of the reaction solution was required to perform the dehydropolymerisation (Fig. S33[†]). A significantly decreased activity was found when performing the reaction in solution (Fig. S34[†]).⁵⁸ To ensure that the catalytic activity of **2** is based on activation and conversion of the silane at the Zr centre we performed NMR scale reactions of PhSiH₃ with different amine bases. NMR analysis of PhSiH₃ (1.85 mmol) in the presence of tetramethylethylenediamine (0.37 mmol) or LiNMe₂ (0.06 mmol) shows no conversion of the substrate (Fig. S43-S48⁺), indicating that the presence of the metal centre is essential for the dehydropolymerisation of PhSiH₃ and the basicity of the NMe_2 group is not sufficient to activate the silane. In line with literature data of reactions using group 4 metal complexes, sterically and electronically different secondary aryl silanes or

alkyl silanes such as Ph_2SiH_2 , Et_2SiH_2 , or *n*-BuSiH₃ showed no conversion (Fig. S49, S50 and S51†).⁵⁹⁻⁶¹ When *p*-tolSiH₃ (*p*-tol = *p*-CH₃-C₆H₄) was used the reaction time increased drastically and only low conversion could be found at room temperature. The formation of minor amounts of polymer was confirmed by ¹H NMR spectroscopy (Fig. S32†).

Catalytic studies using ansa-zirconocene amides. We have next investigated the dehydropolymerisation of PhSiH₃ using the ansa-zirconocene amide complexes rac/meso-3/4 under the same reaction conditions, albeit with a higher concentration of 0.4 mol%, thus providing the same amount of Zr centres per silane as for 2. With complex rac-3 H₂ evolution could be detected by ¹H NMR spectroscopy and was confirmed by gas chromatography (Fig. S35[†]). However, the formation of oligomeric or polymeric silanes was neglectable under these reaction conditions or at 60 °C (Fig. S35[†]). When increasing the catalyst concentration to 0.8 mol% of rac-3 the formation of a mixture of oligomeric silanes could be observed by ¹H and ²⁹Si DEPT NMR spectroscopy at 60 °C after five days. (Fig. S36–S38†). The drastic conditions required as well as the poor reactivity can be rationalised by the increased steric protection of the two amide ligands, which is evident in the buried volume analysis of rac-3 with $V_{\rm bur}$ 62.9%. As already shown, only the basic properties of the amide ligands do not lead to the conversion of the monomer (vide infra). No gas evolution or variations in the viscosity could be observed when using meso-4 at room temperature (Fig. S39[†]), which is in line with a sterically protected chloride ligand placed in the meso pocket (vide infra).

In contrast immediate H₂ evolution could be observed in the catalytic reaction using complex rac-4 (0.4 mol%) at room temperature with subsequent formation of a highly viscous brownish waxy solid. Volumetric measurement showed a reaction time of three hours with approximately 0.95 eq. of H_2 evolved before the stirring bar was fixed in the highly viscous polymer (Fig. S53[†]). Full conversion of PhSiH₃ could be determined by NMR spectroscopy (Fig. S40[†]). The significant difference in reactivity between isomeric meso-4 and rac-4 could also be attributed to the steric protection of the chloride ligand in meso-4 (vide infra). In consequence, this could result in more facile abstraction of the chloride ligand in rac-4, that could lead to highly reactive zirconocene(m) fragments.62 Such species were discussed as an active species in dehydrocoupling of silanes for the less sterically demanding zirconocenes [Cp2Zr] and [CpCp*Zr].^{25,63} In summary, both the mono chloride functionality as well as the accessibility of this in rac-4 could contribute to the higher activity of this ansa zirconocene.

Molecular weight of polysilanes

The molecular weights of the obtained polymers were determined by size exclusion chromatography (SEC) with calibration using polystyrene as standard. Polymer samples were isolated as glassy yellow solids, soluble in most organic solvents such as benzene or THF and analysed by SEC and ²⁹Si NMR spectroscopy (*vide infra*). The molecular weights of polymers isolated from dehydropolymerisation reactions with 2 as catalyst ranged from $M_n = 2100-3000$ g mol⁻¹, depending on the catalyst

[Zr]	<i>c</i> [mol%]	$M_{\rm n} [{ m g \ mol}^{-1}]$	$M_{\rm w} [{ m g \ mol}^{-1}]$	PDI	L/C^a
1	0.4	2650	3935	1.46	83:17
	0.8	2780	4690	1.68	88:12
2	0.1	2000-2200	3160	1.50	85:15
	0.2	2850-3000	5637	1.97	89:11
	0.4	2785-2910	5082	1.74	83:17
rac-4	0.4	2600	3200	1.22	85:15
^a Linea	r-to-evelic rat	ios (L/C) were det	termined by ¹ H N	MR spec	troscopy.

concentration (Table 1). SEC profiles of the polymers show minor tailing in the low molecular weight region (Fig. S63– S65†). Formation of low molecular weight cyclic byproducts in combination with linear polysilanes and the subsequent separation was described before for related systems and could serve as an explanation for this observation.^{12–14,23,29,64} The exact linear-to-cyclic rations (L/C) were determined by SEC and from direct integration of ¹H NMR signals corresponding to Si–H fragments in linear (δ 4.3–4.9 ppm) and cyclic (δ 4.9–5.3 ppm)

structures (Table 1).^{23,65,66} An increase in catalyst concentrations results in the formation of higher molecular weight polymers, which is in line with previously reported results using the mononuclear complex **1** (Table 1, Fig. S61 and S62†).^{34,67} Moreover, higher catalyst concentration leads to longer reaction times and a decrease in conversion (Fig. 2, *vide supra*). Thus, catalyst concentrations of 0.2 mol% were found to be optimal with respect to monomer conversion and molecular weight distribution. Polydispersity indices (PDI) are in the range of 1.22–1.97, suggesting the presence of relatively well-defined polysilanes with narrow mass distribution (Fig. S61–S65†).

We have next analysed the kinetics of polymer growth. Therefore, we quenched the dehydropolymerisation reactions (0.2 mol% 2) at different stages of conversion by addition of THF, which inhibits the reaction. SEC analysis of the reaction mixture after 60 minutes shows a broad low intensity peak corresponding to molecular weights in the range $M_n = 150-400 \text{ g mol}^{-1}$ (Table 2, Fig. S67†). After 90 minutes a significant increase in $M_n = 1300-1500 \text{ g mol}^{-1}$ was found (Table 2, Fig. S68†). Molecular weights determined at full conversion (t = 3 h) correspond to the values given in Table 2 (Fig. S69†). The presence of low molecular weight oligomers at early stages of the reaction and the significant increase in M_n after 60 min indicates that a chain growth mechanism is not likely for the dehydropolymerisation of PhSiH₃ with 2. Instead, a step growth

Table 2Conversion vs. M_n analysis									
[Zr]	c [mol%]	$M_{\rm n} \left[{ m g mol}^{-1} \right]$	$M_{\rm w} \left[{ m g mol}^{-1} ight]$	PDI	Time [min]				
1	0.4	200	400	2.02	5				
		2685	3935	1.46	20				
	0.2	140 - 400	240-400	1.70	60				
2		1340-1550	2850-3000	2.00	90				
		2900-3000	5600	1.95	180				

mechanism could operate. The same scenario could play a role for complex 1, which showed $M_n = 200-400 \text{ g mol}^{-1}$ when measured after 5 minutes (Table 2).

When performing the dehydropolymerisation with higher catalyst concentrations we could observe that the catalyst was still present in the polymeric mixture (Fig. S22†). We have therefore added a second portion of PhSiH₃ (1.85 mmol) after a first catalytic run (0.4 mol% 2) and found that this leads to further conversion to glassy yellow polymer (Fig. S25†). ¹H NMR analysis of the isolated polymer using 0.4 mol% 2 showed that the catalyst was still intact after further monomer addition (Fig. S25–S27†). The addition of a second portion of monomer does not lead to an increase in molecular weight ($M_n = 2500-2600 \text{ g mol}^{-1}$, Fig. S66†), indicating that although the Zr catalyst is still present, reactive polysilane chain ends are not available for further polymer growth.

SEC analysis of polymer fractions obtained with 0.8 mol% *rac*-3 at 60 °C shows only the formation of low molecular weight oligomers ($M_n = 200-450 \text{ g mol}^{-1}$) (Fig. S70†). Polymer isolated using 0.4 mol% *rac*-4 as catalyst showed two SEC signals (2100–2300 and 260–400 g mol⁻¹, Fig. S71†). Compared to 2 low molecular weight fragments dominate, suggesting the formation of cyclic/linear oligomers (Fig. S71†).

Microstructure of isolated polysilanes

The microstructures of isolated polymers were analysed by ²⁹Si DEPT45 and DEPT135 NMR spectroscopy. Polymers that were isolated from reactions using 0.1–0.4 mol% **2** show a complex pattern of resonances in the ²⁹Si DEPT spectra (Fig. S16–S24†). Broad signals in the range of δ –55 to –65 ppm correspond to the typical, mainly atactic structure of the polymer mixture (Fig. 3).^{29,68} ²⁹Si DEPT135 analysis shows that signals from δ –60 to –65 ppm correspond to tertiary Si_n(Ph-SiH)Si_n units (Fig. 3).^{23,29,65} The DEPT135 experiment also confirmed the phase-shifted resonances at δ –56 to –58 ppm as –SiH₂ end groups (Fig. 3).²⁹ Polymer samples synthesised with 0.2 mol% of **2** showed the most well-defined resonance patterns, which can



Fig. 3 Stacked ²⁹Si DEPT135 NMR spectra of poly(phenylsilane) obtained from catalytic dehydropolymerisation of PhSiH₃ using 0.2 mol% **2** (top), 0.4 mol% *rac*-4 (bottom).

be divided into a high-intensity region from δ –60 to –63 ppm and a lower-intensity region at δ –63 to –65 ppm (Fig. S21†),^{62,68} the former corresponding to β silyl centres.⁶ Polymer fractions obtained from reactions using 0.1 and 0.4 mol% 2 show a significantly higher portion of linear/cyclic oligomers in the range δ –50 to –55 ppm (Fig. S17, S18, S23 and S24†).⁶² In the case of 0.1 mol% 2, this could be the explanation for the lower molecular weight (Table 1, Fig. S17and S18†).

Investigations of polymer microstructure have been done before using deconvolution processes.^{6,29,68} Tertiary Si_n(Ph-SiH) Si_n units can be categorised into stereospecific triads, namely linear isotatic (mm), linear atactic (mr) and linear syndiotactic polysilane (rr) (Fig. 3).²⁹ Although reasonably good separation of the ²⁹Si DEPT resonances was observed for samples prepared with 0.2 mol% **2** (Fig. 3), the low resolution and the overlap of resonances made it impossible to analyse the tacticity of the polymer on the basis of these NMR spectra (Fig. S16–S24†).

²⁹Si DEPT NMR analysis of polymers obtained from reactions using ansa-zirconocene amide complex rac-3 suggests the presence of an oligomeric mixture with a complex resonance pattern (Fig. S36-S38[†]). Formation of the products of PhSiH₃ dimerisation (δ –61.7 ppm, SiH₂), trimerisation (δ –59.1, SiH and -68.5 ppm, SiH₂), and tetramerisation (two isomers, two sets of resonances at δ –59.0, SiH and –65.0 to –65.5 ppm, SiH₂) could be detected (Fig. S36-S38[†]).²⁵ The formation of higher oligomers can also be assumed, however the separation of the ²⁹Si DEPT resonances is not sufficient for a detailed assignment (Fig. S37 and S38[†]). These results are consistent with the previously reported formation of two diastereomers of the tetramer, showing that the coupling of the Si-Si bonds proceeds without stereoselectivity.25 29Si DEPT spectra of samples produced with 0.4 mol% rac-4 show the formation of isotatic and atactic polymer fractions with sharp resonances in the range of δ -61.0 ppm (Fig. 3, S40, S41[†]). Compared to materials prepared with 2, the distribution of oligomers and polymers was better resolved in the range upfield of δ -61.0 ppm (Fig. 3, S41[†]). This result is consistent with SEC data indicating a larger amount of oligomers isolated using rac-4 (Fig. S71,[†] vide infra). The C_2 chirality of the ebthi ligand system has a significant effect on the tacticity and the formation of low molecular weight oligomers, as previously shown in the literature.25

Conclusion

The dinuclear zirconocene complex 2 shows selectivity for the dehydropolymerisation of phenylsilane that is comparable to that of the parent mononuclear analog $Cp_2Zr(NMe_2)_2$, producing a polymer that possesses isotactic, atactic and syndiotactic structures. The molecular weights of the isolated polyphenylsilane products are comparable to those prepared by previously studied related catalyst systems, which again shows the previously discussed limitations of this approach of silane dehydropolymerisation. SEC analysis of the polymers at varying conversion suggests step growth as a likely scenario for polymer formation. In contrast to previously reported highly active mononuclear complex $Cp_2Zr(NMe_2)_2$, no decomposition of the

dinuclear catalyst 2 was observed, and the catalyst retains its activity at high conversion of substrate. As a consequence, we could show that selective polymer formation with a well-defined mass distribution can be observed after addition of further monomer. *Ansa*-zirconocene amide complexes prepared in this study were tested as catalysts and the activity of these species was found to be strongly dependent on the symmetry of the metallocene fragment and the presence of amide/chloride ligands. Only the C_2 symmetric mixed amide/chloride complex *rac*-4 showed activity that was comparable to that of dinuclear 2. Future studies will aim at evaluation of the potential of the herein reported and further dinuclear group 4 metallocene complexes for dehydrocoupling reactions.

Author contributions

K. L., F. R. and T. B. conceived and conceptualised the project. K. L. performed the experiments and analysed the data. A. S. performed the SC-XRD and F. R. the DFT study. F. R. and T. B. supervised the project. T. B. acquired funding. K. L., F. R. and T. B. prepared and revised the manuscript.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

We thank our technical and analytical staff, in particular Hanan AlHamwi and PD Dr Wolfgang Baumann for assistance. We thank Sihan Li (LIKAT) for providing $[(meso-(ebthi)ZrCl)_2(\mu-Me_3SiC_3SiMe_3)]$ as well as Lanxess Organometallics GmbH (Bergkamen, Germany) for generously donating *ansa*-metallocene starting materials. Financial support by the Deutsche Forschungsgemeinschaft (project code 419924354) is gratefully acknowledged.

Notes and references

- 1 J. Koe, M. Fujiki, *Organosilicon Compounds*, ed. V. Y. Lee, Academic Press, 2017, pp. 219–300.
- 2 J. R. Koe, *Comprehensive Organometallic Chemistry III*, ed. D. M. P. Mingos and R. H. Crabtree, Elsevier, Oxford, 2007, pp. 549–649.
- 3 H. Jamshidi and A. Rahimi, *Phosphorus, Sulfur Silicon Relat. Elem.*, 2006, **181**, 2565–2576.
- 4 R. D. Miller and J. Michl, Chem. Rev., 1989, 89, 1359-1410.
- 5 J. Koe, Polym. Int., 2009, 58, 255-260.
- 6 R. G. Jones, R. E. Benfield, P. J. Evans, S. J. Holder and J. A. M. Locke, *J. Organomet. Chem.*, 1996, **521**, 171–176.
- 7 K. Matyjaszewski, Y. L. Chen and H. K. Kim, *J. Inorg.* Organomet. Polym., 1988, **360**, 78–88.
- 8 K. Sakamoto, K. Obata, H. Hirata, M. Nakajima and H. Sakurai, *J. Am. Chem. Soc.*, 1989, **111**, 7641–7643.
- 9 M. Ishifune, C. Sana, M. Ando and Y. Tsuyama, *Polym. Int.*, 2011, **60**, 1208–1214.

- 10 T. J. Clark, K. Lee and I. Manners, *Chem.–Eur. J.*, 2006, **12**, 8634–8648.
- 11 J. F. Harrod, Coord. Chem. Rev., 2000, 206-207, 493-531.
- 12 J. Y. Corey, Adv. Organomet. Chem., 2004, 51, 1-52.
- 13 F. Gauvin, J. F. Harrod and H. G. Woo, *Adv. Organomet. Chem.*, 1998, **42**, 363–405.
- 14 T. D. Tilley, Acc. Chem. Res., 1993, 26, 22-29.
- 15 M. Minato, T. Matsumoto, M. Ichikawa and T. Ito, Chem. Commun., 2003, 2968–2969.
- 16 F.-G. Fontaine and D. Zargarian, *Organometallics*, 2002, 21, 401–408.
- 17 E. E. Smith, G. Du, P. E. Fanwick and M. M. Abu-Omar, Organometallics, 2010, 29, 6527–6533.
- 18 N. T. Mucha and R. Waterman, *Organometallics*, 2015, 34, 3865–3872.
- 19 J. P. Banovetz, Y. L. Hsiao and R. M. Waymouth, *J. Am. Chem. Soc.*, 1993, **115**, 2540–2541.
- 20 Y.-L. Hsiao and R. M. Waymouth, J. Am. Chem. Soc., 1994, 116, 9779–9780.
- 21 F. Fang, Q. Jiang and R. S. Klausen, *J. Am. Chem. Soc.*, 2022, **144**, 7834–7842.
- 22 C. P. Folster and R. S. Klausen, *Polymer Chemistry*, 2018, 9, 1938–1941.
- 23 Y. Obora and M. Tanaka, J. Organomet. Chem., 2000, 595, 1–11.
- 24 J. Y. Corey and X. H. Zhu, Organometallics, 1992, 11, 672-683.
- 25 V. K. Dioumaev, K. Rahimian, F. Gauvin and J. F. Harrod, Organometallics, 1999, 18, 2249–2255.
- 26 V. K. Dioumaev and J. F. Harrod, *Organometallics*, 1994, 13, 1548–1550.
- 27 H. G. Woo and T. D. Tilley, J. Am. Chem. Soc., 1989, 111, 3757-3758.
- 28 H. G. Woo, J. F. Walzer and T. D. Tilley, J. Am. Chem. Soc., 1992, 114, 7047–7055.
- 29 B. J. Grimmond and J. Y. Corey, *Organometallics*, 1999, **18**, 2223–2229.
- 30 F. Lunzer, C. Marschner, B. Winkler, N. Peulecke, W. Baumann and U. Rosenthal, *Monatsh. Chem.*, 1999, 130, 215–219.
- 31 H. Hisako, O. Sachiko and K. Mitsuo, *Chem. Lett.*, 2000, **29**, 188–189.
- 32 J. P. Banovetz, H. Suzuki and R. M. Waymouth, *Organometallics*, 1993, **12**, 4700–4703.
- 33 J. F. Harrod and S. S. Yun, Organometallics, 1987, 6, 1381– 1387.
- 34 Q. Wang and J. Y. Corey, Can. J. Chem., 2000, 78, 1434-1440.
- 35 X. Liu, Z. Wu, Z. Peng, Y.-D. Wu and Z. Xue, *J. Am. Chem. Soc.*, 1999, **121**, 5350–5351.
- 36 K. A. Erickson, M. P. Cibuzar, N. T. Mucha and R. Waterman, *Dalton Trans.*, 2018, 47, 2138–2142.
- 37 W. Asim, A. S. Waheeb, M. A. Awad, A. M. Kadhum, A. Ali,
 S. H. Mallah, M. A. Iqbal and M. M. Kadhim, *J. Mol. Struct.*, 2022, **1250**, 131925.
- 38 M. A. Bau, S. Wiesler, S. L. Younas and J. Streuff, *Chem.-Eur. J.*, 2019, 25, 10531–10545.
- 39 A. Razavi, Polyolefins: 50 years after Ziegler and Natta II: Polyolefins by Metallocenes and Other Single-Site Catalysts,

ed. W. Kaminsky, Springer Berlin Heidelberg, Berlin, Heidelberg, 2013, pp. 43–116.

- 40 G. M. Diamond, R. F. Jordan and J. L. Petersen, *Organometallics*, 1996, **15**, 4030–4037.
- 41 G. M. Diamond, R. F. Jordan and J. L. Petersen, *J. Am. Chem. Soc.*, 1996, **118**, 8024–8033.
- 42 J. N. Christopher, G. M. Diamond, R. F. Jordan and J. L. Petersen, *Organometallics*, 1996, **15**, 4038–4044.
- 43 E. Polo, R. M. Bellabarba, G. Prini, O. Traverso and M. L. H. Green, *J. Organomet. Chem.*, 1999, 577, 211–218.
- 44 O. Olabisi, M. Atiqullah and W. Kaminsky, J. Macromol. Sci., Polym. Rev., 1997, 37, 519–554.
- 45 I. Kim and R. F. Jordan, Macromolecules, 1996, 29, 489-491.
- 46 I. Kim, J. Macromol. Sci., Part A: Pure Appl.Chem., 1998, 35, 293-304.
- 47 I. Kim and G. Nam Hwang, J. Macromol. Sci., Part A: Pure Appl.Chem., 1998, 35, 1987–2008.
- 48 K. Lindenau, N. Jannsen, M. Rippke, H. Al Hamwi, C. Selle, H.-J. Drexler, A. Spannenberg, M. Sawall, K. Neymeyr, D. Heller, F. Reiß and T. Beweries, *Catal. Sci. Technol.*, 2021, **11**, 4034–4050.
- 49 M. Trose, M. Reiß, F. Reiß, F. Anke, A. Spannenberg, S. Boye, A. Lederer, P. Arndt and T. Beweries, *Dalton Trans.*, 2018, 47, 12858–12862.
- 50 F. Reiß, M. Reiß, A. Spannenberg, H. Jiao, W. Baumann, P. Arndt, U. Rosenthal and T. Beweries, *Chem.-Eur. J.*, 2018, **24**, 5667–5674.
- 51 For clarity, we have shown only one isomer of the asymmetric unit. The asymmetric unit contains three isomers with disorders in the ebthi ligand system (Fig. S54[†]).
- 52 We optimized the structures, considering empirical dispersion correction, on a double zeta basis set, followed by triple zeta basis set single point calculations. Geometries were confirmed to be local minima on the potential energy surface by harmonic vibration frequency

calculations on the same level of theory (B3LYP/GD3BJ/ def2svpp//def2tzvp).

- 53 J. M. OConnor and C. P. Casey, *Chem. Rev.*, 1987, 87, 307– 318.
- 54 L. Falivene, R. Credendino, A. Poater, A. Petta, L. Serra, R. Oliva, V. Scarano and L. Cavallo, *Organometallics*, 2016, 35, 2286–2293.
- 55 L. Falivene, Z. Cao, A. Petta, L. Serra, A. Poater, R. Oliva, V. Scarano and L. Cavallo, *Nat. Chem.*, 2019, **11**, 872–879.
- 56 X. Shi, S. Li, M. Reiß, A. Spannenberg, T. Holtrichter-Rößmann, F. Reiß and T. Beweries, *Chem. Sci.*, 2021, 12, 16074–16084.
- 57 T. Beweries, J. Thomas, M. Klahn, A. Schulz, D. Heller and U. Rosenthal, *ChemCatChem*, 2011, **3**, 1865–1868.
- 58 M. Horacek, J. Merna, R. Gyepes, J. Sykora, J. Kubista and J. Pinkas, *Collect. Czech. Chem. Commun.*, 2011, 76, 75–94.
- 59 C. T. Aitken, J. F. Harrod and E. Samuel, *J. Am. Chem. Soc.*, 1986, **108**, 4059–4066.
- 60 C. Aitken, J. F. Harrod and E. Samuel, *J. Organomet. Chem.*, 1985, **279**, C11–C13.
- 61 W. H. Campbell, T. K. Hilty and L. Yurga, *Organometallics*, 1989, 8, 2615–2618.
- 62 B. J. Grimmond and J. Y. Corey, *Inorg. Chim. Acta*, 2002, **330**, 89–94.
- 63 V. K. Dioumaev and J. F. Harrod, *Organometallics*, 1997, **16**, 2798–2807.
- 64 J. P. Banovetz, K. M. Stein and R. M. Waymouth, Organometallics, 1991, 10, 3430–3432.
- 65 N. Choi, S.-y. Onozawa, T. Sakakura and M. Tanaka, *Organometallics*, 1997, **16**, 2765–2767.
- 66 P. T. K. Lee, M. K. Skjel and L. Rosenberg, *Organometallics*, 2013, **32**, 1575–1578.
- 67 Details on NMR spectroscopy of polymers using complex 1 are given in the supporting information (Fig. S28–S31[†]).
- 68 B. J. Grimmond, N. P. Rath and J. Y. Corey, *Organometallics*, 2000, **19**, 2975–2984.