Catalysis Science & Technology

PAPER

Check for updates

Cite this: Catal. Sci. Technol., 2023, 13, 5248

Co-activation of methane and nitrogen to acetonitrile over MoC_x/Al_2O_3 catalysts[†]

Korawich Trangwachirachai, 跑^a I-Ting Kao,^a Wei-Hsiang Huang,^b Chi-Liang Chen 🔟^b and Yu-Chuan Lin 🔟^{*a}

Methane and nitrogen are regarded as the most abundant sources of hydrocarbons and nitrogen, respectively. Both compounds exhibit high stability due to the presence of daunting C-H and N=N bond energies of 439 and 945 kJ mol⁻¹, respectively, leading to their abundance. This study investigates the co-activation of methane and nitrogen using Al_2O_3 -supported MoC_x catalysts (1, 5, and 10 wt%) to produce acetonitrile (ACN) at ambient pressure. It was found that the optimum methane conversion (26.1%) and turnover frequency (TOF) of ACN (15.3 h⁻¹) were achieved at 750 °C using 1 wt% Mo loading. To alleviate catalyst deactivation resulting from coking, H₂ co-feeding was implemented and found to effectively sustain the on-stream activity for 50 hours. A plausible mechanism for ACN production, which occurs on the MoC-like surface, was proposed.

Received 28th April 2023, Accepted 4th August 2023

DOI: 10.1039/d3cy00585b

rsc.li/catalysis

Introduction

Methane (CH₄), the major component of natural gas, shale gas, and biogas, has long been used as a heat resource by combustion.¹ Because of its abundance, CH₄ is considered an important building block in the production of value-added chemicals.^{2,3} For example, CH₄ can be converted to syngas (CO and H_2) by steam or dry reforming⁴⁻⁷ and further converted to hydrocarbons by Fischer-Tropsch synthesis.^{8,9} CH₄ can also be converted to olefins, aromatics, or oxygenated compounds (e.g., formaldehyde and methanol) by non-oxidative pyrolysis, dehydroaromatization, or selective partial oxidation.9-11 However, the chemical inertness and high C-H bond dissociation energy of CH4 hinder its conversion to chemicals.⁹ Fig. 1 shows the existing routes for catalytic CH₄ conversion, including CH_4 to olefins, aromatics, and hydrogen (MTO, MTA, and MTOAH), oxidative coupling (OCM), and dehydroaromatization (MDA).

Besides the conventional reforming processes (*e.g.*, steam and dry reforming), limited studies have been dedicated to the direct conversion of CH_4 to chemicals through nonoxidative routes. McFarland *et al.* reported the production of H_2 and solid carbon derived from CH_4 catalyzed by molten metal alloys.¹² The catalysts were prepared by dissolving active metals (Ni, Pd, and Pt) in low-meltingtemperature metal solvents (Sn, Pb, Bi, In, and Ga) at temperatures below 1000 °C. 27 mol% Ni in Bi was the most active catalyst, achieving a $1.7 \times 10^{-8} \text{ mol}_{H_2} \text{ cm}^{-2} \text{ s}^{-1}$ hydrogen production rate with more than 95% selectivity at 950 °C. The Kopyscinski group studied silica-supported GaN prepared by ammonia nitridation for CH₄ conversion to ethylene.¹³ They found that CH₄ can be converted to ethylene at above 700 °C. Our group recently discovered that GaN made by co-pyrolyzing gallium nitrate and organic nitrogen compounds (e.g., melamine, melem, and $g-C_3N_4$) could convert CH4 to acetonitrile (ACN).14,15 The impact of particle size of GaN and residual CN species (including C=N and C=N) on the enhancement of ACN production was found to be significant. However, it is worth noting that the residual CN species cannot be regenerated during the conversion process and gradually get depleted.

ROYAL SOCIETY OF CHEMISTRY

View Article Online

Currently, ACN is obtained primarily as a by-product (approximately 2–4%) from acrylonitrile synthesis known as the Sohio process.¹⁶ This results in a comparatively low ACN



Fig. 1 Existing routes of CH₄ conversion to chemicals.²

^a Department of Chemical Engineering, National Cheng Kung University, Tainan 70101, Taiwan. E-mail: yclin768@mail.ncku.edu.tw

^b National Synchrotron Radiation Research Center, Hsinchu 30076, Taiwan

 $[\]dagger$ Electronic supplementary information (ESI) available: Time on stream (TOS) profiles and N_2 adsorption/desorption isotherms. See DOI: https://doi.org/ 10.1039/d3cy00585b

Catalysis Science & Technology

output that may not meet the escalating demand for ACN. In 2021, the global ACN market was valued at USD 264 million and is expected to grow at an annual rate of 5.5%.¹⁷ Therefore, exploring alternative routes for ACN synthesis to meet the growing demand is needed. The advent of the shale gas revolution has led to a significant increase in natural gas production and a subsequent decline in CH₄ prices.^{18,19} In 2017, the price of ACN in the United States was approximately nine times higher than that of CH₄.²⁰ Accordingly, the conversion of CH₄ to ACN should be worth exploring.

Taking the Mars-van Krevelen redox cycle (Fig. 2) as an example,²¹ the oxide catalyst delivers its mobile oxygen to partially oxidize the reactant to form an O-containing product, leaving the reduced catalyst in the first half of the cycle. Then, the reduced catalyst is re-oxidized by gaseous oxygen, fulfilling the redox cycle.

For the production of ACN via CH4 conversion over supported GaN catalysts, only the first half of the redox cycle is completed. The addition of ammonia as a co-feed was expected to facilitate the remaining half of the cycle. However, the production of ACN was significantly reduced with even small amounts of co-fed NH₃ due to the in situ formed H₂ from NH₃ decomposition.¹⁴ Therefore, using N₂ as a nitrogen source for ACN synthesis seems to be the most promising approach. In other words, a highly effective CH₄ conversion catalyst for ACN production must be capable of activating CH4 and N2 simultaneously. Tiwari et al. reported that CH4 and N2 could be activated simultaneously over a K-doped Ru catalyst to co-produce ammonia and ethylene.²² The in situ H₂ produced from CH₄ conversion was used as a hydrogen source for ammonia synthesis. However, coke is formed in parallel with hydrogen production, resulting in discontinuous ammonia productivity. Nevertheless, this study introduces the possibility of converting two inert compounds into valueadded chemicals.

The crucial step in N_2 activation is the cleavage of the $N \equiv N$ bond. Mo_2C has been demonstrated to be active in ammonia synthesis.²³ As predicted by the d-band model, transition metal carbides with vacant d orbitals exhibit



comparable adsorption behavior towards electron-rich adsorbates.²⁴ In addition, the sp bands of transition metals in metal carbides would hybridize with the d bands from the transition metals and with the s bands from the carbon.²⁵ The extra hybridized orbitals provide more opportunities for back-donation to the π orbitals of the adsorbates, making Mo₂C a promising N₂ activation active site. Moreover, Mo₂C was found as an active site in CH_4 dehydroaromatization.²⁶⁻²⁸ Accordingly, the Mo₂C catalyst should have strong potential for simultaneous activation of CH_4 (C-H) and N_2 (N=N) to synthesize ACN.

In this study, the catalytic conversion of CH_4 and N_2 to ACN using Al_2O_3 -supported MoC_x catalysts was investigated. We found that the catalyst could simultaneously convert both CH_4 and N_2 to produce ACN. The optimum operating temperature and Mo loading were investigated. Catalyst deactivation was suppressed by introducing H_2 into the reaction stream, allowing the catalytic activity to be maintained for 50 h. In addition, a plausible mechanism for ACN formation was proposed to occur *via* the Mo-terminated MoC-like surface structure, which facilitates the reaction between CH_4 and N_2 . Kinetics analysis was performed to support the proposed mechanism, in which the surface reaction was suggested to be rate-limiting. The goal of this research is to validate the feasibility of converting two inert compounds (CH_4 and N_2) into a valuable chemical (ACN).

Experimental section

Chemicals

Alumina (Al₂O₃, 99.5%), ammonium heptamolybdate ($(NH_4)_6$ -Mo₇O₂₄, 99.95%), molybdenum oxide (MoO₃, 99.95%), and commercially available molybdenum carbide (com-Mo₂C, 99.5%) were obtained from Merck, J. T. Baker, Alfa Aesar, and Sigma-Aldrich, respectively. CH₄ (99.999%), argon (Ar, 99.999%), nitrogen (N₂, 99.999%), and hydrogen (H₂, 99.999%) were purchased from Air Products. Al₂O₃ was calcined at 750 °C before being used as a support. All chemicals were used as received.

Catalyst preparation

Al₂O₃-supported MoC_x catalysts were prepared by incipientwetness impregnation followed by carbonization. Briefly, a designated amount of ammonium heptamolybdate solution (0.5 M) was added dropwise onto the Al₂O₃ support to obtain *x*Mo/Al₂O₃ (x = 1, 5, or 10 wt%). The impregnated catalyst was dried at 110 °C overnight and was then calcined at 750 °C (5 °C min⁻¹) for 5 h. Afterward, the calcined catalyst was sieved and crushed into 40–80 mesh particles. The carbonization treatment was performed before activity evaluation.

Characterization

An inductively coupled plasma mass spectrometer (ICP-MS, THERMOELEMENT XR) was utilized to quantify the Mo

Paper

content. X-ray diffraction (XRD) patterns were recorded at 40 mA and 4 kV using a diffractometer (Rigaku D/Max-IIB) equipped with Ni-filtered Cu K α (λ = 1.5406 Å) radiation. A transmission electron microscope (TEM, JEOL JEM-2010) equipped with an energy dispersive X-ray spectrometer (EDS) was used to analyze the morphology of MoC_x particles. N₂ sorption isotherms were analyzed using an automated physisorption analyzer (ASAP 2020 Plus, Micromeritics). The surface area was evaluated by applying the Brunauer–Emmett–Teller (BET) method at a relative pressure of 0.01–0.1.

X-ray absorption spectroscopy (XAS) at the Mo *K*-edge was performed at the Taiwan Photon Source (TPS) 44A beamline of the National Synchrotron Radiation Research Center (NSRRC), Taiwan. Mo-foil was used for energy calibration. The XAS spectra were analyzed by using the Athena and Artemis software ver. 0.9.26 included in the Demeter package.²⁹

The CO pulse titration technique was conducted at 196 K to determine the dispersion of MoC_x particles using a chemisorption analyzer (AutoChem II, Micromeritics) and the signals were recorded using a thermal conductivity detector (TCD). Ammonia and nitrogen temperature-programmed desorption (NH₃- and N₂-TPD) were conducted to determine the acidity and the N₂ desorption temperature, respectively, using the chemisorption analyzer. In a typical run, 0.2 g of catalyst was placed in a U-tube quartz reactor. The catalyst was then pretreated at 750 °C (10 °C min⁻¹) for 30 min in a flow of Ar for dehydrating and outgassing. After cooling to 30 $^{\circ}$ C, the adsorbate (NH₃ or N₂) was charged into the system for 1 h. After that, the sample was purged with He at 30 °C for 1 h to remove the excess gas. TPD was performed in a helium flow from 30 to 700 °C (10 °C min⁻¹). In situ Fourier transform infrared (FTIR) spectra were recorded by using a Thermo Scientific Nicolet iS50 spectrometer equipped with a diffuse reflectance infrared Fourier transform spectroscopy cell (DRIFTS, Praying Mantis, Harrick Scientific). X-ray photoelectron spectroscopy (XPS) spectra were evaluated by using a PHI 5000 VersaProbe spectrometer equipped with a monochromatized aluminum source with a wavelength of 1486.6 eV. The tested samples were placed in a transport chamber from a glove box to the XPS chamber for quasi-in situ analysis to avoid air exposure. The C 1s binding energy of adventitious carbon at 285.0 eV was used to calibrate the energy shift.

Catalytic activity testing

Activity tests were conducted in a horizontal fixed-bed flow reactor. In a typical run, 0.18 g of tested catalyst (no diluent) was sandwiched with quartz wool in the middle of a quartz tube reactor (13 mm OD × 10 mm ID × 220 mm long). The catalyst was pretreated with an Ar stream (20 mL min⁻¹) at 750 °C (10 C min⁻¹) for 30 min to remove moisture. The catalyst was then carbonized at 750 °C using a 10% Ar/CH₄ stream (20 mL min⁻¹) for 15 min to

transform MoO₃ into MoC_x. The carbonized catalysts were denoted as xMoC_x/Al₂O₃. After carbonization, 10 mL min⁻¹ of mixed gases, including 45% CH₄, 45% N₂, and 10% Ar (the internal standard), were admitted to the system and allowed to react for 6 h. The outlet products were separated and analyzed using an online gas chromatograph (GC, SRI 8610C) equipped with a flame ionization detector (FID) and a thermal conductivity detector (TCD) for quantification. A PoraPLOT Q-HT capillary column (25 m × 0.53 mm × 20 μ m) was used for separation. The CH₄ conversion (%) and turnover frequency of each product (TOF, h⁻¹) were calculated based on the observable products by using the following equations:

$$CH_{4} conversion (\%) = \frac{\sum \left[(C atoms in product) \times F_{product} \right]}{F_{methane}} \times 100$$
(1)

$$\operatorname{TOF}\left(\mathbf{h}^{-1}\right) = \frac{\left(\operatorname{C} \operatorname{atoms} \operatorname{in} \operatorname{product}\right) \times F_{\operatorname{product}}}{\left(\operatorname{Mo} \operatorname{mole} \operatorname{in} \operatorname{catalyst} \operatorname{bed}\right) \times \left(\operatorname{dispersion}\right)} \quad (2)$$

"C atoms in product" is the carbon number of each product. F_{product} is the molar flow rate (µmol h⁻¹) of the product at the outlet stream. F_{methane} is the molar flow rate of CH₄ (µmol h⁻¹) at the inlet stream.

Results and discussion

Characterization

The bulk structure of the catalysts was determined by XRD, XAS at the Mo K-edge, and TEM, as shown in Fig. 3. The diffraction patterns of all Al₂O₃-supported MoC_x catalysts were similar to that of the pristine Al_2O_3 (Fig. 3a), indicating the presence of well-dispersed Mo₂C or Mo₂C crystals that are undetectable by XRD. Unsupported Mo₂C prepared by carbonization had similar diffraction to that of com-Mo₂C (Fig. S1[†]), confirming that the Mo₂C phase is successfully synthesized. Fig. 3b shows the Mo K-edge XAS spectra of the tested catalysts. Mo foil, Mo₂C, MoO₃, and 1MoO₃/Al₂O₃ were included for reference. The absorption edge shows an increasing trend as follows: Mo foil (20003.9 eV) $< Mo_2C$ (20010.9 eV) $< 1MoC_x/Al_2O_3$ $(20012.2 \text{ eV}) < 5 \text{MoC}_x/\text{Al}_2\text{O}_3$ $(20013.7 \text{ eV}) < 10 \text{MoC}_x/$ Al_2O_3 (20015.5 eV) < $1MoO_3/Al_2O_3$ (20015.8 eV) = MoO_3 (20015.8 eV), indicating the increasing oxidation state of Mo species. Moreover, the linear combination result of each XAS spectrum (see Fig. 3c) by using Mo₂C and MoO₃ as representatives showed that the composition of Mo₂C decreased following the order $1MoC_x/Al_2O_3$ (73.4%) > $5MoC_x/$ Al_2O_3 (56.0%) > 10MoC_x/Al₂O₃ (20.0%). This fitted result suggested that the Mo₂C phase is formed after carbonization and is dominant in $1MoC_x/Al_2O_3$.

The dark-field TEM images (Fig. 3d, g, and j) do not reveal any distinct Mo particles, likely because of the presence of small and evenly dispersed Mo particles. The Mo L α mapping images (Fig. 3e, h, and k) confirm that



Fig. 3 (a) XRD patterns of Al_2O_3 and tested catalysts, (b) XAS spectra, and (c) linear combination fitting (LCF) results of supported MoC_x catalysts. MoO_3 , Mo_2C , Mo foil, and $1MoO_3/Al_2O_3$ were included as the standards. Representative dark-field TEM images of (d) $1MoC_x/Al_2O_3$, (g) $5MoC_x/Al_2O_3$, and (j) $10MoC_x/Al_2O_3$ and their EDS mapping results at Mo L α and C K α . (e) and (f) show the EDS mappings of $1MoC_x/Al_2O_3$; (h) and (i) $5MoC_x/Al_2O_3$; (k) and (l) $10MoC_x/Al_2O_3$.

Mo is uniformly distributed. Notably, even for $10MoC_x/Al_2O_3$, no aggregated Mo clusters were observed. Moreover, the C K α images (Fig. 3f, i, and l) indicated a higher

concentration of carbon species than that of Mo in each catalyst, suggesting the coexistence of deposited carbon species with carbides.

Published on 04 August 2023. Downloaded on 8/1/2025 12:35:03 AM.

Catalyst	Mo loading ^{a} (%)	Surface area ^{b} (m ² g ⁻¹)	Pore volume ^c (cm ³ g ⁻¹)	Dispersion ^d (%)	Acidity ^e (µmol g ⁻¹)	
1MoC _x /Al ₂ O ₃	1.01	139	0.32	17.8	469	
$5MoC_x/Al_2O_3$	4.74	95	0.24	8.5	393	
$10 \text{MoC}_x/\text{Al}_2\text{O}_3$	9.99	39	0.22	2.1	172	

 Table 1
 Physicochemical properties of Al₂O₃-supported Mo₂C catalysts

^{*a*} Determined by ICP-MS. ^{*b*} Estimated by the BET method. ^{*c*} Calculated by the BJH method. ^{*d*} Obtained by CO pulse titration. ^{*e*} Evaluated by the NH₃-TPD technique.

The physicochemical properties of Al_2O_3 -supported MoC_x catalysts are listed in Table 1. The Mo content of each catalyst is close to its designated value. The N_2 isotherms of all catalysts showed a type IV isotherm and H1 hysteresis loop, indicating the presence of a mesoporous structure (Fig. S2†).^{30,31} The surface areas of the tested catalysts varied in the range of 39 to 139 m² g⁻¹ and they exhibited a pore volume of 0.22–0.32 cm³ g⁻¹. The surface area and pore volume decreased with increasing Mo loading. This is likely due to the occupation of accessible pores by Mo species, making gas adsorption difficult.³² Hence, a higher Mo loading would lead to more available pores being occupied, resulting in a reduced gas adsorption capacity.

The dispersion of MoC_x decreased with increasing Mo loading. As seen from the TEM images, the Mo_2C particle size was increased with increasing Mo loading. The increased particle size indicated a higher degree of Mo_2C agglomeration, which reduced the surface-to-volume ratio of Mo_2C . Therefore, the surface availability of Mo_2C at a high Mo content is suppressed. The total acidity of the Al_2O_3 supported Mo_2C catalysts also decreased when the Mo loading was increased (Fig. S3†). Al_2O_3 exhibits Lewis acidity, whereas Mo_2C has Lewis basic sites.³³ By adjusting the Mo loading, it becomes possible to occupy the acidic sites of Al_2O_3 , leading to a decrease in acidity. The coverage of acid sites increases with higher Mo loading.

Catalytic evaluation

 CH_4 conversion was tested in either a N_2 or Ar stream to verify that gaseous N_2 is activated and reacted with CH_4 to form ACN. Similar profiles of CH_4 conversion and TOF of hydrocarbons (ethylene, ethane, benzene, and toluene) were observed in both N_2 (closed squares) and Ar (open circles) streams (Fig. 4a and S4†). This indicated that the N_2 and Ar atmospheres had little influence on the transformation of CH_4 into hydrocarbons. Moreover, it can be seen that the CH_4 conversion and TOF of hydrocarbons decreased synchronously with time, indicating that the active sites for hydrocarbon formation are deactivated, likely due to coke accumulation.³⁴

Note that ACN production was solely observed when CH_4 was converted in N_2 (Fig. 4a). That is, N_2 activation and N-insertion took place in CH_4 conversion. Since gaseous N_2 is the sole N-containing reagent, the formation of ACN could be attributed to gaseous N_2 activation. To further clarify that ACN

can be produced in the presence of N_2 , N_2 -Ar- N_2 (Fig. 4b) and Ar-N2-Ar (Fig. 4c) switching tests were conducted. Again, operating in varying streams has a negligible impact on the CH₄ conversion (black scatters in Fig. 4b and c). In the N₂-Ar-N₂ switching test (Fig. 4b), the TOF of ACN was initially high $(13.0 h^{-1})$ when operating under N₂ (red closed squares). After switching to Ar (red open circles), the TOF of ACN decreased sharply, indicating that ACN cannot be produced in Ar. When the reaction stream was switched back to N2, the TOF recovered to 8.2 h⁻¹ (red closed squares), underlining that ACN is produced by feeding N₂. Comparatively, in the Ar-N₂-Ar switching test (Fig. 4c), there was no ACN produced at the beginning of the test when feeding Ar (red open circles). After switching the feed to N2, a significant increase in the TOF of ACN was observed (6.1 h⁻¹, red closed squares), emphasizing that N2 activation occurs, which can react with CH4 to form ACN. However, ACN could still be produced when N2 was replaced by Ar (red open circles). Presumably, there is deposited carbon on the MoC_x surface during the first cycle in Ar. After purging N_2 , the converted N_2 could also react with the MoC_x surface, forming a carbonitride-like structure.35 This structure is proposed to act as a N-source for ACN synthesis. It can be concluded at this stage that Al_2O_3 -supported MoC_x is active for the co-activation of CH4 and N2, and ACN can be produced merely in N₂.

The effects of operating temperature (650, 700, 750, and 800 °C) and Mo loading (1, 5, and 10 wt%) were evaluated for the conversion of CH₄ using the MoC_x/Al₂O₃ catalysts (Table 2, entries 1-4 and Fig. S5[†]). Mo₂C and MoO₃ were tested, and both showed negligible activities. The CH₄ conversion is increased with temperature from 9.3% (650 °C) to 25.0% (800 °C). The TOFs of C2 species and coke also increased with reaction temperature. However, aromatics reached the highest TOF at 750 °C and then declined. This is likely caused by the overoligomerization of aromatics to form coke. The TOF of ACN also increased with reaction temperature, suggesting the progressively enhanced extent of C-H bond and N=N bond cleavages. At 800 °C, the TOF of ACN was high at the beginning of the reaction, but showed a rapidly decreasing trend. Hence, a temperature of 750 °C was selected for further investigations.

In addition to determining the effect of reaction temperature, CH_4 -TPSR experiments were also conducted, as shown in Fig. S6.† CH_4 (m/z = 16) started to be converted at 640 °C with a maximum conversion rate at 730



Fig. 4 Time on stream (TOS) profiles of (a) CH₄ conversion (black) and TOF of ACN (red) under N₂ (closed squares) and Ar (open circles) atmospheres and the TOS profiles of CH₄ conversion and TOF of ACN during the (b) N₂-Ar-N₂ and (c) Ar-N₂-Ar switching tests. Reaction conditions: 0.18 g of $1MoC_x/Al_2O_3$, reaction temperature = 750 °C, GHSV = 1500 mL_{CH₄} g_{cat}⁻¹ h⁻¹, feed = 4.5/4.5/1 mL min⁻¹ of CH₄/N₂/Ar or 4.5/5.5 mL min⁻¹ of CH₄/Ar.

°C. The onset temperatures of major products, including ACN (m/z = 41), C₂ species (m/z = 29), and benzene (m/z = 78), were approximately 650 °C. Therefore, it could be

suggested that the formation reactions of ACN and hydrocarbons proceed in parallel.

The effect of Mo loading (Table 2, entries 3, 5, and 6 and Fig. S7†) was tested at a 750 °C. The CH₄ conversion and TOF of C₂ and aromatics decreased with increasing Mo loading. This is likely due to the suppressed acidity at a high Mo loading since C-H activation is promoted by acidic sites.^{36,37} The TOF of ACN had negligible change with respect to the Mo loading. However, a small amount of HCN could be observed when the Mo loading is higher than 5%. Moreover, $1MoC_x/Al_2O_3$ exhibited the most stable TOF of ACN during the 6 h testing. Accordingly, $1MoC_x/Al_2O_3$ was further investigated.

In comparison, the equilibrium conversion of CH₄ and N_2 to ACN (2CH₄ + 0.5N₂ \leftrightarrow CH₃CN + 2.5H₂) was performed from 300 °C to 1000 °C using ThermoSolver. The obtained parameters are presented in Table S1.† It can be seen that the equilibrium constant (K_{eq}) increases with increasing temperature, indicating the endothermic nature of CH_4 conversion to ACN. However, the values of K_{eq} at all tested temperatures are very small. That is, the reaction is highly unpreferable, in which low CH₄ and N₂ conversions and a low ACN yield were expected. The conversion equilibrium CH_4 as a function of temperature is illustrated in Fig. S8.† At 750 °C, only 0.55% of CH₄ is converted in the equilibrium state. Note that using a MoC_x-based catalyst resulted in approximately 1.5% CH₄ conversion, suggesting the effectiveness of Mo₂C in the cleavage of C-H and N≡N bonds.

The above activity results showed that the major products were aromatics and coke, possibly due to the strong interaction between Mo_2C nanoparticles and CH_4 .³⁸ Moreover, a parallel reaction pathway to produce ACN and hydrocarbons was suggested by the similar onset temperature from CH_4 -TPSR. One way to suppress aromatization and coke is through co-feeding hydrogen in the reactant stream.³⁹ Hence, the effect of co-feeding H_2 (10, 20, 25, and 33% v/v) was investigated at 750 °C by using $1MoC_x/Al_2O_3$ (see Fig. 5 and S9†). Co-feeding H_2 varies the concentration of CH_4 which can affect reactivity. Accordingly, using Ar as a diluent with the same concentration as that of H_2 was also investigated to validate that the activity is not only affected by the low CH_4 concentration.

The initial CH_4 conversion and TOFs of hydrocarbons (C_2 and aromatics) and ACN decreased with increasing concentration of diluent. In addition, the initial CH_4 conversion and TOFs under the H_2 stream (magenta bars) were more strongly influenced than those tested in the Ar stream (yellow bars), in which aromatics are the most affected species (see Fig. 5d). In other words, H_2 co-feeding does not only dilute the concentration of CH_4 but also dampens the aromatization activity. Moreover, after 12 h on stream, the CH_4 conversion decreased severely in the Ar stream (22.5%, 19.6%, 18.1%, and 13.7% declined to 0.6%, 0.8%, 0.5%, and 0.4% at 10, 20, 25, and 33% Ar concentration, respectively), compared to those in the H_2 co-

Table 2 Catalytic activity testing for CH_4 conversion over the Al_2O_3 -supported MoC_x catalysts. Reaction conditions: 0.18 g catalyst, 10 mL min⁻¹ of the feed mixture

Entry	Catalyst	Temp. (°C)	CH ₄ conversion ^{<i>a</i>} (%)	$TOF^{a}(h^{-1})$				
				C_2	Aromatics	ACN	HCN	Coke ^b
1	1MoC _x /Al ₂ O ₃	650	9.3 (5.5)	8.6 (5.1)	65.0 (23.3)	1.1 (6.3)	N/D	23.2
2		700	17.2 (6.0)	16.6 (9.6)	123.7 (14.7)	5.1 (9.5)	N/D	26.7
3		750	26.1 (6.0)	30.7 (8.4)	168.8 (1.0)	15.3 (14.3)	N/D	33.6
4		800	25.0 (8.4)	38.6 (11.9)	109.5 (0.5)	20.8 (5.5)	N/D	58.2
5	5MoC _r /Al ₂ O ₃	750	26.5 (5.9)	13.5 (2.3)	72.2 (0.1)	7.8 (4.6)	1.2(0)	18.1
6	$10 Mo \hat{C}_x / A \hat{l}_2 \hat{O}_3$		15.4 (3.0)	15.2 (3.1)	80.3 (0.0)	13.2 (5.9)	2.1 (0)	15.3
^a Data w	vere taken from the T	'OS profiles at 40	min and 6 h (shown in	h brackets). ^b Aver	age coke formatio	n rate. determine	ed by TGA.	

fed stream (20.0%, 10.1%, 5.6%, and 1.2% decreased to 4.6%, 4.1%, 2.5%, and 1.0% at 10, 20, 25, and 33% H_2 concentration, respectively). This implied that the reactivity is more stable when H_2 is present.

As seen by the TOFs at 12 h on stream (Fig. 5b–d), the products were still producible in the H_2 atmosphere, while there were almost no products formed under the Ar stream at the 12th hour. Accordingly, it could be claimed that gaseous H_2 also reduces the amount of carbon deposits on the catalyst surface, resulting in a steadier reactivity.³⁹

XPS spectra of the Mo₂C and 1MoC_x/Al₂O₃ catalysts are illustrated in Fig. 6. The photoline of Mo₂C at Mo 3d (Fig. 6a) could be deconvoluted into five responses. The responses at 235.8 and 232.7 eV are attributed to Mo⁶⁺ (red);⁴⁰ 229.5 eV, Mo³⁺ (magenta);⁴¹ 231.3 and 228.4 eV, Mo²⁺ (blue).⁴² The presence of Mo²⁺ signals indicated the existence of Mo₂C species, while Mo⁶⁺ and Mo³⁺ could be assigned as MoO₃ and Mo₂O₃, respectively. The existence of oxidic species could be attributed to the oxidation of the Mo₂C surface.^{43,44} The spectrum of 1MoC_x/Al₂O₃ also contained these signals. In addition, another response at



Fig. 5 Effects of H_2 co-feeding and Ar dilution on (a) CH_4 conversion and TOF of (b) ACN, (c) C_2 , and (d) aromatics by using $1MoC_x/Al_2O_3$.

234.4 eV assigned to Mo^{4+} species⁴⁵ (cyan) was observed over the $1MoC_x/Al_2O_3$ catalyst, which could be referred to the presence of MoC species, likely due to the overcarbonization of small Mo_2C particles. Oxidic molybdenum species were observed, even though the catalyst was *in situ* carbonized prior to the reaction without exposure to the atmosphere. Therefore, it could be stated that the active phase is composed of carbidic molybdenum species.

The C 1s spectra (Fig. 6b) of both Mo_2C and $1MoC_x/Al_2O_3$ could be deconvoluted into four species, including adventitious carbon (C–C, red) at 285.0 eV, C–O (cyan) at 285.6 eV,⁴⁶ C=O (magenta) at 288.0 eV,⁴⁷ and C–Mo (blue) at 283.7 eV,⁴⁸ respectively. According to the characterization results, it can be concluded that the active sites of the catalysts are predominantly made of the carbide phase.

Table S2† shows the percentage of each Mo and C species obtained from the aforementioned XPS results. $1MoC_x/Al_2O_3$ contained 28.1% Mo₂C (Mo²⁺) phase. Additionally, by including all carbide species (MoC, Mo⁴⁺), the relative composition of MoC_x for $1MoC_x/Al_2O_3$ is 43.7%, which is much higher than that of its unsupported counterpart (7.4%). This is presumably due to the presence of smaller molybdenum particles that lead to a more rapid and complete carbonization. After the reaction, the C–Mo signals were not observed. The percentage of C–C increased together with the appearance of sharper C 1s signals over the spent catalysts. This suggested the formation of graphitic carbon that dominates the signals at a similar region.⁴⁹

It can be seen in Table S2[†] that the surface C/Mo ratios of fresh, 6 h spent (Ar), 6 h spent (H₂), 12 h spent (Ar), and 12 h spent (H₂) 1MoC_x/Al₂O₃ are 1.04, 5.66, 5.56, 11.23, and 6.78, respectively. It has been reported that the reactivity of molybdenum carbides depends on the C/Mo ratio, in which the catalyst with a lower C/Mo ratio is more reactive.³⁸ In this case, the C/Mo ratio rapidly increased when the reaction was performed in the Ar atmosphere (from 1.04 (fresh) to 5.66 (6 h, Ar) to 11.23 (12 h, Ar)), while it was more stable in the H₂ stream (from 1.04 (fresh) to 5.56 (6 h, H₂) to 6.78 (12 h, H₂)). Accordingly, the enhanced stability of CH₄ conversion and TOF is likely related to the more consistent surface C/Mo ratio achieved when H₂ is present.

The TOF of ACN and C_2 was more stable when cofeeding H_2 . Additionally, it can be seen that the TOF of

Paper



aromatics is suppressed by ~87% at 25% H₂. When the concentration of H₂ is further increased to 33%, no aromatics can be initially found. Note that the CH₄ conversion under these conditions is almost negligible, which explains the disappearance of aromatics. Therefore, 25% H₂ was selected for 50 h stability testing.

Fig. 7 shows that the on-stream activity was nearly unchanged in the 50 h duration test, underlining the stability of the reaction process. The CH_4 conversion was maintained



Fig. 7 50 h stability testing at 25% H_2 co-feeding over $1MoC_x/Al_2O_3$.

at approximately 2.5%. Moreover, three major products, including ACN, ethylene, and ethane, were also sustainably produced at a TOF of approximately 6.5 h⁻¹. Aromatics and HCN were observed as by-products at a TOF of ~2.5 h⁻¹. Therefore, the presence of 25% H₂ can not only suppress CH₄ aromatization but also enhance the stability of the catalyst during the 50 h durability test.

Proposed mechanism

Our earlier work claimed that ACN is formed via surface CN species over GaN catalysts. The surface CN species are formed by reacting CH4 with mobile-N of GaN at the surface.⁵⁰ Therefore, CN species may also form over the MoC_x surface by N₂ cleavage. Hence, in situ DRIFTS experiments were performed under a N2 atmosphere, as shown in Fig. S10.† Regrettably, no CN vibrational band (~2220 cm⁻¹) could be observed. This might be attributed to (i) the high instability of evolved intermediates or (ii) no interaction being formed between N₂ and surface carbon of MoC_x. The latter could be clarified by performing N2-H2 co-feeding experiments. In the N2-H2 co-feeding test, HCN should be generated if N2 and surface carbon react since the surface carbon of MoC_x acts similarly to surface oxygen in the Marsvan Krevelen mechanism.51,52 However, no HCN could be generated (not shown), indicating that the surface carbon has



Fig. 8 N₂-TPD profiles of Al₂O₃-supported MoC_x catalysts and unsupported Al₂O₃



To clarify, the CO and N2 uptakes were compared since CO is stoichiometrically adsorbed on Mo sites.⁵⁷ As shown in Table S3,† the CO and N₂ uptakes were nearly identical for the tested catalysts. This indicated that the adsorption behaviors of CO and N₂ are similar. Accordingly, it can be concluded that the adsorption of N2 takes place at the Mo sites.

Although N_2 activation by MoC_x was elucidated, the formation of the C=N bond and ACN is still unclear. A previous study revealed that CH4 tends to be completely dissociated on Mo sites exposed on the MoC_x surface.⁵⁸ The MoC_x surface could be further carburized by the dissociated carbon adatoms diffusing into the subsurface layer, forming a MoC-like surface structure. The MoC-like surface could facilitate CH* coupling to form C2H2 as a potential intermediate.^{58,59} The 1MoC_x/Al₂O₃ had its C/Mo ratio estimated by XPS analysis close to unity (Table S2[†]), similar to that of MoC. That is, the surface of 1MoC_x/Al₂O₃ should have an MoC-like structure. Thus, we propose that the formation of ACN occurs over the Mo sites exposed on the surface of the MoC-like structure, as shown in Fig. 9.

N₂ could be dissociatively adsorbed on the Mo-terminated surface. Then, CH₄ would be activated and dehydrogenated over the adjacent Mo sites, forming CH* species. The CH* species could couple with $C_2H_2^*$ species that further react with



Fig. 9 Proposed co-activation of CH_4 and N_2 to ACN over the MoC_x catalyst (top view of the catalyst surface).

N adatoms, forming ACN. The produced ACN could desorb from the surface, which fulfills the catalytic cycle.

To support this claim, kinetic analysis based on the Langmuir-Hinshelwood (LH) formalism of the proposed mechanism was performed, which is presented in the ESI.† The six possible reactions were grouped into four steps, N_2 adsorption, CH_4 adsorption, including surface reaction, and ACN desorption. The rate expression is derived by assuming that one of the above steps is rate-limiting while the remaining steps are all in equilibrium. The rate expression was fitted to the experimental data (see Table S4[†]) by nonlinear regression subject to minimizing the residual sum of squares to recover the values of the parameters (see Table S5[†]). By resorting to the fitted parameters and the parity plot (Fig. S11[†]), the surface reaction step is the most likely to occur. This result is supported by previous studies showing that the dissociative adsorption of N₂ and the C-H bond cleavage of CH4 on the MoC surface are facile and unlikely to be rate-limiting.59,60

Conclusions

the

In this article, two high-stability compounds (CH₄ and N₂) were simultaneously converted to form ACN over Al2O3supported MoC_x catalysts. ACN could only be produced in the presence of N_2 , confirming the activation of the N=N bond. Due to the strong interaction between MoC_x and CH_4 , aromatization and coking were significant, resulting in catalyst deactivation. The aromatization could be diminished by co-feeding H_2 , in which the catalytic activity and TOF could be maintained for 50 h. The MoC-like surface structure of MoC_x was proposed to be an active center for ACN synthesis. Kinetic analysis suggested that the surface reaction of adsorbed N₂ and C₂H^{*}₂ species is possibly the ratedetermining step.

Author contributions

Korawich Trangwachirachai: investigation, formal analysis, validation, and writing – original draft. I-Ting Kao: investigation and formal analysis. Wei-Hsiang Huang: XAS data collection and analysis. Chi-Liang Chen: XAS data collection and analysis. Yu-Chuan Lin: supervision, project administration, resources, and writing – review & editing.

Conflicts of interest

The authors declare that they have no competing financial interests.

Acknowledgements

This work was supported by the National Science and Technology Council (projects 109-2628-E-006-011-MY3, 110-2221-E-006-165-MY3, 110-2923-E-006-005-MY3, and 110-2927-I-006-506) and by the Higher Education Sprout Project, Ministry of Education to the Headquarters of University Advancement at National Cheng Kung University (NCKU). The authors gratefully acknowledge the use of XPS (ESCA003700) and TEM (EM000800) of NSTC 112-2740-M-006-001 belonging to the Core Facility Center of NCKU.

References

- W. Jiang, J. Low, K. Mao, D. Duan, S. Chen, W. Liu, C. W. Pao, J. Ma, S. Sang, C. Shu, X. Zhan, Z. Qi, H. Zhang, Z. Liu, X. Wu, R. Long, L. Song and Y. Xiong, *J. Am. Chem. Soc.*, 2021, 143, 269–278.
- 2 P. Schwach, X. Pan and X. Bao, *Chem. Rev.*, 2017, **117**, 8497–8520.
- 3 Z. Zhu, W. Guo, Y. Zhang, C. Pan, J. Xu, Y. Zhu and Y. Lou, *Carbon Energy*, 2021, 3, 519–540.
- 4 S. M. Kim, P. M. Abdala, D. Hosseini, A. Armutlulu, T. Margossian, C. Copéret and C. Müller, *Catal. Sci. Technol.*, 2019, 9, 5745–5756.
- 5 M. A. A. Aziz, A. A. Jalil, S. Wongsakulphasatch and D.-V. N. Vo, *Catal. Sci. Technol.*, 2020, **10**, 35–45.
- 6 J. Niu, Y. Wang, Y. Qi, A. H. Dam, H. Wang, Y.-A. Zhu, A. Holmen, J. Ran and D. Chen, *Fuel*, 2020, 266, 117143.
- 7 B. C. Ekeoma, M. Yusuf, K. Johari and B. Abdullah, *Int. J. Hydrogen Energy*, 2022, 47, 41596–41620.
- 8 J. K. Dahl, A. W. Weimer, A. Lewandowski, C. Bingham, F. Bruetsch and A. Steinfeld, *Ind. Eng. Chem. Res.*, 2004, 43, 5489–5495.
- 9 Y.-R. Luo, *Comprehensive Handbook of Chemical Bond Energies*, CRC Press, 2007, p. 1688, DOI: 10.1201/9781420007282.
- 10 W. Taifan and J. Baltrusaitis, *Appl. Catal., B*, 2016, **198**, 525–547.
- 11 L. Sun, Y. Wang, N. Guan and L. Li, *Energy Technol.*, 2019, 8, 1900826.
- 12 D. C. Upham, V. Agarwal, A. Khechfe, Z. R. Snodgrass, M. J. Gordon, H. Metiu and E. W. McFarland, *Science*, 2017, 358, 917–921.

- 13 K. Dutta, V. Chaudhari, C.-J. Li and J. Kopyscinski, Appl. Catal., A, 2020, 595, 117430.
- 14 K. Trangwachirachai, C.-H. Chen and Y.-C. Lin, *Mol. Catal.*, 2021, **516**, 111961.
- 15 K. Trangwachirachai, C.-H. Chen, A.-L. Huang, J.-F. Lee, C.-L. Chen and Y.-C. Lin, *Catal. Sci. Technol.*, 2022, **12**, 320–331.
- 16 Z. Yuan, X. Zhang, Q. Yao, Y. Zhang and Y. Fu, J. Anal. Appl. Pyrolysis, 2019, 140, 376–384.
- 17 Future Market Insights, Acetonitrile Market, https://www. futuremarketinsights.com/reports/acetonitrile-market, 2023.
- 18 A. Sieminski, US Energy Information Administration, 2015.
- 19 J. J. Sattler, J. Ruiz-Martinez, E. Santillan-Jimenez and B. M. Weckhuysen, *Chem. Rev.*, 2014, **114**, 10613–10653.
- 20 K. Trangwachirachai and Y.-C. Lin, *Dalton Trans.*, 2023, 52, 6211–6225.
- 21 A. Daisley and J. S. J. Hargreaves, *Catal. Today*, 2023, **423**, 113874.
- 22 S. Tiwari, T. S. Khan, P. Tavadze and J. Hu, Chem. Eng. J., 2021, 413, 127501.
- 23 R. Kojima and K.-I. Aika, Appl. Catal., A, 2001, 219, 141-147.
- 24 R. Michalsky, Y.-J. Zhang, A. J. Medford and A. A. Peterson, J. Phys. Chem. C, 2014, 118, 13026–13034.
- 25 H. Cheng, L.-X. Ding, G.-F. Chen, L. Zhang, J. Xue and H. Wang, *Adv. Mater.*, 2018, **30**, 1803694.
- 26 J. Gao, Y. Zheng, G. B. Fitzgerald, J. de Joannis, Y. Tang, I. E. Wachs and S. G. Podkolzin, *J. Phys. Chem. C*, 2014, **118**, 4670–4679.
- 27 J. Jeong, A. Hwang, Y. T. Kim, D.-Y. Hong and M.-J. Park, *Catal. Today*, 2020, 352, 140–147.
- 28 B. Cook, D. Mousko, W. Hoelderich and R. Zennaro, *Appl. Catal.*, A, 2009, 365, 34–41.
- 29 B. Ravel and M. Newville, J. Synchrotron Radiat., 2005, 12, 537–541.
- 30 S. Paganelli, R. Tassini, V. D. Rathod, B. Onida, S. Fiorilli and O. Piccolo, *Catal. Lett.*, 2021, **151**, 1508–1521.
- 31 K. S. W. Sing and R. T. Williams, Adsorpt. Sci. Technol., 2004, 22, 773–782.
- 32 M. J. Ramos, A. Casas, L. Rodríguez, R. Romero and Á. Pérez, *Appl. Catal.*, A, 2008, 346, 79–85.
- 33 S. K. Bej, C. A. Bennett and L. T. Thompson, *Appl. Catal.*, A, 2003, 250, 197–208.
- 34 C. H. L. Tempelman and E. J. M. Hensen, *Appl. Catal., B*, 2015, **176–177**, 731–739.
- 35 P. K. Roy and S. Kumar, ACS Appl. Energy Mater., 2020, 3, 7167–7179.
- 36 R. Gounder and E. Iglesia, J. Am. Chem. Soc., 2009, 131, 1958–1971.
- 37 M. C. Cholewinski, M. Dixit and G. Mpourmpakis, ACS Omega, 2018, 3, 18242–18250.
- 38 M. Figueras, R. A. Gutiérrez, H. Prats, F. Viñes, P. J. Ramírez, F. Illas and J. A. Rodriguez, *Phys. Chem. Chem. Phys.*, 2020, 22, 7110–7118.
- 39 H. Ma, R. Kojima, S. Kikuchi and M. Ichikawa, *Catal. Lett.*, 2005, **104**, 63–66.
- 40 C. Wu and J. Li, ACS Appl. Mater. Interfaces, 2017, 9, 41314-41322.

Paper

- 41 Y. N. Regmi, C. Wan, K. D. Duffee and B. M. Leonard, *ChemCatChem*, 2015, 7, 3911–3915.
- 42 X. Kong, S. Chen, Y. Zou, S. Lyu, X. She, Y. Lu, J. Sun, H. Zhang and D. Yang, *Int. J. Hydrogen Energy*, 2018, 43, 13720-13726.
- 43 H. Vrubel and X. Hu, Angew. Chem., Int. Ed., 2012, 51, 12703–12706.
- 44 J. Li, C. Zhou, J. Mu, E.-C. Yang and X.-J. Zhao, *RSC Adv.*, 2018, 8, 17202–17208.
- 45 H. Wei, Q. Xi, X. A. Chen, D. Guo, F. Ding, Z. Yang, S. Wang, J. Li and S. Huang, *Adv. Sci.*, 2018, 5, 1700733.
- 46 L. Diao, J. Qin, N. Zhao, C. Shi, E. Liu, F. He, L. Ma, J. Li and C. He, *J. Mater. Chem. A*, 2018, **6**, 6054–6064.
- 47 Y. Lei, Y. Yang, Y. Liu, Y. Zhu, M. Jia, Y. Zhang, K. Zhang, A. Yu, J. Liu and J. Zhai, *Nanoscale Res. Lett.*, 2019, **14**, 329.
- 48 D. Wang, J. Wang, X. Luo, Z. Wu and L. Ye, *ACS Sustainable Chem. Eng.*, 2018, **6**, 983–990.
- 49 P. Xiao, X. Ge, H. Wang, Z. Liu, A. Fisher and X. Wang, Adv. Funct. Mater., 2015, 25, 1520–1526.
- 50 K. Trangwachirachai, A. L. Huang, H. K. Chen, C. L. Chen, J. F. Lee, H. K. Tian and Y. C. Lin, *Mater. Today Chem.*, 2023, **30**, 101500.

- 51 I. Vollmer, B. van der Linden, S. Ould-Chikh, A. Aguilar-Tapia, I. Yarulina, E. Abou-Hamad, Y. G. Sneider, A. I. O. Suarez, J.-L. Hazemann, F. Kapteijn and J. Gascon, *Chem. Sci.*, 2018, 9, 4801–4807.
- 52 G. Li, I. Vollmer, C. Liu, J. Gascon and E. A. Pidko, ACS Catal., 2019, 9, 8731–8737.
- 53 M. Grunze, M. Golze, W. Hirschwald, H. J. Freund, H. Pulm, U. Seip, M. C. Tsai, G. Ertl and J. Küppers, *Phys. Rev. Lett.*, 1984, 53, 850–853.
- 54 S. Dahl, A. Logadottir, R. C. Egeberg, J. H. Larsen, I. Chorkendorff, E. Törnqvist and J. K. Nørskov, *Phys. Rev. Lett.*, 1999, 83, 1814–1817.
- 55 J. J. Mortensen, L. B. Hansen, B. Hammer and J. K. Nørskov, J. Catal., 1999, 182, 479–488.
- 56 W. Liao, L. Qi, Y. Wang, J. Qin, G. Liu, S. Liang, H. He and L. Jiang, Adv. Funct. Mater., 2021, 31, 2009151.
- 57 J. S. Lee, K. H. Lee and J. Y. Lee, J. Phys. Chem., 1992, 96, 362–366.
- 58 T. Zhang, X. Yang and Q. Ge, Catal. Today, 2021, 368, 140–147.
- 59 T. Zhang, X. Yang and Q. Ge, Catal. Today, 2020, 339, 54-61.
- 60 I. Matanovic and F. H. Garzon, Phys. Chem. Chem. Phys., 2018, 20, 14679–14687.