RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2023, 13, 2903

Received 13th December 2022 Accepted 10th January 2023

DOI: 10.1039/d2ra07949f

rsc.li/rsc-advances

Introduction

Based on their extraordinary electrical, optical, chemical and mechanical properties, two-dimensional (2D) materials have been widely regarded as crucial ingredients in the fabrication of next generation of optoelectronics and nanoelectronics functional devices.¹⁻⁴ As a typical 2D material, sp²-hybridized graphene is expected to replace mainstream silicon-driven semiconductors owing to its excellent mobility up to 2×10^6 cm² V⁻¹ s⁻¹ at room temperature,⁵⁻⁷ massless Dirac fermions and remarkable optical transmittance.⁸ However, the gapless nature and fast carrier recombination of graphene have seriously limited its applications in the field of electronic devices, especially in the logic circuit. Unlike graphene, monolayer MoS₂, comprising one molybdenum atom with two surrounding sulfur atoms, has a direct band gap semiconductor of 1.8 eV.⁹ Meanwhile, the on/off current ratio of MoS₂ exceeds

Interface contact and modulated electronic properties by in-plain strains in a graphene–MoS₂ heterostructure†

Qian Wang, ^[]^a Zhenjun Song, ^[]^b Junhui Tao,^a Haiqin Jin,^a Sha Li,^a Yuran Wang,^a Xuejuan Liu^c and Lin Zhang^{*a}

Designing a specific heterojunction by assembling suitable two-dimensional (2D) semiconductors has shown significant potential in next-generation micro-nano electronic devices. In this paper, we study the structural and electronic properties of graphene–MoS₂ (Gr–MoS₂) heterostructures with in-plain biaxial strain using density functional theory. It is found that the interaction between graphene and monolayer MoS₂ is characterized by a weak van der Waals interlayer coupling with the stable layer spacing of 3.39 Å and binding energy of 0.35 J m⁻². In the presence of MoS₂, the linear bands on the Dirac cone of graphene are slightly split. A tiny band gap about 1.2 meV opens in the Gr–MoS₂ heterojunction due to the breaking of sublattice symmetry, and it could be effectively modulated by strain. Furthermore, an ntype Schottky contact is formed at the Gr–MoS₂ interface with a Schottky barrier height of 0.33 eV, which can be effectively modulated by in-plane strain. Especially, an n-type ohmic contact is obtained when 6% tensile strain is imposed. The appearance of the non-zero band gap in graphene has opened up new possibilities for its application and the ohmic contact predicts the Gr–MoS₂ van der Waals heterojunction nanocomposite as a competitive candidate in next-generation optoelectronics and Schottky devices.

> 10⁸,¹⁰ making it a broad application prospect in nanoelectronics.^{10,11} However, the relatively low carrier mobility^{12,13} which mainly arises from the large contact resistance^{14,15} with metal electrodes, limits its further improvement in device performance.

> Recently, van der Waals (vdW) heterojunctions based on vertically stacked 2D layered materials have attracted considerable attentions.¹⁶⁻¹⁸ It is an effective way to open the graphene band gap through assembling graphene on top of another function 2D materials,¹⁹ since electronic properties of graphene are very sensitive to substrate interactions in preparation and synthesis processes.^{20,21} The calculation results have revealed that bandgap can be opened in graphene, mainly because of the sublattice symmetry breaking. For instance, the band gap at the Dirac point in graphene is opened when graphene deposited on SiC,^{22,23} h-BN,²⁴ and Al₂O₃ (ref. 20) substrates. Besides, the electronic performances of primeval 2D materials are preserved in 2D heterojunctions in which the interface are connected by weak interlayer vdW force without dangling bonds.25 Similar to the interfaces at traditional three-dimensional (3D) metalsemiconductor junctions, the interface between graphene and monolayer MoS₂ leads to the formation of a Schottky barrier (SB) caused by the differences in work function. However, the vdW interface of graphene-MoS₂ (Gr-MoS₂) without dangling bonds is expected to have a weak Fermi-level pinning effect, which enables more effective modulation of the SB and yields

[&]quot;School of Physics and Mechanical & Electrical Engineering, Hubei Engineering Technology Research Center of Environmental Purification Materials, Hubei University of Education, Wuhan 430000, China. E-mail: zhanglin@hue.edu.cn

^bSchool of Parmaceutical and Materials Engineering, Taizhou University, Taizhou 318000, PR China

^cCollege of Physics and Engineering, Chengdu Normal University, Chengdu 611130, China

[†] Electronic supplementary information (ESI) available. See DOI: https://doi.org/10.1039/d2ra07949f

higher carrier mobility than that of 3D metal-MoS₂ junctions with fixed SB.^{26,27} Besides, the vdW Gr–MoS₂ heterojunction is dynamically stable^{28,29} and successfully synthesized experimentally,^{30–32} and the electron mobility of the heterojunction is comparable to graphene, theoretically.³³

On top of that, $Gr-MoS_2$ vdW heterojunction is investigated here. We investigate the structural optimizations and electronic characteristics of $Gr-MoS_2$ vdW heterojunctions with in-plain biaxial strain using first-principles calculations with vdW correction. An n-type ohmic contact is obtained when a tensile strain greater than 6% is applied. Meanwhile, a tiny bandgap up to 1.2 meV of graphene has opened at the Dirac point in the presence of MoS_2 , and the bandgap increases to 2.6 meV when tensile strain increases to 6%. In this present work, a systematic study of $Gr-MoS_2$ heterojunction under in-plane strains is carried out, which gives an insight into the interface contacts and electronic properties.

Methods

First-principles calculations are carried out using density functional theory as implemented in the Vienna ab initio Simulation Package (VASP) with periodic boundary conditions.³⁴⁻³⁶ The projected augmented wave (PAW) method³⁷ is adopted to describe the ion cores with valence electrons. All the calculations are carried out using the newly-developed strongly constrained and appropriately normed (SCAN) metageneralized gradient approximation (meta-GGA) density functional³⁸ with rVV10 (the revised Vydrov-van Voorhis nonlocal correlation functional) for vdW correction.39 The SCAN+rVV10 method has offered a good performance for layered-materials compared with experimental results⁴⁰ and is especially appropriate for metal-semiconductor contacts.41 The Mo 4s and 4p electrons are also taken as valence electrons so that each Mo atom contains 14 valence electrons in the PAW potential. In addition, the plane-wave energy cut-off is taken as 500 eV, and the Brillouin-zone integration of 5 \times 5 \times 1 Monkhorst–Pack mesh is utilized throughout the geometric relaxations and electronic structure calculations. All of geometric models are fully relaxed until achieving the convergence thresholds where atomic forces and energy difference in the self-consistency process are less than 0.01 eV \AA^{-1} and 1×10^{-4} eV per atom, respectively. A vacuum region of 20 Å is added and a dipole correction is applied to avoid spurious interactions between periodic images of the slab.42 In this work, we also carry out the spin-polarized calculation. Our results indicate that the Gr-MoS₂ interfaces are nonmagnetic.

Results and discussions

Geometry optimization and stability

The optimized lattice constants of graphene and monolayer MoS_2 are 2.454 Å and 3.167 Å (see Fig. S1[†] in ESI) respectively, which agree with theoretical and experimental results in literature.^{3,39,43,44} Here graphene is stretched to match the MoS_2 lattice. The unit cell of Gr–MoS₂ heterojunction is comprised of 5×5 primitive cells of graphene and 4×4 primitive cells of MoS_2 along the *X* and *Y* directions. And these two layers can nicely match, whose lattice mismatch is 3.01% for the composed configuration. The equilibrium geometry configurations of the Gr-MoS₂ heterojunctions are depicted in Fig. 1.

Based on previous experience, Gr-MoS₂ heterojunctions can be controlled by an external electric field and vertical strain.45,46 In addition, strain engineering is a prominent mean to modulate the nature of 2D materials since 2D materials are capable to withstand much larger strain than their bulk phase. Thus here, we consider the sensitive response of electronic performances and geometric properties of Gr-MoS₂ contacts in the case of inplane biaxial compression and tension strains. 2D materials can be stretched or compressed by depositing or transferring substrates experimentally, while strain engineering can be simulated by altering the cell lattice constants and relaxing the atoms theoretically. Therefore, the biaxial strain ε is defined as ε $= (a - a_0)/a_0 = \Delta a/a_0$ ⁴⁷ where a_0 and a are the in-plane lattice constants of the unstrained and strained systems, respectively. Thus, if ε is positive, the system is endured an in-plane tensile strain, and vice versa. All of our calculations are performed under in-plane biaxial strain, and the strains considered here are all checked within the elastic limit which enable the deformed structure can be restored to its initial state when the mechanical strains are removed48 (Fig. S2⁺).

In Gr–MoS₂ heterojunctions, the equilibrium distances (*D*) under different strain (defined as the separation between the C atom layer and the S atom layer of MoS₂ close to graphene) are shown in Table 1, which vary from 3.35 Å to 3.45 Å with biaxial strain from -4% (minus indicates a compressive strain of 4%) to 6% (positive 6 represents 6% tensile strain). It can be seen that the *D* decreases with a larger compressive strain and increases with a larger tensile strain. The variation of *D* with strain is opposite to that of common sense, and the main reason is that the thickness of MoS₂ varies with strain (as discussed in



Fig. 1 Supercell used to model the $Gr-MoS_2$ heterostructure, comprising 4 \times 4 primitive cells of MoS_2 and 5 \times 5 primitive cells of graphene. Top (a), and side (b) views of relaxed atomic structures of $Gr-MoS_2$ heterostructures. *D* is the interlayer distance between graphene and MoS_2 .

Table 1 Equilibrium distance of ${\rm Gr-MoS}_2$ vdW heterojunction under different strain

Strain (%)	Distance (Å)
-4	3.349
-2	3.383
0	3.392
2	3.417
4	3.439
6	3.453

Fig. S7[†]). The typical covalent bond length of C–S is about 1.81 Å while the sum of vdW radii of C and S is 3.56 Å, therefore, typical vdW interaction can be expected between graphene and MoS₂ during the strain process. The typical vdW interaction character is further confirmed by binding energies. Here, the binding energy (E_b) between graphene and MoS₂ is defined as $E_b = (E_{tot} - E_{Gr} - E_{MOS_2})/A$, where E_{tot}, E_{Gr} , and E_{MOS_2} are the total energies of Gr–MoS₂ heterojunction, isolated graphene and MoS₂ layer, respectively; and *A* is the surface area of the supercell. The calculated E_b values are in the range of -0.347 and -0.362 J m⁻², which suggests that MoS₂ is physiosorbed on graphene, just like graphene-SnS⁴⁹ and graphene-WSe₂,⁵⁰ whose binding energies are 0.281 and 0.260 J m⁻² close to typical vdW interstratification -0.3 J m⁻².

Electronic property

The energy band structures of monolayer MoS_2 and pristine graphene are checked initially, as plotted in Fig. 2a. It shows that the monolayer MoS_2 is a direct bandgap semiconductor at the *K* point with a band gap of 1.75 eV *via* the SCAN+rVV10 functional, while the graphene has no distinguishable bandgap and manifests as metallic character with π band (bonding) and π^* band (antibonding) cross at the Dirac point at the hexagonal corner of the graphene's Brillouin zone, which agrees with previous theoretical studies.^{6,51} More details can be drawn from the partial density of states (PDOS) in Fig. 2b. In freestanding graphene, the half-filled $2p_z$ orbitals of carbon atoms perpendicular to the planar form the π band and π^* band, which touch at the Dirac point exactly at the Fermi energy, consistent with the energy band results. For MoS₂, it can be seen that the bottom of the conduction band is mainly contributed by Mo-4d orbitals and the top of the valence band is contributed by Mod and S-p orbitals. Also, Mo-d and S-p orbitals are hybridized with each other near the top of the valence band.

The band diagram of Gr-MoS₂ heterostructure is shown in Fig. 2a. As expected, the energy band of the heterojunction is nearly a simple linear superposition compared with the energy bands of graphene and MoS₂, because of the weak vdW force and small lattice mismatch, which further proves that both the semiconducting nature of MoS₂ and the semi-metal performance of graphene with a Dirac cone are basically well preserved. Additionally, relative to the pristine MoS₂ monolayer, bandgap of the MoS₂ in Gr-MoS₂ heterojunction is increased by 0.08 eV, meanwhile, the direct band gap at K points transforms into indirect with valence band maximum value (VBM) places in the Γ point and the conduction band minimum (CBM) remains in the K point. The transform from direct to indirect bandgap in MoS₂ is due to effects of graphene action on MoS₂ orbital contributions, as detailed in Fig. S3.[†] At the same time, Fermi level of the MoS₂ in the heterostructure moves upward around 0.50 eV from the VBM to the CBM, which means that an n-type Schottky barrier is formed in the heterostructure. Obviously from the PDOS of Mo-d and S-p orbitals in Gr-MoS₂ heterojunction in Fig. 2b, the Fermi level is close to CBM which also proves the formation of n-type Schottky barrier at Gr–MoS₂ interface. Notably, for graphene, a minimal band gap of 1.2 meV arises at the K point, which is owing to the sub-lattice symmetry breaking and interlayer force between the separated layers, which is similar to the heterostructure organized of graphene and other monolayer materials, graphene-SnS,49 grapheneh-BN,⁵² and graphene-WSe₂ (ref. 50) et al.



Fig. 2 (a) Band structures of 5×5 graphene sheet with the blue lines, $4 \times 4 \text{ MoS}_2$ monolayer with the purple lines, and $5 \times 5 \text{ Gr}-4 \times 4 \text{ MoS}_2$ heterojunction with the blue point represents the projected band of graphene, and the purple lines represent MoS₂. (b) Partial density of states (PDOS) of C-2p_z orbitals in isolated graphene, Mo-4d and S-3p orbitals in isolated MoS₂ and Gr–MoS₂ heterojunction. The Fermi energy level is set to be zero.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.

Work function (WF) is a central factor that determines the charge distribution upon the interface. Here, the calculated WF of graphene is about 4.59 eV, which agrees well with experimental measured value 4.50 eV53 and previous theoretical results of 4.73 eV,⁵⁴ while the monolayer MoS₂ has an electron affinity energy (EAE) of 4.32 eV and an ionization energy (IE) of 6.07 eV. Since graphene's WF 4.59 eV locates within the band gap of MoS_2 and is closer to the EAE of MoS_2 (4.32 eV), when graphene layer contacts with MoS₂ layer, electrons in the graphene layer spontaneously flow to the MoS₂ layer, so that electrons accumulate on the MoS₂ side, and leave behind the aggregated holes in the graphene layer. Therefore, comparatively speaking, the Fermi level is expected to rise in MoS₂ which will promote the formation of an n-type Schottky barrier, while the Fermi level of the graphene is reduced correspondingly and the Dirac point is going to be higher than the Fermi level in the graphene after stacking.

The charge transfer condition at $Gr-MoS_2$ interface is confirmed in electron density redistribution in Fig. 3, which further visualizes the interface coupling between the graphene and MoS_2 layers. The electron density difference, $\Delta \rho(x, y, z)$, is an effective tool to analyze the bonding at $Gr-MoS_2$ interfaces which is defined as the difference of the electron density distribution of the composite full system and the isolated subsystems:

$$\Delta \rho = \rho_{\rm tot} - \rho_{\rm Gr} - \rho_{\rm MoS_2},\tag{1}$$

where ρ_{tot} , ρ_{Gr} , and ρ_{MOS_2} are electron density of the Gr–MOS₂ junction, the free-standing graphene and the MoS₂, respectively. As described in Fig. 3a and b, the $\Delta \rho$ mainly localized around the Gr–MOS₂ interface, the blue and red area represent the depletion and accumulation of electrons, with respect to pristine graphene and MoS₂, respectively. It is clear that electrons accumulate at MoS₂ layer, while the side of the graphene shows electrons depletion, illustrating that electrons migrate from graphene layer to MoS₂ layer. So that a built-in electric field with the orientation from the positive charges

accumulated graphene to the negative charged MoS_2 will be constituted in the heterostructure, which ultimately leads to the generation of an interface dipole, ΔV^{55} in Gr–MoS₂ heterojunction, since the other important factor causing interface dipole, metal-induced gap states (MIGS), is almost negligible in 2D Gr–MoS₂ junctions as shown in PDOS in Fig. 2b, and band structure in Fig. 2a, the band structure of MoS₂ is clearly identifiable and remains semiconducting characteristics without MIGS.

According to Poisson equation, the interface dipole ΔV and electron density distribution $\Delta \rho$ satisfies the following relation:

$$\Delta V = \frac{e^2}{\epsilon_0 A} \iiint z \Delta \rho(x, y, z) dx dy dz, \qquad (2)$$

In which *z* is the distance from the middle of the Gr–MoS₂ interface and *A* is the contact area. In density functional theory (DFT) calculation with a slab model, ΔV can be alternately obtained as the difference between the asymptotic values of the electrostatic potential difference in the vacuum with an expression:

$$\Delta V = W_{\rm Gr-MoS_2} - W_{\rm Gr},\tag{3}$$

where W_{Gr} and $W_{\text{Gr}-\text{MOS}_2}$ are the work function of the graphene and the graphene covered by MOS₂. The existence of interface dipole makes the Schottky barrier deviate from the Schottky– Mott limit and promotes the formation of Fermi-level pinning effect. However, the ΔV is just 0.066 eV in Gr–MoS₂ heterojunction (shown in Fig. S4†), which means small interface coupling and extremely weak Fermi-level pinning effect. On the other hand, the Schottky barrier at Gr–MoS₂ interface also proves this point. The n-type Schottky barrier height (SBH) is 0.33 eV (Fig. 4c) at Gr–MoS₂ interface which is approximately equal to the difference (0.27 eV) between graphene work function ($W_{\text{Gr}} = 4.59$ eV) and MoS₂ electron affinity energy (4.32 eV). Hence, the SBH basically obeys the Schottky–Mott limit, in which the SBH is obtained by band alignment of the noninteracting subsystems.



Fig. 3 (a) 3D electron density redistribution of $Gr-MoS_2$ heterostructure. The isosurface refers to isovalues of 1×10^{-3} e Å⁻³. (b) The planeaveraged electron density difference $\Delta \rho(z)$ along the z-direction perpendicular to the $Gr-MoS_2$ interfaces. Red (blue) region represents electron accumulation (depletion). The region of interface is indicated by two dotted black lines representing the surface-atom-layers of carbon and sulfur.

Paper



Fig. 4 Projected band structures of MoS_2 in Gr–MoS₂ heterojunction with strain from -4% (a) to 6% (f). The red point represents the projected band of MoS_2 , and the size of the point represents the weight. The blue double arrows represent the Schottky barrier height.

Effects of in-plane strain

Sequentially, sensitive responses of electronic performances in Gr-MoS₂ heterostructure in case of in-plane biaxial compression and tension strains are evaluated. Especially the Schottky barriers at Gr-MoS₂ interfaces as indicated by the project band structures of MoS₂ in heterojunctions are shown in Fig. 4. By assembly with graphene substrate, the direct band gap of monolayer MoS₂ transforms to indirect and an n-type Schottky barrier forms at Gr-MoS₂ interface with absence of strain in Fig. 4c. It is observed that with compress strain changes from 2% to 4% in Fig. 4a and b, the VBM and CBM of MoS₂ keep at the high symmetry point K, manifesting as a direct band gap. Simultaneously, the $E_{\rm F}$ moves downward to the VBM of MoS₂, creating n-type Schottky barriers. However, with tensile strain, the VBM in MoS_2 shifts from K to Γ , the CBM keeps at the high symmetry point K, resulting an indirect band gap. When tensile strain varies from 2% to 6%, the Fermi level gradually moves towards the CBM of MoS₂, representing a reduction in the ntype Schottky barrier of heterostructure, as illustrated in Fig. 4(d-f). Relatively speaking, although the energy difference from VBM to the Fermi level also decreases with tensile strain, it is always significantly greater than that of CBM to the Fermi level, thus the system vigorously preserves the contact of n-type. It is worth noting that the n-type Schottky barrier turns to ohmic contact at a tensile strain of 6%. It could be speculated that the certain biaxial strain is not only conducive to the occurrence of conversion for the contact types, but also the modulation of the Schottky barrier heights.

The band structures of $Gr-MoS_2$ heterojunction are shown in Fig. 5. Since the effective masses are closely associated with

carrier motion capacity, therefore the effective mass of graphene in this heterostructure is firstly considered to check whether the superior carrier motion capacity of graphene is maintained. The electron mobility is inversely proportional to the effective mass, which is described as: $\mu = e\tau/m^*$, where μ is electron mobility, e is the electron charge, m^* is the effective electron mass, and τ is the relaxation time. For semiconductors, both electrons and holes contribute to carrier mobility, therefore, the effective masses of holes (m_h^*) and electrons (m_e^*) of the heterostructure are calculated. The effective masse of electrons and holes are determined by matching parabolic functions to the band structure of CBM and VBM for the wave vectors:^{48,56}

$$m^* = \hbar \left(\frac{\partial^2 E(K)}{\partial k^2}\right)^{-1}.$$
 (4)

Herein, \hbar is the simplified Planck constant and k represents the wave vector. The effective mass values of electron and hole at the K point are simulated to be $2.57 \times 10^{-3} m_0$ and $2.58 \times 10^{-3} m_0$ respectively in Fig. 5c with absence of strain, where m_0 is the mass of the free electron. For carriers, this lower effective masses at the time of preparation contributes to their mobility, which anticipates that this kind of heterostructure is suitable for high performance electronic and optoelectronic applications.

As shown in Fig. 5c, the energy band of graphene remains linear near the Dirac point, while the Fermi level in the heterojunction is shifted and lied slightly below the Dirac point of graphene. This is because electrons transfer from graphene to MoS_2 which is consistent with the charge transfer results (Fig. 3). In addition, since the small quantity of charge transfer



Fig. 5 Band structures of the Gr-MoS₂ heterostructure under different strain. The blue, and red lines stand respectively for bonding π -band and antibonding π *-band of graphene. (a)–(f) represent the strain of -4%, -2%, 0%, 2%, 4%, and 6%, respectively. Detailed information of Dirac Point is shown. The Fermi level is set to zero and marked by black dotted lines.

at Gr–MoS₂ interface, the Fermi level shift is small, according with the vdW characteristics between graphene and MoS₂. When tensile strain is applied, the charge transfer between graphene and MoS₂ increase gradually (as shown in Fig. S5†), so that the Fermi level gradually moving away from the Dirac point (Fig. 5d–f).

A tiny band gap of 1.2 meV for graphene in Gr–MoS₂ heterostructure is opened at the Dirac point due to sublattice symmetry breaking, shown in Fig. 5c. Based on the π -electron tight-binding (TB) approximation of graphene, the dispersion relation near the Fermi level can be approximated as:

$$E(k) = \pm \sqrt{\varDelta^2 + (\hbar \nu_{\rm F} k)^2},\tag{5}$$

where *k* is the wave vector related to the Dirac point, $\nu_{\rm F}$ is the Fermi velocity, Δ is the on-site energy difference between the two sub-lattices of graphene, and the signs \pm correspond to the conduction band and the valence band, respectively. For a freestanding graphene monolayer, the on-site energies of two sub-lattices are identical ($\Delta = 0$), resulting in a zero-band gap and the linear dispersion relation near the Dirac point. For the Gr–MoS₂ heterostructure, the charge redistribution breaks the equivalence of two graphene sub-lattices and the symmetry of graphene is reduced, therefore graphene can lower the total free energy of the system by opening up a band gap at the Dirac point.⁵⁷ Thus, the opened band gap of graphene in the Gr–MoS₂ heterostructure is non-zero as $E_{\rm g} = 2\Delta$.^{58,59}



Fig. 6 Partial density of states (PDOS) of (a) $C-p_z$ orbitals in isolated graphene and in $Gr-MoS_2$ heterojunction; and (b) $C-p_z$, S-p, and Mod orbitals in $Gr-MoS_2$ heterojunction. The Fermi energy level is set to be zero.

Paper

The C-p_z orbitals in isolated graphene and Gr-MoS₂ heterojunction are displayed in Fig. 6a, and it is obvious that the CBM and VBM at Dirac point are both contributed by the C-p_z orbital electrons in both systems. In comparison with freestanding graphene, the PDOS of the $C-p_z$ orbitals in heterostructure are more local. Furthermore, the PDOS of C-pz, S-p, and Mod orbitals in Gr-MoS₂ heterojunction are shown in Fig. 6b, and a weak hybridization is formed between the C-p_z of graphene and S-p orbitals of the MoS₂, as marked by a green circle. Therefore, after the deposition of MoS₂, the symmetry of graphene is broken, and the interaction of $C-p_z$ and S-p in the direction perpendicular to the interface give rise to out-plane sp³ orbitals in graphene, the bonding π and anti-bonding π^* bands repulse each other, forming an energy gap at Dirac point.^{60,61} As tensile strain is applied, the interaction between MoS₂ and graphene becomes stronger, a larger band gap has been opened. Additionally, a maximum gap of 2.6 meV is obtained when 6% tensile strain is imposed.

Conclusions

In conclusion, the structural optimizations and electronic characteristics of Gr-MoS2 vdW heterostructure are explored under the applied in-plane biaxial strains through firstprinciples calculations. The heterostructure is formed by the weak interlayer coupling with the typical vdW binding energy of 0.35 Jm^{-2} . In Gr-MoS₂ heterojunctions, the electronic band structure of graphene and MoS₂ are preserved well, with an ntype SBH of 0.33 eV is obtained at the equilibrium state with absence of strain, which may be effectively adjusted via imposing the in-plane biaxial strains. Especially, the n-type Schottky contact transform to ohmic contact when the tensile strain is greater than 6%. In contrast to metal-MoS₂ contacts, the Gr-MoS₂ interface presents a negligible interface dipole, implying that the SBH at the interface can be obtained from the freestanding layers by aligning the vacuum levels. The linear Dirac-like dispersion relation around the Fermi level of graphene is still preserved in Gr-MoS₂ interface. In addition, a tiny band gap of 1.2 meV of Gr-MoS₂ interface is opened at the Dirac K-point of graphene, and the bandgap increase to 2.6 meV when 6% tensile strain is applied. The appearance of the energy band gap of graphene has opened up new possibilities for using it in graphene-based device applications. Moreover, in-plane strain can be used as an effective means to regulate the Schottky barrier.

Conflicts of interest

There are no conflicts of interest to declare.

Acknowledgements

This work was financially supported by Natural Science Foundation of Hubei Province of China (No. 2020CFB245), teaching research projects in Colleges and Universities of Hubei (No. 2020668), National Natural Science Foundation of China (22101198, 51801057), research start-up funding of Hubei University of Education (19RC03, ESRC20220030), teaching research project of Hubei University of Education (X2019007).

References

- 1 Y. Zhao, M. Gobbi, L. E. Hueso and P. Samori, Molecular Approach to Engineer Two-Dimensional Devices for CMOS and beyond-CMOS Applications, *Chem. Rev.*, 2022, **122**, 50– 131.
- 2 E. C. Ahn, 2D materials for spintronic devices, *npj 2D Mater. Appl.*, 2020, **4**, 17.
- 3 G. G. Naumis, S. Barraza-Lopez, M. Oliva-Leyva and H. Terrones, Electronic and optical properties of strained graphene and other strained 2D materials: a review, *Rep. Prog. Phys.*, 2017, **80**, 1–62.
- 4 Y. Dong, C. Yan, H. Zhao and Y. Lei, Recent Advances in 2D Heterostructures as Advanced Electrode Materials for Potassium-Ion Batteries, *Small Struct.*, 2022, **3**, 2100221.
- 5 K. S. Novoselov, A. K. Geim, S. V. Morozov, D. Jiang, Y. Zhang, S. V. Dubonos, I. V. Grigorieva and A. A. Firsov, Electric Field Effect in Atomically Thin Carbon Films, *Science*, 2004, **306**, 666–669.
- 6 A. H. Castro Neto, F. Guinea, N. M. R. Peres, K. S. Novoselov and A. K. Geim, The electronic properties of graphene, *Rev. Mod. Phys.*, 2009, **81**, 109–162.
- 7 P. V. Pham, S. C. Bodepudi, K. Shehzad, Y. Liu, Y. Xu, B. Yu and X. Duan, 2D Heterostructures for Ubiquitous Electronics and Optoelectronics: Principles, Opportunities, and Challenges, *Chem. Rev.*, 2022, **122**, 6514–6613.
- 8 K. Shi, J. Su, H. Liang, K. Hu and J. Xu, Highly optically transparent graphene mesh for electromagnetic interference shielding, *Diamond Relat. Mater.*, 2022, **123**, 108849.
- 9 K. F. Mak, C. Lee, J. Hone, J. Shan and T. F. Heinz, Atomically Thin MoS₂: A New Direct-Gap Semiconductor, *Phys. Rev. Lett.*, 2010, **105**, 136805.
- 10 H. Liu, A. T. Neal and P. D. Ye, Channel Length Scaling of MoS₂ MOSFETs, *ACS Nano*, 2012, **6**, 8563–8569.
- 11 O. Samy, D. Birowosuto and A. El Moutaouakil, Ieee, A short review on Molybdenum disulfide (MoS₂) applications and challenges, 6th International Conference on Renewable Energy-Generation and Applications (ICREGA), United Arab Emirates Univ, Al Ain, U Arab Emirates, (2021), pp. 220–222.
- 12 G. He, K. Ghosh, U. Singisetti, H. Ramamoorthy, R. Somphonsane, G. Bohra, M. Matsunaga, A. Higuchi, N. Aoki, S. Najmaei, Y. Gong, X. Zhang, R. Vajtai, P. M. Ajayan and J. P. Bird, Conduction Mechanisms in CVD-Grown Monolayer MoS₂ Transistors: From Variable-Range Hopping to Velocity Saturation, *Nano Lett.*, 2015, 15, 5052–5058.
- 13 V. K. Sangwan and M. C. Hersam, Electronic Transport in Two-Dimensional Materials, *Annu. Rev. Phys. Chem.*, 2018, 69, 299–325.
- 14 S. Das, H.-Y. Chen, A. V. Penumatcha and J. Appenzeller, High Performance Multilayer MoS2 Transistors with Scandium Contacts, *Nano Lett.*, 2013, **13**, 100–105.

- 15 D. S. Schulman, A. J. Arnold and S. Das, Contact engineering for 2D materials and devices, *Chem. Soc. Rev.*, 2018, 47, 3037–3058.
- J. Y. Kwak, J. Hwang, B. Calderon, H. Alsalman, N. Munoz,
 B. Schutter and M. G. Spencer, Electrical Characteristics of Multilayer MoS2 FET's with MoS2/Graphene Heterojunction Contacts, *Nano Lett.*, 2014, 14, 4511–4516.
- 17 S. Kang, D. Lee, J. Kim, A. Capasso, H. S. Kang, J.-W. Park, C.-H. Lee and G.-H. Lee, 2D semiconducting materials for electronic and optoelectronic applications: potential and challenge, *2DMaterials*, 2020, 7, 022003.
- 18 S. Gbadamasi, M. Mohiuddin, V. Krishnamurthi, R. Verma, M. W. Khan, S. Pathak, K. Kalantar-Zadeh and N. Mahmood, Interface chemistry of two-dimensional heterostructures-fundamentals to applications, *Chem. Soc. Rev.*, 2021, **50**, 4684–4729.
- 19 J. Shim, D.-H. Kang, Y. Kim, H. Kum, W. Kong, S.-H. Bae, I. Almansouri, K. Lee, J.-H. Park and J. Kim, Recent progress in Van der Waals (vdW) heterojunction-based electronic and optoelectronic devices, *Carbon*, 2018, **133**, 78–89.
- 20 B. Huang, Q. Xu and S.-H. Wei, Theoretical study of corundum as an ideal gate dielectric material for graphene transistors, *Phys. Rev. B*, 2011, **84**, 155406.
- 21 X. Xu, C. Liu, Z. Sun, T. Cao, Z. Zhang, E. Wang, Z. Liu and K. Liu, Interfacial engineering in graphene bandgap, *Chem. Soc. Rev.*, 2018, **47**, 3059–3099.
- 22 F. Varchon, R. Feng, J. Hass, X. Li, B. N. Nguyen, C. Naud, P. Mallet, J. Y. Veuillen, C. Berger, E. H. Conrad and L. Magaud, Electronic Structure of Epitaxial Graphene Layers on SiC: Effect of the Substrate, *Phys. Rev. Lett.*, 2007, 99, 126805.
- 23 R. Nandee, M. A. Chowdhury, A. Shahid, N. Hossain and M. Rana, Band gap formation of 2D materialin graphene: Future prospect and challenges, *Results Eng.*, 2022, **15**, 100474.
- 24 N. Jain, F. Yang, R. B. Jacobs-Gedrim, X. Xu, M. P. Anantram and B. Yu, Extenuated interlayer scattering in double-layered graphene/hexagonal boron nitride heterostructure, *Carbon*, 2018, **126**, 17–22.
- 25 F. Ersan, D. Kecik, V. O. Ozcelik, Y. Kadioglu, O. U. Akturk, E. Durgun, E. Akturk and S. Ciraci, Two-dimensional pnictogens: A review of recent progresses and future research directions, *Appl. Phys. Rev.*, 2019, **6**, 021308.
- 26 D. Qiu and E. K. Kim, Electrically Tunable and Negative Schottky Barriers in Multi-layered Graphene/MoS₂ Heterostructured Transistors, *Sci. Rep.*, 2015, **5**, 13743.
- 27 L. Yu, Y.-H. Lee, X. Ling, E. J. G. Santos, Y. C. Shin, Y. Lin, M. Dubey, E. Kaxiras, J. Kong, H. Wang and T. Palacios, Graphene/MoS₂ Hybrid Technology for Large-Scale Two-Dimensional Electronics, *Nano Lett.*, 2014, 14, 3055–3063.
- 28 S. Singh, C. Espejo and A. H. Romero, Structural, electronic, vibrational, and elastic properties of graphene/MoS₂ bilayer heterostructures, *Phys. Rev. B*, 2018, **98**, 155309.
- 29 Z. Zhuo, F. Yang, J. Han, X. Cao, Y. Tao, L. Zhang, W. Liu,
 Z. Zhu and Y. Dai, Substitutional doping at S site of MoS₂/
 G heterostructure: The influence on voltage-current and

electronic characteristics, *Superlattices Microstruct.*, 2021, **156**, 106978.

- 30 J. N. Coleman, M. Lotya, A. O'Neill, S. D. Bergin, P. J. King, U. Khan, K. Young, A. Gaucher, S. De, R. J. Smith, I. V. Shvets, S. K. Arora, G. Stanton, H. Y. Kim, K. Lee, G. T. Kim, G. S. Duesberg, T. Hallam, J. J. Boland, J. J. Wang, J. F. Donegan, J. C. Grunlan, G. Moriarty, A. Shmeliov, R. J. Nicholls, J. M. Perkins, E. M. Grieveson, K. Theuwissen, D. W. McComb, P. D. Nellist and V. Nicolosi, Two-dimensional nanosheets produced by liquid exfoliation of layered materials, *Science*, 2011, 331, 568–571.
- S1 C. Chang, W. Chen, Y. Chen, Y. Chen, Y. Chen, F. Ding, C. Fan, H. J. Fan, Z. Fan, C. Gong, Y. Gong, Q. He, X. Hong, S. Hu, W. Hu, W. Huang, Y. Huang, W. Ji, D. Li, L.-J. Li, Q. Li, L. Lin, C. Ling, M. Liu, N. Liu, Z. Liu, K. P. Loh, J. Ma, F. Miao, H. Peng, M. Shao, L. Song, S. Su, S. Sun, C. Tan, Z. Tang, D. Wang, H. Wang, J. Wang, X. Wang, X. Wang, A. T. S. Wee, Z. Wei, Y. Wu, Z.-S. Wu, J. Xiong, Q. Xiong, W. Xu, P. Yin, H. Zeng, Z. Zeng, T. Zhai, H. Zhang, H. Zhang, Q. Zhang, T. Zhang, X. Zhang, L.-D. Zhao, M. Zhao, W. Zhao, Y. Zhao, K.-G. Zhou, X. Zhou, Y. Zhou, H. Zhu, H. Zhang and Z. Liu, Recent Progress on Two-Dimensional Materials, *Acta Phys.-Chim. Sin.*, 2021, 37, 2108017.
- 32 D. Yuan, Y. Dou, Z. Wu, Y. Tian, K.-H. Ye, Z. Lin, S. X. Dou and S. Zhang, Atomically Thin Materials for Next-Generation Rechargeable Batteries, *Chem. Rev.*, 2022, **122**, 957–999.
- 33 Y. Ma, Y. Dai, M. Guo, C. Niu and B. Huang, Graphene adhesion on MoS₂ monolayer: An ab initio study, *Nanoscale*, 2011, 3, 3883–3887.
- 34 G. Kresse and J. Hafner, Ab initio molecular dynamics for liquid metals, *Phys. Rev. B*, 1993, 47, 558–561.
- 35 P. E. Blöchl, Projector augmented-wave method, *Phys. Rev. B*, 1994, **50**, 17953–17979.
- 36 G. Kresse and J. Furthmüller, Efficient iterative schemes for ab initio total-energy calculations using a plane-wave basis set, *Phys. Rev. B*, 1996, **54**, 11169–11186.
- 37 G. Kresse and D. Joubert, From ultrasoft pseudopotentials to the projector augmented-wave method, *Phys. Rev. B*, 1999, 59, 1758–1775.
- 38 J. Sun, A. Ruzsinszky and J. P. Perdew, Strongly Constrained and Appropriately Normed Semilocal Density Functional, *Phys. Rev. Lett.*, 2015, **115**, 036402.
- 39 H. Peng, Z.-H. Yang, J. P. Perdew and J. Sun, Versatile van der Waals Density Functional Based on a Meta-Generalized Gradient Approximation, *Phys. Rev. X*, 2016, **6**, 041005.
- 40 H. Peng and J. P. Perdew, Rehabilitation of the Perdew-Burke-Ernzerhof generalized gradient approximation for layered materials, *Phys. Rev. B*, 2017, **95**, 081105.
- 41 Q. Wang, K. Dou and X. Shi, Band alignment in multilayered semiconductor homojunctions supported on metals, *J. Mater. Chem. C*, 2020, **8**, 959–967.
- 42 J. Neugebauer and M. Scheffler, Adsorbate-substrate and adsorbate-adsorbate interactions of Na and K adlayers on Al(111), *Phys. Rev. B*, 1992, **46**, 16067–16080.

- 43 T. Böker, R. Severin, A. Müller, C. Janowitz, R. Manzke, D. Voß, P. Krüger, A. Mazur and J. Pollmann, Band structure of MoS₂, MoSe₂, and α-MoTe₂: Angle-resolved photoelectron spectroscopy and ab initio calculations, *Phys. Rev. B*, 2001, **64**, 235305.
- 44 A. A. Al-Hilli and B. L. Evans, The preparation and properties of transition metal dichalcogenide single crystals, *J. Cryst. Growth*, 1972, **15**, 93–101.
- 45 J. Shi, L. Chen, M. Yang, Z. Mi, M. Zhang, K. Gao, D. Zhang, S. Su and W. Hou, Interface contact and modulated electronic properties by external vertical strains and electric fields in graphene/MoS₂ heterostructure, *Curr. Appl. Phys.*, 2022, **39**, 331–338.
- 46 K. Y. Thai, I. Park, B. J. Kim, A. T. Hoang, Y. Na, C. U. Park, Y. Chae and J.-H. Ahn, MoS₂/Graphene Photodetector Array with Strain-Modulated Photoresponse up to the Near-Infrared Regime, *ACS Nano*, 2021, **15**, 12836–12846.
- 47 Q. Wang, B. Deng and X. Shi, A new insight for ohmic contacts to MoS_2 : by tuning MoS_2 affinity energies but not metal work-functions, *Phys. Chem. Chem. Phys.*, 2017, **19**, 26151–26157.
- 48 X. Lu, L. Li, X. Guo, J. Ren, H. Xue and F. Tang, The controllable electronic characteristics and Schottky barrier of graphene/GaP heterostructure via interlayer coupling and in-plane strain, *Mater. Sci. Eng.*, *B*, 2022, **284**, 115882.
- 49 W. Xiong, C. Xia, X. Zhao, T. Wang and Y. Jia, Effects of strain and electric field on electronic structures and Schottky barrier in graphene and SnS hybrid heterostructures, *Carbon*, 2016, **109**, 737–746.
- 50 M. Sun, J.-P. Chou, J. Yu and W. Tang, Effects of structural imperfection on the electronic properties of graphene/ WSe₂ heterostructures, *J. Mater. Chem. C*, 2017, **5**, 10383–10390.
- 51 A. C. Ferrari, J. C. Meyer, V. Scardaci, C. Casiraghi, M. Lazzeri, F. Mauri, S. Piscanec, D. Jiang, K. S. Novoselov, S. Roth and A. K. Geim, Raman Spectrum of Graphene and Graphene Layers, *Phys. Rev. Lett.*, 2006, **97**, 187401.
- 52 E. Wang, X. Lu, S. Ding, W. Yao, M. Yan, G. Wan, K. Deng,S. Wang, G. Chen, L. Ma, J. Jung, A. V. Fedorov, Y. Zhang,G. Zhang and S. Zhou, Gaps induced by inversion

symmetry breaking and second-generation Dirac cones in graphene/hexagonal boron nitride, *Nat. Phys.*, 2016, **12**, 1111–1115.

- 53 H. Li, Z. Zhou and H. Wang, Tunable Schottky barrier in InTe/graphene van der Waals heterostructure, *Nanotechnology*, 2020, **31**, 335201.
- 54 W. Hu, T. Wang, R. Zhang and J. Yang, Effects of interlayer coupling and electric fields on the electronic structures of graphene and MoS₂ heterobilayers, *J. Mater. Chem. C*, 2016, 4, 1776–1781.
- 55 M. Farmanbar and G. Brocks, First-principles study of van der Waals interactions and lattice mismatch at MoS₂/metal interfaces, *Phys. Rev. B*, 2016, **93**, 085304.
- 56 B. Zhou, X. Wang, S. Dong, K. Zhang and W. Mi, Tunable gap opening and spin polarization of two dimensional graphene/ hafnene van der Waals heterostructures, *Carbon*, 2017, **120**, 121–127.
- 57 I. N. Yakovkin, Dirac Cones in Graphene, Interlayer Interaction in Layered Materials, and the Band Gap in MoS₂, *Crystals*, 2016, **6**, 143.
- 58 H. V. Phuc, N. N. Hieu, B. D. Hoi, L. T. T. Phuong and C. V. Nguyen, First principle study on the electronic properties and Schottky contact of graphene adsorbed on MoS₂ monolayer under applied out-plane strain, *Surf. Sci.*, 2018, 668, 23–28.
- 59 H. V. Phuc, N. N. Hieu, B. D. Hoi and C. V. Nguyen, Interlayer coupling and electric field tunable electronic properties and Schottky barrier in a graphene/bilayer-GaSe van der Waals heterostructure, *Phys. Chem. Chem. Phys.*, 2018, **20**, 17899–17908.
- 60 H. Coy Diaz, J. Avila, C. Chen, R. Addou, M. C. Asensio and M. Batzill, Direct Observation of Interlayer Hybridization and Dirac Relativistic Carriers in Graphene/MoS₂ van der Waals Heterostructures, *Nano Lett.*, 2015, **15**, 1135–1140.
- 61 D. Pierucci, H. Henck, J. Avila, A. Balan, C. H. Naylor,
 G. Patriarche, Y. J. Dappe, M. G. Silly, F. Sirotti,
 A. T. C. Johnson, M. C. Asensio and A. Ouerghi, Band
 Alignment and Minigaps in Monolayer MoS₂-Graphene van
 der Waals Heterostructures, *Nano Lett.*, 2016, 16, 4054–4061.