RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2023, 13, 26041

Received 13th June 2023 Accepted 18th August 2023

DOI: 10.1039/d3ra03935h

rsc.li/rsc-advances

1. Introduction

The ecological and energy transition must address the need for a growing and more energy-intensive economy while respecting environmental constraints and ecological considerations. In this context, there is currently great interest in developing innovative environmental technologies for energy storage and recovery. Furthermore, with the ever-increasing trend of modern electronics integration, miniaturization, and multifunctionalization, nanocomposite materials with high dielectric permittivity may find more widespread use in capacitors, field effect transistors, memory, and energy storage devices.¹⁻⁷

In this particular case, power electronics applications require relatively light passive components that occupy the smallest volume possible, along with high dielectric

^dJožef Stefan Institute, Jamova Cesta 39, Ljubljana, 1000, Slovenia

Dielectric and energy storage properties of surfacemodified BaTi_{0.89}Sn_{0.11}O₃@polydopamine nanoparticles embedded in a PVDF-HFP matrix

Marwa Zahid, ^(b) ^a Salma Touili, ^{ab} M'barek Amjoud, ^(b) ^a Daoud Mezzane, ^{ab} Mohamed Gouné, ^c Hana Uršič, ^(b) ^d Matej Šadl, ^(b) ^d Youssef Elamraoui, ^e Khalid Hoummada, ^f Zdravko Kutnjak^{*d} and Mimoun El Marssi^b

In the most recent electronic and electric sectors, ceramic-polymer nanocomposites with high dielectric permittivity and energy density are gaining popularity. However, the main obstacle to improving the energy density in flexible nanocomposites, besides the size and morphology of the ceramic filler, is the low interfacial compatibility between the ceramic and the polymer. This paper presents an alternative solution to improve the dielectric permittivity and energy storage properties for electronic applications. Here, the poly(vinylidene fluoride-hexafluoropropylene) (PVDF-HFP) matrix is filled with surface-modified BaTi_{0.89}Sn_{0.11}O₃/polydopamine nanoparticles (BTS₁₁) nanoparticles, which is known for exhibiting multiphase transitions and reaching a maximum dielectric permittivity at room temperature. BTS₁₁ nanoparticles were synthesized by a sol-gel/hydrothermal method at 180 °C and then functionalized by polydopamine (PDA). As a result, the nanocomposites exhibit dielectric permittivity (ε_t) of 46 and a low loss tangent (tan δ) of 0.017 at 1 kHz at a relatively low weight fraction of 20 wt% of BTS₁₁@PDA. This is approximately 5 times higher than the pure PVDF-HFP polymer and advantageous for energy storage density in nanocomposites. The recovered energy storage for our composites reaches 134 mJ cm $^{-3}$ at an electric field of 450 kV cm⁻¹ with a high efficiency of 73%. Incorporating PDA-modified BTS_{11} particles into the PVDF-HFP matrix demonstrates highly piezo-active regions associated with BTS₁₁ particles, significantly enhancing functional properties in the polymer nanocomposites.

permittivity, high dielectric breakdown strength, and good machinability. However, optimizing all of this simultaneously is extremely challenging. In general, combining piezoelectric ceramic and a polymer is a compelling solution that results in nanocomposite materials that benefit from the ferroelectric filler's high dielectric permittivity and the polymer's high dielectric breakdown strength.⁸

Lead-based perovskite materials have been considered the best candidates for energy storage, energy harvesting, piezoelectric photodegradation, and hydrogen production due to their astounding dielectric properties.9-13 Due to their excellent dielectric properties, lead-based ceramics such as PbZr_xTi_{1-x}O₃ (PZT) and (1 - x)Pb(Mg_{1/3}Nb_{2/3})O₃₋xPbTiO₃ (PMN-PT) systems dominate the piezoelectric device market today.13-17 On the other hand, barium titanate and its derivates, such as Bar- $Ba_xCa_{(1-x)}Zr_{(1-y)}Ti_yO_3$ (BCZT), and $Sr_{(1-x)}TiO_3$ (BST), $Ba_xCa_{(1-x)}Ti_{(1-y)}Sn_yO_3$ (BCTS) have been wildly used in the energy storage nanocomposites as a replacement for the leadbased ceramics, due to their ecological nature and their dielectric, ferroelectric acceptable and piezoelectric properties.¹⁸⁻²³ In our previous research, we investigated the lead-free $BaTi_{0.89}Sn_{0.11}O_3$ (BTS₁₁), which demonstrated enhanced dielectric properties and energy storage at

8

[&]quot;IMED-Lab, Cadi-Ayyad University, FST, Marrakech, 40000, Morocco. E-mail: marwa. zahid@ced.uca.ma

^bLPMC, University of Picardie Jules Verne, Amiens, 80039, France

ICMCB, University of Bordeaux, Pessac, 33600, France

^eLaMCScI, Faculty of Science, Mohammed V University, BP 1014, Rabat, Morocco

IM2NP, Aix Marseille University, Marseille, 13397, France

temperatures close to room temperature due to the multiphase phenomenon.^{10,24} At room temperature, enhanced dielectric and ferroelectric properties could be advantageous for ceramic/ polymer composites, providing an effective piezoelectric material for flexible energy storage and energy harvesting systems.

PVDF-based polymers are widely used in composites because of their dielectric performance ($\varepsilon_r \sim 10$), simple process, good biocompatibility, stable piezoelectric power output, and other advantages.^{25,26} Sadhu et al. fabricated a 15 vol%-BCZT/PVDF-HFP composite, which exhibited an $\varepsilon_r \sim 19$ at 10 kHz, with an energy storage density of 7.64 J cm⁻³.²³ Li *et al.* obtained an ε_r of ~22 at 1 kHz for5 vol%-BaTiO₃ (BT) nanofiber/PVDF-HFP composite and an energy storage density of 8.55 J cm⁻³ at 300 MV m⁻¹.²⁷ Kumar et al. fabricated the composite samples by synthesizing a BZT-BCT (0.5BZT-0.5BCT) ceramic pellet, sintering it at 1450 °C, grinding it, and then hydroxylating it with an H₂O₂ solution and incorporating 15 wt% of the nanopowder into a PVDF-HFP matrix. This composite sample exhibited an ε_r of 34.3 Moreover, the ε_r of a BST/PVDF composite at 1 kHz increases from ~ 10 for pure PVDF to 37 for the composite containing 25 vol% of BST.18 In contrast, Mei et al. observed a monotonic increase in ε_r from 14 for pure PVDF-HFP to 42 for 40 vol%-BST/PVDF-HFP composite at 100 Hz, with a maximum $U_{\text{discharge}}$ of 3.79 J cm⁻³ at 2100 kV cm⁻¹ with a 20 vol% BST content.28

In this respect, to further improve the dielectric and energy storage properties in the flexible piezo-composites at a low filler percentage, PDA surface-modified BTS₁₁ nanoparticles were embedded into the PVDF-HFP matrix. First, the BTS₁₁ nanopowders were elaborated at low temperatures using a sol–gel/ hydrothermal method. Then the surface of the BTS₁₁ was

hydroxylated with H_2O_2 and finally chemically modified with the PDA to improve the interfacial interaction between the fillers and the PVDF-HFP matrix.

2. Experimental details

2.1. Preparation of the BTS₁₁

Pure crystalline $BaTi_{0.89}Sn_{0.11}O_3$ nanopowders were obtained using previously reported sol-gel/hydrothermal method at 180 ° C.¹⁰ The first step in the surface modification process was hydroxylation. For this, 1 g of the BTS_{11} was sonicated for 30 min and then refluxed in 100 ml H_2O_2 for 4 h at 106 °C. The hydroxylated nanopowder was washed with ethanol and distilled water several times before drying overnight at 80 °C. Next, BTS_{11} nanoparticles were added to a 0.01 M dopamine hydrochloride ((HO)₂C₆H₃CH₂CH₂NH₂·HCl) aqueous solution and stirred on a magnetic stirrer at 60 °C for 24 h. Finally, the black suspension BTS_{11} @PDA was again washed with distilled water and ethanol several times and dried at 80 °C for 12 h.

2.2. Fabrication of the BTS₁₁/PVDF-HFP nano-composites

First, an appropriate amount of poly(vinylidene fluoride-cohexafluoropropylene) (PVDF-HFP) pellets were dissolved in dimethylformamide (DMF) and stirred for 24 h with a magnetic stirrer. Next, an adequate quantity of BTS₁₁@PDA nanopowder was mixed with a DMF solution, sonicated for 30 min, and stirred for an additional hour. The BTS₁₁/DMF slurry was dropped into the PVDF-HFP solution and ultrasonicated for 15 min. Finally, the mixture was poured into a Teflon mold and dried for 12 h in a vacuum oven at 60 °C to remove the solvent. The resulting films were then hot pressed for 10 min at 200 °C.



Fig. 1 Schematic diagram of the process for synthesizing BTS₁₁@PDA/PVDF-HFP nanocomposites.

Paper

Four different compositions were synthesized. All reactants are analytical-grade and used without any further purification. A schematic presentation of the fabrication process is shown in Fig. 1.

2.3. Characterization

X-ray diffraction (XRD) measurements were carried out using an X-ray diffractometer brand "RIGAKU". X-rays were produced from a CuKa radiation source, having a wavelength equal to 1.54056 Å. X-ray diffraction spectra were recorded at room temperature in the range of 2Θ between 20° and 80° with angle steps of 0.02° . A 5° per min scanning speed was employed to perform simple phase identification. Moreover, to have a quick insight into the purity of our samples, the Fourier-transform infrared spectroscopy (FTIR) measurements were carried out using a Bruker Vertex 70 spectrophotometer in transmission mode, 0.001 g of the powders were dispersed in 0.099 g of KBr matrix and analyzed in the frequency range 400-4000 cm⁻¹. The polarization–electric field (P–E) hysteresis loops were performed by CPE1701, PloyK, USA, with a high-voltage power supply (Trek 609-6, USA).

The microstructure of the samples was analyzed using a field emission scanning electron microscope (FE-SEM, JSM-7600F, JEOL, Japan). To prevent charging during analysis, a few nanometers thick carbon layer was deposited on the samples using a Precision Etching and Coating System (PECS 682, Gatan, USA). Piezo-response force microscopy (PFM) was performed on the surface of the prepared composite samples. An atomic force microscope (AFM; Jupiter XR Asylum Research, Oxford Instruments, CA, USA) and platinum-coated silicon tips with a radius of curvature ~10 nm (OMCL-AC240TM-R3, Olympus, Japan) were used for the analysis. The images were scanned in dual AC resonance-tracking mode. An electrical voltage of 3 V and a frequency of ~250 kHz was applied between a conductive AFM tip and the silver paste that served as the bottom electrode. After the PFM scans, the PFM phase hysteresis loops were measured in switching spectroscopy mode using the pulsed DC step signal and the superimposed AC drive signal, as described in ref. 29. The waveform parameters were as follows: the sequence of increasing steps of the DC electric field was driven at 20 Hz and a maximum amplitude of 40 or 50 V; the frequency of the triangular envelope was 0.99 Hz; a superimposed sinusoidal AC signal with an amplitude of 2 V and a frequency of \sim 310 kHz was used. Three cycles were measured in an off-electric-field mode.

3. Results and discussion

The XRD pattern of the as-prepared BTS₁₁ powder is displayed in Fig. 2. According to XRD analysis, the powder exhibits a pure perovskite structure devoid of any secondary phases. The BTS₁₁ multiphase was previously demonstrated in two of our previous published papers,^{10,24} and it was also reported in the literature.^{30,31} Therefore, the as-prepared powder (BTS₁₁), the hydroxylated powder (OH-BTS₁₁), and then the PDA-coated BTS₁₁ powder (BTS₁₁@PDA) were all subjected to FTIR



Fig. 2 XRD pattern of the as-prepared BTS₁₁ powder.

analysis to show whether the dopamine successfully bonded to the surface of the BTS₁₁, as demonstrated in Fig. 3. Particularly for the powders synthesized by the hydrothermal method, hydroxyl groups have reportedly been identified on the surface of barium titanate-based materials.^{32,33} However, the (–OH) amount needed to achieve acceptable compatibility with the polymer matrix is still insufficient and requires surface modification.¹⁰ Therefore, the surface of BTS₁₁ nanopowders was first hydroxylated with H₂O₂ and then coated with a PDA layer to increase the chemical interactions between BTS₁₁ nanoparticles and the PVDF-HFP matrix.

The band at 3445 cm⁻¹, corresponding to the stretching mode of the (–OH), is observed in the FTIR spectrum of asprepared BTS₁₁ powder (Fig. 3a). It grew wider in the spectra of hydroxylated powder and powder coated with PDA (Fig. 3b and c, respectively), suggesting that the surface hydroxylation was accomplished.^{34,35} The increasing intensity of the –M–O



Fig. 3 FTIR spectra of (a) the as-prepared BTS_{11} powder, (b) the hydroxylated BTS_{11} powder, and (c) BTS_{11} @PDA powder.

absorption band, centered between 500 and 650 cm⁻¹, indicates that the surface powder's functionalization was effective. There is noteworthy observation in the vibrations of the M-O functional groups within the treated BTS₁₁ samples compared to the pure BTS₁₁ material. Specifically, following the treatment with hydrogen peroxide, a distinct shift of the M-O bands towards lower wavenumbers was observed, indicating a decrease in the stretching vibration frequency of the M-O bonds. This intriguing phenomenon can be elucidated by considering the effective interaction occurring between the M-O bands and the -H and -OH groups present in the hydrogen peroxide (H_2O_2) and the dopamine $(C_8H_{11}NO_2)$ solutions during the treatment process. As these reactants are introduced to the BTS material, the -H and -OH groups interact with the M-O bonds, causing notable alterations in the electron cloud density surrounding these bonds. Consequently, the M-O bonds experience a spreading effect, leading to a reduction in their rigidity and causing a decrease in the frequency of their stretching vibrations.⁶ Furthermore, bands at 1260 cm^{-1} , 1480 cm^{-1} , 1620 cm^{-1} and 1900 cm⁻¹ correspond to the aromatic amine's C-N stretching vibration, aromatic C-C stretching vibration, N-H bending vibration, and finally, the C-H stretching vibration, respectively. The latter indicates that the BTS₁₁ nanoparticles were successfully coated with PDA.³⁶ The peak at 1450 cm⁻¹, assigned to the stretching vibration of CO_3^{2-} , is significantly weakened when coated with PDA, which could be due to the presence of carbonates due to CO2 adsorption.37,38

Fig. 4a shows the SEM micrograph of the BTS₁₁ nanopowder, while Fig. 4b shows the SEM micrograph of the BTS₁₁@PDA, and Fig. 4c depicts the 20 wt%-BTS₁₁@PDA/PVDF-HFP composites. Dopamine is easily self-polymerized, and the formation of polydopamine has high adherence to the surface of practically all types of oxides. The PDA layer can serve as a foundation for introducing the polymer matrix, allowing the attachment of other molecules onto the nanoparticles' surface. This can also enhance their dispersibility, stability, and compatibility with the PVDF-HFP polymer matrix.

The PDA coating can also improve the nanoparticles' biocompatibility, adhesion, and chemical stability. The Fig. 4c shows that the BTS_{11} nanoparticles are uniformly dispersed in the PVDF-HFP matrix. The SEM image of the BTS_{11} 's core-shell structure is shown in the inset of Fig. 4b, and the polydopamine shell's thickness is approximately 33 nm.



Fig. 5 XRD patterns of x wt%-BTS₁₁@PDA/PVDF-HFP composites with different weight percentage (a) x = 2 wt%, (b) x = 8 wt%, (c) x = 14 wt% and (d) x = 20 wt%.

Fig. 5 illustrates the XRD patterns of the BTS₁₁/PVDF-HFP composites with a different weight percentage of BTS₁₁@PDA in the polymer matrix (2, 8, 14, and 20 wt%). The semicrystalline nature of the PVDF-HFP is proved by the peaks positioned between 16° and 27° (Fig. 5a). The α -phase diffraction peaks situated at 17.4°, 18°, 19.4° and 22°, may be indexed as $\alpha(100)$, $\alpha(020)$, $\alpha(110)$ and $\alpha(020)$ respectively, while the β -phase is situated at 20° and is attributed to $\beta(110)$ and $\beta(200)$.^{39,40} The diffraction peaks of the BTS₁₁ get more detectable with the filler addition, while the PVDF-HFP diffraction peaks gradually vanish. It is important to note that the crystal-linity of the ceramic filler does not change; it just becomes more visible as the filler amount increases.

The PFM analysis was performed to evaluate the local piezoelectricity of prepared nanocomposites. PFM is a valuable technique for the determination of the local piezoelectric properties of composites and thick films.²⁹ It is based on measuring the ferroelectric material's local electromechanical response *via* the converse piezoelectric effect. On surface topography height and deflection images (Fig. 6a and b), the BTS₁₁ particles' filler grains can be clearly distinguished from the polymer matrix. Bright islands in the PFM amplitude image (Fig. 6c) demonstrate the BTS₁₁ particles' strong piezoelectric



Fig. 4 SEM micrographs of the (a) as-prepared BTS₁₁ nanopowder and (b) the PDA functionalized BTS₁₁ (BTS₁₁@PDA) with an inset showing the PDA layer on a BTS₁₁ particle, and (c) 20 wt%-BTS₁₁@PDA/PVDF-HFP nanocomposite.



Fig. 6 The AFM/PFM analysis of 20 wt%-BTS₁₁@PDA/PVDF-HFP nanocomposites. (a) The AFM topography height, (b) deflection images, (c) PFM out-of-plane amplitude, and (d) phase images. The PFM amplitude (e and g) and phase hysteresis loops (f and h), measured at the spots marked in panel (c) by numbers 1 and 2. Three hysteresis cycles were measured, only the second cycle is shown here.



Fig. 7 Frequency-dependent (a) dielectric permittivity and (b) dielectric loss of the BTS₁₁@PDA/PVDF-HFP nanocomposites with different filler content. Thermal evolution of the (c) dielectric permittivity and (d) dielectric loss with different filler content at 1 kHz.

8

activity, which is also evident from the contrast in the PFM phase image (Fig. 6d). The local PFM phase and amplitude hysteresis in two distinct areas were also tested using a PFM switching spectroscopic experiment (Fig. 6e–h). The typical ferroelectric/piezoelectric PFM phase hysteresis loops were obtained in both areas. Furthermore, the butterfly-shaped PFM amplitude hysteresis loops demonstrate the clear piezoelectric aspect of BTS₁₁ filler.

The study aimed to benefit from the BTS_{11} filler's multiphase, in which the tetragonal, orthorhombic, rhombohedric, and cubic phases coexist at room temperature, as demonstrated in our previous works.^{10,24} At room temperature, multiphase coexistence usually leads to enhanced dielectric properties in the lead-free BTS_{11} ceramic.

Hence, the dielectric properties at room temperature of our nanocomposites were measured and depicted in Fig. 7. As shown in Fig. 7a, ε_r increased significantly as the BTS₁₁@PDA amount increased. At the same time, it was only slightly dependent on the frequency over the measured range (1 Hz–1 MHz). Notably, at 20 wt%, the dielectric permittivity of



Fig. 8 Dielectric permittivity and dielectric loss of the BTS₁₁@PDA/ PVDF-HFP composites as a function of filler percentage at 1 kHz.

nanocomposites reaches 54 at 1 Hz, 46 at 1 kHz, and 42 at 100 kHz, which is about 5 times the dielectric permittivity of the pure PVDF-HFP. As shown in Fig. 7b, the value of tan δ decreased with increasing frequency over the range of 1 Hz–1 kHz owing to the relaxation loss caused by Maxwell–Wagner–Sillars (MWS) interfacial polarization.^{41,42} The dielectric loss between 10³ and 10⁵ Hz remains at a low level of less than 0.015. Above 10⁵ Hz, tan δ sharply increases, which is attributed to α relaxation associated with the glass transition of the pure PVDF polymer.^{43,44} It should be noted that in the frequency range of 1–10 (ref. 5) Hz, the tan δ value of the 20 wt%-BTS₁₁@PDA/PVDF-HFP composite was the lowest among all prepared composites. A similar shape of the measured curves of tan δ *versus* frequency was previously observed in literature for other ceramic/polymer nanocomposites.^{38,45}

The thermal evolution of the dielectric permittivity and the dielectric loss of the BTS₁₁@PDA/PVDF-HFP nanocomposites is depicted in Fig. 7c and d, respectively. The dielectric permittivity is remarkably improved by the filler addition. It is observed that the dielectric permittivity reaches a maximum value of 64 at 54 °C at 20 wt% of the BTS₁₁@PDA while at 45 °C, it attains maximum values of 48, 32 and 26 at 14 wt%, 8 wt%, and 2%, respectively. This aspect may be attributed to the β process, characteristic of the PVDF-HFP polymer.²⁵ On the other hand, as the temperature reaches 60 °C, the tan δ starts increasing with the temperature increase. This arises from the relaxation process associated with the crystalline phase defects. Indeed, inserting BTS₁₁@PDA may produce more crystalline phase defects and impact the relaxation process, resulting in a high dielectric loss at high temperatures.^{18,46}

The dielectric permittivity and the dielectric loss in function of the weight fraction of the filler are presented in Fig. 8. The dielectric permittivity remarkably and gradually increases with the increase of the filler content. This is due to the modifier acting as a passivation layer, improving the interfacial polarization while enhancing the filler's dispersion. Meanwhile, the dielectric loss increases slightly when the filler is incorporated into the polymer matrix, starting from 0.010 at 0 wt% to 0.017 at



Fig. 9 The dielectric permittivity (a) and the dielectric loss (b) of 20 wt%-BTS₁₁@PDA/PVDF-HFP and 20 wt%BTS₁₁/PVDF-HFP.

14 wt%, but interestingly is almost independent of the filler content, indicating a minimized agglomeration of the filler in the composites as seen in Fig. $4c.^{47}$

Fig. 9 illustrates the comparison between the dielectric permittivity (ε') and the dielectric loss (tan δ) of two different composites: one containing unmodified 20 wt% of BTS₁₁ nanoparticles dispersed in a PVDF-HFP matrix, and the other composite consisting of modified 20 wt% of BTS₁₁@PDA nanoparticles embedded in the same PVDF-HFP matrix. Dopamine is used to modify BTS₁₁ particles surface. Dopamine's hydroxyl groups strongly interact with the fluorine atoms (-F) in P(VDF-HFP) to produce dipole–dipole interactions. Additionally, because the -F atoms are strongly electronegative, hydrogen bonds (-F…OH–) can easily be formed.⁴⁸ Therefore, the functionalized BTS₁₁ particles exhibit excellent dispersion and compatibility in the PVDF-HFP polymer matrix.



Fig. 10 Comparison of the dielectric permittivity at 1 kHz and different fillers loading between different ceramic/polymer-based nanocomposites.

Thus, by comparing the dielectric properties of the two composites, the Fig. 9 highlights the impact of PDA coating on the BTS11 nanoparticles. The presence of polydopamine coating on the BTS₁₁ particles is expected to influence the interfacial interactions between the ceramic and the polymer phases (Fig. 9).

The composite with 20 wt%-BTS11@PDA exhibits improved dielectric permittivity and reduced dielectric loss compared to the composite containing the bare BTS₁₁. This enhancement in dielectric performance can be attributed to the enhanced interfacial compatibility achieved through the PDA modification.⁴⁹

The literature review on the dielectric permittivity of various ceramic/polymer-based nanocomposites is summarized in Fig. 10. Using surface hydroxylated cube-shaped Ba_{0.6}Sr_{0.4}TiO₃ nanoparticles (BST-NPs) as fillers and PVDF as the matrix, S. Liu et al. reported ceramic-polymer nanocomposites that achieved a dielectric permittivity of just 10 at 20 wt% of Ba_{0.6}Sr_{0.4}TiO₃.⁵⁰ They later employed Ba_{0.6}Sr_{0.4}TiO₃ nanofibers as fillers with a PVDF matrix to improve the properties of the nanocomposites. However, they only achieved a dielectric permittivity of 12 at 20 wt% of Ba0.6Sr0.4TiO3 and 1 kHz.41 Furthermore, Wang et al. also used PVDF-HFP as a polymer matrix with Ba_{0.7}Sr_{0.3}TiO₃ nanowires as the ceramic filler and were able to achieve a dielectric permittivity of 20 at 35 wt% of the filler at1 kHz.42 Bi et al. fabricated a three-dimensional BaTiO₃ (3D BT)/polyvinylidene fluoride (PVDF) composite dielectrics by inversely introducing PVDF solution into a continuous 3D BT network and reached a dielectric permittivity of 25 at 21.1 wt% of the filler at 100 Hz.⁵¹ Du et al. also demonstrated that BaTiO3-PtBA/PVDF nanocomposites can achieve a dielectric permittivity of 14 at 30 wt% of fillers loading at 1 kHz.52 Zhang et al. added significant ceramic filler loading to a PVDF polymer matrix. They employed grafted polymethyl methacrylate (PMMA) in amounts of 5.5% and 8% at BaTiO₃, denoted as BT@PMMA1 and BT@PMMA2, respectively. The 80 wt%-BT@PMMA1/PVDF and 60 wt%-BT@PMMA2/PVDF nanocomposites attained a dielectric permittivity of 29 and



Fig. 11 (a) P–E hysteresis loop of the BTS₁₁@PDA/PVDF-HFP nanocomposites with different filler content, and (b) the evolution of the energy storage properties with the filler content.

()

15, respectively.⁵³ Last but not least, BT@PTFEA/P(VDF-HFP), a PVDF-HFP nanocomposites with core–shell structured fluoropolymer@BT nanoparticles was reported to reach a dielectric permittivity of 42 at 50 wt% of fillers loading.⁵⁴ It is noteworthy that our BTS₁₁@PDA/PVDF-HFP nanocomposite which has never been reported in the literature, exhibits the highest dielectric permittivity at low filler content.

The room-temperature energy storage properties were calculated using the P-E hysteresis loop of the nanocomposites with different wt% of BTS₁₁@PDA fillers (see Fig. 11). The slim aspect of these P-E hysteresis loops is quite remarkable and rarely observed in the ceramic/polymer nanocomposites. For example, at a nanofiller concentration of 20 wt%, the total energy density at 450 kV cmis⁻¹ 192 mJ cm⁻³ is four times more than that of pure PVDF-HFP. The recovered energy for this composition is 134 mJ cm^{-3} with an efficiency of 72%. Meanwhile, the total energy and recovered energy density of the nanocomposite with 14 wt% BTS₁₁@PDA are 157 mJ cm⁻³ and 133 mJ cm⁻³, respectively, reaching an efficiency of 85%. We note that the nanocomposites efficiency is almost independent of filler content until 14 wt% of BTS₁₁@PDA. Beyond this value, it slowly decreases to 72% at 20 wt% of the modified ceramic. The evolution of the W_{tot} , W_{rec} , W_{loss} , and η with the filler weight percentage is depicted in Fig. 10b.

4. Conclusion

A simple solution casting method is successfully used to synthesize nanocomposites with PDA-modified BTS₁₁ as filler and PVDF-HFP as a polymer matrix. The enhanced dielectric permittivity and low-loss tangents are achieved in the nanocomposites with relatively low weight fractions of surface functionalized BTS₁₁. BTS₁₁@PDA/PVDF-HFP nanocomposites with 20 wt% concentration exhibited the highest dielectric permittivity of 46 with low tan $\delta \sim 0.017$ (at 1 kHz), which is the highest value reported so far and is 5 times higher than the pure PVDF-HFP. SEM results show that BTS11@PDA are dispersed homogeneously in the PVDF-HFP polymer matrix. Highly piezoactive regions identified by PFM scanning the composite surface are attributed to the BTS₁₁ nanoparticles. Moreover, the P-E hysteresis loops are ultrafine, resulting in good energy storage properties. At a nanofiller content of 20 wt%, the total energy density is four times higher than that of pure PVDF-HFP with an efficiency of 73%. The findings show that the energy storage density of nanocomposites can be enhanced by adding a small amount of surface-modified ceramic nanoparticles.

Conflicts of interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgements

The authors gratefully acknowledge the generous financial support of the European Union Horizon 2020 Research and

Innovation actions MSCA-RISE-ENGIMA (No. 778072) and MSCA-RISE- MELON (No. 872631). HU and MS acknowledge the Slovenian Research Agency grants (No. 2-0212, P2-0105) and thank Brigita Kmet and Val Fišinger for help in the laboratory. Z. K. acknowledges the Slovenian Research Agency grant P1-0125.

References

- 1 Prateek, V. K. Thakur and R. K. Gupta, *Chem. Rev.*, 2016, **116**, 4260–4317.
- 2 Z.-X. Xu, V. A. L. Roy, P. Stallinga, M. Muccini, S. Toffanin and H.-F. Xiang, *Appl. Phys. Lett.*, 2007, **90**(22), 223509.
- 3 S. Kumar, S. Supriya and M. Kar, *Compos. Sci. Technol.*, 2018, 157, 48–56.
- 4 Y. N. Hao, K. Bi, S. O'Brien, X. X. Wang, J. Lombardi, F. Pearsall, W. L. Li, M. Lei, Y. Wu and L. T. Li, *RSC Adv.*, 2017, 7, 32886–32892.
- 5 W. Zhou, G. Cao, M. Yuan, S. Zhong, Y. Wang, X. Liu, D. Cao,
 W. Peng, J. Liu, G. Wang, Z. Dang and B. Li, *Adv. Mater.*, 2023,
 35, 2207829.
- 6 S. K. Yang, Z. X. Zhang, A. P. Zhang, H. L. Lin, X. T. Zhang, L. X. Xiao, J. Bian and D. Q. Chen, *J. Appl. Polym. Sci.*, 2022, 139(48), e53231.
- 7 W. Li, R. Liang, C. Wu, L. Yang, F. Wang, Z. Liu, X. Chen, H. Mao and W. Zhang, *Adv. Mater. Interfaces*, 2022, 9, 2201257.
- 8 J. Fu, Y. Hou, M. Zheng, Q. Wei, M. Zhu and H. Yan, *ACS Appl. Mater. Interfaces*, 2015, 7, 24480–24491.
- 9 Z. Liang, C.-F. Yan, S. Rtimi and J. Bandara, *Appl. Catal.*, *B*, 2019, **241**, 256–269.
- M. Zahid, O. Kharraz, M. Amjoud, D. Mezzane, M. Gouné, K. Hoummada, I. Saadoune, S. Fourcade, P. Stocker, B. Rožič, Z. Kutnjak and M. El Marssi, *Mater. Today Proc.*, 2022, S2214785322046338.
- 11 P. T. Thuy Phuong, Y. Zhang, N. Gathercole, H. Khanbareh, N. P. Hoang Duy, X. Zhou, D. Zhang, K. Zhou, S. Dunn and C. Bowen, *iScience*, 2020, 23, 101095.
- 12 C. Wang, N. Tian, T. Ma, Y. Zhang and H. Huang, *Nano Energy*, 2020, **78**, 105371.
- 13 Z. Hanani, Nano Energy, 2021, 12.
- 14 S. Das, A. K. Biswal and A. Roy, *IOP Conf. Ser.: Mater. Sci. Eng.*, 2017, **178**, 012020.
- 15 C. Li, W. Luo, X. Liu, D. Xu and K. He, *Nanomaterials*, 2016, 6, 67.
- 16 M.-G. Kang, W.-S. Jung, C.-Y. Kang and S.-J. Yoon, *Actuators*, 2016, 5, 5.
- 17 R. Pramanik, Ceram. Int., 2019, 12, 5731-5742.
- 18 X. Hu, Y. Zhou, J. Liu and B. Chu, *J. Appl. Phys.*, 2018, **123**(15), 154101.
- C. E. Ciomaga, N. Horchidan, L. Padurariu, R. S. Stirbu,
 V. Tiron, F. M. Tufescu, I. Topala, O. Condurache,
 M. Botea, I. Pintilie, L. Pintilie, A. Rotaru, G. Caruntu and
 L. Mitoseriu, *Ceram. Int.*, 2022, S0272884222018429.
- 20 H. Bai, G. Ge, X. He, B. Shen, J. Zhai and H. Pan, *Compos. Sci. Technol.*, 2020, **195**, 108209.
- 21 B. K. Pandey, A. Kumar, K. P. Chandra, A. R. Kulkarni, S. K. Jayaswal and K. Prasad, *J. Adv. Dielectr.*, 2018, 08, 1850027.

- 22 G. A. Kaur, S. Kumar and M. Shandilya, J. Mater. Sci. Mater. Electron., 2020, **31**, 20303–20314.
- 23 S. P. P. Sadhu, S. Siddabattuni, S. Muthukumar and K. B. R. Varma, *J. Mater. Sci. Mater. Electron.*, 2018, 29, 6174–6182.
- 24 M. Zahid, Y. Hadouch, M. Amjoud, D. Mezzane, M. Gouné, K. Hoummada, A. Alimoussa, A. G. Razumnaya, B. Rožič and Z. Kutnjak, *J. Mater. Sci. Mater. Electron.*, 2022, 33, 12900–12911.
- 25 X. Lu, X. Zou, J. Shen, L. Jin, F. Yan, G. Zhao, L. Zhang and Z.-Y. Cheng, *Ceram. Int.*, 2019, **45**, 17758–17766.
- 26 A. Issa, M. Al-Maadeed, A. Luyt, D. Ponnamma and M. Hassan, *C*, 2017, **3**, 30.
- 27 Z. Li, F. Liu, G. Yang, H. Li, L. Dong, C. Xiong and Q. Wang, *Compos. Sci. Technol.*, 2018, **164**, 214–221.
- 28 W. Mei, J. Wei, Z. Ko, Z.-Y. Cheng and J. Hu, *Ceram. Int.*, 2021, 47, 15561–15567.
- 29 H. Uršič and U. Prah, Proc. R. Soc. A, 2019, 475, 20180782.
- 30 Q. Zhao, H. Xiao, G. Huangfu, Z. Zheng, J. Wang, F. Wang and Y. Guo, *Nano Energy*, 2021, 85, 106028.
- 31 J. Gao, Y. Wang, Y. Liu, X. Hu, X. Ke, L. Zhong, Y. He and X. Ren, *Sci. Rep.*, 2017, 7, 40916.
- 32 C.-C. Li, S.-J. Chang, J.-T. Lee and W.-S. Liao, *Colloids Surf., A*, 2010, **361**, 143–149.
- 33 R. Kota and B. I. Lee, *J. Mater. Sci. Mater. Electron.*, 2007, **18**, 1221–1227.
- 34 S. Dash, V. N. Thakur, A. Kumar, R. N. Mahaling, S. Patel, R. Thomas, B. Sahoo and D. K. Pradhan, *Ceram. Int.*, 2021, 47, 33563–33576.
- 35 T. Zhou, J.-W. Zha, R.-Y. Cui, B.-H. Fan, J.-K. Yuan and Z.-M. Dang, *ACS Appl. Mater. Interfaces*, 2011, 3, 2184–2188.
- 36 Y. Xie, Y. Yu, Y. Feng, W. Jiang and Z. Zhang, ACS Appl. Mater. Interfaces, 2017, 9, 2995–3005.
- 37 P. Hu, S. Gao, Y. Zhang, L. Zhang and C. Wang, *Compos. Sci. Technol.*, 2018, **156**, 109–116.

- 38 Y. Li, J. Yuan, J. Xue, F. Cai, F. Chen and Q. Fu, *Compos. Sci. Technol.*, 2015, **118**, 198–206.
- 39 H. Luo, J. Roscow, X. Zhou, S. Chen, X. Han, K. Zhou, D. Zhang and C. R. Bowen, *J. Mater. Chem. A*, 2017, 5, 7091–7102.
- 40 C. Wang, J. Zhang, S. Gong and K. Ren, *J. Appl. Phys.*, 2018, **124**, 154103.
- 41 S. Liu, S. Xiao, S. Xiu, B. Shen, J. Zhai and Z. An, *RSC Adv.*, 2015, 5, 40692–40699.
- 42 S. Wang, X. Huang, G. Wang, Y. Wang, J. He and P. Jiang, *J. Phys. Chem. C*, 2015, **119**, 25307–25318.
- 43 S. Liu, S. Xue, W. Zhang, J. Zhai and G. Chen, *J. Mater. Chem. A*, 2014, **2**, 18040–18046.
- 44 G. Chen, X. Wang, J. Lin, W. Yang, H. Li and Y. Wen, *J. Phys. Chem. C*, 2016, **120**, 28423–28431.
- 45 R. Tamura, E. Lim, T. Manaka and M. Iwamoto, *J. Appl. Phys.*, 2006, **100**, 114515.
- 46 K. Yu, H. Wang, Y. Zhou, Y. Bai and Y. Niu, *J. Appl. Phys.*, 2013, **113**, 034105.
- 47 L. Shaohui, Z. Jiwei, W. Jinwen, X. Shuangxi and Z. Wenqin, ACS Appl. Mater. Interfaces, 2014, 6, 1533–1540.
- 48 Y. Niu, Y. Bai, K. Yu, Y. Wang, F. Xiang and H. Wang, ACS Appl. Mater. Interfaces, 2015, 7, 24168–24176.
- 49 H. Hu, F. Zhang, S. Lim, P. Blanloeuil, Y. Yao, Y. Guo and C. H. Wang, *Composites, Part B*, 2019, **178**, 107459.
- 50 S. Liu, S. Xiu, B. Shen, J. Zhai and L. Kong, *Polymers*, 2016, **8**, 45.
- 51 X. Bi, L. Yang, Z. Wang, Y. Zhan, S. Wang, C. Zhang, Y. Li, Y. Miao and J. Zha, *Materials*, 2021, 14, 3585.
- 52 X. Du, Y. Liu, J. Wang, H. Niu, Z. Yuan, S. Zhao, X. Zhang, R. Cao, Y. Yin, N. Li, C. Zhang, Y. Xing, W. Xu and C. Li, *ACS Appl. Mater. Interfaces*, 2018, **10**, 25683–25688.
- 53 X. Zhang, S. Zhao, F. Wang, Y. Ma, L. Wang, D. Chen, C. Zhao and W. Yang, *Appl. Surf. Sci.*, 2017, **403**, 71–79.
- 54 K. Yang, X. Huang, Y. Huang, L. Xie and P. Jiang, Chem. Mater., 2013, 25, 2327–2338.