RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2023, 13, 26744

Received 5th July 2023 Accepted 17th August 2023 DOI: 10.1039/d3ra04478e

rsc.li/rsc-advances

1. Introduction

The last few eras have seen rapid growth in several areas, such as industrialization and globalization. As a result, energy demands have increased exceptionally. In parallel, the human population has also grown, which accounts for much of the increase in energy consumption. Traditionally, fuels were used as energy sources, but fuel depletion led researchers to move toward electrochemical energy to replace them.^{1,2} The two primary energy power sources used for this were batteries and supercapacitors. Since supercapacitors can deliver higher power densities and longer cycle life than batteries with fast charge and discharge, they have gained significant attention.^{3,4} Supercapacitors were used in electronic devices, such as trains and buses, automobiles, cranes, and elevators.⁵ Double-layer capacitors (EDLC) and pseudocapacitors (PC) fall under the supercapacitor taxonomy. The electric doubler layer capacitor's energy storage and release mechanism rests entirely on the theory of charge separation at the electrode-electrolyte interface.6 As opposed to batteries, herein, there are no chemical oxidation-reduction reactions; thus, the nonfaradic nature of

High-performance hybrid supercapacitorimmobilized Wells–Dawson polyoxometalates on activated carbon electrodes⁺

Madhusree J E,^a Pranay R. Chandewar,^b Debaprasad Shee ^b and Sib Sankar Mal ^b*^a

The nanofabrication of electroactive hybrid materials for next-generation energy storage devices is becoming increasingly significant as supercapacitor (SC) technology develops rapidly. The present study utilizes activated carbon (AC) templates reinforced with Wells–Dawson polyoxotungstates (POMs) to produce nanohybrid electrodes for high-performance supercapacitors. This study analyzes Wells–Dawson polyoxotungstates (P_2W_{18}) for the first time integrated with AC, and its structural and electrochemical performances are discussed. First, the electrochemical performances of symmetric supercapacitors were characterized in an acidic aqueous electrolyte (0.5 M H₂SO₄). It was observed that a supercapacitor cell containing the 5 wt% AC-P₂W₁₈ hybrid symmetric displayed a noteworthy specific capacitance of 289 F g⁻¹ and a remarkable energy density of 40 W h kg⁻¹. Moreover, 5% AC-P₂W₁₈ symmetric supercapacitor cells showed 89% cyclic stability over 4000 cycles. Three LED lights were charged onto the electrode. The LEDs continued to illuminate continuously for red until 160 seconds, yellow until 20 seconds, and blue until 10 seconds after removing the electrode from the electrochemical workstation, demonstrating the device's power and energy density.

this physical charge transfer results in long cycling life.^{7,8} In EDLC, graphene-based,⁹⁻¹¹ activated carbon,¹²⁻¹⁴ and carbon nanotube-based materials15,16 are typically used in the case of pseudocapacitors involved in the oxidation/reduction process. As a result, faradaic redox reactions have higher energy density.^{17,18} The materials used here include transition metal oxides,^{19,20} conducting polymers,^{21,22} metal sulfides,²³ and polyoxometalates.24,25 The most usually used electrode material in commercial supercapacitors is activated carbon (AC) owing to its high surface area, low cost, high electrical conductivity, excellent corrosion resistance, high thermal stability, tuned pore structure, easy processability, and compatibility with other composite materials.26 However, because of its nonfaradic nature, the specific capacitance remains small. As a result, researchers began investigating new electrodes based on hybrid materials, the combination of an electric double layer, and a pseudocapacitor. It can boost the energy and power density while maintaining mechanical strength and the cell's long lifespan.

In this respect, inorganic metal-oxygen cluster polyoxometalates (POMs) have emerged as promising pseudocapacitive materials with diverse properties.²⁷ The most unique property of POMs is that it can absorb and release electrons without changing its structural characteristics, which makes it an admirable supercapacitor electrode material. POMs comprise a multimetal oxide of early transition elements that can be altered in shape, size, and composition. It is nontoxic and nonvolatile, has a large molecular size, and relatively high

^aMaterials and Catalysis Laboratory, Department of Chemistry, National Institute of Technology Karnataka, Surathkal 575025, India. E-mail: malss@nitk.edu.in

^bDepartment of Chemical Engineering, Indian Institute of Technology Hyderabad, Kandi, Sangareddy 502284, Telangana, India

[†] Electronic supplementary information (ESI) available. See DOI: https://doi.org/10.1039/d3ra04478e

Paper

View Article Online **RSC** Advances

molecular weight. Different types of POMs, such as Keggin,²⁸ Dawson,²⁹ Lindquist,³⁰ Waugh,³¹ Silverton,³² and Anderson,³³ and their multidirection applications are reported. POMs have been used in various applications, including sensors, catalysis, medicine, and energy storage. Among these, Keggin and Dawson types of POMs have been extensively investigated because of their thermal and redox stability and can engage reversible multielectron transfer reactions.34 This electron transfer metaloxide cluster type suits electrochemical capacitors (EC). However, poor conductivity, low surface areas, and high solubility in an aqueous solvent prevent the direct application of POMs as an electrode material.³⁵ To decrease the solubility, POMs are often deposited on a high surface area carbonaceous support to yield a nanocomposite for EC electrodes. Carbonaceous materials such as graphene,³⁶ graphene oxide,⁹ singlewalled carbon nanotubes (SWCNT),37,38 and multiwalled carbon nanotubes^{39,40} have been studied mainly as a support for the POM composite electrodes. Keggin POM clusters were mainly immobilized on the carbonaceous materials and investigated extensively in EC, resulting in reduced solubility and enhanced capacitance over soluble POMs. The following Table 1 summarizes the results of a comprehensive literature survey. As a result, different polyoxometalates doped with AC were described and used as supercapacitor electrodes. In 2012, Ruiz V. et al. successfully anchored molybdenum-containing Keggin POM [H₃PMo₁₂O₄₀] (PMo₁₂) onto the AC, and their electrochemical study was conducted in 1 M H₂SO₄, resulting in a specific capacitance value of 160 F g^{-1} at 2 A g^{-1} in a threeelectrode system.41 In 2014, the same group developed an extensive method for impregnating $[H_3PW_{12}O_{40}]$ (PW₁₂) on AC. A combination of double layer and redox activity was discovered to increase the specific capacitance by 254 F g^{-1} at 10 mV $s^{-1.42}$ Hu C. et al. are interested in further exploring the same material PMo12-AC in an ionic liquid electrolyte (1 M [Bmim]HSO4), which attained a specific capacitance of 223 F g^{-1} at 1 mV s^{-1} .⁴³ In a follow-up study by Genovese et al., activated carbon from pinecone biomass was synthesized, and PMo12 was deposited onto the pinecone-derived AC surface. This resulted in a specific capacitance of 361 F g^{-1} at 10 mV s^{-1} .⁴⁴

Maity S. et al. fabricated a symmetric cell using vanadopolymolybdates at the AC surface and achieved a capacitance of 430 F g^{-1} at 0.2 A g^{-1} in 0.25 M H₂SO₄ in a 2-electrode system.⁴⁵ Next, Vannathan A. A. et al. developed manganopolyvandate

into an AC matrix, and the electrochemical performance was measured on a symmetric device in 0.1 M H₂SO₄ electrolyte. The specific capacitance was observed at 479.7 F g^{-1} at 0.4 A g^{-1} .⁴⁶ The research has so far focused on Keggin-based polyoxometalates ranging from homopolyanions to heteropolyanions. In addition, Maity S. et al. synthesized Lindqvist polyoxometalate (NiV14) doped on AC surfaces and performed an electrochemical study in 0.5 M H₂SO₄, which showed a capacitance of 365 F g^{-1} at 0.2 A g^{-1} in a symmetric cell.²⁷

In this respect, Wells-Dawson-type POMs have been overlooked, which may be due to the larger size and higher charges than Keggin ions. In 2015, Mu A. et al. synthesized the first Dawson-based composite of octadecamolybdodiphosphate ((NH₄)₆[P₂Mo₁₈O₆₂]·14.2H₂O) doped on an activated carbon surface and investigated its electrochemical performance. It showed a specific capacitance of 275 F g^{-1} at a 6 A g^{-1} current density in a three-electrode system.⁴⁷ Till today, there is no supercapacitor work reported using Wells-Dawson POM. Hence, it was interesting to investigate Well-Dawson-type POMs for supercapacitor applications. Herein, we explored activated carbon (AC)-supported K₆[P₂W₁₈O₆₂]. xH₂O (P₂W₁₈)based electrode for the electrochemical supercapacitor in a twoelectrode system. In this paper, we doped P₂W₁₈ onto the AC matrix in different concentrations (5 wt%, 10 wt%, and 15 wt%) to examine the maximum amount of P2W18 on AC porous surface, which can enhance its capacitive nature. A symmetric SC cell composed of 5 wt% AC-P2W18, 10 wt% AC-P2W18, and 15 wt% AC-P₂W₁₈ was synthesized, and its electrochemical performance was evaluated using a two-electrode system in 0.5 M H₂SO₄ electrolyte. It has been observed that 5 wt% AC- P_2W_{18} exhibited an excellent specific capacitance of 289 F g⁻¹ at 0.2 A g^{-1} with good energy and power density of 40 W h kg⁻¹ and 1999 W kg⁻¹.

Results and discussion 2.

2.1 FTIR

FTIR spectra were recorded on a Bruker 4000 spectrometer (USA) to determine the chemical structure of the materials. Fig. 1 represents the FTIR spectra of composites with different weight percentages and pure P2W18. The characteristic chemical bands in all the three composite materials and pure P2W18 correlated well with those reported in the literature.48 The bands

Table 1 An overview of the electrodes based on polyoxometalate-activated carbon								
Electrode	Electrolyte	Current density/scan rate	Cell configuration	Specific capacitance	Ref.			
AC-PMo ₁₂	1 M H ₂ SO ₄	2 Ag^{-1}	3-Electrode	$160 { m F g}^{-1}$	41			
AC-PW ₁₂	1 M H ₂ SO ₄	10 mV s^{-1}	3-Electrode	254 Fg^{-1}	42			
AC-PMo ₁₂	1 M [Bmim]HSO ₄	1 mV s^{-1}	3-Electrode	223 Fg^{-1}	43			
Pinecone carbon-PMo ₁₂	$1 \text{ M H}_2 \text{SO}_4$	10 mV s^{-1}	3-Electrode	361 Fg^{-1}	44			
AC-VMo ₁₁	0.25 M H ₂ SO ₄	0.2 A g^{-1}	2-Electrode	430 F g^{-1}	45			
AC-MnV ₁₁	0.1 M H ₂ SO ₄	$0.4 \mathrm{Ag}^{-1}$	2-Electrode	479.73 F g^{-1}	46			
AC-NiV ₁₄	0.5 M H ₂ SO ₄	0.2 Ag^{-1}	2-Electrode	365 F g^{-1}	27			
AC-P ₂ Mo ₁₈	1 M H ₂ SO ₄	6 A g^{-1}	3-Electrode	275 Fg^{-1}	47			
AC-P ₂ W ₁	0.5 M H ₂ SO ₄	$0.2 \stackrel{\sim}{\mathrm{A}} \mathrm{g}^{-1}$	2-Electrode	288.48 F g^{-1}	This work			



Fig. 1 FTIR spectra of pure P_2W_{18} , 5%, 10%, and 15% of AC- P_2W_{18} .

at 1108, 824, 934, and 996 cm⁻¹ of P_2W_{18} are induced by vibrations of the P–O, W–Oe–W, W–Oc–W, and terminal W=O bonds (Table S1†). C=C stretching causes intensity bands at 1600 and 1700 cm⁻¹, while the broad peak at 3500–3650 cm⁻¹ is due to the –OH groups.⁴⁹

2.2 XRD

The powder XRD patterns of AC-P₂W₁₈ composites of different weight percentages are shown in Fig. 2. AC exhibits a broad pattern, indicating amorphous nature. The broad peaks observed at about 24° and 43.8° are due to graphitic carbon (0 0 2) and (1 0 0), respectively. The crystalline nature of P₂W₁₈ has been confirmed from the literature (Fig. 2)⁴⁸ and JCPDS (card no: 01-073-6183). AC-P₂W₁₈ exhibits amorphous and crystalline characteristics as a result of P₂W₁₈ being incorporated in AC. The sharp peaks at about 20.35°, 24.13°, 25.85°, and 26.63° are



Fig. 2 XRD patterns of pure P_2W_{18} , 5%, 10%, and 15% of AC- P_2W_{18} .

due to P_2W_{18} . Pure P_2W_{18} shows more intense peaks due to its well crystalline nature (Fig. 2). Conversely, in AC- P_2W_{18} , only a few intense peaks of P_2W_{18} are visible because the carbon content is more in the nanohybrid than P_2W_{18} and exhibits both amorphous and crystalline nature. The diffractions planes (0 0 2), (1 0 0), and (2 0 0) correspond to 2θ of 24, 43.8, and 20.35, respectively, for AC and P_2W_{18} .

2.3 XPS

X-ray photoelectron spectroscopy (XPS, Thermofisher scientific: Nexsa G2base) was used to probe the electronic states of the nanohybrids. Fig. 3 displays the high-resolution XPS spectra of 5% AC-P₂W₁₈. The survey spectrum shows the peaks of the elements found as C 1s, O 1s, W 4f, and P 2p for 5% AC-P₂W₁₈ in Fig. S1.[†] A single strong peak of C 1s measured at 285.3 eV, as shown in Fig. 3a, is consistent with the literature.45 A Gaussian function centered at 531.2 eV, 532.1 eV, and 533.6 eV due to W= O, O-W-O, and O-H, respectively, are satisfactorily fitted to the O 1s spectrum (Fig. 3b) of Well-Dawson polyoxometalate, which differs from the fit of Keggin polyoxometalate. A similar pattern applies to W, which is in the highest oxidation state of +6 (Fig. 3c), with peaks at 35.68, 37.5, and 42.71 eV, which correspond to 4f7/2, 4f5/2, and 5p3/2, respectively.50 Finally, a Wells-Dawson anion in P_2W_{18} is attributed to the deconvoluted P $2p_{3/2}$ at 134.2 eV in Fig. 3d.

2.4 BET characterization

During electrochemical charge storage, electrode materials have an essential role in porosity and surface area. To characterize the AC and 5% AC-P2W18 nanohybrids, N2 adsorption/ desorption isotherms data were collected using the Micromeritics physisorption analyzer (Model ASAP 2020, USA). The AC possesses the highest surface area of 1340 $m^2 g^{-1}$ with the highest pore volume of 0.37 cm³ g⁻¹ (Table 2). A surface area of 1298 m² g⁻¹ and a pore volume of 0.25 cm³ g⁻¹ was observed for 5% AC-P₂W₁₈, which clarifies that P_2W_{18} is deposited on AC surfaces. The AC-P2W18 composite exhibited type-IV adsorption-desorption isotherms (Fig. 4a) with ill-defined hysteresis loops, suggesting the absence or less fraction of mesopores. The steep rise in volume adsorbed at low relative pressure indicates the presence of micropores. According to Fig. 4b, AC-P₂W₁₈ exhibits a pore size distribution peak at a higher pore diameter, indicating the presence of macropores. As a result, most micropores and some mesopores are covered by P2W18 on the AC surface.

2.5 FESEM

The surface morphology of the nanocomposites was measured by FESEM (FESEM, Carl Zeiss Sigma, Germany). Fig. 5a and b show the FESEM images of pure P_2W_{18} and 5% AC- P_2W_{18} nanocomposites. It is clear from Fig. 5a that the pure P_2W_{18} has a rock-like structure. The morphological study of pure AC has already been published in the literature by our group.⁴⁶ An analysis of the surface morphology of 5% AC- P_2W_{18} composite indicates that pure polyanions are inserted into the micropores of AC surfaces. Energy-dispersive spectroscopy (EDS) analysis



(cc) BY



Table 2 Surface area and porosity of the $AC-P_2W_{18}$ nanohybrid and AC

Sample	BET surface area $(m^2 g^{-1})$	Micropore area $(m^2 g^{-1})$	Micropore volume $(cm^3 g^{-1})$	Mesopore width (Å)	Average nanoparticle size (Å)
AC	1339.8801	717.4	0.37	33.32	44.78
AC-P ₂ W ₁₈	1297.9905	487	0.25	34.36	46.22

was also carried out to identify the elements present in the composites. Fig. S2a⁺ shows the confirmed elemental compositions of pure P_2W_{18} of K, O, P, and W. The elemental

compositions of the composites (K, P, O, W, and C) are also confirmed by EDS results (Fig. S2b†). In addition, HRTEM was evaluated to determine the microstructure of nanohybrids. As



Fig. 4 (a) N₂ adsorption and desorption isotherms of AC and AC-P₂W₁₈, (b) pore size distribution of AC and AC-P₂W₁₈.





Fig. 5 (a) FESEM image of pure P_2W_{18} , (b) 5% AC- P_2W_{18} .

illustrated in Fig. S3a and b,† the well-decorated polyanions of P2W18 in the AC micropores can be seen in the micrograph of 5% AC-P2W18.

2.5.1 Cyclic voltammetry. A two-electrode system of cyclic voltammetry (CV) method was utilized to explore the electrochemical properties of the power cell. An experiment using cyclic voltammetry (CV) measurements was done to study the electrode material's chemical kinetics, degradation process, and specific capacitance.⁴⁶ The electrodes were tested in a cyclic (IVIUM Technologies BV Co., The Netherlands, Model: Vertex) setup using 5% AC-P₂W₁₈, 10% AC-P₂W₁₈, and 15% AC-P₂W₁₈ composite materials in the potential window of 0–1 V using 0.5 M electrolyte solution at various scan rates. A CV graph measuring 5% AC-P₂W₁₈, 10% AC-P₂W₁₈, and 15% AC-P₂W₁₈ has been presented in Fig. 6a–c at different scan rates of 30, 50, 70, and 100 mV s⁻¹. CV analysis indicates that AC-P₂W₁₈ oxidation-reduction peaks of 5% and 10% indicate that is P₂W₁₈ present over AC surfaces. It is noticeable that 15% AC-P₂W₁₈



Fig. 6 Cyclic voltammetry graphs (a) 5% AC-P₂W₁₈, (b) 10% AC-P₂W₁₈, (c) 15% AC-P₂W₁₈, and (d) comparison graph of all three symmetric SC cells.

shows a deformed curve compared to the other two, 5% AC- P_2W_{18} and 10% AC- P_2W_{18} . To better understand the pseudo material's exact oxidation-reduction behavior, the bare P_2W_{18} electrode was also used to perform CV (Fig. S4†) in the same electrolyte at the same scan rate as the pseudomaterial. This indicates that the AC- P_2W_{18} composite has an excellent capacitive response. An electrode's capacitance can be assessed using CV as can the shape of the cathodic and anodic peaks and the current density area (Fig. 6d). To evaluate the specific capacitance of nanohybrids, the CV plots were analyzed using eqn (1).

Specific capacitance(Cs): Cs =
$$\frac{1}{2m \times v \times \Delta V} \int I(V) dV$$
 (1)

where m, v, and ΔV are the active material's mass, scan rate, and potential window, respectively. The specific capacitance increases when P_2W_{18} is impregnated on AC surfaces (Tables S2–S4[†]).

2.5.2 Galvanostatic charge and discharge. Galvanostatic charge–discharge (GCD) at several current densities was examined to understand the electrochemical performance of the AC-

Paper



Fig. 7 GCD graphs of (a) 5% AC-P₂W₁₈, (b) 10% AC-P₂W₁₈, and (c) 15% AC-P₂W₁₈, (d) specific capacitance vs. current density for 5%, 10%, and 15% of AC-P₂W₁₈, (e) Ragone plot for all three nanohybrids and (f) comparison graph for all three symmetric SC cells.

P2W18 composite electrode materials under a defined potential window.48 In a galvanostatic charge and discharge study, three symmetric SC cells were examined with current densities in the range from 0.2 to 5 A g^{-1} in the potential window of 0–1 V. The charge-discharge outline was reshaped by immobilizing POMs onto the AC surface, which differs from the EDLC behavior. The improper linear GCD curve was observed across lower current densities.⁴⁶ At 0.2 A g^{-1} current density (Fig. 7a), the 5% AC- P_2W_{18} electrode exhibited a specific capacitance of 289 F g⁻¹ with an energy density of 40 W h kg⁻¹. The GCD graphs of 5% AC-P₂W₁₈ has showed the redox reaction while charging and discharging. To achieve higher energy density, the device's power must be compromised.44 In contrast to 10% and 15% of AC-P2W18, 5% AC-P2W18 consistently shows high power and energy densities (Fig. 7e) in the current density range from 0.2 to 5 A g^{-1} . The specific capacitances of 5% AC-P₂W₁₈ with its energy and power densities are tabulated in Table S5[†]. Using eqn (2)-(4), we calculated the composite material's specific capacitance, energy, and power density. Meanwhile, the GCD response of 10% AC-P2W18 and 15% AC-P2W18 were recorded, which shows the specific capacitance value of 199 F g^{-1} and 139 Fg^{-1} at 0.2 A g^{-1} current density with specific power and energy density values of 28 W h $\rm kg^{-1},$ 1999 W $\rm kg^{-1}$ and 19W h $\rm kg^{-1},$ 1999 W kg⁻¹, respectively. The GCD graph response of 10% AC- P_2W_{18} and 15% AC- P_2W_{18} are displayed in Fig. 7b and c. The

specific capacitance with their energy and power densities of 10% AC-P2W18 and 15% AC-P2W18 are tabulated in Tables S6 and S7[†]. Based on the GCD results on three different symmetric SC cells with the same current density, it is concluded that the 5% AC-P₂W₁₈-based electrode had a longer discharge time than the other two electrodes containing 10% AC-P2W18 and 15% AC-P₂W₁₈, resulting in a higher capacitance value for the former electrode. As a result, surface charge diffusion will be increased, leading to greater capacitance and energy density. In Fig. 7d, specific capacitance versus current and power versus energy density are plotted (Fig. 7e). It is observed that 5% AC-P₂W₁₈ gives high specific capacitance, high energy, and power densities compared to the other two, which explains that 5% AC-P₂W₁₈ is physisorbed more onto the AC surface. Fig. 7f illustrates that the 5% AC-P2W18 shows 18% higher capacitance than 10% AC-P₂W₁₈ and 45.5% higher than 15% AC-P₂W₁₈.

Specific capacitance (Cs /g)Cs =
$$i \times \Delta \frac{t}{m} \times (\Delta V)V$$

Specific capacitance Cs = $I \times \Delta t / \Delta F g^{-1}$ } (2)

Energy density (E.D)
$$E = i \int V dt W h kg^{-1}$$
 (3)

Power density(PD)
$$P = \frac{E}{\Delta t(s)} \times 3600 \text{ W kg}^{-1}$$
 (4)



Fig. 8 (a) Nyquist plot and cyclic stability of (b) 5% AC-P₂W₁₈, (c) 10% AC-P₂W₁₈, and (d) 15% AC-P₂W₁₈.

Paper

View Article Online **RSC** Advances

2.5.3 Electrochemical impedance spectroscopy. Power-cell impedance was measured using a low-amplitude dc potential with electrochemical impedance spectroscopy (EIS). All three different concentrations of P2W18 were deposited on AC and AC-P₂W₁₈ nanocomposites, and electrochemical impedance spectroscopy measurements were carried out using a dc potential of 0.01 V in the frequency range from 1 Hz to 100 kHz. Nyquist plots can be used to assess the internal resistance of the composites as well as their charge transfer kinetics and ion diffusion processes.⁵¹ The impedance spectroscopy results for the high-frequency region show the electrodes to be arranged in a semicircular arc. Low-frequency measurements of electrodeelectrolyte impedance provide a visual representation of electron transfer kinetics of redox reactions due to limited mass transport.52,53 A partial semicircle was observed when the frequency increased, indicating the charge transfer resistance. As shown in Table S8,† all three different concentrations of AC-P₂W₁₈ nanohybrids exhibit equivalent series and charge transfer resistance. In the higher frequency regime, the RCT value is calculated from the diameter of the semicircle in the Nyquist plot (Fig. 8a). The R_{CT} value of 5% AC-P₂W₁₈ is lower at 3.35 (Fig. 8a) [Table S8[†]] than the other two, indicating that the smaller the electrode diameter, the greater the charge stored.44 Consequently, the 5% AC-P₂W₁₈ electrode has the highest conductivity and kinetics of charging compared to the other two electrodes.

2.5.4 Cycle stability. To determine a supercapacitor device's application, it is essential to consider the cell's stability. Cycle stability has been tested on three symmetric electrodes composed of 5% AC-P₂W₁₈, 10% AC-P₂W₁₈, and 15% AC-P₂W₁₈ (Fig. 8b–d). As a result, in 4000 cycles at 7 A g^{-1} for a symmetrical electrochemical system with 5% AC-P2W18 electrode material (Fig. 8b), the electrochemical capacitors exhibited outstanding cycle stability of 89%, demonstrating that subsequent cycles do not affect long-term electrochemical capacitors but are similar to their initial cycle in terms of the cycle stability. The composite's first and last four cycles of cycle stability are exhibited in Fig. S5.† Based on the fabrication method described above, 5% AC-P2W18 was coated on four pairs of

Fig. 9 LED images of blue light using 5% AC-P₂W₁₈ as the electrode material.

carbon clothes of 4 cm \times 4 cm dimension (149 mg of active electrode material coated) were connected in a series. In the potential window of 0-3 V (Fig. 9, S6a and b†), the electrode was charged with three LEDs (red, yellow, and blue) at a high current density of about 20 A g^{-1} in an electrochemical workstation and lit up. After disconnecting the electrochemical workstation, the LED kept glowing continuously for the red one until 160 s, for vellow until 20 s, and for blue until 10 s after removing it (Video S1a-c[†]), proving the device's high energy and power density.

3. Materials and methodology

Activated carbon, N-methyl pyrrolidone (NMP), and sodium tungstate (Na₂WO₄) were purchased from Sigma-Aldrich. Orthophosphoric (85%), NH₄Cl, KCl, distilled water, HPLC grade water, and methanol were all obtained from Loba Chemie. PVDF was purchased from Alfa Aesar. In this study, all analytical grade reagents were used without further purification.

3.1 Synthesis of the AC-P₂W₁₈ composite

The Wells-Dawson-type Polyoxometalate potassium octadecatungstate diphosphate K₆[P₂W₁₈O₆₄]·xH₂O was synthesized according to the published procedure.54 To achieve different concentrations of P2W18 on AC, the amount of P2W18 was varied. AC-P₂W₁₈ was prepared using the procedure outlined below by varying the amounts of P_2W_{18} of 5 wt%, 10 wt%, and 15 wt%. 1 g AC in 0.010 L methanol was dispersed in a round bottom flask. The methanol solution was agitated for 10 minutes with a magnetic stirrer to ensure even distribution. To prepare the P₂W₁₈ solution, P₂W₁₈ was dissolved in a small quantity of water (<5 mL) and then added dropwise into the ACmethanol solution. The solution form was agitated for approximately 24 hours at room temperature. After drying under reduced pressure, the solution was rinsed with enough quantity of aqueous solution to remove the excess P2W18. The black residue was then collected and finally allowed to dry.

3.2 Electrode preparation and cell fabrication

Electrochemical performances were measured by taking 90% of the active material (composites such as 5 wt% AC- P_2W_{18} , 10 wt% AC-P2W18, and 15 wt% AC-P2W18) mixed with 10% PVDF (as a binder). The mixture was taken in a mortar and pestle to blend the materials after it was combined with N-methyl-2pyrrolidone (NMP, solvent) to make a uniform slurry. Next, a uniform layer of paste was coated on a flexible carbon cloth (each measuring 1 cm \times 1 cm). The carbon cloth was weighed before and after modifications, which allowed us to determine the actual mass of the electrodes. We calculated only the active substance's mass (equivalent to 0.9 mg). 0.5 M H₂SO₄ served as a proton-conducting electrolytes for SC cells, and Whatman filter paper was used as a separator, which was soaked in the electrolyte. Individually symmetric arrangements were constructed to conduct electrochemical studies. As part of the symmetric SC fabrication process, an electrolyte solution-



soaked filter paper separated an equivalent number of identical components from the carbon cloth.

4. Conclusion

The novel electrode materials were produced in situ using simple adsorption methods. In this study, we developed a Dawson polyoxometalate (P_2W_{18}) impregnated on AC surface hybrid electrode material for supercapacitor applications. Furthermore, symmetric cells such as 5% AC-P₂W₁₈, 10% AC-P₂W₁₈, and 15% AC-P₂W₁₈ nanostructures were electrochemically tested in a 0.5 M H₂SO₄ electrolyte solution using the twoelectrode configuration. The 5% AC-P2W18 symmetric cell shows an upgraded specific capacitance value of 289 F g^{-1} with a high energy density of 40 W h kg⁻¹. 5% AC-P₂W₁₈ shows superior electrochemical faradaic charge storage performance compared to other symmetric cells, which indicates that P₂W₁₈ is firmly incorporated onto the AC surface. To determine a supercapacitor's application, the 5% AC-P₂W₁₈ electrochemical capacitors achieved cycle stability of 89% over 4000 cycles.

Author contributions

Madhusree J. E.: visualization, investigation, writing – original draft, software. Pranay R. Chandewar: investigation, data curation. Debaprasad Shee: writing – review and editing. Sib Sankar Mal: conceptualization, methodology, writing – review and editing, supervision.

Conflicts of interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgements

This work is supported by the Council of Scientific and Industrial Research (CSIR) under scheme 01/(2906)/17/EMR-II. The authors acknowledge the central research facility (CRF) at NITK, Surathkal and the Ministry of Education (MoE) for providing analytical facilities.

References

- M. Vangari, T. Pryor and L. Jiang, Supercapacitors: Review of Materials and Fabrication Methods, *J. Energy Eng.*, 2013, 139(2), 72–79, DOI: 10.1061/(ASCE)EY.1943-7897.0000102.
- 2 Z. Yang, J. Zhang, M. C. W. Kintner-Meyer, X. Lu, D. Choi, J. P. Lemmon and J. Liu, Electrochemical Energy Storage for Green Grid, *Chem. Rev.*, 2011, **111**(5), 3577–3613, DOI: **10.1021/cr100290v**.
- 3 A. González, E. Goikolea, J. A. Barrena and R. Mysyk, Review on Supercapacitors: Technologies and Materials, *Renewable Sustainable Energy Rev.*, 2016, **58**, 1189–1206, DOI: **10.1016**/ **j.rser.2015.12.249**.

- 4 T. M. Bandhauer, S. Garimella and T. F. Fuller, A Critical Review of Thermal Issues in Lithium-Ion Batteries, *J. Electrochem. Soc.*, 2011, **158**(3), R1, DOI: **10.1149/1.3515880**.
- 5 M. Conte, Supercapacitors Technical Requirements for New Applications, *Fuel Cells*, 2010, **10**(5), 806–818, DOI: **10.1002**/ **fuce.201000087**.
- 6 D. P. Dubal, O. Ayyad, V. Ruiz and P. Gómez-Romero, Hybrid Energy Storage: The Merging of Battery and Supercapacitor Chemistries, *Chem. Soc. Rev.*, 2015, **44**(7), 1777–1790, DOI: **10.1039/C4CS00266K**.
- 7 C. Largeot, C. Portet, J. Chmiola, P.-L. Taberna, Y. Gogotsi and P. Simon, Relation between the Ion Size and Pore Size for an Electric Double-Layer Capacitor, *J. Am. Chem. Soc.*, 2008, **130**(9), 2730–2731, DOI: **10.1021/ja7106178**.
- 8 T. A. Centeno and F. Stoeckli, The Volumetric Capacitance of Microporous Carbons in Organic Electrolyte, *Electrochem. Commun.*, 2012, 16(1), 34–36, DOI: 10.1016/ j.elecom.2011.12.017.
- 9 B. Rajagopalan and J. S. Chung, Reduced Chemically Modified Graphene Oxide for Supercapacitor Electrode, *Nanoscale Res. Lett.*, 2014, 9(1), 535, DOI: 10.1186/1556-276X-9-535.
- 10 S. Korkmaz and İ. A. Kariper, Graphene and Graphene Oxide Based Aerogels: Synthesis, Characteristics and Supercapacitor Applications, *J. Energy Storage*, 2020, 27, 101038, DOI: 10.1016/j.est.2019.101038.
- 11 S. Maity, M. Je, B. R. Biradar, P. R. Chandewar, D. Shee, P. P. Das and S. S. Mal, Polyoxomolybdate–Polypyrrole– Graphene Oxide Nanohybrid Electrode for High-Power Symmetric Supercapacitors, *Energy Fuels*, 2021, 35(22), 18824–18832, DOI: 10.1021/acs.energyfuels.1c03300.
- 12 F. Cheng, W. Qiu, X. Yang, X. Gu, W. Hou and W. Lu, Ultrahigh-Power Supercapacitors from Commercial Activated Carbon Enabled by Compositing with Carbon Nanomaterials, *Electrochim. Acta*, 2022, **403**, 139728, DOI: **10.1016/j.electacta.2021.139728.**
- 13 Y. Lu, S. Zhang, J. Yin, C. Bai, J. Zhang, Y. Li, Y. Yang, Z. Ge, M. Zhang, L. Wei, M. Ma, Y. Ma and Y. Chen, Mesoporous Activated Carbon Materials with Ultrahigh Mesopore Volume and Effective Specific Surface Area for High Performance Supercapacitors, *Carbon*, 2017, **124**, 64–71, DOI: **10.1016/j.carbon.2017.08.044**.
- 14 Y. Jiang, J. Li, Z. Jiang, M. Shi, R. Sheng, Z. Liu, S. Zhang, Y. Cao, T. Wei and Z. Fan, Large-Surface-Area Activated Carbon with High Density by Electrostatic Densification for Supercapacitor Electrodes, *Carbon*, 2021, **175**, 281–288, DOI: **10.1016/j.carbon.2021.01.016**.
- 15 E. Frackowiak, K. Metenier, V. Bertagna and F. Beguin, Supercapacitor Electrodes from Multiwalled Carbon Nanotubes, *Appl. Phys. Lett.*, 2000, 77(15), 2421–2423, DOI: 10.1063/1.1290146.
- 16 A. L. M. Reddy and S. Ramaprabhu, Nanocrystalline Metal Oxides Dispersed Multiwalled Carbon Nanotubes as Supercapacitor Electrodes, *J. Phys. Chem. C*, 2007, 111(21), 7727–7734, DOI: 10.1021/jp069006m.
- 17 V. Augustyn, P. Simon and B. Dunn, Pseudocapacitive Oxide Materials for High-Rate Electrochemical Energy Storage,

Energy Environ. Sci., 2014, 7(5), 1597, DOI: 10.1039/ c3ee44164d.

- 18 B. E. Conway and W. G. Pell, Double-Layer and Pseudocapacitance Types of Electrochemical Capacitors and Their Applications to the Development of Hybrid Devices, *J. Solid State Electrochem.*, 2003, 7(9), 637–644, DOI: 10.1007/s10008-003-0395-7.
- 19 Z. Wu, Y. Zhu, X. Ji, and C. E. Banks, Transition Metal Oxides as Supercapacitor Materials, in *Nanomaterials in Advanced Batteries and Supercapacitors*, ed. K. I. Ozoemena and S. Chen, Nanostructure Science and Technology, Springer International Publishing, Cham, 2016, pp. 317–344, DOI: 10.1007/978-3-319-26082-2_9.
- 20 J. Wei, X. Li, H. Xue, J. Shao, R. Zhu and H. Pang, Hollow Structural Transition Metal Oxide for Advanced Supercapacitors, *Adv. Mater. Interfaces*, 2018, 5(9), 1701509, DOI: 10.1002/admi.201701509.
- 21 G. A. Snook, P. Kao and A. S. Best, Conducting-Polymer-Based Supercapacitor Devices and Electrodes, *J. Power Sources*, 2011, **196**(1), 1–12, DOI: **10.1016**/ j.jpowsour.2010.06.084.
- 22 D. P. Dubal, S. H. Lee, J. G. Kim, W. B. Kim and C. D. Lokhande, Porous Polypyrrole Clusters Prepared by Electropolymerization for a High Performance Supercapacitor, *J. Mater. Chem.*, 2012, 22(7), 3044, DOI: 10.1039/c2jm14470k.
- 23 F. Qi, L. Shao, X. Shi, F. Wu, H. Huang, Z. Sun and A. Trukhanov, Carbon Quantum Dots-Glue Enabled High-Capacitance and Highly Stable Nickel Sulphide Nanosheet Electrode for Supercapacitors, *J. Colloid Interface Sci.*, 2021, 601, 669–677, DOI: 10.1016/j.jcis.2021.05.099.
- 24 A. Vannathan, P. R. Chandewar, D. Shee and S. Sankar Mal, Asymmetric Polyoxometalate-Polypyrrole Composite Electrode Material for Electrochemical Energy Storage Supercapacitors, *J. Electroanal. Chem.*, 2022, **904**, 115856, DOI: **10.1016/j.jelechem.2021.115856**.
- 25 M. P. K. Anees, A. A. Vannathan, M. B. Abhijith, T. Kella, D. Shee and S. S. Mal, Imidazolium Cation Linkers of Polyoxomolybdate-Polypyrrole Nanocomposite Electrode-Based Energy Storage Supercapacitors, *Mater. Chem. Phys.*, 2022, 277, 125441, DOI: 10.1016/ j.matchemphys.2021.125441.
- 26 J. Jiang, L. Zhang, X. Wang, N. Holm, K. Rajagopalan, F. Chen and S. Ma, Highly Ordered Macroporous Woody Biochar with Ultra-High Carbon Content as Supercapacitor Electrodes, *Electrochim. Acta*, 2013, **113**, 481–489, DOI: **10.1016/j.electacta.2013.09.121**.
- 27 S. Maity, N. BM, T. Kella, D. Shee, P. P. Das and S. S. Mal, Activated Carbon- Supported Vanado-Nickelate (IV) Based Hybrid Materials for Energy Application, *J. Energy Storage*, 2021, 40, 102727, DOI: 10.1016/j.est.2021.102727.
- 28 A. Mhanni, L. Quahab, O. Pena, D. Grandjean, C. Garrigou-Lagrange and P. Delhaes, New Organic-Donor Inorganic-Acceptor Salts: $[(TTF)_6(XMo_{12}O_{40}) (Et4)]$, X = Si and P, *Synth. Met.*, 1991, 42(1-2), 1703-1706, DOI: 10.1016/0379-6779(91)91935-4.

- 29 S. Triki, L. Ouahab, J. Padiou and D. Grandjean, The Use of Polyoxometallates as Acceptors in Charge Transfer Salts: Preparation, X-Ray Crystal Structures, and Preliminary Spectroscopic Characterizations of $D_3M_6O_{19}$, D = TTF, TMTSF; M = Mo, W, J. Chem. Soc., Chem. Commun., 1989, 15, 1068, DOI: 10.1039/c39890001068.
- 30 E. Coronado, J. R. Galán-Mascarós, C. Giménez-Saiz, C. J. Gómez-García and V. N. Laukhin, The First Radical Salt of the Polyoxometalate Cluster $[P_2W_{18}O_{62}]^{6\odot}$ with Bis(Ethylenedithio)Tetrathiafulvalene (ET): $ET_{11}[P_2W_{18}O_{62}]$ · $3H_2O$, *Adv. Mater.*, 1996, **8**(10), 801–803, DOI: **10.1002**/ **adma.19960081005**.
- 31 D. Wu, M. Xu and S. Lin, Synthesis, Crystal Structure and Catalytic Activity of a Waugh Type Polyoxometalate H₁₂[MnMo₉O₃₂(KO)₆], *Front. Chem. China*, 2007, 2(2), 213– 217, DOI: 10.1007/s11458-007-0043-3.
- 32 M. T. Pope and A. Müller, Polyoxometalate Chemistry: An Old Field with New Dimensions in Several Disciplines, *Angew Chem. Int. Ed. Engl.*, 1991, **30**(1), 34–48, DOI: **10.1002/anie.199100341**.
- 33 D. C. Crans, M. Mahroof-Tahir, O. P. Anderson and M. M. Miller, X-Ray Structure of $(NH_4)_6$ (Gly-Gly)₂V₁₀O₂₈.4H₂O: Model Studies for Polyoxometalate-Protein Interactions, *Inorg. Chem.*, 1994, 33(24), 5586–5590, DOI: 10.1021/ic00102a036.
- 34 M. Sadakane and E. Steckhan, Electrochemical Properties of Polyoxometalates as Electrocatalysts, *Chem. Rev.*, 1998, 98(1), 219–238, DOI: 10.1021/cr960403a.
- 35 Y. Ji, L. Huang, J. Hu, C. Streb and Y.-F. Song, Polyoxometalate-Functionalized Nanocarbon Materials for Energy Conversion, Energy Storage and Sensor Systems, *Energy Environ. Sci.*, 2015, 8(3), 776–789, DOI: 10.1039/ C4EE03749A.
- 36 R. Wang, C. Xu and J.-M. Lee, High Performance Asymmetric Supercapacitors: New NiOOH Nanosheet/Graphene Hydrogels and Pure Graphene Hydrogels, *Nano Energy*, 2016, **19**, 210–221, DOI: **10.1016/j.nanoen.2015.10.030**.
- 37 H.-Y. Chen, R. Al-Oweini, J. Friedl, C. Y. Lee, L. Li, U. Kortz, U. Stimming and M. Srinivasan, A Novel SWCNT-Polyoxometalate Nanohybrid Material as an Electrode for Electrochemical Supercapacitors, *Nanoscale*, 2015, 7(17), 7934–7941, DOI: 10.1039/C4NR07528E.
- 38 N. Kawasaki, H. Wang, R. Nakanishi, S. Hamanaka, R. Kitaura, H. Shinohara, T. Yokoyama, H. Yoshikawa and K. Awaga, Nanohybridization of Polyoxometalate Clusters and Single-Wall Carbon Nanotubes: Applications in Molecular Cluster Batteries, *Angew. Chem.*, 2011, 123(15), 3533–3536, DOI: 10.1002/ange.201007264.
- 39 M. Genovese, Y. W. Foong and K. Lian, The Unique Properties of Aqueous Polyoxometalate (POM) Mixtures and Their Role in the Design of Molecular Coatings for Electrochemical Energy Storage, *Electrochim. Acta*, 2016, **199**, 261–269, DOI: **10.1016/j.electacta.2016.01.145**.
- 40 T. Akter, K. Hu and K. Lian, Investigations of Multilayer Polyoxometalates-Modified Carbon Nanotubes for Electrochemical Capacitors, *Electrochim. Acta*, 2011, **56**(14), 4966–4971, DOI: **10.1016/j.electacta.2011.03.127**.

- 41 V. Ruiz, J. Suárez-Guevara and P. Gomez-Romero, Hybrid Electrodes Based on Polyoxometalate–Carbon Materials for Electrochemical Supercapacitors, *Electrochem. Commun.*, 2012, 24, 35–38, DOI: 10.1016/j.elecom.2012.08.003.
- 42 J. Suárez-Guevara, V. Ruiz and P. Gomez-Romero, Hybrid Energy Storage: High Voltage Aqueous Supercapacitors Based on Activated Carbon–Phosphotungstate Hybrid Materials, *J. Mater. Chem. A*, 2014, 2(4), 1014–1021, DOI: 10.1039/C3TA14455K.
- 43 C. Hu, E. Zhao, N. Nitta, A. Magasinski, G. Berdichevsky and G. Yushin, Aqueous Solutions of Acidic Ionic Liquids for Enhanced Stability of Polyoxometalate-Carbon Supercapacitor Electrodes, *J. Power Sources*, 2016, 326, 569– 574, DOI: 10.1016/j.jpowsour.2016.04.036.
- 44 M. Genovese and K. Lian, Polyoxometalate Modified Pine Cone Biochar Carbon for Supercapacitor Electrodes, *J. Mater. Chem. A*, 2017, 5(8), 3939–3947, DOI: 10.1039/ C6TA10382K.
- 45 S. Maity, A. A. Vannathan, T. Kella, D. Shee, P. P. Das and S. S. Mal, Electrochemical Performance of Activated Carbon-Supported Vanadomolybdates Electrodes for Energy Conversion, *Ceram. Int.*, 2021, 47(19), 27132–27141, DOI: 10.1016/j.ceramint.2021.06.128.
- 46 A. A. Vannathan, P. R. Chandewar, D. Shee and S. S. Mal, Polyoxovanadate-Activated Carbon-Based Hybrid Materials for High-Performance Electrochemical Capacitors, *J. Electrochem. Soc.*, 2022, **169**(5), 050538, DOI: **10.1149/1945-7111/ac6c58**.
- 47 A. Mu, J. Li, W. Chen, X. Sang, Z. Su and E. Wang, The Composite Material Based on Dawson-Type Polyoxometalate and Activated Carbon as the Supercapacitor Electrode, *Inorg. Chem. Commun.*, 2015, 55, 149–152, DOI: 10.1016/j.inoche.2015.03.032.
- 48 A. Jarrah and S. Farhadi, K₆P₂W₁₈O₆₂ Encapsulated into Magnetic Fe₃O₄/MIL-101 (Cr) Metal-Organic Framework: A

Novel Magnetically Recoverable Nanoporous Adsorbent for Ultrafast Treatment of Aqueous Organic Pollutants Solutions, *RSC Adv.*, 2018, **8**(66), 37976–37992, DOI: **10.1039/C8RA06287K.**

- 49 A. P. Terzyk, The Influence of Activated Carbon Surface Chemical Composition on the Adsorption of Acetaminophen (Paracetamol) in Vitro, *Colloids Surf., A*, 2001, 177(1), 23–45, DOI: 10.1016/S0927-7757(00)00594-X.
- 50 Q. Zhu, B. Paci, A. Generosi, S. Renaudineau, P. Gouzerh, X. Liang, C. Mathieu, C. Rountree, G. Izzet, A. Proust, N. Barrett and L. Tortech, Conductivity via Thermally Induced Gap States in a Polyoxometalate Thin Layer, *J. Phys. Chem. C*, 2019, **123**(3), 1922–1930, DOI: **10.1021**/ **acs.jpcc.8b08510**.
- 51 S. Zhu, M. Wu, M.-H. Ge, H. Zhang, S.-K. Li and C.-H. Li, Design and Construction of Three-Dimensional CuO/ Polyaniline/RGO Ternary Hierarchical Architectures for High Performance Supercapacitors, *J. Power Sources*, 2016, 306, 593–601, DOI: 10.1016/j.jpowsour.2015.12.059.
- 52 V. Augustyn, P. Simon and B. Dunn, Pseudocapacitive Oxide Materials for High-Rate Electrochemical Energy Storage, *Energy Environ. Sci.*, 2014, 7(5), 1597, DOI: 10.1039/ c3ee44164d.
- 53 B. E. Conway and W. G. Pell, Double-Layer and Pseudocapacitance Types of Electrochemical Capacitors and Their Applications to the Development of Hybrid Devices, *J. Solid State Electrochem.*, 2003, 7(9), 637–644, DOI: 10.1007/s10008-003-0395-7.
- 54 C. R. Graham and R. G. Finke, The Classic Wells–Dawson Polyoxometalate, $K_6[\alpha$ -P₂W₁₈O₆₂]·14H₂O. Answering an 88 Year-Old Question: What Is Its Preferred, Optimum Synthesis?, *Inorg. Chem.*, 2008, 47(9), 3679–3686, DOI: 10.1021/ic702295y.