EES Catalysis



View Article Online

PAPER

Check for updates

Cite this: *EES Catal.*, 2024, 2, 1314

Efficient CO₂-to-CO conversion in dye-sensitized photocatalytic systems enabled by electrostatically-driven catalyst binding⁺

Vasilis Nikolaou, (1)*^a Palas Baran Pati, (1)^a Hélène Terrisse, (1)*^b Marc Robert (1)*^{cd} and Fabrice Odobel (1)*^a

The development of noble metal-free dye-sensitized photocatalytic systems (DSPs) for CO₂-to-CO conversion remains limited. Current literature primarily focuses on a single strategy: the simultaneous loading of both the photosensitizer (PS) and the catalyst (CAT) onto titanium dioxide nanoparticles (TiO₂ NPs) using anchoring groups. Here, we introduce an innovative method through immobilizing a positively-charged molecular CAT onto negatively-charged PS-TiO₂ NPs. Our approach yields promising results, including near-complete CO₂-to-CO conversion (~100% CO) and exceptional stability, achieving 1658 turnover numbers *versus* the CAT and an apparent quantum yield efficiency (AQY) of 16.9%.

Received 30th July 2024, Accepted 21st September 2024

DOI: 10.1039/d4ey00156g

rsc.li/eescatalysis

Broader context

Artificial photosynthetic systems for producing chemicals, fuels, or materials offer a straightforward and cost-effective approach to CO_2 recycling driven by solar energy. While these technologies are still in their early stages, they hold the potential for large-scale production of commodity chemicals and fuels in the future. Hybrid catalytic systems, which combine light-absorbing nano-objects like quantum dots and nanoparticles with catalysts such as molecular catalysts, have garnered significant interest. These systems efficiently convert CO_2 into various products using catalytic processes powered by solar irradiation. However, designing systems that balance efficient photon absorption, catalytic efficiency, and long-term stability remains a major challenge. This work introduces an innovative strategy that leverages electrostatic interactions between negatively charged TiO₂ nanoparticles, functionalized with a molecular photosensitizer, and a positively charged molecular catalyst, using only abundant metals like zinc and iron. Such systems demonstrate an apparent quantum yield (AQY) efficiency of CO formation at 525 nm close to 17% and exhibit good stability under operational conditions—a notable advancement toward achieving higher solar energy conversion efficiency.

An auspicious strategy to convert carbon dioxide (CO₂) emissions involves the utilization of solar-driven catalytic systems to produce valuable chemicals and fuels.^{1–4} Carbon monoxide (CO) is a valuable product of the CO₂ reduction reaction (CO₂RR), serving as a precursor in: (i) Fischer–Tropsch synthesis, (ii) methanol production, (iii) hydrocarbon synthesis, and (iv) manufacturing of various industrial materials.^{5–9} Within the landscape of solar-driven methodologies,^{10–14} dye-sensitized photocatalytic systems (DSPs) have garnered considerable scientific interest due to their high potential.¹⁵ More specifically, DSPs are extremely robust

systems that are easy to fabricate and potentially low-cost. They offer exceptional tunability due to the versatile modifications possible in their individual components, including the photosensitizer, catalyst, and semiconductor nanoparticles.¹⁶

The common DSPs discussed in the literature consist of titanium dioxide (TiO₂) nanoparticles (NPs) functionalized with a molecular catalyst (CAT) to facilitate CO₂ reduction, along with a photosensitizer (PS). Upon absorption of a photon, the photosensitizer (PS) undergoes excitation, leading to the injection of electrons (e⁻) into the conduction band (CB) of TiO₂. These electrons are subsequently transferred to the CO₂ reduction catalyst (CO₂R CAT), initiating the catalytic process. Upon accumulating two electrons, the molecular CAT drives the reduction of CO₂ into CO, while the sacrificial electron donor (SED) regenerates the oxidized photosensitizer (PS⁺), restoring it into its initial ground state (Fig. 1). Several studies have explored various PSs, CATs, and metal-doped TiO₂ NPs, and diverse strategies have been proposed to enhance both the stability and the efficiency of DSPs for H₂ evolution.^{15,17,18}

^a Nantes Université, CNRS, CEISAM, UMR 6230, F-44000 Nantes, France.

 $E\text{-}mail:\ vasile ios.nikola ou @univ-nantes.fr,\ fabrice.odo bel @univ-nantes.fr$

^b Institut des Matériaux de Nantes Jean Rouxel, IMN, Nantes Université, CNRS, F-44000 Nantes, France. E-mail: Helene.Terrisse@cnrs-imn.fr

^c Laboratoire d'Electrochimie Moléculaire, Université Paris Cité, CNRS, F-75006 Paris, France. E-mail: marc.robert@sorbonne-universite.fr

^d Institut Universitaire de France (IUF), Paris, F-75005, France

[†] Electronic supplementary information (ESI) available. See DOI: https://doi.org/

^{10.1039/}d4ey00156g



Fig. 1 DSPs for CO_2 -to-CO reduction: (upper panel) previous examples from the literature; (lower panel) our strategy comprising a positivelycharged molecular catalyst (CAT) and negatively-charged dye-sensitized TiO₂ nanoparticles (PS-TiO₂ NPs).

However, corresponding research into CO_2R remains relatively scarce with pioneering contributions from Kang and coworkers.^{19–21} Recently, our research team explored the first noble metal-free DSPs for CO_2 -to-CO conversion.²² In all these examples, the catalyst was anchored to the TiO₂ nanoparticles through a covalent linkage facilitated by either a carboxylic or phosphonic group. There is obviously significant room for further improving such systems, as well as for exploring new directions and concepts within this area of research.

Herein, we present an innovative strategy involving the utilization of electrostatic interactions between negativelycharged TiO₂ NPs, functionalized with a PS, and a positivelycharged molecular CAT. Although electrostatic interactions have been previously employed to position redox mediators near sensitizers in dye-sensitized solar cells (DSSCs) and photocatalytic systems,²³⁻²⁸ this technique has not yet been applied to the fabrication of DSPs, specifically for assembling catalysts onto sensitized TiO₂ nanoparticles. As depicted in Fig. 1, this approach offers numerous advantages over the conventional CO₂-to-CO reducing DSPs documented in the literature. Specifically, the absence of an anchoring group on the molecular catalyst eliminates the need for additional synthetic steps for its functionalization and facilitates maximal loading of the photosensitizer (PS). This is in contrast to previously reported DSPs, where the molecular CAT requires functionalization with an anchoring group, leading to competition with the chemical adsorption of the PS moiety. Furthermore, by employing electrostatic interactions, the ratio between the PS and the CAT can be easily tuned. In contrast, optimizing this ratio with the conventional approach depends on the relative affinity of each component's anchoring group (PS and CAT) with the TiO₂ NPs. We report in this study novel DSPs, based on the electrostatic interaction approach, that exhibit outstanding CO selectivity (~100% CO₂-to-CO) and remarkable stability (1658 turnovers numbers, TONs *vs.* CAT), surpassing previous noble metal-free DSPs,²² where the PS and the CAT were functionalized with typical anchoring groups and covalently grafted to TiO₂ particles.

Prior to photocatalytic studies, zeta potential experiments were conducted on the TiO2 NPs to verify their electrostatic properties (see ESI,[†] for detailed methodology). The experiments were performed in dimethylformamide (DMF) and acetonitrile (ACN) solutions, showing that the nanoparticles exhibit a negative charge, with zeta potential (ζ) = -21 ± 2 mV in DMF, and $\zeta = -29 \pm 5$ mV in ACN (entries 1 and 4, Table S1, ESI[†]). The anchoring of the PS further increases the negative zeta potential value of the TiO₂ NPs, which reaches $\zeta = -30 \pm 3$ mV (DMF) and $\zeta = -39 \pm 1$ mV (ACN) (entries 2 and 5, Table S1, ESI⁺). Noteworthily, these studies were conducted in the presence of the sacrificial electron donor (SED) 1,3-dimethyl-2-phenyl-2,3-dihydro-1H-benzo[D]imidazole (BIH), to closely mimic the conditions of photocatalytic experiments. Additionally, infrared spectroscopy experiments were performed to validate the successful synthesis of the DSPs, comparing the spectra of bare TiO₂ and the functionalized photocatalytic NPs (see ESI,† and Fig. S2 and S3).

For our solar-driven CO₂-to-CO conversion studies, we selected the positively charged Fe(o-TMA) iron porphyrin as a catalyst, one of the most efficient molecular CATs in the CO₂RR.²⁹⁻³¹ Moreover, this molecular catalyst has been extensively studied by various research groups, consistently demonstrating that the CO produced originates from CO₂ rather than any side reactions or decomposition.²⁹⁻³³ Regarding the choice of the PS, three different dyes were employed: D₃₅, N₇₁₉ and ZnP (as illustrated in Fig. 2). While each of these dyes has demonstrated notable performance in TiO2-based solar cell34-42 and water splitting^{43–47} applications, it is worth highlighting that **ZnP** has proved to be an efficient PS in the CO₂R, when anchored on the photocathodes48,49 and on TiO2-NPs.22 Our initial photocatalytic CO2 reduction experiments demonstrated that ZnP outperformed both the N719- and D35-sensitized systems reaching 124 mmol of CO per g of CAT in 96 hours of irradiation (Fig. S5 and ESI,[†] for experimental details). Remarkably, in all cases, no traces of H₂



Fig. 2 Photosensitizers (PS, upper panel) and molecular catalysts (CAT, lower panel) explored in this work.

were detected, indicating quantitative CO_2 -to-CO conversion (~100% selectivity).

All three dyes exhibit absorption bands in the green region of the visible spectrum, but with significantly different absorption coefficients (Fig. S6a, ESI[†]), even though they can all be effectively excited by the green LED lamp (Fig. S6b, ESI⁺). Specifically, D_{35} exhibits the highest light collection efficiency, followed by N₇₁₉, with ZnP showing the lowest absorption in this region. All three dyes have redox properties suitable for the two key processes: (i) electron injection into the conduction band (CB) of TiO_2 and (ii) dye regeneration by the sacrificial electron donor (SED), BIH. As outlined in Table S2 (ESI[†]), the dyes exhibit similar driving forces for both electron injection (ΔG_{inj}) and dye regeneration (ΔG_{reg}) . Consequently, the differences in redox and absorption properties alone are unlikely to account for the better photocatalytic performance of ZnP. Instead, this enhanced performance is likely due to other factors, such as the molecular organization on the TiO₂ surface. Our current studies in DSPs for CO2 reduction demonstrate that ZnP consistently outperforms other sensitizers.⁵⁰ This suggests that ZnP may possess a structural arrangement on the TiO₂ surface that promotes more effective charge separation and transfer processes, although investigating these details is beyond the scope of this work. Overall, our observations strongly suggest that the superior performance of ZnP is not due to its redox properties and absorption characteristics, but rather to its specific organization, rendering the electronic interactions between TiO₂ and the catalyst more favourable.

To assess the impact of the positively-charged molecular catalyst, we performed additional photocatalytic experiments upon using a neutral (FeTPP) and a negatively-charged (FeTSP) iron-porphyrin (Fig. 2). In both cases, the DSP studies indicated no conversion of CO2 to either CO or H2, further illustrating the key role of the electrostatic interactions between the negatively-charged ZnP-TiO₂ NPs and the positively-charged Fe(o-TMA) CAT. Additional evidence supporting this conclusion was obtained from supplementary zeta potential experiments conducted in the presence of Fe(o-TMA). The negative charge of the ZnP–TiO₂ nanoparticles (ζ = -30 ± 3 mV in DMF and $\zeta = -39 \pm 1$ mV in ACN) was reversed to positive upon the addition of Fe(o-TMA) to the solution ($\zeta = +21 \pm 5 \text{ mV}$ (DMF) and ζ = +24 \pm 1 mV (ACN), entries 3 and 6, Table S1, ESI†), confirming the strong interaction (and adsorption) of the CAT onto the ZnP-TiO₂ NPs (Fig. 3 and Fig. S4, ESI[†]).

Encouraged by these results, we then optimized our DSPs. In our initial experiments, DMF was employed as the solvent and BIH as the SED. In a typical run, the **ZnP-TiO**₂ NPs were dispersed in 4 mL of DMF solution, containing BIH (50 mM) and **Fe(o-TMA)** CAT. To determine the optimal ratio between the PS and the CAT, various combinations were investigated, assessing their corresponding TONs, selectivity, and CO production rates (Table S3, ESI†). First, control experiments revealed no catalytic activity (neither CO nor H₂) in the absence of: (i) PS (entry 1, Table S3, ESI†), (ii) CAT (entry 2, Table S3, ESI†), (iii) SED (entry 3, Table S3, ESI†), and (iv) light irradiation (entry 4, Table S3, ESI†). Noteworthily, the combination of



Fig. 3 Zeta potential determination of $ZnP@TiO_2$ (black) and $ZnP@TiO_2 + Fe(o-TMA)$ (red) in DMF solution containing 50 mM of BIH. See ESI,† for Experimental details.

0.24 µmol (0.2 mg) of ZnP and 0.032 µmol (0.05 mg) of Fe(o-TMA) resulted in quantitative CO selectivity (entry 5, Table S3, ESI[†]). Other tested PS and CAT ratios also exhibited high CO selectivity as well, ranging from 94% to 98% (entries 6-9, Table S3, ESI[†]). By decreasing the amount of Fe(o-TMA) to 0.016 µmol (0.025 mg), both stability (419 TONs) and CO production (268 mmol g^{-1}) were significantly enhanced (entry 6, Table S3, ESI[†]). To investigate the effect of different PS amounts on electron transfer, we compared the results from entries 6 and 9 (Table S3, ESI[†]). In these experiments, all conditions were kept identical except for the PS concentration, which was 0.24 µmol in entry 6 and 0.12 µmol in entry 9. The photocatalytic results indicate that increasing the amount of PS does not hinder electron transfer. The highest CO production though in terms of µmols of CO, was attained using 0.12 µmol of ZnP (0.1 mg) and 0.032 µmol (0.05 mg) of Fe(o-TMA) (entry 8, Table S3, ESI⁺).

In subsequent experiments, we examined the influence of the proton (H⁺) source upon adding trifluoroethanol (TFE) and phenol. As listed in Table 1 (entries 1–3) the addition of either H⁺ source enhanced the photocatalytic parameters (CO yield, CO/H₂ ratio, TONs, and CO production in mmol g⁻¹). However, phenol was a more efficient H⁺ source compared to TFE, yielding 30.1 µmol of CO, with nearly 100% selectivity, 939 TONs, and 601 mmol g⁻¹ of CO (entry 3, Table 1). Phenol serves

Table 1Photocatalysis results under different conditions upon 96 hoursof irradiation. In all cases 0.12 μ mol (0.1 mg) of PS and 0.032 μ mol (0.05 mg, $C = 8 \mu$ M) of CAT were used, unless otherwise stated

			L	L		
Entry	Solvent	H^+ source ^{<i>a</i>}	$H_2^{\ \ b}$	CO^{ρ}	TONS	mmol g^{-1c}
1	DMF	_	0.19	8.0	250	160
2	DMF	TFE	0.16	10.3	321	205
3	DMF	Phenol	0.15	30.1	939	601
4	ACN	_	0.13	8.7	271	174
5	ACN	Phenol	0.80	45.7	1429	915
6^d	ACN	Phenol	1.48	27.1	1658	530

 a 0.1 M. b In µmol. c mmol of CO per gram of CAT. d 0.12 µmol (0.1 mg) of PS and 0.016 µmol of CAT (0.025 mg, $C = 4 \mu$ M).



Fig. 4 Photocatalytic CO₂-to-CO conversion activities of **ZnPaTiO₂** NPs in 4 mL ACN solution containing 50 mM of BIH; (black): 0.12 μ mol (0.1 mg) of PS, 0.032 μ mol (0.05 mg) of **Fe(o-TMA)**, (red): 0.12 μ mol of PS (0.1 mg), 0.032 μ mol (0.05 mg) of **Fe(o-TMA)** and 0.1 M of phenol, (green): 0.12 μ mol of PS (0.1 mg), 0.016 μ mol (0.25 mg) of **Fe(o-TMA)** and 0.1 M of phenol. The reported values are the average of three independently repeated experiments.

as a more effective proton donor compared to weaker acids like TFE.^{51,52} Phenol can also engage more effectively in hydrogen bonding, whereas TFE's bulkier $-CF_3$ group can introduce steric hindrance, diminishing its ability to stabilize intermediates and thereby reducing catalytic efficiency. The better performance of phenol as a proton source in our CO₂-to-CO DSPs is attributed to a combination of its moderate acidity, and effective hydrogen bonding.

Overall, the optimum conditions for our DSPs were observed when ACN was used as a solvent (Fig. 4), a finding in excellent agreement with the zeta potential experiments (Fig. S4 and Table S1, ESI[†]). It is worth noting that the ζ potential of **ZnP@TiO**₂ NPs in ACN was significantly more negative ($\zeta =$ -39 ± 1 mV) than the ζ potential of **ZnP@TiO**₂ NPs in DMF ($\zeta =$ -29 ± 5 mV). In agreement with previous experiments, the addition of phenol significantly improved all the photocatalytic parameters (entries 4 and 5, Table 1), resulting in 1429 TONs and 915 mmol g⁻¹ of CO. Furthermore, reducing the amount of **Fe(o-TMA)** to 0.016 µmol (0.025 mg, entry 6, Table 1) resulted in 1658 TONs.

To shed light on the factors limiting the reactivity of the DSPs during irradiation, we performed post-photocatalytic studies after 96 hours of irradiation, at which point CO production reaches a plateau. Interestingly, the NPs exhibited a negative charge with a ζ -potential of -36 ± 2 mV, in contrast to their initial value of $+24 \pm 1$ mV before photocatalysis (Fig. S7 and Table S1, ESI†). This implies that the CAT was no longer attached to the surface of the NPs. Additionally, the absorption studies of the solution upon photocatalysis revealed porphyrinbased features (Fig. S8, orange line, ESI†). It remained however possible that the PS, the CAT, or both leached into the solution. Regeneration experiments made after 96 hours of irradiation revealed that the CO production could not be restored by adding either the PS or the CAT and purging the suspension with CO₂. These observations suggest that the observed loss of

activity may be attributed to both the PS and the CAT either leaching from the TiO_2 NPs or undergoing degradation, as illustrated in Fig. S9 (ESI[†]).

To elucidate the role of TiO_2 in our photocatalytic system, we performed additional measurements using the PS and the CAT in solution, without TiO₂ nanoparticles. In the absence of TiO₂, we detected a small amount of CO (2.4 µmol), which corresponds to low stability (77 TONs) and CO production (49 mmol g^{-1}). This significantly highlights the importance of TiO₂ as an electron mediator to shuttle electrons between the PS and the CAT, since the respective experiment (entry 4, Table 1) in the presence of TiO₂ demonstrated superior catalytic efficiency, yielding significantly higher photocatalytic values (8.7 μ mol of CO, 271 TONs, and 174 mmol g⁻¹). Additionally, in a previous study we demonstrated fast and efficient photoinduced electron transfer from the zinc porphyrin excited state (ZnP^*) to TiO₂,²² therefore the direct through space electron transfer from the bound ZnP* to FeP is reasonably uncompetitive. As a further control experiment, we tested a mixture of TiO₂, PS, and CAT. This experiment produced 2.9 µmol of CO, corresponding to 91 TONs and 58 mmol of CO per gram of CAT, which is significantly lower than the results obtained from the system based on electrostatic interactions (entry 4, Table 1). This notable difference further emphasizes the importance of anchoring both PS and CAT onto TiO2 for efficient electron transfer between them. Overall, TiO₂ not only serves as a scaffold for anchoring PS, allowing the formation of a heterogeneous photocatalyst through electrostatic interactions with CAT, but it also plays a crucial role in facilitating the electron transfer processes necessary for efficient photocatalysis.

Conclusions

In our study, the solar-driven CO_2 -to-CO conversion operates through an oxidative quenching mechanism. Femtosecond transient absorption spectroscopy measurements revealed rapid regeneration of the radical cation of the PS (**ZnP**^{•+}) by the SED.⁸ Initially, photoexcitation of **ZnP** produces **ZnP**^{*}, which undergoes ultrafast electron injection (11 ps) into TiO₂. The **ZnP**^{•+} formed is quickly regenerated by the SED, while the electron injected into TiO₂ is captured by **Fe**(*o*-**TMA**) (see details in Scheme S1, ESI[†]). Consistent with literature reports, **Fe**(*o*-**TMA**) in our experiments also showed selective and nearly quantitative reduction of CO₂ to CO, without forming additional reduction products.⁹ Importantly, BIH beyond serving as only a SED, could also function as second electron source, due to the formation of the highly reducing BI[•].¹³

In summary, our study unveiled a strategy that combines negatively-charged PS– TiO_2 NPs with a positively-charged ironporphyrin catalyst for selective CO₂-to-CO conversion. Our approach offers distinct advantages including easy assembling of the components of the photocatalytic system (Fig. 1). Table S4 and Fig. S10 (ESI†) provide a comparative overview of the TONs, CO production, and CO/H₂ ratios between previous DSPs in the literature and this work. It should be noted that variations in light intensity and type of irradiation source across the different reports significantly influence parameters like stability and production rates, rendering direct comparisons challenging. Our electrostatic-interaction strategy demonstrates compelling results, evidenced by achieving *ca.* 1500 TONs and a CO production of 915 mmol g⁻¹ (per g of CAT). Furthermore, the apparent quantum yield efficiency (AQY) of CO formation at 525 nm was determined to be 16.9% (see ESI,† for details). This value is higher compared to similar DSPs in the literature, which exhibit AQY values typically ranging from 0.1% to 3.9% (Table S4, ESI†).

In recent years, a plethora of positively-charged complexes have been employed as molecular catalysts in CO_2 reduction. This includes iron-, cobalt-, and nickel-polypyridyl complexes,⁵³ as well as noble metal-free dinuclear molecular catalysts.⁵⁴ Currently, we are exploring additional combinations of charged nanoparticles and catalysts, aiming to develop more efficient systems and with the objective to eliminate the sacrificial reagent, so as to position DSPs as a viable solution in the field of CO_2 photoconversion.

Data availability

The data supporting the findings of this study are available within the paper and its ESI.[†]

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This project was supported by HORIZON TMA MSCA Postdoctoral Fellowships – European Fellowships (HORIZON-TMA-MSCA-PF-EF) action program under the call MSCA Postdoctoral Fellowships 2021 ((HORIZON-MSCA-2021-PF-01)) to V. N., grant agreement no. 101064765, SOLAR-CAT. This study also received financial support under the EUR LUMOMAT project and the Investments for the Future program ANR-18-EURE-0012. Partial financial support to M. R. from the Institut Universitaire de France (IUF) is warmly acknowledged.

Notes and references

- 1 A. Gulzar, A. Gulzar, M. B. Ansari, F. He, S. Gai and P. Yang, *Chem. Eng. J. Adv.*, 2020, **3**, 100013.
- 2 M. Robert, ACS Energy Lett., 2016, 1, 281–282.
- 3 J. C. Wood, Z. Yuan and B. Virdis, *Curr. Opin. Electrochem.*, 2023, 37, 101177.
- 4 D. G. Nocera, Acc. Chem. Res., 2017, 50, 616-619.
- 5 T. A. Atsbha, T. Yoon, P. Seongho and C.-J. Lee, *J. CO2 Util.*, 2021, **44**, 101413.
- 6 A. A. Khan and M. Tahir, J. CO2 Util., 2019, 29, 205–239.
- 7 C. Song, Catal. Today, 2006, 115, 2-32.
- 8 T.-m Su, Z.-z Qin, H.-b Ji, Y.-x Jiang and G. Huang, *Environ. Chem. Lett.*, 2016, **14**, 99–112.

- 9 L. Yang, A. U. Pawar, R. P. Sivasankaran, D. Lee, J. Ye, Y. Xiong, Z. Zou, Y. Zhou and Y. S. Kang, *J. Mater. Chem. A*, 2023, **11**, 19172–19194.
- 10 Z. X. Bi, R. T. Guo, X. Hu, J. Wang, X. Chen and W. G. Pan, *Nanoscale*, 2022, 14, 3367–3386.
- 11 X. J. Liu, T. Q. Chen, Y. H. Xue, J. C. Fan, S. L. Shen, M. S. A. A. Hossain, M. A. Amin, L. K. Pan, X. T. Xu and Y. Yamauchi, *Coord. Chem. Rev.*, 2022, **459**, 214440.
- 12 A. Mustafa, B. G. Lougou, Y. Shuai, Z. J. Wang and H. P. Tan, J. Energy Chem., 2020, **49**, 96–123.
- 13 N. Nandal and S. L. Jain, Coord. Chem. Rev., 2022, 451, 214271.
- 14 Q. S. Wang, Y. C. Yuan, C. F. Li, Z. R. Zhang, C. Xia,
 W. G. Pan and R. T. Guo, *Small*, 2023, 19, 2301892.
- 15 J. Willkomm, K. L. Orchard, A. Reynal, E. Pastor, J. R. Durrant and E. Reisner, *Chem. Soc. Rev.*, 2016, 45, 9–23.
- 16 G. Reginato, L. Zani, M. Calamante, A. Mordini and A. Dessì, *Eur. J. Inorg. Chem.*, 2020, 899–917.
- 17 J.-F. Huang, Y. Lei, T. Luo and J.-M. Liu, *ChemSusChem*, 2020, 13, 5863–5895.
- 18 L. Zani, M. Melchionna, T. Montini and P. Fornasiero, J. Phys. Energy, 2021, 3, 031001.
- M. S. Choe, S. Choi, H. S. Lee, B. Chon, J. Y. Shin, C. H. Kim,
 H. J. Son and S. O. Kang, *ACS Appl. Mater. Interfaces*, 2022,
 14, 50718–50730.
- 20 S. Choi, Y. J. Kim, S. Kim, H. S. Lee, J. Y. Shin, C. H. Kim, H. J. Son and S. O. Kang, ACS Appl. Energy Mater., 2022, 5, 10526–10541.
- 21 H. J. Son, C. Pac and S. O. Kang, Acc. Chem. Res., 2021, 54, 4530-4544.
- 22 V. Nikolaou, C. Govind, E. Balanikas, J. Bharti, S. Diring, E. Vauthey, M. Robert and F. Odobel, *Angew. Chem., Int. Ed.*, 2024, **63**, e202318299.
- 23 H. Kumagai, R. Aoyagi, K. Kato, A. Yamakata, M. Kakihana and H. Kato, *ACS Appl. Energy Mater.*, 2021, 4, 2056–2060.
- 24 S. Nishioka, K. Hojo, L. Xiao, T. Gao, Y. Miseki, S. Yasuda, T. Yokoi, K. Sayama, T. E. Mallouk and K. Maeda, *Sci. Adv.*, 2022, 8, eadc9115.
- L. Casarin, W. B. Swords, S. Caramori, C. A. Bignozzi and G. J. Meyer, *Inorg. Chem.*, 2017, 56, 7324–7327.
- 26 L. Mistry, L. Le-Quang, G. Masdeu, W. Björkman,
 H. Härelind and M. Abrahamsson, *ChemCatChem*, 2022,
 14, e202200897.
- 27 N. Yoshimura, A. Kobayashi, M. Yoshida and M. Kato, *Chem. Eur. J.*, 2020, **26**, 16939–16946.
- 28 W. B. Swords, G. Li and G. J. Meyer, *Inorg. Chem.*, 2015, 54, 4512–4519.
- 29 I. Azcarate, C. Costentin, M. Robert and J.-M. Savéant, J. Am. Chem. Soc., 2016, **138**, 16639–16644.
- 30 V. C. C. Wang, ACS Catal., 2021, 11, 8292-8303.
- 31 D. J. Martin and J. M. Mayer, J. Am. Chem. Soc., 2021, 143, 11423–11434.
- 32 D. J. Martin, B. Q. Mercado and J. M. Mayer, *Inorg. Chem.*, 2021, **60**, 5240–5251.
- 33 A. K. Surendran, G. L. Tripodi, E. Pluhařová, A. Y. Pereverzev, J. P. J. Bruekers, J. A. A. W. Elemans, E. J. Meijer and J. Roithová, *Nat. Sci.*, 2023, 3, e20220019.

- 34 D. P. Hagberg, X. Jiang, E. Gabrielsson, M. Linder, T. Marinado, T. Brinck, A. Hagfeldt and L. Sun, *J. Mater. Chem.*, 2009, 19, 7232–7238.
- 35 X. Jiang, T. Marinado, E. Gabrielsson, D. P. Hagberg, L. Sun and A. Hagfeldt, *J. Phys. Chem. C*, 2010, **114**, 2799–2805.
- 36 J.-H. Yum, T. W. Holcombe, Y. Kim, J. Yoon, K. Rakstys, M. K. Nazeeruddin and M. Grätzel, *Chem. Commun.*, 2012, 48, 10727–10729.
- 37 D. M. Niedzwiedzki, Phys. Chem. Chem. Phys., 2021, 23, 6182-6189.
- 38 K. Portillo-Cortez, A. Martínez, A. Dutt and G. Santana, *J. Phys. Chem. A*, 2019, **123**, 10930–10939.
- 39 B. Selvaraj, G. Shanmugam, S. Kamaraj, A. Gunasekeran and A. Sambandam, *Inorg. Chem.*, 2021, **60**, 1937–1947.
- H. Hayashi, T. Higashino, Y. Kinjo, Y. Fujimori, K. Kurotobi,
 P. Chabera, V. Sundström, S. Isoda and H. Imahori, ACS Appl. Mater. Interfaces, 2015, 7, 18689–18696.
- 41 S. Hayashi, M. Tanaka, H. Hayashi, S. Eu, T. Umeyama, Y. Matano, Y. Araki and H. Imahori, *J. Phys. Chem. C*, 2008, 112, 15576–15585.
- 42 H. Imahori, Y. Matsubara, H. Iijima, T. Umeyama,
 Y. Matano, S. Ito, M. Niemi, N. V. Tkachenko and
 H. Lemmetyinen, *J. Phys. Chem. C*, 2010, 114, 10656–10665.
- 43 B. D. Sherman, M. V. Sheridan, K.-R. Wee, S. L. Marquard, D. Wang, L. Alibabaei, D. L. Ashford and T. J. Meyer, *J. Am. Chem. Soc.*, 2016, **138**, 16745–16753.

- 44 S. Gonuguntla, A. Tiwari, S. Madanaboina, G. Lingamallu and U. Pal, *J. Hydrogen Energy*, 2020, **45**, 7508–7516.
- 45 X. Yao, P.-Y. Ho, S.-C. Yiu, S. Suramitr, W.-B. Li, C.-L. Ho and S. Hannongbua, *Dyes Pigm.*, 2022, **205**, 110508.
- 46 E. Agapaki, K. Ladomenou, V. Nikolaou and A. G. Coutsolelos, J. Porphyrins Phthalocyanines, 2023, 27, 479–489.
- 47 V. Nikolaou, G. Charalambidis, G. Landrou, E. Nikoloudakis,
 A. Planchat, R. Tsalameni, K. Junghans, A. Kahnt, F. Odobel and A. G. Coutsolelos, *ACS Appl. Energy Mater.*, 2021, 4, 10042–10049.
- 48 Y. Kou, S. Nakatani, G. Sunagawa, Y. Tachikawa, D. Masui, T. Shimada, S. Takagi, D. A. Tryk, Y. Nabetani, H. Tachibana and H. Inoue, *J. Catal.*, 2014, **310**, 57–66.
- 49 R. Nakazato, Y. Kou, D. Yamamoto, T. Shimada, T. Ishida,
 S. Takagi, H. Munakata, K. Kanamura, H. Tachibana and
 H. Inoue, *Res. Chem. Intermed.*, 2021, 47, 269–285.
- 50 Unpublished results.
- 51 C. Costentin, M. Robert and J.-M. Savéant, *Chem. Soc. Rev.*, 2013, **42**, 2423–2436.
- 52 H. Rao, L. C. Schmidt, J. Bonin and M. Robert, *Nature*, 2017, 548, 74–77.
- 53 N. Elgrishi, M. B. Chambers, X. Wang and M. Fontecave, *Chem. Soc. Rev.*, 2017, **46**, 761–796.
- 54 J.-W. Wang, D.-C. Zhong and T.-B. Lu, *Coord. Chem. Rev.*, 2018, 377, 225–236.