Green Chemistry

CRITICAL REVIEW

Cite this: Green Chem., 2024, 26, 6261

Received 10th January 2024, Accepted 12th April 2024 DOI: 10.1039/d4gc00140k rsc.li/greenchem

1. Introduction

As an abundant and easily accessible resource, biomass provided the essential materials that have supported humanity for a long time until the rise of fossil resources.¹ Currently, the world is increasingly dependent on non-renewable fossil fuels $(i.e., coal, oil and natural gas)$ to meet the growing demand of development and the challenging requirements of modern industries.2 At the same time, the huge exploitation and burning of fossil resources leads to emission of large amounts of greenhouse gases that are already causing global climate change.³ Therefore, it is an urgent task and a major research challenge worldwide to find sustainable alternatives to the nonrenewable and petroleum-based energies and chemicals. In this context, the renaissance of biomass utilization in a much more efficient manner is expected.³ That is because carbon neutrality could be achieved in theory during biorefinery processes. The emitted greenhouse gases can be recycled

Sunlight-driven photocatalytic conversion of furfural and its derivatives

Qizhao Zhang, Bang Gu **D** and Wenhao Fang D^{*}

Furfural (mainly furfural and 5-hydroxymethylfurfural) and its derivatives stand out as an important platform for C5 and C6 compounds from lignocellulosic biomass. Catalytic valorization of these renewable carbohydrates not only enables the manufacture of various high-valued chemicals but also enriches routes and theories for the direct use of crude biomass. Photocatalytic conversion of furfural and its derivatives using solar energy has recently received great attention. Such an environmentally friendly and energy-saving approach enables activation and transformation of the target chemical bonds under very mild reaction conditions using photoexcited charge carriers or photogenerated reactive species. However, highly selective photocatalysts are somewhat lacking and the reaction mechanisms usually remain obscure. Herein, this review article aims to systematically summarize the recent advances in sunlight-driven photocatalytic conversion of furfural and 5-hydroxymethylfurfural to sustainable buildingblock chemicals. In particular, the strategies of catalyst design and the unique roles of reactive species (i.e., photogenerated electrons and holes, hydroxyl and superoxide radicals, and singlet oxygen) are discussed. This allows insights into the catalytic mechanisms. In addition, the latest progress in the combination of such photooxidation with H₂ evolution or $CO₂$ reduction, as well as photo(electro)chemical conversion, is also reviewed. In addition to the common oxidation and reduction reactions, some nontraditional reaction paths (i.e., reductive coupling, oxidative decarboxylation and ring-opening) and promising products are introduced. Finally, challenges and future opportunities from the perspective of green chemistry are also analyzed. Therefore, a bright prospect can be foreseen in the near future for many more photocatalytic valorizations of furfural-like molecules. **CRITICAL REVIEW**

<sup>[View Article Online](https://doi.org/10.1039/d4gc00140k) and **Surface Conversion of**
 Consection Christian Conversion of **furtherial and its derivatives**

Colzhao Zhang, Bang Gu⁰ and Wentnao Fang[®]

Further limit of proposition in the</sup>

> and fed back to biomass resources through photosynthesis using solar energy. In light of this, innovation and complete use of abundant and renewable biomass resources are particularly important in the pursuit of a sustainable future.

> Plant materials consisting primarily of carbohydrate polymers (i.e., cellulose and hemicellulose) and aromatic polymers (i.e., lignin) are considered as lignocellulose and account for over 90% of all plant biomass.⁴ It is the most abundant source of renewable carbon and would not compete with food reserves.⁵ Thereby conversion of lignocellulosic biomass into value-added fuels and chemicals is a preferred option for harvesting sustainable energy and realizing carbon neutrality. In order to achieve this objective, bioplatform molecules, rather than crude biomass, are usually selected and studied in fundamental research due to the high complexity of biorefinary. $6-9$ Currently, furfural and its derivatives can be readily obtained from chemical and/or biological routes through hydrolysis and/or dehydrogenation of cellulose and hemicellulose. The biomass-derived furanic compounds mainly including furfural (FAL) and 5-hydroxymethylfurfural (HMF) are regarded as the key platform molecules in biorefining processes.^{10,11} They can be converted into a range of value-added building-block

School of Chemical Science and Technology, Yunnan University, 2 North Cuihu Road, Kunming 650091, China. E-mail: wenhao.fang@ynu.edu.cn

Fig. 1 A schematic diagram of photocatalytic conversion of furfural (FAL) with major pathways and products.

Fig. 2 A schematic diagram of photocatalytic conversion of 5-hydroxymethylfurfural (HMF) with major pathways and products.

chemicals (Fig. 1 and 2), typically furfuryl alcohol (FOL), 12 2,5bis(hydroxymethyl)furan (BHMF),¹³ 2,5-diformylfuran (DFF)¹⁴ and 2,5-furandicarboxylic acid (FDCA).¹⁵

Among them, DFF, FDCA and BHMF with a symmetric structure have attracted much attention. That is because they are promising monomers for manufacturing furan-based polymers which could be alternatives to nonrenewable petroleumbased aromatic monomers. For instance, DFF can be widely used in the production of organic conductors and as intermediates for drugs and antifungal agents. FDCA can serve as ideal monomer instead of terephthalic acid to synthesize

renewable bioplastics in the presence of ethylene glycol. Thus it has been listed within the top 12 value-added chemicals from biomass by the U.S. Department of Energy.¹⁶ FOL can be a building-block intermediate for manufacturing fibers, lubricants, and resins.¹²

Over the past two decades, many efforts have made to develop heterogeneous catalysts with the assistance of thermochemistry to achieve those transformations of furfural and its derivatives.^{17,18} However, the processes are usually and essentially operated by using high temperatures and/or pressures, resulting in considerable energy consumption and process cost. In contrast, the use of photocatalysis technology enables conversion of biomass to high-value organic chemicals under mild conditions and has attracted great interest due to its economic and environmental advantages. So far, preliminary studies on the photocatalytic conversion of FAL, HMF and their derivatives have been carried out.¹⁹⁻²¹ Notably, most of the photocatalysts are common ones already used in the classic photoreactions, e.g., water splitting. In some specific reactions, it still remains quite difficult to attain both good conversion and selectivity. For instance, titanium dioxide $(TiO₂)$, which was first applied to the photocatalytic oxidation of HMF, has an inherently large band gap.¹⁹ Hence TiO₂ can only respond to ultraviolet (UV) irradiation. But the UV region only accounts for a very small part (ca. 3%) of the solar radiation spectrum. Unless visible light (ca. 44%) can participate in the photochemical reaction it is obviously a huge waste of solar energy. 22 At the same time, inappropriate placement of the valence band of $TiO₂$ can unfortunately promote the formation of excessive strong oxidants like hydroxyl radicals (• OH). Such reactive species can usually lead to nonselective decomposition (e.g. mineralization) of organic compounds or side reactions. Besides, dedicated photoreactors are necessary for UV light-driven reactions, but these are expensive and environmentally unfriendly. Specifically, the high energy consumption for generating UV light and the size of customized reactors would severely restrict the application of large-scale photosynthesis. As a result, the focus in the field has gradually shifted to developing a range of visible-light-responsive photocatalysts with a suitable band location, in order to address the above issues.²³⁻²⁷ Critical Review Excess to the Unit of the back of the context signal environment of the sig

> In addition, photogenic radical intermediates allow for novel and meaningful reaction paths (Fig. 1 and 2) that are unlikely to be achieved in conventional heterogeneous catalysis. For example, selective dimerization of FAL through photoreductive coupling enables molecules with increased carbon numbers to be further upgraded to gasoline-grade fuels.^{28,29} However, in conventional heterogeneous catalysis, the selective formation of vinyl radical intermediates is rather difficult because the reducing atmosphere usually results in hydrogenation at lower temperatures or hydrolysis at higher temperatures.³⁰ Moreover, owing to the unique redox ability of photogenerated electrons (e^-) and holes (h^+) in the photocatalytic system, selective oxidation and reduction can simultaneously occur over the same catalyst. In such a context, H_2 evolution^{31,32} or CO_2 reduction³³ can be simultaneously per

formed with photoconversion of FAL and HMF. Besides, the tandem photoreduction and oxidation of FAL can yield tetrahydrofurfuryl alcohol (THFA) and γ-butyrolactone (GBL).³⁴ Photooxidative decarboxylation of FAL can be also realized by photocatalysis to form 5-hydroxy-2(5H)-furanone (HFO) , 35 maleic anhydride (MAN),³⁶ succinic anhydride (SAN), maleic acid (MA) ,³⁷ and other value-added products. Photocatalytic oxidative ring-opening can further obtain fumaric semialdehyde (FSA),³⁸ cis-β-formylacrylic acid (β-FAA), and (Z)-5hydroxy-4-keto-2-pentenoic acid (HKPA)³⁹ from furfural and its derivatives. The application values of these unconventional products are introduced in detail towards the end of this review.

In this review article, the recent advances in photocatalytic conversion of furfural and its derivatives into value-added products are summarized. To date, photooxidation of HMF to DFF has been extensively studied. But unsatisfactory selectivity of DFF is often observed due to an over-oxidation of the intermediates resulting from the formation of highly reactive substances. Hence the strategies and methods for improving the catalytic activity and selectivity are discussed. Moreover, the efforts on switching the oxidizing product from DFF to FDCA are summarized. In addition, bifunctional catalysts for simultaneous oxidation and H_2 evolution of HMF and FAL or reduction of $CO₂$ are also reviewed. This transformation has a very high atomic economy in line with the principles of green chemistry. Finally, some nontraditional reaction paths are introduced, such as reductive coupling, oxidative decarboxylation and ring-opening. Without exception these routes show higher selectivity and greater application value. Therefore, this large number of research topics indicates that the photocatalytic conversion of furfural and its derivatives has a broad prospect.

2. Photocatalytic oxidation of HMF to DFF

2.1. $TiO₂$ -based photocatalytic materials

 $TiO₂$ was first reported for the electrochemical photolysis of water among various semiconductor materials used as oxidation photocatalysts, starting a new era of photocatalysis.⁴⁰ $TiO₂$ has been regarded as the most reliable photocatalyst owing to its low cost, chemical inertness, high photoactivity

and stability. Given the strong oxidizing power, $TiO₂$ can easily lead to the direct degradation of organic compounds. Nevertheless, the wide band gap (ca. 3.2 eV) of $TiO₂$ results in its intrinsic photoresponse being limited only to the UV light region. Therefore, many studies have been devoted to improving the product selectivity and visible-light response of $TiO₂$ based photocatalysts.

As summarized in Table 1, Yurdaka et al. successfully prepared amorphous $TiO₂$ with different crystalline shapes and firstly explored their performances for the photocatalytic selective oxidation of HMF to DFF.¹⁹ The partial oxidizing ability of $TiO₂$ photocatalyst was found to originate from its low crystallinity. The authors considered h^+ or $\dot{O}H$ radicals as the active species for this selective oxidation reaction. Ulyankina et al. prepared lowly crystallized $TiO₂$ nanoparticles by electrochemical synthesis, which exhibited 33% selectivity of DFF in the presence of methanol. 41 The value was found to be higher than previously prepared $TiO₂$ catalysts by micro-emulsion and sol–gel methods. Interestingly, an increase in selectivity was observed during the recycling experiments due to the decreased TiO₂ crystallinity. Hence this feature of TiO₂ was further demonstrated to be beneficial for the enhancement of photocatalytic selectivity. Krivtsov et al. used non-metal doping with N into TiO₂, which altered the surface chemistry of TiO₂ and reduced the amount of OH groups on TiO₂ surface.⁴² Unlike Yurdaka, Krivtsov believed that 'OH radicals were nonselective. The N-doping can significantly diminish the surface OH groups, which enabled effective hindering of the generation of 'OH species. Thus this promoted selective photooxidation of HMF to DFF. Allegri et al. also thought that h^+ and 'OH were responsible for the decomposition (i.e., complete oxidation) of HMF and products to $CO₂$ and $H₂O$, whereas the photogenerated e⁻ and/or superoxide radicals $({^0O_2}^-)$ were the main species responsible for the selective conversion of HMF to HMFCA and DFF.⁴³ However, surface hydroxylation of TiO₂ is not the only way to generate 'OH radicals. Khan et al. investigated the ligand–metal charge transfer-mediated selective oxidation of HMF to DFF over a $TiO₂$ photocatalyst (SGH-TiO₂) under visible light. The selectivity of DFF reached as high as 87% at 59% conversion of HMF.⁴⁴ To demonstrate the important role played by OH groups in photocatalysis, $SGH-TiO₂$ was chemically modified by surface fluorination followed by calcination to remove the surface OH groups, and the photocatalytic activity was completely blocked. Therefore, the Green Chemistry

formed with photoconversion of FAL and HMF. Besides, the and stability. Given the strong orditing power, 110, can casif

internet photometrical reading the and τ -buttprolatence (GBL)³⁴ Reverticless,

Table 1 Photocatalytic oxidation of HMF to DFF over TiO₂-based photocatalytic materials

Entry	Catalyst	Solvent	Reaction conditions	Conv. $(%$	Select. $(\%)$	Ref.
	TiO ₂	H ₂ O	Near-UV radiation, $O2$	20	$21 - 25$	19
2	Nano-Ti $O2$	H_2O	Spotlight source (Hamamatsu, LC8) 365 nm (3.0 mW) cm^{-2}), O ₂ (3 mL min ⁻¹), 50 mM methanol	15	33	41
3	N-TiO ₂ treated at 400 $^{\circ}$ C	H ₂ O	500 W lamp with emission maximum at 365 nm, O_2		$30 - 40$	42
4	Au_3Cu_1/TiO_2 -m SFD	H ₂ O	Simulated solar light, 1 atm O_2 , 1 h, 30 °C		67	43
5	SGH-TiO ₂	CH ₃ CN	visible light (λ = 515 nm), O ₂ , 4 h	59	87	44
6	$(Cu_2O)_{0.16}$ TiO ₂ (A)	H ₂ O	Xe lamp, 350–780 nm, 90 min, 35 °C	52	44	45
	$TiO2(\partial MOF)$	CH ₃ CN	300 W Xe lamp, 4 °C, 5 h	94	73	46

surface hydroxyl groups of $TiO₂$ played an important role in bonding the substrate and realizing the visible-light response. Similarly, Zhang et al. modified $TiO₂$ with a visible-lightresponsive p-type semiconductor (*i.e.*, Cu₂O).⁴⁵ The obtained $Cu₂O$ ||TiO₂ heterojunction photocatalyst achieved 52% conversion of HMF and over 44% selectivity of DFF in water. This may be the highest yield of DFF reported to date among $TiO₂$ based catalysts in aqueous phase. In addition, the authors confirmed by free-radical scavenger experiments that in situ-generated ${{}^{\cdot} {\rm O}_2}^{-}$ and singlet oxygen $({}^1 {\rm O}_2)$ were the main active species for the selective photooxidation of HMF to DFF. As proposed in the reaction mechanism (Fig. 3), the formation of the p–n heterojunction can effectively coordinate the energy band positions and promote the separation of photogenerated e[−] and h^+ . As a result, the e^- and h^+ enrich in the conduction band of $TiO₂$ and the valence band of Cu₂O, respectively. As is known to all, the energy band position of a semiconductor is closely related to its redox capacity. Therefore, e[−] in the conduction band of TiO₂ can effectively activate oxygen to generate $^{\cdot} \mathrm{O_2}^{\cdot}$ which is then oxidized by h^+ in the valence band of Cu₂O to generate the final reactive ${}^1\mathrm{O}_2$ species, to realize the selective oxidation of HMF. Zhou et al. prepared a porous $TiO₂(\partial UIO-67-Zr/Ti$ composite as photocatalyst by using microwave-assisted synthesis followed by metal exchange.⁴⁶ The strong interactions between $TiO₂$ and Zr/Ti-MOF material improved not only the transfer of photogenerated e^- and h^+ but also the light absorption range. 94% conversion of HMF and 73% selectivity of DFF were obtained in acetonitrile. Critical Review

Streets Creen Chemistry

where a simple and inportant role in only used sunlight more effectively but also displayed higher

lineuiling the advantar and noticing the shield is terminal scheme. Selectively

2.2. $g - C_3N_4$ -based photocatalytic materials

Graphitized carbonitride $(g-C_3N_4)$ is an organic-polymer semiconductor with rich surface properties, good thermal stability, chemical stability, and particularly narrow band-gap width compared with TiO₂. Therefore, $g - C_3N_4$ has been viewed as a promising visible-light-responsive photocatalyst. As listed in Table 2, Krivtsov et al. firstly investigated different precursors to synthesize $g - C_3N_4$ as photocatalyst.⁴⁷ These catalysts not

only used sunlight more effectively but also displayed higher selectivity. Among them, MCN-540 $(i.e.,$ melamine as precursor calcined in air at 540 °C) showed the optimal photoactivity. The conversion of HMF reached 69% with 43% selectivity of DFF after 4 h of reaction.

Following that, additional treatment of $g - C_3N_4$ becomes a feasible way to improve its catalytic performance. Ilkaeva et al. prepared a PCN-H₂O₂ catalyst by treating $g-C_3N_4$ with H₂O₂.⁴⁸ The bonding of H_2O_2 suppressed the formation of nonselective OH radicals and further promoted the selectivity of DFF. Akhundi et al. modified $g - C_3N_4$ by two effective methods, i.e., $HNO₃$ ultrasonication and thermal stripping.⁴⁹ A higher yield was obtained for US-CHNO₃ catalyst compared with the thermal stripping. Moreover, US-CHNO₃ can expand the specific surface area of original $g - C_3N_4$ and increase the DFF yield. Wu et al. found water treatment of the calcined $g - C_3N_4$ can enlarge the specific surface area and pore volume, thus affecting the pristine photochemical property.⁵⁰ Compared with the common $g - C_3N_4$, the modified catalyst presented lower e[−]–h⁺ recombination rate and better photocatalytic activity. Furthermore, García-López et al. loaded metalloporphyrins on $g - C_3N_4$ and obviously boosted absorption capacity of the photocatalyst upon visible light at higher wavelengths.⁵¹ Porphyrin molecules were found to benefit ${}^{1}O_{2}$ generation and simultaneously inhibit 'OH formation.

In order to promote the separation of photogenerated e[−] and h^+ , modification of g-C₃N₄ by introducing acceptors of e[−] and h^+ are shown to be an effective strategy. Wang *et al.* synthesized a single-atom Cu/p-CNS catalyst by incorporating Cu as e[−] acceptor and S as h⁺ acceptor into g-C₃N₄. Cu-N₄ and C– S–C dual atomic active sites were decorated on polymeric carbon nitride (Cu SAs/p-CNS). Cu and S diatomic sites cooperated to improve the separation of photogenerated carriers, thus enhancing photocatalytic activity.⁵² In the same way, Qian *et al.* prepared a CN-WO₃@MnO₂ photocatalyst.⁵³ $WO₃$ as electron transport channel and $MnO₂$ as photoelectron acceptor can together strengthen the separation and transfer

Fig. 3 Schematic illustration of energy band and charge transfer process of the Z-scheme (Cu₂O)_{0.16}∥TiO₂(A) photocatalyst. Reproduced from ref. 45, with permission of Elsevier, Copyright 2023.

Table 2 Photocatalytic oxidation of HMF to DFF over $g - C_3N_4$ -based photocatalytic materials

Entry	Catalyst	Solvent	Reaction conditions	Conv. $(\%)$	Select. $(\%)$
$1\,$	MCN-540	H_2O	UV lamp, O_2 , 4 h	69	43
$\boldsymbol{2}$	$PCN-H2O2$ (TEO)	H_2O	UV light/natural solar irradiation, O_2 , ~4 h	21/37	71/83
3	$US-CHNO3$	H_2O	UV irradiation/natural solar light irradiation, O_2 , natural pH, 4 h	27/80	32/22
$\overline{\mathbf{4}}$	Metal-free $g - C_3N_4$	$CH3CN + PhCF3$	Xenon lamp (300 W, λ > 400 nm), 10 mL min ⁻¹ O ₂ , 6 h	31	86
5	$\text{ZnPp-C}_3\text{N}_4\text{-TE}$	H_2O	Natural solar light, natural pH, 4 h, 25 °C, 1 atm	73	36
6	Cu SAs/p-CNS	CH ₃ CN	20 W blue LED (λ = 455 ± 10 nm), O ₂ bubbling, 25 °C	77	86
$\overline{7}$	$CN-WO_3$ (a) MnO_2	CH ₃ CN	420 nm LED light (10 W), 24 h	78	80
$\, 8$	$Ti_3C_2/g-C_3N_4$	PhCF ₃	Visible light, O_2 , 10 h	93	97
9	$WO_3/g-C_3N_4$	$CH3CN + PhCF3$	λ > 400 nm, 10 mL min ⁻¹ O ₂ , 6 h, 30 °C	28	87
10	$12\%Bi_2WO_6/mpg$ -C ₃ N ₄	$CH3CN + PhCF3$	λ > 400 nm, 10 mL min ⁻¹ O ₂ , 6 h 300 W Xe lamp (AM 1.5G), 1 atm O ₂ , 6 h	59	84
11 12	$Nb2O5/g-C3N4$ Ni/ACN	$CH3CN + PhCF3$ CH ₃ CN	λ = 390 nm, 25 °C, 1 atm N ₂ , 12 h	53 85	99 97
13	Polyimide M_1P_2	CH ₃ CN	405 nm LED lamp (24 W), 1 atm air, 40 min	61	91
		${10}_2$			
	$E(eV)$ vs. NHE (V) -0.88 CB Visible light 1.82 2.0	CN $HMF/DFF = 1.61$ DFF/oxidized DFF = 2.03 V	$g-C_3N_4 \xrightarrow{\text{light}} g-C_3N_4(h^+,e^-)$	$Ti_3C_2T_X(X=O,F)$	

Fig. 4 Illustration of the mechanism for selective photooxidation of HMF into DFF over the Ti₃C₂/g-C₃N₄ catalyst under visible light irradiation. Reproduced from ref. 23, with permission of Elsevier, Copyright 2020.

of photogenerated e^- and h^+ . As illustrated in Fig. 4, such an effect was greatly boosted by Wang et al. on a Ti₃C₂/g-C₃N₄ photocatalyst by taking advantage of the strong interaction between Ti_3C_2 and g- C_3N_4 . 97% selectivity of DFF at 93% conversion of HMF was attained in trichlorotoluene medium.²³ This is the best result among $g - C_3N_4$ -based photocatalysts in the literature to date.

Alternatively, constructing heterojuction structures on $g - C_3N_4$ can be very useful to facilitate charge separation. For instance, Zhang and Cheng, respectively, combined $WO₃$ and $Bi₂WO₆$ with $g-C₃N₄$ to prepare Z-type $WO₃/g-C₃N₄$ and $Bi₂WO₆/g-C₃N₄$ heterojunction.^{54,55} Li *et al.* integrated Nb₂O₅ to g-C₃N₄ to obtain II-type Nb₂O₅/g-C₃N₄ heterojunction.⁵⁶ The experimental results showed an improved separation efficiency of photogenerated e^- and h^+ due to the existence of the builtin electric field in the heterojunction, thus boosting photocatalytic reaction performance. In addition, the energy band structure can be adjusted by the formation of the heterojunction. When the valence band position is lower than the redox potential of 'OH radicals, the nonselective 'OH cannot be produced. In light of this idea, Liang et al. adapted the band structure by coupling Ni with $g - C_3N_4$ to create a Schottky junction.⁵⁷ Chu et al. modulated the energy band position of polyimide photocatalysts by polymerizing $g - C_3N_4$ with different molar ratios of anhydride.⁵⁸ Both approaches successfully improved the selective photocatalytic conversion of HMF to DFF.

2.3. Metal sulfide-based photocatalytic materials

Metal sulfide semiconductors (mainly CdS and ZnIn_2S_4) have excellent properties such as narrow band gap (ca. 2.4 eV) and wide photoresponse range, and are very suitable catalysts for visible light-driven photocatalytic reactions. However, the high recombination rate of e^- –h⁺ pairs and sensitivity to photocorrosion limit the further application and development of metal sulfides. Thereby various solutions have been proposed to overcome these issues (Table 3). Han et al. modified ultrathin CdS nanosheets with nickel as h^+ acceptor for the first time and achieved photocatalytic oxidation of HMF to DFF under visible light irradiation.⁵⁹ 100% selectivity of DFF was obtained at 20% conversion of HMF. In order to further ameliorate the catalytic activity, Xia and Yuan combined Ru and chitosanderived biochar as e[−] acceptors with CdS quantum dots to synthesize RuCdS and CdSQDs/Ch catalysts, respectively.^{60,61} Due to the effective separation of photogenerated e^- and h^+ , both catalysts can reach over 90% selectivity of DFF in organic sol-

Table 3 Photocatalytic oxidation of HMF to DFF over sulfide-based photocatalytic materials

Entry	Catalyst	Solvent	Reaction conditions	Conv. $(\%)$	Select. $(\%)$	Ref.
$\mathbf{1}$	Ni/CdS	H ₂ O	Blue LED (440-460 nm, 8 W), 10 mM HMF, N ₂ , 22 h	20	100	59
$\boldsymbol{2}$	Ru CdS	DMF	300 W xenon lamp 100 mW cm ⁻² , 16 h	81	92	60
3	CdS QDs/Ch	CH ₃ CN	100 mW cm ⁻² , 25 [°] °C, O ₂ , 10 h	79	97	61
$\overline{4}$	Nitrate-mediated CdS	$CH_3CN/Mn(NO_3)_2$	Blue LED light (447.5 nm, 170 mW cm ⁻²), O_2	$\overline{}$	>99	62
5	$\text{Cd}_x\text{InyS}_{(x+1.5y)}$	H_2O	λ > 420 nm, 20 °C, 6 h	69	63	63
6	$MoS_2/CdIn_2S_4$	H_2O	7 W COB LED lamp (>420 nm). 10 h	62	81	64
$\overline{7}$	$Ti_3C_2F_x$ MXene/CdIn ₂ S ₄	H_2O	λ > 400 nm, 20 °C, 12 h	79	60	65
8	$(110)/(102)$ -ZnIn ₂ S ₄	CH ₃ CN	Simulated solar light irradiation, O_2 , 1 h	91	99	25
9	ZnIn_2S_4 2D	CH ₃ CN	Blue LED, 15 \degree C, air, 2 h	95	70	66
	$ZnIn_2S_4$ -TU	H_2O	$\lambda = 445$ nm, 6 W, 9 h	60	66	67
10						
11	$CC/ZnIn_2S_4$	CH ₃ CN	400-780 nm, air, 4 h	22	69	68
12	SA-PDI/ZnIn ₂ S ₄ vents. DiMeglio et al. directly introduced $NO3-$ into a CdS cata- lytic system to act as a redox mediator in the solution. ⁶²	CH ₃ CN	300 W xenon lamp, O ₂ , 0.5 h photogenerated carriers. Likewise, Zhu and Zhang com- pounded MoS and $Ti_3C_2F_x$ with CdIn ₂ S ₄ , respectively, to obtain	98	90	
	Nitrate-mediated alcohol oxidation proceeded through a mechanism involving the catalytic generation of ' $NO3$ ⁻ rad- icals, which enabled the photooxidation of HMF to DFF with >99% selectivity.		the corresponding heterojunctions. ^{64,65} Compared with the pristine CdIn ₂ S ₄ , the yields of DFF over MoS/CdIn ₂ S ₄ and $Ti_3C_2F_x/CdIn_2S_4$ photocatalysts were increased by 20% and 30%, respectively.			
	In addition to binary metal sulfides, ternary metal sulfides		However, Cd is widely criticized in ecology because of its			69
	have been also studied extensively. Zhang et al. used a one-		high toxicity to kidneys, lungs and bones. Because of the bio-			
	step hydrothermal method to controllably synthesize a		logical and environmental toxicity of Cd, Zhao et al. prepared			
	$Cd_xIn_yS_{(x+1.5y)}$ catalyst. ⁶³ When the Cd : In ratio exceeded 1:2,		Cd-free $(110)/(102)$ -ZnIn ₂ S ₄ nanosheets by crystal-face engin-			
	the catalyst displayed a 1D to 3D heterojunction structure com-		eering strategy. ²⁵ As shown in Fig. 5 for the reaction mecha-			
	posed of CdS nanorods and cubic CdIn ₂ S ₄ . This unique struc-		nism, ESR characterization and scavengers experiment can			
	ture effectively promoted the separation of photoexcited e^- -h ⁺ pairs in $Cd_xIn_yS_{(x+1.5y)}$ and realized the cross-border transfer of		verify the formation of O_2^- , 1O_2 and 'OH species during the photoreaction and clarify the different roles they play in cata-			

Fig. 5 EPR signals of the reaction solution in the dark and simulated solar light irradiation with different time in the presence of DMPO and TMP as spin-trapping reagents for (a) O_2 , (b) 1O_2 and (c) OH. (d) Effect of different scavengers on HMF conversion and DFF selectivity. (e) Proposed photocatalytic mechanism for HMF conversion to DFF over the ZnIn₂S₄ catalyst. Reproduced from ref. 25, with permission of Royal Society of Chemistry, Copyright 2022.

lytic activity. 99% selectivity of DFF at 91% conversion of HMF is reported in O_2 and acetonitrile, being the best result in the literature to date. By introducing $Na₂S$, it can be found that the spontaneous replacement of O^{2-} by S^{2-} for photocatalytic regeneration can significantly improve the durability of ZnIn₂S₄. Following that, Ding et al. obtained 2D ZnIn₂S₄ nanosheets by adding an appropriate amount of sodium citrate during synthesis.⁶⁶ This photocatalyst reached 95% conversion of HMF after only 2 h of blue LED irradiation. It was verified that the formation of 'HMF radicals via oxidation at photogenerated h^+ and the subsequent deprotonation of 'HMF with ${}^{1}O_{2}$ were the key to selectively oxidizing HMF to DFF. Pham et al. treated $ZnIn₂S₄$ nanoparticles by changing different sulfur sources such as thioacetamide or thiourea.⁶⁷ It was disclosed that the latter can induce a greater number of Zn vacancies. This method effectively adjusted the band gap and promoted the separation of charge pairs, thereby improving the photocatalytic efficiency.

To further ameliorate the synthetic method, Qiu et al. combined cellulose-derived carbon dots with ZnIn_2S_4 .⁶⁸ It was disclosed that the added carbon dots can enhance the absorption of visible light, thus freely shuttling electrons to the carbon dots and improving e^- –h⁺ pairs separation. The obtained CC/ ZnIn_2S_4 photocatalyst showed an outstanding performance with a yield of DFF ca. 3.4 fold over the original ZnIn_2S_4 . Similarly, Guo et al. integrated perylene imide supramolecular molecules as $\rm e^-$ acceptors to ZnIn $\rm _2S_4.^{69}$ On the SA-PDI/ZnIn $\rm _2S_4$ catalyst, the functionalized supramolecular served as active sites, which greatly accelerated the generation of $^{\cdot}O_{2}^{-}$ radicals by absorbing O_2 and concentrated the photogenerated e[−] on $ZnIn_2S_4$. Notably, the formation rate of DFF reached 1952 µmol g^{-1} h⁻¹, which was nearly an order of magnitude higher than the previously reported photocatalytic technology. The yield of DFF after 0.5 h of illumination was 9.4 times higher than that of the bare $ZnIn_2S_4$.

2.4. Other photocatalytic materials

Some other semiconductor-based catalysts have also been reported for the photocatalytic selective oxidation of HMF to DFF (Table 4). Zhang *et al.* prepared a $Nb₂O₅$ by calcining at as high as 800 °C and applied it to the oxidation of HMF under visible light. 70 It was found for the first time that the OH group of HMF could be adsorbed on $Nb₂O₅$ to form an alcoholized substance, lowering the band-gap energy of $Nb₂O₅$ to

respond to visible light. This phenomenon can be explained by the ligand–metal charge transfer (LMCT) effect. Although 91% selectivity of DFF was obtained, the conversion of HMF was of only 19%. To improve the photoactivity, Zou et al. introduced Ce during catalyst preparation to enrich oxygen vacancy on the $Nb₂O₅$ surface, as illustrated in Fig. 6.⁷¹ This is believed to enhance the LMCT effect between HMF and the catalyst under visible light. However, the nonselective generation of $H₂O₂$ can easily occur in the aqueous phase, resulting in overoxidation of the produced DFF. Thereby Pt nanoparticles are deposited on Ce-Nb₂O₅ to inhibit the accumulation of H_2O_2 . Eventually the conversion of HMF can be increased to 36% with a superior selectivity (i.e., 93%).

In addition, Bi-based semiconductor materials have received much attention due to their stable crystal structures, excellent photovoltaic properties, and abundant reserves. Kumar et al. prepared and compared $Bi₂WO₆$, BiVO₄ and $Bi₂MoO₆$ photocatalysts.⁷² Among those, the rose-like nanostructured $Bi₂WO₆$ presented higher photocurrent response, efficient charge-carrier separation, and suitable band-edge potential. These features enabled the optimal photocatalytic oxidation activity. Interestingly, BiOBr is composed of alternating $[\text{Bi}_2\text{O}_2]^2$ ⁺ and Br[−] plates, of which oxygen atoms are exposed to the surface and easily produce oxygen vacancies (O_v) . Gong *et al.* obtained a Pt- O_v -BiOBr catalyst by bonding Pt to the BiOBr surface.⁷³ The Pt–O bond acted as electron transport channel to move the photogenerated e[−] from O_v-rich BiOBr to Pt, which efficiently caused generation of $"O_2"$ radicals. Meanwhile the photogenerated $h⁺$ would accumulate at the interface between Pt and O_v -BiOBr to oxidize HMF into HMF radicals. The electron-rich Pt could better adsorb HMF, thus realizing a better contact of ${{}^{\text{+}}\text{O}_2}^{-}$ with reaction intermediates. Ultimately a higher conversion and selectivity were obtained. Green Chemistry

yies activity of Dir at 91% conversion of HMF respond to visible light. This phonomenon can be explained
in coponent in 0, and action in the particle in the statistic of the particle in the particle of th

> In addition, organic–inorganic halide chalcogenide-type materials have been explored owing to their excellent photovoltaic properties. Zhang et al. studied lead halide chalcogenide $(MaPbX_3: Ma = CH_3NH_3^+, X = Br^-, I^-)$ as photocatalyst.⁷⁴ The conversion of HMF in acetonitrile reached 100% and the selectivity of DFF exceeded 90%. However, Pb-based chalcogenides would suffer from severe toxicity and long-term instability. It is well known that Pb can cause serious damage to the neurological, hematopoietic and digestive systems of humans and mammals. In light of that, Yin et al. synthesized

Table 4 Photocatalytic oxidation of HMF to DFF over semiconductor-based photocatalytic materials

Entry	Catalvst	Solvent	Reaction conditions	Conv. $(\%)$	Select. $(\%)$	Ref.
1	Nb_2O_5-800	PhCF ₃	Visible light $(>400 \text{ nm})$, O ₂ , 6 h	19	91	70
2	Pt-Ce-NbO-3	H ₂ O	λ > 420 nm 15 °C, pre-purged with air, 6 h	36	93	71
3	Rose-like Bi_2WO_6	CH ₃ CN	λ > 420 nm, 1 atm air, 10 h	58	99	72
4	$Pt-O_v-BiOBr$	$CH3CN + TFME$	300 W xenon lamp with an AM1.5 filter, O_2 , 3 h	90	78	73
5	MAPbBr ₃	CH ₃ CN	Blue LED light (450 nm), air, 10 h, 15 \degree C	100	90	74
6	Cs_2SnBr_6/rGO	CH ₃ CN	λ = 400 nm, 1 atm O ₂ , 15 °C, 6 h	100	88	75
	$MnO2-NRs$	CH ₃ CN	UV light from LED system (365 nm), O_2 , 4 h, 39 °C	99	100	76
8	$(Cr^{3+}$ or $Co^{3+})$ -NiO	H_2O	λ = 365 nm, 12 h	60	95	77

Fig. 6 Proposed mechanism of photocatalytic selective oxidation of alcohols to aldehydes over the defective $Nb₂O₅$ with deposited Pt nanoparticles. Reproduced from ref. 71, with permission of Elsevier, Copyright 2021.

a stable Pb-free chalcogenide Cs_2SnBr_6 modified with reduced graphene oxide (rGO).⁷⁵ The Cs₂SnBr₆/rGO composite exhibited excellent photocatalytic activity. Almost full conversion of HMF and 88% selectivity of DFF were obtained in acetonitrile.

Interestingly, transition-metal oxides with various valence states have been also investigated. Giannakoudakis et al. prepared $MnO₂$ nanorods (NRS) that allowed reaching almost 100% yield of DFF in acetonitrile under UV irradiation.⁷⁶ The

result is the best reported in the literature to date. As shown in Fig. 7, the charge transfer follows the Mn^{4+}/Mn^{3+} redox cycle with O_2 playing a key role. In the absence of O_2 , the conversion of HMF over MnO_2 -NRS within 6 h is only 21% and the selectivity of DFF is 67%. In this system, the mild heat and light leads to the adsorption of HMF via the C-OH moiety on the O-sites (deprotonated Brønsted sites) of $MnO₂$ -NRS and then it deprotonates twice to form DFF. The formation of water molecules sterically hinders/blocks the catalytic surface-centers by forming hydrogen bonds, which results in activity decrement with time on stream. On the other hand, aprotic and less polar organic solvents (e.g., acetonitrile) can facilitate the rate-determining step by promoting a higher $O₂$ solubility and effective contact of O_2 with the MnO₂-NRS outer surface. Park et al. synthesized NiO nanoparticles bearing different concentrations of O_v by incorporating charge-mismatched $(Cr^{3+}$ or $Co^{3+})$ and charge-matched (Cr^{2+} or Co^{2+}) dopants.⁷⁷ Among these, Cr^{3+} / $Co³⁺$ -doped NiO had the highest amount of O_v and thus attained the best yield of DFF in aqueous phase under UV light.

Other than conventional semiconductors, some polymers are found to have semiconductor-like properties (Table 5). Heterogeneous photocatalytic materials based on conjugated microporous polymers (CMPs) have been reported for organic photoredox reactions. Ayed et al. reported a thiophene-containing covalent triazine backbone (CTF-Th) material for the partial oxidation of HMF to DFF in aqueous phase under visible light.²⁶ Since CTF-Th can be highly dispersed in water during the photocatalytic process, a solid-phase polymerization of CTF-Th@SBA-15 was synthesized, and two possible pathways through O_2 ⁻ or ${}^{1}O_2$ were reported (Fig. 8). Under visible light irradiation, photogenerated e[−] reduce molecular oxygen to active form (O_2^-) , and protons are extracted from HMF (1) to form 1a and highly active 'OOH radicals. The

Fig. 7 Illustrated representation of the light effect and the involved oxidation mechanism of HMF over the MnO₂-NRs photocatalyst. Reproduced from ref. 76, with permission of Elsevier, Copyright 2019.

Table 5 Photocatalytic oxidation of HMF to DFF over other photocatalytic materials

Entry	Catalyst	Solvent	Reaction conditions	Conv. $(\%)$	Select. $(\%)$	Ref.
	CTF -Th $@$ SBA-15	H ₂ O	Blue LED lamp (460 nm, 65 mW cm ⁻²), 1 atm O ₂ , 30 h, 25 °C	57	99	26
2	pTTT-Ben	H ₂ O	LED lamp for 10 h, 30 \degree C	25	100	78
3	TMADT	$CH3CN/6$ M HBr	Visible light, 1 atm O_2 , 12 h, 25-28 °C	83	81	79
4	HBr	DMSO	Visible light, 1 atm O_2 , 8 h, 80 °C	91	89	80
.5	$Au-Ru/rGO$	Toluene	Visible light, 5 bar O_2 , 8 h, 80 °C	96	95	27

Fig. 8 (a) Chemical structure and synthesis routes, (b) SEM and (c) TEM images of CTF-Th@SBA-15, (d) proposed reaction mechanism for the photocatalytic partial oxidation of HMF to DFF using CTF-Th@SBA-15 *via* two possible routes using either 1 O₂ or 'O₂ $^-$. ISC: Inter System Crossing. Reproduced from ref. 26, with permission of John Wiley & Sons, Inc, Copyright 2020.

alkoxy anion 1a formed by deprotonation of HMF can react with h^+ through electron transfer to form the corresponding alkoxy radical 1b. Then it reacts with **OOH** to release H_2O_2 and DFF (2). The ${}^{1}O_{2}$ produced by intersystem crossover (ISC) can be inserted into the C–H bond of the alcohol functional group of HMF (1) to form (3). The intermediate can be formed by independent photolysis to form (4), and then further decomposed into the final product DFF (2) and H_2O_2 byproduct. This catalyst showed a good performance under ambient conditions. >99% selectivity of DFF at 57% conversion of HMF was obtained after 30 h under visible light. Independently, Chen et al. synthesized three CMPs consecutively by C–H direct arylation polymerization using 2,4,6-(tris-2-thienyl)-1,3,5-triazine as a junction and different benzene derivatives as connectors.⁷⁸ Therein the benzene-conjugated pTTT-Ben catalyst displayed a unique nanofibrous morphology, relatively wide band gap, and strong charge separation. Hence it showed the best photocatalytic performance in the selective oxidation reaction of HMF.

Different to CMPs, a simple and effective visible-light photocatalytic system using DT (deuterated tungstate)-HBrbased materials was reported by Yang et al. In the presence of acetonitrile and a concentrated HBr (6 mol L^{-1}), conversion of

HMF and selectivity of DFF could both reach ca. 82% after 12 h of photoexposure.⁷⁹ It was demonstrated that HBr enabled effective utilization of water as an oxygen source for the oxidation reaction. Interestingly, a further study by Hu et al. confirmed that the cheap HBr acid could even catalyze this reaction under visible light in O_2 and water.⁸⁰ However, a higher temperature (80 °C) was required. 91% conversion of HMF and 89% selectivity of DFF were obtained in DMSO.

Ma et al. reported bimetallic AuRu nanoparticles on rGO as efficient photocatalyst for the partial oxidation of HMF to DFF in toluene. 27 The synergistic interaction between the dual metal sites was demonstrated to promote photocatalytic activity upon visible light and even sunlight. Both conversion and selectivity could reach ca. 95%.

3. Combination of photocatalytic oxidation with H_2 evolution or $CO₂$ reduction

3.1. Photocatalytic oxidation of FOL combined with H_2 evolution

The previous photocatalytic systems driven by solar energy basically use O_2 as oxidant to partially oxidize HMF to DFF.

Table 6 Photocatalytic oxidation of FOL to FAL combined with H_2 evolution

					View Article Online	
	Critical Review		Table 6 Photocatalytic oxidation of FOL to FAL combined with H_2 evolution		Green Chemistry	
Entry	Catalyst	Solvent	Reaction conditions	HER (µmol $h^{-1} g^{-1}$)	FAL (µmol $h^{-1} g^{-1}$)	Ref.
$\mathbf{1}$	Ni/CdS ^a	H_2O	Blue LED (440-460 nm, 8 W), 10 mM FOL, N ₂ , 22 h			59
$\,2$	1 wt% $Ru/Zn_{0.5}Cd_{0.5}S$	H_2O	300 W Xe lamp with a UV cutoff filter	870	855	81
3	$Ru-RuO_x/C_3N_4$	H_2O	300 W Xe-lamp, Ar	4240	4500	82
$\overline{4}$	$Ni-Au/CN^b$	H_2O	Xe lamp (200 mW cm ⁻²) for 5 h, 1 atm Ar, 8 °C	471		83
5	$MO_2C@ZnIn_2S_4$	H_2O	300 W Xenon lamp (420 nm), 10 °C, 4 h	2800	11 3 3 0	84
6	$\text{ReS}_2/\text{ZnIn}_2\text{S}_4\text{-S}_v$	H_2O	Xenon lamp (250 mW cm ⁻²), 15 °C, remove air	1080	710	85
$\overline{7}$ 8	LaVO ₄ /g-C ₃ N ₄	H_2O	Xenon lamp (250 mW cm ⁻²), remove air, 15 °C	287	950	86
	$\text{ZnIn}_2\text{S}_4/\text{Tp-Tta COF}$	H_2O	LED (420 nm, 80 W), 3 h, 1 atm N_2	9730	12 100	32
			poor selectivity and low atomic economy. In contrast, photo- catalytic anaerobic oxidation of FOL or HMF combined with $H2$ evolution can be a desirable route. This strategy allows the use of photogenerated h^+ to oxidize furfuryl compounds and to reduce protons by photogenerated e^- for H ₂ formation. Particularly, FOL without C=O group (vs. HMF) combined	$g-C_3N_4$ photocatalyst reached 3 fold over Au/g-C ₃ N ₄ . In addition to using metal as co-catalyst, Yang et al. employed $Mo2C$ as co-catalyst to accept photogenerated e^- and the reac- tion sites of H ₂ evolution. ⁸⁴ The Mo ₂ C@ZnIn ₂ S ₄ catalyst showed a high formation rate of H ₂ (2800 µmol h^{-1} g ⁻¹) and FAL (11 330 µmol h^{-1} g^{-1}). The performance was much better		
			with H_2 evolution can even bring higher efficiencies for H_2 for-	than those over ZnIn_2S_4 and $\text{Pt/ZnIn}_2\text{S}_4$.		
			mation and selective oxidation. Thus a closed loop is estab-	Besides, the preparation of heterojunctions is also a good		
			lished with high atomic economy. The absence of $O2$ basically	way to develop bifunctional catalysts. Hu et al. designed a new		
			excludes the formation of over-oxidation byproducts, which is	type $3D/3D$ ReS ₂ /ZnIn ₂ S ₄ -S _v heterojunction presenting a		
	beneficial for improving product selectivity.			bifunctional cellular layered structure. ⁸⁵ ReS_2 and S vacancies		
			For instance (Table 6), the Ni/CdS catalyst can only convert	(S_v) increased the specific surface area, accelerated the charge		
			20% HMF to DFF under N_2 and blue LED light, but it can	separation and inhibited the recombination of carriers. Such		
			completely convert FOL to FAL under exactly the same con-	features benefited the photocatalytic reaction. In another case,		
			ditions. ⁵⁹ Combining semiconductor with cocatalyst, Yang	the 2D/2D LaVO ₄ /g-C ₃ N ₄ heterostructure prepared by Li et al.		
			et al. successfully prepared Ru-decorated $\text{Zn}_{0.5}\text{Cd}_{0.5}\text{S}$ nanorods by a photodeposition method. ⁸¹ The photocatalytic formation	also showed a good photocatalytic activity. ⁸⁶ The production rate of H_2 and FAL were 3 times higher than that of the orig-		

For instance (Table 6), the Ni/CdS catalyst can only convert 20% HMF to DFF under N_2 and blue LED light, but it can completely convert FOL to FAL under exactly the same conditions.59 Combining semiconductor with cocatalyst, Yang *et al.* successfully prepared Ru-decorated $\text{Zn}_{0.5}\text{Cd}_{0.5}\text{S}$ nanorods by a photodeposition method.⁸¹ The photocatalytic formation rate of H_2 and FAL were 870 and 855 µmol h^{-1} g^{-1} , respectively. The enhanced performance can be attributed to the efficient separation and transport of photogenerated e[−] and h⁺ promoted by the strong interaction between Ru cocatalyst and $\text{Zn}_{0.5}\text{Cd}_{0.5}\text{S}$ semiconductor. In addition, a superior adsorption of Ru atoms toward the OH group in FOL accelerated the selective oxidation. After that, Liu et al. found that the amorphous Ru–RuO_x hybrid structure had ultrafast h⁺ trapping ability compared with Ru atoms.⁸² Due to the abundant atomic interface, amorphous RuO_x sites can inherently capture h⁺ within only 100 fs and promote the subsequent electron transfer (ca. 1.73 ps). As a result, this $Ru-RuO_x$ catalyst triggered a longlived state of charge separation, eventually increasing the H_2 evolution rate to 4240 µmol h^{-1} g^{-1} . Apart from monometal modification, a bimetallic Ni–Au modified $g - C_3N_4$ photocatalyst was synthesized by a step-by-step photodeposition method.⁸³ g-C₃N₄ was the main light-trapping material for generating e^- –h⁺ pairs. The localized surface plasmon resonance effect can be generated when Au nanoparticles are in a specific size range, which broadens the optical absorption region to generate more charge carriers. Hence the plasma Au nanoparticles further improved the efficiency of light utilization over the catalyst. Ni was not only the e[−] trap but also the active

Besides, the preparation of heterojunctions is also a good way to develop bifunctional catalysts. Hu et al. designed a new type $3D/3D$ ReS₂/ZnIn₂S₄-S_v heterojunction presenting a bifunctional cellular layered structure.⁸⁵ ReS₂ and S vacancies (S_v) increased the specific surface area, accelerated the charge separation and inhibited the recombination of carriers. Such features benefited the photocatalytic reaction. In another case, the 2D/2D LaVO₄/g-C₃N₄ heterostructure prepared by Li et al. also showed a good photocatalytic activity.⁸⁶ The production rate of $H₂$ and FAL were 3 times higher than that of the original g- C_3N_4 . In order to further improve the catalytic efficiency, a S-type $\text{Znln}_2\text{S}_4/\text{Tp-Tta COF}$ (i.e., the organic 1,3,5-triformylphloroglucinol-4,4′,4″-(1,3,5-triazine-2,4,6-triyl)trianiline covalent organic framework) heterojunction was synthesized by Sun et al. using an in situ synthetic strategy. 32 As shown in Fig. 9, the layered sandwich structure of the catalyst can expand the interfacial charge transfer and promote the multiple scattering of incident light. Besides, there is huge internal electric field and low charge transfer resistance in S-type heterojunctions. This can significantly facilitate the separation and transfer of photogenerated charges. Therefore, the overall redox performance of this photocatalytic system is greatly improved. The evolution rate of H₂ and FAL reach 9730 and 12 100 µmol h^{-1} g^{-1} , respectively, the highest values reported in the literature to date.

3.2. Photocatalytic oxidation of HMF combined with H_2 evolution

As summarized in Table 7, Han et al. reported for the first time that Ni/CdS enabled selective oxidation of HMF to DFF under N_2 atmosphere and visible light irradiation, while H_2 formation was realized.⁵⁹ This idea of combining semiconductor with cocatalyst aroused great interest for sub-

Fig. 9 A possible mechanism of photocatalytic H₂ release and FOL oxidation on the ZnIn₂S₄/Tp-Tta COF system. Reproduced from ref. 32, with permission of Royal Society of Chemistry, Copyright 2022.

Table 7 Photocatalytic oxidation of HMF to DFF combined with H_2 evolution

H₂ evolution rate (HER in μmol h^{−1} g^{−1}), conversion of HMF and selectivity of DFF are used to evaluate the catalytic performances. ^a Presented in µmol h^{-1} m⁻². ^{*b*} Obtained in CH₃OH solvent. ^{*c*} The blank test without HMF.

sequent works. For instance, Pt/SGCN, Pt/CdS and Pt/Ti-MOF photocatalysts were successfully prepared by loading Pt as cocatalyst onto semiconductor carriers.29,87,88 As illustrated for Pt/CdS (Fig. 10), the formation of the Pt–CdS interface leads to e[−] transfer from semiconductor to Pt, due to the low work function of Pt nanoparticles. Therefore, HMF can be adsorbed on positively charged CdS through OH groups, while the furan ring of HMF can be adsorbed on the surface of Pt due to the strong interaction between Pt and π bonds in HMF. Under irradiation e^- and h^+ are generated on CdS semiconductor, and e[−] are moved to Pt. The adsorbed OH groups of HMF can be attacked by h^+ in CdS, resulting in proton dissociation to form alkoxide radicals which further react with another $h⁺$ to produce the desired DFF. At the same time, protons released from HMF are transferred to nearby Pt nanoparticles, where these protons can be reduced by e^- to generate H₂. Therefore,

the semiconductor-supported Pt achieves effective H_2 evolution and selective formation of DFF (>99%, in select.) from HMF oxidation. Therein the Pt/CdS photocatalyst shows the highest conversion of 100% in the literature to date. Apart from semiconductors, Pt can be also loaded on donor–acceptor polymer, e.g., CMP-Tz (conjugated microporous polymers with triazine group as the central aryl unit). 89 In the presence of ascorbic acid as a sacrificial agent, the Pt-CMP-Tz photocatalyst presented the highest H_2 formation rate at 3207 µmol g⁻¹ h⁻¹. HMF, instead of ascorbic acid, can be also converted to DFF with a high selectivity.

In addition to Pt as cocatalyst, inexpensive nickel compounds (*i.e.*, NiS₂, NiS and NiSe₂) were coupled as cocatalysts with CdS, $Zn_3In_2S_6$ and $Cd_{0.7}Zn_{0.3}S$ semiconductors, respectively.^{90–92} NiS₂, NiS and NiSe₂ can form Schottky junctions with semiconductors because their metal properties are

Fig. 10 Proposed mechanism for photocatalytic dehydrogenation of HMF under visible light over the Pt/CdS nanocomposite. Reproduced from ref. 29, with permission of Elsevier, Copyright 2022.

similar to those of precious metal Pt. Schottky junctions allow effective promotion of separation and transmission of photoexcited charges. The h^+ in the semiconductor carriers can be captured by HMF to produce DFF and release protons, while the separated e^{-1} can react with protons on the surface of cocatalyst to produce H_2 . Besides, Giannakoudakis et al. confirmed that CuO_x nanoclusters can serve as cocatalyst in a P25-CuO_x (i.e., 2 nm CuO_x dispersed on P25 surface) photocatalytic system.⁹³ Therefore, it is reasonable to conclude that participation of photogenerated e[−] and h⁺ in the reaction is vital for the generation of DFF and H_2 . Hence an efficient separation of e[−] and h⁺ is the critical factor.

Instead of adding cocatalyst, the construction of heterojunctions is a more practical method. Wu et al. prepared a p-n heterojunction photocatalyst with Z-type mechanism by in situ growth of ultrasmall 2D CdS nanowires on the surface of 2D CN nanowires.⁹⁴ This 2D/2D CdS/CN heterojunction exhibited superior photocatalytic behavior for oxidation and reduction. Both HMF conversion and DFF selectivity reached ca. 90% over the 50% CdS/CN composite after 2 h of visible light irradiation. In addition, Dhingra and Wang prepared $Zn_{0.5}Cd_{0.5}S/MnO_2$ and $ZnIn_2S_4/Nb_2O_5$ p-n heterojunctions with Z-type mechanism.^{95,96} Both photocatalysts selectively oxidized HMF to DFF and exhibited H_2 formation rate of ca. 1000 μmol $g^{-1} h^{-1}$.

Alternatively, the separation of photogenerated e^- and h^+ can also be realized by surface modification of the catalyst. Ye et al. prepared a $\text{Zn}_{0.5}\text{Cd}_{0.5}\text{S-P}$ photocatalyst and enriched S vacancies by doping P into $\text{Zn}_x\text{Cd}_{1-x}\text{S}$ solid solution.⁹⁷ Such surface vacancies were beneficial for electron accumulation and substrate adsorption, thus the H_2 evolution rate was eight times higher than that of CdS-P. Zhu et al. treated $ZnIn_2S_4$ nanowires with oxygen plasma for 2 min and obtained a hierarchical porous O-ZIS-120 photocatalyst.³¹ It showed the highest H₂ evolution rate of 1522 µmol h⁻¹ g⁻¹ in the current literature.

3.3. Photo(electro)catalytic oxidation of HMF to valuable chemicals combined with $CO₂$ reduction

The use of fossil fuels has greatly promoted modern industrialization and economic development, but at the same time it has brought about serious environmental problems. It is worth noting that the concentration of $CO₂$ in the atmosphere

exceeds an astonishing value of 400 ppm (*i.e.*, an increase of 120 ppm since the Industrial Revolution), resulting in global warming and a more extreme climate. In this context, the chemical reduction of $CO₂$ with $H₂O$ to value-added compounds (*i.e.*, CO, CH₄, CH₃OH and C₂H₆) by solar-driven semiconductors has been generally considered to be a promising technology to achieve carbon neutrality. However, the slow kinetics of semi-reaction by water oxidation leads to recombination of excited e^- and unused h^+ , resulting in catalytic inefficiency. To solve this problem, a common strategy relies on using sacrificial e^- donors as h^+ cleaners. However, this method wastes the oxidation capacity of h^+ . Instead, using HMF as oxidation reactant and hydrogen donor can obtain value-added compounds and simultaneously improve the performance of $CO₂$ reduction. Critical Review

Critical Review

Published on 17 April 2022. The critical Review of 100 ppm (i.e., an increase of
 $\frac{1}{2}$ Published on 17 April 2022. The critical Review of CO, with Fig. 100

The critical Review of Co

As listed in Table 8, Fan et al. prepared a ZnNiFe-LDH (i.e., anionic compound of layered double hydroxides) catalyst by a coprecipitation method. 33 As shown in Fig. 11, LDHs can store $CO₂$ in the form of $CO₃²⁻$ layers based on the strong affinity of LDHs to CO_3^2 ⁻. In addition, the electron-deficient OH sites near the metal vacancies on the LDH layer contribute to adsorb and activate the OH group in HMF. The proximity of electron-rich $Ni²⁺$ to metal vacancies enables promotion of the activation of interlaminar CO_3^2 ⁻. Therefore, HMF and interlayer CO_3^2 ⁻ can be composed for a redox reaction under light. After reaction, LDHs continually absorb $CO₂$ in the air to supplement the $CO₃²⁻$ consumed during reaction, and then use it in the photocatalytic redox reaction. The cumulative yields of CO and DFF reach 76 and 55 µmol g^{-1} after 4 h, respectively.

Interestingly, Yang et al. used 4-(tert-butyl)-phenoxy-decorated cobalt phthalocyanine (TBP-CoPc) and pyrene-tethered 2,2,6,6-tetramethylpiperidin-1-oxy (Py-TEMPO) as reagents to construct a paired electrolysis system, which was non-covalently fixed on carbon nanotubes. 98 As show in Fig. 12, a photovoltaic cell was used to catalyze the reduction of $CO₂$ to CO and oxidize HMF to FDCA. In dual-electrode mode, the Faraday efficiencies (FE) of CO and FDCA were 97% and 91%, respectively, using a battery voltage at 2.5 V.

Obviously, the combination of photocatalytic HMF oxidation with $CO₂$ reduction is of great significance to achieve carbon neutrality, but electrocatalytic $CO₂$ reduction remains very challenging. Particularly, the thermodynamic stability and kinetic inertia of $CO₂$ would lead to a slow reaction that highly competes with H_2 evolution reaction. Therefore, there are very limited reports and further exploration is highly desired.

In short, the photocatalytic oxidation of furanic compounds (FOL and HMF) combined with H_2 evolution or CO_2 reduction shows a very high atom economy. It is greatly in line with green chemistry. However, the separation of photogenerated e[−] and h^+ is essential for the catalyst to achieve the bi-objective. Thereby the catalyst design is often complicated. In addition, O2 molecules present in the system (an aerobic environment) can easily react with the removed protons from FOL/HMF to inhibit H_2 evolution or CO_2 reduction. Hence the reaction conditions also need to be O_2 -free. Therefore, further optimization of catalyst preparations and mechanistic studies are required.

 a CO evolution rate. b Faraday efficiency.

Fig. 11 Proposed mechanism of the integration of $CO₂$ photoreduction with oxidation of HMF. Reproduced from ref. 33, with permission of Royal Society of Chemistry, Copyright 2023.

Fig. 12 Schematic diagram of sunlight-driven paired electrolysis of the CO₂RR and HMFOR by the TBP-CoPc/Py-TEMPOs photocatalyst. Reproduced from ref. 98, with permission of Royal Society of Chemistry, Copyright 2022.

4. Photocatalytic oxidation of HMF to FDCA, as well as HMFCA and FFCA

4.1. Photocatalytic oxidation of HMF to FDCA

Among various oxidation products from HMF, FDCA is undoubtedly the most valuable one. The symmetrical furan dicarboxylic acid shows very similar properties to petroleumderived terephthalic acid, so it can be used as a substituted monomer for manufacturing renewable bioplastics. Obviously, photocatalytic oxidation of HMF to FDCA requires a stronger oxidation power (vs. DFF formation) of the catalytic system.

But highly reactive oxidizing species can decompose HMF to undesired byproducts $(i.e., CO₂)$. Therefore, developing selective photocatalysts with a suitable energy-band structure is challenging yet important for the photooxidation of HMF to FDCA.

As summarized in Table 9, Xu et al. combined metalloporphyrins with $g - C_3N_4$ to prepare $C_0P_Z/g - C_3N_4$ as an efficient photocatalyst for oxidation of HMF in air under simulated sunlight.²⁰ 97% selectivity of FDCA at 99% conversion of HMF was achieved at 25 °C in alkaline aqueous solution ($pH = 9.18$). This may be the highest activity reported in the literature to date. As shown in Fig. 13, the strong interaction between CoPz and $g - C_3N_4$ not only improves the accessibility of the CoPz site and makes the catalyst recyclable, but also prevents the formation of 'OH radicals by $g-C_3N_4$ and promotes the formation of reactive ${}^{1}O_{2}$ at the CoPz site. These catalytic properties significantly boost the catalytic performance. Zhang et al. reported a visible light-driven Au-Ag/TiO₂ catalytic system in $Na₂CO₃$ solution.⁹⁹ Interestingly, the monometallic Ag nanocatalyst can only afford HMFCA, whereas Au and Au–Ag catalysts can produce FDCA under the same reaction conditions. This is because only Au nanoparticles can extract the H atom from the OH group in HMF. Green Chemistry

Table 8 Photosteatrolendship consistent of HMF to valuable chemisals continue with CO₂ reads consistent. (b) Network 12/27/2024

THE CONTRACT DEFA CONTRACT DEFA CONTRACT DEFA CONTRACT DEFA CONTRACT DEFA

Obviously, base additives are important for preventing the metal leaching with formation of carboxylate instead of free acid. But the extra acidification and purification of FDCA-salt would lead to a lower green index and a higher application cost. In order to promote the reaction without alkaline additives, Co^{3+} @ZnO and $(Cr^{3+}$ or Co^{3+} -NiO catalysts were prepared by Pham and Park, respectively, by introducing charge-mismatched metal cations to semiconductors.^{77,100} Moderate selectivity of FDCA (40–50%) was obtained at a high conversion of HMF (95%) under base-free conditions. Pham et al. also reported a Cr-free and base-free Fe@rGO photocatalytic system.¹⁰¹ But this catalyst showed rather a low selectivity of FDCA (29%) at the same conversion of HMF. Pham et al. synthesized $\text{Zn}_x\text{Cd}_{1-x}\text{S}$ nanoparticle photocatalysts with different concentrations of Zn^{2+} ions (x = 0.0, 0.3, 0.5 or 0.7).²⁴ The approach was found to be effective for controlling the band gap and promoting e^- –h⁺ separation, thereby improving the photocatalytic efficiency. In addition, the previous $\text{ZnIn}_2\text{S}_4\text{-TU}$ catalyst with more Zn vacancies also enabled FDCA formation by extending the reaction time. 67 However, the yield of FDCA (ca. 40%) was inadequate without alkaline additives. Instead, Chang et al. integrated Ti_6 -NH₂ nano-sheet (i.e., a Ti clusterbased COF) with benzotrithiophene triformaldehyde (BTT) to obtain a MCOF-Ti $_6$ BTT photocatalyst.¹⁰² This integration provided strong visible-light absorption, effective e⁻–h⁺ separation

Table 9 Photocatalytic oxidation of HMF to FDCA

Entry	Catalyst	Solvent	Reaction conditions	Conv. $(\%)$	Select. (%)	Ref.
$\mathbf{1}$	$CoPZ/g-C_3N_4$	H_2O	Xe light (300–1000 nm, 0.5 W cm ⁻²), Na ₂ B ₄ O ₇ buffer solution (40 mL), pH = 9.18, 1 bar air, 14 h, 25 °C	99	97	20
2	Ag_1 -Au ₂ /TiO ₂	H_2O	λ > 420 nm, 0.3365 g Na ₂ CO ₃ , 5 h	43	98	99
3	$Co3+(a)ZnO$	H_2O	$\lambda \geq 365$ nm, air	95	40	100
4	$(Cr^{3+}$ or Co^{3+})-NiO	H_2O	λ = 365 nm, 36 h	95	50	77
5	Fe@rGO	H_2O	λ = 365 nm, 6 W, 36 h	95	29	101
6	$Zn_{1-x}Cd_xS$	H_2O	λ = 445 nm, 6 W, 24 h, air	98	40	24
7	$ZnIN_2S_4$ -TU	H_2O	λ = 445 nm, 6 W, 24 h	92	43	67
8	$MCOF-Ti6BTT$	CH ₃ CN	Visible light (400–800 nm), 25 °C, 1 atm O_2	100	95	102
	CoPz* $g - C_3 N_4$ permission of American Chemical Society, Copyright 2017.		$-H + HO$ Fig. 13 Possible mechanism for photocatalytic oxidation of HMF to FDCA over the CoPz/g-C ₃ N ₄ catalyst. Reproduced from ref. 20, with $+ H2O + H'$ $2H+$			
				H ₂		
			Fig. 14 Schematic mechanism for selective photocatalytic oxidation of efficiency, and appropriate photooxidation ability. Notably, the HMF to DFF or HMFCA by the Ru CdS catalyst. Reproduced from ref. 60, highest photocatalytic activity (i.e., >95% selectivity of FDCA at with permission of John Wiley & Sons, Inc, Copyright 2022. a full conversion of HMF) under base-free conditions has been			
	reported to date in the literature.		selectivity of HMFCA (93%) is obtained at 85% conversion of			
			4.2. Photocatalytic oxidation of HMF to HMFCA and FFCA HMF under an air atmosphere.			
			HMFCA is the paralleling intermediate to DFF during the first Table 11 displays the results for the photocatalytic oxidation			
			step of HMF oxidation. Thereby, it is difficult to selectively of HMF to FFCA. A $g-C_3N_4/NaNbo_3$ catalyst was prepared by			

Fig. 13 Possible mechanism for photocatalytic oxidation of HMF to FDCA over the CoPz/g-C₃N₄ catalyst. Reproduced from ref. 20, with permission of American Chemical Society, Copyright 2017.

4.2. Photocatalytic oxidation of HMF to HMFCA and FFCA

HMFCA is the paralleling intermediate to DFF during the first step of HMF oxidation. Thereby, it is difficult to selectively regulate the oxidation sequence of the $C=O$ or OH groups in HMF. Besides, the asymmetric structures of HMFCA and FFCA may hamper their direct use in downstream applications. Hence, there are only limited catalytic systems reported. As listed Table 10, Au/TiO₂ and Ag/TiO₂ catalysts enabled selective oxidation of HMF to HMFCA under visible light irradiation in Na_2CO_3 solution.^{103,104} Au/TiO₂ reached 99% conversion and 95% selectivity, this being the best result in the literature to date. Notably, Xia et al. gained insight into the formation mechanism of HMFCA via selective oxidation of HMF over a Ru-CdS photocatalyst (i.e., Ru complex anchored onto CdS quantum dots) in N , N -dimethylformamide.⁶⁰ As illustrated in Fig. 14, 'OH or ' O_2 ⁻ radicals can be generated over Ru-CdS under Ar or air atmosphere, respectively. Accordingly, such reactive species are found to be responsible for selectively oxidizing the OH or $C=O$ group in a HMF molecule. A high

Fig. 14 Schematic mechanism for selective photocatalytic oxidation of HMF to DFF or HMFCA by the Ru CdS catalyst. Reproduced from ref. 60, with permission of John Wiley & Sons, Inc, Copyright 2022.

Table 11 displays the results for the photocatalytic oxidation of HMF to FFCA. A $g-C_3N_4/NaNbO_3$ catalyst was prepared by calcining the mixture of $NaNbo₃$ and melamine, showing 87% selectivity of FFCA at 36% conversion of HMF.¹⁰⁵ As demonstrated in Fig. 15, $^{\circ}O_{2}^{-}$ radicals as the main active species can oxidize HMF to DFF with formation of adequate H_2O_2 which further oxidizes DFF to FFCA. The polarity of substrates greatly influences product selectivity. Since the polarity of DFF is weaker than those of HMF and FFCA, the oxidation rate of DFF is faster than that of HMF, promoting FFCA formation. Besides, Li et al. used polyoxometalate (i.e., a tetrabutylammonium salt of $W_{10}O_{32}^{4-}$ as photocatalyst to realize 88% conversion of HMF and 32% selectivity of FFCA in acetonitrile under UV irradiation.¹⁰⁶

In conclusion, the addition of base additives and/or the use of organic solvents are often required to achieve better results in the photocatalytic selective oxidation of HMF to FDCA. Therefore, it is also necessary to further optimize the prepa-

Table 10 Photocatalytic oxidation of HMF to HMFCA

Entry	Catalyst	Solvent	Reaction conditions	Conv. $(\%)$	Select. $(\%)$	Ref.
	Au/TiO ₂	$_{\rm H_2O}$	Visible light (420–780 nm, 0.3 W cm ⁻²), Na ₂ CO ₃ , 8 h, 30 °C	>99	95	103
2	Ag/TiO ₂	H_2O	λ > 420 nm, Na ₂ CO ₃ /HMF = 2 (in mole)	40	97	104
	Ru CdS	DMF	300 W xenon lamp 100 mW cm ⁻² , 17.5 h	85	93	60

Table 11 Photocatalytic oxidation of HMF to FFCA

Fig. 15 (a) Schematic diagram of e⁻-h⁺ pair separation over the g-C₃N₄/NaNbO₃ heterojunction. (b) Proposed mechanism for the g-C₃N₄/ NaNbO₃-catalyzed oxidation of HMF under visible light. Reproduced from ref. 105, with permission of Elsevier, Copyright 2020.

ration of catalysts and modulate the appropriate energy-band positions in anticipation of higher FDCA yield in the base-free and aqueous phase. The studies on HMFCA and FFCA intermediates can help us to further understand the routes and mechanisms of the oxidation processes. It is of guiding significance to improve the construction of the theoretical system of photocatalysis.

5. Photo(electro)catalytic oxidation of HMF

Photo(electro)chemical cells can directly use photogenerated e⁻–h⁺ pairs in semiconductor electrodes for fuel production, just as nature does through photosynthesis. In a typical H_2 -producing photoelectrochemical cell, water reduction $(H₂$ evolution) in the cathode is accompanied by anodic water oxidation $(O₂$ evolution). However, water oxidation is not kinetically favorable and the produced O_2 is of little value. Therefore, using photo(electro)chemical oxidation of HMF as an anodic reaction system would be a more efficient and practical scheme.

As summarized in Table 12, Cha et al. constructed a photo (electro)chemical cell using photo(electro)chemical oxidation

of HMF mediated by TEMPO as an anodic reaction.¹⁰⁷ In this unit, the n-type nano-porous $B\dot{N}O_4$ photoanode absorbs light and produces e^- –h⁺ pairs (Fig. 16). The e^- in the conduction band is transferred to the Pt counter electrode to reduce the water to H_2 . The h^+ in the valence band is used for TEMPOmediated HMF oxidation. Because the valence-band position of BiVO₄ is 2.4 V (vs. RHE), the photogenerated h^+ in the valence band of $BivO₄$ has sufficient overpotential to oxidize TEMPO before any external bias voltage is applied. Therefore, compared with electrochemical oxidation of HMF using metal electrodes, the use of photogenerated h^+ in the valence band of BiVO₄ can significantly lower the applied bias voltage to initiate TEMPO oxidation. The bias voltage applied is to enhance separation of e^- and h^+ so that the h^+ on the semiconductor surface can be used in the oxidation reaction rather than changing the overpotential of the oxidation reaction. Surprisingly, this smart system has provided >99% conversion of HMF and selectivity of FDCA. The high FE (93%) of FDCA produced at 40 C (charge passage) indicated that TEMPOmediated HMF oxidation is more beneficial for kinetics rather than water oxidation.

On this basis, Chadderdon et al. used BiVO₄ modified by CoPi as photoanode to drive TEMPO-mediated oxidation of

Entry	Photo-anode	Reaction conditions	Main product	Conv. (9)	Select. (%)	Ref.
	BiVO ₄	AM 1.5 G illumination (100 mW cm ⁻²), 1.04 V vs. RHE in a 0.5 M borate	FDCA	>99	>99	107
		buffer solution ($pH = 9.2$) containing 7.5 mM TEMPO, 40 C				
2	$BiVO4/CoPi-30$	Simulated solar illumination (AM 1.5 G, 100 mW $\rm cm^{-2}$), 0.64 V vs. RHE	FDCA	99	89	108
		for 2.7 h, 5.0 mM TEMPO in sodium borate electrolytes ($pH = 9.2$), 12 C				
3	D-Lig-Fe/NiCoB	5 mM HMF (1.6 V) 4 h, NiCoB catalyst-based electrocatalysis	FDCA	99	80	109
$\overline{4}$	$Ti/TiO2NT-1h-500-Pt$	Fluorescent lamps (Philips, 8 W) emitting mainly at 365 nm, 150 mL	DFF	59	40	110
		50 mM Na ₂ SO ₄ , 0.50 V bias and at pH = 5, 3 h, 25 °C				

Table 12 Photo(electro)catalytic oxidation of HMF to FDCA or DFF

Fig. 16 Schematic comparison of (a) photo(electro)chemical TEMPO-mediated HMF oxidation. (b) Electrochemical TEMPO-mediated HMF oxidation. CB, conduction band; E_F , Fermi energy. Reproduced from ref. 110, with permission of Springer Nature, Copyright 2015.

HMF to FDCA.¹⁰⁸ Compared with BiVO₄, BiVO₄/CoPi-30 lowered the potential required for TEMPO oxidation by ca. 0.5 V. To reducing the cost that originated from the TEMPO additive, Zhao et al. effectively converted lignin into photothermal materials (D-Lig-Fe) through demethylation of lignin and coordination with Fe^{3+} , with a photothermal efficiency of 36%.¹⁰⁹ Solar-thermal-electric conversion was realized by coupling D-Lig-Fe with a thermoelectric generator. Then, the generated voltage was applied to convert HMF to FDCA with a high conversion (99%) and selectivity (80%). Different from FDCA as the final product, Özcan et al. used $Ti/TiO₂NT$ as a photoanode for the first time to synthesize DFF.¹¹⁰ This photo (electro)chemical cell showed 59% conversion of HMF with 40% selectivity of DFF at a bias voltage of 0.5 V.

To sum up, electrochemical oxidation can provide the advantages of controlling oxidation potential and monitoring reaction rate by current, which may provide additional insights into the mechanism. However, there have been very few reports so far on photo(electro)catalytic oxidation of HMF to value-added chemicals. Because water oxidation is the main competitive reaction, it could limit the FE of HMF oxidation. Therefore, the developed photoanode needs to be able to selectively adsorb and activate HMF so as to effectively reduce the oxidation overpotential of HMF and eliminate the interference of water oxidation.

6. Photo(electro)catalytic reduction of HMF and FAL

Reports on the photo(electro)catalytic reduction of HMF and FAL are relatively scarce compared with their oxidation reactions (Table 13). There is only one article to date on the photo (electro)chemical reduction of HMF. Roylance et al. constructed a photo(electro)chemical cell by using BiVO₄ semiconductor as anode and Ag_{GD} as cathode.¹¹¹ As shown in Fig. 17, the h^+ on BiVO₄ surface is used to oxidize water to O₂

and the e[−] in BiVO4 conduction band is transferred to the AgGD cathode to reduce HMF to BHMF. The electrode can diminish energy input by directly using solar energy. In electrochemical batteries, it is necessary to provide sufficient overpotential for the cathodic reaction (i.e., HMF reduction) and anodic reaction (i.e., water oxidation) through external bias voltage. The FE and selectivity of BHMF both reach ca. 95% when the bias voltage is 1.0 V.

Guo and Dhingra successfully photoreduced HMF to BHMF over a Pt/g-C₃N₄ and a NiTiO₃/ZnIn₂S₄ catalyst, respectively.^{112,113} The reactions were driven by visible light in water with triethylamine as sacrificial e⁻ donor. The NiTiO₃/ZnIn₂S₄ catalyst presented 100% selectivity of BHMF at almost full conversion of HMF. That was the highest yield reported in the literature to date using water as hydrogen source. As illustrated in Fig. 18, the high photocatalysis of NiTiO₃/ZnIn₂S₄ benefits from the Z-type heterojunction between NiTiO₃ and ZnIn₂S₄, which promotes an easy separation and migration of interfacial charge carriers.

However, using water as hydrogen donor would easily generate reactive oxygen species to interfere with the hydrogenation of HMF. In this context, Cui and Kumar, respectively, obtained BHMF over the PtNi/TiO₂ and WO₃/PdO_x@C photocatalysts using methanol as hydrogen donor.^{114,115} The strong electron coupling between PtNi alloy and $TiO₂$ not only ameliorated the charge transfer, but also promoted the evolution of surface chemical bonds during photoreduction of HMF. As a result, a highest yield of BHMF (100%) can be obtained on PtNi/TiO₂, and the reaction conditions (i.e., base-free, H_2 -free) were among the mildest in the reported literature.

Interestingly, a few catalysts have been shown to enable photoreduction of both HMF and FAL into BHMF and FOL. Qiao et al. obtained BHMF and FOL on the amorphous $TiO₂$ $(A-TiO₂)$ photocatalyst using ethanol as hydrogen source.¹¹⁶ The yields of desired products achieved around 99%. As displayed in Fig. 19, the surface of A-TiO₂ stores e[−] under UV

^{*a*} Presented in yield (%). ^{*b*} Presented in productivity (mmol $g^{-1} h^{-1}$).

Fig. 17 Schematic diagrams comparing the external bias necessary to achieve HMF reduction for (a) a photo(electro)chemical cell and (b) an electrochemical cell. Reproduced from ref. 111, with permission of American Chemical Society, Copyright 2016.

Fig. 18 Pictorial representation of Z-scheme mechanism for photocatalytic H₂ generation and subsequent HMF reduction by NiTiO₃/ ZnIn₂S₄ hierarchical nanostructures. Reproduced from ref. 113, with permission of Elsevier, Copyright 2022.

Fig. 19 Hypothetical mechanism of HMF hydrogenation to BHMF over A-TiO₂. Reproduced from ref. 116, with permission of Royal Society of Chemistry, Copyright 2019.

irradiation while the h^+ can deprotonate ethanol into acetaldehyde. When the system is switched to a "dark" state, the $C=O$ group in HMF is attracted by the hydrogen bond interaction with the surface OH group. At the same time, the stored h^+ -e⁻ pairs are subjected to proton-coupled electron transfer to achieve highly selective hydrogenation of HMF. Besides, Hao et al. used tert-butanol as hydrogen donor for Au/SiC catalyzed photoreduction of HMF and FAL.²¹ Therein 100% yield of FOL was attained. Similarly, Dong et al. realized BHMF and FOL formation on a Pd/ MIL-101(Fe)-NH₂ photocatalyst using formic acid as hydrogen source.¹¹⁷

FAL in comparison with HMF has no interference from the OH group attached to furan ring, thereby photohydrogenation of FAL may be easier. Firstly, molecular H_2 can serve as reductant and hydrogen donor. Wang et al. prepared a Cu@C-600 catalyst that achieved 99% yield of FOL under 1 atm of H_2 and visible light irradiation.¹¹⁸ However, a high temperature of 100 °C was required. Also under a hydrogen atmosphere, ultrathin $SnNb₂O₆$ nanosheets with functional Pt nanoparticles allowed the use of H_2 to selectively phororeduce FAL to FOL. This composite photocatalyst showed the highest performance (*i.e.*, 100% yield of FOL) without any additives.¹¹⁹

However, the use of H_2 would bring certain safety risks and cost problems. In light of this, the catalytic transfer hydrogenation using organic solvents as hydrogen donor could be alternative route. Nakanishi et al. investigated the selective hydrogenation of FAL to FOL on a TiO₂ catalyst at room temperature in 2-pentanol. 120 FAL was almost completely converted to FOL under ultraviolet irradiation for 30 min. It was also found that 2-pentanol was oxidized to 2-pentanone by photogenerated h^+ . Zhang et al. prepared a $Cu/Cu₂O-MC$ (mesoporous carbon) photocatalyst which can directly convert FAL (94%) into FOL (96%) in iso-propanol at room temperature.¹²¹

Other than the metal photocatalysts, Hu et al. reported a covalent triazine polymer containing thiophene (CTP-Th) as visible-light responsive catalyst for photohydrogenation of FAL to FOL. 122 The thiophene and triazine units can be expressed as electron donor (D) and receptor (A), respectively. The D–A structure promoted the delocalization of π electrons and enhanced charge separation. Under visible light irradiation $(\lambda > 420 \text{ nm})$, CTP-Th can hydrogenate FAL to FOL at a rate of ca. 0.5 mmol g^{-1} h⁻¹ using ascorbic acid as a h⁺ sacrificial agent. In addition, Zhao et al. constructed a sustainable photoenzyme coupling system.¹²³ Instead of the conventional active cells, a $\text{ZnIn}_{2}S_{4}$ photocatalyst enabled driving of the regeneration of biocoenzyme nicotinamide adenine dinucleotide (NADH) with a rate of 90%. NADH served as the reductant to realize the selectively catalytic reduction of FAL. Full conversion of FAL with 79% selectivity of FOL was obtained in water. This result showed a high compatibility between photobased and bio-based catalysts. Critical Review General on expression and the properties of the control of the same and the properties of the control on the same and the propert

In short, most of the reported catalysts could photoreduce HMF and FAL with superior conversion. However, expensive precious metals are needed, the preparation cost is high, and

Table 14 Photocatalytic reductive coupling reactions of HMF and FAL

Fig. 20 Photocatalytic conversion of FAL over TiO₂ nanocrystals. (A) Structures of products from hydrogenation of C=O group and reductive coupling of FAL. Variations of product yield and selectivity with time over (B) A-bipyramid, (C) A-sheet, and (D) R-rod. Reproduced from ref. 28, with permission of Elsevier, Copyright 2020.

various additives are required. Therefore, novel catalysts with better selectivity and efficiency under lower costs and milder conditions are still highly desired.

7. Photocatalytic reductive coupling of FAL and HMF

FAL and HMF can be upgraded by chain-extension reaction to high-energy density diesel or jet fuels. It is particularly difficult to selectively produce biofuel precursors through homo-coupling or cross-coupling of furfuryl platform molecules, and despite the significance of this type of reaction, only limited success has been achieved. 124 Therefore, the photocatalytic reductive coupling of FAL and HMF still remains challenging for biomass valorization. As listed in Table 14, Wu et al. reported for the first time that the crystal plane of $TiO₂$ can regulate the product selectivity during photocatalytic reductive coupling of $HMF.²⁸$ As demonstrated in Fig. 20, the surface oxygen vacancy plays a decisive role. The catalyst without surface oxygen vacancy $(i.e.,$ the (110) facet) is beneficial for the reductive coupling of FAL to hydrofuroin (HDFO) or furoin (FO), i.e., high-quality fuel precursor. The selectivity of coupling products can reach as high as 100%. On the other hand, the catalyst with abundant oxygen vacancies $(i.e.,$ the (001) facet) gives priority to the hydrogenation of FAL to FOL. Green Chemistry

various additives are required. Therefore, novel estatises with the interfacial charge transfer is the key to improving the

heurt website in the signal of the signal of the signal of the signal of the si

Following that, Lv et al. prepared a series of metal-supported P25 catalysts (Cu, Ni, Pt and Pd). 125 Among them, 1% Cu/P25 could completely convert FAL in methanol to HDFO (50%, in select.) via C–C coupling. Notably, when 50 μ L of H₂O was added to the reaction mixture, the selectivity of HDFO significantly dropped. Interestingly, this phenomenon was observed over all prepared catalysts. Further characterizations revealed that a trace of H_2O increased the charge transfer resistance, which led to a slow interfacial charge transfer and inhibited reductive coupling reaction. Therefore, facilitating

the interfacial charge transfer is the key to improving the selectivity of coupling products. Kowalik et al. prepared nonstoichiometric $Ag_{1.0}In_{1.5}Zn_{0.3}S_{3.3}$ nanocrystals for photoreduction of FAL using p-toluenethiol as reductant and D_2O as solvent.¹²⁶ It was disclosed that base additives (*i.e.*, AcOCs, $Et₃N$, and *tert*-BuOK) were essential for the selective formation of FOL. But the absence of alkali can totally switch the product to HDFO through C–C coupling, at a high conversion of FAL (95%).

Regarding the photoreductive coupling of HMF, only a $MoS₂/CdS$ nanocomposite catalyst has been reported in the literature.²⁹ The OH group in HMF was adsorbed on CdS and attacked by the proton-coupled electron transfer steps to form keto free radicals. The coupling of two keto free radicals gave rise to the production of 5,5′-bis(hydroxymethyl)hydrofuroin (BHH), in addition to the main product of DFF. However, the selectivity of BHH would be rather low (9%).

In summary, it can be concluded from these limited reports that the adsorption state of carbon center free radicals on the surface of a photocatalyst is the key factor in determining the selectivity of the reductive coupling reaction. Therefore, modifying the surface structure of the catalyst and regulating the adsorption energy are effective approaches.

8. Other unconventional and promising photocatalytic reactions of FAL and HMF

Last but not least, some unconventional and promising photocatalytic reactions of FAL and HMF, such as oxidative decarboxylation, ring-opening and so forth, have emerged and received attention very recently. As summarized in Table 15, Esser et al. first reported that FAL could be converted to 5-hydroxy-2 (5H)-furanone (HFO) in ethanol through oxidative

Table 15 Other photocatalytic reactions of HMF and FAL

	Entry Catalyst	Solvent	Reaction conditions	Main product	Conv. (%)	Select. (%)	Ref.
$\mathbf{1}$	Organic dyes	EtOH	Lights, in alcohols, ≤ 40 °C	HFO	>99	>95	35
2	Methylene blue	MeOH	10 W LED, 1 L flask	HFO	100	85	128
3	EY/RB	H_2O	30 W green LEDs (530-540 nm), 4 mL of phosphate buffer (0.2 M, pH = 7), 25 °C, 9 h	HFO	97	99	38
$\overline{4}$	EY@DVB	H_2O	30 W green LEDs (530-540 nm), 25 °C, 200 rpm, 48 h	FSA	94	99	38
5	SGCN	CH ₃ CN	Solar simulator (AM 1.5 G, 100 mW cm ⁻²), 30 h, 25 °C	MAN/HFO/SAN/ β -FAA	>95	42/33/8/11	36
6	$P(Pd)$ - PDMA-PPEGMA	MeOH	λ = 350–650 nm, purged with O ₂ for 30 min	HFO	90	100	133
$\overline{7}$	$1\%M \cdot CN$	Solvent free	Sunlight (3 days), 36 ± 3 °C, 82.4–94.5 mW cm ⁻² , H_2O_2 (1.2 mmol)/ $O_2/O_2/O_2$	MA/FU/MA/HFO	98/94/94/ 94	100/37/40/ 23	37
8	1% Pd@E-g- C_3N_4	IPA	Light source (150 W LED), IPA (5 mL), 2 bar H_2 , 1 h	FOL	65	90	34
9	3% Pd@E-g-C ₃ N ₄	IPA	Light source (150 W LED), IPA (5 mL), 2 bar H ₂ , 5.5 h	THFA	100	100	34
10	3% Pd@E-g-C ₃ N ₄	CH ₃ CN	Light source (150 W LED), THFA (0.1 mmol), $CH3CN$ (3 mL) , 8 h, 1 bar O_2	GBL	75	100	34
11	RuphenPy	H_2O	525 nm LED, 25 °C, 9 h, air	HMFO	85	94	39
12	RuphenPy	H_2O	525 nm LED, ice bath, 9 h, air, NaOH (45 mM)	HKPA	62°		39

 a Presented in yield (%).

Fig. 21 Schematic illustration of photocatalytic FAL to HFO over organic dye. Reproduced from ref. 35, with permission of John Wiley & Sons, Inc., Copyright 1994. Organic dye combined with biological and chemical photocatalysts for FAL to HFO or FSA. Reproduced from ref. 38, with permission of Royal Society of Chemistry, Copyright 2021.

Fig. 22 (a) Generation of 1O_2 on the surface of SGCN via h⁺, (b) 1O_2 generation via triplet state energy transfer, and (c) plausible mechanistic pathway of FAL photooxidation. Reproduced from ref. 36, with permission of Royal Society of Chemistry, Copyright 2022.

decarboxylation using organic dyes as photocatalysts.³⁵ Furanone is a ubiquitous component found in a variety of natural products and can be used as synthetic intermediate for many bioactive chemicals, such as pesticides, prostaglandins and alkaloids. 127 In light of this pioneering study, Hermens et al. used methylene blue as a photocatalyst to obtain 100% conversion of FAL and 85% selectivity of HFO. 128 In the same way, Huang et al. reported the photocatalytic conversion of FAL over organic dyes $(i.e.,$ rose bengal (RB), eosin Y (EY) and methylene blue (MB)) in water.³⁸ Unfortunately, a low yield of HFO (<35%) was obtained in organic solvents with the selfmade photoreactor. Compared with FAL, 2-furoic acid (FCA) was the preferred substrate for the photocatalytic synthesis of HFO. Moreover, the solvent effect was significant. The yields of HFO obtained from FCA over the series photocatalysts in water medium still remained very low (22–27%). However, the yield can be fairly good (>90%) in organic solvents. Interestingly, using a phosphate buffer together with acetone enabled a further increase in the yield of HFO up to 94%. Green Chemistry

oceanicosytation using organic dyes as photocaralysts,³² bined with as to synthesize H4O from PAL. Norably, this

Future is a ubiquireal component furth in a view of or instalation, i.e., 97% conversion

In order to realize a more efficient conversion of FAL to HFO in the aqueous phase, a whole-cell biocatalyst *(i.e., E. coli*) co-expression of vanillin dehydrogenase (VDH2) and NADH oxidase (NOX), E. coli_CtVDH2_NOX) was developed to oxidize FAL to FCA. Therefore, E. coli_CtVDH2_NOX cells were combined with RB to synthesize HFO from FAL. Notably, this unique mode attained an excellent result under green LED irradiation, i.e., 97% conversion of FAL and 99% selectivity of HFO. In addition, the combination of E. coli CtVDH2 NOX cells and EY@DVB (i.e., weakly basic anionic resin based on styrene-divinylbenzene (DVB) copolymer) can be used for synthesis of fumaric semialdehyde (FSA). FSA is a versatile intermediate usually used in the synthesis of value-added chemicals because it can be easily oxidized and reduced.³⁸ As shown in Fig. 21, FAL is completely oxidized to FCA by E. coli_CtVDH2_NOX cells within 2 h, and FCA is subsequently ring-opened to FSA with an outstanding yield (93%) by ${}^{1}O_{2}$ photooxygenation on EY@DVB. This is the very first report on FSA formation from FAL ring-opening by photocatalytic biooxidation.

Based on the above work, HFO with one less carbon has been obtained from FAL by photooxidative decarboxylation. However, the specific reaction mechanism remains unclear. Chauhan et al. reported a mesoporous graphite carbon nitride $(SGCN)$ as photocatalyst.³⁶ It showed a superior FAL conversion (>95%) with selectivity of 42% and 33% for maleic anhydride (MAN) and HFO, respectively. The selectivity of MAN can be greatly increased up to 66% even under natural sunlight, which became a groundbreaking approach for the sustainable

Fig. 23 (a) Scheme for oxidation of FAL, (b) detailed reaction mechanism of FAL oxidation utilizing amphiphilic block copolymer, reaction kinetics for FAL oxidation, (c) using porphyrin-based copolymers, and (d) using P(Pd)-PDMA-PPEGMA with varying block fraction. Reproduced from ref. 133, with permission of Elsevier, Copyright 2022.

production of MAN. MAN is an important raw material for the synthesis of unsaturated polyester resins. 129 In addition, the plausible mechanism of photooxidation of FAL was investigated by scavenger experiments and electron spin resonance spectroscopy. As demonstrated in Fig. 22, FAL is initially converted to FCA via photooxidation by ${}^{1}O_{2}$ and then decarboxylated to furan. Further oxidation gives rise to the formation of $2(5H)$ -furanone which is then oxidized to HFO. Finally, MAN is produced by further oxidation of HFO. Besides, HFO shows partial tautomerism. Hence, succinic anhydride (SAN) and cisβ-formylacrylic acid (β-FAA) are formed by in situ rearrangement during the reaction. SAN is used as an intermediate in

the chemical, pharmaceutical and food industries, while β-FAA is an intermediate for synthesizing furanones. $130,131$ MAN can be continually transformed to maleic acid (MA) by photooxidation by ${}^{1}O_{2}$ species.

MA as an unsaturated dicarboxylic acid is a critical raw material in the manufacture of unsaturated polyester resins, surface coatings, plasticizers, pharmaceuticals, and fine chemicals.132 In order to further improve the yield of MA, Ebrahimian et al. combined expired metformin drugs with urea to prepare a g-C₃N₄ photocatalyst with a high N/C ratio.³⁷ Benefiting from the high specific surface area and the efficient separation of photogenerated e^-h^+ pairs, this photocatalyst

Fig. 24 Proposed mechanism and reaction steps associated with photocatalytic conversion of FAL to THFA and THFA to GBL. Reproduced from ref. 34, with permission of Royal Society of Chemistry, Copyright 2023.

achieved 98% conversion of FAL and 100% selectivity of MA using H_2O_2 as oxidant.

In order to further promote the yield of HFO, Seo et al. synthesized a Pd-containing porphyrin core (P(Pd)) amphiphilic block copolymer (P(Pd)-PDMA-PPEGMA) by Ru-catalyzed atom transfer radical polymerization.¹³³ This copolymer had a hydrophilic outer layer composed of poly(dodecyl methacrylate) (PDMA) and polyethylene glycol methacrylate (PEGMA). As illustrated in Fig. 23, the relatively hydrophobic FAL molecule diffuses into hydrophobic blocks and is adsorbed through the hydrophobic–hydrophobic interaction. After that, the adsorbed FAL reacts with the ${}^{1}O_{2}$ species formed by the porphyrin core, leading to hydrophilic products (i.e., HFO and methyl formate). As a result, the hydrophilic product is desorbed, which accelerates the catalytic reaction. This catalytic system showed 90% conversion of FAL and 100% selectivity of HFO within 10 h.

In addition to photoreduction of the $C=O$ group in FAL, Ghalt *et al.* firstly reported photoreduction of the $C=C$ bond in furan ring, that is, the selective photosynthesis of tetrahydrofurfuryl alcohol (THFA) from FAL.³⁴ THFA is not only used as an environmentally sound solvent but also can be converted into useful linear polyols by hydrogenolysis.¹³⁴ Pd nanoparticles decorated on E-g-C₃N₄ (*i.e.*, a high-surface-area $g - C_3N_4$ obtained by ultrasonic peeling) showed superior photo (electro)chemical performance due to effective separation of charge carriers. FAL was selectively hydrogenated to valueadded FOL and THFA. Specifically, 0.5% Pd@E-g-C₃N₄ selectively photoreduced FAL to FOL, whereas 3% Pd@E-g-C₃N₄ directly photoreduced FAL to THFA under 2 bar of H_2 . As shown in Fig. 24, photogenerated e[−] are transmitted and accumulated on Pd nanoparticles. These e[−] can promote desorption of the desorbed-H atom from the Pd site, thus reducing the FAL adsorbed on the E-g-C₃N₄ surface. The higher Pd content provides additional sites for the adsorption of FOL through furan ring, which promotes the over hydrogenation of FOL to THFA. Hence, the one-step conversion of FAL to THFA is realized. Furthermore, THFA can be selectively converted to γ-butyrolactone (GBL) over the same catalyst under $O₂$ atmosphere under 150 W LED light. GBL shows a wide range of biological characteristics and can be used as a lead structure for new drugs.135 It is also used to synthesize degradable polymers.¹³⁶ In addition, it can be used as an auxiliary electrolyte to supplement insufficient characteristics.¹³⁷

In addition to FAL, other photocatalytic reactions of HMF have been also reported. Sell et al. synthesized two structurerelated water-soluble Ru complexes (RubpyPy and RuphenPy).³⁹ The couple groups were decorated with covalently attached pyrene chromophores. The triplet energy of the latter one was slightly lower than that of the metal complexes, thus prolonging the lifetime of the so-called triplet reservoir and excited state by up to two orders of magnitude. Taking advantage of the excellent sensitization of ${}^{1}O_{2}$ of RuphenPy, this dyad was used as a photocatalyst for laboratory-scale reactions. As presented in Fig. 25, when HMF (30 mM) aqueous solution is irradiated with green light at 25 °C in a continuous air flow, two main stoichiometric products (i.e., formic acid and unsaturated lactone 5-hydroxy-5- (hydroxymethyl)furan-2(5H)-one (H^2MF) are observed. 85% conversion of HMF and 94% selectivity of HMFO can be obtained after 9 h. Furthermore, the photooxidation of HMF with NaOH additive was investigated in ice bath. It is interest-Green Chemistry

which was selectively of BA mulated on 12 analyzarics. Insee C can promote despines the published on 17 Applies the state of t

Fig. 25 ¹H NMR spectra of photooxidation of HMF (30 mM) in air-saturated water with RuphenPy as sensitizer (0.2 mol%) before and after 9 h of irradiation with color-coded peaks of key species. Reproduced from ref. 39, with permission of Royal Society of Chemistry, Copyright 2022.

ing to find that the main product switches to a ring-opening product, i.e., (Z)-5-hydroxy-4-keto-2-pentenoic acid (HKPA). The yield can reach 62%. $\mathrm{H}^{2}\mathrm{MF}$ and HKPA can be used to produce polyHKPA, a novel biopolymer.¹³⁸

In a word, this section strongly implies great potential for photocatalytic conversion of FAL and HMF. More unexpected high-value products could probably be obtained by photocatalysis. Therefore, it is particularly important to develop more general and accurate analytical methods (apart from the conventional NMR and GC-MS) for rapid separation and detection of those complicated products.

9. Conclusion and outlook

The conversion of biomass-derived furfuryl compounds into value-added chemicals through photocatalysis has recently gained significant attention due to its potential for achieving high efficiency, low pollution, and low-cost performance under mild reaction conditions. Since the first report in 2013 on the photocatalytic selective oxidation of HMF to DFF using $TiO₂$, an increasing number of photocatalysts have been developed for the photocatalytic oxidation of HMF. At present, there are already over sixty photocatalytic systems reported in the literature. Interestingly, about one-fourth of them show that H_2 evolution or $CO₂$ reduction can be carried out at the same time as oxidizing HMF to DFF. This strategy makes full use of photogenerated e^- and h^+ so it has higher economic value and better efficiency. For instance, an O-ZIS-120 photocatalyst exhibits the best performance, *i.e.*, a DFF yield of 1624 µmol h^{-1} g^{-1} with a selectivity >97%, along with a H₂ evolution rate of 1522 μmol h^{-1} g⁻¹. In addition to the typical photocatalytic oxidation of HMF and FOL, some unconventional reactions such as reduction, coupling, decarboxylation, ring-opening have been also studied. Many unexpected but promising highvalue products can be obtained in these ways. This shows an enormous potential in the photocatalytic transformation of furfural and its derivatives. Critical Review

Forence Chemistry

from Chemistry

product, $P_0(3+3)$ -product switches to a ting opening using water as solvent of
em alternative product product (TRI-), The impact on the readed in reaching

product can

Unraveling the reaction mechanism is undoubtedly a central task in addition to developing novel photocatalysts. Some important conclusions can be drawn by summarizing the state of the art. Firstly, photogenerated e[−] have reducing ability, and the magnitude of this competence is determined by the position of the conduction band (LUMO orbitals). Accordingly, photogenerated h^+ have oxidizing ability, the magnitude of which is decided by the position of the valence band (HOMO orbitals). Therefore, developing a catalyst with an appropriate energy band position is crucial for achieving photocatalytic selective oxidation and/or reduction of furfuryl compounds. Specifically, the energy band position can be rationally adjusted by optimizing preparation methods, doping elements, and constructing heterojunctions. Meanwhile, the plasma resonance effect and the ligand metal electron transfer effect (LMCT) can achieve visible light response of a catalyst. In addition, the influence of solvents and reaction atmospheres should not be ignored. Notably,

using water as solvent often has a significantly negative impact on the reduction reactions. Moreover, the roles played by various active oxygen species in the oxidation systems must be seriously distinguished. For example, hydroxyl radicals ('OH) with quite a strong oxidizing ability can usually over-oxidize reactants or products. Therefore, suppressing the generation of • OH can probably improve product selectivity in the oxidation reactions. Instead, superoxide anion radicals $({^1O_2}^-)$ and singlet oxygen $({^1O_2})$ are widely accepted as the key active species in achieving highly selective photocatalytic oxidations.

Although some breakthroughs have been reported, there are still many issues and significant challenges that need to be well addressed. Owing to the numerous advantages of photocatalysis, future research should focus on the following aspects particularly in line with the principles of green chemistry:

(1) Atom economy. Develop photocatalytic systems that can simultaneously and fully utilize photogenerated e^- and h^+ , such as selective oxidation of HMF combined with H_2 evolution or $CO₂$ reduction. Establish highly atom-economical closed-loop processes.

(2) Design for energy efficiency. Develop photocatalytic systems that can respond to visible light at room temperature and under atmospheric pressure. It is preferable to use catalysts that are simple and readily available, and optimize the preparation methods to reduce costs and maximize the utilization of solar energy.

(3) Low or non-toxic metal elements. Catalytic systems containing toxic elements such as Cr, Cd and Pb should preferably be avoided. This will allow us to boost the green footprint of the photocatalytic transformations.

(4) Safe solvents and additives. Develop photocatalysts that can work in environmentally friendly solvents, especially water, without the assistance of any additives. This can reduce environmental pollution and operational maintenance costs.

(5) Use of renewable feedstocks. Platform chemicals such as FAL and HMF are derived from acid-catalyzed dehydration of lignocellulosic biomass. Therefore, it would be significant to develop photocatalytic systems that can directly obtain highvalue chemicals from the crude starting materials, promoting the industrialization of photocatalysis.

In addition to fulfilling the above principles of green chemistry, there should be further understanding of the reaction mechanisms and expansion of the types of reactions. Currently, the photooxidation of HMF is intensively studied and has already obtained some advances. But investigation of some unconventional reactions (such as reduction, coupling, ring-opening, decarboxylation, etc.) is still in the very early stages. Meanwhile, the development of more universal and accurate analytical methods for detecting complicated reaction products is crucial and essential. Furthermore, a unified unit of measurement is vital for convenient and rigorous comparison studies on different photocatalytic systems. Therefore, the apparent quantum efficiency (AQE) should be used to measure catalyst performances, yet this is often overlooked in most works.

Last but not least, the isolation and purification of the target products need to be considered. This is particularly important for industrial applications. The concentration of substrates in photocatalysis is usually much lower compared with traditional catalysis. As expected, the concentration of products can be also low. Therefore, developing low-cost enrichment, separation, and purification strategies is essential.

In summary, the concept of carbon neutrality has received much attention in recent years, and the prospect of biomassbased photocatalytic transformations is very promising. It is necessary to continuously develop photocatalysts with better selectivity and efficiency for upgrading furfural and its derivatives under mild reaction conditions. However, many challenges still remain. We hope this review will provide better perspectives, from materials design to reaction mechanism and to practical application. Finally, further studies can be stimulated on sunlight-driven catalytic valorization of furfural molecules. Green Chemistry

Last but toot least, the siohtion and purification of the 10 R. Matical, P. Matical-3 Uncertain Review

impercant for industrial applications. This concertration of 11 R.J., Commole, Develope, Review, Soi

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by the National Natural Science Foundation of China (22272149 and 22062025), the Yunnan Fundamental Research Projects (202101AT070171), the Yunnan University's Research Innovation Fund for Graduate Students (KC-23234000), the Workstation of Academician Chen Jing of Yunnan Province (202105AF150012), and the Free Exploration Fund for Academician (202205AA160007). The authors thank the Advanced Analysis and Measurement Center of Yunnan University for the sample testing service.

References

- 1 X. Wu, N. Luo, S. Xie, H. Zhang, Q. Zhang, F. Wang and Y. Wang, Chem. Soc. Rev., 2020, 49, 6198–6223.
- 2 A. V. Puga, Coord. Chem. Rev., 2016, 315, 1–66.
- 3 Z. Zhang, J. Song and B. Han, Chem. Rev., 2017, 117, 6834–6880.
- 4 M. Wang and F. Wang, Adv. Mater., 2019, 31, 1901866.
- 5 C. Li, X. Zhao, A. Wang, G. W. Huber and T. Zhang, Chem. Rev., 2015, 115, 11559–11624.
- 6 D. Esposito and M. Antonietti, Chem. Soc. Rev., 2015, 44, 5821–5835.
- 7 Y. Wang, Y. Lu, Q. Cao and W. Fang, Chem. Commun., 2020, 56, 3765–3768.
- 8 Y. Wang, Y. Wang, Y. Lu, Q. Cao and W. Fang, Chem. Commun., 2021, 57, 1742–1745.
- 9 R. Zhang, Y. Wang, W. Zhang, Y. Lu, Q. Tang, Q. Cao, B. Gu and W. Fang, Chem. Commun., 2023, 59, 9134–9137.
- 10 R. Mariscal, P. Maireles-Torres, M. Ojeda, I. Sádaba and M. L. Granados, Energy Environ. Sci., 2016, 9, 1144–1189.
- 11 R.-J. van Putten, J. C. van der Waal, E. de Jong, C. B. Rasrendra, H. J. Heeres and J. G. de Vries, Chem. Rev., 2013, 113, 1499–1597.
- 12 C. Xu, E. Paone, D. Rodríguez-Padrón, R. Luque and F. Mauriello, Chem. Soc. Rev., 2020, 49, 4273–4306.
- 13 S. Chen, R. Wojcieszak, F. Dumeignil, E. Marceau and S. Royer, Chem. Rev., 2018, 118, 11023–11117.
- 14 P. Pal and S. Saravanamurugan, ChemSusChem, 2019, 12, 145–163.
- 15 M. Sajid, X. Zhao and D. Liu, Green Chem., 2018, 20, 5427–5453.
- 16 J. J. Bozell and G. R. Petersen, Green Chem., 2010, 12, 539– 554.
- 17 X. Kong, Y. Zhu, Z. Fang, J. A. Kozinski, I. S. Butler, L. Xu, H. Song and X. Wei, Green Chem., 2018, 20, 3657–3682.
- 18 Z. Zhang and K. Deng, ACS Catal., 2015, 5, 6529–6544.
- 19 S. Yurdakal, B. S. Tek, O. Alagöz, V. Augugliaro, V. Loddo, G. Palmisano and L. Palmisano, ACS Sustainable Chem. Eng., 2013, 1, 456–461.
- 20 S. Xu, P. Zhou, Z. Zhang, C. Yang, B. Zhang, K. Deng, S. Bottle and H. Zhu, J. Am. Chem. Soc., 2017, 139, 14775– 14782.
- 21 C.-H. Hao, X.-N. Guo, Y.-T. Pan, S. Chen, Z.-F. Jiao, H. Yang and X.-Y. Guo, J. Am. Chem. Soc., 2016, 138, 9361– 9364.
- 22 G. Lu, F. Chu, X. Huang, Y. Li, K. Liang and G. Wang, Coord. Chem. Rev., 2022, 450, 214240.
- 23 X.-X. Wang, S. Meng, S. Zhang, X. Zheng and S. Chen, Catal. Commun., 2020, 147, 106152.
- 24 V. N. Pham, S. Lee, H. Lee and H. S. Kim, Inorg. Chem., 2023, 62, 3703–3711.
- 25 H. Zhao, D. Trivedi, M. Roostaeinia, X. Yong, J. Chen, P. Kumar, J. Liu, B.-L. Su, S. Larter, M. G. Kibria and J. Hu, Green Chem., 2023, 25, 692–699.
- 26 C. Ayed, W. Huang, G. Kizilsavas, K. Landfester and K. A. I. Zhang, ChemPhotoChem, 2020, 4, 571–576.
- 27 B. Ma, Y. Wang, X. Guo, X. Tong, C. Liu, Y. Wang and X. Guo, Appl. Catal., A, 2018, 552, 70–76.
- 28 X. Wu, J. Li, S. Xie, P. Duan, H. Zhang, J. Feng, Q. Zhang, J. Cheng and Y. Wang, Chem, 2020, 6, 3038–3053.
- 29 J. Wang, Y. Yuan, K. Ren, B. Wang and Z. Li, J. Catal., 2023, 417, 178–184.
- 30 Y.-B. Huang, Z. Yang, J.-J. Dai, Q.-X. Guo and Y. Fu, RSC Adv., 2012, 2, 11211–11214.
- 31 Y. Zhu, W. Deng, Y. Tan, J. Shi, J. Wu, W. Lu, J. Jia, S. Wang and Y. Zou, Adv. Funct. Mater., 2023, 2304985.
- 32 L. Sun, W. Wang, T. Kong, H. Jiang, H. Tang and Q. Liu, J. Mater. Chem. A, 2022, 10, 22531–22539.
- 33 J. Fan, Y. Zhao, Q. Wang, M. Gao, X. Li, D. Li and J. Feng, Dalton Trans., 2023, 52, 1950–1961.
- 34 R. Ghalta and R. Srivastava, Sustainable Energy Fuels, 2023, 7, 1707–1723.
- 35 P. Esser, B. Pohlmann and H.-D. Scharf, Angew. Chem., Int. Ed. Engl., 1994, 33, 2009–2023.
- 36 D. K. Chauhan, V. R. Battula, A. Giri, A. Patra and K. Kailasam, Catal. Sci. Technol., 2022, 12, 144–153.
- 37 M. R. Ebrahimian, M. Tavakolian and M. Hosseini-Sarvari, J. Environ. Chem. Eng., 2023, 11, 109347.
- 38 Y.-M. Huang, G.-H. Lu, M.-H. Zong, W.-J. Cui and N. Li, Green Chem., 2021, 23, 8604–8610.
- 39 A. C. Sell, J. C. Wetzel, M. Schmitz, A. W. Maijenburg, G. Woltersdorf, R. Naumann and C. Kerzig, Dalton Trans., 2022, 51, 10799–10808.
- 40 A. Fujishima and K. Honda, Nature, 1972, 238, 37–38.
- 41 A. Ulyankina, S. Mitchenko and N. Smirnova, Processes, 2020, 8, 647.
- 42 I. Krivtsov, M. Ilkaeva, E. Salas-Colera, Z. Amghouz, J. R. García, E. Díaz, S. Ordóñez and S. Villar-Rodil, J. Phys. Chem. C, 2017, 121, 6770–6780.
- 43 A. Allegri, V. Maslova, M. Blosi, A. L. Costa, S. Ortelli, F. Basile and S. Albonetti, Molecules, 2020, 25, 5225.
- 44 A. Khan, M. Goepel, A. Kubas, D. Łomot, W. Lisowski, D. Lisovytskiy, A. Nowicka, J. C. Colmenares and R. Gläser, ChemSusChem, 2021, 14, 1351–1362.
- 45 Q. Zhang, H. Zhang, B. Gu, Q. Tang, Q. Cao and W. Fang, Appl. Catal., B, 2023, 320, 122006.
- 46 Y. Zhou, J. Liu and J. Long, J. Solid State Chem., 2021, 303, 122510.
- 47 I. Krivtsov, E. I. García-López, G. Marcì, L. Palmisano, Z. Amghouz, J. R. García, S. Ordóñez and E. Díaz, Appl. Catal., B, 2017, 204, 430-439.
- 48 M. Ilkaeva, I. Krivtsov, E. I. García-López, G. Marcì, O. Khainakova, J. R. García, L. Palmisano, E. Díaz and S. Ordóñez, J. Catal., 2018, 359, 212–222.
- 49 A. Akhundi, E. I. García-López, G. Marcì, A. Habibi-Yangjeh and L. Palmisano, Res. Chem. Intermed., 2017, 43, 5153–5168.
- 50 Q. Wu, Y. He, H. Zhang, Z. Feng, Y. Wu and T. Wu, Mol. Catal., 2017, 436, 10–18. The water treatment was to add 5 mL of water to $g - C_3N_4$ obtained from the primary calcination. After the secondary calcination, the modified $g - C_3N_4$ catalyst showed a large specific surface area and pore volume.
- 51 E. I. García-López, F. R. Pomilla, E. Bloise, X.-f. Lü, G. Mele, L. Palmisano and G. Marcì, Top. Catal., 2021, 64, 758–771.
- 52 G. Wang, R. Huang, J. Zhang, J. Mao, D. Wang and Y. Li, Adv. Mater., 2021, 33, 2105904.
- 53 H. Qian, Q. Hou, W. Zhang, Y. Nie, R. Lai, H. Ren, G. Yu, X. Bai, H. Wang and M. Ju, Appl. Catal., B, 2022, 319, 121907.
- 54 H. Zhang, Z. Feng, Y. Zhu, Y. Wu and T. Wu, J. Photochem. Photobiol., A, 2019, 371, 1–9.
- 55 L. Cheng, D. Huang, Y. Zhang and Y. Wu, Appl. Organomet. Chem., 2021, 35, e6404.
- 56 H. Li, H. Zhao, Y. Dong, Y. Zhu and J. Li, Adv. Energy Sustainability Res., 2022, 3, 2200116.
- 57 W. Liang, R. Zhu, X. Li, J. Deng and Y. Fu, Green Chem., 2021, 23, 6604–6613.
- 58 S. Chu, J. Shao, H. Qu, X. Wang, R. Xiao and H. Zhang, ChemSusChem, 2023, e202300886.
- 59 G. Han, Y.-H. Jin, R. A. Burgess, N. E. Dickenson, X.-M. Cao and Y. Sun, J. Am. Chem. Soc., 2017, 139, 15584– 15587.
- 60 T. Xia, W. Gong, Y. Chen, M. Duan, J. Ma, X. Cui, Y. Dai, C. Gao and Y. Xiong, Angew. Chem., Int. Ed., 2022, 61, e202204225. Critical Review General Asteronom, Control and SS Chu, J. Shao, H. Qu, X. Wang, R. Xiso and H. Zhang K. Xiso and K. Europhanished on 12. Europhanished on 12. Europhanished on 12. Europhanished on 12. Europhanished on 12.
	- 61 C. Yuan, Q. Liu, M. Wei, S. Zhao, X. Yang, B. Cao, S. Wang, A. E.-F. Abomohra, X. Liu and Y. Hu, Fuel, 2022, 320, 123994.
	- 62 J. L. DiMeglio, A. G. Breuhaus-Alvarez, S. Li and B. M. Bartlett, ACS Catal., 2019, 9, 5732–5741.
	- 63 M. Zhang, Z. Yu, J. Xiong, R. Zhang, X. Liu and X. Lu, Appl. Catal., B, 2022, 300, 120738.
	- 64 Q. Zhu, Y. Zhuang, H. Zhao, P. Zhan, C. Ren, C. Su, W. Ren, J. Zhang, D. Cai and P. Qin, Chin. J. Chem. Eng., 2023, 54, 180–191.
	- 65 M. Zhang, Y. Zhang, L. Ye, Z. Yu, R. Liu, Y. Qiao, L. Sun, J. Cui and X. Lu, Appl. Catal., B, 2023, 330, 122635.
	- 66 S. Ding, J. B. G. Filho, T. Peppel, S. Haida, J. Rabeah, N. Steinfeldt and J. Strunk, Sustainable Energy Fuels, 2023, 7, 4396–4400.
	- 67 V. N. Pham, S. Lee, D. T. Hoang, J. Baik, H. S. Kim and H. Lee, Inorg. Chem., 2023, 62, 12913–12919.
	- 68 J. Qiu, L. Zhang, D. Dai, G. Xia and J. Yao, ChemSusChem, 2022, 15, e202200399.
	- 69 Y. Guo, B. Liu, J. Zhang, G. Wang, C. Pan, H. Zhao, C. Wang, F. Yu, Y. Dong and Y. Zhu, Appl. Catal., B, 2024, 123217.
	- 70 H. Zhang, Q. Wu, C. Guo, Y. Wu and T. Wu, ACS Sustainable Chem. Eng., 2017, 5, 3517–3523.
	- 71 Y. Zou, Y. Hu, A. Uhrich, Z. Shen, B. Peng, Z. Ji, M. Muhler, G. Zhao, X. Wang and X. Xu, Appl. Catal., B, 2021, 298, 120584.
	- 72 A. Kumar and R. Srivastava, ACS Appl. Nano Mater., 2021, 4, 9080–9093.
	- 73 M. Gong, H. Zhao, C. Pan, Y. Dong, Y. Guo, H. Li, J. Zhang, G. Wang and Y. Zhu, New J. Chem., 2023, 47, 7118–7126.
	- 74 M. Zhang, Z. Li, X. Xin, J. Zhang, Y. Feng and H. Lv, ACS Catal., 2020, 10, 14793–14800.
	- 75 L. Yin, Y. Wu, X. Bao, X. Liu, D. Dai, M. Zhang, Z. Wang, Z. Zheng, Y. Liu, H. Cheng, Y. Dai, B. Huang and P. Wang, Chem. – Eur. J., 2023, 29, e202300999.
	- 76 D. A. Giannakoudakis, V. Nair, A. Khan, E. A. Deliyanni, J. C. Colmenares and K. S. Triantafyllidis, Appl. Catal., B, 2019, 256, 117803.
	- 77 Y. Park, V. N. Pham, K. Lee and H. Lee, Inorg. Chem., 2023, 62, 13428.
	- 78 B. Chen, L. Chen, Z. Yan, J. Kang, S. Chen, Y. Jin, L. Ma, H. Yan and C. Xia, Green Chem., 2021, 23, 3607–3611.
	- 79 B. Yang, W. Hu, F. Wan, C. Zhang, Z. Fu, A. Su, M. Chen and Y. Liu, Chem. Eng. J., 2020, 396, 125345.
	- 80 W. Hu, J. She, Z. Fu, B. Yang, H. Zhang and D. Jiang, RSC Adv., 2021, 11, 23365–23373.

- Green Chemistry Critical Review
- 81 F. Yang, S. Liu, T. Tang, S. Yao and C. An, Catal. Sci. Technol., 2023, 13, 2469–2474.
- 82 D. Liu, T. Ding, L. Wang, H. Zhang, L. Xu, B. Pang, X. Liu, H. Wang, J. Wang, K. Wu and T. Yao, Nat. Commun., 2023, 14, 1720.
- 83 Q. Yang, T. Wang, F. Han, Z. Zheng, B. Xing and B. Li, J. Alloys Compd., 2022, 897, 163177.
- 84 J. Yang, X. Zhang, Z. Zeng, C. Han and Y. Liang, Inorg. Chem. Front., 2023, 10, 6308–6319.
- 85 J. Hu, X. Li, J. Qu, X. Yang, Y. Cai, T. Yang, F. Yang and C. M. Li, Chem. Eng. J., 2023, 453, 139957.
- 86 X. Li, J. Hu, T. Yang, X. Yang, J. Qu and C. M. Li, Nano Energy, 2022, 92, 106714.
- 87 V. R. Battula, A. Jaryal and K. Kailasam, J. Mater. Chem. A, 2019, 7, 5643–5649.
- 88 P. Qiu, Y. Yao, S. Lu, L. Chen, Y. Chen and X. Liao, Fuel, 2023, 351, 129043.
- 89 Y. Yan, X. Yu, C. Shao, Y. Hu, W. Huang and Y. Li, Adv. Funct. Mater., 2023, 2304604.
- 90 S. Liu, B. Zhang, Z. Yang, Z. Xue and T. Mu, Green Chem., 2023, 25, 2620–2628.
- 91 S. Meng, H. Wu, Y. Cui, X. Zheng, H. Wang, S. Chen, Y. Wang and X. Fu, Appl. Catal., B, 2020, 266, 118617.
- 92 T. Shan, L. Luo, T. Chen, L. Deng, M. Li, X. Yang, L. Shen and M.-Q. Yang, Green Chem., 2023, 25, 2745– 2756.
- 93 D. A. Giannakoudakis, A. Qayyum, V. Nair, A. Khan, S. R. Pradhan, J. Prekodravac, K. Rekos, A. P. LaGrow, O. Bondarchuk, D. Łomot, K. S. Triantafyllidis and J. C. Colmenares, Mol. Catal., 2021, 514, 111664. Green Chemistry

9. F. Kang, S. Yao and C. An, Catal. 3ci. 106 Z. Li, M. Zhang, X. Kin and H. Lv, Chem.CatChem, 2021

7. Lo, Nor, Lo, No. 2024. Download, 2024. Download, 1024. Download, 1024. Download, 2023. H. Wing, D. W
	- 94 H. Wu, S. Meng, J. Zhang, X. Zheng, Y. Wang, S. Chen, G. Qi and X. Fu, Appl. Surf. Sci., 2020, 505, 144638.
	- 95 S. Dhingra, T. Chhabra, V. Krishnan and C. M. Nagaraja, ACS Appl. Energy Mater., 2020, 3, 7138–7148.
	- 96 Y. Wang, X. Kong, M. Jiang, F. Zhang and X. Lei, Inorg. Chem. Front., 2020, 7, 437–446.
	- 97 H.-F. Ye, R. Shi, X. Yang, W.-F. Fu and Y. Chen, Appl. Catal., B, 2018, 233, 70–79.
	- 98 Z.-W. Yang, J.-M. Chen, L.-Q. Qiu, W.-J. Xie and L.-N. He, Catal. Sci. Technol., 2022, 12, 5495–5500.
	- 99 W. Zhang, Q. Li and H. Xia, Appl. Surf. Sci., 2023, 613, 156036.
	- 100 V. N. Pham, H. Jeon, S. Hong and H. Lee, Inorg. Chem., 2022, 61, 16887–16894.
	- 101 V. N. Pham, H. Jeon, S. Han, S. Hong and H. Lee, Adv. Sustainable Syst., 2022, 6, 2200355.
	- 102 J.-N. Chang, Q. Li, Y. Yan, J.-W. Shi, J. Zhou, M. Lu, M. Zhang, H.-M. Ding, Y. Chen, S.-L. Li and Y.-Q. Lan, Angew. Chem., Int. Ed., 2022, 61, e202209289.
	- 103 B. Zhou, J. Song, Z. Zhang, Z. Jiang, P. Zhang and B. Han, Green Chem., 2017, 19, 1075–1081.
	- 104 W. Zhang, X. Li, S. Liu, J. Qiu, J. An, J. Yao, S. Zuo, B. Zhang, H. Xia and C. Li, ChemSusChem, 2022, 15, e202102158.
	- 105 Y. Zhu, Y. Zhang, L. Cheng, M. Ismael, Z. Feng and Y. Wu, Adv. Powder Technol., 2020, 31, 1148–1159.
- 106 Z. Li, M. Zhang, X. Xin and H. Lv, ChemCatChem, 2021, 13, 1389–1395.
- 107 H. G. Cha and K.-S. Choi, Nat. Chem., 2015, 7, 328– 333.
- 108 D. J. Chadderdon, L.-P. Wu, Z. A. McGraw, M. Panthani and W. Li, ChemElectroChem, 2019, 6, 3387–3392.
- 109 X. Zhao, L. Shi, B. Tian, S. Li, S. Liu, J. Li, S. Liu, T. D. James and Z. Chen, J. Mater. Chem. A, 2023, 11, 12308–12314.
- 110 L. Özcan, P. Yalçın, O. Alagöz and S. Yurdakal, Catal. Today, 2017, 281, 205–213.
- 111 J. J. Roylance, T. W. Kim and K.-S. Choi, ACS Catal., 2016, 6, 1840–1847.
- 112 Y. Guo and J. Chen, RSC Adv., 2016, 6, 101968–101973.
- 113 S. Dhingra, M. Sharma, V. Krishnan and C. M. Nagaraja, J. Colloid Interface Sci., 2022, 615, 346–356.
- 114 E. Cui, Q. Li, X. Wang, N. Xu, F. Zhang, G. Hou, M. Xie, Z. Wang, X. Yang and Y. Zhang, Appl. Catal., B, 2023, 329, 122560.
- 115 A. Kumar and R. Ananthakrishnan, ACS Appl. Energy Mater., 2022, 5, 2706–2719.
- 116 S. Qiao, Y. Zhou, H. Hao, X. Liu, L. Zhang and W. Wang, Green Chem., 2019, 21, 6585–6589.
- 117 S. Dong, Z. Liu, R. Liu, L. Chen, J. Chen and Y. Xu, ACS Appl. Nano Mater., 2018, 1, 4247–4257.
- 118 R. Wang, H. Liu, X. Wang, X. Li, X. Gu and Z. Zheng, Catal. Sci. Technol., 2020, 10, 6483–6494.
- 119 Y. Shi, H. Wang, Z. Wang, C. Liu, M. Shen, T. Wu and L. Wu, J. Energy Chem., 2022, 66, 566–575.
- 120 K. Nakanishi, A. Tanaka, K. Hashimoto and H. Kominami, Chem. Lett., 2017, 47, 254–256.
- 121 M. Zhang and Z. Li, ACS Sustainable Chem. Eng., 2019, 7, 11485–11492.
- 122 Y. Hu, W. Huang, H. Wang, Q. He, Y. Zhou, P. Yang, Y. Li and Y. Li, Angew. Chem., Int. Ed., 2020, 59, 14378– 14382.
- 123 H. Zhao, Q. Zhu, Y. Zhuang, P. Zhan, Y. Qi, W. Ren, Z. Si, D. Cai, S. Yu and P. Qin, GreenChE, 2022, 3, 385–394.
- 124 A. Gumidyala, B. Wang and S. Crossley, Sci. Adv., 2016, 2, e1601072.
- 125 S. Lv, H. Liu, J. Zhang, Q. Wu and F. Wang, J. Energy Chem., 2022, 73, 259–267.
- 126 P. Kowalik, P. Bujak, M. Penkala, W. Tomaszewski, W. Lisowski, J. W. Sobczak, D. Siepietowska, A. M. Maroń, J. Polak, M. Bartoszek and A. Pron, Chem. Mater., 2023, 35, 6447.
- 127 B. Mao, M. Fañanás-Mastral and B. L. Feringa, Chem. Rev., 2017, 117, 10502–10566.
- 128 J. G. H. Hermens, A. Jensma and B. L. Feringa, Angew. Chem., Int. Ed., 2022, 61, e202112618.
- 129 X. Li, B. Ho and Y. Zhang, Green Chem., 2016, 18, 2976– 2980.
- 130 L. Pu, L. Ye and Y. Yuanqi, J. Mol. Catal. A: Chem., 1999, 138, 129–133.
- 131 P. Rapado, L. Faba and S. Ordóñez, J. Environ. Chem. Eng., 2023, 11, 111466.
- 132 R. Wojcieszak, F. Santarelli, S. Paul, F. Dumeignil, F. Cavani and R. V. Gonçalves, Sustainable Chem. Processes, 2015, 3, 9. Critical Review

Green Chemistry

132 R. Wojcieszka, Dr. Stone, Published *Chem.*

132 R. Wojcieszka, 2015, 3, 5.

Processka, 2015, 3, 5.

Processka, 2015, 3, 5.

13 J. V. Sten, J. B. Wenn, S. H. Kim, S. Cho, 2024, 2022, 1
	- 133 J. Y. Seo, J. E. Kim, Y. J. Kwon, S. H. Kim, S. Cho, D. H. Choi, K. Y. Cho and K.-Y. Baek, Mater. Lett., 2022, 311, 131577.
	- 134 Y. Nakagawa, M. Tamura and K. Tomishige, ACS Catal., 2013, 3, 2655–2668.
- 135 M. Seitz and O. Reiser, Curr. Opin. Chem. Biol., 2005, 9, 285–292.
- 136 T. Moore, R. Adhikari and P. Gunatillake, Biomaterials, 2005, 26, 3771–3782.
- 137 H.-Y. Oh, S.-J. Park and S.-J. In, J. Mol. Liq., 2020, 314, 113627.
- 138 T. S. A. Heugebaert, C. V. Stevens and C. O. Kappe, ChemSusChem, 2015, 8, 1648–1651.