

Materials Advances

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: M. Yang, N. Wang, R. Zhang, S. Khan, B. Hou and W. Sand, *Mater. Adv.*, 2024, DOI: 10.1039/D4MA00700J.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.

Biomimetic haloperoxidases for antifouling on the surface of marine materials: a review

Meinan Yang,^{ab} Nan Wang,^{*ac} Ruiyong Zhang,^{*ac} Sikandar Khan,^{ad} Baorong Hou,^{ac}

Wolfgang Sand,^a

a Key Laboratory of Advanced Marine Materials, Key Laboratory of Marine Environmental Corrosion and Bio-fouling, Institute of Oceanology, Chinese Academy of Sciences, Qingdao, 266071, China

b College of Marine Science and Biological Engineering, Qingdao University of Science and Technology, Qingdao, 266042, China

c Institute of Marine Corrosion Protection, Guangxi Key Laboratory of Marine Environmental Science, Guangxi Academy of Sciences, 98 Daling Road, Nanning 530007, P. R. China

d Department of Biotechnology, Shaheed Benazir Bhutto University, Sheringal, KP, 18000, Pakistan

Corresponding authors: wangnan123@qdio.ac.cn (Nan Wang)

ruiyong.zhang@qdio.ac.cn (Ruiyong Zhang)



Abstract

View Article Online
DOI: 10.1039/D4MA00700J

Biological fouling has brought many direct and indirect adverse effects on human and life since ancient times. For decades, researchers have tried to develop effective antifouling strategies to prevent biofouling of marine organism. The toxicity of conventional antifouling agents to nontarget organisms has led to the gradual banning of them all over the world. Therefore, researchers have begun to focus on biomimetic haloperoxidases, after the natural antifouling capability of some marine algae that can effectively prevent the attachment of microorganisms by self-secreting haloperoxidases. Biomimetic haloperoxidases exhibit high stability and low cost, making them a good alternative to natural enzymes, and perform well in both laboratory and natural marine conditions. This review mainly focuses on vanadium-based, cerium-based, molybdenum-based and other biomimetic haloperoxidases materials. Among them, vanadium-based materials mainly include V_2O_5 and vanadium-based derivatives. Cerium-based materials mainly include CeO_2 , heteroatoms (such as carbon, nitrogen and lanthanide) doping cerium oxide, cerium oxide composite and Ce-MOF. Molybdenum-based materials mainly include molybdenum single-atom and molybdenum-based composite. Other biomimetic haloperoxidases materials mainly include W-UiO and Cr-SA-CN semiconductor. Their efficient antifouling behavior and mechanisms have been highlighted. Certain shortcomings of biomimetic haloperoxidases and their prospects have also been described. Researchers are enthusiastic to exploit biomimetic haloperoxidases as efficient antifouling substances in marine environment.

Key Word: Haloperoxidase, Antifouling, Catalytic properties, Biomimetic catalyst, Hypobromous acid



1. Introduction

Scope and definition of biofilm varies depending on the field of research.^{1,2} Most of the time the biofilms consist of a mixture of bacteria, fungi, protozoa, and/or algae that live in symbiosis with each other, and they usually formed on moist surfaces, such as pipelines, cooling towers, drains, and other water delivery systems. Biofilms affect various industrial settings and production. Biofilms attached to ship hulls and seabed equipment traveling in the ocean are commonly called marine fouling.³ Marine biofouling has many direct and indirect effects on human life and activities. Marine fouling can contribute to surface deterioration of ships, damaging propellers, increasing resistance to forward movement and hence, resulting in more fuel consumption and excessive maintenance costs.^{4,5} In addition, marine fouling indirectly contributes to global warming because excessive fuel consumption brings more greenhouse gas emissions.⁶ Besides, marine fouling also leads to the collapse of ecosystem due to biological invasion.⁷ Some equipment for offshore operations has reduced capacity and safety due to the impact of marine fouling, such as subsea oil production and cross-sea bridges.⁸ Therefore, it is particularly important to minimize or mitigate marine biofouling and reduce its huge financial impact.

Many measures have been taken to deal with marine fouling. Surface coating is the most widely used antifouling strategy in marine industry. For example, the traditional antifouling coatings, consist of arsenic, zinc, tin and mercury, to control marine fouling problems.⁹ However, the impact of their toxicity on the marine creatures cannot be ignored.¹⁰ The International Maritime Organization decided to ban the use of aforementioned metals containing biocide in the manufacture of antifouling coatings in 2003 and on the surface of ships since 2008.¹¹ Gradually, these biofouling control measures were banned worldwide, and the search for safe, non-toxic, reliable and efficient antifouling measures began to develop. So far, there have been a number of green antifouling strategies and materials have been researched, such as novel functional polymers, micro-surface engineering, natura products and biomimetic



materials.¹² Nature itself has plenty of ways to deal with the issue of biofilms attachment. Some compounds, such as terpenoids, steroids, carotenoids and capsaicin, are antifouling and can prevent biofouling.¹³ In particular, vanadium-dependent haloperoxidase (VHPO) secreted by the marine algae (*Corallina officinalis* and *Delisea pulchra*) have been reported to prevent biofouling by catalyzing halides (Cl⁻, Br⁻) from seawater to hypohalous acids (HOBr, HOCl).¹⁴ The hypohalous acids interfere the cell-to-cell communication (quorum sensing) of bacteria by reacting with the signaling molecules of the marine bacteria, such as N-acyl homoserine lactones (AHLs). So it is not easy for marine microorganisms to develop biofilms and adhere to surfaces.¹⁵ But as natural enzymes, they have inevitable problems of high extraction/production costs, poor long-term stability, appropriate reaction conditions, etc. Therefore, it is need of the day to develop biomimetic haloperoxidases with same or better enzyme catalytic performance and long-term stability in natural marine environment.

Many biomimetic haloperoxidases with excellent performance have been developed so far. In 1992, the cis-dioxovanadium (VO²⁺) in acidic aqueous solution was the first reported vanadium bromoperoxidase biomimetic enzyme.¹⁶ Natalio and his colleagues have developed vanadium pentoxide nanoparticles that mimic vanadium haloperoxidases thwarting biofilm formation in 2012.¹⁷ In addition to vanadium oxides, there are many vanadium-based complexes. A series of oxoperoxovanadium model complexes were characterized as functional model for the vanadium haloperoxidase.¹⁸ As observed in enzymes, the complexes have the reactivity of reproducing the peroxidative halogenation and halide-assisted peroxide disproportionation reactions. Due to toxic effects of vanadium on the environment, subsequent research has gradually focused on green biomimetic enzymes. Herget and co-workers found that oxides of cerium (CeO_{2-x} nanorods) have the properties of quorum-sensing-regulators, similar to natural vanadium haloperoxidases (V-HPOs).¹⁴ Wu et al. used a room temperature synthesis method to obtain a new morphology of CeO₂ rich in oxygen vacancies.¹⁹ Wang and her colleagues synthesized nitrogen-doped CeO₂ of core-shell structure using



a simple coprecipitation method.²⁰ Certain carbon-nitrogen and lanthanide-doped cerium oxide have also been developed.^{21,22} In addition to single atoms, cerium oxide can also be combined with other metal oxides such as zirconia.²³ The emergence of these derivatives can help reduce the amount of cerium atoms, while maintaining or even improving the performance of the catalyst. Molybdenum-based biomimetic enzymes and their derivatives have also become a focus of attention, such as molybdenum single-atom and Co-MoS₂.^{24,25} Some metal nanoparticles also have the antimicrobial effect.^{26,27} Therefore, this review focuses on biomimetic haloperoxidases, their antifouling efficacy and mechanism of fouling inhibition.

2. Vanadium-based biomimetic enzyme

Inspired by the natural vanadium haloperoxidase produced by certain marine algae, which prevents colonization of certain fouling causing marine organisms and seaweeds, the functional recombinant VHPO was manufactured.²⁸ Although the effect of functional recombinant VHPO is better than VHPO itself, some issues still need to be addressed. For instance, the production costs of additives used in antifouling coatings is higher in mass production. There are problems with its stability and reactivity in seawater conditions. Therefore, it is necessary to find suitable enzyme analogues as catalysts to replace VHPO. Researchers are gradually started their research with vanadium-based materials. For example, De la Rosa et al the first reported vanadium bromoperoxidase biomimetic enzyme was VO²⁺ in acidic aqueous solution.¹⁶ Butler and his co-workers found ammonium metavanadate (NH₄VO₃), a functional mimic of Vanadium-dependent bromoperoxidase (VBPO) in 1992 (**Figure 1(a)**).^{16,29} They successfully discovered that NH₄VO₃ can catalyze the oxidative bromination of 3,3',5,5'-tetramethylbenzidine with KBr and H₂O₂ under acidic condition (> 0.001 M H⁺). Melissa and others found a six-coordinate vanadium complex (LVO(OEt)(EtOH)), which can catalyze the oxidative bromination by hydrogen peroxide in DMF solution as the catalyst precursor (**Figure 1(b)-(e)**).³⁰ In addition, Eshita and co-workers have synthesized two new substances-vanadium (IV) dioxide and vanadium (V) oxido-



peroxido, and confirmed that they have the bioinspired catalytic activities.¹⁰ The bromoperoxidase activities of these complexes are determined by activating the C-H bonds (such as activating phenols, adjacent tithenols, and tailphenols). Mannar and colleagues have synthesized one dioxidovanadium (V) complex using 1-(2-pyridylazo)-2-naphthol donor ligand, and grafted the complex through coordination of an imidazole functionalized chloromethylated polystyrene (cross-linked with 5% divinylbenzene) (**Figure 1(f)**).³² It has been reported that these complexes exhibit catalytic activity as functional mimics of oxidative bromination of organic substrates.




Figure 1 (a) Reaction equation of NH_4VO_3 .²⁹ Reproduced from reference 29 with permission from Elsevier, copyright 2022. (b)-(e) are four possible reaction mechanisms of $\text{LVO}(\text{OEt})(\text{EtOH})$.³⁰ Reproduced from reference 30 with permission from ACS, copyright 1993. (f) Reaction schematic diagram of a tridentate Oxygen-Nitrogen-Nitrogen donor ligand, 1-(2-pyridylazo)-2-naphthol.³² Reproduced from reference 32 with permission from Elsevier, copyright 2014.

2.1 V_2O_5

Natalio and coworkers demonstrated that vanadium pentoxide (V_2O_5) nanowires have peroxidase-like activity.¹⁷ V_2O_5 nanowires are widely used as catalyst materials



that are stable, cheap and easily available.³³ In the experimental conditions and the presence of H_2O_2 and Br^- , V_2O_5 nanowires exhibit intrinsic bromination activity similar to natural enzymes (VHPO), producing HOBr acid with bactericidal effects (**Figure 2a**). And the bactericidal performance does not weaken in marine/field test. The test plate which contains V_2O_5 nanowires coating, after 60 days of exposure to seawater, there was no biofouling on its surface, indicating that V_2O_5 nanowires can effectively prevent biological fouling. This biomimetic method is stable, water-insoluble, slightly toxic and inexpensive. It replaces traditional chemical biocides with a new antibacterial, antifouling and disinfection formula.




Figure 2 (a) catalytic bromination mechanism for V_2O_5 nanowires.¹⁷ Reproduced from reference 17 with permission from Springer Nature, copyright 2012. (b), (c) and (d) are several possible mechanisms of halide oxidation in the vanadium haloperoxidase functional model.¹⁸ Reproduced from reference 18 with permission from ACS, copyright 1996. (b) The halide oxidation reaction mechanism involves nucleophilic attack of halides on the protonated peroxide ligand of the complex, resulting in oxygen transfer and simultaneous two-electron transfer. (c) The limiting forms for the potential mechanistic pathways. (d) A catalytic cycle of the vanadium haloperoxidase enzyme.

2.2 Vanadium-based derivatives

To study biomimetic catalysts, researchers could start from the natural compound



itself and adjust it on the basis of the original to obtain a better simulant.³⁴ VHPO naturally present in some algae and fungi, and due to its catalytic activity and defense mechanism against microorganisms (**Figure 2b-d**),¹⁷ has aroused the interest of researchers. By mimicking the structure and function of VHPO in the form of reactive peroxides, the researchers designed different metal-organic compounds. Colpas and colleagues produced a series of oxoperoxovanadium complexes, which have the ligands: H₃n₃ta = nitrilotriacetic acid, H₃heida = N-(2-hydroxyethyl)iminodiacetic acid, H₂ada = N-(2-amidomethyl)iminodiacetic acid, Hbpg = N,N-bis(2-pyridylmethyl)-glycine, and tpa = N,N,N-tris(2-pyridylmethyl)amine, and were characterized as functional models of vanadium peroxidase.¹⁸ These complexes contain the crystal structures of K[VO(O₂)Hheida], K[VO(O₂)ada], [VO(O₂)bpg], and H[VO-(O₂)bpg]₂(ClO₄). They were designed after getting inspired by the structure of VHPO, namely recombinant functional enzymes. These complexes were verified to have the ability of catalyzing peroxidative halogenation reaction with the support of experimental data.¹⁸ VHPOs have the umbrella-type vanadium peroxo-oxo structure that is valid model in vanadium oxide biocatalyst system, as do mimics compounds for example KVO(O₂)(heida)].

Although vanadium-based materials have excellent antifouling effect, its large-scale applications could be limited because of the mutagenic, carcinogenic and teratogenic of vanadium compounds.¹⁴ Since a great deal of environmental toxicity issues exist in the use of heavy metal vanadium, the antifouling metal that has the biocompatibility would be highly advantageous.

3. Cerium-based biomimetic enzyme

Following the catalytic activity of oxidation/halogenation reaction,³⁵ the oxyhalogenation of activated arenes,³⁶ and role of the Ce³⁺/Ce⁴⁺ redox couple in the halogenation of malonic acid in the Belousov–Zabotinsky reaction,³⁷ Karoline Herget deeply investigated the intrinsic haloperoxidase activity of ceria nanoparticles on anti-biological antifouling.¹⁴


3.1 CeO₂



Cerium can be reversibly converted between trivalent and tetravalent states by the redox potential of $\text{Ce}^{3+}/\text{Ce}^{4+}$. CeO_2 is an excellent oxide in industry because it has oxygen vacancy defects. These defects can be quickly filled and discharged, which makes CeO_2 as a high oxygen storage compound.³⁸ For example, Deshpande et al showed that CeO_2 nanoparticles could form more oxygen vacancies as particle size decreases to improve its activity and exhibit catalytic properties.³⁹ In addition, the valence states of cerium in cerium oxide and cerium oxides' defect structure are dynamic, and effected by physical factors (such as reaction temperature, time and other ions).⁴⁰ Tremel's group showed the synthesis time could directly control the surface properties of mesoporous ceria, and the chemical activity of CeO_{2-x} nanoparticles in haloperoxidase- and peroxidase-like reactions scales with their surface defects (via the $\text{Ce}^{3+}/\text{Ce}^{4+}$ ratio).⁴¹

Herget et al. clearly showed that CeO_{2-x} nanorods embody intrinsic haloperoxidase-like activity because CeO_{2-x} nanorods could successfully catalyze organic signaling compounds and cause them to undergo a bromination reaction.¹⁴ Test plates are daubed with the coatings, self-polishing resin formulation (SF) used for boat hull and hard paint formulations (HF), contained experimentally synthesized CeO_{2-x} nanorods. In static field tests, the plates illustrated favorable nanoparticle enzyme mimic property—upsetting surface seaweed colonization (**Figure 3a**). Under many environments, biofouling could significantly reduce the usage life of polymer nanofibers. Biofouling, especially biofilm contaminations, is adhering to surface by microbiological nonspecific adhesion.⁴² The adhesion layer existed in nanofibrous surface is difficult or even is impossible to remove. Hu's team synthesized CeO_{2-x} nanorods and used them to electrospin with polyvinyl alcohol (PVA) to create freestanding nanofiber pads.⁴³ Synthetic mechanically sturdy mixing pads can catalyze the oxidation of Br^- and H_2O_2 to HOBr on account of cerium compound has the activity similar to natural halogenated peroxidase. The destruction of quorum sensing effect by HOBr prevents the formation of biofilms on the surface of the fiber pad (**Figure 3b**).





View Article Online
DOI: 10.1039/D4MA00700J

Figure 3 (a) Selected samples after seven and half weeks of the static field immersion.¹⁴ Reproduced from reference 14 with permission from Wiley, copyright 2017. (b) Fabrication of CeO_{2-x} nanofibrous mats by electrospinning.⁴³ Reproduced from reference 43 with permission from ACS, copyright 2018.

Due to CeO₂ nanoparticles widespread applications, it is urgent for human to fully understand ecotoxicological effects of nano-ceria oxide on human health and environment. Some reports showed that CeO₂ nanomaterials have the negative impacts on organisms at very low concentrations.⁴⁴ The toxicity of different morphologies and doped materials of nano-ceria has further way needed to investigate.

3.2 Heteroatoms doping cerium oxide

Cerium oxides have excellent catalytic activity as haloperoxidase mimic. As a rare earth metal, cerium is very difficult to extract although its chemical elements are stored in abundant quantities on the earth. They are usually formed into alloys in pairs, which need to be separated. These rare earth elements are relatively dispersed in the earth's crust and there are few mineral deposits with high abundance. This feature limits its large-scale application. Doped with other elements in cerium oxide is an efficient measure to decrease consumption of cerium.

3.2.1 Carbon-doped cerium oxide

Carbon-based materials have demonstrated the ability of enzyme mimics. Shi et al.⁴⁵ found that carbon nanodots possess intrinsic peroxidase-like activity and can produce chromogenic reactions by H₂O₂-catalyzed oxidation of 3,3',5,5'-tetramethylbenzidine. Carbon-based materials show great prospects as substitutes for similar enzyme catalysts because of their rich reserves, adjustability and high



stability.^{20,46} Hence it is a valid strategy to improve catalytic activity and reduce the use of rare metals by carbon doping. Using carbon spheres as a template, the core-shell structure of carbon was prepared by a simple coprecipitation method. Wang and co-workers have successfully synthesized CeO₂@C using this approach.²⁰ Prior to field experiments, phenol red (PR) was used to test whether the material had the required catalytic properties and excellent performance (**Figure 4a**). Due to carbon doping the performance and stability of CeO₂@C got improved. As shown in **Figure 4b**, there is a sharp and prominent peak at 590 nm, illustrating that CeO₂@C equally has good intrinsic haloperoxidase mimicry activity. Through the comparison of experimental results of CeO₂ and CeO₂@C, it is obvious that the catalytic activity of the same amount carbon doped CeO₂ is higher than CeO₂. Antimicrobial performance analysis, in the presence of substrates H₂O₂ and Br⁻, experimental titanium plate containing CeO₂@C was shown to be completely black (**Figure 4c**). It illustrates that the surface of this titanium plate is free of bacterial adhesion, which was in stark contrast to the dense bacterial population on the CeO₂@C-free group (blank). These results indicated that CeO₂@C possesses significant bromination activity and could catalyze the oxidation of Br⁻ by H₂O₂ to generate the relevant HOBr, which pose an antibacterial activity. Compared to CeO₂, the CeO₂@C composite reduce the usage of rare-earth metal cerium during synthesis process and measurably enhance the catalytic activity. This work provides a new method and research direction for antimicrobial, antifouling and disinfection.






Figure 4 (a) Reaction mechanism of CeO₂@C as haloperoxidase mimicry.²⁰ Reproduced from reference 20 with permission from Elsevier, copyright 2020. (b) Absorbance spectra of solutions catalyzed by CeO₂@C and CeO₂ HS.²⁰ Reproduced from reference 20 with permission from Elsevier, copyright 2020. (c) Live/dead staining images of *E. coli*, *S. aureus* and *P. aeruginosa*.^{20,21} Reproduced from reference 20 and 21 with permission from Elsevier and MDPI, copyright 2020 and 2023. (d) Crystal violet staining assay of *P. aeruginosa* grown in lysogeny broth.²² Reproduced from reference 22 with permission from RSC, copyright 2022.

3.2.2 Nitrogen-doped cerium oxide

In addition to carbon doping cerium oxide, nitrogen doping is also a better option. Wang et al. synthesized nitrogen and carbon-doped CeO₂ (N-C/CeO₂) using a combination of liquid and solid.²¹ The product has halogenated peroxidase activity over a wide temperature range (20~50°C), simultaneously with high catalytic stability/recyclability (**Figure 4c**). Unlike the synthetic method of other studies,^{20,47} N-C/CeO₂ only uses melamine to provide a combine nitrogen and carbon source. Coupled with the synthesis methods of liquid and solid phase, it makes synthesis easier. There is one defect of existing unknown parts in the formation mechanism of N-C/CeO₂, which need to be further improved because its catalytic activity is mainly derived from CeO₂. Generally, this work offers one haloperoxidase mimic that is efficient, novel and



sustainable antimicrobial material.

3.2.3 Lanthanide-doped cerium oxide

The defects of ceria are closely related to its catalytic performance. The metal related to oxygen vacancies is able to substitute these defects,⁴⁸ namely use metal dopants. A synthesis method of mechanochemistry is different to our normal hydrothermal synthesis method. In mechanochemistry of oxide, its external mechanical force is using high-energy ball milling or grinding to accomplish.⁴⁹ Hence, using chlorides of lanthanides as starting compounds and then the doped activated ceria that has non-balanced structure. Opitz et al. selected the elements of lanthanide series, such as europium(Eu), dysprosium(Dy), gadolinium(Gd) and samarium(Sm), and doped in nanoceria²² to investigate if they could enhance the catalytic activity of halogenated peroxide reactions. Some of them have shown enhancement of catalytic activity, while others have less effect. They selected four materials for the detailed study:

- (i) pure, undoped ceria.
- (ii) Tb-doped ceria with moderate catalytic activity as a doped representative.
- (iii) Pr-doped ceria with the highest catalytic activity as a representative.
- (iv) $\text{Ce}_{1-x}\text{Ln}_x\text{O}_{2-x/2}$ nanocrystal prepared by hydrothermal synthesis as a comparison of balance structure.

From i to iii, the mechanochemical synthesis method is used. Lanthanide metals can be incorporated into the body of ceria by this synthesis method without solubility limitations. Agglomeration influences the formation of nanoceria, but sodium chloride, a by-product of mechanochemical metathesis reaction, inhibits agglomeration by matrix effects. In subsequent experiments, some verdicts are showed and reasonable to explain the enhancement of catalytic activity. In the characterization of ESR spectroscopy, it acclaims that doping Pr^{3+} and Tb^{3+} by ball milling synthesis increases the oxygen defect of surface sites. This means that these dopants stabilize O_2^- radicals which are important for catalysis. Dopants bring high defect density and positive surface point which might be the cause of high catalytic performance. According to the crystal violet staining assay, the number of adherent *P. aeruginosa* cells is CeO_2 (ht) >



CeO_2 (bm) > $\text{Ce}_{0.9}\text{Tb}_{0.1}\text{O}_{1.95}$ > $\text{Ce}_{0.9}\text{Pr}_{0.1}\text{O}_{1.95}$ (ht: hydrothermal, bm: ball milled)

View Article Online
DOI: 10.1039/D4MA00700J

(**Figure 4d**). Contrary to pure CeO_2 and blank surface, $\text{Ce}_{0.9}\text{Pr}_{0.1}\text{O}_{1.95}$ demonstrate obviously reduction of biofilm formation.

Through a series of experiments, Phil Opitz demonstrated that the halogenated activity of CeO_2 can be reinforced by substituting Ce^{4+} with Ln^{3+} in $\text{Ce}_{1-x}\text{Ln}_x\text{O}_{2-x/2}$. And mechanochemical synthesis could accomplish energy saving in large industrial quantities, production of residuum-free Ln doped nanoceria. Bionic method replaces traditional bactericide and expensive enzyme preservation system with steady, nontoxic and abundant rare earth oxides. This is an important step towards sustainable solution to problem of antifouling.

3.3 Cerium oxide composite

Ultra-small nanoclusters on different supports will have coalescence and agglomeration, which will lead to the loss of their catalytic activity.⁵⁰ Luo et al. proposed a way to make hybrid $\text{CeO}_2@\text{ZrO}_2$ (**Figure 5a**).²³ This ceria clusters are having high density and ultra-small (≈ 0.8 nm) size, which are steadied on the ZrO_2 substrates. This unique feature of heterografted $\text{CeO}_2@\text{ZrO}_2$ nanozymes resulted in excellent and stable haloperoxidase mimicry performance in selectively catalyzing the oxidation of Br^- to HOBr by H_2O_2 . Its performance is much better than the original CeO_2 nanoparticles. By producing bactericidal hypobromous acid, $\text{CeO}_2@\text{ZrO}_2$ can effectively combat colonization of antibiotic-resistant bacteria. Not only in lab experiments, $\text{CeO}_2@\text{ZrO}_2$ shows excellent antibacterial activity in the presence of Br^- and H_2O_2 (**Figure 5b**), but also in field (marine environments) illustrate good results. As a surface coating additive, $\text{CeO}_2@\text{ZrO}_2$ added to test plates significantly prevented marine biofilm colonization. It is important that this work emphasizes the role of reasonable design and synthesis in improving nanozyme performance and provides a new insight to the design of highly active catalytic nanomaterials for various antibacterial application.






Figure 5 (a) Schematic illustration of the synthetic process of $\text{CeO}_2@\text{ZrO}_2$.²³ Reproduced from reference 23 with permission from Wiley, copyright 2022. (b) Antibacterial and antibiofouling capacity of $\text{CeO}_2@\text{ZrO}_2$. Growth behavior of (b1) *E. coli* and (b2) *S. aureus* after coincubation with different combinations.²³ Reproduced from reference 23 with permission from Wiley, copyright 2022. (c) Schematic illustration of Ce-MOF-808 for antibacterial and inhibiting the formation of biofilms based on its HPO-like activity.⁵¹ Reproduced from reference 51 with permission from Wiley, copyright 2022.

3.4 Ce-MOF

During last decade, metal-organic frameworks (MOFs) have become one of the most promising catalyst materials. The reason is that MOF has large surface area, high porosity, homogeneous structure, molecular/atom-level catalytic centers and so on.⁵² The easily doped heteroatoms in MOFs provide a good opportunity for the synthesis of catalysts with excellent performance. The special structure of MOF, ultra-high surface area⁵³ and numerous substrate binding reaction sites,⁵⁴ conducive to the binding of cerium ions and the great prospect of assembling multiple active sites make it an excellent choice. Zhou and et al. selected MOF with a different nature of the materials used (**Figure 5c**).⁵¹ The MOF in this work has the primary and secondary coordination environment similar to natural enzymes⁵⁵ and is an ideal enzyme-like mimic.⁵⁶ The synthetic biomimetic material they named Ce-MOF-808. MOF-808 is one of the MOFs, its framework contains H_3BTC as a ligand. According to BET analysis, the good surface area may expose multiple active sites, thereby promoting good catalytic activity of



MOFs, which in turn produces good biofilm inhibition capacity. Although the antibacterial effect of Ce-MOF-808 is not as good as V_2O_5 nanowires, Ce-MOF-808 is another potential antifouling option due to their activity of HPO-like inhibition of bacterial growth. Ce-MOF-808 is easy to prepare and its HPO-like activity could catalyze the oxidative bromination of bacterial quorum sensing (QS) signal molecule AHLs. This response achieves the effect of quorum quenching (QQ), thereby preventing biofilm formation and growth. In pipes, they build a pipe-adhered biofilm model. Hence in the presence of Br^- and H_2O_2 , Ce-MOF-808 shows efficient role in restraining surface-adhered biofilm formation. these findings make it useful for water pipe cleaning. In addition to excellent enzyme-like activity, Ce-MOF-808 also has better performance in terms of long-stability, recyclability and biosecurity.

The discovery of Ce-MOF-808 enlarges the finite scope of HPO-like mimics and promotes the substitution of natural HPO to prevent the formation of biofilm attached to interior of pipeline. Moreover, it offers extensive antifouling application possibilities in multiple material surfaces.

4. Molybdenum-based biomimetic enzyme

4.1 Molybdenum single-atom

For general nanozymes, it is important to compare the number of active sites in nanozymes with corresponding enzymes.⁵⁷ However, only a small number of active atoms on the surface contribute to the enzyme-like catalysis. Consequently, this leads to a low density of active sites, poor atom utilization efficiency, and reduced catalytic activity.⁵⁸ Therefore, single atom becomes the site of focus for many researchers. As catalysis materials, single atoms have the advantage of atomic dispersion active sites,^{58,59} high utilization, high activity and high selectivity,⁶⁰ which can be good substitutes. According to Arrhenius equation, chemical reactions has direct proportion to temperature.⁶¹ The thermal effect of sunlight is a non-invasive external stimulus, and this thermal effect can be considered to enhance the activity of HPO-like nanozymes. Wang and co-workers explored a single atom molybdenum nanozyme (Mo SA-N/C)



with photothermal effect to prevent biofouling.²⁴ As a result of Mo doping, the nano materials possess intrinsic HPO-like activity that could catalyze the oxidation of Br and H₂O₂ to produce HOBr. Under visible light irradiation, the photothermal effect of Mo SA-N/C enhances HPO-like activity. It is evident that the antibacterial effect under light conditions is about twice that of under dark conditions (**Figure 6a**). This study offered a new idea for efficient and eco-friendly antifouling materials preparation.

4.2 Molybdenum-based composite

MoS₂ itself has a certain haloperoxidase activity. Doped with Co transition metal in MoS₂,²⁵ the new biomimetic enzyme has good halogenated peroxidase activity, which can catalyze the oxidation of Br to HOBr (**Figure 6b**). It is about 2 times higher than Ni doped MoS₂ and about 23 times higher than undoped MoS₂. The EPR analysis proves that the increase in activity is attributed to changes in sulfur vacancy concentrations. The sulfur vacancy concentration of Co-MoS₂ is evidently higher than Ni-MoS₂ and pure MoS₂ (**Figure 6c**). The stability, antibacterial performance and yield test of Co-MoS₂ in marine water shown good performance same as HPO-like mimic. One drawback is that it depends on the pH of the water environment. Compared to pH 5.7, the activity in pH 8.0 is 52%. The reduction may be related to the decrease of reactant activity and the decrease of the stability of HOBr and other reaction intermediates.

MoS₂ nanozyme was one of the primary attempts of transition metals engineering as functional mimic of natural haloperoxidases in anti-biofouling research. The HPO-like activity is effectively enhanced by doping Co, and produces a significant antibacterial role to *E. coli*, *S. aureus* and biofilm colonization in seawater. This study opens a new way of the potential application of transition metal disulfides combating biofouling.

MoS₂ is a kind of inorganic two-dimensional material. Except the haloperoxidase mimics, it has many other applications, such as energy, electronic, biosensor and immobilizing DNA strands after functionalization.⁶² Therefore, the biological safety of



molybdenum-based materials has become a problem worthy of attention. The studies showed that there was a strong connection between well-exfoliated MoS₂ nanosheets and their cytotoxic behavior. Their toxicity was decreased by selecting catalyst concentration.⁶³ However, so far there is no absolute statement about the toxicity of MoS₂.




Figure 6 (a) The disinfection efficiency of Mo SA-N/C, Mo SA-N/C+H₂O₂, and Mo SA-N/C + Br- + H₂O₂ under dark or visible light illumination.²⁴ Reproduced from reference 24 with permission from Wiley, copyright 2022. (b) Schematic diagram of structure and reaction mechanism of Co-MoS₂ nanozyme.²⁵ Reproduced from reference 25 with permission from ACS, copyright 2022. (c) Time-dependent absorbance variation of phenol red solution at 590 nm with the use of different transition metal-doped MoS₂ nanozymes.²⁵ Reproduced from reference 25 with permission from ACS, copyright 2022.

5. Others biomimetic enzyme

5.1 W-UiO nanozyme

For nuclear power plants, uranium (U) is the essential element. Thus, the extraction of uranium is equally important.⁶⁴ Ocean contain approximately 4 billion tons of uranium resources, which equates to an inexhaustible supply for nuclear power production.⁶⁵ Uranium adsorbent is one of the strategies that have been used to extract U from marine resources. Metal-organic framework is a special porous hybrid material using metal ions and organic ligands,⁶⁶ which has a large surface area, high selectivity and good chemical stability.⁶⁷ Therefore, metal-organic framework is a good adsorbent for uranium extraction. However, it needs to stay in seawater for a long time, so it also comes in contact with marine organisms causing marine fouling. Furthermore, the performance of uranium adsorbent would gradually weaken.⁶⁸ Wang and co-workers



gave a strategy of Tungsten single atom anchored to atomic engineering in a metal-organic framework.⁶⁹ This W-UiO nanozyme has intrinsic HPO-like activity, which can catalyze bromine ions into HOBr that has a bactericidal effect (**Figure 7a**). Consequently, it can improve the impact of adsorption performance from marine microbial colonization. After five regeneration cycles in natural seawater, the performance of W-UiO still remains 78% compared to unused W-UiO.

This provides a new idea to design recyclable, highly stable sorbents for extracting uranium from seawater, we can consider designing and manufacturing them to mimic the defenses of natural organisms.

5.2 Cr-SA-CN semiconductor nanozyme

The use of HPO-like nanozymes instead of natural enzymes to prevent biofouling in the ocean is a widely adopted measure.^{14,17} Haloperoxidase-catalyzed oxidation reactions require the involvement of H₂O₂, but in a normal marine water environment, the content of H₂O₂ is very low. The upper layer of oceans generally contain H₂O₂ at a concentration of about 102 nmol/L.⁷⁰ The lower content of H₂O₂ is a major obstacle to the full production of hypohalogenic acid by HPO-like mimics. Because of this, building one generation system of H₂O₂ is a good strategy. Luo and et al. constructed a semiconductor nanozyme that is composed of Cr single atoms coordinated on CN.⁷¹ This is a dual functional nanozyme that has non-sacrificial H₂O₂ photosynthesis and HPO-like activity. It uses water and O₂ to produce H₂O₂ under visible light, thereby self-supplying H₂O₂ in a continuous manner for HPO-like reactions (**Figure 7b**). In actual field tests in seawater, the experimental results show that Cr-SA-CN can form an inert surface on the outer layer of the material when added to the coating as an antimicrobial agent, thereby preventing the colonization of marine microorganisms.






Figure 7 (a) Schematic illumination of the antibiofouling and uranium extraction process of W-UiO.⁶⁹ Reproduced from reference 69 with permission from Elsevier, copyright 2022. (b) Schematic illustration of bifunctional Cr-SA-CN nanozyme: (b1) Bromide oxidation with H_2O_2 on a natural vanadium bromoperoxidase, (b2) Schematic illustration of the cascade reactions on an artificial bifunctional Cr-SA-CN nanozyme: photocatalytic H_2O_2 production from water and O_2 , and in situ self-supply of H_2O_2 for bromide oxidation reaction.⁷¹ Reproduced from reference 71 with permission from Wiley, copyright 2022.

This work also proves the potential of single atom nanozymes in combating biofouling, and also promotes the development of multifunctional nanozymes for biomimetic antifouling.

6. Conclusion

In this review, we have summarized prevalent biomimetic haloperoxidases and briefly introduce their antifouling mechanism and effects. The oxidative halogenation reactions (several parameters, reaction conditions and catalytic activity) of different biomimetic catalysts were summarized and compared as shown in Table 1. It can be observed that the biomimetic catalysts have gone through many metal-based changes. Due to toxicity of vanadium, the metallic groups have changed from vanadium-based to cerium-based materials. In addition to cerium, there are also biomimetic haloperoxidases composed of molybdenum, cobalt, uranium, chromium and many more. Compared to other metal-based biomimetic haloperoxidases, ceria has comparatively an excellent catalytic performance. At the same substrate concentration, ceria requires less catalyst content. This is one reason why many catalysts are cerium-based. Another reason is that catalytic reaction conditions containing ceria can be



carried out at room temperature, and do not depend on limits of pH or light.

Although a lot of biomimetic haloperoxidases have been proposed and studied for antifouling applications, there is still a long way to go before biomimetic enzymes can truly replace natural enzymes. Biomimetic enzymes have overcome some of the shortcomings of natural enzymes, but their catalytic activity is still lower than that of natural enzymes. Moreover, they have a lower binding affinity. Since most biomimetic enzymes are nanozymes, and many nanozymes have been shown to have the characteristics of multiplicate enzymes at the same time, it is not clear whether the activities of different enzymes will affect each other or not. Moreover, the antifouling mechanism of many biomimetic enzymes to kill bacteria and inhibit the formation of biofilms has not been deeply explored, and the detailed mechanism needs to be further explored.

Table 1 Summary of catalysts for oxidative halogenation reactions. (a): PR, (b): MCD, (c): NH₄Br, (d): KBr. RT= room temperature.

Natural enzymes / biomimetic enzymes	Dye [$\times 10^{-6}$ M]	Br ⁻ [$\times 10^{-3}$ M]	H ₂ O ₂ [$\times 10^{-3}$ M]	Catalyst [$\times 10^{-6}$ g/ml]	Reaction conditions	Ref.
V-HPO	50 ^(a)	100 ^(c)	2.50	-	-	72
V ₂ O ₅	50 ^(b)	1	0.01	0-30	Tris-SO ₄ buffer (0.1M), PH=8.3	17
CeO ₂	50 ^(a)	25 ^(c)	0.30	25	23-25°C	14
C/CeO ₂	28 ^(a)	69.4 ^(c)	0.83	80	RT	20
N, C/CeO ₂	28 ^(a)	69.4 ^(c)	0.83	50	RT	21
Lan/CeO ₂	53.5 ^(a)	26.7 ^(d)	0.32	26.74	-	22
CeO ₂ /ZrO ₂	50 ^(a)	25 ^(c)	0.35	50	25°C	23
Ce-MOF-808	50 ^(a)	25 ^(c)	1	100	Acetate-acetic acid buffer, pH 5.5, 37°C	51
Mo SA-N/C	50 ^(a)	25 ^(c)	0.80	100	Light-dependent	24
Co-MoS ₂	50 ^(a)	25 ^(c)	0.35	50	pH 5.7	25
W-UiO	50 ^(a)	25 ^(c)	0.49	50	pH 6	69



Cr-SA-CN 100^(b) 0.5 0.035 50 Tris-SO4 buffer (0.1M), DOI: 10.1039/D4MA00700J
PH=8.1, dark

The catalytic activity of biomimetic enzymes can reach a higher level by effective optimization, such as size, morphology, composition and surface modification. Under the same cost conditions, the antifouling and antibacterial activities can be studied from a multi-functional point of view, and it maybe has a better effect than the single functional enzymes. There are still many possibilities for the development of biomimetic enzymes in the field of antifouling in future: such as exploring new, easily obtainable and environmentally friendly metal biomimetic enzymes, modifying cerium oxides that has recently emerged to get better catalytic activity, combining biomimetic enzymes that prevent aggregation on the surface of biological cells and other classes of enzymes that inhibit growth or kill cells, and it can acquire a new biomimetic enzyme with better persistence and effectiveness. The development of modern society pays more attention to environmental friendliness and the safety and non-toxicity of materials used, which is also in line with the advantages of biomimetic enzymes.

With the development of science and technology, researchers have explored various fields, which could promote the research on biomimetic enzyme antifouling in more detail. Researchers' enthusiastic exploration of biomimetic haloperoxidases and the rapid development of nanotechnology may solve existing problems of biofouling in the near future, and biomimetic haloperoxidases will flourish in the field of antifouling.

Conflicts of interest

The authors declare that they have no conflict of interest.

Data availability

No primary research results, software or code have been included and no new data were generated or analyzed as part of this review.

Acknowledgements

The present work was supported by Shandong Provincial Natural Science Youth



Fund Project (ZR2022QD001), National Natural Science Foundation of China (No. 42306228), Key R&D Program of Shandong Province, China (No. 2022CXPT027) and the Taishan Scholars Program.

[View Article Online](#)

DOI: 10.1059/D4MA00700J

Reference

1. N. Høiby, *Journal of Pathology, Microbiology and Immunology*, 2017, **125**, 272-275.
2. Y. A. Nikolaev and V. K. Plakunov, *Microbiology*, 2007, **76**, 125-138.
3. M. S. Rahaman, H. Thérien-Aubin, M. Ben-Sasson, C. K. Ober, M. Nielsen and M. Elimelech, *Journal of Materials Chemistry B*, 2014, **2**, 1724-1732.
4. M. H. Mohd, M. A. Zalaya, M. Latheef, H. S. Choi, M. A. A. Rahman and D. K. Kim, *Latin American Journal of Solids and Structures*, 2019, **16**, e182.
5. M. E. Callow and J. A. Callow, *Biologist*, 2002, **49**, 1-5.
6. M. Salta, J. A. Wharton, P. Stoodley, S. P. Dennington, L. R. Goodes, S. Werwinski, U. Mart, R. J. K. Wood and K. R. Stokes, *Philosophical Transactions of the Royal Society A: Mathematical, Physical and Engineering Sciences*, 2010, **368**, 4729-4754.
7. S. K. Chakraborty, in *Impacts of Invasive Species on Coastal Environments: Coasts in Crisis*, eds. C. Makowski and C. W. Finkl, Springer International Publishing, Cham, 2019, DOI: 10.1007/978-3-319-91382-7_6, pp. 171-245.
8. L. Chen, Y. Duan, M. Cui, R. Huang, R. Su, W. Qi and Z. He, *Science of the Total Environment*, 2021, **766**, 144469.
9. K. Bosselmann, in *Tributyltin: Case Study of an Environmental Contaminant*, ed. S. J. De Mora, Cambridge University Press, Cambridge, 1996, DOI: DOI: 10.1017/CBO9780511759772.009, pp. 237-263.
10. S. Sonak, P. Pangam, A. Giriyan and K. Hawaldar, *Journal of Environmental Management*, 2009, **90**, S96-S108.
11. H. Jin, L. Tian, W. Bing, J. Zhao and L. Ren, *Progress in Materials Science*, 2022, **124**, 100889.
12. I. Banerjee, R. C. Pangule and R. S. Kane, *Advanced Materials*, 2011, **23**, 690-718.
13. J. R. Almeida and V. Vasconcelos, *Biotechnology Advances*, 2015, **33**, 343-357.



14. K. Herget, P. Hubach, S. Pusch, P. Deglmann, H. Götz, T. E. Gorelik, J. V. A. Gural'skiy, F. Pfitzner, T. Link, S. Schenk, M. Panthöfer, V. Ksenofontov, U. Kolb, T. Opatz, R. André and W. Tremel, *Advanced Materials*, 2017, **29**, 1603823. View Article Online
DOI: 10.1039/D4MA00700J
15. A. Butler and M. Sandy, *Nature*, 2009, **460**, 848-854.
16. R. I. De la Rosa, M. J. Clague and A. Butler, *Journal of the American Chemical Society*, 1992, **114**, 760-761.
17. F. Natalio, R. André, A. F. Hartog, B. Stoll, K. P. Jochum, R. Wever and W. Tremel, *Nature Nanotechnology*, 2012, **7**, 530-535.
18. G. J. Colpas, B. J. Hamstra, J. W. Kampf and V. L. Pecoraro, *Journal of the American Chemical Society*, 1996, **118**, 3469-3478.
19. R. Wu, W. Wang, Q. Luo, X. Zeng, J. Li, Y. Li, Y. Li, J. Li and N. Wang, *Advanced Composites and Hybrid Materials*, 2022, **5**, 2163-2170.
20. N. Wang, W. Q. Li, Y. D. Ren, J. Z. Duan, X. F. Zhai, F. Guan, L. F. Wang and B. R. Hou, *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 2020, **608**.
21. N. Wang, X. F. Zhai, F. Guan, R. Y. Zhang, B. R. Hou and J. Z. Duan, *International Journal of Molecular Sciences*, 2023, **24**.
22. P. Opitz, O. Jegel, J. Nasir, T. Rios-Studer, A. Gazanis, D.-H. Pham, K. Domke, R. Heermann, J. Schmedt auf der Günne and W. Tremel, *Nanoscale*, 2022, **14**, 4740-4752.
23. Q. Luo, Y. Li, X. Huo, J. Li, L. Li, W. Wang, Y. Li, S. Chen, Y. Song and N. Wang, *Small*, 2022, **18**, e2107401.
24. W. Wang, Q. Luo, J. Li, L. Li, Y. Li, X. Huo, X. Du, Z. Li and N. Wang, *Advanced Functional Materials*, 2022, **32**, 2205461.
25. Q. Luo, J. Li, W. Wang, Y. Li, Y. Li, X. Huo, J. Li and N. Wang, *ACS Applied Materials & Interfaces*, 2022, **14**, 14218-14225.
26. Y. Tao, E. Ju, J. Ren and X. Qu, *Advanced Materials*, 2015, **27**, 1097-1104.
27. G. Fang, W. Li, X. Shen, J. M. Perez-Aguilar, Y. Chong, X. Gao, Z. Chai, C. Chen, C. Ge and R. Zhou, *Nature Communications*, 2018, **9**, 129.
28. Z. Hasan, R. Renirie, R. Kerkman, H. J. Ruijssenaars, A. F. Hartog and R. Wever, *Journal of Biological Chemistry*, 2006, **281**, 9738-9744.



29. Z. Chen, *Coordination Chemistry Reviews*, 2022, **457**, 214404. View Article Online
DOI: 10.1039/D4MA00700J
30. M. J. Clague, N. L. Keder and A. Butler, *Inorganic Chemistry*, 1993, **32**, 4754-4761.
31. E. Palmajumder, S. Patra, M. G. B. Drew and K. K. Mukherjea, *New Journal of Chemistry*, 2016, **40**, 8696-8703.
32. M. R. Maurya, N. Chaudhary and F. Avecilla, *Polyhedron*, 2014, **67**, 436-448.
33. R. André, F. Natálio, M. Humanes, J. Leppin, K. Heinze, R. Wever, H.-C. Schröder, W. E. G. Müller and W. Tremel, *Advanced Functional Materials*, 2011, **21**, 501-509.
34. Paterson and I., *Science*, 2005, **310**, 451-453.
35. J. Asakura and M. J. Robins, *The Journal of Organic Chemistry*, 1990, **55**, 4928-4933.
36. A. Leyva-Pérez, D. Cómbita-Merchán, J. R. Cabrero-Antonino, S. I. Al-Resayes and A. Corma, *ACS Catalysis*, 2013, **3**, 250-258.
37. R. J. Field, E. Koros and R. M. Noyes, *Journal of the American Chemical Society*, 1972, **94**, 8649-8664.
38. C. T. Campbell and C. H. F. Peden, *Science*, 2005, **309**, 713-714.
39. S. Deshpande, S. Patil, S. V. Kuchibhatla and S. Seal, *Applied Physics Letters*, 2005, **87**.
40. G. S. Herman, *Surface Science*, 1999, **437**, 207-214.
41. E. Pütz, G. J. Smales, O. Jegel, F. Emmerling and W. Tremel, *Nanoscale*, 2022, **14**, 13639-13650.
42. T. R. Garrett, M. Bhakoo and Z. Zhang, *Progress in Natural Science*, 2008, **18**, 1049-1056.
43. M. Hu, K. Korschelt, M. Viel, N. Wiesmann, M. Kappl, J. Brieger, K. Landfester, H. Thérien-Aubin and W. Tremel, *ACS Applied Materials & Interfaces*, 2018, **10**, 44722-44730.
44. C. Xie, Y. Ma, P. Zhang, J. Zhang, X. Li, K. Zheng, A. Li, W. Wu, Q. Pang, X. He and Z. Zhang, *Environmental Science: Nano*, 2021, **8**, 1701-1712.
45. H. An, L. Liu, N. Song, H. Zhu and Y. Tang, *Nano Research*, 2023, **16**, 3622-3640.



46. H. Wei and E. Wang, *Chemical Society Reviews*, 2013, **42**, 6060-6093. View Article Online
DOI: 10.1039/D4MA00700J
47. Z. Ji, X. Wang, H. Zhang, S. Lin, H. Meng, B. Sun, S. George, T. Xia, A. E. Nel and J. I. Zink, *ACS Nano*, 2012, **6**, 5366-5380.
48. R. Schmitt, A. Nanning, O. Kraynis, R. Korobko, A. I. Frenkel, I. Lubomirsky, S. M. Haile and J. L. M. Rupp, *Chemical Society Reviews*, 2020, **49**, 554-592.
49. V. Šepelák, A. Düvel, M. Wilkening, K.-D. Becker and P. Heitjans, *Chemical Society Reviews*, 2013, **42**, 7507-7520.
50. B. Weng, K.-Q. Lu, Z. Tang, H. M. Chen and Y.-J. Xu, *Nature Communications*, 2018, **9**, 1543.
51. Z. Zhou, S. Li, G. Wei, W. Liu, Y. Zhang, C. Zhu, S. Liu, T. Li and H. Wei, *Advanced Functional Materials*, 2022, **32**, 2206294.
52. L. Ma, F. Jiang, X. Fan, L. Wang, C. He, M. Zhou, S. Li, H. Luo, C. Cheng and L. Qiu, *Advanced Materials*, 2020, **32**, 2003065.
53. H. Furukawa, K. E. Cordova, M. O’Keeffe and O. M. Yaghi, *Science*, 2013, **341**, 1230444.
54. A. H. Chughtai, N. Ahmad, H. A. Younus, A. Laypkov and F. Verpoort, *Chemical Society Reviews*, 2015, **44**, 6804-6849.
55. J. Wu, Z. Wang, X. Jin, S. Zhang, T. Li, Y. Zhang, H. Xing, Y. Yu, H. Zhang, X. Gao and H. Wei, *Advanced Materials*, 2021, **33**, 2005024.
56. M. Li, J. Chen, W. Wu, Y. Fang and S. Dong, *Journal of the American Chemical Society*, 2020, **142**, 15569-15574.
57. H. Wei, L. Gao, K. Fan, J. Liu, J. He, X. Qu, S. Dong, E. Wang and X. Yan, *Nano Today*, 2021, **40**, 101269.
58. W. Wu, L. Huang, E. Wang and S. Dong, *Chemical Science*, 2020, **11**, 9741-9756.
59. L. Jiao, H. Y. Yan, Y. Wu, W. L. Gu, C. Z. Zhu, D. Du and Y. H. Lin, *Angewandte Chemie-International Edition*, 2020, **59**, 2565-2576.
60. B. L. Xu, H. Wang, W. W. Wang, L. Z. Gao, S. S. Li, X. T. Pan, H. Y. Wang, H. L. Yang, X. Q. Meng, Q. W. Wu, L. R. Zheng, S. M. Chen, X. H. Shi, K. L. Fan, X. Y. Yan and H. Y. Liu, *Angewandte Chemie-International Edition*, 2019, **58**, 4911-4916.
61. X. Wang, Q. Shi, Z. Zha, D. Zhu, L. Zheng, L. Shi, X. Wei, L. Lian, K. Wu and L.



Cheng, *Bioactive Materials*, 2021, **6**, 4389-4401.

View Article Online
DOI: 10.1039/D4MA00700J

62. E. L. K. Chng, Z. Sofer and M. Pumera, *Nanoscale*, 2014, **6**, 14412-14418.
63. S. Arefi-Oskoui, A. Khataee, O. K. Uzun, M. Kobya, T. Ö. Hanci and I. Arslan-Alaton, *Chemosphere*, 2021, **268**, 128822.
64. W. Liu, X. Dai, Z. Bai, Y. Wang, Z. Yang, L. Zhang, L. Xu, L. Chen, Y. Li, D. Gui, J. Diwu, J. Wang, R. Zhou, Z. Chai and S. Wang, *Environmental Science & Technology*, 2017, **51**, 3911-3921.
65. W. Luo, G. Xiao, F. Tian, J. J. Richardson, Y. Wang, J. Zhou, J. Guo, X. Liao and B. Shi, *Energy & Environmental Science*, 2019, **12**, 607-614.
66. H. Zhou, M. Zheng, H. Tang, B. Xu, Y. Tang and H. Pang, *Small*, 2020, **16**, 1904252.
67. Y. Bai, C. Liu, Y. Shan, T. Chen, Y. Zhao, C. Yu and H. Pang, *Advanced Energy Materials*, 2022, **12**, 2100346.
68. Z. Huang, H. Dong, N. Yang, H. Li, N. He, X. Lu, J. Wen and X. Wang, *ACS Applied Materials & Interfaces*, 2020, **12**, 16959-16968.
69. W. Wang, Q. Luo, J. Li, Y. Li, R. Wu, Y. Li, X. Huo and N. Wang, *Chemical Engineering Journal*, 2022, **431**, 133483.
70. L.-S. Zhang and G. T. F. Wong, *Talanta*, 1999, **48**, 1031-1038.
71. Q. Luo, Y. Li, X. Huo, L. Li, Y. Song, S. Chen, H. Lin and N. Wang, *Advanced Science*, 2022, **9**, e2105346.
72. B. Sels, D. D. Vos, M. Buntinx, F. Pierard, A. Kirsch-De Mesmaeker and P. Jacobs, *Nature*, 1999, **400**, 855-857.



Data availability

View Article Online
DOI: 10.1039/D4MA00700J

No primary research results, software or code have been included and no new data were generated or analysed as part of this review.

