RSC Advances

REVIEW

Cite this: RSC Adv., 2024, 14, 4946

Received 22nd November 2023 Accepted 11th January 2024

DOI: 10.1039/d3ra07998h

rsc.li/rsc-advances

All-inorganic lead halide perovskites for photocatalysis: a review

Yaj[i](http://orcid.org/0000-0003-1182-8826)e Huang, Jiaxing Yu, Zhiyuan Wu, Borui Li and Ming Li^{D*}

Nowadays, environmental pollution and the energy crisis are two significant concerns in the world, and photocatalysis is seen as a key solution to these issues. All-inorganic lead halide perovskites have been extensively utilized in photocatalysis and have become one of the most promising materials in recent years. The superior performance of all-inorganic lead halide perovskites distinguish them from other photocatalysts. Since pure lead halide perovskites typically have shortcomings, such as low stability, poor active sites, and ineffective carrier extraction, that restrict their use in photocatalytic reactions, it is crucial to enhance their photocatalytic activity and stability. Huge progress has been made to deal with these critical issues to enhance the effects of all-inorganic lead halide perovskites as efficient photocatalysts in a wide range of applications. In this manuscript, the synthesis methods of all-inorganic lead halide perovskites are discussed, and promising strategies are proposed for superior photocatalytic performance. Moreover, the research progress of photocatalysis applications are summarized; finally, the issues of all-inorganic lead halide perovskite photocatalytic materials at the current state and future research directions are also analyzed and discussed. We hope that this manuscript will provide novel insights to researchers to further promote the research on photocatalysis based on all-inorganic lead halide perovskites. **PEVIEW All-inorganic lead halide perovskites for**
 (A) Cheek for guidates **All-inorganic lead halide perovskites for**
 $\frac{1}{2}$ Cheek for guidates **contained and the properties contained by the contained and the sec**

1 Background and development of perovskite materials

1.1 Non-perovskite photocatalysts and oxide perovskite photocatalysts

Globally, the challenges of the energy crisis and environmental pollution are becoming more severe.¹ An increasing number of studies have investigated the efficient use of solar energy to overcome these problems.²–⁴ Among these methods, visible light catalysis technique has demonstrated considerable promise. A wide range of photocatalysts has been extensively studied in photocatalytic processes.

 $TiO₂$ was originally used as a photocatalyst to break down water into H_2 and O_2 .⁵ Different catalysts have been employed, including metal oxides (ZnO, WO₃, Co₂O, CeO₂),⁶⁻⁸ metal sulfides (MoS₂, WS₂, Co₃S₄),⁹⁻¹⁴ nitrides (C₃N₄, GaN),^{15,16} phosphides (InP, Ni₂P, CoP, FeP),¹⁷⁻²⁶ and carbides (C₃N₄, rGO, MoC).²⁷⁻³¹ Photocatalysts with band gap (E_g) larger than 3 eV, such as $TiO₂$, ZnO, and MnS, have a fatal flaw: they can only be activated by UV light and cannot respond to a wide range of visible light regions. However, independent photocatalysts with E_g less than 3 eV, such MoS₂, WO₃, and C₃N₄, are impacted by the quick recombination of photogenerated carriers even though they exhibit photocatalytic activity under visible light

irradiation. In short, these conventional photocatalysts still have several issues such as poor light absorption,³² low quantum efficiency,³³⁻³⁶ high interfacial charge transfer resistance, 37 and rapid photogenerated carrier complexation, $38-41$ thus signicantly restricting the development and practical applications of photocatalysis. A range of efficient techniques, such as doping, implementing cocatalysts, building heterostructures, as well as controlling the morphology and crystallography, have been employed to conquer the aforementioned drawbacks and enhance the photocatalytic activity (Table 1).

Perovskite materials have drawn considerable attention as suitable photocatalysts. The general chemical formula of perovskites is ABX₃, where A, B, and X represent monovalent cations $(La^+, Bi^+, CH(NH_2)_2^+, CH_3NH_3^+, Cs^+, etc.),$ divalent cations (Pb²⁺, Mn²⁺, Co²⁺, Ti²⁺, etc.), and oxygen, halogen, etc. $(0, Cl^-, I^-, Br^-, etc.),$ respectively.⁴² When X is O, ABO₃ is called an oxide perovskite; organic–inorganic hybrid perovskites generally use $\mathrm{CH_3NH_3}^+$ (MA) or $\mathrm{CH(NH_2)_2}^+$ (FA) as the A-site cation. When Pb²⁺ is the B-site cation and Cl[−], I[−], Br[−] or their mixtures are the halide ions (X) , CsPb X_3 is called an allinorganic lead halide perovskite.⁴³ The three-dimensional structure of a perovskite is formed by connecting the vertex corners of the $(BX_6)^{n-}$ octahedron, which is made up of X⁻ and B^{2+} , with B^{2+} occupying the middle position within the octahedron. The photocatalytic performance of perovskites will be influenced by its crystal structure. The hybridization of the $O 2p$

College of Forestry, Northeast Forestry University, Harbin 150040, China. E-mail: orbital of the cation in the crystal structure and the 3d orbital of liming1986@nefu.edu.cn; Tel: +86-451-82192120

Table 1 Comparison and summary of the photocatalytic performance of inorganic halide perovskites and non-perovskites⁴

^a MB: methylene blue, PMMA: polymethyl methacrylate, TC: tetracycline hydrochloride, RhB: rhodamine B.

Fig. 1 Development process of perovskite in the photocatalysis field.

Table 2 Summary of typical work of oxide perovskite catalysts (ABO₃) in the field of photocatalysis⁶

^a ARS: alizarin red S, BP: phenol, BPA: bisphenol A, PNP: p-nitrophenol, DCP: dichlorophenol, MO: methyl orange.

the transition metal in the $(BO₆)$ octahedron will not only induce lattice distortion but also induce changes in the dipole and electronic structure, thereby affecting the separation of photogenerated carriers, finally leading to perovskites that have unique and variable photocatalytic properties. Furthermore, researchers can specifically build the electronic structure to enhance the stability, charge migration, and light absorption because of a variety of A and B site ions.^{44,45} Perovskite materials can also enhance the photocatalytic activity by combining ferroelectric and piezoelectric phenomena.^{46,47}

Due to differences in the photoelectric characteristics, different perovskites exhibit varying photocatalytic efficiency. The following characteristics are mostly indicative of the attributes that influence photocatalytic efficiency: (i) light absorption coefficient. The light absorption ability of catalysts affects their photocatalytic performance. The intensity and range of light absorption are crucial markers. (ii) The length of carrier diffusion. Long carrier diffusion length improves photocatalytic efficacy, decreases charge recombination, and helps separate electrons and holes. (iii) Bandgap width. The narrower the band gap of the perovskite, the worse its stability. With an

appropriate $E_{\rm g}$ (2.4–2.7 eV), the all-inorganic perovskite CsPbX₃ exhibits excellent stability.

ABO3 perovskite has been the target of most studies, with impressive findings being obtained in the field of photocatalysis. Mulani et al. prepared Ni-doped LaFe $_{0.6}$ Ni $_{0.4}$ O₃ through a hydrothermal method to degrade crystal violet (CV), Congo red (CR), and their mixtures under visible light. The degradation efficiencies were 99.2% (210 min), 99.1% (100 min), and 98.4% (70 min), respectively, which were far higher than that of LaFeO₃. LaFe_{0.6}Ni_{0.4}O₃ degraded CV dye through dealkylation and benzene ring cleavage, while azo bond cleavage and oxidation lead to the production of low molecular weight intermediate products of CR dye.⁴⁸ In recent years, oxide perovskites have been rapidly developed in the field of photocatalysis (Fig. 1). Table 2 summarizes the synthesis methods, reaction conditions, and photocatalytic performances of oxide perovskites compared with traditional photocatalysts.

1.2 Oxide perovskite to all-inorganic lead halide perovskites

 $ABO₃$ perovskite exhibited structural flexibility and stability compared with metal oxides; however, it also has shortcomings

| No. | All-inorganic lead halide perovskite | Method | Reaction conditions | Ref. |
|--------------|---------------------------------------------------------------------------------|----------------------|---------------------------------------------------------------------|------|
| $\mathbf{1}$ | CsPbX ₃ nanocubes (410–530 nm) (X = Cl, Br, I, and mixed systems) | Hot injection method | 140-200 \degree C inert gas protection | 115 |
| 2 | $CsPbBr3$ nanocrystals (6.8–13.6 nm) | LARP | Room temperature (25 \degree C) octylphosphonic acid | 116 |
| 3 | $CsPbBr3$ (film) | Anti-solvent method | Room temperature (varies with season) toluene as an antisolvent. | 117 |
| 4 | $CsPbBr3$ (bulk) | Ball milling method | Ball mill (500 rpm) | 112 |
| 5 | $CsPbI_3 (8-12 nm)$ | Ultrasonic method | Room temperature tip ultrasound (power 30 W) | 107 |
| 6 | $CsPbX_3$ (X = Cl/Br, Br and Br/I) nanowires (diameters as small as 2.6 nm) | Solvothermal method | 160 °C (high temperature reactor) | 113 |
| 7 | $CsPbBr3$ quantum dots | Template method | Kaolin as template | 118 |
| 8 | $CsPbBr3$ nanocrystals (nanoplates, nanocubes) | Microwave synthesis | Microwave reactor 80 °C (nano-plate) 160 °C (nano-cube) | 119 |

Table 4 Advantages and disadvantages of various synthesis methods

including large band gap, rapid carrier recombination, small specific surface area, and poor selectivity. Due to the high tunability of band gap, excellent charge mobility, and suitable redox capabilities, organic–inorganic hybrid lead halide perovskites stand out from various materials. Studies have demonstrated that MAPbI₃ is consistently and effectively capable of producing H_2 from HI under visible light irradiation, and the solar HI separation efficiency by $MAPbI₃$ is 0.81% when Pt is utilized as a noble catalyst.⁷⁷

Due to their poor stability, organic–inorganic hybrid lead halide perovskites have limited application in photocatalysis. In contrast, all-inorganic lead halide perovskites exhibit highly efficient semiconductor properties. They are employed in various applications, including X-ray fluorescence imaging,⁷⁸⁻⁸² visible light communication, $83-85$ solar cells, $86-89$ light-emitting diodes $(LEDs)$,^{90–92} lasers,^{93,94} photodetectors,^{95–97} and photocatalysis. However, most of the previous studies have focused on the optoelectronic properties of all-inorganic lead halide perovskites; a thorough overview of the all-inorganic lead halide perovskites in photocatalysis is urgently required to provide a guide for future research. Herein, all-inorganic lead halide perovskites are summarized in detail with an emphasis on the approaches of synthesis, modification, and applications in photocatalysis. Moreover, the problems and the future development in the field of photocatalysis are summarized and prospected.

2 Synthesis methods of all-inorganic lead halide perovskites

The properties of all-inorganic lead halide perovskites largely depend on their structures, which are directly related to the synthesis methods. Numerous techniques have been investigated to synthesize all-inorganic lead halide perovskites, such

RSC Advances **Review Review Review Review Review Review Review Review**

as hot injection,⁹⁸–¹⁰⁰ room-temperature ligand-assisted deposition,¹⁰¹–¹⁰³ microwave synthesis,¹⁰⁴–¹⁰⁶ ultrasound synthesis,¹⁰⁷ template method,¹⁰⁸⁻¹¹⁰ laser irradiation-assisted method,¹¹¹ ball milling method,¹¹² and solvothermal method.¹¹³ These methods can be broadly classified as "bottomup" or "top-down" depending on the growth process.¹¹⁴ The two techniques covered in this paper are the hot-injection and ligand-assisted deposition in room-temperature method (LARP), which are widely used for creating all-inorganic lead halide perovskites. The synthesis methods, advantages, and disadvantages of all-inorganic lead halide perovskites are summarized in Tables 3 and 4.

2.1 Hot injection method

The hot-injection method is a typical complex decomposition procedure that involves developing $CsPbX₃$ nanocrystals by completely mixing the PbX_2 precursor material with oleic acid, oleylamine, and octadecene and then rapidly cooling them at high temperatures (140–200 °C). In general, perovskite precursors crystallize into nanoplate-like morphologies at lower reaction temperatures, while they frequently generate cubic nanocrystals at higher reaction temperatures. When the temperature cools down, the size of the perovskite nanocubes also minimizes. The hot injection method can usually obtain dispersed $CsPbX₃$ nanocubes, and the halide composition of the nanocubes can be easily adjusted by changing the proportion of the PbX_2 precursor. **PSC** Advances article. Published on 1992. The bottle common and the properties are commonly the properties are the properties are the properties are the properties are the set of the set of the set of the set of the set o

Nedelcu et al. firstly achieved the successful hot-injection synthesis of the all-inorganic lead halide perovskite $CsPbX₃$, which also indicated that $CsPbBr₃$ and $CsPbI₃$ had higher photoluminescence quantum yield (PLQY) compared to $CsPbCl₃$,¹²⁰ For instance, the PLQY of $CsPbBr₃$ nanocrystals reached 90% ¹¹⁵ (Fig. 2). The hot injection method not only synthesizes pure CsPbX₃ but also yields CsPbX₃-based composites. Wang et al. designed $CsPbBr₃-CdZnS$ heterojunctions to photocatalytically reduce $CO₂$ by the hot-injection method; it was found that the $CsPbBr₃-CdZnS$ heterojunction achieved a higher CO yield (55.8 µmol \rm{g}^{-1} $\rm{h}^{-1})$ than that of the pristine CsPbBr $_3$ (13.9 µmol \rm{g}^{-1} \rm{h}^{-1}). $^{\rm 121}$

The hot-injection method for synthesizing all-inorganic lead halide perovskite nanocrystals has been continuously optimized using different precursors and ligands to achieve the controlment of shape and size as well as better stability over the years.¹²² Leng et al. successfully synthesized highly stable nanocrystals by designing a "modified hot-injection method" to maximize the number of ligand molecules and lowering the temperature $(\leq 40 \degree C)$ during precursor mixing to separate the nucleation and growth processes.¹²³ However, in large-scale production, the inability to adjust the high temperature when combining precursor solutions leads to poor material reproducibility.

2.2 Room-temperature ligand-assisted deposition

Even though the hot-injection method has been widely used to produce all-inorganic perovskite nanocrystals, it is a laborious process that needs extra steps in the synthesis of the Cs-oleate precursor and is typically carried out in an inert environment. LARP is an appropriate remedy for these limitations. Organic ligands and perovskite precursors are dissolved in solvent, and then spontaneous crystallization in a supersaturated state of the crystal can be achieved by lowering the temperature, evaporating the solvent, or adding a lean solvent with a lower solubility of the substance.¹²⁴ If crystallization is carried out in the presence of ligands, crystal nucleation and growth can be controlled, which is LARP.

Guvenc *et al.* produced CsPbX₃ (X = Br, Cl, I) by LARP; the PLQY of synthesized $CsPbBr₃$ was 85%.¹²⁵ By altering the experimental conditions, the LARP method can be used to manufacture all-inorganic lead halide perovskite with various morphologies. Deng et al. formed all-inorganic $CsPbX₃$ perovskite in a variety of shapes, including 0D spherical quantum dots, 1D nanorods, and 2D nanoplates¹²⁶ (Fig. 3). Zhang et al. discovered that stable $CsPbBr₃$ nanocrystals could be manufactured by adding small amounts of water to the reaction mixture, and the PLQY of the CsPbBr₃ nanocrystals was 90% .¹²⁷

It is worth noting that perovskite nanocrystals are sensitive to polar solvents; therefore, the synthesized nanocrystals have different sizes, poor crystallinity, and low experimental

Fig. 2 Colloidal perovskite CsPbX₃ (X = Cl, Br, I) exhibit size- and composition-tunable bandgap energies covering the entire visible spectral region with narrow and bright emission: (a) colloidal solutions in toluene under UV lamp ($\lambda = 365$ nm); (b) representative PL spectra (λ_{exc} 400 nm for all but 350 nm for CsPbCl₃ samples); (c) typical optical absorption and PL spectra; (d) time-resolved PL decays for all samples shown in (c) except CsPbCl₃.¹¹⁵

Fig. 3 Schematic illustrating the formation process for different $CsPbX_3$ (X = Cl, Br, I) nanocrystals mediated by organic acid and amine ligands at room temperature. Spherical quantum dots represent hexanoic acid and octylamine; nanocubes represent oleic acid and dodecylamine; nanorods represent acetate acid and dodecylamine; few unit cell-thick nanoplatelets represent oleic acid and octylamine.¹²⁶

repeatability, which are not suitable for large-scale production. To create high-performance all-inorganic lead halide perovskites, the researchers modified the original room-temperature ligand-assisted deposition method. Zeng et al. developed a comparable room-temperature supersaturation recrystallization technique to produce $CsPbX_3$ quantum dots.¹¹⁸ A highly supersaturated state is produced as soon as the halide salt precursor is transferred from a polar (N,N-dimethylformamide) to a nonpolar solvent (toluene), and the process can be finished without using a protective environment, heating, or injection in only a few seconds. Pan et al. investigated the ligand-mediated synthesis of all-inorganic CsPbBr₃ perovskite nanocrystals, and the results revealed that CsOAc was a more versatile precursor substance than the commonly used Cs_2CO_3 , displaying a greater solubility and a wider temperature.¹²²

2.3 Other synthesis methods

2.3.1 Ultrasonic method. The direct sonication of the appropriate precursor solution to create high-quality allinorganic lead halide perovskite in the presence of organic capping molecules is referred to as the "ultrasonic method". Rao et al. used ultrasonic-assisted method to synthesize CsPbBr₃ nanocrystals with various shapes and sizes.^{128,129}

2.3.2 Ball milling method. Ball milling can be used to produce all-inorganic lead halide perovskites on a large scale,¹³⁰ for example, Jiang et al. synthesized $CsPbBr₃/Cs₂PbBr₅$ with chemical stability and good photostability by ball milling,¹³¹ showing exceptional stability when exposed to UV light, heat, and water. However, mechanical grinding will result in surface flaws and diminish the photocatalytic effectiveness. Kim et al. created a simple two-step ball milling approach to create stable $CsPbBr₃$ ¹³² and discovered that these materials were more stable after 30 days than those that were thermally synthesized under the same circumstances.

2.3.3 Solvothermal method. The solvothermal method produces scattered nanocubes by loading precursors and ligands into an autoclave lined with Teflon and heating it to a high temperature for a predetermined amount of time. Chen et al. reported that high-quality all-inorganic cesium lead halide nanocrystals could be acquired by a simple solvothermal method,¹¹³ and the high-quality CsPbBr₃ nanocrystals are ideal for lighting applications.

2.3.4 Microwave synthesis. Pan et al. proposed a microwave-assisted strategy to synthesize high-quality $CsPbX₃$ with controllable morphologies (nanocubes, nanoplates, and nanorods),¹¹⁹ and the prepared CsPbX₃ nanocubes showed high PLQY (75%). In addition to the above-mentioned synthetic methods, two or more methods can be combined to synthesize all-inorganic lead halide perovskites. Li et al. prepared $CsPbBr₃/$ $SiO₂$ using a template-assisted method¹³³ and then used hightemperature synthesis by adding a specific quantity of mesoporous silica template to a mixture of CsBr and PbBr₂.

3 Modification of all-inorganic lead halide perovskite

Although all-inorganic lead halide perovskites have a great deal of potential for photocatalysis, however, pure halide perovskites typically have some issues, such as low stability, lack of active sites, and ineffective carrier extraction, which restrict the utilization of photocatalytic materials.¹³⁹⁻¹⁴² To improve the photocatalytic activity, several techniques have been developed, including ion doping, $143,144$ metal loading, $145,146$ creation of heterojunctions,^{147,148} and anion exchange.¹⁴⁹⁻¹⁵²

3.1 Ion-doping

Doping is a valuable modification strategy that adjusts the chemical structure of the lattice by incorporating some "impurities" to broaden the photoresponse range or enhance the separation of photogenerated carriers.¹⁵³⁻¹⁵⁶ To this end, researchers have explored methods of incorporating metal ions at the A-site and B-site. Generally speaking, A-site and B-site doping can be achieved through cation exchange or in situ synthesis. Mn^{2+} is the most common dopant ion in the B-site of all-inorganic lead halide perovskites.¹⁵⁷⁻¹⁶² Liu et al. prepared Mn^{2+} -doped CsPbBr₃ to improve the efficiency of CO₂ reduction¹⁶³ (Fig. 4). The results showed that the yields of CO and CH₄ reached 1917 µmol g^{-1} and 82 µmol g^{-1} , which were 14.2 and 1.4 times that of CsPbBr₃. In addition, other metal atoms have also been successfully doped into all-inorganic lead-halide perovskites. Patil et al. doped CsPbI₂Br nanocrystals with Sr^{2+} to obtain more stable solar cells,¹⁶⁴ and the CsPb_{0.98}Sr_{0.02}I₂Br device maintained more than 85% of its initial efficiency for 100 hours under ambient conditions. Shyamal et al. partially substituted Pb^{2+} with Fe^{2+} to create Fe^{2+} -doped CsPbBr₃,¹⁶⁵ which was utilized in ethyl acetate/aqueous solution for the photocatalytic reduction of CO₂. Dong et al. produced Co^{2+} doped CsPbBr₃/Cs₄PbBr₆ for CO₂ reduction with 1835 mol per g CO2 yield.¹⁶⁶ All-inorganic lead-halide perovskites are also doped with new ions. In addition to equivalent doping,

Fig. 4 TEM images of Mn-doped CsPb(Br/Cl)₃ mixed-halide perovskites (a) sample 1: the ratio of PbBr₂/MnCl₂ is 4 : 1, (b) sample 2: the ratio of PbBr₂/MnCl₂ is 2 : 1, (c) sample 3: the ratio of PbBr₂/MnCl₂ is 2 : 3, (d) sample 4: the ratio of $PbBr_2/MnCl_2$ is $3:7.^{163}$

heterovalent ions can also be introduced. Zhou et al. stabilized $CsPbBr₃$ by co-doping Na⁺, and the results showed that codoping metal ions significantly improved the thermal stability and optical properties of quantum dots.¹⁶⁷ Using calculations based on density functional theory, Wang et al. investigated how ${\rm Bi}^{3+}$ doping affected the structural,¹⁶⁸ electrical, and optical characteristics of CsPbBr₃, and the results revealed that Bi^{3+} doping can improve the stability.

Studies on A-site doping are becoming increasingly prevalent. Ru^{+} and K^{+} are a couple of alkali metal ions that have drawn increased interest as possible dopants. These dopants can be applied to boost the photoluminescence efficiency and stability of perovskite nanocrystals. For example, Huang et al. created K–CsPbBr₃ nanocrystals that maintained 97.9% of their initial intensity after 30 hours.¹⁶⁹ Ouaaka et al. assessed the electrical, optical, thermoelectric, and elastic characteristics of Rb -doped $CsPbBr₃$ by density functional theory. The findings demonstrated that $Rb_xCs_{1-x}PbBr₃$ had excellent ultraviolet absorption capabilities, a low range of $E_{\rm g}$, and enhanced thermal–electrical conductivity.¹⁷⁰

In brief, ion doping has been thoroughly investigated to modify the electronic structure or create new energy and charge transfer routes to enhance the optical, electrical, and structural stability of all-inorganic lead halide perovskites. By the interaction of excitons and dopants, doping can bring additional optical, electronic, and magnetic features in addition to increasing the photocatalytic efficiency.171,172

3.2 Heterojunction construction

The formation of a heterojunction at the interface between two distinct materials can efficiently improve the separation efficiency of photogenerated carriers, thus enhancing the photocatalytic performance. There are three types of heterojunctions suitable for photocatalysis: type II heterojunction, direct Z-type heterojunction, and S-type heterojunction. Different types of heterojunctions and their applications are summarized in Table 5.

3.2.1 Type-II heterogeneous junction. As exhibited in Fig. 5a, type II heterojunction consists of two semiconductors with two energy levels interlocked. When exposed to light, photogenerated holes will be transfer from the semiconductor with lower valence band to the other semiconductor with higher valence band; meanwhile, photogenerated electrons will be excited from the semiconductor with higher conduction band to other semiconductor with lower conduction band for reduction, promoting the spatial separation of charge carriers.¹⁹⁷ Interestingly, the system of type-II heterojunctions not only enhances the photocatalytic ability but also improves the stability of all-inorganic lead-halide perovskites. Wang et al. developed a layer-by-layer $NiO_x/CsPbBr₃/TiO₂ planar II hetero$ junction photocatalyst; the system demonstrated a 7-fold increase in photoactivity compared to CsPbBr₃.¹⁹⁸ Kamat et al. reported a quasi-type II $CsPbBr₃-CdS$ core–shell heterojunction with significantly improved stability and photocatalytic performance.¹⁷⁸ Yin et al. reported an efficient CsPbBr₃/CdSe heterojunction photocatalytically to reduce $CO₂$ employing water as an electron donor in organic solutions.¹⁹⁹ The type II heterojunction with strong electronic coupling of the Pb–Se and Br–Cd bonds between CdSe and $CsPbBr₃$ facilitated the transfer of electrons, and the CO yield of the main product reached 115.26 µmol g^{-1} , which was 4.6 times higher than that of CsPbBr₃. **Excel of the state of the**

However, the type II heterojunction still has some issues: on the one hand, the oxidizing capacity of two semiconductor photocatalysts decreased by the separation of photogenerated electron–holes; on the other hand, the presence of holes prevents the transfer of electron–holes between surfaces in other catalysts.

3.2.2 Z-type heterogeneous junction. Z-type heterojunction also consists of two semiconductors with an alternating band arrangement (Fig. 5b). Under photoexcitation, the photogenerated holes of the semiconductor with the higher valence band will recombine with the photogenerated electrons from the semiconductor with the lower conduction band. The Z-type heterojunction structure can maintain the photocatalyst in the proper valence band position and can spatially separate electron-hole pairs to enhance redox capability.¹⁹⁵ Jiang et al. created an all-solid Z-type heterojunction by connecting CsPbBr₃ with -Fe₂O₃, and this Z-type photocatalyst²⁰⁰ demonstrated a six-fold improvement in photocatalytic activity to convert $CO₂$ into fuel (CO and CH₄). Xue et al. fabricated a waterstable Z-type Ag/CsPbBr3/Bi₂WO₆ photocatalyst for the degradation of rhodamine B, and the catalyst degraded rhodamine B at a rate of 93.9% in 120 minutes, which was 4.41 times faster than Bi_2WO_6 ¹⁹⁵

It should be noted that unanticipated side effects will result from Z-type heterojunction. The Z-type heterojunction increases the electron and hole-driving force of photogenerated chemical reactions; however, half of the electrons and holes produced during the photosynthesis process are lost. Therefore, when designing and building all-inorganic lead-halide perovskitebased heterojunction photocatalysts, the reaction process and the necessary redox potential should be taken into account.

3.2.3 S-type heterogeneous junction. As exhibited in Fig. 5c, the S-type heterojunction is formed by the interlaced structure of the reduced semiconductor photocatalyst with

a low work function and high Fermi level as well as the oxidized semiconductor photocatalyst with a high work function and low Fermi level.²⁰¹ The S-type heterojunction achieves the spatial

Fig. 5 Mechanism diagram of type-II heterojunction (a); mechanism diagram of Z-scheme heterojunction (b); mechanism diagram of S-scheme heterojunction (c).

separation of photogenerated electron–holes in the semiconductor with stable redox ability through the three methods of built-in electric field, energy band bending, and electrostatic contact.^{202,203} Zhang et al. created CsPbBr₃ quantum dot/BiOBr nanosheets to reduce $CO₂$ with an electron consumption rate of 72.3 mol g^{-1} h⁻¹, which was 4.1 and 5.7 times higher than that of single CsPbBr₃ and BiOBr, respectively.²⁰⁴ Xu et al. also created $TiO₂/CsPbBr₃$ S-type heterojunctions, which exhibited higher CO₂ reduction rates.²⁰⁵ Pu et al. prepared CsPbBr₃/ α - $Fe₂O₃$ S-type heterojunction,²⁰⁶ and the electron consumption rate was 3.38 mmol g^{-1} $\mathrm{h}^{-1},$ which was 2.4 times of that of the original CsPbBr₃.

In conclusion, all-inorganic halide perovskites are highly advantageous for photocatalysis due to their high absorption coefficient, defect tolerance, and variable band position. An extensive density of active sites, strong stability, and recyclability are also necessary for photocatalysts in addition to effective charge separation and transfer. In general, it is difficult for single-component halide perovskite photocatalysts to meet all these requirements. Integrating heterostructures of different functional materials into a single system through precise design is a common strategy to improve semiconductor performance because interactions between different components create synergistic effects. Consequently, halide-based perovskite heterostructures exhibit higher photocatalytic performance. RSC Advances

separation of photographical distribution-bids in the semi-bora distribution schemes are able to the product on the creation of the creation of the semi-bidde of the creation of the semi-bidde or semi-bidde

3.3 Other modification methods

3.3.1 Anion exchange method. By altering the X element in $CsPbX₃$, the anion exchange method could enhance the photocatalytic performance. Nedelcu et al. carried out anion exchange on CsPbX₃ (Cl, Br, I);¹²⁰ the results showed that this exchange can easily tune the emission color over the entire visible range. Guo et al. reported the use of mixed halide chalcogenides CsPb(Br_x/Cl_{1-x})₃ (x = 0.7, 0.5, 0.3) to reduce CO₂, which proceeded for 9 h under simulated sunlight with great stability and selectivity for the conversion of $CO₂$ to CO and CH₄.²⁰⁷ Zhao et al. successfully oxidized toluene using an anionexchange synthesis of CsPbBr_xCl_{3−x}/TiO₂ composite catalyst.²⁰⁸ Faceting and morphological adjustment can also improve the photocatalytic activity of all-inorganic lead halide perovskites. Das et al. prepared $CsPbBr₃$ nanocrystals by adjusting the (110) and (200) facets and found that $CsPbBr₃$ exhibits shapedependent optoelectronic properties.²⁰⁹

3.3.2 Ligand modification. The surface modification of allinorganic lead halide compounds,^{210,211} such as ligand modification,²¹²⁻²¹⁴ can also increase their stability and photocatalytic performance. Surface ligands play a key role in forming perovskites, which not only affect the nucleation and growth processes but are also extremely important for charge transport and structural stability.²¹⁵⁻²¹⁷

3.3.3 Encapsulation. The resistance of all-inorganic lead halide perovskites to moisture, oxygen, light, and high temperatures is still a significant challenge because of their intrinsic ionic characteristics, which restricts their further development and practical applications.^{218,219} Efforts have been made to encapsulate it in various materials over the years. It has

been demonstrated that encapsulation with inert materials is a practical and efficient technique to avoid decomposition and increase stability against treatment conditions involving light, heat, and water.²²⁰ Silica, organic polymers, metal oxides, and metal salts are some examples of the various protective materials that have been proposed.²²¹ It turns out that enhancing the thermal and photostability of mesoporous $SiO₂$ by incorporating perovskite nanocrystals is a wise decision. Liang et al. evaluated the difference in the optical stability before and after encapsulating CsPbBr₃ in nano-SiO₂.²²² These findings indicate that the $SiO₂$ shell can significantly increase the photothermal stability of the shell by successfully restraining anion exchange and photodegradation.

In addition to ion doping and heterostructure, other modi fication methods such as anion exchange, surface ligand modification, and encapsulation can improve the stability of allinorganic lead halide perovskites while maintaining high photocatalytic activity. All-inorganic lead halide perovskites typically consist of an all-inorganic core capped with organic ligands. We hope to find the most suitable ligands for surface passivation that will bring out the best and unique properties of the perovskite, thus broadening its applicability. Furthermore, encapsulation with materials has been proven to be a feasible and effective way to prevent decomposition and improve stability to survive water, light, and heat treatment conditions.

The two problems of low photocatalytic efficiency and poor stability of all-inorganic lead halide perovskites and the proposed solutions were already mainly discussed. As mentioned above, (1) adding dopants to the photocatalytic system can increase the active sites of the photocatalyst to promote adsorption capacity and redox reactions. By introducing appropriate doping metal ions, especially transition metal ions, the E_g of the catalyst can be adjusted, and the recombination of electrons and holes can be suppressed; (2) the construction of heterojunction nanocomposites is considered as an alternative strategy to promote all-inorganic lead halide perovskite photocatalysts. Coupling different types of cocatalysts with all-inorganic lead halide perovskites can induce the separation of photogenerated carriers and maximize the photocatalytic efficiency; (3) the instability problem of all-inorganic lead halide perovskites could be solved. The top priority is to build a protective layer or encapsulate ligands. The existence of a protective layer can isolate the perovskite from the external environment and prevent its interaction.

4 Applications of all-inorganic halide perovskites

Environmental protection and sustainable energy development are two major problems. Green, efficient storage, and renewable solar energy can be achieved using solar radiation to form chemical fuels, which are hydrogen and oxygen (from water splitting) or methane (from $CO₂$ reduction). The attractive optical properties of all-inorganic halide perovskites (e.g., high absorption coefficient in the UV-visible region, tunable band gap, and high PLQY) make them suitable candidates for solar-

driven photocatalytic applications. This section will provide an overview of the current state of development for all-inorganic lead halide perovskites in photocatalytic pollutant degradation, $CO₂$ reduction, and $H₂$ evolution.

4.1 Photocatalytic hydrogen production

H2, as an ideal clean energy source in the 21st century, is considered as an alternative to fossil fuels. Photocatalytic hydrolysis for hydrogen production has potential applications, in which the photocatalyst $CsPbX₃$ has been widely utilized.²²³–²²⁵ The balance between photocatalytic activity and stability of $CsPbBr₃$ is achieved through the rational control of surface ligands. Wang et al. successfully achieved photocatalytic hydrogen evolution by synthesizing CsPbBr₃/Pt-TiO₂ composites.²²⁶ Song et al. prepared the CsPbBr₃@polyaniline, which was stable even in an aqueous solution and had a photocatalytic hydrogen generation efficiency of 4.81 mmol (h $^{-1}\,\mathrm{g}^{-1}$). 227 Xiang et al. utilized Zn^{2+} -doped CsPbBr₃ nanocrystals to directly reduce hydrogen atoms in water, which exhibited excellent photocatalytic activity and enhanced hydrogen production efficiency.²²⁸ Sun et al. developed a new CsPbBr₃ nanocrystalline coupled NiFe-LDH photocatalyst for high-efficiency photocatalytic CO_2 reduction,²²⁹ and the photocatalyst's optimum electron consumption rate was 39.58 mol g^{-1} h⁻¹, which was higher than that of pristine NiFe-LDH. Review Wave the motion place is a section will provide an 4.2 Photonalytic erduction of Ca₂
notesting. This is a complete the access are determined on the access are also associated to the common Ca₂
notes Articles. T

Low-polarity solvents can be utilized to produce stable reaction conditions for photocatalytic hydrogen production. Sun et al. produced 0.8 mol per g hydrogen during 8 hours of simulated solar irradiation using ethyl acetate.²³⁰ In hydrogen halide (HX, $X = Br$, I) solutions, all-inorganic lead halide perovskites also show high photocatalytic hydrogen generation efficiency, for example, $CsPbBr_{3-x}I_x/Pt$ exhibited excellent hydrogen production performance with 224 mol h^{-1} in saturated aqueous HBr solution.²³¹

The attractive optical properties of all-inorganic halide perovskites (e.g., high absorption coefficient in the UV-visible region, tunable $E_{\rm g}$, and high PLQY) make them suitable candidates to produce hydrogen. Despite the exciting progress, the field is still in its infancy and there is still much room for development in designing targeted reaction systems, improving the stability and efficiency, and eliminating the toxicity of halide systems in converting solar into chemical energy.

4.2 Photocatalytic reduction of $CO₂$

 $CO₂$ and other greenhouse gases have been rapidly accumulating in the atmosphere²³² due to mankind's overreliance on fossil fuels, leading to severe and permanent effects on the ecosystem.^{233,234} China is supposed to reach a "carbon peak" by 2030,²³⁵ indicating that greenhouse gas emissions play an important role in environmental issues,; thus, photocatalytic reduction of $CO₂$ is considered the most promising method.²³⁶–²³⁹ Due to their outstanding qualities, such as affordability, simplicity of the synthesis method, visible light absorption, high $CO₂$ adsorption surface area, and adjustable structure, all-inorganic lead halide perovskites have been proved as effective catalysts.²⁴⁰⁻²⁴⁶ The all-inorganic lead-halide perovskite materials generate electron–hole pairs by absorbing solar energy, and the generated electrons can reduce $CO₂$ to high value-added chemicals such as $CO²⁴⁷, CH₄,²⁴⁸, CH₃OH, ²⁴⁹$ $HCHO²⁵⁰ HCOOH¹⁹⁶$ and $C₂H₄²⁵¹$

Hou et al. accomplished $CO₂$ reduction with CsPbBr₃ quantum dots in ethyl acetate/ H_2O solution with reduction product yields of 4.3, 1.5, and 0.1 mol g^{-1} h⁻¹ for CO, CH₄, and H_2 , respectively, where the CO_2 reduction selectivity was approximately $100\%^{230}$ (Fig. 6). Currently, the surface modification of $CsPbX₃$ or the creation of multi-component composites is the most cost-effective and promising solution to several issues with pure $CsPbX_3$ in the photocatalytic reduction of CO_2 . Xu et al. fabricated CsPbBr₃/GO nanocomposites, which showed a CO₂ reduction rate of 23.7 mol h^{-1} g^{-1} .¹⁷⁶ Additionally, to increase the effectiveness of $CO₂$ reduction, all-inorganic lead halide perovskites combined with other substances could generate heterojunctions. Wang et al. created a 0D/2D heterojunction photocatalyst with $CsPbBr₃/Bi₂WO₆$ nanosheets for the photocatalytic reduction of CO₂; the yield was 503 mol g^{-1} , which was 9.5 times greater than that of a single $CsPbBr₃.²⁵²$

The humidity stability, $CO₂$ capture capacity, and charge separation efficiency were significantly increased when $CsPbBr₃$ nanocrystals combined with metal–organic frameworks (MOFs) for the photocatalytic reduction of $CO₂$.²⁵³ The performance of perovskite nanocrystals can be significantly influenced by the special structure of MOFs. Wan et al. combined $CsPbBr₃$ and UiO-66 $(NH₂)²⁵⁴$ to create a composite photocatalyst with $CsPbBr₃$ QDs/UiO-66(NH₂) MOF structure, which was able to convert $CO₂$ to chemical fuel in a non-aqueous system. The

Fig. 6 Solar reduction CO₂ into fuels under 300 W Xe lamp irradiation by CsPbBr₃ quantum dots: 8.5 nm CsPbBr₃ quantum dots (a) and tunable $CsPbBr₃$ quantum dots with different particle sizes (b).²³⁰

reported photocatalytic reduction of $CO₂$ by all-inorganic lead halide perovskites is summarized in Table 6.

All-inorganic lead halide perovskites are sensitive to water or other polar solvents, resulting in insufficient activity and low selectivity of all-inorganic lead halide perovskites. Therefore, it is considered a feasible method to improve the activity and stability of photocatalytic $CO₂$ reduction by means of element doping, morphology control, and construction of heterojunctions.

4.3 Contaminant degradation

Many harmful pollutants are emitted into the air, water, and soil as a result of the growth of the industry.²⁵⁹⁻²⁶¹ Photocatalysis is an effective method to degrade pollutants.²⁶²⁻²⁶⁴ However, the efficiency of photocatalytic degradation of pollutants in water is still limited due to the low efficiency of solar energy utilization and the rapid recombination of photogenerated holes and electrons.²⁶⁵–²⁶⁹ Among these materials for the photocatalytic degradation of pollutants, all-inorganic lead halide perovskite photocatalysts can efficiently utilize solar energy and have many advantages in terms of efficiency, greenness, and cost.⁶⁰ In particular, the photocatalytic degradation of organic dyes, $270-272$ phenols,^{273–275} and antibiotics^{276–278} in water has generated a lot of interest in all-inorganic lead halide perovskites.

Among the various pollutants, synthetic dyes such as rhodamine B,²⁷⁹⁻²⁸¹ Sudan red III,²⁸²⁻²⁸⁵ methyl red,²⁸⁶⁻²⁸⁸ methyl violet,²⁸⁹⁻²⁹³ malachite green,^{294,295} acid black dye,²⁹⁶⁻²⁹⁹ Congo red,³⁰⁰ and methyl orange³⁰¹⁻³⁰³ are common. Feng et al. created $CSPb(Br_{1-x}Cl_x)_3$ -Au nanoheterojunction materials,²⁷¹ which were used to decompose Sudan red III pollutants, and the results showed that after 6 hours of visible light exposure, the heterostructures had degraded 71% of Sudan dye. Liu et al. prepared CsPbBr₃ perovskite quantum dots/polymethyl methacrylate composites by ball milling; the degradation rate of rhodamine B by the composites under visible light reached 92.2% within 60 min.³⁰⁴

Besides dyes, the abuse of broad-spectrum antibiotics $(ciproflox (or 305-307 norflox (or 308-311 2-mercap to benzothia$ zole, 312 and tetracycline hydrochloride³¹³⁻³¹⁵) causes harm to ecosystems and poses a threat to human health. Using allinorganic lead halide perovskites, antibiotics can be successfully removed from water sources. Chen et al. produced allinorganic $CsPbBr₃$ calcium titanite quantum dot materials by anti-solvent precipitation,³¹⁶ which was successfully used to remove antibiotic residues from ethanol, showing excellent photocatalytic activity. Zhao et al. synthesized Ag–CsPbBr₃/g- C_3N_4 ternary composites with excellent photocatalytic activity by loading nano-Ag on the surface of $CsPbBr_3/bulky g-C_3N_4$

Fig. 7 Possible mechanism diagram for cephalosporin antibiotics degradation with Ag–CsPbBr₃/CN composite under visible light irradiation.³¹⁷

Table 7 Summary of common all-inorganic lead-halide perovskites in terms of synthesis, modification, and application

composites³¹⁷ (Fig. 7), which were applied to the visible light catalytic degradation of 7-aminocephalosporanic acid; 7%-Ag– $CsPbBr₃/g-C₃N₄$ composites showed excellent photocatalytic activity, and 92.79% of 7-aminocephalosporanic acid was

degraded. The stability and electron–hole separation rate of photocatalytic reactions can generally be improved by the heterostructures. Zhao et al. created type II CsPbCl₃ heterostructures,²⁷⁶ and the catalysts showed excellent photocatalytic

performance for the degradation of penicillin–6-aminopenicillins acid. Liu et al. synthesized stable $CsPbBr₃-TiO₂$ heterojunction, which was applied in the visible light-driven photodegradation of tetracycline hydrochloride;⁵⁶ 80% of tetracycline hydrochloride was degraded in this experiment.

Oxygen activation typically initiates photodegradation reactions by generating reactive oxygen species (such as \cdot OH and \cdot O^{2−}), which react with the target pollutants. When allinorganic lead halide perovskites are used as photocatalysts to breakdown organic dyes, some encouraging results have been obtained. All-inorganic lead halide perovskites have attracted great interest due to their excellent optoelectronic properties. Table 7 summarizes the application of all-inorganic lead halide perovskites in the field of photocatalysis, including $CO₂$ reduction, H_2 evolution, and degradation of pollutants in water. Inspired by natural photosynthesis, artificial photocatalysts that can convert solar energy into useable fuels and chemicals have been extensively studied. The structure of photocatalytic systems has been extensively studied to improve the photocatalytic activity; however, the problems of poor light absorption and conversion efficiency still need to be improved. Researchers are investigating possible strategies to improve the light harvesting and conversion efficiency of efficient photocatalysts. In addition to the effectiveness of the photocatalyst, the environmental friendliness, durability, and recyclability of the materials have also been focused on. **PSC** Advances Server Access Article Controlling Common Access Article is the controlling and the common access Article is licensed under the common access Article is licensed under the common access Article is licensed un

5 Challenges and prospects

All-inorganic lead halide perovskites have made signicant progress in the field of photocatalysis. However, the strong ionic character of this substance makes its interior structure less stable. In addition, the existing reports have insufficient research on the growth kinetics of all-inorganic lead halide perovskite in the actual manufacturing process, which makes it difficult to control the formation and leads to low practical application efficiency, mainly due to the following aspects.

(1) The toxicity of lead is the main reason that restricts the actual production and large-scale commercial application of allinorganic lead halide perovskites. Lead poisoning in humans can result in major health issues such as renal failure, nerve damage, and other disorders even at very low exposure levels.

(2) Due to the inherent ionic nature of all-inorganic lead halide perovskites, the resistance to moisture, oxygen, light, and high temperatures remains a significant challenge, and the perovskite structure is destroyed when exposed to polar solvents or water, which reduces its photocatalytic activity and limits practical application.

(3) The corresponding mechanism of photocatalysis has been extensively studied, but the precise redox pathway is still unknown.

(4) Inorganic lead halide perovskites have weak thermal and light stability and are easily harmed by external stimuli like heat, light, and oxygen.

Future enhancements will mostly focus on the following areas in response to the aforementioned issues.

(1) To reduce the toxicity of inorganic lead halide perovskites, it is necessary to develop efficient and environmentfriendly lead-free metal halide perovskites by replacing Pb with other transition metals (such as Sn, Ge, Bi, and Ag). However, the activity of lead-free perovskites will be reduced. Therefore, the development of such lead-free photocatalysts should be combined with several improvement strategies.

(2) To simultaneously maintain high stability and catalytic activity, the A-site is modified with mixed ions. Mixing organic cations and inorganic cations to prepare organic–inorganic hybrid halide perovskites is a promising method. By this way, organic components can be added to improve the photocatalytic activity while retaining the stability of inorganic components. Common hybrid organic cations include FA⁺ and MA⁺ ; however, the ratio between organic and inorganic ions needs to be further refined.

(3) The development of novel protective layers or ligands to form a core–shell structure should be taken into consideration to address the deciencies of inorganic perovskite's poor stability. Stable co-catalysts can be developed to form the same structure as various heterojunctions that match the energy bands of inorganic lead halide perovskites.

 (4) Photocatalysis can be widely used in various fields. Exploring novel photocatalytic applications, such as (i) removal of organic matter and heavy metals in soil. Inorganic lead halide perovskite catalysts have strong redox capabilities and have broad application prospects in remediating soil organic matter and heavy metals. (ii) Organic synthesis: photocatalytic organic synthesis is an economical and green synthesis method that uses sunlight to drive chemical reactions under mild conditions. Many photoreduction reactions proceed via free radicals or radical ion intermediates. This reactive intermediate can be easily and efficiently generated by visible light. (iii) Environmental monitoring: with the continuous development of the chemical industry, the discharge of various pollutants has led to an increasing demand for the detection of various heavy metals and other pollutants present in waters. Utilizing the luminescent properties of all-inorganic lead halide perovskites is considered a highly sensitive detection method.

In summary, the development of catalysts with excellent catalytic properties is crucial for practical applications. However, how to improve the activity of the catalyst while maintaining the stability of the catalyst requires more research. The problems and challenges encountered so far will motivate researchers to develop more effective perovskite catalysts in the future.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by Fundamental Research Funds for the Central Universities (2572022BA09), Natural Science Foundation of Heilongjiang Province of China (LH2023D003).

References

- 1 L. Wang, S. Li, I. M. Ahmad, G. Zhang, Y. Sun, Y. Wang, C. Sun, C. Jiang, P. Cui and D. Li, Sci. Total Environ., 2023, 887, 164055.
- 2 S. Kuskaya, F. Bilgili, E. Mugaloglu, K. Khan, M. E. Hoque and N. Toguc, Renewable Energy, 2023, 206, 858–871.
- 3 A. Wazeer, A. Das and S. Vidya, Trans. Indian Inst. Met., 2023, 76, 1155–1163.
- 4 J. Zheng and B. Zeng, Sustain. Energy Technol. Assess., 2023, 57, 103303.
- 5 A. Fujishima and K. Honda, Nature, 1972, 238, 37–38.
- 6 J. Luo, Z. Wang, H. Jiang, S. Liu, F.-Q. Xiong and J. Ma, Langmuir, 2020, 36, 4637–4644.
- 7 C. Xie, W. Chen, S. Du, D. Yan, Y. Zhang, J. Chen, B. Liu and S. Wang, Nano Energy, 2020, 71, 104653.
- 8 T. Paik, M. Cargnello, T. R. Gordon, S. Zhang, H. Yun, J. D. Lee, H. Y. Woo, S. J. Oh, C. R. Kagan, P. Fornasiero and C. B. Murray, ACS Energy Lett., 2018, 3, 1904–1910.
- 9 L. Yin, X. Hai, K. Chang, F. Ichihara and J. Ye, Small, 2018, 14, 1704153.
- 10 M. Shen, Z. Yan, L. Yang, P. Du, J. Zhang and B. Xiang, Chem. Commun., 2014, 50, 15447–15449.
- 11 L. Guo, C. Zhong, L. Shi, L. Ju, X. Wang, D. Yang, K. Bi, Y. Hao and Y. Yang, Adv. Opt. Mater., 2019, 7, 1801403.
- 12 Y. Zou, J. W. Shi, D. Ma, Z. Fan, L. Cheng, D. Sun, Z. Wang and C. Niu, ChemSusChem, 2018, 11, 1187–1197.
- 13 P. Kumar, S. Kataria, S. Roy, A. Jaiswal and V. Balakrishnan, ChemistrySelect, 2018, 3, 7648–7655.
- 14 D. Zeng, L. Xiao, W. J. Ong, P. Wu, H. Zheng, Y. Chen and D. L. Peng, ChemSusChem, 2017, 10, 4624–4631.
- 15 F. He, Z. Wang, Y. Li, S. Peng and B. Liu, Appl. Catal., B, 2020, 269, 118828.
- 16 C. Xu, P. Ravi Anusuyadevi, C. Aymonier, R. Luque and S. Marre, Chem. Soc. Rev., 2019, 48, 3868–3902.
- 17 E. E. Barton, D. M. Rampulla and A. B. Bocarsly, J. Am. Chem. Soc., 2008, 130, 6342–6344.
- 18 T. Arai, S. Sato, T. Kajino and T. Morikawa, Energy Environ. Sci., 2013, 6, 1274–1282.
- 19 Y. Chen, B. Jia, G. Qin, H. Zhao, L. Han and P. Lu, RSC Adv., 2023, 13, 15055–15062.
- 20 A. Dabbous, E. Colson, D. Chakravorty, J.-M. Mouesca, C. Lombard, S. Caillat, J.-L. Ravanat, F. Dubois, F. Denes, P. Renaud and V. Maurel, Chem.–Eur. J., 2023, 29, e202300303.
- 21 M. Asim, S. Zhang, B. Maryam, J. Xiao, C. Shi, L. Pan and J.-J. Zou, Appl. Surf. Sci., 2023, 620, 156787.
- 22 X. Li, J. Hu, Y. Deng, T. Li, Z.-Q. Liu and Z. Wang, Appl. Catal., B, 2023, 324, 122243.
- 23 F. Wang, J. Li, X. Yu, H. Tang, J. Xu, L. Sun and Q. Liu, J. Mater. Sci. Technol., 2023, 146, 49–60.
- 24 X. Feng and L. Zhang, J. Mater. Sci. Technol., 2023, 156, 54– 63.
- 25 A. U. Hasanah, P. L. Gareso, N. Rauf and D. Tahir, ChemBioEng Rev., 2023, 10, 698–710.
- 26 A. Sinha, S. K. Sahu, S. Biswas and T. K. Ghorai, RSC Adv., 2023, 13, 22029–22042.
- 27 Y. Xue, Y. Guo, Z. Liang, H. Cui and J. Tian, J. Colloid Interface Sci., 2019, 556, 206–213.
- 28 C. Lu, E. Wu, C. Li, W. Dou, Y. Lian, Y. Liang, X. Xiang and H. Wang, J. Phys. Chem. Solids, 2021, 158, 110228.
- 29 R. Ranjan, M. Kumar and A. S. K. Sinha, Int. J. Hydrogen Energy, 2019, 44, 16176–16189.
- 30 N. Sharma, S. Swami, V. Shrivastava, R. Nair and R. Shrivastava, Mater. Today: Proc., 2021, 43, 3309–3317.
- 31 F. Cai, J. J. Ibrahim, Y. Fu, W. Kong, J. Zhang and Y. Sun, Appl. Catal., B, 2020, 264, 118500.
- 32 L. Gui, Y. Xu, Q. Tang, X. Shi, J. Zhang, B. He and L. Zhao, J. Colloid Interface Sci., 2021, 603, 252–258.
- 33 X. Wang, Z. Zhu, J. Jiang, R. Li and J. Xiong, Chemosphere, 2023, 337, 139206.
- 34 T. Xu, R. Wang, C. Gu and T. Jiang, Spectrochim. Acta, Part A, 2023, 299, 122801.
- 35 W. Ashraf, S. H. Parvez and M. Khanuja, Environ. Res., 2023, 236, 116715.
- 36 L. Li, H. Yang and P. Yang, J. Colloid Interface Sci., 2023, 650, 1312–1318.
- 37 S. Liu, X. Zhou, J. Qin, C. Wei and Y. Hu, J. Colloid Interface Sci., 2023, 635, 59–71.
- 38 Q. Ding, X. Zou, J. Ke, Y. Dong, Y. Cui and H. Ma, J. Colloid Interface Sci., 2023, 649, 148–158.
- 39 Z. Jiang, Q. Long, B. Cheng, R. He and L. Wang, J. Mater. Sci. Technol., 2023, 162, 1–10.
- 40 R. Del Sole, C. Lo Porto, S. Lotito, C. Ingrosso, R. Comparelli, M. L. Curri, G. Barucca, F. Fracassi, F. Palumbo and A. Milella, Molecules, 2023, 28, 5131.
- 41 A. Saleem, F. F. Alharbi, M. N. Ashiq, S. Manzoor, S. I. Abbas Shah, K. Z. Khan, S. Aman, N. Ahmad, H. A. Alzahrani and M. Messali, Phys. Status Solidi A, 2023, 220, 2200734. Review Saccess Articles. Articles. Article 2024. Downloaded on 07 February 2024. Downloaded on 5/2023. Downloaded on 5/25/2023. Downloaded on 5/25/2023. Download article is licensed under a Creative Commons Article is lic
	- 42 Y. Yang, Y. Sun and Y. Jiang, Mater. Chem. Phys., 2006, 96, 234–239.
	- 43 P. Priyadarshini, S. Das and R. Naik, RSC Adv., 2022, 12, 9599–9620.
	- 44 X. Zhu, Y. Lin, J. San Martin, Y. Sun, D. Zhu and Y. Yan, Nat. Commun., 2019, 10, 2843.
	- 45 P. Priyadarshini, S. Senapati and R. Naik, Renewable Sustainable Energy Rev., 2023, 186, 113649.
	- 46 J. M. Frost, K. T. Butler, F. Brivio, C. H. Hendon, M. van Schilfgaarde and A. Walsh, Nano Lett., 2014, 14, 2584–2590.
	- 47 A. Walsh, J. Phys. Chem. C, 2015, 119, 5755–5760.
	- 48 S. R. Mulani, S. Bimli, E. Choudhary, R. Bunkar, U. A. Kshirsagar and R. S. Devan, Chemosphere, 2023, 340, 139890.
	- 49 D. Komaraiah, E. Radha, J. Sivakumar, M. V. Ramana Reddy and R. Sayanna, Opt. Mater., 2020, 108, 110401.
	- 50 Q. Zhang, X. Deng, C. Tan, Y. Zhou, X. Chen, X. Bai, J. Li, B. Tang, S. Li and H. Lin, J. Chem. Phys., 2020, 153, 024703.
	- 51 Z. Lu, J. Gao, S. Rao, C. Jin, H. Jiang, J. Shen, X. Yu, W. Wang, L. Wang, J. Yang and Q. Liu, Appl. Catal., B, 2024, 342, 123374.
- 52 Q. Guo, J.-D. Zhang, Y.-J. Chen, K.-Y. Zhang, L.-N. Guo, Q.-C. Shan, J.-L. Lu, X.-H. Duan and L.-Z. Wu, Chem. Commun., 2023, 59, 4189–4192.
- 53 A. Sabbah, I. Shown, M. Qorbani, F.-Y. Fu, T.-Y. Lin, H.-L. Wu, P.-W. Chung, C.-I. Wu, S. R. M. Santiago, J.-L. Shen, K.-H. Chen and L.-C. Chen, Nano Energy, 2022, 93, 106809. PSC Advances Articles. Articles. Articles. Articles. Article is licensed on 5/25/2023. Downloaded on 5/25/2023. Downloaded on 5/25/2023. This article is licensed under a strained on 5/25/2023. This article is licensed unde
	- 54 K. Su, S.-X. Yuan, L.-Y. Wu, Z.-L. Liu, M. Zhang and T.-B. Lu, Small, 2023, 19, 2301192.
	- 55 H. Peng, L. Duan, W. Xie, C. Shao, H. Cao, D. Wang, S. Rao and H. Guo, Chemosphere, 2024, 346, 140614.
	- 56 C. Liu, X. Qian, Q. Wei, Z. Chen, J. Chen, W. Wang, X. Chen, J. Gao, Y. Liu and L. Xie, J. Cleaner Prod., 2022, 365, 132830.
	- 57 R.-J. Huang, Z.-K. Qin, L.-L. Shen, G. Lv, F. Tao, J. Wang and Y.-J. Gao, J. Mater. Chem. A, 2023, 11, 6217–6225.
	- 58 S. Feng, S. Ning, L. Wang, J. Zhao, J. Ou, Z. Wu, S. Luo, Z. Lin, K. Yan, C. Wu and Y. Xu, ACS Appl. Energy Mater., 2022, 5, 6248–6255.
	- 59 N. Luo, C. Chen, D. Yang, W. Hu and F. Dong, Appl. Catal., B, 2021, 299, 120664.
	- 60 S. Gull, S. Batool, G. Li and M. Idrees, Front. Chem., 2022, 10, 1020484.
	- 61 D. Wang, C. Miao, H. Li, B. Yu, W. Wang, Y. Wang, G. Che, C. Liu and B. Hu, Mater. Res. Bull., 2024, 170, 112552.
	- 62 W. Liu, H. Xie, X. Guo, K. Wang, C. Yang, N. Wang and C. Ge, Opt. Mater., 2023, 136, 113398.
	- 63 J. Cui, C. Xu, Z. Jin, H. Liu, R. Hu and F. Liu, Environ. Sci. Pollut. Res., 2023, 30, 96875–96890.
	- 64 H. Mohan, S. Vadivel and T. Shin, Ultrason. Sonochem., 2023, 101, 106650.
	- 65 H. Zhang, F. Meng, H. Wei, W. Yu and S. Yao, J. Colloid Interface Sci., 2023, 652, 1282–1296.
	- 66 T. Ishii, A. Anzai, A. Yamamoto and H. Yoshida, Appl. Catal., B, 2020, 277, 119192.
	- 67 Q. Li, X. Bai, J. Luo, C. Li, Z. Wang, W. Wu, Y. Liang and Z. Zhao, Nanotechnology, 2020, 31, 375402.
	- 68 K. Sathiyamoorthy, A. Silambarasan, M. Navaneethan and S. Harish, Chemosphere, 2024, 348, 140575.
	- 69 D. E. Mazouzi, F. Djani, A. Soukeur, W. Bouchal, A. Manseri, K. Derkaoui, A. Martínez-Arias, A. Ksouri, F. Şen and M. M. Kaci, Surf. Interfaces, 2024, 44, 103581.
	- 70 G. E. de la Huerta-Hernández, J. Chávez-Carvayar, T. Rodríguez-Flores, I. Castro-Cisneros, A. Reyes-Montero and I. Hernández-Pérez, Environ. Sci. Pollut. Res., 2023, 30, 102986–103000.
	- 71 V. K. Amritha and S. Badhulika, New J. Chem., 2023, 47, 17897–17907.
	- 72 A. H. Jawhari, N. Hasan, I. A. Radini, K. Narasimharao and M. A. Malik, Nanomaterials, 2022, 12, 2985.
	- 73 A. S. Rodrigues, J. E. Silveira, J. Carbajo, J. A. Zazo, J. A. Casas, A. Fernandes, M. J. Pacheco, L. Ciriaco and A. Lopes, Environ. Sci. Pollut. Res., 2021, 28, 23822–23832.
	- 74 Y. Zhang, W. Wang, Y. Guo, Q. Shen and Z. Liu, J. Phys. Chem. Solids, 2021, 149, 109766.
	- 75 X. Chen, Q. Dong, S. Chen, Z. Zhang, X. Zhang, Y. Di, A. Jiang, D. Zhang and T. Li, Colloids Surf., A, 2023, 664, 131143.
- 76 F. Li, Z. Wu, X. Tang, X. Li, X. Liu, S. Yu, L. Wei and C. Yu, J. Water Process. Eng., 2023, 56, 104470.
- 77 S. Park, W. J. Chang, C. W. Lee, S. Park, H.-Y. Ahn and K. T. Nam, Nat. Energy, 2016, 2, 16185.
- 78 W. Ma, T. Jiang, Z. Yang, H. Zhang, Y. Su, Z. Chen, X. Chen, Y. Ma, W. Zhu, X. Yu, H. Zhu, J. Qiu, X. Liu, X. Xu and Y. Yang, Advanced Science, 2021, 8, 2003728.
- 79 F. Cao, D. Yu, W. Ma, X. Xu, B. Cai, Y. M. Yang, S. Liu, L. He, Y. Ke, S. Lan, K.-L. Choy and H. Zeng, ACS Nano, 2020, 14, 5183–5193.
- 80 J. H. Heo, D. H. Shin, J. K. Park, D. H. Kim, S. J. Lee and S. H. Im, Adv. Mater., 2018, 30, 1801743.
- 81 L. Wang, K. Fu, R. Sun, H. Lian, X. Hu and Y. Zhang, Nano-Micro Lett., 2019, 11, 52.
- 82 Y. Zhou, J. Chen, O. Bakr and O. Mohammed, ACS Energy Lett., 2021, 6, 739–768.
- 83 X. Li, W. Cai, H. Guan, S. Zhao, S. Cao, C. Chen, M. Liu and Z. Zang, Chem. Eng. J., 2021, 419, 129551.
- 84 Y. Huang, L. Zhang, J. Wang, B. Zhang, L. Xin, S. Niu, Y. Zhao, M. Xu, X. Chu, D. Zhang, C. Qu and F. Zhao, Opt. Lett., 2019, 44, 1908–1911.
- 85 Q. Mo, C. Chen, W. Cai, S. Zhao, D. Yan and Z. Zang, Laser Photonics Rev., 2021, 15, 2100278.
- 86 M. Liu, M. B. Johnston and H. J. Snaith, Nature, 2013, 501, 395–398.
- 87 Y. Zhou, Q. Gu, Y. Li, L. Tao, H. Tan, K. Yin, J. Zhou and S. Guo, Nano Lett., 2021, 21, 4861–4867.
- 88 Y. Zhao, J. Zhu, B. He and Q. Tang, Chem. Commun., 2021, 57, 7577–7580.
- 89 C. Ponti, G. Nasti, D. Di Girolamo, I. Cantone, F. A. Alharthi and A. Abate, Trends Ecol. Evol., 2022, 37, 281–283.
- 90 C. Sun, Y. Zhang, C. Ruan, C. Yin, X. Wang, Y. Wang and W. W. Yu, Adv. Mater., 2016, 28, 10088–10094.
- 91 H. C. Yoon, H. Kang, S. Lee, J. H. Oh, H. Yang and Y. R. Do, ACS Appl. Mater. Interfaces, 2016, 8, 18189–18200.
- 92 G. Jin, T. Liu, Y. Li, J. Zhou, D. Zhang, P. Pang, Z. Ye, Z. Xing, G. Xing, J. Chen and D. Ma, Nanoscale, 2022, 14, 919–929.
- 93 G. Xing, N. Mathews, S. S. Lim, N. Yantara, X. Liu, D. Sabba, M. Grätzel, S. Mhaisalkar and T. C. Sum, Nat. Mater., 2014, 13, 476–480.
- 94 S. Chen, K. Roh, J. Lee, W. K. Chong, Y. Lu, N. Mathews, T. C. Sum and A. Nurmikko, ACS Nano, 2016, 10, 3959–3967.
- 95 L. Dou, Y. M. Yang, J. You, Z. Hong, W. H. Chang, G. Li and Y. Yang, Nat. Commun., 2014, 5, 5404.
- 96 J. Ding, S. Du, Z. Zuo, Y. Zhao, H. Cui and X. Zhan, J. Phys. Chem. C, 2017, 121, 4917–4923.
- 97 W. Zhai, J. Lin, C. Li, S. Hu, Y. Huang, C. Yu, Z. Wen, Z. Liu, Y. Fang and C. Tang, Nanoscale, 2018, 10, 21451–21458.
- 98 A. Bhardwaj, K. Kundu, R. Sasmal, P. Acharyya, J. Pradhan, S. Kalita, S. S. Agasti and K. Biswas, Chem. Sci., 2023, 14, 7161–7169.
- 99 M. Wang, S. Wang, R. Chen, M. Zhu, Y. Liu, H. Ding, J. Ren, T. Xuan and H. Li, Coatings, 2023, 13, 1062.
- 100 H. Wei, T. Si, F. Xu, W. Fan, T. Yang, B. Cao, F. Juan, J. Xu and Y. Wu, Opt. Express, 2023, 31, 25298–25306.
- 101 Y. Chen, S. Lu, M. Nan, J. Xie, W. Shen, A. N. Aleshin, G. Cheng, S. Chen and W. Huang, Adv. Opt. Mater., 2023, 11, 2300473.
- 102 Y. Ma, F. Zheng, S. Li, Y. Liu, J. Ren, Y. Wu, Q. Sun and Y. Hao, ACS Appl. Mater. Interfaces, 2023, 15, 34862–34873.
- 103 A. Pieniazek, F. Dybala, M. P. Polak, L. Przypis, A. P. Herman, J. Kopaczek and R. Kudrawiec, J. Phys. Chem. Lett., 2023, 14, 6470–6476.
- 104 J. Hou, Z. Wang, P. Chen, V. Chen, A. K. Cheetham and L. Wang, Angew. Chem., Int. Ed. Engl., 2020, 59, 19434– 19449.
- 105 C. Zhang, W. Li and L. Li, Angew. Chem., Int. Ed. Engl., 2021, 60, 7488–7501.
- 106 J. Cai, K. Gu, Y. Zhu, J. Zhu, Y. Wang, J. Shen, A. Trinchi, C. Li and G. Wei, Chem. Commun., 2018, 54, 8064–8067.
- 107 Y. Tong, E. Bladt, M. F. Aygüler, A. Manzi, K. Z. Milowska, V. A. Hintermayr, P. Docampo, S. Bals, A. S. Urban, L. Polavarapu and J. Feldmann, Angew. Chem., Int. Ed. Engl., 2016, 55, 13887–13892. Review Water Access Articles. Articles. Article 22. Downloaded on 12. Literatury 2023. Downloaded on 5/25/2023. Downloaded on 5/25/2023. The Creative Commons Article is like the same of the same of the same of the same of
	- 108 J. Yan, Q. Wang, T. Wei, L. Jiang, M. Zhang, X. Jing and Z. Fan, ACS Nano, 2014, 8, 4720–4729.
	- 109 M. S. Sander, M. J. Côté, W. Gu, B. M. Kile and C. P. Tripp, Adv. Mater., 2004, 16, 2052–2057.
	- 110 M. Fu, J. Zhou, Q. Xiao, B. Li, R. Zong, W. Chen and J. Zhang, Adv. Mater., 2006, 18, 1001–1004.
	- 111 R. Wu, S. Gong, L. Wu, H. Yu, Q. Han and W. Wu, Phys. Chem. Chem. Phys., 2022, 24, 8303–8310.
	- 112 L. Protesescu, S. Yakunin, O. Nazarenko, D. N. Dirin and M. V. Kovalenko, ACS Appl. Nano Mater., 2018, 1, 1300– 1308.
	- 113 M. Chen, Y. Zou, L. Wu, Q. Pan, D. Yang, H. Hu, Y. Tan, Q. Zhong, Y. Xu, H. Liu, B. Sun and Q. Zhang, Adv. Funct. Mater., 2017, 27, 1701121.
	- 114 V. A. Hintermayr, A. F. Richter, F. Ehrat, M. Döblinger, W. Vanderlinden, J. A. Sichert, Y. Tong, L. Polavarapu, J. Feldmann and A. S. Urban, Adv. Mater., 2016, 28, 9478– 9485.
	- 115 L. Protesescu, S. Yakunin, M. I. Bodnarchuk, F. Krieg, R. Caputo, C. H. Hendon, R. X. Yang, A. Walsh and M. V. Kovalenko, Nano Lett., 2015, 15, 3692–3696.
	- 116 A. A. M. Brown, P. Vashishtha, T. J. N. Hooper, Y. F. Ng, G. V. Nutan, Y. Fang, D. Giovanni, J. N. Tey, L. Jiang, B. Damodaran, T. C. Sum, S. H. Pu, S. G. Mhaisalkar and N. Mathews, Chem. Mater., 2021, 33, 2387–2397.
	- 117 X. Li, Y. Wu, S. Zhang, B. Cai, Y. Gu, J. Song and H. Zeng, Adv. Funct. Mater., 2016, 26, 2435–2445.
	- 118 X. l. Zeng, L. x. Yu, K. l. Peng, Y. Yu, Y. k. Deng, Y. j. Zhao and Y. n. Xu, J. Alloys Compd., 2023, 945, 169213.
	- 119 Q. Pan, H. Hu, Y. Zou, M. Chen, L. Wu, D. Yang, X. Yuan, J. Fan, B. Sun and Q. Zhang, J. Mater. Chem. C, 2017, 5, 10947–10954.
	- 120 G. Nedelcu, L. Protesescu, S. Yakunin, M. I. Bodnarchuk, M. J. Grotevent and M. V. Kovalenko, Nano Lett., 2015, 15, 5635–5640.
	- 121 Y. Wang, J. Wang, M. Zhang, S. Zheng, J. Wu, T. Zheng, G. Jiang and Z. Li, Small, 2023, 19, e2300841.
- 122 A. Pan, B. He, X. Fan, Z. Liu, J. J. Urban, A. P. Alivisatos, L. He and Y. Liu, ACS Nano, 2016, 10, 7943–7954.
- 123 J. Leng, T. Wang, Z. K. Tan, Y. J. Lee, C. C. Chang and K. Tamada, ACS Omega, 2022, 7, 565–577.
- 124 Y. Yang, S. Wei, X. Kang, O. Tegus and D. Pan, J. Lumin., 2019, 211, 26–31.
- 125 C. M. Guvenc, A. Kocabas and S. Balci, J. Mater. Chem. C, 2023, 11, 3039–3049.
- 126 S. Sun, D. Yuan, Y. Xu, A. Wang and Z. Deng, ACS Nano, 2016, 10, 3648–3657.
- 127 X. Zhang, X. Bai, H. Wu, X. Zhang, C. Sun, Y. Zhang, W. Zhang, W. Zheng, W. W. Yu and A. L. Rogach, Angew. Chem., Int. Ed. Engl., 2018, 57, 3337–3342.
- 128 L. Rao, Y. Tang, C. Song, K. Xu, E. T. Vickers, S. Bonabi Naghadeh, X. Ding, Z. Li and J. Z. Zhang, Chem. Mater., 2018, 31, 365–375.
- 129 L. Rao, X. Du, G. Liang, Y. Tang, K. Tang and Z. Jin, Beilstein J. Nanotechnol., 2019, 10, 666–676.
- 130 Y. El Ajjouri, F. Palazon, M. Sessolo and H. Bolink, Chem. Mater., 2018, 30, 7423–7427.
- 131 G. Jiang, C. Guhrenz, A. Kirch, L. Sonntag, C. Bauer, X. Fan, J. Wang, S. Reineke, N. Gaponik and A. Eychmüller, ACS Nano, 2019, 13, 10386–10396.
- 132 J. Kim, N. T. Manh, H. T. Thai, S. K. Jeong, Y. W. Lee, Y. Cho, W. Ahn, Y. Choi and N. Cho, Nanomaterials, 2022, 12, 920.
- 133 Q. Zhang, W. Zheng, Q. Wan, M. Liu, X. Feng, L. Kong and L. Li, Adv. Opt. Mater., 2021, 9, 2002130.
- 134 Z. Long, S. Yang, J. Pi, D. Zhou, Q. Wang, Y. Yang, H. Wu and J. Qiu, Ceram. Int., 2022, 48, 35474–35479.
- 135 H. T. Ramolahloane, G. B. Nair and H. C. Swart, Mater. Res. Bull., 2023, 165, 112285.
- 136 X. Wu, K. Yin, M. Yang, Y. Hu and H. Peng, Flexible Printed Electron., 2023, 8, 035008.
- 137 S. Ye, M. Huang, Q. Han, J. Song and J. Qu, J. Alloys Compd., 2023, 965, 171442.
- 138 Y. Ji, L. Liang, T. Ma, J. Hu, Z. Chen and J. Chen, Opt. Mater., 2023, 143, 114254.
- 139 P. V. Kamat, J. Phys. Chem. C, 2007, 111, 2834–2860.
- 140 J. Yang, D. Wang, H. Han and C. Li, Acc. Chem. Res., 2013, 46, 1900–1909.
- 141 J. Low, S. Cao, J. Yu and S. Wageh, Chem. Commun., 2014, 50, 10768–10777.
- 142 X. Li, J. Yu and M. Jaroniec, Chem. Soc. Rev., 2016, 45, 2603– 2636.
- 143 R. Asahi, T. Morikawa, T. Ohwaki, K. Aoki and Y. Taga, Science, 2001, 293, 269–271.
- 144 U. Diebold, Surf. Sci. Rep., 2003, 48, 53–229.
- 145 V. Subramanian, E. E. Wolf and P. V. Kamat, J. Am. Chem. Soc., 2004, 126, 4943–4950.
- 146 J. Low, J. Yu, Q. Li and B. Cheng, Phys. Chem. Chem. Phys., 2014, 16, 1111–1120.
- 147 M. S. Akple, J. Low, S. Wageh, A. A. Al-Ghamdi, J. Yu and J. Zhang, Appl. Surf. Sci., 2015, 358, 196–203.
- 148 Y. Bessekhouad, D. Robert and J. V. Weber, J. Photochem. Photobiol., A, 2004, 163, 569–580.
- 149 N. Lamers, Z. Zhang, I. G. Scheblykin and J. Wallentin, Adv. Opt. Mater., 2023, 2300435.
- 150 S. Wang, Z. Wei, L. Yu, J. Hou, G. Wu and Y. Xiao, Chem. Eng. J., 2023, 468, 143503.
- 151 L. Yu, Y. Wei, Y. Lei, C. Liu, Y. Liu and M. Hong, CCS Chem., 2023, DOI: [10.31635/ccschem.023.202302845](https://doi.org/10.31635/ccschem.023.202302845).
- 152 C. Zhang, M. Wang, J. Shi, J. Wang, Z. Da, Y. Zhou, Y. Xu, N. V. Gaponenko and A. S. Bhatti, Front. Chem., 2023, 11, 1199863.
- 153 D. J. Norris, N. Yao, F. T. Charnock and T. A. Kennedy, Nano Lett., 2001, 1, 3–7.
- 154 N. Pradhan and X. Peng, J. Am. Chem. Soc., 2007, 129, 3339– 3347.
- 155 A. Malavika, S. Suresh, M. R. Subramaniam and S. K. Batabyal, New J. Chem., 2023, 47, 13783–13788.
- 156 Z. Wei, Y. Lv and X. Su, Microchem. J., 2023, 192, 108940.
- 157 A. Du, W. Zhao, Y. Peng, X. Qin, Z. Lin, Y. Ye, E. Chen, S. Xu and T. Guo, Nanomaterials, 2023, 13, 17.
- 158 L. Jing, Q. Cen, Q. Pang and J. Z. Zhang, J. Phys. Chem. C, 2023, 127, 2448–2455.
- 159 Y. Li, W. Li, Y. Yu and C. Zheng, Opt. Mater. Express, 2023, 13, 1488–1496.
- 160 D. Patra and S. P. Singh, J. Phys. Chem. C, 2023, 127, 9397– 9406.
- 161 R. Yun, H. Yang, W. Sun, L. Zhang, X. Liu, X. Zhang and X. Li, Laser Photonics Rev., 2023, 17, 2200524.
- 162 R. Zhang, G. Chen, H. Liu, J. Zhang, Y. Yuan, Z. Lv, L. Zhang, C. Wang, Z. Qin, W. Yang and J. Wang, Opt. Mater., 2023, 135, 113308.
- 163 Y.-W. Liu, S.-H. Guo, S.-Q. You, C.-Y. Sun, X.-L. Wang, L. Zhao and Z.-M. Su, Nanotechnology, 2020, 31, 215605.
- 164 J. V. Patil, S. S. Mali and C. K. Hong, J. Energy Chem., 2021, 62, 451–458.
- 165 S. Shyamal, S. K. Dutta and N. Pradhan, J. Phys. Chem. Lett., 2019, 10, 7965–7969.
- 166 G. X. Dong, W. Zhang, Y. F. Mu, K. Su, M. Zhang and T. B. Lu, Chem. Commun., 2020, 56, 4664–4667.
- 167 X. Zhou, Q. Chang, G. Xiang, S. Jiang, L. Li, X. Tang, F. Ling, Y. Wang, J. Li, Z. Wang and X. Zhang, Spectrochim. Acta, Part A, 2023, 300, 122773.
- 168 W. Wang, S. Song, B. Cao and J. Li, J. Lumin., 2022, 247, 118901.
- 169 S. Huang, B. Wang, Q. Zhang, Z. Li, A.-d. Shan and L. Li, Adv. Opt. Mater., 2018, 6, 1701106.
- 170 E. Ouaaka, M. Aazza, A. Bouymajane and F. Cacciola, Molecules, 2023, 28, 2880.
- 171 S. Paul, E. Bladt, A. F. Richter, M. Doeblinger, Y. Tong, H. Huang, A. Dey, S. Bals, T. Debnath, L. Polavarapu and J. Feldmann, Angew. Chem., Int. Ed., 2020, 59, 6794–6799.
- 172 N. Pradhan, J. Phys. Chem. Lett., 2019, 10, 2574–2577.
- 173 S. Jiang, Y. Song, H. Kang, B. Li, K. Yang, G. Xing, Y. Yu, S. Li, P. Zhao and T. Zhang, ACS Appl. Mater. Interfaces, 2022, 14, 3385–3394.
- 174 H. Bian, D. Li, S. Wang, J. Yan and S. F. Liu, Chem. Sci., 2022, 13, 1335–1341.
- 175 Y. Zhao, X. Liang, X. Hu and J. Fan, Colloids Surf., A, 2021, 626, 127098.
- 176 Y. F. Xu, M. Z. Yang, B. X. Chen, X. D. Wang, H. Y. Chen, D. B. Kuang and C. Y. Su, J. Am. Chem. Soc., 2017, 139, 5660–5663. PSC Advances Articles. Articles. Articles. Articles. Published on 07 February 2022. Downloaded on 5/25/2023. Download article. Published on 5/25/2023. Download a Creative Commons Attribution-Noncommercial 3.0 AM. This arti
	- 177 J.-Y. Li, H.-Y. Chen, Y. Jiang and D.-B. Kuang, Sol. RRL, 2021, 5, 2100036.
	- 178 A. Kipkorir, J. DuBose, J. Cho and P. Kamat, Chem. Sci., 2021, 12, 14815–14825.
	- 179 H. Jin, Y. Chen, L. Zhang, R. Wan, Z. Zou, H. Li and Y. Gao, Nanotechnology, 2021, 32, 085202.
	- 180 R. Huang, M. Zhang, Z. Zheng, K. Wang, X. Liu, Q. Chen and D. Luo, Nanomaterials, 2021, 11, 2422.
	- 181 M. T. Hossain, M. Das, J. Ghosh, S. Ghosh and P. K. Giri, Nanoscale, 2021, 13, 14945–14959.
	- 182 H. Cong, X. Chu, F. Wan, Z. Chu, X. Wang, Y. Ma, J. Jiang, L. Shen, J. You and C. Xue, Small Methods, 2021, 5, e2100517.
	- 183 E. Zhu, Y. Zhao, Y. Dai, Q. Wang, Y. Dong, Q. Chen and Y. Li, Chin. J. Chem., 2020, 38, 1718–1722.
	- 184 Y. Liu, Y. Yang, P. Chen, Y. Shan, Y. Li, J. Shi, J. Hou, N. Zhang, G. Zhao, J. Xu, Y. Fang and N. Dai, Small, 2020, 16, e2004126.
	- 185 Q. Huang, Z. Liang, F. Qi, N. Zhang, J. Yang, J. Liu, C. Tian, C. Fu, X. Tang, D. Wu, J. Wang, X. Wang and W. Chen, J. Phys. Chem. Lett., 2022, 13, 2418–2427.
	- 186 X. Xiao, S. Guo, C. Ding, Z. Zhang, H. Huang and J. Xu, J. Inorg. Mater., 2021, 36, 507–512.
	- 187 H. Zhao, Y. Zhang, T. Li, Q. Li, Y. Yu, Z. Chen, Y. Li and J. Yao, Nanotechnology, 2020, 31, 035202.
	- 188 Z. P. Huang, B. Ma, H. Wang, N. Li, R. T. Liu, Z. Q. Zhang, X. D. Zhang, J. H. Zhao, P. Z. Zheng, Q. Wang and H. L. Zhang, J. Phys. Chem. Lett., 2020, 11, 6007–6015.
	- 189 T. Paul, D. Das, B. K. Das, S. Sarkar, S. Maiti and K. K. Chattopadhyay, J. Hazard. Mater., 2019, 380, 120855.
	- 190 M. Shu, J. Lu, Z. Zhang, T. Shen and J. Xu, J. Inorg. Mater., 2021, 36, 1217.
	- 191 T. Chen, M. Li, L. Shen, M. B. J. Roeffaers, B. Weng, H. Zhu, Z. Chen, D. Yu, X. Pan, M.-Q. Yang and Q. Qian, Front. Chem., 2022, 10, 833784.
	- 192 P. Kour and S. P. Mukherjee, J. Mater. Chem. A, 2021, 9, 6819–6826.
	- 193 C. Zhang, J. Miao, L. Guo, T. Tan, W. Cai, X. Lei, Y. Li and Z. Wang, Appl. Organomet. Chem., 2023, 37, e7122.
	- 194 Z. Dong, Y. Shi, Y. Jiang, C. Yao and Z. Zhang, J. CO2 Util., 2023, 72, 102480.
	- 195 J.-R. Xue, R.-C. Xue, P.-Y. Chen, Y. Wang and L.-P. Yu, J. Chin. Chem. Soc., 2023, 70, 1481–1492.
	- 196 P. Wang, X. Ba, X. Zhang, H. Gao, M. Han, Z. Zhao, X. Chen, L. Wang, X. Diao and G. Wang, Chem. Eng. J., 2023, 457, 141248.
	- 197 H. McDaniel, P. E. Heil, C.-L. Tsai, K. Kim and M. Shim, ACS Nano, 2011, 5, 7677–7683.
	- 198 C. H. Wang, H. W. Huang, B. Weng, D. Verhaeghe, M. Keshavarz, H. D. Jin, B. Liu, H. P. Xie, Y. Ding, Y. J. Gao, H. F. Yuan, J. A. Steele, J. Hofkens and M. B. J. Roeffaers, Appl. Catal., B, 2022, 301, 120760.
	- 199 G. Yin, X. Qi, Y. Chen, Q. Peng, X. Jiang, Q. Wang, W. Zhang and X. Gong, J. Mater. Chem. A, 2022, 10, 22468–22476.
- 200 Y. Jiang, J. F. Liao, H. Y. Chen, H. H. Zhang, J. Y. Li, X. D. Wang and D. B. Kuang, Chem, 2020, 6, 766–780.
- 201 D.-E. Lee, N. Mameda, K. P. Reddy, B. M. Abraham, W.-K. Jo and S. Tonda, J. Mater. Sci. Technol., 2023, 161, 74–87.
- 202 J. Lu, S. Gu, H. Li, Y. Wang, M. Guo and G. Zhou, J. Mater. Sci. Technol., 2023, 160, 214–239.
- 203 M. Luo, G. Jiang, M. Yu, Y. Yan, Z. Qin, Y. Li and Q. Zhang, J. Mater. Sci. Technol., 2023, 161, 220–232.
- 204 Z. Zhang, L. Li, Y. Jiang and J. Xu, Inorg. Chem., 2022, 61, 3351–3360.
- 205 F. Xu, K. Meng, B. Cheng, S. Wang, J. Xu and J. Yu, Nat. Commun., 2020, 11, 4613.
- 206 Y.-C. Pu, Y.-H. Chuang, M.-W. Zheng, Y.-J. Chang and S.-H. Liu, J. Environ. Chem. Eng., 2023, 11, 109103.
- 207 S.-H. Guo, J. Zhou, X. Zhao, C.-Y. Sun, S.-Q. You, X.-L. Wang and Z.-M. Su, J. Catal., 2019, 369, 201–208.
- 208 Y. Zhao, Y. Dai, Q. Wang, Y. Dong, T. Song, A. Mudryi, Q. Chen and Y. Li, ChemCatChem, 2021, 13, 2592–2598.
- 209 R. Das, A. Patra, S. K. Dutta, S. Shyamal and N. Pradhan, J. Am. Chem. Soc., 2022, 144, 18629–18641.
- 210 F.-B. Chiu, Y.-W. Wu and S.-H. Yang, ACS Omega, 2023, 8, 19109–19118.
- 211 M. Giancaspro, R. Grisorio, G. Alò, N. Margiotta, A. Panniello, G. P. Suranna, N. Depalo, M. Striccoli, M. L. Curri and E. Fanizza, Mater. Chem. Front., 2023, 7, 2637–2650. Review BSC X, Butg., J. F. Licence. Articles. Article is licensed on 02 February 2024. Download a N. This article is licensed under a Common C. Franchise Commons Attribution-Non-Commons Article is licensed under a Creative
	- 212 Y. Duan, K. Chordiya, M. U. Kahaly, F. E. Oropeza, V. A. de la Pena O'shea, D.-Y. Wang and R. D. Costa, Adv. Opt. Mater., 2022, 10, 2201176.
	- 213 C. H. Tien, H.-H. Tsai and L. C. Chen, J. Mater. Res. Technol., 2022, 19, 3842–3851.
	- 214 M. Wang, D. Liang, W. Ma, Q. Mo, Z. Zang, Q. Qian and W. Cai, Opt. Lett., 2022, 47, 4512–4515.
	- 215 S. Bera, R. K. Behera, S. K. Dutta and N. Pradhan, ACS Mater. Lett., 2023, 5, 1332–1339.
	- 216 M.-G. Jeon, A. Kirakosyan, C. Shin, S. Yun, J. Kim, L. Li and J. Choi, Chem. Eng. J., 2023, 462, 142120.
	- 217 H. Wang, W. Lu, P. Xu, J. Luo, K. Yao, J. Zhang, X. Wei, S. Peng, H. Cheng, H. Hu and K. Sun, ACS Sustainable Chem. Eng., 2023, 11, 5963–5972.
	- 218 Y. He, L. Zhang, G. Chen, Y. Liu, S. Shi, P. Jiang, J. Ding, S. Xu and C. Geng, Appl. Surf. Sci., 2023, 611, 155724.
	- 219 C. Wang, M. Zhang, H. Yu, W. Zhang, G. Shi, X. Zhang, Z. Cui, P. Fu, M. Liu, X. Qiao, Y. He and X. Pang, ACS Appl. Nano Mater., 2023, 6, 3416–3424.
	- 220 L. Wu, H. Hu, Y. Xu, S. Jiang, M. Chen, Q. Zhong, D. Yang, Q. Liu, Y. Zhao, B. Sun, Q. Zhang and Y. Yin, Nano Lett., 2017, 17, 5799–5804.
	- 221 A. Pan, M. J. Jurow, F. Qiu, J. Yang, B. Ren, J. J. Urban, L. He and Y. Liu, Nano Lett., 2017, 17, 6759–6765.
	- 222 X. Liang, W. Chen, J. Yang, X. Liu, X. Fang and W. Xiang, ACS Appl. Electron. Mater., 2023, 5, 2309–2317.
	- 223 M. Xiao, M. Hao, M. Lyu, E. G. Moore, C. Zhang, B. Luo, J. Hou, J. Lipton-Duffin and L. Wang, Adv. Funct. Mater., 2019, 29, 19056831–19056838.
- 224 X. Zhang, M. He, H. Fang, J. Bao, X. Bu, C. Yang, X. Sheng, B. Wu, Z. Zhang and Y. Zhou, Int. J. Hydrogen Energy, 2022, 47, 40860–40871.
- 225 M. Knezevic, V.-D. Quach, I. Lampre, M. Erard, P. Pernot, D. Berardan, C. Colbeau-Justin and M. N. Ghazzal, J. Mater. Chem. A, 2023, 11, 6226–6236.
- 226 H. Wang, X. M. Wang, R. T. Chen, H. F. Zhang, X. L. Wang, J. H. Wang, J. Zhang, L. C. Mu, K. F. Wu, F. T. Fan, X. Zong and C. Li, Int. J. Hydrogen Energy, 2019, 4, 40–47.
- 227 W. Song, Y. Wang, C. Wang, B. Wang, J. Feng, W. Luo, C. Wu, Y. Yao and Z. Zou, ChemCatChem, 2021, 13, 1711– 1716.
- 228 L. Ding, C. Shen, Y. Zhao, Y. Chen, L. Yuan, H. Yang, X. Liang, W. Xiang and L. Li, Mol. Catal., 2020, 483, 110764.
- 229 H. Sun, R. Tang, X. Zhang, S. Zhang, W. Yang, L. Wang, W. Liang, F. Li, R. Zheng and J. Huang, Catal. Sci. Technol., 2023, 13, 1154–1163.
- 230 J. Hou, S. Cao, Y. Wu, Z. Gao, F. Liang, Y. Sun, Z. Lin and L. Sun, Chem.–Eur. J., 2017, 23, 9481–9485.
- 231 Z. Guan, Y. Wu, P. Wang, Q. Zhang, Z. Wang, Z. Zheng, Y. Liu, Y. Dai, M.-H. Whangbo and B. Huang, Appl. Catal., B, 2019, 245, 522–527.
- 232 N. S. Lewis and D. G. Nocera, Proc. Natl. Acad. Sci. U. S. A., 2006, 103, 15729–15735.
- 233 M. E. El-Khouly, E. El-Mohsnawy and S. Fukuzumi, J. Photochem. Photobiol., C, 2017, 31, 36–83.
- 234 A. Crake, Mater. Sci. Technol., 2017, 33, 1737–1749.
- 235 W. Dong, Y. Ji, J. Wang, B. Li, F. Yang and J. Yang, ACS Omega, 2021, 6, 34675–34686.
- 236 Y.-H. Chen, K.-A. Tsai, T.-W. Liu, Y.-J. Chang, Y.-C. Wei, M.-W. Zheng, S.-H. Liu, M.-Y. Liao, P.-Y. Sie, J.-H. Lin, S.-W. Tseng and Y.-C. Pu, J. Phys. Chem. Lett., 2023, 14, 122–131.
- 237 H. Xiao, Q. Qian and Z. Zang, Sci. China Mater., 2023, 66, 1810–1819.
- 238 Y.-J. Dong, Y. Jiang, J.-F. Liao, H.-Y. Chen, D.-B. Kuang and C.-Y. Su, Sci. China Mater., 2022, 65, 1550–1559.
- 239 D. Laishram, S. Zeng, K. M. Alam, A. P. Kalra, K. Cui, P. Kumar, R. K. Sharma and K. Shankar, Appl. Surf. Sci., 2022, 592, 153276.
- 240 C. Han, X. Zhu, J. S. Martin, Y. Lin, S. Spears and Y. Yan, ChemSusChem, 2020, 13, 4005–4025.
- 241 J. Fan, B. Jia and M. Gu, Photonics Res., 2014, 2, 111–120.
- 242 S. A. Kulkarni, S. G. Mhaisalkar, N. Mathews and P. P. Boix, Small Methods, 2019, 3, 1800231.
- 243 A. Tabish, A. M. Varghese, M. A. Wahab and G. N. Karanikolos, Catalysts, 2020, 10, 95.
- 244 M. Singh and I. Sinha, Sol. Energy, 2020, 208, 296–311.
- 245 S. Shyamal and N. Pradhan, J. Phys. Chem. Lett., 2020, 6921– 6934.
- 246 H. Huang, B. Pradhan, J. Hofkens, M. B. J. Roeffaers and J. A. Steele, ACS Energy Lett., 2020, 5, 1107–1123.
- 247 X. X. Chang, T. Wang and J. L. Gong, Energy Environ. Sci., 2016, 9, 2177–2196.
- 248 H.-L. Wu, X.-B. Li, C.-H. Tung and L.-Z. Wu, Adv. Mater., 2019, 31, 1900709.

- 249 W. Zhang, Z. Wang, P. Lin, D. Wu, Z. Shi, X. Chen, T. Xu, Y. Tian and X. Li, J. Mater. Sci., 2020, 55, 6826–6833.
- 250 G.-X. Dong, M.-R. Zhang, K. Su, Z.-L. Liu, M. Zhang and T.-B. Lu, J. Mater. Chem. A, 2023, 11, 9989–9999.
- 251 X. Liu, J. Qiu, Q. Huang, X. Chen, J. Yu and J. Bao, Phys. Chem. Chem. Phys., 2023, 25, 11620–11629.
- 252 J. Wang, J. Wang, N. Li, X. Du, J. Ma, C. He and Z. Li, ACS Appl. Mater. Interfaces, 2020, 12, 31477–31485.
- 253 Z.-C. Kong, J.-F. Liao, Y.-J. Dong, Y.-F. Xu, H.-Y. Chen, D.-B. Kuang and C.-Y. Su, ACS Energy Lett., 2018, 3, 2656– 2662.
- 254 S. Wan, M. Ou, Q. Zhong and X. Wang, Chem. Eng. J., 2019, 358, 1287–1295.
- 255 Y.-H. Chen, J.-K. Ye, Y.-J. Chang, T.-W. Liu, Y.-H. Chuang, W.-R. Liu, S.-H. Liu and Y.-C. Pu, Appl. Catal., B, 2021, 284, 119751.
- 256 M. Ou, W. Tu, S. Yin, W. Xing, S. Wu, H. Wang, S. Wan, Q. Zhong and R. Xu, Angew. Chem., Int. Ed. Engl., 2018, 57, 13570–13574.
- 257 A. Pan, X. Ma, S. Huang, Y. Wu, M. Jia, Y. Shi, Y. Liu, P. Wangyang, L. He and Y. Liu, J. Phys. Chem. Lett., 2019, 10, 6590–6597.
- 258 Y.-F. Xu, X.-D. Wang, J.-F. Liao, B.-X. Chen, H.-Y. Chen and D.-B. Kuang, Adv. Mater. Interfaces, 2018, 5, 1801015.
- 259 O. Lefebvre and R. Moletta, Water Res., 2006, 40, 3671–3682.
- 260 J. Wang, J. Liu, Z. Du and Z. Li, J. Energy Chem., 2021, 54, 770–785.
- 261 D. Wang, S. C. Pillai, S.-H. Ho, J. Zeng, Y. Li and D. D. Dionysiou, Appl. Catal., B, 2018, 237, 721–741.
- 262 V. N. Salomone, J. M. Meichtry, G. Zampieri and M. I. Litter, Chem. Eng. J., 2015, 261, 27–35.
- 263 P. A. K. Reddy, P. V. L. Reddy, E. Kwon, K.-H. Kim, T. Akter and S. Kalagara, Environ. Int., 2016, 91, 94–103.
- 264 X. Yang and D. Wang, ACS Appl. Energy Mater., 2018, 1, 6657–6693.
- 265 B. Ai, M. Luo and I. Khan, Processes, 2023, 11, 1398.
- 266 I. Bolognino, R. Pelosato, G. Marci and I. Natali Sora, Molecules, 2023, 28, 3807.
- 267 M. Humayun, A. Bahadur, A. Khan and M. Bououdina, Catalysts, 2023, 13, 907.
- 268 Y.-Y. Lin, P.-H. Lu, F.-Y. Liu, C.-S. Lu and C.-C. Chen, Catalysts, 2023, 13, 812.
- 269 J. Wang, N. Li, Y. Tang, Y. He and K. Shan, Int. J. Electrochem. Sci., 2022, 17, 22081.
- 270 X. Hu, Y. Xu, J. Wang, J. Ma, L. Wang and W. Jiang, Chem. Eng. J., 2023, 451, 139031.
- 271 X. Feng, H. Ju, T. Song, T. Fang, W. Liu and W. Huang, ACS Sustainable Chem. Eng., 2019, 7, 5152–5156.
- 272 G. Gao, Q. Xi, H. Zhou, Y. Zhao, C. Wu, L. Wang, P. Guo and J. Xu, Nanoscale, 2017, 9, 12032–12038.
- 273 E. Fan, H. Xu, S. Sun, C. Huang, M. Li, B. Fan, G. Shao, W. Liu, H. Wang, H. Lu and R. Zhang, Colloids Surf., A, 2023, 669, 131510.
- 274 X. Jia, C. Liu, X. Xu, F. Wang, W. Li, L. Zhang, S. Jiao, G. Zhu and X. Wang, RSC Adv., 2023, 13, 19140–19148.
- 275 R. Sun, X. Yu, J. Chen, W. Zhang, Y. Huang, J. Zheng and Y. Chi, Anal. Chem., 2022, 94, 17142–17150.
- 276 Y. Zhao, H. Shi, X. Hu, E. Liu and J. Fan, Chem. Eng. J., 2020, 381, 122692.
- 277 Y. Zhao, Y. Xu, X. Jing and W. Ma, Food Chem., 2023, 412, 135420.
- 278 S. Sharma, S. K. Mehta, A. O. Ibhadon and S. K. Kansal, J. Colloid Interface Sci., 2019, 533, 227–237.
- 279 G. V. S. R. P. Kumar, Y. B. Pydiraju, G. V. Lokesh and U. V. S. Likith, Water Conserv. Sci. Eng., 2023, 8, 17.
- 280 E. A. Namikuchi, R. D. L. Gaspar, I. M. Raimundo Jr and I. O. Mazali, Spectrochim. Acta, Part A, 2023, 300, 122915.
- 281 A. Solinska, J. Marchewka, M. Sitarz and T. Bajda, Spectrochim. Acta, Part A, 2023, 299, 122758.
- 282 K. Guo, P. Lin, D. Wu, Z. Shi, X. Chen, Y. Han, Y. Tian and X. Li, Chem.–Eur. J., 2023, 29, e202300400.
- 283 A. Jimenez-Almarza, A. Lopez-Magano, R. Cano, B. Ortin-Rubio, D. Diaz-Garcia, S. Gomez-Ruiz, I. Imaz, D. Maspoch, R. Mas-Balleste and J. Aleman, Mater. Today Chem., 2021, 22, 100548. PSC Advances Articles. Published on 1923. Article is licensed on 1924. Downloaded on 5/25/2023. The main V. He and T. A. Noncommercial Access Article is licensed under a strength on 5/25/2023. The main V. He and J. All and
	- 284 H. Ju, T. Fang, Y. Zhou, X. Feng, T. Song, F. Lu and W. Liu, Appl. Surf. Sci., 2021, 551, 149452.
	- 285 X.-F. Qi, F. Zhang, Z.-P. Chen, X. Chen, M.-C. Jia, H.-F. Ji and Z.-F. Shi, J. Mater. Chem. C, 2023, 11, 3715–3725.
	- 286 E. D. M. Isa, N. W. C. Jusoh and A. A. M. Rodzi, Environ. Sci. Pollut. Res., 2023, 30, 116921–116933.
	- 287 Y. Khan, U. Sharafat, S. Gul, M. I. Khan, M. Ismail, M. A. Khan, R. Younus and S. B. Khan, Green Process. Synth., 2023, 12, 20228128.
	- 288 F. Yang, X. He, T. Xin, H. Yang, L. Bai, L. Gao and Y. Wang, Molecules, 2023, 28, 3968.
	- 289 P. Nehra, P. S. Rana and S. Singh, Environ. Sci. Pollut. Res. Int., 2023, 30, 70094–70108.
	- 290 A. Panahi, R. Monsef, E. A. Dawi, A. S. Hussein and M. Salavati-Niasari, Sol. Energy, 2023, 258, 372–382.
	- 291 S. Sharma, P. Jakhar and H. Sharma, J. Appl. Polym. Sci., 2023, 140, e54038.
	- 292 U. A. A. Yasin, M. M. Ahmed, J. Zhang, Z. Jia, T. Guo, R. Zhao, J. Shi and J. Du, J. Mater. Sci., 2023, 58, 7333–7346.
	- 293 F. Yousefzadeh, M. Ghanbari, E. A. Dawi and M. Salavati-Niasari, Arabian J. Chem., 2023, 16, 104904.
	- 294 S. Liu, M. Li, Y. Tang and X. Wen, J. Alloys Compd., 2023, 959, 170528.
	- 295 S. M. M. Yakout and M. E. E. El-Zaidy, J. Sol-Gel Sci. Technol., 2023, 107, 417–429.
	- 296 S. S. Ahmed, J. Nanostruct., 2023, 13, 48–58.
	- 297 K. Balu, E. Chicardi, R. Sepulveda, M. Durai, F. Ishaque, D. Chauhan and Y.-H. Ahn, Sep. Purif. Technol., 2023, 309, 122998.
	- 298 S. Moradi, M. Farhadian, A. R. S. Nazar and M. Moghadam, J. Mol. Liq., 2023, 377, 121520.
	- 299 S. Ravikumar, D. Mani, E. Chicardi, R. Sepulveda, K. Balu, V. Pandiyan and Y. H. Ahn, Ceram. Int., 2023, 49, 9551– 9559.
	- 300 A. Moulahi, J. Inorg. Organomet. Polym. Mater., 2023, 33, 3948–3960.
	- 301 I. Ahmad, M. Muneer, A. S. Khder and S. A. Ahmed, ACS Omega, 2023, 25, 22708–22720.
- 302 S. Asgari, G. M. Ziarani, A. Badiei, R. S. Varma, S. Iravani and F. Mohajer, RSC Adv., 2023, 13, 17324–17339.
- 303 K. Layek, Catal. Surv. Asia, 2023, 27, 349–362.
- 304 W. Liu, H. Xie, X. Guo, K. Wang, C. Yang, N. Wang and C. Ge, Opt. Mater., 2023, 136, 113398.
- 305 P. Li, Z. Wang, S. Yang, G. Lyu, Y. Gu, J. Chen and G. Yang, Int. J. Biol. Macromol., 2023, 242, 125137.
- 306 M. Lv, H. Liu, L. He, B. Zheng, Q. Tan, M. Hassan, F. Chen and Z. Gong, Environ. Res., 2023, 231, 116218.
- 307 M. Sharma, D. Rajput, V. Kumar, I. Jatain, T. M. Aminabhavi, G. Mohanakrishna, R. Kumar and K. K. Dubey, Environ. Res., 2023, 231, 116132.
- 308 D.-E. Lee, S. Moru, K. P. Reddy, W.-K. Jo and S. Tonda, J. Mater. Sci. Technol., 2023, 148, 19–30.
- 309 J. Lv, X. Lu, C. Zhou, X. Zeng and Y.-y. Li, J. Alloys Compd., 2023, 960, 170514.
- 310 D. Song, M. Li, L. Liao, L. Guo, H. Liu, B. Wang and Z. Li, Nanomaterials, 2023, 13, 1841.
- 311 Q. Sun, X. Hu, Y. Zhao, J. Zhang and J. Sheng, Environ. Sci. Pollut. Res., 2023, 30, 75247–75261.
- 312 D. Cardenas-Morcoso, A. F. Gualdrón-Reyes, A. B. Ferreira Vitoreti, M. García-Tecedor, S. J. Yoon, M. Solis de la Fuente, I. Mora-Seró and S. Gimenez, J. Phys. Chem. Lett., 2019, 10, 630–636. Review Water Access Articles. Articles. Article 2024. Downloaded on 2024. Downloaded on 5/25/2025 9:23:10 AM. This article is licensed with the state of the
	- 313 L. Wang, M. Niu, Y. Liu, Y. Xie, Z. Ma, M. Zhang and C. Hou, J. Colloid Interface Sci., 2023, 645, 639–653.
	- 314 Y. Xiao, Y. Jiang, E. Zhou, W. Zhang, Y. Liu, J. Zhang, X. Wu, Q. Qi and Z. Liu, J. Mater. Sci. Technol., 2023, 153, 205–218.
	- 315 J. Xing, J. Huang, X. Wang, F. Yang, Y. Bai, S. Li and X. Zhang, J. Environ. Manage., 2023, 343, 118210.
- 316 X. Qian, Z. Chen, X. Yang, W. Zhao, C. Liu, T. Sun, D. Zhou, Q. Yang, G. Wei and M. Fan, J. Cleaner Prod., 2020, 249, 119335.
- 317 Y. Zhao, Y. Wang, X. Liang, H. Shi, C. Wang, J. Fan, X. Hu and E. Liu, Appl. Catal., B, 2019, 247, 57–69.
- 318 P. Wang, X. Diao, X. Zhang, Z. Zhao, H. Gao, J. T. S. Irvine and G. Wang, Mater. Today Phys., 2023, 35, 101043.
- 319 X. Wang, J. He, L. Mao, X. Cai, C. Sun and M. Zhu, Chem. Eng. J., 2021, 416, 128077.
- 320 M. T. Hoang, C. Han, Z. Ma, X. Mao, Y. Yang, S. S. Madani, P. Shaw, Y. Yang, L. Peng, C. Y. Toe, J. Pan, R. Amal, A. Du, T. Tesfamichael, Z. Han and H. Wang, Nano-Micro Lett., 2023, 15, 161.
- 321 A. A. Alothman, M. R. Khan, M. D. Albaqami, S. Mohandoss, Z. A. Alothman, N. Ahmad and K. N. Alqahtani, Nanomaterials, 2023, 13, 3026.
- 322 S. Das, T. Paul, S. Maiti and K. K. Chattopadhyay, Mater. Lett., 2020, 267, 127501.
- 323 A. A. Bhat, S. A. Khandy, I. Islam and R. Tomar, Sci. Rep., 2021, 11, 16473.
- 324 A. Asadi, N. Khosroshahi, M. Hosseinpour and V. Safarifard, Mater. Sci. Semicond. Process., 2023, 165, 107707.
- 325 Y. Liu and Z. Ma, Colloids Surf., A, 2021, 628, 127310.
- 326 M. Karami, M. Ghanbari, O. Amiri and M. Salavati-Niasari, Sep. Purif. Technol., 2020, 253, 117526.
- 327 G. Yuan, S. Feng, Q. Yang, F. Yi, X. Li, Y. Yuan, C. Wang and H. Yan, J. Mater. Chem. C, 2023, 11, 7570–7574.