RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2024, 14, 16685

Green synthesis of ZnO-TiO₂/RGO nanocomposites using Senna surattensis extract: a novel approach for enhanced anticancer efficacy and biocompatibility

ZabnAllah M. Alaizeri, ^b*^a Hisham A. Alhadlaq, ^a Saad Aldawood^a and Naaser A. Y. Abduh^b

The purpose of the present study is to enhance the anticancer and biocompatibility performance of TiO_2 NPs, ZnO NPs, ZnO-TiO₂ (NCs), and ZnO-TiO₂/reduced graphene oxide (RGO) NCs against two types of human cancer (HCT116) and normal (HUVCE) cells. A novel procedure for synthesizing ZnO-TiO₂/RGO NCs has been developed using Senna surattensis extract. The improved physicochemical properties of the obtained samples were investigated using different techniques such as XRD, TEM, SEM, XPS, FTIR, DLS and UV-visible spectroscopy. XRD results showed that the addition of ZnO and RGO sheets affects the crystal structure and phase of TiO₂ NPs. SEM and TEM images displayed that the TiO₂ NPs and ZnO NPs were small with uniform spherical morphology in the prepared ZnO-TiO₂/RGO NCs. Besides, it is shown that ZnO-TiO₂ NCs anchored onto the surface of RGO sheets with a particle size of 14.80 \pm 0.5 nm. XPS data confirmed the surface chemical composition and oxidation states of ZnO-TiO₂/RGO NCs. Functional groups of prepared NPs and NCs were determined using FTIR spectroscopy. DLS data confirmed that the addition of ZnO and RGO sheets improves the negative surface charge of the prepared pure TiO₂ NPs (-22.51 mV), ZnO NPs (-18.27 mV), ZnO-TiO₂ NCs (-30.20 mV), and ZnO-TiO₂/RGO NCs (-33.77 mV). Optical analysis exhibited that the bandgap energies of TiO₂ NPs (3.30 eV), ZnO NPs (3.33 eV), ZnO-TiO₂ NCs (3.03 eV), and ZnO-TiO₂/RGO NCs (2.78 eV) were further enhanced by adding ZnO NPs and RGO sheets. This indicates that the synthesized samples can be applied to cancer therapy and environmental remediation. The biological data demonstrated that the produced ZnO-TiO₂/RGO NCs show a more cytotoxic effect on HCT116 cells compared to pure TiO₂ NPs and ZnO-TiO₂ NCs. On the other hand, these NCs displayed the lowest level of toxicity towards normal HUVCE cells. These results indicate that the ZnO-TiO₂/RGO NCs have strong toxicity against HCT116 cells and are compatible with normal cells. Our results show that the plant extract enhanced the physicochemical properties of NPs and NCs compared with the traditional chemical methods for synthesis. This study could open new avenues for developing more effective and targeted cancer treatments

Received 2nd March 2024 Accepted 12th April 2024

DOI: 10.1039/d4ra01634c

1. Introduction

Cancer is a major worldwide health issue, requiring the development of new and innovative treatment approaches.¹ Currently, nanotechnology and nanomaterials science have attracted attention to address this challenge by providing approaches to improve the effectiveness and specificity of anticancer therapy.² Among these nanomaterials, metal oxide nanoparticle-based nanocomposites (NCs) have attracted much interest owing to their unique properties and applications. Besides, they have been applied in a wide range of applications including catalysis, energy storage, and biomedical engineering.^{3,4} Many previous studies have reported the use of Ag₂O/TiO₂,⁵ WO₃/ZnO NCs,⁶ SnO₂/MgO NCs,⁷ In₂O₃/ZnO NCs⁸ in antibacterial, and anticancer applications due to their excellent properties. Additionally, the physicochemical properties of these NCs can be enhanced by the addition of another material (graphene oxide (GO), reduced graphene oxide (RGO), and polymers) by improved synthesis processes.

Different approaches have been explored for preparation and biomedical applications of different metal oxide NPs with reduced graphene oxide (RGO) to improve their physicochemical properties.^{9,10} For instance, fruit extract (*Phoenix*

[&]quot;Department of Physics and Astronomy, College of Science, King Saud University, Riyadh 11451, Saudi Arabia. E-mail: zabn1434@gmail.com

^bDepartment of Chemistry, College of Science, King Saud University, Riyadh 11451, Saudi Arabia

View Article Online Paper

dactylifera L.) was used to synthesize Mo-ZnO/RGO NCs by Ahamed *et al.*¹⁰ The authors observed that the biocompatibility and anticancer performance were increased in green stabilized Mo-ZnO/RGO NCs compared with pure ZnO NPs. In another study, the TiO₂/reduced graphene oxide NCs synthesized by the anodization method displayed excellent analytical capability in detecting MCF-7 cancer cells.¹¹ Saravanan *et al.*¹² used the thermal decomposition method to prepare ZnO/Ag/Mn₂O₃ NCs with enhanced antimicrobial activity.

To enhance the anticancer properties of these nanocomposites (NCs), several researchers have focused on combining two metal oxides with RGO as NCs in biomedical applications. For example, Ahamed et al.13 used ginger rhizome extract to prepare ZrO2-doped ZnO/rGO NCs, which exhibited far greater anticancer activity on lung (A549) and breast (MCF-7) cancer cells than pure ZnO NPs. Yao et al.14 synthesized SnO2/ TiO₂/RGO NCs using green hydrothermal methods with increased visible-light photocatalytic and antibacterial activity. Hossain et al.¹⁵ improved the antibacterial properties of TiO₂-MWCNT NCs by doping with Fe or Ag, which reduced their bandgap energy. Ahamed et al.¹⁶ reported a green synthesis approach that employs garlic clove extract to produce SnO2--ZnO/RGO NCs with improved anticancer activity against breast (MCF-7) cancer cells.

The present work aimed to fabricate ZnO-TiO₂/RGO NCs by novel green synthesis for their biological response. Prepared NCs were successfully characterized by different analytical techniques, such as XRD, TEM, SEM, XPS FTIR, DLS and UVvisible spectroscopy. The selective anticancer activity of the samples was assessed using an MTT assay. Biochemical data indicate that the ZnO-TiO₂/RGO NCs had strong cytotoxicity against HTC116 cells and great biocompatibility with normal HUVEC cells.

2. Experimental section

2.1 Materials, reagents, and cells

Titanium butoxide (Ti(O-But)₄), zinc nitrate hexahydrate (Zn(NO₃)₂·6H₂O), sodium hydroxide (NaOH), reduced graphene oxide (RGO), MTT (3-[4,5-dimethylthiazol-2-yl]-2,5-diphenyl tetrazolium bromide), and dimethyl sulfoxide (DMSO) were purchased from Sigma-Aldrich, St. Louis, MO, USA. All reagents were of analytical grade and used without additional purification. The human colorectal cancer (HCT116) and human umbilical vein endothelial (HUVEC) normal cell lines were acquired from the American Type Culture Collection (ATTC) based in Manassas, WV, USA.

2.2 Preparation of Senna surattensis extract

Senna surattensis flowers were collected from the campus of King Saud University (KSU), Riyadh, KSA. Then, it was cleaned with deionized water, shade-dried for two weeks, and then mixer-ground. Hence, the shade drying process was less affected by the chemical composition and biological activity of plants compared with oven drying. After drying, 10 g of *Senna surattensis* flowers were added to 100 ml of deionized water to

prepare the extract solution. For optimal extraction of plant water-soluble components, the mixture solution was heated to 60 °C under stirring for 10 min. Lastly, the prepared extract solution was cooled, filtered with filter paper, and kept at 4 °C for future use in the present work.

2.3 Synthesis of ZnO-TiO₂ NCs and ZnO-TiO₂/RGO NCs

4.37 g of Zn(NO₃)₂·6H₂O was dispersed in 40 ml of extract aqueous solution in an Erlenmeyer flask. Next, 5 ml of Ti(O-But)₄ was dissolved in 10 ml of ethanol dropwise. After that, 15 ml of NaOH solution (2 M) was added. Subsequently, the mixed solution was heated to 60 °C. Then, a separating process was used to remove the precipitate from the solution. Next, it was washed several times with water/ethanol at a volume ratio equal to (3/1). This precipitate was dried overnight in a 60 °C oven and annealed in a tube furnace at 500 °C for 3 h under atmospheric air. Pure ZnO NPs were prepared by the same route without Ti(O-But)₄. Similarly, pure TiO₂ NPs were synthesized without Zn(NO₃)₂·6H₂O and NaOH solution. ZnO-TiO₂/RGO NCs were also fabricated using a sonication process. Initially, 1 g of ZnO-TiO₂ NCs and 10% of RGO sheets were further dispersed in 30 ml of deionized water under an ultra-sonicate wave at 80 kW for 2 h. Then, the mixture solution was dried in an oven at 60 °C overnight for 12 h to obtain ZnO-TiO₂/RGO NCs as nanopowder. Pure TiO₂ NPs, ZnO₂ NPs, and ZnO-TiO₂ NCs were synthesized without $Zn(NO_3)$ using RGO, $Ti(O-But)_4$, and RGO sheets under the same conditions. The procedures for preparing ZnO-TiO₂/RGO NCs are presented in Scheme 1.

2.4 Characterization techniques

X-ray diffraction (XRD) (PanAnalytic X'Pert Pro instrument from Malvern Instruments, UK) was applied to examine the crystalline structures and phases of synthesized NPs and NCs. Morphological and surface properties of prepared samples were further investigated through scanning electron microscopy (SEM) (JSM-7600F instrument from JEOL, Inc). X-ray photoelectron spectroscopy (XPS) (PerkinElmer PHI-5300 ESCA device in Boston, MA, USA) was used to confirm the chemical states and compositions of the produced samples. The functional groups of the obtained samples were recorded at a wavenumber range of 400 to 4000 cm⁻¹ using Fourier transform infrared (FTIR) spectroscopy (PerkinElmer Paragon 500, USA). Dynamic light scattering (DLS) (Malvern Panalytical Ltd, located in Worcestershire, UK) was used to assess the surface charge of synthesized NPs and NCs. The optical properties of the obtained NPs and NCs were studied by UV-vis spectroscopy (Hitachi U-2600).

2.5 Anticancer and biocompatibility assessments by MTT bioassay

The HTC116 cancer cells and HUVECs normal cells were cultured in Dulbecco's Modified Eagle Medium (DMEM) with 10% Fetal Bovine Serum (FBS), 100 U mL⁻¹ penicillin, and 10 mg L⁻¹ streptomycin. For each cell line, 70–80% of cell growth was trypsinized in culture fluxes and plated on 96-well plates. After seeding 10⁴ cancer cells per well onto plates, they



were allowed to adhere and develop overnight in 200 μ L of culture media. Cells were cultured with new media with varied doses (3.125–200 μ g ml⁻¹) of prepared samples for 24 hours. The plates were incubated at 37 °C and 5% CO₂ for 3 hours after adding 20 μ L of MTT solution (5 μ g ml⁻¹) to each well with 100 μ L of the medium. Post-incubation, the MTT solution was removed, and 100 μ L of dimethyl sulfoxide (DMSO) was added to dissolve formazan crystals in each well. The plates were shaken for 20 minutes on a plate shaker to ensure solubility. The biocompatibility of prepared NPs was tested using the same methods.

2.6 Statistical analysis

This study used SPSS (SPSS Inc., Routledge, NY, USA) for all statistical analysis. Comparing mean values using Duncan's multiple range tests revealed significant differences (p < 0.05).

3. Results and discussion

3.1 XRD study

XRD analysis provides significant insights into the crystal structure and composition of synthesized samples. XRD spectra of RGO (Fig. 1a) exhibit a strong peak at $2\theta = 25^{\circ}$, corresponding to the graphene sheet interlayer spacing (002). Moreover, XRD spectra of RGO demonstrate a small peak at $2\theta = 43^{\circ}$, indicating graphitic carbon (111) reflection.¹⁷ The XRD spectra of prepared TiO₂ NPs, ZnO NPs, ZnO-TiO₂ NCs, and ZnO-TiO₂/RGO NCs are presented in Fig. 1b–e. As shown in Fig. 1b, the XRD peaks at 2θ values of 25.3°, 37.8°, 48.0°, 53.9°, 55.4°, 62.7°, 69.8°, and 75.6° indicate the crystallographic planes (101), (004), (200), (105), (204), (211), (220), and (215) of anatase TiO₂. Similarly, XRD

spectra of ZnO NPs (Fig. 1c) reveal peaks at 2θ values of 31.9° , 34.5° , 36.3° , 47.6° , 56.6° , 62.9° , 66.3° , 67.9° , 69.0° , and 77.2° , corresponding to wurtzite crystal structure planes (100), (002), (101), (102), (110), (103), (200), (112), (201), and (202), respectively. These results match with those from previous studies.^{18,19} Furthermore, the XRD spectra of ZnO-TiO₂ NCs (Fig. 1d) show a mixture of the distinct peaks observed in TiO₂ NPs and ZnO



Fig. 1 XRD spectra of RGO (a), TiO₂ NPs (b), ZnO NPs (c), ZnO-TiO₂ NCs (d), and ZnO-TiO₂/RGO NCs (e).

NPs, as reported in earlier study.²⁰ This indicates that ZnO-TiO₂ NCs were successfully prepared. Fig. 1e demonstrates the XRD spectra of synthesized ZnO-TiO₂/RGO NCs, wherein reduced graphene oxide (RGO) affects the crystallite size and structure of prepared NCs, similar to previous studies.^{21,22} By applying the Scherrer equation, the average crystallite size (*D*) of peaks (100), (004), and (101) for TiO₂ NPs, ZnO NPs, ZnO-TiO₂ NCs, and ZnO-TiO₂/RGO NCs were 8 ± 0.9 nm, 20 ± 0.2 nm, 14 ± 0.6 nm, and 11 ± 0.2 nm, respectively. Our XRD results suggest the crystal structures and phases with purity of prepared NPs and NCs, which were further examined and supported by FTIR data (Fig. 4).

3.2 TEM study

The morphologies and particle sizes of synthesized NPs and NCs were imaged by the TEM technique, as illustrated in Fig. 2a–d. The TEM image (Fig. 2a) of TiO_2 NPs was observed as small spherical particles with a uniform size distribution without any significant agglomeration, which is consistent with recent studies.^{23,24} Similarly, the TEM image of ZnO NPs exhibits a similar morphology to that of TiO_2 NPs with aggregation, as

reported in an earlier study.²⁵ Nevertheless, the difference in these particle behaviors is due to several factors related to the specific properties of ZnO and TiO₂ (surface area properties) and their interactions with the plant extract. As observed in Fig. 2c, the particles of ZnO NPs and TiO₂ NPs are randomly distributed in ZnO-TiO₂ NCs. Significantly, the TEM image of ZnO-TiO₂/RGO NCs (Fig. 2d) confirmed that the ZnO-TiO₂ NCs were integrated into the RGO sheets. In addition, the RGO sheets appear as thin, transparent layers, which are well-dispersed among the ZnO-TiO₂ NCs. The histograms in Fig. 2a and b show the estimated diameters of TiO₂ NPs, ZnO NPs, ZnO-TiO₂ NCs, and ZnO-TiO₂/RGO NCs were 10.50 ± 1.2 nm, 23.32 ± 0.8 nm, 17.21 ± 0.4 nm, and 14.80 ± 0.5 nm, respectively. These results from the TEM images were consistent with the data previously published.^{26,27}

3.3 SEM study

Fig. 3a–d displays the SEM images of TiO_2 NPs, ZnO- TiO_2 NCs, and ZnO- TiO_2/RGO NCs. The SEM image of TiO_2 NPs (Fig. 3a) displays that the particles of TiO_2 NPs were uniform with a smooth surface, matching with earlier studies.^{28–30} Thus, the



Fig. 2 TEM characterization: TiO₂ NPs (a), ZnO NPs (b), ZnO-TiO₂ NCs (c), and ZnO-TiO₂/RGO NCs (d).



Fig. 3 SEM images of TiO₂ NPs (a), ZnO NPs (b), ZnO-TiO₂ NCs (c), and ZnO-TiO₂/RGO NCs (d).

particle size of ZnO NPs (Fig. 3b) was slightly higher, exhibiting the same shape and homogeneous distribution as reported in these investigations.^{31,32} In Fig. 3c, the SEM image of ZnO-TiO₂ NCs exhibits fewer agglomeration particles with increased particle size due to combined TiO₂ NPs and ZnO NPs.³³ Compared to TiO₂, the morphology of prepared ZnO-TiO₂ NCs was similar to ZnO NPs. As seen in the SEM image (Fig. 3d), the particle size of prepared ZnO-TiO₂ NCs was decreased after attaching RGO sheets, supporting TEM observations (Fig. 2d) and as reported in a previous study.34 This phenomenon indicates that the ZnO-TiO₂/RGO NCs were successfully prepared. One the other hand, the addition of RGO sheets leads to a change in the morphology of prepared TiO₂ NPs, enhancing the photocatalytic activity of obtained NPs and NCs. SEM images revealed that the surface morphology of ZnO-TiO₂/RGO NCs was enhanced due to the reduction in the particle size of these NCs.

3.4 XPS analysis

The use of XPS spectroscopy is important in order to investigate the quantitative surface chemical composition and oxidation states of the prepared samples of ZnO-TiO₂/RGO NCs, as presented in Fig. 4a–e. The presence of Zn 2p, Ti 2p, O 1s, and C 1s on the surface of ZnO-TiO₂/RGO NCs was clearly observed in Fig. 4a. Additionally, the high-resolution XPS spectra of these elements are shown in Fig. 4b–e. The atomic concentration of each element present on the surfaces of ZnO-TiO₂/RGO NCs was calculated using the following formula.³⁵

$$C_{i} = \frac{\left[A_{i}/S_{i}\right]}{\left[\left.\sum_{j}^{m}A_{j}\right/S_{j}\right]}$$
(1)

 A_j represents the area of the photoelectron peak for the element "*i*", S_i is the sensitivity factor for that element, and *m* is the total number of elements. The atomic concentrations of Zn, Ti, O, and C are presented in Table 1.

As shown in Fig. 4b, the XPS spectra of Zn 2p have two peaks at the binding energy of 1023.13 eV and 1046.22 eV for Zn $2p_{3/2}$ and Zn $2p_{1/2}$, respectively.³⁶ Similarly, the two peaks of Ti 2p (Fig. 4c) were produced by spin-orbital coupling with binding energies of 457.66 eV and 463.90 eV for the Ti $2p_{3/2}$ and Ti $2p_{1/2}$ orbital states.³⁷ The O 1s XPS spectra (Fig. 4d) showed three distinct peaks at 530.09 eV, 531.47 eV, and 533.58 eV.³⁸ The peak at 531.47 eV is ascribed to the oxygen lattice in TiO₂, whereas the peak at 530.09 eV and 533.58 eV were associated with surface defects, the O–H group bonded to Ti⁴⁺ covalently, and oxygen vacancy.³⁹ Fig. 4e displays the XPS spectra of C 1s, which have three peaks at 284.19 eV, 285.05 eV, and 286.40 eV.⁴⁰ The presented XPS results agreed with earlier studies.^{41,42}

3.5 FTIR study

The chemical bonding and functional groups present in the prepared NPs and NCs were determined *via* FTIR technique, as



Fig. 4 Full scan of XPS spectra of ZnO-TiO₂/RGO NCs (a), XPS spectra of Zn 2p (b), XPS spectra of Ti 2p (c), XPS spectra of O 1s (d), and XPS spectra of C 1s (e).

Table I Sunace Composition Analysis of ZhO- HO2/NGO NC:	Table 1	Surface	Composition	Analysis of	ZnO-TiO ₂ /RGO NO	Cs
---	---------	---------	-------------	-------------	------------------------------	----

Elements		Area/S	Atomic (%)
С	C 1s	118.59	21.64
0	C 1s	251.14	45.83
Zn	Zn 2p _{1/2}	61.07	15.63
	Zn 2p _{3/2}	24.58	
Ti	Ti 2p _{1/2}	84.418	16.78
	Ti 2p _{3/2}	7.56	

depicted in the FTIR spectra (Fig. 5). As observed, the bands of synthesized samples at 411.62 cm⁻¹ and 589.78 cm⁻¹ were related to Zn–O and Ti–O bands, respectively.^{33,43,44} The peak

observed at 730.70 cm⁻¹ corresponds to the bending vibrations of the C=C bonds in both the prepared ZnO-TiO₂ NCs and ZnO-TiO₂/RGO NCs. The peaks detected at 1374.24 cm⁻¹ and 1614.85 cm⁻¹ were assigned to the stretching vibrations of C-O and C-H bonds, respectively, in agreement with an earlier study.^{45,46} Furthermore, the stretching vibrations of H-O groups were associated with the band at 3423.10 cm⁻¹, as reported in the previous study.⁴⁷

3.6 UV-vis Measurements

Fig. 6a and b depict the UV-vis spectra and the optical bandgap energy of prepared samples, respectively. It can be observed in

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Open Access Article. Published on 22 May 2024. Downloaded on 7/5/2025 7:28:36 AM.







Fig. 6 UV spectra of RGO, TiO₂ NPs, ZnO NPs, ZnO -TiO₂ NCs, and ZnO -TiO₂/RGO NCs (a), and the optical bandgap energy of prepared samples (b).

Fig. 6a that the absorption peaks exhibited in the UV and visible region are RGO (366.25 nm), TiO_2 NPs (356.75 nm), ZnO NPs (350.74 nm), ZnO-TiO_2 NCs (376.81 nm), and ZnO-TiO_2/RGO NCs (425.82 nm), respectively, as reported in many studies.^{26,27,48} The absorption peaks have shifted toward the absorption edge, which was determined by UV absorbance. This shift indicates that there are changes in the band energy of synthesized NPs and NCs. The bandgap energy of these samples was further estimated by the Tauc eqn (2).³⁰

$$\left[\alpha hv = A \left(hv - E_g\right)^{1/2}\right]$$
 (2)

A is a constant, E_g is the bandgap energy of the sample, and 1/2 signifies a direct allowed transition. The calculated bandgap values (Fig. 6b) for RGO, TiO₂ NPs, ZnO NPs, ZnO-TiO₂ NCs, and ZnO-TiO₂/RGO NCs were 2.27 eV, 3.30 eV, 3.33 eV, 3.03 eV and 2.87 eV, respectively. These values indicate that the bandgap energy (E_g) of TiO₂ NPs was tailored after the addition of ZnO

RSC Advances

and RGO sheets due to the efficient charge transport and the creation of oxygen vacancies.⁴³ The UV findings indicate that the produced NCs may be used in photocatalytic and biological applications because of the increased absorption edge efficiency and reduced bandgap energy.

3.7 Surface charge analysis

The dynamic light scattering (DLS) analysis was employed to measure the surface charge in the culture medium for synthesized NPs and NCs. As shown in Fig. 7a–d, the zeta potential values of pure TiO₂ NPs, pure ZnO NPs, ZnO-TiO₂ NCs, and ZnO-TiO₂/RGO NCs were -22.51 mV, -18.20 mV, -30.2 mV, and -33.7 mV, respectively, as reported in this study.⁴⁹ After the addition of ZnO NPs and RGO sheets, the negative zeta potential of TiO₂ NPs was increased due to ZnO NPs and RGO sheets having a high surface charge.⁵⁰ These negative charges indicated that the surface charge of NCs plays a role in determining their behavior in their interaction with cell membranes through electrostatic repulsion. Surface charge analysis confirmed that the negative zeta potential was essential for enhanced stability.^{28,51}

3.8 Biological studies

3.8.1 Cytotoxicity study. Metal oxide NPs and nanocomposites (NCs) have been applied in cancer therapy, as reported in many studies.^{29,33,52-55} In the present work, the anticancer activities of synthesized NPs at different concentrations (3.125-200 µg ml⁻¹) against HTC 116 cells and NCs were assessed using MTT assay in the dark after 24 h and 48 h of exposure, respectively. As shown in Fig. 8a and b, the prepared TiO₂ NPs exhibited high toxicity at high concentrations after 24 h and 48 h compared with the control group. Conversely, ZnO NPs displayed minimal cytotoxicity toward HCT116 cells after 24 h and 48 h of exposure (Fig. 8a and b), as shown in the previous study.56 It can be seen in Fig. 8a and b that the cell viability was highly decreased for ZnO-TiO₂ NC due to the addition of the ZnO sheet due to their increasing surface charges. Similarly, the incorporation of RGO into ZnO-TiO₂ NCs induces the highest cytotoxicity against HCT116 cancer cells at high concentrations (25, 50, 100, and 200 µg ml^{-1}). It can be observed in Fig. 8a and b that the cell viability of HCT116 cancer cells was decreased with increasing exposure time due to prolonged exposure or the accumulation of reactive oxygen species. At a high concentration of 200 μ g ml⁻¹ at 48 h, the cell viability of HCT116 cancer cells of pure TiO₂ NPs, pure ZnO NPs, ZnO-TiO₂ NCs, and ZnO-TiO₂/RGO NCs were 28.2%, 30.9%, 21.1%, 9.1%, respectively. The IC₅₀ values of prepared NPs and NCs are presented in Table 2. Our results showed that the addition of ZnO NPs and RGO sheets plays a role in the high cytotoxicity of TiO2 NPs.

3.8.2 Biocompatibility evaluation. Several nanoparticles (NPs) and nanocomposites (NCs) have good biocompatibility with various normal human cells.^{57–59} Fig. 9 shows the biocompatibility results of prepared NPs and NC against normal HUVCs. The findings showed that all NPs and NCs had



Fig. 7 Zeta potential analysis of TiO₂ NPs (a), ZnO NPs (b), ZnO-TiO₂ NCs (c), and ZnO-TiO₂/RGO NCs (d).



Fig. 8 Cytotoxicity results of TiO₂ NPs, ZnO NPs, ZnO-TiO₂ NCs, and ZnO-TiO₂/RGO NCs against HCT116 cells using MTT assay after 24 h (a) and 48 (b) exposure.

Table 2 IC₅₀ values of prepared samples for HCT116 cells

NPs and NCs used	HCT116 cell lines				
$\mathrm{IC}_{50}(\mu\mathrm{g}\;\mathrm{mL}^{-1}\pm\mathrm{SD})$					
	24 h	48 h			
TiO ₂ NPs	123.38 ± 0.9	105.02 ± 0.8			
ZnO NPs	133.17 ± 0.4	113.79 ± 0.2			
ZnO-TiO ₂ NCs	108.80 ± 0.7	79.44 ± 0.5			
ZnO-TiO ₂ /RGO NCs	77.82 ± 0.9	48.99 ± 0.3			



Fig. 9 Biocompatibility results of TiO₂ NPs, ZnO NPs, ZnO-TiO2 NCs, and ZnO-TiO₂/RGO NCs against normal cells HUVCES cells by using MTT assay.

excellent biocompatibility, as shown by the high cell viability of HUVEC cells. The findings indicate that the ZnO-TiO₂/RGO NCs exhibit significant cytotoxicity against cancer cells and have great biocompatibility with normal cells. The results presented indicate that these samples are safe for normal cell lines and might be useful in biomedical applications. Due to its eco-friendliness, biocompatibility, and probable bioactivity, our plant extract enhances physicochemical NPs and NCs compared with traditional chemical methods for synthesis.

4. Conclusion

The present work proposed green synthesis and sonication routes to synthesize TiO2 NPs, pure ZnO NPs, ZnO-TiO2 NCs and ZnO-TiO₂/RGO NCs. XRD, SEM with EDX, TEM, XPS, FTIR, UVvis and DLS spectroscopy were applied to examine the physicochemical properties of the obtained NPs and NCs. XRD analysis confirms that the crystal structure of synthesized TiO₂ is affected by adding ZnO and RGO sheets. TiO₂ NPs, ZnO NPs, ZnO-TiO₂ NCs, and ZnO-TiO₂/RGO NCs displayed average crystallite sizes (D) of 8 \pm 0.9, 20 \pm 0.2, 14 \pm 0.6, and 11 \pm 0.2 nm, respectively. TEM and SEM images revealed that the addition of ZnO NPs and RGO plays a role in the particle size and morphology of TiO₂ NPs. Furthermore, XPS analysis confirmed that prepared ZnO-TiO2/RGO NCs consisted of elements zinc (Zn), titanium (Ti), oxygen (O), and carbon (C) without impurities. FTIR revealed the chemical bonding and functional groups present in the synthesized NPs and NCs. UVvis study showed that the bandgap energy of TiO₂ decreased from 3.30 eV to 2.78 eV after ZnO and RGO sheets. DLS results showed that ZnO and RGO sheets increase the surface charge of pure TiO₂ NPs (-22.51 mV), ZnO NPs (-18.27 mV), ZnO-TiO₂-NCs (-30.20 mV), and ZnO-TiO₂/RGO NCs (-33.77 mV). These results suggest that the prepared NPs and NCs can be used for photocatalytic and biomedical applications. MTT experiments were performed to assess the cytotoxicity and biocompatibility of synthesized NPs and NCs against HTC116 cancer and normal HUVEC cells for 24 h and 48 h exposure. These results showed that the cell viability of HCT116 cancer cells reduced with time due to extended exposure or reactive oxygen species formation. Furthermore, the ZnO-TiO₂/RGO NCs exhibited the maximum cytotoxicity, suggesting cancer treatment potential. Also, the biocompatibility data on normal HUVEC cells showed that all synthesized NPs and NCs are safe for cancer therapy applications due to their low-toxic properties. Additionally, this study shows that the plant extract provides natural reducing and capping properties for NPs and NCs due to its eco-friendliness, biocompatibility, and possible bioactivity. This study suggests

that cytotoxic effects and potential applications of these samples could be further investigated using *in vivo* models.

Data availability

The data in this work may be obtained by contacting the corresponding author.

Author contributions

Conceptualization was done by Z. M. A.; investigation and methods were carried out by Z. M. A., H. A. A., and S. A. Original draft preparation was done by Z. M. A. Review and editing were conducted by Z. M. A., H. A. A., S. A., and N. A. Y. All authors have reviewed and approved the final version of the text for publication.

Conflicts of interest

This work is original research and has not been submitted for publication anywhere.

Acknowledgements

The authors extend their sincere appreciation to researchers supporting project number (RSPD2024R813), King Saud University, Riyadh, Saudi Arabia for funding this research.

References

- 1 M. Lorscheider, A. Gaudin, J. Nakhlé, K.-L. Veiman, J. Richard and C. Chassaing, *Ther. Delivery*, 2021, **12**, 55–76.
- 2 A. Tewabe, A. Abate, M. Tamrie, A. Seyfu and E. Abdela Siraj, *J. Multidiscip. Healthc.*, 2021, **14**, 1711–1724.
- 3 G. D. Cha, W. H. Lee, C. Lim, M. K. Choi and D. Kim, *Nanoscale*, 2021, **193**, 2121–2139.
- 4 S. Karki, M. B. Gohain, D. Yadav and P. P. Ingole, *Int. J. Biol. Macromol.*, 2023, 116222.
- 5 J. C. Durán-Álvarez, V. A. Hernández-Morales, M. Rodríguez-Varela, D. Guerrero-Araque, D. Ramirez-Ortega, F. Castillón, P. Acevedo-Peña and R. Zanella, *Catal. Today*, 2020, 341, 71– 81.
- 6 C. Siriwong, N. Wetchakun, B. Inceesungvorn, D. Channei,
 T. Samerjai and S. Phanichphant, *Prog. Cryst. Growth Charact. Mater.*, 2012, 58, 145–163.
- 7 A. H. Naggar, T. A. Seaf-Elnasr, M. Thabet, E. M. A. El-Monaem, K. F. Chong, Z. H. Bakr, I. H. Alsohaimi, H. M. Ali, K. S. El-Nasser and H. Gomaa, *Environ. Sci. Pollut. Res. Int.*, 2023, 30, 108247–108262.
- 8 P. K. Shihabudeen and A. R. Chaudhuri, *Nanoscale*, 2022, **14**, 5185–5193.
- 9 W. Wu, C. Jiang and V. A. L. Roy, *Nanoscale*, 2016, 8(47), 19421-19474.
- 10 M. Ahamed, M. J. Akhtar, M. Khan and H. A. Alhadlaq, *ACS Omega*, 2022, 7, 7103–7115.
- 11 M. Safavipour, M. Kharaziha, E. Amjadi, F. Karimzadeh and A. R. Allafchian, *Talanta*, 2020, **208**, 120369.

- 12 R. R. Saravanan, M. M. Khan, V. K. Gupta, E. Mosquera,
 F. Gracia, V. Narayanan and A. Stephen, *RSC Adv.*, 2015, 5, 34645–34651.
- 13 M. Ahamed, R. Lateef, M. A. M. Khan, P. Rajanahalli and M. J. Akhtar, J. Funct. Biomater., 2023, 9, 14–38.
- 14 S. Yao, S. Zhou, J. Wang, W. Li and Z. Li, *Photochem. Photobiol. Sci.*, 2019, **18**, 2989–2999.
- 15 M. A. Hossain, M. Elias, D. R. Sarker, Z. R. Diba, J. M. Mithun, M. A. K. Azad, I. A. Siddiquey, M. M. Rahman, J. Uddin and M. N. Uddin, *Res. Chem. Intermed.*, 2018, 44, 2667–2683.
- 16 M. Ahamed, M. J. Akhtar, M. A. M. Khan and H. A. Alhadlaq, *Int. J. Nanomed.*, 2021, **16**, 89–104.
- 17 Z. M. Alaizeri, H. A. Alhadlaq, S. Aldawood, M. J. Akhtar and M. Ahamed, *Polymers*, 2022, 14(10), 2036.
- 18 M. R. Arefi and S. Rezaei-Zarchi, *Int. J. Mol. Sci.*, 2012, **13**, 4340–4350.
- 19 V. N. Kalpana, B. A. S. Kataru, N. Sravani, T. Vigneshwari, A. Panneerselvam and V. Devi Rajeswari, *OpenNano*, 2018, 3, 48–55.
- 20 R. Tao, J.-M. Wu, J. Xiao, Y. Zhao, W. Dong and X. Fang, *Appl. Surf. Sci.*, 2013, **279**, 324–328.
- 21 S. Karki, M. B. Gohain, D. Yadav and P. G. Ingole, *J. Biol. Macromol.*, 2021, 2121–2139.
- 22 K. Pal, S. Chakroborty, P. Panda, N. Nath and S. Soren, *Environ. Sci. Pollut. Res.*, 2022, **29**, 76626–76643.
- 23 F. Bovand, S. Chavoshi and M. Ghorbanpour, Nanotechnol. Environ. Eng., 2023, 8, 281–295.
- 24 M. A. Hanif, H. Shin, D. Chun, H. G. Kim, L. K. Kwac and Y. S. Kim, *Membranes*, 2022, **13**(1), 50.
- 25 M. Pudukudy and Z. Yaakob, *J. Cluster Sci.*, 2015, **26**, 1187–1201.
- 26 H. Van Bao, N. M. Dat, N. T. H. Giang, D. B. Thinh, L. T. Tai,
 D. N. Trinh, N. D. Hai, N. A. D. Khoa, L. M. Huong,
 H. M. Nam, M. T. Phong and N. H. Hieu, *Surf. Interfaces*, 2021, 23, 100950.
- 27 A. Gunasekaran, A. K. Rajamani, C. Masilamani,
 I. Chinnappan, U. Ramamoorthy and K. Kaviyarasu, *Catalysts*, 2023, 13(2), 215.
- 28 R. A. Gonçalves, R. P. Toledo, N. Joshi and O. M. Berengue, *Molecules*, 2021, **26**, 2236.
- 29 J. Xu, H. Shi, M. Ruth, H. Yu, L. Lazar, B. Zou, C. Yang, A. Wu and J. Zhao, *PLoS One*, 2013, **8**, e70618.
- 30 G. Gohari, A. Mohammadi, A. Akbari, S. Panahirad, M. R. Dadpour, V. Fotopoulos and S. Kimura, *Sci. Rep.*, 2020, **10**, 1–14.
- 31 M. N. Shamhari, S. B. Wee, F. S. Chin and Y. K. Kok, *Acta Chim. Slov.*, 2018, **65**(3), 578–585.
- 32 J. Wojnarowicz, T. Chudoba, S. Gierlotka and W. Lojkowski, *Nanomaterials*, 2020, **10**(6), 1086.
- 33 M. Zamani, M. Rostami, M. Aghajanzadeh, H. Kheiri Manjili,
 K. Rostamizadeh and H. Danafar, *J. Mater. Sci.*, 2018, 53, 1634–1645.
- 34 Y. Huang, D. Chen, X. Hu, Y. Qian and D. Li, *Nanomaterials*, 2018, **8**, 1–9.
- 35 Y. Wang, T. Brezesinski, M. Antonietti and B. Smarsly, *ACS Nano*, 2009, **3**, 1373–1378.

- 36 D. Zhang, C. Du, J. Chen, Q. Shi, Q. Wang, S. Li, W. Wang,
 X. Yan and Q. Fan, *J. Sol-Gel Sci. Technol.*, 2018, 88, 422–429.
- 37 T. Y. Lee, C. Y. Lee and H. T. Chiu, ACS Omega, 2018, 3, 10225–10232.
- 38 S. Y. Kim, Y. H. Jung, M. J. Cho, J. W. Lee, H. G. Park, D. H. Kim, T. W. Kim, I. Yun and D. S. Seo, *ECS Solid State Lett.*, 2015, 4, P22–P24.
- 39 R. Heinhold and M. W. Allen, *J. Mater. Res.*, 2012, 27, 2214–2219.
- 40 G. Qin, H. Zhang, H. Liao, Z. Li, J. Tian, Y. Lin, D. Zhang and Q. Wu, *J. Mater. Sci.*, 2017, **52**, 10981–10992.
- 41 Z. Liao, Y. Yu, Z. Yuan and F. Meng, *Chemosensors*, 2021, 9, 284.
- 42 F. A. Alharthi, A. A. Alsyahi, S. G. Alshammari, H. A. Al-Abdulkarim, A. AlFawaz and A. Alsalme, *ACS Omega*, 2022, 7, 2786–2797.
- 43 M. G. Ghoniem, S. A. Talab, A. K. Modwi and K. K. Taha, *Orient. J. Chem.*, 2021, 37, 609–618.
- 44 J. M. Abisharani, R. Dineshkumar, S. Devikala, M. Arthanareeswari and S. Ganesan, *Mater. Res. Express*, 2020, 025507.
- 45 Y. M. A. Mohamed and Y. A. Attia, *Environ. Sci. Pollut. Res.*, 2023, **30**, 51344–51355.
- 46 P. Rungqu, O. O. Oyedeji and A. O. Oyedeji, *Chemical Composition of Hypoxis Hemerocallidea Fisch. & C.A. Mey from Eastern Cape*, South Africa, 2019.
- 47 S. A. Hosseini and S. Babaei, *J. Braz. Chem. Soc.*, 2016, 28, 299–307.
- 48 F. Zheng, W. L. Xu, H. D. Jin, X. T. Hao and K. P. Ghiggino, *RSC Adv.*, 2015, 5, 89515–89520.

- 49 R. A. El-Kholy, H. Isawi, E. Zaghlool, E. A. Soliman, M. M. H. Khalil, M. M. Said, A. elhameed and M. El-Aassar, *Environ. Sci. Pollut. Res.*, 2023, **30**, 69514–69532.
- 50 R. Ebrahimi, M. Mohammadi, A. Maleki, A. Jafari,
 B. Shahmoradi, R. Rezaee, M. Safari, H. Daraei, O. Giahi,
 K. Yetilmezsoy and S. H. Puttaiah, *J. Inorg. Organomet. Polym. Mater.*, 2020, **30**, 923–934.
- 51 A. A. Sharwani, K. B. Narayanan, M. E. Khan and S. S. Han, *Sci. Rep.*, 2022, **12**, 1–18.
- 52 I. L. Hsiao and Y. J. Huang, Chem. Res. Toxicol., 2011, 24, 303-313.
- 53 F. Mohammad, I. B. Bwatanglang, H. A. Al-Lohedan, J. P. Shaik, H. H. Al-Tilasi and A. A. Soleiman, *Coatings*, 2023, **13**, 172.
- 54 A. Y. Elderdery, B. Alzahrani, S. M. A. Hamza, G. Mostafa-Hedeab, P. L. Mok and S. K. Subbiah, *Bioinorg. Chem. Appl.*, 2022, **11**, 5949086.
- 55 S. Albukhaty, L. Al-Bayati, H. Al-Karagoly and S. Al-Musawi, *Anim. Biotechnol.*, 2022, **33**, 864–870.
- 56 P. S. Mohan, F. Sonsuddin, A. B. Mainal, R. Yahya, G. Venkatraman, J. Vadivelu, D. A. Al-Farraj, A. M. Al-Mohaimeed and K. M. Alarijani, *Antibiotics*, 2021, **10**, 1–18.
- 57 J. Wojnarowicz, T. Chudoba, S. Gierlotka, K. Sobczak and W. Lojkowsk, *Crystals*, 2018, **8**, 179.
- 58 S. J. Soenen, B. B. Manshian, J.-M. Montenegro, F. Amin,
 B. Meermann, T. Thiron, M. J. Cornelissen, F. Vanhaecke,
 S. H. Doak, W. J. Parak, S. C. De Smedt and
 K. Braeckmans, ACS Nano, 2012, 6(7), 5767–5783.
- 59 G. Sanità, B. Carrese and A. Lamberti, *Front. Mol. Biosci.*, 2020, 7, 587012.