RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2024, 14, 23645

Structural, optical, magnetic properties and energy-band structure of MFe_2O_4 (M = Co, Fe, Mn) nanoferrites prepared by co-precipitation technique

Tran Dang Thanh,^{ab} Tran Thi Ngoc Nha,^b Tran Thi Ha Giang,^a Pham Hong Nam,^a Dang Ngoc Toan, ^b ^{cd} Dinh Thanh Khan,^e Do Hung Manh ^b ^{ab} and Pham Thanh Phong ^b *^{fg}

 MFe_2O_4 (M = Co, Fe, Mn) nanoparticles were successfully formed through the chemical co-precipitation technique. X-ray diffraction, scanning electron microscopy, and energy-dispersive X-ray analysis were used to investigate samples' structural properties. The investigated structural properties included phases formed, crystallite size, cation distribution, hopping length, bond length, bond angle, edge length, and shared and unshared octahedral edge length. Scanning electron micrographs of the prepared samples demonstrated well-defined crystalline nanoparticles. The grain diameter was 15, 9, and 34 nm for CoFe₂O₄, Fe₃O₄, and MnFe₂O₄, respectively. The energy-dispersive X-ray analysis confirmed the existence of every element (Co, Fe, and O) and no discernible impurities in the samples. The optical properties were studied in detail through photoluminescence (PL) spectroscopy and Raman spectroscopy. The presence of active modes in Raman spectra confirmed the spinel structure of the MFe₂O₄ nanoparticles. The direct bandgap energy estimated through UV-visible spectroscopy was about 2.59–2.64 eV, corresponding with the energy-band structures of the octahedral site (1.70 eV) and the tetrahedral site (0.9 eV). This result was further confirmed by PL emission spectra. Based on Mie theory and UV-visible and PL spectral data, the mechanism of photothermal characterization for MFe_2O_4 nanoparticles was determined. Investigating the changes in temperature of magnetic parameters including coercivity, squareness ratio, and saturation magnetization for MFe₂O₄ samples showed the dominant influence of ion distribution and A-A, A-B, and B-B exchange interactions. This study also showed that strong anisotropy and weak dipolar interaction tended to increase the coercivity and squareness ratio of CoFe₂O₄. Conversely, weaker anisotropy and stronger dipolar interaction corresponded with the small coercivity and squareness ratio of Fe_3O_4 and $MnFe_2O_4$ samples.

Received 28th June 2024 Accepted 23rd July 2024

DOI: 10.1039/d4ra04692g

rsc.li/rsc-advances

1. Introduction

The needs of emerging industries require various multifunctional materials that can be applied in diverse applications. Nanomaterials, especially nanosized spinel ferrites with the general formula MFe_2O_4 (M = divalent cation), exhibit many outstanding properties in the fields of magnetism, conductivity, and optics. Thus, they are a potential candidate in various fields from the electronics industry to biomedicine.¹⁻³ In general, the cation distribution between the A-site and B-site of an AB₂O₄ spinel structure decides the structural type of ferrites, *i.e.*, whether it is normal or inverse or mixed.⁴ If all divalent M²⁺ ions occupy the tetrahedral site (A site) and the trivalent Fe³⁺ ions occupy the octahedral site (B site), one would have normal spinel ferrites, and the inverse spinel structure becomes possible only when all divalent ions occupy the B site. The trivalent Fe³⁺ ions can be equally divided between the A and remaining B sites.5,6 Among nanoferrites, CoFe2O4, Fe3O4, and MnFe₂O₄ nanoferrites are excellent because of their unique physical properties and important applications.⁷ Bulk CoFe₂O₄, MnFe₂O₄ and Fe₂O₄ ferrites are predominantly inverse spinel

^aInstitute of Materials Science, Vietnam Academy of Science and Technology, 18-Hoang Quoc Viet, Hanoi City, Vietnam

^bGraduate University of Science and Technology, Vietnam Academy of Science and Technology, 18-Hoang Quoc Viet, Hanoi City, Vietnam

^cInstitute of Research and Development, Duy Tan University, 550000 Danang, Vietnam ^dFaculty of Natural Sciences, Duy Tan University, 550000 Danang, Vietnam

[&]quot;The University of Danang-University of Science and Education, Danang 550000, Vietnam

Laboratory of Magnetism and Magnetic Materials, Science and Technology Advanced Institute, Van Lang University, Ho Chi Minh City, Vietnam. E-mail: phamthanhphong@vlu.edu.vn

^sFaculty of Applied Technology, School of Technology, Van Lang University, Ho Chi Minh City, Vietnam

ferrites in which Co²⁺/Fe²⁺/Mn²⁺ ions primarily occupy the Bsite and Fe³⁺ ions are distributed equally among the A- and Bsites.8 However, in most cases, the preparation methods and the reduced size of spinels to the nanometer scale, the degree of inversion of the crystal structure becomes different from that of their bulk counterparts. Thus, the cation distribution directly affects the mechanical, chemical, and physical characteristics of spinel ferrite nanoparticles (NPs). This issue is well documented in the literature.9 However, owing to the cation exchange between tetrahedral and octahedral sites, the properties of some spinels become complicated; they are not the same even if they have the same chemical formula.¹⁰ This is a result of the quantum-confinement effect and the strength between the two A and B sublattice interactions.¹⁰ Therefore, controlling the fabrication parameters and choosing the appropriate sample-preparing method can confer beneficial properties for nanoferrite applications in engineering and biomedicine. The fabrication of CoFe₂O₄ and Fe₃O₄ NPs and most of their optical and magnetic properties have been thoroughly studied and are well documented.

Hunpratub *et al.*¹¹ synthesized CoFe₂O₄ NPs through a coprecipitation method and investigated the effect of cation distribution on their magnetic properties. They found that the predicted net magnetic moment values of all samples corresponded with the decrease in migration of Co^{2+} and Fe^{3+} between A and B sites. This result agreed with those of Yadav *et al.*¹² and Kumar *et al.*¹³ Besides cation distribution and particle size, they suggested that the noncollinear structure of spins on the surface also needs to be considered as an important factor affecting the magnetization of CoFe_2O_4 NPs.

Ansari *et al.*¹⁴ studied the structural, physical, chemical, electronic, and magnetic properties of solvothermally synthesized CoFe₂O₄ NPs. In particular, they found a doublet peak of $T_{2g}(1)$ mode for CoFe₂O₄ with different sizes, consistent with the observation of Chandramohan *et al.*¹⁵ Å. de Jesús Ruíz-Baltazar *et al.*¹⁶ found that the $T_{2g}(1)$, $T_{2g}(2)$, and E_g modes are located at 312, 545, and 667 cm⁻¹, respectively, consistent with the strange modes at 453, 755, 870, and 950 cm⁻¹ for 40 nm-sized Fe₃O₄. They attributed the appearance of these unknown modes to iron oxides left over from the magnetite formation. However, many authors believe that the Raman characteristics of the inverse and mixed spinel structure are double peaks.¹⁷⁻¹⁹ Therefore, 10 Raman peaks at most can be observed in Fe₃O₄ NPs.

It is clear that the previous reports of MFe_2O_4 only confined to analyze the structural, optical, magnetic, and the correlation between the cation distribution with the modification of its physical properties. In addition, in recent years, the MFe_2O_4 superparamagnetic nanomaterials were investigated for magnetic hyperthermia therapy. As a whole, this confirmed a fact that the role of dipolar interaction in the magnetic property were not investigated at length for MFe_2O_4 nanoferrites *via* the co-precipitation method. Therefore, an intention was carried out to study the above said property for MFe_2O_4 nanoferrites.

The photothermal effect in Fe₃O₄ NPs and its process based on photoluminescence emission in the near-infrared (NIR) region are attracting scientific research attention. Sadat *et al.*²⁰ used PL emission spectra in the NIR region and UV-visible (UV-Vis) spectra to establish the mechanism for interpreting the photothermal effect in (PAA)/Fe₃O₄, PS/Fe₃O₄, and Si/PS/Fe₃O₄ NPs. Zhao et al.²¹ studied the photothermal effect of Fe₃O₄ NPs in solution and thin-film forms under the influence of white light and NIR laser irradiation. Interestingly, they obtained a stronger photothermal effect for Fe₃O₄ under the stimulation of white-light irradiation. Their results are also explained based on PL and UV-Vis spectra and energy bands structure. However, the energy bands structure of ferrites is still a subject of debate. In general, the relatively complex electronic structure of transition metals has led to various confusing interpretations of the optical and magneto-optical Kerr spectra for ferrites owing to different assignments of the observed transitions.²² Specifically, the photothermal effect mechanism of CoFe₂O₄ and MnFe₂O₄ NPs has not yet been studied.

Recently, we have synthesized and determined the elastic parameters and nanocrystalline size of spinel ferrites MFe_2O_4 (M = Co, Fe, Mn, and Zn) through X-ray diffraction and infrared spectroscopy analyses.²³ In the present work, we continued to fabricate and study the structural, optical, and magnetic characteristics of the hard magnetic $CoFe_2O_4$ and the soft magnetic Fe_3O_4 and $MnFe_2O_4$ NPs. We focused on discussing the relationship between UV-Vis and PL spectra from building the energy-band structure diagram of the three samples, as well as the role of dipolar interaction in the magnetic property of MFe_3O_4 NPs.

Experimental detail

2.1. Synthesis of MFe_2O_4 (M = Co, Fe, Mn)

The co-precipitation technique was used to synthesize MFe₂O₄ NPs following a previous procedure.²³ Cobalt(II) chloride hexahydrate (CoCl₂·6H₂O, \geq 98%), iron(m) chloride hexahydrate (FeCl₃·6H₂O, \geq 98%), manganese(II) chloride tetrahydrate (MnCl₂·4H₂O, \geq 98%), ferrous chloride tetrahydrate (FeCl₂- $\cdot 4H_2O$, $\geq 98\%$), sodium hydroxide (NaOH, $\geq 98\%$) were purchased from Sigma-Aldrich, US. Each MFe₂O₄ sample was prepared from 50 mL of mixed aqueous solution by dissolving required amounts of CoCl2.6H2O and FeCl3.6H2O (for $CoFe_2O_4$), $FeCl_2 \cdot 4H_2O$ and $FeCl_3 \cdot 6H_2O$ (for Fe_3O_4), and $MnCl_2 \cdot 4H_2O$ and $FeCl_3 \cdot 6H_2O$ (for $MnFe_2O_4$) with 2:1 molar ratio of Fe³⁺ to M²⁺, respectively. Chemical precipitation was achieved at room temperature under vigorous stirring by adding 200 mL of 2 M NaOH solution and mixing for 60 min at pH 11 to 13. Afterward, the black precipitate of each sample was cooled to room temperature, the precipitates were separated with a permanent magnet, and they were washed with deoxygenated distilled water until neutral pH. Finally, MFe₂O₄ was washed with acetone and dried in an oven at 70 °C for 120 min. All steps of preparing MFe₂O₄ nanoferrites are clearly illustrated in Fig. 1.

2.2. Characterization

The crystalline phase of the synthesized MFe₂O₄ NPs was examined using a Rigaku X-ray diffractometer equipped with Cu

Paper



Fig. 1 Schematic for synthesis MFe₂O₄ (M = Co, Fe, Mn) nanoferrites using co-precipitation method.

Kα ($\lambda = 1.5406$ Å). The 2 θ range of 10° to 80° and a step size of 0.02° with a dwell time of 0.05 s were used during the measurement. Morphology and particle size were analyzed by scanning electron microscopy (SEM; Hitachi S-4800). The chemical compositions of MFe₂O₄ NPs were obtained by the energy-dispersive X-ray (EDX) analysis using a Hitachi S-4800 FESEM equipped with an EDX energy-dispersive spectroscopy attachment.

Optical properties were assessed by PL emission. Measurements were made at an excitation wavelength of 310 nm using a fluorescence spectrophotometer (Fluorolog 3 FL3-22; Horiba). Raman spectra were obtained using an XploRA PLUS Micro Raman spectrometer (Horiba) with a laser wavelength of 785 nm as an excitation source. UV-Vis spectroscopy (JASCO V-770) was used to determine the bandgap of MFe₂O₄ NPs. A 3 T Physical Property Measurement System VersaLab (model VL173; USA) was used to analyze magnetic properties.

3. Results and discussion

3.1. Structural characteristics of MFe₂O₄ NPs

Fig. 2 illustrates the X-ray diffraction (XRD) pattern and Rietveld refinement of CoFe₂O₄, Fe₃O₄, and MnFe₂O₄ compatible with the JCPDS card number of CoFe₂O₄ (No. 156-5326), Fe₃O₄ (No. 151-3304), MnFe₂O₄ (No. 230-0618). Their patterns showed typical diffraction peaks assigned to the (111), (220), (311), (222), (400), (422), (511), (440), (620), and (533) planes of the cubic spinel structure with the *Fd*3*m* space group of ferrites. No additional peaks arising from impurities were detected within the limits of XRD measurement. The goodness factor (χ^2) was less than 2, which lay within the confidence threshold ($1 \le \chi^2 < 2$), demonstrating high refinement reliability.

The experimental lattice constant (a_{exp}) , unit-cell volume (V) and oxygen positional parameter (u) were determined from Rietveld refinement and are listed in Table 1. The lattice

constant and oxygen positional parameter of Fe₃O₄ were less than those of CoFe₂O₄ and MnFe₂O₄, which was attributed to the redistribution of cations (Fe³⁺, Mn²⁺, and Co²⁺) between the two interstitial sites.^{11,24} Conversely, the disparity of the oxygen positional parameter with ideal value (u = 0.375 Å) may be due to anion displacement from the ideal position to expand the tetrahedral interstices.²⁵ However, these experimental values were close to the values obtained for the ferrite system in the literature.^{26,27}



Fig. 2 The Rietveld refinement of XRD patterns for MFe_2O_4 nanoparticles (observed – black line, calculated – red line and difference – blue line).

RSC Advances

Table 1 Cation distribution, experimental and theoretical lattice parameter (a_{exp} , a_{th}), unit cell volume (V) and oxygen positional parameter (u) mean ionic radii of A site ($\overline{r_A}$) and B site ($\overline{r_B}$), crystalline grain diameter (d), grain size (D) of MFe₂O₄ nanoparticles

	Cation distribution									
Sample	A site	B site	a_{\exp} (Å)	$a_{ m th}$ (Å)	$V\left(\text{\AA}^3\right)$	u	$\overline{r_{\rm A}}({\rm \AA})$	$\overline{r_{\mathrm{B}}}(\mathrm{\AA})$	<i>d</i> (nm)	D (nm)
$CoFe_2O_4$	$Co_{0.08}^{2+}Fe_{0.92}^{3+}$	$Co_{0.92}^{2+}Fe_{1.08}^{3+}$	8.4093	8.4093	594.67	0.3806	0.4972	0.6910	14.6	14.7
$MnFe_2O_4$	Fe ³⁺	$Mn^{2+}Fe^{3+}$	8.3628 8.4981	8.3628 8.4981	584.86 613.71	0.3762	0.4900 0.4900	0.7125	7.0 27.4	9.0 34.3

The cation distribution at the A and B sites was determined based on the assumption that the occupancies of the cations with a sum of cations at A site equal to 1 and a sum of cations at B site equal to 2 of the three samples are represented in Table 1. Thus, according to the cation distribution, the theoretical lattice constant (a_{th}) was calculated using the following expression:^{11,26,28}

$$a_{\rm th} = \frac{8}{3\sqrt{3}} \Big[(r_{\rm A} + R_{\rm O}) + \sqrt{3} (r_{\rm B} + R_{\rm O}) \Big]$$
 (1)

where r_A and r_B are the ionic radius of tetrahedral and octahedral sites, respectively, and were calculated using the equations:

$$r_{\rm A} = a_{\rm exp} \sqrt{3(u - 0.25)} - R_{\rm O}$$
 (2a)

$$r_{\rm B} = a_{\rm exp}\sqrt{3}\left(\frac{5}{8} - u\right) - R_{\rm O} \tag{2b}$$

where $R_{\rm O}$ is the radius of oxygen ion (1.38 Å). The ($a_{\rm th}$) values of three samples are listed in Table 1. The lattice constants $a_{\rm th}$ and $a_{\rm exp}$ well agreed with each other, indicating the migration of Co²⁺, Mn²⁺, and Fe³⁺ ions into the tetrahedral and octahedral sites, respectively.²⁸

Moreover, the mean cation radii at the tetrahedral $(\overline{r_A})$ and octahedral sites $(\overline{r_B})$ were determined based on the following cation distribution:

$$\overline{r_{\mathrm{A}}} = C(\mathrm{M_{A}}^{2+}) \cdot r(\mathrm{M_{A}}^{2+}) + C(\mathrm{Fe_{A}}^{3+}) \cdot r(\mathrm{Fe_{A}}^{3+})$$
(3a)

$$\overline{r_{\rm B}} = \frac{C({\rm M_{B}}^{2+}) \cdot r({\rm M_{B}}^{2+}) + C({\rm Fe_{B}}^{3+}) \cdot r({\rm Fe_{B}}^{3+})}{2} \qquad (3b)$$

where *C* is the ionic concentration at the tetrahedral and octahedral sites; $r(M_A^{2+})$ are the ionic radii of $Co^{2+}(0.58 \text{ Å})$ and $Fe^{3+}(0.49 \text{ Å})$ ions in the tetrahedral sites, respectively; $r(M_B^{2+})$, $r(Fe_B^{3+})$ are the ionic radii of $Co^{2+}(0.745 \text{ Å})$, $Mn^{2+}(0.83 \text{ Å})$, $Fe^{2+}(0.78 \text{ Å})$, and $Fe^{3+}(0.645 \text{ Å})$ ions in the octahedral sites, respectively.²⁹ The $\overline{r_A}$ and $\overline{r_B}$ values of three samples are shown in Table 1. The average ionic radius of the tetrahedral site was reduced whereas the average ionic radius of the octahedral site increased in the order Co > Fe > Mn ions in MFe_2O_4 . This finding was because Fe^{3+} ions (0.49 Å) with a smaller ionic radius. Conversely, in (B) sites, all Mn^{2+} ions (0.83 Å) and Fe^{2+} ions (0.78 Å) with larger ion radii migrated to the B site, so the average ion radius of the B site increased.

The hopping length ($L_{\rm A}$ and $L_{\rm B}$), tetrahedral and octahedral bond lengths ($d_{\rm AO}$ and $d_{\rm BO}$), tetrahedral edge length ($d_{\rm AOE}$), and shared and unshared octahedral edge length ($d_{\rm BOE}$ and $d_{\rm BOEU}$) of the three samples were computed according to the equations below,^{28,30,31} and the results are listed in Table 2.

$$L_{\rm A} = 0.25 a_{\rm exp} \sqrt{3} \tag{4a}$$

$$L_{\rm B} = 0.25 a_{\rm exp} \sqrt{2} \tag{4b}$$

$$d_{\rm AO} = a_{\rm exp} \sqrt{3} \left(u - \frac{1}{4} \right) \tag{5a}$$

$$d_{\rm BO} = a_{\rm exp} \left(3u^2 - \frac{11}{4}u + \frac{43}{64} \right)^{1/2}$$
(5b)

$$d_{\text{AOE}} = a_{\text{exp}}\sqrt{2}\left(2u - \frac{1}{2}\right) \tag{6a}$$

$$d_{\rm BOE} = a_{\rm exp}\sqrt{2}(1-2u) \tag{6b}$$

$$d_{\rm BOEU} = a_{\rm exp} \left(4u^2 - 3u + \frac{11}{16} \right)^{1/2}$$
(6c)

In ferrites, the distances between intrinsic ions (cation–anion and cation–cation distances) and bond angles between metal ions directly affect the strength of the magnetic exchange interactions, thus, to gain deeper insight into the magnetic properties of the samples, the inter-ionic length and bond angles between ions were calculated, and results are provided in Tables 3 and 4. The interionic distances were determined using relations,^{32–35}

$$p = a_{\exp}\left(\frac{5}{8} - u\right) \tag{7a}$$

$$q = a_{\exp}\sqrt{3}\left(u - \frac{1}{4}\right) \tag{7b}$$

$$r = a_{\exp}\sqrt{11}\left(u - \frac{1}{4}\right) \tag{7c}$$

$$s = a_{\exp}\sqrt{3}\left(\frac{u}{3} + \frac{1}{8}\right) \tag{7d}$$

for cation-anion length,

Table 2 Hopping length (L_A and L_B), tetrahedral bond length (d_{AO}), octahedral bond length (d_{BO}), tetrahedral edge length (d_{AOE}), shared octahedral edge length (d_{BOE}), unshared octahedral edge length (d_{BOEU}) of MFe₂O₄ nanoparticles

	Hopping le	ngth	Edges							
Sample	$L_{\mathrm{A}}\left(\mathrm{\AA} ight)$	$L_{\mathrm{B}}\left(\mathrm{\AA}\right)$	$d_{ m AO}~({ m \AA})$	$d_{ m BO}$ (Å)	$d_{ m AOE} ({ m \AA})$	$d_{ ext{BOE}}\left(ext{\AA} ight)$	$d_{ ext{boeu}}\left(ext{\AA} ight)$			
CoFe ₂ O ₄	3.641	2.973	1.902	2.056	3.106	2.840	2.975			
Fe ₃ O ₄	3.621	2.957	1.828	2.081	2.985	2.928	2.957			
MnFe ₂ O ₄	3.680	3.005	1.925	2.076	3.144	2.865	3.006			

$$b = \sqrt{2} \ \frac{a_{\exp}}{4} \tag{8a}$$

$$c = \sqrt{11} \ \frac{a_{\exp}}{8} \tag{8b}$$

$$d = \sqrt{3} \ \frac{d_{\exp}}{4} \tag{8c}$$

$$e = \sqrt{3} \ \frac{3a_{\exp}}{8} \tag{8d}$$

$$f = \sqrt{6} \ \frac{a_{\exp}}{4} \tag{8e}$$

for cation-cation distances.

All these parameters of the three samples are given in Table 3. The change in values of these intrinsic distances well agreed with the unit-cell volume of the samples (Table 1).

The bond angles $(\theta_1; \theta_2; \theta_3; \theta_4; \theta_5)$ between metal ions were computed from values of cation-cation and cation-anion lengths using expressions.³²⁻³⁵ Results are listed in Table 4.

$$\theta_1 = \cos^{-1}\left(\frac{p^2 + q^2 - c^2}{2pq}\right)$$
(9a)

$$\theta_2 = \cos^{-1}\left(\frac{p^2 + r^2 - e^2}{2pr}\right)$$
(9b)

$$\theta_3 = \cos^{-1}\left(\frac{2p^2 - b^2}{2p^2}\right)$$
(9c)

$$\theta_4 = \cos^{-1}\left(\frac{p^2 + s^2 - f^2}{2ps}\right)$$
(9d)

$$\theta_5 = \cos^{-1}\left(\frac{r^2 + q^2 - d^2}{2rq}\right)$$
(9e)

The values of θ_1 , θ_2 , and θ_5 for Fe₃O₄ exceeded those of CoFe₂O₄ and MnFe₂O₄, whereas those of θ_3 and θ_4 for Fe₃O₄

Table 4 Values of the interionic angles (in degrees) of $\mathsf{MFe}_2\mathsf{O}_4$ nanoparticles

	Bond angle									
Sample	θ_1	θ_2	θ_3	θ_4	θ_5					
CoFe ₂ O ₄	123.47	145.55	92.65	125.87	74.84					
Fe ₃ O ₄	124.87	152.52	90.55	125.39	78.82					
MnFe ₂ O ₄	123.40	145.23	92.75	125.90	74.65					

were smaller than those of CoFe₂O₄ and MnFe₂O₄. Generally, the greater decrease in θ_3 and θ_4 corresponded with stronger interactions in B–B; conversely, the greater increment in θ_1 , θ_2 , and θ_5 corresponded with weaker interactions in A–B.³³ Fig. 3 illustrates the visualization of the arrangement of ion pairs with the intrinsic lengths between them and the angles formed by these lengths in the spinel structure. The influence of changing the value of bond angles on the magnetic properties of the samples is discussed in detail in the following section.

To minimize the total absolute value of errors, the average crystallite size (*D*) of the prepared MFe₂O₄ samples was calculated using the full width at half-maximum (β) values and angle values corresponding with all peaks, as proposed by Monshi *et al.*³⁴

$$\ln \beta = \ln\left(\frac{K\lambda}{D}\right) + \ln\left(\frac{1}{\cos \theta}\right) \tag{10}$$

The $\ln \beta vs. \ln \left(\frac{1}{\cos \theta}\right)$ graphs of the samples are drawn in

Fig. 4. The obtained average crystallite size (*D*) was 14.5, 7.0, and 27.4 nm for $CoFe_2O_4$, Fe_3O_4 , and $MnFe_2O_4$, respectively, as listed in Table 1. The large difference in crystal size between samples showed the role of pH and reaction time on phase formation and crystal size. This finding was consistent with that of Saf *et al.*²⁸ They found that $CoFe_2O_4$ samples synthesized at low pH have smaller crystallite sizes with poor crystallinity,

Table 3	Values of the interionic distances of MFe ₂ O ₄ nanoparticles

	Me–O (Å)				Me-O (Å)				
Sample	р	q	r	S	b	С	d	е	f
CoFe ₂ O ₄	2.0554	1.9019	3.6419	3.6684	2.9731	3.4863	3.6413	5.4620	5.1496
Fe ₃ O ₄ MnFe ₂ O ₄	2.0807 2.0752	$1.8280 \\ 1.9253$	3.5003 3.6866	3.6270 3.7082	2.9567 3.0045	3.4670 3.5231	3.6212 3.6798	5.4318 5.5197	$5.1211 \\ 5.2040$



Fig. 3 Schematics of the configuration of the ion pairs in ideal spinel ferrites with advantageous distances and angles for effective magnetic interactions.²⁶



whereas $CoFe_2O_4$ samples synthesized at high pH have a larger crystallite size with a greater degree of crystallinity.

3.2. FE-SEM and EDX of MFe₂O₄ NPs

The morphology of MFe₂O₄ NPs was examined by the FE-SEM technique, and results are shown in Fig. 5(a–c). Fig. 5 reveals particle agglomeration with spherical NPs and a narrow particle-size distribution. Analysis results of SEM images using ImageJ software demonstrated the average particle size to be 14.7, 9.0, and 34.3 nm for CoFe₂O₄, Fe₃O₄, and MnFe₂O₄, respectively. Experimental studies have determined the critical sizes for superparamagnetic (SPM) behavior of CoFe₂O₄, Fe₃O₄, and MnFe₂O₄, and MnFe₂O₄ NPs to be 10–17 nm,³⁶ 20 nm,^{37,38} and 43 nm,³⁹ respectively. Therefore, our samples satisfy the conditions for the existence of the SPM state at temperature $T > T_B$ and blocked state at temperature $T < T_B$ (here T_B is a blocking temperature).

The values of the average particle sizes from SEM images well agreed with those of the average crystallite sizes determined from the XRD patterns. The structure of MFe_2O_4 NPs was further investigated by EDX spectroscopy. The results are presented in Fig. 5(d–f). Co, Fe, Mn, and O elements were present without any impurity elements from precursors. As shown in the inset of Fig. 5(d–f), the observed atomic percentage of metal cations and anions determined from the average value of three different positions of each sample was close to the standard metal cation-to-anion ratio (3 : 4) of ferrites. This finding further confirmed that all precursors reacted very well with one another to finally form the desired nanoferrite samples.

3.3. Raman spectra of MFe₂O₄ NPs

Raman spectroscopy measurements were performed at room temperature to further study the surface and structural properties of materials, and results are presented in Fig. 6(a). Calculations from group theory predict $A_{1g} + E_g + 3T_{2g}$ Raman modes in the normal cubic spinel structure.40,41 Thus, the phonon-mode assignment for our samples was conducted in accordance using the vailable literature.17,19,40-47 The highest frequency A_{1g} mode above 600 cm⁻¹ was assigned to the symmetric breathing mode of oxygen atoms concerning Co, Fe, and Mn ions in the tetrahedral void (AO₄).⁴² The second-highest frequency $T_{2g}(3)$ mode from 450 cm⁻¹ to below 600 cm⁻¹ was due to as either the antisymmetric breathing mode of the AO₄ unit^{40,43} or to the asymmetric bending motion of oxygen bonded to the tetrahedral cation.⁴⁴ The $T_{2g}(2)$ mode from 330 cm⁻¹ to below 480 cm⁻¹ was due to a translation along one direction of the lattice, with the cation and oxygen atoms moving in opposite directions.40,45 The Eg mode from 140 cm⁻¹ to below 330 cm⁻¹ was ascribed to the symmetric bending motion of oxygen anions within the AO4 unit.40 The lowest frequency Raman-active mode $T_{2g}(1)$ was a complete translation of the tetrahedral void within the spinel lattice.40,42,45 However, all Raman modes were asymmetric (or dissociated). The deconvoluted Raman spectrum for all major peaks of the samples along with their fits are presented in Fig. 6(b-d), whereas parameters derived are summarized in Table 5. These results showed that each peak can be presented like a doublet, which was



Fig. 5 (a-c) HR-SEM image, particle size distribution histogram and (d-f) corresponding EDX spectra of MFe₂O₄ nanoparticles.

characteristic of the inverse or mixed spinel structure,^{19,46,47} similar to the peak positions reported for NiFe₂O₄ and ZnFe₂O₄ NPs.¹⁷ This variation in the relative Raman intensities of CoFe₂O₄, Fe₃O₄, and MnFe₂O₄ was due to ionic-radius differences in Co²⁺, Fe²⁺, Fe³⁺, and Mn²⁺. Moreover, the downshifts and broadening of the Raman peaks in CoFe₂O₄, Fe₃O₄, and MnFe₂O₄ NPs primarily originated from the strain growth and quantum-confinement effect of optical phonons in nanosized crystalline particles.⁴⁸

3.4. Optical properties and electronic band structure of $MFe_2O_4 NPs$

To investigate the optical-absorption properties of the materials, UV-Vis-NIR absorption spectra of the MFe_2O_4 NP samples were measured using a spectrophotometer (JASCO V-770) within the wavelength range of 300 nm to 900 nm. Fig. 7 shows the absorbance spectra of MFe_2O_4 NPs. As shown in Fig. 7, the Fe_3O_4 NPs exhibited an absorbance peak at 390 nm, following the finding of Zhao *et al.*²¹ Meanwhile, those of $MnFe_2O_4$ NPs were about 410 nm, and a wide absorbance band was observed for $CoFe_2O_4$ NPs. This result was due to the change in optical-energy bandgap and the effect of nanoferrites' surface roughness.^{48,49} The absorbance spectra were related to the electronic structure and were thus used to determine the relation of crystallite size to the optical bandgap. The optical energy bandgap of $CoFe_2O_4$, Fe_3O_4 , and $MnFe_2O_4$ NPs were evaluated using the Tauc model⁵⁰ with the help of UV-Vis data.

$$\alpha h\nu = A(h\nu - E_{\rm g})^n \tag{11}$$

where *n* represents the nature of transitions with n = 1/2 for allowed direct transitions and n = 2 for indirect transitions, respectively; *A* is a constant that depends on the transition



Fig. 6 (a) Experimental Raman spectrum under excitation wavelength of 785 nm and (b–d) Raman active modes fitted with cumulative fit are displayed for MFe₂O₄ nanoparticles.

 Table 5
 Assigned Raman modes for MFe₂O₄ nanoparticles

Sample	${T_{2g}(1) \choose (cm^{-1})}$	${{ m T_{2g}(1)}\over{ m (cm^{-1})}}$	${\mathop{\rm Eg}\limits_{({ m cm}^{-1})}}$	${ m E_g \over (cm^{-1})}$	${ m T_{2g}(2) \over (cm^{-1})}$	${ m T_{2g}(2) \over (cm^{-1})}$	${ m T_{2g}(3) \over (cm^{-1})}$	${ m T_{2g}(3) \over (cm^{-1})}$	$\stackrel{A_{1g}}{(cm^{-1})}$	$\stackrel{A_{1g}}{(cm^{-1})}$
CoFe ₂ O ₄	78.49	105.51	146.89	307.24	360.10	472.37	490.37	560.81	630.03	685.45
Fe ₃ O ₄	77.92	106.90	147.48	329.72	373.56	397.73	478.60	509.08	665.32	717.67
MnFe ₂ O ₄	80.86	109.78	150.31	307.14	337.33	413.11	453.70	595.30	619.36	666.88



Fig. 7 Room temperature UV-Vis absorbance spectrum of $\mathsf{MFe}_2\mathsf{O}_4$ nanoparticles.

probability, and E_g is the optical bandgap. Fig. 8(a–c) displays $(\alpha h\nu)^2 \nu s$. $h\nu$ for the samples. Direct bandgap values were obtained by extrapolating the linear regions of these plots along the *X*-axis. The obtained bandgap energy was found to be 2.63, 2.64, and 2.59 eV for the CoFe₂O₄, Fe₃O₄, and MnFe₂O₄ NPs, respectively, showing a decrease in the bandgap from Fe₃O₄ to MnFe₂O₄. The decrease in bandgap energy was due to the size effect and the redistribution of anion ions from octahedral to tetrahedral sites. The obtained direct bandgap value of CoFe₂O₄ and Fe₃O₄ NPs were comparable with previously reported

values.⁵¹⁻⁵³ Fig. 8(d–f) shows the plot of the absorption coefficient (α) against photon energy for the three samples based on the absorbance data from Fig. 7. The absorption coefficient α is depicted by the relation⁵⁴

$$\alpha = \alpha_0 \left[\sigma \left(\frac{E - E_0}{k_{\rm B} T} \right) \right] \tag{12}$$

where α_0 , E, and E_0 are the absorption coefficient, incident energy, and onset of absorption, respectively. Notably, α_0 and E_0 depends on the nature of the material. $E_{\rm u} = k_{\rm B}T/\sigma$ is specified as the Urbach energy (also known as Urbach "tail"), where σ is the steepness parameter and $k_{\rm B}$ is the Boltzmann constant. Generally, the Urbach energy is governed by the crystal defect originating from thermal fluctuations, impurities, and crystallinelattice disordering.^{20,55} The Urbach energy is determined from the reciprocal of the slope of the linear portion's fitting line in the $\ln(\alpha)$ versus photon energy $(h\nu)$ plot. The Urbach energy values obtained for CoFe₂O₄, Fe₃O₄, and MnFe₂O₄ were 0.94, 1.32, and 1.20 eV, respectively. $E_{\rm u}$ increased with decreased grain size, indicating that electrons experienced a larger extent of disorder while passing across the bandgap. Thus, the behavior of the optical bandgap was consistent with the characterization of Urbach energy. The E_{μ} obtained for our samples also well agreed with those in the literature.²¹

To study the energy-transfer mechanism of MFe₂O₄ NPs in detail, we proposed an energy-band structure model based on



Fig. 8 (a–c) Plot of $(E\alpha)^2 vs. (h\nu)$, in which red line represents the experimental absorption spectra, and dashed black line is the fit to the linear portion of the data, where the intercept of that curve in the *x*-axis gives estimating the optical band gap and (d–f) the red line represents the experimental absorption curve, and dashed black line is the fit to the linear portion of the curve; and the Urbach energy and onset of absorption are calculated from the fitting for MFe₂O₄ nanoparticles.

theoretical calculations from the literature20,21,56-60 and the results of our PL and UV-Vis measurements. According to Camphausen et al.,⁵⁶ the energy gap between the O(2p) to the empty M(4s) in the 3d transition-metal oxides is about 6 eV, whereas Zaanen et al.⁵⁷ found that this bandgap ranges within 4-6 eV. Between these bands is the octahedral and tetrahedral crystal-field energies generated from the orbitals of 3d metals. The splitting energy between lower t_{2g} and higher e_g levels in an octahedral crystal field is $\varDelta_{cf,O}$ ~1.75 eV, and those of lower e and higher t_2 levels in a tetrahedral crystal field is $\Delta_{cf,t}$ ${\sim}1.55\,$ eV. 58 Moreover, the energy gap between the $t_{\rm 2g}$ level (octahedral crystal field) and e level (tetrahedral crystal field) and the valence band of O(2p), respectively, approaches 0.9 eV.^{22,59,60} From the above analysis, the energy-band structure of MFe₂O₄ NPs is illustrated in Fig. 9. Using this approach, the bandgap values for the CoFe₂O₄ (2.63 eV), Fe₃O₄ (2.64 eV), and MnFe₂O₄ (2.59 eV) determined from the absorbance data (Fig. 8(a-c)) were consistent with the bandgap (~ 2.65 eV) between the O(2p) and eg level of the octahedral site. Fig. 8(d-f) also shows that the onset of absorption was very close to the crystal-field splitting energy for the octahedral site (1.75 eV).

Sadat *et al.*²⁰ obtained the PL spectra for 10 nm to 5 µm-sized Fe₃O₄ NPs. They found three main peaks near 565 nm (2.2 eV), 690 nm (1.79 eV), and 840 nm (1.47 eV) when the samples were illuminated with laser light at a wavelength of 407 nm (3.05 eV). They suggested that the peak at 565 nm is due to the radiative recombination of mobile electrons from $t_{2g} \rightarrow e_g$ on the octahedral site, the peak at 690 nm to the recombination of trapped

electrons from the octahedral site to O(2p), and the peak at 840 nm to the electron traps on the tetrahedral site. These observations were consistent with the energy-band structure that they proposed. However, Zhao *et al.*²¹ observed only the peak at 674 nm (1.84 eV) for 10 nm-sized Fe₃O₄ NPs illuminated with a laser of 449 nm (2.76 eV). This large difference may be due to the influence of the quantum-confinement effect originating from the nanoscale of particle size and the use of dissimilar excitation light when measuring the PL spectra of Fe₃O₄.



Fig. 9 Schematic of the energy bands for MFe₂O₄ system.

PL measurements of MFe₂O₄ NPs were performed using Xe light under an excitation wavelength of 310 nm (4.0 eV). Fig. 10(a) depicts the PL spectra of $CoFe_2O_4$, Fe_3O_4 , and $MnFe_2O_4$ NPs. As shown in Fig. 10(a), the emission spectrum at each sample primarily comprised three dominated clear emission peaks at around 469 nm (2.64 eV), 728 nm (1.70 eV), and 823 nm (1.51 eV). The peak of UV emission at around 469 nm was consistent with the energy gaps caused by the e_g orbital of the octahedral site and the O(2p) level, whereas the visible peak at around 728 nm and NIR peak at around 823 nm were attributed to the crystal-field splitting energy for the octahedral and tetrahedral sites, respectively.

According to Mie's theory, to evaluate the photothermal performance of a material, the ratio of absorption efficiency (Q_{abs}) to extinction efficiency (Q_{ext}) needs to be analyzed and considered in detail, where Q_{ext} is the imaginary part of the complex refractive index, related to light absorption. Therefore, the absorption (Q_{abs}) , extinction (Q_{ext}) , and scattering (Q_{sca}) efficiencies as a function of wavelength for MFe₂O₄ NPs were calculated using equations:^{20,21}

$$Q_{\text{ext}} = \frac{2}{x^2} \sum_{n=1}^{\infty} (2n+1) \operatorname{Re}[a_n + b_n]$$
 (13a)

$$Q_{\rm sca} = \frac{2}{x^2} \sum_{n=1}^{\infty} (2n+1) \left[|a_n|^2 + |b_n|^2 \right]$$
(13b)

$$Q_{\rm abs} = Q_{\rm ext} - Q_{\rm sca} \tag{13c}$$

in which a_n and b_n are the coefficients, $x = \frac{2\pi n_{\text{med}}D}{\lambda_0}$ is the size parameter with *D* being the mean radius of the particles, n_{med} is the refractive index of the media, and λ_0 is the vacuum wavelength. Using the code "Mie-Plot" written by Philip Laven,⁶¹ the

numerical values of Qext, Qsca, and Qabs were calculated as a function of wavelength for MFe₂O₄ NPs and are shown in Fig. 10(b-d). Fig. 10(b) reveals that the extinction efficiency of Fe₃O₄ NPs was mostly absorption-dominated, whereas those $CoFe_2O_4$ and $MnFe_2O_4$ NPs were not [Fig. 10(b) and (d)]. Thus, $CoFe_2O_4$ and $MnFe_2O_4$ had lower Q_{abs}/Q_{ext} than Fe_3O_4 (1.00) and less efficient photothermal performance. This finding was consistent with the fact that smaller particles have higher surface area, so photothermal heating is more efficient.20 However, the scattering efficiency of MnFe₂O₄ exceeded those of $CoFe_2O_4$ and Fe_3O_4 owing to the difference in their grain size. This finding indicated good agreement with Mie's scattering theory because with decreased particle size, the pattern of the diffracted and scattered light spread away from the forward direction. Consequently, the larger grain size of MnFe₂O₄ contributed to a greater scattering efficiency.

3.5. Magnetic properties of MFe₂O₄ NPs

Magnetic measurements of the MFe₂O₄ NPs were performed at different temperatures. Fig. 11 shows the magnetization (M-H) loops (3 T \leq *H* \leq 3 T) measured at 55, 100, 150, 200, 250, and 300 K. The magnetic parameters of all three samples including saturation magnetization (M_s) , remnant magnetization (M_r) , coercivity (H_c) , exchange bias field (H_{ex}) , effective anisotropy constant ($K_{\rm eff}$), and squareness ratio ($R = M_{\rm r}/M_{\rm s}$) at various temperatures were extracted from these hysteresis loops and are listed in Table 6. For CoFe₂O₄, the value of M_s at 55 K (83.58 emu g^{-1} or 3.51 μ_B) was slightly higher than the theoretical value of ideal inverted structural ferrite (3.0 µ_B per F.U.),^{62,63} bulk counterpart (80 emu g⁻¹),^{62,63} and some nanosized CoFe₂O₄ samples in literature.⁶² The increment in M_s may be due to the distribution of Co and Fe ions at tetrahedral and octahedral sites compared with the ideal spinel structure. This was also confirmed by Ansari et al.14 in oleic acid-coated CoFe2O4, that is,



Fig. 10 Photoluminescence spectrum (a), the wavelength dependence of extinction (Q_{ext}), absorption (Q_{abs}), scattering (Q_{sca}) efficiencies (b–d) for MFe₂O₄ system. The values are calculated based to the Mie theory using the complex refractive indices of the samples.



Fig. 11 M(H) loops measured at different temperatures for the MFe₂O₄ system.

even the organic coating does not significantly affect the high value of $M_{\rm s}$ in an inverted-structure CoFe₂O₄. For MnFe₂O₄, $M_{\rm s}$ was 88.87 emu g⁻¹ (3.67 $\mu_{\rm B}$ per F.U.) at 55 K, which was significantly higher than that of its bulk counterpart (3.3–4.5 $\mu_{\rm B}$ per F.U.).^{64–68} Notably, Mn²⁺ has an isoelectronic configuration (3d⁵), which was zero crystal-field stabilization energy; thus, the influence of the inverse parameter on the magnetic properties of MnFe₂O₄ was less pronounced than that of other spinel ferrites such as MgFe₂O₄ or Fe₃O₄.⁶⁹ Consequently, similar to

 $CoFe_2O_4$, the M_8 of MnFe_2O_4 was larger than those of an inverted structural spinel (3.0 µB per F.U.).64,65 In contrast to the above two samples, M_s at 55 K (59.22 emu g⁻¹) of Fe₃O₄ was smaller than that of its bulk counterpart (90 emu g^{-1}).⁷⁰ This was due to the spin-canting phenomena originating from the enhancement in the surface-to-volume ratio of the smaller-sized (9 nm) Fe_3O_4 . This characteristic has been mentioned in most studies on the magnetic properties of nanosized Fe₃O₄.⁷⁰ The value of M_s in our samples was consistent with the change in the value of bond angles determined in Section 3.1. As shown in Table 5, the decrease in bond angle θ_3 and increase in length between the metal ions at the octahedral site and anion (p) for Fe₃O₄ indicated the weakening of the B-B interaction. Likewise, the bond angle θ_5 for Fe₃O₄ increased, again confirming a weak interaction between A-B and A-A. Therefore, according to ref. 71, $M_{\rm s}$ of Fe₃O₄ was smaller than that of the remaining samples. Table 6 reveals that the H_c of all samples monotonically decreased with increased temperature.

Furthermore, the coercivity values of CoFe_2O_4 , Fe_3O_4 , and MnFe_2O_4 at 55 K reached 9.13 kOe, 233 Oe, and 266 Oe, respectively. For CoFe_2O_4 , H_c was remarkably higher than that for bulk CoFe_2O_4 (\sim 5 kOe at 5 K),⁷² whereas the low coercivity of Fe_3O_4 and MnFe_2O_4 indicated the soft magnetic nature of two these samples. The temperature variation of H_c for three samples can be fitted according to Keller's law, *i.e.*,

$$H_{\rm c} = H_{\rm c0}[1 - (T/T_{\rm B})^{1/2}]$$
(14)

where H_{c0} is coercivity at 0 K and T_B is the blocking temperature. The experimental data and fitting curves for CoFe₂O₄, Fe₃O₄ and MnFe₂O₄ are revealed in Fig. 12. H_{c0} was 15 230, 356, and 389 Oe for CoFe₂O₄, Fe₃O₄ and MnFe₂O₄, respectively, and their T_B values were 328, 399 and 630 K, respectively. The good fitting according to Keller's law proved that three samples were non-interacting, randomly oriented spherical particles with cubic anisotropy. Thus, the relationship among coercivity, saturation

Table 6 Saturation magnetization (M_s), remnant magnetization (M_r), coercivity (H_c) exchang bias field (H_{ex}), effective anisotropy constant (K_{eff}), squareness ratio (M_r/M_s) and a magnetic grain size (D_m) at various temperature of MFe₂O₄ nanoparticles

Sample	Temp. (K)	$M_{\rm s}$ (emu g ⁻¹)	$M_{ m s}\left(\mu_{ m B} ight)$	$M_{\rm r}$ (emu g ⁻¹)	$H_{\rm c}$ (Oe)	$H_{\mathrm{ex}}\left(\mathrm{Oe}\right)$	$K_{\rm eff} \left({\rm erg} \ {\rm cm}^{-3} \right)$	$M_{\rm r}/M_{\rm s}$	$H_{\mathrm{dip}}\left(\mathrm{kOe}\right)$	$D_{\rm m}$ (nm)
CoFe ₂ O ₄	55	83.58	3.51	59.74	9129.04	191.52	$6.25 imes10^6$	0.71	0.29	5.6
2 1	100	83.48	3.51	54.59	6902.64	55.86	$4.72 imes10^6$	0.66	0.38	6.2
	150	82.47	3.46	47.13	4782.10	69.70	$3.23 imes10^6$	0.58	0.55	7.0
	200	80.07	3.36	38.09	3024.39	7.98	1.98×10^6	0.48	0.87	8.2
	250	76.59	3.22	29.02	1843.36	7.98	1.16×10^6	0.39	1.43	9.9
	300	72.06	3.03	22.26	1015.72	21.32	5.99×10^{5}	0.31	2.60	12.3
Fe_3O_4	55	59.22	2.45	9.24	233.02	-9.00	1.13×10^5	0.16	138.47	23.0
	100	58.18	2.41	6.88	167.12	11.00	7.98×10^4	0.12	193.07	25.8
	150	56.54	2.34	5.45	136.50	0.50	6.34×10^4	0.10	236.38	27.9
	200	54.39	2.25	4.32	94.01	2.00	4.20×10^4	0.08	343.22	32.0
	250	51.88	2.15	4.36	94.02	3.00	4.01×10^4	0.08	343.18	32.5
	300	48.88	2.03	0.63	41.32	3.00	1.65×10^4	0.01	780.89	43.6
MnFe ₂ O ₄	55	88.87	3.67	13.40	266.00	4.00	1.84×10^{5}	0.15	1.67	22.8
	100	85.29	3.52	11.80	243.50	3.50	1.62×10^5	0.14	1.82	23.7
	150	80.05	3.31	9.17	198.50	1.50	1.24×10^5	0.11	2.24	26.0
	200	74.10	3.06	9.17	177.50	0.50	1.08×10^5	0.12	2.37	27.2
	250	67.86	2.80	8.73	138.50	2.50	$9.44 imes10^4$	0.13	2.49	28.4
	300	61.52	2.54	7.51	118.00	1.00	8.06×10^4	0.12	2.64	30.0



Fig. 12 Temperature dependence of coercivity (solid circle) and the fitting line according to Kneller's law (solid black line) for MFe_2O_4 samples.

magnetization, and effective anisotropy constant (K_{eff}) can be given by the formula $H_{\rm c} = 0.64 K_{\rm eff}/M_{\rm s}$. The obtained $K_{\rm eff}$ values are listed in Table 6. The effective anisotropy constant values at 55 K were compatible with those of CoFe₂O₄, Fe₃O₄, and MnFe₂O₄ published in the literature.⁷³⁻⁷⁵ Indeed, according to the Stoner–Wohlfarth (SW) model,⁷⁶ if R < 0.5, magnetostatic interactions between particles would dominate, whereas if R =0.5, the particles would have no exchange-coupling and become randomly oriented uniaxial anisotropic ferromagnets. Finally, 0.5 < R < 1.0 confirmed the existence of exchange-coupling between particles. Therefore, from the low value of R (<0.2), we assumed that the interaction was much stronger between MnFe₂O₄ and Fe₃O₄ particles⁷⁷ and that the particle assembly was multidomain.71 Accordingly, the SW model was less relevant for MnFe₂O₄ and Fe₃O₄ NPs. CoFe₂O₄ is known to exhibit cubic magnetic anisotropy with the first crystalline magnetic anisotropy constant $K_1 > 0$, so the theoretical value of R should be 0.832. However, R in our $CoFe_2O_4$ sample was smaller than the theoretical value, so we inferred that the contribution of surface spins to the value of $K_{\rm eff}$ was negligible. Thus, the SW model was less consistent for explaining the high values of H_{c} and K_{eff} in this case. These findings indicated that for our MFe₂O₄ samples, surface anisotropy and dipole interactions were the main factors affecting H_c and K_{eff} .

To evaluate in more detail the role of these factors on the magnetic properties of the system, their magnetic grain volume $(V_{\rm m})$ is calculated by the formula $V_{\rm m} = 25k_{\rm B}T_{\rm B}/K_{\rm eff}$,⁷⁸ where $k_{\rm B}$ is the Boltzmann constant. Subsequently, the diameters of

magnetic grains (D_m) for the three samples, respectively, were obtained; results are listed in Table 6. Table 6 shows that $D_{\rm m}$ increased monotonically with temperature. Moreover, the $D_{\rm m}$ of both CoFe₂O₄ and MnFe₂O₄ samples were smaller than the average physical size, indicating the significant influence of canted surface spins around CoFe₂O₄ and MnFe₂O₄ NPs; whereas D_m of Fe₃O₄ NPs were larger than the average size because of the collective behavior of several particle moments stimulated by the dipole-dipole interparticle interactions.73 Thus, for CoFe₂O₄ and MnFe₂O₄ NPs, the K_{eff} mainly originates from the surface spins. Conversely, for Fe₃O₄ NPs, surface spins do not provide K_{eff} but those induce magnetocrystalline anisotropy and dipole interaction. The strength of dipolar interparticle interactions for MFe2O4 samples was calculated using the maximum dipolar field H_{dip} between nearestneighbor particles through the relation $H_{dip} = 2\mu/d^3$, in which μ is the particle moment ($\mu = M_{\rm s} \times V_{\rm m}$) and *d* is the distance between the centers of two particles.⁷⁹ The H_{dip} parameters obtained for the samples are presented in Table 6. Notably, H_{dip} for Fe₃O₄ was larger than that for the remaining samples, indicating that H_{dip} increased rapidly for larger-sized magnetic particles. Given that the magnetic particle size of Fe₃O₄ was larger than that of MnFe₂O₄ and CoFe₂O₄, more canted surface spins occurred around the CoFe₂O₄ and MnFe₂O₄ particles. Thus, the surface anisotropy in Fe₃O₄ was weaker than that of MnFe₂O₄ and CoFe₂O₄. Meanwhile, the smaller values of H_{dip} in CoFe₂O₄ and MnFe₂O₄ compared with that of Fe₃O₄ confirmed that the magnetocrystalline anisotropy was weaker and the dipole-dipole interaction was stronger in CoFe2O4 and MnFe₂O₄. However, a comparison of H_c and R for all three samples and the H_{dip} calculated for three samples suggested that the dipolar interactions between particles for MFe2O4 NPs were predominant. Fe_3O_4 and $CoFe_2O_4$ particles synthesized with organic precursors also show similar behaviors.14,73,79-81

4. Conclusions

 MFe_2O_4 (M = Co, Fe, Mn) NPs were synthesized successfully using co-precipitation technique. The distribution of cations within interstitial sites was determined by X-ray diffraction, which showed that Co²⁺ and Fe³⁺ions were distributed over both A and B sites for CoFe₂O₄. Conversely, Fe²⁺ and Mn²⁺ ions occupied the tetrahedral site only for Fe₂O₄, and MnFe₂O₄, respectively. The cation distribution within A and B sites induced changes in structural parameters, such as mean radii of tetrahedral and octahedral sites, edge lengths, bond lengths, and bond angles in the unit cell of MFe₂O₄. SEM images showed that MFe₂O₄ NPs had a narrow size distribution with an average size of 14.7, 9.0, and 34.3 nm for CoFe₂O₄, Fe₃O₄, and MnFe₂O₄, respectively. The observation of doublet phenomena of characteristic Raman peaks confirmed the feature of the inverse or mixed spinel structure for MFe₂O₄ NPs. The optical energy bandgap calculated through UV-Vis spectroscopy was 2.63, 2.64, and 2.59 eV for CoFe₂O₄, Fe₃O₄, and MnFe₂O₄, respectively. Based on the bandgap energy determined from UV-Vis and PL measurements, the energy-band structure diagram of MFe₂O₄ was established, in which the bandgap energy determined from

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.

the PL spectrum corresponded with the crystal-field splitting energy for the octahedral (1.70 eV) and tetrahedral (1.51 eV) sites. The mechanism of photothermal behavior of MFe₃O₄ NPs was further determined based on the PL emission and UV-Vis spectra. Magnetic parameters such as coercivity, remanence, squareness ratio, and effective anisotropy constant were deduced from the magnetization loops under an applied magnetic field of 3 T \leq $H \leq$ 3 T. The change in magnetic saturation of MFe₂O₄ samples was explained based on the cation distribution and A–A, A–B, and B–B interactions. The large coercivity and squareness ratio of CoFe₂O₄ corresponded with strong effective anisotropy primarily due to the surface spins. Meanwhile, the smaller coercivity and squareness ratio of MnFe₂O₄ and Fe₃O₄ resulted from the weaker anisotropy and stronger dipolar interaction.

Data availability

The data that support the findings of this study are available within the article.

Author contributions

Tran Dang Thanh: writing – original draft, review & editing, investigation, project administration. Tran Thi Ngoc Nha: writing – original draft, investigation. Tran Thi Ha Giang: investigation. Dang Ngoc Toan: resources, investigation. Pham Hong Nam: resources, investigation. Dinh Thanh Khan: resources, investigation. Do Hung Manh: writing – review & editing, investigation. Pham Thanh Phong: writing – review & editing, investigation.

Conflicts of interest

The authors confirm that there are no known conflicts of interest associated with this publication.

Acknowledgements

This work was supported by an excellent research team development program grant funded by the Vietnam Academy of Science and Technology (VAST) under Project Code NCXS01.04/ 22–24.

References

- 1 C. N. R. Rao, A. Müller and A. K. Cheetham, *Nanomaterials Chemistry: Recent Developments and New Directions*, John Wiley & Sons, 2007.
- 2 P. P. Hong, V. H. Nguyen, N.-V. Nguyen and V. H. Nguyen, Directly electrospun copper ferrite CuFe₂O₄ nanofiberbased for gas classification, *Adv. Nat. Sci.: Nanosci. Nanotechnol.*, 2024, **15**, 025010, DOI: **10.1088/2043-6262/ ad4850.**
- 3 B. Lin, C. Tang, Z. Zheng, M. Zhang, Y. Huang, X. Yuan, X. Liu and Y. Wu, Efficient activation of peroxymonosulfate by Co/Cu co-substituted-ferrite and carbon composite for

rapid degradation of tetracycline in aqueous phase: Performance evaluation and mechanisms, *Chem. Eng. J.*, 2024, **488**, 150858, DOI: **10.1016/j.cej.2024.150858**.

- 4 T. N. N. Tran, D. N. Toan, P. H. Nam, Do H. Manh, D. T. Khan and P. T. Phong, Determine elastic parameters and nanocrystalline size of spinel ferrites MFe_2O_4 (M = Co, Fe, Mn, Zn) through X-ray diffraction and infrared spectrum: Comparative approach, *J. Alloys Compd.*, 2024, **996**, 174773, DOI: **10.1016/j.jallcom.2024.174773**.
- 5 K. R. Desai, S. T. Alone, S. R. Wadgane, S. E. Shirsath, K. M. Batoo, A. Imran, E. H. Raslan, M. Hadi, M. F. Ijaz and R. H. Kadam, X-ray diffraction based Williamson–Hall analysis and Rietveld refinement for strain mechanism in Mg–Mn co-substituted CdFe₂O₄ nanoparticles, *Phys. B*, 2021, **614**, 413054, DOI: **10.1016/j.physb.2021.413054**.
- 6 P. H. Nam, N. X. Phuc, P. H. Linh, L. T. Lu, D. H. Manh and P. T. Phong, In-Ja Lee, Effect of zinc on structure, optical and magnetic properties and magnetic heating efficiency of Mn₁. _xZn_xFe₂O₄ nanoparticles, *Phys. B*, 2018, 55, 428–435, DOI: 10.1016/j.physb.2018.09.004.
- 7 R. A. Pawar, S. M. Patange, Q. Y. Tamboli, V. Ramanathan and S. E. Shirsath, Spectroscopic, elastic and dielectric properties of Ho³⁺ substituted Co-Zn ferrites synthesized by sol-gel method, *Ceram. Int.*, 2016, **42**, 16096–16102, DOI: **10.1016/j.ceramint.2016.07.122**.
- 8 D. K. Mondal, C. Borgohain, N. Paul and J. P. Borah, Tuning hyperthermia efficiency of MnFe₂O₄/ZnS nanocomposites by controlled ZnS concentration, *J. Mater. Res. Technol.*, 2019, 8(6), 5659–5670, DOI: 10.1016/j.jmrt.2019.09.034.
- 9 T. Tatarchuk, M. Bououdina, J. Judith Vijaya and L. John Kennedy, Nanophysics, Nanomaterials, Interface Studies, and Applications, *Selected Proceedings of the 4th International Conference Nanotechnology and Nanomaterials* (*NANO2016*), August 24–27, 2016, Lviv, Ukraine, pp. 305–326.
- 10 O. Dehghani Dastjerdi, H. Shokrollahi and S. Mirshekari, A review of synthesis, characterization, and magnetic properties of soft spinel ferrites, *Inorg. Chem. Commun.*, 2023, **153**, 110797, DOI: **10.1016/j.inoche.2023.110797**.
- 11 S. Hunpratub, S. Phokha, P. Kidkhunthod, N. Chanlek and P. Chindaprasirt, The effect of cation distribution on the magnetic properties of CoFe₂O₄ nanoparticles, *Results Phys.*, 2021, 24, 104112, DOI: 10.1016/j.rinp.2021.104112.
- 12 R. S. Yadav, I. Kuřitka, J. Vilcakova, J. Havlica, J. Masilko, L. Kalina, J. Tkacz, J. Švec, V. Enev and M. Hajdúchová, Impact of grain size and structural changes on magnetic, dielectric, electrical, impedance and modulus spectroscopic characteristics of CoFe₂O₄ nanoparticles synthesized by honey mediated sol-gel combustion method, *Adv. Nat. Sci.: Nanosci. Nanotechnol.*, 2017, 8(14pp), 045002, DOI: 10.1088/2043-6254/aa853a.
- 13 Y. Kumar, A. Sharma and P. M. Shirage, Impact of different morphologies of CoFe₂O₄ nanoparticles for tuning of structural, optical and magnetic properties, *J. Alloys Compd.*, 2019, 778, 398–409, DOI: 10.1016/j.jallcom.2018.11.128.
- 14 S. M. Ansari, B. B. Sinha, D. Phase, D. Sen, P. U. Sastry, Y. D. Kolekar and C. V. Ramana, Particle Size, Morphology,

and Chemical Composition Controlled $CoFe_2O_4$ Nanoparticles with Tunable Magnetic Properties *via* Oleic Acid Based Solvothermal Synthesis for Application in Electronic Devices, *ACS Appl. Nano Mater.*, 2019, **2**, 1828– 1843, DOI: **10.1021/acsanm.8b02009**.

- 15 P. Chandramohan, M. P. Srinivasan, S. Velmurugan and S. V. Narasimhan, Cation distribution and particle size effect on Raman spectrum of CoFe₂O₄, *J. Solid State Chem.*, 2011, 184, 89–96, DOI: 10.1016/j.jssc.2010.10.019.
- 16 Á. de Jesús Ruíz-Baltazar, S. Y. Reyes-López and R. Pérez, Magnetic structures synthesized by controlled oxidative etching: Structural characterization and magnetic behavior, *Results Phys.*, 2017, 7, 1828–1832, DOI: 10.1016/ j.rinp.2017.05.001.
- 17 Z. Z. Lazarevic, C. Jovalekic, A. Milutinovic, D. Sekulic, V. N. Ivanovski, A. Recnik, B. Cekic and N. Z. Romcevic, Nanodimensional spinel NiFe₂O₄ and ZnFe₂O₄ ferrites prepared by soft mechanochemical synthesis, *J. Appl. Phys.*, 2013, **113**, 187221, DOI: **10.1063/1.4801962**.
- 18 A. Ahlawat and V. G. Sathe, Raman study of NiFe₂O₄ nanoparticles, bulk and films: effect of laser power, *J. Raman Spectrosc.*, 2011, 42, 1087, DOI: 10.1002/jrs.2791.
- 19 M. H. Sousa, F. A. Tourinho and J. C. Rubim, Use of Raman micro-spectroscopy in the characterization of $M^{II}Fe_2O_4$ (M = Fe, Zn) electric double layer ferrofluids, *J. Raman Spectrosc.*, 2000, **31**, 185, DOI: **10.1002/(SICI)1097-4555(200003)**.
- 20 M. E. Sadat, M. K. Baghbador, A. W. Dunn, H. P. Wagner, R. C. Ewing, J. Zhang, H. Xu, G. M. Pauletti, D. B. Mast and D. Shi, Photoluminescence and photothermal effect of Fe₃O₄ nanoparticles for medical imaging and therapy, *Appl. Phys. Lett.*, 2014, **105**, 091903, DOI: **10.1063/1.4895133**.
- 21 Y. Zhao, M. E. Sadat, A. Dunna, H. Xu, C. –H. Chen, W. Nakasuga, R. C. Ewing and D. Shi, Photothermal effect on Fe_3O_4 nanoparticles irradiated by white-light for energyefficient window applications, *Sol. Energy Mater. Sol. Cells*, 2017, **161**, 247–254, DOI: **10.1016/j.solmat.2016.11.039**.
- 22 W. F. J. Fontijn, P. J. van der Zaag, L. F. Feiner, R. Metselaar and M. A. C. Devillers, A consistent interpretation of the magneto-optical spectra of spinel type ferrites (invited), *J. Appl. Phys.*, 1999, **85**, 5100, DOI: **10.1063/1.369091**.
- 23 Do Hung Manh, T. T. N. Nha, L. T. H. Phong, P. H. Nam, D. T. Tran and P. T. Phong, Determination of the crystalline size of hexagonal $La_{1-x}Sr_xMnO_3$ (x = 0.3) nanoparticles from X-ray diffraction – a comparative study, *RSC Adv.*, 2023, **13**, 25007–25017, DOI: **10.1039/D3RA04018F**.
- 24 E. Ranjith Kumar, Ch. Srinivas, M. Deepty, I. Pradeep, M. V. K. Mehar, C. L. Prajapat, T. V. Chandrasekhar Rao, N. Krishna Mohan and D. L. Sastry, Synergistic effect of heat treatment on structural, magnetic and dielectric properties of spinel ferrite nanoparticles, *J. Mater. Sci.: Mater. Electron.*, 2018, 29, 20968–20977, DOI: 10.1007/ s10854-018-0241-4.
- 25 S. S. Jadhav, S. E. Shirsath, S. M. Patange and K. M. Jadhav, Effect of Zn substitution on magnetic properties of nanocrystalline cobalt ferrite, *J. Appl. Phys.*, 2010, **108**, 093920, DOI: **10.1063/1.3499346**.

- 26 T. R. Tatarchuk, M. Bououdina, N. D. Paliychuk, I. P. Yaremiy and V. V. Moklyak, Structural characterization and antistructure modeling of cobaltsubstituted zinc ferrites, *J. Alloys Compd.*, 2017, 694(15), 777–791, DOI: 10.1016/j.jallcom.2016.10.067.
- 27 S. Jonak and J. P. Borah, Correlation between cation distribution and heating efficiency of annealed Fe₃O₄ nanoparticles, *Mater. Today Commun.*, 2021, **26**, 101789, DOI: **10.1016/j.mtcomm.2020.101789**.
- 28 R. Saf, A. Ghasemi, R. Shoja-Razavi and M. Tavousi, The role of pH on the particle size and magnetic consequence of cobalt ferrite, *J. Magn. Magn. Mater.*, 2015, **396**, 288–294, DOI: **10.1016/j.jmmm.2015.08.022**.
- 29 R. D. Shannon, Revised Effective Ionic Radii and Systematic Studies of Interatomic Distances in Halides and Chalcogenides, Acta Crystallogr., Sect. A: Cryst. Phys., Diffr., Theor. Gen. Crystallogr., 1976, 32, 751, DOI: 10.1107/ S0567739476001551.
- 30 P. T. Phong, P. H. Nam, N. X. Phuc, B. T. Huy, L. T. Lu and D. H. Manh, In-Ja Lee, Optical, and Magnetic Properties of Mixed Co-Zn Ferrites Nanoparticles Synthesized by Low-Temperature Hydrothermal Method, *Metall. Mater. Trans. A*, 2019, **50**, 1571–1581, DOI: **10.1007/s11661-018-5096-z**.
- 31 T. Abbas, Y. Khan, M. Ahmad and S. Anwar, X-ray diffraction study of the cation distribution in the Mn-Zn ferrites, *Solid State Commun.*, 1992, **82**(9), 701–703, DOI: **10.1016/0038-1098(92)90064-G**.
- 32 R. Sharma, P. Thakur, M. Kumar, N. Thakur, N. S. Negi, P. Sharma and V. Sharma, Improvement in magnetic behaviour of cobalt doped magnesium zinc nanoferrites *via* Co-precipitation route, *J. Alloys Compd.*, 2016, 684, 569– 581, DOI: 10.1016/j.jallcom.2016.05.200.
- 33 V. K. Lakhani, T. K. Pathak, N. H. Vasoya and K. B. Modi, Structural parameters and Xray Debye temperature determination study on copper-ferrite-aluminates, *Solid State Sci.*, 2011, 13, 539–547, DOI: 10.1016/ j.solidstatesciences.2010.12.023.
- 34 A. Monshi, M. R. Foroughi and M. R. Monshi, Modified Scherrer Equation to Estimate More Accurately Nano-Crystallite Size Using XRD, *World J. Nano Sci. Eng.*, 2012, 2, 154–160, DOI: 10.4236/WJNSE.2012.23020.
- 35 S. B. Somvanshi, M. V. Khedkar, P. B. Kharat and K. M. Jadhav, Influential diamagnetic magnesium (Mg²⁺) ion substitution in nano-spinel zinc ferrite (ZnFe₂O₄): Thermal, structural, spectral, optical and physisorption analysis, *Ceram. Int.*, 2020, 46(7), 8640–8650, DOI: 10.1016/ j.ceramint.2019.12.097.
- 36 V. Blanco-Gutiérrez, E. Climent-Pascual, R. Sáez-Puchea and M. J. Torralvo-Fernándeza, Temperature dependence of superparamagnetism in CoFe₂O₄ nanoparticles and CoFe₂O₄/SiO₂ nanocomposites, *Phys. Chem. Chem. Phys.*, 2016, 18, 9186–9193, DOI: 10.1039/C6CP00702C.
- 37 C. T. Yavuz, J. T. Mayo, W. W. Yu, *et al.*, Low-field magnetic separation of monodisperse Fe₃O₄ nanocrystals, *Science*, 2006, **314**, 964–967, DOI: **10.1126/science.1131475**.
- 38 Y. W. Jun, Y. M. Huh, J. S. Choi, *et al.*, Nanoscale size effect of magnetic nanocrystals and their utilization for cancer

diagnosis *via* magnetic resonance imaging, *J. Am. Chem. Soc.*, 2005, **127**, 5732–5733, DOI: **10.1021/ja0422155**.

- 39 P. T. Phong, L. H. Nguyen, L. T. H. Phong, P. H. Nam, D. H. Manh, I.-J. Lee and N. X. Phuc, Study of specific loss power of magnetic fluids with various viscosities, *J. Magn. Magn. Mater.*, 2017, **428**, 36–42, DOI: **10.1016**/ j.jmmm.2016.12.008.
- 40 T. Yamanaka and M. Ishii, Raman scattering and lattice vibrations of Ni₂SiO₄ spinel at elevated temperature, *Phys. Chem. Miner.*, 1986, 13, 156–160, DOI: 10.1007/BF00308157.
- 41 T. Yu, Z. X. Shen, Y. Shi and J. Ding, Cation migration and magnetic ordering in spinel CoFe₂O₄: micro-Raman scattering study, *J. Phys.: Condens. Matter*, 2002, **14**, L613–L618, DOI: **10.1088/0953-8984/14/37/101**.
- 42 M. P. Dojcinovic, Z. Z. Vasiljevic, V. P. Pavlovic, D. Barisic, D. Pajic, N. B. Tadic and M. V. Nikolic, Mixed Mg–Co spinel ferrites: Structure, morphology, magnetic and photocatalytic properties, *J. Alloys Compd.*, 2021, 855(1), 157429, DOI: 10.1016/j.jallcom.2020.157429.
- 43 J. L. Verble, Temperature-dependent light-scattering studies of the Verwey transition and electronic disorder in magnetite, *Phys. Rev. B: Solid State*, 1974, 9(12), 5236–5248, DOI: 10.1103/PhysRevB.9.5236.
- 44 H. Cynn, S. K. Sharma, T. F. Cooney and M. Nicol, Hightemperature Raman investigation of order-disorder behavior in the MgAl₂O₄ spinel, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1992, 45(1), 500–502, DOI: 10.1103/ PhysRevB.45.500.
- 45 C. Pernechele, M. Solzi, M. Ghidini, E. Arisi, I. Bergenti and V. Dediu, Magnetic behaviour of hybrid magnetite/organic semiconductor bilayers, *J. Phys. D: Appl. Phys.*, 2008, 41, 134013, DOI: 10.1088/0022-3727/41/13/134013.
- 46 A. Ahlawat and V. G. Sathe, Raman study of NiFe₂O₄ nanoparticles, bulk and films: effect of laser power, *J. Raman Spectrosc.*, 2011, 42, 1087, DOI: 10.1002/jrs.2791.
- 47 W. Wang, Z. Ding, X. Zhao, S. Wu, F. Li, M. Yue and J. Ping Liu, Microstructure and magnetic properties of MFe₂O₄ (M = Co, Ni, and Mn) ferrite nanocrystals prepared using colloid mill and hydrothermal method, *J. Appl. Phys.*, 2015, 117, 17A328, DOI: 10.1063/1.4917463.
- 48 P. Chand, S. Vaish and P. Kumar, Structural, optical and dielectric properties of transition metal (MFe₂O₄; M= Co, Ni and Zn) nanoferrites, *Phys. B*, 2017, 524, 53–63, DOI: 10.1016/j.physb.2017.08.060.
- 49 A. S. Ahmed, M. M. Shafeeq, M. L. Singla, S. Tabassum, A. H. Naqvi and A. Azam, Band gap narrowing and fluorescence properties of nickel doped SnO₂ nanoparticles, *J. Lumin.*, 2010, **131**, 1–6, DOI: **10.1016**/ j.jlumin.2010.07.017.
- 50 J. Tauc, *Amorphous and Liquid Semiconductors*, ed. J. Tauc, Plenum, New York, 1974, ch. 4.
- 51 M. Sundararajan, L. John Kennedy, J. Judith Vijaya and U. Aruldoss, Microwave combustion synthesis of Co_{1-x}Zn_xFe₂O₄ ($0 \le x \le 0.5$): structural, magnetic, optical and vibrational spectroscopic studies, *Spectrochim. Acta, Part A*, 2015, **140**, 421–430, DOI: **10.1016/j.saa.2014.12.035**.

- 52 M. Srivastava, J. Singh, M. Yashpal, D. K. Gupta, R. K. Mishra, S. Tripathi and A. K. Ojha, Synthesis of superparamagnetic bare Fe₃O₄ nanostructures and core/ shell (Fe₃O₄/alginate) nanocomposites, *Carbohydr. Polym.*, 2012, **89**, 821–829, DOI: **10.1016/j.carbpol.2012.04.016**.
- 53 M. A. Shilpa Amulya, H. P. Nagaswarupa, M. R. Anil Kumar, C. R. Ravikumar and K. B. Kusuma, Sonochemical synthesis of MnFe₂O₄ nanoparticles and their electrochemical and photocatalytic properties, *J. Phys. Chem. Solids*, 2021, **148**, 109661, DOI: **10.1016/j.jpcs.2020.109661**.
- 54 F. Urbach, The Long-Wavelength Edge of Photographic Sensitivity and of the Electronic Absorption of Solids, *Phys. Rev.*, 1953, 92, 1324, DOI: 10.1103/PhysRev.92.1324.
- 55 S. M. Wasim, C. Rincon, G. Marin, P. Bocaranda, E. Hernandez, I. Bonalde and E. Medina, Effect of structural disorder on the Urbach energy in Cu ternaries, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2001, 64, 195101, DOI: 10.1103/PhysRevB.64.195101.
- 56 D. L. Camphausen, J. M. D. Coey and B. K. Chakraverty, One-Electron Energy Levels in Fe₃0₄, *Phys. Rev. Lett.*, 1972, 29, 657, DOI: 10.1103/PhysRevLett.29.657.
- 57 J. Zaanen, G. A. Sawatzky and J. W. Allen, Band gaps and electronic structure of transition-metal compounds, *Phys. Rev. Lett.*, 1985, 55, 418, DOI: 10.1103/PhysRevLett.55.418.
- 58 S. F. Alvarado, M. Erbudak and P. Munz, Final-state effects in the 3d photoelectron spectrum of Fe₃O₄ and comparison with Fe_xO, *Phys. Rev. B: Solid State*, 1976, **14**, 2740, DOI: **10.1103/PhysRevB.14.2740**.
- 59 C. Boxall, G. Kelsall and Z. Zhang, Photoelectrophoresis of colloidal iron oxides. Part 2.—Magnetite (Fe₃O₄), *J. Chem. Soc., Faraday Trans.*, 1996, 92, 791, DOI: 10.1039/ FT9969200791.
- 60 I. Balberg and H. L. Pinch, The optical absorption of iron oxides, J. Magn. Magn. Mater., 1978, 7, 12, DOI: 10.1016/ 0304-8853(78)90138-5.
- 61 P. Laven, MiePlot, http://www.philiplaven.com/mieplot.htm.
- 62 B. Cai, M. Zhao, Y. Ma, Z. Ye and J. Huang, Bioinspired Formation of 3D Hierarchical CoFe₂O₄ Porous Microspheres for Magnetic-Controlled Drug Release, ACS Appl. Mater. Interfaces, 2015, 7, 1327–1333, DOI: 10.1021/ am507689a.
- 63 Y. Kumar, A. Sharma and P. M. Shirage, Impact of different morphologies of CoFe₂O₄ nanoparticles for tuning of structural, optical and magnetic properties, *J. Alloys Compd.*, 2019, 778, 398–409, DOI: 10.1016/j.jallcom.2018.11.128.
- 64 J.-R. Huang and C. Cheng, Cation and magnetic orders in MnFe₂O₄ from density functional calculations, *J. Appl. Phys.*, 2013, 113, 33912, DOI: 10.1063/1.4776771.
- 65 Z. Simsa and V. Brabers, Influence of the degree of inversion on magnetic properties of MnFe₂O₄, *IEEE Trans. Magn.*, 1975, **11**, 1303–1305, DOI: **10.1109/TMAG.1975.1058861**.
- 66 G. Balaji, N. Gajbhiye, G. Wilde and J. Weissmüller, Magnetic properties of MnFe₂O₄ nanoparticles, *J. Magn. Magn. Mater.*, 2002, 242–245, 617–620, DOI: 10.1016/S0304-8853(01)01043-5.

- 67 M. Zheng, X. Wu, B. Zou and Y. Wang, Magnetic properties of nanosized MnFe₂O₄ particles, *J. Magn. Magn. Mater.*, 1998, 183, 152–156, DOI: 10.1016/S0304-8853(97)01057-3.
- 68 Z. X. Tang, C. M. Sorensen, K. J. Klabunde and G. C. Hadjipanayis, Size-dependent Curie temperature in nanoscale MnFe₂O₄ particles, *Phys. Rev. Lett.*, 1991, 67, 3602–3605, DOI: 10.1103/PhysRevLett.67.3602.
- 69 C. Simon, A. Blösser, M. Eckardt, H. Kurz, B. Weber, M. Zobel and R. Marschall, Magnetic properties and structural analysis on spinel MnFe₂O₄ nanoparticles prepared *via* non-aqueous microwave synthesis, *Z. Anorg. Allg. Chem.*, 2021, 647, 2061–2072, DOI: 10.1002/ zaac.202100190.
- 70 B. S. Corrêa, M. S. Costa, G. A. Cabrera-Pasca, C. Sena, R. H. Holanda Pinto, A. P. S. Silva, R. N. Carvalho Junior, L. Ishida, J. G. A. Ramon, R. S. Freitas, M. Saiki, I. T. Matos, E. L. Corrêa and A. W. Carbonari, High-saturation magnetization in small nanoparticles of Fe₃O₄ coated with natural oils, *J. Nanopart. Res.*, 2020, 22, 68, DOI: 10.1007/s11051-020-4761-5.
- 71 S. N. Kane and M. Satalkar, Correlation between magnetic properties and cationic distribution of Zn_{0.85-} _xNi_xMg_{0.05}Cu_{0.1}Fe₂O₄ nano spinel ferrite: effect of Ni doping, *J. Mater. Sci.*, 2017, **52**, 3467–3477, DOI: **10.1007**/ **s10853-016-0636-7**.
- 72 S. Bhattacharyya, J. P. Salvetat, R. Fleurier, A. Husmann, T. Cacciaguerra and M. L. Saboungi, One Step Synthesis of Highly Crystalline and High Coercive Cobalt-ferrite Nanocrystals, *Chem. Commun.*, 2005, 4818–4820, DOI: 10.1039/B509026A.
- 73 S. T. Xua, Y. Q. Ma, G. H. Zheng and Z. X. Dai, Simultaneous effects of surface spins: rarely large coercivity, high remanence magnetization and jumps in the hysteresis loops observed in CoFe₂O₄ nanoparticles, *Nanoscale*, 2015, 7, 6520–6526, DOI: 10.1039/C5NR00582E.

- 74 C. Iacovita, A. Florea, L. Scorus, E. Pall, R. Dudric, A. I. Moldovan, R. Stiufiuc, R. Tetean and C. M. Lucaciu, Hyperthermia, Cytotoxicity, and Cellular Uptake Properties of Manganese and Zinc Ferrite Magnetic Nanoparticles Synthesized by a Polyol-Mediated Process, *Nanomaterials*, 2019, **9**, 1489, DOI: **10.3390/nano9101489**.
- 75 K. D. Sattler, Handbook of Nanophysics: Nanomedicine and Nanorobotics, 2010, vol. 23, p. 11.
- 76 E. C. Stoner and E. P Wohlfarth, A Mechanism of Magnetic Hysteresis in Heterogeneous Alloys, *Philos. Trans. R. Soc.*, A, 1948, 240, 599–642, DOI: 10.1098/rsta.1948.0007.
- 77 I. P. Muthuselvam and R. N. Bhowmik, Mechanical alloyed Ho³⁺ doping in CoFe₂O₄ spinel ferrite and understanding of magnetic nanodomains, *J. Magn. Magn. Mater.*, 2010, 322, 767–776, DOI: 10.1016/j.jmmm.2009.10.057.
- 78 T. Hyeon, Y. Chung, J. Park, S. S. Lee, Y. W. Kim and B. H. Park, Synthesis of Highly Crystalline and Monodisperse Cobalt Ferrite Nanocrystals, *J. Phys. Chem. B*, 2002, **106**, 6831–6833, DOI: **10.1021/jp026042m**.
- 79 S. Laureti, G. Varvaro, A. M. Testa, D. Fiorani, E. Agostinelli, G. Piccaluga, A. Musinu, A. Ardu and D. Peddis, Magnetic interactions in silica coated nanoporous assemblies of $CoFe_2O_4$ nanoparticles with cubic magnetic anisotropy, *Nanotechnology*, 2010, 21(6pp), 315701, DOI: 10.1088/0957-4484/21/31/315701.
- 80 D. Peddis, F. Orru, A. Ardu, C. Cannas, A. Musinu and G. Piccaluga, Interparticle Interactions and Magnetic Anisotropy in Cobalt Ferrite Nanoparticles: Influence of Molecular Coating, *Chem. Mater.*, 2012, 24, 1062–1071, DOI: 10.1021/cm203280y.
- 81 A. G. Roca, M. P. Morales, K. O'Grady and C. Serna, Structural and Magnetic Properties of Uniform Magnetite Nanoparticles Prepared by High Temperature Decomposition of Organic Precursors, *Nanotechnology*, 2006, 17, 2783–2788, DOI: 10.1088/0957-4484/17/11/010.