RSC Advances

PAPER

Cite this: RSC Adv., 2024, 14, 34037

Received 14th August 2024 Accepted 14th October 2024

DOI: 10.1039/d4ra05899b

rsc.li/rsc-advances

1 Introduction

One of the most pressing environmental issues in modern times is the contamination of natural water systems caused by many factors, such as population growth, urbanization, $¹$ and rapid</sup> industrialization.² Among these, industrial activities—particularly in the textile, food processing, dyeing, paper, and dye manufacturing sectors—are significant sources of water pollution.³ The pollutants can dissolve in water, remain suspended,⁴ or settle on sediments,⁵ thereby degrading the water quality.⁶ In particular, organic dyes released from many industries are

b Vietnam National University, Ho Chi Minh City, Vietnam

Modified hydrothermal method for synthesizing titanium dioxide-decorated multiwalled carbon nanotube nanocomposites for the solar-driven photocatalytic degradation of dyes†

Nhu-Bao Trinh,‡^{ab} Thu Anh Nguyen, D‡^{ab} Sy Van Vu,^{ab} Hong-Gam Thi Vo,^{ab} Tien Nu Hoang Lo, \mathbf{D}^{c} In Par[k](http://orcid.org/0000-0002-1555-5717) \mathbf{D}^{cd} and Khuong Quoc Vo $\mathbf{D}^{\star{\sf ab}}$

This study aimed to address the issue of rapid electron–hole recombination in photocatalysis by exploiting multi-phase TiO₂ decorated on multiwalled carbon nanotubes (MWCNTs) to improve the photocatalytic degradation of dyes. A simple and eco-friendly one-pot method was utilized to create the TiO₂/MWCNT nanostructure using glucose as both a structure-directing agent and a carbon source without requiring any prior covalent or non-covalent functionalization of the MWCNTs at 160 °C. Furthermore, it was found that the average width of the nanocomposites changed from 20 \pm 1 and 42 \pm 2 nm to 56 \pm 3 nm, corresponding to MWCNT contents of 1.0, 2.0, and 3.0 (wt%), respectively. Specifically, TiO₂/ MWCNTs with a low content of MWCNTs demonstrated enhanced performance for the photocatalytic degradation of dyes, with the bandgap of the nanocomposites decreasing to 2.5 eV with 1.0% MWCNTs and 2.4 eV with 2.0% MWCNTs. The TiO₂/MWCNT-1.0 catalyst demonstrated high photocatalytic efficiency for methylene blue (MB) degradation with a rate constant of 0.0051 min⁻¹. TiO₂/MWCNT-2.0 was more effective for rhodamine (RhB) degradation than pristine $TiO₂$, with a rate constant of 0.0065 min−¹ within 120 min of solar-light exposure. This novel modified approach can be used to synthesize nanocomposites simply and is potentially feasible for efficient dye degradation and beyond, offering a promising solution for water-pollution treatment. PAPER
 (A) Check for updates
 **Modified hydrothermal method for synthesizing

Club and the star infinite control in the color star in the star of the solar-driven**

Club and the star in the star in the star in the star

dominant health threats to living organisms and human beings.⁷ RhB is one of the reddish violet dyes that can have harmful effects on human health, causing eye and skin irritation and even malfunction of the respiratory system.⁸ Another dye is MB, which is toxic and non-biodegradable, and it can induce dizziness, headache, and nausea.⁹ Therefore, RhB and MB dye removal in the aqueous environment is fundamentally necessary.

Titanium dioxide $(TiO₂)$ is widely regarded as the leading photocatalyst for breaking down dyes in wastewater because of its low cost and toxicity, high photoactivity¹⁰ and chemical stability, and environmental friendliness.¹¹ However, the high band gap of $TiO₂$ (3.2 eV for anatase and 3.0 eV for rutile phase) decreases the photocatalyst efficiency in visible light. Besides, a major challenge in photocatalyst applications is the rapid recombination of photoexcited electrons and holes, which diminishes the quantum efficiency and photocatalytic activity.¹² Much research has been conducted to solve this problem by integrating it with conductive organic materials, such as graphene (Gr), graphene oxide (GO), and carbon nanotubes (CNTs), which could greatly enhance the photocatalytic performance of $TiO₂$ due to accelerated electron transfer and improved charge-separation efficiency.¹³

Carbon nanotubes (CNTs) have garnered considerable attention due to their high conductivity, large specific surface

a Faculty of Chemistry, Ho Chi Minh City University of Science, Vietnam National University, Ho Chi Minh City, 227 Nguyen Van Cu Street, Ward 4, District 5, Ho Chi Minh City 70000, Vietnam. E-mail: vqkhuong@hcmus.edu.vn

c Research Institute of Clean Manufacturing System, Korea Institute of Industrial Technology (KITECH), 89 Yangdaegiro-gil, Ipjang-myeon, Cheonan 31056, South Korea

d KITECH School, University of Science and Technology (UST), 176 Gajeong-dong, Yuseong-gu, Daejeon 34113, South Korea

[†] Electronic supplementary information (ESI) available. See DOI: <https://doi.org/10.1039/d4ra05899b>

[‡] These authors contributed equally to this work.

area, and porous structure, which can enhance the overall photocatalytic effectiveness.¹⁴ At the TiO₂–CNT interface, a photoexcited electron (e−) can be transferred to the CNT, which has a lower Fermi level.¹⁵ Therefore, electrons ca be persistently accepted on CNTs, and the recombination rate of photoexcited electron–hole pairs could be decreased.¹⁶ Furthermore, it was reported that incorporating CNTs into a composite with $TiO₂$ provided ample active sites on the surface, significantly enhancing the photodegradation rate of dyes.¹⁷ Thus, TiO₂/CNTs nanocomposites are promising materials for attaining high photocatalytic activity and have consequently attracted significant attention in different areas, such as wastewater treatment,¹⁸ water splitting, photocatalytic reduction of CO_2 ,¹⁹ sensor devices, and sensing applications.²⁰ Mohamed Shaban et al. found that a composite of titanium dioxide nanorods on carbon nanotubes (TiO₂NRs/CNTs) could halve the irradiation time required to degrade MB dye compared to pure $TiO₂$ nanorods (NRs) under sunlight.²¹ Shaari et al. examined rare earth elements Ce-doped CNT-TiO₂ and recorded a significant degradation of about 94% of phenol at a concentration of 50 mg L⁻¹ over 3 h.²² Moreover, a combination of the two phases of $TiO₂$, anatase and rutile, is known to have synergistic effects, resulting in remarkably improved photocatalytic activity compared to the individual pure phases.²³ Though not yet fully understood, this effect may involve the migration of photoexcited charges between the two phases, leading to enhanced charge separation.²⁴ Although numerous studies have been conducted on $CNT-TiO₂$ nanocomposites to improve photocatalytic activity, multi-phase compositions of $TiO₂$ have not received much attention. RSC Advances Articles. which can enhance the overall 2 Experimental pioneering article in the property of the property of the method on 6/14/2024. The common spectra article is licensed and the common spectra are alternal

In this research, we investigated the synergistic effects between the multi-phase of anatase-rutile $TiO₂$ and MWCNTs (multiwalled CNTs). This addresses a significant challenge in TiO2 photocatalysis, involving the rapid recombination of electrons and holes and decreased band gap to absorb visible light efficiently. Here, TiO₂/MWCNTs nanocomposites were synthesized by a novel modified process based on a hydrothermal method, and the phase composition showed a dependence on the pH conditions. Moreover, we also adapted a simple, eco-friendly one-pot method to produce a $TiO₂/$ MWCNT nanostructure utilizing glucose as an adhesion bridge between the $TiO₂$ and MWCNTs. The characterization of the TiO2/CNT nanocomposites at different pH conditions exhibited the presence of multiple phases at pH 1.0 and the predominance of the anatase phase at higher pH values. Besides, the percentage of MWCNTs had an impact on the nanomaterial with the bandgap decreasing to 2.5 eV with 1.0% MWCNTs and 2.4 eV with 2.0% MWCNTs compared to pure $TiO₂$ with a band gap of 3.1 eV, which were remarkably lower than reported in previous studies.¹⁴ From this,²⁵ it can be seen that the TiO₂/ MWCNT catalyst demonstrated higher photocatalytic efficiency for the photodegradation of MB and RhB. These findings indicated that the as-developed $TiO₂/MWCNTs$ nanocomposites offers signicantly enhance photocatalytic performance compared to $TiO₂$, and is feasible for application in environmental treatment.

2 Experimental

2.1. Chemicals and materials

Titanium isobutoxide (TTIB, \geq 99.0%), multiwalled carbon nanotubes (MWCNTs, $\geq 80\%$ as carbon nanotubes), p-glucose $(C_6H_{12}O_6, \geq 99.0\%)$, and hydrochloric acid (HCl, 37%) were purchased from Sigma-Aldrich Chemie GmbH (Taufkirchen, Germany). Sulfuric acid $(H₂SO₄, 95.0-98.0%)$, methylene blue $(MB, \geq 99.0\%)$, and rhodamine B (RhB, $\geq 99.0\%$) were obtained from Xilong Scientific Co., Ltd (Jiangsu, China). Deionized (DI) water was used to prepare all the solutions. All the reagents were directly used without further purification.

2.2. Synthesis of TiO₂/MWCNTs nanocomposite by a modified hydrothermal method

In the typical synthesis for the $TiO₂/MWCNTs$ 1.0% sample as representative, 37 mL of glucose 1.95% (w/v), 3.0 mL of hydrochloric acid 36.0% (v/v) , and 0.06 g of MWCNTs were respectively added into z glass beaker under stirring at 600 rpm. Subsequently, 6.0 mL of titanium isobutoxide (TTIB) was added dropwise into the mixture and stirred for 30 min. Then, the mixture was poured in to a Teflon tube (90 mL) lined with a hydrothermal steel autoclave and heated at 160 °C for 6 h. Afterward, the mixture was naturally cooled to room temperature and centrifuged at 6000 rpm for 10 min. The obtained precipitant was washed three times with DI water to remove the undesired byproducts and the residual precursors. The products were finally dried at 60 °C over 480 min to obtain TiO₂/ MWCNTs nanocomposites. Subsequently, the $TiO₂/MWCNTs$ nanocomposites were synthesized under different pH conditions (ranging from 1, 4, 8, to 10) and adjusted using 1.0 M HCl and 1.0 M NaOH aqueous solutions. The MWCNTs contents were varied and examined at 1.0, 2.0, and 3.0 wt%, namely $TiO₂/$ MWCNTs-1.0, $TiO_2/MWCNTs-2.0$, and $TiO_2/MWCNTs-3.0$, respectively.

2.3. Investigation of the photocatalytic activity of the $TiO₂/$ MWCNTs nanocomposite

The performances for the photodegradation of dyes (RhB and MB) were studied with the TiO₂/MWCNTs catalyst using a solarlight simulator Moritex MME-250 (Moritex Corporation) and UV light. Briefly, 60.0 mg of TiO₂/MWCNTs was added into 100 mL of a 5.0 mg L⁻¹ aqueous dye solution. Subsequently, the mixture was stirred at 300 rpm in the dark for 30 min to attain the adsorption/desorption equilibrium and then irradiated to ignite the dye photodegradation reaction. After each interval time, a 5.0 mL solution was extracted and centrifuged at 6000 rpm to remove the catalyst. The dye concentration at the interval time was determined by UV-vis spectroscopy (at $\lambda_{\text{max(MB)}} = 664 \text{ nm}$, $\lambda_{\text{max(RhB)}}$ = 554 nm). The photodegradation efficiency was calculated using eqn (1):

$$
H = \frac{(C_{\rm o} - C_t)}{C_{\rm o}}\tag{1}
$$

where C_t is the concentration of the organic dyes studied at the interval times, C_0 is the initial concentration of dyes, and H is the degradation efficiency.

The degradation rate constant was determined based on the first-order kinetics using eqn (2):

$$
k = \frac{-\ln\left(\frac{C_t}{C_o}\right)}{t} \tag{2}
$$

For the trapping experiment tests, potassium iodide (KI), dimethyl sulfoxide (DMSO), benzoquinone (BQ), and isopropyl alcohol (IPA) were used as trapping reagents to identify the role of different reactive species, specifically photogenerated holes $(h⁺)$, electrons $(e⁻)$, superoxide radicals $(O^{2−})$, and hydroxyl radicals ('OH), respectively. The dye solution was prepared with 0.01 M of each trapping reagent, and the experimental procedure was conducted similarly to the dye degradation experiments, using a catalyst dosage of 0.4 g L^{-1} . The used TiO2/ MWCNTs were re-collected, rinsed with distilled water, and airdried under ambient conditions.

2.4. Characterization of the photocatalysts

Ultraviolet-visible (UV-vis) spectra of the dye solution and diffuse reflectance spectra (DRS) of the solid state of $TiO₂/MWCNTs$ were recorded using a Jasco V-670 UV-vis spectrophotometer, equipped with a Jasco-ARN 731 accessory in the wavelength range from 250 to 850 nm. UV-vis measurements were conducted using a quartz cuvette and blank sample for further comparison. For analyzing the $TiO₂/CNT$ nanocomposites, the sample was evenly spread on a quartz film to avoid inconsistent signal measurements. The flat band potentials of the $TiO₂/MWCNTs-1.0$ and TiO2/MWCNTs-2.0 nanocomposites were determined using Mott–Schottky (M–S) plots. In such plots, the linear portion of the plot reflects the depletion region of carriers in the space charge region, as defined by eqn $(3):^{16}$

$$
\frac{1}{C_{sc}^2} = \frac{2}{e\epsilon\epsilon_0 N} \left(E - E_{\text{fb}} - \frac{KT}{e} \right)
$$
 (3)

where C_{sc} is the specific capacity, ε is the relative dielectric constant of the material, ε_0 is the permittivity for vacuum space, N is the donor density for the semiconductor, E is the potential application, E_{fb} is the flat band potential, K is the Boltzmann constant, T is the absolute temperature, and e is the electronic charge.

FE-SEM (JEOL JSM-7600F, USA) was used to analyze the morphology of the TiO₂/MWCNTs, utilizing a Quanta FEG 250 instrument at an accelerating voltage of 10.0 kV. The elemental composition on the surface of $TiO₂/MWCNTs$ was also analyzed by energy-dispersive X-ray spectroscopy (EDS) using an Oxford Instruments 50 mm^2 X-max (UK) detector and a Gatan mono system (Gatan, UK). The TiO₂/MWCNTs were further examined by transmission electron microscopy with an accelerating voltage of 200 kV. The crystalline structure and surface morphology of the heterojunction nanocomposite photocatalysts were analyzed through high-resolution transmission electron microscopy (HR-TEM) using a JEOL ARM 200F

instrument (JEOL Ltd, Japan). The elemental distribution in the $TiO₂/MWCNT$ nanomaterials was assessed by TEM mapping with a JEOL JEM-2100 instrument (JEOL Ltd, Tokyo, Japan). For TEM analysis, a small portion of the sample was dispersed in ethanol via sonication and then placed onto a copper grid coated with a lacy carbon film. Moreover, the crystal structure of the materials was examined using X-ray diffraction (D8 Advance, Bruker, Germany), with analysis angles ranging from 30° to 80° and an angle change rate of 0.02° per sec.

The interactions between the functional groups on the surface of MWCNTs and $TiO₂$ were investigated based on their Fourier transform infrared (FT-IR) spectra over the range 4000– 400 cm−¹ using an FT/IR-6600 type A system (Jasco, Japan). The chemical composition at the surface of the samples was determined by X-ray photoelectron spectrometry (XPS; Thermo Scientific, Waltham, MA, USA) with a monochromatic Al K α Xray source at a photon energy of 1486.7 eV. The textural properties of the prepared materials were measured using a Tristar II Plus 3030 instrument (Micromeritics, USA). BET surface analysis was used to determine the surface area using a partial pressure (P/P_o) range of 0.01–0.45. The total pore volume was calculated at a single-point adsorption P/P_o of 0.950, and the pore-size distribution was assessed using the Barrett–Joyner– Halenda (BJH) porosity model. Raman spectra were evaluated using an XploRa Plus confocal Raman microscope (Horiba SAS, Longjumeau, France) with an excited laser source of 532 nm, power of 25 mW, and $50\times$ objective lens. The catalytic activity of the materials was studied using a sunlight simulator system (MORITEX MME-250-220, Metal Halide Light Source, 250 W). **Paper**
 Secretaristics As the contentration of the organic dyes studied at the **16/2** This article common the studied on the mean of the studies are principal mean of the common the studies are proported by FM. This ar

The photoelectrochemical (PEC) properties of the $TiO₂/$ MWCNTs were evaluated using a Gamry Interface 1010T system. In detail, 5.0 mg TiO₂/MWCNTs were dispersed in 2.0 mL isopropanol, and then 0.5 mL of solution was dropped onto a fluorine-doped tin oxide (FTO) electrode (1.0 \times 1.0 cm) and dried at 100 °C for 2 h. The measurements were performed using a three-electrode PEC system, with Ag/AgCl as the reference electrode, Pt sheet as the counter electrode, and $TiO₂/$ MWCNTs-coated FTO electrode as the working electrode (WE) in 0.5 M Na_2SO_4 solution. The transient photocurrent responses were measured using the chronoamperometry method to determine the carrier mobility of the materials. Mott–Schottky plots were obtained to determine the flat band potential of the materials,¹⁶ measured in the dark conditions in the potential range from −0.8 to 0.5 V and a frequency of 10 Hz. Electrochemical impedance spectroscopy (EIS) was performed in the range from 0.1 Hz to 10 kHz.

2.5. Cyclic performance using $TiO₂/MWCNTs$

The stability of catalysts plays a crucial role in assessing their practicality and cost-efficiency. To evaluate the operational stability, the $TiO_2/MWCNTs$ photocatalyst was repeatedly tested for RhB degradation over several cycles under identical conditions (0.4 g L^{-1} catalyst concentration, 120 min of irradiation, 5.0 mg L⁻¹ dye solution, and neutral pH). After each cycle, the catalyst was washed with distilled water, centrifuged at 6000 rpm, and dried for 6 h at 80 °C.

3 Results and discussion

3.1. Synthesis of $TiO₂/MWCNTs$ nanocomposites

The $TiO₂/MWCNTs$ nanocomposites were initiated with the hydrothermal process involving strong Lewis acid TTIB precursors in the presence of hydrochloric acid (HCl) and glucose diluted with deionized water (DI). When the TTIB hydrolyzes with water, Ti^{4+} increases from +4 to +6, thus forming Ti–O bonds. Under high pressure and temperature, these six-fold structural units form octahedra that eventually precipitate into crystals. Corner- and edge-sharing occur as the octahedra aggregate during condensation reactions and form TiO2. ²⁶ The chemical reactions involved in the hydrolysis (eqn (4)) and dehydration or condensation (eqn (5) and (6)) during the hydrothermal synthesis process can be described as follows:

$$
Ti(OR)_4 + 4H_2O \rightarrow Ti(OH)_4 + 4ROH \tag{4}
$$

$$
Ti(OH)_4 + Ti(OH)_4 \to 2TiO_2 + 4H_2O
$$
 (5)

 $Ti(OH)₄ + Ti(OR)₄ \rightarrow 2TiO₂ + 4ROH$ (6)

The overall reaction is:

$$
Ti(OR)4 + 4H2O \rightarrow 2TiO2 + 4ROH
$$
 (7)

The one-pot synthesis of $TiO₂/MWCNTs$ was achieved using glucose as a structure-directing agent and a carbon source without requiring any prior covalent or non-covalent functionalization of MWCNTs. Using glucose to facilitate the formation of $TiO₂/MWCNTs$, it was reported that the hydrothermal process of glucose can produce some aromatic compounds with multiple hydroxyl groups, which act as a bridge to connect $TiO₂$ and MWCNTs. The phenyl ring of these aromatic compounds attach to the graphitic surface of CNTs through $\pi-\pi$ stacking, while its hydroxyl group directly interact with the TTIB precursors.²⁷

3.2. Effect of pH

 $TiO₂/MWCNTs-2.0%$ was prepared at different pH values $(1, 4, 4)$ 8, and 10) to evaluate the effect of the pH conditions on the TiO2/MWCNTs nanocomposites formation. XRD patterns and

Raman spectra were employed to determine the crystalline structure of the samples, as shown in Fig. 1. The XRD pattern (Fig. 1(a)) of TiO₂/MWCNTs-2.0% at pH 1 displayed all the diffraction peaks of the tetragonal anatase TiO₂ (JCPDS No. 21-1272) and other peaks at 2-theta of 27.4°, 35.9°, and 41.1°, which were related to the (110), (101), and (111) facets of the rutile TiO₂ (JCPDS No. 21-1276).²⁸ At higher pH values, only diffraction peaks characteristic of the anatase phase were observed, and the intensity of the anatase $TiO₂ (101)$ diffraction peak at 25.2° increased as the pH increased from 4 to 8, but decreased at pH 10. This indicates that the pH influences the phase transition from rutile to anatase and affects the crystallinity of $TiO₂$ during the hydrothermal process. Additionally, the crystal size was estimated using Scherrer's equation, as given in eqn (8):²⁹ **PSC Advances**
 S Results and discussion
 S Results Article. Some composites

The TiO_CAWCSYR annocempesites

The TiO_CAWCSYR annocempesites

Interdecting roots are initiated with the difference profess are the regu

$$
D = \frac{K\lambda}{\beta \cos \theta} \tag{8}
$$

where D represents the crystalline size (nm), K is 0.9 (Scherrer's constant), λ is 0.15406 nm (the wavelength of the X-ray source— CuK α), β is the full width at half maximum FWHM (in radians), and θ is the Bragg-diffraction angle (peak position in radians) (Table 1).

3.3. Crystalline structure and composition

Further evidence for the crystalline structure of $TiO₂/MWCNTs$ was obtained from Raman spectroscopy (Fig. 1(b)), which recorded the characteristic vibrations of TiO₂. At pH 1, the spectrum revealed the formation of a rutile and anatase phase mixture, as indicated by the peak at 150 cm⁻¹ assigned to the symmetries of the E_g mode of anatase, and two stretching peaks

Table 1 Variation in crystalline size with varying the pH condition as determined by Scherrer's equation

Sample	2 theta $(°)$	FWHM $(°)$	D(nm)
pH ₁	25.12	1.56	5.4
pH ₄	25.30	2.19	3.9
pH ₈	25.19	2.18	3.9
pH 10	25.35	2.25	3.8

Fig. 1 (a) XRD patterns and (b) Raman spectra of TiO₂/MWCNTs-2.0 synthesized at different pH conditions, including pH 1, 4, 8, 10.

at 409 and 618 cm⁻¹ corresponding to the symmetries of the E_g and A_{1g} of rutile TiO₂. As the pH increased, there were only Raman active modes of anatase $TiO₂$ shown by peaks at 150 cm⁻¹ (E_g), 390 cm⁻¹ (B_{1g}), 508 cm⁻¹ (A_{1g}), and 624 cm⁻¹ (E_g) .³⁰ Additionally, the Raman spectra showed signals at 1340 and 1574 cm^{-1} , corresponding to the D and G bands of MWCNTs, respectively, indicating that the hydrothermal process preserved the structure of the CNTs. The ratio of the D and G bands intensity (I_D/I_G) in a CNT sample is indicative of the presence of structural defects and sp³-hybridized carbon atoms, providing insights into the level of sidewall functionalization.³¹ The I_D/I_G ratio varied from 0.52, 0.57, and 0.58 to 0.60, at pH values of 0, 4, 8, and 10, respectively. A higher I_D/I_G ratio was observed at elevated pH values, implying the interaction between the MWCNTs surfaces and TiO₂ nanoparticles.

The pH value directly affects the dispersion of MWCNTs in water and the process of attaching $TiO₂$ to the MWCNTs surface. Multiwalled carbon nanotubes (MWCNTs) comprise non-polar graphene walls, making them poorly dispersed in water. However, when the pH of the solution increases, the number of COOH functional groups on the surface of MWCNTs that deprotonate to form carboxylate anions (COO−) also increases. This process enhances the dispersion of MWCNTs in water.³² The negative charge positioned on the two oxygen atoms in the carboxylate anion will repel each other, loosening the CNT bundles and helping the CNT have many opportunities for separate distribution, which is beneficial in the process of $TiO₂$ agglomeration on the MWCNTs surface.

In the hydrothermal method, the acidity was supposed to be crucial for the hydrolysis of TTIB. Under highly acidic conditions (with a high concentration of H^+ ions), the hydrolysis of titanium isobutoxide (TTIB) can lead to the formation of protonated groups as intermediate compounds $[Ti(OH)₃(-)]$ $OH₂)₃$ ⁺.²⁶ These intermediate compounds will readily bond with OH⁻ groups from other TiO₆ octahedra. Then, Ti-O-Ti oxygen bridge bonds are formed with water dehydration. To achieve a dense and favorable orientation in the rutile phase, the $TiO₆$ octahedra must exhibit a high degree of protonation, making hydrolysis and dehydration reactions effectively catalyzed. Thus, both rutile and anatase phases were obtained at pH 1.0. In contrast, higher pH conditions that lead to the increase in the concentration of OH− ions promote the rapid oxidation of titanium precursors to form $Ti(OH)_{3+x}$, resulting in the formation of only the anatase phase.²³ Following the dehydration reaction, insufficient protonation leads to a face-sharing anatase phase, while adequate protonation results in cornerand edge-sharing in the rutile phase.²⁶ Paper

Access Articles. Are prime in consider the Eq. 10. In hydroductural method, the acidity was apposed to be
 $\frac{1}{2}$ and $\frac{1}{2}$

XPS was next employed to determine the surface components of the TiO₂/MWCNTs. The XPS spectra of TiO₂/MWCNTs-2.0 synthesized at pH 1 and 10 are shown in Fig. 2(a). The XPS survey spectra indicated the interaction of $TiO₂$ and CNT by the appearance of C, O, and Ti elements in both samples, while pristine MWCNTs only presented O and C atoms. The Ti 2p high-resolution XPS (HR-XPS) spectrum of $TiO₂/MWCNTs-2.0$ synthesized at pH 1 (Fig. 2(b)) displayed two peaks at binding energies (BE) of approximately 465.1 and 459.3 eV,

Fig. 2 (a) Survey XPS spectra, (b) high-resolution Ti 2p XPS spectra, (c) C 1s XPS spectra, and (d) O 1s XPS spectra of bare MWCNTs, and TiO₂/ MWCNTs 2.0% nanocomposite synthesized at pH 1.0 and pH 10.0.

corresponding to Ti $2p_{3/2}$ and Ti $2p_{1/2}$ splitting of the Ti⁴⁺ state.³³ The analysis of the Ti-2p peaks showed that the samples contained Ti^{4+} . For the sample synthesized at pH 10, these peak positions were shifted to around 465.3 and 459.6 eV for the $Ti⁴⁺$ state, and these intensities were significantly decreased. Compared to standard values, the higher binding energies of the Ti 2 $p_{3/2}$ and Ti 2 $p_{1/2}$ peaks were attributed to the formation of Ti–C bonds.³⁴ Moreover, the Ti 2p high-resolution XPS (HR-XPS) spectra of the TiO₂ sample (Fig. S1(b)[†]) showed two peaks at binding energies (BE) of around 464.7 and 459.0 eV, corresponding to the splitting of Ti 2p_{3/2} and Ti 2p_{1/2} in the Ti⁴⁺ state. The Ti 2p HR-XPS spectra of $TiO_2/MWCNTs$ exhibited a slight shift to higher binding energies compared to $TiO₂$, indicating the presence of lattice bonding in the form of Ti–O– C. This shift in binding energy was also attributed to lattice distortion, further confirming the interaction between $TiO₂$ and carbon.³⁵ The HR-XPS spectra of C 1s (Fig. 2(c)) further provided more evidence for the presence of Ti–C bonds. For pristine MWCNTs, there was a sharp peak at 284.5 eV corresponding to C–C and C $=$ C sp² hybridization and a weak peak around 285.4 eV related to C–C sp³ hybridization.³⁶ In the case of TiO₂/ MWCNTs 2.0% synthesized at pH 1.0 and 10, these peaks were shifted to a lower binding energy of 284.3 eV. This shift was associated with the formation of Ti–C bonds in the nanocomposites.³⁷ Meanwhile, other peaks in the nanocomposites RSC Advances

corresponding to 51 P₂ on 21² D₂ applicing of the T⁴⁺ case abouted to the article is light on 25 October 2024. Downloaded on 25 October 2024. Downloaded on 25 October 2022. Downloaded on 5/14/2022. C

Fig. 3 Transient photocurrent responses of $TiO₂/MWCNT$ nanocomposites synthesized under different pH conditions (pH 0, 4, 8, and 10).

were observed, centered at a BE of 288.9 eV, which were attributed to C sp³ and C=O species bonded to oxygen.¹⁵ These functional groups in the functionalized CNTs undergo an esterification reaction with the -OH groups of the Ti precursor, forming covalent bonds, such as C –O–Ti or O $=$ C–O–Ti. The HR-XPS O 1s spectrum of TiO₂/MWCNTs-2.0 synthesized at pH 1.0 showed two deconvoluted peaks at approximately 530.8 and 532.6 eV, corresponding to lattice oxygen (O_2^2) in anatase Ti-O-Ti and surface hydroxyl groups (-OH), respectively.³⁸ For $TiO₂/MWCNTs-2.0$ synthesized at pH 10, the lattice oxygen peak decreased, and the non-lattice peak significantly increased, indicating the formation of more oxygen defects in the crystal structure when synthesized in alkaline conditions.

Next, photoelectrochemical (PEC) measurements were employed to investigate the photocatalyst performance of the nanocomposites. The photocurrent response of $TiO₂/MWCNTs$ nanocomposites synthesized at different pH values (1, 4, 8, and 10) was recorded over three on–off cycles of light irradiation. As shown in Fig. 3, all four samples exhibited reversible photocurrent responses and high reproducibility under light-on and light-off conditions, indicating the efficient separation and transfer of photogenerated electron-hole pairs.³⁹ The TiO₂/ MWCNTs synthesized at pH 1 demonstrated the highest photocurrent, approximately 9 μ A cm⁻² (curve red), while the photocurrent significantly decreased for the samples synthesized at pH 4, 8, and 10. These results suggest that the mixture of anatase and rutile $TiO₂$ phases can enhance the photoelectron density of the $TiO₂$ photocatalyst rather than the pure anatase crystal phase, thus enabling a higher photocatalyst performance.⁴⁰ This proved that the TiO₂/MWCNTs nanocomposite synthesized in an acidic environment exhibited higher photocatalyst performance.

3.4. Effect of the MWCNT contents

The XRD patterns of pristine $TiO₂$ and $TiO₂/MWCNTs-2.0$ nanocomposites (Fig. 4) indicated the presence of both rutile and anatase phases of $TiO₂$ in both samples.⁴¹ The absence of a MWCNTs peak in the TiO₂/MWCNTs-2.0 nanocomposite pattern was due to the prominent TiO₂ peak at $2\theta = 25.3^{\circ}$, which might overlap the MWCNTs peak at $2\theta = 25.9^{\circ}$. Compared to

Fig. 4 (a) XRD patterns of (a) TiO₂/MWCNTs-2.0 nanocomposite, (b) pure TiO₂, and standard patterns of (c) anatase TiO₂ and (d) rutile TiO₂. (b) Raman spectra of TiO2/MWCNTs synthesized at different percentages of MWCNTs, including 1.0, 2.0, and 3.0 wt%.

the pristine $TiO₂$ pattern, a significant decrease in the intensity of all peaks in the $TiO₂/MWCNTs$ nanocomposite could be observed. Besides, the anatase TiO₂ (101) peak at $2\theta = 25.3^\circ$ and the rutile (110) peak at $2\theta = 27.4^{\circ}$ became broadened, indicating that the addition of MWCNTs reduced the crystallinity of $TiO₂$. Raman spectra were collected for the MWCNTs and $TiO₂/$ MWCNTs nanocomposite catalysts with varying weight percentages (1.0, 2.0, 3.0 wt%) of MWCNTs, as illustrated in Fig. 4(b). The results showed that all the samples contained a mixture of rutile and anatase phases. This was evident from the presence of peaks at 150 cm⁻¹ associated with the E_{α} mode of anatase and peaks at 409 and 618 cm−¹ corresponding to the E_{φ} and $A_{1\varphi}$ symmetries of rutile TiO₂. Compared to the MWCNTs, the D- and G-band signals of the $TiO₂/MWCNTs$ were reduced, indicating a decrease in amorphous carbon and an increase in the crystallinity of the samples.¹⁶

The morphologies of the $TiO₂/MWCNTs$ nanocomposites synthesized with MWCNT contents of 0, 1.0, 2.0, and 3.0 wt% were characterized by SEM images (Fig. 5). The addition of MWCNTs significantly impacted the morphologies of the $TiO₂$ nanoparticles. The sample synthesized without MWCNTs exhibited rod shapes with an aspect ratio of 4 and an average length of 105 \pm 3 nm (Fig. 5(a)). In contrast, the TiO₂/MWCNTs nanocomposites featured smaller $TiO₂$ nanoparticles, and this shape became more unclear as the MWCNTs content increased. The $TiO₂/MWCNTs-1.0 nanocomposite$ (Fig. 5(b)) exhibit the aggregation of smaller $TiO₂$ nanorods with an aspect ratio of 2.6 and a length of 18 ± 1 nm. These nanorods formed irregular clusters attached to the MWCNTs. As the MWCNT contents increase from 1.0% to 3.0%, the TiO₂ layer exhibited a high degree of dispersion that formed a dense and continuous layer

around the MWCNTs due to the self-agglomeration and aggregation of small particles (Fig. 5(c and d)). It could be observed that the increase in the average width of MWCNTs from 20 ± 1 and 42 \pm 2 nm to 56 \pm 3 nm corresponded to the MWCNT content of 1.0, 2.0, and 3.0 wt%, respectively (Fig. 5(e)). Here, the MWCNTs provide a scaffold that supports the attachment and growth of $TiO₂$, thus enhancing the surface area and structural integrity.

TEM and HR-TEM images of the $TiO₂/MWCNTs-2.0$ nanocomposites were analyzed to confirm the structure of the nanocomposites (Fig. 6(a–c)). These images revealed that small TiO₂ nanoparticles were uniformly distributed on the surface of the MWCNTs. Fig. 6(d) shows the size-distribution histogram of TiO2 nanoparticles, indicating that they were monodispersed with an average size of 6.4 \pm 0.1 nm, distributed on the MWCNTs with an average diameter of 17.5 ± 3.0 nm. The HR-TEM image (Fig. 6(c)) displays the crystal lattice fringes with spacings of 0.35 and 0.235 nm, corresponding to the (101) and (001) lattice planes in anatase $TiO₂$ decorated on the MWCNTs. Besides, the STEM-EDS mapping images of the $TiO₂/MWCNTs$ -2.0 nanocomposites (Fig. 6(e)) further demonstrated that $TiO₂$ nanocrystals were uniformly distributed around the surface of MWCNTs. The mapping results for titanium (Ti) and oxygen (O) indicated that these elements were evenly distributed on the surface of the CNT fibers. This suggests the successful decoration of TiO₂ particles on the MWCNTs surface.⁴² Moreover, the carbon (C) element mapping revealed an uneven distribution, further supporting that $TiO₂$ particles effectively surrounded the MWCNTs. Additionally, the uneven C distribution indicated the dense attachment of TiO₂ nanoparticles on the CNT fibers, as the carbon signal was partially obscured by the $TiO₂$ layer.⁴² Paper

One prisoner, a significant decrease in the initiality around the MWCNTs due to the application and aggre

of all peaks are 2π at Postmach on 25 October 2024. The gas are the set of the set of the set of the set

Fig. 5 SEM images of (a) TiO₂ without MWCNTs, (b) TiO₂/MWCNTs-1.0, (c) TiO₂/MWCNTs-2.0, and (d) TiO₂/MWCNTs-3.0 synthesized by the hydrothermal method. (e) The corresponding size distribution graph of the TiO₂/MWCNT nanocomposite width, synthesized with MWCNT contents of 0, 1, 2, and 3%.

Fig. 6 (a) TEM image, scale bar 50 nm. (b) High-magnification TEM image, scale bar 20 nm. (c) HR-TEM image of TiO₂/MWCNT-2.0 nanocomposites. (d) Size-distribution histogram of TiO₂ nanoparticles on MWCNTs. (e) TEM-EDS elemental mapping for (D) titanium, (E) oxygen, and (F) carbon.

The $TiO_2/MWCNTs-1.0$ and $TiO_2/MWCNTs-2.0$ nanocomposites were analyzed for determining their elemental composition by X-ray energy-dispersive spectroscopy (EDS) (Fig. S2†). The mass percentages and elements in the corresponding Table S1 \dagger also show that the TiO₂/MWCNTs materials were initially successfully synthesized. The obtained results showed peaks appearing at the 4.6 and 5.0 keV potential regions, which were typical for the Ti element. In addition, peaks appeared at positions 0.2 to 0.6 keV attributed to C and O elements.⁴³ The mass percentages and elements presented in the table show that $TiO₂$ –MWCNTs materials were successfully synthesized with the percentage weight of carbon in $TiO₂/CNT-$ 1.0% and 2.0% at 14.06% and 39.66%, respectively (Table S1†). Besides, the EDS spectrum also presents some peaks of Cl, Si, and S at 2.6, 1.8, and 2.3 keV, respectively.⁴³ However, these

peak intensities were low compared to the significant elements, possibly because the sample was still mixed with some reactants remaining after the reaction. Fig. $S3$ (ESI†) presents the electrochemical impedance spectroscopy (EIS) results, illustrating the electron transportation between the electrode interface of TiO₂/MWCNTs with different MWCNT contents and electrodes, showing that the nanocomposite 2.0% MWCNTs possessed a smaller resistance and faster electron transport with a smaller radius arc in the Nyquist plots.⁴⁴

Fourier transform infrared (FTIR) spectroscopy was next used to analyze the chemical bonding and functional groups of the nanostructured $TiO₂/MWCNTs$. A series of spectra of MWCNTs, $TiO₂$, and $TiO₂$ –MWCNTs-2.0 were investigated to identify potential interactions between $TiO₂$ and the MWCNTs (Fig. 7). In detail, the FTIR spectrum of TiO₂ (Fig. 7(a)) exhibited

Fig. 7 FTIR spectra of (a) bare MWCNTs, (b) pristine $TiO₂$, and (c) $TiO₂$ / MWCNTs-2.0 nanocomposites.

a characteristic peak for Ti–O bond vibrations at 547 $\rm cm^{-1.45}$ Additionally, peaks were displayed at 3405 and 1631 cm^{-1} corresponding to the stretching and bending vibrations of the O–H group, indicating the presence of adsorbed water molecules on the TiO₂ surface.⁴⁶ The FTIR spectrum of the MWCNTs showed a characteristic oscillation signal for the $C=C$ bond around 1631 cm⁻¹ (Fig. 7(b)).⁴⁷ In the FTIR spectrum of TiO₂-MWCNTs 2.0 (Fig. 7(c)), peaks also appeared at 3405 and 1631 cm^{-1} , suggesting the decoration of $TiO₂$ around the MWCNTs.

The UV-vis spectra of pristine $TiO₂$ and the $TiO₂/MWCNTs$ nanocomposites synthesized with varying MWCNT contents (0, 1.0, 2.0, and 3.00 wt%) are presented in Fig. $8(a)$. The red shift observed in the $TiO₂/MWCNTs$ nanocomposite samples compared to pristine $TiO₂$ indicated a reduction in the electron ionization energy of the nanocomposites, facilitating efficient charge transfer between the $TiO₂$ and MWCNTs structure.¹⁶ The bandgap energy values were calculated from Tauc plots, yielding values of 2.5, 2.4, and 1.5 eV for the nanocomposites with MWCNT contents of 1.0, 2.0, and 3.0 wt%, respectively. These bandgap values were significantly lower than that of pristine TiO₂, which was 3.1 eV (Fig. 8(b)). The decrease in the bandgaps of the $TiO₂/MWCNTs$ nanocomposites was attributed to the interaction between $TiO₂$ and MWCNTs by forming Ti-O-C bonds. The formation of these chemical bonds creates new energy states within the bandgap of $TiO₂$, allowing for longerwavelength light excitation.⁴⁸ Mott-Schottky (M-S) plots were employed to determine the flat band potential of the $TiO₂/$ MWCNTs-1.0 and TiO₂/MWCNTs-2.0 nanocomposites Fig. 8(c).

Moreover, a linear regression could be observed in this plot, corresponding to the depletion state of the carriers in the space charge region, as described by eqn (3), characteristic of an ntype semiconductor.⁴⁹ The flat band potentials (E_{fb}) for TiO₂, $TiO₂/MWCNTs-1.0$, and $TiO₂/MWCNTs-2.0$ were approximately –0.51, –0.47, and –0.39 V vs. Ag/AgCl, equivalent to –0.31, –0.27, and –0.19 V vs. NHE. Based on the formula $E_{VB} = E_{CB} - E_{g}$, the valence band edge (E_{VB}) values were calculated. Additionally, the valence band potentials for $TiO₂$, $TiO₂/MWCNTs-1.0$, and $TiO₂/MWCNTs-2.0$ were determined to be 2.8, 2.2, and 2.2 eV vs. NHE, respectively. The recorded photocurrent response of the pristine $TiO₂$ and $TiO₂/MWCNTs$ nanocomposites showed that the photocurrent induced by the nanocomposites was significantly higher than that of pristine TiO₂ (Fig. 8(d)). Among them, TiO₂/MWCNTs-2.0 exhibited the highest photocurrent, three times greater than that of pristine $TiO₂$ and twice that of $TiO₂/$ MWCNTs-1.0. Conversely, $TiO₂/MWCNTs-3.0$ displayed the lowest photocurrent response among the nanocomposites. The increased photocurrent signals could be due to the interaction between $TiO₂$ and CNTs, which improved the separation rate of photogenerated electrons. However, a drop in the photocurrent value was observed in the $TiO₂/CNT-3.0%$ composite due to the excess MWCNTs obstructing $TiO₂$ light absorption.⁵⁰ This indicates that the MWCNT content in the nanocomposites significantly impacts their photocatalytic properties.

The N_2 adsorption–desorption isotherms and pore-size distributions of the TiO₂/MWCNTs-2.0 nanocomposites were obtained and are presented in Fig. 8(e) and (f). The plot shows a type IV adsorption isotherm, indicating capillary condensation in mesopores, with an H1 hysteresis loop appearing at relatively high pressures (0.4 < P/P_0 < 1.0). The primary pore diameters were found to be around 4.9 nm. The BET surface area obtained was 189.20 m² g^{−1}. Mahdi Kazazi *et al.* prepared a TiO₂/MWCNT nanocomposite anode material for aqueous RABs using a simple template-free hydrothermal method with pore sizes around 4.02 nm.⁵¹ In this study, the pore diameter of the material was enhanced by around 4.9 nm. Compared to the previous study,⁵¹ the surface performance of these nanocomposites was improved. These larger pores in a catalyst could facilitate the adsorption of organic molecules on its surface during photodegradation, thereby boosting its photocatalytic activity. Thus, the addition of MWCNTs can effectively prevent $TiO₂$ particle agglomeration and increase the specific surface area.

3.5. Photocatalytic of dye degradation

The photocatalytic degradation of MB and RhB dyes was employed to investigate the photocatalyst properties of the modified materials. The effects of many parameters, such as adsorption time, catalyst dosage, pH condition, and type of catalysts, were further investigated.

3.5.1. Effect of the MWCNT contents on dye photodegradation. The dependence of the catalytic activity under visible light on the MWCNT content in the nanocomposite catalysts was further investigated. The kinetics of dye degradation followed a first-order reaction, as evidenced by the linear

Fig. 8 (a) Solid-state UV-vis spectra, (b) Tauc plots for calculation of the band gap, (c) Mott–Schottky plot (d) transient photocurrent responses plots of TiO₂/MWCNTs nanocomposites synthesized with different MWCNTs contents (0, 1.0%, 2.0%, 3.0%). (c) Mott–Schottky plots of TiO₂/ MWCNTs-1.0 and TiO₂/MWCNT-2.0, and (e) N₂ adsorption–desorption isotherms. (f) BHJ adsorption pore-size distribution and isotherms of the TiO₂/MWCNTs-2.0 nanocomposite.

Fig. 9 Photocatalytic degradation rate of MB (a) and RhB dyes (c) using TiO₂/MWCNTs nanocomposite catalysts with different MWCNTs contents (0, 1.0, 2.0, 3.0 wt%). The photocatalytic degradation rates of MB (b) and RhB (d) in the presence of the trapping reagents benzoquinone (BQ), dimethyl sulfoxide (DMSO), isopropyl alcohol (IPA), and potassium iodide (KI) under visible-light irradiation using the $TiO₂/$ MWCNTs-2.0 nanocomposite.

relationship of $ln(C_t/C_0)$ versus time (t) (Fig. 9). The UV-vis spectra of MB and RhB solutions at different time intervals using pristine $TiO₂$ and $TiO₂/MWCNTs$ nanocomposites are exhibited in Fig. S4 and S5 (ESI†). The rate constants for MB degradation were 0.0051, 0.004, and 0.003 min⁻¹ when using $TiO₂/MWCNTs$ with MWCNT contents of 1.0, 2.0, and 3.0 wt%, respectively (Table S2†). For RhB dye, the rate constants were 0.005, 0.0065, and 0.0039 min⁻¹ (Table S2†), respectively. The $TiO₂/MWCNTs-1.0$ catalyst demonstrated the highest photocatalytic efficiency for MB photodegradation (Fig. 9(a)). In contrast, $TiO_2/MWCNTs-2.0$ exhibited the highest performance for RhB photodegradation (Fig. 9(c)), while $TiO₂/MWCNTs-3.0$ showed lower photocatalytic activity for both dyes (Fig. 9(a) and (c)). Fig. S6 and S7 (ESI†) exhibit the change in UV-vis spectra of the MB and RhB solutions during various time intervals when using pristine $TiO₂$ and $TiO₂/MWCNTs$ (with different contents), respectively. It could be seen that the $TiO₂/$ MWCNTs nanocomposites exhibited significantly enhanced photocatalytic performance compared to pristine $TiO₂$, whose rate constants were 0.0013 and 0.0032 min^{-1} for MB and RhB degradation, respectively. The effects of the irradiation time, pH conditions, and the photodegradation process of dyes using TiO2/MWCNTs were also studied (Fig. S8†). The photodegradation rate of RhB dye exhibited a considerable decrease under acidic and alkaline conditions, with corresponding rate constants of 0.0019 and 0.002 min^{-1} , respectively, in contrast to 0.0065 min^{-1} under neutral conditions.

The degradation mechanism of MB was previously analyzed based on the bond dissociation energy (BDE) theory by Huang et al.⁵² N–CH₃ was previously dissociated due to having the lowest BDE to form $-CH_3$ groups, which could be further oxidized into HCHO or HCOOH. Furthermore, the 'OH radical has the potential to engage with the $C-S^+=C$ functional group in MB. This interaction may result in the cleavage of the $C-S^+$ C bond and the subsequent opening of the aromatic ring structure of phenothiazine. Subsequently, single-ring structures, such as 2,5-diamino benzene sulfonic acid and 4 aminobenzene-1,2-diol, could be formed. Phenyl thiophene is formed from these single-ring structure molecules.⁵² It can be seen from the UV-vis spectra of MB solution that there was a double peak located at 664 and 615 nm, attributed to the monomer and dimers. An increase in the adsorption peak at 615 nm was correlated with more extended time intervals, likely attributable to a higher monomer degradation rate than the dimer. In addition, the decrease in the intensity of the 664 nm peak could be attributed to the N-demethylene and the phenothiazine degradation.⁵³ For the RhB degradation intermediates, based on the O_2 ⁻/'OH generated in the reaction solution, the initial RhB molecules undergo an interruption step, such as Nde-ethylation, chromophore breaking, opening-ring, and mineralization. These primary intermediates from the degradation of RhB could be benzoic acid, succinic acid, 2-hydroxypentane dioic acid, adipic acid, 3-hydroxybenzoic acid, phthalic acid, and terephthalic acid.⁵⁴ Paper

The degradation mechanism of MB was previously analyzed in the cader of e^{-y} by $^{1/2}$ Of the same of the time of the same of the paper of the same of

The enhanced photocatalytic performance of the $TiO₂/$ MWCNTs nanocomposite was attributed to the formation of Ti– O–C bonds, as evidenced by the XPS results. These bonds generate new electronic energy states between the valence band (VB) and conduction band (CB) of $TiO₂$. This increases the number of photogenerated holes (h $^\mathrm{+})$ and electrons (e $^-$) because less energy from the incident light is required to separate the electrons and holes. Additionally, MWCNTs, known for their high work function and conductivity, act as electron sinks that reduce the h^+ and e^- recombination rate. This increase in the lifetime of h^+ and e^- significantly improves the photodegradation rate of dye molecules.⁵⁵

The photodegradation of dyes involves the oxidation of free radical species, such as excited electrons (e−), photoexcited holes (h⁺), hydroxyl radicals ('OH), and superoxide radicals (C^2) ⁻⁵⁶. The roles of these free radical species in the photodegradation mechanism of dyes with the $TiO₂/MWCNTs-2.0$ nanocomposite catalysts were explored using potassium iodide (KI), isopropanol (IPA), benzoquinone (BQ), and DMSO as the trapping reagents of h⁺, 'OH, 'O^{2−}, and e⁻, respectively. The UV-vis spectra of RhB solutions at the adsorption time intervals using $TiO₂/MWCNTs-2.0$ nanocomposites in the presence of different radical trapping agents are shown in Fig. S9.† It was found that the degradation rate in the presence of the trapping reagents DMSO, KI, IPA, and BQ was reduced by 83.1%, 76.0%, 65.9%, and 36.7% for RhB dye (Fig. 9(b)), while that for MB dye corresponded to 32.7%, 41.1%, 32.1%, and 24.6% (Fig. 9(d)) in comparison to without using trapping reagents. Therefore, it could be assumed that RhB photodegradation occurred through the contribution of free radicals

in the order of e^- > h⁺ > 'OH > 'O^{2−} and the ability to capture radicals in the case of MB dye corresponded to $h^+ > e^- >$ 'OH > \cdot O^{2−}.

The mechanism of organic compound degradation using the TiO2/MWCNTs photocatalyst suggested by Chen et al. is based on electron transfer from the TiO₂ to CNTs.¹⁶ Furthermore, in the presence of hydrogen ions and water molecules, the decomposition of MB and RhB could be described as follows (eqn (9)–(19)):

$$
Dye + hv \to dye^* + e^-
$$
 (9)

$$
Dye^* + TiO_2 \rightarrow TiO_2 (e_{CB}^-) + dye
$$
 (10)

$$
Dye^* \to \text{dye} + h_{VB}^{\dagger} \tag{11}
$$

$$
TiO2 + hv \rightarrow TiO2 (eCB-) + hVB+
$$
 (12)

 $TiO₂ (e_{CB}⁻) + MWCNTs \rightarrow TiO₂ + MWCNTs (e⁻)$ (13)

$$
MWCNTs (e^-) + O_2 \rightarrow MWCNTs + 'O_2^-
$$
 (14)

$$
^{\cdot}O_{2}^{-} + H_{2}O \rightarrow HO_{2}^{-} + \cdot OH \tag{15}
$$

$$
\mathrm{HO_2}^- + \mathrm{H}^+ \rightarrow \mathrm{H_2O_2} \tag{16}
$$

$$
h_{VB}^+ + 2OH^- \rightarrow \text{`OH} + 0.5O_2 \tag{17}
$$

$$
OH + dye \rightarrow degradation product
$$
 (18)

$$
h_{VB}^{\dagger} + \text{dye} \rightarrow \text{degradation product} \tag{19}
$$

In reaction (14), oxygen reacts with electrons on MWCNTs to form free radicals 'O₂ $^-$, leading to the formation of 'OH radicals (reaction (15)), which catalyzes the decomposition reaction of RhB (reaction (18)). If O_2 ⁻ radicals are limited and little formed, the efficiency of the RhB degradation reaction will be significantly reduced. Previous studies also showed that superoxide radicals O_2 ⁻ and HO_2 ⁻ have a very strong activity that can degrade the aromatic ring structure of some organic compounds.⁵⁷

3.5.2. Cyclic performance of $TiO₂/MWCNTs$. The recyclability of photocatalysts is crucial because it allows for their repeated use and significantly reduces costs. The recyclability of photocatalysts containing 2.0% MWCNTs was evaluated over six cycles, and the photodegradation efficiency was calculated using eqn (1). Fig. S10 (ESI†) presents the degradation efficiency across six cycles. In the first two cycles, the degradation efficiencies were 55.3% and 47.1%. In the third cycle, the efficiency remained nearly unchanged at 47.1%. By the fourth cycle, there was a slight decline to 45.2%. The efficiency dropped to 40.0% in the fifth cycle, and by the final cycle, the photocatalyst's recyclability had decreased to 33.3%.

The thermal properties of the $TiO₂/MWCNTs$ nanocomposite before and after the photocatalyst recyclability test were evaluated using thermogravimetric analysis (TGA). The investigations were performed from room temperature to 800 ° C. The TGA curves of the TiO₂/MWCNTs composites heated in air are depicted in Fig. S11.† The observed weight losses at 40 °C

to 200 °C corresponded to the evaporation of residual solvents and water. At a temperature of 200 °C, complete removal of the water and organic precursors occurred, resulting in residual masses of 96.67% and 96.98% of the initial weight of the $TiO₂/$ MWCNT-2.0 sample after and before the photocatalyst recyclability test, respectively. The sharp weight loss at 200 °C signaled the onset of MWCNTs oxidation, with the activation energy for this process being influenced by factors such as the number of walls, defects, and impurities present in the MWCNTs.⁵⁸ The thermogravimetric analysis also revealed a two-step weight loss pattern: the first stage, at lower temperatures, was due to the loss of solvents and water, while the second stage, at higher temperatures, corresponded to the oxidation of MWCNTs. The TiO₂ content in the composites was determined through TGA, assuming complete MWCNTs oxidation at 480 °C. Following six cycles, the TiO₂/MWCNTs-2.0 sample exhibited mass percentages of 90.17% and 91.99% post- and pre-photocatalyst recyclability testing (Fig. S11†), respectively, implying the recyclability of the photocatalyst. After six cycles of testing in the photodegradation reaction, the changes in the $TiO₂/MWCNTs$ nanocomposite structure were investigated based on the FTIR spectrum (Fig. S12†). It was observed that the intensity of the characteristic peaks attributed to the vibrations of $O-H$, $C=H$, $CH₂$, and Ti-O groups remarkably increased after six cycles of the photocatalytic performance studies, indicating the degradation of the $TiO₂/MWCNTs$ nanocomposite. RSC Advances Computed the conormistic of the conormistic shemical shemical computer and article is likeled to the computer and the strength or the creative computer and the entropy of α . The positive Commons are the st

The efficacy of the as-prepared $TiO₂/MWCNTs$ was also compared with that of commercial $TiO₂$ under similar conditions. Experiments were conducted to assess the photodegradation of dyes. The findings indicated that the $TiO₂/$ MWCNTs nanocomposite outperformed commercial $TiO₂$ as depicted in Fig. S13.†

3.5.3. Photodegradation mechanism. TiO₂ is a well-known semiconductor with a band gap larger than 3.0 eV, with the valence band attributed to the occupied O 2p orbital and the conduction band involving the unoccupied Ti 3d orbital, making $TiO₂$ primarily active under UV light. When exposed to UV light, electrons in the valence band of $TiO₂$ are excited into the conduction band, forming photogenerated electron–hole (e^{-}/h^{+}) pairs. The lifetime of these e^{-}/h^{+} pairs is only at the nanosecond level, leading to their rapid recombination and limiting their participation in photocatalytic reactions.⁵⁵ Integrating MWCNTs into the $TiO₂$ matrix significantly enhanced the photocatalytic performance. The $TiO₂/MWCNTs$ nanocomposites exhibited higher photocatalytic degradation efficiency for MB and RhB dyes, which could be attributed to the formation of new energy bands within the $TiO₂$ band gap, created by the formation of new Ti–O–C bonds in the $TiO₂$ structure. This modification narrows the band gap of the nanocomposite materials, leading to greater absorption in the visible-light spectral range, which accounts for a dominant part of sunlight.

Another advantage of MWCNTs is their role as an electron sink. Due to the high conductivity of MWCNTs, photogenerated electrons can easily transfer to the carbon nanotubes, which limits the interaction between electrons and holes, slowing down the charge-carrier recombination rate. This behavior was

similarly observed in the case of MWCNTs, which also served as electron-trap centers to slow the recombination rate of electron–hole e^-/h^+ pairs.¹⁶ MWCNTs possess a great number of active sites, resulting in a strong affinity for the targeted contaminant molecules on the surface of the photocatalyst.⁵⁹ The positively charged non-metal and MWCNTs also promote photocatalytic activity by increasing the rate of e-transfer to dissolved oxygen molecules by generating highly reactive superoxide ions radicals $({^{\circ}O_2}^-)$, which oxidize the pollutants. The h⁺ may oxidize OH[−] or H₂O to form the most potent and non-selective hydroxyl radical ('OH), which can degrade a wide range of organic dyes and biomolecules.

4 Conclusion

In the study, we successfully synthesized $TiO₂/MWCNTs$ nanomaterials using a hydrothermal method and assessed their photocatalytic performance in dye decomposition under simulated sunlight. The $TiO₂/MWCNTs$ nanomaterials exhibited a pore size of 4.9 nm and a BET surface area of 189.20 $\mathrm{m}^2 \mathrm{g}^{-1}$, representing an increase over previous studies. The characterization studies showed that $TiO₂$ nanoparticles were successfully decorated on the MWCNTs surface, providing sufficient active sites on the photocatalyst surface. Additionally, incorporating CNTs reduced the bandgap from 3.1 eV to 2.5 eV with 1.0% MWCNTs and 2.4 eV in 2% MWCNTs and suppressed electron–hole recombination. The effects of the adsorption time, the percentage of MWCNTs in the nanomaterial, and the catalyst dose on the photocatalytic properties of pure $TiO₂$ and TiO₂/MWCNTs were carefully studied. TiO₂/MWCNTs-2.0 was more effective for RhB degradation, boosting a rate constant of 0.0065 min⁻¹. These findings suggested that the TiO₂/MWCNTs nanocomposites had significantly enhanced photocatalytic performance compared to $TiO₂$, with rate constants of 0.0013 min⁻¹ for MB and 0.0032 min⁻¹ for RhB degradation. This modified approach can contribute to a novel approach for the rapid synthesis of nanocomposites and can be extended to the degradation of other organic pollutants.

Data availability

The data used to support the findings of this study are included in the article.

Author contributions

Conceptualization: Nhu-Bao Trinh, Thu Anh Nguyen, Sy Van Vu. Methodology and analysis: Nhu-Bao Trinh, Sy Van Vu, Hong-Gam Thi Vo, In Park, Tien Nu Hoang Lo, Thu Anh Nguyen, and Khuong Quoc Vo. Investigation: Nhu-Bao Trinh, Hong-Gam Vo Thi, In Park, Tien Nu Hoang Lo, and Thu Anh Nguyen. Writing - original draft preparation: Nhu-Bao Trinh, Thu Anh Nguyen, Khuong Quoc Vo. Writing – review and editing: Nhu-Bao Trinh, Sy Van Vu, Thu Anh Nguyen, Hong-Gam Thi Vo, and Khuong Quoc Vo. Supervision: Nhu-Bao Trinh, In Park, Khuong Quoc Vo. All authors reviewed the manuscript.

Abbreviations

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This research is funded by the University of Science VNU-HCM under grant number T2023-113.

References

- 1 K. K. Agrawal, C. Panda, and M. K. Bhuyan, Impact of Urbanization on Water Quality, in Current Advances in Mechanical Engineering, Springer Singapore, Singapore, 2021.
- 2 A. Ebenstein, The Consequences of Industrialization: Evidence from Water Pollution and Digestive Cancers in China, Rev. Econ. Stat., 2012, 94(1), 186–201.
- 3 B. Lellis, et al., Effects of textile dyes on health and the environment and bioremediation potential of living organisms, Biotechnol. Res. Innov., 2019, 3(2), 275–290.
- 4 A. Saravanan, et al., Effective water/wastewater treatment methodologies for toxic pollutants removal: Processes and applications towards sustainable development, Chemosphere, 2021, 280, 130595.
- 5 Y. Li, et al., Interactions between nano/micro plastics and suspended sediment in water: Implications on aggregation and settling, Water Res., 2019, 161, 486–495.
- 6 Y. Zhao, et al., Degradation of 2,4-dichlorophenol by carboxymethylcellulose stabilized Fe/Ni activating persulfate system: The DFT calculation and mechanistic insights, J. Environ. Chem. Eng., 2023, 11(6), 111204.
- 7 M. Hassanpour, H. Safardoust-Hojaghan and M. Salavati-Niasari, Degradation of methylene blue and Rhodamine B as water pollutants via green synthesized Co3O4/ZnO nanocomposite, J. Mol. Liq., 2017, 229, 293–299.
- 8 S. S. Naik, et al., Pulsed laser-assisted synthesis of metal and nonmetal-codoped ZnO for efficient photocatalytic degradation of Rhodamine B under solar light irradiation, Chemosphere, 2021, 274, 129782.
- 9 I. Khan, et al., Review on Methylene Blue: Its Properties, Uses, Toxicity and Photodegradation, Water, 2022, 14, 242.
- 10 Z. Tai, et al., Netted C-Doped TiO2 Mesoporous Nanostructure Decorated by Cu Nanoparticles for Photocatalytic CO2 Reduction, ACS Appl. Nano Mater., 2022, 5(12), 18070–18079.
- 11 K. Bisaria, et al., Recent advances in structural modifications of photo-catalysts for organic pollutants degradation – A comprehensive review, Chemosphere, 2021, 284, 131263.
- 12 M. Ismael, Latest progress on the key operating parameters affecting the photocatalytic activity of TiO2-based photocatalysts for hydrogen fuel production: comprehensive review, Fuel, 2021, 303, 121207.
- 13 D. Zhao, et al., Enhanced photocatalytic degradation of methylene blue under visible irradiation on graphene@TiO2 dyade structure, Appl. Catal., B, 2012, 111– 112, 303–308.
- 14 T. S. Natarajan, et al., Synthesis of multiwall carbon nanotubes/TiO2 nanotube composites with enhanced photocatalytic decomposition efficiency, Catal. Today, 2017, 282, 13–23.
- 15 H. K. Sharma, et al., CNT facilitated interfacial charge transfer of TiO2 nanocomposite for controlling the electron-hole recombination, Solid State Sci., 2021, 112, 106492.
- 16 Y. Chen, et al., In-situ synthesis of CNT/TiO2 heterojunction nanocomposite and its efficient photocatalytic degradation of Rhodamine B dye, Inorg. Chem. Commun., 2020, 119, 108071.
- 17 P. Akhter, et al., TiO2 decorated CNTs nanocomposite for efficient photocatalytic degradation of methylene blue, Diamond Relat. Mater., 2024, 141, 110702.
- 18 F. Aisien, A. Amenaghawon and E. Ekpenisi, Photocatalytic decolourisation of industrial wastewater from a soft drink company, J. Eng. Appl. Sci., 2014, 9, 11–16.
- 19 X.-H. Xia, et al., Preparation of multi-walled carbon nanotube supported TiO2 and its photocatalytic activity in the reduction of CO2 with H2O, Carbon, 2007, 45(4), 717– 721.
- 20 M. Shooshtari and A. Salehi, An electronic nose based on carbon nanotube -titanium dioxide hybrid nanostructures for detection and discrimination of volatile organic compounds, Sens. Actuators, B, 2022, 357, 131418.
- 21 M. Shaban, A. M. Ashraf and M. R. Abukhadra, TiO2 Nanoribbons/Carbon Nanotubes Composite with Enhanced Photocatalytic Activity; Fabrication, Characterization, and Application, Sci. Rep., 2018, 8(1), 781.
- 22 N. Shaari, S. H. Tan and A. R. Mohamed, Synthesis and characterization of CNT/Ce-TiO2 nanocomposite for phenol degradation, J. Rare Earths, 2012, 30(7), 651–658.
- 23 K. Bourikas, C. Kordulis and A. Lycourghiotis, Titanium Dioxide (Anatase and Rutile): Surface Chemistry, Liquid– Solid Interface Chemistry, and Scientific Synthesis of Supported Catalysts, Chem. Rev., 2014, 114(19), 9754–9823.
- 24 Y. K. Kho, et al., Photocatalytic H2 Evolution over TiO2 Nanoparticles. The Synergistic Effect of Anatase and Rutile, J. Phys. Chem. C, 2010, 114(6), 2821–2829.
- 25 A. Shafei and S. Sheibani, Visible light photocatalytic activity of Cu doped TiO2-CNT nanocomposite powder prepared by sol–gel method, Mater. Res. Bull., 2019, 110, 198–206.
- 26 A. Prathan, et al., Controlled Structure and Growth Mechanism behind Hydrothermal Growth of TiO2 Nanorods, Sci. Rep., 2020, 10(1), 8065.
- 27 B. Wang, et al., Mesoporous CNT@TiO2-C Nanocable with Extremely Durable High Rate Capability for Lithium-Ion Battery Anodes, Sci. Rep., 2014, 4(1), 3729.
- 28 A. Sacco, et al., Quantification of titanium dioxide $(TiO2)$ anatase and rutile polymorphs in binary mixtures by Raman spectroscopy: an interlaboratory comparison, Metrologia, 2023, 60(5), 055011.
- 29 A. W. Burton, et al., On the estimation of average crystallite size of zeolites from the Scherrer equation: A critical evaluation of its application to zeolites with onedimensional pore systems, Microporous Mesoporous Mater., 2009, 117(1), 75–90. **PSC** Advances 22 October 2024. Design and the model of the simulation of the
	- 30 S. Challagulla, et al., Structure sensitive photocatalytic reduction of nitroarenes over TiO₂, Sci. Rep., 2017, 7, 8783.
	- 31 L. Zhang, et al., Preparation of Polybenzimidazole/ Functionalized Carbon Nanotube Nanocomposite Films for use as Protective Coatings, Polym. Eng. Sci., 2011, 51, 1525–1532.
	- 32 W. Zhao, C. Song and P. E. Pehrsson, Water-soluble and optically pH-sensitive single-walled carbon nanotubes from surface modification, J. Am. Chem. Soc., 2002, $124(42)$, 12418–12419.
	- 33 M. Biesinger, et al., Quantitative Chemical State XPS Analysis of First Row Transition Metals, Oxides and Hydroxides, J. Phys.: Conf. Ser., 2008, 100, 012025.
	- 34 J. O. Olowoyo, et al., Insights into Reinforced Photocatalytic Activity of the CNT–TiO2 Nanocomposite for CO2 Reduction and Water Splitting, J. Phys. Chem. C, 2019, 123(1), 367–378.
	- 35 N. U. M. Nor and N. A. S. Amin, Glucose precursor carbondoped TiO2 heterojunctions for enhanced efficiency in photocatalytic reduction of carbon dioxide to methanol, J. CO2 Util., 2019, 33, 372–383.
	- 36 J. Akter, et al., Selective growth of Ti3+/TiO2/CNT and Ti3+/ TiO2/C nanocomposite for enhanced visible-light utilization to degrade organic pollutants by lowering TiO2 bandgap, Sci. Rep., 2021, 11(1), 9490.
	- 37 O. Akhavan, et al., Visible light photo-induced antibacterial activity of CNT-doped TiO2 thin films with various CNT contents, J. Mater. Chem., 2010, 20(35), 7386–7392.
	- 38 X. Peng, et al., Revisiting cocatalyst/TiO2 photocatalyst in blue light photothermalcatalysis, Catal. Today, 2019, 335, 286–293.
	- 39 V. P. Prasadam, A. M. Huerta Flores and N. Bahlawane, CNT-TiO(2) core-shell structure: synthesis and photoelectrochemical characterization, RSC Adv., 2021, 11(52), 33169–33178.
	- 40 T. Zheng, et al., Zwitterionic Polymer-Gated Au@TiO(2) Core-Shell Nanoparticles for Imaging-Guided Combined Cancer Therapy, Theranostics, 2019, 9(17), 5035–5048.
	- 41 A. K. John, S. Palaty and S. S. Sharma, Greener approach towards the synthesis of titanium dioxide nanostructures with exposed {001} facets for enhanced visible light photodegradation of organic pollutants, J. Mater. Sci.: Mater. Electron., 2020, 31(23), 20868–20882.
	- 42 E. J. Kim, et al., Carbon nanotube–titanium dioxide nanocomposite support for improved activity and stability of an iridium catalyst toward the oxygen evolution reaction, RSC Adv., 2022, 12(55), 35943–35949.
	- 43 M. Wongaree, et al., Photocatalytic performance of electrospun $CNT/TiO(2)$ nanofibers in a simulated air

purifier under visible light irradiation, Environ. Sci. Pollut. Res. Int., 2016, 23(21), 21395–21406.

- 44 Q. Yi, et al., Self-Cleaning Glass of Photocatalytic Anatase TiO2@Carbon Nanotubes Thin Film by Polymer-Assisted Approach, Nanoscale Res. Lett., 2016, 11, 457.
- 45 K. Hemalatha, et al., TiO2 coated carbon nanotubes for electrochemical energy storage, J. Mater. Chem. A, 2014, 2, 1757–1766.
- 46 L. Chougala, et al., A Simple Approach on Synthesis of TiO2 Nanoparticles and its Application in dye Sensitized Solar Cells, J. Nano-Electron. Phys., 2017, 9, 04005.
- 47 H. Fayazfar, A. Afshar and A. Dolati, Controlled Growth of Well-Aligned Carbon Nanotubes, Electrochemical Modification and Electrodeposition of Multiple Shapes of Gold Nanostructures, Mater. Sci. Appl., 2013, 04, 667–678.
- 48 Y. Zhang, et al., Growth and characterization of CNT–TiO2 heterostructures, Beilstein J. Nanotechnol., 2014, 5, 946-955.
- 49 W. Zhang, et al., Hydrothermal synthesis and photoelectrochemical performance enhancement of TiO2/ graphene composite in photo-generated cathodic protection, Appl. Surf. Sci., 2016, 382, 128–134.
- 50 N. Liu, et al., Steering Charge Directional Separation in MXenes/Titanium Dioxide for Efficient Photocatalytic Nitrogen Fixation, Catalysts, 2023, 13, 1487.
- 51 M. Kazazi, et al., TiO2/CNT nanocomposite as an improved anode material for aqueous rechargeable aluminum batteries, Solid State Ionics, 2018, 320, 64–69.
- 52 F. Huang, et al., Analysis of the degradation mechanism of methylene blue by atmospheric pressure dielectric barrier discharge plasma, Chem. Eng. J., 2010, 162(1), 250–256.
- 53 F. Wang, et al., Visible-light-induced photocatalytic degradation of methylene blue with polyaniline-sensitized TiO2 composite photocatalysts, Superlattices Microstruct., 2010, 48(2), 170–180.
- 54 Z. He, et al., Photocatalytic degradation of rhodamine B by Bi2WO6 with electron accepting agent under microwave irradiation: Mechanism and pathway, J. Hazard. Mater., 2009, 162(2), 1477–1486.
- 55 F. H. Abdulrazzak, et al., Sonochemical/hydrationdehydration synthesis of Pt—TiO2 NPs/decorated carbon nanotubes with enhanced photocatalytic hydrogen production activity, Photochem. Photobiol. Sci., 2016, 15(11), 1347–1357.
- 56 N. Van Hung, et al., Photocatalytic Degradation of Methylene Blue by Using ZnO/Longan Seed Activated Carbon Under Visible-Light Region, J. Inorg. Organomet. Polym. Mater., 2021, 31(1), 446–459.
- 57 J. Wang, et al., The Potential of Carbon-based Materials for Photocatalytic Application, Curr. Org. Chem., 2014, 18(10), 1346–1364.
- 58 A. Yürüm and G. KarakaS¸, Synthesis of Na-, Fe-, and Copromoted TiO\$_{2}\$/multiwalled carbon nanotube composites and their use as a photocatalyst, Turk. J. Chem., 2017, 41, 440–454.
- 59 D. R. Sarker, et al., P-doped TiO2-MWCNTs nanocomposite thin films with enhanced photocatalytic activity under visible light exposure, Clean. Eng. Technol., 2022, 6, 100364.