


 Cite this: *RSC Adv.*, 2024, 14, 22858

Correction and removal of expression of concern: Palladium supported on mixed-metal–organic framework (Co–Mn–MOF-74) for efficient catalytic oxidation of CO

 Reda S. Salama,^{*a} Mohammed A. Manna,^b Hatem M. Altass,^c Amr Awad Ibrahim^d and Abd El-Rahman S. Khder^{*cd}

DOI: 10.1039/d4ra90078b

rsc.li/rsc-advances

 Correction and removal of expression of concern for 'Palladium supported on mixed-metal–organic framework (Co–Mn–MOF-74) for efficient catalytic oxidation of CO' by Reda S. Salama *et al.*, *RSC Adv.*, 2021, 11, 4318–4326, <https://doi.org/10.1039/D0RA09970H>.

The authors regret that the original XRD measurements and figures had a high signal-to-noise ratio, which resulted in excessive smoothing of the data. The authors have now repeated the experiments, and have provided the replacement figures here:




Fig. 1 XRD patterns of monometallic and bimetallic MOF-74.

^aBasic Science Department, Faculty of Engineering, Delta University for Science and Technology, Gamasa, Egypt. E-mail: reda.salama@deltouniv.edu.eg; dr.reda.salama@gmail.com

^bChemistry Department, Faculty of Science, Sa'ada University, Yemen. E-mail: mnaam@yahoo.com

^cResearch Laboratories Unit, Chemistry Department, Faculty of Applied Science, Umm Al-Qura University, 21955 Makkah, Saudi Arabia. E-mail: hutass@uqu.edu.sa

^dChemistry Department, Faculty of Science, Mansoura University, Mansoura, Egypt. E-mail: amr_awad@mans.edu.eg; askhder2244@yahoo.com






Fig. 2 XRD patterns of 2 wt% Pd NPs loaded on (a) Mn-MOF-74, (b) Co_{0.5}-Mn_{0.5}-MOF-74 and (c) Co-MOF-74.

The measurements for peaks at 2θ are adjusted slightly, and the text in section 3.1 X-ray diffraction pater (XRD) should be:

Mn-MOF-74 shows characteristic peaks at 2θ equal 8.5, 9.6, 10.4, 11.9, 14.2, 15.5, 17.9, 19.6, 21.2, 27.1, 28.6, 30.6, 32.5, 37.6, 41.7, 54.3, and 57.5°. On the other hand, XRD patterns of Co-MOF-74 were recognized at 2θ equal 9.5, 10.2, 11.4, 14.7, 16.4, 18.4, 26.8, 29.5, 31.6, 33.4, 37.8, 46.5, and 59.6°, which were almost identical to the previously reported XRD pattern of Mn-MOF-74,^{41–43} and Co-MOF-74,^{44–46} respectively.

An independent expert has viewed the corrected images and raw data and has concluded that they are consistent with the discussions and conclusions presented.

This correction supersedes the information provided in the Expression of Concern related to this article.

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

