Chemical Science

EDGE ARTICLE



View Article Online View Journal | View Issue

Check for updates

Cite this: Chem. Sci., 2024, 15, 2141

All publication charges for this article have been paid for by the Royal Society of Chemistry

Received 28th September 2023 Accepted 20th December 2023

DOI: 10.1039/d3sc05146c

rsc.li/chemical-science

Introduction

Covalency versus magnetic axiality in Nd molecular magnets: Nd-photoluminescence, strong ligand-field, and unprecedented nephelauxetic effect in fullerenes NdM₂N@C₈₀ (M = Sc, Lu, Y)⁺

Wei Yang,^a Marco Rosenkranz,^a Georgios Velkos,^a Frank Ziegs,^a Vasilii Dubrovin, ^b^a Sandra Schiemenz,^a Lukas Spree, ^b^{ab} Matheus Felipe de Souza Barbosa,^a Charles Guillemard, ^b^c Manuel Valvidares,^c Bernd Büchner,^a Fupin Liu, ^b^{*a} Stanislav M. Avdoshenko^{*a} and Alexey A. Popov ^b^{*a}

Nd-based nitride clusterfullerenes NdM₂N@C₈₀ with rare-earth metals of different sizes (M = Sc, Y, Lu) were synthesized to elucidate the influence of the cluster composition, shape and internal strain on the structural and magnetic properties. Single crystal X-ray diffraction revealed a very short Nd-N bond length in NdSc₂N@C₈₀. For Lu and Y analogs, the further shortening of the Nd-N bond and pyramidalization of the NdM₂N cluster are predicted by DFT calculations as a result of the increased cluster size and a strain caused by the limited size of the fullerene cage. The short distance between Nd and nitride ions leads to a very large ligand-field splitting of Nd^{3+} of 1100–1200 cm⁻¹, while the variation of the NdM₂N cluster composition and concomitant internal strain results in the noticeable modulation of the splitting, which could be directly assessed from the well-resolved fine structure in the Nd-based photoluminescence spectra of NdM₂N@C₈₀ clusterfullerenes. Photoluminescence measurements also revealed an unprecedentedly strong nephelauxetic effect, pointing to a high degree of covalency. The latter appears detrimental to the magnetic axiality despite the strong ligand field. As a result, the ground magnetic state has considerable transversal components of the pseudospin g-tensor, and the slow magnetic relaxation of NdSc₂N@C₈₀ could be observed by AC magnetometry only in the presence of a magnetic field. A combination of the well-resolved magneto-optical states and slow relaxation of magnetization suggests that Nd clusterfullerenes can be useful building blocks for magneto-photonic guantum technologies.

The partially filled 4f-shell in lanthanide compounds is an inexhaustible source of magnetic and optical phenomena with a plethora of already practical and equally numerous prospective applications. The splitting and wavefunction composition of the ligand-field (LF) levels of the lanthanide ground-state multiplet determine the magnetic anisotropy and magnetization relaxation pathways and therefore are of paramount importance for lanthanide-based molecular magnets, such as single-molecule magnets (SMMs). Optical spectroscopy can contribute to the understanding of the SMM properties by the analysis of the fine structure of f–f transitions, in particular in low-temperature photoluminescence (PL) spectra, and by the correlation of the determined level splitting with magnetic behaviour.^{1–5} Since the first report on the Dy(DOTA) complex by Sessoli *et al.* in 2012,⁶ the vast majority of such studies were devoted to Dy^{6–17} and Yb^{8,18–25} complexes, with rare instances of Tb,^{8,26–28} Ho,²⁹ Nd,^{30–33} and Er SMMs.^{34,35} Recent trends also include a development of luminescence thermometry based on the temperature-dependent PL of Ln-SMMs,^{2,21,29,36,37} and the use of lanthanide complexes with a narrow optical linewidth for photonic quantum technologies.^{38,39}

Lanthanide-based endohedral metallofullerenes (Ln-EMFs) represent an important class of SMMs due to their air and thermal stability, ability to encapsulate Ln ions in rather unusual yet simple chemical environments with strong ligand fields, and stabilization of unconventional bonding interactions between lanthanide ions.^{40–44} Ab initio computational methods are very instrumental in predicting single-ion magnetic

[&]quot;Leibniz Institute for Solid State and Materials Research (IFW Dresden), 01069 Dresden, Germany

^bCenter for Quantum Nanoscience, Institute for Basic Science (IBS), Seoul, Republic of Korea

^cALBA Synchrotron Light Source, E-08290 Barcelona, Spain. E-mail: f.liu@ifw-dresden. de; s.avdoshenko@ifw-dresden.de; a.popov@ifw-dresden.de

[†] Electronic supplementary information (ESI) available: Additional experimental details, SC-XRD data, results of DFT and CASSCF calculations, and magnetic and spectroscopic data. CCDC 2194854. For ESI and crystallographic data in CIF or other electronic format see DOI: https://doi.org/10.1039/d3sc05146c

anisotropy in Ln-EMFs,42,45-52 but verification of such predictions by direct experimental access to the LF splitting in fullerene-based Ln-SMMs is still missing. A natural prerequisite for the realization of the Ln-based PL in Ln-EMFs is that the lowest-energy fullerene excited state should have higher energy than the lanthanide emitting state. However, the optical gaps of EMFs rarely exceed 1.5 eV. For instance, recent PL studies of the $Y_rSc_{3-r}N@I_h-C_{80}$ (x = 0-3) family revealed that the energy of the triplet emitting state (T1) in this series depends on the Sc content in the endohedral cluster and varies from 1.51 eV in YSc₂N@C₈₀ to 1.68 eV in Y₃N@C₈₀.^{53,54} As M₃N@I_h-C₈₀ clusterfullerenes have the highest optical gaps among EMFs, these energies set the upper limit for Ln-emitting states in Ln-EMFs. The possibility of Ln-based PL in Ln-EMFs is thus essentially restricted to the near-infrared (NIR) range. To date, only different types of Er-EMFs exhibited well-established Er-based NIR luminescence,55-63 including the fine structure at low temperatures in some of them, and one study reported on Tmbased NIR-PL in Tm-EMFs.⁶⁴ Unfortunately, Er and Tm tend to have easy-plane type magnetic anisotropy in EMFs42,65 and are thus not well suited for the design of EMF-SMMs. The vast majority of EMF-SMMs are based on Tb,41,42,66-70 Dy,43,49,51,71-73 and Ho,42,74 but none of them fulfills the criterion of low Lnemitting state energy, and thus their Ln-based luminescence is not to be expected unless the fullerene excited states are driven to much higher energies.

Among different lanthanides, Nd seems to be a suitable candidate for Ln-based luminescence in EMF-SMMs. The freeion energy of the Nd^{3+} NIR-emitting state, ${}^{4}F_{3/2}$ at 1.45 eV,⁷⁵ is just below the fullerene excited triplet state in M₃N@I_b-C₈₀. Nd₃N@I_h-C₈₀ cannot be produced in a reasonable yield because Nd³⁺ ions are too large,⁷⁶ but this limitation can be circumvented by using mixed-metal analogs with smaller rare-earth ions, such as NdSc₂N@I_h-C₈₀.⁷⁷ The high magnetic anisotropy in nitride clusterfullerenes is caused by the close proximity of the nitride N³⁻ to lanthanide ions, and paramagnetic NMR studies of the LnSc2N@C80 series accompanied by point-charge ligand field calculations demonstrated that Nd³⁺ in NdSc₂-N@C₈₀ has the easy-axis type anisotropy favorable for SMMs.⁶⁵ Nd-EMFs are among the least studied Ln-EMFs, and the first example of the SMM behavior of EMFs with light lanthanides, Nd₂(aC₈₀(CF₃), has only recently been reported.⁷⁸ This lack of studies echoes the situation with light-lanthanide SMMs in general, which are substantially less explored than their heavylanthanide congeners.79,80 Thus, despite the ubiquitous NIR luminescence known for Nd^{III} complexes and solids, the reports on the combination of slow relaxation of magnetization and Ndbased luminescence remain scarce.30-33,36,81-85

In this work, we synthesized a series of $NdM_2N@C_{80}$ (M = Sc, Lu, Y) molecules to study if the ligand-field experienced by the Nd^{3+} ion and SMM performance can be increased by deliberately shortening the Nd–N bond length and increasing the internal strain induced by complementary M^{3+} metal ions of a different size. By detecting the finely structured Nd-based near-infrared photoluminescence of the NdM₂N@C₈₀ series, we demonstrate the largest ligand-field splitting ever reported for Nd³⁺ in molecular compounds. Furthermore, we show that the ligand field splitting in NdM₂N@C₈₀ is indeed modulated by the increase of the size of M^{3+} ions. However, we also found that shortening of the Nd–N bond not only increases the LF splitting, but also enhances the covalency, which manifests itself in the strongest nephelauxetic effect ever observed in the PL spectra of Nd compounds. The influence of the enhanced LF and covalency on the magnetic and SMM properties of NdSc₂N@C₈₀ is evaluated by SQUID magnetometry and X-ray magnetic circular dichroism.

Synthesis and molecular structure

Synthesis and isolation

Metallofullerenes $NdM_2N@C_{80}$ (M = Sc, Y, Lu) were synthesized by the arc-discharge method using guanidinium thiocyanate as a solid source of nitrogen (see the ESI for further details of synthesis and HPLC separation, Fig. S1-S3[†]).⁸⁶ The increase of the metal size decreases the propensity of the nitride clusterfullerene formation and thus strongly affects the yield of the arc-discharge synthesis. Thus, in accordance with the ionic radii of M³⁺, the yield of NdM₂N@C₈₀ species follows Sc >> Lu > Y. The main efforts were therefore focused on NdSc₂N $(@C_{80},$ which could be accumulated in sufficient amounts for its structural, spectroscopic, and AC/DC magnetic studies. For NdLu₂N@C₈₀ and NdY₂N@C₈₀, as their yield is considerably lower, we only accumulated amounts required for spectroscopic studies. All isolated compounds were characterized by LDI-TOF mass-spectrometry to ensure their compositional purity (Fig. S1-S3[†]). The UV-Vis-NIR absorption spectra of NdM₂N@C₈₀ showed a typical absorption pattern of M₃N@C₈₀ nitride clusterfullerenes with the Ih fullerene cage isomer (Fig. S4[†]); no absorption features caused by f-f transitions of Nd³⁺ could be identified. The vibrational spectra of NdSc₂- $N@C_{80}$ (Fig. S5[†]) are also in line with the data on other M₃N@C₈₀ compounds.

Single-crystal X-ray diffraction

The molecular structure of $NdSc_2N@I_h-C_{80}$ was established by single-crystal X-ray diffraction (SC-XRD) using a co-crystal with nickel(II) octaethylporphyrin (NiOEP) grown by layering benzene solutions of the fullerene and NiOEP and allowing a slow diffusion thereof for one month. Measurements were performed at 100 K with synchrotron irradiation at the BESSY storage ring (BL14.2, Berlin-Adlershof, Germany).⁸⁷ The XDSAPP2.0 suite was employed for data processing.^{88,89} The structure was solved by direct methods and refined with SHELXL-2018.⁹⁰

The NdSc₂N@C₈₀·NiOEP·2C₆H₆ co-crystal gives a rare example of a fully ordered EMF molecule in the crystal, allowing detailed analysis of the molecular structure (Fig. 1a, S6 and Table S1[†]). The NdSc₂N cluster is planar and oriented perpendicular to the porphyrin backbone. Two Sc atoms are located above NiOEP nitrogens, while Nd is facing the opposite side of the fullerene. This orientation of the cluster is typical for MSc₂N@C₈₀ molecules in co-crystals with NiOEP.⁹¹⁻⁹⁴ Nd is coordinated to the fullerene hexagon in an η^6 -fashion with Nd–



Fig. 1 (a) NdSc₂N@C₈₀·NiOEP fragment from the NdSc₂N@C₈₀·NiOEP·2C₆H₆ single crystal. (b) NdSc₂N cluster and fullerene carbons nearest to endohedral metals; Nd–C distances in the Nd-(η^{6} -C₆) fragment are 2.527(2)–2.604(2) Å. Color code: Nd – cyan, Sc – magenta, N – blue, C – gray, and Ni – red. (c) and (d) Histograms of Nd–N (c) and Nd–C (d) bond lengths in molecular compounds deposited in the CCDC database. Insets show expansion of the ranges with the shortest bonds, and the pink line in (c) and the rectangle in (d) denote Nd–N and Nd–C bond lengths in NdSc₂N@C₈₀.

C distances of 2.527(2)-2.604(2) Å, while the shortest Sc–C bonds of 2.228(3)-2.245(3) Å are to carbons on pentagon/hexagon edges (Fig. 1b).

The large difference of ionic radii⁹⁵ of Nd³⁺ (0.983 Å) and Sc³⁺ (0.745 Å) results in a considerable distortion of the NdSc₂N cluster, with a 0.320(2) Å displacement of nitrogen from the centroid of the C₈₀ cage towards Sc ions. Sc–N bond lengths are 1.944(2) and 1.951(2) Å, while the Nd–N bond length is 2.170(2) Å. Similar structural parameters were found in LnSc₂N@C₈₀ molecules with other light lanthanides, La⁹¹ (La–N 2.196(4) Å, Sc–N 1.943(6)/1.921(7) Å) and Ce⁹³ (Ce–N 2.184(2) Å, and Sc–N 1.942(2)/1.933(2) Å). For heavier lanthanides, the decrease of the Ln³⁺ ionic radius results in a systematic shortening of the Ln–N bond and increase of Sc–N bond lengths. For instance, the Dy–N bond length in DySc₂N@C₈₀ is 2.096(6) Å, while Sc–N bonds are 1.965(6) and 1.978(6) Å.⁹⁴

To consider the structural parameters of $NdSc_2N@C_{80}$ in a broader context, we analyzed Nd–N and Nd–C bonds for all compounds deposited in the Cambridge Crystallographic Data Centre (CCDC) database. The Nd–N bond length distribution with more than 5800 entries peaks near 2.62 Å (Fig. 1c). The Nd– N bond in NdSc₂N@C₈₀ appears to have one of the shortest lengths in the whole dataset. Shorter Nd–N distances are found only in terminal imides with Nd=N double bonds (2.04–2.08 Å)⁹⁶ and some μ_2 -imide^{97,98} and amide⁹⁹ complexes (2.15–2.17 Å), all reported by Anwander *et al.*

Nd–C bond lengths fall closer to a normal range although being still rather short for their type. For comparison, the peak in the Nd–C bond length distribution (4300 entries) is near 2.75 Å (Fig. 1d). Nd–C distances in complexes with η^n -coordinated arenes span the range of 2.65–2.85 Å for variously substituted η^5 -cyclopentadienyls,^{100–102} 2.60–2.72 Å for η^8 -C₈H₈,^{103–105} and 2.845(6)–2.915(7) for η^9 -C₉H₉.¹⁰⁴ In another Nd-EMF characterized by SC-XRD, Nd@C_{2v}(9)-C₈₂, Nd is coordinated to two carbons in the η^2 -fashion, and the corresponding Nd–C bonds are rather short, 2.25–2.30 Å.¹⁰⁶

DFT calculations

An increase of the metal size in M₃N@C₈₀ molecules leads to the accumulation of the internal strain, which at first manifests itself in the unusually short M-N bonds, and then changes the M₃N cluster shape from planar to pyramidal when the M-N bonds reach their limits of shortening.107,108 The influence of the metal size on the molecular structures in the NdM2N@C80 series was analyzed with the help of DFT calculations. As the M₃N cluster can have somewhat different orientations (conformers) inside the fullerene cage, we first performed a full search of conformers for isolated NdSc2N@C80 molecules. 120 uniformly distributed NdSc2N cluster orientations inside the C80 cage were generated using Fibonacci sampling109 and used as starting geometries in DFT optimization. The procedure resulted in 6 unique conformers, of which the most stable one (conformer Sc-1) is identical to the SC-XRD structure (see Fig. S7 in the ESI[†]). Four others are only 2–3 kJ mol⁻¹ less stable, while the least stable one (Sc-6) has a relative energy of 9 kJ mol⁻¹. For all conformers, DFT calculations predict a planar NdSc₂N cluster, showing that a comparably small Sc³⁺ ion compensates for the large radius of Nd³⁺. DFT-optimized Nd–N bond lengths in all conformers are in the range of 2.22-2.23 Å and overestimated compared to the experimental value by 0.05 Å.

When Sc^{3+} is substituted by larger Lu^{3+} (0.861 Å) and Y^{3+} (0.900 Å), the Nd–N bond lengths in the most stable DFT conformers of NdLu₂N@C₈₀ (**Lu-1**) and NdY₂N@C₈₀ (**Y-1**) are shortened to 2.165 Å and 2.170 Å, respectively (Fig. S8 and S9†). These similar values for metals of different sizes indicate that the Nd–N bond has reached its shortening limit. As a result, the NdM₂N cluster cannot sustain a planar shape in NdM₂N@C₈₀ and becomes pyramidal. In different conformers of NdLu₂N@C₈₀ and NdY₂N@C₈₀, the nitrogen is elevated above the NdM₂ plane by 0.37–0.51 Å and 0.52–0.62 Å, respectively (Fig. S8 and S9†).

Photoluminescence and ligand-field splitting

Short Ln–N bonds along with the large negative charge of the nitride ion lead to a strong axial ligand field imposed on lanthanide ions in nitride clusterfullerenes. To address the size of LF splitting in Nd-EMFs experimentally, we turned to

photoluminescence spectroscopy. The photophysical behavior of $MSc_2N@C_{80}$ molecules without a partially filled 4f-shell in the metal can be illustrated by $YSc_2N@C_{80}$.⁵³ After photoexcitation and internal conversion to S₁, it undergoes a fast intersystem crossing to the T₁ state located at 1.5–1.6 eV above the ground state. However, the energy difference between S₁ and T₁ is only 0.03 eV, facilitating inversed intersystem crossing. As a result, $YSc_2N@C_{80}$ exhibits thermally activated delayed fluorescence at room temperature and down to 30 K. At lower temperature, the thermal repopulation of the S_1 state from T_1 is frozen, leaving weak phosphorescence as the only radiational decay process. 53 However, when the endohedral cluster contains Nd instead of Y, the energy can be further transferred from the fullerene-based T_1 state to the 4f-shell of the lanthanide and produce Nd-based NIR luminescence with the origin at the ${}^4F_{3/2}$ state (Fig. 2a). Indeed, our PL measurements of NdSc_2N@C_{80} showed very characteristic Nd-centered NIR luminescence with three bands caused by ${}^4F_{3/2} \rightarrow {}^4I_{9/2}, {}^4F_{3/2} \rightarrow {}^4I_{11/2},$ and ${}^4F_{3/2} \rightarrow {}^4I_{13/2}$



Fig. 2 (a) Schematic description of the Nd-based luminescence in NdM₂N@C₈₀. In non-4f M₃N@C₈₀, a fullerene-based excitation is followed by an internal conversion to the singlet state S₁, which then undergoes intersystem crossing to the triplet state T₁, and both S₁ and T₁ participate in the radiational decay in the form of thermally activated delayed fluorescence and phosphorescence.⁵³ When one M in the endohedral cluster is replaced with Nd, the energy is further transferred from the T₁ state to the 4f-shell of Nd, which then emits from the ⁴F_{3/2} state giving three nearinfrared ⁴F_{3/2} \rightarrow ⁴I_J PL bands (J = 9/2, 11/2, 13/2). Their fine structure is caused by the ligand-field splitting in each ⁴I_J multiplet, while hot bands appear when the LF-excited state in the ⁴F_{3/2} doublet has significant thermal population. (b) Luminescence spectra of solid NdM₂N@C₈₀ (M = Sc, Lu, Y) measured at 5–300 K with 50 K steps using laser excitation at 488 nm. The energy values listed on the right scale in (a) are obtained from PL measurements at 5 K, and the LF splitting of ⁴F_{3/2} is estimated from hot bands at 300 K (see Fig. 3a and S12–S17†), while conservative estimations of fullerene T₁ energies are based on the VT-PL data on YSc₂N@C₈₀ and Y₃N@C₈₀ from ref. 53 and preliminary VT-PL measurements of Lu₃N@C₈₀.

transitions (Fig. 2b). Similar luminescence spectra were also observed for $NdLu_2N@C_{80}$ and $NdY_2N@C_{80}$ (Fig. 2b). As far as we know, this is the first observation of Nd-based luminescence in endohedral metallofullerenes.

The PL spectra of NdM₂N@C₈₀ are remarkable in several aspects. First, the ${}^{4}F_{3/2} \rightarrow {}^{4}I_{I}$ PL bands are shifted from 900 nm, 1060 nm, and 1350 nm, at which they are usually centered in Nd³⁺ complexes,¹¹⁰ to longer wavelengths. Particularly, the characteristic Nd3+ emission at 1060 nm used in solid-state lasers is "missing" as the $^4F_{3/2}$ \rightarrow $^4I_{11/2}$ PL band of NdM₂N@C₈₀ occurs at 1100-1250 nm (Fig. 2b). As we discuss below, this shift of PL bands is the manifestation of a strong nephelauxetic effect. Second, the bands have atypical intensity distribution. Normally, the ${}^{4}F_{3/2} \rightarrow {}^{4}I_{11/2}$ band is the strongest one, followed by ${}^{4}F_{3/2} \rightarrow {}^{4}I_{9/2}$ with 2-4 times lower intensity, while the ${}^{4}F_{3/2} \rightarrow {}^{4}I_{13/2}$ band is the weakest. In NdM₂N@C₈₀, the latter is also very weak, but the ${}^{4}F_{3/2} \rightarrow {}^{4}I_{9/2}$ band is considerably stronger than ${}^{4}F_{3/2} \rightarrow {}^{4}I_{11/2}$. Third, the luminescence lifetimes of NdM2N@C80 are very short. PL lifetimes in Nd complexes are usually found in the 0.2-2 µs range. For the polycrystalline film of NdSc₂N@C₈₀, the PL decay is biexponential with the lifetimes of 4.5 ns/13 ns at room temperature, and 4 ns/19 ns between 200 and 5 K, with the longer component having the main contribution with a weight of 80% (Fig. S10[†]). To check if this fast decay can be caused by intermolecular Nd… Nd quenching, the fullerene was diluted in a polystyrene matrix. In the latter, the decay was mono-exponential with the lifetime near 20 ns. Polycrystalline NdLu₂N@C₈₀ and NdY₂N@C₈₀ showed monoexponential PL decay with very weak temperature dependence and lifetimes of 10.5-11.0 ns and 9.0-9.5 ns, respectively (Fig. S11[†]). These short lifetimes suggest a low quantum yield and explain the weak PL intensity of $NdM_2N@C_{80}$. Fourth, each PL band of $NdM_2N@C_{80}$ exhibits unusually broad and well-resolved fine structure already at room temperature. Upon cooling, the narrowing of the lines and increase of their intensity took place down to 50–100 K, while further cooling did not bring considerable changes in the spectra (Fig. 2b and S12–S17[†]).

LF splitting in PL spectra. The fine structure of PL bands is of primary interest for this work since it represents the LF splitting of ${}^{4}I_{I}$ multiplets. In the ${}^{4}F_{3/2} \rightarrow {}^{4}I_{I}$ band, one can expect (2J+1)/2lines corresponding to the number of Kramers doublets (KDs) in the ⁴I₁ multiplet. However, when not only KD1, but also KD2 of the emitting ⁴F_{3/2} state has a significant population, transitions originating from ${}^{4}F_{3/2}$ (KD2) and known as hot bands can increase the number of detectable PL features (Fig. 2a). Further complication may be caused by vibronic transitions, involving vibrational excitations in emitting or final states. Finally, different sites, by which we understand molecules with different surroundings or with different orientations of the endohedral cluster (conformers), may also have unequal energy levels and thus multiply the number of lines in PL spectra. To aid the interpretation of PL spectra, we performed variabletemperature measurements (Fig. 2 and 3 and S12-S17[†]) since hot bands decrease their intensity and eventually disappear upon cooling. Likewise, zero-phonon electronic transitions tend to exhibit pronounced narrowing at low temperatures, while the accompanying phonon sidebands usually remain broader.

At low temperatures, the ${}^{4}F_{3/2} \rightarrow {}^{4}I_{9/2}$ band of NdSc₂N@C₈₀ is reduced to seven narrow peaks, of which three are standalone and four form two doublets with the splitting of 70 and 50 cm⁻¹ (Fig. 3a). We assign these peaks to five pure electronic ${}^{4}F_{3/2}(KD1) \rightarrow {}^{4}I_{9/2}(KDn)$ transitions. The splitting of KD3 and KD5 features into doublets is likely caused by a coexistence of



Fig. 3 The fine structure of (a) ${}^{4}F_{3/2} \rightarrow {}^{4}I_{9/2}$ and (b) ${}^{4}F_{3/2} \rightarrow {}^{4}I_{11/2}$ photoluminescence bands of NdM₂N@C₈₀ (M = Sc, Lu, Y) measured at 5 K and 300 K (250 K). Vertical bars are the CASSCF-computed energies of LF states in ${}^{4}I_{9/2}$ (a) and ${}^{4}I_{11/2}$ (b) multiplets in Sc-3, Lu-3, and Y-3 conformers scaled by 1.15 to account for the systematic underestimation. The peaks assigned to pure electronic ${}^{4}F_{3/2}$ (KD1) $\rightarrow {}^{4}I_{3}$ (KDn) transitions are labeled with \bullet and broad peaks with uncertain assignment to KD2 are labelled with (\bullet). The ΔE scale for each NdM₂N@C₈₀ is given *versus* the peak of the lowest-energy Kramers doublet in the ${}^{4}I_{9/2}$ or ${}^{4}I_{11/2}$ multiplet. In (a), the peaks at negative ΔE in 300 K spectra labelled with "n" are hot bands caused by the ${}^{4}F_{3/2}$ (KD2) $\rightarrow {}^{4}I_{9/2}$ (KD1) transition of each NdM₂N@C₈₀, which allow estimation of ${}^{4}I_{12}$ in the ${}^{4}F_{3/2}$ multiplet. The intensity of 5 K and higher-temperature spectra is given off-scale (see Fig. 2b and S12–S17† for the real relative intensity at different temperatures). To guide the eye, the vertical dashed line marks the highest energy KD in the ${}^{4}F_{3/2} \rightarrow {}^{4}I_{9/2}$ band (NdY₂N@C₈₀) and in the ${}^{4}F_{3/2} \rightarrow {}^{4}I_{11/2}$ band (NdLu₂N@C₈₀).

two emitting sites,^{53,111} but the lack of analogous splitting for other KDs is not clear. Two broad peaks located between KD1 and KD2, at $\Delta E = 115$ and 370 cm⁻¹, can be tentatively assigned to vibronic transitions, but may also correspond to different conformers (*vide infra*). The low-*T* PL spectrum thus allows determination of experimental $\Delta_{1,2}$ and Δ_{LF} values in NdSc₂-N@C₈₀ as 536 cm⁻¹ and 1061/1110 cm⁻¹. The roomtemperature PL spectrum also features a peak at $\Delta E =$ -410 cm⁻¹, which disappears upon cooling (Fig. 3a). This hot band is likely caused by the ${}^{4}F_{3/2}(KD2) \rightarrow {}^{4}I_{9/2}(KD1)$ transition and thus allows estimation of the LF splitting in the ${}^{4}F_{3/2}$ multiplet.

The interpretation of the ${}^{4}F_{3/2} \rightarrow {}^{4}I_{9/2}$ PL bands of NdLu₂-N@C₈₀ and NdY₂N@C₈₀ is more straightforward as they show neither pronounced vibronic features nor additional splitting (Fig. 3 and Table S2^{\dagger}). The five peaks in low-*T* spectra are thus readily assigned to five KDs of the ⁴I_{9/2} multiplet. The only peculiarity is the strongly enhanced linewidth of the KD2 peak, which is still well-defined for NdLu₂N@C₈₀, but is barely discernible for NdY₂N@C₈₀. Such a strong broadening indicates that this state experiences very fast relaxation even at 5 K. The LF splitting of ⁴I_{9/2} in the NdM₂N@C₈₀ series increases systematically with the size of the M ion from NdSc₂N@C₈₀ (Δ_{LF} = 1111 cm⁻¹) to NdLu₂N@C₈₀ (1161 cm⁻¹) and further to $NdY_2N@C_{80}$ (1188 cm⁻¹). The LF splitting of the ${}^4F_{3/2}$ multiplet is also larger for Lu and Y and amounts to 440 cm⁻¹ versus 410 cm⁻¹ for Sc. At the same time, $\Delta_{1,2}$ decreases from 536 cm⁻¹ (Sc) to 510 cm⁻¹ (Lu) and 420 cm⁻¹ (Y). The energies of other KDs also vary considerably in the NdM₂N@C₈₀ series. Besides, not only the energies, but also the intensities of transitions are quite different from Sc to Lu to Y, which indicates that the state composition is also considerably affected by the internal strain.

Thus, analysis of the ${}^4\mathrm{F}_{3/2} \rightarrow {}^4\mathrm{I}_{9/2}$ PL band demonstrates that enclosing Nd3+ in a molecular environment with a very short Nd-N bond and further increasing the internal strain by changing the size of the NdM2N cluster indeed result in a record-high LF splitting in NdM2N@C80 compounds exceeding 1100 cm⁻¹. For comparison, a resolved structure of LF levels allowing estimation of $\Delta_{\rm LF}$ for the Nd-⁴I_{9/2} multiplet was observed in the optical spectra of five Nd-SMMs, including NdTp₃,^{112,113} acetato-diphenoxo bridged {ZnNd} complex,³⁰ dinuclear {Nd₂} complexes with 9-anthracenecarboxyl and 2,2'bipyridine³¹ or phenanthroline³² ligands, and in the Nd complex with N-(diphenylphosphoryl)pyrazine-2-carboxamide.33 None of them had the $\Delta_{\rm LF}$ exceeding 460 cm⁻¹. Among the Nd-SMMs studied ab initio, Δ_{LF} values exceeding 500 cm⁻¹ were reported only for three Nd-SMMs: metallocenium complex [Nd(Cp^{ttt})₂] $B(C_6F_5)_4$ ($\Delta_{LF} = 672 \text{ cm}^{-1}$ and $\Delta_{1,2} = 130 \text{ cm}^{-1}$),¹⁰⁰ Nd complex with equatorial metallacrowns and axial n-Bu₃PO ligands in hexagonal bipyramidal coordination ($\Delta_{\rm LF} = 586 {\rm ~cm^{-1}}$ and $\Delta_{1,2}$ = 104 cm⁻¹),¹¹⁴ and (COT)Nd(Cp^{ttt}) sandwich complex (Δ_{LF} = 545 cm⁻¹ and $\Delta_{1,2} = 78$ cm⁻¹).¹¹⁵ Among non-SMMs, a very large LF splitting almost rivaling the results of this work was determined by Amberger et al. based on absorption and PL spectra and phenomenological crystal-field modelling in some tris(η^5 cyclopentadienyl)Nd(III) complexes, such as Nd(η^{5} -C₅Me₅)₃ (Δ_{LF} $= 861 \text{ cm}^{-1}$,¹¹⁶ Nd(η^{5} -C₅Me₄H)₃ ($\Delta_{LF} = 1000 \text{ cm}^{-1}$),¹¹⁷ Nd(η^{5} -

 $C_5H_4{}^tBu)_3$ and $Nd(\eta^5-C_5H_4SiMe_3)_3$ (in both, $\Delta_{LF} = 1030 \text{ cm}^{-1}$).¹¹⁸ The SMM properties of these complexes were not studied, but the ground state with the dominating $|\pm 5/2\rangle$ term (see the ESI for results of *ab initio* calculations†) suggests that the slow relaxation of magnetization can hardly be expected.

In addition to the ground-state LF structure, well-resolved PL spectra also enable analysis of the ${}^4I_{11/2}$ multiplet. For NdSc₂-N@C₈₀, the experimental KD2 is found at 491 cm⁻¹, whereas the overall $\Delta_{LF}({}^4I_{11/2})$ splitting is 880 cm⁻¹, considerably smaller than $\Delta_{LF}({}^4I_{9/2})$ of 1111 cm⁻¹. Broad features in the gap between KD1 and KD2 at 50 cm⁻¹ and 280 cm⁻¹ can be preliminary assigned to vibronic transitions. In NdLu₂N@C₈₀ and NdY₂N@C₈₀, the ${}^4F_{3/2} \rightarrow {}^4I_{11/2}$ band is dominated by the ${}^4F_{3/2}(KD1) \rightarrow {}^4I_{11/2}(KD1)$ transition, whereas other features have much lower intensity (Fig. 2b and 3b). Similar to the ${}^4F_{3/2} \rightarrow {}^4I_{9/2}$ band, the ${}^4I_{11/2}(KD2)$ peaks appear strongly broadened, which makes their assignment less certain. The ${}^{}\Delta_{LF}({}^4I_{11/2})$ splitting of 920 cm⁻¹ in NdLu₂N@C₈₀ and 900 cm⁻¹ in NdY₂N@C₈₀ exceed that in NdSc₂N@C₈₀.

A complete set of ${}^{4}F_{3/2} \rightarrow {}^{4}I_{13/2}$ transitions can be identified only for NdSc₂N@C₈₀ (Fig. 2b and Table S2†). Seven KDs of the ${}^{4}I_{13/2}$ multiplet span the energy range of 890 cm⁻¹ and show similar motifs to the ${}^{4}F_{3/2} \rightarrow {}^{4}I_{11/2}$ band with a large gap between KD1 and KD2 of 530 cm⁻¹ and a dense group of other KDs at higher energy. For NdLu₂N@C₈₀ and NdY₂N@C₈₀, the position of the KD1 peak cannot be determined because of its very low intensity (Fig. 2b), which prevents further analysis of the LF splitting in ${}^{4}I_{13/2}$.

Ab initio calculations of LF splitting. To analyze the composition of LF-split states, we performed ab initio calculations at the CASSCF(3,7)/RASSI level. While the lowest-energy conformer of NdSc₂N@C₈₀ corresponds to the SC-XRD structure in the NdSc₂N@C₈₀·Ni(OEP) co-crystal (Fig. S7[†]), the energy span of only 9 kJ mol⁻¹ predicted by DFT for other conformers is quite small, and other conformers can also be present in powder samples studied by PL (and later by magnetometry). Therefore, calculations were performed for all six DFTcomputed conformers of NdSc2N@C80. Our earlier ab initio studies of LF in conformers of various Dy-SMMs showed that the influence of the lanthanide coordination to the fullerene cage is noticeable but not decisive.^{51,119,120} Unexpectedly, the situation found here for NdSc2N@C80 is quite dissimilar. The $\Delta_{\rm LF}$ splitting of the ${}^{4}I_{9/2}$ multiplet in different conformers varies from 690 to 1018 cm⁻¹, and even larger relative variation is found for $\Delta_{1,2}$, which spans from 80 to 470 cm⁻¹ (Fig. 4 and Table S3[†]).

The variation of the LF splitting can be correlated with the Nd-fullerene coordination motif (Fig. 4). The smallest $\Delta_{1,2}$ of 80 cm⁻¹ is found for conformers **Sc-1** and **Sc-4**, in which Nd is coordinated to the center of a fullerene hexagon in an η^6 -manner. Even a small shift of Nd from the hexagon center toward a C–C bond yields a 3-fold increase of $\Delta_{1,2}$ in **Sc-2** (hapticity η^4), while the more pronounced shift toward one of the carbon atoms increases $\Delta_{1,2}$ to 407 cm⁻¹ in **Sc-5** (η^3) and further to 467 cm⁻¹ in **Sc-3** (η^3). The largest $\Delta_{1,2}$ and Δ_{LF} values are achieved when Nd faces one carbon atom in **Sc-6** (hapticity between η^1 and η^3). The deviation of the quantization axis of

View Article Online Chemical Science



Fig. 4 Coordination of Nd atoms to the closest carbon atoms in six conformers of NdSc₂N@C₈₀, their geometrical Nd–N axes (thin blue lines) and g_z axes of the two lowest-energy Kramers doublets from CASSCF calculations (KD1 – red lines and KD2 – green lines). Color code: Nd – cyan, N – blue, and C – light cyan ($d_{Nd-C} \le 2.6$ Å) or light gray ($d_{Nd-C} \ge 2.6$ Å). Nd–C distances shorter than 2.6 Å are shown as bonds. Also listed for each conformer are its relative energy from DFT calculations and $d_{1,2}$ and d_{LF} splitting from CASSCF calculations.

the ground-state Kramers doublet (KD1) from the Nd–N bond axis (Fig. 4) is another manifestation of the strong influence of the Nd-fullerene coordination. The two axes coincide only in **Sc-6**, while the angle between them in other conformers reaches 13°.

The comparison of theoretical LF splitting to the fine structure of PL spectra shows that only conformers **Sc-3** and **Sc-6** agree reasonably well with experimental data (Fig. 5 and S18†), while predictions for other conformers, including the lowestenergy **Sc-1**, are far off. Thus, it appears that only the conformers, in which Nd is coordinated close to one C atom in the $\eta^1-\eta^3$ manner, contribute to the fine structure of PL spectra. The only features which might be attributed to other



Fig. 5 The fine structure of ${}^{4}F_{3/2} \rightarrow {}^{4}I_{9/2}$ photoluminescence bands of NdSc₂N@C₈₀ measured at 5 K compared to LF splitting of the ${}^{4}I_{9/2}$ multiplet in six conformers of NdSc₂N@C₈₀ from CASSCF calculations (see Tables S3b–S3f† for numerical values).

conformers of NdSc₂N@C₈₀ are broad peaks in the gap between 0 and 500 cm⁻¹ (KD1 and KD2, Fig. 5), for which our preferred assignment is vibronic transitions. It is hard to determine at this moment whether other conformers have more efficient non-radiative decay channels and do not show up in the spectra, or the CASSCF predictions for these conformers are incorrect, or they are destabilized in powder samples. The technical aspects of CASSCF computations also indicate some untrivial behavior. For some conformers, the CASSCF wavefunction was found seamlessly, while for others, they were sensitive to initial guesses, and it took an effort to converge the wavefunction to a decent 4f-pure state.

Following the calculation results on NdSc₂N@C₈₀, for NdLu₂N@C₈₀ and NdY₂N@C₈₀ we performed CASSCF calculations for two representative conformers, conformer Lu(Y)-1 with η^6 -type coordination of Nd, and conformer Lu(Y)-3 with η^3 pentagon-coordinated Nd (see Fig. S19†). The difference between LF splitting of conformers is also considerable but less pronounced than in NdSc₂@C₈₀ (Tables S7 and S8†), and the conformer Lu(Y)-3 provides better match to the fine structure in experimental PL spectra (Fig. 3). Remarkably, while the total LF splitting in NdM₂N@C₈₀ increases with the size of M, the $\Delta_{1,2}$ value exhibits the opposite trend and shows a gradual decrease, which is correctly captured by CASSCF calculations for Lu(Y)-3 (Fig. 3).

LF splitting, magnetic axiality, and covalency. The aims we followed in creating the strongly strained environment around the Nd–N bond was to achieve a large LF splitting and enhanced magnetic axiality. While the LF splitting in NdM₂N@C₈₀ is indeed unprecedentedly large, the problem of axiality appears to be more complicated. For the subsequent analysis, we use conformer Sc-3. Table 1 summarizes the energies of its Kramers doublets (KDs) in the ground-state Nd³⁺-⁴I_{9/2} multiplet, along with their composition in the $|m_{J}\rangle$ basis and principal components of pseudospin g-tensors. Analogous data for other conformers can be found in Tables S3, S7, and S8 in the ESI.† Aside from the systematic underestimation of the LF splitting by 10–15%, the calculated spectrum agrees well with the

Table 1	jand-field splitting of the Nd ³⁺ - ⁴ I _{9/2} multiplet and pseudospin g-tensors of Kramers doublets (KDs) in NdSc ₂ N@C ₈₀ (conformer S c	c-3)
comput	at the CASSCF/RASSI level and with the point-charge model	

KD	Exp. E^a cm ⁻¹	Calc. $E \mathrm{cm}^{-1}$	% Composition in the $ m_j\rangle$ basis $(J = 9/2)^{b}$	g _x	<i>g</i> _y	ġz	$\varphi^{\circ c}$
			CASSCF/RASSI				
KD1	0	0	$85 \pm9/2\rangle + 7 \pm5/2\rangle + 6 \pm3/2\rangle$	0.0371	0.0445	5.6890	_
KD2	536	467	$48 \pm 5/2\rangle + 25 \pm 7/2\rangle + 19 \pm 3/2\rangle + 8 \pm 1/2\rangle$	0.5312	1.3555	3.1828	21
KD3	693/763	648	$31 \pm 3/2\rangle + 29 \pm 5/2\rangle + 19 \pm 7/2\rangle + 14 \pm 9/2\rangle$	0.0369	1.0730	3.6643	25
KD4	923	786	$48 \pm7/2\rangle + 30 \pm3/2\rangle + 14 \pm1/2\rangle + 8 \pm5/2\rangle$	2.0524	0.3009	3.7618	55
KD5	1061/1110	968	$70 \pm 1/2\rangle + 14 \pm 3/2\rangle + 8 \pm 5/2\rangle + 8 \pm 7/2\rangle$	4.3734	2.4200	0.4013	7
			Point-charge model				
KD1	0	0	$99.9 \pm 9/2\rangle$	0.0000	0.0000	6.5437	_
KD2	536	466	$99.6 \pm7/2\rangle$	0.0013	0.0014	5.0823	3
KD3	693/763	643	$99.0 \pm5/2\rangle$	0.0937	0.1002	3.6158	1
KD4	923	770	$95.0 \pm 3/2\rangle + 4.4 \pm 1/2\rangle$	1.4408	1.4927	2.0604	7
KD5	1061/1110	867	$94.8 \pm 1/2\rangle + 4.5 \pm 3/2\rangle$	5.0352	2.0948	0.6166	0

^{*a*} Experimental values are from photoluminescence measurements at 5 K (see Fig. 3a). ^{*b*} For each KD, 4 main terms exceeding 5% are shown in the descending order of their contribution. ^{*c*} φ is the angle between the g_z direction of the given KD and that of the ground state KD1.

experimental data for all spectrally characterized multiplets (Fig. 3 and S18[†]). Besides, the *ab initio* $\Delta_{1,2}$ value computed for **Sc-3** in the ⁴F_{3/2} multiplet is 401 cm⁻¹, also in good agreement with the experiment.

The strongly axial LF for 4f-prolate Kramers ions (Ce³⁺, Nd³⁺, and Dy^{3+}) normally leads to the high purity of KDs in the $|m_l\rangle$ representation, with the ground state featuring the largest J_z projection. It also implies that pseudospin g-tensors of KDs have small transversal $g_{x,y}$ components, colinear principal g_z axes, and g_z values close to $2|m_l|g_l$, where g_l is the Landé g-factor. The description we infer from ab initio calculations of Sc-3 is quite different (Table 1; see Table S3[†] for other conformers). KD1 indeed resembles the $|\pm 9/2\rangle$ state with 85% contribution and the quantization axis aligned along the Nd-N bond with a deviation of 4.1°. The g_z and $g_{x,y}$ values of KD1 are 5.689 and near 0.04, respectively, which can be compared to $g_z = 6.545$ and $g_{\rm x,y} = 0$ expected for the pure $|\pm 9/2\rangle$ doublet. However, higherenergy KDs have strongly mixed $|m_I\rangle$ composition and enhanced $g_{x,v}$ components, while their g_z axes are rotated away from that of KD1. In contrast, the ab initio description of the isostructural DySc2N@C80 is entirely consistent with expectations for a strongly axial ligand field.45,120 The ground state KD1 has 99.7% weight of the $|\pm 15/2\rangle$ state and $g_{x,y}$ is less than 10^{-4} , while $g_z = 19.84$ (*versus* 20.00 expected for the pure $m_J = \pm 15/2$ state).¹²⁰ The next three KDs of DySc₂N@C₈₀ also have high contribution of one of the $|\pm m_I\rangle$ states (>80%), and the principal z axes of their pseudospin g-tensors are nearly collinear. The overall LF splitting in DySc₂N@C₈₀ is 1284 cm⁻¹.

Thus, the molecular environment, in which the strong axiality is expected and indeed realized for Dy, produces quite different properties for Nd. We can recall that Nd³⁺ has considerably larger Steven's factor γ_j (-38×10^6) than Dy³⁺ (1.03×10^6), which increases the weight of $B_q^{\ k}$ terms with k = 6 in the ligand field. While for DyM₂N@C₈₀ molecules, $B_q^{\ 2}$, $B_q^{\ 4}$, and $B_q^{\ 6}$ contribute 65–80%, 5–10%, and 10–25% to *ab initio* computed LF splitting, respectively, in NdM₂N@C₈₀ the balance changes to similar contributions of $B_q^{\ 2}$ and $B_q^{\ 6}$ near 40–45%,

while B_q^4 terms cover 10–15%. The enhanced B_q^6 weight implies the higher sensitivity of the Nd³⁺ ligand field to the environment, yet the deviation from axiality in NdM2N@C80 is too strong and cannot be explained by the γ_i factor alone. To understand if low symmetry or unobvious peculiarities of the electrostatic distribution may play a role, we obtained the LF parameters of NdSc₂N@C₈₀ using a point-charge model with LoProp¹²¹ charges from CASSCF calculations scaled by a factor of 1.08 to reproduce the *ab initio* $\Delta_{1,2}$ value. The KD energies calculated with such a LF Hamiltonian are not far from ab initio LF energies (Table 1), but the states are described by almost pure $|m_l\rangle$ functions, and KD1-KD3 have g_z values close to $2|m_J|g_I$. Similar results with a slightly higher degree of m_T mixing were obtained when the model was adjusted by treating the Nd³⁺ ion quantum chemically at the CASSCF/RASSI level, while keeping point charges instead of all other atoms (Table S5[†]). From these models, we infer that the electrostatic environment around Nd³⁺ indeed favors LF axiality, while deviations from axiality in NdSc₂N@C₈₀ should be caused by non-electrostatic contributions, such as the covalency.122-124 Indeed, when CASSCF/RASSI computations were performed for the (NdSc₂N)⁶⁺ cluster augmented with point charges mimicking the carbon atoms of the fullerene cage, a considerable state mixing was observed (Table S5c[†]). We thus conclude that the expansion of the valence space from Nd³⁺ through NdSc₂N⁶⁺ to $NdSc_2N@C_{80}$ results in the systematic increase of the m_I mixing in Nd KDs and decrease of the axiality. Significant changes of the LF splitting induced by subtle variation of the local Nd environment in NdSc2N@C80 conformers also cannot be expected based on simple electrostatic considerations. Pointcharge calculations for the conformer Sc-1 do not follow CASSCF results and predict similarly large KD2 energy as in Sc-3 (compare values in Table S5[†]). These facts highlight the importance of valence interactions and show that pure electrostatic models would be inappropriate for the description of Nd-EMF SMMs.

Comparison to other coordination environments, in which heavy lanthanide analogs exhibit very high magnetic axiality, reveals that the situation found here for NdSc₂N@C₈₀ is not unique for fullerenes but rather describes a common behaviour of Nd in molecular magnets. For instance, $[Nd(H_2O)_5L_2]^{3+}$ complexes with pentagonal bipyramidal coordination and axial phosphine oxide ligands,125,126 or Nd metallocenium complexes,¹⁰⁰ all have the ground state KD with enhanced $|\pm 9/2\rangle$ contribution (86-99%), but their higher-energy KDs are mixed considerably in the $|m_I\rangle$ representation. Likewise, the g_{xy} values of 0.01-0.02 found in KD1 of these complexes are small in comparison to g_z values near 6.3, but appear quite large when compared to transversal g-tensor components of 10⁻⁴ in KD1 of similar Dy complexes. In other Nd-SMMs, for which ab initio calculations were performed, the degree of axiality is considerably smaller.

Nd–N distance and LF splitting. The discussion above showed that by creating unusually short Nd–N bonds and a highly strained endohedral environment, we achieved large LF splitting but simultaneously increased the degree of covalency and decreased the magnetic axiality. As coordination of Nd to the fullerene π -system also played a considerable role, it is hard to disentangle it from the influence of Nd–N bonding. To study the isolated effect of the extreme shortening of the Nd–N bond, we used the NdN molecule as a toy system and computed LF splitting at different Nd–N distances with a point charge model and *ab initio* at the CASSCF(3,7)/RASSI level.

For the linear NdN molecule with the axial ligand field of $C_{\infty v}$ symmetry, the LF Hamiltonian should include only B_0^2 , B_0^4 , and B_0^6 terms, while LF states are described by pure $|m_j\rangle$ functions.

At a Nd–N distance of 2.3 Å, the *ab initio* computed LF splitting is 726 cm⁻¹, and the state energies increase in the descending order of $|m_I|$ (Fig. 6a). The structure of states and their energies are reproduced closely by a point charge model using a LoProp charge of nitrogen (-1.513 e) scaled by a factor of 1.08 (Fig. 6b). The same factor was used then to scale the LoProp charges of nitrogen for point-charge computations at shorter Nd-N distances. According to the electrostatic model, a stepwise decrease of the Nd-N distance from 2.3 Å to 1.55 Å does not change the order of states and only gradually increases the LF splitting to 2836 cm⁻¹, while the energies of all LF states increase monotonously (Fig. 6b). A very different Nd-N distance dependence emerges from CASSCF calculations. The energies of $|\pm 7/2\rangle$ and $|\pm 1/2\rangle$ doublets relative to $|\pm 9/2\rangle$ pass through a maximum and then decrease, and $|\pm 3/2\rangle$ also changes a curvature at short Nd–N, and only $|\pm 5/2\rangle$ grows continuously in the whole range. The order of $|m_I\rangle$ states thus changes several times, and the overall LF splitting at 1.55 Å is almost twice smaller than predicted by the point-charge model (Fig. 6a).

From the contributions of *ab initio* computed $B_q^{\ k}$ terms to LF splitting provided by the Single_aniso code,^{122,127} we infer that the weight of the B_0^2 term, which amounts to 87% at 2.3 Å, decreases to 49% at 1.55 Å, and the weight of $B_0^{\ 6}$ increases from 7% at 2.3 Å to 38% at 1.55 Å, while the sign of $B_0^{\ 6}$ changes from negative to positive below 2.1 Å (in the point-charge model, $B_0^{\ 6}$ is negative through the whole range). Furthermore, the LF Hamiltonian, comprising only $B_0^{\ 2}$, $B_0^{\ 4}$, and $B_0^{\ 6}$, cannot reproduce the LF splitting at short Nd–N distances, and requires addition of $B_0^{\ 8}$. The weight of the latter increases from negligible 0.05% at 2.3 Å to significant 5.5% at 1.55 Å (Fig. 6a). As $B_q^{\ k}$



Fig. 6 (a) LF splitting in the NdN molecule computed at the CASSCF/RASSI level as a function of the Nd–N distance and the sum of B_0^2 , B_0^4 , and B_0^6 contributions to the total LF splitting (cyan spheres with the dashed curve and the scale on the right side); (b) LF splitting in the NdN molecule computed with the point charge model and scaled LoProp atomic charge of N at the same Nd–N distances as in (a); (c) 4f-electron density in Nd–N built upon orbitals from CASSCF(3, 7) calculations, and concentric isosurfaces are plotted at the values of (from inner to outer) 0.25, 0.05, 0.01, and 0.002 a.u.; to guide the eye, the rightmost figure shows a circle centered on the Nd atom and plotted with the gray dashed line.

terms with k > 6 should vanish for pure f orbitals, their non-zero contribution serves as a diagnostic criterion for the breakdown of the assumption of the isolated spherically shaped 4f shell.¹²² Indeed, the shape of 4f-electron density distribution changes from nearly spherical at 2.3 Å to a considerably elongated one at short Nd–N distances (Fig. 6c). This naturally leads to the notion of 4f AOs mixing with other orbitals and the overall increase of the covalency as the Nd–N distance shrinks. Of course, the distance of 1.55 Å is unrealistically short, but it serves here only for a clear-cut demonstration, whereas the effect is already present at more realistic distances (Fig. 6c). Importantly, *ab initio* calculations of NdM₂N@C₈₀ similarly showed that the LF Hamiltonian including B_q^{k} terms with $k \leq 6$ recovers only ~95% of the *ab initio* LF splitting, while covering the remaining 5% requires B_q^{8} terms.

Nephelauxetic effect. The enhanced covalency of the Nd bonding with surrounding atoms in NdM₂N@C₈₀ has an experimental manifestation in the aforementioned red shift of ${}^{4}\mathrm{F}_{3/2} \rightarrow {}^{4}\mathrm{I}_{J}$ PL bands when compared to other Nd compounds. From the KD1 line of the ${}^{4}\mathrm{F}_{3/2} \rightarrow {}^{4}\mathrm{I}_{9/2}$ band in the low-temperature PL spectrum, the energy of the emitting state, KD1 of ${}^{4}\mathrm{F}_{3/2}$, is determined to be 10 900–11 000 cm⁻¹, which is lower than the usual energy of the ${}^{4}\mathrm{F}_{3/2}$ multiplet by around 1100 cm⁻¹. Such a covalency-induced reduction of the excitation energies in coordination compounds of transition metals and lanthanides is known as the nephelauxetic effect.¹²⁸

Numerical representation of the nephelauxetic effect is often given by nephelauxetic parameters $\beta_{\rm F} = F^2(\text{compound})/F^2(\text{free}$ ion), where F^2 is the second-order Slater integral describing interelectron repulsion, or $\beta' = \zeta_{4\rm f}/\zeta_{4\rm f}$ (free ion), where $\zeta_{4\rm f}$ is the Lande spin–orbit coupling constant. The degree of covalency, defined as an admixture of ligand orbitals to f-like orbitals, is sometimes estimated as $b^{0.5} = [(1 - \beta)/2]^{0.5}$, although it appears somewhat ambiguous because $\beta_{\rm F}$ and β' can be quite different, F^2 being more sensitive to the bonding nature.^{129,130} For

instance, the energy differences between ${}^{4}I_{J}$ levels are mainly determined by ζ_{4f} , and since the gaps between ${}^{4}I_{J}$ levels in the NdM₂N@C₈₀ series are similar to other Nd compounds, we can conclude that ζ_{4f} is not strongly affected. The energy differences between multiplets with different *L*, on the other hand, are more sensitive to inter-electron repulsion parameters, and the reduced ${}^{4}F_{3/2}$ energy in NdM₂N@C₈₀ indicates that F^{2} is significantly modified.

Experimentally, ζ_{4f} , F^2 and other F^k integrals can be determined by fitting the Hamiltonian, comprising free-ion and crystal-field terms, to spectroscopic data. As such a Hamiltonian includes a large number of parameters, extended data on many multiplets in a broad energy range are required for a reliable fitting. In the absence of such data, which is the case for NdM₂N@C₈₀ and the majority of Nd-SMMs, a simplified spectroscopic nephelauxetic parameter β_{spec} based on the transition energy between selected multiplets can be used: $\beta_{\text{spec}} =$ ΔE (compound)/ ΔE (standard). For the following discussion, we define β_{spec} as the energy difference between barycenters of ${}^{4}I_{9/2}$ and ${}^{4}F_{3/2}$ multiplets divided by the free ion value⁷⁵ $\Delta E({}^{4}F_{3/2} - {}^{4}I_{9/2})$ = 11 699 cm⁻¹. When the ${}^{4}F_{3/2} \rightarrow {}^{4}I_{9/2}$ PL band is not resolved into LF components, as is the case for many Nd-SMMs, PL band energy is simply used instead of barycenters, which can introduce an uncertainty to β_{spec} of ~0.01.

Fig. 7a plots $\beta_{\rm spec}$ values in NdM₂N@C₈₀, all 17 PLcharacterized Nd-SMMs reported before this work.^{30–33,36,81–85,112,131,132} selected tris(n⁵-cyclopentadienyl)Nd complexes with large ligand field splitting,116-118 and several inorganic salts and garnets thoroughly characterized by optical spectroscopy133-139 (see Table S9† for the compound titles, numerical values, and literature references for each entry). The latter group is the most studied experimentally, and for this analysis we selected the set of compounds encompassing the broadest range of β_{spec} parameters, from the most ionic ones like Nd:LaF₃ (ref. 139) with $\beta_{\text{spec}} = 0.976$ to the most covalent



Fig. 7 (a) Distribution of the spectroscopic nephelauxetic parameter β_{spec} in four groups of Nd compounds, including NdM₂N@C₈₀ molecules from this work, spectroscopically characterized Nd-SMMs, selected Nd-tris(η^5 -cyclopentadienyl) complexes Nd(CpR)₃, and Nd³⁺ salts and garnets; (b) correlation between β_{spec} and $\Delta_{LF}(^{4}I_{9/2})$ for the same compounds. The range of typical β_{spec} values in Nd compounds is shaded. For many Nd-SMMs, β_{spec} is estimated from the unresolved ${}^{4}F_{3/2} \rightarrow {}^{4}I_{9/2}$ PL band instead of multiplet barycenters, which introduces an uncertainty of ~0.01 plotted in (a). As $\Delta_{LF}(^{4}I_{9/2})$ is determined spectroscopically only for a small fraction of Nd-SMMs, the number of Nd-SMM datapoints in panel (b) is much smaller than in panel (a).

Nd:Y₂O₃ (ref. 133) and Nd₂S₃ (ref. 134) with β_{spec} of 0.943–0.945. A similar span of β_{spec} from 0.948 to 0.982 is found for Nd-SMMs. It appears safe to state that the β_{spec} range of 0.94– 0.98 is where the vast majority of Nd compounds will be found. Amberger *et al.* demonstrated that $Nd(CpR)_3$ complexes (CpR = C_5Me_5 , C_5Me_4H , $C_5H_4^{t}Bu$, $C_5H_4SiMe_3$, etc.) with enhanced metal-ligand interactions have large LF splitting and reduced nephelauxetic parameters $\beta_{\rm F}$ (see ref. 116 for comparison of LF strength and $\beta_{\rm F}$ in a series of Nd complexes).^{116–118} Likewise, their β_{spec} values of 0.934–0.936 fall below the normal β_{spec} range and were presumably the lowest values among Ndcompounds before our study. Analyzed in this broad context, the β_{spec} parameters found in this work for the NdM₂N@C₈₀ series, 0.893 for $NdLu_2N@C_{80}, 0.894$ for $NdY_2N@C_{80}, and 0.903$ for NdSc₂N@C₈₀, are unprecedently small. This very strong nephelauxetic effect evidences one more time that by increasing the internal strain in metallofullerenes we achieved a much higher degree of covalency than is usually observed in Nd compounds. It is also instructive to find that there is seemingly no correlation between the nephelauxetic effect and ligand field splitting for the compounds in the normal β_{spec} range (Fig. 7b). However, as we leave this range, the decrease of β_{spec} starts to correlate with the increase of Δ_{LF} . This is not surprising given that the strengthening of the ligand field is achieved by enhancing the interactions between the lanthanide ion and the

ligands, but it will require more compounds with such unusual properties to establish firm correlations.

The strong nephelauxetic effect and ligand field splitting may also be among the reasons for the short luminescence lifetimes of NdM₂N@C₈₀. The low energy of the NIR-emitting state in lanthanide compounds is responsible for the efficient nonradiative vibrational relaxation. For Nd³⁺, the non-radiative relaxation rate is determined by the gap between ${}^{4}F_{3/2}$ and ${}^{4}I_{15/2}$, which typically is around 5400 cm⁻¹. The ⁴I_{15/2} multiplet of NdM₂N@C₈₀ is not directly accessible in our experiments, but based on the experimental and computational data on other ${}^{4}I_{I}$ multiplets (Table S4[†]), we can assume that the energy of ${}^{4}I_{15/2}$ is also close to standard values for Nd³⁺ and that the LF splitting of the ${}^{4}I_{15/2}$ multiplet amounts to $\varDelta_{LF} \approx 1300 \text{ cm}^{-1}$ (Table S4†). The lower than usual energy of the 4F3/2 state and the strong LF splitting of the ⁴I_{15/2} multiplet reduce the gap between the KD1 of ${}^{4}F_{3/2}$ and KD8 of ${}^{4}I_{15/2}$ to $\approx 3600 \text{ cm}^{-1}$. This low gap opens the possibility for two-phonon relaxation and thus, in accordance with the energy gap law, is a plausible reason for the anomalously short Nd3+ luminescence lifetimes in NdM2N@C80 molecules.

Magnetic properties of NdSc₂N@C₈₀

While the energies of LF states are accessible *via* PL spectroscopy, experimental verification of the state compositions is not straightforwardly available from this technique.



Fig. 8 (a) Experimental magnetization curves of NdSc₂N@C₈₀ (gray dots) compared to calculations (colored lines) for pseudospin $\vec{s} = 1/2$ with the *ab initio* computed g-tensor corresponding to the ground-state Kramers doublet (KD1, Table 1). (b) Magnetization curves of NdSc₂N@C₈₀ measured between 1.8 K and 50 K and presented as a function of the HT⁻¹ product; the inset shows the comparison of experimental and calculated data for T = 1.8 K. (c) and (d) AC magnetometry measurements of in-phase χ' (c) and out-of-phase χ'' (d) magnetic susceptibility of NdSc₂N@C₈₀ in the constant field of 0.2 T at T = 1.9-7 K; dots are experimental data, and lines are fits with the generalized Debye model, from which relaxation times are extracted. (e) Magnetic field dependence of magnetization relaxation time at T = 1.8 K. (f) Temperature dependencies of magnetization relaxation times measured in the field of 0.02 T, 0.04 T, and 0.2 T; dashed line is a fit of 0.2 T data with the function $\tau_{M}^{-1} = CT^{n}$ (C = 0.0205 and n = 6.59).

Complimentary information on the ground state may be given by magnetometry. The large $\Delta_{1,2}$ value in the ⁴I_{9/2} multiplet suggests that the low-temperature magnetic properties of NdM₂N@C₈₀ will be dominated by the ground state doublet.

SQUID magnetometry. The experimental magnetic properties of $NdSc_2N@C_{80}$ powder were first studied by SQUID magnetometry (Fig. 8a and b). The magnetization curves of the sample measured below 30 K are compared to simulations for the pseudospin with the *ab initio* computed g-tensor for KD1 in **Sc-3** in Fig. 8a. A very good match between the shapes of the experimental and calculated curves points to the reliability of the theoretical predictions for the ground state KD. Furthermore, the *M versus* HT⁻¹ plots superimpose at least up to 50 K (Fig. 8b). It shows that only the ground state KD contributes to the magnetization at these temperatures, in line with the large predicted energy gap between the first and second KDs (Table 1).

XMCD. The determination of the absolute value of the magnetic moment of $NdSc_2N@C_{80}$ by SQUID measurements is not sufficiently reliable because of the limited sample amount. Complimentary information on the ground state magnetic properties of $NdSc_2N@C_{80}$ was thus obtained from X-ray magnetic circular dichroism (XMCD) measurements performed on the sample, which was drop-casted onto a HOPG substrate. In the absence of a magnetic field, the X-ray absorption spectrum of $NdSc_2N@C_{80}$ has no dichroism and shows the typical absorption features of Nd(m) at the $Nd-M_{4,5}$ edges ($3d \rightarrow 4f$ excitations) (Fig. 9 and $S20\dagger$). When a magnetic field is applied, circular polarized XAS develops a dichroism proportional to the sample magnetization in the direction of the beam (which was kept parallel to the field in our measurements) (Fig. 9). The maximum of the XMCD signal at the Nd-M₅ edge at



Fig. 9 XAS (upper panel) and XMCD (lower panel) spectra of NdSc₂-N@C₈₀ at the Nd- $M_{4,5}$ edges (3d \rightarrow 4f), $T \approx 5.5$ K, and $\mu_0 H = 6$ T. Lefthand and right-hand polarized XAS spectra are denoted as σ^+ and σ^- , and non-polarized XAS spectrum is their sum, while XMCD (in %) is their difference normalized to the maximum of XAS. Dotted lines are integrals of XAS and XMCD used in the sum rule analysis, which provided $\langle \hat{L}_z \rangle$, $\langle \hat{S}_z \rangle$, and μ_z values (see the ESI for details†). Measurements were performed at the BOREAS beamline (synchrotron ALBA).¹⁴⁰

a photon energy of 1001.5 eV was used to follow the magnetization of NdSc₂N@C₈₀ during magnetic field ramps between -6 T and +6 T. The magnetization curves measured this way reproduced the results of the SQUID measurements at 5.5 K closely (see Fig. S21 in the ESI[†]). By applying sum rules^{141,142} and tabulated correction factors,143 the XAS and XMCD spectra recorded in the field of 6 T were used to calculate the expectation values of angular and spin momentum operators, $\langle \hat{L}_z \rangle =$ 2.02 $\mu_{\rm B}$ and $\langle \hat{S}_{\rm z} \rangle = -0.45 \ \mu_{\rm B}$, and the magnetic moment along the beam direction, $\mu_z = 1.11 \mu_B$ (see the ESI for the calculation details[†]). The uncertainty in the determined value of μ_z is mainly caused by ambiguities in integration limits for the Nd- M_4 edge and is estimated to be less than $\pm 0.1 \mu_B$. The ratio $\langle \hat{S}_z \rangle / \langle \hat{L}_z \rangle = -0.22$ is close to the *ab initio* prediction of -0.24 for the ground state doublet (note that a theoretical expectation for the f^3 system is -0.25). For comparison, in the assumption of a disordered powder, the ab initio predicted ground-state gtensor of NdSc₂N@C₈₀ gives a saturated magnetic moment of 1.38 $\mu_{\rm B}$. At T = 5.5 K and under an applied magnetic field of 6 T, the theoretical moment is reduced to $1.14 \mu_B$, which is very close to the value we determined from XMCD measurements. At the same time, the ground state with the pure $m_I = \pm 9/2$ composition would have a saturated magnetic moment of 1.65 $\mu_{\rm B}$, while the value at 5.5 K and 6 T would be 1.43 μ_B . Thus, XMCD measurements confirm the ab initio prediction of the considerable deviation of the NdSc₂N@C₈₀ ground state KD from the pure $m_I = \pm 9/2$ state.

ESR spectroscopy. Precise information on the ground-state g-tensor can in principle be obtained by ESR spectroscopy. We therefore performed X-band ESR measurements of frozen NdSc₂N@C₈₀ solution in glassy d_8 -toluene. However, the sample did not show any discernible ESR signal at 10 K or higher temperature. Note that with $m_J = \pm 9/2$ being the main components of KD1, the ground-state wavefunction requires an admixture of $m_J = \pm 7/2$ terms to fulfill the ESR selection rule, $\Delta m_J = \pm 1$. As can be seen in Table 1, the contribution of $m_J = \pm 7/2$ terms to KD1 is very small (less than 1%), suggesting that the absence of the ESR signal can be caused by negligible transition matrix elements.

Dynamic magnetic properties. $NdSc_2N@C_{80}$ did not show hysteresis in DC magnetic measurements, and the sample was further studied by AC magnetometry (Fig. 8c-f and S22†). The relaxation of magnetization was too fast in zero magnetic field, and no peaks of the out-of-phase χ'' signal were recorded. The slow relaxation at 1.8 K could be detected only in the external fields exceeding 0.015 T (Fig. S22†). The relaxation time τ_M gradually increased with the field and approached tenths of a second near 0.1 T, with a sign of levelling-off at higher fields (Fig. 8e and Table S10†). The fast relaxation in zero field is caused by the quantum tunneling of magnetization (QTM) as the ground state g-tensor has rather large transversal components $g_{x,y}$ (Table 1). When the constant magnetic field is applied, the QTM is gradually suppressed, resulting in the increase of the relaxation time.

The temperature dependence of τ_M was measured in the fields of 0.02, 0.04, and 0.2 T (Table S11†). The QTM is fully suppressed at 0.2 T, and the temperature dependence of τ_M can

be well described by the Raman relaxation mechanism, $\tau_{\rm M}^{-1} = {\rm CT}^n$, with the fitted parameters $C = 0.0205 \pm 0.0026 \,{\rm s}^{-1} \,{\rm K}^{-n}$ and $n = 6.59 \pm 0.09$ (Fig. 8f). The contribution of the QTM, inducing faster relaxation with flatter temperature dependence at lower temperatures, is clearly visible in smaller fields (Fig. 8f). Higher-energy LF states are thus not involved in the reorientation of NdSc₂N@C₈₀ magnetic moment as the system finds an underbarrier shortcut with the help of phonon excitations.

The relaxation behavior observed in this work for NdSc₂-N@C₈₀ can be compared to that of non-fullerene Nd-SMMs. As discussed above, Nd-SMMs usually have considerable $g_{x,y}$ components in the ground state, which lead to fast zero-field QTM. Only three Nd complexes, two of $[Nd(H_2O)_5L_2]^{3+}$ type with pentagonal bipyramidal coordination geometry (L = ^tBuPO(NH^tPr)₂ in ref. 125 and CyPh₂PO in ref. 126), and the (COT)Nd(Cp^{ttt}) sandwich diluted with the Y analog,¹¹⁵ exhibited slow relaxation of magnetization in zero magnetic field. In all other Nd-SMMs, the slow relaxation required the DC magnetic field to suppress the fast QTM. $[Nd(H_2O)_5(CyPh_2PO)_2]^{3+}$ and (COT)Nd(Cp^{ttt}) complexes are also the only Nd-SMMs, for which a narrow magnetic hysteresis could be recorded at 2 K.115,126 For other Nd-SMMs, the slow relaxation was attested only by AC measurements, implying relaxation times shorter than 1 s. The temperature dependence of relaxation times for some Nd-SMMs was described by the Raman mechanism with an exponent of n= 6-7, $^{100,114,126,144-146}$ similar to the value of n = 6.59 determined in this work for NdSc2N@C80. When instead the Orbach mechanism was assumed to describe the relaxation of Nd-SMMs, the barriers obtained from the fits of the temperature dependence were usually several times smaller than the energies of excited LF states predicted ab initio.113,114,125,126,144-146 This inconsistency is a strong indication that the Orbach mechanism is rarely operative for Nd-SMMs, while relaxation of magnetization is more often governed by the Raman mechanism, which may also involve coupling to optical phonons.

Conclusions

The synthesis of a NdM2N@C80 series with diamagnetic rareearth metals of different sizes (M = Sc, Y, Lu) allowed us to analyze the influence of internal strain on the magnetic states and optical properties of Nd³⁺ in these metallofullerenes. We found that Nd³⁺ ions in nitride clusterfullerenes experience the strongest ligand field ever observed in molecular complexes of Nd, causing the LF splitting of the ground-state ⁴I_{9/2} multiplet reaching 1100–1200 cm⁻¹. This strong ligand field is the result of the unusually short Nd-N bond lengths and the large negative charge of the nitride ion. At the same time, a confinement of the NdM₂N cluster of a variable size inside the fullerene cage results in the increase of the strain from Sc to Lu to Y, which leads to the change of the geometrical shape of the cluster and substantial variation of the LF splitting pattern of the Nd³⁺ ion. The latter could be directly addressed by photoluminescence spectroscopy, which showed finely structured narrow emission lines caused by f-f transitions in Nd³⁺. When compared to their energies in Nd³⁺ compounds, the PL bands of NdM₂N@C₈₀ are considerably red-shifted, which points to the very strong

nephelauxetic effect and enhanced contribution of covalency in Nd bonding.

The enhanced covalency is the price for the large LF splitting and, as shown by *ab initio* modelling, is the reason for the reduced magnetic axiality in NdM₂N@C₈₀. Point-charge modelling demonstrates that pure electrostatic interactions in these molecules would produce highly axial LF states with sheer m_J wavefunction compositions. Experimental studies of magnetic properties revealed that NdSc₂N@C₈₀ exhibits slow relaxation of magnetization only in the presence of an external magnetic field, whereas its zero-field relaxation is dominated by the fast tunneling process. The large LF splitting also does not help to slow down the in-field relaxation of magnetization, which appears to be governed by the under-barrier Raman mechanism.

The results of this work demonstrate that pushing the LF strength to its extreme by enhancing interactions of Nd ions with surrounding atoms does not improve the magnetic axiality even in the molecular geometry, which favors such axiality for heavy lanthanides. The reason is that the larger ionic radius makes Nd more susceptible to enhanced covalency. Theoretically, the single-ion magnetic anisotropy of Nd³⁺ could be made highly axial by placing point charges at short distances, but in reality, the strong LF would require an interaction with strong ligands placed at close distances, which inevitably leads to the enhanced covalency and all its negative effects on the magnetic axiality discussed in this work. This dichotomy between the strong ligand field and reduced magnetic axiality appears to be a fundamental limitation for creating high-performance SMMs based on light lanthanides. Nevertheless, the large LF splitting appears very instrumental in separating f-f transitions and enabling direct optical access to individual spin states of Nd³⁺, which can be useful for application in magneto-photonic quantum technologies. Another possible consequence of enhanced covalency worth mentioning is that the 4f-shell can become more susceptible to manipulations by other methods like scanning tunneling microscopy, which is usually considered not amenable to probe 4f electrons in molecules due to their core-like behavior. Thus, while Nd-EMFs may not perform great as single molecular magnets, they show good prospects for optically and electronically addressable quantum bits. Importantly, their LF splitting and spin-state wavefunction can be further tuned by varying the composition of the endohedral exohedral chemical modification cluster or of metallofullerenes.

Data availability

The data supporting the findings of this study are available from the corresponding authors upon reasonable request.

Author contributions

WY synthesized fullerenes with help and supervision from FL; MR and FZ performed PL measurements; VD performed DFT calculations under the supervision of SMA; GV and MB performed SQUID measurements; SS performed vibrational spectroscopic studies; MR, GV, MB, LS, CG, MV and AAP performed the XMCD study; SMA performed *ab initio* calculations; FL grew single-crystals and performed the SC-XRD study; AAP conceived and supervised the study; FL, SMA, and AAP wrote the manuscript with contributions from all co-authors.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The authors acknowledge financial support by the Deutsche Forschungsgemeinschaft (grants PO 1602/7-1, PO 1602/11-1, LI 3055/3-1, and AV 169/3-1) and the China Scholarship Council (Fellowship to W. Y.). Diffraction data have been collected on BL14.2 at the BESSY II electron storage ring operated by the Helmholtz-Zentrum Berlin; we would like to acknowledge the help and support of Manfred Weiss and his group members during the experiments at BESSY II. XMCD measurements at the synchrotron ALBA were performed in the framework of the beamtime proposal ID 20201035073. Computational resources were provided by the Center for High Performance Computing at the TU Dresden. We appreciate the technical support with computational resources in IFW Dresden by Ulrike Nitzsche. Dr Anja Wolter-Giraud and Sebastian Ga β are acknowledged for the help with SQUID magnetic measurements.

References

- 1 J. Long, Y. Guari, R. A. S. Ferreira, L. D. Carlos and J. Larionova, *Coord. Chem. Rev.*, 2018, **363**, 57–70.
- 2 R. Marin, G. Brunet and M. Murugesu, Angew. Chem., Int. Ed., 2021, 60, 1728–1746.
- 3 J.-H. Jia, Q.-W. Li, Y.-C. Chen, J.-L. Liu and M.-L. Tong, *Coord. Chem. Rev.*, 2019, **378**, 365–381.
- 4 F. Pointillart, B. le Guennic, O. Cador, O. Maury and L. Ouahab, *Acc. Chem. Res.*, 2015, **48**, 2834–2842.
- 5 R. Jankowski, M. Wyczesany and S. Chorazy, *Chem. Commun.*, 2023, **59**, 5961–5986.
- 6 G. Cucinotta, M. Perfetti, J. Luzon, M. Etienne, P. E. Car, A. Caneschi, G. Calvez, K. Bernot and R. Sessoli, *Angew. Chem., Int. Ed.*, 2012, **51**, 1606.
- 7 J. Long, R. Vallat, R. A. S. Ferreira, L. D. Carlos, F. A. Almeida Paz, Y. Guari and J. Larionova, *Chem. Commun.*, 2012, **48**, 9974–9976.
- 8 S. Shintoyo, K. Murakami, T. Fujinami, N. Matsumoto, N. Mochida, T. Ishida, Y. Sunatsuki, M. Watanabe, M. Tsuchimoto, J. Mrozinski, C. Coletti and N. Re, *Inorg. Chem.*, 2014, 53, 10359–10369.
- 9 Y. Bi, C. Chen, Y.-F. Zhao, Y.-Q. Zhang, S.-D. Jiang, B.-W. Wang, J.-B. Han, J.-L. Sun, Z.-Q. Bian, Z.-M. Wang and S. Gao, *Chem. Sci.*, 2016, 7, 5020–5031.
- 10 E. Mamontova, J. Long, R. A. S. Ferreira, A. M. P. Botas, D. Luneau, Y. Guari, L. D. Carlos and J. Larionova, *Magnetochemistry*, 2016, 2, 41.

- 11 J. Long, E. Mamontova, V. Freitas, D. Luneau, V. Vieru,
 L. F. Chibotaru, R. A. S. Ferreira, G. Felix, Y. Guari,
 L. D. Carlos and J. Larionova, *RSC Adv.*, 2016, 6, 108810–108818.
- 12 Y.-C. Chen, J.-L. Liu, Y. Lan, Z.-Q. Zhong, A. Mansikkamäki, L. Ungur, Q.-W. Li, J.-H. Jia, L. F. Chibotaru, J.-B. Han, W. Wernsdorfer, X.-M. Chen and M.-L. Tong, *Chem.-Euro. J.*, 2017, 23, 5708–5715.
- 13 F. Guégan, F. Riobé, O. Maury, J. Jung, B. Le Guennic, C. Morell and D. Luneau, *Inorg. Chem. Front.*, 2018, 5, 1346–1353.
- M. Perfetti, M. Gysler, Y. Rechkemmer-Patalen, P. Zhang, H. Taştan, F. Fischer, J. Netz, W. Frey, L. W. Zimmermann, T. Schleid, M. Hakl, M. Orlita, L. Ungur, L. Chibotaru, T. Brock-Nannestad, S. Piligkos and J. van Slageren, *Chem. Sci.*, 2019, **10**, 2101–2110.
- D. Guettas, F. Gendron, G. Fernandez Garcia, F. Riobé, T. Roisnel, O. Maury, G. Pilet, O. Cador and B. Le Guennic, *Chem.-Eur. J.*, 2020, 26, 4389-4395.
- 16 R. A. S. Ferreira, E. Mamontova, A. M. P. Botas, M. Shestakov, J. Vanacken, V. Moshchalkov, Y. Guari, L. F. Chibotaru, D. Luneau, P. S. André, J. Larionova, J. Long and L. D. Carlos, *Adv. Opt. Mater.*, 2021, 9, 2101495.
- 17 Y. Liu, B.-H. Lyu, S.-N. Du, G.-Z. Huang, Z.-Y. Ruan, S.-G. Wu, J.-L. Liu and M.-L. Tong, *Dalton Trans.*, 2021, 50, 6778–6783.
- 18 F. Pointillart, B. L. Guennic, S. Golhen, O. Cador, O. Maury and L. Ouahab, *Chem. Commun.*, 2013, 49, 615–617.
- K. S. Pedersen, J. Dreiser, H. Weihe, R. Sibille, H. V. Johannesen, M. A. Sørensen, B. E. Nielsen, M. Sigrist, H. Mutka, S. Rols, J. Bendix and S. Piligkos, *Inorg. Chem.*, 2015, 54, 7600–7606.
- 20 K. Soussi, J. Jung, F. Pointillart, B. Le Guennic, B. Lefeuvre, S. Golhen, O. Cador, Y. Guyot, O. Maury and L. Ouahab, *Inorg. Chem. Front.*, 2015, 2, 1105–1117.
- 21 G. Brunet, R. Marin, M.-J. Monk, U. Resch-Genger, D. A. Gálico, F. A. Sigoli, E. A. Suturina, E. Hemmer and M. Murugesu, *Chem. Sci.*, 2019, **10**, 6799–6808.
- 22 F. Guégan, J. Jung, B. Le Guennic, F. Riobé, O. Maury,
 B. Gillon, J.-F. Jacquot, Y. Guyot, C. Morell and
 D. Luneau, *Inorg. Chem. Front.*, 2019, 6, 3152–3157.
- 23 W.-B. Chen, L. Zhong, Y.-J. Zhong, Y.-Q. Zhang, S. Gao and W. Dong, *Inorg. Chem. Front.*, 2020, 7, 3136–3145.
- 24 F. Gendron, S. Di Pietro, L. Abad Galán, F. Riobé, V. Placide, L. Guy, F. Zinna, L. Di Bari, A. Bensalah-Ledoux, Y. Guyot, G. Pilet, F. Pointillart, B. Baguenard, S. Guy, O. Cador, O. Maury and B. Le Guennic, *Inorg. Chem. Front.*, 2021, 8, 914–926.
- 25 K. Karachousos-Spiliotakopoulos, V. Tangoulis,
 N. Panagiotou, A. Tasiopoulos, E. Moreno-Pineda,
 W. Wernsdorfer, M. Schulze, A. M. P. Botas and
 L. D. Carlos, *Dalton Trans.*, 2022, 51, 8208–8216.
- 26 K. Yamashita, R. Miyazaki, Y. Kataoka, T. Nakanishi, Y. Hasegawa, M. Nakano, T. Yamamura and T. Kajiwara, *Dalton Trans.*, 2013, **42**, 1987–1990.
- 27 K. Ehama, Y. Ohmichi, S. Sakamoto, T. Fujinami, N. Matsumoto, N. Mochida, T. Ishida, Y. Sunatsuki,

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Open Access Article. Published on 21 December 2023. Downloaded on 8/12/2025 4:54:31 AM.

M. Tsuchimoto and N. Re, *Inorg. Chem.*, 2013, **52**, 12828-12841.

- 28 E. A. Mikhalyova, M. Zeller, J. P. Jasinski, R. J. Butcher, L. M. Carrella, A. E. Sedykh, K. S. Gavrilenko, S. S. Smola, M. Frasso, S. C. Cazorla, K. Perera, A. Shi, H. G. Ranjbar, C. Smith, A. Deac, Y. Liu, S. M. McGee, V. P. Dotsenko, M. U. Kumke, K. Müller-Buschbaum, E. Rentschler, A. W. Addison and V. V. Pavlishchuk, *Dalton Trans.*, 2020, 49, 7774–7789.
- 29 J. Wang, J. J. Zakrzewski, M. Zychowicz, V. Vieru, L. F. Chibotaru, K. Nakabayashi, S. Chorazy and S.-i. Ohkoshi, *Chem. Sci.*, 2021, **12**, 730–741.
- 30 I. Oyarzabal, B. Artetxe, A. Rodríguez-Diéguez, J. Á. García, J. M. Seco and E. Colacio, *Dalton Trans.*, 2016, 45, 9712–9726.
- 31 B. Casanovas, S. Speed, O. Maury, M. S. El Fallah, M. Font-Bardía and R. Vicente, *Eur. J. Inorg. Chem.*, 2018, 2018, 3859–3867.
- 32 B. Casanovas, S. Speed, O. Maury, M. Font-Bardía and R. Vicente, *Polyhedron*, 2019, **169**, 187–194.
- 33 Y. H. Pham, V. A. Trush, M. Korabik, V. M. Amirkhanov and P. Gawryszewska, *Dyes Pigm.*, 2021, **186**, 108986.
- 34 F. Pointillart, B. Le Guennic, T. Cauchy, S. Golhen, O. Cador, O. Maury and L. Ouahab, *Inorg. Chem.*, 2013, 52, 5978.
- 35 M. Karbowiak, C. Rudowicz, T. Nakamura, R. Murakami and T. Ishida, *Chem. Phys. Lett.*, 2016, **662**, 163–168.
- K. Kumar, D. Abe, K. Komori-Orisaku, O. Stefańczyk,
 K. Nakabayashi, J. R. Shakirova, S. P. Tunik and
 S.-i. Ohkoshi, *RSC Adv.*, 2019, 9, 23444–23449.
- 37 D. Errulat, R. Marin, D. A. Gálico, K. L. M. Harriman,
 A. Pialat, B. Gabidullin, F. Iikawa, O. D. D. Couto,
 J. O. Moilanen, E. Hemmer, F. A. Sigoli and M. Murugesu,
 ACS Cent. Sci., 2019, 5, 1187–1198.
- 38 D. Serrano, S. K. Kuppusamy, B. Heinrich, O. Fuhr, D. Hunger, M. Ruben and P. Goldner, *Nature*, 2022, 603, 241–246.
- 39 D. W. Laorenza and D. E. Freedman, J. Am. Chem. Soc., 2022, 144, 21810–21825.
- 40 R. Westerström, J. Dreiser, C. Piamonteze, M. Muntwiler, S. Weyeneth, H. Brune, S. Rusponi, F. Nolting, A. Popov, S. Yang, L. Dunsch and T. Greber, *J. Am. Chem. Soc.*, 2012, 134, 9840–9843.
- 41 L. Spree, F. Liu, V. Neu, M. Rosenkranz, G. Velkos, Y. Wang,
 S. Schiemenz, J. Dreiser, P. Gargiani, M. Valvidares,
 C.-H. Chen, B. Büchner, S. M. Avdoshenko and
 A. A. Popov, *Adv. Funct. Mater.*, 2021, 31, 2105516.
- 42 F. Liu, G. Velkos, D. S. Krylov, L. Spree, M. Zalibera, R. Ray, N. A. Samoylova, C.-H. Chen, M. Rosenkranz, S. Schiemenz, F. Ziegs, K. Nenkov, A. Kostanyan, T. Greber, A. U. B. Wolter, M. Richter, B. Büchner, S. M. Avdoshenko and A. A. Popov, *Nat. Commun.*, 2019, **10**, 571.
- 43 L. Spree and A. A. Popov, *Dalton Trans.*, 2019, **48**, 2861–2871.
- 44 W. Li, C.-R. Wang and T. Wang, *Chem. Commun.*, 2021, 57, 10317–10326.

- 45 V. Vieru, L. Ungur and L. F. Chibotaru, *J. Phys. Chem. Lett.*, 2013, 4, 3565–3569.
- 46 F. Cimpoesu, N. Dragoe, H. Ramanantoanina, W. Urland and C. Daul, *Phys. Chem. Chem. Phys.*, 2014, **16**, 11337– 11348.
- 47 M. K. Singh and G. Rajaraman, *Chem. Commun.*, 2016, **52**, 14047–14050.
- 48 G. Rajaraman, M. K. Singh and N. Yadav, *Chem. Commun.*, 2015, **51**, 17732–17735.
- 49 C.-H. Chen, D. S. Krylov, S. M. Avdoshenko, F. Liu, L. Spree, R. Yadav, A. Alvertis, L. Hozoi, K. Nenkov, A. Kostanyan, T. Greber, A. U. B. Wolter and A. A. Popov, *Chem. Sci.*, 2017, 8, 6451–6465.
- 50 D. S. Krylov, F. Liu, S. M. Avdoshenko, L. Spree, B. Weise, A. Waske, A. U. B. Wolter, B. Büchner and A. A. Popov, *Chem. Commun.*, 2017, 53, 7901–7904.
- 51 W. Yang, G. Velkos, F. Liu, S. M. Sudarkova, Y. Wang, J. Zhuang, H. Zhang, X. Li, X. Zhang, B. Büchner, S. M. Avdoshenko, A. A. Popov and N. Chen, *Adv. Sci.*, 2019, 6, 1901352.
- 52 L. Spree, C. Schlesier, A. Kostanyan, R. Westerström,
 T. Greber, B. Büchner, S. Avdoshenko and A. A. Popov, *Chem.-Eur. J.*, 2020, 26, 2436–2449.
- 53 M. Zalibera, F. Ziegs, S. Schiemenz, V. Dubrovin, W. Lubitz,
 A. Savitsky, S. Deng, X.-B. Wang, S. Avdoshenko and
 A. A. Popov, *Chem. Sci.*, 2021, 12, 7818–7838.
- 54 M. Zalibera, D. S. Krylov, D. Karagiannis, P.-A. Will, F. Ziegs,
 S. Schiemenz, W. Lubitz, S. Reineke, A. Savitsky and
 A. A. Popov, *Angew. Chem., Int. Ed.*, 2018, 57, 277–281.
- 55 G. Dantelle, A. Tiwari, R. Rahman, S. R. Plant, K. Porfyrakis, M. Mortier, R. A. Taylor and A. D. Briggs, *Opt. Mater.*, 2009, 32, 251–256.
- 56 A. Tiwari, G. Dantelle, K. Porfyrakis, R. A. Taylor,
 A. A. R. Watt, A. Ardavan and G. A. D. Briggs, *J. Chem. Phys.*, 2007, 127, 194504.
- 57 R. M. Macfarlane, D. S. Bethune, S. Stevenson and H. C. Dorn, *Chem. Phys. Lett.*, 2001, **343**, 229–234.
- 58 M. Nie, J. Xiong, C. Zhao, H. Meng, K. Zhang, Y. Han, J. Li,
 B. Wang, L. Feng, C. Wang and T. Wang, *Nano Res.*, 2019, 12, 1727–1731.
- 59 M. Nie, L. Yang, C. Zhao, H. Meng, L. Feng, P. Jin, C.-R. Wang and T. Wang, *Nanoscale*, 2019, **11**, 18612–18618.
- 60 Y. Ito, T. Okazaki, S. Okubo, M. Akachi, Y. Ohno,
 T. Mizutani, T. Nakamura, R. Kitaura, T. Sugai and
 H. Shinohara, *ACS Nano*, 2007, 1, 456–462.
- 61 S. R. Plant, G. Dantelle, Y. Ito, T. C. Ng, A. Ardavan, H. Shinohara, R. A. Taylor, A. D. Briggs and K. Porfyrakis, *Chem. Phys. Lett.*, 2009, 476, 41–45.
- 62 D. Xu, Y. Jiang, Y. Wang, T. Zhou, Z. Shi, H. Omachi, H. Shinohara, B. Sun and Z. Wang, *Inorg. Chem.*, 2019, 58, 14325–14330.
- 63 H. Jin, J. Xin, W. Xiang, Z. Jiang, X. Han, M. Chen, P. Du, Y.-R. Yao and S. Yang, *Adv. Mater.*, 2023, **35**, 2304121.
- 64 Z. Wang, N. Izumi, Y. Nakanishi, T. Koyama, T. Sugai, M. Tange, T. Okazaki and H. Shinohara, *ACS Nano*, 2016, 10, 4282–4287.

- 65 Y. Zhang, D. Krylov, M. Rosenkranz, S. Schiemenz and A. A. Popov, *Chem. Sci.*, 2015, 6, 2328–2341.
- 66 A. Kostanyan, R. Westerström, D. Kunhardt, B. Büchner, A. A. Popov and T. Greber, *Phys. Rev. B*, 2020, **101**, 134429.
- 67 F. Liu, S. Wang, C.-L. Gao, Q. Deng, X. Zhu, A. Kostanyan, R. Westerström, F. Jin, S.-Y. Xie, A. A. Popov, T. Greber and S. Yang, *Angew. Chem., Int. Ed.*, 2017, **56**, 1830–1834.
- 68 F. Liu, C.-L. Gao, Q. Deng, X. Zhu, A. Kostanyan, R. Westerström, S. Wang, Y.-Z. Tan, J. Tao, S.-Y. Xie, A. A. Popov, T. Greber and S. Yang, *J. Am. Chem. Soc.*, 2016, 138, 14764–14771.
- 69 G. Velkos, D. Krylov, K. Kirkpatrick, L. Spree, V. Dubrovin,
 B. Büchner, S. Avdoshenko, V. Bezmelnitsyn, S. Davis,
 P. Faust, J. Duchamp, H. Dorn and A. A. Popov, *Angew. Chem., Int. Ed.*, 2019, 58, 5891–5896.
- Y. Wang, G. Velkos, N. J. Israel, M. Rosenkranz, B. Büchner,
 F. Liu and A. A. Popov, *J. Am. Chem. Soc.*, 2021, 143, 18139– 18149.
- 71 F. Liu, D. S. Krylov, L. Spree, S. M. Avdoshenko, N. A. Samoylova, M. Rosenkranz, A. Kostanyan, T. Greber, A. U. B. Wolter, B. Büchner and A. A. Popov, *Nat. Commun.*, 2017, 8, 16098.
- 72 R. Westerström, J. Dreiser, C. Piamonteze, M. Muntwiler,
 S. Weyeneth, K. Krämer, S.-X. Liu, S. Decurtins, A. Popov,
 S. Yang, L. Dunsch and T. Greber, *Phys. Rev. B*, 2014, 89, 060406.
- 73 Y. Wang, J. Xiong, J. Su, Z.-Q. Hu, F. Ma, R. Sun, X.-Y. Tan, H.-L. Sun, B. Wang, Z. Shi and S. Gao, *Nanoscale*, 2020, 12, 11130–11135.
- 74 J. Dreiser, R. Westerström, Y. Zhang, A. A. Popov,
 L. Dunsch, K. Krämer, S.-X. Liu, S. Decurtins and
 T. Greber, *Chem.-Eur. J.*, 2014, 20, 13536–13540.
- 75 J.-F. Wyart, A. Meftah, A. Bachelier, J. Sinzelle, W.-Ü. L. Tchang-Brillet, N. Champion, N. Spector and J. Sugar, J. Phys. B: At., Mol. Opt. Phys., 2006, 39, L77–L82.
- 76 F. Melin, M. N. Chaur, S. Engmann, B. Elliott, A. Kumbhar,
 A. J. Athans and L. Echegoyen, *Angew. Chem., Int. Ed.*, 2007,
 46, 9032–9035.
- 77 S. Yang, A. A. Popov, C. Chen and L. Dunsch, *J. Phys. Chem. C*, 2009, **113**, 7616–7623.
- 78 W. Yang, G. Velkos, M. Rosenkranz, S. Schiemenz, F. Liu and A. A. Popov, *Adv. Sci.*, 2024, 1, 202305190.
- 79 F. Pointillart, O. Cador, B. Le Guennic and L. Ouahab, *Coord. Chem. Rev.*, 2017, 346, 150–175.
- 80 A. Borah and R. Murugavel, *Coord. Chem. Rev.*, 2022, 453, 214288.
- 81 G. Huang, G. Calvez, Y. Suffren, C. Daiguebonne, S. Freslon,O. Guillou and K. Bernot, *Magnetochemistry*, 2018, 4, 44.
- 82 B. Casanovas, M. Font-Bardía, S. Speed, M. S. El Fallah and R. Vicente, *Eur. J. Inorg. Chem.*, 2018, 2018, 1928–1937.
- 83 B. Casanovas, S. Speed, R. Vicente and M. Font-Bardía, *Polyhedron*, 2019, **173**, 114113.
- 84 R. Vicente, A. Tubau, S. Speed, F. A. Mautner,
 F. Bierbaumer, R. C. Fischer and S. S. Massoud, *New J. Chem.*, 2021, 45, 14713–14723.
- 85 H. Chen, L. Sun, K. Zheng, J. Zhang, P. Ma, J. Wang and J. Niu, *Dalton Trans.*, 2022, **51**, 10257–10265.

- 86 S. Yang, L. Zhang, W. Zhang and L. Dunsch, *Chem.-Eur. J.*, 2010, **16**, 12398–12405.
- 87 U. Mueller, R. Förster, M. Hellmig, F. U. Huschmann,
 A. Kastner, P. Malecki, S. Pühringer, M. Röwer, K. Sparta,
 M. Steffien, M. Ühlein, P. Wilk and M. S. Weiss, *Eur. Phys. J. Plus*, 2015, 130, 141.
- 88 W. Kabsch, Acta Crystallogr., Sect. D: Biol. Crystallogr., 2010, 66, 125–132.
- 89 K. M. Sparta, M. Krug, U. Heinemann, U. Mueller and M. S. Weiss, *J. Appl. Crystallogr.*, 2016, 49, 1085–1092.
- 90 G. Sheldrick, Acta Crystallogr., Sect. C: Struct. Chem., 2015, 71, 3-8.
- 91 S. Stevenson, C. B. Rose, J. S. Maslenikova, J. R. Villarreal, M. A. Mackey, B. Q. Mercado, K. Chen, M. M. Olmstead and A. L. Balch, *Inorg. Chem.*, 2012, **51**, 13096–13102.
- 92 S. Stevenson, C. Chancellor, H. M. Lee, M. M. Olmstead and A. L. Balch, *Inorg. Chem.*, 2008, 47, 1420–1427.
- 93 X. L. Wang, T. M. Zuo, M. M. Olmstead, J. C. Duchamp, T. E. Glass, F. Cromer, A. L. Balch and H. C. Dorn, *J. Am. Chem. Soc.*, 2006, **128**, 8884–8889.
- 94 D. Krylov, F. Liu, A. Brandenburg, L. Spree, V. Bon, S. Kaskel, A. Wolter, B. Buchner, S. Avdoshenko and A. A. Popov, *Phys. Chem. Chem. Phys.*, 2018, 20, 11656– 11672.
- 95 R. Shannon, Acta Crystallogr., Sect. A: Cryst. Phys., Diffr., Theor. Gen. Crystallogr., 1976, 32, 751-767.
- 96 T. E. Rieser, R. Thim-Spöring, D. Schädle, P. Sirsch, R. Litlabø, K. W. Törnroos, C. Maichle-Mössmer and R. Anwander, *J. Am. Chem. Soc.*, 2022, **144**, 4102–4113.
- 97 D. Schädle, C. Schädle, D. Schneider, C. Maichle-Mössmer and R. Anwander, *Organometallics*, 2015, 34, 4994–5008.
- 98 D. Schädle, C. Schädle, K. W. Törnroos and R. Anwander, Organometallics, 2012, **31**, 5101–5107.
- 99 W. J. Evans, R. Anwander, J. W. Ziller and S. I. Khan, *Inorg. Chem.*, 1995, 34, 5927–5930.
- 100 J. Liu, D. Reta, J. A. Cleghorn, Y. X. Yeoh, F. Ortu, C. A. P. Goodwin, N. F. Chilton and D. P. Mills, *Chem.– Euro. J.*, 2019, 25, 7749–7758.
- 101 R. Taube, S. Maiwald and J. Sieler, *J. Organomet. Chem.*, 2001, **621**, 327–336.
- 102 D. Barbier-Baudry, O. Blacque, A. Hafid, A. Nyassi,
 H. Sitzmann and M. Visseaux, *Eur. J. Inorg. Chem.*, 2000, 2000, 2333–2336.
- 103 S. M. Cendrowski-Guillaume, M. Nierlich, M. Lance and M. Ephritikhine, Organometallics, 1998, 17, 786–788.
- 104 L. Münzfeld, C. Schoo, S. Bestgen, E. Moreno-Pineda, R. Köppe, M. Ruben and P. W. Roesky, *Nat. Commun.*, 2019, **10**, 3135.
- 105 F. M. Sroor, C. G. Hrib, P. Liebing, L. Hilfert, S. Busse and F. T. Edelmann, *Dalton Trans.*, 2016, **45**, 13332–13346.
- 106 Y. Zhang, R. Guan, M. Chen, Y. Shen, Q. Pan, Y. Lian and S. Yang, *Inorg. Chem.*, 2021, **6**, 1462–1471.
- 107 M. M. Olmstead, T. Zuo, H. C. Dorn, T. Li and A. L. Balch, *Inorg. Chim. Acta*, 2017, 468, 321–326.
- 108 C. Schlesier, F. Liu, V. Dubrovin, L. Spree, B. Büchner, S. Avdoshenko and A. A. Popov, *Nanoscale*, 2019, **11**, 13139–13153.

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Open Access Article. Published on 21 December 2023. Downloaded on 8/12/2025 4:54:31 AM.

- 109 V. Dubrovin, L.-H. Gan, B. Büchner, A. A. Popov and S. M. Avdoshenko, *Phys. Chem. Chem. Phys.*, 2019, 21, 8197–8200.
- 110 S. V. Eliseeva and J.-C. G. Bünzli, *Chem. Soc. Rev.*, 2010, **39**, 189–227.
- 111 J. G. M. Morton, A. Tiwari, G. Dantelle, K. Porfyrakis, A. Ardavan and G. A. D. Briggs, *Phys. Rev. Lett.*, 2008, **101**, 013002.
- 112 H. Reddmann, C. Apostolidis, O. Walter and H.-D. Amberger, Z. Anorg. Allg. Chem., 2006, 632, 1405– 1408.
- 113 J. D. Rinehart and J. R. Long, *Dalton Trans.*, 2012, 41, 13572–13574.
- 114 Q.-W. Li, R.-C. Wan, Y.-C. Chen, J.-L. Liu, L.-F. Wang, J.-H. Jia, N. F. Chilton and M.-L. Tong, *Chem. Commun.*, 2016, 52, 13365–13368.
- 115 M. D. Korzyński, M. Bernhardt, V. Romankov, J. Dreiser, G. Matmon, F. Pointillart, B. Le Guennic, O. Cador and C. Copéret, *Chem. Sci.*, 2022, 13, 10574–10580.
- 116 H.-D. Amberger, H. Reddmann, T. J. Mueller and W. J. Evans, *J. Organomet. Chem.*, 2011, **696**, 2829–2836.
- 117 H.-D. Amberger and H. Reddmann, Z. Anorg. Allg. Chem., 2007, 633, 443–452.
- 118 S. Jank, H. Reddmann, H.-D. Amberger and C. Apostolidis, *J. Organomet. Chem.*, 2004, **689**, 3143–3157.
- 119 R. Westerström, V. Dubrovin, K. Junghans, C. Schlesier,
 B. Büchner, S. M. Avdoshenko, A. A. Popov, A. Kostanyan,
 J. Dreiser and T. Greber, *Phys. Rev. B*, 2021, **104**, 224401.
- 120 Y. Hao, G. Velkos, S. Schiemenz, M. Rosenkranz, Y. Wang, B. Büchner, S. M. Avdoshenko, A. A. Popov and F. Liu, *Inorg. Chem. Front.*, 2023, 10, 468–484.
- 121 L. Gagliardi, R. Lindh and G. Karlström, J. Chem. Phys., 2004, **121**, 4494–4500.
- 122 L. Ungur and L. F. Chibotaru, *Chem.-Euro. J.*, 2017, 23, 3708-3718.
- 123 M. Briganti, G. F. Garcia, J. Jung, R. Sessoli, B. Le Guennic and F. Totti, *Chem. Sci.*, 2019, **10**, 7233–7245.
- 124 R. Alessandri, H. Zulfikri, J. Autschbach and H. Bolvin, *Chem.-Eur. J.*, 2018, 24, 5538-5550.
- 125 S. K. Gupta, T. Rajeshkumar, G. Rajaraman and R. Murugavel, *Chem. Commun.*, 2016, **52**, 7168–7171.
- 126 Y.-C. Chen, X.-S. Huang, J.-L. Liu and M.-L. Tong, *Inorg. Chem.*, 2018, 57, 11782–11787.

- 127 L. F. Chibotaru and L. Ungur, J. Chem. Phys., 2012, 137, 064112.
- 128 C. K. Jørgensen, Prog. Inorg. Chem., 1962, 73-124.
- 129 S. P. Sinha and H. H. Schmidtke, *Mol. Phys.*, 1965, **10**, 7–11.
- 130 D. E. Henrie, Mol. Phys., 1974, 28, 415-421.
- S. Chorazy, T. Charytanowicz, J. Wang, S.-i. Ohkoshi and B. Sieklucka, *Dalton Trans.*, 2018, 47, 7870–7874.
- 132 R. Jankowski, J. J. Zakrzewski, M. Zychowicz, J. Wang, Y. Oki, S.-i. Ohkoshi, S. Chorazy and B. Sieklucka, J. Mater. Chem. C, 2021, 9, 10705–10717.
- 133 N. C. Chang, J. Chem. Phys., 1966, 44, 4044-4050.
- 134 J. B. Gruber, R. P. Leavitt and C. A. Morrison, *J. Chem. Phys.*, 1983, **79**, 1664–1668.
- 135 J. A. Koningstein and J. E. Geusic, *Phys. Rev.*, 1964, **136**, A711–A716.
- 136 J. B. Gruber, M. E. Hills, T. H. Allik, C. K. Jayasankar, J. R. Quagliano and F. S. Richardson, *Phys. Rev. B*, 1990, 41, 7999–8012.
- 137 H. M. Crosswhite, H. Crosswhite, F. W. Kaseta and R. Sarup, *J. Chem. Phys.*, 1976, **64**, 1981–1985.
- 138 R. M. Hammond, M. F. Reid and F. S. Richardson, J. Less-Common Met., 1989, **148**, 311-319.
- 139 W. T. Carnall, H. Crosswhite and H. M. Crosswhite, *Energy level structure and transition probabilities in the spectra of the trivalent lanthanides in LaF₃*, United States, 1978, DOI: DOI: 10.2172/6417825.
- 140 A. Barla, J. Nicolás, D. Cocco, S. M. Valvidares, J. Herrero-Martín, P. Gargiani, J. Moldes, C. Ruget, E. Pellegrin and S. Ferrer, *J. Synchrotron Radiat.*, 2016, 23, 1507–1517.
- 141 B. T. Thole, P. Carra, F. Sette and G. van der Laan, *Phys. Rev. Lett.*, 1992, **68**, 1943–1946.
- 142 P. Carra, B. T. Thole, M. Altarelli and X. Wang, *Phys. Rev. Lett.*, 1993, **70**, 694–697.
- 143 Y. Teramura, A. Tanaka, B. T. Thole and T. Jo, *J. Phys. Soc. Jpn.*, 1996, **65**, 3056–3059.
- 144 M.-X. Xu, Y.-S. Meng, J. Xiong, B.-W. Wang, S.-D. Jiang and S. Gao, *Dalton Trans.*, 2018, **47**, 1966–1971.
- 145 E. Regincós Martí, A. B. Canaj, T. Sharma, A. Celmina, C. Wilson, G. Rajaraman and M. Murrie, *Inorg. Chem.*, 2022, **61**, 9906–9917.
- 146 J. Li, L. Yin, S.-J. Xiong, X.-L. Wu, F. Yu, Z.-W. Ouyang, Z.-C. Xia, Y.-Q. Zhang, J. van Tol, Y. Song and Z. Wang, *iScience*, 2020, 23, 100926.