Nanoscale Advances

REVIEW



Cite this: Nanoscale Adv., 2025, 7, 384

Received 28th September 2024 Accepted 2nd November 2024

DOI: 10.1039/d4na00806e

rsc.li/nanoscale-advances

1 Introduction

In recent years, photocatalysis and electrocatalysis have shown great advantages and broad application prospects in coping with the challenges of renewable clean energy.¹ Photocatalysis, driven by solar energy, initiates photocatalytic reactions via the generation of photo-induced electrons and holes, providing a friendly and sustainable way to transform solar energy into chemical energy (e.g. H_2 production through water splitting), which is beneficial for tackling environmental challenges.^{2,3} Electrocatalysis, on the other hand, can realize efficient energy conversion through electrocatalytic reactions on well-designed electrodes, such as hydrogen evolution reaction (HER), oxygen evolution reaction (OER), oxygen reduction reaction (ORR), and so on, opening up broad prospects for the development of efficient energy devices with excellent performances.4-8 In this regard, photocatalysis and electrocatalysis are of great significance for achieving green sustainable development.9 However,

Recent advances in irradiation-mediated synthesis and tailoring of inorganic nanomaterials for photo-/electrocatalysis

Shoushuang Huang, (1) *ab Can Yue, a Kajsa Uvdal^b and Zhangjun Hu (1) *b

Photo-/electrocatalysis serves as a cornerstone in addressing global energy shortages and environmental pollution, where the development of efficient and stable catalysts is essential yet challenging. Despite extensive efforts, it's still a formidable task to develop catalysts with excellent catalytic behaviours, stability, and low cost. Because of its high precision, favorable controllability and repeatability, radiation technology has emerged as a potent and versatile strategy for the synthesis and modification of nanomaterials. Through meticulous control of irradiation parameters, including energy, fluence and ion species, various inorganic photo-/electrocatalysts can be effectively synthesized with tailored properties. It also enables the efficient adjustment of physicochemical characteristics, such as heteroatom-doping, defect generation, heterostructure construction, micro/nanostructure control, and so on, all of which are beneficial for lowering reaction energy barriers and enhancing energy conversion efficiency. This review comprehensively outlines the principles governing radiation effects on inorganic catalysts, followed by an in-depth discussion of recent advancements in irradiation-enhanced catalysts for various photo-/electrocatalytic applications, such as hydrogen and oxygen evolution reactions, oxygen reduction reactions, and photocatalytic applications. Furthermore, the challenges associated with ionizing and non-ionizing radiation are discussed and potential avenues for future development are outlined. By summarizing and articulating these innovative strategies, we aim to inspire further development of sustainable energy and environmental solutions to drive a greener future.

the efficiency, selectivity, and stability of photo-/electro-catalytic reactions strongly depend on the utilized nanomaterials. For example, the band gap structure of a photocatalyst directly affects its light absorption and separation efficiency for photo-induced electrons and holes, which subsequently determines its photocatalytic performance.^{10,11} As a result, the controllable preparation and modification of photo-/electrocatalysts to achieve excellent catalytic activity, selectivity, and stability is essential for advancing catalytic technologies.

Currently, there are many ways to fabricate inorganic catalysts with different morphologies, phases and chemical constitutions, mainly including the top down and the bottomup methods.^{12–15} However, certain inherent limitations in these methods may restrict their broader practical applications across different contexts. In particular, the "top-down" methods often suffer from inconsistencies in the size of particles, probable contamination from the starting bulk raw materials, and lack of ability to achieve perfectly homogeneous chemical compositions, which brings about their reduced effectiveness in all applications where a high degree of accuracy or uniformity is required. On the other hand, while giving much better control over the size and shape of the catalysts, the bottom-up methods have several drawbacks: complex synthesis processes mostly involving multiple steps, high sensitivity to conditions, variable



View Article Online

View Journal | View Issue

[&]quot;School of Environmental and Chemical Engineering, Shanghai University, Shanghai 200444, China. E-mail: sshuang@shu.edu.cn

^bDivision of Molecular Surface Physics & Nanoscience, Department of Physics, Chemistry and Biology, Linköping University, Linköping 58183, Sweden. E-mail: zhangjun.hu@liu.se

yields, and difficulties in reproducibility, which are critical constraints when it comes to scaling up production.¹⁶ Moreover, both "top-down" and "bottom-up" processes may use toxic and expensive chemicals or harsh conditions, posing environmental and safety concerns. These disadvantages highlight the urgent need for developing new methods to fabricate excellent photo/ electro-catalysts.

Recently, the use of radiation technology to control the synthesis and modification of nano-catalysts has received extensive attention.17 Radiation is the emission or transmission of energy via electromagnetic waves or particle beams. The radiation source can be regarded as an energy reservoir, and the energy is released in the form of photons, particles, and other basic carriers. These carriers can transfer energy to matter through direct interactions with atoms and/or molecules, resulting in various unique radiation effects, which are suitable for developing multi-functional nanomaterials for energy storage and conversion (Fig. 1). Recently, several reviews have summarized the use of ion irradiation in the fields of textiles, supercapacitors, microelectronics, and solar cells.10,18-22 However, a comprehensive review encompassing the full spectrum of electromagnetic waves and particle beams is still absent. To this end, this review aims to bridge this gap by thoroughly exploring the characteristics of various ionizing radiation techniques and underscoring the recent progress of

ionizing radiation-mediated synthesis and tailoring of inorganic nanomaterials for energy conversion. We begin with a concise overview of the principles behind radiation technology. Next, we discuss the controlled synthesis and modification of inorganic catalysts with various radiation sources, detailing radiation effects on the catalysts, including defect engineering, phase transformation, heterostructure formation, element doping, band gap engineering, morphology control, and so on. Following this, we highlight recent advances in irradiated catalysts for photo-/electrocatalytic applications, emphasizing the significant contributions of irradiation technology in energy and environmental protection. Finally, we articulate our perspective on the prospects and challenges of using ionizing irradiation technology.

2 Fundamentals of radiation technology

2.1 Fundamental concepts

The term "radiation" refers to the transfer of energy through space or any other medium in the form of electromagnetic waves or subatomic particles (Fig. 2a). In the case of electromagnetic radiation, the spectrum extends from the high-energy gamma (γ) rays at one end to long-wave radio waves at the other, all of which propagate at the speed of light and are capable of



Fig. 1 Schematic illustration of the application of ionizing irradiation technology in photo-/electrocatalysis.



Fig. 2 (a) Schematic illustration of the electromagnetic waves and particle beams accompanied by a comparison of their penetrating capabilities. An overview of the six effects of ionizing radiation on (b) atoms and (c) molecules.¹⁶

transporting energy without requiring a physical medium. In contrast, particle beam radiation is made of atomic or subatomic particles, including protons, neutrons, electrons, and ions. These particles carry enough energy that can interact with atoms and molecules directly with different radiation effects, including radiolysis, photolysis, knock-on collisions and photothermal.16,23 Fig. 2b and c show six common effects observed in substances exposed to different types of radiation sources. Atomic ionization, a key consequence of radiation, involves the ejection of electrons from atoms or molecules, typically caused by high-energy radiation, such as strong X-rays and alpha, beta and γ -rays. These radiation sources cause electrons in shell and nuclear orbitals to be released, as their photon energies exceed the binding energy of the electrons.²⁴⁻²⁶ On the other hand, lower-energy radiation, such as soft X-rays, causes only electron transitions to higher energy levels without inducing dislocation due to the absorption of photon energy by the core electrons.

The response of molecules to irradiation is determined by their structural characteristics. Typically, polar molecules can undergo ionization, leading to the formation of electron-hole pairs. In contrast, electronic excitation is more common in nonpolar molecules and leads to chemical bond dissociation. This phenomenon stems from the intrinsic interactions among electron orbitals that establish chemical bonds. As the energy of radiation extends into the UV, visible light, and infrared ranges, the photon energy becomes more closely aligned with the electronic and vibrational energy levels of molecules. This alignment facilitates molecular and vibrational transitions that promote photochemical reactions and the formation of reactive radicals. At lower energy levels, like those in the microwave range, the photothermal effect induces rotational transitions in polar molecules.

2.1.1 Ionizing radiation. On the basis of energy levels, radiation can be divided into ionizing radiation and nonionizing radiation. High-energy particle beams, made up of subatomic particles and ions and electromagnetic waves of yrays, X-rays, and high-frequency UV rays, are examples of ionizing radiation, all of which have the capacity to ionize electrons in atoms and molecules by ejecting electrons.27-29 Table 1 presents a comparative classification of common irradiation techniques. The controlled adjustment of dose, fluence, and radiation source enables the synthesis and modification of nanomaterials with unique advantages for catalytic reactions. For example, ionizing radiation facilitates precise control over the size, shape, and crystallinity of the nanoparticles (NPs) without the need for hazardous chemicals, thus reducing environmental risks and costs. Additionally, it enables surface modifications, making the process more sustainable and energy-efficient.^{19,21} Additionally, ionizing radiation can intentionally introduce defects into catalysts. By adjusting parameters such as the intensity and energy of irradiating ions and irradiation time, the depth and concentration of defects within the catalysts can be controlled, which is a significant advantage over chemical methods to produce defects. These defects can

Category	Subcategory	Energy ^a	Source	Classification ^b
γ-Ray irradiation	-(<0.001 nm)	$>1.24 \times 10^{6} \text{ eV}$	Electromagnetic wave	Ionizing radiation
X-ray irradiation	Hard X-rays (0.001–0.1 nm)	$1.24 imes 10^4$ – $1.24 imes 10^6 \ { m eV}$	Electromagnetic wave	Ionizing radiation
	Soft X-rays (0.1–10 nm)	124–1.24 $ imes$ 10 ⁴ eV	Electromagnetic wave	Ionizing radiation
Electron beam irradiation	Low energy	0.1-0.3 MeV	Particle beam	Ionizing radiation
	Medium energy	0.3-5 MeV	Particle beam	Ionizing radiation
	High energy	5-10 MeV	Particle beam	Ionizing radiation
Ion beam irradiation	Low energy ion irradiation	Less than 1 keV	Particle beam	Ionizing radiation
	Medium energy ion-irradiation	A few hundred keV to a few MeV	Particle beam	Ionizing radiation
	Swift heavy ion irradiation (SHII)	More than 1 MeV	Particle beam	Ionizing radiation
Neutron beam irradiation	Thermal neutron irradiation	$\sim 0.025 \text{ eV}$	Particle beam	Ionizing radiation
	Cold neutron irradiation	$5 imes 10^{-5}$ –0.025 eV	Particle beam	Ionizing radiation
	Fast neutron irradiation	0.1 MeV	Particle beam	Ionizing radiation
	Fusion neutron irradiation	14.1 MeV	Particle beam	Ionizing radiation
Proton beam irradiation	_	A few keV to a few hundred keV	Particle beam	Ionizing radiation
UV (ultraviolet)	Extreme UV (10–121 nm)	10.2-124 eV	Electromagnetic wave	Non-ionizing irradiation
	Far UV (122–200 nm)	6.2–10.2 eV	Electromagnetic wave	Non-ionizing irradiation
	Middle UV (200–300 nm)	4.1-6.2 eV	Electromagnetic wave	Non-ionizing irradiation
	Near UV (300–400 nm)	3.1-4.1 eV	Electromagnetic wave	Non-ionizing irradiation
Visible light	Visible light (400–700 nm)	1.8-3.1 eV	Electromagnetic wave	Non-ionizing irradiation
IR (infrared)	Near IR (0.7–1.4 μm)	0.89–1.8 eV	Electromagnetic wave	Non-ionizing irradiation
	Middle IR (1.4–3 μ m)	0.41-0.89 eV	Electromagnetic wave	Non-ionizing irradiation
	Far IR (3 μ m -1 mm)	$1.2 imes 10^{-3}$ -0.41 eV	Electromagnetic wave	Non-ionizing irradiation
Microwave	-(1 mm -1m)	$1.2 \times 10^{-6} 1.2 \times 10^{-3} \text{ eV}$	Electromagnetic wave	Non-ionizing irradiation

^{*a*} These energy ranges are typical and can vary depending on the specific application or source. ^{*b*} There is no clear dividing line between ionizing and non-ionizing radiation in the spectrum of electromagnetic waves.

modulate the electronic structure of the catalysts or generate new active sites, which is conducive to improving the catalytic performance. Finally, ionizing radiation is able to treat catalysts uniformly, ensuring consistency and reliability for scaling up to industrial production, thus expanding its practical application.

2.1.2 Non-ionizing radiation. Compared to ionizing radiation, non-ionizing radiation, such as low-frequency UV rays, visible light, infrared light and microwaves, has lower photon energy. This type of radiation can excite electrons or molecules to higher energy states, facilitating molecular transition and rotation.30 Additionally, molecular vibrations and rotations are often accompanied by the release and absorption of thermal energy. For example, UV treatments are gentler and can effectively dissociate ligand bonds, which is favourable for promoting catalytic activity. The power, duration and wavelength of UV irradiation have a critical influence on the synthesis and modification of nanocatalysts.³⁰ The irradiation of visible light is cost-effective, environmentally friendly, and safe, and it has been studied for decades. In contrast to UV and visible light, infrared photons lack sufficient energy to generate free radicals or electrons. Therefore, the synthesis and modification of catalysts by infrared radiation is primarily limited to infrared lasers. Although microwaves have higher photon energies, their primary role in catalyst synthesis is through thermal heating effects. Microwave radiation offers high efficiency and energy conversion rates but faces limitations in scalability. Based on these merits, non-ionizing radiation sources are more prevalent, less costly, and less hazardous than ionizing radiation, making them more common in laboratory settings.

2.2 Characteristics of different irradiation technologies

2.2.1 γ -Ray and X-ray irradiation. Both γ -rays and X-rays are essentially composed of high-energy photons and have good penetration capabilities. However, their origins are different: γ -rays are emitted by the radioactive decay of atomic nuclei, while X-rays are produced when high-energy electrons or ions interact with a substance.31 In recent years, irradiation with both γ-rays and X-rays has been used for the synthesis of metal and metal compound NPs as well as carbon nanomaterials. This is because the γ -ray and X-ray radiation can induce radiolysis of the metal precursor solution, producing active substances such as electrons and free radicals that reduce or oxidize the metal ions to the corresponding elemental state or metal oxides. In addition, their high penetration capacity ensures uniform exposure and treatment of the entire precursor solution, thus promoting the nucleation and formation of NPs with different mass ratios. In this way, it can achieve the precise adjustment of particle size and distribution, which is critical for optimizing their physicochemical properties for a variety of applications.

The overall configuration of γ -ray radiation is depicted in Fig. 3a, primarily including the components of the S-band photocathode microwave electron gun, convergence cavity, pre-acceleration section, and X-band main acceleration section. The γ -ray irradiation process begins with the accelerator generating a continuous beam, which is matched and focused. Laser pulses are generated by collision and scattering in the light source, resulting in the generation of a γ -ray pulse in the direction of the electron beam motion. Following the separation of the deflection magnet and electron beam, the generated γ -ray



Fig. 3 The principles and configurations of various types of irradiations: (a) overview of the construction of a generic electron beam accelerator; (b) structural design for a typical ion implanter; (c) configuration of advanced scattered neutron source accelerators; (d) structure of a proton accelerator; (e) general composition of a γ -ray source accelerator.

enters the γ -ray transmission section, where it is irradiated onto the substance through the collimation hole. Due to their high energy and strong penetration capabilities, γ -rays can pass entirely through the samples, providing uniform irradiation. The γ -ray irradiation process is straightforward to operate and can be conducted in atmospheric environments. Additionally, the sample station exposed to γ -rays is extensive, covering an area of several square meters.³² These characteristics position γ ray irradiation as a promising way of realizing the development of highly efficient, cost-effective, mass-produced, and chemically stable catalysts.

2.2.2 Electron beam irradiation. Electron irradiation accelerators are pivotal tools in radiation processing, primarily using high-energy electrons to treat various materials. As shown in Fig. 3b, a typical electrostatic accelerator includes key components such as an electron source, an acceleration tube, and an irradiation window. Operating in a vacuum, the accelerator propels the emitted electron beam, or X-rays, through the tube, accelerating them to high speeds. The irradiation window and the scanning system are then responsible for scanning the accelerated electrons/X-rays to the required irradiation width, ensuring that the irradiation energy is precisely delivered to the target material. A significant advantage of electron accelerators over other irradiation sources is that radiation dissipates

immediately after shutdown, eliminating the risk of environmental contamination. In addition, the dose rate of the electron accelerator source is significantly higher than that of the ⁶⁰Co source, reaching 3 to 4 orders of magnitude.^{33–35} It is clear that the high efficiency of electron accelerators greatly reduces the irradiation time and increases the yields, making them a key enabler for expanding the production process. Therefore, electron beam irradiation has the potential to play a crucial role in promoting the large-scale production of photo-/electrocatalysts.

2.2.3 Ion beam irradiation. Ion beam irradiation, including ion implantation and ion irradiation, is an effective technique for modification of catalysts. Ion beam modification is typically categorized by energy level, including low-energy ion implantation (below 1 keV), medium-energy ion implantation (from tens of keV to several MeV), and high energy ion irradiation, such as swift heavy ion irradiation (above 1 MeV per amu). Fig. 3c illustrates the construction of a typical ion implanter, highlighting its four key components: the ion source, magnetic selection system, acceleration system and sample stage. In general, the basic process proceeds as follows: firstly, the hot electrons emitted from the ion source filament collide with gas molecules that are exposed to an electric field, resulting in ionization. The ions are then sorted using a magnetic analyzer based on their mass-to-charge ratio. The selected ions are

accelerated through a tube to reach higher energy levels. Finally, the sample is exposed to the ion beam using a deflection scanner. The ion irradiation technique can be used to effectively tailor various catalysts by controlling the ion species, energies, fluence and irradiation angle.^{36,37} This technique offers distinct advantages, including high precision, favourable controllability, and reliable repeatability. Moreover, it allows for fine defect control and flexible element doping in numerous catalyst materials.

2.2.4 Neutron beam irradiation. Neutron irradiation has distinctive characteristics, such as neutral charge, low magnetic moment, strong penetration capability, and a non-destructive effect on target samples. These properties make neutron beam irradiation an ideal tool for studying the static microstructure and dynamic behaviors of matter.^{38,39} In particular, significant progress has been made in spallation neutron sources driven by high-intensity proton accelerators, which have now entered the stage of practical application. As shown in Fig. 3d, spallation neutron source facilities consist of key elements such as a high-energy proton accelerator, a neutron target station, a neutron spectrometer, and the requisite supporting facilities. The principle behind this involves utilizing a high-energy, high-intensity proton accelerator to generate a high-power proton beam. The accelerator bombards heavy metals like tungsten (W) or mercury (Hg) with high-energy protons, triggering complex nuclear reactions, including intranuclear and extranuclear cascades, which produce a high flux of neutrons. Subsequently complex nuclear reactions, including intranuclear and exonuclear cascades of atoms, result in the production of high-fluence neutrons. Then, these neutrons are moderated and utilized for neutron irradiation research. Given its unique advantages, neutron irradiation has the potential to play an irreplaceable role in materials science, sustainable energy development, and other research domains.

2.2.5 Proton beam irradiation. Proton irradiation distinguishes itself as a precise and controllable method for engineering nanomaterials. Its key advantage lies in the proton beam's ability to penetrate deeply with a well-defined range, determined by the Bragg peak phenomenon, where maximum energy deposition occurs. This property facilitates the creation of defects or the introduction of heteroatoms that can regulate band gap, enhance carrier separation, or increase the availability of active sites.⁴⁰ As shown in Fig. 3e, proton irradiation technology commonly utilizes accelerators that include a frontend accelerator and a drift tube linear accelerator (DTL) main accelerator. The front-end accelerators consist mainly of an H⁻ ion source, low energy beam transport line (LEBT), radio frequency quadrupole accelerator (RFQ) and medium energy beam transport line (MEBT). The H⁻ ion source is accelerated by the RFQ to the MEBT, and finally to the DTL main accelerator. Notably, proton beam irradiation ensures a uniform dose distribution, making it particularly advantageous for large areas and irregularly shaped samples. Herein, high-energy protons enable the required modifications on the surface of catalysts, effectively adjusting the electronic and surface properties of catalysts with better catalytic performance.41

2.2.6 UV irradiation/visible light/IR/microwave irradiation. Based on ionizing radiation discussed in the previous sections, including electromagnetic waves and high-energy particles that penetrate deep into catalysts and induce important atomic interactions, non-ionizing radiation, including ultraviolet (UV), visible, infrared (IR), and microwave irradiation, offers distinct advantages. These low-energy radiation features vary in photon energies and wavelengths, enabling controlled interactions with catalysts through excitation, vibration, and thermal mechanisms, rather than through direct ionization or high-energy particle impacts. Non-ionizing radiation methods are particularly valued for their accuracy, efficiency and adaptability in the synthesis and modification of nanomaterials, making them complementary tools in the design and enhancement of photo-/ electrocatalysts.

Typically, UV wavelengths range from 10 to 400 nm, corresponding to photon energies between 3 and 120 eV.16 UV light can be further categorized into near-ultraviolet, mid-ultraviolet, far-ultraviolet and extreme ultraviolet, in descending order of photon energy. The power, duration, and wavelength of UV irradiation significantly impact the growth of NPs. For example, far-ultraviolet and extreme ultraviolet light can act as ionizing radiation, as its photon energy exceeds atomic ionization thresholds. In contrast, visible light, which spans a wavelength range of 400-700 nm, interacts with catalysts in a different manner. Typically, visible light has photon energies between 1.8 and 3.1 eV, which is perceptible to the human eye.⁴² Similar to UV irradiation, visible light can ionize solvents through multiphoton effects, generating reactive groups and solvated electrons. Visible light irradiation is cost-effective, highly controllable, environmentally friendly, and safe, and researchers have been experimenting with this technique for decades. Moving further down the spectrum, infrared (IR) light features even lower photon energies and distinct interaction pathways. Infrared light has a lower photon energy than UV light, with wavelengths ranging from 700 nm to 1 mm, and is further classified into near-infrared, mid-infrared, and farinfrared. Infrared frequencies align closely with the vibrational and rotational frequencies of molecular bonds, allowing infrared photons to be absorbed or emitted by molecules during vibrational or rotational transitions. Different from UV and visible light, infrared photons lack sufficient energy to generate free radicals or electrons, thus limiting their use for the synthesis and modification of inorganic nanocrystals. At the longest wavelengths of the non-ionizing spectrum, microwaves offer unique thermal capabilities. Microwaves, with wavelengths between 1 mm and 1 m and photon energies from 1.24 MeV to 1.24 µeV, differ significantly from higher-energy portions of the electromagnetic spectrum. Microwaves are primarily used for the thermal heating of nanomaterials due to their high efficiency and energy conversion rates, though scalability remains a limitation. Non-ionizing irradiation plays an integral role in the synthesis of metals, metal compounds, and carbon materials.43-45 One of the common advantages shared by both non-ionizing and ionizing irradiation is their high versatility across various materials, eliminating the need for

conventional heating equipment.¹⁶ Consequently, the issues associated with inhomogeneous heat transfer, commonly encountered in traditional wet chemistry, can be effortlessly alleviated.

2.3 Important factors for the radiation process

2.3.1 Irradiation energy (*E*). Irradiation energy, referred to as E, determines the depth to which the implanted particles penetrate the material matrix. Typically, this energy ranges from a few kiloelectron volts (keV) to several megaelectron volts (MeV), resulting in implantation depths from a few tens of nanometers to a few micrometers. Moreover, the penetration depth implanted into a material is linearly proportional to the incident energy.

2.3.2 Irradiation fluence (*j*). The irradiation fluence is usually represented by j and is defined as the number of particles introduced into the surface unit of the material per unit time. It can be expressed by formula (1):

$$j = N/t \tag{1}$$

where j is the irradiation fluence, N represents the number of implanted particles, and t is the irradiation time.

2.3.3 Radiolysis and G-values. Radiolysis is a radiochemical change that describes the dissociation of molecules in the presence of radiation. The process of radiolysis of substances is very complex. Radiolysis products can be a combination of the following: subatomic particles, free radicals, ions and molecules, and to quantify these radiolysis products, the concept of the *G*-value is employed, which represents the number of molecules, atoms, or radicals produced (or consumed) per 100 eV of absorbed energy. Among all substances, water is the most extensively studied in terms of radiolysis, with established *G*-values provided in parentheses, as shown in formula (2).

$$\begin{array}{l} H_2 O \xrightarrow{\text{radiation}} e_{aq^-}(2.7), \ HO^*(2.8), H^*(0.6), \\ H_3 O^+(2.7), H_2(0.47), H_2 O_2(0.75) \end{array}$$
(2)

When water absorbs ionizing radiation, it produces cations, excited molecules, and electrons, which are distributed along the path of the incident particle, creating a localized highenergy region. These primary products undergo rapid transformations, including excited molecule dissociation, ionmolecule reactions, and electron solvation processes to form hydrogen atoms, hydroxyl radicals, and hydrated electrons. Some free radicals interact to form stable molecular products, such as hydrogen and hydrogen peroxide, or recombine to regenerate water molecules. The remaining unreacted radicals diffuse outward as the spike expands, eventually achieving uniform distribution in the aqueous medium.¹⁶ The extent of radiolysis depends on several factors, including the type and energy of the radiation, dose rate, impurities in the system, scavengers, irradiation environment (such as temperature and atmosphere), and the nature and state of the irradiated material.

2.3.4 Absorbed dose (Gy) and dose rate. The absorbed dose is defined as the amount of energy imparted by ionizing

radiation per unit mass of a material. This dose is crucial in understanding the response of the catalyst to irradiation and is commonly measured in units of grays (Gy) or kilorads (krad), where 1 krad is equivalent to 10 Gy. The absorbed dose quantifies the ionizing energy that is transferred to the catalyst, which can cause molecular changes, including ionization and excitation events within the irradiated substance. In addition to the absorbed dose, the dose rate describes the rate of energy delivery over time, typically expressed in units of Gy s⁻¹. The dose rate is particularly important in radiolysis studies, as it affects the distribution and stability of radiolytic species, and thereby the efficiency of synthesis or modification processes. Together, the absorbed dose and dose rate serve as critical kinetic parameters that determine the yield, concentration, and overall quantity of active species produced. These active species play pivotal roles in chemical reactions, facilitating the precise synthesis and functional modification of catalysts.

3 Synthesis and tailoring of inorganic nanomaterials with ionizing radiation

3.1 Material synthesis

The synthesis of inorganic nanomaterials through radiation represents a cutting-edge way to modify chemical compositions and catalyze atomic-level reactions in solution by using highenergy particles or photons. By carefully controlling irradiation parameters, such as energy, fluence and ion species, the size, morphology and crystallinity can be well controlled, enabling the tailored preparation of catalysts beyond the reach of traditional methods. This process entails irradiating a precursor solution in which solvated electrons and free radicals generated by radiation drive reduction or oxidation reactions, culminating in the nucleation and growth of NPs. Therefore, ionizing radiation synthesis offers distinct advantages, including uniform size distribution, minimized aggregation, and improved purity. In addition, it can operate under ambient conditions and avoid the use of toxic chemicals, making it an efficient and environmentally friendly approach that is essential for the sustainable synthesis of nanocatalysts.

3.1.1 γ -Ray and X-ray irradiation. Despite the risk associated with radiation, researchers have shown strong interest in using γ -rays and X-rays for nanomaterials synthesis due to their unique benefits. The primary advantages of γ -ray and X-ray irradiation are simplicity, low cost and zero emission. Typically, the process involves placing a prepared solution in an irradiation chamber, setting irradiation parameters, and allowing the sample to undergo irradiation. Compared to X-rays, γ -rays have higher energy levels, enabling a wider range of applications in nanomaterials synthesis.

In a pioneering study conducted in 1962, Yamazaki and colleagues investigated the effects of γ -rays on the synthesis of Au nanoparticles. They observed the formation of Au sol from an aqueous solution of chloroauric acid under γ -ray irradiation with ⁶⁰Co as the radiation source.⁴⁶ Building on this foundational work, subsequent studies have successfully synthesized both mono- and bimetallic nanoparticles using a similar

strategy,⁴⁷⁻⁴⁹ which has led to widespread exploration of γ -ray irradiation for the synthesis of metal-based nanomaterials. For instance, Kianfar et al. synthesized Pt NPs/reduced graphene oxide (rGO) hybrids using y-radiation. The rGO served as an electron sink, facilitating the formation of Pt nanoclusters and increasing the number of active sites.⁵⁰ They observed that the particle size ranged from 1-8 nm, with an average size of 4.11 nm at an acid ratio (sulfuric to phosphoric acid) of 100. However, at a lower acid ratio of 50, the average size of particles increased to about 71.09 nm. This results indicated that a combination of reducing agents and irradiation creates a highly reducing environment, which favors metal precursor reduction and promotes seed formation and NP growth.^{16,51} Extending the versatility of γ -ray irradiation synthesis, Yu and colleagues prepared Vulcan xc72-supported Pt NPs by y-radiation, NaBH₄ reduction and polyol reduction methods, respectively.⁵² They found that the Pt NPs prepared by γ -radiation exhibited higher ORR activity and Pt utilization, even better than that of commercial Pt/C catalysts. Wang et al.53 also reported the preparation of Pt-decorated MoS_r catalysts using a two-step y-ray radiation-induced reduction method in an ethylene glycol medium. The γ -radiation synthesis approach offered a shorter reaction time and higher yield, demonstrating its potential for practical applications.

Most recently, electron beam irradiation has also been utilized for the synthesis of metal–organic frameworks (MOFs). For example, Zhang *et al.*⁵⁶ reported the synthesis of HKUST-1@Cu₂O heterostructures using γ -radiation under ambient conditions, which exhibited superior catalytic activity in the reduction of *p*-nitrophenol to *p*-aminophenol to the pristine HKUST-1. This approach offers advantages in terms of convenience, environmental compatibility, and significant time and energy savings. Furthermore, the γ -radiation-induced post-synthesis technique can be applied to other crystalline porous materials to produce a variety of derivatives, thus expanding its applicability across diverse fields.

Despite the numerous advantages of y-ray and X-ray irradiation in the synthesis of inorganic nanomaterials, gaining a deeper understanding of the mechanisms underlying crystal formation is essential, as it's crucial for further optimizing their properties and enabling precise control over the synthesis process to achieve desired performance. A key factor in achieving efficient synthesis through γ-ray and X-ray irradiation lies in the modulation of radiation parameters. Among different parameters, precursor concentration plays a significant role, because it influences the final shape, size, and dispersion of NPs. Theoretically, higher concentrations of precursor tend to produce larger particles with lower dispersion, as the nuclei have more reactive atoms available in solution, promoting growth of nanocrystals. However, the effects of irradiation dose on nanoparticle size remain a subject of ongoing research. Some studies reported a decrease in particle size with increasing dose.57,58 For example, Wiguna et al.59 synthesized Ag NPs using γ -ray irradiation. TEM images showed that the Ag NPs were spherical in shape and the average size became larger with increasing irradiation dose. However, others found that particle size increased with the decrease of dose. This variation

highlights the need for precise dose control to optimize particle characteristics. In addition to dose, the dose rate is another critical parameter that influences the growth habits of NPs. The dose rate can affect metal atom production rate, thereby influencing the size and shape of resulting products. According to classical nucleation and growth theory, a higher dose rate leads to a faster production of metal ions, increasing atomic concentration and supersaturation, which reduces critical nucleus size.60 Consequently, smaller sized nuclei form at higher dose rates, resulting in smaller sized nuclei. Recent studies further emphasize the importance of dose rate control in tailoring nanoparticle characteristics. For example, Kepić et al. used low γ -ray doses (1–20 kGy) to prepare Au NPs anchored on RGO sheets, and they observed that higher doses promoted larger particle growth (at 5 and 10 kGy) or a broader particle size distribution (at 20 kGy).61 This result demonstrates that the control of dose rate is important to achieve the desired size and distribution during the process of irradiation-based synthesis.

3.1.2 Electron beam irradiation (e-beam radiation). Electron beam irradiation has been demonstrated to be a versatile and potent technique for the synthesis of nanomaterials. Using high-energy electron beams induces structural changes and catalyzes chemical reactions, providing precise control over the formation of nanomaterials. Through careful modulation of the electron beam parameters, the sizes, shapes, and crystallinity of NPs can be well controlled. A distinct advantage of electron beam irradiation lies in its ability to deliver energy directly to targeted regions. This localized energy delivery enables the synthesis of nanomaterials without the need for hightemperature conditions or harsh chemical environments, making the process both efficient and mild. Thus, electron beam irradiation can enhance the uniformity and purity of catalysts, while significantly reducing the cost. Moreover, ebeam radiation aligns with the principles of green chemistry by reducing energy consumption and minimizing waste production.

Recent empirical studies underscore the efficacy of e-beam irradiation for the synthesis of nanomaterials. For example, Lee and colleagues successfully prepared PVP-stabilized Cu NPs in CuSO₄ solution dissolved in isopropanol (IPA) by e-beam radiation.62 By controlling the beam energy, beam current, and absorbed dose, the particle sizes of the Cu NPs were well tuned. More specifically, they observed that higher beam energy and beam current produced smaller particles, while an increase in radiation dose led to larger particle sizes. Similarly, Zhou et al. prepared colloidal Ag NPs from an aqueous AgNO3 solution using e-beam irradiation. Their results demonstrated that a higher dose rate was necessary to achieve optimal yields of Ag NPs, which underscores the importance of dose rate control in maximizing nanoparticle production. To further explore the comparative efficacy of electron beam and γ -ray irradiation in radiosynthesis, Nguyen et al. synthesized gold nanoparticles (Au NPs) by exposing an aqueous HAuCl₄ solution to both e-beam and γ -ray radiation.⁶³ The results from this work showed that the Au NPs synthesized with e-beam irradiation were significantly smaller than those produced using γ -rays at an

equivalent dose rate, highlighting the enhanced precision of ebeam irradiation for achieving finer particle sizes.

Electron beam irradiation has also been demonstrated to be effective in constructing complex core-shell structured nanocatalysts. For instance, Lee *et al.* used a two-step e-beam irradiation process to fabricate 57FePt@Pt core-shell structures, followed by heat treatment to produce 57FePt@Pt/C catalysts.⁵⁴ As depicted in Fig. 4a, the Fe core is initially formed by a first ebeam irradiation at 80 kGy, followed by a second e-beam irradiation at 40 kGy to form a Pt shell layer. The TEM image of Fig. 4b confirms the successful synthesis of the core-shell structure. The rapid formation of the 57FePt@Pt/C core-shell structure and its excellent electrocatalytic activity demonstrate the suitability of e-beam irradiation for synthesis.

Beyond inorganic nanomaterials, e-beam irradiation has also shown promise in the synthesis of MOFs. Most recently, Chen et al.55 synthesized ZIF-8 by using high energy e-beam irradiation (Fig. 4c-e). The cumulative absorbed dose was 50 kGy in 80 s. For comparison, ZIF-8 can also be synthesized using conventional solvent heating at 140 °C for 24 h to achieve similar crystallinity and yield. Notably, the energy consumption for e-beam irradiation was two orders of magnitude lower than that required under solvent-heated conditions, suggesting that e-beam irradiation offers ultra-rapid synthesis with significant energy savings. This is because the e-beam radiation effectively activates the whole reaction system, forming highly reactive anionic radicals, leading to a reduction of the energy barrier and significantly increasing the nucleation rate of ZIF-8 nanocrystals. The versatility of e-beam irradiation is further demonstrated in the synthesis of other MOFs, such as MIL-53, MIL-101, and MOF-73, under conditions similar to those used for ZIF-8, proving the effectiveness and broad applicability of ebeam irradiation for the synthesis of MOF materials. In addition, e-beam irradiation has shown potential for synthesizing



Fig. 4 (a) Schematic illustration of the synthesis of 57FePt@Pt/C *via* electron-beam irradiation. (b) TEM image of 57FePt@Pt/C. Copyright 2023 Wiley-VCH. (c) The synthesis setup of ZIF-8 *via* electron beam radiation. (d) The photo of ZIF-8 synthesized at an absorbed dose of 50 kGy. (e) SEM image of ZIF-8 at an absorbed dose of 50 kGy.^{54,55} Copyright 2022, Wiley-VCH.

covalent organic frameworks (COFs). For instance, Wang's group demonstrated that COFs can be rapidly synthesized *via* ebeam irradiation, with various products obtainable within minutes under ambient conditions.⁶⁴ This strategy requires only a single radiation source and minimal equipment, presenting a scalable and high-throughput strategy that holds promise for revolutionizing the industrial production of MOFs and COFs.

3.1.3 Non-ionizing irradiation. Similar to ionizing radiation, non-ionizing radiation is versatile for synthesizing a wide range of nanomaterials.¹⁶ However, non-ionizing radiation primarily interacts with substances at the molecular level. In all cases, if not reflected, photon energy is absorbed, exciting molecular motion and heating the substance. Consequently, non-ionizing radiation can produce both photothermal and photochemical effects. When matter is heated to extreme temperatures, plasma may form, with electrons in the plasma potentially inducing further chemical reactions. Due to these effects, it is often challenging to elucidate the precise mechanisms involved during the synthesis and modification process. Moreover, UV, infrared, and visible light irradiation often require photoinitiators, while microwave radiation generates thermal shock waves. The transient rise and fall of high temperatures make the control of size and shape challenging, often resulting in a broader size distribution. Despite these challenges, non-ionizing radiation remains a promising tool for the efficient synthesis of nanomaterials. With growing interest, extensive research is being conducted in this area, indicating substantial potential and room for further development.

3.2 Material modifications

3.2.1 Defect engineering. The presence of defects in catalysts exerts a substantial influence on their catalytic activity. Most recently, numerous research works have demonstrated that defect engineering not only activates the host substrate but also generates more sites, which are beneficial for photo-/ electrocatalysis reactions.65,66 Among various methods, ionizing irradiation stands out for being an impurity-free, highenergy and momentum-driven approach. These distinctive merits render it a promising way to introduce defects into catalysts. Specifically, when energetic particles pass through solid matter, they collide with the nuclei and electrons of the catalyst, transferring kinetic energy. If the recoil atoms in the target gain enough kinetic energy to deviate from their original positions, various atomic-scale defects such as point vacancies are created. Although most point defects disappear in submicrosecond time, some defects persist in the system. Additionally, the electronic structure of the material strongly influences the outcome of electron or ion collisions due to the varying mechanisms by which electronic excitations are converted to heat. In materials with conducting electrons, the action of electronic excitations in nanosystems differs from that in bulk materials due to the different mechanisms. In materials with conducting electrons, the electronic excitations are dispersed, thus reducing their impact. Thus, radiation damage is mainly caused by atomic displacements. In contrast, in insulators, excitation can lead to localized bond breaking. These varied responses of these systems to radiation can be exploited to selectively modify the structure of composites, allowing the tailoring of catalysts with excellent electrochemical properties.

The interaction of irradiation with nanoscale systems often leads to the formation of defects, which can impose size constraints in one or more dimensions. These resulting defects can either enhance or restrict their catalytic behaviours, depending on their nature and distribution. Particularly, in some small-volume nanosystems, electronic excitations generated by irradiation, such as those caused by high-energy electrons or particles, tend to disperse more rapidly. This dispersion reduces their localized impacts, thereby diminishing the overall effects of irradiation in such systems. Therefore, in metallic nanosystems, radiation damage is predominantly caused by atomic displacements, leading to the formation of vacancies, interstitials, or other structural defects. In contrast, in insulators, excitation can lead to localized bond breaking. The different responses of these systems to radiation can be exploited to selectively modify the structure of composites, allowing the tailoring of catalysts with excellent photoelectrochemical properties. However, in bulk systems, all energy is eventually absorbed.⁶⁷ Thus, when energies are high, nanoscale damage is relatively minor as long as displacement cascades do not play a significant role. However, it is not the case that smaller material sizes are better. It is worth noting that the reduction in size leads to a different temperature distribution, resulting in localized temperatures above the melting point, which may have a significant impact on nano-systems, especially in processes such as nanoscale material modification and fabrication. The selection of nanomaterials with appropriate sizes and further exploration of the behaviour of nanosystems under irradiation with energetic particles is crucial for optimizing and controlling the formation of defects, as well as for exploiting the unique properties and functionalities of nanomaterials for various catalytic applications.

For ion beam irradiation, when the incident ions sweep over the surface of the sample, a small number of atoms recoil from the surface. The heavier ions are used to hit the lighter nuclei from the sample and probe the recoil atoms so that the depth distribution of the recoil atoms in the surface region can be obtained. Meanwhile, the deceleration of high-energy ions as they pass through solid matter can be categorized into two mechanisms: electronic stopping and nuclear stopping. A nuclear stopping occurs when the ion collides with the nucleus of the target atom, transferring kinetic energy to the target atom and resulting in translational motion of the target atom. The energy loss is determined by screening the Coulomb interaction. It should be noted that nuclear stopping is only effective for relatively slower and heavier ions of all types. In contrast, electron stopping is influenced by inelastic collisions between moving ions and target electrons, which can be either bound or free. This type of stopping is the result of various physical processes, including ionization of target atoms, electronphonon coupling, and collective electronic excitation such as plasma. At higher ion energies, electron stopping becomes

Recently, Mravik et al. reported the irradiation of MoS₂ nanopowder with C^{2+} ions (energy 20 keV and 40 keV and ion fluences of 5 $\times 10^{14}$ and 10¹⁶ ions per cm²) and H⁺ ions (energy 30 keV and ion fluences of 1016 and 1017 ions per cm2).68 Stopping and Range of Ions in Matter (SRIM) calculations were performed to understand the effects of different ion irradiation sources on the MoS_2 structure. It was found that the lighter H^+ ions penetrate deeper compared to the heavier C^{2+} ions (Fig. 5a). At 20 keV and 40 keV energies, H⁺ ions produce only 6 vacancies per ion, while C²⁺ ions produce 189 and 304 vacancies per ion, respectively (Fig. 5b). Typically, incident ions can be halted on the target material by either electronic or nuclear stopping. Thus, the effect of ion irradiation on the material depends on whether the stopping mode predominates. Electronic stopping leads to ionization and electronic excitation, while nuclear stopping causes bond breaking, atomic displacement, vacancy creation and phonon excitation. It can be seen that the main energy loss mechanism for H⁺ ions is ionization, and therefore H⁺ ions are predominantly blocked by electrons, while nuclear blocking is negligible. If the incident ion is a C^{2+} ion, the main energy loss mechanism is also ionization, but there is a significant amount of energy transfer to the target lattice (phonon excitation) and recoils and successive cascades of Mo and S. The main energy loss mechanism is the ionization of the carbon ion. Thus, electronic stagnation dominates, but the contribution of nuclear stagnation is also significant, which is consistent with higher vacancy production. When irradiating a material, the



Fig. 5 SRIM simulations of ion irradiation effects on MoS_2 using H-30 keV, C-20 keV and C-40 keV. (a) The depth of ion density penetration for each ion type; (b) the analysis of electronic and nuclear stopping powers for the irradiated ions; Copyright 2013 Elsevier Ltd. (c) Schematic illustration of electron transfer from MoS_2 to O_2 adsorbed at defect sites. Copyright 2018, American Chemical Society. (d) Schematic illustration under N⁺ irradiation. (e) The relationship between nuclear stopping powers, electronic stopping powers and projected range under N⁺ irradiation. Copyright 2019, Elsevier Ltd. (f) Schematic illustrations of the formation of Co_3O_4 , Co_3O_4 - O_{v} , and CoO/Co_3O_4 samples. (g) PDOS plots.^{28,68-70} Copyright 2020, Wiley-VCH.

different ion penetration depths in the material may have different effects on the number of vacancies, where the intrinsic reaction mechanisms vary, while the effects of ion energy, fluence and incidence angle on defects such as vacancies remain to be explored.

Luxa et al.⁶⁹ investigated the impacts of radiation (S, Se, Te) on the electrocatalytic performance of bulk MoS₂ nanosheets. The study was conducted with ionic fluences ranging from 1 \times 10^{14} to 1×10^{16} ions per cm² at a mean ion energy of 400 keV. Exploring the penetration of ions in materials provides valuable insights into the formation of defects and the distribution of defect concentrations. Thus, SRIM simulations were carried out to investigate the ion beam penetration of MoS₂. The simulation projected range (the depth at which the maximum ion injection occurs) decreases as the ion mass is increased. The range of individual projections varies as S (338 nm) > Se (162 nm) > Te (105 nm). He et al.²⁸ fabricated a single layer of MoS₂ using 500 keV high-energy Au-ion irradiation. They found that ion irradiation primarily generated S vacancies. As the defect increases, the photoluminescence (PL) peak position shifts from high to low energy levels due to the electron transfer from MoS₂ to the adsorbed O₂ at the defect sites, resulting in electron depletion and hole enrichment (Fig. 5c).

In addition, the modification of catalysts with ion irradiation is inextricably linked to different electron stopping/nuclear stopping mechanisms. Typically, electronic stopping leads to the ionization of the target by releasing electrons, while nuclear stopping leads to bond breaking, atomic displacement and vacancy formation. It is also important to consider the case of electron stop/nuclear stop crossover. Fig. 5d illustrates the interaction between electron stopping and nuclear stopping, as evidenced by SRIM simulations. The simulations show that the nuclear stop is about 10 times higher for Te ions compared to S ions, and that the nuclear stop is dominant for Te ions, whereas the electronic stop is significant for S and Se ions. In addition, vacancy depth profiles were simulated and displacement energies were calculated to estimate the formation of vacancies (Fig. 5e). The results show that ion irradiation mainly leads to preferential sputtering of S atoms, resulting in S vacancies. In addition, numerical simulations of the vacancy depth profiles show that S vacancies are predominantly produced in the case of Se and Te ion bombardment, whereas this effect is much smaller in the case of bombardment with S ions. Moreover, the formation rate of Mo vacancies is significantly lower due to the higher displacement energy value of Mo. Drawing from the aforementioned findings, it is evident that comprehending interactions between the electronic and nuclear stopping mechanisms and their effects on vacancy formation is critical for customizing ion irradiation processes to achieve specific modifications in material properties.

In Huang's study, N^+ ion irradiation was used to modify the crystal and electronic structure of Sb₂Te₃ nanoplates.⁷¹ A series of characterization results revealed that the electronic structure changes induced by irradiation are closely linked to electron stopping and nuclear stopping processes. The relationship between electron stopping, nuclear stopping, incidence range, and energy of N⁺ ions was further evaluated with SRIM (2013)

simulations. The simulation results indicated that the kinetic energy of N^+ ions is dissipated through both electronic and nuclear stopping mechanisms, with a primary implantation depth of 29 nm. That's to say the N-doping enhanced the intrinsic activity of the Sb₂Te₃ catalyst by altering the electronic structure of the surface atoms. Additionally, the electrocatalytic activity and electronic structure of catalysts can be adjusted by introducing various types of defects and increasing the number of dangling bonds around the active site. In particular, the unique ion beam sputtering effect not only strips the surface of the catalyst, but also increases the degree of catalyst roughening, and this irradiated sputtering effect dramatically increases the specific electrochemical area of the catalyst, providing more active sites.

In a recent study, He *et al.*⁷⁰ demonstrated the effective regulation of the surface-active electron density of Co_3O_4 through an argon-ion irradiation method. Through a combination of DFT calculations and characterization of the ultraviolet photoelectron spectrometer spectrum, a notable upshift in the band center of Co_3O_4 was unveiled (Fig. 5f and g). This shift substantially enhanced the adsorption capacity of the oxygen-containing groups and reduced the barrier for the OER, leading to enhanced performance toward water splitting. These results demonstrated that ion radiation could effectively optimize the surface electron density of catalysts, holding the potential for shaping the future rational design and discovery of superior devices.

Remarkably, ion irradiation has demonstrated remarkable efficacy in augmenting the volume of interfacial area through defect and interface engineering, which significantly enhanced their catalytic performance. Recently, Sun et al.72 tuned and optimized the defects and interfacial engineering on PtPb nanoplates by C^+ ion irradiation. By adjusting the C^+ ion fluence, the crystalline phase of PtPb nanoplates was transformed from single crystal to polycrystalline, while the surface layer of PtPb nanoplates was distributed with different degrees of dislocation and subcrystalline boundaries, and some of them were even amorphized. Electrochemical measurement results indicated that irradiation-treated PtPd nanoplates with defects and single-crystal/polycrystalline interfaces and appropriate amorphous phases are favourable for the ORR. In a related study, the same group investigated PtPb nanoparticles under nonaqueous conditions through 1 MeV Kr³⁺ ion irradiation.⁷³ It was found that Kr³⁺ ion irradiation induces the formation of a crystalline/amorphous phase interface characterized by a unique electronic structure. This interface consisted of a crystalline phase surrounded annularly by an amorphous phase, playing a dominant role in lowering the reaction barrier. DFT calculations further confirmed that the novel interface activated the C-H and O-H bonds, optimized the adsorption of hydroxyl groups and intermediates on the surface and promoted the oxidation reaction, ultimately exhibiting enhanced electrocatalytic activity.

Dong *et al.* used a controlled flux of F-ion beams to irradiate MoS₂, combining doping and defect engineering to investigate whether F-ions can effectively modulate the electrical structure of MoS₂ for better HER performance.⁷⁴ Fig. 6a illustrates the



Fig. 6 (a) Schematic illustration of the irradiation process of MoS_2 structure evolution. Copyright 2023 American Chemical Society. DOS of (b) FeNi₃–V_{Fe}, (c) FeNi₃–V_{Ni}, and (d) FeNi₃–V_{Fe}–_{Ni}. PDOS of (e) Fe and (f) Ni atoms under three different structures. (g) Changes in the d-band center. Copyright 2024 Elsevier Ltd.

schematic structure evolution of MoS2 under irradiation. The pristine MoS₂, with a small number of sulfur vacancies, exhibited poor HER catalytic activity. As the ion fluence increased, the concentration of F doping and sulfur vacancies increased proportionally, reaching optimal HER catalytic activity at a fluence of 2×10^{13} ions per cm². However, when the fluence is further increased to 5×10^{13} ions per cm², a large number of disordered regions and subgrain boundaries were generated, resulting in a suppression of HER performance. Additionally, the reduced crystallinity of MoS₂ nanosheets led to an increased number of grain boundaries, with sulfur vacancy boundaries located within or near these grain boundaries being less catalytically active, thereby diminishing HER performance. Moreover, when the concentration of sulfur vacancies became too high, the intrinsic activity of the sites decreased. Although the number of vacancies correlated positively with ion fluence,

excessive lattice symmetry disorder and reduced crystallinity significantly hindered catalytic performance.

Felix *et al.*⁷⁵ provided the first comprehensive study on the effects of γ -radiation on the structural, optical, and magnetic properties of monolayer WS₂ nanosheets, highlighting significant alterations induced by γ -ray exposure. It was found that the interactions in radiometry, such as photoelectric absorption, Compton scattering, pair production, vacancies and fast electrons, played an essential role in modifying these properties. Collectively, these processes lead to notable changes in the electrical, optical and structural properties of WS₂ nanosheets. Experimental results confirmed that the γ -irradiation significantly affected the physical properties of WS₂ nanosheets. X-ray photoelectron spectroscopy (XPS) results revealed that irradiation introduces defects, with defect density increasing along-side irradiation dose. Furthermore, Raman spectroscopy tests showed that as the γ -irradiation dose increased, a blue Raman

shift of the $A_{1g}(\Gamma)$ peak was observed, along with an increase in the Raman intensity ratio between the $A_{1g}(\Gamma)$ and $E^{1}{}_{2g}(\Gamma)$ modes, and an enhancement in the intensity. Notably, at an irradiation intensity of 400 Gy, a phase transition from antiferromagnetic to ferromagnetic behavior was observed, underscoring the profound impact of γ -radiation on the magnetic properties of the WS₂ monolayer.

When a high-energy electron interacts with the nucleus in the target, only a small fraction of the incident electron energy can be transferred to the nucleus due to the conservation of momentum. In this way, high electron energies (greater than or equal to 'threshold energies') are required to displace an atom by electron-nucleus scattering.²³ For instance, to permanently displace an atom in a graphite structure, about 20 eV of energy must be transferred to a carbon atom with an electron energy of 100 keV. Conversely, electron-electron scattering has the potential to induce ionization or bond breaking even at low electron energies. Although this energy transfer typically doesn't lead to atomic displacement, the localized reaction can still cause damage to the targeted materials. The cross-sections for nuclear and electron scattering decrease as electron energy increases. However, observable electron-nuclear scattering effects only occur at energies above the displacement threshold. Thus, the modification of catalysts with electron beams usually requires high energies, and the concentration of defects can be modulated by adjusting different energies and doses. As a result, a comprehensive understanding of these interactions, along with the threshold energies required for atomic displacements, is essential for controlling and optimizing the performance of catalysts at the nanoscale.

Defects induced by high-energy irradiation play a crucial role in expanding the surface area of catalysts, therefore facilitating the greater absorption of pollutants. For example, Sun et al.⁷⁶ successfully enhanced the photocatalytic activity of Ag/Bi2WO6/ CdWO₄ through electron beam irradiation treatment. The intentional irradiation treatment not only induced interface defects but also facilitated the migration of catalytically active substances to the surface of the catalyst, leading to an increase in the content of free hydroxyl groups and significantly boosting the photocatalytic activity. Zhang et al.⁷⁷ synthesized an FeNi₃-16 catalyst with abundant defects by irradiating FeNi₃ with H⁺ ions, which exhibited remarkable electrocatalytic activity towards the OER. The experimental results showed that the introduction of dual metal ion-induced defects activated initially inactive metal sites and significantly improved the OER catalytic performance compared to that of FeNi₃. To further explore these effects, different defect models were constructed using DFT calculations, including iron defects (V_{Fe}), nickel defects (V_{Ni}), and iron and nickel defects (V_{Fe⁻Ni}). The total density of states (TDOS) analysis revealed minimal variation in the electron occupation states. However, partial density of states (PDOS) for Fe and Ni atoms (Fig. 6b-d) showed significant differences. For Fe atoms, the distances between the d-band centers and the Fermi level are -2.47, -2.58, and -2.32 eV, while for Ni atoms, these distances are -1.57, -2.58, and -2.32 eV, respectively. The separation between levels is 1.57, 1.67, and 1.44 eV, respectively (Fig. 6e-g). These results suggest

that H⁺ ion irradiation brings the d-band center closer to the Fermi level, due to the synergistic effects of the dual defects. This closer proximity enhances electron transfer and improves the binding affinity of adsorbed oxygen to metal ions, ultimately boosting OER catalytic activity.

 γ -Ray irradiation is produced by the decay of the radioisotope ⁶⁰Co, and the high-energy photons generated from irradiation have high penetration.78,79 The experimental conditions of γ -ray irradiation are feasible and straightforward, and it can be performed in the ambient environment. Thus, γ -ray irradiation can be performed with a large sample stage area of up to one square meter, making possible the development of catalysts with high efficiency, economy, mass production, and stable chemical properties. y-Ray irradiation plays an important role in changing the surface structure and electronic properties of catalysts by interacting with matter through processes such as the photoelectric effect, Compton scattering, and the electron pair effect.^{32,78} In a recent study, Dong et al.³² used ⁶⁰Co γ-ray irradiation to introduce defects in MoS₂ to optimize HER performance. Interestingly, irradiation induced the generation of abundant sulfur (S) vacancies, which not only increased the number of active sites on the surface but also effectively tuned the intrinsic electronic structure of MoS₂, thus accelerating reaction kinetics and ultimately enhancing the performance of the HER. It is noteworthy that excessive irradiation led to the passivation of S vacancies by oxygen atoms, which reduced the concentration of S vacancies and exhibited inferior electrocatalytic activity. Thus, the appropriate irradiation dose is crucial for enhancing the HER performance of MoS2 nanosheets. These findings highlight the potential of gamma-ray irradiation as a powerful tool to tailor the properties of catalyst materials and provide insights into the development of advanced highly functional photo-/electrocatalyst catalysts. Similarly, Chavda et al.⁸⁰ investigated the effect of γ -ray irradiation on the physical properties of the MoS₂ monolayer. The DFT calculations indicate that the bandgap of MoS₂ decreases as the gamma irradiation dose increases, and the conductivity qualitatively increases due to the creation of additional defect states.

In addition, proton beam irradiation has been increasingly utilized to introduce vacancies into the material. For example, Choi *et al.*⁴⁰ found that the ORR performance of the MnO₂ catalyst can be effectively boosted by high-energy proton particles (14 MeV). The research found the material surface had produced abundant oxygen vacancies through the radioactive decomposition of water along the proton beam. These irradiation-induced oxygen vacancies create additional levels in the conduction or valence band, narrowing the band gap of MnO₂. This narrow band gap enhances the electronic conductivity of oxygen-deficient MnO₂, allowing easier electron transfer between MnO₂ and oxygen molecules.

3.2.2 Phase transformation. Phase transformation engineering has garnered significant attention due to its critical roles in modulating the crystal structure of catalysts to enhance catalytic activity. However, achieving desired crystalline phases or precisely controlled phase transitions at the nanoscale is challenging with conventional hydrothermal methods. In

contrast, irradiation provides precise control over crystal phase transitions due to its nanoscale resolution and adjustable energy and dose parameters. Under optimal conditions, irradiation technology enables the tuning of catalyst structures and induces phase transformations, significantly altering their chemical and physical properties for better catalytic performance.

Recently, Dong et al.81 investigated the enhancement of HER performance in MoS₂ nanosheets through phase transition engineering via 1 MeV e-beam irradiation. Following irradiation, the Raman spectra of MoS₂ nanosheets revealed new characteristic peaks, indicating the formation of the 1T-MoS₂ phase. Additionally, Fourier transform (FT) analysis of the irradiated samples showed a notable decrease in the Mo-Mo bond length, confirming the phase transition. With increasing electron beam fluence, a higher proportion of 1T phases was observed, activating additional electrocatalytic sites on the inert planes, resulting in better HER performance. Yue et al.82 employed 1 MeV electron beam irradiation to convert 2H-WSe₂ to 1T-WSe₂, which induced new characteristic peaks for the 1T phase of W at 31.5 and 33.6 eV, corresponding to the W4f_{5/2} and W4f_{7/2} states in WSe₂. Additionally, new selenium peaks emerged at 54.6 and 55 eV, with binding energies for Se3d_{5/2} and $\text{Se3d}_{3/2}$ measured at 5 eV. These changes in binding energy indicated alterations in lattice symmetry due to the irradiation. As irradiation fluence increased, the crystalline phase of WSe₂ transitioned from 2H to 1T. The 1T-WSe₂ structure not only activates previously inert basal planes and increases the total number of active sites but also improves electrical conductivity, thereby enhancing electron transport efficiency and exhibiting enhanced HER performance. Similarly, Jouini et al.83 utilized yray irradiation to induce a phase change from NiO to Ni₂O₃. Fluorescence quenching behavior indicated the degradation of NiO and its transformation to Ni₂O₃.

3.2.3 Morphology control. The morphology of a catalyst influences not only its surface area but also the exposure of active sites, diffusion pathways, and the overall reactivity properties. By adjusting parameters such as particle beam density, energy and irradiation time, the chemical composition and morphology of the catalyst surface can be precisely controlled. Recently, Kozlovskiy et al.84 investigated the structure and morphology of TiO₂ thin films with O²⁺ ion radiation with an irradiation dose of 10¹⁴-10¹⁶ ions per cm². The irradiation mechanism can be described as follows: the low energies of the incident ions lead to the approximately equal probabilities of elastic interactions and inelastic interactions. Consequently, the probabilities of point defect formation and initial atomic breakdown are also equal. The transfer of energy from the incident nucleus to the target nucleus is so strong that it can easily break chemical and crystal bonds. As a result, the oxygen atom is displaced from its equilibrium position due to its lighter mass compared to the titanium atom. Once the oxygen atom deviates from its equilibrium position, irradiationimplanted oxygen ions with high residual energy progressively fill cavities and gaps as they move across the surface of nanostructures, which distorts the crystal structure. In addition, the electrons generated by the collision form a secondary

breakdown electron cascade, exacerbating the structural distortion. The results show that high doses of irradiation resulted in the appearance of mound-like and wavy inclusions in the films. Due to the magnetron sputtering of the film formation process, the initially synthesised films contain a small number of defects and dislocations. However, during the irradiation process, the energy transferred to the target atoms greatly exceeds the binding energy of the target nucleus, resulting in the lighter atoms being impacted out of the target nucleus and detached from their lattice sites, and the lattice being deformed as well. An orthogonal lattice structure characterised by three crystal axes leads to anisotropic deformation and the formation of defects and hollow regions. These regions can be filled with implanted oxygen atoms. Furthermore, the deformation and distortion of the crystal structure leads to changes in the lattice volume, and some of the deformed regions are squeezed towards the grain boundaries, which are the source of defects. The modification of thin films by ion beam irradiation will lead to the change of grain orientation and further change of morphology, which is beneficial for us to reasonably regulate the morphology of catalyst materials to obtain the ideal catalytic performance.

In particular, helium implantation has some advantages in the modification of the shape of the material. As a light element, it can cause little damage to catalysts, and it is easy to form gas bubbles. Recently, Liu and his colleagues⁸⁵ have developed porous TiO₂ nanorod array photoelectrodes by using He⁺ ion implantation to enhance photoelectrochemical water-splitting. Generally, when He atoms are implanted into TiO₂ nanorod arrays, their insolubility in water allows them to be easily trapped by defects, forming bubbles as the fluence is increased or the temperature is raised. The study revealed that the size of the bubbles increased as the irradiation fluence increased. Additionally, annealing the sample in air at 500 °C resulted in larger bubbles and a more uniform distribution. The annealing process allowed the bubbles to absorb other dispersed helium atoms and vacancies. At high enough annealing temperatures, some He atoms escape from the bubbles and form nanoholes. This process generates a large number of nanoholes in the implantation layer of TiO₂ nanorod arrays (NRAs). The formation of nanoholes effectively improves the hole trapping rate and charge carrier separation efficiency, and inhibits recombination, which therefore improves the photo-/electrocatalytic performance. Similarly, the combination of He⁺ ion implantation and post-annealing methods to regulate the morphology of α -Fe₂O₃ for enhanced photoelectrochemical performance has also been investigated by Wu et al.⁸⁶ As the irradiation increases, a significant number of nanocavities are formed inside the He⁺ ion-implanted α-Fe₂O₃ NRAs. Relevant studies have shown that reasonable control of the parameters of helium ion irradiation fluence and thermal annealing can modulate the catalyst morphology to obtain more efficient catalytic performance.

3.2.4 Element doping. High-energy irradiation offers a pollution-free approach with precise control over impurity distribution, enabling high-purity doping with excellent uniformity.¹⁰ Functionalization of catalysts by doping heteroatoms through irradiation techniques shows significant

promise.87 Notably, medium-energy ion beams and high-energy γ -ray irradiation can penetrate the surface from several hundred nanometers to micron-scale depths, facilitating modifications in various nanostructured catalysts.²¹ Recently, high-energy ionizing irradiation technology has been used to dope heteroatoms into TiO₂, WS₂, NiO and graphene to boost their photo-/electrocatalytic activity. Specifically, WS2 is a promising electrocatalyst, but still faces serious challenges due to its poor electron transfer ability, lack of available active sites and poor long-term stability.88-90 In order to overcome these inherent drawbacks and further enhance the HER activity, numerous studies have been devoted to the improvement of electrical conductivity and the generation of more active sites.⁹¹⁻⁹³ Among them, doping Fe ions is a promising strategy for tuning its electronic structure and modulating the hydrogen adsorption energy on its surface. Typically, the introduction of Fe ions is achieved through ordinary hydrothermal methods, which face many problems such as uneven doping, long reaction time, and low success rate.^{91,94} Recently, Cao et al.⁹⁵ reported that Fe¹³⁺ ions were successfully introduced into WS₂ after irradiation under the fluence of 8×10^{13} and 5×10^{14} ions per cm² followed by annealing treatment. Within a few picoseconds, Fe13+ ion irradiation created multiple vacancies in WS₂, enabling the incorporation of Fe ions. The XPS results confirmed the existence of Fe²⁺ and Fe³⁺ in the sample. This catalyst exhibited superior HER electrocatalytic activity in alkaline medium after irradiation, and the improved HER activity was attributed to the exposure of more active sites on the inert basal plane of WS2 and the improved electrical



Fig. 7 (a) XPS spectra of F 1s from irradiated MoS_2 and (b) line-scan profiling analysis of irradiated MoS_2 . Copyright 2018, American Chemical Society. (c) Schematic illustration of the formation of NiO/ NiFe₂O₄. Copyright 2021, Wiley-VCH. (d) HRTEM images of pristine ReS₂ nanosheets with observation direction [001], (e) Ar⁺ ion beam irradiation of ReS₂ nanosheets for 10 s, (f) 30 s, and (g) 60 s.^{74,84,96,97} Copyright 2018, Wiley-VCH.

conductivity due to the Fe-doping, which thereby reduced the resistance to charge transfer, and accelerated the electron transfer.

Dong *et al.*⁷⁴ doped F ions into MOS_2 by heavy-ion irradiation, achieving successful doping through XPS analysis. The chemical compositions and valence states of MOS_2 NSs before and after irradiation are shown in Fig. 7a. Generally, the F 1s peak is located at ~688 eV in the XPS spectrum. However, F 1s does not show a significant peak in the XPS spectrum of $F-2 \times 10^{13}$. This is because the XPS penetration depth is less than ~10 nm, which limits the detection of the sample surface. Line-scan profiling in Fig. 7b further confirms successful F doping in MOS_2 . All of this suggests that ion beam irradiation serves as a novel and effective method for elemental doping.

 γ -Ray irradiation is a promising, convenient and environmentally friendly method for the production of graphene-based nanomaterials. It also contributes to the reduction of metal ions and the modification of the carbon properties and the chemical reactions on the surface. Recently, Rahman *et al.*⁹⁸ have synthesized a N-doped RGO-supported Fe-based catalyst with 100 kGy γ -ray irradiation, and the percentage by weight (wt%) of Fe loading is in the range of 10% to 20%. XRD, Raman, FTIR, and EDS characterizations revealed that the γ -ray radiation effectively introduced N and Fe into the sample. The N-doping increases the electron density and forms N-support sites with carbon and iron, which directly improved its ORR performance. Additionally, the strong interactions between Fe-N_x and O₂ facilitated rapid electron transfer.

Recently, Ghicov *et al.*⁹⁹ investigated the effects of N ion implantation on the structure and doping efficiency of TiO₂ nanotubes, using ion fluences of 1×10^{15} and 1×10^{16} ions per cm² under 60 keV acceleration energy. At a high fluence of 1×10^{16} ions per cm², the ion implantation disrupts the original morphology of the self-organized TiO₂ nanotubes, resulting in complete amorphization of the anatase structure. This amorphous state, however, created traps for photogenerated electron-hole pairs, leading to reduced photocurrents in the UV range. Interestingly, despite these structural alterations, the specific dose of 1×10^{16} ions per cm² enabled effective N doping, which enhanced the photo-response in the visible range.

Different forms of heteroatom doping play distinct roles in enhancing catalyst properties, necessitating the strategic selection of ions for catalyst irradiation. Recently, Liu et al. 100 investigated the effects of noble metal nanoparticles and metal (Fe, V) and non-metal (N) doped TiO₂, using energies from 20-50 kV and fluences ranging from $0.1-20 \times 10^{16}$ ions per cm². After ion implantation and annealing treatments, the photocatalytic activity of the Au-TiO2 samples was enhanced, which was attributed to the increased absorption of incident light by Au nanoparticles, enhanced local electric field and reactive electron and hole excitation. Additionally, a Schottky junction also formed when Au nanoparticles made direct contact with the TiO₂, significantly promoting electron-hole separation and reducing recombination. For Fe-doped TiO₂, the mixing of Ti⁴⁺ 3d and Fe³⁺ 3d orbitals introduced new energy levels into the TiO₂ band structure, increasing visible light responsiveness.

Meanwhile, V doping accelerated the phase transition of TiO_2 from anatase to rutile. In the case of N-doped TiO_2 , experimental and theoretical analyses demonstrated that replacing oxygen with nitrogen created isolated N 2p localized states above the O 2p-dominant valence band. The mixing of N 2p and O 2p states reduced the TiO_2 band gap, enhancing visible light absorption. Overall, TiO_2 thin films prepared *via* ion irradiation with Au, Fe, V, and N were highly crystalline, stable, and showed improved photocatalytic activity under visible light. These promising results underscore that different ion sources have varying effects on the structural and physicochemical properties of catalysts, emphasizing the importance of tailored doping strategies.

3.2.5 Band gap engineering. Generally, the ideal photocatalyst should have a band gap of 1.8-2.3 eV, which allows for effective visible light absorption and generates sufficient photogenerated charge carriers.¹⁰¹ However, many common photocatalysts have larger band gaps, such as ZnO, SnO₂ and TiO₂ (3.2 eV), limiting their visible light utilization. To address this, regulating the band gap of these semiconductor photocatalysts can improve their optical and electrical properties for better performance. In particular, doping metal ions is a widely employed tactic for introducing impurity levels into the forbidden band gap, thereby narrowing the band gap to facilitate the absorption of visible light. The impurity levels are strategically positioned above the valence band or below the conduction band, functioning as acceptor or donor levels, respectively. Specifically, the presence of acceptor levels and donor levels affects key properties of semiconductors such as light absorption, carrier lifetime, and photoconductivity. The acceptor level is located near the conduction band, where it traps electrons in the conduction band, thereby affecting the electron concentration and conductivity of the semiconductor. Meanwhile, donor levels are located near the valence band, which provides additional free electrons and increases the conductivity of the semiconductor.

There are many methods for doping metal ions into wide bandgap materials, such as co-precipitation synthesis and advanced ion implantation.102-105 Unlike the conventional chemical methods that yield unstable metal ion doping, advanced physical doping methods (e.g., ion beam irradiation) can effectively dope metal ions into catalysts in a controlled manner.¹⁰⁶ Specifically, ion irradiation not only facilitates metal ion doping but also alters the electronic and surface properties of catalysts, making it particularly effective for doping. In a recent work, hydrothermal growth of ZnO nanorod arrays on fluorine-doped tin oxide (FTO) substrates was reported by Wang *et al.*, followed by doping with varying fluxes $(3 \times 10^{15}, 5 \times 10^{15})$, and 2×10^{16} ions per cm²) of Cu ions using ion implantation techniques.107 The doping of Cu ions within the forbidden band gap notably reduces the band gap of ZnO, attributable to the introduction of impurities in the form of Cu²⁺ and Cu⁺ states. Electrons in the valence band can be excited to additional copper doping levels and subsequently enter the conduction band of ZnO when exposed to visible light, thereby expanding the light absorption range of the Cu-doped ZnO nanorods. Similarly, Cai et al.¹⁰⁸ successfully prepared ZnO NRs doped

with V ions by an ion implantation method (energy of 50 keV, flux of 2.5×10^{14} – 5×10^{15} ions per cm²). The introduction of impurity donor levels through the doping of V⁴⁺ ions within the forbidden band has been observed to notably reduce the band gap of ZnO, thereby extending the light absorption of ZnO NRs into the visible region. As a result, the V-ion doped ZnO NRs exhibited superior photocatalytic activity to pristine ZnO. Under visible light irradiation, the V-ion doped ZnO NRs demonstrated the ability to excite additional electrons from the V⁴⁺ dopant into the conduction band of ZnO. Furthermore, as the V ion implantation dose increased, so did the charge carrier density, leading to the generation of more electrons and holes for water oxidation reactions.

3.2.6 Heterostructure formation. The creation of heterojunctions in a hybrid nanosystem can effectively enhance the catalytic performance of catalysts.¹⁰⁹ The heterogeneous structure not only expands the electrode surface area, but also increases the contact area of the reactants on the catalyst surface, thereby achieving high catalytic activity. Ionizing irradiation facilitates the formation of distinct heterogeneous structures due to its controllability and the non-uniform distribution of energy.^{110,111} In particular, ion beam irritation offers a precise method for adjusting the electronic structure of a catalyst by promoting the formation of two distinct nanostructures. For example, if the impact caused by the implanted ions exceeds the solid solubility of the material, these ions will disperse and aggregate on the surface of the material, resulting in the formation of NPs.¹¹² By carefully controlling the implantation-precipitation process, it is possible to create heterostructures within the catalyst, which have the potential to significantly enhance the intrinsic activity of the catalyst. Recently, Zhong et al.96 have successfully fabricated a NiO/ NiFe₂O₄ heterostructure by the controlled irradiation of NiFe layered double hydroxide (LDH) nanosheets with Ar⁺ ions (Fig. 7c). During irradiation, the incident Ar^+ ions undergo a series of collisions with NiFe LDH atoms. When the energy of the injected Ar⁺ ions exceeds the displacement energy, NiFe LDH atoms are ejected from the lattice and a large number of atomic voids are formed. Due to the lower displacement energy, O and H atoms are more easily ejected from the lattice. As the fluence increases, more and more H and O atoms are displaced, leading to the transformation of NiFe LDH into NiO and amorphous NiFe2O4. The DFT calculations revealed that this heterogeneous structure effectively reduced the energy barrier for the O^{*} to OOH^{*} transition. The synergistic effect of NiO and NiFe₂O₄ enhances the reaction kinetics and accelerates the charge transfer as well as increasing the active site exposure, thereby exhibited better OER performance.

4 Catalytic applications

4.1 Electrocatalysis

Electrochemical water splitting for hydrogen production is a highly promising strategy for sustainable energy supply, offering a clean alternative to reduce reliance on fossil fuels. However, the inherent slow kinetics of the HER and OER necessitate the use of highly active catalysts.^{113,114} Noble metals, Open Access Article. Published on 27 November 2024. Downloaded on 8/2/2025 8:28:20 AM. This article is licensed under a Creative Commons Attribution 3.0 Unported Licence. (cc)) BY

Table 2 Summary of the applications of various types of irradiation technology in synthesis/modification of electrocatalysts from recent work

Catalyst materials	Irradiation sources	Energy	Fluence	Roles	Application	Ref.
Thin-layer MoS ₂ MoS ₂ nanosheets	γ-Ray irradiation/ ⁶⁰ Co Electron beam irradiation	— 1 MeV	100 rad s ⁻¹ (0.1, 1, 10, 100 Mrad) 5 × 10 ¹⁴ , 5 × 10 ¹⁵ , 1 × 10 ¹⁶ e cm ⁻²	Defect introduction Defect introduction and phase	HER HER	32 81
Bulk MoS ₂ Layer MoS ₂	Ion beam irradiation/S, Se, and Te Swift heavy ion irradiation/Xe	400 keV 91 MeV	$\begin{array}{l} 1\times10^{14}1\times10^{16} \text{ ions per cm}^2 \\ 5\times10^{12},2\times10^{13} \text{ and } 5\times10^{13} \text{ ions per} \end{array}$	transformation Doping and vacancy introduction Vacancy introduction	HER HER	69 94
MoS_2	Ion beam irradiation/C ⁺	3 MeV	cm^2 5 $\times 10^{12}$, 2 \times 10 ¹³ and 5 \times 10 ¹³ ions per	Defect engineering	HER	115
WS ₂ Bi ₂ Te ₃ nanosheets	Ion beam irradiation/Fe ¹³⁺ Ion beam irradiation/Fe ¹⁰⁺	— 320 keV	${ m cm}^2$ 8 $ imes$ 10 ¹³ and 5 $ imes$ 10 ¹⁴ ions per ${ m cm}^2$ 4 $ imes$ 10 ¹⁴ ions per ${ m cm}^2$	Fe-doping and vacancy introduction Defect introduction and surface	HER HER	95 116
$\mathrm{Sb}_{2}\mathrm{Te}_{3}/\mathrm{Ti}$	Ion beam irradiation/N $^{+}$	15 keV	2×10^{14} , 2×10^{15} , and 2×10^{16} ions per	modification Doping and defect introduction	HER	71
Si	Ion beam irradiation/Ar ⁺	90 keV	cm^2 5 ×10 ¹⁶ –2 × 10 ¹⁷ ions per cm ²	Morphology control	HER	117
MoSe ₂ nanosheets	Ion beam irradiation/Ar ²⁺		5×10^{-14} , 5×10^{-15} ions per cm ²	Vacancy introduction	HER	118
WSe_2	Electron beam irradiation	1 MeV	$1 imes 10^{1.5}, 1 imes 10^{1.4}, 5 imes 10^{1.4}, 1 imes 10^{1.5}, 1 imes 10^{16}$ a cm ⁻²	Phase transformation	HER	82
${ m Ti}_3{ m C}_3{ m T}_7$ mxene	y-ray irradiation/Core fuel bundles	I	$500 \text{ Gy } \text{h}^{-1}$ (100, 300 kGv)	Morphology control	HER	119
12- Tungstophosphoric acid	Ion beam irradiation/C ⁺	10 keV	5×10^{14} -2.5 × 10 ¹⁵ ions per cm ²	Structural modification	HER	120
Single-layer MoS ₂	Ion beam irradiation/Au	500 keV	$5 imes 10^{11}$ – $1 imes 10^{14}$ ions per cm 2	Defect engineering	HER	28
CoO/Co ₃ O ₄	Ion beam irradiation/Ar ⁺	50 keV	5×10^{15} ions per cm ²	Morphology control/phase	OER	70
(+ • • • • • • • • • • • • • • • • • • •			transformation		c I
Co ₃ O ₄ -Ov	Ion beam irradiation/Ar	25 keV	5×10^{-5} ions per cm ²	Oxygen vacancy introduction	OER	20 20 20
	Ion beam irrediction/Ar ⁺	JOD LeV	3×10^{-10115} pet CIII 1 10 20 20 40 $\times 10^{15}$ ions nor am^2	IN-UUPILIS ALLA VACALICY IIILUUUUCUULI Ustaroctuustuse formation	OED	171
Dt/NGV	1011 Dealth Intaulation/Al v-Rav irradiation/60Co	100 KCV	1, 10, 20, 30, 40 \times 10 10115 per CIII 140 kGv	Membology control	OER	47
Pt-Ru/HOPG	Ion beam irradiation/N	100 eV	4×10^{15} -9.6 $\times 10^{16}$ ions per cm ²	Doping and defect	ORR	166
Fe/N-rGO	γ -Ray irradiation/ ⁶⁰ Co		100 kGy	Fe/N-doping	ORR	98
CN/Pt , $g-C_3N_4$, Pt	γ -Ray irradiation		$20, 60, 100, 140, 180 \mathrm{kGy}$	Material synthesis	ORR	167
${ m Pt}_{0.9 m nm}/{ m Pt}_{25}{ m Ni}_{75}(111)$	Ion beam irradiation/ N_2^+ , N_2^0	≤100 eV	1	Material synthesis	ORR	168
Pt-CeO _x nanowire/C	Proton irradiation		5 kGy	Defect introduction	ORR	41
MnO_2	Proton irradiation	14 MeV	I	Vacancy introduction	ORR	40
Pd/CNT	γ -Ray irradiation/ ⁶⁰ Co		15, 25, 50, 100 kGy	Material synthesis	ORR	169
PRGO	γ -Ray irradiation/ ⁶⁰ Co	1.33 MeV	15, 25 kGy	Vacancy introduction	ORR	129
Pt NPs/GC	Ion beam irradiation/Ar	380 kev	$7.5 imes 10^{15}$ ions per cm ²	Defect introduction	ORR	128
Pt/CN-CB	γ-ray irradiation/ ⁶⁰ Co		140 kGy	Material synthesis	ORR	170
Pt/HOPG	Ion beam irradiation/Ar ⁺	1 keV	$1.0 imes 10^{14} { m ~ions~per~cm^2}$	Vacancy introduction	ORR	171
Pt/HOPG	Ion beam irradiation/Ar	100 eV	${\sim}5 imes10^{16}~{ m ions~per~cm^2}$	Defect engineering	ORR	172
Pt/HOPG	Ion beam irradiation/N	100 eV	${\sim}5 imes10^{16}$ ions per cm 2	N-doping	ORR	173
Pt-Ru/HOPG	Ion beam irradiation/Ar	100 eV	4×10^{15} –9.6 × 10^{16} ions per cm ²	Doping and defect	ORR	174
PtPb nanoplates	Ion beam irradiation/C ⁺	10 eV	$1 imes 10^{16}, 2 imes 10^{16}, 3 imes 10^{16} ext{ ions per cm}^2$	Defect engineering and interface	ORR	72,73
				engineering		
GY-PtPd	γ -ray irradiation		150 kGy	Material synthesis	ORR	175
Fe-N-C	Electron beam irradiation	10 eV	80 kGy	Forming Fe–N _x active site	ORR	176
PtNPs/NrGO	γ -Ray irradiation/ ^{ov} Co		100 kGy	Morphology control	ORR	177

such as Pt and IrO₂, exhibit excellent electrocatalytic activity, but their scarcity and high cost pose significant barriers to large-scale application. Transition metal-based compounds, such as those containing, *e.g.*, Fe, Co, Ni, Mo and W, offer a promising alternative due to their abundance and easy synthesis. However, optimizing these materials to achieve outstanding catalytic activity and high stability for practical applications remains a major challenge. In this context, ionizing and non-ionizing radiation techniques offer unique merits for the development of catalysts toward water splitting (Table 2). By creating atomic-scale defects, activating surface sites, and altering the electronic structure of the catalysts, radiation can significantly enhance their intrinsic electrocatalytic activity.

4.1.1 Hydrogen evolution reaction (HER). Recently, twodimensional layered chalcogenides, such as MoS₂, WS₂ and MoSe₂, have emerged as a promising, cost-effective alternative to Pt.122,123 Nevertheless, the catalytically active sites of these layered chalcogenides are primarily located at the edge sites, whereas the basal plane remains largely inert toward the HER.¹²⁴ Given that the surface area of the basal plane of 2D layered chalcogenides significantly surpasses that of edges, introducing defects into the basal plane can effectively improve the number of active sites for better performance. However, it's a challenge to achieve controlled defect introduction into the basal plane. Coincidentally, ionizing irradiation offers several advantages for introducing defects into the basal plane of MoS₂. Firstly, ionizing irradiation operates on a high-energy and momentum-driven basis, facilitating a swift and efficient introduction of defects into the basal plane, enabling a timeefficient and scalable process. Secondly, ionizing irradiation can precisely tailor the number and distribution of defects in the basal plane by adjusting the irradiation parameters, which allows for a precise modulation of electrocatalytic behaviours. Furthermore, ionizing radiation is a non-chemical and impurity-free strategy, ensuring that the introduced defects do not compromise the structural integrity of the material, maintaining the favourable electronic structure.

Recently, Xia et al.¹¹⁸ have synthesized defective MoSe₂ nanosheets on carbon cloth by a CVD method and it was found that the intentional irradiation with high energy Ar²⁺ ions $(5 \times 10^{14} \text{ and } 5 \times 10^{15} \text{ ions per cm}^2$, respectively) had induced multifold in the basal plane. Four types of vacancy were observed in their work: native Mo and Se vacancy (V_{Mo} and V_{Se}), double Se vacancy (V_{Se2}) , and the absence of one MoSe₂ (V_{MOSe2}) . As expected, the irradiated MoSe₂ with a dose of 5×10^{15} ions per cm² displayed a much lower overpotential and Tafel slope than those of pure MoSe₂. The improved HER performance can be attributed to the increased catalytic sites and optimized electronic structure due to the formed vacancies. Sun et al.115 utilized C⁺ ions to irradiate MoS₂ with an energy of 3 MeV at various ion fluences $(5 \times 10^{12}, 2 \times 10^{13}, \text{and } 5 \times 10^{13} \text{ ions per}$ cm²). The ion irradiation activated the inert basal plane of MoS₂ NSs by introducing numerous S vacancies, which thereby exhibited much improved HER performance. Additionally, it was found that different ion fluences could modulate the number of S vacancies and amorphous phases on the MoS₂

substrate. In particular, the MoS₂ nanosheets irradiated at an ion fluence of 2×10^{13} ions per cm² exhibited the best HER performance with an onset potential of 77 mV and a Tafel slope of 66 mV dec $^{-1}$. In addition, the ion species, energy, fluence, and other irradiation parameters has distinct effects on vacancy formation within the catalyst. Madauss et al.94 reported a new method to improve the HER performance of MoS₂ by using a rapid heavy Xe ion irradiation (irradiation energy 91 MeV). At -0.6 V vs. RHE, the irradiated MoS₂ sample exhibited a higher current density (35.3 mA cm⁻²) than pristine MoS₂ (-13.3 mA cm^{-2}). The irradiated samples also had a smaller Tafel slope $(104 \text{ mV dec}^{-1})$ compared to pristine MoS₂ (106 mV dec⁻¹). He et al.28 fabricated a single layer of MoS2 using 500 keV highenergy Au-ion irradiation. They found that ion irradiation primarily generated S vacancies. As the defect density increases, the photoluminescence (PL) peak first blueshifts and then redshifts due to the electron transfer from MoS₂ to the adsorbed O₂ at the defect sites.

 γ -ray radiation serves as a source of high-energy photons with strong penetrating ability, allowing strong penetration through the sample and ensuring a more uniform irradiation effect. In a recent study, Dong et al.32 employed ⁶⁰Co γ-ray irradiation to modify MoS₂ nanosheets at doses of 0.1, 1, 10, and 100 Mrad to investigate the effect of irradiation fluence on the electrocatalytic performance. A series of characterizations showed that numerous S vacancies were produced on the MoS₂ nanosheets after irradiation. Electrochemical measurements showed that at a dose of 10 Mrad, MoS₂ nanosheets achieved a low overpotential (η_{10}) value of 269.4 mV to achieve a current density of 10 mA cm⁻² with a Tafel slope of 65.96 mV dec⁻¹, which was much smaller than that of bare MoS_2 (327.4 mV, 130.88 mV dec⁻¹) and the irradiated samples with 100 krad $(121.23 \text{ mV dec}^{-1})$, 1 Mrad $(74.97 \text{ mV dec}^{-1})$ and 100 Mrad $(74.97 \text{ mV dec}^{-1})$ of MoS₂, respectively. The above results indicated that the introduction of S vacancies increased the number of active sites on the MoS₂ nanosheets, resulting in better HER performance. Subsequently, the same research group employed 1 MeV electron irradiation to irradiate MoS₂ nanosheets, discovering that, besides forming S vacancies, it also induced a transition from the 2-H phase to the 1-T phase.⁸¹ This transition can be attributed to the charge redistribution associated with electronic excitation, the formation of S vacancies, and the accumulation of mechanical strain in defective MoS₂ nanosheets. The formation of S vacancies and the 1T phase transition during irradiation greatly enhanced the HER activity. In particular, when the irradiation fluence reaches 5×10^{14} e cm⁻², a current density of 10 mA cm⁻² can be achieved with an initial overpotential of only 141 mV and an overpotential of 235 mV.111 Similarly, Li et al.82 achieved the conversion of 2Hphase tungsten selenide (2H-WSe₂) to 1T-phase tungsten selenide (1T-WSe₂) under 1 MeV electron irradiation. At an irradiation fluence of 5 \times 10¹⁴ e cm⁻², the minimum onset overpotential of WSe2 was 247 mV (vs. RHE), much lower than that of the as-prepared WSe₂ (348 mV.) The Tafel slope of 1T-WSe₂ was 67 mV dec⁻¹, which was also lower than that of unirradiated WSe₂ (117 mV dec⁻¹). The enhanced electrocatalytic performance of WSe2 under electron beam irradiation

is attributed to the presence of 1T-WSe₂ components in properly irradiated samples. However, it's important to note that further increases in irradiation fluence lead to agglomeration of WSe₂, which severely hindered the exposure of catalytically active sites and resulted in the decrease of HER catalytic activity.⁹²

More recently, in an innovative work by Huang et al.,⁹⁷ Re vacancy defects were intentionally introduced in ReS₂ by a controlled Ar ion beam bombardment. The presence of Re vacancies not only generates enough unsaturated bonds but also affects the intrinsic charge compensation of the S-Re-Re bond, leading to the adsorption of H⁺ being neither too strong nor too weak. In addition, the vacancy densities increase with the increase of the ion beam intensity. When the irradiation time was extended to 60 s, a significant increase in lattice defects was observed, and most of the zigzag Re-Re chains were disrupted, which impeded the adsorption of H⁺ at the active site. The HRTEM images, as illustrated in Fig. 7d-g, demonstrate that Ar⁺ ion beam irradiation is conducive to the formation of Re vacancies with appropriate duration, and it is possible to efficiently control the vacancy density on 2D ReS₂ nanosheets.

The hydrophilic/hydrophobic properties have a significant impact on the electrocatalytic performance of catalysts.

Enhancing the hydrophilicity of catalysts by various methods and strategies is an encouraging pursuit. Recently, Wang et al.¹¹⁶ investigated the effect of Fe¹⁰⁺ ion irradiation on the HER properties of Bi₂Te₃ nanosheets deposited on titanium plates. In acidic solution, the HER performance of Bi₂Te₃ nanosheets was significantly improved after irradiation with Fe¹⁰⁺ ions compared to that of pristine Bi₂Te₃ nanosheets, with η_{10} decreasing from 436 mV to 395 mV (Fig. 8a-c). The increase in activity can be attributed to the change of Bi₂Te₃ surface properties from hydrophobic to hydrophilic by irradiation with iron ions, which promotes the release of H₂ bubbles on the catalyst surface and exposes the active sites in time. At the same time, it also prevents large gas bubbles from damaging the electrode, thus improving the stability of the catalyst. This efficient Fe³⁺ ion irradiation method provides an innovative approach for designing other efficient catalysts.

To enhance the intrinsic HER catalytic activity for flower-like MoS_2 , Mravik *et al.* irradiated MoS_2 nanopowder with carbon and hydrogen ions.⁶⁶ The HER performance of the irradiated samples was tested and the polarization curves of the prepared samples are shown in Fig. 8d. It was observed that all irradiated samples exhibited enhanced HER catalytic activity compared to bare MoS_2 , achieving an optimal η_{10} of 213 mV. A similar trend



Fig. 8 (a) LSV curves of Ti, Bi_2Te_3/Ti and $Fe-Bi_2Te_3/Ti$ at a scan rate of 5 m V s⁻¹. (b) Corresponding Tafel plots. (c) Contact angles for Bi_2Te_3/Ti (top) and $Fe-Bi_2Te_3/Ti$ (bottom), respectively. Copyright 2020 The Royal Society of Chemistry. The HER properties of MoS₂ (d); iR polarization curves; (e) EIS spectrum at an overpotential of 0.2 V vs. RHE; SEM images of as-prepared MoS₂ (f) and irradiated sample C-40(16) (g); inset: magnified SEM image of as-prepared and irradiated MoS₂. Copyright 2013 Elsevier Ltd. OER performance (h) and Tafel plots (i) of NiO/NiFe₂O₄ (ir-2e¹⁶), NiFe₂O₄, NiO, and RuO₂^{68,96,116} Copyright 2021, Wiley-VCH.

is observed for carbon ion irradiation, with an η_{10} of 259 mV for sample C-40 (16) and below 280 mV for sample C-40 (14). However, the impact of varying the energy of incident carbon ions was less pronounced.

Apparently, the HER performance of these catalysts was significantly enhanced after irradiation, resulting in a current density at 300 mV that was up to six times higher than that of the non-irradiated sample. Electrode kinetics were evaluated using EIS (Fig. 8e), revealing that the charge transfer resistance $(R_{\rm ct})$ of irradiated samples was considerably reduced, with hydrogen ion-irradiated samples showing an R_{ct} as low as 12 Ω , up to 14 times lower than that of unirradiated samples. Fig. 8f and g illustrate the morphology of the catalyst before and after irradiation. Initially, the sample displayed spherical flower-like structures composed of nanosheet petals (inset in Fig. 8f). After irradiation, the morphology was altered, with smoother spherical surfaces, disrupted flower-like structures, and partially "opened up" microspheres, as seen in the dashed circles in Fig. 8g, allowing easier access to the interior. Both carbon and hydrogen ion beams produced similar morphological changes. These findings suggest that ion irradiation induces structural defects and morphological changes, which enhance the conductivity and intrinsic activity of the catalysts, which significantly impacted their HER performance.

Wu *et al.*¹¹⁷ also reported the preparation of nanoporous silica (SiO₂) NPs as HER catalysts by irradiation with 90 MeV Ar⁺ ions and annealing in a vacuum. The effect of fluence on cathode morphology and HER performance was investigated. The η_{10} of the samples irradiated at fluences of 5×10^{16} , 1×10^{17} , and 2×10^{17} ions cm⁻² were 590, 357, and 483 mV, respectively, which were much smaller than that of the pristine silicon. The improvement in the HER performance was attributed to the formation of a porous structure by the irradiation of Ar⁺ ions, which facilitated the spillage of the H₂ bubbles from the surface of the catalysts, exposing more active sites. The application of irradiation technology in the HER offers new perspectives in the energy fields, but many mechanisms remain to be explored.

4.1.2 Oxygen evolution reaction (OER). As one of the halfreactions in the water splitting process, the oxygen evolution reaction suffers from kinetic retardation due to its complex four-proton-electron transfer process.125 Despite extensive research on various transition metal compounds, there is still much space to improve their OER performance. Ionizing irradiation emerges as a potent tool for enhancing transition metal compounds with several obvious merits. Firstly, ionizing irradiation can introduce defects into materials, such as vacancies and interstitial sites, enhancing the number of active sites. Secondly, ionizing irradiation allows for the manipulation of crystal structures, inducing lattice distortions and phase transitions that optimize the exposure of active sites and formation of a heterostructure. Thirdly, the enhancement of electrical conductivity through ionizing irradiation plays a pivotal role in promoting efficient electron transfer during the OER process. Moreover, the ionizing irradiation treatment enhances the stability of catalysts, making the catalysts have stronger corrosion resistance and intrinsic activity during the OER process.

Numerous studies have showcased that irradiation can be employed as a distinctive method for engineering efficient and durable OER catalysts for overall water splitting. For example, Zhong et al.⁹⁶ irradiated a NiFe LDH with Ar⁺ ions with various fluences. Benefiting from the formed oxygen vacancies and NiO/ NiFe₂O₄ heterostructure, the catalyst with a fluence of 2×10^{16} ions per cm² presented significantly improved OER performance with an η_{10} of 279 mV and a low Tafel slope of 42 mV dec⁻¹, superior to that of NiFe LDH/Ti (Fig. 8h-j). Also, the DFT calculations have shown that the NiO/NiFe2O4 heterostructure has optimized the free energy of the oxygen-containing intermediates, thereby showing greater OER performance. Xia et al.121 prepared NiO nanosheets by a hydrothermal method following annealing treatment. Then, N⁺ ions were irradiated to introduce more oxygen vacancies and dope N into NiO, and the dose of N^+ ion beam was 5×10^{15} ions per cm². The roles of Ndoping and O vacancies in the NiO substrate were examined by DFT calculation. The results of the density of states (DOS) showed that the bandgap of NiO decreased from 2.9 eV to 0.56 eV. Meanwhile, the charges are clustered around the O vacancy and N atoms, indicating that it has better electronic conductivity. Thus, the OER catalytic activity of NiO was much improved. In particular, the OER properties of N^+ -5 \times 10¹⁵ (5 \times 10¹⁵ N⁺ ions per cm² irradiated samples) were superior to those of NiO/CC (2.32 V, 198.74 mV dec $^{-1}$), and the potential is 1.98 V at 100 mA $\rm cm^{-2}$ and Tafel slope is 135.97 mV dec⁻¹. Moreover, the high TOF value of N^+ -5 \times 10¹⁵ (92.1 s⁻¹) shows that the electron transfer rate is improved after N⁺ ion irradiation.

4.1.3 Oxygen reduction reaction (ORR). Fuel cells with high energy and power densities are regarded as ideal solutions for next-generation devices, standing out among the various energy conversion and storage systems developed to date. In the development of advanced fuel cells, maximizing the ORR activity of the Pt cathode while minimizing its Pt content is crucial. Transition metal oxides favor redox reactions due to their electronic properties.¹²⁶ In addition, transition metals can exhibit a variety of oxidation states, thus facilitating electron transfer. Recently, Baeck et al.40 investigated the effect of a 14 MeV proton beam irradiation on the intrinsic ORR catalytic activity of MnO₂. It was found that the proton irradiation introduced a large number of low-coordinate oxygen and defective sites, which provided multiple active sites and thus increased the ORR activity. Furthermore, the presence of oxygen vacancies introduced additional levels in the conduction or valence band, resulting in a narrower band gap. This narrower band gap enhanced the electronic conductivity of oxygendeficient MnO₂, as electrons can be easily transferred from MnO_2 to O_2 . Additionally, the current density of proton-treated MnO_2 reached -4.6 mA cm^{-2} at 0.65 V (vs. RHE). Therefore, the MnO₂ treated by proton radiation exhibited remarkable durability, and the activity still remained at 95% after a 10 000 second time chronoamperometric stability test. Chauhan et al.41 fabricated Pt-CeO_x/C (Pt/C = 0.02) using 5 kGy proton beam irradiation. Since the free radical density generated by the proton beam irradiation is twice as high as the electron beam irradiation, the surface of the CeO_x nanowire is completely transformed into a thin layer of Pt-O-Ce. As expected, the ORR performance is higher than that of the conventional Pt/C (Pt/C = 0.2) and the same as that for Pt-CeO_x/C (Pt/C = 0.2). The characterization and surface atomistic simulations indicate that Pt-O-Ce bonds are formed in the defect-rich region of CeO_x nanowires, resulting in the maximum ORR activity of the prepared samples. The results suggest that the surface modification of CeO_x nanowires by proton beam irradiation can reduce the Pt content and maintain its high activity.

As previously mentioned, ionizing irradiation can introduce defects into catalysts through ionization, electron excitation, and cascade collisions. Among these methods, ion irradiation is the most prominent because it allows for the precise control over the energy, type of incident ions, and position of the beam spot.¹²⁷ This enables adjustment of the irradiation site, doping ion type, and number of defects on the catalysts, which is beneficial for photocatalysis and electrocatalysis. For example, Sun *et al.*⁷² reported an effective strategy for optimizing defects and interfaces in intermetallic PtPb nanosheets through 10 MeV C⁺ ion irradiation. The structure changed from single-crystal to



Fig. 9 TEM (a) and HRTEM (b) images of PtPb nanosheets; (c-f) HRTEM image of PtPb/C after C⁺ irradiation. The inset in (c) is the FFT image of the whole nanosheet. The inset in (e) is the FFT image of the orange region. The red "T" represents dislocations, the blue line represents subcrystalline boundaries, the white line represents crystal orientation, the area surrounded by the yellow curve represents disordered regions, and the orange area represents disordered domains. Copyright 2017 Wiley-VCH. (g) Photocatalytic performance of different ZIF-8 samples. (h) Comparison of the photocatalytic performance of a ZIF-8-1000 kGy and ZnO/ZIF-8 mixture. (i) Photocatalytic degradation of methyl bromide by ZIF-8-1000 kGy.^{55,72} Copyright 2022, Wiley-VCH.

polycrystalline, with the introduction of defects such as dislocations, subgranular boundaries, amorphization, and multiple defect-related interfaces (Fig. 9a-f). The optimized Pt nanoplates exhibited 2.97 times higher ORR specific activity and 3.00 times higher mass activity compared to the pristine Pt nanoplates. Additionally, they also exhibited excellent stability. This work emphasizes the superiority and significance of ion irradiation in inducing and tuning defects and interfaces for better performance. Kakitani et al.128 investigated the interfacial effects of Ar⁺-induced defects in glassy carbon substrates on the size and electronic structure of Pt NPs. First, a glassy carbon substrate was irradiated with Ar⁺ ions at 380 keV. Then, Pt nanoparticles were deposited on the substrate by radio frequency magnetron sputtering. The irradiation defects in the carbon substrate promoted the growth of Pt NPs on the substrate, resulting in larger Pt NPs. The DFT calculations revealed that lattice vacancies in the graphite structure lowered the position of the d-band centres, leading to higher ORR activity.

Devadoss et al.¹²⁹ demonstrated that RGO films were significantly affected by y-ray irradiation. The exfoliation and formation of defects on the surface of RGO nanosheets lead to additional edge sites and lots of hydrophilic groups. Meanwhile, oxygen doping into the GO lattice increases the hole size at the Fermi level, leading to the shift of the Fermi level towards positive potential, which is favorable for water oxidation. The enhanced hydrophilicity of 25 kGy C-irradiated RGO also increases hydroxide (OH^{-}) adsorption and facilitates O_2 desorption. As a result, at 1.0 V vs. Ag/AgCl, the ORR performance of the 25 kGy-GO catalyst was six times that of untreated RGO. Most recently, Rahman et al.98 synthesized N-doped rGOsupported iron catalysts with different iron loadings using y-ray irradiation. The results show that γ -ray irradiation introduces both N and Fe into the samples while also generating structural defects. The strong interaction between Fe-Nx and O2 promotes rapid electron transfer. The ORR performance was further influenced by Fe loading, with higher Fe content introduced through irradiation leading to increased ORR activity.

4.2 Photocatalysis

Photocatalysis is a promising approach for producing low-cost hydrogen energy and decomposing organic pollutants.²¹ However, the limited number of active sites in photocatalysts creates a significant gap between the actual and theoretical efficiencies of photocatalysts. Thus, developing effective modification methods to enhance photocatalytic efficiency is essential to achieving optimal performance in photocatalytic hydrogen production and pollutant decomposition. Irradiation technology enables precise doping and defect control in photocatalysts, allowing for fine-tuning of their electronic structures and optimizing photocatalytic performance (Table 3).

4.2.1 Photocatalytic degradation of organic pollutants. Photocatalytic degradation of organic pollutants produces highly active free radicals that react with or replace organic contaminants, offering an effective method for environmental remediation.¹⁴⁶ It has many advantages, such as environmental Open Access Article. Published on 27 November 2024. Downloaded on 8/2/2025 8:28:20 AM.

Table 3 Summary of the application of various types of irradiation technology in synthesis/modification of photocatalysts from recent reports

Catalyst materials	Irradiation sources	Energy	Fluence	Roles	Application	Ref.
TiNRs, Ag-TiNRs, Au-TiNRs	Ion beam irradiation/P	50 keV	$1 imes 10^{14}, 1 imes 10^{15}, 5 imes 10^{14}, 5 imes 10^{15}$ ions per cm ²	Defect engineering	Degradation of methylene blue	101
TiO ₂ ZIF-8@ZnO	γ-ray irradiation/ ⁶⁰ Co Fleetron heam irradiation	1.2 MeV 1 5 MeV	7, 11 kGy 50-100-250-500-750-1000 kGv	Band gap engineering Matarial sunthesis and	Degradation of methylene blue Degradation of methylene blue	130 55
0117000-117		A DIAL C.T	JU, 100, 230, 300, 730, 1000 NO	heterostructure formation	Degradation of intentyrene blue	ſſ
TiO ₂ /CNTs	Proton irradiation	120 keV	$5 imes 10^{14},1 imes 10^{16}~{ m cm}^{-2}$	Defect introduction	Degradation of methylene blue	131
TiO_2	Electron beam irradiation	6 MeV	$5, 10, 20 \ \mathrm{kGy}$	Structural modification	Degradation of direct blue 1	132
MOS_2	γ-ray irradiation/ ⁶⁰ Co	Ι	1, 10, 100, 1000 kGy	Band gap engineering	Degradation of methylene blue	133
$Pb_{0.98}Cu_{0.01}Sr_{0.01}S$	γ-ray irradiation/ ⁶⁰ Co	25.2 MeV	90 kGy	Band gap engineering and defect	Degradation of methylene blue	31
				engineering		
NiO	γ -ray irradiation/ ⁶⁰ Co	1.173, 1.332 MeV	180 Gy to 10 kGy	Phase transformation	Photocatalytic	83
WO ₃	Ion beam irradiation/He ²⁺	40 keV	1×10^{13} -10 ¹³ ions per cm ²	Morphology control	Degradation of indigo carmine	83
M/O.	Ion heam irradiation/He ²⁺	40 keV	1×1015 ion per cm^2	Mornholow control	uye anu Congo teu Decradation of Rhodamine R	134
ZnO	Ion beam irradiation/N	100 keV	5×10^{14} , 1×10^{15} , 5×10^{15} ion per cm ²	Band gap engineering and vacancy	Degradation of methyl orange	135
				introduction		
$In_2O_3:F$	γ -ray irradiation/ ⁶⁰ Co		$1, 5, 10, 100 \mathrm{kGy}$	Band gap engineering and defect engineering	Degradation of methylene blue	136
Ag/Bi ₂ WO ₆ /CdWO ₄	Electron beam irradiation		100 kGy	Defect engineering	Degradation of carmine,	76
1)	rhodamine B and Cr ⁶⁺	
rGO-TNTAs	γ-ray irradiation/ ⁶⁰ Co	I	$0, 10, 20, 30, 40 \ \mathrm{kGy}$	Reduce GO to partial rGO	Degradation of ethylene (C ₂ H ₄)	137
COF	Electron beam irradiation	1.5 MeV	5, 100, 300, 500 kGy	Material synthesis	Photoelectrochemical water	64
WO.	Ion heam irradiation/Zr ⁺	3 keV	0.33×10^{15} 1 $\times 10^{15}$ 3 $\times 10^{15}$ ions ner cm ²	Zr-doning and hand gan	splitting Photoelectrochemical water	138
65				engineering	solitting	
TiO_2	Ion beam irradiation/Ar ⁺	190 keV	$1 \times 10^{12}, 5 \times 10^{12}, 5 \times 10^{13}, 5 \times 10^{13}, 5 \times 10^{14}$ ions	Defect engineering	Photoelectrochemical water	139
			per cm ²		splitting	
TiO ₂ nanorods	Ion beam irradiation/N ⁺	65 keV	1×10^{17} ions per cm ²	Nanostructure formation	Photoelectrochemical water	140
TiO. nanotuhes	Ion heam irradiation/N	60 keV	1×10^{15} 1 $\times 10^{16}$ ions per cm^2	N-doning	spuung Dhotoelectrochemical water	oo and
7000				8Jon	splitting	141
ZnO nanorod arrays	Ion beam irradiation/Cu	30 keV	$3 \times 10^5, 5 \times 10^{15}, 2 \times 10^{16}$ ions per cm ²	Doping	Photoelectrochemical water	107
orono pononon Ont	Ton hoom imadiation N	50 Lot	0 E \ 1014 E \ 1015 jour mu m2		splitting Theteolographimical meter	100
LIIU IIAIUUUU AILAYS		JU NCV	$7.7 \times 10^{-2} \times 10^{-1}$ inits bet citi	Sundor	r nousefectiounennear water	001
TiO ₂ nanowire	Ion beam irradiation/N	30 keV	$7 imes 10^{14},1 imes 10^{16}~{ m ions~per~cm^2}$	N-doping	Photoelectrochemical water	142
arrays					splitting	
ZnO nanorod arrays	Ion beam irradiation/N	30 keV	1.25×10^{14} - 5×10^{15} ions per cm ²	N-doping	Photoelectrochemical water	143
TiO ₂ nanowire	Ion beam irradiation/C, N	25, 30 keV	$1 imes 10^{15}, 1 imes 10^{16} ext{ ions per cm}^2$	Doping	splitting Photoelectrochemical water	144
arrays			:		splitting	
α -Fe ₂ O ₃	Ion beam irradiation/Au	30 keV	1×10^{10} , 2.5 × 10^{10} , 5 × 10^{10} , 1 × 10^{17} ions	Heterostructure formation	Photoelectrochemical water	145
			per cm ⁻		splitting	

Nanoscale Advances

View Article Online Review

protection, energy-saving and easy operation. However, the development of efficient photocatalysts with excellent activity and stability is crucial for the practical implementation of this technology in water and air purification. Recently, Wang et al.55 synthesized a ZIF-8@ZnO heterostructure by using electron beam irradiation and investigated its photocatalytic ability toward methylene blue (MB). Under simulated sunlight, ZIF-8-1000 kGy showed fast degradation kinetics and high degradation efficiency for MB, which was superior to those of the ZIF-8 prepared by a solvothermal method (Fig. 9g). In addition, a physical mixture of ZnO and ZIF-8 was also tested, and the corresponding degradation rate was significantly lower than that of ZIF-8-1000 kGy (Fig. 9h). The increased photocatalytic activity was attributed to the following reason: Firstly, the layered pore structure enables ZIF-8-1000 kGy to pre-enrich MB from solution, as demonstrated under dark conditions, which facilitates faster degradation when exposed to light (Fig. 9i).

Secondly, the formed ZIF-8@ZnO heterostructure facilitates photogenerated charge separation. These results demonstrate that electron beam irradiation is a promising method for compositing ZIF-8 and forming ZIF-8@ZnO heterostructures, offering significant advantages over conventional solvothermal reactions. Wang et al.111 fabricated CdTe/ZnO heterostructures by N ion irradiation. The photocatalytic activity was improved after N ion irradiation treatment due to the introduction of oxygen vacancy defects. Lv et al.135 fabricated ZnO nanowires on Si substrates via a hydrothermal growth method, followed by an N ion irradiation treatment with an energy of 100 keV (fluences of 5 \times 10¹⁴, 1 \times 10¹⁵, and 5 \times 10¹⁵ ions per cm²). Compared with the as-grown ZnO nanowires, the photocatalytic performance of ZnO heterostructures was improved by the reduction of the band gap and the generation of oxygen vacancies at 5×10^{15} ions per cm². The reduction of the band gap promotes the transfer of electrons and holes, which improves the charge separation efficiency and visible light absorption. On the other hand, the N ion radiation increases the gap of oxygen vacancies and hinders the recombination of photoexcited electrons and holes. Gallegos et al.132 investigated the degradation of Direct Blue 1 by using a 6 MeV electron beam irradiation of TiO2. The 10 kGy irradiation of TiO2 allows DB1 to degrade more rapidly than the degradation with TiO₂ irradiated at 0, 5, and 20 kGy. The absorption rate of the TiO₂ irradiated at 10 kGy is lower than that of the other used materials (TiO₂ irradiated at 0, 5, and 20 kGy). This is obviously favourable to the degradation of DB1, as excessive adsorption would prevent sufficient light from passing through the photocatalyst, resulting in a reduction in the rate of degradation.

Bamola *et al.*¹⁰¹ irradiated TiO₂ nanorod (TiNR)-based hybrids (Ag-TiNRs and Au-TiNRs) with varying fluences of P ions at 50 keV. They found that Ag-TiNRs irradiated at a fluence of 5×10^{14} ions/cm² degraded 78% of methyl bromide under visible light irradiation, outperforming samples irradiated at 1 $\times 10^{14}$ ions per cm² (65%), 1×10^{15} ions per cm² (74%), and $5 \times$ 10^{15} ions per cm² (68%). Notably, the best degradation performance was achieved with Au-TiNRs irradiated at 5×10^{14} ions per cm², achieving an 84% degradation rate, which was superior to that of samples irradiated at 1×10^{14} ions per cm² (80%), $1 \times$ 10^{15} ions per cm² (76%), and 5×10^{15} ions per cm² (73%). The study also indicated that these hybrid nanostructures are modified at low fluence, while high fluence leads to structural damage. Low-fluence ion implantation of Ag-TiNRs and Au-TiNRs reduces surface states and enhances charge-harvesting efficiency, with less structural damage compared to high fluence. As a result, charge carriers are more effectively separated in low-fluence hybrid materials, thereby improving photocatalytic activity.

As discussed earlier, e-beam irradiation has proven to be an effective method for surface modification and the induction of microstructural evolution in electrocatalysts. Notably, this technique also has potential applications in the field of photocatalysts.¹⁴⁷ For example, Latthe et al.¹⁴⁸ altered the micro/ nanostructure of photocatalysts by electron beam treatment. The catalytic activity of the irradiated photocatalysts in water splitting was greatly improved. Similarly, Chen et al. 149,150 also demonstrated that the oxygen containing groups in the GNSs could be partially removed by medium electron beam irradiation, leading to a significant improvement of the lithium storage performance. In related work, the same group irradiated SnS₂ quantum dots (QDs)/amino-functionalized graphene nanosheets (SAGNSs) with electron beams at doses of 70, 140, and 280 kGy.151 They observed that N-doped graphene nanosheets (NGNSs) were successfully prepared by the e-beam irradiation, and the microstructure was further refined. Additionally, it allowed precise control over the crystallinity and lattice defects in SnS₂ QDs, influencing the amorphization of NGNSs and the surface oxygen-containing groups. The performance of SAGNSs and SnS₂ quantum dots/N-doped graphene nanocomposites (SNGNSs) for degradation of methyl orange (MO) was evaluated under the same experimental conditions. The results showed that the photodegradation rate of SNGNSs reached 95.6% under the irradiation condition of 70 kGy, and that of SAGNSs reached 59.5% after 60 min. The rate constants of SNGNSs were 3.19 times higher than those of SAGNSs at 70 kGy. These findings indicate that e-beam irradiation is a versatile and effective method for the surface modification of graphene-based nanocomposites, enabling the construction of photocatalysts with better performance.

Xie et al.137 utilized y-ray irradiation to reduce rGO and investigated the photocatalytic properties of rGO-modified TiO₂ nanotube arrays (rGO-TNTAs) for ethylene degradation under UV light. It was found that the degradation rate (K) increased first, then decreased, and finally reached the highest value when the dose was 20 kGy. This trend corresponded with a decrease in the ID/IG ratio from 0.9174 to 0.8468. The enhanced photocatalytic activity was attributed to a strong interaction between TiO₂ and rGO, facilitated by defects in the rGO structure. After the 20 kGy γ-ray irradiation, optimal changes occurred in the D band to G band intensity ratio of GO, resulting in a 40.9% increase in K for rGO-TNTAs compared to TNTAs following 120 keV proton beam irradiation. Simultaneously, the CNTs experienced damage, a reduction in tube diameter, and a decrease in the Raman peak ID/IG ratio with increased proton fluence. Notably, the nano-TiO₂/CNT films demonstrated remarkable MB degradation performance under irradiation. Furthermore,

CNTs coated with thinner TiO_2 layers exhibited relatively improved photocatalytic activity, likely due to the crystallization of the TiO_2 layer and the carrier-trapping effect of the CNTs.

Recently, a research group led by Martinez D conducted a series of experiments to study the photocatalytic properties of WO₃ microparticles in organic dyes. They elucidated the size dependence of photocatalytic activity, showing that smaller grain sizes and larger active surface areas corresponded to increased photoactivity and reaction rates.152-155 In related work, Kozovskiy et al.¹⁵⁶ studied the effect of low-energy WO₃ microparticle irradiation on the structure and photocatalytic activity of organic dyes. Their findings showed that an increase in radiation dose led to small but significant changes in surface area. At a dose of 10¹³ ions/ per m², there was a 3.7% increase in Brunauer-Emmett-Teller (BET) surface area. Further dose increases to 10¹⁴ and 10¹⁵ ions per cm² resulted in larger increases of 13.8% and 28.1% in BET surface area, respectively. Photocatalytic testing revealed that the initial, non-irradiated WO3 microparticles achieved only 45-50% degradation of indigo carmine dve after 300 min. However, complete degradation was observed after 200 min for microparticles irradiated at 10¹³ ions per cm², and after 270 min for those irradiated at 10¹⁴ ions per cm². Notably, partial amorphization at 10¹⁵ ions per cm² led to a reduction in degradation and a decrease in photocatalytic activity. Similarly, in the decomposition of Congo red dye, non-irradiated WO3 microparticles degraded no more than 20% of the initial dye concentration. In contrast, irradiation-modified particles achieved 45-50% degradation. Kozovskiy et al.134 further explored the effects of irradiation on WO₃ microparticles in additional experiments. The effect of irradiation of commercial WO₃ microparticles with low energy He ions toward Rhodamine B degradation was studied. For the initial microparticles without irradiation, reduction in the maximum absorption intensity takes place and the intensity gradually reaches the minimum after 300 min of testing, whereas in the case of the modified microparticles, the change of the solution is observed after 210 min. The rate of photocatalytic decomposition proceeds much more quickly for the irradiated samples, with a reduction in the band gap value and a shift in the fundamental absorption edge, indicating an obvious change in the electron density of catalysts.

4.2.2 Photoelectrochemical water splitting. Photoelectrochemical (PEC) water splitting is considered to be one of the most promising strategies for the generation of hydrogen. However, PEC water splitting is a complicated process, which involves several sequential physical and chemical reactions, including light-absorbing, photo-excited, and surfaceoxidation-reduction reactions. The development of low cost, high efficiency, and stable semiconductor-based photocatalysts is a key step in the development of economically feasible PEC energy transformation worldwide. Despite there being hundreds of studies focused on various photocatalysts, TiO₂ is still one of the most frequently used semiconductive materials. Nevertheless, when TiO₂ is used as a catalyst without a cocatalyst such as Pt, Pd, or Au, a major shortcoming is that the charge-transfer reaction kinetics and therefore the H₂ generation rate are very slow. Coincidentally, ion beam irradiation is

a powerful tool for tailing the structure of photocatalysts. In particular, helium ion implantation can be used to create nanoporous structures in various metals, which has been systematically investigated by Prof. Peter B. Johnson and colleagues.^{157,158} Liu et al.⁸⁵ proposed an effective method for fabricating porous TiO₂ nanorod arrays (NRAs). Crystalline rutile TiO2 NRAs were grown on FTO substrates and subjected to He⁺ ion implantation at different energies (Samples 1A, 2A, and 3A correspond to ion irradiation energies of 30, 50, and 70 keV, respectively). Helium ion implantation has advantages in altering material structure due to its light element nature, which causes less damage to the target material and promotes bubble formation. By selecting the ion energy, fluence, and temperature, this method offers the possibility of controlling the pore size of photocatalysts. The TiO₂ NRAs obtained after irradiation were found to be porous structures with internal nanocavities. The nanocavities formed in the nanorods trap holes and facilitate the separation of electron-hole pairs. The photocurrent densities increased to 0.25, 0.38, and 0.36 mA cm^{-2} at 0.5 V vs. SCE, respectively, compared to the pure TiO₂ NRAs (0.19 mA cm^{-2}).

Zhou et al.¹⁵⁹ investigated the impact of N implantation on the structure of semiconducting TiO₂ at 8 \times 10¹⁴ ions per cm² and 1×10^{16} ions per cm² at 60 keV. At a low irradiation dose, it activated anatase TiO₂ nanotubes for noble metal-free photocatalytic H₂ generation. Low-dose nitrogen implantation increases the sub-bandgap response of the anatase, which reduces the charge-transfer resistance. However, high doses have an adverse effect on the photocurrent magnitude, leading to excessive charge transfer efficiency. The implantation of various elements in particulate photocatalysts has been shown to significantly enhance photocatalytic performance. Ion beam irradiation is also readily available for various doping modifications of photocatalysts. Additionally, ion implantation introduces oxygen vacancies that lead to an upward shift of the valence band maximum. These findings suggested that the upshift of the conduction and valence bands is beneficial for photoelectrochemical water splitting. Wang et al. 107 successfully produced Cu-doped ZnO nanorod arrays under visible light using ion irradiation. The photocurrent density reached 18 µA cm^{-2} (with respect to the saturated mercuric glycol electrode), which is approximately 11 times higher than that of the undoped ZnO nanorod arrays (0.8 V).

Graphitic carbon nitride (g-C₃N₄) has been considered as an efficient metal-free catalyst for photocatalytic water splitting, but its performance is constrained by lower charge carrier separation efficiency and less visible light absorption. It has been reported that the visible light absorption and charge carrier separation efficiency of g-C₃N₄ can be enhanced by introducing carbon vacancies or nitrogen vacancies. There are several methods to produce N or C vacancies in g-C₃N₄, including hydrogen treatment, calcination in an Ar, N₂, or NH₃ atmosphere, and thermal polymerization at high temperatures or in strongly alkaline environments.^{42,160–163} However, the above common chemical methods can only produce one kind of vacancy (V_C or V_N) and it is very difficult to control its concentration. In addition, these processes are complex and



Fig. 10 Structural models of $g-C_3N_4$: (a) pristine, (b) with carbon vacancies, (c) with nitrogen vacancies, and (d) with both carbon and nitrogen vacancies. (e–h) DOS of post-implantation annealed $N-TiO_2$ and prepared $N-TiO_2$. Copyright 2019, Wiley-VCH. (i) XPS spectra of N 1s. (j) Upper panel: XPS Ti 2p spectra for air-annealed pristine TiO₂, as-prepared $N-TiO_2$ and annealed $N-TiO_2$. Lower panel: Ti 2p fitted curve for $N-TiO_2$. (k) Relaxation structures of (1) pristine TiO₂, (2) interstitial N-doped TiO₂, (3) interstitial N-doped TiO₂ and (4) substituted N-doped TiO₂. (l) Calculated escape energies for various nitrogen chemical states.^{142,164} Copyright 2015, American Chemical Society.

cumbersome and may introduce impurities. To solve this problem, Wang *et al.*¹⁶⁴ have developed an ion beam irradiation method to fabricate defective $g-C_3N_4$ nanosheets with the annealing process. They found that the concentration and distribution of incident vacancies can be tuned by incident ion beam energy and fluence. During ion irradiation, vacancies of carbon and nitrogen are simultaneously introduced into $g-C_3N_4$ due to the cascade collisions between irradiated ions and target atoms. DFT calculations presented in Fig. 10a–h demonstrate that the introduction of V_C with irradiation leads to a narrowing of the bandgap, along with a shifted absorption edge. Local charge density (LDOS) analysis shows that electrons are more inclined around the V_N , suggesting effective capture of photogenerated electrons by the V_N . This defective state has the potential to improve the performance of photocatalysts and can be used as a high performance photocatalyst for PEC water decomposition.

Wang *et al.*¹⁴² reported the enhancement in the performance of N–TiO₂ for visible light-driven PEC water splitting through ion beam irradiation. As shown in Fig. 10i–l, the DFT calculations and XPS characterization revealed that the annealed substituted N dopants became the major introduced species. One can see that the annealed N⁺ implanted TiO₂ exhibited an improved ability to absorb visible light. The optical band gap of the implanted N-TiO₂ (2.34 eV) is significantly reduced compared to that of the pristine TiO₂ (3.0 eV). On the other hand, the carrier injection efficiency is not significantly improved after N⁺ implantation, indicating that there is no



Fig. 11 The PEC catalytic properties of TiO₂, as-prepared N-TiO₂ and annealed N-TiO₂. (a) Photoabsorption properties, (b) linear swept voltammetry curves with a 100 mW cm⁻² xenon lamp in a 1.0 M NaOH aqueous electrolyte, (c) IPCE spectra collected at 0.5 V vs. Ag/AgCl. The PEC catalytic properties of pristine Fe_2O_3 , $Au-Fe_2O_3$ -550, and $Au-Fe_2O_3$ -700. Copyright 2015, American Chemical Society. (d) Mott–Schottky curves of BVO-A and the irradiated BiVO₄ films in the dark. (e) EIS curves (inset: the equivalent circuit model) at 1.23 V vs. RHE under AM 1.5 G illumination.^{145,165} Copyright 2022, ACS Publications.

obvious change in kinetics of the surface water oxidation. The results suggested that N⁺ ion injection improves the performance of the photoanode mainly by increasing the carrier separation efficiency. After the annealing process, the photocatalytic performance of N⁺ ion-incorporating TiO₂ was improved. The photocurrent density of N-TiO₂ after annealing was -1.92 mA cm⁻² at 0.5 V vs. Ag/AgCl, which was 4 times higher than that of pure TiO₂ nanowires and N⁺ implanted TiO₂ nanowires without the annealing process (Fig. 11a-c). Remarkably, the incident photon-to-current efficiency (IPCE) of N^+ -implanted TiO₂ at 450 nm reaches an impressive 17%, the highest reported among all studies on TiO2-based photoanodes for PEC water splitting without the addition of co-catalysts. However, excessive N⁺ fluence decreases the PEC performance and separation efficiency of photoexcited carriers at the optimal defect concentration. The samples were subsequently annealed.

Ion irradiation can be used to control the implanted elements, and multi-element doping can be achieved and multi-element synergistic modification can be realized. Song *et al.*¹⁴⁴ reported for the first time the utilization of a C/N co-doping strategy to achieve the "Midas Touch" transformation of single-crystal linear rutile TiO₂ NW arrays in visible-light PEC water separation. It was demonstrated that good synergistic interactions between C/N dopant atoms ensured a high concentration of substituted n-ti states and Ti³⁺ morphologies in the C/N co-doped TiO₂ NW, which resulted in a significant

enhancement of visible-light absorbance, charge separation and transfer efficiency. Therefore, the visible light photoactivity of C/N co-doped TiO₂ nanocrystals is nearly 253 times higher than that of pure TiO₂ nanocrystals. Moreover, C/N-TiO₂ achieved high incident photon/electron conversion efficiency without using any other co-catalysts. The ion implantation doping combined with co-doping strategy has been demonstrated to increase the photoelectrochemical conversion and improve the PEC water separation performance of semiconductor photocatalysts. Wu et al.144 introduced oxygen vacancies into TiO₂ by Ar⁺ ion irradiation, resulting in enhanced photocatalytic performance. They found that low concentrations of oxygen vacancies could form shallow donor energy levels in conduction bands, which can trap photogenerated electrons and release them into the conduction band. The oxygen vacancies generated through irradiation increased the carrier concentration and inhibited photogenerated carrier recombination, thereby improving the PEC water separation properties of TiO₂.

Most recently, He *et al.*¹⁴⁵ reported an effective route to improve the PEC water splitting properties of α -Fe₂O₃ by using Au ion irradiation followed by annealing. After annealing, Au atoms recrystallized, diffused and precipitated on the α -Fe₂O₃ nanorods to form Au nanoparticles, which promoted stronger contact between the formed Au particles and hematite, enhancing the surface charge injection (C–I) efficiency, which

reached 89% at 1.5 V *vs.* RHE. Furthermore, the Au-implanted Fe_2O_3 photoelectrode exhibits high stability in a non-photocurrent decay test, with no noticeable photocurrent decay. This work suggests that heterogeneous structures, with embedded metal particles, can be readily formed on film surfaces through ion implantation and subsequent annealing, offering improved PEC performance.

Duan et al.¹⁶⁵ fabricated nanoporous BiVO₄ with abundant bulk oxygen vacancies through helium ion irradiation followed by vacuum annealing. Under optimal irradiation conditions, the PEC performance of the irradiated samples was significantly improved. As shown in Fig. 11d and e, with an ion flux of 5 \times 10¹³ ions per cm², the photocurrent density was significantly increased by about 70%, and the photonic current efficiency doubled compared to that of untreated BiVO₄. The enhanced PEC performance is attributed to the formation of bulk oxygen vacancies, which improve conductivity, enhance electron-hole pair separation efficiency, and accelerate charge transfer. The results indicate that ion irradiation is a powerful tool to accurately tailor the electronic structure of BiVO₄ by inducing oxygen vacancies, thus improving the PEC performance of the material. Moreover, this controllable technique can be further applied to other semiconductor photoelectrodes. The results provide strong evidence that ion beam technology can enhance PEC catalytic performance by manipulating the catalyst structure, implementing co-doping, and generating heterostructures. These findings underscore the importance of accurately controlling irradiation fluence to optimize PEC activity, offering valuable insights for developing advanced photocatalytic materials with tailored performance characteristics.

5 Future perspectives

In summary, this review provides a comprehensive overview of the characteristics of ionizing and non-ionizing radiation, highlighting their advantages over conventional methods for the efficient and rapid synthesis of photo-/electrocatalysts. Additionally, a detailed summary of recent advances in ionizing irradiation for renewable energy materials, particularly in electrocatalytic and photocatalytic applications, is presented. Ionizing radiation enables heteroatom-doping, defect engineering and heterostructure formation. Tables 2 and 3 provide a summary of irradiation applications in the modification and optimization of catalytic materials. Radiation technology has emerged as a promising and efficient tool with applications that can extend to various other fields.

(1) Some studies have demonstrated that irradiation technology, different from other chemical methods, can introduce defects within catalysts. Therefore, it becomes crucial to perform targeted simulation calculations of the irradiation effect to guide and predict various doping elements and defect control strategies. SRIM calculations have been employed to simulate the penetration depth of ion beam irradiation in materials. However, accurately determining the penetration depths of electron beams, proton beams, and gamma rays remains a challenge and often requires Monte Carlo simulation methods. (2) Irradiation has proven to be a highly precise and advanced technique for catalyst modification. For example, it enables the determination of the structure-activity relationship between defect concentration and catalytic properties. However, the underlying mechanisms of the interaction between irradiation processes and structural changes in catalysts require further investigation. The use of *in situ* characterization technology, such as *in situ* TEM and Raman measurements, can provide valuable insights into the continuous atomic structural changes in catalyst materials and their intrinsic relationship with the evolution of catalytic properties.

(3) Currently, the modification of catalysts by irradiation primarily relies on a single type of irradiation. This, while effective, may have limitations in fully optimizing catalytic performance for specific applications. By strategically choosing different irradiation types and combining them synergistically, more approaches could be achieved. This will open up the potential to develop novel catalysts with better performance, allowing for applications in new scenarios. For example, such advancements could address critical processes like carbon dioxide reduction and nitrogen fixation, providing pathways for the creation of advanced materials that meet the evolving demands of diverse catalytic applications and align with sustainability goals.

(4) At present, the modification of catalysts through irradiation primarily revolves around precious metal-based materials, due to their unique catalytic properties and broad applications. The continuous improvements in equipment and characterization techniques are paving the way for innovative approaches such as the development of single-atom catalysts. It holds the potential to embrace various catalyst types with tailored structures and enhanced performances, which may revolutionize diverse catalytical applications and contribute to sustainable advancements in materials science.

(5) With the continuous development of various accelerator technologies, the utilization of proton irradiation and neutron irradiation will play an important role in practical industrial production. The high throughput and cost-effectiveness of irradiation technology make it an attractive option for largescale applications. Its unique ability to modify catalysts at multiple levels, including atomic and molecular levels, presents vast opportunities for improving product quality and reducing costs. This transformative capability contributes significantly to advances in efficiency, sustainability, and innovation across various sectors. The impact of these advanced irradiation techniques on catalysis production needs further exploration and in-depth research. Understanding how these techniques can be harnessed to enhance the catalytic performance of catalysts will undoubtedly uncover new possibilities, driving the evolution of industrial catalysis and paving the way for more sustainable and efficient production methods.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The work was supported by the National Natural Science Foundation of China (12275168), the Science and Technology Commission of Shanghai Municipality (21010500300), Carl Tryggers Foundation for Scientific Research (CTS 24:3314, 23:2433 and 22:2365), STINT Joint China-Sweden Mobility Project (CH2017-7243), and Swedish Government Strategic Research Area in Materials Science on Advanced Functional Materials at Linköping University (SFO-Mat-LiU, No. 2009 0097).

Notes and references

- 1 P. Zhou, I. A. Navid, Y. J. Ma, Y. X. Xiao, P. Wang, Z. W. Ye, B. W. Zhou, K. Sun and Z. T. Mi, Solar-to-hydrogen efficiency of more than 9% in photocatalytic water splitting, *Nature*, 2023, **613**, 66–70.
- 2 Y. F. Xu, M. Z. Yang, B. X. Chen, X. D. Wang, H. Y. Chen, D. B. Kuang and C. Y. Su, A CsPbBr₃ Perovskite Quantum Dot/Graphene Oxide Composite for Photocatalytic CO₂ Reduction, *J. Am. Chem. Soc.*, 2017, **139**, 5660–5663.
- 3 M. Y. Ye, Z. H. Zhao, Z. F. Hu, L. Q. Liu, H. M. Ji, Z. R. Shen and T. Y. Ma, 0D/2D Heterojunctions of Vanadate Quantum Dots/Graphitic Carbon Nitride Nanosheets for Enhanced Visible-Light-Driven Photocatalysis, *Angew. Chem., Int. Ed.*, 2017, **56**, 8407–8411.
- 4 F. Guo, T. J. Macdonald, A. J. Sobrido, L. X. Liu, J. R. Feng and G. J. He, Recent Advances in Ultralow-Pt-Loading Electrocatalysts for the Efficient Hydrogen Evolution, *Adv. Sci.*, 2023, **10**, 2301098.
- 5 R. Balaji, T. T. Nguyen, M. P. Austeria, D. Kim, J. H. Lee and N. H. Kim, Electronic coupling coordinated vanadium nitride/magnesium oxide hetero-junction for accelerating oxygen reaction and long-life flexible zinc-air batteries, *Appl. Catal.*, *B*, 2023, 335, 122895.
- 6 J. X. Guo, Y. Zheng, Z. P. Hu, C. Y. Zheng, J. Mao, K. Du, M. Jaroniec, S. Z. Qiao and T. Ling, Direct seawater electrolysis by adjusting the local reaction environment of a catalyst, *Nat. Energy*, 2023, 8, 264–272.
- 7 C. Y. Wang, L. C. Yu, F. L. Yang and L. G. Feng, MOS_2 nanoflowers coupled with ultrafine Ir nanoparticles for efficient acid overall water splitting reaction, *J. Energy Chem.*, 2023, **87**, 144–152.
- 8 T. Hou, T. R. Wei, Y. Y. Wu, L. Zhang, J. Y. Ding, Q. Liu, L. G. Feng and X. J. Liu, FeCu bimetallic clusters for efficient urea production via coupling reduction of carbon dioxide and nitrate, *J. Colloid Interface Sci.*, 2024, **674**, 834–840.
- 9 Y. Zhang, Z. H. Li, K. Chen, X. Yang, H. Zhang, X. J. Liu and K. Chu, Promoting Electroreduction of CO_2 and NO_3 . to Urea via Tandem Catalysis of Zn Single Atoms and InO_2O_{3-xy} *Adv. Energy Mater.*, 2024, 1614–6832.
- 10 Y. H. Wang, X. Cheng, K. Zhang, G. Chen, R. Z. Wang and J. J. Zhang, Ion-irradiation of catalyst and electrode materials for water electrolysis/photoelectrolysis cells,

rechargeable batteries, and supercapacitors, *Adv. Mater.*, 2022, **3**, 7384–7405.

- 11 S. S. Huang, X. S. Cong, T. Ye, L. B. Liu, K. M. Peng, L. C. Zhang, J. M. Bao, P. Y. Gao, Q. C. Chen and Q. Q. He, Colloidal synthesis of hexagonal CuFe(S_xSe_{1-x})₂ nanoplates with exposed highly active (220) facets for boosting overall water splitting, *Inorg. Chem. Front.*, 2023, 10, 2387–2398.
- 12 Y. Y. Yang, R. G. Wang, L. J. Yang, Y. Jiao and T. Ling, Two dimensional electrocatalyst engineering via heteroatom doping for electrocatalytic nitrogen reduction, *Chem. Commun.*, 2020, **56**, 14154–14162.
- 13 S. B. Lee, J. W. Jung and H. N. Han, Transition to bodycentered cubic structure in Au thin films under electronbeam irradiation, *Acta Mater.*, 2023, **247**, 118759.
- 14 P. Garrido-Barros, J. Derosa, M. J. Chalkley and J. C. Peters, Tandem electrocatalytic N_2 fixation via proton-coupled electron transfer, *Nature*, 2022, **609**, 71.
- 15 Y. B. Kuang, W. Qiao, F. L. Yang and L. G. Feng, Electrochemical hydrogen evolution efficiently boosted by interfacial charge redistribution in Ru/MoSe₂ embedded mesoporous hollow carbon spheres, *J. Energy Chem.*, 2023, **85**, 447–454.
- 16 K. Guo, A. Baidak and Z. X. Yu, Recent advances in green synthesis and modification of inorganic nanomaterials by ionizing and non-ionizing radiation, *J. Mater. Chem. A*, 2020, **8**, 23029–23058.
- 17 H. Han, A. Sharma, J. Yoon, Z. Wang, C. Körner, H. Deniz, A. K. Sharma, F. Li, C. Sturm, G. Woltersdorf and S. S. P. Parkin, All-Oxide Metasurfaces Formed by Synchronized Local Ionic Gating, *Adv. Mater.*, 2024, **36**, 2401064.
- 18 Z. Y. Yuan, W. Z. Zhou, V. Parvulescu and B. L. Su, Electron beam irradiation effect on nanostructured molecular sieve catalysts, *J. Electron Spectrosc. Relat. Phenom.*, 2003, **129**, 189–194.
- 19 Z. Q. Li and F. Chen, Ion beam modification of twodimensional materials: Characterization, properties, and applications, *Appl. Phys. Rev.*, 2017, **4**, 11103.
- 20 K. Satoh and Y. Oono, Studies on Application of Ion Beam Breeding to Industrial Microorganisms at TIARA, *Quantum Beam Sci.*, 2019, **3**, 11.
- X. N. Wang, W. J. Wan, S. H. Shen, H. Y. Wu, H. Z. Zhong, C. Z. Jiang and F. Ren, Application of ion beam technology in (photo)electrocatalytic materials for renewable energy, *Appl. Phys. Rev.*, 2020, 7, 041303.
- 22 M. Migdal, E. Balcer, L. Bartosik, L. Bak, A. Celinska, J. Cybowska, K. Dobrzelewski, J. Jaroszewicz, K. Jezierski, N. Knake, W. Kubinski, J. Lechniak, M. Lipka, G. Madejowski, A. Malkiewicz, L. Murawski, I. Owsianko, B. Piwowarski, R. Prokopowicz, A. Talarowska, E. Wilinska, T. Witkowski, P. Witkowski, G. Wojtania and M. Wojcik, MARIA Reactor Irradiation Technology Capabilities towards Advanced Applications, *Energies*, 2021, 14, 8153.

- 23 A. V. Krasheninnikov and F. Banhart, Engineering of nanostructured carbon materials with electron or ion beams, *Nat. Mater.*, 2007, **6**, 723–733.
- 24 S. Conrad, P. Kumar, F. Xue, L. M. Ren, S. Henning, C. H. Xiao, K. A. Mkhoyan and M. Tsapatsis, Controlling Dissolution and Transformation of Zeolitic Imidazolate Frameworks by using Electron-Beam-Induced Amorphization, *Angew. Chem., Int. Ed.*, 2018, 57, 13592– 13597.
- 25 S. Ghosh, H. Yun, P. Kumar, S. Conrad, M. Tsapatsis and K. A. Mkhoyan, Two Distinct Stages of Structural Modification of ZIF-L MOF under Electron-Beam Irradiation, *Chem. Matter.*, 2021, **33**, 5681–5689.
- 26 Q. L. Chen, C. Dwyer, G. Sheng, C. Z. Zhu, X. N. Li, C. L. Zheng and Y. H. Zhu, Imaging Beam-Sensitive Materials by Electron Microscopy, *Adv. Mater.*, 2020, 32, 1907619.
- 27 B. B. Jin, D. Zhao, F. Liang, L. F. Liu, D. L. Liu, P. Wang and M. Qiu, Electron-Beam Irradiation Induced Regulation of Surface Defects in Lead Halide Perovskite Thin Films, *Research*, 2021, 9797085.
- 28 Z. Y. He, R. Zhao, X. F. Chen, H. J. Chen, Y. M. Zhu, H. M. Su, S. X. Huang, J. M. Xue, J. F. Dai, S. Cheng, M. L. Liu, X. W. Wang and Y. Chen, Defect Engineering in Single-Layer MoS₂ Using Heavy Ion Irradiation, ACS Appl. Mater. Interfaces, 2018, 10, 42524–42533.
- 29 Y. F. Zhang, J. Shi, C. Chen, N. Li, Z. W. Xu, L. S. Liu, L. H. Zhao, J. Li and M. L. Jing, Structural evolution of defective graphene under heat treatment and gamma irradiation, *Phys. E*, 2018, **97**, 151–154.
- 30 A. Aridi, D. Naoufal, H. El-Rassy and R. Awad, Photocatalytic activity of ZnFeO/NiO nanocomposites carried out under UV irradiation, *Ceram. Int.*, 2022, **48**, 30905–30916.
- 31 P. Jeya, S. Keerthana, L. Kungumadevi, R. Yuvakkumar, G. Ravi, A. Kandasami and T. S. Senthil, Gamma irradiation effect on photocatalytic properties of Cu and Sr ions codoped PbS, *Environ. Res.*, 2023, **226**, 115651.
- 32 L. Dong, J. Q. Yang, X. Q. Yue, H. M. Geng, W. Q. Li, Y. B. Zhang and X. J. Li, Effects of Co-60 gamma-ray irradiation of thin-layer molybdenum disulfide for the hydrogen evolution reaction, *New J. Chem.*, 2023, 47, 8214–8222.
- 33 X. H. Fei, W. B. Jia, J. Q. Wang, T. Chen and Y. S. Ling, Study on enzymatic hydrolysis efficiency and physicochemical properties of cellulose and lignocellulose after pretreatment with electron beam irradiation, *Int. J. Biol. Macromol.*, 2020, **145**, 733–739.
- 34 Y. Liu, L. Zhou, F. Ding, S. S. Li, R. Li, Z. G. Li, D. Huang and X. H. Ren, Flame-retardant cotton fabrics modified with phosphoramidate derivative via electron beam irradiation process, *J. Ind. Text.*, 2021, **51**, 396–408.
- 35 T. Abou Elmaaty, S. Okubayashi, H. Elsisi and S. Abouelenin, Electron beam irradiation treatment of textiles materials: a review, *J. Polym. Res.*, 2022, **29**, 117.

- 36 S. Yeo, J. Han, S. Bae and D. S. Lee, Coherence in defect evolution data for the ion beam irradiated graphene, *Sci. Rep.*, 2018, **8**, 13973.
- 37 R. C. Ramola, S. Negi, R. C. Singh and F. Singh, Gas sensing response of ion beam irradiated Ga-doped ZnO thin films, *Sci. Rep.*, 2022, **12**, 22351.
- 38 Z. X. Qu, C. J. Yu, Y. T. Wei, X. P. Su and A. B. Du, Thermal conductivity of boron carbide under fast neutron irradiation, *J. Adv. Ceram.*, 2022, **11**, 482–494.
- 39 D. Nesheva, Electron and Neutron Beam Irradiation Effects in Homogeneous and Nanostructured Oxides, *ACS Omega*, 2023, 8, 12603–12612.
- 40 Y. Choi, D. Lim, E. Oh, C. Lim and S. H. Baeck, Effect of proton irradiation on electrocatalytic properties of MnO₂ for oxygen reduction reaction, *J. Mater. Chem. A*, 2019, 7, 11659–11664.
- 41 S. Chauhan, T. Mori, T. Kobayashi, S. Yamamoto, S. Ito, G. Auchterlonie, R. Wepf, S. Ueda and F. Ye, Surface layer of Pt-O-Ce bonds on CeO_x-nanowire with high ORR activity converted by proton beam irradiation, *J. Am. Chem. Soc.*, 2021, **104**, 1945–1952.
- 42 Y. F. Li, M. Yang, Y. Xing, X. C. Liu, Y. Yang, X. Wang and S. Y. Song, Preparation of Carbon-Rich g- C_3N_4 Nanosheets with Enhanced Visible Light Utilization for Efficient Photocatalytic Hydrogen Production, *Small*, 2017, **13**, 1701552.
- 43 L. Chetibi, D. Hamana, M. M. Silvan and S. Achour, Electrochemical synthesis of graphite nanorings under UV irradiation, *Mater. Lett.*, 2024, **372**, 137024.
- 44 R. Sharma, S. Gyergyek and S. M. Andersen, Microwave-Assisted Scalable Synthesis of Pt/C: Impact of the Microwave Irradiation and Carrier Solution Polarity on Nanoparticle Formation and Aging of the Support Carbon, *ACS Appl. Energy Mater.*, 2022, 5, 705–716.
- 45 Y. M. Sun, X. L. Hu, W. Luo, H. H. Xu, C. C. Hu and Y. H. Huang, Synthesis of Amorphous FeOOH/Reduced Graphene Oxide Composite by Infrared Irradiation and Its Superior Lithium Storage Performance, *ACS Appl. Mater. Interfaces*, 2013, **5**, 10145–10150.
- 46 H. Fujita, M. Izawa and H. Yamazaki, γ-Ray-induced Formation of Gold Sol from Chloroauric Acid Solution, *Nat. Commun.*, 1962, **196**, 666–667.
- 47 W. Wang, F. T. Yao, M. Zeng, M. F. Pei, C. Y. Min, Z. W. Xu, R. Q. Shao, S. K. Liu, H. T. Shi and Y. H. Xia, S_p-nitrogen and gamma-ray modulating multiply gamma-graphyne for anchoring Pt nanoparticles to boost oxygen reduction activity and stability, *Appl. Mater.*, 2022, **29**, 101626.
- 48 Z. Y. Zhang, T. M. Nenoff, J. Y. Huang, D. T. Berry and P. P. Provencio, Room Temperature Synthesis of Thermally Immiscible Ag-Ni Nanoalloys, *J. Phys. Chem. C*, 2009, **113**, 1155–1159.
- 49 F. Ksar, L. Ramos, B. Keita, L. Nadjo, P. Beaunier and H. Remita, Bimetallic Palladium-Gold Nanostructures: Application in Ethanol Oxidation, *Chem. Matter.*, 2009, **21**, 3677–3683.
- 50 S. Kianfar, A. N. Golikand and B. Zarenezhad, Experimental and artificial intelligence for modeling the cyclic

voltammogram behavior of Pt/reduced graphene oxide nanocatalyst synthesized using gamma irradiation at different experimental conditions of graphene oxide, *J. Solid State Electrochem.*, 2022, **26**, 2195–2207.

- 51 D. C. Clifford, C. E. Castano and J. V. Rojas, Supported transition metal nanomaterials: Nanocomposites synthesized by ionizing radiation, *Radiat. Phys. Chem.*, 2017, **132**, 52–64.
- 52 H. Y. Park, D. S. Yang, D. Bhattacharjya, M. Y. Song and J. S. Yu, A highly efficient carbon-supported Pt electrocatalyst prepared by γ -irradiation for cathodic oxygen reduction, *Int. J. Hydrogen Energy*, 2014, **39**, 1688–1697.
- 53 Y. C. Wang, S. X. Li, X. Y. Que, Z. Y. Zhang, L. Xu, Y. Wang, J. Peng, J. Q. Li, S. L. Hu, Y. Y. Ao and M. L. Zhai, Low loading of Pt in radiation-synthesized Pt-MoS/KB nanocomposites for enhancing the electrocatalytic hydrogen evolution reaction, *J. Mater. Chem. A*, 2024, **12**, 18476–18486.
- 54 C. Lee, Y. R. Uhm, G. M. Sun, H. Choi-Yim, J. H. Park and T. Ha, Synthesis of Electrocatalyst FePt@Pt/C Using Electron Beam Irradiation, *Phys. Status Solidi A*, 2024, **221**, 2300941.
- 55 J. C. Chen, M. X. Zhang, S. T. Zhang, K. C. Cao, X. Z. Mao,
 M. J. Zhang, L. W. He, X. Dong, J. Shu, H. C. Dong,
 F. W. Zhai, R. F. Shen, M. J. Yuan, X. F. Zhao, G. Z. Wu,
 Z. F. Chai and S. Wang, Metal-Organic Framework@Metal
 Oxide Heterostructures Induced by Electron-Beam
 Radiation, Angew. Chem., Int. Ed., 2022, 61, 202212532.
- 56 M. X. Zhang, J. C. Chen, X. F. Zhao, X. Z. Mao, C. Y. Li, J. Diwu, G. Z. Wu, Z. F. Chai and S. O. Wang, A MOF@Metal Oxide Heterostructure Induced by Post-Synthetic Gamma-Ray Irradiation for Catalytic Reduction, *Angew. Chem., Int. Ed.*, 2024, **63**, e202405213.
- 57 Q. Zhang, S. Y. Ye, X. M. Chen, X. L. Song, L. Q. Li and X. Huang, Photocatalytic degradation of ethylene using titanium dioxide nanotube arrays with Ag and reduced graphene oxide irradiated by γ-ray radiolysis, *Appl. Catal.*, *B*, 2017, **203**, 673–683.
- 58 K. Naghavi, E. Saion, K. Rezaee and W. M. M. Yunus, Influence of dose on particle size of colloidal silver nanoparticles synthesized by gamma radiation, *Radiat. Phys. Chem.*, 2010, **79**, 1203–1208.
- 59 P. A. Wiguna, D. Djuhana, C. Imawan and A. Umar, Physicochemical properties of colloidal Ag/PVA nanoparticles synthesized by gamma irradiation, *J. Phys.: Conf. Ser.*, 2020, **1428**, 012022.
- 60 Z. I. Ali, O. A. Ghazy, G. Meligi, H. H. Saleh and M. Bekhit, Radiation-Induced Synthesis of Copper/Poly(vinyl alcohol) Nanocomposites and Their Catalytic Activity, *Adv. Polym. Technol.*, 2018, 37, 365–375.
- 61 D. P. Kepic, A. M. Stefanovic, M. D. Budimir, V. B. Pavlovic, A. Bonasera, M. Scopelliti and B. M. Todorovic-Markovic, Gamma rays induced synthesis of graphene oxide/gold nanoparticle composites: structural and photothermal study, *Radiat. Phys. Chem.*, 2023, **202**, 110545.

- 62 J. H. Park, H. W. Kim, H. S. Kang, Y. H. Koo and B. C. Lee, Size control of copper nanoparticle by electron beam irradiation, *Mater. Res. Innovations.*, 2014, **18**, 678–684.
- 63 T. D. Nguyen, J. D. Kim, M. G. So and K. S. Kim, Experimental measurements of gold nanoparticle nucleation and growth by citrate reduction of HAuCl₄, *Adv Powder Technol.*, 2010, **21**, 111–118.
- 64 M. X. Zhang, J. C. Chen, S. T. Zhang, X. Q. Zhou, L. W. He, M. V. Sheridan, M. J. Yuan, M. J. Zhang, L. Chen, X. Dai, F. Y. Ma, J. D. Wang, J. T. Hu, G. Z. Wu, X. Q. Kong, R. H. Zhou, T. E. Albrecht-Schmitt, Z. F. Chai and S. Wang, Electron Beam Irradiation as a General Approach for the Rapid Synthesis of Covalent Organic Frameworks under Ambient Conditions, *J. Am. Chem. Soc.*, 2020, **142**, 9169–9174.
- 65 T. M. Tang, Z. L. Wang and J. Q. Guan, A review of defect engineering in two-dimensional materials for electrocatalytic hydrogen evolution reaction, *Chin. J. Catal.*, 2022, **43**, 636–678.
- 66 J. Li, G. S. Li, J. H. Wang, C. L. Xue, X. S. Li, S. Wang, B. Q. Han, M. Yang and L. P. Li, A novel core-double shell heterostructure derived from a metal-organic framework for efficient HER, OER and ORR electrocatalysis, *Inorg. Chem. Front.*, 2020, 7, 191–197.
- 67 F. Banhart, Irradiation effects in carbon nanostructures, *Rep. Prog. Phys.*, 1999, **62**, 1181–1221.
- 68 J. R. Mravik, I. Milanovic, S. M. Govedarovic, A. Mrakovic, E. Korneeva, I. S. Simatovic and S. Kurko, Improvement of MoS₂ electrocatalytic activity for hydrogen evolution reaction by ion irradiation, *Int. J. Hydrogen Energy*, 2023, 48, 38676–38685.
- 69 J. Luxa, V. Mazanek, A. Mackova, P. Malinsky, S. Akhmadaliev and Z. Sofer, Tuning of electrocatalytic properties of MoS₂ by chalcogenide ion implantation, *Appl. Mater.*, 2019, 14, 216–223.
- 70 D. He, X. Y. Song, W. Q. Li, C. Y. Tang, J. C. Liu, Z. J. Ke, C. Z. Jiang and X. H. Xiao, Active Electron Density Modulation of Co₃O₄-Based Catalysts Enhances their Oxygen Evolution Performance, *Angew. Chem., Int. Ed.*, 2020, **59**, 6929–6935.
- 71 L. Q. Huang, Q. T. Wang, H. P. Liu, Y. X. Wu, Y. X. Yang, G. F. Ma, Z. Q. Lei and S. F. Ren, N plus irradiation regulates surface defects and doping towards efficient hydrogen evolution reaction on Sb₂Te₃, *Appl. Surf. Sci.*, 2023, **609**, 155347.
- 72 Y. J. Sun, Y. X. Liang, M. C. Luo, F. Lv, Y. N. Qin, L. Wang, C. Xu, E. G. Fu and S. J. Guo, Defects and Interfaces on PtPb Nanoplates Boost Fuel Cell Electrocatalysis, *Small*, 2018, **14**, 1702259.
- 73 Y. X. Liang, Y. J. Sun, X. Y. Wang, E. G. Fu, J. Zhang, J. L. Du,
 X. D. Wen and S. J. Guo, High electrocatalytic performance inspired by crystalline/amorphous interface in PtPb nanoplate, *Nanoscale*, 2018, **10**, 11357–11364.
- 74 L. Dong, J. Q. Yang, X. Q. Yue, S. L. Dong, W. Q. Li and X. J. Li, Defect Engineering of MoS₂ Nanosheets by Heavy-Ion Irradiation for Hydrogen Evolution, ACS Appl. Nano Mater., 2023, 6, 18858–18868.

- 75 J. F. Felix, A. F. da Silva, S. W. da Silva, F. Qu, B. Qiu, J. F. Ren, W. M. de Azevedo, M. Henini and C. C. Huang, A comprehensive study on the effects of gamma radiation on the physical properties of a two-dimensional WS_2 monolayer semiconductor, *Nanoscale Horiz.*, 2020, 5, 259–267.
- 76 R. R. Sun, J. Wang, T. L. Yang, R. He, K. H. Xue, L. Wang, X. L. Yu, J. T. Wang, T. Yang and W. L. Wang, Electron beam irradiation treatment of Ag/Bi₂WO₆/CdWO₄ heterogeneous material with enhanced photocatalytic activity, *New J. Chem.*, 2019, 43, 13764–13774.
- 77 R. F. Zhang, C. Y. Qi, X. P. Gao, Y. Y. Li and B. Wang, FeNi₃ nanosheets with multiple defects induced by H plus -ion irradiation show enhanced electrocatalytic action during the oxygen evolution reaction, *FlatChem*, 2024, **45**, 100649.
- 78 X. L. Wu, X. J. Zheng, G. B. A. Zhang, X. N. Chen and J. W. Ding, Tightly-bound trion and bandgap engineering via gamma-ray irradiation in the monolayer transition metal dichalcogenide WSe₂, *Nanotechnology*, 2021, 32, 1361–6528.
- 79 G. Y. Zhao, H. Deng, N. Tyree, M. Guy, A. Lisfi, Q. Peng, A. A. Yan, C. Wang and Y. Lan, Recent Progress on Irradiation-Induced Defect Engineering of Two-Dimensional 2H-MoS₂ Few Layers, *Appl. Sci.*, 2019, 9, 648.
- 80 C. P. Chavda, A. Srivastava, E. Vaughan, J. W. Wang, M. R. Gartia and G. Veronis, Effect of gamma irradiation on the physical properties of MoS₂ monolayer, *Phys. Chem. Chem. Phys.*, 2023, 25, 22359–22369.
- 81 L. Dong, J. Q. Yang, X. Q. Yue, W. Q. Li, Y. H. Jing, Y. B. Zhang and X. J. Li, The effects of the fluence of electron irradiation on the structure and hydrogen evolution reaction performance of molybdenum disulfide, *J. Mater. Chem. C*, 2022, **10**, 7839–7848.
- 82 X. Q. Yue, J. Q. Yang, W. Q. Li, Y. H. Jing, L. Dong, Y. B. Zhang and X. J. Li, Electron Irradiation Induces the Conversion from 2H-WSe₂ to 1T-WSe₂ and Promotes the Performance of Electrocatalytic Hydrogen Evolution, ACS Sustain. Chem. Eng., 2022, **10**, 2420–2428.
- 83 K. Jouini, A. Raouafi, W. Dridi, M. Daoudi, A. B. Mustapha, R. Chtourou and F. Hosni, Investigation of gamma-ray irradiation induced phase change from NiO to Ni₂O₃ for enhancing photocatalytic performance, *Optik*, 2019, **195**, 163109.
- 84 A. Kozlovskiy, M. Zdorovets, I. Kenzhina, A. Berguzinov, D. Tishkevich, T. Zubar and A. Trukhanov, The study of the applicability of ionizing radiation to increase the photocatalytic activity of TiO_2 thin films, *J. Nanostruct. Chem.*, 2020, **10**, 331–346.
- 85 Y. C. Liu, S. H. Shen, F. Ren, J. N. Chen, Y. M. Fu, X. D. Zheng, G. X. Cai, Z. Xing, H. Y. Wu and C. Z. Jiang, Fabrication of porous TiO_2 nanorod array photoelectrodes with enhanced photoelectrochemical water splitting by helium ion implantation, *Nanoscale*, 2016, **8**, 10642–10648.
- 86 H. Y. Wu, L. Wu, S. H. Shen, Y. C. Liu, G. X. Cai, X. N. Wang, Y. H. Qiu, H. Z. Zhong, Z. Xing, J. Tang, Z. Q. Dai, C. Z. Jiang and F. Ren, Enhanced photoelectrochemical performance of an alpha-Fe₂O₃ nanorods photoanode with embedded

nanocavities formed by helium ions implantation, *Int. J. Hydrogen Energy*, 2020, **45**, 9408–9415.

- 87 V. Stará, P. Procházka, D. Marecek, T. Sikolaa and J. Cechal, Ambipolar remote graphene doping by low-energy electron beam irradiation, *Nanoscale*, 2018, **10**, 17520–17524.
- 88 Y. Ling, Z. H. Yang, Q. Zhang, Y. F. Zhang, W. W. Cai and H. Cheng, A self-template synthesis of defect-rich WS₂ as a highly efficient electrocatalyst for the hydrogen evolution reaction, *Chem. Commun.*, 2018, 54, 2631–2634.
- 89 D. Escalera-Lopez, R. Griffin, M. Isaacs, K. Wilson, R. E. Palmer and N. V. Rees, Electrochemical sulfidation of WS₂ nanoarrays: Strong dependence of hydrogen evolution activity on transition metal sulfide surface composition, *Electrochem. Commun.*, 2017, **81**, 106–111.
- 90 J. J. Duan, S. Chen, B. A. Chambers, G. G. Andersson and S. Z. Qiao, 3D WS₂ Nanolayers@Heteroatom-Doped Graphene Films as Hydrogen Evolution Catalyst Electrodes, *Adv. Mater.*, 2015, 27, 4234–4241.
- 91 D. Q. Gao, B. R. Xia, C. R. Zhu, Y. H. Du, P. X. Xi, D. S. Xue, J. Ding and J. Wang, Activation of the MoSe₂ basal plane and Se-edge by B doping for enhanced hydrogen evolution, *J. Mater. Chem. A*, 2018, **6**, 510–515.
- 92 Y. Yin, Y. M. Zhang, T. L. Gao, T. Yao, X. H. Zhang, J. C. Han, X. J. Wang, Z. H. Zhang, P. Xu, P. Zhang, X. Z. Cao, B. Song and S. Jin, Synergistic Phase and Disorder Engineering in 1T-MoSe₂ Nanosheets for Enhanced Hydrogen-Evolution Reaction, *Adv. Mater.*, 2017, **29**, 1700311.
- 93 X. Shang, K. L. Yan, Z. Z. Liu, S. S. Lu, B. Dong, J. Q. Chi, X. Li, Y. R. Liu, Y. M. Chai and C. G. Liu, Oxidized carbon fiber supported vertical WS₂ nanosheets arrays as efficient 3 D nanostructure electrocatalyts for hydrogen evolution reaction, *Appl. Surf. Sci.*, 2017, **402**, 120–128.
- 94 L. Madauss, I. Zegkinoglou, H. V. Muinos, Y. W. Choi, S. Kunze, M. Q. Zhao, C. H. Naylor, P. Ernst, E. Pollmann, O. Ochedowski, H. Lebius, A. Benyagoub, B. Ban-d'Etat, A. T. C. Johnson, F. Djurabekova, B. Roldan Cuenya and M. Schleberger, Highly active single-layer MoS₂ catalysts synthesized by swift heavy ion irradiation, *Nanoscale*, 2018, **10**, 22908–22916.
- 95 D. L. Cao, T. M. Zhang, J. Zeng, L. Cai, X. F. Pu, J. M. Qian, D. Q. Gao and J. Liu, Fe^{13+} -ion irradiated WS_2 with multivacancies and Fe dopants for hydrogen evolution reaction, *FlatChem*, 2021, 27, 2452–2627.
- 96 H. Z. Zhong, G. P. Gao, X. N. Wang, H. Y. Wu, S. H. Shen, W. B. Zuo, G. X. Cai, G. Wei, Y. Shi, D. J. Fu, C. Z. Jiang, L. W. Wang and F. Ren, Ion Irradiation Inducing Oxygen Vacancy-Rich NiO/NiFe₂O₄ Heterostructure for Enhanced Electrocatalytic Water Splitting, *Small*, 2021, 17, 2103501.
- 97 W. T. Huang, Q. W. Zhou, S. Q. Su, J. Li, X. B. Lu, X. S. Gao, X. Wang, M. L. Jin, G. F. Zhou, Z. Zhang and J. M. Liu, Ion Beam Defect Engineering on ReS₂/Si Photocathode with Significantly Enhanced Hydrogen Evolution Reaction, *Adv. Mater. Interfaces*, 2019, 6, 1801663.
- 98 K. R. Rahman, K. Y. Kok, W. Y. Wong, H. Yang and K. L. Lim, Effect of Iron Loading on the Catalytic Activity of Fe/N-Doped Reduced Graphene Oxide Catalysts via Irradiation, *Appl. Sci.*, 2021, **11**, 431.

- 99 A. Ghicov, J. M. Macak, H. Tsuchiya, J. Kunze, V. Haeublein, L. Frey and P. Schmuki, Ion implantation and annealing for an efficient N-doping of TiO₂ nanotubes, *Nano Lett.*, 2006, 6, 1080–1082.
- 100 D. Liu, F. Ren, G. X. Cai, Y. C. Liu, M. Q. Hong, J. J. Ying, Y. Liu, J. Zhou, W. Wu, X. H. Xiao and C. Z. Jiang, Fabrication of TiO₂-based composite films by sequential ion implantation and subsequent annealing, *Mater. Res. Express*, 2014, **1**, 25703.
- 101 P. Bamola, S. Rawat, M. Tanwar, K. Asokan, C. Dwivedi, R. Kumar and H. Sharma, Effect of low energy ion irradiation on TiO₂-based hybrid nanostructures for enhanced photocatalytic activity, *Eur. Phys. J.: Spec. Top.*, 2022, 231, 2941–2949.
- 102 M. Takeuchi, S. Sakai, M. Matsuoka and M. Anpo, Preparation of the visible light responsive TiO_2 thin film photocatalysts by the RF magnetron sputtering deposition method, *Res. Chem. Intermed.*, 2009, **35**, 973–983.
- 103 H. Narayan, H. Alemu, L. Macheli, M. Thakurdesai and T. K. G. Rao, Synthesis and characterization of Y^{3+} -doped TiO₂ nanocomposites for photocatalytic applications, *Nanotechnology*, 2009, **20**, 255601.
- 104 M. M. Ba-Abbad, A. A. H. Kadhum, A. Mohamad, M. S. Takriff and K. Sopian, Visible light photocatalytic activity of Fe³⁺-doped ZnO nanoparticle prepared via solgel technique, *Chemosphere*, 2013, **91**, 1604–1611.
- 105 A. P. Bhirud, S. D. Sathaye, R. P. Waichal, L. K. Nikam and B. B. Kale, An eco-friendly, highly stable and efficient nanostructured p-type N-doped ZnO photocatalyst for environmentally benign solar hydrogen production, *Green Chem.*, 2012, 14, 2790–2798.
- 106 M. Ni, M. K. H. Leung, D. Y. C. Leung and K. Sumathy, A review and recent developments in photocatalytic watersplitting using TiO_2 for hydrogen production, *Renewable Sustainable Energy Rev.*, 2007, **11**, 401–425.
- 107 M. Wang, F. Ren, G. X. Cai, Y. C. Liu, S. H. Shen and L. J. Guo, Activating ZnO nanorod photoanodes in visible light by Cu ion implantation, *Nano Res.*, 2014, 7, 353–364.
- 108 L. Cai, F. Ren, M. Wang, G. X. Cai, Y. B. Chen, Y. C. Liu, S. H. Shen and L. J. Guo, V ions implanted ZnO nanorod arrays for photoelectrochemical water splitting under visible light, *Int. J. Hydrogen Energy*, 2015, **40**, 1394–1401.
- 109 D. H. Deng, K. S. Novoselov, Q. Fu, N. F. Zheng, Z. Q. Tian and X. H. Bao, Catalysis with two-dimensional materials and their heterostructures, *Nat. Nanotechnol.*, 2016, **11**, 218–230.
- 110 J. Sitek, K. Czerniak-Losiewicz, A. P. Gertych, M. Giza, P. Dabrowski, M. Rogala, K. Wilczynski, A. Kaleta, S. Kret, B. R. Conran, X. C. Wang, C. McAleese, M. Macha, A. Radenovic, M. Zdrojek, I. Pasternak and W. Strupinski, Selective Growth of van der Waals Heterostructures Enabled by Electron-Beam Irradiation, ACS Appl. Mater. Interfaces, 2023, 15, 33838–33847.
- 111 Y. Z. Wang, W. Li, Y. M. Feng, S. S. Lv, M. Y. Li and Z. C. Li, Nitrogen ion irradiation effect on enhancing photocatalytic performance of CdTe/ZnO heterostructures, *Front. Mater. Sci.*, 2018, **12**, 392–404.

- 112 S. Dhara, Formation, dynamics, and characterization of nanostructures by ion beam irradiation, *Crit. Rev. Solid State Mater. Sci.*, 2007, **32**, 1–50.
- 113 P. Z. Chen, K. Xu, S. Tao, T. P. Zhou, Y. Tong, H. Ding, L. D. Zhang, W. S. Chu, C. Z. Wu and Y. Xie, Phase-Transformation Engineering in Cobalt Diselenide Realizing Enhanced Catalytic Activity for Hydrogen Evolution in an Alkaline Medium, *Adv. Mater.*, 2016, 28, 7527–7532.
- 114 B. A. Zhang, H. Y. Qin, L. C. Diao, N. Q. Zhao, C. S. Shi, E. Z. Liu and C. N. He, Strongly coupled hollow-oxide/ phosphide hybrid coated with nitrogen-doped carbon as highly efficient electrocatalysts in alkaline for hydrogen evolution reaction, *J. Catal.*, 2019, 377, 582–588.
- 115 C. Sun, P. P. Wang, H. Wang, C. Xu, J. T. Zhu, Y. X. Liang, Y. Su, Y. N. Jiang, W. Q. Wu, E. G. Fu and G. F. Zou, Defect engineering of molybdenum disulfide through ion irradiation to boost hydrogen evolution reaction performance, *Nano Res.*, 2019, **12**, 1613–1618.
- 116 Q. T. Wang, K. Cui, J. Li, Y. X. Wu, Y. X. Yang, X. Z. Zhou, G. F. Ma, Z. W. Yang, Z. Q. Lei and S. F. Ren, Iron ion irradiated Bi₂Te₃ nanosheets with defects and regulated hydrophilicity to enhance the hydrogen evolution reaction, *Nanoscale*, 2020, **12**, 16208–16214.
- 117 L. Wu, F. Ren, G. X. Cai, Z. Xing, H. Y. Wu, X. D. Zheng, X. N. Wang and C. Z. Jiang, Fabrication of nanoporous Si electrocathode by high-energy argon ion irradiation for improved electrocatalytic hydrogen production, *Int. J. Hydrogen Energy*, 2018, **43**, 64–71.
- 118 B. R. Xia, T. T. Wang, X. D. Jiang, T. M. Zhang, J. Li, W. Xiao, P. X. Xi, D. Q. Gao, D. S. Xue and J. Ding, Ar²⁺ Beam Irradiation-Induced Multivancancies in MoSe₂ Nanosheet for Enhanced Electrochemical Hydrogen Evolution, ACS Energy Lett., 2018, 3, 2167–2172.
- 119 M. T. Mehran, M. M. Baig, F. Shahzad, S. R. Naqvi and S. Iqbal, Gamma irradiated structural modification of $Ti_3C_2T_x$ for high performance supercapacitors and the hydrogen evolution reaction, *New J. Chem.*, 2023, 47, 7205–7210.
- 120 Z. Mravik, D. Bajuk-Bogdanovic, Α. Mrakovic, Vukosavljevic, I. Trajic, J. Kovac, D. Perusko, L. N. Gavrilov and Z. Jovanovic, Structural and electrochemical properties of carbon ion beam irradiated 12-tungstophosphoric acid, Radiat. Phys. Chem., 2021, 183, 109422.
- 121 B. R. Xia, T. T. Wang, X. D. Jiang, J. Li, T. M. Zhang, P. Xi, D. Q. Gao and D. S. Xue, N⁺-ion irradiation engineering towards the efficient oxygen evolution reaction on NiO nanosheet arrays, *J. Mater. Chem. A*, 2019, 7, 4729–4733.
- 122 T. T. Li, T. Y. Jing, D. W. Rao, S. Mourdikoudis, Y. P. Zuo and M. Y. Wang, Two-dimensional materials for electrocatalysis and energy storage applications, *Inorg. Chem. Front.*, 2022, **9**, 6008–6046.
- 123 D. Voiry, H. Yamaguchi, J. W. Li, R. Silva, D. C. B. Alves,T. Fujita, M. W. Chen, T. Asefa, V. B. Shenoy, G. Eda andM. Chhowalla, Enhanced catalytic activity in strained

chemically exfoliated WS_2 nanosheets for hydrogen evolution, *Nat. Mater.*, 2013, **12**, 850–855.

- 124 G. Q. Li, D. Zhang, Q. Qiao, Y. F. Yu, D. Peterson, A. Zafar, R. Kumar, S. Curtarolo, F. Hunte, S. Shannon, Y. M. Zhu, W. T. Yang and L. Y. Cao, All The Catalytic Active Sites of MoS₂ for Hydrogen Evolution, *J. Am. Chem. Soc.*, 2016, 138, 16632–16638.
- 125 J. H. Kim, D. H. Youn, K. Kawashima, J. Lin, H. Lim and C. B. Mullins, An active nanoporous Ni(Fe) OER electrocatalyst via selective dissolution of Cd in alkaline media, *Appl. Catal., B*, 2018, 225, 1–7.
- 126 S. D. Bhoyate, J. Kim, F. M. de Souza, J. R. Y. Lin, E. H. Lee, A. Kumar and R. K. Gupta, Science and engineering for non-noble-metal-based electrocatalysts to boost their ORR performance: A critical review, *Coord. Chem. Rev.*, 2023, 474, 214854.
- 127 Y. H. Wang, X. Cheng, K. Zhang, G. Chen, R. Z. Wang and J. J. Zhang, Ion-irradiation of catalyst and electrode materials for water electrolysis/photoelectrolysis cells, rechargeable batteries, and supercapacitors, *Mater. Adv.*, 2022, 3, 7384–7405.
- 128 K. Kakitani, T. Kimata, T. Yamaki, S. Yamamoto, T. Taguchi, T. Kobayashi, W. Mao and T. Terai, The interface between platinum nanoparticle catalysts and an Ar⁺-irradiated carbon support, *Surf. Coat. Technol.*, 2018, 355, 259–263.
- 129 A. Devadoss, S. Ramasundaram, K. Asokan, B. Kim and S. Pitchaimuthu, Enhanced water oxidation catalytic performance of graphene oxide by gamma ray irradiation post-treatment, *Mater. Lett.*, 2019, **241**, 31–34.
- 130 A. Bourezgui, I. Kacem, M. Daoudi and A. F. Al-Hossainy, Influence of Gamma-Irradiation on Structural, Optical and Photocatalytic Performance of TiO₂ Nanoparticles Under Controlled Atmospheres, *J. Electron. Mater.*, 2020, 49, 1904–1921.
- 131 Y. Chen, H. Y. Zhao, Y. Y. Wu, X. Q. Huang, L. Wang and B. Guo, Effects of proton irradiation on structures and photo-catalytic property of nano-TiO₂/CNTs films, *Radiat. Phys. Chem.*, 2018, **153**, 79–85.
- 132 E. Gallegos, F. M. Bisesti, K. Vaca-Escobar, C. Santacruz,
 L. Fernandez, A. Debut and P. J. Espinoza-Montero,
 Degradation of Direct Blue 1 through Heterogeneous
 Photocatalysis with TiO₂ Irradiated with E-Beam, *Processes*, 2020, 8, 1181.
- 133 Y. P. He, X. Xiang, L. J. Sun, C. X. Tian, G. X. Yang and X. T. Zu, Effect of gamma-irradiation on adsorption and photocatalytic ability of MoS₂ nanomaterials, *Int. J. Mod. Phys. B*, 2019, 33, 1250275.
- 134 A. L. Kozlovskiy, A. Alina and M. V. Zdorovets, Study of the effect of ion irradiation on increasing the photocatalytic activity of WO₃ microparticles, *J. Mater. Sci.: Mater. Electron.*, 2021, **32**, 3863–3877.
- 135 S. H. Lv, M. Y. Li, M. L. Qiu, Y. Z. Wang, F. H. Dong, C. H. Chen, J. P. Cheng and Z. C. Li, Effect of nitrogen ion irradiation treatment to the enhancement of ZnO photocatalytic performance, *Surf. Interface Anal.*, 2020, 52, 348–354.

- 136 C. Nefzi, N. Beji, M. Souli, A. Mejri, S. Alleg and N. Kamoun-Turki, Effect of gamma-irradiation on optical, structural and electrical properties of In_2O_3 : F thin films for photocatalysis application, *Opt Laser. Technol.*, 2019, **112**, 85–92.
- 137 X. T. Xie, L. Q. Li, S. Y. Ye, Q. Zhang, X. M. Chen and X. Huang, Photocatalytic degradation of ethylene by TiO₂ nanotubes/reduced graphene oxide prepared by gamma irradiation, *Radiat. Phys. Chem.*, 2020, **169**, 108371.
- 138 H. Y. Wu, F. Ren, Z. Xing, X. D. Zheng, L. Wu and C. Z. Jiang, Cathodic shift of onset potential for water oxidation of WO₃ photoanode by Zr^+ ions implantation, *J. Appl. Phys.*, 2017, **121**, 085305.
- 139 H. Y. Wu, Z. W. Wang, S. X. Jin, X. Z. Cao, F. Ren, L. Wu, Z. Xing, X. N. Wang, G. X. Cai and C. Z. Jiang, Enhanced photoelectrochemical performance of TiO_2 through controlled Ar+ ion irradiation: A combined experimental and theoretical study, *Int. J. Hydrogen Energy*, 2018, **43**, 6936–6944.
- 140 X. D. Zheng, S. H. Shen, F. Ren, G. X. Cai, Z. Xing, Y. C. Liu,
D. Liu, G. Z. Zhang, X. H. Xiao, W. Wu and C. Z. Jiang,
Irradiation-induced TiO_2 nanorods for
photoelectrochemical hydrogen production, *Int. J.*
Hydrogen Energy, 2015, **40**, 5034–5041.
- 141 A. Ghicov, J. M. Macak, H. Tsuchiya, J. Kunze, V. Haeublein, S. Kleber and P. Schmuki, TiO_2 nanotube layers: Dose effects during nitrogen doping by ion implantation, *Chem. Phys. Lett.*, 2006, **419**, 426–429.
- 142 G. M. Wang, X. H. Xiao, W. Q. Li, Z. Y. Lin, Z. P. Zhao, C. Chen, C. Wang, Y. J. Li, X. Q. Huang, L. Miao, C. Z. Jiang, Y. Huang and X. F. Duan, Significantly Enhanced Visible Light Photoelectrochemical Activity in TiO₂ Nanowire Arrays by Nitrogen Implantation, *Nano Lett.*, 2015, 15, 4692–4698.
- 143 M. Wang, F. Ren, J. G. Zhou, G. X. Cai, L. Cai, Y. F. Hu, D. N. Wang, Y. C. Liu, L. J. J. Guo and S. H. Shen, N Doping to ZnO Nanorods for Photoelectrochemical Water Splitting under Visible Light: Engineered Impurity Distribution and Terraced Band Structure, *Sci. Rep.*, 2015, 5, 12925.
- 144 X. Y. Song, W. Q. Li, D. He, H. Y. Wu, Z. J. Ke, C. Z. Jiang, G. M. Wang and X. H. Xiao, The "Midas Touch" Transformation of TiO₂ Nanowire Arrays during Visible Light Photoelectrochemical Performance by Carbon/Nitrogen Coimplantation, *Adv. Energy Mater.*, 2018, 8, 1800165.
- 145 D. He, X. Y. Song, Z. J. Ke, X. H. Xiao and C. Z. Jiang, Construct Fe^{2+} species and Au particles for significantly enhanced photoelectrochemical performance of alpha- Fe_2O_3 by ion implantation, *Sci. China Mater.*, 2018, **61**, 878–886.
- 146 C. L. Zhang, R. H. Ma, Q. We, M. R. Yang, R. Cao and X. N. Zong, Photocatalytic degradation of organic pollutants in wastewater by heteropolyacids: a review, *J. Coord. Chem.*, 2021, 74, 1751–1764.
- 147 R. T. Huang, L. J. Wang, Q. Zhang, Z. W. Chen, Z. Li, D. Y. Pan, B. Zhao, M. H. Wu, C. M. L. Wu and

C. H. Shek, Irradiated Graphene Loaded with SnO₂ Quantum Dots for Energy Storage, *ACS Nano*, 2015, **9**, 11351–11361.

- 148 S. S. Latthe, S. An, S. Jin and S. S. Yoon, High energy electron beam irradiated TiO₂ photoanodes for improved water splitting, *J. Mater. Chem. A*, 2013, **1**, 13567–13575.
- 149 L. M. Wang, T. L. Zhang, P. Y. Li, W. X. Huang, J. L. Tang, P. Y. Wang, J. Liu, Q. X. Yuan, R. Bai, B. Li, K. Zhang, Y. L. Zhao and C. Y. Chen, Use of Synchrotron Radiation-Analytical Techniques To Reveal Chemical Origin of Silver-Nanoparticle Cytotoxicity, ACS Nano, 2015, 9, 6532– 6547.
- 150 S. S. Huang, W. F. Wang, D. Y. Chen, Z. J. Hu, Y. Jiang, Z. W. Chen, Z. Li, D. Y. Pan and B. Zhao, Enhancing lithium-ion batteries performance *via* electron-beam irradiation strategies: A case study of graphene aerogels loaded with SnO₂ quantum dots, *Electrochim. Acta*, 2018, 281, 769–776.
- 151 D. Y. Chen, S. S. Huang, R. T. Huang, Q. Zhang, T. T. Le,
 E. B. Cheng, R. Yue, Z. J. Hu and Z. W. Chen, Electron Beam-Induced Microstructural Evolution of SnS₂ Quantum Dots Assembled on N-Doped Graphene Nanosheets with Enhanced Photocatalytic Activity, *Adv. Mater. Interfaces*, 2019, 6, 1801759.
- 152 D. S. Martinez, A. Martinez-de la Cruz and E. L. Cuellar, Photocatalytic properties of WO₃ nanoparticles obtained by precipitation in presence of urea as complexing agent, *Appl. Catal., A*, 2011, **398**, 179–186.
- 153 A. B. D. Nandiyanto, F. Triawan, R. Firly, A. G. Abdullah, Y. Aono, K. Inaba and K. Kishimoto, Identification of Micro-Mechanical Characteristics of Monoclinic Tungsten Trioxide Microparticles by Nanoindentation Technique, *Mater. Phys. Mech.*, 2019, 42, 323–329.
- 154 D. Sanchez-Martinez, A. Martinez-de la Cruz and E. Lopez-Cuellar, Synthesis of WO₃ nanoparticles by citric acidassisted precipitation and evaluation of their photocatalytic properties, *Mater. Res. Bull.*, 2013, **48**, 691– 697.
- 155 A. Martinez-de la Cruz, D. S. Martinez and E. L. Cuellar, Synthesis and characterization of WO_3 nanoparticles prepared by the precipitation method: Evaluation of photocatalytic activity under vis-irradiation, *Solid State Sci.*, 2010, **12**, 88–94.
- 156 A. L. Kozlovskiy and M. V. Zdorovets, Study of the photocatalytic activity of irradiated WO₃ microparticles, *Appl. Phys. A*, 2020, **126**, 638.
- 157 P. B. Johnson, A. Markwitz and P. W. Gilberd, Shallow nanoporous surface layers produced by helium ion implantation, *Adv. Mater.*, 2001, **13**, 997–1000.
- 158 M. Bruel, Application of hydrogen ion beams to Silicon On Insulator material technology, Nucl. Instrum. Methods Phys. Res., Sect. B, 1996, 108, 313–319.
- 159 X. M. Zhou, V. Haublein, N. Liu, N. T. Nguyen,
 E. M. Zolnhofer, H. Tsuchiya, M. S. Killian, K. Meyer,
 L. Frey and P. Schmuki, TiO₂ Nanotubes: Nitrogen-Ion Implantation at Low Dose Provides Noble-Metal-Free

Photocatalytic H_2 Evolution Activity, Angew. Chem., Int. Ed., 2016, 55, 3763–3767.

- 160 S. S. Lee, H. Zhu, E. Q. Contreras, A. Prakash, H. L. Puppala and V. L. Colvin, High Temperature Decomposition of Cerium Precursors To Form Ceria Nanocrystal Libraries for Biological Applications, *Chem. Matter.*, 2012, 24, 424– 432.
- 161 X. B. Li, G. Hartley, A. J. Ward, P. A. Young, A. F. Masters and T. Maschmeyer, Hydrogenated Defects in Graphitic Carbon Nitride Nanosheets for Improved Photocatalytic Hydrogen Evolution, *J. Phys. Chem. C*, 2015, **119**, 14938– 14946.
- 162 P. Niu, G. Liu and H. M. Cheng, Nitrogen Vacancy-Promoted Photocatalytic Activity of Graphitic Carbon Nitride, *J. Phys. Chem. C*, 2012, **116**, 11013–11018.
- 163 H. J. Yu, R. Shi, Y. X. Zhao, T. Bian, Y. F. Zhao, C. Zhou,
 G. I. N. Waterhouse, L. Z. Wu, C. H. Tung and
 T. R. Zhang, Alkali-Assisted Synthesis of Nitrogen
 Deficient Graphitic Carbon Nitride with Tunable Band
 Structures for Efficient Visible-Light-Driven Hydrogen
 Evolution, *Adv. Mater.*, 2017, 29, 1605148.
- 164 X. N. Wang, L. Wu, Z. W. Wang, H. Y. Wu, X. M. Zhou, H. Y. Ma, H. Z. Zhong, Z. Xing, G. X. Cai, C. Z. Jiang and F. Ren, C/N Vacancy Co-Enhanced Visible-Light-Driven Hydrogen Evolution of g-C₃N₄ Nanosheets Through Controlled He⁺ Ion Irradiation, *Sol. RRL*, 2019, 3, 1800298.
- 165 H. Duan, H. Y. Wu, H. Z. Zhong, X. N. Wang, W. J. Wan, D. R. Li, G. X. Cai, C. Z. Jiang and F. Ren, Improving PEC Performance of BiVO₄ by Introducing Bulk Oxygen Vacancies by He Ion Irradiation, *J. Phys. Chem. C*, 2022, 126, 7688–7695.
- 166 S. Pylypenko, A. Queen, T. S. Olson, A. Dameron, K. O'Neill,
 K. C. Neyerlin, B. Pivovar, H. N. Dinh, D. S. Ginley,
 T. Gennett and R. O'Hayre, Tuning Carbon-Based Fuel
 Cell Catalyst Support Structures via Nitrogen
 Functionalization. I. Investigation of Structural and
 Compositional Modification of Highly Oriented Pyrolytic
 Graphite Model Catalyst Supports as a Function of
 Nitrogen Implantation Dose, *J. Phys. Chem. C*, 2011, 115, 13667–13675.
- 167 X. Shi, W. Wang, X. R. Miao, F. Tian, Z. W. Xu, N. Li and M. L. Jing, Constructing Conductive Channels between Platinum Nanoparticles and Graphitic Carbon Nitride by Gamma Irradiation for an Enhanced Oxygen Reduction Reaction, ACS Appl. Mater. Interfaces, 2020, 12, 46095– 46106.
- 168 M. Asano, R. Kawamura, N. Todoroki and T. Wadayama, ORR Properties for Model Pt-Shell Layers Prepared on Nitrogen-Beam Irradiated Pt₂₅Ni₇₅(111) Substrate, ECS Trans., 2016, 75, 809–814.
- 169 T. F. Choo, N. M. Zali, N. U. Saidin and K. Y. Kok, Gamma Radiolysis-Synthesized Carbon Nanotube-Supported Palladium as Electrocatalyst for Oxygen Reduction Reaction, *Electrocatalysis*, 2023, **14**, 418–428.
- 170 L. S. Liu, X. Shi, W. Wang, M. F. Pei, C. X. Hong, Y. L. Xue,Z. W. Xu, F. Tian and X. F. Guo, Carbon nitride/positive carbon black anchoring Pt NPs assembled by gamma-rays

as ORR catalyst with excellent stability, *Nanotechnology*, 2021, **32**, 345601.

- 171 H. Okazaki, K. Kakitani, T. Kimata, A. Idesaki, H. Koshikawa, D. Matsumura, S. Yamamoto and T. Yamaki, Changes in electronic structure of carbon supports for Pt catalysts induced by vacancy formation due to Ar⁺ irradiation, *J. Chem. Phys.*, 2020, **152**, 124708.
- 172 Y. K. Zhou, T. Holme, J. Berry, T. R. Ohno, D. Ginley and R. O'Hayre, Dopant-Induced Electronic Structure Modification of HOPG Surfaces: Implications for High Activity Fuel Cell Catalysts, *J. Phys. Chem. C*, 2010, **114**, 506–515.
- 173 Y. K. Zhou, R. Pasquarelli, T. Holme, J. Berry, D. Ginley and R. O'Hayre, Improving PEM fuel cell catalyst activity and durability using nitrogen-doped carbon supports: observations from model Pt/HOPG systems, *J. Mater. Chem.*, 2009, **19**, 7830–7838.
- 174 S. Pylypenko, A. Queen, T. S. Olson, A. Dameron, K. O'Neill,K. C. Neyerlin, B. Pivovar, H. N. Dinh, D. S. Ginley,T. Gennett and R. O'Hayre, Tuning Carbon-Based Fuel

Cell Catalyst Support Structures via Nitrogen Functionalization. II. Investigation of Durability of Pt-Ru Nanoparticles Supported on Highly Oriented Pyrolytic Graphite Model Catalyst Supports As a Function of Nitrogen Implantation Dose, *J. Phys. Chem. C*, 2011, **115**, 13676–13684.

- 175 W. Wang, S. S. Liu, C. Y. Min, M. Zeng, H. T. Shi, R. Q. Shao, S. K. Liu, Z. W. Xu, Y. H. Xia and N. Li, A Cathode Material of Fuel Cells: F-Doped gamma-Graphyne/PtPd Nanocomposite from Plasma Activation and Gamma Irradiation, ACS Appl. Energy Mater., 2022, 5, 2036–2044.
- 176 Y. R. Uhm, G. M. Sun, J. Lee, C. S. Kim, J. H. Park and T. Ha, Fe-Nx active sites in Fe-N-C electrocatalysts synthesized using electron beam irradiation, *J. Korean Phys. Soc.*, 2023, **82**, 286–292.
- 177 W. Wang, X. M. Zhao, H. T. Shi, L. S. Liu, H. Deng, Z. W. Xu, F. Tian and X. R. Miao, Shape inducer-free polygonal angle platinum nanoparticles in graphene oxide as oxygen reduction catalyst derived from gamma irradiation, *J. Colloid Interface Sci.*, 2020, 575, 1–15.