Nanoscale Advances

PAPER

Check for updates

Cite this: Nanoscale Adv., 2025, 7, 1452

ROYAL SOCIETY OF CHEMISTRY

> View Article Online View Journal | View Issue

Highly selective ethanol gas sensor based on CdS/ Ti₃C₂T_x MXene composites[†]

Ly Tan Nhiem, () ‡^a Jianbin Mao, ‡^b Qui Thanh Hoai Ta () *^c and Soonmin Seo () *^b

Sensing of hazardous gases has an important role in ensuring safety in a variety of industries as well as environments. Mainly produced by the combustion of fossil fuels and other organic matter, ethanol is a dangerous gas that endangers human health and the environment. Stability and sensing sensitivity are major considerations when designing gas sensors. Here, a superior ethanol sensor with a high response and fast recovery was synthesized by "wrapping" CdS nanoparticles on metallic $Ti_3C_2T_x$ MXene using a simple method. CdS nanoparticles were uniformly covered on the $Ti_3C_2T_x$ MXene surface, forming a "rice crust"-like heterostructure. The sensor displayed good detection of ethanol gas at room temperature. Response signals up to 31% were obtained for ethanol molecules (20 ppm) with quick recovery (41 s). The performance of the ethanol sensor was evaluated across a range of concentrations (5–100 ppm) and relative humidity (60% and 90% RH) at room temperature. Our method could open up a new strategy for the development of ethanol sensors.

Received 9th November 2024 Accepted 7th January 2025

DOI: 10.1039/d4na00927d

rsc.li/nanoscale-advances

1. Introduction

Volatile organic compounds (VOCs) are flammable and poisonous gases. They are found mostly in refineries, mining industries, and our daily lives. Exposure to VOCs by animals and humans can affect the respiratory system. Ethyl alcohol (ethanol) is popularly utilized as a organic solvent in cosmetics, and chemical laboratories.1-4 Ethyl alcohol is a well-known VOC and can be hazardous to consciousness upon heavy exposure, causing dizziness, vomiting, and nausea. Additionally, extreme leakage of ethyl alcohol could cause fires and explosions because of its high flammability. Most detection sensors in the market are costly and consume a lot of power because of the sensor material and design.5,6 Consequently, developing a willingly accessible and low-cost gas detector with a limit of detection towards that of ethyl alcohol is crucial for environmental monitoring. Resistive gas sensors are attractive thanks to their swift and specific determination of toxic gases compared with heavyweight and nonportable systems such as

‡ These authors contributed equally to this work.

liquid chromatography-mass spectrometry, flue gas analyzers, and gas chromatography-mass spectrometry.^{7,8}

Since the first exploration of two-dimensional materials in 2004, graphene has garnered rigorous research curiosity owing to its chemical and physical properties.9 Besides, MXenes could be used as gas sensors owing to their surface functional groups and metallic properties. These multilayer MXenes have a universal formulation of $M_{n+1}X_nT_z$ (n = 1-3) whereby M denotes early transition metals (Mo, Ti, V, Nb, Cr), X is nitrogen and/or carbon, and T_z represents the termination groups (F, Cl, Br, I, O, OH).¹⁰⁻¹⁴ In 2017, the first report about gas sensing of Ti₃C₂T_x MXene was published by Lee *et al.*,¹⁵ which displayed ptype sensing properties toward ammonia, acetone, methanol, and ethanol. That report was followed by a speedily increasing number of studies due to their excellent properties, such as electrical conductivity $(10^3 - 10^4 \text{ S cm}^{-1})$, large surface area, high hydrophilicity, versatile surface chemistry, and high mechanical stability. Interestingly, the surface termination groups of $Ti_3C_2T_x$ MXene offer a hydrophilic surface with a greatly negative zeta potential (-30 to -80 mV), which enables effective processing of a combination of $Ti_3C_2T_x$ MXene with other nanomaterials to form a smart composition.16-19

2D MXene nanosheets are readily restacked after a long time, which results in low sensitivity and stability of gas sensors made of pristine MXene.²⁰ Furthermore, pure $Ti_3C_2T_x$ -MXene gas sensors are unsatisfactory in terms of the limit of detection and selectivity.²¹ In order to overcome these problems, the construction of heterostructures has improved the performance of MXene-based gas sensors. $Ti_3C_2T_x$ MXene is modifiable thanks to its excellent electrical characteristics and its high electronic density in the Fermi energy level. Studies have shown

^aFaculty of Chemical and Food Technology, Ho Chi Minh City University of Technology and Education, 01 Vo Van Ngan Street, Linh Chieu Ward, Thu Duc City, Ho Chi Minh City, Vietnam. E-mail: nhiemlt@hcmute.edu.vn

^bCollege of BioNano Technology, Gachon University, Gyeonggi 13120, Republic of Korea. E-mail: mg2895852@gmail.com; soonmseo@gachon.ac.kr

^cInstitute of Chemical Technology, Vietnam Academy of Science and Technology, 1A TL29 Street, Thanh Loc Ward, District 12, Ho Chi Minh City, 700000, Vietnam. E-mail: tathanhhoaiqui2292@gmail.com

[†] Electronic supplementary information (ESI) available. See DOI: https://doi.org/10.1039/d4na00927d

Paper

that the construction of heterostructures can effectively increase the number of adsorption sites and improve gas sensing capabilities.^{22,23} The MXene/In₂O₃ heterostructure, formed via a simple process, disperses In₂O₃ on MXene layers, enabling NH₃ detection with high sensitivity and selectivity at room temperature.²⁴ The MXene/SnS₂ heterojunction sensor exhibits excellent sub-ppm ammonia detection, sensing NH₃ down to 10 ppb at room temperature.²⁵ The room temperature sensor has a crucial role because high temperatures impede its usability in wearable applications. Operating at high temperatures results in increased energy consumption when detecting toxic gases at high concentrations. Furthermore, hightemperature operation compromises the nanostructure of the sensing material (thereby reducing its gas sensing efficiency) but also poses challenges in detecting explosive or flammable gases.12,26

Cadmium sulfide (CdS) stands out due to its small bandgap (2.4 eV), efficient absorption of light, and excellent charge separation properties.^{27,28} Additionally, CdS is stable, non-toxic, and safe.29 As an important member of the II-VI compound family, CdS has been widely applied in various fields and studies, including sensors, lasers, solar cells, photoelectric detection, biomedical tags, photocatalysis, electroluminescent devices, the hydrogen evolution reaction (HER), and photoconductors.30-33 CdS has also been reported in sensor applications for the detection of gases.^{34,35} For example, Giberti et al. developed a gas sensor using an as-synthesized CdS thick film.³⁶ However, the strong selectivity for alcohols requires a temperature of 300 °C, which is too high for practical applications. The high working temperature, high limit of detection, and poor conductivity of CdS hinder its application in CdSbased gas sensing. Therefore, there is an immediate requirement to develop a CdS-based gas sensor with high selectivity and enhanced responding performance at room temperature. Recently, Guo et al. demonstrated that having many active sites can enhance gas sensing properties by boosting the adsorption capacity for the target gas, thus increasing the affinity for gas molecules.29 According to our previous research, nanostructured semiconductors with mesoporous, nanomesh, and nanowire structures can provide many active sites.37-39 Moreover, semiconductors with narrow energy band gaps (e.g., CdS, CdO) exhibit higher charge carrier concentrations but also lower resistivity, which enhances the adsorption energy of oxidizing gas molecules.40-42

It has been reported that $CdS/Ti_3C_2T_x$ can be used in the photocatalytic field. A stable $Ti_3C_2T_x$ MXene/CdS heterojunction catalyst, created *via in situ* growth of CdS on $Ti_3C_2T_x$ MXene, enhances hydrogen production by broadening NIR absorption, accelerating photochemical reactions, enabling efficient electron separation, and reducing carrier recombination.⁴³ In another study, it has been demonstrated that grafting MXene with CdS enhances charge separation, optimizes pore structure, and increases surface area, improving photocatalyst-reactant contact.⁴⁴ In the meantime, ultrathin $Ti_3C_2T_x$ can reduce CdS aggregation, forming Schottky junctions that boost photocatalytic activity by improving charge separation and electron transfer.⁴⁵ It also enhances H_2O_2 selectivity and enables a high-

performance photo-Fenton system. In CdS, the sulfur (S) element exhibits low electronegativity, which facilitates the adsorption of oxygen molecules and their subsequent reaction with reactive sulfur species (S²⁻) to generate a series of ionized oxygen species. Consequently, the activation energy required for the conversion of O₂ molecules to these ionized oxygen species at CdS sites is lower than that necessary on metal oxide surfaces. As a result, more ionized oxygen species are generated on CdS structures. It is well established that ionized oxygen species have critical roles in gas sensing reactions. Thus, CdS-based sensors may operate at lower temperatures compared with traditional oxide semiconductor materials.⁴⁶ However, the combination of Ti₃C₂T_x MXene and CdS nanomaterials for use as a gas sensor has rarely been reported.

In this research, we synthesized a $CdS/Ti_3C_2T_r$ composite using Ti₃C₂T_x MXene and mesoporous CdS nanomaterials with a large surface area and uniform pore size. KIT-6, an ordered mesoporous silica, was chosen as a template because of its bicontinuous mesoporous structure, which belongs to the cubic Ia3d space group.33 This silica consists of enantiomeric pairs of interpenetrating mesoporous networks, all with uniform pore diameters. The three-dimensional (3D) connectivity of the pores make it an ideal template for creating a self-retaining replica.^{27,39} In addition, the pore diameters can be controlled in the range 4-12 nm by adjusting the synthetic conditions. Overall, the combination of the large pore size and high stability of KIT-6 and 3D interconnected mesopores makes it a highly versatile and effective template for the synthesis of advanced functional materials with "tailored" properties. We examined the VOCs gas-sensing activity of pure $Ti_3C_2T_x$ MXene and its hybrid structure at room temperature. The mesoporous structure significantly enhanced gas sensing performance by providing a high surface area and interconnected pores that facilitated efficient gas adsorption and diffusion. This structure ensured that target gas molecules could readily access the active sensing sites, thereby increasing sensitivity and enabling fast response and recovery times. In addition, the mesoporous framework supported the formation of nanostructures with optimized morphology, thereby improving the stability and reproducibility of sensor performance. These combined effects make mesoporous materials highly effective for gas-sensing applications. The optimized composite specified a response of 31% at 20 ppm at room temperature with outstanding repeatability. We demonstrated that the mesoporous CdS nanostructures covering $Ti_3C_2T_x$ strengthened the surface area but also improved electron transfer between composite and gas molecules. Additionally, the plausible sensing mechanism of $CdS/Ti_3C_2T_x$ sensor was investigated further.

2. Experimental

2.1. $Ti_3C_2T_x$ MXene preparation

To prepare $Ti_3C_2T_x$ MXene, the *in situ* HF etching method was applied. Briefly, two grams of LiF were spread in 50 mL of HCl solution (5.5 M) under vigorous stirring. Subsequently, two grams of Ti_3AlC_2 MAX phase powder (MilliporeSigma) were progressively placed into the solution in an ice bath to mitigate

exothermic reactions. The mixture solution was then kept in a bath at 50 °C for 1 day. The final product was separated by vacuum filtration and washed several times using deionized water until the pH reached around 6–7. The multilayered $Ti_3C_2T_x$ MXene was dried in a freeze-dryer before being stored for further experiments.

2.2. Synthesis of KIT-6

KIT-6 was produced according to the previously reported softtemplate method with some modifications. KIT-6 was synthesized hydrothermally, following a procedure documented in previous studies.38 KIT-6 was synthesized by preparing an aqueous solution with a 1:1 weight ratio of Pluronic P123 $(EO_{20}PO_{70}EO_{20}, MW = 5800)$ and butanol, maintaining an HCl concentration around 0.5 M at temperatures between 25 and 35 °C. Both tetraethoxysilane (TEOS) and sodium silicate can serve as silica sources. For a typical synthesis using TEOS, we dissolved 6 g of P123 in 217 g of distilled water and added 11.8 g of concentrated HCl (35%). Then, we incorporated 6 g of butanol while stirring at 35 °C. After 1 h of stirring, we added 12.9 g of TEOS at the same temperature. We continued stirring the mixture for 24 h at 35 °C, then heated it for an additional 24 h at 100 °C under static conditions in a sealed polypropylene bottle. The solid product from the hydrothermal treatment was filtered and dried at 100 °C without washing. The template was removed by extracting it in an ethanol solution over 3 days.

2.3. Preparation of mesoporous CdS nanomaterials

We dissolved 0.6 g of $Cd(NO_3)_2 \cdot 4H_2O$ and 0.2 g of thiourea in 15 mL of ethanol at room temperature, then added 0.8 g of the

KIT-6 template to the stirring solution. After evaporating the ethanol, we spread the solid mixture in a Petri dish. The mixture was heated at 160 °C for 24 h in an air atmosphere to form the CdS@KIT-6 intermediate. The silica template was removed by treating the mixture with 50 mL of 2 M NaOH aqueous solution, which served as an etching agent, to obtain mesoporous CdS.

2.4. Preparation of CdS/Ti₃C₂T_x hybrids

We dissolved 0.11 g of Cd(NO₃)₂·4H₂O and 0.03 g of thiourea in 10 mL of ethanol at room temperature, and then added 0.3 g of the KIT-6 template to the stirring mixture. Subsequently, we gradually incorporated the pre-prepared Ti₃C₂T_x MXene (100, 200, or 300 mg) into the solution and stirred vigorously for 15 min. After evaporating the ethanol, we spread the solid mixture in a Petri dish. The mixture was heated at 160 °C for 24 h in an air atmosphere to form the CdS@KIT-6/Ti₃C₂T_x intermediate. The silica template was removed by treating the mixture with 50 mL of 2 M NaOH aqueous solution, which acted as an etching agent, to obtain CdS/Ti₃C₂T_x. The final products were named "CT1" (100 mg), "CT2" (200 mg), and "CT3" (300 mg) (Fig. 1). For comparison, pure mesoporous CdS was also prepared under the same conditions, without the addition of Ti₃C₂T_x MXene.

2.5. Characterization and measurements

The characterization methods employed in this study were: Xray diffraction (XRD; Rigaku SmartLab) using Cu K α radiation to analyze sample phase composition; scanning electron microscopy (SEM; Hitachi S-4700) to observe surface chemical characteristics and morphologies; high-performance X-ray

Fig. 1 Synthesis of CdS/Ti₃C₂T_x composites (schematic).



Paper

photoelectron spectroscopy (XPS; K-Alpha⁺) for investigating chemical states; and Brunauer–Emmett–Teller (BET) analysis using an ASAP 2020 accelerated surface area and porosimetry system to determine the specific surface areas and pore distributions of the powders. The optical properties of synthesized samples were recorded using UV-vis diffuse reflectance spectroscopy (Jasco V-770).

2.6. Gas sensor experiments

The toxic gas sensing activity of the CdS/Ti₃C₂T_x heterostructure gas sensor was recorded using a homemade system. The assynthesized samples were dispersed in deionized water at a concentration of 1 mg mL⁻¹ and then drop-coated onto a silicon wafer $(1 \times 1 \text{ cm})$ with a thickness of approximately 8– 10 µm. The sensor wafer was dried overnight to evaporate the solvent and subsequently placed within a stainless-steel chamber connected to a source measure unit (Keysight 34465A). The relative humidity of the gas testing system was calibrated by adjusting the parameters in a humidity meter. The gas concentration was calibrated to the desired level using a mass flow controller and mass flow meter (MFC/MFM) by adjusting the flow rates of synthetic air and the target gas. The diluted gas mixture was subsequently injected into the chamber after thorough mixing. The response of the CdS/Ti₃C₂T_r heterostructure was calculated as the alteration in the relative resistance in the target gas (R_{gas}) compared with that in synthetic air (R_{air}) before and after target gas injection, as follows:

$$\text{Response}(\%) = \frac{R_{\text{gas}} - R_{\text{air}}}{R_{\text{air}}} \times 100$$

3. Results and discussion

3.1. Morphological and component characterization

Fig. 2 displays the FE-SEM images of pure Ti_3AlC_2 , $Ti_3C_2T_x$, CdS and the CdS/T $i_3C_2T_x$ heterostructure. As shown in Fig. 2a, commercial Ti_3AlC_2 , had stacked, laminated and compact structures. After etching with HF acid, the $Ti_3C_2T_x$ MXene with layered and accordion-like structures was observed in Fig. 2b. Pure CdS showed a spherical granule-like structure with and average diameter of 20 nm (Fig. 2c). With abundant hydrophilic groups, CdS nanoparticles covered readily on the superficial of $Ti_3C_2T_x$ MXene, further confirming the combination of the intimate interfacial interaction between $Ti_3C_2T_x$ MXene and CdS (Fig. 2d–f).

Moreover, the results of EDS elemental mapping revealed the uniform distribution of Cd, S, Ti, C, and O elements in the CdS/ Ti₃C₂T_x heterostructure. As shown in Fig. 3a, numerous CdS NPs were decorated on the Ti₃C₂T_x MXene and a few were agglomerated on the Ti₃C₂T_x MXene. The direct close interaction between CdS and Ti₃C₂T_x MXene boosted the fast transfer and migration of generated electrons. As presented in Fig. 3b, a higher oxygen atom content (32.6% atomic%) than that in pristine Ti₃C₂T_x MXene (14%) was obtained, resulting in more oxygen termination groups, and partial formation of TiO₂ during the hydrothermal reaction.

To understand the optical properties, we also obtained the energy band gap of typical samples. Fig. S1[†] displays the UV-vis diffuse reflectance spectra of selected samples over a wavelength range of 300-800 nm. Notably, an absorption edge peak of CdS was observed at \sim 500 nm (Fig. S1a[†]). In comparison with pristine CdS, the optical absorption edge of the composite exhibited a distinct red shift to ~550 nm. This 550 nm absorption edge arose from the interband electronic transitions in CdS, indicating that CdS had been decorated and coupled within the composite.⁴⁷ As shown in Fig. S1b and d,[†] the estimated energy band gap (Eg) of pure CdS and the composite was 2.14 eV and 1.58 eV, respectively. A composite with a narrow band gap allows for easier excitation of electrons from the valence band (VB) to the conduction band (CB) with lower energy. This implies that less energy is required to trigger the electronic response of a composite to external stimuli, such as gas adsorption, potentially enhancing the sensitivity of the sensor due to the increased responsiveness to environmental changes of the material.40-42

3.2. Structural properties

Fig. 4 illustrates the detailed crystalline phase structures measured by XRD. Fig. 4a clearly shows that the (002) and (004) peaks of the as-prepared Ti₃C₂T_x MXene were shifted to smaller angles and broadened compared with those of Ti₃AlC₂ powder, indicating the formation of a laminated microstructure after HF etching.48 The diffraction peak intensity of Ti₃C₂T_r was significantly lower than that of Ti₃AlC₂. This disparity may have arisen from differences in the distribution of carbon atoms within the crystal structure and the crystal symmetry of both materials. Additionally, diffraction peaks of the original Ti₃AlC₂ MAX phase between 35° and 40° vanished, which suggested that Al atoms had been removed. This result also showed that our synthesized $Ti_3C_2T_x$ had high purity, which is in good agreement with previous reports.49 In the CdS/Ti₃C₂T_x MXene heterostructure, the diffraction peak of both Ti₃C₂T_x MXene and mesoporous CdS nanoparticles could be observed. The clear diffraction peaks at $2\theta = 26.6^{\circ}$, 30.4° , 44.1° , and 52.5° corresponded to the phases (111), (200), (220) together with (311) planes, and confirmed the existence of lattice plates of cubic zinc blended crystal structure (PDF 01-075-0581).50 In particular, in the CdS/Ti₃C₂T_x MXene heterostructure, the (002) peak was notably broadened and shifted to a lower angle compared with that in the pure $Ti_3C_2T_x$ MXene material, indicating an enlarged layer spacing (Fig. 4b).

XPS spectra were used to analyze the overall XPS spectra chemical state of the surface as well as the composition of the CdS/Ti₃C₂T_x heterostructure. The survey spectra of Ti₃C₂T_x MXene, mesoporous CdS nanoparticle, and CdS/Ti₃C₂T_x heterostructure are depicted in Fig. 5a. In addition, there were five main chemical elements on the surface, which corresponded to the elements of Cd, S, Ti, O, and C. The highly resolved spectra of the Cd 3d, S 2p, Ti 2p, O 1s and C 1s core levels for the CdS/ Ti₃C₂T_x heterostructure are displayed in Fig. 5b–f. The Cd-3d characteristic peaks located at 405.6 and 412.4 eV belonged to the Cd $3d_{5/2}$ and Cd $3d_{3/2}$ orbitals (Fig. 5b), respectively,



Fig. 2 SEM images of (a) pristine Ti_3AlC_2 , (b) $Ti_3C_2T_x$ MXene, (c) CdS (the inset figure is the TEM of CdS) and (d-f) the CdS/ $Ti_3C_2T_x$ heterostructure.



Fig. 3 (a) SEM images and (b) SEM-EDX elemental mapping of the $CdS/Ti_3C_2T_x$ heterostructure.

indicating the presence of Cd ions in the +2 oxidation state.^{51,52} Two significant peaks located at 162.0 and 163.2 eV, which were equal to the binding energy of S $2p_{3/2}$ and S $2p_{1/2}$ (Fig. 5c), showed the presence of S–S bonding in CdS.^{44,53} The Ti 2p binding energy exhibited three distinct peaks centered at 455.2 eV, 459.1 eV, and 464.9 eV, which corresponded to Ti–C

and Ti–O bonds, respectively, within the Ti 2p domain (Fig. 3d). As shown in Fig. 3e, the O 1s spectrum exhibited two main peaks at 530.8 eV and 532.1 eV, which were attributed to hydroxyl/oxygen-terminated surfaces and *in situ* oxidized TiO₂.⁵⁴ The spectrum of the C 1s peak showed two distinct peaks at 285.3 eV and 288.5 eV, which corresponded to C=C and C-Ti



Fig. 4 (a) High angle and (b) low angle XRD patterns of Ti_3AlC_2 powder, $Ti_3C_2T_x$ MXene, mesoporous CdS nanoparticle, and the CdS/ $Ti_3C_2T_x$ heterostructure.



Fig. 5 (a) Survey spectra of the mesoporous CdS nanoparticle, $Ti_3C_2T_x$ MXene, and CdS/ $Ti_3C_2T_x$ heterostructure. XPS spectra of the CdS/ $Ti_3C_2T_x$ heterostructure Cd 3d (b), S 2p (c), Ti 2p (d), O 1s (e), and C 1s (f).

Open Access Article. Published on 08 January 2025. Downloaded on 8/2/2025 4:38:23 PM.



Fig. 6 Nitrogen adsorption–desorption isotherms were conducted for Ti₃C₂T_x MXene, mesoporous CdS nanoparticles, and the CdS/Ti₃C₂T_x heterostructure. Pore-size distributions are depicted in the inset.

bonds on the surface, respectively, as depicted in Fig. 5f.^{55,56} The characterization data further indicated fabrication of the CdS/ $Ti_3C_2T_x$ heterostructure.

The nitrogen adsorption-desorption isotherms of the asprepared materials were employed to evaluate the impact of mesoporous CdS nanoparticles on the surface area of $Ti_3C_2T_x$ MXene. This evaluation aimed to assess potential improvements in gas sensing performance in terms of gas recovery and response time. As illustrated in Fig. 6, the nitrogen sorption isotherms of CdS, and CdS/Ti₃C₂T_x samples indicated the pore characteristics of these samples with respect to a type-IV isotherm with a long and narrow hysteresis loop, suggesting the presence of uniform mesoporosity.57 The BET surface area of the mesoporous CdS and the CdS/Ti₃C₂T_x heterostructure was estimated to be 81.1 and 78.4 m² g⁻¹, respectively. In addition, the average pore width of the mesoporous CdS, and $CdS/Ti_3C_2T_x$ heterostructure was 8.9, and 6.7 nm, respectively (inset of Fig. 6). These results showed that, after the preparation of mesoporous CdS and Ti₃C₂T_x MXene as heterojunction materials, a larger pore size and higher specific surface area were observed, which increased the number of active sites and facilitated electron transport.

3.3. Target gas sensing performance and mechanism

The gas sensing activity of the as-prepared CdS/Ti₃C₂T_x heterostructure-based sensors was recorded at room temperature by analyzing the resistance variation in target gases and air. First, the synthesis air was used to flow the chamber and obtain a stable condition. Fig. 7 displays the gas response of prepared CdS/Ti₃C₂T_x-based sensors to different target gas molecules. In Fig. 7a, we analyzed the responses of the as-synthesized CT1, CT2, CT3, and pure Ti₃C₂T_x MXene to 20 ppm ethanol gas. The CdS/Ti₃C₂T_x heterostructure displayed an obvious reaction to ethanol, while Ti₃C₂T_x MXene had no signal as metallic properties. The CT2 heterostructure displayed the highest gas response as compared with that of CT1, CT3, and pure $Ti_3C_2T_x$. The repeatability performance of CT2 sensors to 20 ppm ethanol after three cycles was also tested under the same parameter. As revealed in Fig. 7b, the gas responses of the CT2 sample varied slightly and had a similar tendency, which displayed reproducible results.

Fig. 7c presents the sensor response curves of CT2 against ethanol concentrations ranging from 5 to 100 ppm. All response signals increased with an increase in ethanol concentration, demonstrating a good correlation. The calculated linear regression coefficient (R^2) was ~0.88, indicating that CT2 was logarithmic in detecting ethanol molecules within this concentration range. Fig. 7d illustrates the response and recovery times as a function of gas concentration, with error bars included. The response time was \sim 507 s, compared with a recovery time of 41 s. The relatively long response time could be attributed to the need for ethanol gas to diffuse and undergo subsequent oxidation during sensing. The response time of a sensor was influenced by the number of available reactive sites, which required time to reach the optimal configuration for gas-sensing reactions. In contrast, a faster recovery time was attributed to the porous structure and rapid electron transport of the material, which provided a large surface area for diffusion and facilitated the removal of ethanol molecules under 100% airflow. This phenomenon has also been observed in previous studies.49,58

To further confirm the selectivity of the CdS/Ti₃C₂T_r heterostructure, the signal histograms of the optimized CT2 sensor for a variety of target gases to 20 ppm are presented in Fig. 7e. The signal responses to different target gases (acetone, toluene, formaldehyde, ammonia, benzene, triethylamine) were negligible. Only the $CdS/Ti_3C_2T_x$ heterostructure displayed a response to ethanol. These results further confirmed the selectivity of the CdS/Ti₃C₂T_x sensor to ethanol. Several factors may have contributed to the observed selectivity. Ethanol possesses a hydroxyl (-OH) group and a hydrocarbon chain. Although it is not perfectly symmetrical, it exhibits some symmetry that can influence its interaction with surfaces. The presence of methyl groups affects polarity and induces dipole moments. Ethanol, which primarily contains single bonds, has a lower molecular mass and volatile nature, whereas others contain carbonyl or aromatic structures with double bonds. In contrast, toluene and benzene are nonpolar compounds, resulting in minimal interaction with the sensor surface.⁵⁹ On the other hand, the greater selectivity of the $CdS/Ti_3C_2T_x$ composite can be explained via the different unoccupied molecule orbit (LUMO) energies of these gas molecules. The high value of the LUMO energy indicates that a significant amount of energy is required for the interaction between the sensor material and target gas.^{60,61} The LUMO energy of ethanol (0.12 eV) is the lowest among the gases stated above, which is better for electrons and the reaction between the composite and ethanol molecules.⁴⁶ Thus, the CdS/Ti₃C₂T_x composite had excellent selectivity towards ethanol at ambient atmosphere.

Fig. 7f illustrates the response curve of the $CdS/Ti_3C_2T_x$ composite to ethanol (20 ppm) at various levels of relative humidity. As the humidity increases, the hydroxyl groups in

80

70

60

30

20

10

50 (s) 40 Lime



Fig. 7 (a) The response/recovery properties of pristine $Ti_3C_2T_x$ MXene, and prepared CdS/ $Ti_3C_2T_x$ -based sensors, toward ethanol molecules (20 ppm). (b) Repeatability curve and (c) Langmuir isotherm curve of CT2 responses against different ethanol concentrations, and (d) response and recovery time. Response of the CT2 sensor to (e) several gases (f) at various levels of relative humidity.

 $\rm H_2O$ molecules exhibit weak electron-withdrawing behavior, interacting with electrons from the sensor material and enhancing electrical conductivity, which results in an improved response. However, a further increase in humidity leads to a decrease in response, which can be attributed to the $\rm H_2O$ poisoning effect. This phenomenon occurs if a significant number of $\rm H_2O$ molecules adsorb onto the material, obstructing the available adsorption sites for ethanol.⁶²

Moreover, the ethanol sensing response of our CdS/Ti₃C₂T_x heterostructures was compared with different MXene composite-based gas sensors: CdS nanostructures, PPy@Ti₃C₂-T_x, $W_{18}O_{49}$ @Ti₃C₂T_x, MoO₃@Ti₃C₂T_x, and Co₃O₄@Ti₃C₂T_x composites. As shown in Table 1, the optimized CT2 did not exhibit the best ethanol sensing response, but it was a promising material for ethanol detection at room temperature.

The improved ethanol sensor mechanism of the $CdS/Ti_3C_2T_x$ composite is displayed schematically in Fig. 8. The p–n junction

interface in the composite was formed due to the difference in work functions between n-type CdS (3.2 eV) and p-type $Ti_3C_2T_x$ MXene (5.9 eV).⁷⁰ As a result, electrons from CdS tend to migrate to the MXene interface to form a depletion layer. When the CdS/ $Ti_3C_2T_x$ composite is exposed to an air atmosphere, O_2 molecules are chemically adsorbed and captured on the surface of the sensor material. In particular, the oxygen molecules were converted into ionized adsorbed oxygen (O^- , O_2^- , and O^{2-}). When the CdS/Ti₃C₂T_x composite was in contact with and exposed to ethanol molecules, the chemical interaction of ethanol molecules with the ionized adsorbed oxygen could release the generated electron back to the sensor material, resulting in a thinner depletion layer, reduced hole concentration, and increased the resistance of the CdS/Ti₃C₂T_x composite.64,71-74 This sophisticated route can be explained by the following equation:

Nanoscale Advances

Paper

Material	Temp. (°C)	Concentration (ppm)	Response (%)	Ref.
PPy@Ti ₃ C ₂ T _r	RT	20	16	63
CdS film	250	5	10	36
CdS hierarchical microspheres	200	10	8	64
0.5 at% CuO-CdS	160	100	7	65
CdS quantum dot	200	1000	0	66
$W_{18}O_{49}$ (a) $Ti_3C_2T_x$	300	20	1.67	67
MoO_3 (a) $Ti_3C_2T_x$	100	20	39	68
Co_3O_4 (a) $Ti_3C_2T_x$	200	50	11	69
CdS/Ti ₃ C ₂ T _x	RT	20	31	This work





$$O_2 (g) \rightarrow O_2 (ads)$$

$$O_2 (ads) + e^- \rightarrow O_2^- (ads)$$

$$O_2^- (ads) + e^- \rightarrow 2O_2^- (ads)$$

$$C_2H_5OH (gas) + 6O_2^- \rightarrow CH_3CHO + 3H_2O + 12$$

4. Conclusions

We synthesized VOCs sensors *via* combining CdS nanostructures with $Ti_3C_2T_x$ MXene using a simple method. The asobtained CdS/ $Ti_3C_2T_x$ heterostructures sensor showed a superior sensing activity in the enhanced detection of ethanol gas at room temperature. The CdS/ $Ti_3C_2T_x$ heterostructure presented a good response of 31% towards 20 ppm ethanol, which was superior to that of pure MXene. Moreover, the optimized CdS/ $Ti_3C_2T_x$ heterostructure presented excellent selectivity with fast recovery time to ethanol molecules. The combination effect of CdS and metallic $Ti_3C_2T_x$ in the composite had a crucial role in ethanol sensing performance. Thus, the optimized CdS/ $Ti_3C_2T_x$ heterostructure provides a potential composite to synthesize and improve superior ethanol sensors.

Data availability

The data supporting this article have been included as part of the ESI.†

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was funded by the Vietnam Academy of Science and Technology (THTEXS.02/24-26).

References

- 1 B. Han, T. H. Rupam, A. Chakraborty and B. B. Saha, A comprehensive review on VOCs sensing using different functional materials: Mechanisms, modifications, challenges and opportunities, *Renewable Sustainable Energy Rev.*, 2024, **196**, 114365.
- 2 S. Sahani, S. J. Park, Y. Myung, T.-H. Pham, T. T. Tung and T. Kim, Enhanced Room-Temperature Ethanol Detection by Quasi 2D Nanosheets of an Exfoliated Polymeric Graphitized Carbon Nitride Composite-Based Patterned Sensor, *ACS Omega*, 2022, 7, 41905–41914.
- 3 A. Mangotra and S. K. Singh, Volatile organic compounds: A threat to the environment and health hazards to Living Organisms–A Review, *J. Biotechnol.*, 2024, **382**, 51–69.
- 4 Y. Xiang, X. Xie, H. Zhong, F. Xiao, R. Xie, B. Liu, H. Guo, D. Hu, P. Zhang and H. Huang, Efficient Catalytic Elimination of Toxic Volatile Organic Compounds *via* Advanced Oxidation Process Wet Scrubbing with

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Bifunctional Cobalt Sulfide/Activated Carbon Catalysts, *Environ. Sci. Technol.*, 2024, **58**, 8846–8856.

- 5 V. Sonde, A. D'souza, R. Tarapore, L. Pereira, M. P. Khare, P. Sinkar, S. Krishnan and C. V Rao, Simultaneous administration of diethylphthalate and ethyl alcohol and its toxicity in male Sprague–Dawley rats, *Toxicology*, 2000, **147**, 23–31.
- 6 S. C. Bondy, Ethanol toxicity and oxidative stress, *Toxicol. Lett.*, 1992, **63**, 231–241.
- 7 R. Guo, H. Wang, R. Tian, D. Shi, H. Li, Y. Li and H. Liu, The enhanced ethanol sensing properties of CNT@ ZnSnO3 hollow boxes derived from Zn-MOF (ZIF-8), *Ceram. Int.*, 2020, **46**, 7065–7073.
- 8 H. Roshan and M. H. Sheikhi, A novel room temperature ethanol sensor based on PbS: SnS2 nanocomposite with enhanced ethanol sensing properties, *J. Alloys Compd.*, 2020, **816**, 152666.
- 9 K. S. Novoselov, A. K. Geim, S. V Morozov, D. Jiang, Y. Zhang, S. V Dubonos, I. V Grigorieva and A. A. Firsov, Electric field effect in atomically thin carbon films, *Science*, 2004, **306**, 666–669.
- 10 S. Liu, M. Wang, C. Ge, X. Zhang, S. Lei, S. Hussain, M. Wang, G. Qiao and G. Liu, ZnO/Ti3C2 composite with oxygen vacancies and Schottky barrier for effective detection of ppb-level NO2 at room temperature, *Appl. Surf. Sci.*, 2023, **610**, 155440.
- 11 M. A. Hope, A. C. Forse, K. J. Griffith, M. R. Lukatskaya, M. Ghidiu, Y. Gogotsi and C. P. Grey, NMR reveals the surface functionalisation of Ti3C2 MXene, *Phys. Chem. Chem. Phys.*, 2016, **18**, 5099–5102.
- 12 L. X. Ou, M. Y. Liu, L. Y. Zhu, D. W. Zhang and H. L. Lu, Recent progress on flexible room-temperature gas sensors based on metal oxide semiconductor, *Nano-Micro Lett.*, 2022, 14(1), 206.
- 13 D. Xiong, X. Li, Z. Bai and S. Lu, Recent advances in layered Ti3C2Tx MXene for electrochemical energy storage, *Small*, 2018, 14, 1703419.
- 14 Z. Wei, Z. Peigen, T. Wubian, Q. Xia, Z. Yamei and S. ZhengMing, Alkali treated Ti3C2Tx MXenes and their dye adsorption performance, *Mater. Chem. Phys.*, 2018, 206, 270–276.
- 15 E. Lee, A. VahidMohammadi, B. C. Prorok, Y. S. Yoon, M. Beidaghi and D.-J. Kim, Room temperature gas sensing of two-dimensional titanium carbide (MXene), ACS Appl. Mater. Interfaces, 2017, 9, 37184–37190.
- 16 A. Gentile, C. Ferrara, S. Tosoni, M. Balordi, S. Marchionna, F. Cernuschi, M. Kim, H. Lee and R. Ruffo, Enhanced Functional Properties of Ti3C2Tx MXenes as Negative Electrodes in Sodium-Ion Batteries by Chemical Tuning, *Small Methods*, 2020, 4, 2000314.
- 17 C. Ferrara, A. Gentile, S. Marchionna and R. Ruffo, Ti3C2Tx MXene compounds for electrochemical energy storage, *Curr. Opin. Electrochem.*, 2021, **29**, 100764.
- 18 M. Benchakar, L. Loupias, C. Garnero, T. Bilyk, C. Morais, C. Canaff, N. Guignard, S. Morisset, H. Pazniak and S. Hurand, One MAX phase, different MXenes: A guideline to understand the crucial role of etching conditions on

Ti3C2Tx surface chemistry, *Appl. Surf. Sci.*, 2020, **530**, 147209.

- 19 A. Jastrzebska, E. Karwowska, D. Basiak, A. Zawada, W. Ziemkowska, T. Wojciechowski, D. Jakubowska and A. Olszyna, Biological activity and bio-sorption properties of the Ti2C studied by means of zeta potential and SEM, *Int. J. Electrochem. Sci.*, 2017, **12**, 2159–2172.
- 20 X. Wu, Y. Gong, B. Yang, Z. Mao, Z. Yan, C. Su, S. Xiong, X. Long and X. Wang, Fabrication of SnO2-TiO2-Ti3C2Tx hybrids with multiple-type heterojunctions for enhanced gas sensing performance at room temperature, *Appl. Surf. Sci.*, 2022, **581**, 152364.
- 21 R. Tian, Y. Ding, Q. Wang and P. Song, Designing advanced 2D/2D heterojunctions of MoS2 nanosheets/Ti3C2Tx MXene in gas-sensing applications, *Vacuum*, 2024, **222**, 112991.
- 22 X. Song, T. Liu, K. Gu, Z. Luo and M. Zhang, Highly selective and ultra-sensitive gas sensor based on Fe2O3/Ti3C2Tx MXene heterostructure for ppb-level n-butanol detection, *J. Alloys Compd.*, 2024, **976**, 173153.
- 23 B. Sun, F. Qin, L. Jiang, J. Gao, Z. Liu, J. Wang, Y. Zhang, J. Fan, K. Kan and K. Shi, Room-temperature gas sensors based on three-dimensional Co3O4/Al2O3@Ti3C2Tx MXene nanocomposite for highly sensitive NOx detection, *Sens. Actuators, B*, 2022, 368, 132206.
- 24 Z. Liu, T. He, H. Sun, B. Huang and X. Li, Layered MXene heterostructured with In2O3 nanoparticles for ammonia sensors at room temperature, *Sens. Actuators, B*, 2022, **365**, 131918.
- 25 T. He, S. Sun, B. Huang and X. Li, MXene/SnS2 Heterojunction for Detecting Sub-ppm NH3 at Room Temperature, *ACS Appl. Mater. Interfaces*, 2023, **15**, 4194– 4207.
- 26 C. Qi, X. Yan, Y. Wang, Y. Ning, X. Yu, Y. Hou and J. Yu, Flammability limits of combustible gases at elevated temperatures and pressures: recent advances and future perspectives, *Energy Fuels*, 2022, **36**(21), 12896–12916.
- 27 P. Zhang, M. He, W. Teng, F. Li, X. Qiu, K. Li and H. Wang, Ordered mesoporous materials for water pollution treatment: Adsorption and catalysis, *Green Energy Environ.*, 2024, 9(8), 1239–1256.
- 28 S. Hwang, H. Gu, J. L. Young, M. A. Steiner, A. B. Laursen, R. A. Crichton, Y. W. Yeh, P. E. Batson, L. C. Feldman, M. Li, K. Wyatt, A. Safari, T. G. Deutsch, E. Garfunkel and G. C. Dismukes, TiO2/TiN Interface Enables Integration of Ni5P4 Electrocatalyst with a III-V Tandem Photoabsorber for Stable Unassisted Solar-Driven Water Splitting, ACS Energy Lett., 2024, 9, 789–797.
- 29 F. Guo, C. Feng, Z. Zhang, H. Wu, C. Zhang, X. Feng, S. Lin, C. Xu, B. Zhang and H. Bai, A room-temperature and ppblevel NO2 sensor based on n-CdS/p-CuO heterojunction modified with rGO nanosheets, *Sens. Actuators, B*, 2022, 364, 131898.
- 30 S. Y. Lee, J. Y. Oh, R. P. Patil, M. Kim, J. S. Jang, H. Jin, S. Kim and H. J. Lee, A general guide for adsorption of cadmium sulfide (CdS) quantum dots by successive ionic layer adsorption and reaction (SILAR) for efficient CdS-

sensitized photoelectrochemical cells, *Appl. Surf. Sci.*, 2022, **589**, 152898.

- 31 R. Balu, A. Panneerselvam, J. R. Rajabathar, G. Devendrapandi, S. Subburaj, S. Anand, U. S. Veerasamy and S. Palani, Synergistic effect of Echinops flower-like Copper sulfide@Cadmium sulfide heterostructure for highperformance all-solid-state asymmetric supercapacitor, *J. Energy Storage*, 2023, 72, 108447.
- 32 Y. H. Li, L. Cheng, P. F. Liu, L. Zhang, M. Y. Zu, C. W. Wang,
 Y. H. Jin, X. M. Cao, H. G. Yang and C. Li, Simple Cadmium
 Sulfide Compound with Stable 95 % Selectivity for Carbon
 Dioxide Electroreduction in Aqueous Medium, *ChemSusChem*, 2018, 9, 1421–1425.
- 33 Q. Rui, J. Gao, Z. Z. Yin, J. Li, W. Cai, D. Wu and Y. Kong, A biodegradable pH and glutathione dual-triggered drug delivery system based on mesoporous silica, carboxymethyl chitosan and oxidized pullulan, *Int. J. Biol. Macromol.*, 2023, **224**, 1294–1302.
- 34 Q. T. H. Ta, L. T. Nhiem, D. T. Y. Oanh, N. H. Hieu and P. K. T. Nguyen, Review on progress in synthesis of CdS-based composites and their potential applications, *Vietnam J. Chem.*, 2024, DOI: 10.1002/vjch.202400155.
- 35 H. Bai, H. Guo, Y. Tan, J. Wang, Y. Dong, B. Liu, Z. Xie, F. Guo, D. Chen, R. Zhang and Y. Zheng, Facile synthesis of mesoporous CdS/PbS/SnO2 composites for highselectivity H2 gas sensor, *Sens. Actuators, B*, 2021, **340**, 129924.
- 36 A. Giberti, D. Casotti, G. Cruciani, B. Fabbri, A. Gaiardo, V. Guidi, C. Malagù, G. Zonta and S. Gherardi, Electrical conductivity of CdS films for gas sensing: Selectivity properties to alcoholic chains, *Sens. Actuators, B*, 2015, **207**, 504–510.
- 37 J. Mao, L. Zhou, Y. Li, Y. Tao, K. Chai, Y. Shi and W. Xu, Synthesis of MoTe2 nanowire as an efficient hydrogen evolution reaction material, *Mater. Lett.*, 2021, **290**, 129471.
- 38 J. Mao, Q. T. H. Ta, N. N. Tri, L. Shou, S. Seo and W. Xu, 2D MoTe2 nanomesh with a large surface area and uniform pores for highly active hydrogen evolution catalysis, *Appl. Mater. Today*, 2023, 35, 101939.
- 39 W. F. Peng, X. Sun, Y. Ding, P. Liu, Q. Yao and Z. H. Lu, Enhanced Activity of WOx-Promoted PdNi Nanoclusters Confined by Amino-Modified KIT-6 for Dehydrogenation of Additive-Free Formic Acid, ACS Sustain. Chem. Eng., 2023, 11(5), 1898–1908.
- 40 S. Yang, G. Lei, H. Xu, Z. Lan, Z. Wang and H. Gu, Metal oxide based heterojunctions for gas sensors: A review, *Nanomaterials*, 2021, **11**, 1026.
- 41 T. Wang, X. Kou, L. Zhao, P. Sun, C. Liu, Y. Wang, K. Shimanoe, N. Yamazoe and G. Lu, Flower-like ZnO hollow microspheres loaded with CdO nanoparticles as high performance sensing material for gas sensors, *Sens. Actuators, B*, 2017, **250**, 692–702.
- 42 T. Wang, P. Sun, F. Liu and G. Lu, Revealing the correlation between gas selectivity and semiconductor energy band structure derived from off-stoichiometric spinel CdGa2O4, *Sens. Actuators, B*, 2022, **352**, 131039.

- 43 T. Y. Huang, Z. Yang, S. Y. Yang, Z. H. Dai, Y. J. Liu, J. H. Liao, G. Y. Zhong, Z. J. Xie, Y. P. Fang and S. S. Zhang, Construction of 2D/2D Ti3C2Tx MXene/CdS heterojunction with photothermal effect for efficient photocatalytic hydrogen production, *J. Mater. Sci. Technol.*, 2024, **171**, 1–9.
- 44 J.-Y. Li, Y.-H. Li, F. Zhang, Z.-R. Tang and Y.-J. Xu, Visiblelight-driven integrated organic synthesis and hydrogen evolution over 1D/2D CdS-Ti3C2Tx MXene composites, *Appl. Catal.*, *B*, 2020, **269**, 118783.
- 45 Z. Yang and J. Wang, CdS Nanoparticles Supported on Ti3C2Tx MXene for the Efficient Photocatalytic Production of H2O2: Implications for the Photocatalytic Degradation of Emerging Contaminants, *ACS Appl. Nano Mater.*, 2023, 6, 558–572.
- 46 L. Zhu, C. Feng, F. Li, D. Zhang, C. Li, Y. Wang, Y. Lin, S. Ruan and Z. Chen, Excellent gas sensing and optical properties of single-crystalline cadmium sulfide nanowires, *RSC Adv.*, 2014, 4, 61691–61697.
- 47 X. Geng, J. You and C. Zhang, Microstructure and sensing properties of CdS-ZnO_{1-x} coatings deposited by liquid plasma spray and treated with hydrogen peroxide solution for nitrogen dioxide detection at room temperature, *J. Alloys Compd.*, 2016, **687**, 286–293.
- 48 Y. Yang, L. Shi, Z. Cao, R. Wang and J. Sun, Strain Sensors with a High Sensitivity and a Wide Sensing Range Based on a Ti3C2Tx (MXene) Nanoparticle–Nanosheet Hybrid Network, *Adv. Funct. Mater.*, 2019, **29**, 201807882.
- 49 J. Liang, Y. Han, H. Chen, Y. Zhang and X. Gao, Layered Ti3C2Tx MXene heterostructured with V2O5 nanoparticles for enhanced room temperature ammonia sensing, *J. Alloys Compd.*, 2024, **1010**, 177798.
- 50 A. Karkhaneh and M. Marandi, Facile modified chemical precipitation approach for the synthesis of $\text{CuIn}_{1-x}\text{S2}$ nanocrystals and their application in high-performance $\text{CuIn}_{1-x}\text{S2}/\text{CdS}$ co-quantum dots sensitized solar cells, *J. Mater. Sci.:Mater. Electron.*, 2024, **35**, 847.
- 51 G. Burashev, B. Tatykayev, M. Baláž, N. Khan, A. Jumagazieva, Z. Iskakbayeva, A. Seysembekova, S. Tugelbay, N. Turgynbay and A. Niyazbayeva, The superiority of the photocatalytic and antibacterial performance of mechanochemically synthesized CdS nanoparticles over solvothermal-prepared ones, *Semicond. Sci. Technol.*, 2024, **39**, 045006.
- 52 Z. Wei, W. Mao, J. Liu, Y. Xiao, M. Zhu and Y. Tian, CdS nanorods decorated with ultrathin MoS 2 nanosheets for efficient visible-light photocatalytic H 2 production, *J. Mater. Sci.:Mater. Electron.*, 2020, **31**, 4574–4581.
- 53 Y. Chen, T. Shan, L. Liu, L. Shen, H. Xue and M.-Q. Yang, Construction of embedded CdS nanosheets@ PEA2PbBr4 nanoplate pn heterojunction photocatalysts with spatial charge transfer for enhanced benzylic C (sp3)-H bond oxidation, *Chem. Eng. J.*, 2024, **480**, 148099.
- 54 Y. Liu, H. Zhang, D. Zhu, J. Duan, A. C. Miruka, L. Tang and L. Cai, Enhanced degradation of tetracycline by TiO2@ MXene with peroxydisulfate under visible light irradiation, *Sep. Purif. Technol.*, 2024, 343, 127122.

- 55 Y. Vasseghian, V. D. Doan, T. T. T. Nguyen, T.-T. T. Vo, H. H. Do, K. B. Vu, Q. H. Vu, T. Dai Lam and V. A. Tran, Flexible and high-sensitivity sensor based on Ti3C2–MoS2 MXene composite for the detection of toxic gases, *Chemosphere*, 2022, **291**, 133025.
- 56 G. Huang, S. Li, L. Liu, L. Zhu and Q. Wang, Ti3C2 MXenemodified Bi2WO6 nanoplates for efficient photodegradation of volatile organic compounds, *Appl. Surf. Sci.*, 2020, 503, 144183.
- 57 T.-L. T. Le, T.-H. T. Le, H. T. Huu, D. T. T. Nu, L. N. Thi, T. T. T. Phan, K. N. Van, P. H. Nguyen and V. Vo, Designing S-scheme of TiO2(a) g-C3N4/graphene Heterojunction with enhanced photocatalytic activity under visible light: Experiments and DFT calculations, *J. Alloys Compd.*, 2024, 174716.
- 58 Z. Wang, T. Han, T. Fei, S. Liu and T. Zhang, Investigation of microstructure effect on NO2 sensors based on SnO2 nanoparticles/reduced graphene oxide hybrids, ACS Appl. Mater. Interfaces, 2018, 10, 41773–41783.
- 59 P. Dwivedi, S. Das and S. Dhanekar, Wafer-Scale Synthesized MoS2/Porous Silicon Nanostructures for Efficient and Selective Ethanol Sensing at Room Temperature, ACS Appl. Mater. Interfaces, 2017, 9, 21017–21024.
- 60 L. Liu, S. Shu, G. Zhang and S. Liu, Highly Selective Sensing of C2H6O, HCHO, and C3H6O Gases by Controlling SnO2 Nanoparticle Vacancies, ACS Appl. Nano Mater., 2018, 1, 31–37.
- 61 J. Walker, P. Karnati, S. A. Akbar and P. A. Morris, Selectivity mechanisms in resistive-type metal oxide heterostructural gas sensors, *Sens. Actuators, B*, 2022, **355**, 131242.
- 62 K. Y. Shin, A. Mirzaei, W. Oum, E. B. Kim, H. M. Kim, S. Moon, S. S. Kim and H. W. Kim, Enhanced NO2 gas response of ZnO–Ti3C2Tx MXene nanocomposites by microwave irradiation, *Sens. Actuators, B*, 2024, **409**, 135605.
- 63 G. Wu, H. Du, K. Pakravan, W. Kim, Y. L. Cha, M. Beidaghi, X. Zhang, X. Pan and D.-J. Kim, Wearable room-temperature ethanol sensor based on Ti3C2Tx/Polypyrrole functionalized face mask for drunk driving monitoring, *Carbon*, 2024, **216**, 118565.
- 64 T. Xu, X. Wei, F. Zhao, G. Wang, Z. Deng, J. Zhao and J. Yao, One-step synthesis of CdS hierarchical microspheres and its ethanol sensing property, *Appl. Surf. Sci.*, 2022, **595**, 153545.
- 65 N. Zhang, X. Ma, Y. Yin, Y. Chen, C. Li, J. Yin and S. Ruan, Synthesis of CuO-CdS composite nanowires and their

ultrasensitive ethanol sensing properties, *Inorg. Chem.* Front., 2019, 6, 238–247.

- 66 S. Chakraborty and M. Pal, Improved ethanol sensing behaviour of cadmium sulphide nanoflakes: Beneficial effect of morphology, *Sens. Actuators, B*, 2017, **242**, 1155–1164.
- 67 S. Sun, M. Wang, X. Chang, Y. Jiang, D. Zhang, D. Wang, Y. Zhang and Y. Lei, W18O49/Ti3C2Tx Mxene nanocomposites for highly sensitive acetone gas sensor with low detection limit, *Sens. Actuators, B*, 2020, **304**, 127274.
- 68 S. Zhang, P. Song, J. Sun, Y. Ding and Q. Wang, MoO3/ Ti3C2Tx MXene nanocomposites with rapid response for enhanced ethanol-sensing at a low temperature, *Sens. Actuators, B*, 2023, **378**, 133216.
- K. Bu, F. Ma, Q. Wu, H. Wu, Y. Yuan, L. Hu, C. Han, X. Wang, W. Liu and X. Li, Metal-organic frameworks-derived Co3O4/Ti3C2Tx Mxene nanocomposites for high performance ethanol sensing, *Sens. Actuators, B*, 2022, 369, 132232.
- 70 T. Y. Huang, Z. Yang, S. Y. Yang, Z. H. Dai, Y. J. Liu, J. H. Liao and S. S. Zhang, Construction of 2D/2D Ti3C2Tx MXene/CdS heterojunction with photothermal effect for efficient photocatalytic hydrogen production, *J. Mater. Sci. Technol.*, 2024, **171**, 1–9.
- 71 M. Sbeah, A. Zyoud, M. Ishteiwi, M. Hajjyahya, N. Al Armouzi, N. Qamhieh, A. R. Hajamohideen, S. Zyoud, H. H. S. Helal and H. Bsharat, Assessment of flexible pristine CdS film electrodes in photoelectrochemical lightto-electricity conversions, *Mater. Chem. Phys.*, 2023, 293, 126967.
- 72 C. Yue, Z. Zhang, Z. Liu, Y. Mu, Z. Yang, D. Dastan, X.-T. Yin and X. Ma, High-performance ethanol gas sensor with fast response/recovery rate based on the construction of SnO2-CdS heterojunction, *J. Alloys Compd.*, 2024, **981**, 173742.
- 73 F. Chen, C. Hong, J. Jiang, Z. Zhang and Q. Zhou, A comparative DFT study on the adsorption properties of lithium batteries thermal runaway gases CO, CO2, CH4 and C2H4 on pristine and Au doped CdS monolayer, *Surf. Interfaces*, 2024, **46**, 104200.
- 74 Y. He, H. Hu, J. Wang, X. Wang, M. Sun, C. Tian and C. Deng, Fabrication of multi-scale CdS/ZnO heteroarchitectures with boosted dual photocatalytic activities for hydrogen generation and organic dye degradation under solar light, *Mater. Res. Bull.*, 2023, **162**, 112180.