Polymer Chemistry

COMMUNICATION



View Article Online View Journal | View Issue

Check for updates

Cite this: *Polym. Chem.*, 2025, **16**, 1131

Received 17th January 2025, Accepted 18th February 2025 DOI: 10.1039/d5py00062a

rsc.li/polymers

Novel hyperbranched polymers from transferdominated branching radical telomerisation (TBRT) of diacrylate taxogens[†]

Samuel Mckeating,^{a,b} Corinna Smith,^{a,b} Oliver Penrhyn-Lowe,^{a,b} Sean Flynn,^{a,b} Stephen Wright,^{a,b} Pierre Chambon,^{a,b} Andrew Dwyer^{a,b} and Steve Rannard () *^{a,b}

Transfer-dominated Branching Radical Telomerisation (TBRT) allows the free radical homopolymerisation of multi-vinyl monomers whilst avoiding gelation. When using dimethacrylates, high molecular weight branched polyesters are formed with complete reaction of all vinyl functional groups. Here, we present the first report of TBRT using diacrylates and compare their homopolymerisation with that of analogous dimethacrylates. To establish very high molecular weight polyesters, diacrylate TBRT reactions required elevated temperatures. The reasons for this are investigated, including the use of model linear telomerisations of analogous mono-vinyl methacrylate and acrylate monomers.

Introduction

Transfer-dominated branching radical telomerisation (TBRT) has recently been shown to be an effective strategy for the homopolymerisation of multi-vinyl methacrylates.¹ As a chaingrowth process employing conventional free radical chemistries, TBRT provides ready and scalable access to a considerable array of new polymeric structures containing backbone chemistries typically associated with step-growth polymers (for example, polyesters from dimethacrylates).²

Since its initial report in 2020, TBRT has been employed to synthesise soluble, high molecular weight, highly branched polymers and new copolymers with a range of physical properties and potential applications.³ For example, the production of functional materials with polyester backbones, with weight-average molecular weight (M_w) values greater than 500 000 g mol⁻¹, has been consistently achieved by TBRT.⁴

TBRT differs from other approaches that have aimed to homopolymerise multi-vinyl monomers which require quenching at vinyl conversions <80% to avoid gelation.^{5,6} As a telomerisation reaction,⁷ monomers are more appropriately referred to as taxogens,⁸ and multi-vinyl taxogens (MVTs) employed in TBRT have included bisphenol-A dimethacrylate, *N*,*N*-bis(methacryloxyethyl) methylamine, 1,6-hexanediol dimethacrylate, 1,12dodecanediol dimethacrylate, and ethylene glycol dimethacrylate.^{2,3,9,10} Thiols are used in high concentrations and are known as telogens rather than the conventional term 'chain transfer agent' when used at relatively low levels.⁸

Whilst methacrylic MVTs have been instrumental in the determination of many of the mechanistic features of the polymerisation, and characterisation of the resulting TBRT polymer architectures,¹¹ MVTs containing acrylate functionality are also of interest. Acrylic and methacrylic monomers have remarkably different reactivity given their very small structural differences.^{12,13} During radical polymerisation, acrylic monomers form secondary radicals as a propagating end group, as opposed to methacrylic monomers which form more stable tertiary radicals.¹⁴ As a result, the free radical homopolymerisations of acrylic monomers proceed at a greater rate compared to their methacrylic counterparts.¹⁵

Under ideal TBRT conditions the molar ratio of MVT to telogen in the final polymer is 1:1, and thiols may be considered as side-chains within the nominal polymer repeat structure.³ Thiols are excellent Michael donors, due to the polarisable nature of the sulfur atom, and are known to undergo radical-mediated thiol-ene addition reactions; examples have been reported under photo- and thermal initiation.^{16,17} Within a TBRT diacrylate homopolymerisation, one would therefore expect the observed vinyl group consumption to result from a significant competition between radicalmediated thiol-acrylate Micheal addition and propagation to form telomer chains. If the balance of this competition favours the hydrothiolation reaction, propagation will be highly restricted, possibly leading to limited growth in molecular weight, Fig. 1A. If propagation is favoured, the TBRT of diacrylate MVTs may allow the formation of highly branched polyesters in a manner similar to those already reported for dimethacrylates, Fig. 1B.

^aDepartment of Chemistry, University of Liverpool, Crown Street, L69 7ZD, UK. E-mail: srannard@liv.ac.uk

^bMaterials Innovation Factory, University of Liverpool, Crown Street, L69 7ZD, UK † Electronic supplementary information (ESI) available: Materials, full experimental details and characterisation. See DOI: https://doi.org/10.1039/ d5py00062a



Fig. 1 Schematic representations of possible outcomes of diacrylate TBRT: (A) hydrothiolation resulting from radical mediated thiol-ene addition, and (B) thiols acting as telogens under TBRT conditions and significant propagation.

Here, we explore the potential for forming new polymers from the homopolymerisation of diacrylates using TBRT approaches. Comparative reactions with analogous dimethacrylate MVTs have been conducted, and we present studies aimed at enabling very high molecular weight branched polymer synthesis that form the basis for future studies.

Results and discussion

TBRT of acrylic and methacrylic multi-vinyl taxogens

Numerous TBRT polymerisations have demonstrated the effectiveness of 1-dodecanethiol (DDT) under TBRT conditions, therefore DDT was selected for this initial study of diacrylate homopolymerisation.¹⁻⁴ Four MVTs, two diacrylates and two dimethacrylates, were selected for comparative TBRT reactions with DDT; namely, 1,4-butanediol diacrylate (BDA), 1,6-hexanediol diacrylate (HDA), 1,4-butanediol dimethacrylate (BDMA), and 1,6-hexanediol dimethacrylate (HDMA), Scheme 1. The acrylate/methacrylate comparative pairs chosen here enable the impact of the different reactivities to be studied directly.

The TBRT conditions were standardised across all reactions of BDA, BDMA, HDA, and HDMA for consistency. In summary, the homopolymerisations were conducted in toluene (50 wt% solids content), using α, α' -azoisobutyronitrile as the radical source (AIBN, 1.5 mol% relative to total vinyl groups), and at a temperature of 70 °C. The concentration of telogen required to avoid gelation and create a soluble high molecular weight polymer is not immediately clear for unstudied MVTs, therefore the ratio of MVT to telogen ([MVT]₀/[DDT]₀) was varied in each reaction. In this manner, the limiting [MVT]₀/[DDT]₀ gel point



Scheme 1 TBRT synthesis of study branched polyesters. (A) General reaction scheme of multi-vinyl taxogens (diacrylate and dimethacrylate) with DDT; (B) nominal repeat unit structures detailing the synthesis of four branched polyesters *via* the TBRT of (i) BDA, (ii) BDMA, (iii) HDA and (iv) HDMA, with DDT utilised as the common telogen. Each polymer is shown as ideal (1:1) structures with pendant telogen residues.

ratios may also be determined. To accurately report the reagent ratios, 1 H nuclear magnetic resonance spectroscopy (NMR) was performed on all reactions prior to initiation, ESI Fig. S1–7.†

Under TBRT conditions, the expected differences in reactivity of the diacrylate and dimethacrylate MVTs were immediately apparent at 70 °C, Table 1. Triple-detection size exclusion chromatography (TD-SEC, ESI Fig. S8[†]) showed systematic increases in [MVT]₀/[DDT]₀ during the TBRT of BDMA led to a steadily increasing weight-average molecular weight (M_w) as reported previously for dimethacrylate MVTs, ESI Fig. S9.† When BDA was subjected to the same study, it was clear that the purified recovered polymers showed far lower M_w values than the analogous BDMA reactions. For example, reactions conducted at $[MVT]_0/[DDT]_0 = 0.60$ showed M_w values of 39 200 g mol⁻¹ and 8700 g mol⁻¹ for BDMA and BDA respectively. As the ratio increased, the resulting polymers followed this trend $([MVT]_0/[DDT]_0 = 0.70, BDMA: M_w = 468900 g$ mol^{-1} ; BDA: $M_w = 27\ 300\ g\ mol^{-1}$). The limiting $[MVT]_0/[DDT]_0$ gel point ratios were also substantially different with BDMA reaching an observable gel point at $[MVT]_0/[DDT]_0 > 0.72$ (and <0.75) and BDA progressing through to $[MVT]_0/[DDT]_0$ ratios up to 0.82 (and <0.85) whilst avoiding gelation.

Table 1 ¹H NMR spectroscopic and TD-SEC analyses of branched polymers generated *via* TBRT of BDA, BDMA, HDA and HDMA, using DDT at 70 °C in toluene (50 wt% solids)^e

MVT	Temperature (°C)	¹ H NMR		$\mathrm{TD}\operatorname{-}\mathrm{SEC}^d$				
		[MVT]0/[DDT]0 ^a	$[MVT]_F/[DDT]_F^b$	$M_{\rm w} \left({ m g mol}^{-1} \right)$	$M_{\rm n} \left({ m g mol}^{-1} \right)$	Đ	α	dn/da
BDMA	70	0.50	0.77	37 600	10 900	3.45	0.44	0.067
		0.60	0.82	39 200	12 100	3.24	0.43	0.068
		0.65	0.93	86 600	17 400	4.98	0.36	0.071
		0.68	0.90	210 200	17 100	12.29	0.43	0.069
		0.70	1.01	468 900	13 300	35.26	0.39	0.070
		0.72	0.95	1 180 900	23 400	50.47	0.40	0.071
		0.75	Gel formed ^{<i>c</i>}					
BDA	70	0.60	0.94	8700	3700	2.35	0.21	0.083
		0.65	0.90	12 400	5100	2.43	0.29	0.084
		0.70	0.98	27 300	5000	5.46	0.29	0.084
		0.75	0.97	31 700	6100	5.20	0.36	0.087
		0.80	0.96	40 900	5700	7.18	0.33	0.088
		0.82	0.99	64 300	7200	8.93	0.35	0.088
		0.85	Gel formed ^c					
BDA	100	0.80	0.93	19 100	2020	9.46	0.35	0.078
	100	0.83	0.92	20 400	2150	9.49	0.27	0.085
		0.89	0.99	31 800	2510	12.67	0.28	0.086
		0.95	1.03	71 800	4950	14 51	0.30	0.084
		1.01	1.00	194 700	6520	29.86	0.37	0.083
		1.05	0.99	568 100	9490	59.86	0.39	0.083
		1.00	Microsel fraction ^{c}	2 147 300	51 430	41 75	0.47	0.000
		1.05	Gel formed ^c	211,000	01 100	11.70	0.17	
HDMA	70	0.50	0.85	24 000	12,400	1 94	0.40	0.083
	, 0	0.55	0.93	25 400	11 100	2.29	0.10	0.083
		0.60	0.89	35 700	9500	3.76	0.39	0.085
		0.65	0.05	71 300	12 600	5.66	0.35	0.000
		0.67	0.94	104 900	10 410	10.08	0.42	0.004
		0.71	1 00	104 500	20 400	24.19	0.40	0.007
		0.73	0.98	2 202 200	20 400	40.21	0.41	0.087
		0.75	Gel formed ^c	2 202 200	29 900	40.21	0.39	0.007
HDA	70	0.70	0.82	5800	3000	1 03	0.30	0.081
	70	0.65	0.82	8400	3400	2.47	0.30	0.001
		0.05	0.90	17 200	5300	3 25	0.25	0.000
		0.75	0.07	16 000	6000	2.25	0.35	0.002
		0.75	0.95	10 500	7000	6.07	0.35	0.070
		0.77	0.95	42 300 54 800	6300	8 70	0.30	0.070
		0.80	Col formod ^c	34 800	0300	8.70	0.35	0.077
HDA	100	0.85		14 700	2270	6.20	0.42	0.000
	100	0.75	0.91	14 / 00	4400	4.22	0.43	0.080
		0.00	0.93	22 100	4450	4.20 5.72	0.30	0.082
		0.90	0.97	23 100 44 500	4030	0.70	0.34	0.078
		0.93	0.99	44 500	7020	22.30	0.31	0.080
		0.99	1.00	90 200 502 100	7020	12.85	0.33	0.079
		1.03	1.00 Microral fraction ^C	2 796 200	11 020	4/.4/	0.30	0.079
		1.08	Microger fraction	3 / 80 200	2/1200	13.96	0.39	_
		1 1 1	GELTOFINED.					

^{*a*} Calculated from ¹H NMR analysis of the reaction mixture at t = 0 (examples ESI Fig. S1 and S5[†]). ^{*b*} Determined by ¹H NMR analysis of purified polymers (examples ESI Fig. S3, S4 and S7[†]). ^{*c*} Formation of a microgel indicated by observed pressure during sample filtration prior to TD-SEC analysis, values shown are from the filtered sample; gel formation confirmed by visual analysis of the crude reaction. ^{*d*} Determined by triple-detection size exclusion chromatography using a 0.5% v/v TEA/THF eluent system (examples ESI Fig. S14 and S15[†]). ^{*e*} All polymerisations achieved >99% vinyl group consumption as determined by ¹H NMR (CDCl₃) analysis of crude samples of the reaction mixtures after 24 h (ESI Fig. S2 and S6[†]).

TBRT reactions utilising HDMA and HDA showed the same trend, with HDMA achieving $M_w > 70\,000$ g mol⁻¹ at [MVT]₀/ [DDT]₀ as low as 0.65 and HDA failing to match these values at [MVT]₀/[DDT]₀ \leq 0.80. Very high molecular weight polymer (M_w > 2 200 000 g mol⁻¹) was able to be formed using HDMA prior to reaching the limiting [MVT]₀/[DDT]₀ gel point ratio but purified polymers with $M_w < 60\,000$ g mol⁻¹ were only achievable with HDA before further reductions of DDT led to network formation. Under these reaction conditions, p(DDT-BDMA), p(DDT-BDA), p(DDT-HDMA), and p(DDT-HDA) all exhibited $[MVT]_{F}/[DDT]_{F}$ ratios close to 1, when appreciable molecular weight material was formed, strongly suggesting near ideal structures and the absence of significant cyclisation.¹¹

Kinetic analysis of TBRTs utilising structurally similar acrylic and methacrylic taxogens

As previously reported, the disappearance of ¹H NMR resonances relating to vinyl functionality is conventionally con-

sidered as being indicative of monomer being 'converted' to polymer within mono-vinyl polymerisations; however, within the homopolymerisation of multi-vinyl monomers a decreasing vinyl group concentration is not necessarily related to polymer formation or molecular weight growth.⁴ With two vinyl functionalities within a divinyl monomer and the presence of pendant unsaturation within the growing polymer, it is possible that vinyl groups undergo reactions that are not related to propagation. This is especially true under TBRT conditions where the formation of structures with a degree of polymerisation of just one vinyl group (DP₁) is critical to avoid gelation, Fig. 1. The term 'vinyl group consumption' is therefore used here.

To compare the TBRT polymerisation of diacrylates and dimethacrylates in finer detail, kinetic studies were undertaken for each of the MVTs using the conditions described above, Table 1.

As mentioned previously, acrylates are known to react faster than methacrylates,¹⁷ and this was also seen in the consumption of the different vinyl functionalities under TBRT conditions, Fig. 2. When monitored by ¹H NMR, all TBRT polymerisations reached >99% vinyl group consumption with BDA achieving this faster than HDA and BDMA reacting faster than HDMA. Full disappearance of vinyl resonances within 3.5 hours of initiation is entirely consistent with previous reports; for example, EGDMA exhibits >99% vinyl group consumption within 3 hours when using DDT as the telogen.¹

In stark contrast, the TBRT reactions utilising the diacrylate taxogens showed no detectable vinyl resonances within the ¹H NMR spectra of samples from BDA and HDA polymerisations after 8 minutes and 14 minutes, respectively, Fig. 2. As mentioned above, consumption of acrylic vinyl functionality may progress via two routes and it is clear from the molecular weight data, Table 1, that reactions between vinyl groups (i.e. propagation) may be playing a lesser role compared to hydrothiolation. The rapid formation of DP1 structures within TBRT polymerisations of diacrylates would, however, have two effects. Firstly, and even in the absence of propagation, each DP₁ formed removes a vinyl group, even in the early stages of the reaction, thereby decreasing the concentration of vinyl groups overall, and secondly, rapid DP1 structure formation minimises the potential for intermolecular branching reactions and high molecular weight polymers would only be formed if the rate of hydrothiolation can be moderated. Under these conditions, this is readily achieved by reducing the DDT telogen concentration relative to MVT.

The impact of reaction temperature on the TBRT of diacrylate taxogens

Studies of the effect of temperature on the TBRT of dimethacrylates showed that a thermally driven increase in chain transfer coefficient ($C_{\rm T}$) allowed a reduction in the concentration of thiol telogen to be used, with a subsequent increase in [MVT]₀/ [DDT]₀ ratios that would successfully avoid gelation.¹⁸ Essentially, the rate of chain transfer increased relative to the rate of propagation, therefore shorter telomer formation was



Fig. 2 Kinetic studies of the TBRT synthesis of (A) p(DDT-BDA) using $[MVT]_0/[DDT]_0 = 0.80$ (open yellow circles) and p(DDT-BDAA) using $[MVT]_0/[DDT]_0 = 0.67$ (grey triangles), and (B) p(DDT-HDA) using $[MVT]_0/[DDT]_0 = 0.75$ (open blue squares) and p(DDT-HDA) using $[MVT]_0/[DDT]_0 = 0.65$ (purple diamonds). $[MVT]_0/[DDT]_0$ ratios for this study were chosen as representative TBRT polymerisations unhindered by potential microgel formation.

preferred and intermolecular reactions were reduced; at any given [MVT]₀/[DDT]₀ ratio, lower molecular weight TBRT polymers were formed at higher temperatures.¹⁸

To establish the impact of temperature on diacrylate TBRT, the reactions of BDA and HDA with DDT were repeated at 100 °C. The competing reactions are potentially more complex in this scenario as hydrothiolation, chain transfer, and propagation all need to be considered.

As seen with the TBRT of dimethacrylates at elevated temperature, the limiting $[MVT]_0/[DDT]_0$ gel point ratios were again considerably increased when conducting the diacrylate TBRT reactions at 100 °C, Table 1. Homopolymerisations of BDA were successful at $[MVT]_0/[DDT]_0$ values <1.09 (previously <0.85 at 70 °C) and the TBRT of HDA avoided gelation at $[MVT]_0/[DDT]_0 < 1.08$ (previously <0.83 at 70 °C).

By conducting the diacrylate TBRTs at 100 °C and accessing the higher $[MVT]_0/[DDT]_0$ ratios, much higher molecular weight branched polyesters were achievable; for the homopolymerisations of BDA and HDA it was possible to achieve $M_w >$ 500 000 g mol⁻¹ at comparable $[MVT]_0/[DDT]_0$ ratios of 1.05

Communication

and 1.03 respectively, representing values approximately an order of magnitude higher than those achievable at 70 °C, Table 1 & Fig. 3.

As molecular weight evolution within TBRT is governed by the intermolecular reaction of pendant vinyl groups,¹ it is clear that the elevated reaction temperature enables a higher degree of propagation. In addition, this must be accompanied with a concomitant higher rate of chain transfer to avoid gelation at lower concentrations of DDT. The behaviour of both BDA and HDA under TBRT conditions is remarkably similar in this respect, Fig. 4.



Fig. 3 Size exclusion chromatography (RI detector signal) of branched polyesters formed from the TBRT of BDA at 70 °C (yellow solid lines) and 100 °C (yellow dotted line), and HDA at 70 °C (blue solid line) and 100 °C (blue dotted line) using DDT as the telogen. Samples shown were synthesised at the highest achievable [MVT]₀/[DDT]₀ ratios before indication of the onset of gelation ([MVT]₀/[DDT]₀: BDA (70 °C, 0.82); BDA (100 °C, 1.05) HDA (70 °C, 0.80) HDA (100 °C, 1.03)). Chromatograms are approximately normalised to peaks at \approx 18.5 mL elution for comparative analysis of temperature effects



Fig. 4 Variation in M_w for the diacrylate TBRT reactions conducted at 70 °C (BDA – yellow open circles; HDA – blue open squares) and 100 °C (BDA - yellow closed circles; HDA - blue closed squares) in the presence of DDT and varying [MVT]₀/[DDT]₀ ratios.

Investigating the temperature dependence of linear telomerisations using mono-vinyl acrylate taxogens

In our previous report of the impact of temperature on the TBRT of dimethacrylate taxogens, branched polyesters with comparable M_{w} values were ultimately achievable even though higher [MVT]₀/[DDT]₀ ratios (reduced telogen) were able to be employed.¹⁸ For the formation of branched polyesters from diacrylate taxogens it is evident that far higher $M_{\rm w}$ polymers are available when conducting the polymerisations at elevated temperature and reduced DDT concentration. It is not clear, however, whether this is due to a considerable increase in $C_{\rm T}$ relative to hydrothiolation, therefore linear telomerisation studies of mono-vinyl taxogens were conducted over a range of reaction temperatures (70 °C-100 °C).

Both n-butyl acrylate (BuA) and n-butyl methacrylate (BuMA) mono-vinyl taxogens were employed in the linear telomerisation study as contrasting, or similar, behaviour was expected to be readily observed.^{2,19} Each reaction was carried out at 50 wt% solids in toluene and a $[Taxogen]_0: [DDT]_0$ molar ratio of 2:1 with AIBN (1.5 mol% relative to vinyl group), ESI Fig. S10-12, Table S1 and Scheme S1.[†] The resulting telomer products were characterised by oligomer-SEC with each multimodal distribution subjected to deconvolution analysis using a Gaussian-Loren Cross function to establish the proportions of each telomeric species relative to the total chain length distribution, ESI Fig. S13 and 14.[†] To compensate for the reduced resolution of peaks at lower retention volume, the data was grouped into one peak representative of telomer chains with DP₅ or higher and the corresponding total area was integrated, Fig. 5A.

Comparison of the telomeric products tel(DDT-BuMA) and tel(DDT-BuA) from the temperature study showed a number of trends, Fig. 5B & C, ESI Table S2 and Fig. S15.† Firstly, as the temperature was increased within the tel(DDT-BuMA) synthesis, a general increase in the proportion of DP_1 and DP_2 structures was observed with a subsequent decrease in DP5+ telomers. This is consistent with an increasing $C_{\rm T}$, the enhancement in chain transfer relative to propagation, and the formation of shorter chain species. This is entirely consistent with our previous reports.^{2,4,18}

When considering the formation of tel(DDT-BuA)at different temperatures, it is clear that DP_1 and DP_2 structures contribute a far higher percentage of the overall distribution than their equivalents within the tel(DDT-BuMA), and structures >DP₄ are dramatically reduced in number. Far more striking is the lack of any noticeable impact across a 30 °C increase in reaction temperature on the overall ratio of telomers formed. Not only do the relative proportions of each telomer chain species stay essentially unchanged in samples generated at each temperature, there is also negligible variation in absolute percentage of these species between samples, Fig. 5C. The rationale for this lack of variation is not entirely clear but it would suggest that the rates of chain transfer, propagation, and, potentially, hydrothiolation have increased but remain in proportion, or hydrothiolation has potentially become unim-



Fig. 5 Comparative study of linear telomerisation of n-butyl methacrylate (BuAA) and n-butyl acrylate (BuA): (A) example of oligomer SEC and deconvolution of peaks to allow quantification of telomer species with different chain lengths, (B) comparison of fraction integrals *tel*(DDT-BuAA) synthesised between 70 °C-100 °C, and (C) comparison of fraction integrals *tel*(DDT-BuA) synthesised between 70 °C-100 °C. Solid arrows indicate increases or decreases for species within the *tel*(DDT-BuA) distributions relative to *tel*(DDT-BuAA).

portant at higher temperature and the rate of chain transfer has increased far faster than propagation. This latter possibility is unlikely given how consistent the data is across the four temperatures studied.

Mechanistic considerations for TBRT of diacrylate MVTs

The lack of any temperature dependence on the linear telomer distributions within *tel*(DDT-BuA) samples is contrary to the results seen when p(DDT-BDA) as synthesised under TBRT conditions at high temperatures. If the rates of chain transfer, propagation, and, presumably, hydrothiolation are not affected relative to each other it would be unlikely that higher [MVT]₀/ [DDT]₀ ratios would be accessible or higher M_w polymers would be achievable at 100 °C.

One plausible mechanism involves the formation of DP_1 structures early in the TBRT of diacrylates by hydrothiolation, Scheme 2A. As mentioned previously, it is generally believed that DP_1 structures are formed predominantly in the latter stages of dimethacrylate TBRT reactions, however, if one of the

acrylate functional groups is modified to form a DP₁ structure, leaving the second acrylate to still react into the growing branched polymer, this would be analogous to a copolymerisation using a small concentration of mono-vinyl taxogen, Scheme 2B. This has been explored within previous reports and even very low incorporation of mono-vinyl taxogen decreases the molecular weight of the polymers formed at any given [MVT]₀/[DDT]₀ ratio. This is readily understood as incorporation of mono-vinyl species decreases the average vinyl functionality of any telomeric substructure and reduces the probability of intermolecular branching.³ This allows reduced telogen to be used in further reactions and higher molecular weights to be accessed.

From a different perspective, the primary difference between the linear telomerisations studied here and TBRT reactions is the presence of divinyl functionality. Flory– Stockmayer theory assumes that the reactivity of vinyl species is unchanged during polymerisation, therefore pendant vinyl groups have the same reactivity as unreacted monomers.^{20–23}



Scheme 2 Proposed mechanisms for the enhanced formation of DP_1 structures within diacrylate TBRT. (A and B) Hydrothiolation leading to a mixed mono-/multi-vinyl taxogen feedstock and copolymerisation, and (C and D) conventional TBRT with additional chain transfer to polymer generating DP_1 structures without the intervention of additional telogen.

This assumption has been widely debated and is too simplistic when considering TBRT.

During linear telomerisations, all vinyl functional groups are monomeric and the impact of steric hinderance on the reaction of the active radical species is presumably relatively small when generating such short chains ($DP_n < 5$ monomer units). TBRT utilises the intermolecular branching that occurs when pendant vinyl groups on growing polymeric structures react together. The steric constraints increase with vinyl consumption and DP_1 structures are assumed to predominantly form towards the end of the reaction and hinder gelation. By definition, DP_1 structures do not require propagation and are formed by either chain transfer to a small molecule telogen (DDT used here) or hydrothiolation in the case of diacrylates. The linear telomerisation model, therefore, potentially holds limited relevance to the mechanistic understanding of diacrylate TBRT reactions.

The question of what is allowing additional control of diacrylate TBRT at high temperatures remains. Acrylate polymerisations under free radical conditions are known to undergo backbiting reactions resulting from intramolecular chaintransfer. Intermolecular chain-transfer to polymer is also well understood.²⁴ TBRT does not generate extended C–C polymer backbones, hence the formation of polyesters from di(meth) acrylate MVTs, however, backbiting reactions do not require very long chains to exist, and are understood to proceed through the formation of a six-membered transition state.¹³ Along with backbiting, intermolecular chain transfer to polymer provides additional mechanisms for DP₁ formation that are not available in the TBRT of dimethacrylates, and are not reliant on the action of a telogen, Scheme 2C & D.

This would allow successful TBRT at reduced telogen concentrations (higher $[MVT]_0/[DDT]_0$ ratios). The formation of new backbone-situated secondary and tertiary radical species *via* these routes may become more important for diacrylate TBRT at higher temperatures, and provide additional routes for propagation, resulting in the observed higher molecular weight polymers.

As discussed earlier, TBRT has been reported to form intramolecular cycles which also aid the avoidance of gelation.¹¹ As with the reactions carried out at 70 °C, the $[MVT]_F/[DDT]_F$ ratios of purified branched p(BDA-DDT) and p(HDA-DDT) polyesters formed at 100 °C are also very close to 1, Table 1, indicating a lack of any significant cyclisation.

Conclusions

As a novel polymerisation technology, the scope of TBRT for producing functional materials still requires detailed exploration. Numerous descriptions of dimethacrylate homopolymerisation have shown the formation of a range of new branched polymer structures, however, diacrylate homopolymerisation has, until now, been unreported. TBRT has again been shown to be a versatile synthetic platform for producing high molecular weight branched macromolecules, but to successfully achieve very high molecular weight samples, elevated temperatures were required in this case. Attempting TBRT with varying vinyl functionalities may require additional considerations, but branched polyesters derived from diacrylates may offer new opportunities and novel copolymers. This will require future study, especially when assessing the use of different telogens, the impact of polymerisation solvent and the structure of the diacrylate taxogens themselves.

Author contributions

SMck, OPL and CS were responsible for conceptualisation, methodology, experimentation, investigation, data curation, formal analysis, visualisation and writing of the original draft. SF and SW contributed to validation and scrutiny of data. AD contributed to supervision, project administration, analytical services and validation. SPR was responsible for funding acquisition, conceptualisation of the research programme, methodology, validation, visualisation, supervision, project administration and manuscript review and editing.

Data availability

All data generated during this study supporting its findings are available within the manuscript and the ESI.[†] All data is available from the corresponding author upon reasonable request.

Conflicts of interest

SPR and SW are co-inventors on patents that protect TBRT chemistry; several of these patents have been licensed to Scott Bader and form the basis of Polymer Mimetics Ltd (Company number 12598928).

Communication

Acknowledgements

The Engineering & Physical Sciences Research Council (EPSRC) are gratefully acknowledged for funding through grant EP/X010864/1. CS is grateful to the Centre of Excellence for Long-acting Therapeutics (CELT) for PhD funding. The authors would like to thank the Materials Innovation Factory (University of Liverpool) for analytical support.

References

- 1 S. R. Cassin, P. Chambon and S. P. Rannard, *Polym. Chem.*, 2020, **11**, 7637–7649.
- 2 O. B. Penrhyn-Lowe, S. Flynn, S. R. Cassin, S. Mckeating, S. Lomas, S. Wright, P. Chambon and S. P. Rannard, *Polym. Chem.*, 2021, **12**, 6472–6483.
- 3 S. R. Cassin, S. Flynn, P. Chambon and S. P. Rannard, *Polym. Chem.*, 2022, **13**, 2295–2306.
- 4 S. Flynn, B. Linthwaite, O. B. Penrhyn-Lowe, S. Mckeating,
 S. Wright, S. R. Cassin, P. Chambon and S. P. Rannard, *Polym. Chem.*, 2023, 14, 5102–5114.
- 5 T. Zhao, Y. Zheng, J. Poly and W. Wang, Nat. Commun., 2013, 4, 1873.
- 6 M. L. Koh, D. Konkolewicz and S. Perrier, *Macromolecules*, 2011, 44, 2715–2724.
- 7 C. Boyer, G. Boutevin, J. J. Robin and B. Boutevin, *Polymer*, 2004, **45**, 7863–7876.
- 8 B. Boutevin, J. Polym. Sci., Part A: Polym. Chem., 2000, 38, 3235-3243.

- 9 O. B. Penrhyn-Lowe, S. R. Cassin, P. Chambon and S. Rannard, *Nanoscale Adv.*, 2022, 4, 4051–4058.
- 10 S. Cassin, S. Flynn, P. Chambon and S. P. Rannard, RSC Adv., 2021, 11, 24374–24380.
- S. R. Cassin, S. Wright, S. Mckeating, O. B. Penrhyn-Lowe, S. Flynn, S. Lomas, P. Chambon and S. P. Rannard, *Polym. Chem.*, 2023, 14, 1905–1914.
- 12 E. Takács and L. Wojnárovits, *Radiat. Phys. Chem.*, 1995, **46**, 1007–1010.
- 13 T. Pirman, M. Ocepek and B. Likozar, *Ind. Eng. Chem. Res.*, 2021, **60**, 9347–9367.
- 14 N. Ballard and J. M. Asua, Prog. Polym. Sci., 2018, 79, 40-60.
- 15 C. Corsaro, G. Neri, A. Santoro and E. Fazio, *Materials*, 2022, 15, 282.
- 16 D. P. Nair, M. Podgórski, S. Chatani, T. Gong, W. Xi, C. R. Fenoli and C. N. Bowman, *Chem. Mater.*, 2014, 26, 724–744.
- 17 A. B. Lowe, Polym. Chem., 2010, 1, 17-36.
- 18 S. Flynn, O. B. Penrhyn-Lowe, S. McKeating, S. Wright, S. Lomas, S. R. Cassin, P. Chambon and S. P. Rannard, *RSC Adv.*, 2022, **12**, 31424–31431.
- 19 M. Destarac, B. Pees and B. Boutevin, *Macromol. Chem. Phys.*, 2000, **201**, 1189–1199.
- 20 P. J. Flory, J. Am. Chem. Soc., 1941, 63, 3083-3090.
- 21 W. H. Stockmayer, J. Chem. Phys., 1944, 12, 125-131.
- 22 C. Walling, J. Am. Chem. Soc., 1945, 67, 441-447.
- 23 J. Lyu, Y. Gao, Z. Zhang, U. Greiser, H. Tai and W. Wang, *Sci. China: Chem.*, 2018, **61**, 319–327.
- 24 T. Junkers and C. Barner-Kowollik, J. Polym. Sci., Part A: Polym. Chem., 2008, 46, 7585–7605.