View Article Online

Journal of Materials Chemistry A

Materials for energy and sustainability

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: D. J. Donnelly III, M. Y. Yang, N. Dimakis, S. S. Jang, W. A. Goddard III and E. S. Smotkin, *J. Mater. Chem. A*, 2025, DOI: 10.1039/D5TA03973H.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the Information for Authors.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.



rsc.li/materials-a

7

Normer Musices Autique Rublishted on (3.1 June 2025-Downloaded on 6/6/2025 428:49 PM -Provident of the second of the second se

- 1 Journal: Energy and Environmental Science
- 2 **Title**: Atomistic Characterization of Hydration-Dependent Fuel Cell Ionomer Nanostructure: Validation by
- 3 Vibrational Spectroscopy

Dan J. Donnelly III^{1†}, Moon Young Yang^{2†}, Nicholas Dimakis^{3*}, Seung Soon Jang⁴, William A. Goddard III^{2*}, Eugene S.
 Smotkin^{1,5*}

¹Department of Chemistry and Chemical Biology, Northeastern University, Boston, MA 02115
 ²Materials and Process Simulation Center, California Institute of Technology, Pasadena, CA 91125
 ³Department of Physics and Astronomy, University of Texas Rio Grande Valley, Edinburg, TX 78539
 ⁴School of Materials Science and Engineering, Georgia Institute of Technology, Atlanta, GA 30332
 ⁵Department of Chemical Engineering Affiliate, Northeastern University, Boston, MA 02115

[†]Co-first authors | *Corresponding authors

*Eugene Smotkin: e.smotkin@northeastern.edu |*Nicholas Dimakis: nicholas.dimakis@utrgv.edu *William A. Goddard III: wag@caltech.edu

<u>Abstract</u>

The development of Nafion alternatives for fuel cells and electrolyzers requires a fundamental understanding of hydrationdependent ion-exchange site acid/base chemistry. We present here reactive force field (ReaxFF) molecular dynamics (MD) simulations of Nafion at varying molar water/ion-exchange-site ratios (λ), which we correlate to our experimental and density functional theory-based vibrational spectra. ReaxFF describes the formation and breaking of covalent bonds, enabling simulations of proton exchange between sulfonic acid/sulfonate groups and water/hydronium. Our MD simulations determine the λ -dependent equilibrium proportions of protonated and deprotonated sites. We find that protonated sites persist across all λ from 0 to 20, challenging the widely accepted notion that all sites are ionized above a threshold λ value (e.g., 3 or 4). Our simulations generate hundreds of realistic exchange site environments, the characterization of which are based on 6 Å radii sulfur-centered 'inner-spheres'. These inner- and outer-sphere regions elucidate an interplay of stereoelectronic factors that influence protonation states, including the number of inner-sphere waters (Λ). Our simulations produce broad λ -dependent distributions of Λ values, representing non-uniform exchange site hydration. Moreover, we demonstrate that these distributions are specific to both protonated and deprotonated sites, with significant overlap between the two distributions for all non-zero λ . These distributions underpin the IR spectra of hydrated membranes, with each exchange site contributing an IR spectrum characteristic of its protonation state and Λ . We expect that these nanostructural characterizations of Nafion exchange sites will contribute to the development of new ionomers.

1. Introduction 1

2

3

4

5

6

7

8

33

34

35 36

37

38 39

40 41

42

Clean hydrogen technologies underpin long-term strategies established by the Paris Agreement.^{1,2} Efficacious use of clean hydrogen relies on infrastructure spanning production, storage, delivery, and consumption of the fuel which generates electricity and clean water as byproducts. The primary and terminal stages are accomplished by electrolyzers and fuel cells, respectively. Polymer electrolyte membrane (PEM) electrolyzers and fuel cells are low-temperature (~80 °C) devices with over half a century of development.³⁻⁶ PEMs are solid-state ionomer membranes that also serve as separators of anode and cathode reactant streams, enabling compact system integration for rapid response to load demand changes.^{6–8}

Nation is a benchmark perfluorinated sulfonic acid (PFSA) ionomer with superior chemical-mechanical stability and high Open AccessAnticle, Dublished 10003 June 2003. Downloaded on 6/6/2025 4:28:44 PM. 1 protonic conductivity (Fig. 1).⁹⁻¹¹ PFSAs feature polytetrafluoroethylene (PTFE) backbones with randomly grafted perfluoroether sidechains, each terminated by a superacidic sulfonic acid group (i.e., the proton exchange site). The PTFE backbone provides structural integrity and resistance to thermochemical degradation, while the exchange sites promote the sorption^{12–16} and retention of water required for proton transport via diffusion (vehicular) and Grotthuss (hopping or shuttling) mechanisms.^{17–21} The contrasting backbone and exchange site polarities give rise to a dynamic multiphase morphology driven by an interplay of electrostatic (hydration of ionic sites) and mechanical (deformation of backbone) force minimizations.^{10,14,22} Hydration dependent forces balance the distribution of hydrophobic (semicrystalline), hydrophilic (interphasial), and water-rich domains.^{9,10,23-25} Despite decades of investigation, a consensus on hydrationdependent size, shape, and interconnectivity of domains remains elusive. 15,22,26,27

Exceptional details of hydration-dependent exchange site environments have been derived from analyses of IR and confocal Raman spectra, correlated to density functional theory (DFT) calculated normal modes and molecular dynamics (MD) simulations (Fig. 2a-b).^{8,28-35} Eigenvector normal mode animations^{36,37} guide vibrational group mode assignments, involving major contributions by multiple functional groups with intimately (mechanically) coupled^{38–40} internal coordinates.^{8,28–35} For example, the PFSA fingerprint region hosts a set of group modes that are primarily attributed to the mechanically coupled exchange site and its nearest ether link (Table 1).^{8,28–35,37,40–46} These group modes are specific to either the proton associated (i.e., α) or proton dissociated (β) exchange site states (Fig. 2c). All sites are protonated (i.e., α -sites) in exhaustively dehydrated^a PFSAs (blue spectra) and contribute to high and low frequency α -bands (i.e., α_{HF} and α_{LF}). respectively). Nearly all sites are deprotonated (i.e., β) in the fully hydrated state (red spectra) and contribute to high and low frequency β -bands (i.e., β_{HF} and β_{LF} , respectively). At partial hydration states (purple spectra), in situ, ^{8,29,35,47–50} ex situ,^{29,30,35,51,52} and operando³¹ hydration-dependent spectra show the coexistence of both α - and β -bands. A video of the simultaneous evolution of α -bands and the disappearance of β -bands during Nafion dehydration (e.g., Nafion column of Fig. 2b) is available (ESI Video). Doubly protonated exchange sites $^{19,53-55}$ (i.e., -SO₃H₂⁺) are assumed not to be statistically significant (3.2.2) and are therefore not considered in this work.

PFSA hydration is often specified by the *overall* water/SO₃(H) ratio, λ .⁵⁶ Exchange site specific *local* water content, Λ .^b specifies the number of waters within a designated radial boundary ('inner-sphere') of individual exchange sites.^{8,33} Ab initio studies show that exchange site protonation states are A-dependent.^{8,29,30,33,35,47,53,57-67} For example, DFT geometryoptimizations show that isolated RSO₃H molecule dissociation requires at least three waters of solvation (i.e., $\Lambda_d = 3$).^{47,53,60-} ^{63,66,67} In contrast, classical MD (CMD) simulations require *a priori* designation of protonation states, as their empirical force fields do not accommodate dynamic proton transfer reactions.^{64,65} Accordingly, Nafion is typically modeled with a minimum λ value of 3.^{68–84} with the assumption that *all* exchange sites are β for $\lambda \geq 3.^{68-78,80-88}$ This approach implies a uniform Λ distribution, contrary to an evolving number of works suggesting non-uniform water content^{8,40,64,79,89–91} and our recent CMD study^c showing a wide Λ distribution for all simulated non-zero λ cells.⁸ This approach also presupposes that DFT-optimized Λ environments are sufficiently realistic and applicable to MD-modeled exchange site environments. This paper addresses the validity of this presumption.

43 Sengupta and Lyulin demonstrated the profound morphological impact of *a priori* designated protonation levels (i.e., asite/β-site ratios) in Nafion CMD simulations.⁷⁹ Their work stimulated us to perform reactive force field (ReaxFF)-based 44 MD simulations, which explicitly accommodates modeling of proton dissociation and association processes without 45 46 requiring *a priori* knowledge of protonation levels.⁹² ReaxFF offers a unique balance between accuracy and computational

^a Total dehydration of ionomers requires a rigorous drying procedure as described by Doan et al.²⁹

^b The symbol, Λ , is read as 'lambda local'. The symbol replaces λ_{site}^{33} and λ_{local}^{8} , both introduced by Loupe et al.

^c All exchange sites were *a priori* designated β and all $\Lambda \leq \Lambda_d$ sites were assumed to represent α -sites.

9ġ

OpenAccessArticle: Publishedon 08June 2025. Downloaded on 646/2025 4:28:49 PM. D This Strictle Is licensed under a Creative Common's Attribution 3:0 Unported Licen

2

25

30 31

32

33

34

expense,⁹³ enabling simulations of systems with up to a million atoms for much larger length and time scales than those 1 modeled with empirical valence bond^{20,94–98} and *ab initio* MD simulations.^{21,42,99,100} 2

3 In section 3.1, DFT-calculated normal modes of Nafion repeat units are correlated to acquired spectra by visualization of

eigenvector animations. In section 3.2, ReaxFF MD simulations of Nafion cells at λ values ranging from 0 to 20 are 4

5 presented. Each hydrated simulation produces equilibrium proportions of α - and β -sites. In section 3.2.3, stereoelectronic 6 factors that affect exchange site protonation states are discussed. To our knowledge, this is the first report of ReaxFF

modeling of proton exchange between ion-exchange sites and water within an ionomer membrane. 7

The following premises (further developed in the supplementary information) underpin the approach adopted in this work. Given that, let Λ_{α} and Λ_{β} represents the number of inner-sphere water molecules for protonated (α) and deprotonated (β) sites, respectively:

- **Premise I** For any overall ionomer water content λ , there are characteristic Λ_{α} and Λ_{β} distributions. The total frequency of each distribution (i.e., the sum of all Λ_{α} and Λ_{β} number frequencies) is λ -dependent.
 - Premise II The fingerprint region of any membrane spectrum can be interpreted as the convolution of either:
 - **a.** the site-spectrum of every exchange site environment (characterized as Λ_{α} or Λ_{β}).
 - **b.** two subspectra¹⁰¹: an α -subspectrum (convolution of all Λ_{α} site-spectra) and a β -subspectrum (convolution of all Λ_{β} site-spectra).
 - **Premise III** The IR spectrum of an ionomer membrane is characteristic of its overall water content λ .

The **Figure 2b** spectra exemplifies the premises: Any dry membrane spectrum (blue) has no β -subspectrum component; any fully hydrated membrane spectrum (red) has a negligible α -subspectrum component; any partially hydrated spectrum (purple) is a convolution of an α -subspectrum and β -subspectrum.

2. Methods

2.1 DFT Calculations

Unrestricted hybrid DFT (PBE0-D3/LACV3P**++) was used for all quantum mechanics (QM) calculations including geometry-optimization and IR vibrational normal mode analyses (i.e., frequency analysis). Calculations were performed in Jaguar (v. 12.1, ©Schrödinger, LLC, New York, NY, 2024) and executed on a high-performance computing cluster (Discovery cluster, Holyoke, MA) accessed through Northeastern University. The D3 semi-empirical correction¹⁰² was paired with the PBE0 hybrid functional¹⁰³⁻¹⁰⁵ to account for long-range van der Waals attraction interactions. Polarization (i.e., "**")¹⁰⁶ and diffuse (i.e., "++")¹⁰⁷ functions were added to the triple-ζ Gaussian-type basis set LACV3P.^d

Three Nafion 'component models' (perfluorinated dimethyl ether, triflic acid, and triflate) and three Nafion monomer models (1-mer-sbb, 1-mer-CH₃, and 1-mer-CF₃) were the model compounds¹⁰¹ considered (Fig. S1-1; ESI). The component models represent minimal ionomer fragments, making them useful for elucidating individual functional group contributions to ionomer vibrational normal modes (ESI-S1).⁸ All models were optimized without an external dielectric medium or implicit solvent.^{30,35} QM calculations were performed on incrementally hydrated 1-mer-CF₃ as previously reported for triflic acid.8,30,35

35 **2.2 MD Simulations**

36 2.2.1 System Setup and Equilibration

Nafion membranes were modeled using 32 10-mer chains (i.e., 320 total exchange sites per system) at nine hydration levels: 37

38 $\lambda = 0, 1, 2, 3, 5, 7, 10, 15, 20$ (Fig. 3). Each monomer has 14 -CF₂- units followed by a single sidechain and an additional 39 CF₂ unit. Oligomer backbones are capped with fluorine atoms. All exchange sites are protonated (and remain so) during the

40 non-reactive equilibration stage. The above results involve 692 atoms per oligomer and 22144 Nafion atoms per cell. The

total number of atoms per cell varies from 22144 ($\lambda = 0$) to 41344 ($\lambda = 20$). Initial cell structures were generated using 41 Packmol.¹⁰⁸

^d LACV3P is identical to 6-311G for atoms lighter than K.

All cells were first relaxed by steepest-descent energy minimization, followed by a 10 ps NVT^{17,109} simulation at 10 K to

generate initial velocities. All cell densities were then set to an initial 1.8 g/cm³ (N117 at $\lambda = 15$ is ~1.75 g/cm³)¹⁶ before

undergoing the following 1.6 ns annealing procedure: **1a**) heating from 10 K to 400 K over 150 ps; **1b**) 100 ps equilibration at 400 K; **2a**) cooling to 300 K over 50 ps; **2b**) 100 ps equilibration; **2c**) heating to 400 K over 50 ps; **2d**) 100 ps equilibration;

2e) three repetitions of steps **2a-2d**; **3a**) cooling to 300 K over 50 ps; **3b**) 100 ps equilibration. The cells were then

equilibrated for another 10 ns at 300 K.

The universal force field¹¹⁰ was employed for the non-reactive simulations using LAMMPS.^{111,112} The equations of motion were integrated using the Verlet algorithm¹¹³ (1.0 fs time step). Electrostatic interactions were calculated with the particle-particle particle-mesh method.¹¹⁴

2.2.2 ReaxFF MD Simulations

1

2

3

4

5

6

7

8 9....

Auticle-Published on 03-June-2025. Downloaded on 6/6/2025 4:28:49 PM. If This article is licensed under a Creative Commons Attribution 3:0 Unported Licen-

Open(Access

24 25

26 27

28

ReaxFF, developed by Goddard and co-workers, describes bond formation and breaking in terms of a bond energy and bond order versus distance relation, which allows bond order changes within MD simulations.⁹² ReaxFF partitions the total system energy (E_{system}) into bonded and nonbonded terms (**Eq. 1**).

$$E_{\text{system}} = E_{\text{bonded}} + E_{\text{nonbonded}} \tag{1}$$

Bonded terms include bond, over-coordination penalty (over), under-coordination stability (under), lone-pair (lp), valence angle (val), and torsion (tor) energies. Nonbonded terms include Coulombic (Coul), van der Waals (vdW), and hydrogen bond (HB) energies (**Eq. 2**).

$$E_{\text{system}} = (E_{\text{bond}} + E_{\text{over}} + E_{\text{under}} + E_{\text{lp}} + E_{\text{val}} + E_{\text{tor}}) + (E_{\text{Coul}} + E_{\text{vdW}} + E_{\text{HB}})$$
(2)

ReaxFF determines bonded interactions among all atoms in the system using the bond order (BO) concept, where BOs are expressed as a continuous function of interatomic distance. Contributions from σ , π , and $\pi\pi$ bonds are calculated as follows:

$$BO_{ij} = BO_{ij}^{\sigma} + BO_{ij}^{\pi} + BO_{ij}^{\pi\pi} = \exp\left[p_{bo1}\left(\frac{r_{ij}}{r_0^{\sigma}}\right)^{p_{bo2}}\right] + \exp\left[p_{bo3}\left(\frac{r_{ij}}{r_0^{\pi}}\right)^{p_{bo4}}\right] + \exp\left[p_{bo5}\left(\frac{r_{ij}}{r_0^{\pi\pi}}\right)^{p_{bo6}}\right]$$
(3)

where BO_{ij}^{σ} , BO_{ij}^{π} , and $BO_{ij}^{\pi\pi}$ are the partial contributions of σ , π , and $\pi\pi$ bonds, respectively, between atoms *i* and *j* (r_{ij} is the distance between *i* and *j*). The σ , π , and $\pi\pi$ bond radii are r_0^{σ} , r_0^{π} , and $r_0^{\pi\pi}$, respectively. The p_{bo} terms are empirical parameters fitted against reference QM results (or sometimes experimental data). The nonbonded terms (i.e., Coul, vdW, and HB) are calculated between every pair of atoms regardless of their connectivity. The QEq charge equilibration method¹¹⁵ was used for electrostatic interactions. A more comprehensive review of ReaxFF is described elsewhere.⁹³

If all charges are allowed to respond to the forces and electric fields, the proper dielectric constant is 1. Accordingly, our DFT calculations of model compounds employ a dielectric constant of 1 (2.1). Typical force fields use fixed point charges and hence, should have a non-unit dielectric constant, but the correct value is generally unknown. UFF and ReaxFF allow charges to fluctuate according to the QEq charge equilibration model. Thus, the proper dielectric constant is 1, just as for QM. Applying macroscopic dielectric constants to atomistically modeled environments is not justified.

In this study, ReaxFF was trained to capture the correct qualitative trends in reactivity and proton dynamics in hydrated polymeric systems, based on QM data for triflic acid in the presence of one to five explicit water molecules. ReaxFFminimized structures show that proton transfer occurs when three or more water molecules are present, in good agreement with QM results (**Fig. S2-1**; **ESI**).^{47,53,60–63,66,67}

ReaxFF MD (RMD) simulations were conducted on all classically equilibrated cells (2.2.1) to simulate proton exchange between Nafion and water. The cells were relaxed by steepest-descent energy minimization, followed by a 10 ps NVT simulation at 10 K. The cells were then heated to 300 K over 50 ps. ReaxFF simulations were conducted for 2 ns under NPT¹⁷ conditions (300 K and 1 atm), during which the cell densities were monitored (Fig. S2-2; ESI).

37 RMD simulations were performed using LAMMPS (0.5 fs time step). RMD structure files corresponding to snapshots at 2

38 ns are available (ESI PDB Files). Molecular surfaces were generated in Maestro (version 13.3, ©Schrödinger, LLC, New

39 York, NY, 2023). Closed Connolly surfaces with a 1.4 Å probe radius were applied to various atom groupings.

NopenAccess Auticle.

3

3

32

3. Results and Discussion 1

3.1 DFT Calculated Nafion Monomer Vibrational Normal Modes

3 We have reported extensive frequency analyses (at the X3LYP/6-311G**++ level) of dry (i.e., $\Lambda = 0$) RSO₃(H) models (e.g., 1-mer-CH₃; Fig. 4a).^{8,29-31,33-35} These include group mode assignments (Table 1) correlated to hydration-dependent 4 5 PFSA vibrational bands (Fig. 2a,b). Assignments are based on the visualization of eigenvector normal mode animations 6 (ESI Videos).^{8,30,36,37,40} Excellent agreement was found between X3LYP 1-mer-CH₃ frequencies and corresponding IR^e 7 band frequencies (Fig. 4b). The calculated frequencies are within ~1% of experimental values, except for α_{LF} , which is 14% 8 lower than the observed 910 cm⁻¹ band. Frequency errors are often attributed to scaling factors (varies with functional and Rublished on U3 June 2025. Dewnloaded on 6(20254:28:49 PM-Ens Reensed under a Creditive Commons Attribution 3:00 mported Licence. basis set) and the choice of chemical repeat unit.28,35,101

Yamaguchi and Ohira evaluated several hybrid functional and basis set combinations for PFSA sidechain models, finding that PBE0/6-311G(d) offers the best balance of accuracy and computational time.³⁷ Thus, we performed frequency analyses with the PBE0-D3 hybrid functional,¹⁰³⁻¹⁰⁵ which accounts for long-range interactions,¹⁰² and the same basis set as previously reported^{8,29–31,33–35} (2.1). The 1-mer-CH₃ α_{LF} value improves by ~6% and the β_{LF} value improves slightly with PBE0-D3 (Fig. 4b). All other listed modes increase in error. The insensitivity of the Nafion side chain (NSC)^f band to stateof-hydration^{8,30,35} (band stays fixed at 983 cm⁻¹) is better captured with PBE0-D3. Yet, the X3LYP NSC values are much closer to the observed band. Thus, for 1-mer-CH₃, neither functional clearly outperforms the other, deeming both suitable for frequency analyses.

Historically, the 1-mer-CH₃ model was used to avoid "computational interference" with the sidechain -CF₃ group.^{8,29,33-35} Replacing methyl groups with -CF₃ groups (1-mer-CF₃; Fig. 4a), however, has a negligible effect on the PBE0-D3 frequencies (Fig. 4b). Notably, the NSC group modes (dominated by sidechain -CF₃ and COC-B motions) are unaffected by the backbone capping groups, as their large separation from the COC-B group prevents significant coupling of their motions.

The exceptional accuracy of the X3LYP-calculated dry 1-mer-CH₃ β_{HF} frequency (1059 cm⁻¹; Fig. 4b) is fortuitous given that β -sites are formed and stabilized in the presence of water.^{47,53} In comparison, the PBE0-D3 β_{HF} frequency for all monomer models are 26 cm⁻¹ less than the observed 1058 cm⁻¹ band. Hydration of the 1-mer-CF₃ β -site greatly reduces the PBE0-D3 β_{HF} frequency error (**Table S1-2**): β_{HF} increases to 1049 cm⁻¹ at Λ_d (i.e., $\Lambda = 3$); β_{HF} is 1052 ± 1.5 cm⁻¹ between Λ = 3 and Λ = 15. As Λ increases, the local permittivity around the β -site should approach that of hydrated membrane β sites,^{10,116} allowing for a more realistic β_{HF} group mode calculation.

DFT-calculated exchange site environments are typically derived from a limited landscape of energy-minimized structures,⁵⁷ lacking both the structural complexity and site-to-site variation inherent in real ionomer repeat units.¹⁰¹ Thousands of realistic exchange site environments are accessed with a lower level of theory like MD, as discussed below (3.2).

33 QM-calculated IR spectra of all model compounds (ESI-S1) and normal mode animations for component models and 1-34 mer-CF₃ are available (ESI Videos).

35 **3.2 Nafion ReaxFF MD Simulations**

RMD simulations of nine Nafion cells were performed at λ values ranging from 0 to 20. Trajectories of protonation levels 36 37 versus time established a standard simulation duration of 2 ns (Fig. S2-3; ESI). In this section, 'water' includes all water molecules whether they are neutral or are part of a protonated hydration complex (i.e., hydronium, Zundel, Eigen, etc.) 21,73 , 38 unless otherwise specified. A standard sulfur-centered radial cutoff distance (b) of 6 $Å^g$ defines an 'inner-sphere' and 'outer-39 sphere' boundary in this work. The integer number of inner-sphere waters is A. Each DFT and RMD-generated exchange 40

^e Transmission FTIR of Nafion 212 (NR212; See Fig. 1 for membrane specifications).

^f NSC group modes are dominated by $\delta_{u}(CF_{3})$ (see **ESI videos**).

^g The arbitrarily chosen 6 Å cutoff boundary contains all 1-mer-CF₃ hydration waters (Fig. S1-6; ESI).

Page 6 of 32

- 1 site environment will be referred to by its protonation state (i.e., α or β) and a numerical subscript representing the site's Λ
- 2 value (e.g., β_{14} denotes an ionized exchange site with 14 inner-sphere waters).

3 3.2.1 Inner-Sphere and Outer-Sphere Waters

4 For real and theoretical ionomer samples, W_{tot} is the total number of waters (Eq. 4):

$$W_{tot} = \lambda N_A \frac{m_{dry}}{EW} = \lambda N_S$$
(4)

where N_A is Avogadro's number, m_{dry} is the dry mass, and N_s is the total number of sulfur atoms. For both the RMD simulations and our previous all-classical simulations, N_s is 320.⁸ Every exchange site has an integer Λ value representing inner-sphere water oxygens. Waters contributing to multiple Λ (i.e., multiple sulfur-spheres) are "bridge"⁸⁴ waters. Waters that contribute to single sulfur-spheres are "non-bridge" waters. The sum of all inner-sphere waters (W_{IS}) and all outer-sphere waters (W_{OS}) is W_{tot} (Eq. 5).

$$W_{tot} = W_{IS} + W_{OS}$$
(5)

Figure 5a shows histograms of Λ number frequencies (f_{Λ}) versus Λ for the nine simulated cells, where f_{Λ} values range from 0 to N_s. Thus, the range of f_{Λ} values can formally be defined by the set, $\{f_{\Lambda} \in \mathbb{N}_0 | f_{\Lambda} \le \mathbb{N}_s\}$. The histogram color coding is discussed later (3.2.2). The sum of the f_{Λ} by Λ products is the MD cell's histogram number, n_{hist} (Eq. 6).

$$n_{\rm hist} = \sum_{\Lambda=0}^{p} f_{\Lambda} \Lambda \tag{6}$$

Open-Access Article. Published on 0.3 June 2025. Downloaded on 6/6/2025 4:28:49 PM.

The upper limit *p* is the maximum Λ value recorded for a Λ distribution, which depends on *b* and λ (e.g., *p* is 19 for $\lambda = 20$; **Fig. 5a**). The domain of Λ is formally, { $\Lambda \in \mathbb{N}_0 | \Lambda \le p$ }. If there are no bridge waters, n_{hist} equals W_{IS} . The presence of bridge waters breaks the equality and thus contributes towards a net overcount (n_{over}) of W_{IS} (**Eq. 7**).

$$W_{\rm IS} = n_{\rm hist} - n_{\rm over} \tag{7}$$

Bridge-waters within *j* inner-spheres are overcounted *j*-1 time(s), where *j* is 2 or larger. The domain of *j* is formally, $\{j \in \mathbb{N} \mid j \ge 2\}$. The number of bridge waters occupying *j* spheres is f_j . The sum of f_j by *j*-1 products is n_{over} (**Eq. 8**).

$$n_{\text{over}} = \sum_{j=2}^{q} f_j (j-1) \tag{8}$$

18 The upper limit q is the maximum number of inner-spheres that a water resides in, which, similar to p, depends on b and λ 19 (q is either 4 and 5 across the nine λ systems, **Table S2-1**; **ESI**). A more descriptive W_{IS} definition is now obtained by 20 substitution of **equations 6** and **8** into **equation 7** (**Eq. 9**).

$$W_{IS} = \sum_{\Lambda=0}^{p} f_{\Lambda} \Lambda - \sum_{j=2}^{q} f_{j} \left(j - 1 \right)$$
(9)

21 A full expression for W_{tot} is established by substitution of equation 9 into equation 5 (Eq. 10).

$$W_{tot} = \sum_{\Lambda=0}^{p} f_{\Lambda} \Lambda - \sum_{j=2}^{q} f_{j} (j-1) + W_{OS}$$
(10)

22 The water-count discrepancy (δ) represents the amount by which n_{hist} is an overcount ($\delta > 0$) or undercount ($\delta < 0$) of W_{tot}, 23 relative to W_{tot} (**Eq. 11**).

$$\delta = \frac{n_{\text{hist}} - W_{\text{tot}}}{W_{\text{tot}}} \times 100\% \tag{11}$$

2:

26

27 28

- Alternatively, δ may be recast in terms of n_{over} and W_{OS} (total number of over- and under-counts, respectively) by substitution 1
- 2 of equations 5 and 7 into equation 11 (Eq. 12).

$$\delta = \frac{n_{\text{over}} - W_{\text{OS}}}{W_{\text{tot}}} \times 100\%$$
(12)

Equations 4-12 are summarized as a two-dimensional conceptual illustration (Fig. S2-4; ESI). 3

Figure 5b shows δ versus λ for the simulations of the eight hydrated systems. There are two linear segments with slopes of C Open Micross Article-Published-on 03 June 2025. Downloaded on-6/6/2025 4:28:49 PM. This article is ficensed under a Creative Commons Attribution 3:0 Unported Licence. -0.08 (between $\lambda = 1$ and $\lambda = 7$) and -0.02 (between $\lambda = 7$ and $\lambda = 20$) that intersect at λ_7 . The steeper segment results from a reduction of overlapping sulfur-spheres (i.e., n_{over} decreases), concurrent with the emergence of a water-rich phase (i.e., W_{OS} increases). For very low λ , waters are predominantly inner-sphere¹⁰ and bridge exchange sites. Figure 6 depicts bridge waters as light blue spheroids bridging yellow trefoils (exchange sites). Protonated bridge waters, or "hydronium-mediated bridges", have been reported in CMD simulations of Nafion, Aquivion, and a perfluorinated phosphoric acid by Jang and coworkers.^{69,83} The $\lambda = 0$ and $\lambda = 2$ cell cross-sectional surfaces both show a greater extent of clustered exchange sites than that of $\lambda = 20$, consistent with reports of stronger S-S pairwise correlations with decreasing λ .^{69,71,76-78,83,84,87} At $\lambda = 5$, while n_{over} is counterbalanced by W_{OS}, there remain bridge waters that impact the slope up until the intersection at $\lambda = 7$. The shallower slope is attributed almost exclusively to the progressive increase of outer sphere waters (i.e., W_{OS} increases while n_{over} is negligible). Outer-sphere waters (green) are either clustered or isolated (**Fig. 6**). The hydration-dependent growth of a three-phase nanomorphology is illustrated in Fig. S2-5 (ESI).

3.2.2 Λ_{α} and Λ_{β} Distributions

The $\lambda = 0$ cell (i.e., $W_{tot} = 0$) has 320 locally dry exchange sites (i.e., $f_0 = 320$), corresponding to the single $\Lambda = 0$ bar in Figure 5a. All sites remained protonated throughout the simulation period (Fig. S2-3; ESI), consistent with no autoprotolysis products (i.e., $-SO_3H_2^+$ and $-SO_3^-$).^{19,53-55} A solvent autoprotolysis constant (K_{ap}), depends on the solvent equivalent weight, density, and dielectric constant (κ).¹¹⁷ Although K_{ap} for Nafion is not reported, it is likely negligible because of its low κ ($\kappa \approx 4$ for $\lambda = 1$)¹¹⁶, high equivalent weight, and low anhydrous ionic conductivity.^{118,119} Even for sulfuric acid, which has a high κ ($\kappa \approx 100$; $K_{ap} = 2.4*10^{-4}$ at 25 °C)^{120,121} and low equivalent weight, only three H₃O₄⁺ ions are expected at equilibrium in a $\lambda = 0$ cell volume (ESI-S3). In a transmission FTIR study of 'dry' Nafion, Buzzoni et al. attributed a weak intensity 1060 cm⁻¹ band ($\beta_{\rm HF}$) to -SO₃⁻ groups formed via autoprotolysis.¹²² This is unlikely given the above discussion of sulfuric acid. In an ATR-FTIR study of 'dry' Nafion by Negro et al., the 1060 cm⁻¹ band is attributed to $-SO_3^-$ groups persisting due to residual membrane water.¹²³ Whatever the acquisition technique, complete absence of the 1060 cm⁻¹ band requires maintenance of a completely dry atmosphere during measurement.²⁹ Loupe et al. describes in detail the challenges of obtaining completely dry PFSA spectra in an ATR configuration.⁸

29 All non-zero λ cells result in α -site and β -site Λ distributions, visualized as blue and red histograms, respectively (Fig. 5a). Each histogram is represented as a numerical set, with each element corresponding to a single bar. For example, each blue 30 31 histogram is represented by the set H_{α} (Eq. 13).

$$\mathbf{H}_{\alpha} = \left\{ f_{\Lambda_{\alpha}} \in \mathbb{N} | \Lambda \in \mathbb{N}_0 \right\}$$
(13)

Each H_{α} element corresponds to a blue bar, representing non-zero frequencies of α -sites with specific Λ values ($f_{\Lambda_{\alpha}}$). The 32 number of $f_{\Lambda_{\alpha}}$ elements (i.e., number of blue bars) is the cardinality of H_{α} , $|H_{\alpha}|$ (**Table 2**). The sum of $f_{\Lambda_{\alpha}}$ over all Λ 33 34 represents the total number of α -sites in the cell (N_{S_{\alpha}; Eq. 14).}

$$N_{S_{\alpha}} = \sum_{\Lambda=0}^{p} f_{\Lambda_{\alpha}}$$
(14)

35 Similarly, each red histogram is represented as the set, H_{β} (Eq. 15).

$$\mathbf{H}_{\beta} = \left\{ f_{\Lambda_{\beta}} \in \mathbb{N} | \Lambda \in \mathbb{N}_0 \right\}$$
(15)

Each H_{β} element corresponds to a red bar, representing non-zero frequencies of β -sites with specific Λ values ($f_{\Lambda_{\beta}}$). The number of $f_{\Lambda_{\beta}}$ elements is the cardinality of H_{β}, |H_{β}| (**Table 2**). The sum of $f_{\Lambda_{\beta}}$ over all Λ is the total number of β -sites for the cell (N_{S_{$\beta}}, Eq. 16).</sub></sub>$

$$N_{S_{\beta}} = \sum_{\Lambda=0}^{p} f_{\Lambda_{\beta}}$$
(16)

The sum of $N_{S_{\alpha}}$ and $N_{S_{\beta}}$ is N_{S} (Eq. 17, 18).

1

2 3

Article. Published on 03 June 2025. Downloaded on 6/6/2025 4:28:49 PM. This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Open Acces

16

17

18

$$N_{\rm S} = N_{\rm S_{\alpha}} + N_{\rm S_{\beta}} = \sum_{\Lambda=0}^{p} (f_{\Lambda_{\alpha}} + f_{\Lambda_{\beta}})$$
(17)

The sum of corresponding $f_{\Lambda_{\alpha}}$ and $f_{\Lambda_{\beta}}$ values is f_{Λ} , which represents the number of exchange sites with a given Λ , independent of protonation state. The rightmost expression of equation 17 is then simplified to represent the sum of every **Fig. 5a** histogram bar, independent of its color (**Eq. 18**).

$$N_{\rm S} = \sum_{\Lambda=0}^{P} f_{\Lambda} \tag{18}$$

Figure 7 shows $N_{S_{\alpha}}$ versus λ . According to equation 14, the value of each bar is the sum of all blue histogram bars from Figure 5a, for the corresponding λ . Thus, the exponential decay of $N_{S_{\alpha}}$ versus λ represents the diminishing significance of blue histograms with λ , and a sharp decrease in the proportion of α -sites with increasing water content. The persistence of α -sites across all λ contradicts the widely adopted notion that all exchange sites are ionized for $\lambda \geq 3.^{68-78,80-87}$ Our finding concurs with Sengupta and Lyulin's report of α -sites at high λ .⁷⁹

All eight hydrated cells result in overlapping histograms across variable Λ intervals (**Fig. 5a**). For λ_1 , both H_{\alpha} and H_{\beta} span Λ values from 0 to 5 (i.e., $|H_{\alpha}| = |H_{\beta}| = 6$). With increasing λ , both histograms shift towards higher Λ , signifying a growing number of inner-sphere waters for every exchange site. Consequently, the proportion of locally dry sites (i.e., f_0/N_s) diminishes from 100% to 2% between $\lambda = 0$ and $\lambda = 3$. For $\lambda = 5$ and beyond, all exchange sites are hydrated by at least one water. It is noteworthy that the absence of $\Lambda = 0$ sites starting at $\lambda = 5$, coincides with the equality of over- and undercounted waters (i.e., $\delta \approx 0$ at $\lambda = 5$, **Fig. 5b**).

Table 2 shows that $|H_{\beta}|$ generally increases with λ , reflecting a growing variety of β -site Λ values with hydration. This is consistent with a 3-mer Aquivion model, which shows an increasing preference for non-uniform hydration as λ increases.⁸⁹ In contrast, $|H_{\alpha}|$ remains roughly the same across all non-zero λ . The number of Λ values over which H_{α} and H_{β} overlap also show little variation with λ (**Fig. 5a**). The tails of the α histograms, on the high Λ side, never overlap with the β histograms beyond $\lambda = 1$, indicating that sites with the largest Λ values in any cell are always ionized.

For any non-zero λ , the proportion of α -sites with a given Λ generally decreases with increasing Λ (i.e., $f_{\Lambda_{\alpha}}/f_{\Lambda}$; Fig. 8). In

25 the $\lambda = 3$ cell, for example, $f_{\Lambda_{\alpha}}/f_{\Lambda}$ decreases from 61% to 4% as Λ increases from 1 to 6. In every hydrated cell, $f_{\Lambda_{\alpha}}/f_{\Lambda}$ is

26 generally less than 15% if Λ is at least 6. The negative correlation between $f_{\Lambda_{\alpha}}/f_{\Lambda}$ and Λ is consistent with reports of an

- 27 increased ionization propensity for CF₃SO₃H (i.e., triflic acid) and CF₃CF₂SO₃H as Λ increases.^{47,53}
- 28 3.2.3 ReaxFF MD Exchange Site Environments

7

2025. Downloaded on 646/2025 4:28:49 PM. Creative Common's Attribution 3.0 Unported Licence.

Article Published on 03 June This article is licensed under a

NOpen Access

2

27

28 29

- Our RMD simulations model the spatial and temporal heterogeneity of 320 exchange sites per λ (3.2.1 and 3.2.2), where
- 2 each site is embedded in a realistic environment with up to ~40,000 surrounding atoms. The coexistence of α and β -sites

3 with identical Λ values in a hydrated simulation cell (Fig. 8) suggests that additional variables beyond Λ influence

4 protonation states. The interplay of three stereoelectronic variables is identified through visualization of inner- and outer-5 sphere environments (**Fig. 9**): (i) the local number density of polar and non-polar fragments, (ii) the spatial arrangement of 6 water, polymer fragments, and ions, and (iii) long-range electrostatic effects.

The ionization propensity (i.e., acidity) of exchange sites is primarily influenced by the identity and number density of inner-sphere atoms (variable i). Exchange site acidity is expected to increase with Λ (since water molecules are highly polar) and decrease with the number density of non-polar fragments within the inner-sphere (e.g., CF₂ and COC groups). The latter parameter is enumerated by the number of non-SO₃(H) Nafion atoms (N_{np}). Consider, the sixteen 1-mer-CF₃ monomer models geometry-optimized with DFT, each with a unique Λ ranging from 0 to 15 (**Fig. S1-6**; **ESI-S1**). Since the monomer N_{np} values vary minimally (**Fig. S1-7b**; **ESI**), their acidities primarily depend on Λ , leading to the establishment of a Λ dissociation threshold ($\Lambda_d = 3$): the exchange site is α for $\Lambda < 3$ and β for $\Lambda \ge 3$ (**Fig. S1-6**; **ESI**). In contrast, the RMD-modeled inner-spheres exhibit larger and more diverse N_{np} values that vary independently of Λ , precluding the establishment of a Λ_d (**Fig. 9**). The RMD inner-sphere structural diversity is facilitated by the abundant presence of polymer fragments from neighboring monomers, with minimal disruption to native³⁴ backbone dihedral angles.^{17,37,57,58,124}

The spatial arrangement of water, polymer atoms, and ions (variable ii) is also expected to influence exchange site protonation states. Consider the two arbitrarily selected α_5 and β_5 sites from the $\lambda = 5$ cell (**Fig. 9**). The α_5 site proton is partially stabilized by its nearest ether linkage, rather than by a water molecule. Moreover, the α_5 site is directly hydrated by only a single water, while the four remaining waters contribute to the stabilization of a neighboring β -site and two other protons. In contrast, the β_5 site has a much smaller N_{np}, lacks excess charge carriers, and is directly hydrated by two waters. The $\lambda = 2$ cell hosts a nearly equal number of α_2 and β_2 sites (**Fig. 8**). Despite the selected β_2 site (**Fig. 9**) having a large N_{np}, two nearby exchange sites contribute to stabilizing the dissociated proton (the proton serves as a hydronium-mediated bridge^{69,83} between three exchange sites). Similarly, Paddison and Elliot reported that the number of waters required to cause exchange site ionization is less than three when exchange sites are nearby one another.^{57,58} The inclusion of a high dielectric constant continuum solvation model has also been shown to decrease the number of waters required for ionization.⁶¹ Meanwhile, the selected α_2 site proton lacks any direct interaction with water, causing it to remain associated. These observations from arbitrarily selected exchange sites highlight how the highly variable spatial arrangement of inner-sphere

species influence proton association and dissociation.

Finally, exertion of long-range electrostatic forces (variable iii) on RMD sites should not be excluded as a variable that influences protonation states. While these forces may be individually insignificant compared to shorter-range coulombic interactions, the MD cells contain significantly more atoms contributing to these forces than the 1-mer-CF₃ complexes. The

33 overall water content (i.e., λ) is expected to have impact the long-range forces exerted on any exchange site.

34 4. Conclusion

This is the first report on ReaxFF modeling of proton exchange between water molecules and ion-exchange sites within an MD framework. MD simulations were performed on the perfluorinated sulfonic acid (PFSA) ionomer Nafion at λ values ranging from 0 to 20. Over each 2 ns simulation, proton exchange between initially protonated exchange sites (sulfonic acid

38 groups) and water molecules resulted in λ -dependent equilibrium proportions of protonated sites (α , i.e., sulfonic acid) and

- 39 deprotonated sites (β , i.e., sulfonate ion). An exponential decrease in the proportion of α -sites was observed with increasing
- 40 λ . Notably, we found that α -sites persist across all λ cells, challenging the notion that all exchange sites are ionized above a
- fixed λ threshold.^{68,70–78,80–88} Exchange sites are hydrated non-uniformly, as demonstrated by λ -dependent distributions of Λ values, representing the number of waters within sulfur-centered 'inner-spheres' with 6 Å radii.^{8,40,64,79,89–91} For lower λ cells,

ournal of Materials Chemistry A Accepted

the majority of waters reside either within a single exchange site inner-sphere ('non-bridge' waters) or multiple innerspheres ('bridge' waters). As λ increases, the proportion of bridge waters decreases, due to the separation of sulfonate groups.^{69,71,76–78,83,84,87} concurrent with the evolution of a water-rich phase composed of outer-sphere waters.

Distributions of α - and β -site Λ values (Λ_{α} and Λ_{β} distributions, respectively) with significant overlap were observed.

Examination of inner-spheres revealed the complex interplay of three stereoelectronic variables affecting protonation state:

(i) the local number density of polar and non-polar fragments, (ii) the spatial arrangement of water, polymer fragments, and ions, and (iii) long-range electrostatic effects. We assert that each exchange site environment yields a characteristic IR

spectrum (premise II),⁸ and that our Λ_{α} and Λ_{β} distributions form the basis for any observed IR spectrum (premises I, III).

Taken together, our study focuses on the intrinsic behavior of proton-exchanged Nafion, particularly the interactions between –SO₃H groups and water molecules. By modeling simplified H⁺/H₃O⁺ environments, we systematically explored hydration-dependent proton transfer dynamics, hydrogen-bond structures, and the microstructural organization driven by the acidic side chains. We acknowledge that in real PEM environments, contaminants such as alkali metal cations can influence the acid–base equilibrium and local hydration structure through ionic screening or competitive interactions. While this study aims to isolate and understand the fundamental interactions between –SO₃H groups and water molecules, we reported on the hydration-dependent spectroscopy of metal ion-exchanged Nafion (K⁺, Na⁺, Li⁺, Ca²⁺, Cd²⁺, Ni²⁺, and Al³⁺).^{29,33} Future work can correlate our spectroscopic findings with ReaxFF simulations of metal ion-exchanged Nafion to better understand the impact of external cations.

Intense efforts are focused on the development of environmentally friendly polymer electrolytes that offer high proton conductivity, low gas permeability, and improved water-retention at elevated temperatures. Our methodology is not only applicable to any ionomer, but also to any molecular system undergoing solvation-dependent chemical changes.

3

4

5

6

7

8

99ં

Open Access Article. Publishedton 03-June 2025. Dovunloaded on 6/6/2025 4:28:49-I2M. 1

1 Author Contributions

- D.J.D.: conceptualization, data curation, formal analysis, methodology, visualization, and writing original draft and editing.
 - M.Y.Y.: data curation, formal analysis, investigation, software, writing MD methods, and writing review & editing.
- N.D.: data curation, investigation, supervision, writing DFT methods, and writing review & editing.
- S.S.J.: supervision and writing review & editing.
- W.A.G.: conceptualization, project administration, resources, supervision, and writing review & editing.
- E.S.S.: conceptualization, funding acquisition, project administration, resources, supervision, writing review & editing.

Conflicts of Interest

There are no conflicts of interest to declare.

Data Availability

A collection of files supporting this article are available as part of the Supplementary Information: vibrational normal mode animations of model compounds, PDB files of RMD cells, RMD data analysis files, and supporting figures with corresponding discussion. The Supplementary Information document provides a description of each supporting file (**ESI**).

Acknowledgements

The authors acknowledge financial support from A3 Global (grant code G0007820) and Northeastern University. The ReaxFF work used Expanse at San Diego Supercomputer Center through allocation DMR160114 from the Advanced Cyberinfrastructure Coordination Ecosystem: Services & Support (ACCESS) program, which is supported by National Science Foundation grants #2137603, #2138259, #2138286, #2138296, and #2138307.

1 <u>References</u>

7

Article. Published on (3) June 2025. Downloaded on 6/6/2025.4:22:49 PM. This aftects is licensed under a Creative Commons Attribution 3.0 Unported Elecence.

SupernA poess

- 2 (1) United States Department of Energy. US National Clean Hydrogen Strategy and Roadmap; 2023.
- United States Department of State; United States Executive Office of the President. *The Long-Term Strategy of the United States: Pathways to Net-Zero Greenhouse Gas Emissions by 2050*; 2021.
- 5 (3) El-Shafie, M. Hydrogen Production by Water Electrolysis Technologies: A Review. *Results Eng.* 2023, 20
 (September), 101426. https://doi.org/10.1016/j.rineng.2023.101426.
 - Miyake, J.; Miyatake, K. Fluorine-Free Sulfonated Aromatic Polymers as Proton Exchange Membranes. *Polym. J.* 2017, 49 (6), 487–495. https://doi.org/10.1038/pj.2017.11.
 - (5) Adamski, M.; Peressin, N.; Holdcroft, S. On the Evolution of Sulfonated Polyphenylenes as Proton Exchange Membranes for Fuel Cells. *Mater. Adv.* **2021**, *2* (15), 4966–5005. https://doi.org/10.1039/D1MA00511A.
 - (6) Carmo, M.; Fritz, D. L.; Mergel, J.; Stolten, D. A Comprehensive Review on PEM Water Electrolysis. *Int. J. Hydrogen Energy* **2013**, *38* (12), 4901–4934. https://doi.org/10.1016/j.ijhydene.2013.01.151.
 - United States Department of Energy. Comparison of Fuel Cell Technologies https://www.energy.gov/eere/fuelcells/comparison-fuel-cell-technologies (accessed Mar 7, 2024).
 - (8) Loupe, N.; Abu-Hakmeh, K.; Gao, S.; Gonzalez, L.; Ingargiola, M.; Mathiowetz, K.; Cruse, R.; Doan, J.; Schide, A.; Salas, I.; Dimakis, N.; Jang, S. S.; Goddard, W. A.; Smotkin, E. S. Group Vibrational Mode Assignments as a Broadly Applicable Tool for Characterizing Ionomer Membrane Structure as a Function of Degree of Hydration. *Chem. Mater.* 2020, *32* (5), 1828–1843. https://doi.org/10.1021/acs.chemmater.9b04037.
 - (9) Mauritz, K. A.; Moore, R. B. State of Understanding of Nafion. *Chem. Rev.* **2004**, *104* (10), 4535–4586. https://doi.org/10.1021/cr0207123.
 - (10) Kusoglu, A.; Weber, A. Z. New Insights into Perfluorinated Sulfonic-Acid Ionomers. *Chem. Rev.* 2017, *117* (3), 987–1104. https://doi.org/10.1021/acs.chemrev.6b00159.
 - (11) Kreuer, K.-D. Ion Conducting Membranes for Fuel Cells and Other Electrochemical Devices. *Chem. Mater.* 2014, 26 (1), 361–380. https://doi.org/10.1021/cm402742u.
 - (12) Crothers, A. R.; Kusoglu, A.; Radke, C. J.; Weber, A. Z. Influence of Mesoscale Interactions on Proton, Water, and Electrokinetic Transport in Solvent-Filled Membranes: Theory and Simulation. *Langmuir* 2022, *38* (34), 10351–10728. https://doi.org/10.1021/acs.langmuir.2c00706.
 - (13) Soniat, M.; Houle, F. A. How the Hydrophobic Interface between a Perfluorosulfonic Acid Polymer and Water Vapor Controls Membrane Hydration. ACS Appl. Polym. Mater. 2022, 4 (5), 2960–4046. https://doi.org/10.1021/acsapm.1c01805.
- (14) Fumagalli, M.; Lyonnard, S.; Prajapati, G.; Berrod, Q.; Porcar, L.; Guillermo, A.; Gebel, G. Fast Water Diffusion
 and Long-Term Polymer Reorganization during Nafion Membrane Hydration Evidenced by Time-Resolved Small Angle Neutron Scattering. J. Phys. Chem. B 2015, 119 (23), 7068–7076. https://doi.org/10.1021/acs.jpcb.5b01220.
- (15) Hwang, G. S.; Parkinson, D. Y.; Kusoglu, A.; MacDowell, A. A.; Weber, A. Z. Understanding Water Uptake and Transport in Nafion Using X-Ray Microtomography. *ACS Macro Lett.* 2013, 2 (4), 288–291. https://doi.org/10.1021/mz300651a.
- 37 (16) Morris, D. R.; Sun, X. Water-Sorption and Transport Properties of Nafion 117 H. J. Appl. Polym. 1993, 50 (8), 1445–1452.
- (17) Elliott, J. A.; Paddison, S. J. Modelling of Morphology and Proton Transport in PFSA Membranes. *Phys. Chem. Chem. Phys.* 2007, 9 (21), 2602–2618. https://doi.org/10.1039/b701234a.
- (18) Rivera, H.; Lawton, J. S.; Budil, D. E.; Smotkin, E. S. Effect of Sorbed Methanol, Current, and Temperature on Multicomponent Transport in Nafion-Based Direct Methanol Fuel Cells. *J. Phys. Chem. B* 2008, *112* (29), 8542– 8548. https://doi.org/10.1021/jp803158h.
- 44 (19) Sagarik, K.; Phonyiem, M.; Lao-ngam, C.; Chaiwongwattana, S. Mechanisms of Proton Transfer in Nafion®:

31

- Elementary Reactions at the Sulfonic Acid Groups. Phys. Chem. Chem. Phys. 2008, 10 (15), 2098. 1 2 https://doi.org/10.1039/b718480h.
- 3 (20)Feng, S.; Voth, G. A. Proton Solvation and Transport in Hydrated Nafion. J. Phys. Chem. B 2011, 115 (19), 5903-4 5912. https://doi.org/10.1021/jp2002194.
- 5 (21)Devanathan, R.; Idupulapati, N.; Baer, M. D.; Mundy, C. J.; Dupuis, M. Ab Initio Molecular Dynamics Simulation 6 of Proton Hopping in a Model Polymer Membrane. J. Phys. Chem. B 2013, 117 (51), 16522–16529. 7 https://doi.org/10.1021/jp410229u.
- Kusoglu, A.; Savagatrup, S.; Clark, K. T.; Weber, A. Z. Role of Mechanical Factors in Controlling the Structure-(22)Function Relationship of PFSA Ionomers. *Macromolecules* **2012**, 45 (18), 7467–7476. https://doi.org/10.1021/ma301419s.
 - (23)Komarov, P. V.; Veselov, I. N.; Chu, P. P.; Khalatur, P. G. Mesoscale Simulation of Polymer Electrolyte Membranes Based on Sulfonated Poly(Ether Ether Ketone) and Nafion. Soft Matter 2010, 6 (16), 3939–3956. https://doi.org/10.1039/b921369d.
 - Laporta, M.; Pegoraro, M.; Zanderighi, L. Perfluorosulfonated Membrane (Nafion): FT-IR Study of the State of (24)Water with Increasing Humidity. Phys. Chem. Chem. Phys. 1999, 1 (19), 4619–4628. https://doi.org/10.1039/a904460d.
 - Yeager, H. L.; Steck, A. Cation and Water Diffusion in Nafion Ion Exchange Membranes: Influence of Polymer (25)Structure. J. Electrochem. Soc. 1981, 128 (9), 1880–1884. https://doi.org/10.1149/1.2127757.
 - Allen, F. I.; Comolli, L. R.; Kusoglu, A.; Modestino, M. A.; Minor, A. M.; Weber, A. Z. Morphology of Hydrated (26)As-Cast Nafion Revealed through Cryo Electron Tomography. ACS Macro Lett. 2015, 4 (1), 1–5. https://doi.org/10.1021/mz500606h.
 - Rongpipi, S.; Chan, J. M.; Bird, A.; Freychet, G.; Kusoglu, A.; Su, G. M. Revealing Mesoscale Ionomer (27)Membrane Structure by Tender Resonant X-Ray Scattering. ACS Appl. Polym. Mater. 2024, 6 (23), 14115–14123. https://doi.org/10.1021/acsapm.4c00286.
 - Doan, J.; Kingston, E.; Kendrick, I.; Anderson, K.; Dimakis, N.; Knauth, P.; Di Vona, M. L.; Smotkin, E. S. (28)Theoretical and Experimental Infrared Spectra of Hydrated and Dehydrated Sulfonated Poly(Ether Ether Ketone). Polymer (Guildf). 2014, 55 (18), 4671–4676. https://doi.org/10.1016/j.polymer.2014.07.011.
 - Doan, J.; Navarro, N. E.; Kumari, D.; Anderson, K.; Kingston, E.; Johnson, C.; Vong, A.; Dimakis, N.; Smotkin, (29)E. S. Symmetry-Based IR Group Modes as Dynamic Probes of Nation Ion Exchange Site Structure. Polymer (Guildf). 2015, 73, 34-41. https://doi.org/10.1016/j.polymer.2015.07.017.
 - (30)Webber, M.; Dimakis, N.; Kumari, D.; Fuccillo, M.; Smotkin, E. S. Mechanically Coupled Internal Coordinates of Ionomer Vibrational Modes. *Macromolecules* **2010**, *43* (13), 5500–5502. https://doi.org/10.1021/ma100915u.
- 33 (31) Kendrick, I.; Fore, J.; Doan, J.; Loupe, N.; Vong, A.; Dimakis, N.; Diem, M.; Smotkin, E. S. Operando Raman 34 Micro-Spectroscopy of Polymer Electrolyte Fuel Cells. J. Electrochem. Soc. 2016, 163 (4), H3152-H3159. https://doi.org/10.1149/2.0211604jes. 35
- 36 Anderson, K.; Kingston, E.; Romeo, J.; Doan, J.; Loupe, N.; Dimakis, N.; Smotkin, E. S. Infrared Spectroscopy of (32) Ion-Induced Cross-Linked Sulfonated Poly(Ether Ether Ketone). Polymer (Guildf). 2016, 93, 65–71. 37 38 https://doi.org/10.1016/j.polymer.2016.04.015.
- 39 (33)Loupe, N.; Nasirova, N.; Doan, J.; Valdez, D.; Furlani, M.; Dimakis, N.; Smotkin, E. S. DFT - Experimental IR 40 Spectroscopy of Lithiated Single Ion Conducting Perfluorinated Sulfonated Ionomers: Ion Induced Polarization 41 Band Broadening. J. Electroanal. Chem. 2017, 800, 176–183. https://doi.org/10.1016/j.jelechem.2017.02.041.
- Kendrick, I.; Kumari, D.; Yakaboski, A.; Dimakis, N.; Smotkin, E. S. Elucidating the Ionomer-Electrified Metal 42 (34) 43 Interface. J. Am. Chem. Soc. 2010, 132 (49), 17611–17616. https://doi.org/10.1021/ja1081487.
- 44 (35) Kendrick, I.; Yakaboski, A.; Kingston, E.; Doan, J.; Dimakis, N.; Smotkin, E. S. Theoretical and Experimental 45 Infrared Spectra of Hydrated and Dehydrated Nafion. J. Polym. Sci. Part B Polym. Phys. 2013, 51 (18), 1329-1334. https://doi.org/10.1002/polb.23348. 46

- View Article Online
- DOI: 10.1039/D5TA03973H Kraka, E.; Quintano, M.; La Force, H. W.; Antonio, J. J.; Freindorf, M. The Local Vibrational Mode Theory and 1 (36) 2 Its Place in the Vibrational Spectroscopy Arena. J. Phys. Chem. A 2022, 126 (47), 8781-8798. 3 https://doi.org/10.1021/acs.jpca.2c05962.

5

6

7

8

3

34

32

- Yamaguchi, M.; Ohira, A. Vibrational Analysis of Side Chain Model Compounds of Perfluorinated Alkyl Sulfonic (37) Acid Ionomers. J. Phys. Chem. A 2012, 116 (44), 10850–10863. https://doi.org/10.1021/jp308663c.
- Moran, A.; Mukamel, S. The Origin of Vibrational Mode Couplings in Various Secondary Structural Motifs of (38)Polypeptides. Proc. Natl. Acad. Sci. 2004, 101 (2), 506–510. https://doi.org/10.1073/pnas.2533089100.
- Kraka, E.; Zou, W.; Tao, Y. Decoding Chemical Information from Vibrational Spectroscopy Data: Local (39) Brend acress Autida Rublished an ORJune 2025, Downhoaded on 662025 428:49 PM-Article Is Reensed under a Creative Commons Attribution 3.0 Unported Dicence. Vibrational Mode Theory. *WIREs Comput. Mol. Sci.* **2020**, *10* (5), 1–34. https://doi.org/10.1002/wcms.1480.
 - (40)Silva, N. J.; Tunega, D.; Korzeniewski, C.; Lischka, H.; Aquino, A. J. A. Microhydration of Polymer Electrolyte Membranes: A Comparison of Hydrogen-Bonding Networks and Spectral Properties of Nafion and Bis[(Perfluoroalkyl)Sulfonyl] Imide. J. Phys. Chem. B 2019, 123 (46), 9899-9911. https://doi.org/10.1021/acs.jpcb.9b07815.
 - Liang, Y.; Kitt, J. P.; Minteer, S. D.; Harris, J. M.; Korzeniewski, C. Vibrational Spectroscopic Monitoring of the (41) Gelation Transition in Nation Ionomer Dispersions. Appl. Spectrosc. 2021, 75 (4), 376–384. https://doi.org/10.1177/0003702820949129.
 - Barique, M. A.; Tsuchida, E.; Ohira, A.; Tashiro, K. Effect of Elevated Temperatures on the States of Water and (42)Their Correlation with the Proton Conductivity of Nafion. ACS Omega 2018, 3 (1), 349–360. https://doi.org/10.1021/acsomega.7b01765.
 - (43) Singh, R. K.; Kunimatsu, K.; Miyatake, K.; Tsuneda, T. Experimental and Theoretical Infrared Spectroscopic Study on Hydrated Nafion Membrane. *Macromolecules* 2016, 49 (17), 6621–6629. https://doi.org/10.1021/acs.macromol.6b00999.
 - Byun, C. K.; Parker, T.; Liang, C.; Kendrick, I.; Dimakis, N.; Smotkin, E. S.; Jin, L. M.; Zhuang, D.; Desmarteau, (44)D. D.; Creager, S. E.; Korzeniewski, C. Thermal Processing as a Means to Prepare Durable, Submicron Thickness Ionomer Films for Study by Transmission Infrared Spectroscopy. Anal. Chem. 2012, 84 (19), 8127–8132. https://doi.org/10.1021/ac301662f.
 - Danilczuk, M.; Lin, L.; Schlick, S.; Hamrock, S. J.; Schaberg, M. S. Understanding the Fingerprint Region in the (45)Infra-Red Spectra of Perfluorinated Ionomer Membranes and Corresponding Model Compounds: Experiments and Theoretical Calculations. J. Power Sources 2011, 196 (20), 8216-8224. https://doi.org/10.1016/j.jpowsour.2011.05.067.
 - (46)Warren, D. S.; McOuillan, A. J. Infrared Spectroscopic and DFT Vibrational Mode Study of Perfluoro(2-Ethoxyethane) Sulfonic Acid (PES), a Model Nafion Side-Chain Molecule. J. Phys. Chem. B 2008, 112 (34), 10535-10543. https://doi.org/10.1021/jp801838n.
- 34 Shimoaka, T.; Wakai, C.; Sakabe, T.; Yamazaki, S.; Hasegawa, T. Hydration Structure of Strongly Bound Water (47) 35 on the Sulfonic Acid Group in a Nafion Membrane Studied by Infrared Spectroscopy and Quantum Chemical 36 Calculation. Phys. Chem. Chem. Phys. 2015, 17 (14), 8843–8849. https://doi.org/10.1039/c5cp00567a.
- Ludvigsson, M.; Lindgren, J.; Tegenfeldt, J. FTIR Study of Water in Cast Nafion Films. Electrochim. Acta 2000, 37 (48) 45 (14), 2267–2271. https://doi.org/10.1016/S0013-4686(99)00438-7. 38
- 39 (49) Bernardina, S. D.; Brubach, J.-B.; Berrod, Q.; Guillermo, A.; Judeinstein, P.; Roy, P.; Lyonnard, S. Mechanism of Ionization, Hydration, and Intermolecular H-Bonding in Proton Conducting Nanostructured Ionomers. J. Phys. 40 41 Chem. C 2014, 118 (44), 25468–25479. https://doi.org/10.1021/jp5074818.
- Feng, K.; Hou, L.; Tang, B.; Wu, P. Does Thermal Treatment Merely Make a H2O-Saturated Nafion Membrane 42 (50)43 Lose Its Absorbed Water at High Temperature? Phys. Chem. Chem. Phys. 2015, 17 (14), 9106–9115. https://doi.org/10.1039/c5cp00203f. 44
- 45 (51) Basnayake, R.; Peterson, G. R.; Casadonte, D. J.; Korzeniewski, C. Hydration and Interfacial Water in Nafion Membrane Probed by Transmission Infrared Spectroscopy. J. Phys. Chem. B 2006, 110 (47), 23938–23943. 46 https://doi.org/10.1021/jp064121i. 47

Writcle, PublisherLon 03 Juno 2025. Downloaded on 662025 428:49 PM. 1 This article is licensed under a Creative Commons Attribution 3:0 Upported Licence.

Open Nacqeas

- (52) Ostrowska, J.; Narebska, A. Infrared Study of Hydration and Association of Functional Groups in a Perfluorinated Nafion Membrane, Part 1. *Colloid Polym. Sci.* **1983**, *261* (2), 93–98. https://doi.org/10.1007/BF01410686.
- Glezakou, V.-A.; Dupuis, M.; Mundy, C. J. Acid/Base Equilibria in Clusters and Their Role in Proton Exchange
 Membranes: Computational Insight. *Phys. Chem. Chem. Phys.* 2007, 9 (43), 5752.
 https://doi.org/10.1039/b709752b.
- 6 (54) Phonyiem, M.; Chaiwongwattana, S.; Lao-ngam, C.; Sagarik, K. Proton Transfer Reactions and Dynamics of
 7 Sulfonic Acid Group in Nafion[®]. *Phys. Chem. Chem. Phys.* 2011, *13* (23), 10923–10939.
 8 https://doi.org/10.1039/c1cp20469f.
 - (55) Paddison, S. J.; Kreuer, K. D.; Maier, J. About the Choice of the Protogenic Group in Polymer Electrolyte Membranes: Ab Initio Modelling of Sulfonic Acid, Phosphonic Acid, and Imidazole Functionalized Alkanes. *Phys. Chem. Chem. Phys.* **2006**, *8* (39), 4530–4542. https://doi.org/10.1039/b611221h.
 - (56) Springer, T. E.; Zawodzinski, T. A.; Gottesfeld, S. Polymer Electrolyte Fuel Cell Model. J. Electrochem. Soc. 1991, 138 (8), 2334–2342. https://doi.org/10.1149/1.2085971.
 - (57) Paddison, S. J.; Elliott, J. A. On the Consequences of Side Chain Flexibility and Backbone Conformation on Hydration and Proton Dissociation in Perfluorosulfonic Acid Membranes. *Phys. Chem. Chem. Phys.* 2006, 8 (18), 2193–2203. https://doi.org/10.1039/b602188c.
 - (58) Paddison, S. J.; Elliott, J. A. Molecular Modeling of the Short-Side-Chain Perfluorosulfonic Acid Membrane. J. *Phys. Chem. A* **2005**, *109* (33), 7583–7593. https://doi.org/10.1021/jp0524734.
 - (59) Ilhan, M. A.; Spohr, E. Ab Initio Molecular Dynamics of Proton Networks in Narrow Polymer Electrolyte Pores. *J. Phys. Condens. Matter* **2011**, *23* (23), 234104. https://doi.org/10.1088/0953-8984/23/23/234104.
 - (60) Sakai, H.; Tokumasu, T. Reaction Analysis for Deprotonation of the Sulfonic Group of Perfluorosulfonic Acid Molecules at Low Hydration Levels. J. Phys. Chem. A **2014**, 118 (1), 275–282. https://doi.org/10.1021/jp409781s.
 - (61) Sepehr, F.; Paddison, S. J. Primary Hydration and Proton Transfer of Electrolyte Acids: An Ab Initio Study. *Solid State Ionics* **2017**, *306*, 2–12. https://doi.org/10.1016/j.ssi.2017.03.013.
 - (62) Singh, S.; Taketsugu, T.; Singh, R. K. Hydration, Prediction of the PKa, and Infrared Spectroscopic Study of Sulfonated Polybenzophenone (SPK) Block-Copolymer Hydrocarbon Membranes and Comparisons with Nafion. *ACS Omega* **2021**, *6* (48), 32739–32748. https://doi.org/10.1021/acsomega.1c04484.
 - (63) Singh, R. K.; Tsuneda, T.; Miyatake, K.; Watanabe, M. Theoretical Investigation of Local Proton Conductance in the Proton Exchange Membranes. *Chem. Phys. Lett.* **2014**, *608*, 11–16. https://doi.org/10.1016/j.cplett.2014.05.076.
- (64) Zelovich, T.; Winey, K. I.; Tuckerman, M. E. Hydronium Ion Diffusion in Model Proton Exchange Membranes at Low Hydration: Insights from Ab Initio Molecular Dynamics. *J. Mater. Chem. A* 2021, *9* (4), 2448–2458.
 https://doi.org/10.1039/d0ta10565a.
- (65) Habenicht, B. F.; Paddison, S. J.; Tuckerman, M. E. The Effects of the Hydrophobic Environment on Proton
 Mobility in Perfluorosulfonic Acid Systems: An Ab Initio Molecular Dynamics Study. J. Mater. Chem. 2010, 20
 (30), 6342–6351. https://doi.org/10.1039/c0jm00253d.
- Wang, C.; Clark, J. K.; Kumar, M.; Paddison, S. J. An Ab Initio Study of the Primary Hydration and Proton Transfer of CF 3SO3H and CF3O(CF2) 2SO3H: Effects of the Hybrid Functional and Inclusion of Diffuse Functions. *Solid State Ionics* 2011, *199–200* (1), 6–13. https://doi.org/10.1016/j.ssi.2011.07.002.
- 40 (67) Paddison, S. J. The Modeling of Molecular Structure and Ion Transport in Sulfonic Acid Based Ionomer
 41 Membranes. J. New Mater. Electrochem. Syst. 2001, 4, 197–207.
- (68) Flottat, T.; Latour, B.; Goujon, F.; Hauret, P.; Malfreyt, P. Investigating Percolation and Clustering Effects on
 Aquivion and Nafion Membranes at the Molecular Scale. *Int. J. Hydrogen Energy* 2023, *48* (85), 33283–33296.
 https://doi.org/10.1016/j.ijhydene.2023.05.086.
- (69) Lawler, R.; Caliendo, C.; Ju, H.; Kim, J. Y.; Lee, S. W.; Jang, S. S. Effect of the Side-Chain Length in
 Perfluorinated Sulfonic and Phosphoric Acid-Based Membranes on Nanophase Segregation and Transport: A

Molecular Dynamics Simulation Approach. J. Phys. Chem. B 2020, 124 (8), 1571–1580. https://doi.org/10.1021/acs.jpcb.9b10408.

1 2

3

4 5

6

7

8

Access Auticle Rublished 100 BJ uner 20 25. Downloaded on 6/6/2025 4:28:49 PM. 1

- (70) Jang, S. S.; Molinero, V.; Çağin, T.; Goddard, W. A. Nanophase-Segregation and Transport in Nafion 117 from Molecular Dynamics Simulations: Effect of Monomeric Sequence. J. Phys. Chem. B 2004, 108 (10), 3149–3157. https://doi.org/10.1021/jp036842c.
- (71) Kuo, A. T.; Shinoda, W.; Okazaki, S. Molecular Dynamics Study of the Morphology of Hydrated Perfluorosulfonic Acid Polymer Membranes. *J. Phys. Chem. C* **2016**, *120* (45), 25832–25842. https://doi.org/10.1021/acs.jpcc.6b08015.
- (72) Hofmann, D. W. M.; Kuleshova, L.; D'Aguanno, B.; Noto, V. Di; Negro, E.; Conti, F.; Vittadello, M. Investigation of Water Structure in Nafion Membranes by Infrared Spectroscopy and Molecular Dynamics Simulation. J. Phys. Chem. B 2009, 113 (3), 632–639. https://doi.org/10.1021/jp806761h.
- (73) Wang, R.; Liu, S.; Wang, L.; Li, M.; Gao, C. Understanding of Nanophase Separation and Hydrophilic Morphology in Nafion and SPEEK Membranes: A Combined Experimental and Theoretical Studies. *Nanomaterials* 2019, 9 (6), 869. https://doi.org/10.3390/nano9060869.
- (74) Zhao, Y.; Gao, Q.; Xu, X.; Ma, C.; He, Q.; Min, Y.; Zhao, S. Compromise Mechanism of Proton Transfer in Crown Ether-Based Biomimetic Proton Exchange Membranes: Insights from Molecular Dynamics Simulations; Elsevier B.V., 2025; Vol. 715. https://doi.org/10.1016/j.memsci.2024.123456.
- (75) Akbari, S.; Hamed Mosavian, M. T.; Moosavi, F.; Ahmadpour, A. Elucidating the Morphological Aspects and Proton Dynamics in a Hybrid Perfluorosulfonic Acid Membrane for Medium-Temperature Fuel Cell Applications. *Phys. Chem. Chem. Phys.* **2018**, *20* (47), 29778–29789. https://doi.org/10.1039/C8CP05377D.
- (76) Cui, S.; Liu, J.; Selvan, M. E.; Paddison, S. J.; Keffer, D. J.; Edwards, B. J. Comparison of the Hydration and Diffusion of Protons in Perfluorosulfonic Acid Membranes with Molecular Dynamics Simulations. *J. Phys. Chem. B* 2008, *112* (42), 13273–13284. https://doi.org/10.1021/jp8039803.
- (77) Cui, S.; Liu, J.; Selvan, M. E.; Keffer, D. J.; Edwards, B. J.; Steele, W. V. A Molecular Dynamics Study of a Nafion Polyelectrolyte Membrane and the Aqueous Phase Structure for Proton Transport. J. Phys. Chem. B 2007, 111 (9), 2208–2218. https://doi.org/10.1021/jp066388n.
- (78) Venkatnathan, A.; Devanathan, R.; Dupuis, M. Atomistic Simulations of Hydrated Nafion and Temperature Effects on Hydronium Ion Mobility. *J. Phys. Chem. B* **2007**, *111* (25), 7234–7244. https://doi.org/10.1021/jp0700276.
- (79) Sengupta, S.; Lyulin, A. V. Molecular Modeling of Structure and Dynamics of Nafion Protonation States. *J. Phys. Chem. B* **2019**, *123* (31), 6882–6891. https://doi.org/10.1021/acs.jpcb.9b04534.
- Kuleshova, L.; D'Aguanno, B. Molecular Dynamics Simulation of Hydrated Nafion with a
 Reactive Force Field for Water. J. Mol. Model. 2008, 14 (3), 225–235. https://doi.org/10.1007/s00894-007-0265-9.
- (81) Cui, R.; Li, S.; Yu, C.; Zhou, Y. The Evolution of Hydrogen Bond Network in Nafion via Molecular Dynamics
 Simulation. *Macromolecules* 2023, 56 (4), 1688–1703. https://doi.org/10.1021/acs.macromol.2c02106.
- (82) Rahbari, A.; Hartkamp, R.; Moultos, O. A.; Bos, A.; van den Broeke, L. J. P.; Ramdin, M.; Dubbeldam, D.;
 Lyulin, A. V.; Vlugt, T. J. H. Electro-Osmotic Drag and Thermodynamic Properties of Water in Hydrated Nafion
 Membranes from Molecular Dynamics. *J. Phys. Chem. C* 2022, *126* (18), 8121–8133.
 https://doi.org/10.1021/acs.jpcc.2c01226.
- 40 (83) Bazaid, M.; Huang, Y.; Goddard, W. A.; Jang, S. S. Proton Transport through Interfaces in Nanophase-Separation
 41 of Hydrated Aquivion Membrane: Molecular Dynamics Simulation Approach. *Colloids Surfaces A Physicochem.* 42 *Eng. Asp.* 2023, 676, 1–11. https://doi.org/10.1016/j.colsurfa.2023.132187.
- (84) Urata, S.; Irisawa, J.; Takada, A.; Shinoda, W.; Tsuzuki, S.; Mikami, M. Molecular Dynamics Simulation of
 Swollen Membrane of Perfluorinated Ionomer. *J. Phys. Chem. B* 2005, *109* (9), 4269–4278.
 https://doi.org/10.1021/jp0464340.
- 46 (85) Devanathan, R.; Venkatnathan, A.; Dupuis, M. Atomistic Simulation of Nafion Membrane. 2. Dynamics of Water

31

- Molecules and Hydronium Ions. J. Phys. Chem. B 2007, 111 (45), 13006–13013. https://doi.org/10.1021/jp0761057.
- 3 (86) Devanathan, R.; Venkatnathan, A.; Rousseau, R.; Dupuis, M.; Frigato, T.; Gu, W.; Helms, V. Atomistic Simulation of Water Percolation and Proton Hopping in Nafion Fuel Cell Membrane. J. Phys. Chem. B 2010, 114 4 5 (43), 13681–13690. https://doi.org/10.1021/jp103398b.
- Devanathan, R.; Venkatnathan, A.; Dupuis, M. Atomistic Simulation of Nafion Membrane: I. Effect of Hydration 6 (87)7 on Membrane Nanostructure. J. Phys. Chem. B 2007, 111 (28), 8069–8079. https://doi.org/10.1021/jp0726992.
- 8 Lvulin, A. V.; Sengupta, S.; Varughese, A.; Komarov, P.; Venkatnathan, A. Effect of Annealing on Structure and (88)son Access Articles Rublished on 08 June 2025. Downloaded on 6(2025.4:28:49 PM. 1 Diffusion in Hydrated Nafion Membranes. ACS Appl. Polym. Mater. 2020, 2 (11), 5058–5066. https://doi.org/10.1021/acsapm.0c00875.
 - (89)Paddison, S. J.; Elliott, J. A. Selective Hydration of the 'Short-Side-Chain' Perfluorosulfonic Acid Membrane. An ONIOM Study. Solid State Ionics 2007, 178 (7–10), 561–567. https://doi.org/10.1016/j.ssi.2007.01.007.
 - (90) Wang, M.; Feindel, K. W.; Bergens, S. H.; Wasylishen, R. E. In Situ Quantification of the In-Plane Water Content in the Nafion® Membrane of an Operating Polymer-Electrolyte Membrane Fuel Cell Using 1H Micro-Magnetic Resonance Imaging Experiments. J. Power Sources 2010, 195 (21), 7316–7322. https://doi.org/10.1016/j.jpowsour.2010.05.029.
 - (91) Peng, Z.; Badets, V.; Huguet, P.; Morin, A.; Schott, P.; Tran, T. B. H.; Porozhnyy, M.; Nikonenko, V.; Deabate, S. Operando u -Raman Study of the Actual Water Content of Perfluorosulfonic Acid Membranes in the Fuel Cell. J. Power Sources 2017, 356, 200–211. https://doi.org/10.1016/j.jpowsour.2017.04.095.
 - van Duin, A. C. T.; Dasgupta, S.; Lorant, F.; Goddard, W. A. ReaxFF: A Reactive Force Field for Hydrocarbons. (92)J. Phys. Chem. A 2001, 105 (41), 9396–9409. https://doi.org/10.1021/jp004368u.
 - (93) Senftle, T. P.; Hong, S.; Islam, M. M.; Kylasa, S. B.; Zheng, Y.; Shin, Y. K.; Junkermeier, C.; Engel-Herbert, R.; Janik, M. J.; Aktulga, H. M.; Verstraelen, T.; Grama, A.; Van Duin, A. C. T. The ReaxFF Reactive Force-Field: Development, Applications and Future Directions. npj Comput. Mater. 2016, 2, 15011. https://doi.org/10.1038/npjcompumats.2015.11.
 - (94)Mabuchi, T.; Tokumasu, T. Molecular Dynamics Simulation of Proton Transport in Polymer Electrolyte Membrane. J. Nanosci. Nanotechnol. 2015, 15 (4), 2958–2963. https://doi.org/10.1166/jnn.2015.9647.
 - (95) Mabuchi, T.; Tokumasu, T. Relationship between Proton Transport and Morphology of Perfluorosulfonic Acid Membranes: A Reactive Molecular Dynamics Approach. J. Phys. Chem. B 2018, 122 (22), 5922-5932. https://doi.org/10.1021/acs.jpcb.8b02318.
 - (96) Petersen, M. K.; Voth, G. A. Characterization of the Solvation and Transport of the Hydrated Proton in the Perfluorosulfonic Acid Membrane Nafion. J. Phys. Chem. B 2006, 110 (37), 18594–18600. https://doi.org/10.1021/jp062719k.
- 34 (97) Seeliger, D.; Hartnig, C.; Spohr, E. Aqueous Pore Structure and Proton Dynamics in Solvated Nafion Membranes. *Electrochim. Acta* **2005**, *50* (21), 4234–4240. https://doi.org/10.1016/j.electacta.2005.03.071. 35
- 36 (98) Tse, Y.-L. S.; Herring, A. M.; Kim, K.; Voth, G. A. Molecular Dynamics Simulations of Proton Transport in 3M and Nafion Perfluorosulfonic Acid Membranes. J. Phys. Chem. C 2013, 117 (16), 8079-8091. 37 38 https://doi.org/10.1021/jp400693g.
- (99) 39 Choe, Y. K.; Tsuchida, E.; Ikeshoji, T.; Yamakawa, S.; Hyodo, S. A. Nature of Water Transport and Electro-40 Osmosis in Nafion: Insights from First-Principles Molecular Dynamics Simulations under an Electric Field. J. 41 Phys. Chem. B 2008, 112 (37), 11586–11594. https://doi.org/10.1021/jp8041878.
- (100) Choe, Y. K.; Tsuchida, E.; Ikeshoji, T.; Yamakawa, S.; Hyodo, S. A. Nature of Proton Dynamics in a Polymer 42 43 Electrolyte Membrane, Nafion: A First-Principles Molecular Dynamics Study. Phys. Chem. Chem. Phys. 2009, 11 (20), 3892-3899. https://doi.org/10.1039/b819535h. 44
- 45 (101) Bower, D. I.; Maddams, W. F. The Vibrational Spectroscopy of Polymers; Cambridge University Press: Cambridge, 1989. 46

DOI: 10.1039/D5TA03973H (102) Grimme, S.; Antony, J.; Ehrlich, S.; Krieg, H. A Consistent and Accurate Ab Initio Parametrization of Density Functional Dispersion Correction (DFT-D) for the 94 Elements H-Pu. J. Chem. Phys. 2010, 132 (15), 154104. https://doi.org/10.1063/1.3382344.

1 2

3

4

5

6 7

8

pondeceus Anticle Publishedon 03 June 2025. Downloaded on 6/6/2025 4:28:49 PM-Priss anticle is the need under a Creative Commons Attribution 3. Duported Dicence.

- (103) Perdew, J. P.; Burke, K.; Ernzerhof, M. Generalized Gradient Approximation Made Simple. Phys. Rev. Lett. 1996, 77 (18), 3865–3868. https://doi.org/10.1103/PhysRevLett.77.3865.
- (104) Perdew, J. P.; Burke, K.; Ernzerhof, M. Generalized Gradient Approximation Made Simple [Phys. Rev. Lett. 77, 3865 (1996)]. Phys. Rev. Lett. 1997, 78 (7), 1396–1396. https://doi.org/10.1103/PhysRevLett.78.1396.
- (105) Adamo, C.; Barone, V. Toward Reliable Density Functional Methods without Adjustable Parameters: The PBE0 Model. J. Chem. Phys. 1999, 110 (13), 6158–6170. https://doi.org/10.1063/1.478522.
- (106) Frisch, M. J.; Pople, J. A.; Binkley, J. S. Self-Consistent Molecular Orbital Methods 25. Supplementary Functions for Gaussian Basis Sets. J. Chem. Phys. 1984, 80 (7), 3265–3269. https://doi.org/10.1063/1.447079.
- (107) Clark, T.; Chandrasekhar, J.; Spitznagel, G. W.; Schlever, P. V. R. Efficient Diffuse Function-augmented Basis Sets for Anion Calculations. III. The 3-21+G Basis Set for First-row Elements, Li-F. J. Comput. Chem. 1983, 4 (3), 294–301. https://doi.org/10.1002/jcc.540040303.
- (108) Martínez, L.; Andrade, R.; Birgin, E. G.; Martínez, J. M. Packmol: A Package for Building Initial Configurations for Molecular Dynamics Simulations. J. Comput. Chem. 2009, 30 (13), 2157-2164. https://doi.org/10.1002/jcc.21224.
- (109) Devanathan, R.; Idupulapati, N.; Baer, M. D.; Mundy, C. J.; Dupuis, M. Ab Initio Molecular Dynamics Simulation of Proton Hopping in a Model Polymer Membrane. J. Phys. Chem. B 2013, 117 (51), 16522–16529. https://doi.org/10.1021/jp410229u.
- (110) Rappé, A. K.; Casewit, C. J.; Colwell, K. S.; Goddard III, W. A.; Skiff, W. M. UFF, a Full Periodic Table Force Field for Molecular Mechanics and Molecular Dynamics Simulations. J. Am. Chem. Soc. 1992, 114 (25), 10024– 10035. https://doi.org/10.1021/ja00051a040.
- (111) Plimpton, S. Fast Parallel Algorithms for Short-Range Molecular Dynamics. J. Comput. Phys. 1995, 117 (1), 1–19. https://doi.org/10.1006/jcph.1995.1039.
- (112) Thompson, A. P.; Aktulga, H. M.; Berger, R.; Bolintineanu, D. S.; Brown, W. M.; Crozier, P. S.; in 't Veld, P. J.; Kohlmeyer, A.; Moore, S. G.; Nguyen, T. D.; Shan, R.; Stevens, M. J.; Tranchida, J.; Trott, C.; Plimpton, S. J. LAMMPS - a Flexible Simulation Tool for Particle-Based Materials Modeling at the Atomic, Meso, and Continuum Scales. Comput. Phys. Commun. 2022, 271, 108171. https://doi.org/10.1016/j.cpc.2021.108171.
- 3 (113) Verlet, L. Computer "Experiments" on Classical Fluids. I. Thermodynamical Properties of Lennard-Jones Molecules. Phys. Rev. 1967, 159 (98), 98–103. https://doi.org/10.1103/PhysRev.159.98.
- (114) Hockney, R. W.; Eastwood, J. W. Computer Simulation Using Particles; McGraw-Hill International Book 32 33 Company: New York, 1981.
- (115) Rappe, A. K.; Goddard III, W. A. Charge Equilibration for Molecular Dynamics Simulations. J. Phys. Chem. 34 1991, 95 (8), 3358-3363. https://doi.org/10.1021/j100161a070. 35
- (116) Paddison, S. J.; Reagor, D. W.; Zawodzinski Jr, T. A. High Frequency Dielectric Studies of Hydrated Nafion. J. 36 *Electroanal. Chem.* **1998**, *459* (1), 91–97. https://doi.org/10.1016/S0022-0728(98)00321-0. 37
- (117) Laitinen, H. A.; Harris, W. E. Chemical Analysis, 2nd ed.; Summersgill, R. H., Langman, S. L., Eds.; McGraw-38 39 Hill, Inc.: New York, 1975.
- 40 (118) Herath, M. B.; Creager, S. E.; Kitaygorodskiy, A.; DesMarteau, D. D. Perfluoroalkyl Phosphonic and Phosphinic Acids as Proton Conductors for Anhydrous Proton-Exchange Membranes. ChemPhysChem 2010, 11 (13), 2871-41 42 2878. https://doi.org/10.1002/cphc.201000184.
- 43 (119) Schuster, M.; Rager, T.; Noda, A.; Kreuer, K. D.; Maier, J. About the Choice of the Protogenic Group in PEM 44 Separator Materials for Intermediate Temperature, Low Humidity Operation: A Critical Comparison of Sulfonic 45 Acid, Phosphonic Acid and Imidazole Functionalized Model Compounds. Fuel Cells 2005, 5 (3), 355–365. https://doi.org/10.1002/fuce.200400059. 46

- (120) Wyatt, P. A. H. Sulphuric Acid Autoprotolysis and the Theory of Dissociated Solvents. *Trans. Faraday Soc.* 1969, 65, 585–590. https://doi.org/10.1039/tf9696500585.
- (121) Flowers, R. H.; Gillespie, R. J.; Robinson, E. A. THE SULPHURIC ACID SOLVENT SYSTEM: PART I. ACID BASE REACTIONS. *Can. J. Chem.* 1960, *38* (8), 1363–1370. https://doi.org/10.1139/v60-190.
- (122) Buzzoni, R.; Bordiga, S.; Ricchiardi, G.; Spoto, G.; Zecchina, A. Interaction of H2O, CH3OH, (CH3)2O, CH3CN, and Pyridine with the Superacid Perfluorosulfonic Membrane Nafion: An IR and Raman Study. *J. Phys. Chem.* 1995, 99 (31), 11937–11951. https://doi.org/10.1021/j100031a023.
- (123) Negro, E.; Vittadello, M.; Vezzù, K.; Paddison, S. J.; Di Noto, V. The Influence of the Cationic Form and Degree of Hydration on the Structure of NafionTM. *Solid State Ionics* **2013**, *252*, 84–92. https://doi.org/10.1016/j.ssi.2013.09.017.
 - (124) Vishnyakov, A.; Neimark, A. V. Molecular Dynamics Simulation of Nafion Oligomer Solvation in Equimolar Methanol–Water Mixture. *J. Phys. Chem. B* 2001, *105* (32), 7830–7834. https://doi.org/10.1021/jp004082p.

Figure 1. General perfluorinated sulfonic acid structure (top left) and physical parameters of Nafion membranes (bottom left). Snapshot of hydrated molecular dynamics Nafion cell (top right).

Figure 2. Operando and ex-situ vibrational spectra. (a) Potential dependent Raman spectra of 25 wt.% Nafion cathode catalyst (Fe- N_x/C + Pt under O_2), adapted with permission from Kendrick et al.³¹ 2016 under Creative Commons Attribution 4.0 License. (b) Hydration-state dependent PFSA membrane transmission spectra, adapted with permission from Loupe et al.⁸ Copyright 2020 American Chemical Society. (c) α - and β -site Newman projections.

Figure 3. Nation oligomer for molecular dynamics (MD) simulations (top) and table of specified number of atoms, MD cell dimensions, and densities.

Figure 4. Theoretical and experimental Nafion vibrational group mode analyses: (a) model monomer structures; (b) Effect of functional and backbone capping groups on calculated frequencies (columns 1-3). Animations for all listed 1-mer-CF₃ normal modes (column 3) are available (ESI). X3LYP-based frequencies (column 3), FTIR band frequencies (column 4), and NR212 spectra are adapted with permission from Loupe et al.⁸ Copyright 2020 American Chemical Society.

Figure 5. Inner- and outer-sphere water content versus λ . (a) Overlapping histograms of f_{Λ} versus Λ , for nine λ values. Blue and red histograms correspond to protonated and deprotonated exchange sites, respectively. (b) Water-count discrepancy, δ , versus λ . Structural examples contributing to δ are inset: (top) pronated bridge-water overcounted twice (i.e., j = 3) and (bottom) non-bridge inner-sphere waters (light blue) and undercounted outer-sphere waters (green).

Figure 6. Colored Connolly surfaces applied to atom groupings from $\lambda = 0$, 2, and 20 MD cells. Inner-sphere waters (light blue) are either bridge (overcounted) or non-bridge. Outer-sphere waters (green) are either isolated or bulk-like (both are undercounted).

Figure 7. -SO₃H counts versus λ after 2 ns of ReaxFF.

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Open Access Article. Published on 03 June 2025. Downloaded on 6/6/2025 4:28:49 PM

Figure 8. Proportion of protonated (i.e., α) exchange sites versus Λ for all $\lambda > 0$ cells.

Figure 9. DFT and ReaxFF MD generated exchange site inner-sphere environments. The number of non-SO₃H inner-sphere atoms is N_{np} (np stands for nonpolar). Not all outer-sphere atoms (purple) are shown. Atom colors: hydrogen (white), carbon (grey), non-hydronium oxygen (red), hydronium oxygen (blue), fluorine (green), sulfur (yellow). An animated version of this figure is available (ESI).

Table 1. Vibrational group mode assignments for Nafion 212 transmission FTIR bands and corresponding DFT-calculated normal modes (X3LYP/6-311G**++), adapted with permission from Loupe et al.⁸ Copyright 2020 American Chemical Society. Eigenvector animations for each normal mode are available.⁸

Table 2. Cardinality of H_{α} , H_{β} , and the union of both sets versus λ for the nine simulated Nafion cells.

Journal of Materials Chemistry A Accepted Manuscript



General perfluorinated sulfonic acid structure (top left) and physical parameters of Nafion membranes (bottom left). Snapshot of hydrated molecular dynamics Nafion cell (top right).

82x62mm (300 x 300 DPI)



Operando and ex-situ vibrational spectra. (a) Potential dependent Raman spectra of 25 wt.% Nafion cathode catalyst (Fe-N_x/C + Pt under O₂), adapted with permission from Kendrick et al. 2016 under Creative Commons Attribution 4.0 License. (b) Hydration-state dependent PFSA membrane transmission spectra, adapted with permission from Loupe et al. [Ref. 8] Copyright 2020 American Chemical Society. (c) a- and β -site Newman projections.

299x160mm (300 x 300 DPI)

Open Access Article. Published on 03 June 2025. Downloaded on 6/6/2025 4:28:49 PM.	This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.		
	(cc))		

Model Nafion Oligomer for ReaxFF MD									
oligomer = 10-mer						1144 g/eq			
[ſ			1		32 10-mers per cell			
$F + CF_2 - CF_2 + CF_2 - CF_2 + I_1$				320 SO ₃ (H) groups					
$\begin{array}{c c} & & & & \\ \hline \\ \hline$									
Number of Atoms					MD Cell Dimensions				
λ	Nafion [†] water [†]		water [†]	total	۱ (Å) nm ³	ρ (g/ml)		
0	22	144	0	22144	64.1	260	2.31		
1	u	"	960	23104	65.5	5 280	2.20		
2	u	"	1920	24064	66.9	9 300	2.10		
3	u	"	2880	25024	68.1	320	2.01		
5	"	"	4800	26944	70.6	5 350	1.86		
7	"	"	6720	28864	73.0) 390	1.75		
10	"	"	9600	31744	76.2	2 440	1.60		
15	u	"	14400	36544	80.2	2 520	1.46		
20	"	"	19200	41344	82.9	9 570	1.41		

¹ Initial number of atoms before initiation of ReaxFF simulation.

Nafion oligomer for molecular dynamics (MD) simulations (top) and table of specified number of atoms, MD cell dimensions, and densities.

83x87mm (300 x 300 DPI)

Journal of Materials Chemistry A Accepted Manuscript



Theoretical and experimental Nafion vibrational group mode analyses: (a) model monomer structures; (b) Effect of functional and backbone capping groups on calculated frequencies (columns 1-3). Animations for all listed 1-mer-CF₃ normal modes (column 3) are available (ESI). X3LYP-based frequencies (column 3), FTIR band frequencies (column 4), and NR212 spectra are adapted with permission from Loupe et al. [Ref. 8] Copyright 2020 American Chemical Society.

447x152mm (300 x 300 DPI)



Inner- and outer-sphere water content versus λ . (a) Overlapping histograms of f_{Λ} versus Λ , for nine λ values. Blue and red histograms correspond to protonated and deprotonated exchange sites, respectively. (b) Water-count discrepancy, δ , versus λ . Structural examples contributing to δ are inset: (top) pronated bridge-water overcounted twice (i.e., j = 3) and (bottom) non-bridge inner-sphere waters (light blue) and undercounted outer-sphere waters (green).

185x107mm (300 x 300 DPI)



Colored Connolly surfaces applied to atom groupings from $\lambda = 0, 2$, and 20 MD cells. Inner-sphere waters (light blue) are either bridge (overcounted) or non-bridge. Outer-sphere waters (green) are either isolated or bulk-like (both are undercounted).

221x104mm (300 x 300 DPI)



Number of -SO₃H groups versus λ after 2 ns of ReaxFF simulation.

326x190mm (300 x 300 DPI)

Journal of Materials Chemistry A Accepted Manuscript



Proportion of protonated (i.e., a) exchange sites versus Λ for all λ > 0 cells. 138x149mm (300 x 300 DPI)



DFT and ReaxFF MD generated exchange site inner-sphere environments. The number of non-SO₃H innersphere atoms is N_{np} (np stands for nonpolar). Not all outer-sphere atoms (purple) are shown. Atom colors: hydrogen (white), carbon (grey), non-hydronium oxygen (red), hydronium oxygen (blue), fluorine (green), sulfur (yellow). A video showing each sphere in rotation is available (ESI Video).

338x182mm (300 x 300 DPI)

<u>frequency (cm⁻¹)</u>		lahal	group mode assignment				
FTIR	DFT	label	(dominant contributors in bold)				
1414	1405	$\alpha_{\rm HF}$	$\mathbf{v}_{as}(\mathrm{SO}_{3}\mathrm{H}) + \mathbf{v}_{as}(\mathrm{COC-A})$				
1058	1059	$\beta_{\rm HF}$	$\mathbf{v}_{as}(\text{COC-A}) + \mathbf{v}_{s}(\mathbf{SO}_{3}^{-})$				
969	983	β_{LF}	$\mathbf{v}_{\mathbf{s}}(\mathbf{SO}_{3}^{-}) + \mathbf{v}_{as}(\text{COC-A})$				
910	786	α_{LF}	$\mathbf{v}_{\mathbf{s}}(\mathbf{SO}_{3}\mathbf{H}) + \mathbf{v}_{\mathbf{s}}(\mathbf{COC}-\mathbf{A})$				

 v_s : symmetric stretching; v_{as} : asymmetric stretching;

HF: high-frequency; LF: low-frequency

Vibrational assignments for Nafion 212 transmission FTIR bands and DFT-calculated normal modes (X3LYP/6-311G**++) adapted with permission from Loupe et al. [Ref. 8] Copyright 2020 American Chemical Society. Eigenvector animations for each normal mode are available. [Ref. 8]

81x39mm (300 x 300 DPI)

λ	0	1	2	3	5	7	10	15	20
H _α	1	6	6	7	8	7	7	7	6
H _β	0	6	9	10	11	10	12	12	13
[H _α UH _β]	1	12	15	17	19	17	19	19	19

Cardinality of $H_{\alpha},\,H_{\beta},$ and the union of both sets versus λ for the nine simulated Nafion cells.

142x41mm (300 x 300 DPI)

Journal of Materials Chemistry A Accepted Manuscript

Data Availability Statement

A collection of files supporting this article are available as part of the Supplementary Information: vibrational normal mode animations of Nafion models, PDB files of RMD cells, RMD data analysis files, and supporting figures with corresponding discussion. The Supplementary Information document provides a description of each supporting file.