

# PCCP

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

*Accepted Manuscripts* are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.

Cite this: DOI: 10.1039/c0xx00000x

www.rsc.org/xxxxxx

ARTICLE TYPE

## Constant capacitance in nanopores of carbon monoliths

Alejandra García-Gómez,<sup>a</sup> Gelines Moreno-Fernández,<sup>a</sup> Belén Lobato<sup>b</sup> and Teresa A. Centeno<sup>\*b</sup>

Received (in XXX, XXX) Xth XXXXXXXXX 200X, Accepted Xth XXXXXXXXX 200X

DOI: 10.1039/b000000x

5 The results obtained for binder-free electrodes made of carbon monoliths with narrow micropore size distributions confirm that the specific capacitance in the electrolyte (C<sub>2</sub>H<sub>5</sub>)<sub>4</sub>NBF<sub>4</sub>/acetonitrile does not depend significantly on the micropore size and support the foregoing constant result of 10 0.094±0.011 F/m<sup>2</sup>

The reliable assessment of surface areas in nanoporous carbons is of great relevance to gain clear insights into their performance in supercapacitors. It was shown recently that there are important differences between the surface area estimated by the standard 15 BET model and practically all other methods.<sup>1</sup> Basically, S<sub>BET</sub> underestimates the real surface area of carbons with a high proportion of micropores below 0.8 nm and gradually overestimates it in micropores above 1.1 nm. Only in the micropore range of 0.8-1.1 nm, S<sub>BET</sub> coincides with the values 20 from the other determinations.<sup>1,2</sup>

In this context, it was illustrated that the anomalous increase<sup>3</sup> in the surface-capacitance (C/S in F/m<sup>2</sup>) claimed for carbide-derived carbons (CDCs) with pores smaller than 1 nm derives from the unreliable assessment of their area by the classical BET 25 equation.<sup>2,4</sup> The original sampling used by Chmiola *et al.*<sup>3</sup> was limited to 5 CDCs for the region below 1.1 nm and for wider pores they considered data quoted in the literature. Stoeckli *et al.*<sup>4</sup> re-examined this issue by considering: (a) a larger variety of carbons and (b) the reliable determination of the total surface area 30 available to the electrolyte ions by using simultaneously several independent methods. Such extended study showed that there is a linear correlation between the gravimetric capacitance [in F/g] and the surface involved in the electrochemical double-layer formation [in m<sup>2</sup>/g]. Therefore, the contribution from the carbon 35 surface to the capacitance in the (C<sub>2</sub>H<sub>5</sub>)<sub>4</sub>NBF<sub>4</sub>/acetonitrile electrolyte (Et<sub>4</sub>NBF<sub>4</sub>/AN) is practically constant around 0.094 ± 0.011 F/m<sup>2</sup> in the range of 0.66 to 1.6 nm and shows a similar pattern even up to 15 nm.<sup>4</sup> Additionally, following corrections for pseudocapacitance effects, it resulted that C/S is also independent 40 of the micropore width in the aqueous H<sub>2</sub>SO<sub>4</sub> and KOH electrolytes.<sup>5</sup>

The reliability of the constant experimental values of C/S within the experimental uncertainty was confirmed by further studies from different approaches by Stoeckli *et al.*<sup>2,6,7</sup> Additionally, 45 evidences supporting the constant pattern were also provided by other authors. The study of Feng *et al.*<sup>8</sup>, based on the surface area of carbons beads estimated by the Density Functional Theory (DFT) and in disagreement with S<sub>BET</sub>, led to values in

Et<sub>4</sub>NBF<sub>4</sub>/PC of 0.087, 0.099 and 0.097 F/m<sup>2</sup> at pore widths 50 below 1 nm, between 1 and 2 nm, and above 2 nm, respectively. Relatively constant C/S in pores larger than 0.8 nm was also obtained from modeling based on DFT and taking into account the solvent.<sup>9,10</sup>

This paper presents a new and straightforward demonstration as a 55 response to the criticisms addressed to the constant capacitance, namely that<sup>11-14</sup>

- The presence of binder in the electrode could push the increase in C/S further down.
- The pore size distribution of carbons may hide an 60 underlying variation of the surface-capacitance with the pore size.

The fact that the results of C/S<sub>BET</sub> vs micropore size obtained by Chmiola *et al.* and Stoeckli *et al.* are very similar already weakens these points but the controversy over this issue still 65 remains.


It has been shown that monolithic electrodes report direct correlations between porous features of carbons and their supercapacitor performance.<sup>15,16</sup> The present study of binder-free electrodes made of carbon monoliths with a very narrow 70 micropore size distribution provides further experimental evidences on the constant surface-capacitance in the organic electrolyte Et<sub>4</sub>NBF<sub>4</sub>/AN.

Two carbon monoliths, here-after called M1 and M2, were obtained as slices of multichannel carbon bars. They consist of 75 carbon walls and square channels both arranged along the cylinder axis (Fig. 1, inset). A detailed description of the carbon walls was reported elsewhere.<sup>16</sup> Carbon monolith M1-A resulted from the activation of M1 in flowing CO<sub>2</sub>.

As summarized in Table 1, the three monoliths achieve similar 80 gravimetric capacitance, being 91 and 93 F/g for M1 and M1-A and 86 F/g for M2.

The type-I isotherms obtained for the three carbon monoliths (Fig. 1) reveal that their porosity consists exclusively of micropores (width < 2 nm) with a negligible contribution of 85 meso-macropores (Fig. S1-Supplementary Information).

The analysis of the isotherm of M1 by the Dubinin-Radushkevich (DR) equation reports that it has a volume of micropores of 0.42 cm<sup>3</sup>/g corresponding to pores with an average size (L<sub>0</sub>) of 0.73 nm. These values lead to a 90 microporous surface area of 1151 m<sup>2</sup>/g. Additionally, the comparison with the isotherm obtained for the non-porous carbon Vulcan 3G confirmed that the contribution of pores larger than 2 nm is not significant and the external surface (non-microporous)



**Fig. 1**  $N_2$  adsorption-desorption isotherms of the carbon monoliths (inset, pictures of the carbon monoliths M1 and M2)


is only  $1 \text{ m}^2/\text{g}$ . Therefore, the total area of M1 is the sum of both values,  $S_{\text{DR}} = 1152 \text{ m}^2/\text{g}$  (Table 1).

Immersion calorimetry of M1 into liquids with molecular dimensions between 0.33 and 1.5 nm leads to the effective micropore size distribution (PSD),<sup>17</sup> as opposed to the adsorption which provides the absolute distribution by using the small  $N_2$  molecule as probe. Figure 2 shows an extremely narrow PSD in M1, with the majority of the pores in the range 0.63–0.76 nm, suiting the size of the cation  $\text{Et}_4\text{N}^+$ .<sup>3</sup> The good agreement observed between the adsorption and immersion experiments indicates the absence of "molecular sieves" effects or "bottle-neck" at the entrance of the micropores.<sup>17</sup>

The DR analysis conducted on the isotherm of M2 reveals comparable characteristics to those of M1 with a micropore volume of  $0.44 \text{ cm}^3/\text{g}$ , an average micropore size of 0.69 nm, a microporous surface of  $1275 \text{ m}^2/\text{g}$ , an external surface of  $3 \text{ m}^2/\text{g}$  and a total surface area of  $1278 \text{ m}^2/\text{g}$  (Table 1). In spite of the similar average micropore width of M1 and M2, the latter displays a more heterogeneous PSD with significant presence of micropores in all ranges (Fig. 2).

**Table 1** Porosity features and capacitance values of the carbon monoliths

Carbon monolith	Porosity characteristics							Gravimetric capacitance		Surface-capacitance	
	$L_o$ (nm)	$S_{\text{DR}}$ ( $\text{m}^2/\text{g}$ )	$S_{\text{comp}}$ ( $\text{m}^2/\text{g}$ )	$S_{\text{phenol}}$ ( $\text{m}^2/\text{g}$ )	$S_{\text{BET}}$ ( $\text{m}^2/\text{g}$ )	$S_{\text{total}}^{(2)}$ ( $\text{m}^2/\text{g}$ )	$S_{>0.63}$ ( $\text{m}^2/\text{g}$ )	C (F/g)	$C/S_{\text{BET}}$ ( $\text{F}/\text{m}^2$ )	$C/S_{\text{total}}$ ( $\text{F}/\text{m}^2$ )	$C/S_{>0.63}$ ( $\text{F}/\text{m}^2$ )
M1	0.73	1152	1107	1000	619	1086	878	91	0.147	0.084	0.104
M2	0.69	1278	1276	1286	599	1280	933	86	0.144	0.067	0.092




**Fig. 2** Micropore size distribution obtained by immersion calorimetry of the carbon monoliths

It appears that the activation process does not modify the porous structure above 2 nm but it increases the micropore volume and the average micropore size is enlarged to 1.01 nm. The PSD obtained for M1-A confirms the enlargement of the pores, the surface area being mostly in pores with sizes between 0.76 and 1.5 nm (Fig. 2). The  $S_{\text{DR}}$  of the activated monolith accounts for  $1151 \text{ m}^2/\text{g}$  (Table 1).

In order to get a more reliable determination of the specific surface area of the carbon monoliths, the  $N_2$  isotherms were also analyzed by other methods such as the comparison plot ( $S_{\text{comp}}$ ) and the BET equation ( $S_{\text{BET}}$ ). These data were further cross-checked with the corresponding enthalpy of immersion of the carbon monoliths into dilute aqueous solution of phenol ( $S_{\text{phenol}}$ ).<sup>1,2</sup> Table 1 summarizes the total surface areas derived from the different approaches.

M1-A 1.01 1151 1114 1193 1154 1153 898 93 0.081 0.081 0.104



**Fig. 3** Variation of the surface-capacitances in the  $\text{Et}_4\text{BF}_4/\text{AN}$  electrolyte for the carbon monoliths, a variety of porous carbons ( $\square$ )<sup>2</sup> and carbide-based carbons ( $\blacktriangle$ ) of different average micropore size. Left: The use of  $S_{BET}$  leads to a decreasing contribution of the surface of pores above 0.63 nm (accessible to the larger ion) leads to a constant contribution

The good agreement (Table 1) between  $S_{DR}$ ,  $S_{comp}$ ,  $S_{phenol}$  and  $S_{BET}$  for M1-A confirms that the BET method provides reliable results for materials with pores around 0.9-1.0 nm.<sup>1</sup> On the contrary, there is a noticeable difference (around 50%) between the value obtained by the BET equation and the other determinations in the case of M1 and M2 (Table 1). As reported previously,<sup>1</sup>  $S_{BET}$  underestimates the total surface area of carbons with a high proportion of pores below 0.8-0.9 nm, which is precisely the case of M1 and M2. Based on the convergence of values, the total surface area of the carbon monoliths was derived from the average between the areas obtained from the three independent methods  $(S_{DR} + S_{comp} + S_{phenol})/3$ .

In a first step,  $S_{total}$  appears to be more reliable than  $S_{BET}$ , with the corresponding consequences on surface-capacitance  $C/S$  values summarized in Table 1. Thus,  $C/S_{BET}$  and  $C/S_{total}$  are similar in M1-A but  $C/S_{total}$  is clearly much lower than  $C/S_{BET}$  in the two monoliths with micropores below 1 nm.

Secondly, it must be emphasized that  $S_{total}$  corresponds to the area accessible to small molecules such as nitrogen and phenol which probe the surface area of pores down to  $\sim 0.4$  nm. In the case of the present carbons with a significant fraction of their porosity below 0.7 nm (Fig. 1a), the surface area accessible to the desolvated cation (the largest dimension being  $0.68 \text{ nm}^3$ ) would

be much reduced.<sup>4,18</sup> The extent of the surface involved in the energy storage is limited by that accessible to  $\text{Et}_4\text{N}^+$  as the anion  $\text{BF}_4^-$  has a smaller size.<sup>19</sup>

For the three monoliths, the combination of  $\text{N}_2$  adsorption and the enthalpies of immersion into  $\text{CH}_2\text{Cl}_2$ ,  $\text{C}_6\text{H}_6$  and  $\text{CCl}_4$  allow estimating the surface area of the micropores in the ranges 0.33–0.41 and 0.41–0.63 nm ( $S_{<0.63}$ ).<sup>17,20</sup> It follows that the surface close to that accessible to  $\text{Et}_4\text{N}^+$  corresponds to  $S_{>0.63} = S_{total} - S_{<0.63}$ . Table 1 shows that  $S_{>0.63}$  for the present monoliths is around 75% of their  $S_{total}$ .

As implied by the data of Table 1, the determination of the surface-capacitance leads to strongly diverging results, depending on the choice of the surface area. Figure 3 clearly illustrates the difference in the  $C/S$  vs micropore size based on  $S_{BET}$  or on the surface accessible to the electrolyte. Figure 3a shows the trend for  $C/S_{BET}$  and it includes data for the present monoliths, a variety of 21 porous carbons tested by Stoeckli *et al.*<sup>4</sup> ( $\square$ ) and the 5 carbide-based carbons ( $\blacktriangle$ ) which led to the hypothesis of an anomalous increase in pores below 1 nm.<sup>3</sup> It is observed that carbon monoliths with pore widths around 0.7 nm achieve outstanding capacitances of 0.147 and 0.144  $\text{F/m}^2$ , even surpassing the highest value obtained for CDCs,<sup>3</sup> whereas  $C/S_{BET}$  decreases to 0.081  $\text{F/m}^2$  for the activated monolith with a porosity around 1

nm. Fig. 3a illustrates that these data fit into the general profile, an enhancement below 1 nm and a drop above 1.3 nm, reported earlier on the basis of the unreliable BET-surface area by Chmiola *et al.*<sup>3</sup> and Stoeckli *et al.*<sup>4</sup>

5 On the contrary, the values referred to the more reliable  $S_{>0.63}$  drop to 0.104 and 0.092 F/m<sup>2</sup> for M1 and M2, respectively (Table 1) in accordance with 0.104 F/m<sup>2</sup> for M1-A. As shown in Figure 3b, these refined data based on the real surface involved in the electrochemical double-layer formation follow the regular pattern  
10 found by Stoeckli *et al.* with a contribution in Et<sub>4</sub>NBF<sub>4</sub>/AN of (0.094 ± 0.011) F/m<sup>2</sup> between 0.7 and 15 nm.<sup>2</sup>

The present results obtained for binder-free electrodes made of carbon monoliths with narrow micropore size distributions provide a strong evidence that the specific capacitance  $C/S$  in  
15 F/m<sup>2</sup> does not depend significantly on the micropore size and support the foregoing constant result. The gravimetric capacitance of carbons depends only on the surface available to the cation of the organic electrolyte.

The need for a reliable characterization of carbons in SC is often  
20 overlooked, but of fundamental importance to assess competing claims.

## Experimental

Carbon monoliths M1 and M2 were obtained from multichannel  
25 carbon bars 650 CPI and 1200 CPI, respectively. They were manufactured by MAST Carbon International Ltd from extrusion of a phenolic resin and subsequent carbonization and activation and 650 and 1200 channels per square inch. Carbon monolith M1-A was obtained by heating M1 in flowing CO<sub>2</sub> at 800°C for 6  
30 hours, up to a weight loss of 7 %.

The porosity of the carbon monoliths was characterized by N<sub>2</sub> adsorption at 77 K (Micromeritics ASAP 2010) and by immersion calorimetry at 293 K. The N<sub>2</sub> isotherm was analyzed by the Dubinin's theory, the Kaneko's comparison plot and the  
35 BET equation. The total surface area was also determined from the enthalpy of immersion of the carbon monoliths into 0.4 M aqueous solution of phenol ( $S_{\text{phenol}}$ ).<sup>2,17</sup>

The assessment of the micropore accessibility was obtained from the enthalpies of immersion into liquids having different critical  
40 molecular sizes such as dichloromethane (0.33 nm), benzene (0.41 nm), carbon tetrachloride (0.63 nm), cyclododeca-1,5,9-triene (0.76 nm), and tri-2,4-xylylphosphate (1.50 nm).<sup>17</sup>

The electrochemical study was carried out in two-electrode Swagelok<sup>TM</sup>-type cells at room temperature. The carbon  
45 monoliths acting as electrodes were separated by a glassy fibrous paper (Whatman 934 AH) and immersed in 1M solution of (C<sub>2</sub>H<sub>5</sub>)<sub>4</sub>NBF<sub>4</sub> in acetonitrile. Two tantalum rods were used as current collectors. The gravimetric capacitance was determined from galvanostatic measurements between 0 and 2 V (Autolab  
50 potentiostat/galvanostat-302 N) at a current density of 1 mA/cm<sup>2</sup>, i.e. in nearly steady state to prevent any kinetic effect on the capacitance measurement.

The specific capacitance was determined from the discharge run by using  $C=2 \cdot I \cdot t_d / E \cdot m$ , where  $I$  is the current applied,  $t_d$  is the  
55 time spent along the discharge, and  $m$  is the mass of one electrode.

## Acknowledgements

We thank Dr. Jose M. Rojo (ICMM-CSIC) for his useful assistance.

60 Financial support from Spanish MICINN (project MAT 2011-25198) is gratefully acknowledged. G. Moreno-Fernandez thanks Spanish MINECO for a FPI fellowship.

## Notes and references

<sup>a</sup> Instituto de Ciencia de Materiales de Madrid, ICMM-CSIC. Sor Juana Ines de la Cruz, 3, Cantoblanco, 28049 Madrid, Spain.

<sup>b</sup> Instituto Nacional del Carbón, INCAR-CSIC, Apartado 73,33080 Oviedo, Spain. Fax: (+34) 985 297662; Tel: (+34) 985 119 090; E-mail: 70 teresa@incar.csic.es

† Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/b000000x

75

- 1 T.A. Centeno and F. Stoeckli, *Carbon*, 2010, **48**, 2478.
- 2 F. Stoeckli and T.A. Centeno, *J. Mater. Chem. A*, 2013, **1**, 6865.
- 3 J. Chmiola, G. Yushin, Y. Gogotsi, C. Portet, P. Simon and P.L.Taberna, *Science*, 2006, **313**, 1760.
- 80 4 T.A. Centeno, O. Sereda and F. Stoeckli, *Phys. Chem. Chem. Phys.*, 2011, **13**, 12403.
- 5 T.A. Centeno and F. Stoeckli, *Electrochim. Acta*, 2011, **56**, 7334.
- 6 F. Stoeckli and T.A. Centeno, *Phys. Chem. Chem. Phys.*, 2012, **14**, 11589.
- 85 7 T.A. Centeno and F. Stoeckli, *Electrochem. Comm.*, 2012, **16**, 34.
- 8 Z. Feng, R. Xue and X. Shao, *Electrochim. Acta*, 2010, **55**, 7334.
- 9 D Jiang, Z. Jin, D. Henderson, and J. Wu, *J. Phys. Chem. Lett.*, 2012, **3**, 1727
- 10 D. Jiang and J. Wu, *Nanoscale*, 2014, **6**, 5545.
- 90 11 G. Feng and P.T. Cummings, *J. Phys. Chem. Lett.*, 2011, **2**, 2859.
- 12 S. Kondrat, C.S. Pérez, V. Presser, Y. Gogotsi and A.A. Kornyshev, *Energy Environ. Sci.*, 2012, **5**, 6474.
- 13 W. Gu and G.Yushin, *WIREs Energy Environ*, 2014, **3**, 424.
- 14 T. Ohba and K. Kaneko, *J. Phys. Chem. C*, 2013, **117**, 17092.
- 95 15 G. Hasegawa, K. Kanamori, K. Nakanishi, and T. Abe, *J. Phys. Chem. C*, 2012, **116**, 26197.
- 16 A. Garcia-Gomez, V. Barranco, G. Moreno-Fernandez, J. Ibáñez, T. A. Centeno and J. M. Rojo, *J. Phys. Chem. C*, 2014, **118**, 5134.
- 17 F. Stoeckli, in Porosity in carbons. Characterization and applications, (Ed: J. Patrick), Arnold, London, 1995, pp. 67-92.
- 100 18 T.A. Centeno, J.A. Fernández and F. Stoeckli, *Carbon*, 2008, **46**, 1025.
- 19 J. Huang, B.G. Sumpter and V. Meunier, *Chem. Eur. J.*, 2008, **14**, 6614.
- 105 20 T.A. Centeno and F. Stoeckli, *Carbon*, 1997, **35**, 1097.