



**Synthesis and Characterization of Metal-Rich Phosphonium  
Polyelectrolytes and Their Use as Precursors to  
Nanomaterials**


Journal:	<i>Dalton Transactions</i>
Manuscript ID	DT-ART-06-2016-002541.R2
Article Type:	Paper
Date Submitted by the Author:	22-Sep-2016
Complete List of Authors:	Rabiee Kenaree, Amir; The University of Western Ontario, Department of Chemistry Gilroy, Joe; The University of Western Ontario, Department of Chemistry

# Synthesis and Characterization of Metal-Rich Phosphonium Polyelectrolytes and Their Use as Precursors to Nanomaterials

*Amir Rabiee Kenaree and Joe B. Gilroy\**

Department of Chemistry and the Centre for Advanced Materials and Biomaterials Research  
(CAMBR), The University of Western Ontario, 1151 Richmond St. N., London, Ontario,  
Canada, N6A 5B7. Tel: +1-519-661-2111 ext. 81561; E-mail: joe.gilroy@uwo.ca.

## Graphical Abstract:



A unique family of polyelectrolytes with four different stoichiometric Fe/Ru ratios were prepared and characterized. Pyrolysis in a reducing atmosphere led to crystalline, mixed phase nanomaterials containing iron, ruthenium, and phosphorus with compositions influenced by the structure of the parent polyelectrolytes.

**Abstract:** Upon efficient quaternization and salt metathesis of stable triethyl ferrocene/ruthenocene phosphines, styrene-based phosphonium triflate monomers with four different stoichiometric ratios of Fe/Ru were synthesized. Free-radical polymerization of the monomers afforded four polyelectrolytes ( $M_n$ : 38,650–69,100 g mol<sup>-1</sup>,  $D$ : 3.16–4.10) that retained many of the spectroscopic and electrochemical properties of the ferrocene/ruthenocene units. TGA studies demonstrated the thermal stability (onset of decomposition: ~310 °C) and high char yields (33–54% at 1000 °C) of the polyelectrolytes. Pyrolysis in N<sub>2</sub>/H<sub>2</sub> (95/5) (film thickness of ~6 μm, 1000 °C, 3h) yielded crystalline, mixed-phase nanomaterials containing iron, ruthenium, and phosphorus with compositions influenced by the structure of the parent polyelectrolytes.

## Introduction


Metallopolymers, which differ from coordination polymers that have dynamic structures, are an intriguing class of materials that benefit from the processability of macromolecules and functional properties of transition metals.<sup>1</sup> To date, many metallopolymers have been successfully synthesized and utilized as redox-active, catalytic, emissive, biomedical, and magnetic materials.<sup>2</sup> However, examples of heterobimetallic polymers, which can take advantage of the properties of more than one type of metal, are far less common.

There are several existing strategies for the incorporation of more than one type of transition metal into polymer structures. For example, post-polymerization functionalization of metallopolymers can be employed for the addition of transition metals to the repeating unit of the polymer backbone.<sup>3</sup> However, it can be a challenge to completely functionalize all of the repeating units in the polymer backbone. Manners and co-workers have used their well-

established ring-opening polymerization methodology for the synthesis of polyferrocenylsilanes (PFS) to prepare monometallic acetylide-substituted PFSs, which were further reacted with  $\text{Co}_2(\text{CO})_8$ ,  $[\text{MoCp}(\text{CO})_2]_2$ , and  $[\text{NiCp}(\text{CO})_2]_2$  to produce heterobimetallic polymers **1**.<sup>3a-c</sup> They also showed that reactive ion etching (RIE),<sup>3a</sup> electron-beam lithography,<sup>3b</sup> and pyrolysis<sup>3c</sup> can be used to convert the heterobimetallic polymers produced to the corresponding bimetallic alloy nanoparticles (NPs).

Copolymerization of more than one type of metal-containing monomer is another strategy that can yield heterobimetallic polymers, where the metal ratio can be adjusted by controlling the ratio of the repeating units.<sup>4</sup> Following this strategy and starting with two methacrylate-based ferrocene- and cobaltocenium-containing monomers, the Tang group recently performed a reversible addition-fragmentation chain-transfer (RAFT) polymerization and successfully synthesized heterobimetallic diblock copolymers containing cobaltocenium and ferrocene units **2**. By pyrolysis of the heterobimetallic copolymer under  $\text{N}_2/\text{H}_2$ , magnetic nanomaterials comprised of  $\text{Fe}_x\text{Co}_y\text{P}$  (where  $x+y=2$ ) were realized.<sup>4e</sup>

Starting with a monomer that has more than one metal within its structure is a strategy that affords heterobimetallic polymers with transition metal content equal to that of the monomer.<sup>5</sup> For instance, Wong and co-workers synthesized an iron- and platinum-containing heterobimetallic polymer and used nanoimprint lithography to generate nanopatterns of the resulting polymer **3**. RIE converted the polymer to nanopatterned magnetic Fe/Pt NPs.<sup>5c</sup> The Manners group has also reported the synthesis of a palladium-based [1]ferrocenophane **4** that was thermolized at 190 °C under vacuum to directly yield Fe/Pd alloy NPs, presumably via a heterobimetallic polymer.<sup>5e</sup>



Bimetallic particles are an interesting subclass of nanomaterials that benefit from their high surface area.<sup>6</sup> For example, Fe/Ru heterobimetallic particles are industrially valuable materials due to their catalytic role in processes including hydrogenation,<sup>7</sup> the water-gas shift reaction,<sup>8</sup> and the Fischer-Tropsch synthesis.<sup>9</sup> They are conventionally prepared by techniques such as thermolysis and co-reduction of metal ions.<sup>10</sup> Although, metallopolymers can serve as precursors to metal-containing nanomaterials,<sup>11</sup> few reports of the generation of bimetallic nanomaterials from heterobimetallic polymers have been made. To the best of our knowledge Fe/Ru nanomaterials have not been prepared via the degradation of heterobimetallic polymers.

Herein, we describe our efforts to address this deficiency. Specifically, we have prepared polyelectrolytes based on phosphonium scaffolds containing ethylferrocene and ethylruthenocene units (Fe/Ru: 3/0, 2/1, 1/2, 0/3) and explored their preceramic properties by conducting pyrolysis experiments under a reducing atmosphere.

## Experimental section

### General considerations

Reactions and manipulations were carried out under a nitrogen atmosphere using standard glove box or Schlenk techniques unless otherwise stated. Solvents were obtained from Caledon Laboratories and Fischer Scientific, dried using an Innovative Technologies Inc. solvent purification system, collected under vacuum, and stored under a nitrogen atmosphere over 4 Å molecular sieves. Reagents were purchased from Sigma-Aldrich or Alfa Aesar and used as received, aside from 4-vinylbenzyl chloride which was purified according to a literature procedure and stored under N<sub>2</sub> at -35 °C.<sup>12</sup> Tertiary phosphines **5a–d** were synthesized according to reported protocols.<sup>13</sup> <sup>1</sup>H, <sup>13</sup>C, <sup>19</sup>F and <sup>31</sup>P NMR spectra were recorded on a 600 MHz (<sup>1</sup>H: 599.5 MHz, <sup>13</sup>C: 150.8 MHz, <sup>19</sup>F: 563.9 MHz and <sup>31</sup>P: 242.6 MHz) Varian INOVA instrument. <sup>1</sup>H NMR spectra were referenced to residual (CD<sub>3</sub>)(CD<sub>2</sub>H)SO (2.50 ppm) and <sup>13</sup>C NMR spectra were referenced to DMSO-*d*<sub>6</sub> (39.5 ppm). <sup>31</sup>P NMR spectra were referenced to PPh<sub>3</sub> as an internal standard (-6.0 ppm relative to H<sub>3</sub>PO<sub>4</sub>). Mass spectrometry data were recorded in positive-ion mode using a Micromass/Waters Q-TOF Ultima LC-MS/MS system. UV-vis absorption spectra were recorded using a Cary 300 Scan instrument. Infrared spectra were recorded using a PerkinElmer Spectrum Two FT-IR spectrometer as thin films on KBr plates. Elemental analyses (C and H) were carried out by Laboratoire d'Analyse Élémentaire de l'Université de Montréal, Montréal, QC, Canada.

### Cyclic voltammetry

Cyclic voltammograms were collected using a Bioanalytical Systems Inc. (BASi) Epsilon potentiostat and analyzed using BASi Epsilon software. Typical electrochemical cells consisted of a three-electrode setup including a glassy carbon working electrode, platinum wire counter

electrode, and silver wire *pseudo*-reference electrode. 1 mM degassed solutions of monomers **7a–d**, combined with supporting electrolyte (0.1 M [*n*-Bu<sub>4</sub>N][OTf]), in a CH<sub>2</sub>Cl<sub>2</sub>/CH<sub>3</sub>CN (2/1) solvent mixture were prepared and run at a scan rate of 250 mV s<sup>-1</sup> under a blanket of argon. To study the electrochemical behavior of the polymers, different solvents such as THF, DMF, CH<sub>3</sub>CN, and CH<sub>2</sub>Cl<sub>2</sub> containing 0.1 M [*n*-Bu<sub>4</sub>N][OTf] were used to make 0.2 mM solutions of the analytes. In each case, severe plating of the oxidized forms of **8a–d** was observed on the glassy carbon working electrode. Therefore, a 2/1 solvent mixture of CH<sub>2</sub>Cl<sub>2</sub> and CH<sub>3</sub>CN was used as it was the least problematic combination. Degassed solutions of polyelectrolytes **8a–d** in a CH<sub>2</sub>Cl<sub>2</sub>/CH<sub>3</sub>CN (2/1) solvent mixture were prepared by stirring the mixture overnight at 40 °C. After addition of the supporting electrolyte, the mixtures were sonicated for 20 s, filtered (Nylon membrane, 0.22 μm) and using these solutions electrochemical studies were performed at a scan rate of 250 mV s<sup>-1</sup> under a blanket of argon. Cyclic voltammograms were referenced relative to a decamethylferrocene internal standard (1 mM, -520 mV relative to ferrocene/ferrocenium under identical conditions) and corrected for internal cell resistance using the BASi Epsilon software.

### **X-ray diffraction studies**

Single crystals of monomer **7a** suitable for X-ray diffraction studies were grown by slow evaporation of a THF solution. The sample was mounted on a MiTeGen polyimide micromount with a small amount of Paratone N oil. X-ray diffraction measurements were made on a Bruker Kappa Axis Apex2 diffractometer at a temperature of 110 K. Initial indexing indicated that the sample crystal was non-merohedrally twinned. The twin law was determined to be:

0.99635	0.00646	0.00848
0.00835	-1.00086	0.00433
0.85236	-0.00198	-0.99547

which represents a  $179.8^\circ$  rotation about [100]. The twin fraction was included in the refinement as an adjustable parameter (*vide infra*). The unit cell dimensions were determined from a symmetry constrained fit of 5386 reflections with  $6.58^\circ < 2\theta < 47.88^\circ$ . The data collection strategy was a number of  $\omega$  and  $\phi$  scans which collected data up to  $53.538^\circ$  ( $2\theta$ ). The frame integration was performed using SAINT.<sup>14</sup> The resulting raw data was scaled and absorption corrected using a multi-scan averaging of symmetry equivalent data using TWINABS.<sup>15</sup>

The structure was solved by using a dual space methodology using the SHELXT program.<sup>16</sup> All non-hydrogen atoms were obtained from the initial solution. The hydrogen atoms were introduced at idealized positions and were allowed to ride on the parent atom. The twin fraction refined to a value of 0.465(1). The structural model was fit to the data using full matrix least-squares based on  $F^2$ . The calculated structure factors included corrections for anomalous dispersion from the usual tabulation. The structure was refined using the SHELXL-2014 program from the SHELX suite of crystallographic software.<sup>17</sup> Graphic plots were produced using Mercury software (version 3.3). For additional collection and refinement details, see CCDC 1476067, Table 1 and Fig. 1.

Powder X-ray diffraction (PXRD) data for nanomaterial films deposited on silicon wafers were acquired using an Inel CPS powder diffractometer with an Inel XRG 3000 generator and Inel CPS 120 detector using a  $\text{CuK}\alpha$  radiation source. For diffractograms, see Fig. 5 and S36–S39.



**Table 1** Selected X-ray diffraction data collection and refinement details for **7a**.

<b>7a</b>	
Chemical formula	C <sub>46</sub> H <sub>48</sub> F <sub>3</sub> Fe <sub>3</sub> O <sub>3</sub> PS
FW (g mol <sup>-1</sup> )	936.42
Temp (K)	110
Crystal syst.	Triclinic
Crystal habit	yellow Plate
Space group	P -1
$\lambda$ (Å)	0.71073
a (Å)	12.378(6)
b (Å)	12.619(5)
c (Å)	14.252(7)
$\alpha$ (deg)	79.298(7)
$\beta$ (deg)	68.524(10)
$\gamma$ (deg)	89.953(7)
V (Å <sup>3</sup> )	2030.1(17)
Z	2
$\rho$ (g cm <sup>-3</sup> )	1.532
$\mu$ (cm <sup>-1</sup> )	1.204
R <sub>1</sub> [I > 2 $\sigma$ (I)]	0.0534
wR <sub>2</sub> [I > 2 $\sigma$ (I)]	0.1278
R <sub>1</sub> (all data)	0.0917
wR <sub>2</sub> (all data)	0.1463
GOF	1.042

$R_1 = \Sigma(|F_o| - |F_c|) / \Sigma F_o$ ,  $wR_2 = [\Sigma(w(F_o^2 - F_c^2)^2) / \Sigma(wF_o^4)]^{1/2}$ ;  $GOF = [\Sigma(w(F_o^2 - F_c^2)^2) / (\text{No. of reflns.} - \text{No. of params.})]^{1/2}$ .

### Gel permeation chromatography (GPC)

GPC experiments were performed by PolyAnalytik Inc. Canada (London, Ontario). Molecular weights and dispersities ( $D = M_w / M_n$ ) were obtained using a Viscotek TDA302/GPCmax gel permeation chromatograph equipped with automatic sampler, isocratic pump, injector, in-line degasser, column and detector oven (60 °C), refractive index detector, and Viscotek Inert Series Columns: 1 × Mixed Bed Low Molecular Weight (I-MBLMW, exclusion limit of 20 kDa PS) and 1 × Mixed Bed High Molecular Weight (I-MBHMW, exclusion limit of 10,000 kDa PS). The eluent employed was DMF (60 °C) containing 0.02 M [*n*-Bu<sub>4</sub>N][OTf] at a flow rate of 0.7 mL min<sup>-1</sup>. Samples were dissolved in the eluent (5 mg mL<sup>-1</sup>), heated for 1.5 h, and filtered

(Nylon membrane, 0.22  $\mu\text{m}$ ) before analysis. Conventional calibration of the refractive index detector was performed using a series of monodisperse polystyrene standards (PolyAnalytik). All data were processed using Viscotek's OmniSEC v4.6.2 software.

### **Thermal analysis**

Thermal degradation studies were performed using a TA Instruments Q50 TGA instrument under an atmosphere of  $\text{N}_2$ . Samples were placed in a platinum pan and heated at a rate of  $10\text{ }^\circ\text{C min}^{-1}$  from  $20\text{ }^\circ\text{C}$  to  $1000\text{ }^\circ\text{C}$  under a flow of  $\text{N}_2$  ( $60\text{ mL min}^{-1}$ ). Glass transition temperatures were determined under an atmosphere of  $\text{N}_2$  using differential scanning calorimetry (DSC) on a TA Instruments DSC Q20. The polymer samples were placed in an aluminum Tzero pan and heated from room temperature to  $300\text{ }^\circ\text{C}$  at  $10\text{ }^\circ\text{C min}^{-1}$  under a flow of  $\text{N}_2$  ( $50\text{ mL min}^{-1}$ ) and cooled down to  $0\text{ }^\circ\text{C}$  at  $5\text{ }^\circ\text{C min}^{-1}$ , before they underwent two more heat/cool cycles. The glass transitions were determined from the second heat/cool cycle.

### **Pyrolysis studies and scanning electron microscopy**

Films of polyelectrolytes **8a–d** were prepared by drop-casting  $250\text{ }\mu\text{L}$  of a  $20\text{ mg mL}^{-1}$  chlorobenzene solution of each polyelectrolyte onto a silicon wafer ( $A = 2.5\text{ cm}^2$ ). The samples were dried in air, transferred into a vacuum oven, and allowed to dry at  $50\text{ }^\circ\text{C}$  for 16 h before they were heated at a rate of  $10\text{ }^\circ\text{C min}^{-1}$  to a temperature of  $1000\text{ }^\circ\text{C}$  under a gentle flow (*ca.*  $60\text{ mL min}^{-1}$ ) of a  $\text{N}_2/\text{H}_2$  (95/5) gas mixture in a Lindberg Blue M tube furnace. The temperature was maintained at  $1000\text{ }^\circ\text{C}$  for an additional 3 h before the furnace was cooled to room temperature at a rate of  $10\text{ }^\circ\text{C min}^{-1}$ . Polymer film thickness and the surface morphologies of thermally deposited nanomaterials on silicon wafers were assessed directly using scanning electron microscopy (SEM) at 1 keV beam energy using LEO/Zeiss 1530 and LEO/Zeiss 1540XB instruments. Energy dispersive X-ray spectroscopy (EDX) experiments were performed

at 10 keV beam energy on the 1540XB with the equipped Oxford X-sight X-ray detector and INCA analysis software.

### Representative procedure for the preparation of 6a–d

#### Phosphonium chloride salt 6a (3 × Fc)

In a sealed tube, tertiary phosphine **5a** (1.00 g, 1.49 mmol) and 4-vinylbenzyl chloride (230  $\mu$ L, 1.63 mmol, 1.1 equiv.) were combined with DMF/THF (5/1, 12 mL) before the mixture was heated for 1 h at 75 °C. After cooling to room temperature, the flask was opened to air and the phosphonium chloride salt was extracted with  $\text{CHCl}_3$  (3  $\times$  40 mL), washed with  $\text{H}_2\text{O}$  (5  $\times$  20 mL), dried over  $\text{MgSO}_4$ , and concentrated *in vacuo*. The resulting oily orange residue was then dissolved in a minimum amount of  $\text{CH}_2\text{Cl}_2$  and precipitated into pentane. The resulting yellow powder was isolated by centrifugation before it was again dissolved, precipitated, and filtered to yield **6a** as an orange powder. Yield = 1.20 g, 98%. M.p. 74–76 °C.  $^1\text{H}$  NMR ( $\text{DMSO}-d_6$ ):  $\delta$  7.59 (d,  $^3J_{\text{HH}} = 8$  Hz, 2H, aryl CH), 7.46 (dd,  $^3J_{\text{HH}} = 8$  Hz,  $^5J_{\text{HP}} = 2$  Hz, 2H, aryl CH), 6.74 (dd,  $^3J_{\text{HH},\text{cis}} = 11$  Hz,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.86 (d,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.26 (d,  $^3J_{\text{HH},\text{cis}} = 11$  Hz, 1H, ArCH=CH<sub>2</sub>), 4.17 (*pseudo-t*,  $^3J_{\text{HH}} = 2$  Hz, 6H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R), 4.12 (s, 15H, C<sub>5</sub>H<sub>5</sub>), 4.10 (*pseudo-t*,  $^3J_{\text{HH}} = 2$  Hz, 6H,  $\alpha$ -C<sub>5</sub>H<sub>4</sub>R), 4.06 (d,  $^2J_{\text{HP}} = 15$  Hz, 2H, PCH<sub>2</sub>Ar), 2.59–2.43 (m, 12H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub> and C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>, overlaps with residual CD<sub>3</sub>CD<sub>2</sub>HSO signal).  $^{13}\text{C}\{^1\text{H}\}$  NMR ( $\text{DMSO}-d_6$ ):  $\delta$  137.0 (d,  $J_{\text{CP}} = 3$  Hz), 135.9 (d,  $J_{\text{CP}} = 2$  Hz), 130.4 (d,  $J_{\text{CP}} = 6$  Hz), 128.8 (d,  $J_{\text{CP}} = 8$  Hz), 127.0 (d,  $J_{\text{CP}} = 3$  Hz), 115.1 (s), 86.8 (d,  $J_{\text{CP}} = 17$  Hz), 68.5 (s), 67.7 (s), 67.4 (s), 25.4 (d,  $J_{\text{CP}} = 43$  Hz), 20.8 (d,  $J_{\text{CP}} = 2$  Hz), 19.3 (d,  $J_{\text{CP}} = 44$  Hz).  $^{31}\text{P}\{^1\text{H}\}$  NMR ( $\text{DMSO}-d_6$ ):  $\delta$  31.1 (s). FT-IR: 3092 (w), 3009 (w), 2922 (m), 2455 (w), 1629 (w), 1511 (w), 1410 (w), 1219 (w), 1105 (m), 1000 (m), 922 (w), 820 (m), 753 (s), 660 (w)  $\text{cm}^{-1}$ . UV-vis (THF):  $\lambda_{\text{max}}$  285 nm ( $\epsilon = 2,620 \text{ M}^{-1} \text{ cm}^{-1}$ ), 295 nm ( $\epsilon = 1,380 \text{ M}^{-1} \text{ cm}^{-1}$ ), 325 nm ( $\epsilon = 290 \text{ M}^{-1}$

$\text{cm}^{-1}$ ), 436 nm ( $\epsilon = 300 \text{ M}^{-1} \text{ cm}^{-1}$ ). Mass Spec. (ESI, +ve mode): exact mass calculated for  $[\text{C}_{45}\text{H}_{48}^{56}\text{Fe}_3\text{P}]^+$ : 787.1542; exact mass found: 787.1563; difference: +2.7 ppm.

### Phosponium chloride salt **6b** (2 × Fc, 1 × Rc)

From tertiary phosphine **5b** (1.00 g, 1.40 mmol) and 4-vinylbenzyl chloride (217  $\mu\text{L}$ , 1.54 mmol, 1.1 equiv.). Yield = 1.16 g, 96%. M.p. 80–82 °C.  $^1\text{H}$  NMR (DMSO- $d_6$ ):  $\delta$  7.62 (d,  $^3J_{\text{HH}} = 8$  Hz, 2H, aryl CH), 7.48 (dd,  $^3J_{\text{HH}} = 7$  Hz,  $^5J_{\text{HP}} = 2$  Hz, 2H, aryl CH), 6.78 (dd,  $^3J_{\text{HH},\text{cis}} = 11$  Hz,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.90 (d,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.30 (d,  $^3J_{\text{HH},\text{cis}} = 11$  Hz, 1H, ArCH=CH<sub>2</sub>), 4.65 [s, 2H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R(Ru)], 4.57 [s, 5H, C<sub>5</sub>H<sub>5</sub>(Ru)], 4.51 [s, 2H,  $\alpha$ -C<sub>5</sub>H<sub>5</sub>R(Ru)], 4.21 [s, 4H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R(Fe)], 4.16 [s, 10H, C<sub>5</sub>H<sub>5</sub>(Fe)], 4.13 [s, 4H,  $\alpha$ -C<sub>5</sub>H<sub>5</sub>R(Fe)], 4.10 (d,  $^2J_{\text{HP}} = 16$  Hz, 2H, PCH<sub>2</sub>Ar), 2.65–2.30 (m, 12H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub> and C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>, overlaps with residual CD<sub>3</sub>CD<sub>2</sub>HSO signal).  $^{13}\text{C}\{^1\text{H}\}$  NMR (DMSO- $d_6$ ):  $\delta$  137.0 (d,  $J_{\text{CP}} = 3$  Hz), 135.9 (s), 130.4 (d,  $J_{\text{CP}} = 5$  Hz), 128.8 (d,  $J_{\text{CP}} = 9$  Hz), 126.9 (d,  $J_{\text{CP}} = 3$  Hz), 115.1 (s), 91.2 (d,  $J_{\text{CP}} = 18$  Hz), 86.8 (d,  $J_{\text{CP}} = 17$  Hz), 70.6 (s), 70.4 (s), 69.6 (s), 68.4 (s), 67.7 (s), 67.3 (s), 25.3 (d,  $J_{\text{CP}} = 43$  Hz), 20.8 (s), 20.2 (s), 20.0 (d,  $J_{\text{CP}} = 45$  Hz), 19.3 (d,  $J_{\text{CP}} = 45$  Hz).  $^{31}\text{P}\{^1\text{H}\}$  NMR (DMSO- $d_6$ ):  $\delta$  30.9 (s). FT-IR: 3091 (w), 3008 (w), 2922 (m), 2455 (w), 1629 (w), 1511 (w), 1410 (w), 1221 (w), 1104 (m), 999 (m), 918 (w), 811 (m), 753 (s), 661 (w)  $\text{cm}^{-1}$ . UV-vis (THF):  $\lambda_{\text{max}}$  287 nm ( $\epsilon = 2,170 \text{ M}^{-1} \text{ cm}^{-1}$ ), 295 nm ( $\epsilon = 1,290 \text{ M}^{-1} \text{ cm}^{-1}$ ), 320 nm ( $\epsilon = 420 \text{ M}^{-1} \text{ cm}^{-1}$ ), 431 nm ( $\epsilon = 220 \text{ M}^{-1} \text{ cm}^{-1}$ ). Mass Spec. (ESI, +ve mode): exact mass calculated for  $[\text{C}_{45}\text{H}_{48}^{56}\text{Fe}_2\text{P}^{102}\text{Ru}]^+$ : 833.1236; exact mass found: 833.1259; difference: +2.8 ppm.

### Phosponium chloride salt **6c** (1 × Fc, 2 × Rc)

From tertiary phosphine **5c** (1.00 g, 1.32 mmol) and 4-vinylbenzyl chloride (204  $\mu\text{L}$ , 1.45 mmol, 1.1 equiv.). Yield = 1.14 g, 95%. M.p. 84–86 °C.  $^1\text{H}$  NMR (DMSO- $d_6$ ):  $\delta$  7.62 (d,  $^3J_{\text{HH}} = 8$  Hz, 2H, aryl CH), 7.44 (dd,  $^3J_{\text{HH}} = 7$  Hz,  $^5J_{\text{HP}} = 2$  Hz, 2H, aryl CH), 6.78 (dd,  $^3J_{\text{HH},\text{cis}} = 11$  Hz,

$^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.92 (d,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.31 (d,  $^3J_{\text{HH},\text{cis}} = 11$  Hz, 1H, ArCH=CH<sub>2</sub>), 4.65 [s, 4H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R(Ru)], 4.56 [s, 10H, C<sub>5</sub>H<sub>5</sub>(Ru)], 4.52 [s, 4H,  $\alpha$ -C<sub>5</sub>H<sub>5</sub>R(Ru)], 4.21 [*pseudo*-t,  $^3J_{\text{HH}} = 2$  Hz, 2H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R(Fe)], 4.16 [s, 5H, C<sub>5</sub>H<sub>5</sub>(Fe)], 4.14 [*pseudo*-t,  $^3J_{\text{HH}} = 2$  Hz, 2H,  $\alpha$ -C<sub>5</sub>H<sub>5</sub>R(Fe)], 4.06 (d,  $^2J_{\text{HP}} = 16$  Hz, 2H, PCH<sub>2</sub>Ar), 2.60–2.30 (m, 12H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub> and C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>, overlaps with residual CD<sub>3</sub>CD<sub>2</sub>HSO signal). <sup>13</sup>C{<sup>1</sup>H} NMR (DMSO-*d*<sub>6</sub>):  $\delta$  137.0 (d,  $J_{\text{CP}} = 5$  Hz), 135.9 (s), 130.3 (d,  $J_{\text{CP}} = 5$  Hz), 128.7 (d,  $J_{\text{CP}} = 9$  Hz), 126.9 (d,  $J_{\text{CP}} = 3$  Hz), 115.1 (s), 91.1 (d,  $J_{\text{CP}} = 17$  Hz), 86.7 (d,  $J_{\text{CP}} = 17$  Hz), 70.6 (s), 70.4 (s), 69.7 (s), 68.4 (s), 67.7 (s), 67.4 (s), 25.3 (d,  $J_{\text{CP}} = 43$  Hz), 20.8 (s), 20.3 (d,  $J_{\text{CP}} = 3$  Hz), 20.0 (d,  $J_{\text{CP}} = 44$  Hz), 19.3 (d,  $J_{\text{CP}} = 45$  Hz). <sup>31</sup>P{<sup>1</sup>H} NMR (DMSO-*d*<sub>6</sub>):  $\delta$  30.8 (s). FT-IR: 3095 (w), 3010 (w), 2923 (m), 2455 (w), 1630 (w), 1511 (w), 1409 (w), 1219 (w), 1101 (m), 998 (m), 918 (w), 810 (m), 753 (s), 666 (w) cm<sup>-1</sup>. UV-vis (THF):  $\lambda_{\text{max}}$  287 nm ( $\epsilon = 2,520$  M<sup>-1</sup> cm<sup>-1</sup>), 295 nm ( $\epsilon = 1,600$  M<sup>-1</sup> cm<sup>-1</sup>), 320 nm ( $\epsilon = 680$  M<sup>-1</sup> cm<sup>-1</sup>), 434 nm ( $\epsilon = 150$  M<sup>-1</sup> cm<sup>-1</sup>). Mass Spec. (ESI, +ve mode): exact mass calculated for [C<sub>45</sub>H<sub>48</sub><sup>56</sup>FeP<sup>96</sup>Ru<sup>99</sup>Ru]<sup>+</sup>: 870.0978; exact mass found: 870.1002; difference: +2.8 ppm.

### Phosphonium chloride salt **6d** (3 × **Rc**)

From tertiary phosphine **5d** (1.00 g, 1.24 mmol) and 4-vinylbenzyl chloride (192  $\mu$ L, 1.36 mmol, 1.1 eq). Yield = 1.12 g, 94%. M.p. 102–104 °C. <sup>1</sup>H NMR (DMSO-*d*<sub>6</sub>):  $\delta$  7.62 (d,  $^3J_{\text{HH}} = 8$  Hz, 2H, aryl CH), 7.40 (dd,  $^3J_{\text{HH}} = 8$  Hz,  $^5J_{\text{HP}} = 2$  Hz, 2H, aryl CH), 6.77 (dd,  $^3J_{\text{HH},\text{cis}} = 11$  Hz,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.90 (d,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.31 (d,  $^3J_{\text{HH},\text{cis}} = 11$  Hz, 1H, ArCH=CH<sub>2</sub>), 4.64 (*pseudo*-t,  $^3J_{\text{HH}} = 2$  Hz, 6H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R), 4.55 (s, 15H, C<sub>5</sub>H<sub>5</sub>), 4.51 (*pseudo*-t,  $^3J_{\text{HH}} = 2$  Hz, 6H,  $\alpha$ -C<sub>5</sub>H<sub>4</sub>R), 3.98 (d,  $^2J_{\text{HP}} = 15$  Hz, 2H, PCH<sub>2</sub>Ar), 2.27–2.47 (m, 12H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub> and C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>). <sup>13</sup>C{<sup>1</sup>H} NMR (DMSO-*d*<sub>6</sub>):  $\delta$  137.1 (d,  $J_{\text{CP}} = 3$  Hz), 135.9 (s), 130.3 (d,  $J_{\text{CP}} = 5$  Hz), 128.6 (d,  $J_{\text{CP}} = 9$  Hz), 127.0 (s), 115.3 (s), 91.1 (d,  $J_{\text{CP}} = 18$  Hz), 70.6 (s),

70.5 (s), 69.8 (s), 25.4 (d,  $J_{CP} = 44$  Hz), 20.4 (s), 20.0 (d,  $J_{CP} = 45$  Hz).  $^{31}\text{P}\{^1\text{H}\}$  NMR (DMSO- $d_6$ ):  $\delta$  30.8 (s). FT-IR: 3093 (w), 3010 (w), 2919 (m), 2460 (w), 1670 (w), 1511 (w), 1409 (m), 1218 (w), 1100 (m), 997 (m), 917 (w), 809 (s), 752 (s), 660 (w)  $\text{cm}^{-1}$ . UV-vis (THF):  $\lambda_{\text{max}}$  287 nm ( $\epsilon = 2,060 \text{ M}^{-1} \text{ cm}^{-1}$ ), 297 nm ( $\epsilon = 1,560 \text{ M}^{-1} \text{ cm}^{-1}$ ), 315 nm ( $\epsilon = 890 \text{ M}^{-1} \text{ cm}^{-1}$ ). Mass Spec. (ESI, +ve mode): exact mass calculated for  $[\text{C}_{45}\text{H}_{48}^{96}\text{Ru}^{99}\text{Ru}^{100}\text{RuP}]^+$ : 914.0671; exact mass found: 914.0678; difference: +0.8 ppm.

### Representative procedure for the preparation of phosphonium salts 7a–d

#### Phosphonium triflate salt 7a (3 × Fc)

In a Schlenk flask, **6a** (1.00 g, 1.22 mmol) was dissolved in dry and degassed  $\text{CHCl}_3$  (10 mL) before NaOTf (0.63 g, 3.6 mmol, 3 equiv.) was charged into the reaction flask. The resulting mixture was allowed to stir at 20 °C for 16 h, gravity filtered to remove precipitate, washed with  $\text{H}_2\text{O}$  (3 × 10 mL), dried over  $\text{MgSO}_4$ , and gravity filtered. NaOTf (0.21 g, 1.2 mmol, 1 equiv.) was once again charged into a flask containing the filtrate before the contents were allowed to stir for an additional 16 h. The reaction mixture was then gravity filtered to remove precipitate, washed with  $\text{H}_2\text{O}$  (3 × 10 mL), dried over  $\text{MgSO}_4$ , and gravity filtered before it was concentrated *in vacuo*. The resulting orange residue was then dried *in vacuo* for 2 h at 45 °C to remove residual solvent to afford monomer **7a** as an orange solid. Yield = 1.12 g, 98%. M.p. 66–68 °C.  $^1\text{H}$  NMR (DMSO- $d_6$ ):  $\delta$  7.61 (d,  $^3J_{\text{HH}} = 8$  Hz, 2H, aryl CH), 7.44 (dd,  $^3J_{\text{HH}} = 8$  Hz,  $^5J_{\text{HP}} = 2$  Hz, 2H, aryl CH), 6.76 (dd,  $^3J_{\text{HH},\text{cis}} = 11$  Hz,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.89 (d,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.29 (d,  $^3J_{\text{HH},\text{cis}} = 11$  Hz, 1H, ArCH=CH<sub>2</sub>), 4.19 (s, 6H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R), 4.14 (s, 15H, C<sub>5</sub>H<sub>5</sub>), 4.13 (s, 6H,  $\alpha$ -C<sub>5</sub>H<sub>4</sub>R), 3.96 (d,  $^2J_{\text{HP}} = 15$  Hz, 2H, PCH<sub>2</sub>Ar), 2.60–2.42 (m, 12H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub> and C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>, overlaps with residual CD<sub>3</sub>CD<sub>2</sub>HSO signal).  $^{13}\text{C}\{^1\text{H}\}$  NMR (DMSO- $d_6$ ):  $\delta$  137.1 (d,  $J_{CP} = 5$  Hz), 135.9 (s), 130.4 (d,  $J_{CP} = 3$  Hz), 128.6 (d,  $J_{CP} = 9$  Hz), 127.0

(s), 120.7 (q,  $J_{CF} = 322$  Hz), 115.2 (s), 86.8 (d,  $J_{CP} = 18$  Hz), 68.4 (s), 67.7 (s), 67.4 (s), 25.4 (d,  $J_{CP} = 44$  Hz), 20.8 (s), 19.2 (d,  $J_{CP} = 45$  Hz).  $^{19}\text{F}$  NMR (DMSO- $d_6$ ):  $\delta$  -77.6 (s).  $^{31}\text{P}\{^1\text{H}\}$  NMR (DMSO- $d_6$ ):  $\delta$  31.2 (s). FT-IR: 3095 (w), 3010 (w), 2913 (w), 1512 (w), 1410 (w), 1262 (s), 1157 (m), 1124 (w), 1105 (w), 1030 (s), 1000 (w), 922 (w), 821 (m), 754 (m), 637 (s)  $\text{cm}^{-1}$ . UV-vis (THF):  $\lambda_{\text{max}}$  285 nm ( $\epsilon = 2,470 \text{ M}^{-1} \text{ cm}^{-1}$ ), 295 nm ( $\epsilon = 1,290 \text{ M}^{-1} \text{ cm}^{-1}$ ), 325 nm ( $\epsilon = 260 \text{ M}^{-1} \text{ cm}^{-1}$ ), 436 nm ( $\epsilon = 320 \text{ M}^{-1} \text{ cm}^{-1}$ ). Mass Spec. (ESI, +ve mode): exact mass calculated for  $[\text{C}_{45}\text{H}_{48}^{56}\text{Fe}_3\text{P}]^+$ : 787.1542; exact mass found: 787.1564; difference: +2.7 ppm. Anal. Calcd. (%) for  $\text{C}_{46}\text{H}_{48}\text{F}_3\text{Fe}_3\text{O}_3\text{PS}$ : C, 59.00; H, 5.17. Found: C, 58.94; H, 5.37.

### Phosphonium triflate salt **7b** (2 $\times$ Fc, 1 $\times$ Rc)

From phosphonium chloride **6b** (1.00 g, 1.15 mmol) and NaOTf (0.60 g, 3.5 mmol, 3 equiv. for the first metathesis reaction and 0.20 g, 1.2 mmol, 1 equiv. for the second metathesis reaction). Yield = 1.11 g, 98%. M.p. 68–70 °C.  $^1\text{H}$  NMR (DMSO- $d_6$ ):  $\delta$  7.64 (d,  $^3J_{\text{HH}} = 8$  Hz, 2H, aryl CH), 7.44 (d,  $^3J_{\text{HH}} = 7$  Hz, 2H, aryl CH), 6.78 (dd,  $^3J_{\text{HH},\text{cis}} = 11$  Hz,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.91 (d,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.31 (d,  $^3J_{\text{HH},\text{cis}} = 11$  Hz, 1H, ArCH=CH<sub>2</sub>), 4.64 [s, 2H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R(Ru)], 4.56 [s, 5H, C<sub>5</sub>H<sub>5</sub>(Ru)], 4.52 [s, 2H,  $\alpha$ -C<sub>5</sub>H<sub>5</sub>R(Ru)], 4.20 [s, 4H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R(Fe)], 4.15 [s, 10H, C<sub>5</sub>H<sub>5</sub>(Fe)], 4.14 [s, 4H,  $\alpha$ -C<sub>5</sub>H<sub>5</sub>R(Fe)], 3.96 (d,  $^2J_{\text{HP}} = 15$  Hz, 2H, PCH<sub>2</sub>Ar), 2.57–2.32 (m, 12H, C<sub>3</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub> and C<sub>3</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>, overlaps with residual CD<sub>3</sub>CD<sub>2</sub>HSO signal).  $^{13}\text{C}\{^1\text{H}\}$  NMR (DMSO- $d_6$ ):  $\delta$  137.2 (d,  $J_{CP} = 3$  Hz), 135.9 (s), 130.4 (d,  $J_{CP} = 6$  Hz), 128.6 (d,  $J_{CP} = 9$  Hz), 127.1 (d,  $J_{CP} = 2$  Hz), 120.7 (q,  $J_{CF} = 322$  Hz), 115.3 (d,  $J_{CP} = 164$  Hz), 91.2 (d,  $J_{CP} = 18$  Hz), 86.8 (d,  $J_{CP} = 17$  Hz), 70.6 (s), 70.5 (s), 69.8 (s), 68.5 (s), 67.8 (s), 67.5 (s), 25.4 (d,  $J_{CP} = 43$  Hz), 20.9 (s), 20.3 (s), 20.1 (d,  $J_{CP} = 45$  Hz), 19.3 (d,  $J_{CP} = 45$  Hz).  $^{19}\text{F}$  NMR (DMSO- $d_6$ ):  $\delta$  -77.8 (s).  $^{31}\text{P}\{^1\text{H}\}$  NMR (DMSO- $d_6$ ):  $\delta$  31.0 (s). FT-IR: 3089 (w), 3011 (w), 2912 (w), 1630 (w), 1512 (w), 1410 (w), 1262 (s), 1224 (m), 1158 (m), 1104 (w), 1030 (s),

999 (w), 919 (w), 813 (m), 755 (s), 637 (s)  $\text{cm}^{-1}$ . UV-vis (THF):  $\lambda_{\text{max}}$  284 nm ( $\epsilon = 2,860 \text{ M}^{-1} \text{ cm}^{-1}$ ), 295 nm ( $\epsilon = 1,390 \text{ M}^{-1} \text{ cm}^{-1}$ ), 320 nm ( $\epsilon = 440 \text{ M}^{-1} \text{ cm}^{-1}$ ), 431 nm ( $\epsilon = 240 \text{ M}^{-1} \text{ cm}^{-1}$ ). Mass Spec. (ESI, +ve mode): exact mass calculated for  $[\text{C}_{45}\text{H}_{48}^{56}\text{Fe}_2\text{P}^{96}\text{Ru}]^+$ : 827.1268; exact mass found: 827.1274; difference: +0.7 ppm. Anal. Calcd. (%) for  $\text{C}_{46}\text{H}_{48}\text{F}_3\text{Fe}_2\text{O}_3\text{PRuS}$ : C, 56.28; H, 4.93. Found: C, 56.22; H, 5.11.

### Phosponium triflate salt **7c** (1 × Fc, 2 × Rc)

From phosphonium chloride **6c** (1.00 g, 1.10 mmol) and NaOTf (0.57 g, 3.3 mmol, 3 equiv. for the first metathesis reaction and 0.19 g, 1.1 mmol, 1 equiv. for the second metathesis reaction). Yield = 1.09 g, 97%. M.p. 70–72 °C.  $^1\text{H}$  NMR (DMSO- $d_6$ ):  $\delta$  7.64 (d,  $^3J_{\text{HH}} = 8$  Hz, 2H, aryl CH), 7.42 (d,  $^3J_{\text{HH}} = 8$  Hz, 2H, aryl CH), 6.78 (dd,  $^3J_{\text{HH},\text{cis}} = 11$  Hz,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.92 (d,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.32 (d,  $^3J_{\text{HH},\text{cis}} = 11$  Hz, 1H, ArCH=CH<sub>2</sub>), 4.65 [s, 4H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R(Ru)], 4.56 [s, 10H, C<sub>5</sub>H<sub>5</sub>(Ru)], 4.52 [s, 4H,  $\alpha$ -C<sub>5</sub>H<sub>5</sub>R(Ru)], 4.21 [s, 2H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R(Fe)], 4.16 [s, 5H, C<sub>5</sub>H<sub>5</sub>(Fe)], 4.15 [s, 2H,  $\alpha$ -C<sub>5</sub>H<sub>5</sub>R(Fe)], 3.96 (d,  $^2J_{\text{HP}} = 15$  Hz, 2H, PCH<sub>2</sub>Ar), 2.57–2.21 (m, 12H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub> and C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>, overlaps with residual CD<sub>3</sub>CD<sub>2</sub>HSO signal).  $^{13}\text{C}\{^1\text{H}\}$  NMR (DMSO- $d_6$ ):  $\delta$  137.1 (d,  $J_{\text{CP}} = 3$  Hz), 135.9 (s), 130.3 (d,  $J_{\text{CP}} = 5$  Hz), 128.5 (d,  $J_{\text{CP}} = 8$  Hz), 127.0 (d,  $J_{\text{CP}} = 2$  Hz), 115.2 (s), 91.0 (d,  $J_{\text{CP}} = 18$  Hz), 86.7 (d,  $J_{\text{CP}} = 17$  Hz), 70.6 (s), 70.4 (s), 69.7 (s), 68.4 (s), 67.6 (s), 67.4 (s), 25.3 (d,  $J_{\text{CP}} = 44$  Hz), 20.8 (s), 20.2 (s), 19.9 (d,  $J_{\text{CP}} = 45$  Hz), 19.2 (d,  $J_{\text{CP}} = 45$  Hz).  $^{19}\text{F}$  NMR (DMSO- $d_6$ ):  $\delta$  -77.7 (s).  $^{31}\text{P}\{^1\text{H}\}$  NMR (DMSO- $d_6$ ):  $\delta$  30.9 (s). FT-IR: 3093 (w), 3013 (w), 2911 (w), 1630 (w), 1512 (w), 1410 (w), 1262 (s), 1224 (s), 1159 (s), 1101 (m), 1030 (s), 998 (w), 918 (w), 811 (m), 756 (s), 637 (s)  $\text{cm}^{-1}$ . UV-vis (THF):  $\lambda_{\text{max}}$  283 nm ( $\epsilon = 3,260 \text{ M}^{-1} \text{ cm}^{-1}$ ), 295 nm ( $\epsilon = 1,770 \text{ M}^{-1} \text{ cm}^{-1}$ ), 320 nm ( $\epsilon = 730 \text{ M}^{-1} \text{ cm}^{-1}$ ), 434 nm ( $\epsilon = 140 \text{ M}^{-1} \text{ cm}^{-1}$ ). Mass Spec. (ESI, +ve mode): exact mass



calculated for  $[\text{C}_{45}\text{H}_{48}^{56}\text{FeP}^{96}\text{Ru}^{99}\text{Ru}]^+$ : 870.0978; exact mass found: 870.1000; difference: +2.5 ppm. Anal. Calcd. (%) for  $\text{C}_{46}\text{H}_{48}\text{F}_3\text{FeO}_3\text{PRu}_2\text{S}$ : C, 53.80; H, 4.71. Found: C, 53.94; H, 4.77.

### Phosphonium triflate salt **7d** (**3** × **Rc**)

From phosphonium chloride **6d** (1.00 g, 1.04 mmol) and NaOTf (0.54 g, 3.1 mmol, 3 equiv. for the first metathesis reaction and 0.18 g, 1.1 mmol, 1 equiv. for the second metathesis reaction). Yield = 1.07 g, 96%. M.p. 88–90 °C.  $^1\text{H}$  NMR (DMSO- $d_6$ ):  $\delta$  7.62 (d,  $^3J_{\text{HH}} = 8$  Hz, 2H, aryl CH), 7.38 (dd,  $^3J_{\text{HH}} = 8$  Hz,  $^5J_{\text{HP}} = 2$  Hz, 2H, aryl CH), 6.78 (dd,  $^3J_{\text{HH},\text{cis}} = 11$  Hz,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.92 (d,  $^3J_{\text{HH},\text{trans}} = 18$  Hz, 1H, ArCH=CH<sub>2</sub>), 5.32 (d,  $^3J_{\text{HH},\text{cis}} = 11$  Hz, 1H, ArCH=CH<sub>2</sub>), 4.64 (*pseudo-t*,  $^3J_{\text{HH}} = 2$  Hz, 6H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R), 4.56 (s, 15H, C<sub>5</sub>H<sub>5</sub>), 4.52 (*pseudo-t*,  $^3J_{\text{HH}} = 2$  Hz, 6H,  $\alpha$ -C<sub>5</sub>H<sub>4</sub>R), 3.94 (d,  $^2J_{\text{HP}} = 15$  Hz, 2H, PCH<sub>2</sub>Ar), 2.49–2.25 (m, 12H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub> and C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>).  $^{13}\text{C}\{^1\text{H}\}$  NMR (DMSO- $d_6$ ):  $\delta$  137.1 (s), 135.8 (s), 130.3 (s), 128.5 (d,  $J_{\text{CP}} = 8$  Hz), 127.0 (s), 120.6 (q,  $J_{\text{CF}} = 321$  Hz), 115.2 (s), 91.0 (d,  $J_{\text{CP}} = 17$  Hz), 70.6 (s), 70.4 (s), 69.7 (s), 25.3 (d,  $J_{\text{CP}} = 44$  Hz), 20.3 (s), 20.0 (d,  $J_{\text{CP}} = 45$  Hz).  $^{19}\text{F}$  NMR (DMSO- $d_6$ ):  $\delta$  -77.7 (s).  $^{31}\text{P}\{^1\text{H}\}$  NMR (DMSO- $d_6$ ):  $\delta$  30.8 (s). FT-IR: 3094 (w), 3013 (w), 2911 (w), 1630 (w), 1512 (w), 1409 (w), 1261 (s), 1159 (m), 1101 (w), 1030 (s), 997 (w), 917 (w), 810 (m), 755 (s), 637 (s)  $\text{cm}^{-1}$ . UV-vis (THF):  $\lambda_{\text{max}}$  286 nm ( $\epsilon = 1,970 \text{ M}^{-1} \text{ cm}^{-1}$ ), 296 nm ( $\epsilon = 1,510 \text{ M}^{-1} \text{ cm}^{-1}$ ), 315 nm ( $\epsilon = 910 \text{ M}^{-1} \text{ cm}^{-1}$ ). Mass Spec. (ESI, +ve mode): exact mass calculated for  $[\text{C}_{45}\text{H}_{48}^{96}\text{Ru}^{99}\text{Ru}^{100}\text{RuP}]^+$ : 914.0671; exact mass found: 914.0664; difference: -0.8 ppm. Anal. Calcd. (%) for  $\text{C}_{46}\text{H}_{48}\text{F}_3\text{O}_3\text{PRu}_3\text{S}$ : C, 51.53; H, 4.51. Found: C, 51.84; H, 4.62.

### Representative procedure for the preparation of polyelectrolytes **8a–d**

#### Polyelectrolyte **8a** (**3** × **Fc**)

In a grease-free Schlenk flask, monomer **7a** (0.25 g, 0.27 mmol) was dissolved in 1.00 mL of a THF stock solution containing AIBN (0.2 mg, 0.001 mmol). The resulting solution was degassed

during 3 freeze-pump-thaw cycles before the flask was sealed and the solution was allowed to stir at 85 °C for 16 h. After cooling to room temperature, the polymerization mixture was poured into diethyl ether and the solids were separated by centrifugation before they were collected, dissolved in a minimum amount of CH<sub>2</sub>Cl<sub>2</sub>, and precipitated in diethyl ether. This precipitation/centrifugation process was repeated once more in diethyl ether and pentane. The polyelectrolyte **8a** was dried *in vacuo* at 50 °C for 16 h to yield a yellow powder. Yield = 0.25 g, 98%. <sup>1</sup>H NMR (DMSO-*d*<sub>6</sub>, 125 °C): δ 6.94 (s, br, 2H, aryl CH), 6.19 (s, br, 2H, aryl CH), 4.17 (s, br, 27H, α-C<sub>5</sub>H<sub>4</sub>R, β-C<sub>5</sub>H<sub>4</sub>R, and C<sub>5</sub>H<sub>5</sub>), 3.77 (s, br, 2H, PCH<sub>2</sub>Ar), 2.61 (s, br, 6H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>), 2.45 (s, br, 6H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>, overlaps with residual CD<sub>3</sub>CD<sub>2</sub>HSO signal), 1.96 (s, 1H, br, ArCHCH<sub>2</sub>), and 1.32 (s, br, 2H, ArCHCH<sub>2</sub>). <sup>19</sup>F NMR (DMSO-*d*<sub>6</sub>, 125 °C): δ -77.1 (s). <sup>31</sup>P{<sup>1</sup>H} NMR (DMSO-*d*<sub>6</sub>, 125 °C): δ 31.1 (s). FT-IR: 3094 (w), 2949 (w), 2919 (w), 1510 (w), 1410 (w), 1261 (s), 1159 (m), 1105 (w), 1030 (s), 1001 (w), 822 (m), 756 (s), 637 (s) cm<sup>-1</sup>. UV-vis (THF): λ<sub>max</sub> 325 nm (ε = 260 M<sup>-1</sup> cm<sup>-1</sup>), 436 nm (ε = 330 M<sup>-1</sup> cm<sup>-1</sup>). GPC (DMF, 0.02 M [*n*-Bu<sub>4</sub>N][OTf], 60 °C, conventional calibration vs. PS standards): M<sub>n</sub> = 46,900, M<sub>w</sub> = 148,000 g mol<sup>-1</sup>, DP<sub>n</sub> = 50, *D* = 3.16.

#### **Polyelectrolyte 8b (2 × Fc, 1 × Rc)**

From monomer **7b** (0.25 g, 0.26 mmol) and AIBN (0.2 mg, 0.001 mmol). Yield = 0.24 g, 96%. <sup>1</sup>H NMR (DMSO-*d*<sub>6</sub>, 125 °C): δ 6.94 (s, br, 2H, aryl CH), 6.21 (s, br, 2H, aryl CH), 4.63 [s, br, 2H, β-C<sub>5</sub>H<sub>4</sub>R(Ru)], 4.56 [s, br, 7H, C<sub>5</sub>H<sub>5</sub>(Ru) and α-C<sub>5</sub>H<sub>5</sub>R(Ru)], 4.17 [s, br, 18H, α-C<sub>5</sub>H<sub>4</sub>R(Fe), β-C<sub>5</sub>H<sub>4</sub>R(Fe), and C<sub>5</sub>H<sub>5</sub>(Fe)], 3.75 (s, br, 2H, PCH<sub>2</sub>Ar), 2.61 (s, br, 6H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>), 2.42 (s, br, 6H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>, overlaps with residual CD<sub>3</sub>CD<sub>2</sub>HSO signal), 1.96 (s, br, 1H, ArCHCH<sub>2</sub>), and 1.34 (s, br, 2H, ArCHCH<sub>2</sub>). <sup>19</sup>F NMR (DMSO-*d*<sub>6</sub>, 125 °C): δ -76.3 (s). <sup>31</sup>P{<sup>1</sup>H} NMR (DMSO-*d*<sub>6</sub>, 125 °C): δ 30.9 (s). FT-IR: 3093 (w), 3013 (w), 2916 (w), 1510 (w), 1410 (w), 1260

(m), 1221 (m), 1105 (w), 1030 (s), 1000 (w), 814 (w), 772 (s), 637 (m)  $\text{cm}^{-1}$ . UV-vis (THF):  $\lambda_{\text{max}}$  320 nm ( $\epsilon = 440 \text{ M}^{-1} \text{ cm}^{-1}$ ), 431 nm ( $\epsilon = 230 \text{ M}^{-1} \text{ cm}^{-1}$ ). GPC (DMF, 0.02 M [*n*-Bu<sub>4</sub>N][OTf], 60 °C, conventional calibration vs. PS standards):  $M_n = 45,100$ ,  $M_w = 184,900 \text{ g mol}^{-1}$ ,  $DP_n = 46$ ,  $D = 4.10$ .

### Polyelectrolyte 8c (1 × Fc, 2 × Rc)

From monomer 7c (0.25 g, 0.24 mmol) and AIBN (0.2 mg, 0.001 mmol). Yield = 0.24 g, 97%. <sup>1</sup>H NMR (DMSO-*d*<sub>6</sub>, 125 °C):  $\delta$  6.97 (s, br, 2H, aryl CH), 6.21 (s, br, 2H, aryl CH), 4.63 [s, br, 4H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R(Ru)], 4.56 [s, br, 14H, C<sub>5</sub>H<sub>5</sub>(Ru) and  $\alpha$ -C<sub>5</sub>H<sub>5</sub>R(Ru)], 4.17 [s, br, 9H,  $\alpha$ -C<sub>5</sub>H<sub>4</sub>R(Fe),  $\beta$ -C<sub>5</sub>H<sub>4</sub>R(Fe), and C<sub>5</sub>H<sub>5</sub>(Fe)], 3.78 (s, br, 2H, PCH<sub>2</sub>Ar), 2.62 (s, br, 6H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>), 2.42 (s, br, 6H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>, overlaps with residual CD<sub>3</sub>CD<sub>2</sub>HSO signal), 1.90 (s, br, 1H, ArCHCH<sub>2</sub>), and 1.34 (s, br, 2H, ArCHCH<sub>2</sub>). <sup>19</sup>F NMR (DMSO-*d*<sub>6</sub>, 125 °C):  $\delta$  -76.3 (s). <sup>31</sup>P{<sup>1</sup>H} NMR (DMSO-*d*<sub>6</sub>, 125 °C):  $\delta$  30.8 (s). FT-IR: 3095 (w), 3014 (w), 2916 (w), 1510 (w), 1410 (w), 1260 (m), 1224 (m), 1101 (w), 1030 (s), 999 (w), 811 (m), 756 (s), 637 (s)  $\text{cm}^{-1}$ . UV-vis (THF):  $\lambda_{\text{max}}$  320 nm ( $\epsilon = 620 \text{ M}^{-1} \text{ cm}^{-1}$ ), 434 nm ( $\epsilon = 150 \text{ M}^{-1} \text{ cm}^{-1}$ ). GPC (DMF, 0.02 M [*n*-Bu<sub>4</sub>N][OTf], 60 °C, conventional calibration vs. PS standards):  $M_n = 69,100$ ,  $M_w = 278,100 \text{ g mol}^{-1}$ ,  $DP_n = 67$ ,  $D = 4.02$ .

### Polyelectrolyte 8d (3 × Rc)


From monomer 7d (0.25 g, 0.23 mmol) and AIBN (0.2 mg, 0.001 mmol). Yield = 0.24 g, 97%. <sup>1</sup>H NMR (DMSO-*d*<sub>6</sub>, 125 °C):  $\delta$  6.98 (s, br, 2H, aryl CH), 6.26 (s, br, 2H, aryl CH), 4.63 (s, br, 6H,  $\beta$ -C<sub>5</sub>H<sub>4</sub>R), 4.56 (s, br, 21H, C<sub>5</sub>H<sub>5</sub>, and  $\alpha$ -C<sub>5</sub>H<sub>5</sub>R), 3.80 (s, br, 2H, PCH<sub>2</sub>Ar), 2.43 (s, br, 12H, C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub> and C<sub>5</sub>H<sub>4</sub>CH<sub>2</sub>CH<sub>2</sub>), 1.85 (s, br, 1H, ArCHCH<sub>2</sub>), and 1.37 (s, br, 2H, ArCHCH<sub>2</sub>). <sup>19</sup>F NMR (DMSO-*d*<sub>6</sub>, 125 °C):  $\delta$  -76.5 (s). <sup>31</sup>P{<sup>1</sup>H} NMR (DMSO-*d*<sub>6</sub>, 125 °C):  $\delta$  30.8 (s). FT-IR: 3095 (w), 3013 (w), 2914 (w), 1510 (w), 1409 (w), 1261 (s), 1224 (m), 1160 (m), 1101 (m),

1030 (s), 997 (w), 810 (m), 755 (m), and 637 (s)  $\text{cm}^{-1}$ . UV-vis (THF):  $\lambda_{\text{max}}$  315 nm ( $\epsilon = 870 \text{ M}^{-1} \text{ cm}^{-1}$ ). GPC (DMF, 0.02 M [*n*-Bu<sub>4</sub>N][OTf], 60 °C, conventional calibration vs. PS standards):  $M_n = 38,650$ ,  $M_w = 143,450 \text{ g mol}^{-1}$ ,  $DP_n = 36$ ,  $D = 3.71$ .

## Results


### Synthesis and characterization

Reaction of phosphines **5a–d**<sup>13</sup> with a slight excess of 4-vinylbenzyl chloride and heating at 75 °C afforded phosphonium chloride monomers **6a–d** in quantitative yields (Scheme 1). Due to the poor solubility of phosphines **5a–d** in DMF, they were initially dissolved in a minimum amount of THF and later combined with DMF, an effective solvent for the quaternization reaction. Butylated hydroxytoluene (BHT) was added to prevent the undesired polymerization of the styrene groups during the quaternization reaction. To improve the solubility of the phosphonium salts in organic solvents and to prevent metallocene degradation,<sup>2k</sup> the chloride counter anions were exchanged with triflate anions to quantitatively afford monomers **7a–d**. The structure and purity of the monomers were confirmed using multinuclear NMR spectroscopy, IR and UV-vis absorption spectroscopy, mass spectrometry, elemental analysis, and X-ray crystallography (Fig. 1, S1–S16 and Table 2).



**Scheme 1** Synthetic pathway for the preparation of polyelectrolytes **8a–d**.

Phosphonium triflate monomers **7a–d** gave rise to a singlet in their  $^{19}\text{F}$  NMR spectra at  $\delta \sim -77$  and a singlet in their  $^{31}\text{P}\{^1\text{H}\}$  NMR spectra at  $\delta \sim 31.0$ . Single crystals of monomer **7a** suitable for X-ray crystallography were grown by slow evaporation of the solvent from a THF solution (Fig. 1 and Table 1). In the solid-state structure, each tetrahedral phosphonium cation was in close proximity to a triflate anion (shortest contact: P1-O2 3.958 Å). The C-P bond lengths ranged from 1.782(6) to 1.803(5) Å, and are shorter than those of the parent phosphine **5a** [1.843(1) to 1.855(1) Å].<sup>2k</sup> The average C-P-C angle was 109.5(3)° and the C44-C45 bond length for the vinyl group was 1.162(9) Å.



**Fig. 1** Solid-state structure of monomer **7a**. Anisotropic displacement ellipsoids are shown at 50% probability and hydrogen atoms have been omitted for clarity. Selected bond lengths (Å): P1-C12 1.782(6), P1-C24 1.803(5), P1-C36 1.798(5), P1-C37 1.791(6), C44-C45 1.162(9). Selected bond angles (degrees): C12-P1-C24 111.7(3), C12-P1-C36 108.5(3), C12-P1-C37 110.9(3), C24-P1-C36 110.0(3), C24-P1-C37 106.2(2), and C36-P1-C37 109.6(3).

Using azobisisobutyronitrile (AIBN) as an initiator, the phosphonium triflate monomers **7a–d** were polymerized in THF before they were precipitated into diethyl ether to yield the corresponding polyelectrolytes **8a–d** (Scheme 1). At room temperature, these polyelectrolytes gave rise to very broad  $^1\text{H}$ ,  $^{31}\text{P}\{^1\text{H}\}$ , and  $^{19}\text{F}$  NMR spectra. However, upon heating to 125 °C the spectra sharpened (Fig. S17–S20). Disappearance of the vinyl proton resonances and the observation of broad peaks associated with the unsaturated polyelectrolyte backbone ( $\delta$  0.75–2.15) in the  $^1\text{H}$  NMR spectra of the polyelectrolytes confirmed successful polymerization. The presence of the aromatic ( $\delta$  5.75–7.50), metallocene ( $\delta$  4.00–5.00), methylene bridge ( $\delta$  3.40–4.20), and ethylene bridge ( $\delta$  2.10–3.25) proton resonances in the  $^1\text{H}$  NMR spectra; a peak for each polyelectrolyte ( $\delta \sim 31.0$ ) in the  $^{31}\text{P}\{^1\text{H}\}$  NMR spectra; and a peak for each polyelectrolyte ( $\delta \sim -77$ ) in the  $^{19}\text{F}$  NMR spectra further supported the proposed structures of the polyelectrolytes.

Gel permeation chromatography (GPC) experiments were carried out to evaluate the molecular weight distributions for polyelectrolytes **8a–d**. To overcome common issues regarding strong interactions between polyelectrolytes and GPC columns, a 60 °C DMF solution containing 0.02 M [*n*-Bu<sub>4</sub>N][OTf] was used as an eluent in tandem with Teflon-treated size-exclusion columns. The results confirmed the macromolecular nature of the polyelectrolytes **8a–d** ( $M_n$ : 38,650–69,100 gmol<sup>-1</sup>,  $D$ : 3.16–4.10, Tables 2 and S1, and Fig. S21).

### UV-vis absorption spectroscopy and cyclic voltammetry

Similar to phosphines **5a–d**,<sup>13</sup> the ferrocene units in polyelectrolytes **8a–d** gave rise to two absorption maxima at *ca.* 434 nm and 320 nm while the ruthenocene units exhibited a single absorption maximum at *ca.* 320 nm. The relative intensities of each peak varied with the number of ferrocene/ruthenocene units present (Table 2 and Fig. S22–S24).

The electrochemical properties of the phosphonium triflate monomers **7a–d** and the corresponding polyelectrolytes **8a–d** were examined by cyclic voltammetry (CV) in a CH<sub>2</sub>Cl<sub>2</sub>/CH<sub>3</sub>CN (2/1) solvent mixture containing 0.1 M [*n*-Bu<sub>4</sub>N][OTf] as supporting electrolyte. Consistent with the electrochemical properties of the parent phosphines,<sup>13</sup> the ferrocene units of the monomers and polyelectrolytes were oxidized reversibly, while the ruthenocene moieties demonstrated an irreversible oxidation wave. The observed irreversible behavior was consistent with the ability of ruthenocenium cations to rapidly engage in electrochemically-induced reactions.<sup>5d, 18</sup> Due to the presence of the cationic phosphonium centers in the monomers, the recorded  $E_{1/2, Fc}$  and  $E_{pa, Rc}$  values were slightly more positive than those of the parent phosphines (Table 2, Fig. S25 and S26).<sup>13</sup>

**Table 2** Selected characterization data for monomers **7a–d** and polyelectrolytes **8a–d**.


Compound	$^{31}\text{P}$ NMR shift <sup>a</sup> ( $\delta$ )	$\epsilon$ , 320 nm <sup>b</sup> ( $\text{M}^{-1} \text{cm}^{-1}$ )	$\epsilon$ , 434 nm <sup>b</sup> ( $\text{M} \text{cm}^{-1}$ )	$E_{\text{pa,Rc}}$ <sup>c,d</sup> (mV)	$E_{1/2,\text{Fc}}$ <sup>c</sup> (mV)	$M_n$ <sup>e</sup> ( $\text{g mol}^{-1}$ )	$\text{DP}_n$ <sup>e</sup>	$\bar{D}$ <sup>e</sup>
<b>7a</b>	31.2	260	320	-	10	-	-	-
<b>7b</b>	31.0	440	240	465	15	-	-	-
<b>7c</b>	30.9	730	140	510	20	-	-	-
<b>7d</b>	30.8	910	-	555	-	-	-	-
<b>8a</b>	31.1	260	330	-	20	46,900	50	3.16
<b>8b</b>	30.9	440	230	-	20	45,100	46	4.10
<b>8c</b>	30.8	620	150	410	35	69,100	67	4.02
<b>8d</b>	30.8	870	-	450	-	38,650	36	3.71

<sup>a</sup>Recorded in DMSO-*d*<sub>6</sub> and referenced relative to triphenylphosphine internal standard.

<sup>b</sup>Recorded in THF. <sup>c</sup>Recorded at a scan rate of 250 mV s<sup>-1</sup> in degassed CH<sub>2</sub>Cl<sub>2</sub>/CH<sub>3</sub>CN (2/1) solutions of the analyte containing 0.1 M [*n*-Bu<sub>4</sub>N][OTf] as supporting electrolyte and referenced relative to the ferrocene/ferrocenium redox couple. <sup>d</sup>Irreversible process; anodic peak potential reported. <sup>e</sup>Determined by conventional calibration GPC vs. polystyrene standards in THF containing 0.02 M [*n*-Bu<sub>4</sub>N][OTf].

### Thermal analysis and pyrolysis studies


Differential scanning calorimetry (DSC) studies of polyelectrolytes **8a–d** revealed glass transition temperatures ( $T_g$ ) between 165 and 177 °C (Fig. S27 and Table 3). TGA studies demonstrated that polyelectrolytes **8a–d** have high thermal stability, with the onset of decomposition observed at *ca.* 310 °C and char yields ranging from 33 to 54% (Fig. 2 and Table 3).



**Fig. 2** TGA data obtained for polyelectrolytes: **8a** (3 × Fc, black), **8b** (2 × Fc, 1 × Rc; red), **8c** (1 × Fc, 2 × Rc; blue), and **8d** (3 × Rc, green).




Based on the high char yields observed and growing interest in the catalytic and electrochemical properties of nano-structured metal phosphides,<sup>19</sup> we decided to explore the preceramic behavior of polyelectrolytes **8a–d**. Polyelectrolyte films with approximate thickness of 6  $\mu\text{m}$  (Fig. S28) were prepared by drop casting and pyrolyzed at 1000  $^{\circ}\text{C}$  under a flow of  $\text{N}_2/\text{H}_2$  (95/5) for 3h. Each pyrolysis experiment was repeated in triplicate, and representative SEM images and relevant data are shown in Fig. 3 and Table 3. It is worth noting that we were unable to employ transmission electron microscopy (TEM) for our studies as our thorough attempts to dislodge the nanomaterials produced by pyrolysis from silicon substrates using physical scraping (razor blade), ultrasonication, and solvent rinsing were unsuccessful. However, our SEM analyses provided significant insight into the structures of the nanomaterials produced. In each case, pyrolysis of polyelectrolyte films resulted in the formation of large particles and/or continuous materials surrounded by numerous smaller particles. In the case of the nanomaterials produced from **8b** and **8c**, the multi-faceted appearance of the imaged materials hinted to the fact that they may be crystalline (*vide infra*).



**Fig. 3** SEM images of the nanomaterials prepared via the pyrolysis of films of polyelectrolytes (a) **8a**, (b) **8b**, (c) **8c**, and (d) **8d**. Scale bars = 1  $\mu\text{m}$ .

Elemental maps (EDX spectroscopy) revealed that the nanomaterials produced were comprised of C, O, P, Fe, and/or Ru and that the inorganic components were distributed throughout the nanomaterials produced (Fig. 4, S29–S31). The presence of carbon was attributed to incomplete volatilization of the polystyrene backbone and oxidation during brief (and unavoidable) exposure of the samples to air prior to SEM analysis accounts for the presence of oxygen. Unfortunately, the elemental maps obtained provide little quantitative information about the composition of the nanomaterials produced. With this in mind, at least five different data sets were collected for regions (*ca.* 1  $\mu\text{m}^2$ ) of the nanomaterial surfaces densely populated with relatively large particles and/or continuous material ('bulk') and with relatively small particles ('particles') for each of the samples (Fig. S32–S35 and Table 3). For each sample, the smaller particles produced were clearly embedded within a carbon-rich matrix, and the overall phosphorus/metal content was significantly lower than those observed for areas densely populated with bulk material.



**Fig. 4** SEM images and elemental maps (O, Ru, Fe, P, C) for the nanomaterials prepared via the pyrolysis of a film of polyelectrolyte **8b**. Scale bar = 1  $\mu\text{m}$ .


**Table 3** Thermal characterization and elemental composition data for the nanomaterials produced via the pyrolysis of polyelectrolytes **8a–d**.<sup>a</sup>

Polymer	T <sub>g</sub> <sup>b</sup> (°C)	Onset of Decomposition <sup>c</sup> (°C)	Char Yield <sup>b</sup> (%)	Region <sup>d</sup>	Atomic Ratio <sup>d,e</sup>			
					P	Fe	Ru	Fe + Ru
<b>8a</b>	177	310	33	<i>bulk</i>	1	1.9 ± 0.3	-	1.9 ± 0.3
				<i>particles</i>	1	2.1 ± 0.5	-	2.1 ± 0.5
<b>8b</b>	165	311	51	<i>bulk</i>	1	1.7 ± 0.7	1.1 ± 0.4	2.8 ± 0.8
				<i>particles</i>	1	1.5 ± 0.3	0.9 ± 0.1	2.4 ± 0.3
<b>8c</b>	173	312	39	<i>bulk</i>	1	0.5 ± 0.1	1.6 ± 0.1	2.1 ± 0.1
				<i>particles</i>	1	0.6 ± 0.3	1.8 ± 0.5	2.4 ± 0.6
<b>8d</b>	171	330	54	<i>bulk</i>	1	-	2.1 ± 0.0	2.1 ± 0.0
				<i>particles</i>	1	-	1.5 ± 0.1	1.5 ± 0.1

<sup>a</sup>Carried out at 1000 °C under N<sub>2</sub>/H<sub>2</sub> (95/5) gas mixture as the carrier gas at an approximate flow rate of *ca.* 60 mL min<sup>-1</sup>. <sup>b</sup>Determined using DSC. <sup>c</sup>Determined using TGA. <sup>d</sup>Atomic ratios determined using EDX spectroscopy for dense regions of relatively large particles (*'bulk'*) and less dense regions of relatively small particles (*'particles'*). See electronic supplementary information for additional details. <sup>e</sup>Phosphorus stoichiometry fixed at 1.

### Powder X-ray diffraction studies

Powder X-ray diffraction studies of the nanomaterials produced by pyrolysis of films of polyelectrolytes **8a–d** are shown in Fig. 5. In each case, the patterns produced confirmed the presence of crystalline materials. Qualitative phase identification studies were performed through careful comparison of our diffraction data with those of a PXRD database,<sup>20</sup> which included data for known mono- and bimetallic phosphides (*i.e.*, M<sub>4</sub>P, M<sub>3</sub>P, M<sub>2</sub>P, and MP; where M: Fe and/or Ru), metal carbides, pure metals, etc. (Fig. S36–S39). The PXRD data for the films produced from polyelectrolytes **8a–c** were not closely matched with those of any known phases, and were indicative of the presence of multiple crystalline phases, which prevented us from indexing the data. Conversely, the PXRD data collected for the film produced from polyelectrolyte **8d** was consistent with that of Ru<sub>2</sub>P (Fig. 5d and S39).



**Fig. 5** Powder X-ray diffractograms for the nanomaterials prepared via the pyrolysis of films of polyelectrolytes (a) **8a**, (b) **8b**, (c) **8c**, and (d) **8d**. Miller indices corresponding to Ru<sub>2</sub>P are shown in panel (d).

## Discussion

Considering the PXRD, EDX spectroscopy, and elemental mapping results obtained for the nanomaterials produced from pyrolyzed films of polyelectrolytes **8a–c**, two points become immediately obvious. First, given the large standard deviations associated with the atomic ratios determined from the EDX data collected, it is clear that phosphorus, iron, and/or ruthenium are not distributed uniformly throughout the nanomaterials produced. It is therefore probable that multiple different materials/phases have been produced. For the heterobimetallic materials derived from **8b** and **8c**, PXRD data confirmed the absence of simple Fe<sub>2</sub>P/Ru<sub>2</sub>P/Fe<sub>3</sub>P/Ru<sub>3</sub>P phases and supported this hypothesis. Second, within a single standard deviation, the average composition of the small particles and bulk materials analyzed were the same. Conversely, for the nanomaterials derived from **8d**, the relatively smaller standard deviations calculated point

toward the uniform distribution of phosphorus and ruthenium throughout regions containing bulk material and relatively small particles. Furthermore, this was the only case where the composition of the bulk (P:Ru, 1:  $2.1 \pm 0.0$ ) and small-particle-rich (P:Ru, 1:  $1.5 \pm 0.1$ ) were statistically different. When these results are combined with the PXRD data collected and indexed for this sample, it becomes clear that the bulk phase produced from the pyrolysis of films of polyelectrolyte **8d** is comprised of  $\text{Ru}_2\text{P}$ .

## Conclusion

In conclusion, starting from stable tertiary phosphines containing all possible combinations of ethylferrocene and ethylruthenocene substituents, styrene-based phosphonium triflate monomers with four different stoichiometric ratios of Fe/Ru were synthesized and fully characterized. Via free-radical polymerization of the triflate salts, four polyelectrolytes were prepared and analyzed. Due to the presence of ferrocene/ruthenocene, these materials exhibited redox properties and gave rise to UV-vis absorption maxima consistent with the number of each metallocene present. GPC and DSC results confirmed the macromolecular nature of the polyelectrolytes and TGA studies confirmed their stability up to  $\sim 310$  °C. Studies of the nanomaterials that resulted from the pyrolysis of polyelectrolytes **8a–d** using SEM and PXRD showed that they can be used as precursors to crystalline nanomaterials. EDX spectroscopy and elemental mapping data indicated that the crystalline nanomaterials contained Fe, Ru, and P distributed throughout, with Fe/Ru/P ratios influenced by the polyelectrolyte structures.

## Supplementary information

Electronic supplementary information (ESI) available. See DOI: #####.

## Acknowledgments

The authors acknowledge the University of Western Ontario, the Natural Science and Engineering Research Council (NSERC) of Canada (DG, 435675), the Ontario Ministry of Research and Innovation (ERA, ER14-10-147) and the Canada Foundation for Innovation (JELF, 33977) for funding this work. We thank Prof. Paul Ragnogna and Mr. Tyler Cuthbert for assistance with phosphine experiments, use of equipment, and helpful discussions. We thank Mr. Tim Goldhawk and Dr. Todd Simpson of the Western Nanofabrication Facility for assistance with SEM and EDX spectroscopy studies, and Dr. Paul Boyle, Ms. Stephanie Barbon, Dr. Anastasia Colomba, and Mr. Joe Paquette for assistance with X-ray diffraction experiments and helpful discussions. We also appreciate the time and effort that Mr. Eric Landry and Mr. Ahmad Abu Romeh (PolyAnalytik Canada) spent collecting the GPC data presented.

## Notes and references

- 1 (a) C.-L. Ho and W.-Y. Wong, *Coord. Chem. Rev.*, 2011, **255**, 2469–2502; (b) G. R. Whittell; M. D. Hager; U. S. Schubert and I. Manners, *Nat. Mater.*, 2011, **10**, 176–188; (c) D. Astruc, *Nat. Chem.*, 2012, **4**, 255–267; (d) C. Friebe; M. D. Hager; A. Winter and U. S. Schubert, *Adv. Mater.*, 2012, **24**, 332–345; (e) C. G. Hardy; L. Ren; J. Zhang and C. Tang, *Isr. J. Chem.*, 2012, **52**, 230–245; (f) H. Bhattacharjee and J. Müller, *Coord. Chem. Rev.*, 2016, **314**, 114–133; (g) Y. Yan; J. Zhang; L. Ren and C. Tang, *Chem. Soc. Rev.*, 2016, DOI: 10.1039/C6CS00026F.
- 2 (a) T. J. Peckham; A. J. Lough and I. Manners, *Organometallics*, 1999, **18**, 1030–1040; (b) B. F. G. Johnson; K. M. Sanderson; D. S. Shephard; D. Ozkaya; W. Zhou; H. Ahmed; M. D. R. Thomas; L. Gladden and M. Mantle, *Chem. Commun.*,

- 2000, 1317–1318; (c) Y. Ma; W.-F. Dong; M. A. Hempenius; H. Mohwald and G. Julius Vancso, *Nat. Mater.*, 2006, **5**, 724–729; (d) X. Wang; G. Guerin; H. Wang; Y. Wang; I. Manners and M. A. Winnik, *Science*, 2007, **317**, 644–647; (e) C. Ornelas; J. Ruiz; C. Belin and D. Astruc, *J. Am. Chem. Soc.*, 2009, **131**, 590–601; (f) H. Zhan; S. Lamare; A. Ng; T. Kenny; H. Guernon; W.-K. Chan; A. B. Djurišić; P. D. Harvey and W.-Y. Wong, *Macromolecules*, 2011, **44**, 5155–5167; (g) Z. M. Al-Badri; R. R. Maddikeri; Y. Zha; H. D. Thaker; P. Dobriyal; R. Shunmugam; T. P. Russell and G. N. Tew, *Nat. Commun.*, 2011, **2**, 482; (h) L. Ren; J. Zhang; C. G. Hardy; S. Ma and C. Tang, *Macromol. Rapid Commun.*, 2012, **33**, 510–516; (i) R. H. Staff; M. Gallei; M. Mazurowski; M. Rehahn; R. Berger; K. Landfester and D. Crespy, *ACS Nano*, 2012, **6**, 9042–9049; (j) X. Wang; K. Cao; Y. Liu; B. Tsang and S. Liew, *J. Am. Chem. Soc.*, 2013, **135**, 3399–3402; (k) A. Rabiee Kenaree; B. M. Berven; P. J. Ragona and J. B. Gilroy, *Chem. Commun.*, 2014, **50**, 10714–10717; (l) R. Guterman; A. Rabiee Kenaree; J. B. Gilroy; E. R. Gillies and P. J. Ragona, *Chem. Mater.*, 2015, **27**, 1412–1419; (m) J. Zhang; J. Yan; P. Pageni; Y. Yan; A. Wirth; Y.-P. Chen; Y. Qiao; Q. Wang; A. W. Decho and C. Tang, *Sci. Rep.*, 2015, **5**, 11914; (n) M. Hadadpour; J. Gwyther; I. Manners and P. J. Ragona, *Chem. Mater.*, 2015, **27**, 3430–3440.
- 3 (a) S. B. Clendenning; S. Han; N. Coombs; C. Paquet; M. S. Rayat; D. Grozea; P. M. Brodersen; R. N. S. Sodhi; C. M. Yip; Z. H. Lu and I. Manners, *Adv. Mater.*, 2004, **16**, 291–296; (b) W. Y. Chan; S. B. Clendenning; A. Berenbaum; A. J. Lough; S. Aouba; H. E. Ruda and I. Manners, *J. Am. Chem. Soc.*, 2005, **127**, 1765–1772; (c) K. Liu; S. B. Clendenning; L. Friebe; W. Y. Chan; Zhu; M. R. Freeman; G. C.

- Yang; C. M. Yip; D. Grozea; Z.-H. Lu and I. Manners, *Chem. Mater.*, 2006, **18**, 2591–2601; (d) M. Zamora; S. Bruña; B. Alonso and I. Cuadrado, *Macromolecules*, 2011, **44**, 7994–8007.
- 4 (a) J. B. Gilroy; S. K. Patra; J. M. Mitchels; M. A. Winnik and I. Manners, *Angew. Chem. Int. Ed.*, 2011, **50**, 5851–5855; (b) Y. Zha; H. D. Thaker; R. R. Maddikeri; S. P. Gido; M. T. Tuominen and G. N. Tew, *J. Am. Chem. Soc.*, 2012, **134**, 14534–14541; (c) J. Zhang; L. Ren; C. G. Hardy and C. Tang, *Macromolecules*, 2012, **45**, 6857–6863; (d) J. Zhang; Y. Yan; M. W. Chance; J. Chen; J. Hayat; S. Ma and C. Tang, *Angew. Chem. Int. Ed.*, 2013, **52**, 13387–13391; (e) J. Zhang; Y. Yan; J. Chen; W. M. Chance; J. Hayat; Z. Gai and C. Tang, *Chem. Mater.*, 2014, **26**, 3185–3190; (f) R. Ciganda; H. Gu; P. Castel; P. Zhao; J. Ruiz; R. Hernández and D. Astruc, *Macromol. Rapid Commun.*, 2016, **37**, 105–111.
- 5 (a) K. Liu; C.-L. Ho; S. Aouba; Y.-Q. Zhao; Z.-H. Lu; S. Petrov; N. Coombs; P. Dube; H. E. Ruda; W.-Y. Wong and I. Manners, *Angew. Chem. Int. Ed.*, 2008, **47**, 1255–1259; (b) B. Bagh; J. B. Gilroy; A. Staubitz and J. Müller, *J. Am. Chem. Soc.*, 2010, **132**, 1794–1795; (c) Q. Dong; G. Li; C.-L. Ho; M. Faisal; C.-W. Leung; P. W.-T. Pong; K. Liu; B.-Z. Tang; I. Manners and W.-Y. Wong, *Adv. Mater.*, 2012, **24**, 1034–1040; (d) M. Erhard; K. Lam; M. Haddow; G. R. Whittell; W. E. Geiger and I. Manners, *Polym. Chem.*, 2014, **5**, 1264–1274; (e) A. D. Russell; G. R. Whittell; M. F. Haddow and I. Manners, *Organometallics*, 2014, **33**, 5349–5357; (f) Q. Dong; G. Li; H. Wang; P. Wing-Tat Pong; C.-W. Leung; I. Manners; C.-L. Ho; H. Li and W.-Y. Wong, *J. Mater. Chem.*, 2015, **3**, 734–741; (g) H. Braunschweig; A. Damme; S. Demeshko; K. Dück; T. Kramer; I. Krummenacher; F. Meyer; K.



- Radacki; S. Stellwag-Konertz and G. R. Whittell, *J. Am. Chem. Soc.*, 2015, **137**, 1492–1500; (h) Z. Meng; K. Sato; T. Sukegawa; K. Oyaizu; C.-L. Ho; J. Xiang; Y.-H. Feng; Y. H. Lo; H. Nishide and W.-Y. Wong, *J. Organomet. Chem.*, 2016, 51–55.
- 6 (a) J. Rodriguez; xe; A and D. W. Goodman, *Science*, 1992, **257**, 897–903; (b) S. Sun; C. B. Murray; D. Weller; L. Folks and A. Moser, *Science*, 2000, **287**, 1989–1992; (c) D. Astruc; F. Lu and J. R. Aranzaes, *Angew. Chem. Int. Ed.*, 2005, **44**, 7852–7872; (d) A.-H. Lu; E. L. Salabas and F. Schüth, *Angew. Chem. Int. Ed.*, 2007, **46**, 1222–1244; (e) K. J. Major; C. De and S. O. Obare, *Plasmonics*, 2009, **4**, 61–78; (f) S. Shylesh; V. Schünemann and W. R. Thiel, *Angew. Chem. Int. Ed.*, 2010, **49**, 3428–3459; (g) H. Goesmann and C. Feldmann, *Angew. Chem. Int. Ed.*, 2010, **49**, 1362–1395; (h) U. Banin; Y. Ben-Shahar and K. Vinokurov, *Chem. Mater.*, 2014, **26**, 97–110; (i) P. Buchwalter; J. Rosé and P. Braunstein, *Chem. Rev.*, 2015, **115**, 28–126.
- 7 (a) B. Li; J. Wang; Y. Yuan; H. Ariga; S. Takakusagi and K. Asakura, *ACS Catal.*, 2011, **1**, 1521–1528; (b) V. Kelsen; A. Meffre; P.-F. Fazzini; P. Lecante and B. Chaudret, *ChemCatChem.*, 2014, **6**, 1714–1720; (c) M. Kaushik; H. M. Friedman; M. Bateman and A. Moores, *RSC Adv.*, 2015, **5**, 53207–53210; (d) R. Hudson; V. Chazelle; M. Bateman; R. Roy; C.-J. Li and A. Moores, *ACS Sustain. Chem. Eng.*, 2015, **3**, 814–820.
- 8 J.-Q. Du; Y. Zhang; T. Tian; S.-C. Yan and H.-T. Wang, *Mater. Res. Bull.*, 2009, **44**, 1347–1351.

- 9 (a) G. L. Ott; T. Fleisch and W. N. Delgass, *J. Catal.*, 1979, **60**, 394–403; (b) M. C. Bahome; L. L. Jewell; K. Padayachy; D. Hildebrandt; D. Glasser; A. K. Datye and N. J. Coville, *Appl. Catal. A*, 2007, **328**, 243–251.
- 10 (a) J. P. Wilcoxon and B. L. Abrams, *Chem. Soc. Rev.*, 2006, **35**, 1162–1194; (b) N. Semagina and L. Kiwi-Minsker, *Cat. Rev. - Sci. Eng.*, 2009, **51**, 147–217.
- 11 M. Zaheer; T. Schmalz; G. Motz and R. Kempe, *Chem. Soc. Rev.*, 2012, **41**, 5102–5116.
- 12 T. Nishikubo; T. Iizawa; K. Kobayashi and M. Okawara, *Tetrahedron Lett.*, 1981, **22**, 3873–3874.
- 13 A. Rabiee Kenaree; T. J. Cuthbert; S. M. Barbon; P. D. Boyle; E. R. Gillies; P. J. Ragogna and J. B. Gilroy, *Organometallics*, 2015, **34**, 4272–4280.
- 14 S. v. Bruker-AXS, 2013, Bruker-AXS, Madison, WI 53711, USA.
- 15 T. v. Bruker-AXS, 2012, Bruker-AXS, Madison, WI 53711, USA.
- 16 G. M. Sheldrick, *Acta Cryst.*, 2015, **A71**, 3–8.
- 17 G. M. Sheldrick, *Acta Cryst.*, 2015, **C71**, 3–8.
- 18 (a) S. Trupia; A. Nafady and W. E. Geiger, *Inorg. Chem.*, 2003, **42**, 5480–5482; (b) J. C. Swarts; A. Nafady; J. H. Roudebush; S. Trupia and W. E. Geiger, *Inorg. Chem.*, 2009, **48**, 2156–2165.
- 19 (a) H. Teller; O. Krichevski; M. Gur; A. Gedanken and A. Schechter, *ACS Catal.*, 2015, **5**, 4260–4267; (b) Y. Shi and B. Zhang, *Chem. Soc. Rev.*, 2016, **45**, 1529–1541; (c) A. Berenguer; T. M. Sankaranarayanan; G. Gómez; I. Moreno; J. M. Coronado; P. Pizarro and D. P. Serrano, *Green Chem.*, 2016, **18**, 1938–1951; (d) Y. Lu; T. Wang; X. Li; G. Zhang; H. Xue and H. Pang, *RSC Adv.*, 2016, **6**,

87188–87212; (e) J. F. Callejas; C. G. Read; C. W. Roske; N. S. Lewis and R. E. Schaak, *Chem. Mater.*, 2016, **28**, 6017–6044.

20 The PXRD patterns were compared using the ICSD database and PDF4+ software.