



Nanoscale

Freestanding Carbon Nanofoam Papers with Tunable Porosity as Lithium-Sulfur Battery Cathodes

Journal:	<i>Nanoscale</i>
Manuscript ID	NR-ART-06-2023-002699.R1
Article Type:	Paper
Date Submitted by the Author:	04-Aug-2023
Complete List of Authors:	Neale, Zachary; National Research Council Postdoctoral Associate, US Naval Research Laboratory Lefler, Matthew; National Research Council Postdoctoral Associate, US Naval Research Laboratory Long, Jeffrey; U.S. Naval Research Laboratory, Surface Chemistry Branch Rolison, Debra; Naval Research Laboratory, Code 6170 Sassin, Megan; U.S. Naval Research Laboratory, Surface Chemistry Branch Carter, Rachel; US Naval Research Laboratory, Chemistry Division

SCHOLARONE™
Manuscripts

Freestanding Carbon Nanofoam Papers with Tunable Porosity as Lithium-Sulfur Battery Cathodes

Zachary G. Neale,¹ Matthew J. Lefler,¹ Jeffrey W. Long,² Debra R. Rolison,² Megan B. Sassin,² and Rachel E. Carter^{2*}

¹*National Research Council Postdoctoral Associate,
U.S. Naval Research Laboratory, Washington, DC, USA*

²*Surface Chemistry Branch (Code 6170),
U.S. Naval Research Laboratory, Washington, DC, USA*

Abstract

To reach energy density demands greater than 3 mAh/cm² for practical applications, the electrode structure of lithium-sulfur batteries must undergo an architectural redesign. Freestanding carbon nanofoam papers derived from resorcinol–formaldehyde aerogels provide a three-dimensional conductive mesoporous network while facilitating electrolyte transport. Vapor-phase sulfur infiltration fully penetrates >100 μm thick electrodes and conformally coats the carbon aerogel surface providing areal capacities up to 4.1 mAh/cm² at sulfur loadings of 6.4 mg/cm². Electrode performance can be optimized for energy density or power density by tuning sulfur loading, pore size, and electrode thickness.

Corresponding Author: Rachel Carter, Rachel.carter@nrl.navy.mil

1. Introduction

Sulfur is a naturally abundant, low-cost, nonstrategic resource to exploit for electrochemical energy-storage applications.¹ Interest in sulfur-based batteries is further driven by the high theoretical specific capacity of 1675 mAh/g that derives from the 16-electron reduction of S₈ to 8 S²⁻.² Despite being investigated since the 1940s in high-temperature battery systems,³ the implementation of ambient-temperature sulfur-based batteries faces many remaining

challenges before practical commercialization: intrinsically poor electronic conductivity, low sulfur utilization, limited cyclability, and redox shuttling of soluble polysulfides. The twenty-first century pursuit for battery cell chemistries delivering specific energy >500 Wh/kg has kindled a renaissance of academic and commercial research in lithium–sulfur (Li–S) batteries aimed to solve these roadblocks.¹

For practical battery use, sulfur should be expressed in a conductive, porous matrix that contains and constrains the sulfur and its electrochemical byproducts (i.e., polysulfides).⁴ Numerous nanostructured carbons such as carbon nanotubes,⁵⁻¹⁰ graphene,^{11, 12} and “yolk-shell” spheres¹³⁻¹⁵ have also been demonstrated as hosts for sulfur, providing polysulfide confinement, facile electronic conduction, and short ion transport pathways. While reports of porous carbon hosts for Li–S batteries are numerous, many lab-scale studies use electrodes comprising carbons with needlessly low density, insufficient sulfur weight loadings, or those made via processes that would otherwise be difficult to scale. Coupled with unrealistic electrochemical testing protocols that are sometimes employed, the results of such early-stage investigations often fail to yield results directly relevant to large-scale, real-world Li–S batteries.^{3, 16}

The design of sulfur–carbon composite electrodes must account for such performance metrics as gravimetric, volumetric, and geometric capacity, as well as high-rate capability. These metrics are, in turn, affected by such cathode-specific factors as pore size distribution, accessible surface area, local and macroscale electronic conductivity, sulfur distribution within the electrode, and porosity/tap density.^{17, 18} High-surface-area microporous carbons offer better confinement of polysulfides but typically have lower sulfur loadings and correspondingly suboptimal capacity. Mesoporous, macroporous, and hierarchical porous structures allow more space for higher sulfur loadings and promote electrolyte transport to maximize sulfur utilization.^{1, 19-24} Melt-infiltration is

a common approach to load sulfur into these porous hosts, but such methods rely on capillary action and require time to produce uniform and conformal distributions of sulfur.^{5, 12, 17, 20, 25-29} These sulfur–carbon composites are often prepared in powder form and mixed with carbon black, binder, and solvent, then cast as a slurry onto a foil current collector.^{5, 9, 12, 17, 19, 20, 26-31} The resulting electrodes have suboptimal conductivity and mechanical strength, impeding rate capability and hindering the use of thicker electrodes to achieve high areal capacity.

Among mesoporous/macroporous scaffolds, carbon aerogels and related aerogel-like carbons (e.g., nanofoams) exhibit many desirable structural characteristics for serving as an effective sulfur host, including through-connected pore networks of tunable size (nm to μm), high specific surface area (100s of m^2/g), and moderately high electronic conductivity (10s of S/cm).³²⁻
³⁶ Carbon aerogels have shown promising initial results in Li–S cells when the aerogel powder is infused with sulfur and then processed into a conventional composite electrode with polymer binder.^{26, 31, 37} Alternatively, we have demonstrated the electrochemical versatility of freestanding carbon nanofoam papers (CNFPs), in which porous aerogel-like carbon networks fill and span the macroscale voids of a supporting carbon-fiber paper.³⁸⁻⁴⁶ The CNFP requires no additional binders or conductive additives before incorporation into an electrochemical cell, and the continuity of intermingled networks of conductive carbon and void volume is not interrupted across the macroscale thickness of the electrode, as would be the case for most powder-composite constructions.

In order to take advantage of the freestanding nature of the CNFPs, we here utilize isothermal vapor infiltration^{7, 8, 47-49} to incorporate sulfur (forming “S@CNFP”) and then deploy the resulting S@CNFP object as a cathode in a Li–S cell without any additional processing. We examine the performance of Li–S cells with S@CNFPs while varying such structural parameters

as pore size distribution, sulfur weight loading, and electrode thickness. Our findings illustrate the ability to balance pore size and weight loading to tune high capacity with respect to mass, volume, or footprint to optimize Li–S performance.

2. Experimental

Synthesis of Carbon Nanofoam Papers

Freestanding CNFPs with tunable pore size distributions were synthesized via a resorcinol–formaldehyde (RF) sol–gel process described elsewhere.⁴¹ In brief, resorcinol (R) and formaldehyde (F) in a 1R:2F mole ratio were mixed in water with a Na₂CO₃ catalyst (C) and aged at room temperature for 3 h creating a sol precursor. The CNFP formulations are designated by their RF-water wt% and R:C molar ratio, herein labeled as “RF wt%/R:C”, with three formulations selected for testing: 40/300, 40/500, and 40/1000. Commercial carbon fiber papers (Lydall Technimat®, density 0.2 g/cm³, ~90 μm thick) were cut to 4 × 4 cm² and cleaned in an air/ice plasma for 45 min then soaked in the RF sol under vacuum. The RF-soaked carbon fiber papers were sandwiched between glass slides with excess sol added and clamped together with binder clips. Multi-ply CNFPs were made by stacking multiple sheets of sol-infused carbon fiber paper in between glass slides. The assemblies were wrapped in duct tape to prevent leaking of sol and packaged together in aluminum foil with a few milliliters of water added to maintain humidity, then aged at room temperature for an additional 21 h. The aluminum foil packages were then cured in a commercial pressure cooker (Nesco 3-in-1 pressure cooker) set to steam mode for 9.5 h on slow-cook setting (~88–94 °C) followed by a 14.5 h warm cycle (~80 °C). The RF–polymer @ CNFP nanofoam composite sheets were soaked in water and then acetone for 1–2 h, followed by drying in air at room temperature. The dry polymer nanofoam papers were pyrolyzed into CNFPs under flowing argon, ramping at 1 C°/min and holding at 1000 °C for 2 h.

Synthesis of S@CNFPs

Based on our prior work,^{7, 8, 47, 48} sulfur vapor deposition into CNFP was performed in a round chamber (~3 cm tall with a 3.75 cm radius, inner volume ~106 cm³) consisting of a PTFE body and cap with a Viton O-ring for sealing (Figure S1). The CNFP was punched into 15 mm diameter discs and placed onto a piece of stainless-steel mesh which sat on a ledge above a well containing 1 g of sulfur powder. The infiltration chamber was sealed and placed inside a muffle furnace preheated to 175 °C. Vapor infiltration time varied, and lasted for 2 h, 6 h, or 18 h depending on the experiment. After infiltration to the set time, the chamber was removed from the furnace and allowed to cool for ~30 min. The S@CNFP were weighed before and after infiltration to determine the sulfur loading. A simplified schematic of the synthesis of S@CNFPs can be found in Figure S2.

Structural Characterization of Carbon Nanofoam Papers

Scanning electron microscopy (SEM; Zeiss Supra 55) was performed on CNFP cross-sections prepared by fast fracturing samples soaked in liquid nitrogen with a fresh razor blade. Pore size distribution and specific surface area were determined by nitrogen physisorption (Micromeritics ASAP 2020 Plus) with samples degassed prior to testing for 10 h at 150 °C. Pore size distributions were calculated from the adsorption isotherm data using a density functional theory (DFT) model. Apparent porosities and total specific pore volumes were estimated by Archimedes principle using water.

Electrochemical Characterization

Coin cells (CR2032) were fabricated with the sulfur-infiltrated CNFP discs versus a Li chip electrode (MTI, 16 mm diameter, 0.6 mm thick), an Entek Gold LP separator (19 mm diameter),

and ~80 μL of electrolyte (1 M LiTFSI (Sigma-Aldrich, bis(trifluoro-methane)sulfonimide lithium salt, 99.95% trace metals basis) and 0.2 M LiNO_3 (ACROS Organics, lithium nitrate salt, 99.999% trace metals basis) in a 1:1 ratio of DOL (Sigma-Aldrich, 1,3-dioxolane, anhydrous, contains ~75 ppm BHT as inhibitor, 99.8%) and DME (Sigma-Aldrich, 1,2-dimethoxyethane, anhydrous, 99.5%, inhibitor free). The coin cell components (can, spacer, and wave spring) were purchased through Hohsen Corp (Japan), and the cells were assembled using Hohsen Corp's automatic coin cell crimper for 2032 cells.

Cycling was performed at a C-rate of 0.1C (based on the theoretical capacity of the sulfur deposited on the specific electrode) between 1.8 V and 2.6 V on a Maccor model 4300 desktop automated test system. Rate studies were performed on an Ametek PARSTAT MC Multichannel Potentiostat using PMC-1000 modules. These symmetric rate studies utilized C-rates of 0.1C for 10 cycles, 0.2C for 5 cycles, 0.5C for 5 cycles, 1C for 5 cycles, and a return to 0.1C for 10 cycles.

3. Results and discussion

3.1 Carbon Nanofoam Paper

Three variants of CNFPs were prepared in which the pore size distribution within the CNF component is tuned by controlling the resorcinol:catalyst (Na_2CO_3) ratio in the precursor RF sols. Increasing the R:C ratio (decreasing catalyst concentration) results in larger RF particles and correspondingly larger pores in the polymer nanofoam, and ultimately in the pyrolyzed carbon form (Figure 1).^{32, 35} Consequently, the nitrogen adsorption isotherms change from mesoporous type IV to macroporous type II behavior (Figure S3) and pore size distributions broaden and shift to larger pore sizes (Figure 2) while specific surface areas decrease from 515 m^2/g for CNFP-40/300 to 480 and 420 m^2/g for CNFP-40/500 and CNFP-40/1000, respectively (Table 1).

Table 1. Pore size distribution, volume, and surface area of CNFPs determined by nitrogen physisorption and Archimedes principle.

CNFP	Total Surface Area ^a (m ² /g)	Micropore Area ^b (m ² /g)	Micropore Volume ^b (cm ³ /g)	Mesopore Area ^c (m ² /g)	Pore Volume ^c (cm ³ /g)	Bulk Density ^d (g/cm ³)	Bulk Pore Volume ^d (cm ³ /g)	Bulk Porosity ^d (%)
40/300	515	238	0.12	270	1.45	0.46	1.60	74.0
40/500	480	302	0.15	225	1.54	0.47	1.56	74.0
40/1000	420	338	0.17	198	0.70	0.42	1.80	76.5

^a Total surface area determined by Brunauer-Emmett-Teller (BET) specific surface area. ^b Micropore surface area and volume estimated using *t*-plot method. ^c Mesopore surface area and pore volume determined by DFT. ^d Bulk properties determined by Archimedes Principle using water.




Figure 1. Scanning electron micrographs of 1-ply CNFP cross-sections for CNFP-40/300 (a), CNFP-40/500 (b), and CNFP-40/1000 (c), and their respective magnified images (d-f). In (a-c), the carbon nanofoam appears as a solid filling the gaps in the carbon fiber paper, and the pores are only visible at much higher magnifications (d-f).

The nitrogen physisorption-measured pore volume in CNFPs is dominated by mesopores (2–50 nm) and macropores (> 50 nm), with micropores (< 2 nm) contributing only a small fraction. CNFP-40/300 and CNFP-40/500 possess similar specific pore volumes of about 1.5 cm³/g; however, CNFP-40/1000 results in a drastically lower pore volume of 0.7 cm³/g in mesopores and small macropores. This result reflects the limits of nitrogen physisorption to measure pores >100

nm, a size range that is prevalent in CNFP-40/1000, as evident in SEM images (see Figure 1). In comparison to nitrogen physisorption, bulk density determined by the Archimedes Principle estimates the total pore volume of CNFPs to be between 1.6 – 1.8 cm³/g, which better demonstrates the contribution of pores >100 nm. All formulations should nominally have the same total pore volume because all derive from a 40 wt% RF sol.

The CNFPs provide higher volumetric surface areas between 168 – 259 m²/cm³ compared to other as-synthesized high-surface area carbon aerogels with porosities over 90% due to the higher bulk density of the former.³¹ The bulk density of freestanding CNFP is also directly related to its electrode tap density without need for further processing.




Figure 2. Pore size distributions of CNFPs determined by nitrogen physisorption using the DFT model.

When employing mesoporous/macroporous materials that are expressed as unitary macroscale objects, self-limiting non-line-of-sight coating/modification schemes are essential to decorate interior surfaces without clogging the pore structure, as we previously demonstrated with CNFPs coated with nanoscale metal oxides⁴⁴⁻⁴⁶ and polymers.⁵⁰ Thus, the present vapor-phase approach^{7, 8, 30, 47-49} is ideally suited to incorporate sulfur within the device-ready CNFP architecture. When tracking the CNFP mass as a function of vapor-infiltration time, uptake is

initially rapid, with weight loading correlating to the specific surface area of a CNFP (Figure 3a). Beyond 6 h infiltration, the rate of weight gain for all CNFP formulations stabilizes at about 1 wt%/h, reaching 69, 63, and 40 wt% sulfur loadings after 18 h for CNFP-40/300, CNFP-40/500, and CNFP-40/1000, respectively. The decrease in deposition rate beyond 6 h indicates that all nanostructured carbon surfaces are coated by sulfur, emphasizing the self-limiting nature of the vapor infiltration process, which prevents the formation of thick regions of sulfur.

Elemental mapping using EDS reveals uniform incorporation of sulfur throughout the CNF component but not along the supporting carbon fibers (Figure 3b&c). The supporting carbon-fiber paper component contributes ~34 wt.% of the total mass of the CNFP and provides mechanical integrity and enhanced electrical conductivity, but the carbon fibers themselves contribute minimally to the charge-storage capacity.³⁹ Thus, we also note sulfur loading as normalized to the mass of the CNF domains in the CNFP in Figure 3a for fundamental comparison with other porous carbons.




Figure 3. (a) Mass uptake by CNFPs upon vapor infiltration of S_8 as a function of time: solid line represents the measured mass uptake in the CNFP, and the dotted line shows the mass of S_8 uptake relative to the carbon nanofoam component of the CNFP. Scanning electron microscopy and cross-sectional EDS analysis of C and S for (b) 2 h and (c) 6 h infiltrations.

Sulfur coating thicknesses derived mathematically based on BET surface area, sulfur mass loadings, and density of sulfur ($\sim 2 \text{ g/cm}^3$) result in coatings between 1–9 nm thick (Table S1). In

general, CNFPs with smaller pores obtain thicker coatings. The condensation of sulfur from the vapor phase is influenced by surface energy, whereby smaller pores of negative curvature have higher surface energies.⁸ In contrast, the supporting carbon fiber paper has larger positive curvature, along with a dense non-porous interior, that results in the low sulfur EDS signal.

Thicker sulfur coatings result in higher pore-volume occupation by sulfur and this relation is stronger for smaller pores (Table S2). For example, after 18 h infiltration CNFPs nominally have 68, 53, and 18 vol% of pore-volume occupied by sulfur corresponding to 69, 63, and 40 wt% sulfur loading for CNFP-40/300, CNFP-40/500, and CNFP-40/1000, respectively. Comparing between CNFP-40/300 and CNFP-40/1000, the smaller pore CNFP-40/300 has 73% greater sulfur mass loading but corresponds to 278% greater pore-volume occupation due to the smaller pore radius. Remaining void space in S@CNFPs is important to facilitate volume expansion and electrolyte diffusion. If pore volume is insufficient the electrode will suffer from electrolyte starvation and high concentration overpotentials.

Table 2. Average areal sulfur loadings in 1-ply CNFP electrodes.

Infiltration Time (h)	Areal Loading ($\text{mg}_{\text{sulfur}}/\text{cm}^2_{\text{CNFP}}$)		
	40/300	40/500	40/1000
2	2.5	1.9	1.1
6	6.1	3.7	1.7
18	10.2	6.7	3.0

The porous carbon network with minimal dead volume grants high volumetric sulfur loadings up to 1 g/cm^3 for 1-ply S@CNFP-40/300-18h (Table S3). However, areal sulfur loading is a more important metric to the design of practical Li-S battery cathodes. Average sulfur loadings for 1-ply CNFP samples are tabulated in Table 2, with the highest reaching 10.2 mg/cm^2 for S@CNFP-40/300-18h. Novel thin-film and composite electrodes may exhibit high gravimetric

and volumetric capacities but lack practical applicability due to low areal weight loadings. Increasing sulfur loadings by producing thick-film composite electrodes are prone to cracking and separation from the current collector. In contrast, the interconnected mesoporous carbon framework and carbon fiber backbone of CNFPs act as an integrated current collector and allow for thick electrode structures without sacrificing electronic conductivity.

3.2 Li–S battery performance

Multiple variants of sulfur-loaded CNFPs were incorporated into Li–S coin cells and electrochemically evaluated by galvanostatic charge–discharge. These cells show the two typical discharge plateaus associated with sulfur reduction to soluble, anionic polysulfides commencing at ~ 2.4 V followed by reduction to insoluble Li_2S at ~ 2.1 V (Figure 4). The re-dox activity at these voltages is further revealed with dQ/dV in Figure S4.




Figure 4. Charge–discharge curves of S@CNFPs with different sulfur infiltration durations.

Specific capacity metrics in sulfur-cathode studies are often reported in terms of $\text{mAh/g}_{\text{sulfur}}$, which only considers the mass of the active sulfur material. This method of calculation can often be misleading, sometimes overstating the capabilities of certain cathode materials that have efficient sulfur utilization but require significant additional mass from other electrode components. Here, we also tabulate specific capacity normalized to total weight of the CNFP-based electrode ($\text{mAh/g}_{\text{electrode}}$), which includes the mass of the infiltrated sulfur, the carbon nanofoam domains, and the supporting carbon fibers (which themselves do not store significant sulfur, as noted above). Charge–discharge cycling at a 0.1C ($0.167 \text{ A/g}_{\text{sulfur}}$) rate illustrates general trends in measured capacity as a function of CNFP pore structure and sulfur loading (Figure 5a). For example, CNFPs with intermediate sulfur loadings at 35–50wt% exhibit the best specific capacity values (up to $350 \text{ mAh/g}_{\text{electrode}}$ at cycle 30 for S@CNFP-40/500-6h at 48 wt% sulfur), while capacity rapidly decreases as loadings surpass ~50%, as seen for S@CNFP-40/300-6h and S@CNFP-40/500-18h.

Sulfur utilization, the fraction of sulfur that is redox active, is another important metric to track across this series. Figure 5b shows that highest sulfur utilization is realized at low weight loadings (e.g., S@CNFP-40/1000-2h), but at the expense of overall specific capacity. We find an optimal balance of utilization and electrode capacity with S@CNFP-40/500-6h at 48% S loading and $719 \text{ mAh/g}_{\text{sulfur}}$ at cycle 30. We attribute decreasing sulfur utilization at high loadings to increased electronic resistance from thicker sulfur coatings, as evidenced by impedance spectroscopy (Figure S6). The decrease in both total capacity and sulfur utilization at the highest weight loadings is likely caused by impeded electrolyte transport from pore narrowing. Insufficient electrolyte flux results in local saturation of soluble polysulfide species during discharge, which increases overpotential due to reduced conductivity and increased viscosity (see S@CNFP-40/300-6h, S@CNFP-40/300-18h, and S@CNFP-40/500-18h; Figure 4).^{25, 51} Our findings show that a balance

of electrode pore volume and sulfur loading is needed to achieve optimal specific capacity for given electrochemical conditions. Prior studies with mesoporous carbons have shown that partial sulfur fillings lead to improved performance.²⁷⁻²⁹ Upon identifying S@CNFP-40/500-6h as a pore-solid architecture that balances sulfur utilization and electrode specific capacity, we cycled additional cells for 100 cycles demonstrating good capacity retention and high coulombic efficiency (>95%).




Figure 5. (a) Summary of Li-S cycling capacities at 0.1C for CNFPs using different sulfur infiltration durations and (b) their corresponding gravimetric capacities per weight sulfur and per total electrode weight after cycle 30 versus their sulfur weight loadings. (c) Long-term cycling of the S@CNFP-40/500-6h sample to 100 cycles. Results are summarized in Table S4, and cycling capacity normalized to sulfur mass is shown in Figure S5.

The role of pore structure in transport and concentration polarization are further exacerbated at higher rates. In order to explore rate capability within varied pore structures, we selected CNFPs of similar sulfur loadings—S@CNFP-40/300-2h (37 wt% S), S@CNFP-40/500-

6h (48 wt% S), and S@CNFP-40/1000-18h (40 wt% S)—probing specific currents of 0.1, 0.2, 0.5, 1, 2, and 5 A/g_{sulfur} (0.06, 0.12, 0.3, 0.6, 1.2, and 3 C), followed by a return to 0.1 A/g_{sulfur} (0.06C) to assess the damage issued as a result of high rate excursion; see Figure 6a. At moderate rates, the intermediate pore-sized S@CNFP-40/500-6h demonstrates superior specific capacity as observed in Figure 5. Yet, sharp capacity loss is observed at 1 A/g_{sulfur} where transport limitations dominate. Overall, we see that CNFPs with larger pores (mix of mesopores and macropores) support moderately lower capacity but better rate capability, while CNFPs that are primarily mesoporous (2-50 nm) deliver higher capacity at low rates but inferior rate performance. The Ragone plot in Figure 6b summarizes the tradeoff in capacity and rate for this series, highlighting the high specific energy that can be achieved with S@CNFP cathodes at moderate power requirements, but also showcasing the ability for respectable energy density under high power conditions (i.e., 578 Wh/kg_{electrode} at 166 W/kg and 388 Wh/kg_{electrode} at 700 W/kg).




Figure 6. (a) Rate study of Li–S coin cells from 0.1A/g_{sulfur} to 5A/g_{sulfur}, (b) the Ragone plot produced from the third cycle of each rate, and (c–e) their corresponding charge–discharge curves.

Looking more closely at the charge–discharge voltage profiles, increasing polarization is evident as the discharge rate is increased for S@CNFP-40/300 and S@CNFP-40/500, as demonstrated by the decrease in the discharge voltage at higher rates, possibly arising from electrolyte starvation due to small pore volume (Figure 6 c–e). We calculated the moles of lithium ions residing in internal void volume and divided by the number of moles required to satisfy the specific capacity recorded at $0.1 \text{ A/g}_{\text{sulfur}}$, determining ratios of 0.11, 0.10, and 0.33 for S@CNFP-40/300-2h, S@CNFP-40/500-6h, and S@CNFP-40/1000-18h, respectively. Significantly more lithium from outside the electrode must diffuse into the voids of S@CNFP-40/300 and S@CNFP-40/500 compared to S@CNFP-40/1000 with larger pore size, leading to poor sulfur utilization and low energy density at high power demand. The effect that pore size has on concentration polarization at high rate in CNFPs is analogously observed in aqueous lithium-ion electrochemical capacitors.⁴³

In some discharge profiles we observe a dip in voltage between these two plateaus, a feature ascribed to the nucleation of solid lithium sulfide products, which is strongly influenced by kinetic transport limitations. At a modest rate of $0.5 \text{ A/g}_{\text{sulfur}}$ the voltage minima of this transition are 2.03, 2.00, and 2.06 V for S@CNFP-40/300-2h, S@CNFP-40/500-6h, and S@CNFP-40/1000-18h, respectively. Prior studies conclude that sulfide nucleation is limited by mass transfer rather than electron transfer.^{51, 52} Pore clogging in S@CNFP-40/500-6h restricts ion transport to a greater extent and generates higher concentration polarization, in turn lowering specific energy more severely when diffusion limitations dominate at higher rate.

3.3 Multi-ply carbon nanofoam papers

The thickness of CNFPs can be varied based on the number of carbon fiber paper plies used during the RF-sol infiltration step in increments beyond the “1-ply” used for CNFPs discussed

thus far.⁴³ As a means to further increase areal-capacity metrics, we fabricate 2-ply and 3-ply CNFPs (Figure 7a), which exhibit average thickness values of 210 and 290 μm , respectively, compared to 120 μm for 1-ply CNFP. The nonlinearity in thickness per ply results from increased clamping force on RF sheets during curing due to increased ply count. Subjecting these multi-ply CNFPs to vapor-phase sulfur infiltration for 6 h decreases sulfur loading as thickness increases (Table S5). Non-constant weight loading suggests that sulfur loading depends on total surface area, not just specific surface area, thus longer vapor exposure times are required for thicker electrodes. Additionally, the 2- and 3-ply CNFPs have a larger mass fraction of inactive carbon fiber due to their smaller thicknesses.




Figure 7. (a) Schematic of multi-ply CNFPs and (b) the gravimetric, volumetric, and areal capacities of these multi-ply papers.

The areal discharge capacity of multi-ply S@CNFP-40/500-6h at a rate of 0.1C (Figure 7b) is highest for 3-ply S@CNFP-40/500-6h at 4.1 mAh/cm². Tradeoffs appear between gravimetric and

volumetric capacity due to decreased sulfur loading and greater inactive carbon fiber content. This areal capacity is much higher compared to carbon-based powder composite cathodes with lower areal sulfur loadings (Table S6). The scalable and tunable properties of the CNFP proves valuable to applications where footprint is the dominant constraint. We also note the impressive tap density of the device-ready 1-ply CNFP supports high volumetric capacity of 209 mAh/cm³.

4. Conclusions

Carbon nanofoam papers are efficacious cathode architectures for rechargeable Li–S cells. The adaptable nature of the CNFP synthesis permits pore structure tuning to optimize sulfur loading and ultimately balance such electrochemical performance metrics as gravimetric/volumetric/areal capacity and rate capability. In contrast with the ad hoc structures of most conventional Li–S cathodes, the CNFP provides the benefits of designer pore–solid architectures expressed in freestanding form factors that are device ready and require minimal additional processing or components. The ability to scale the CNFP in thickness while maintaining electronic and ionic continuity through the volume of the architecture electrode also enables high areal capacity, which is becoming an important performance metric for many energy-storage applications.

References

1. P. G. Bruce, S. A. Freunberger, L. J. Hardwick and J.-M. Tarascon, *Nature Materials*, 2012, **11**, 19-29.
2. A. Fotouhi, D. J. Auger, L. O'Neill, T. Cleaver and S. Walus, *Energies*, 2017, **10**, 1937.
3. K. Zhu, C. Wang, Z. Chi, F. Ke, Y. Yang, A. Wang, W. Wang and L. Miao, *Frontiers in Energy Research*, 2019, **7**, 123.
4. M. Wang, X. Xia, Y. Zhong, J. Wu, R. Xu, Z. Yao, D. Wang, W. Tang, X. Wang and J. Tu, *Chemistry – A European Journal*, 2019, **25**, 3710-3725.
5. S. Xin, L. Gu, N.-H. Zhao, Y.-X. Yin, L.-J. Zhou, Y.-G. Guo and L.-J. Wan, *Journal of the American Chemical Society*, 2012, **134**, 18510-18513.
6. B. Zhang, X. Qin, G. R. Li and X. P. Gao, *Energy & Environmental Science*, 2010, **3**, 1531-1537.
7. R. Carter, L. Oakes, N. Muralidharan, A. P. Cohn, A. Douglas and C. L. Pint, *ACS Applied Materials & Interfaces*, 2017, **9**, 7185-7192.
8. M. Li, R. Carter, A. Douglas, L. Oakes and C. L. Pint, *ACS Nano*, 2017, **11**, 4877-4884.

9. M. Li, X. Zhou, X. Ma, L. Chen, D. Zhang, S. Xu, D. Duan, C. Chen, Q. Yuan and S. Liu, *Chemical Engineering Journal*, 2021, **409**, 128164.
10. Y.-J. Yen and S.-H. Chung, *Chemical Communications*, 2021, **57**, 2009-2012.
11. J. Kim, Y. Kang, S.-W. Song and J. Suk, *Electrochimica Acta*, 2019, **299**, 27-33.
12. T. Wang, Q. Zhang, J. Zhong, M. Chen, H. Deng, J. Cao, L. Wang, L. Peng, J. Zhu and B. Lu, *Advanced Energy Materials*, 2021, **11**, 2100448.
13. A. Fu, C. Wang, F. Pei, J. Cui, X. Fang and N. Zheng, *Small*, 2019, **15**, 1804786.
14. S. Li and Z. Fan, *Energy Storage Materials*, 2021, **34**, 107-127.
15. Y. Xu, Y. Wen, Y. Zhu, K. Gaskell, K. A. Cychosz, B. Eichhorn, K. Xu and C. Wang, *Advanced Functional Materials*, 2015, **25**, 4312-4320.
16. T. Cleaver, P. Kovacic, M. Marinescu, T. Zhang and G. Offer, *Journal of The Electrochemical Society*, 2018, **165**, A6029.
17. N. Kang, Y. Lin, L. Yang, D. Lu, J. Xiao, Y. Qi and M. Cai, *Nature Communications*, 2019, **10**, 4597.
18. Y.-T. Liu, S. Liu, G.-R. Li and X.-P. Gao, *Advanced Materials*, 2021, **33**, 2003955.
19. Q. Hu, H. Dong, B. Wang, C. Yang, X. Wang, J. Lu, Y. Hong and L. Zhang, *Electrochimica Acta*, 2021, **377**, 138063.
20. C. Kensy, D. Leistenschneider, S. Wang, H. Tanaka, S. Dörfler, K. Kaneko and S. Kaskel, *Batteries & Supercaps*, 2021, **4**, 612-622.
21. E. Markevich, G. Salitra, S. Bretler, H. Yoshida, S. Sawada and D. Aurbach, *Journal of Power Sources*, 2022, **552**, 232250.
22. A. D. Dysart, J. C. Burgos, A. Mistry, C.-F. Chen, Z. Liu, C. Hong, P. B. Balbuena, P. P. Mukherjee and V. G. Pol, *ECS Meeting Abstracts*, 2016, **MA2016-03**, 403.
23. C. Lv, H. Cao, W. Deng, M. Zhao, Y. Miao, C. Guo, P. Liu and Y. Wu, *Dalton Transactions*, 2023, **52**, 4700-4707.
24. C.-C. Wu and S.-H. Chung, *Journal of Power Sources*, 2023, **566**, 232944.
25. R. Carter, D. EJORH, K. Share, A. P. Cohn, A. Douglas, N. Muralidharan, T. M. Tovar and C. L. Pint, *Journal of Power Sources*, 2016, **330**, 70-77.
26. M. M. Gaikwad, K. K. Sarode, A. D. Pathak and C. S. Sharma, *Chemical Engineering Journal*, 2021, **425**, 131521.
27. L. Li, Z. Ma and Y. Li, *Carbon*, 2022, **197**, 200-208.
28. X. Li, Y. Cao, W. Qi, L. V. Saraf, J. Xiao, Z. Nie, J. Mietek, J.-G. Zhang, B. Schwenzer and J. Liu, *Journal of Materials Chemistry*, 2011, **21**, 16603-16610.
29. S. Zhang, A. Ikoma, Z. Li, K. Ueno, X. Ma, K. Dokko and M. Watanabe, *ACS Applied Materials & Interfaces*, 2016, **8**, 27803-27813.
30. R. Carter, L. Oakes, A. Douglas, N. Muralidharan, A. P. Cohn and C. L. Pint, *Nano Letters*, 2017, **17**, 1863-1869.
31. M. Nojabaei, B. Sievert, M. Schwan, J. Schettler, F. Warth, N. Wagner, B. Milow and K. A. Friedrich, *Journal of Materials Chemistry A*, 2021, **9**, 6508-6519.
32. S. A. Al-Muhtaseb and J. A. Ritter, *Advanced Materials*, 2003, **15**, 101-114.
33. M. Antonietti, N. Fehler and T.-P. Fellinger, *Chemistry of Materials*, 2014, **26**, 196-210.
34. F. Li, L. Xie, G. Sun, Q. Kong, F. Su, Y. Cao, J. Wei, A. Ahmad, X. Guo and C.-M. Chen, *Microporous and Mesoporous Materials*, 2019, **279**, 293-315.
35. A. M. ElKhatat and S. A. Al-Muhtaseb, *Advanced Materials*, 2011, **23**, 2887-2903.
36. A. Kausar, I. Ahmad, T. Zhao, M. H. Eisa and O. Aldaghri, *Journal*, 2023, **3**, 37-56.
37. S.-Y. Chen and S.-H. Chung, *Journal*, 2021, **11**.
38. R. H. DeBlock, R. Carter, M. J. Lefler, M. B. Sassin, D. R. Rolison and J. W. Long, *Journal of The Electrochemical Society*, 2022, **169**, 060514.

39. R. H. DeBlock, J. S. Ko, M. B. Sassin, A. N. Hoffmaster, B. S. Dunn, D. R. Rolison and J. W. Long, *Energy Storage Materials*, 2019, **21**, 481-486.
40. J. S. Ko, M. B. Sassin, J. F. Parker, D. R. Rolison and Jeffrey W. Long, *Sustainable Energy & Fuels*, 2018, **2**, 626-636.
41. J. C. Lytle, J. M. Wallace, M. B. Sassin, A. J. Barrow, J. W. Long, J. L. Dysart, C. H. Renninger, M. P. Saunders, N. L. Brandell and D. R. Rolison, *Energy & Environmental Science*, 2011, **4**, 1913-1925.
42. M. B. Sassin, S. G. Greenbaum, P. E. Stallworth, A. N. Mansour, B. P. Hahn, K. A. Pettigrew, D. R. Rolison and J. W. Long, *Journal of Materials Chemistry A*, 2013, **1**, 2431-2440.
43. M. B. Sassin, C. P. Hoag, B. T. Willis, N. W. Kucko, D. R. Rolison and J. W. Long, *Nanoscale*, 2013, **5**, 1649-1657.
44. M. B. Sassin, A. N. Mansour, K. A. Pettigrew, D. R. Rolison and J. W. Long, *ACS Nano*, 2010, **4**, 4505-4514.
45. A. E. Fischer, K. A. Pettigrew, D. R. Rolison, R. M. Stroud and J. W. Long, *Nano Letters*, 2007, **7**, 281-286.
46. A. E. Fischer, M. P. Saunders, K. A. Pettigrew, D. R. Rolison and J. W. Long, *Journal of The Electrochemical Society*, 2008, **155**, A246.
47. R. Carter, B. Davis, L. Oakes, M. R. Maschmann and C. L. Pint, *Nanoscale*, 2017, **9**, 15018-15026.
48. R. Carter, L. Oakes, N. Muralidharan and C. L. Pint, *The Journal of Physical Chemistry C*, 2017, **121**, 7718-7727.
49. L. Oakes, R. Carter and C. L. Pint, *Nanoscale*, 2016, **8**, 19368-19375.
50. A. E. Fischer, M. P. Saunders, J. C. Lytle, D. R. Rolison and J. Long, *ECS Transactions*, 2008, **6**, 159.
51. F. Y. Fan and Y.-M. Chiang, *Journal of The Electrochemical Society*, 2017, **164**, A917.
52. T. Zhang, M. Marinescu, S. Walus, P. Kovacic and G. J. Offer, *Journal of The Electrochemical Society*, 2018, **165**, A6001.