# Journal of Materials Chemistry A

## REVIEW

Check for updates

Cite this: J. Mater. Chem. A, 2023, 11, 5460

Received 5th December 2022 Accepted 23rd February 2023

DOI: 10.1039/d2ta09448g

rsc.li/materials-a

### 1. Introduction

Nuclear power is one of the most important low-carbon energy sources, which is used to currently generate  $\sim 10\%$  of the global electricity.1 However, the reprocessing of used fuel rods or severe nuclear accidents can produce radioactive gaseous fission products such as <sup>129/131</sup>I, <sup>127</sup>Xe, and <sup>85</sup>Kr.<sup>2-4</sup> Therefore, technologies are required to efficiently capture these radioactive wastes, particularly iodine, because of its high volatility and wellestablished adverse effects on human health. Among the iodine radioisotopes, <sup>129</sup>I has an extremely long half-life of 15.7 imes 10<sup>6</sup> years and a lasting environmental impact. Although <sup>131</sup>I has a relatively short half-life (approximately eight days), it requires to be immediately captured upon its release because it can damage the thyroid and interfere with the human metabolic process.5,6 The common forms of radioactive iodine in the offgases of nuclear power plants include molecular iodine  $(I_2)$ , organic iodides such as methyl iodide (CH<sub>3</sub>I) and ethyl iodide (CH<sub>3</sub>CH<sub>2</sub>I). Inorganic radioactive iodine-containing compounds, such as HI, HOI, and ICN, may also be present, but usually in vary small amounts.7-10 Because of the different physicochemical

# Adsorption-based capture of iodine and organic iodides: status and challenges

Tingting Pan, Kaijie Yang, Xinglong Dong 🕩 and Yu Han 🕩\*

Nuclear energy is a sustainable low-carbon energy source that plays an increasingly important role in supporting the progress of human society. However, there are safety issues associated with the operation of nuclear reactors. In particular, volatile radioactive elements, primarily <sup>129</sup> and <sup>131</sup>, in the form of molecular iodine (I2) or organic iodides (e.g., CH3I and CH3CH2I), are harmful for the environment and human health and must be removed before discharging the off-gas. Adsorption processes employing porous solid adsorbents to capture radioactive iodine compounds have attracted considerable attention owing to their simple operation and low maintenance cost and because they avoid the use of highly corrosive solutions. Despite the efforts devoted to developing novel adsorbents for iodine capture, certain critical issues related to practical applications have been overlooked. This review summarizes the adsorption mechanisms employed to capture I<sub>2</sub> and CH<sub>3</sub>I, focusing on the different adsorbent requirements. This review also compares the static and dynamic evaluation systems, analyzes the structure-function relationship under different testing conditions, and highlights the importance of using appropriate conditions to evaluate adsorbents. Moreover, the simultaneous capture of I<sub>2</sub> and CH<sub>3</sub>I is discussed, which is guite challenging but has been largely ignored in previous studies. Finally, this review outlines the challenges and opportunities in this field from the perspective of materials design and system evaluation, indicating that properly designing adsorbents to provide sufficient chemisorption sites may be the only way to meet the practical application requirements.

> properties of molecular iodine and organic iodides, specially designed absorption or adsorption systems are needed to achieve the desired capture efficiency and capacity.

ROYAL SOCIETY OF CHEMISTRY

View Article Online

View Journal | View Issue

Liquid scrubbing processes have been used to capture radioactive  $I_2$  and other I-containing compounds from the off-gas, requiring highly corrosive solutions and high maintenance costs.<sup>11</sup> Therefore, adsorption-based radioiodine capture has attracted considerable attention (Fig. 1). Activated carbon and



Fig. 1 Schematic of the components in nuclear off-gas generated during the reprocessing process and emerging iodine adsorbents.

Advanced Membranes and Porous Materials (AMPM) Center, Physical Sciences and Engineering Division, King Abdullah University of Science and Technology (KAUST), Thuwal, 23955-6900, Saudi Arabia. E-mail: yu.han@kaust.edu.sa

### Review

zeolite materials are the most popular industrial adsorbents, but they have low adsorption capacities for iodine and organic iodides. Hence, they cannot meet the requirements of practical applications.12-15 Emerging porous materials, such as metal organic frameworks (MOFs),16-20 porous organic polymers (POPs),<sup>21-26</sup> and covalent organic frameworks (COFs),<sup>27-29</sup> provide new platforms for developing high-performance adsorbents because of their diverse structures, large surface areas, tunable pore sizes, and designable surface functionalities. Many studies have examined iodine capture based on these emerging adsorbent materials.<sup>30-32</sup> However, the conditions most studies used to evaluate adsorbents were not related to practical applications. In particular, many studies measured the I2 adsorption capacity of the developed adsorbents using saturated I2 vapor, ignoring that the actual concentration of I<sub>2</sub> in the off-gas stream is orders of magnitude lower. Furthermore, most studies have focused only on the I<sub>2</sub> adsorption and ignored the coexisting organic iodides. Adsorbents are difficult to assess without standardizing the measurement conditions because the adsorption capacity is closely related to the type and concentration of the adsorbate. Moreover, although multiple review articles have summarized the adsorption capacities of various reported adsorbent materials, there has been no systematic analysis of the differences in the adsorption mechanism of iodine and organic iodides.

This review article differs from the previous ones in the following ways. First, this article is structured based on the adsorption mechanism rather than the material type, in which iodine adsorption and organic iodide adsorption are separately discussed because of their different requirements for the adsorbent. Second, this article critically points out that the experimental conditions used in most studies were different from actual off-gas treatment applications and analyzes the origin of unreasonably high I<sub>2</sub> adsorption capacities reported in the literature. Third, this article highlights the importance of evaluating adsorbent materials for simultaneous capture of iodine and organic iodides at low concentrations (<150 ppmv), high temperatures (~150 °C), and dynamic conditions, which has largely been overlooked in previous original research and review articles. Lastly, this article discusses the challenges and future opportunities in this field from material design and performance evaluation perspectives.

# 2. Mechanisms for molecular iodine capture

Molecular iodine is the primary component of radioactive iodine species in off-gas, which can be captured chemically or physically using various mechanisms, including redox reactions, coordination interactions, electrophilic aromatic substitution, Lewis acid-base interactions, Coulomb interactions, hydrogen bonding, van der Waals interactions, and hydrophobic interactions.

### 2.1 Redox reactions

Metal-containing adsorbents can capture  $I_2$  *via* redox reactions. Ag is the most commonly used metal because it can specifically react with  $I_2$ . Among the various support materials,<sup>13-15</sup> zeolites are used widely because of their ion-exchange ability and inherent porosity, allowing for the easy loading and high dispersion of silver. The capture of  $I_2$  by Ag-zeolites involves the following reactions, depending on the state of Ag:<sup>33</sup>

$$I_2 + 2Ag^0 \rightarrow 2AgI$$
 (1)

$$I_2 + 2Ag^+ + H_2O \rightarrow AgI + AgIO + 2H^+$$
 (2)

$$AgIO + O_2 \rightarrow AgIO_3 \tag{3}$$

The standard practice is to reduce the Ag species on the adsorbent to  $Ag^0$  prior to use for  $I_2$  capture, and studies have been performed to understand the respective roles of  $Ag^0$  and  $Ag^+$  in this process. For example, Nenoff *et al.* examined the distribution and structure of AgI formed in the Ag-MOR zeolite using a differential pair distribution function method.<sup>34</sup> They reported that for reduced Ag-MOR (Ag<sup>0</sup>-MOR), two AgI phases are formed after  $I_2$  capture, *i.e.*,  $\alpha$ -AgI clusters in the zeolite pores and  $\gamma$ -AgI nanoparticles on the surface. For unreduced Ag-MOR (Ag<sup>+</sup>-MOR), all formed AgI was confined within the pores as  $\alpha$ -AgI clusters (Fig. 2a). These results suggest that  $Ag^+$ -MOR is superior to  $Ag^0$ -MOR for the long-term storage of  $I_2$  because it can trap all captured  $I_2$  in the zeolite pores.

In addition to  $Ag^+$  and  $Ag^0$ ,  $Ag_2O$  can capture  $I_2$ .<sup>35,36</sup> However, the reactivity of  $Ag_2O$  towards  $I_2$  is controversial. Nan *et al.* suggested that the decreased adsorption capacity of  $Ag^0$ -MOR above 150 °C in the presence of water is associated with the oxidation of  $Ag^0$  to  $Ag_2O$  or AgOH.<sup>15</sup> Holladay *et al.* attributed the adverse effects of NO<sub>2</sub> on  $I_2$  adsorption to it slowly oxidizing  $Ag^0$  in  $Ag^0$ -MOR.<sup>37</sup> In general, the primary advantage of Agzeolites compared to other adsorbents for  $I_2$  capture is their high capacity at high temperatures because of the chemical reaction-based capture mechanism. Nevertheless, Ag-zeolites have limitations such as high cost and potential environmental toxicity.

Other metals have been assessed as alternatives to Ag for  $I_2$  capture. Huve *et al.* compared the Gibbs free energies of iodides and oxides of different metals (Ag, Cu, Hg, Fe, Tl, Sn, Cd, Pb, and Ti). They reported that oxides form preferentially over halides for all metals except Ag and Hg.<sup>38</sup> In recent years, Bi-



Fig. 2 (a) Schematic of the I<sub>2</sub> capture process using Ag-MOR zeolite as the adsorbent. For Ag<sup>0</sup> sites, I<sub>2</sub> adsorption leads to the formation of two AgI phases, *i.e.*,  $\alpha$ -AgI clusters in the zeolite pores and  $\gamma$ -AgI nanoparticles on the zeolite surface. For Ag<sup>+</sup> sites, only  $\alpha$ -AgI clusters are formed in the pores. Reproduced with permission from ref. 34. Copyright 2010, American Chemical Society. (b) Structure model of MOF MFM-300(V<sup>III</sup>) and the redox reaction upon I<sub>2</sub> adsorption. Color code: blue, V<sup>III</sup>; red, O; gray, C; white, H.<sup>43</sup>

based materials are becoming promising alternatives to Agbased adsorbents because they incur lower production costs while maintaining high  $I_2$  capture capacity.<sup>39-41</sup> The reactions of Bi with  $I_2$  are as follows:

$$Bi + 1.5I_2 \rightarrow BiI_3 \tag{4}$$

$$2\text{BiI}_3 + \text{O}_2 \rightarrow 2\text{BiOI} + 2\text{I}_2 \tag{5}$$

$$5BiOI + O_2 \rightarrow Bi_5O_7I + 2I_2 \tag{6}$$

Yim *et al.* used thiol-functionalized mesoporous silica SBA-15 to immobilize Bi for capturing I<sub>2</sub> vapor.<sup>39</sup> The prepared Bi-SBA-15 outperformed Ag-zeolites in terms of I<sub>2</sub> uptake capacity at 150 °C. However, as the temperature was increased to 250 °C, the I<sub>2</sub> uptake of Bi-SBA-15 sharply decreased to ~50% of Ag-X zeolite.<sup>42</sup> This reversal in adsorption capacity may be attributed to two reasons. The chemical bond between bismuth and sulfur is less stable than that between Ag and zeolite, which breaks at 250 °C. Moreover, the Gibbs free energy of BiI<sub>3</sub> is less than that of AgI at high temperatures.

Metal sites in redox-active MOFs can capture  $I_2$  *via* redox reactions. Schröder *et al.* examined the forms of adsorbed iodine in MFM-300(V<sup>III</sup>) and its oxidized analogue, MFM- $300(V^{IV})$ .<sup>43</sup> A redox reaction occurred when MFM-300(V<sup>III</sup>) was used as the adsorbent, as evidenced by the generation of  $I_3^-$  and  $V^{IV}$  (Fig. 2b). However,  $I_2$  was only physically adsorbed when MFM-300 (V<sup>IV</sup>) was used as the adsorbent because the highvalence metal sites (V<sup>IV</sup>) could not be oxidized. In this study, the difference in the  $I_2$  adsorption capacity between the two adsorbents was insignificant because, under the measurement conditions used (343 K; high  $I_2$  concentrations), the  $I_2$  uptake was primarily determined by the pore volume of the adsorbent rather than the adsorbent/adsorbate interaction strength.

### 2.2 Coordination interactions

In addition to redox reactions, the metal sites in adsorbents can capture I<sub>2</sub> via coordination interactions if they are coordinately unsaturated. For example, Baladi et al. reported that polymers containing three-coordinated Cu<sup>+</sup> are favorable for I<sub>2</sub> adsorption, while those with similar structures but with fourcoordinated Cu<sup>+</sup> barely adsorb I2.44 Similarly, coordinately unsaturated (open) metal sites in MOF materials have been used for I<sub>2</sub> capture. The MOF  $Co_2(p$ -DOBDC) (p-DOBDC<sup>4-</sup> = 2,5dioxo-1,4-benzenedicarboxylate) has open Co sites that can adsorb I2 in an end-on configuration with a Co-I-I angle of 123°, as determined via single-crystal X-ray diffraction (SXRD) (Fig. 3a).<sup>45</sup> As per the studies of the I<sub>2</sub> coordination behaviors in organometallics, I<sub>2</sub> can act as a donor or an acceptor, depending on the nature of the metal center.<sup>46</sup> When I<sub>2</sub> acts as the acceptor, it bonds with the metal center collinearly using the  $\sigma^{*}(I-I)$ orbital as the acceptor orbital. When I2 acts as the donor, it exhibits a bent coordination bond with the metal center using a p-type lone pair localized on one of the two iodine atoms as a dominant donation. For  $I_2$ -loaded  $Co_2(p$ -DOBDC), the determined bond angle suggested that I2 acted as the donor while the open Co sites acted as acceptors.



View Article Online



Fig. 3 (a) Structure of  $Co_2(p-DOBDC)$  ( $p-DOBDC^{4-} = 2,5$ -dioxo-1,4benzenedicarboxylate) with 10% I<sub>2</sub> loading, where I<sub>2</sub> coordinately interacts with open Co sites in an end-on configuration. Reproduced with permission from ref. 45. Copyright 2019, American Chemical Society. (b and c) Structures of  $Co_2(m-DOBDC)$  (m-DOBDC<sup>4-</sup> = 4,6dioxo-1,3-benzenedicarboxylate) with 10 wt% (b) and 100 wt% (c) I2 loading. Reproduced with permission from ref. 45. Copyright 2019, American Chemical Society. At 10 wt% I<sub>2</sub> loading, m-DOBDC chemically adsorb I2 via an electrophilic aromatic substitution reaction, with the remaining I<sup>-</sup> coordinated to the open Co site. At 100% I<sub>2</sub> loading, additional I<sub>2</sub> coordinates with residual open Co sites and bridges the neighboring  $I^-$ , forming triiodides  $(I_3^-)$ . (d) Scheme of the electrophilic aromatic substitution reaction between I<sub>2</sub> and *m*-DOBDC<sup>4-</sup>. Reproduced with permission from ref. 45. Copyright 2019, American Chemical Society. (e) A reaction mechanism proposed for the iodination reaction between I2 and 2,6 position of BODIPY (4,4-difluoro-4bora-3a,4a-diaza-s-indacene). Reproduced with permission from ref. Copyright 2013, Royal Society of Chemistry. Color code: cyan, Co; red, O; purple, I; gray, C; white, H.

Because the real-world nuclear off-gas contains a considerable amount of water, Nenoff *et al.* examined the I<sub>2</sub> adsorption behavior of HKUST-1 using a mixture of I<sub>2</sub> and H<sub>2</sub>O.<sup>47</sup> They reported that the coordinated water molecules impede the direct interaction of I<sub>2</sub> with the open sites, and these water molecules "hold" I<sub>2</sub> molecules *via* weak interactions with I···O distances of 3.46–3.84 Å. The adsorbed I<sub>2</sub> molecules form a hydrophobic barrier that minimizes H<sub>2</sub>O sorption. To summarize, HKUST-1 exhibits an I<sub>2</sub>/H<sub>2</sub>O selectivity of 1.5 when considering the same concentrations of I<sub>2</sub> and H<sub>2</sub>O in the mixture.

### 2.3 Electrophilic aromatic substitution

Electrophilic aromatic substitution reactions involve the replacement of a hydrogen atom on a benzene ring with an electrophile. As an electrophile,  $I_2$  can be captured by adsorbents containing suitable functional groups *via* such reactions, where the substituent groups on the aromatic ring directly affect the reactive site. For example, when the MOF  $Co_2(m-DOBDC)$  (*m*-DOBDC<sup>4-</sup> = 4,6-dioxo-1,3-benzenedicarboxylate) was used to capture  $I_2$ , in addition to the Co sites, the organic linker *m*-DOBDC could adsorb  $I_2$  chemically *via* an electrophilic aromatic substitution reaction (Fig. 3b).<sup>45</sup> However, the organic linker in  $Co_2(p$ -DOBDC) could not react with  $I_2$  (Fig. 3a) because the different distribution of substituent groups results in different reactivity, *i.e.*, *m*-DOBDC is more electron-rich at the fifth position of the benzene ring than *p*-DOBDC.

#### Review

During I<sub>2</sub> adsorption on Co<sub>2</sub>(*m*-DOBDC), the open Co sites and electron-rich ligands cooperatively polarize I<sub>2</sub> to the  $[I^{\delta^+}-I^{\delta^-}]$  state at a low I<sub>2</sub> loading. Subsequently, the aryl C5–H bond reacts with I<sup> $\delta^+$ </sup> to form a C–I bond, and the remaining I<sup>-</sup> coordinated to the open Co site (Fig. 3b and d).<sup>45</sup> At a higher I<sub>2</sub> loading, additional I<sub>2</sub> coordinates with the residual open Co sites and bridges the neighboring I<sup>-</sup>, thus forming triiodides (I<sub>3</sub><sup>-</sup>) (Fig. 3c).

The 2,6-positions of 4,4-difluoro-4-bora-3a,4a-diaza-s-indacene (BODIPY) bearing a lower positive charge can undergo rapid iodination when exposed to I<sub>2</sub> at room temperature (Fig. 3e).<sup>48</sup> Therefore, Zhu *et al.* synthesized two BODIPY based conjugated porous polymers, BDP-CPP-1 and BDP-CPP-2.<sup>49</sup> They hypothesized that in BDP-CPP-2, ethyl groups were substituted at the 2,6positions of BODIPY, therefore these positions were not useful for electrophilic aromatic substitution. They observed that BDP-CPP-1 could adsorb additional I<sub>2</sub> than BDP-CPP-2 (2.83 *vs.* 2.23 g g<sup>-1</sup>) and attributed this to the additional adsorption capacity of BDP-CPP-1 associated with electrophilic aromatic substitution. However, they ignored the difference in the number of functional groups per unit mass between the two polymers.

Although chemisorption based on covalent C–I bond formation prevents the release of adsorbed  $I_2$ , it poses challenges to the regeneration of the organic adsorbent. In contrast, inorganic adsorbents that chemisorb  $I_2$  by forming AgI can be regenerated *via* calcination in a reducing atmosphere.<sup>50</sup>

### 2.4 Lewis acid-base interactions

Molecular iodine is widely used as a mild Lewis acid catalyst for various organic reactions. Therefore,  $I_2$  capture can be achieved using adsorbents with basic groups *via* Lewis acid-base interactions.<sup>51</sup> Neutral charge-transfer complexes (D·I<sub>2</sub>) or charged polyiodides, such as  $I_3^-$  and  $I_5^-$ , can be generated depending on the donor ability of the Lewis bases (D).<sup>52</sup>

X-ray photoelectron spectroscopy (XPS) and Raman spectroscopy are the most commonly used characterization tools for identifying the formed iodine species. However, the assignments of the XPS peaks for different iodine species ( $I_2$ ,  $I_3^-$  and  $I_5^-$ ) are inconsistent in the literature. For example, peaks at 630.2 and 618.6 eV were assigned to  $I_2$  in certain studies<sup>49,53,54</sup> but to  $I_3^-$  in others.<sup>55,56</sup> By comparison, Raman spectroscopy is a more reliable approach for distinguishing the formed iodine species. When neutral D·I<sub>2</sub> complexes are formed, the characteristic Raman band of solid  $I_2$  at 180 cm<sup>-1</sup> is expected to move toward a lower frequency (Fig. 4a). When charged polyiodides are formed,  $I_3^$ exhibits a symmetric stretching band at ~110 cm<sup>-1</sup> and an asymmetric stretching band at ~140 cm<sup>-1</sup>, while the band around 160 cm<sup>-1</sup> is usually assigned to  $I_5^-$  species (Fig. 4b).<sup>57</sup>

Although the generation of negatively charged polyiodides is generally accepted, there is no consensus on the species balancing of these negative charges. In previous studies, positively charged species, such as  $(D-I)^+$  (Fig. 4c)<sup>58-60</sup> and  $D_2^+$  (Fig. 4d),<sup>61,62</sup> were proposed as counter cations.

The Lewis basic sites commonly incorporated into adsorbents for  $I_2$  capture can be divided into different categories (see Fig. 5), which are separately discussed below.



Fig. 4 (a) Raman spectra of AlOC-27, AlOC-28,  $I_2@AlOC-27$ -NC,  $I_2@AlOC-28$ -NC, and solid  $I_2$ . In the spectra of  $I_2@AlOC-27$ -NC and  $I_2@AlOC-28$ -NC, the peak at 180 cm<sup>-1</sup> assigned to solid  $I_2$  was red-shifted, indicating the formation of neutral charge transfer complex D·I<sub>2</sub>. Reproduced with permission from ref. 73. Copyright 2021, American Chemical Society. (b) Raman spectra of pure  $I_2$ , pristine COF-TAPT, and  $I_2$ -saturated COF-TAPT. In the spectra of  $I_2@COF-TAPT$ , peaks attributed to  $I_3^-$  and  $I_5^-$  appeared, indicating the formation of charged polyiodides in COF-TAPT. Reproduced with permission from ref. 99. Copyright 2022, Springer Nature. (c and d) The interaction mechanisms between electron donors and  $I_2$  proposed by different researchers.<sup>58-62</sup>



**Fig. 5** Classification of Lewis basic sites used for  $I_2$  capture, including N/O/S-containing organic moleties, electron-rich  $\pi$  systems, chalcogens, and halide sites. (Top left panel) The upper figure is reproduced with permission from ref. 68. Copyright 2021, MDPI. The lower figure is reproduced with permission from ref. 67. Copyright 2019, Elsevier. (Top right panel) The upper figure is reproduced with permission from ref. 75. Copyright 2013, American Chemical Society. The lower figure is reproduced with permission from ref. 71. Copyright 2021, Wiley. (Bottom right panel) The upper figure is reproduced with permission from ref. 77. Copyright 2013, American Chemical Society. The lower figure is reproduced with permission from ref. 78. Copyright 2020, Elsevier. (Bottom left panel) The upper figure is reproduced with permission from ref. 80. Copyright 2017, Wiley. The lower figure is reproduced with permission from ref. 81 with permission from the Royal Society of Chemistry.

2.4.1 N/O/S-containing organic moieties. Organic moieties containing N/S/O heteroatoms can be incorporated into adsorbents to improve their I2 adsorption capacities. The heteroatom lone-pair electrons are transferred to the antibonding orbital  $(\sigma^*)$  of I<sub>2</sub>, thus forming charge-transfer complexes. This strategy has often been used in porous organic polymers (POPs) because their flexible structures can easily incorporate functional groups containing heteroatoms.<sup>63-68</sup> For example, Jiang et al. synthesized a number of COFs containing abundant tertiary amine active sites.<sup>69</sup> Owing to the high density of N sites, these COFs could efficiently capture iodine with the optimal adsorption capacity reaching 5.54 g  $g^{-1}$ . The adsorption strength was regulated by introducing different functional groups into the structure. Among the materials investigated, COF TAPD-DMTA with electron-donating methoxy groups demonstrated the highest binding energy with  $I_2$  (-17.32 kcal mol<sup>-1</sup>). However, COF TAPD-DHTA with hydroxyl groups had the lowest binding energy  $(-14.91 \text{ kcal mol}^{-1})$  because hydroxyl groups tend to form an intramolecular hydrogen bond with N active sites, thus resulting in a lower electron cloud density.

2.4.2 Electron-rich  $\pi$  systems. Organic moieties containing localized or conjugated  $\pi$  electrons, such as double bonds, triple bonds, benzene rings, and other aromatic conjugated structures, have been demonstrated to help promote I<sub>2</sub> adsorption.<sup>70-73</sup> The promotion effect is based on the Lewis acid–base interactions between the  $\pi$  electrons of the adsorbent and the  $\sigma^*$  orbital of I<sub>2</sub>. Porous aromatic frameworks (PAF-23, PAF-24, and PAF-25) incorporating ionic bonds, phenyl rings, and triple bonds exhibited high I<sub>2</sub> adsorption capacity.<sup>74</sup> As a control sample, PAF-21, structurally similar to PAF-23 but without triple bonds, was synthesized and assessed for I<sub>2</sub> adsorption. PAF-21 had a considerably lower I<sub>2</sub> uptake than PAF-23 (1.52 *vs.* 2.71 g g<sup>-1</sup>), indicating the important role of  $\pi$ electron donors in promoting I<sub>2</sub> adsorption.

Moreover, the pore geometry of the adsorbent material affects the distribution of adsorption sites and thus the binding strength to  $I_2$ . For example, Nenoff *et al.* reported that each  $I_2$  molecule adsorbed in MOF ZIF-8 simultaneously interacts with two opposing 2-methylimidazolate linkers to form an iodine-aromatic charge-transfer complex because of the special pore size and shape of ZIF-8.<sup>75</sup> The consequence of such multiple interactions is that ZIF-8 can firmly trap the adsorbed  $I_2$  until the framework decomposes at ~575 K.<sup>76</sup>

2.4.3 Chalcogens. Usually, chalcogens (S, Se, and Te) are incorporated into aerogels to form chalcogels for I<sub>2</sub> capture. Riley *et al.* fabricated various chalcogels (Co<sub>0.7</sub>Bi<sub>0.3</sub>MoS<sub>4</sub>, Co<sub>0.7</sub>Cr<sub>0.3</sub>-MoS<sub>4</sub>, Co<sub>0.5</sub>Ni<sub>0.5</sub>MoS<sub>4</sub>, PtGe<sub>2</sub>S<sub>5</sub>, and Sn<sub>2</sub>S<sub>3</sub>) and examined their I<sub>2</sub> adsorption capability.<sup>77</sup> Under their testing conditions, all chalcogels exhibited > 99.0% I<sub>2</sub> capture efficiency. The electron-donating property of chalcogens can be enhanced by designing the surrounding chemical environment. For example, a polymeric adsorbent for I<sub>2</sub> capture was prepared, in which phosphine chalcogenide ligands, P = X (X refers to O, S, and Se) could transfer  $\pi$ -electrons from adjacent aromatic rings to the captured I<sub>2</sub>, thereby increasing the interaction strength.<sup>78</sup> Consequently, the as-prepared polymer, POSS-TPPX, captured a considerable

amount of  $I_2$  (0.26 g g<sup>-1</sup>) even at a high temperature of 160 °C and an extremely low  $I_2$  concentration of 0.16 ppmv.

**2.4.4** Halide sites. Halide sites are electron-rich and can act as Lewis bases to facilitate I<sub>2</sub> adsorption.<sup>79,80</sup> Brunet *et al.* examined the I<sub>2</sub> adsorption on a porous MOF ([[ $(ZnI_2)_3(-TPT)_2 \cdot 5.5(C_6H_5NO_2)]_n$ ), in which iodides were attached to Zn to form metal iodide sites.<sup>81</sup> Single-crystal X-ray crystallography showed that the guest I<sub>2</sub> molecules were initially bound with two terminal iodides in the framework to form  $[I_4]^{2-}$  units. As adsorption progressed, each  $[I_4]^{2-}$  unit was converted to two less energetically favorable  $I_3^-$  groups to accommodate additional I<sub>2</sub> molecules.

### 2.5 Coulomb interactions

Another effective strategy to promote I<sub>2</sub> adsorption is to generate ionic sites in the adsorbent, which can bind the dynamically formed polyiodide anions via Coulomb interactions.21,74,82 However, despite the enhanced affinity to I<sub>2</sub>, the generation of ionic sites in various amorphous POPs via post-synthesis modification usually leads to a greatly reduced surface area and limited improvement in the I2 adsorption capacity. Xie et al. introduced ionic sites into crystalline COFs using a "multivariate" strategy combined with a post-synthesis modification to overcome this issue.83 The as-prepared ionic COF (iCOF-AB-50) combined large surface areas, high pore volume, and abundant binding sites, resulting in excellent I<sub>2</sub> capture performance under dynamic conditions (279 wt% at 25 °C). In particular, the significant promoting effect of the introduced ionic groups (quaternary ammonium) was attributed to their strong interactions with [I<sub>2</sub>Br]<sup>-</sup> and [2I<sub>2</sub>Br]<sup>-</sup> species via Coulomb forces.<sup>83</sup>

A highly stable ionic guanidinium-based COF (TGDM) was developed recently (Fig. 6).<sup>84</sup> TGDM has a high density of robust ionic sites owing to the reduced linker length and the unique stability of the guanidium moieties, which makes it particularly useful for I<sub>2</sub> capture at high temperatures. At 150 °C and 150 ppmv of I<sub>2</sub>, TGDM exhibited an I<sub>2</sub> adsorption capacity of ~30 wt%, which was considerably higher than that of multiple benchmark adsorbents.

### 2.6 Hydrogen bonding

Hydrogen bonding has been used to facilitate  $I_2$  adsorption. The polyiodide  $I_3^-$  is readily formed in multiple adsorbents, which



Fig. 6 Schematic of the design and synthesis of ionic COF TGDM and explanation of its high stability and  $I_2$  uptake mechanism. Reproduced with permission from ref. 84. Copyright 2022, American Chemical Society. The ionic sites (quaternary ammonium) strongly interact with  $[I_2CI]^-$  species through Coulomb forces.



**Fig. 7** (a) DFT-calculated hexamer model of MFP bound with  $I_3^-$ , the green iso-surface represents strong hydrogen bonding between I and  $-NH-/-NH_2-$ . Reproduced with permission from ref. 22. Copyright 2014, Royal Society of Chemistry. (b) Structure of MIL-53 (AI) with  $I_2$  adsorbed *via* hydrogen bonding with the hydroxyl groups. Reproduced with permission from ref. 86. Copyright 2017, American Chemical Society. (c) Schematic of triple-helical chains of iodine molecules formed within the channel of MOF MFM-300 (Sc) because of the strong inter-molecular interaction. Reproduced with permission from ref. 88. Copyright 2017, American Chemical Society.

can dissociate to I2 and I-, resulting in the release of I2.85 Lu et al. fabricated a melamine-based polymer (MFP) to stabilize the formed I3<sup>-</sup> species.<sup>23</sup> They claimed that the MFP could effectively capture I<sub>3</sub><sup>-</sup> via multiple synergistic NH…I hydrogen bonds, and the binding energy was approximately four times higher than that of the conventional Ag-I ionic bond (Fig. 7a). Hydrogen bonding can occur between the proton and the electronegative end of molecular I2. Paul et al. analyzed the potential of three MOFs (MIL-53(Al), MIL-120(Al), and HKUST-1(Cu) for  $I_2$  adsorption using periodic dispersion density functional theory. They reported that MIL-53 has stronger interactions with I2 than the other two MOFs.86 The infrared spectrum simulated via molecular dynamics calculations confirmed that this strong interaction originated from the hydrogen bonding between I2 and the hydroxyl groups of MIL-53 (Fig. 7b).

### 2.7 Van der Waals interactions

The van der Waals force is a relatively weak but major interaction force. As a nonpolar molecule,  $I_2$  does not have a permanent dipole. However, when close to a charged adsorbent framework,  $I_2$  can interact with the framework by inducing a transient dipole. Accordingly, Shetty *et al.* prepared porous polymers (covalent polycalix[4]arenes) and modified them by lithiation.<sup>87</sup> Compared to the original polymers, lithiated polymers demonstrated faster adsorption kinetics and higher  $I_2$ uptake because of the charge-induced dipole interactions, the London dispersion force plays an important role in  $I_2$ capture. For  $I_2$  molecules, temporary dipoles can induce strong intermolecular interactions (dispersion forces), which are influenced by the size and shape of micropores in the adsorbent. For example, the suitable pore geometry MOF MFM-300(Sc) facilitates the self-aggregation of I<sub>2</sub> molecules into an unusual triple helical chain through intermolecular interactions, thus resulting in the efficient packing of I<sub>2</sub> with an exceptional storage density of 3.08 g cm<sup>-3</sup> (Fig. 7c).<sup>88</sup>

### 2.8 Hydrophobic interactions

The real off-gas contains a significant amount of moisture, in addition to  $I_2$  and organic iodides. The presence of water molecules poses a significant challenge to  $I_2$  capture because the competitive adsorption of water can significantly reduce the  $I_2$  adsorption capacity. Many strategies used to promote  $I_2$ adsorption, such as Lewis acid-base interactions, Coulomb interactions, and hydrogen bonding, can promote water adsorption. Therefore, adsorption sites capable of preferentially adsorbing  $I_2$  over water are required. Hydrophobic porous materials can selectively capture  $I_2$  in the presence of water *via* hydrophobic interactions because  $I_2$  is a nonpolar hydrophobic molecule. However, such experiments are usually performed at low temperatures<sup>33,89</sup> because relatively weak hydrophobic interactions cannot prevent  $I_2$  desorption at high temperatures.

A chiral polymer zinc D-saccharate having two types of parallel channels, one hydrophilic and the other hydrophobic, has been investigated for  $I_2$  capture.<sup>89</sup> Upon exposure to  $I_2$ vapor, water molecules in the hydrophobic channels are replaced with  $I_2$ , while water molecules in the hydrophilic channels remain. This result shows that the preferential adsorption of  $I_2$  over water can be achieved by forming a hydrophobic environment in the adsorbent. Pham *et al.* synthesized a hydrophobicity-intensified silicalite-1 (HISL) zeolite and evaluated its  $I_2$  adsorption properties under various conditions relevant to practical off-gas treatment applications.<sup>33</sup> HISL has similar  $I_2$  adsorption capacity in the presence and absence of water because of its super-hydrophobicity and demonstrates good tolerance to the presence of acids.<sup>33</sup>

# 3. Mechanisms for methyl iodide capture

In the off-gas from nuclear power plants,  $CH_3I$  is produced from a reaction of  $I_2$  with volatile organic compounds (*e.g.*, methane). Compared to  $I_2$ ,  $CH_3I$  is more difficult to capture because of its considerably lower concentration and lack of intermolecular interactions.<sup>90,91</sup> There are relatively few studies on  $CH_3I$ capture, and the adsorption strategies employed can be classified broadly into catalytic decomposition reactions, coordination interactions, methylation reactions, halogen bonding, and hydrogen bonding.

#### 3.1 Catalytic decomposition reactions

As in the case of  $I_2$  adsorption, Ag-containing adsorbents, such as Ag-zeolites, can capture CH<sub>3</sub>I *via* chemical reactions. For example, Ag<sup>0</sup>-MOR zeolite was reported to catalyze the decomposition of CH<sub>3</sub>I, where the Brønsted acid sites of the zeolite act as catalytic centers. The surface methoxy species react with other components in the off-gas (*e.g.*, H<sub>2</sub>O and NO<sub>x</sub>) to form



Fig. 8 (a) Schematic of the mechanism of CH<sub>3</sub>I adsorption on the Ag<sup>0</sup>-MOR zeolite. Brønsted acid sites catalyze the decomposition of CH<sub>3</sub>I, and the formed I · reacts with Ag<sup>0</sup> to form AgI, while the CH<sub>3</sub>· reacts with H<sub>2</sub>O to form by-products such as CH<sub>3</sub>OH or CH<sub>3</sub>OCH<sub>3</sub>. Color code: yellow, Si; red, O; pink, Al; gray, C; and white, H. (b) Crystal structures of CH<sub>3</sub>I (@Co<sub>2</sub>(p-DOBDC), where CH<sub>3</sub>I reacts with open Co sites by coordination interaction. Reproduced with permission from ref. 95. Copyright 2020, Wiley. Color code: cyan, Co; red, O; purple, I; gray, C; and white, H.

volatile by-products. The liberated iodine reacts with Ag in the micropore to form sub-nm AgI clusters (Fig. 8a).<sup>92</sup>

Multiple exchangeable metal cations, including Cu<sup>2+</sup>, Ag<sup>+</sup>, Pb<sup>2+</sup>, and Na<sup>+</sup>, have been introduced into FAU-type X and Y zeolites for CH<sub>3</sub>I adsorption.<sup>93</sup> The adsorption capacity of these metal ions followed the order: Cu<sup>2+</sup> > Ag<sup>+</sup>  $\gg$  Pb<sup>2+</sup> > Na<sup>+</sup>. This suggests that Cu<sup>2+</sup> has the highest CH<sub>3</sub>I capture efficiency. However, Ag–Y zeolite rather than Cu–Y zeolite was considered the best candidate for CH<sub>3</sub>I adsorption because the adsorption of CH<sub>3</sub>I on Cu<sup>2+</sup> leads to undesirable I<sub>2</sub> generation because of the following reaction:

$$Cu^{2+} + 2I^{-} \rightarrow CuI_2 \rightarrow 2CuI + 1/2I_2$$
(7)

### 3.2 Coordination interactions

The open metal sites in MOFs can adsorb  $CH_3I$  *via* coordination interactions. For example, a mesoporous bimetallic organic framework ECUT-300-200-Ac was synthesized with purposely generated structural defects that render many open metal sites.<sup>94</sup> XPS revealed a blue shift of the  $Cd_{3d}$  and  $U_{4f}$  binding energies in ECUT-300-200-Ac when exposed to  $CH_3I$ , indicating the participation of these metal sites in adsorption. Similarly, SXRD indicated that MOF  $Co_2(p$ -DOBDC) can adsorb  $CH_3I$  at its open Co sites through coordination, with the I end of the  $CH_3I$ molecule interacting with Co in a side-on configuration (Fig. 8b).<sup>95</sup>

### 3.3 Methylation reactions

Another effective strategy to capture  $CH_3I$  is to functionalize the adsorbent with multiple amine groups that can bind  $CH_3I$  *via N*-methylation reactions. For example, a number of nucleophilic amines, including triethylenediamine (TEDA), hexamethylene-tetramine (HMTA), *N,N'*-dimethylethylenediamine, *N,N'*-dimethyl-1,3-propanediamine, and *N,N'*-dimethyl-1,4-



**Fig. 9** (a) Calculated geometries of the reactant, transition state, and product during the CH<sub>3</sub>I dissociation on the TEDA-modified activated carbon surface. TEDA lowers the dissociation energy of CH<sub>3</sub>I and forms quaternary ammonium salt with CH<sub>3</sub>I by *N*-methylation reaction. Reproduced with permission from ref. 96. Copyright 1999, Royal Society of Chemistry. (b) Crystal structures of CH<sub>3</sub>I<sub>(a</sub>Co<sub>2</sub>(*m*-DOBDC) and the proposed mechanism for the reaction between *m*-DOBDC<sup>4–</sup> and CH<sub>3</sub>I. CH<sub>3</sub>I reacts with electron-rich *m*-DOBDC<sup>4–</sup> groups via electrophilic aromatic substitution reaction, while the dissociated I<sup>–</sup> ions coordinate to the open Co<sup>2+</sup> sites. Reproduced with permission from ref. 95. Copyright 2020, Wiley. Color code: green, Co; red, O; purple, I; gray, C; and white, H.

butanediamine, were loaded onto activated carbon by impregnation to enhance their  $CH_3I$  binding strength.<sup>12</sup> Density functional theory (DFT) calculations and *ab initio* molecular dynamics simulations indicate that TEDA can reduce the dissociation activation barrier of  $CH_3I$  and participate in the subsequent alkylation to form a quaternary ammonium salt (Fig. 9a).<sup>96</sup> For example, tertiary amines, TEDA and HMTA, were grafted to the open metal sites of MIL-101 (Cr) for  $CH_3I$  capture. The resulting MIL-101-Cr-TED exhibited an ultrahigh  $CH_3I$ uptake of 71 wt% at 150 °C, which is more than three times that of  $Ag^0$ -MOR.<sup>97</sup> In addition to tertiary aliphatic amines, aromatic N species have been used to capture  $CH_3I$  through *N*methylation reactions, such as pyridine-N,<sup>98</sup> aniline-N,<sup>25</sup> pyrazole-N,<sup>94</sup> imine-N, and triazine-N.<sup>99</sup>

The adsorbent can also capture  $CH_3I$  through electrophilic aromatic substitution reactions. Park *et al.* synthesized two MOFs,  $Co_2(m$ -DOBDC) and  $Co_2(p$ -DOBDC), and compared their structures after  $CH_3I$  adsorption.<sup>95</sup> SXRD indicated that  $CH_3I$ reacted with electron-rich *m*-DOBDC<sup>4-</sup> groups, converting the aryl C-H bond to the C–C bond, with the dissociated I<sup>-</sup> coordinating to the open  $Co^{2+}$  sites (Fig. 9b). However, for the isostructural  $Co_2(p$ -DOBDC) lacking electron-rich C,  $CH_3I$  was coordinately adsorbed at the open  $Co^{2+}$  sites without undergoing electrophilic aromatic substitution (Fig. 8b).

### 3.4 Halogen bonding and hydrogen bonding

Quantum chemical calculations report that halogen bonds may play an important role in promoting CH<sub>3</sub>I adsorption when electron-rich moieties are present in the adsorbent. For example, CH<sub>3</sub>I can form weak halogen bonds with -C=N- in 1,2-dihydrophenazine in polymer MHP-P5Q, in which the bond length  $d_{[N\cdots I]}$  is 3.39 Å (Fig. 10a).<sup>25</sup> A halogen bond between I and an electron-rich group appears counterintuitive because halogen atoms are electronegative. Brinck *et al.* theoretically explained this.<sup>100</sup> They reported that the electrostatic potential of covalently bonded halogens is anisotropic and possesses



Fig. 10 (a) Calculated structure of CH<sub>3</sub>I interacting with 1,2-dihydrophenazine, showing that CH<sub>3</sub>I forms weak halogen bonds with – C=N- in a head-on configuration. Reprinted with permission from ref. 25. Copyright 2020, Springer Nature. Color code: gray, C; white, H; blue, N; brown, I. (b) DFT-optimized structure of CH<sub>3</sub>I in the CAU-11-SO<sub>3</sub>H pore channel, showing that CH<sub>3</sub>I interacts with the modified sulfonic acid by I···O and I···S electrostatic interactions. Color code: gray, C; white, H; red, O; pink, Al; brown, I and yellow, S. Reprinted with permission from ref. 101. Copyright 2021, American Chemical Society.

positive regions at the tip of X (X = Cl, Br, and I). Therefore, halogen bonds can be formed between  $CH_3I$  with nucleophiles in a head-on configuration.

In a purely theoretical study, Wu *et al.* screened a series of Albased MOFs for CH<sub>3</sub>I capture from the simulated off-gas using Grand canonical Monte Carlo (GCMC) simulations and DFT calculations.<sup>101</sup> Among the MOFs evaluated, CAU-11 with 1D narrow channels demonstrated the highest isosteric heat ( $Q_{st}$ ) of CH<sub>3</sub>I. Note that additional modification of CAU-11 with sulfonic acid groups enabled highly efficient capture of trace CH<sub>3</sub>I, which was attributed to the formation of I···O and I···S electrostatic interactions (Fig. 10b). Such interactions were not assigned as halogen bonds possibly because the calculated configuration of CH<sub>3</sub>I was "side-on" rather than "head-on".

Endowing adsorbents with hydrogen bonding sites is another approach for promoting their  $CH_3I$  capture capability. Unlike halogen bonding, when  $CH_3I$  is immobilized by hydrogen bonding, the iodine atom acts as an electron donor.<sup>102</sup> Chebbi *et al.* compared the  $CH_3I$  capture capability of a number of MOFs, including ZIF-8 (Zn), MIL-53 (Al), MIL-100 (Al), UiO-66 (Zr), HKUST-1 (Cu), CAU-1 (Al), and MIL-120 (Al). They reported that MIL-120 (Al) had the strongest interaction with  $CH_3I$ because of its abundant –OH groups, which promoted the formation of H-bonded complexes with  $CH_3I$ .<sup>103</sup> The captured  $CH_3I$  could not be desorbed from MIL-120 (Al) by He evacuation.

### 4. Performance evaluation

The adsorbents developed for  $I_2/CH_3I$  capture can be evaluated under static or dynamic conditions or both. Static measurements are easy to operate but have multiple limitations. Whereas dynamic measurements require the development of gas circuits and the use of detectors, they provide more flexible test conditions relevant to practical applications. This section describes typically used static and dynamic systems and their applications for  $I_2$  and  $CH_3I$  adsorption measurements.

#### 4.1 Static measurement

In most studies on  $I_2$  (or  $CH_3I$ ) capture, the adsorption capacity of the adsorbent is measured under static conditions using a closed system, in which  $I_2$  (or  $CH_3I$ ) and the adsorbent are heated simultaneously to the target temperature (Fig. 11a). After some time (assuming adsorption equilibrium has been achieved), the system is cooled to room temperature, and the adsorption capacity is determined based on the mass increase of the adsorbent. The static system is also used to determine the adsorption kinetics by recording the mass changes at different time intervals. The commonly used index for adsorption kinetics is  $K_{80\%}$ , which refers to the average adsorption rate before the adsorption capacity reaches 80%.<sup>104</sup>

Despite its simplicity and widespread use, there are several problems with such a static measurement system. For example, static I<sub>2</sub> adsorption is typically conducted at 75 °C and ambient pressure; under such conditions, the partial pressure of I<sub>2</sub> is 1.6 kPa. The corresponding I<sub>2</sub> volumetric concentration is ~1.6 ×  $10^4$  ppmv, which is several orders of magnitude higher than the actual I<sub>2</sub> concentration in the off-gas. Hence, the measured I<sub>2</sub> adsorption capacity does not truly reflect the I<sub>2</sub> capture performance in practical applications. Moreover, during the cooling process of the system, a large amount of I<sub>2</sub> may condense on the surface of the adsorbent and the vial containing the adsorption capacity. Although using an empty vial as a blank control can eliminate this overestimation to a certain extent (Fig. 11a), the adsorption capacity determined in this manner remains



Fig. 11 (a) Schematic of the static system used to measure the  $I_2$  or  $CH_3I$  adsorption capacity of adsorbents. (b) Schematic of the dynamic system used to measure the  $I_2$  or  $CH_3I$  adsorption capacity of adsorbents, which is based on a column breakthrough setup. The concentration of  $I_2$  in the effluent can be determined by collecting  $I_2$  using NaOH solution followed by elemental analysis using ICP-MS. (c) Typical breakthrough profiles obtained from the dynamic measurement to determine the adsorption capacity. Reproduced with permission from ref. 99. Copyright 2022, Springer Nature.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.

unreliable. This can explain why certain reported adsorption capacities are considerably higher than the theoretical values calculated based on the adsorbent pore volume.<sup>105–109</sup> Moreover, using a static measurement system, it is impossible to control the I<sub>2</sub> concentration and adsorption temperature independently or co-feed other components, such as H<sub>2</sub>O and NO<sub>x</sub>, to simulate the actual off-gas conditions.

Considering these limitations and problems, using such a static measurement system to evaluate the performance of adsorbents for I<sub>2</sub> capture is not recommended. Compared to I<sub>2</sub>, CH<sub>3</sub>I has weaker intermolecular forces and is less prone to condensation. Therefore, the CH<sub>3</sub>I adsorption capacity determined using a static system is relatively more reliable. However, when CH<sub>3</sub>I is adsorbed *via* chemical reactions (for example, when CH<sub>3</sub>I is adsorbed on Ag-zeolites), the adsorption capacity cannot be determined accurately by the mass change because of the production of volatile byproducts such as CH<sub>3</sub>OH and CH<sub>3</sub>OCH<sub>3</sub>.

Compared to the I<sub>2</sub> capture, which has been extensively studied, there are only a few studies of CH<sub>3</sub>I capture. Xie et al. compared the different adsorption behavior of CH<sub>3</sub>I and I<sub>2</sub> under static and dynamic conditions using specially designed COFs as adsorbents.99 They reported that I2 adsorption is dominated by intermolecular interactions under commonly used static evaluation conditions (saturated  $I_2$  vapor at 75 °C). The capacity is primarily determined by the textural properties (surface area and pore volume) of the adsorbent. However, the CH<sub>3</sub>I adsorption capacity depends on the number of strong binding sites of the adsorbent rather than its textural properties, thus exhibiting a positive correlation with the N content (strong binding sites) in the COFs. The observed one-to-one correspondence between CH<sub>3</sub>I and N suggests that CH<sub>3</sub>I molecules are only adsorbed on N sites possibly by forming salts.99 The adsorption kinetics of I2 and CH3I on these COFs demonstrate a similar trend, *i.e.*, they are primarily determined by the textural properties and the number of strong binding sites, respectively.

### 4.2 Dynamic measurement

The problems associated with the static system can be circumvented by dynamic adsorption measurements using a fixed-bed setup (Fig. 11b). The dynamic measurement system allows free adjustment of the  $I_2/CH_3I$  concentration, precise control of the adsorbent temperature, and easy simulation of off-gas compositions.<sup>110</sup> Importantly, it is close to the actual application scenario using adsorbent-packed columns to capture iodine.

In a dynamic system, the carrier gas flows continuously through the  $I_2/CH_3I$  generator to produce  $I_2/CH_3I$  vapor, the concentration of which can be adjusted by the dilution gas. The adsorbent is separated from the vapor generator, and its temperature can be controlled independently using an oven. Other substances can be introduced into the system with independent gas lines to simulate the off-gas composition (Fig. 11b). Breakthrough curves can be plotted by analyzing the  $I_2/CH_3I$  content in the outlet gas *via* inductively coupled plasma mass spectrometry (ICP-MS) and online mass spectrometry, respectively (Fig. 11c). From this, a reliable adsorption capacity can be determined by curve integration (eqn (8)):

$$q = \frac{F_{\rm i} \times t_0 - V_{\rm dead} - \int_0^{t_0} F_{\rm e} \Delta t}{m} \tag{8}$$

where  $F_i$  is the influent flow rate of the I<sub>2</sub>/CH<sub>3</sub>I (mL min<sup>-1</sup>);  $t_0$  is the adsorption time (min);  $V_{dead}$  is the dead volume of the system (cm<sup>3</sup>);  $F_e$  is the effluent flow rate of I<sub>2</sub>/CH<sub>3</sub>I (mL min<sup>-1</sup>); and *m* is the weight of the adsorbents (g).

Han *et al.* used a dynamic system to measure the I<sub>2</sub> uptake capacity of an ionic COF (iCOF-AB-50) at a low I<sub>2</sub> concentration of 400 ppmv and 25 °C.<sup>111</sup> They attributed the high I<sub>2</sub> uptake capacity (2.79 g g<sup>-1</sup>) to the combination of high pore volume and abundant binding sites in iCOF-AB-50. Moreover, they examined the effects of competitive water adsorption on the I<sub>2</sub> capture of iCOF-AB-50 by introducing water vapor (relative humidity: 50%) to the dynamic I<sub>2</sub> adsorption system at 25 °C. The presence of water vapor caused only a slight decrease in the I<sub>2</sub> uptake of iCOF-AB-50 to 2.70 g g<sup>-1</sup> compared to that without water vapor addition (2.79 g g<sup>-1</sup>), during which a certain amount of water was adsorbed. This suggests that although iCOF-AB-50 is not completely water-repellant, most of its adsorptive sites bind preferentially to I<sub>2</sub>, thus leaving their I<sub>2</sub> adsorption capacity almost intact under humid conditions.

In a more recent study, the same group developed a guanidinium-based ionic COF, termed TGDM, and evaluated its I<sub>2</sub> capture ability using a dynamic measurement system.<sup>84</sup> The tests were conducted at 150 ppmv of I<sub>2</sub> and 150 °C to simulate the actual off-gas conditions. Under low-concentration and high-temperature conditions, TGDM exhibited significantly higher I<sub>2</sub> uptake capacity than iCOF-AB-50 (0.3 *vs.* 0.08 g g<sup>-1</sup>) despite its lower pore volume. Compared with iCOF-AB-50, the superior high-temperature I<sub>2</sub> capture performance of TGDM was attributed to its higher density of ionic groups and improved thermal stability.

The CH<sub>3</sub>I concentration in the off-gas of actual nuclear power plants is extremely low, typically <50 ppmv. However, most studies on CH<sub>3</sub>I capture evaluated the adsorbents at considerably higher CH<sub>3</sub>I concentrations (e.g.,  $2 \times 10^5$  ppmv), even with a dynamic system.94,97,98 Among the adsorbents investigated, mesoporous MOF ECUT-300-200-Ac demonstrated record CH<sub>3</sub>I uptake capacities of > 2.8 g g<sup>-1</sup> at 25 °C and > 0.87 g g<sup>-1</sup> at 150 °C. Its excellent CH<sub>3</sub>I capture ability was attributed to the combined effects of coordination interactions, methylation reactions, and hydrogen bonding.94 Han et al. compared the CH<sub>3</sub>I capture performance of multiple state-of-the-art adsorbents at 50 ppmv of CH<sub>3</sub>I and 25 °C.99 The CH<sub>3</sub>I adsorption capacities obtained were as follows: MIL-101-Cr-HMTA97 (0.51 g  $g^{-1}$  > COF-TAPT<sup>99</sup> (0.39 g  $g^{-1}$  ) > TFPA-TAPT<sup>99</sup> (0.18 g  $g^{-1}$  ) > COF-TAPB<sup>99</sup>  $\approx$  iCOF-AB-50<sup>111</sup> (0.12 g g<sup>-1</sup>) > SCU-COF-2<sup>98</sup> (0.08 g g<sup>-1</sup>). These results confirm that the adsorption of CH<sub>3</sub>I is determined primarily by the type and number of binding sites and is not related significantly to the textural properties of the adsorbent. These results indicate that unlike I<sub>2</sub> adsorption, ionic groups have little effect on CH<sub>3</sub>I adsorption, which may be because I<sub>2</sub> readily forms charged polyiodide species, such as  $I_3^-$  and  $I_5^-$ , whereas CH<sub>3</sub>I cannot.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence. Open Access Article. Published on 24 2 2023. Downloaded on 2025-05-07 7:48:10. (cc) BY-NC

Table 1 12/CH31 capture performance of various adsorbents tested using dynamic systems

		Adsorbent name	Test temperature (°C)	Vapor concentration (ppmv)	Adsorption capacity $(g \ g^{-1})$	Adsorption mechanisms	Ref.
$I_2$ capture	Inorganic materials	$Ag^0Z$	150	50	0.12	Redox reaction	112
•	)	HISL	RT	400	0.53	Hydrophobic interaction	33
		SL-1	RT	400	0.48	Hydrophobic interaction	33
		Si-BEA	RT	400	0.47	Hydrophobic interaction	33
		AC	RT	400	0.70	Van der Waals interaction	33
		23Ag/Y	100	1250	0.22	Redox reaction	113
		35Ag/13X	100	1250	0.46	Redox reaction	113
		C@ETS-10	20	32	0.04	Van der Waals interaction	114
	MOFS	HKUST-1	RT	400	0.38	Hydrogen bonding	33
		ZIF-8	RT	400	0.03	Lewis acid-base interaction	33
		MIL-101-Cr-HMTA	25	150	0.83	Lewis acid-base interaction	66
	COFS	iCOF-AB-50	25	400	2.79	Coulomb interaction	111
		iCOF-AB-50	25	150	1.52	Coulomb interaction	66
		iCOF-AB-50	75	400	0.44	Coulomb interaction	111
		SCU-COF-2	25	400	0.98	Lewis acid-base interaction	98
		SCU-COF-2	25	150	0.49	Lewis acid-base interaction	66
		SCU-COF-2	75	400	0.35	Lewis acid-base interaction	98
		TGDM	150	150	0.30	Coulomb interaction	84
		JUC-561	150	150	0.20	Lewis acid-base interaction	84
		COF-TAPT	25	150	1.25	Lewis acid-base interaction	66
		COF-TAPB	25	150	1.12	Lewis acid-base interaction	66
		TFPA-TAPT	25	150	0.42	Lewis acid-base interaction	66
	POPs	POSS-TPPSe	160	0.16	0.26	Lewis acid-base interaction	78
CH <sub>3</sub> I capture	Inorganic	22.8Ag/Y	35	1333	0.25	Catalytic decomposition reaction	115
<b>4</b>	materials	22.8Ag/Y	100	1333	0.223	Catalytic decomposition reaction	115
		22.8Ag/Y	250	1333	0.193	Catalytic decomposition reaction	115
		$Ag^+$ (a)13X	150	200 000	0.48	Catalytic decomposition reaction	97
		TED@AC	150	200 000	0.17	Methylation reaction	97
		HMTA@AC	150	200 000	0.14	Methylation reaction	97
		Ag <sup>+</sup> @ZSM-5	150	200 000	0.24	Catalytic decomposition reaction	97
		HISL	25	532 967	0.42	· ·	33
	MOFS	MIL-101-Cr-TED	30	$200\ 000$	1.60	Methylation reaction	97
		MIL-101-Cr-TED	150	200 000	0.71	Methylation reaction	97
		MIL-101-Cr-HMTA	30	200 000	1.74	Methylation reaction	97
		MIL-101-Cr-HMTA	150	200 000	0.62	Methylation reaction	97
		MIL-101-Cr-HMTA	25	50	0.51	Methylation reaction	66
		ECUT-300-200-Ac	25	200 000	2.80	Methylation reaction/hydrogen bonding/	94
						coordination interaction	
		ECUT-300-200-Ac	150	$200\ 000$	0.87	Methylation reaction/hydrogen bonding/	94
						coordination interaction	
		MIL-53	35	1333	0.13	Hydrogen bonding	103
		MIL-120	35	1333	0.16	Hydrogen bonding	103
		HKUST-1	35	1333	0.43	Coordination interaction	103
		MIL-101-RSO <sub>3</sub> Ag	30	20	0.16	Coordination interaction	116

Article. Published on 24 2 2023. Downloaded on 2025-05-07 7:48:10.	is article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licenc
ss Articlé	This artio
Open Acce	(cc)) BY-NC

പ

	-	
1		1
1	-	÷
1	~	٩
7		-
1	5	2
1	r	١
,	~	
C		J
-	-	2
		1
2		2
	٥	1
-	-	2
17	Ĉ	j
-	-	-
÷	C	J
h	-	

		Test temperature	Vapor concentration	Adsorption		
	Adsorbent name	(oc)	(http://www.icea.com/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/action/acti	capacity (g $g^{-1}$ )	Adsorption mechanisms	Ref.
COFS	SCU-COF-2	25	200 000	0.564	Methylation reaction	98
	SCU-COF-2	75	200 000	0.17	Methylation reaction	98
	SCU-COF-2	25	50	0.08	Methylation reaction	66
	iCOF-AB-50	25	200 000	0.62		66
	iCOF-AB-50	25	50	0.11		66
	COF-TAPT	25	200 000	1.30	Methylation reaction	66
	COF-TAPT	25	50	0.39	Methylation reaction	66
	COF-TAPB	25	200 000	0.71	Methylation reaction	66
	COF-TAPB	25	50	0.12	Methylation reaction	66
	TFPA-TAPT	25	50	0.18	Methylation reaction	66

Journal of Materials Chemistry A

Few studies have used dynamic systems to test the  $I_2/CH_3I$  capture performance of adsorbents. Table 1 lists the relevant results reported in the literature.

# 5. Simultaneous capture of low-concentration $I_2$ and $CH_3I$

Molecular iodine and organic iodides (represented by  $CH_3I$ ) coexist in the off-gas of nuclear power plants at low concentrations, and both need to be captured. Because of their different properties, it is important to develop adsorbents that can capture both  $I_2$  and  $CH_3I$  with high efficiency. However, few studies have evaluated the ability of adsorbents to simultaneously capture  $I_2$  and  $CH_3I$  (Table 2), possibly because such measurements require dynamic adsorption systems that are difficult to operate and are less common.

Li *et al.* modified MOF MIL-101 (Cr) with various tertiary amines to simultaneously capture I<sub>2</sub> and CH<sub>3</sub>I under simulated off-gas conditions.<sup>97</sup> The tertiary amine groups can adsorb I<sub>2</sub> through Lewis acid–base interactions and adsorb CH<sub>3</sub>I through methylation reactions. Consequently, amine-functionalized MIL-101 (Cr) MOFs exhibit high total iodine (I<sub>2</sub> + CH<sub>3</sub>I) uptake when used for iodine capture from gas streams containing 150 ppmv I<sub>2</sub> and 50 ppmv CH<sub>3</sub>I in the presence of HNO<sub>3</sub>, NO<sub>x</sub>, and water vapor. Specific iodine uptake depends on the density of the amine groups and test temperature (Table 2). At 150 °C, both MIL-101-Cr-TED and MIL-101-Cr-HMDA rendered a "decontamination factor" (DF) value as high as > 5000, which met the regulatory standards of nuclear processing facilities (DF > 3000).

Xie *et al.* reported the iodine capture performance of several COFs from gas streams containing 150 ppmv I<sub>2</sub> and 50 ppmv CH<sub>3</sub>I at 25 °C.<sup>99</sup> Two COF materials (iCOF-AB-50 and COF-TAPT) ranked the top two among all the adsorbents evaluated, with a total iodine uptake of 1.59 and 1.51 g g<sup>-1</sup>, respectively. These values are higher than the total iodine uptake of MIL-101-Cr-HMDA (1.08 g g<sup>-1</sup>) obtained under the same conditions. According to the single-component dynamic adsorption results, the ultrahigh total iodine uptake of iCOF-AB-50 is derived from the contribution of I<sub>2</sub> adsorption because of the abundant ionic groups that effectively promote I<sub>2</sub> adsorption *via* strong Coulomb interactions.

## 6. Summary and outlook

Over the past decade, many nanoporous materials, primarily COFs, POPs, and MOFs, have been reported as adsorbents for iodine capture. Compared to traditional industrial adsorbents, such as zeolites and activated carbon, these emerging adsorbents are characterized by easily regulated pore structures and abundant surface functionality, enabling the capture of molecular iodine and organic iodides *via* novel adsorption mechanisms.

This review summarizes the common mechanisms for adsorption-based iodine capture. Molecular iodine can be adsorbed *via* redox reactions, coordination interactions,

Table 2 Summary of the reported results for the simultaneous capture of  $l_2$  and  $\mbox{CH}_3 l$ 

	Adsorbent name	Test temperature (°C)	I <sub>2</sub> concentration (ppmv)	CH <sub>3</sub> I concentration (ppmv)	Total iodine uptake (g g <sup>-1</sup> )	Adsorption mechanisms	Ref.
Zeolites	Ag <sup>0</sup> @MOR	150	150	50	$0.16^a$	Redox reaction/catalytic decomposition reaction	97
	Ag <sup>0</sup> @MOR	25	150	50	$0.44^a$	Recommendation/catalytic decomposition	97
	TSIH	150	150	50	$0.05^a$	reaction Hydrophobic interaction	97
	HISL	25	150	50	$0.08^{a}$	Hydrophobic interaction	97
MOFs	MIL-101-Cr-TED	25	150	50	$0.55^a$	Lewis acid-base interaction/methylation	97
						reaction	
	MIL-101-Cr-TED	150	150	50	$0.38^a$	Lewis acid-base interaction/methylation	97
		;		;		reaction	
	MIL-101-Cr-HMTA	25	150	50	$0.44^{u}$	Lewis acid-base interaction/methylation	97
				Ĩ	0000	reaction	ļ
	MIL-101-Cr-HMTA	150	150	50	0.33''	Lewis acid-base interaction/methylation	97
						reaction	
	MIL-101-Cr-HMTA	25	150	50	$1.08^b$	Lewis acid-base interaction/methylation	66
						reaction	
COFs	SCU-COF-2	25	150	50	$0.56^b$	Lewis acid-base interaction/methylation	66
						reaction	
	iCOF-AB-50	25	150	50	$1.59^b$	Coulomb interaction	66
	COF-TAPT	25	150	50	$1.51^b$	Lewis acid-base interaction/methylation	66
						reaction	
	COF-TAPB	25	150	50	$1.17^b$	Lewis acid-base interaction/methylation	66
						reaction	
	TFPA-TAPT	25	150	50	$0.47^b$	Lewis acid-base interaction/methylation	66
						reaction	

electrophilic aromatic substitution, Lewis acid–base interactions, Coulomb interactions, hydrogen bonding, van der Waals interactions, and hydrophobic interactions. As a representative of organic iodides,  $CH_3I$  can be adsorbed *via* catalytic decomposition reactions, coordination interactions, methylation reactions, halogen bonding, and hydrogen bonding. In general,  $CH_3I$  is extremely difficult to capture by physisorption than  $I_2$ because of the lack of strong intermolecular forces and its ultralow concentration in the off-gas.

Despite the multiple studies on iodine capture in recent years, most did not consider the needs of practical applications. The adsorbents for capturing iodine from actual off-gas require to meet two requirements because the off-gas produced during the reprocessing of used fuel rods generally has high temperatures (~150 °C), low concentrations of I<sub>2</sub> (<150 ppmv) and organic iodides (~50 ppmv), and various acidic (pH < 1) components and water vapor. First, they should be able to capture iodine at low concentrations and high temperatures. Second, they should be chemically and thermally stable under strongly acidic hydrothermal conditions.

However, previous studies did not consider these two important factors when examining whether the adsorbent has practical value. Indeed, a vast majority of "emerging" adsorbents, such as MOFs, COFs, and POPs, were evaluated at low temperatures ( $\leq$ 75 °C) with high I<sub>2</sub> concentrations (using saturated I<sub>2</sub> vapor). As high temperature and low I<sub>2</sub> concentration are unfavorable factors for I<sub>2</sub> adsorption, the I<sub>2</sub> uptake of these adsorbents under the actual industrial conditions must be considerably lower than the reported values. Therefore, the reported adsorption capacity is meaningless for practical applications, and the static measurement method is unreliable (Section 4.1). Another neglected issue is the stability of the adsorbents under the hydrothermally acidic conditions of industrial off-gas. The intrinsic porous structures of organic or organic-inorganic hybrid adsorbents can be destroyed under harsh conditions with few exceptions.84,97,99 Structural damage to adsorbents indicates a significant reduction in adsorption capacity and loss of reusability.

Based on these considerations, although organic-based adsorbents are valuable for fundamental research, they are unlikely to be directly applied to capture iodine from industrial off-gas. They may be useful for capturing iodine from pretreated off-gas to remove moisture and reduce acidity at lower temperatures or under other mild-condition applications. It remains a considerable challenge to develop high-performance adsorbents for direct off-gas treatment that combine high iodine uptake with excellent structural stability and reusability. Considering the highly unfavorable adsorption conditions (*i.e.*, high temperature of ~150 °C and low iodine concentration), the desired iodine adsorption capacity is difficult to achieve by physisorption, whereas chemisorption may be the only option because of its high adsorption strength. Therefore, the ideal adsorbents for iodine capture from off-gas should have many easily regenerated chemisorption sites while maintaining structural integrity during adsorption and regeneration. Achieving this goal may require new adsorption strategies. For example, a single strong binding site can make regeneration

difficult, but coupling several moderately strong binding sites may provide a balance between adsorption efficiency and recyclability. To avoid structural damage, it is necessary to understand the mechanisms responsible for the structural degradation of adsorbents caused by common species in nuclear off-gas. In this regard, quantum chemistry calculations and simulations would be a useful tool. The revealed adsorbateadsorbent interaction modes can provide insight into the degradation mechanism, thereby guiding the design of stable iodine adsorbents.

Dynamic measurement systems are recommended for evaluating developed adsorbents because they can easily realize precise concentration and temperature control while allowing the incorporation of multiple components to simulate the actual application conditions and scenarios. For example, the experiments of simultaneously capturing I<sub>2</sub> and CH<sub>3</sub>I can be easily performed using a dynamic system. Competitive adsorption between I2/CH3I and coexisting species in the offgas, including H<sub>2</sub>O, NO, CO, CH<sub>3</sub>Cl, and Cl<sub>2</sub>, can be investigated using a dynamic system. There is still a lack of systematic research on the competitive adsorption of these components, except for a few studies focusing only on water. Finally, this study proposes to evaluate the adsorbents developed for iodine capture under conditions close to actual off-gas. Alternatively, researchers should discuss the correlation between the test conditions and specific application scenarios.

### Conflicts of interest

There are no conflicts to declare.

### Acknowledgements

This research is supported by the AMPM CCF fund (FCC/1/1972-43-01) to Y. H. from King Abdullah University of Science and Technology.

### Notes and references

- 1 I. A. E. Agency, https://www.iaea.org/newscenter/news/theuse-of-nuclear-power-beyond-generating-electricity-nonelectric-applications.
- 2 E. Kintisch, Science, 2005, 310, 1406.
- 3 J. E. Ten Hoeve and M. Z. Jacobson, *Energy Environ. Sci.*, 2012, 5, 8743–8757.
- 4 P. A. Kharecha and J. E. Hansen, *Environ. Sci. Technol.*, 2013, 47, 4889–4895.
- 5 F. C. Kupper, M. C. Feiters, B. Olofsson, T. Kaiho,
  S. Yanagida, M. B. Zimmermann, L. J. Carpenter,
  G. W. Luther, Z. L. Lu, M. Jonsson and L. Kloo, *Angew. Chem., Int. Ed.*, 2011, **50**, 11598–11620.
- 6 A. Saiz-Lopez, J. M. C. Plane, A. R. Baker, L. J. Carpenter, R. von Glasow, J. C. G. Martin, G. McFiggans and R. W. Saunders, *Chem. Rev.*, 2012, **112**, 1773–1804.
- 7 K. Nakamura, M. Saeki and E. Tachikaw, J. Nucl. Sci. Technol., 1973, 10, 367–373.

- 8 E. C. Beahm, Y. M. Wang, S. J. Wisbey and W. E. Shockley, *Nucl. Technol.*, 1987, **78**, 34–42.
- 9 J. Paquette and B. L. Ford, *Abstr. Pap. Am. Chem. Soc.*, 1988, **195**, 88–Nucl.
- 10 D. R. Haefner and T. J. Tranter, Report No. INL/EXT-07-12299; TRN: US0800243, 2007.
- 11 S. U. Nandanwar, K. Coldsnow, V. Utgikar, P. Sabharwall and D. E. Aston, *Chem. Eng. J.*, 2016, **306**, 369–381.
- 12 C. M. Gonzalez-Garcia, J. F. Gonzalez and S. Roman, *Fuel Process. Technol.*, 2011, **92**, 247–252.
- 13 N. Mnasri, C. Charnay, L. C. de Menorval, Y. Moussaoui,
  E. Elaloui and J. Zajac, *Microporous Mesoporous Mater.*, 2014, 196, 305–313.
- 14 Q. H. Cheng, Z. J. Li and T. W. Chu, *Nucl. Sci. Technol.*, 2015, 26, 43–47.
- 15 Y. Nan, L. L. Tavlarides and D. W. DePaoli, *AIChE J.*, 2017, 63, 1024–1035.
- 16 H. J. Choi and M. P. Suh, *J. Am. Chem. Soc.*, 2004, **126**, 15844–15851.
- 17 M. H. Zeng, Q. X. Wang, Y. X. Tan, S. Hu, H. X. Zhao, L. S. Long and M. Kurmoo, *J. Am. Chem. Soc.*, 2010, 132, 2561–2563.
- 18 N. X. Zhu, C. W. Zhao, J. C. Wang, Y. A. Li and Y. B. Dong, *Chem. Commun.*, 2016, 52, 12702–12705.
- 19 B. Guo, F. Li, C. Wang, L. Zhang and D. Sun, J. Mater. Chem. A, 2019, 7, 13173–13179.
- 20 T. Xu, J. T. Li, M. W. Jia, G. H. Li and Y. L. Liu, *Dalton Trans.*, 2021, **50**, 13096–13102.
- G. Das, T. Prakasam, S. Nuryyeva, D. S. Han, A. Abdel-Wahab, J. C. Olsen, K. Polychronopoulou, C. Plataslglesias, F. Ravaux, M. Jouiad and A. Trabolsi, *J. Mater. Chem. A*, 2016, 4, 15361–15369.
- 22 T. Geng, Z. Zhu, W. Zhang and Y. Wang, *J. Mater. Chem. A*, 2017, **5**, 7612–7617.
- 23 J. Wang, Z. L. Li, Y. Wang, C. T. Wei, K. L. Ai and L. H. Lu, *Mater. Horiz.*, 2019, 6, 1517–1525.
- 24 W. Xie, D. Cui, S. R. Zhang, Y. H. Xu and D. L. Jiang, *Mater. Horiz.*, 2019, **6**, 1571–1595.
- 25 K. C. Jie, Y. J. Zhou, Q. Sun, B. Li, R. Zhao, D. E. Jiang, W. Guo, H. Chen, Z. Z. Yang, F. H. Huang and S. Dai, *Nat. Commun.*, 2020, **11**, 1086.
- 26 M. Y. Xu, T. Wang, L. Zhou and D. B. Hua, *J. Mater. Chem. A*, 2020, **8**, 1966–1974.
- 27 Y. S. Lan, M. M. Tong, Q. Y. Yang and C. L. Zhong, Crystengcomm, 2017, 19, 4920–4926.
- 28 J. H. Li, H. X. Zhang, L. Y. Zhang, K. Wang, Z. K. Wang, G. Y. Liu, Y. L. Zhao and Y. F. Zeng, *J. Mater. Chem. A*, 2020, 8, 9523–9527.
- 29 L. Y. Zhang, J. H. Li, H. X. Zhang, Y. Liu, Y. M. Cui, F. C. Jin, K. Wang, G. Y. Liu, Y. L. Zhao and Y. F. Zeng, *Chem. Commun.*, 2021, 57, 5558–5561.
- 30 P. Wang, Q. Xu, Z. P. Li, W. M. Jiang, Q. H. Jiang and D. L. Jiang, *Adv. Mater.*, 2018, **30**, 1801991.
- 31 Q. Zhao, L. Zhu, G. Lin, G. Chen, B. Liu, L. Zhang, T. Duan and J. Lei, *ACS Appl. Mater. Interfaces*, 2019, **11**, 42635– 42645.

- 32 T.-M. Geng, F.-Q. Wang, X.-C. Fang and H. Xu, *Microporous Mesoporous Mater.*, 2021, **317**, 111001.
- 33 T. C. T. Pham, S. Docao, I. C. Hwang, M. K. Song, D. Y. Choi, D. Moon, P. Oleynikov and K. B. Yoon, *Energy Environ. Sci.*, 2016, 9, 1050–1062.
- 34 K. W. Chapman, P. J. Chupas and T. M. Nenoff, J. Am. Chem. Soc., 2010, 132, 8897–8899.
- 35 Y. Lu, H. W. Liu, R. N. Gao, S. L. Xiao, M. Zhang, Y. F. Yin, S. Q. Wang, J. Li and D. J. Yang, ACS Appl. Mater. Interfaces, 2016, 8, 29179–29185.
- 36 R. N. Gao, Y. Lu, S. L. Xiao and J. Li, Sci. Rep., 2017, 7, 4303.
- 37 D. W. Holladay, Literature survey: methods for the removal of iodine species from off-gases and liquid waste streams of nuclear power and nuclear fuel reprocessing plants, with emphasis on solid sorbents, *Oak Ridge National Lab.*(ORNL), Report No. ORNL/TM-6350, 1979, DOI: 10.2172/6394859.
- 38 J. Huve, A. Ryzhikov, H. Nouali, V. Lalia, G. Auge and T. J. Daou, *RSC Adv.*, 2018, 8, 29248–29273.
- 39 J. H. Yang, Y. J. Cho, J. M. Shin and M. S. Yim, J. Nucl. Mater., 2015, 465, 556–564.
- 40 H. Zou, F. C. Yi, M. X. Song, X. Q. Wang, L. Bian, W. M. Li, N. Pan and X. Q. Jiang, *J. Hazard. Mater.*, 2019, 365, 81–87.
- 41 A. T. Reda, M. Pan, D. X. Zhang and X. Y. Xu, *J. Environ. Chem. Eng.*, 2021, **9**, 105279.
- 42 S. W. Kang, J. H. Yang and M. S. Yim, *Nucl. Technol.*, 2020, 206, 1593–1606.
- 43 X. R. Zhang, I. da Silva, R. Fazzi, A. M. Sheveleva, X. Han,
  B. F. Spencer, S. A. Sapchenko, F. Tuna, E. J. L. McInnes,
  M. Li, S. H. Yang and M. Schroder, *Inorg. Chem.*, 2019, 58, 14145–14150.
- 44 E. Baladi, V. Nobakht, A. Tarassoli, D. M. Proserpio and L. Carlucci, *Cryst. Growth Des.*, 2018, **18**, 7207–7218.
- 45 B. Lee, Y. P. Chen, J. Park and J. Park, ACS Appl. Mater. Interfaces, 2019, 11, 25817–25823.
- 46 A. Y. Rogachev and R. Hoffmann, J. Am. Chem. Soc., 2013, 135, 3262–3275.
- 47 D. F. Sava, K. W. Chapman, M. A. Rodriguez, J. A. Greathouse, P. S. Crozier, H. Y. Zhao, P. J. Chupas and T. M. Nenoff, *Chem. Mater.*, 2013, 25, 2591–2596.
- 48 J. H. Ye, Z. J. Hu, Y. X. Wang, W. C. Zhang and Y. Zhang, *Tetrahedron Lett.*, 2012, 53, 6858–6860.
- 49 Y. Zhu, Y.-J. Ji, D.-G. Wang, Y. Zhang, H. Tang, X.-R. Jia, M. Song, G. Yu and G.-C. Kuang, *J. Mater. Chem. A*, 2017, 5, 6622–6629.
- 50 T. R. Thomas, B. A. Staples, L. P. Murphy, Dry method for recycling iodine-loaded silver zeolite, US Pat. 4088737/A, 1978, http://inis.iaea.org/search/ search.aspx?orig\_q=RN:10456359.
- 51 J. A. Wang, K. L. Ai and L. H. Lu, *J. Mater. Chem. A*, 2019, 7, 16850–16858.
- 52 A. J. Blake, F. A. Devillanova, R. O. Gould, W. S. Li, V. Lippolis, S. Parsons, C. Radek and M. Schroder, *Chem. Soc. Rev.*, 1998, 27, 195–205.
- 53 X. Qian, Z. Q. Zhu, H. X. Sun, F. Ren, P. Mu, W. Liang, L. Chen and A. Li, ACS Appl. Mater. Interfaces, 2016, 8, 21063–21069.

- 54 X. W. Pan, C. H. Ding, Z. M. Zhang, H. Z. Ke and G. E. Cheng, *Microporous Mesoporous Mater.*, 2020, 300, 110161.
- 55 P. Chen, X. H. He, M. B. Pang, X. T. Dong, S. Zhao and W. Zhang, ACS Appl. Mater. Interfaces, 2020, 12, 20429– 20439.
- 56 T. H. Niu, C. C. Feng, C. Yao, W. Y. Yang and Y. H. Xu, ACS Appl. Polym. Mater., 2021, 3, 354–361.
- 57 P. Deplano, F. A. Devillanova, J. R. Ferraro, F. Isaia, V. Lippolis and M. L. Mercuri, *Appl. Spectrosc.*, 1992, 46, 1625–1629.
- 58 N. S. Rao, G. B. Rao and D. Ziessow, *Spectrochim. Acta, Part A*, 1990, **46**, 1107–1124.
- 59 M. Hasani and M. Shamsipur, J. Inclusion Phenom. Macrocyclic Chem., 2004, 48, 135–139.
- 60 N. Alizadeh and A. Roomiani, J. Chil. Chem. Soc., 2012, 57, 1130–1133.
- 61 E. M. Nour, Spectrochim. Acta, Part A, 2000, 56, 167-170.
- 62 X. Q. Yan, H. Wang, W. Di Chen and W. J. Jin, *Anal. Sci.*, 2014, **30**, 365–370.
- 63 T. M. Geng, S. N. Ye, Z. M. Zhu and W. Y. Zhang, *J. Mater. Chem. A*, 2018, **6**, 2808–2816.
- 64 A. Hijazi, B. Azambre, G. Finqueneisel, F. Vibert and J. L. Blin, *Microporous Mesoporous Mater.*, 2019, 288, 109586.
- 65 S. Xiong, X. Tang, C. Pan, L. Li, J. Tang and G. Yu, ACS Appl. Mater. Interfaces, 2019, 11, 27335–27342.
- 66 N. Liu, J. Chen, Z. Wu, P. Zhan, L. Zhang, Q. Wei, F. Wang and L. Shao, ACS Appl. Polym. Mater., 2021, 3, 2178–2188.
- 67 Z. J. Yan, B. Cui, T. Zhao, Y. F. Luo, H. C. Zhang, J. L. Xie, N. Li, N. S. Bu, Y. Yuan and L. X. Xia, *Molecules*, 2021, 26, 5263.
- 68 X. H. Xu, Y. X. Li, L. Zhou, N. Liu and Z. Q. Wu, *Chem. Sci.*, 2022, 13, 1111–1118.
- 69 B. Jiang, Y. Qi, X. F. Li, X. H. Guo, Z. M. Jia, J. Zhang, Y. Li and L. J. Ma, *Chin. Chem. Lett.*, 2022, 33, 3556–3560.
- 70 K. C. Jie, Y. J. Zhou, E. R. Li, Z. T. Li, R. Zhao and F. H. Huang, J. Am. Chem. Soc., 2017, **139**, 15320–15323.
- 71 C. C. Feng, G. J. Xu, W. Xie, S. R. Zhang, C. Yao and Y. H. Xu, *Polym. Chem.*, 2020, **11**, 2786–2790.
- 72 D. H. Dai, J. Yang, Y. C. Zou, J. R. Wu, L. L. Tan, Y. Wang,
  B. Li, T. Lu, B. Wang and Y. W. Yang, *Angew. Chem., Int.* Ed., 2021, 60, 8967–8975.
- 73 S. Y. Yao, W. H. Fang, Y. Y. Sun, S. T. Wang and J. Zhang, *J. Am. Chem. Soc.*, 2021, **143**, 2325–2330.
- 74 Z. J. Yan, Y. Yuan, Y. Y. Tian, D. M. Zhang and G. S. Zhu, Angew. Chem., Int. Ed., 2015, 54, 12733–12737.
- 75 J. T. Hughes, D. F. Sava, T. M. Nenoff and A. Navrotsky, *J. Am. Chem. Soc.*, 2013, **135**, 16256–16259.
- 76 D. F. Sava, M. A. Rodriguez, K. W. Chapman, P. J. Chupas,
   J. A. Greathouse, P. S. Crozier and T. M. Nenoff, *J. Am. Chem. Soc.*, 2011, 133, 12398–12401.
- 77 B. J. Riley, J. Chun, W. Um, W. C. Lepry, J. Matyas,
  M. J. Olszta, X. H. Li, K. Polychronopoulou and
  M. G. Kanatzidis, *Environ. Sci. Technol.*, 2013, 47, 7540–7547.

- 78 W. Zhang, Y. Mu, X. He, P. Chen, S. Zhao, C. Huang, Y. Wang and J. Chen, *Chem. Eng. J.*, 2020, **379**, 122365.
- 79 Y. Q. Hu, M. Q. Li, Y. Y. Wang, T. Zhang, P. Q. Liao, Z. P. Zheng, X. M. Chen and Y. Z. Zheng, *Chem.-Eur. J.*, 2017, 23, 8409–8413.
- 80 H. C. Hu, F. Y. Chen, Z. Y. Zhang, D. C. Liu, Y. N. Liang and Z. L. Chen, *Front. Chem.*, 2022, **10**, 864131.
- 81 G. Brunet, D. A. Safin, M. Z. Aghaji, K. Robeyns, I. Korobkov, T. K. Woo and M. Murugesu, *Chem. Sci.*, 2017, 8, 3171–3177.
- 82 Y. Z. Tang, H. L. Huang, J. Li, W. J. Xue and C. L. Zhong, J. Mater. Chem. A, 2019, 7, 18324–18329.
- 83 C. Y. Yan and T. C. Mu, Phys. Chem. Chem. Phys., 2014, 16, 5071–5075.
- 84 Z. Zhang, X. Dong, J. Yin, Z. G. Li, X. Li, D. Zhang, T. Pan, Q. Lei, X. Liu, Y. Xie, F. Shui, J. Li, M. Yi, J. Yuan, Z. You, L. Zhang, J. Chang, H. Zhang, W. Li, Q. Fang, B. Li, X. H. Bu and Y. Han, *J. Am. Chem. Soc.*, 2022, 144, 6821– 6829.
- 85 J. H. Liu, Y. J. Qi, D. Zhao, H. H. Li and S. T. Zheng, *Inorg. Chem.*, 2019, 58, 516–523.
- 86 S. Chibani, F. Chiter, L. Cantrel and J. F. Paul, *J. Phys. Chem.* C, 2017, **121**, 25283–25291.
- 87 D. Shetty, J. Raya, D. S. Han, Z. Asfari, J. C. Olsen and A. Trabolsi, *Chem. Mater.*, 2017, **29**, 8968–8972.
- 88 X. R. Zhang, I. da Silva, H. G. W. Godfrey, S. K. Callear, S. A. Sapchenko, Y. Q. Cheng, I. Vitorica-Yrezabal, M. D. Frogley, G. Cinque, C. C. Tang, C. Giacobbe, C. Dejoie, S. Rudic, A. J. Ramirez-Cuesta, M. A. Denecke, S. H. Yang and M. Schroder, *J. Am. Chem. Soc.*, 2017, 139, 16289–16296.
- 89 B. F. Abrahams, M. Moylan, S. D. Orchard and R. Robson, Angew. Chem., Int. Ed., 2003, 42, 1848–1851.
- 90 A. Karhu, Methods to prevent the source term of methyl iodide during a core melt accident, Report No. NKS-13, ISBN 87-7893-063-4, VTT Energy, Finland, 1999.
- 91 S. H. Bruffey, R. T. Jubin and J. A. Jordan, Report No. FCRD-MRWFD-2016-000357; ORNL/TM-2016/568, 2016.
- 92 T. M. Nenoff, M. A. Rodriguez, N. R. Soelberg and K. W. Chapman, *Microporous Mesoporous Mater.*, 2014, 200, 297–303.
- 93 B. Azambre, M. Chebbi and A. Hijazi, *Chem. Eng. J.*, 2020, 379, 122308.
- 94 H. P. Zhang, L. L. Gong, M. J. Yin, X. H. Xiong, Q. Y. Zhang, X. F. Feng, F. Luo, J. B. Carney and Y. F. Yue, *Cell Rep. Phys. Sci.*, 2022, 3, 100830.
- 95 B. Lee, D. Moon and J. Park, Angew. Chem., Int. Ed. Engl., 2020, 59, 13793–13799.
- 96 H. Chun, J. Kang and B. Han, Phys. Chem. Chem. Phys., 2016, 18, 32050–32056.
- 97 B. Y. Li, X. L. Dong, H. Wang, D. X. Ma, K. Tan, S. Jensen,
  B. J. Deibert, J. Butler, J. Cure, Z. Shi, T. Thonhauser,
  Y. J. Chabal, Y. Han and J. Li, *Nat. Commun.*, 2017, 8, 485.
- 98 L. W. He, L. Chen, X. L. Dong, S. T. Zhang, M. X. Zhang, X. Dai, X. J. Liu, P. Lin, K. F. Li, C. L. Chen, T. T. Pan, F. Y. Ma, J. C. Chen, M. J. Yuan, Y. G. Zhang, L. Chen, R. H. Zhou, Y. Han, Z. F. Chai and S. Wang, *Chem*, 2021, 7, 699–714.

- 99 Y. Q. Xie, T. T. Pan, Q. Lei, C. L. Chen, X. L. Dong, Y. Y. Yuan, W. Al Maksoud, L. Zhao, L. Cavallo, I. Pinnau and Y. Han, *Nat. Commun.*, 2022, **13**, 2878.
- 100 T. Brinck, J. S. Murray and P. Politzer, Int. J. Quantum Chem., 1992, 44, 57-64.
- 101 X. Y. Wu, L. J. Chen, E. J. Amigues, R. Y. Wang, Z. F. Pang and L. F. Ding, *Acs Omega*, 2021, **6**, 18169–18177.
- 102 A. M. S. Riel, R. K. Rowe, E. N. Ho, A. C. C. Carlsson, A. K. Rappe, O. B. Berryman and P. S. Ho, *Acc. Chem. Res.*, 2019, **52**, 2870–2880.
- 103 M. Chebbi, B. Azambre, C. Volkringer and T. Loiseau, *Microporous Mesoporous Mater.*, 2018, **259**, 244–254.
- 104 X. Guo, Y. Li, M. Zhang, K. Cao, Y. Tian, Y. Qi, S. Li, K. Li, X. Yu and L. Ma, *Angew. Chem., Int. Ed. Engl.*, 2020, 59, 22697–22705.
- 105 Y. Z. Liao, J. Weber, B. M. Mills, Z. H. Ren and C. F. J. Faul, *Macromolecules*, 2016, **49**, 6322–6333.
- 106 Z. J. Yin, S. Q. Xu, T. G. Zhan, Q. Y. Qi, Z. Q. Wu and X. Zhao, *Chem. Commun.*, 2017, **53**, 7266–7269.
- 107 X. M. Li, G. Chen, J. T. Ma and Q. Jia, *Sep. Purif. Technol.*, 2019, **210**, 995–1000.
- 108 G. J. Xu, Y. Zhu, W. Xie, S. R. Zhang, C. Yao and Y. H. Xu, *Chem.-Asian J.*, 2019, **14**, 3259–3263.

- 109 L. Shao, N. Liu, L. Wang, Y. Sang, H. Wan, P. Zhan, L. Zhang, J. Huang and J. Chen, *Chemosphere*, 2022, 288, 132499.
- 110 N. Soelberg and T. Watson, FY-2016 methyl iodide higher NOx adsorption test report, Report No. FCRD-MRWFD-2016-000352, INL/EXT-15-36817, Idaho National Laboratory, 2015.
- 111 Y. Q. Xie, T. T. Pan, Q. Lei, C. L. Chen, X. L. Dong, Y. Y. Yuan, J. Shen, Y. C. Cai, C. H. Zhou, I. Pinnau and Y. Han, *Angew. Chem., Int. Ed.*, 2021, **60**, 22432–22440.
- 112 S. Choi, Y. Nan and L. L. Tavlarides, *AIChE J.*, 2021, **67**(67), e17182.
- 113 B. Azambre, M. Chebbi, O. Leroy and L. Cantrel, *Ind. Eng. Chem. Res.*, 2018, **57**, 1468–1479.
- 114 S. U. Nandanwar, K. Coldsnow, M. Green, V. Utgikar, P. Sabharwall and D. E. Aston, *Chem. Eng. J.*, 2016, 287, 593–601.
- 115 M. Chebbi, B. Azambre, C. Monsanglant-Louvet, B. Marcillaud, A. Roynette and L. Cantrel, *J. Hazard. Mater.*, 2021, 409, 124947.
- 116 G. Y. Cha, S. E. Sivan, M. Lee, K. R. Oh, A. H. Valekar, M. K. Kim, H. Jung, D. Y. Hong and Y. K. Hwang, *J. Hazard. Mater.*, 2021, **417**, 125904.