View Article Online

# Journal of Materials Chemistry A

Materials for energy and sustainability

# Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: P. Kumar, T. Paul, A. Sahoo, M. Singh, A. Pathak, R. Thapa and R. Banerjee, *J. Mater. Chem. A*, 2025, DOI: 10.1039/D4TA08601E.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the Information for Authors.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.



rsc.li/materials-a

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

# Harnessing Self-powered and Photoresponsive Biomechanical Activity/D4TA08601E Sensors by Exploring Piezo-phototronic Effect in Lead-free Layered Halide Perovskite/PVDF Composites

Prabhat Kumar<sup>1</sup>, Tufan Paul<sup>1</sup>, Aditi Sahoo<sup>1</sup>, Manoj Singh<sup>1</sup>, Arupjyoti Pathak<sup>2</sup>, Ranjit Thapa<sup>2,3</sup>, and Rupak Banerjee<sup>1,4\*</sup>

<sup>1</sup>Department of Physics, Indian Institute of Technology Gandhinagar, Palaj 382355, Gujarat, India.

<sup>2</sup>Department of Physics, SRM University AP, Amaravati 522240, Andhra Pradesh, India

<sup>3</sup>Centre for Computational and Integrative Sciences, SRM University -AP, Amaravati 522240, Andhra Pradesh, India

<sup>4</sup>K C Patel Centre for Sustainable Development, Indian Institute of Technology Gandhinagar, Palaj 382355, Gujarat, India

\*Corresponding author E-mail: rupakb@iitgn.ac.in

#### Abstract

Developing flexible, wearable, efficient, and self-powered electronic devices based on piezoelectric nanogenerators aspires to be a sustainable solution to renewable energy harvesting and storage. We report on a lead-free halide perovskite  $Cs_3Sb_2I_9$  and polyvinylidene fluoride (PVDF) based composite device capable of scavenging energy from routine biomechanical activities. Regulated incorporation and optimization of  $Cs_3Sb_2I_9$  into the PVDF matrix increased the electroactive phase of the device to ~ 82% with a piezoelectric coefficient of 7.48 pm/V. The champion device produced an open circuit output voltage of 85 V and a current of 2.6  $\mu$ A. Furthermore, the device generated approximately ~1.26  $\mu$ W/cm<sup>2</sup> of power density when connected to a 0.8 M $\Omega$  resistor, sufficient to operate portable electronic gadgets. We tested the device for its energy generation capabilities under simple human biomechanical movements such as hand hammering, finger tapping, elbow bending, knee bending, and toe pressing. To demonstrate the versatility of the nanogenerator device, we also tested its energy

Journal of Materials Chemistry A Accepted Manuscript

generation and storage capabilities by charging capacitors up to ~2.2 V. The device exhibited the online impressive durability and repeatability over 10000 cycles, underscoring its potential as a promising solution for addressing the energy demand of portable and Internet of Things (IoT) devices through piezoelectric nanogenerators. Work function calculations by density functional theory demonstrated that the composite exhibited reduced work function compared to individual components, indicating favorable electron emission characteristics. We also realized the piezo-phototronic effect in the composite by a self-powered photodetector exhibiting an increment of 63%, offering a potential in piezotronics and optoelectronic devices.

*Keywords:* Lead-free halide perovskite, Self-powered sensor, Piezoelectric nanogenerator, Density functional theory, Piezo-phototronic effect.

#### 1. Introduction:

The ever-increasing demand for energy and the strained resources of traditional energy necessitate the development of self-powered electronic devices for efficient, sustainable energy sources, which is consequently an important focus area of global research. Environment protection and sustainable energy sources are the two main pillars of our future world, and much research has been undertaken to harness various types of renewable energy resources, including solar, thermal, mechanical, wind, and vibration [1,2]. In this context, the halide perovskites (e.g., CsPbBr<sub>3</sub>, MAPbI<sub>3</sub>, FAPbI<sub>3</sub>) have emerged significantly because of their exceptional properties like bandgap tunability, high charge carrier mobility and low exciton binding energies [3–6] due to which they have demonstrated tremendous potential in various energy and environmental applications, such as CO<sub>2</sub> reduction, light-emitting diodes, solar cells, piezoelectric and triboelectric nanogenerators, and enhanced photodetectors with piezo-phototronic effects [7–13].

The piezoelectric nanogenerators (PENGs) have gathered attention due to difference of the piezoelectric nanogenerators (PENGs) have gathered attention due to difference of the piezoelectric is in energy harvesting, self-powered electronics, wearable devices, and the Internet of Things (IoT) [11,14,15]. The nanogenerators can generate an electric field under external strain, making them suitable for energy harvesting from readily available environmental sources. Additionally, the photodetectors can convert light signals to electrical signals, making them useful in automation, live-cell imaging, and light sensing [16,17]. Although many organic and inorganic perovskite materials, including ceramics and semiconductors have been extensively used because of their ferroelectric, dielectric, and piezoelectric properties [18–22], lead toxicity, in the context of environmental safety, remains a critical issue. The manufacturing, usage, and disposal of lead-based materials can lead to soil, water, and air contamination, posing detrimental effects on ecosystems and human health, due to which the development and suitable integration of lead–free perovskites in energy harvesting devices is imperative.

Journal of Materials Chemistry A Accepted Manuscript

Replacing lead (Pb) to reduce environmental toxicity while retaining the critical physicochemical properties of halide perovskites is challenging, although some metal cations like tin (Sn<sup>2+</sup>) [23,24], germanium (Ge<sup>2+</sup>) [25,26], bismuth (Bi<sup>3+</sup>) [27–29], and antimony (Sb<sup>3+</sup>) [30,31], have been attempted with mixed success. Many different materials such as ceramics (BaTiO<sub>3</sub>, PZT, PMN-PT, NaNbO<sub>3</sub>, ZnSnO<sub>3</sub>, etc.) [32–36], semiconductors (ZnO, CdS, ZnS, GaN, etc.) [37–40], and polymers have been reported to have demonstrated superior energy conversion efficiencies and piezoelectric coefficients. Piezoelectric polymers and copolymers, such as polyvinylidene fluoride (PVDF), have been utilized for energy harvesting due to their high piezoelectric coefficient, chemical and thermal stability, flexibility, biocompatibility, and lightweight. Depending on their chain arrangements, these semi-crystalline polar polymers typically display active crystalline phases, including  $\alpha$ ,  $\beta$ ,  $\gamma$ , and  $\delta$  (a polar variant of  $\alpha$ ). The  $\alpha$  phase is non-polar in nature and the most thermodynamically stable phase [41]. The  $\beta$  and  $\gamma$ 

Journal of Materials Chemistry A Accepted Manuscript

are polar and semi-polar phases of PVDF. The non-polar phase of PVDF is used as an insular Article Online At the same time, the presence (and, if possible, enhancement) of the  $\beta$ -phase (TTTT conformation) is ideal for piezoelectric response since it has the maximum dipole moment per unit volume [42–45]. Additionally, one can attain ultrahigh content of the electroactive  $\beta$  phase of PVDF for high energy storage density [46].

Very recently, the piezo-phototronic effect has been explored to improve the performance of optoelectronic devices [13,47,48]. Due to the non-centrosymmetric crystal structure, piezoelectric charges and potentials in micro/nanostructures at the heterojunction or interface are capable of modulating the heterojunction band structure and tuning the charge separation, transport, and recombination in optoelectronic processes under normal stress. The hybrid perovskites (in pristine and in conjunction with polymeric systems) have shown potential applications as PENGs for energy harvesting by exploiting piezoelectric properties. Although the methods to harness the energy from light irradiation and mechanical stress are substantially different, developing materials that can synergistically combine the aforementioned energy sources through a suitable technique for self-powered optoelectronic devices is quite desirable. Thus, exploring the piezo-phototronic effect in such halide perovskites for use in self-powered photodetectors and piezoelectric nanogenerators is very intriguing.

This study focuses on a piezoelectric nanogenerator and piezo-phototronic effect based on lead-free perovskite  $Cs_3Sb_2I_9$ –PVDF composites, which can open up new avenues in the area of strain-induced optical sensing. The  $Cs_3Sb_2I_9$  perovskite was synthesized using a solution method and loaded (in different weight fractions) into the PVDF matrix to fabricate  $Cs_3Sb_2I_9$ -PVDF composites. The electroactive  $\beta$  phase increased up to ~82% in the optimized composite, which is much higher than that of pristine PVDF. The maximum and residual polarizations of the optimized composite (estimated from the P-E hysteresis loop) are 0.525  $\mu$ C/cm<sup>2</sup> and 0.026  $\mu$ C/cm<sup>2</sup>, respectively. The piezoresponse force microscopy of the optimized content composite shows a butterfly loop with a maximum deformation of ~ 150 pm under ±20 V bias, and the piezoelectric coefficient ( $d_{33}$ ) is found to be ~7.48 pm/V. The PENG device fabricated from the best composite generated an open circuit output voltage of ~85 V, a short circuit current of ~ 2.6  $\mu$ A, and a power density of ~1.26  $\mu$ W/cm<sup>2</sup> across a 0.8 MΩ resistance. Further, the best-performing device was used to generate electrical signals via various biomechanical motions and showed the capability of charging different capacitors, making it useful for small portable devices. The density functional theory (DFT) study showed a reduced work function at 5.27 eV of the composite of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> and PVDF, indicating the favorable electron emission properties from the Fermi level to the external environment. The piezo-phototronic effect was observed under tensile and compressive strains in dark and light conditions. The synergistic coupling of semiconducting properties of halide perovskites with piezoelectric properties and optical excitation offers newer perspectives on exploring mechanical energy harvesters as well as piezoresponse-based sensors and actuators.

Journal of Materials Chemistry A Accepted Manuscript

#### 2. Experimental Section

#### 2.1 Materials and chemicals:

Antimony (III) triiodide (SbI<sub>3</sub>, 98 %, OttoChem), cesium iodide (CsI, 99.99 % trace metals basis, Sigma Aldrich), N, N – dimethylformamide (DMF, dried,99.5%, water 0.005%, Sisco Research Laboratories Pvt. Ltd., India), isopropanol (IPA), acetone (Extra pure M.F.: (CH<sub>3</sub>)<sub>2</sub>CO, M.W. 58.08), and polyvinylidene fluoride (PVDF) (Mw-1,83,000) were procured from Sigma Aldrich. All chemical reagents were used without anyfurther purification.

#### 2.2 Synthesis of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> perovskite:

2 mmol of antimony triiodide (SbI<sub>3</sub>) was mixed in 1.5 mmol of DMF and stirred at 1000 rpm at room temperature until dissolved. After that, 3 mmol of cesium iodide (CsI) was mixed in the solution and stirred for one hour. The prepared solution was article Online centrifuged at 4000 rpm for 10 minutes in IPA. The collected compound was dried at 90 °C for 12 hours in a vacuum oven. The schematic representation of this synthesis is shown in Fig. S1 (see supplementary information).

#### 2.3 Preparation of the composite:

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

750 mg PVDF was dissolved in the mixture of 6 ml acetone and 4 ml DMF at 70 °C and 1000 rpm. Afterward, we added Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> with varying concentrations (2, 4, 6, 8, and 10 wt.%) and stirred for two hours. Upon getting a dark orange-colored homogeneous solution, it was drop cast on the cleaned glass slides and kept in a vacuum oven at 70 °C for 12 hours. Thereafter, the composites were removed from the glass slides and used for various characterization and fabrication of devices. To minimize the presence of the triboelectric effect, the fabricated devices were encapsulated in PDMS according to our previous work [49]. The schematic representation is shown in Fig. S2 (see SI). The composites were named PCSI2, PCSI4, PCSI6, PCSI8, and PCSI10, where PCSI signifies PVDF/Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> into the PDVF matrix.

#### 3. Characterization

X-ray diffraction (XRD) of the synthesized sample was performed on a Multipurpose XRD (SmartLab, Rigaku Corp.) with Cu-K<sub> $\alpha$ </sub> radiation of wavelength 1.5404 Å at room temperature. We used the JEOL JSM–7900F instrument for Field Emission Scanning Electron Microscopy (FESEM) for morphology and energy dispersive X-ray spectroscopy (EDX) for the elemental study of the sample. UV-vis spectra were done using a QE-R quantum efficiency measurement system (EnliTech, Taiwan). The thermogravimetric analysis (TGA) was

performed from room temperature to 800 °C under N<sub>2</sub> environment using a Perkin Elmer Trackereconteres system. The differential scanning calorimetry (DSC) was done on a Perkin Elmer DSC system. The vibrational modes of the Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> and PVDF composites were evaluated using Fourier Transform Infrared Spectroscopy (FTIR) (FTIR-Spectrum 2, PerkinElmer). Compositional analysis of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> was investigated by X-ray Photoelectron Spectroscopy (XPS) using a SPECS HSA-3500 hemispherical analyzer with a monochromatic Mg-K<sub>α</sub> X-ray source. An LCR spectrometer was used to make dielectric measurements in the frequency range of 4 Hz– 8 MHz (HIOKI, model: IM 3536). PFM measurement was performed in an Asylum Research AFM (MFP-3D BIO) to investigate the local piezo response properties. The spring constant value of the AFM tip is 2.80 N/m. The room temperature ferroelectric measurement was performed using the RADIANT ferroelectric test apparatus (Radiant Technologies Inc.) and Vision software. A digital storage oscilloscope was used to investigate the piezoelectric properties.

#### 3.1 Computational Details for DFT Study:

Theoretical studies have been carried out using the density functional theory (DFT) with the Vienna Ab initio Simulation packages (VASP) [50]. Projected Augmented Wave (PAW) pseudopotential [51] is used to depict the behavior of core electrons, and the electron exchange-correlation interaction is described by Perdew, Burke and Ernzerhof (PBE) within the Generalised Gradient Approximation (GGA) [52]. The kinetic energy cut-off for the plane wave basis set is taken as 450 eV, which is set after the convergence test. The convergence criteria for total energy and force during electronic and ionic relaxation were set at  $10^{-5}$  eV and  $10^{-2}$  eV/Å, respectively. The Brillouin zone in the *k*-space is sampled using the Monkhorst-Pack scheme with  $3\times3\times1$  *K*-Point grid. A heterostructure is constructed with a  $2\times3\times1$  supercell of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> and Polyvinylidene fluoride (PVDF), where Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> was cleaved along (003) plane [53]. To prevent the interaction between repeating images, a vacuum length of 30 Å is

Journal of Materials Chemistry A Accepted Manuscript

employed in the *c*-direction. DFT-D3 method is applied with the Becke-Johnson damping Addice Online function [54].

## 4. Results and Discussion:

The XRD profile of the synthesized Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> is shown in Fig. 1(a). The diffraction peaks at  $2\theta = 25.5^{\circ}$ , 26.1°, 27.8°, 30.1°, 32.7°, and 43.3° correspond to the planes (006), (202), (203), (204), (205), and ( $4\overline{2}0$ ) respectively, and matches with earlier reports [55]. The Rietveld refinement of XRD data was performed using FullProf Suite software. The estimated values of lattice parameters are a = 8.36 Å, b = 8.36 Å, c = 20.94 Å,  $\alpha = \beta = 90^{\circ}$ , and  $\gamma = 120^{\circ}$ , and is ascribed to the space group  $P\overline{3}m1$ . Figure 1(b) shows the crystal structure of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>,

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42.

) BΥ-NC

(00)



*Figure 1:* (a) The XRD profile and Rietveld refinement, (b) the crystal structure, and (c) UVvis spectroscopy of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>. Core level XPS spectra of (d) Cs, (e) Sb, and (f) I of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>.

which is rendered using VESTA software [56]. The UV-vis spectroscopy of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> (Fig. 1(c)) shows a sharp decrease at 580 nm. The bandgap is calculated using the Kubelka-Munk function and approximated to 2.08 eV (inset of Fig. 1(c)). The chemical compositions and oxidation

Journal of Materials Chemistry A Accepted Manuscript

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

states of the constitute elements of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> were examined using XPS and shown in Fig. <sup>yirwarticle Online</sup> (f). The peaks for Cs 3d<sub>5/2</sub>, Cs 3d<sub>3/2</sub>, Sb 3d<sub>5/2</sub>, Sb 3d<sub>3/2</sub>, I 3d<sub>5/2</sub>, and I 3d<sub>3/2</sub> appear at 725.3 eV, 739.4 eV, 530.5 eV, 539.8 eV, 619.1 eV, and 630.6 eV, respectively [53]. These peaks suggest that all the elements of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> are in their normal oxidation states. The survey scan of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> is shown in Fig. S3 (see SI). The FESEM image and the EDX spectrum of the prepared Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> sample are shown in Fig. S4 (a) and (b), respectively (see SI). The EDX of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> shown in Fig. S4 (b) (see SI) reveals only the presence of Cs, Sb, and I in the sample. The absence of impurity-related peaks in the EDX confirms that Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> is in its pure phase. In Fig. S4 (c) (see SI), the EDX mapping of the sample shows the uniform distribution of the elements, and the atomic ratio of the elements is found to be in the stoichiometric ratio of Cs: Sb: I = 22:14:64. The thermal analysis of  $Cs_3Sb_2I_9$  powder has been performed using thermogravimetric analysis (TGA) and differential scanning calorimetry (DSC). Figure S5(a) shows the TGA of the sample in the temperature range of 30 °C to 800 °C. The material remains stable up to ~370 °C, where a significant weight loss starts, indicating its decomposition. Around 600 °C, the weight drops to  $\sim$ 40% and continues to decrease gradually after this point. In Figure S5(b), the DSC curve illustrates heat flow during heating and cooling cycles from 30 °C to 410 °C. An exothermic peak is noticed around 370 °C during heating. However, upon cooling, the heat flow remains relatively stable, suggesting that the decomposition is irreversible. Figure S5(c) shows the TGA of PVDF and all the composites. PVDF is stable up to ~430 °C and starts degrading after that. However, in the case of composites, they start decomposing at an earlier temperature, ~400 °C. The reason for this could be the effect of the addition of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> as its weight decreases after 370 °C. The DSC curves of PVDF and all the composites are shown in Figure S5(d)-(i). From the plots, it is clear that there is not much change in the heat flow during the heating and cooling cycles.

The XRD profile of PVDF and all composites (PVDF with Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>) PCSI<sub>S</sub> are show the order in Fig. 2(a). The presence of peaks corresponding to Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> confirms the stability of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> structural phases within the PVDF matrix. In Fig. 2(b), the peaks appearing at  $2\theta$  = 18.6°, 20.2°, and 20.8° are related to the non-polar phase ( $\alpha$ ), semi-polar phase ( $\gamma$ ), and polar phase ( $\beta$ ) of PVDF, respectively [19,57,58]. In pristine PVDF, the  $\alpha$  phase is dominant as compared to the semi-polar and polar phases in Fig 2(b). Once Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> is added as a filler in the PVDF matrix, there is a notable enhancement in  $\beta$  and  $\gamma$  peak intensities (at 20.2° and 20.8°) while the  $\alpha$  peak intensity at (18.6°) decreases, as seen in Fig. 2(c). The deconvoluted XRD profiles of all other composites are shown in Fig. S6 (see SI). FTIR spectra of all the composite films are shown in Fig. 2(d). The bare PVDF shows the dominant non-polar  $\alpha$  phase as evident from the vibrational bands at 1214,1150, 976, 856, 796, 764, and 763 cm<sup>-1</sup>. The bands related to the semi-polar  $\gamma$  phase appeared at 1234 and 812 cm<sup>-1</sup>, [59] and the polar  $\beta$  phase appeared at 1275 cm<sup>-1</sup> [60,61]. Generally, PVDF consists of a low percentage of  $\beta$  phase (about 35%), which limits its piezoelectric energy harvesting properties. The incorporation of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>

Journal of Materials Chemistry A Accepted Manuscript



Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42.

) BY-NC

*Figure 2:* (a) The XRD of all composites, fitted XRD profile of (b) PVDF, and (c) PCSI8. (d) FTIR spectra of all the films, (e) variation of electroactive phase content as a function of weight % of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> in PVDF, (f) FESEM of PCSI8 over a vast area, and (g) EDX mapping of PCSI8.

increases the  $\beta$  phase content at the expense of the  $\alpha$  phase in the PVDF matrix. The bands at 764 cm<sup>-1</sup> and 840 cm<sup>-1</sup> are used to determine the electroactive phase content using the formula [49,62].

$$F_{EA} = \frac{A_{840}}{\frac{K_{840}}{K_{764}}A_{764} + A_{840}} \times 100\%$$
(1)

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

Here,  $A_{840}$  and  $A_{764}$  are the absorption intensities at 840 and 764 cm<sup>-1</sup>, respectively  $S_{840AOBCOTE}$ and  $K_{764}$  are the absorption coefficients corresponding to the bands 840 and 764 cm<sup>-1</sup> with the values  $7.7 \times 10^4$  cm<sup>2</sup>/mol and  $6.1 \times 10^4$  cm<sup>2</sup>/mol, respectively. The electroactive phase content increases as more and more Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> is loaded into the PVDF matrix, reaches a maximum of up to 82% for PCS18, and then it decreases when loading is increased further, as observed in Fig. 2(e). The surface of PCS18 shown in Fig. 2(f) shows a homogeneous mixing of the Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> perovskites with the PVDF matrix, with uniformly distributed oriented fibrils and the spherulitic shape of the composite. The EDX elemental mapping of the PCS18 composite is shown in Fig. 2(g), indicating the presence of Cs, Sb, I, C, and F. The EDX scan profile for the same sample is shown in Fig. S7 (see SI) and confirms the successful synthesis of the Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>\_PVDF hybrid. The FESEM images of PVDF and other PCSIs are shown in Fig. S8 (see SI).



*Figure 3:* Schematic representation of interfacial interaction between PVDF matrix and Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>.

The schematic representation of the interaction between PVDF and Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> is demonstrated in Fig. 3. Pristine PVDF consists of a significantly large portion of  $\alpha$  phase (TGTG configuration) compared to the  $\beta$  phase (TTTT configuration), limiting its piezoelectric energy harvesting properties. The incorporation of a filler increases the  $\beta$  phase at the experies of low phase in the PVDF matrix. When a filler like Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> is added, the interaction between the surface charges of the filler and  $-CH_2-$  and  $-CF_2-$  dipoles of PVDF induces the desired ordering of  $\beta$  phase, resulting in the enhanced electroactive phase content. We note from Fig. 2(e) that the electroactive phase content increases up to 82% with 8% loading, and after that, it decreases. This could be because the increased concentration creates the agglomeration of the filler, reducing the  $\beta$  phase, hence the reduced piezoelectric response [6,62].

#### 4.1. P-E hysteresis, dielectric, and PFM study

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

The P-E hysteresis loop of PVDF and other composite films is represented in Fig. 4(a), performed by sweeping the electric field (E) in the range of  $\pm 10$  kV/cm. Although the observed loops are not indicative of classical ferroelectric switching, they display characteristic dielectric polarization with distinguishable residual and maximum polarization values. The presence of polarization hysteresis, shown in the inset of Fig. 4(a), suggests dipolar alignment and interfacial polarization effects induced by the embedded perovskite crystals. While pure PVDF has a residual polarization ( $P_r$ ) of 0.01  $\mu$ C/cm<sup>2</sup> and a maximum polarization ( $P_s$ ) value of 0.184  $\mu$ C/cm<sup>2</sup>, the PCSI8 has a P<sub>r</sub> value of 0.026  $\mu$ C/cm<sup>2</sup> and a P<sub>s</sub> value of 0.525  $\mu$ C/cm<sup>2</sup>, the largest among all the PCSIs. The remanent and maximum polarization as a function of the weight percent of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> in PVDF are shown in Fig. 4(b). This implies that PCSI8 has the largest dipole moment per unit volume out of all the composites since it shows the maximum values of P<sub>r</sub> and P<sub>s</sub>, which can be attributed to an optimal filler-matrix interaction enhancing the net dipole contribution. After the loading of 8%, the values of  $P_r$  and  $P_s$  decrease due to the agglomeration of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> in the PVDF matrix. The pure PVDF shows the lowest remnant and saturation polarization, indicating the smallest dipole-dipole interaction. This also corroborates the fact that adding Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> to PVDF increases the dipolar interaction in the system, which in

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

turn enhances the electroactive β phase in the PVDF matrix. The leakage current densities of the online PVDF and all the composites were also measured to understand their insulating behavior, and are shown in Fig. S9 (see SI). The leakage current measurements reveal that the PCSI8 composite exhibits a slightly higher current than pristine PVDF and the 2 wt% sample, but remains significantly lower than those with 4%, 6%, and 10% loading. This suggests that while increasing perovskite content can introduce localized conductive pathways, the 8 wt% composition still maintains a good dielectric character with controlled leakage. This moderate leakage, combined with enhanced polarization, indicates an optimal trade-off between dipolar response and electrical insulation, suitable for the nanogenerator application.

Impedance spectroscopy (IS) is a useful study that explores the electrical properties of a material as a function of frequency and temperature. It helps in understanding the behavior of bound and mobile charges, energy storage, and dissipation in solid-state devices. The temperature-dependent complex dielectric permittivity spectra were deduced using the IS data. A qualitative discussion on the complex impedance spectra, comprising of frequency and temperature variation in the real ( $Z'(\omega)$ ) and imaginary ( $Z''(\omega)$ ) part of impedance, can also be found in the supplementary information (see SI).

The behavior of a dielectric material towards an electric field can be understood using complex dielectric formalism, which is represented as

$$\epsilon^*(\omega) = \epsilon'(\omega) - j\epsilon''(\omega)$$

where  $\epsilon'(\omega)$  and  $\epsilon''(\omega)$  are the real and imaginary parts of complex dielectric permittivity  $\epsilon^*(\omega)$  which represent the stored energy and energy dissipation of the applied electric field [63] and can be calculated using the below equations.

$$\epsilon'(\omega) = \frac{Z'}{\omega C_o(Z'^2 + Z''^2)}$$

 $\epsilon''(\omega) = \frac{Z''}{\omega C_0 (Z'^2 + Z''^2)}$ 

Journal of Materials Chemistry A Accepted Manuscript

Here,  $C_0 = \frac{\epsilon_0 A}{t}$  is the free space capacitance,  $\epsilon_0$  is the permittivity of free space, A is the area of the electrode, and d is the thickness of the pellet.

Figure S10(c) and (d) show the frequency dependent  $\epsilon'(\omega)$  and  $\epsilon''(\omega)$ , respectively, at different temperatures, indicating that  $\epsilon'(\omega)$  and  $\epsilon''(\omega)$  are higher when the frequency is low and gradually decreases when the frequency increases for a particular temperature. The dielectric behavior mainly depends on electronic, ionic, interfacial, and orientational polarizations.  $\epsilon'(\omega)$  is higher in the low frequency region and decreases as the frequency increases. In the low frequency region (< 10 KHz), interfacial polarizations are more dominant, which contributes to the value of the dielectric constant,  $\epsilon'(\omega)$ . However, in the high frequency region (>10 KHz), orientational, electronic, and ionic polarizations take over. At low frequencies, dipoles in the material have enough time to align themselves with the applied field, leading to a high dielectric constant. Since the orientation polarization also depends on the temperature,  $\epsilon'(\omega)$  also increases with the increase in the temperature. However, the dipoles struggle to keep up with the fast-changing field, hence the reduced dielectric constant. To understand whether or not the materials (Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>, PVDF, and PCSI) exhibit ferroelectric phase transition, we further checked the  $\epsilon'$  vs T behavior at higher frequencies (10 kHz) shown in Fig. S10(e)-(g). However, in the  $\epsilon'$  vs T plot, we do not observe the typical  $\lambda$ -shaped behavior characteristic of a ferro-to-paraelectric phase transition, which indicates the predominant dielectric nature of the Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> and the composite samples. The  $\epsilon'$  value for PCSI8 shows a strong temperature dependence as compared to that for the Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> and bare PVDF, implying that PCSI8 has a higher tendency of orienting dipoles compared to Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> and bare PVDF. However, none of the samples follow the typical Curie-Wiess law for ferroelectric to paraelectric transition.

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

The dielectric loss,  $\epsilon''(\omega)$ , shows higher values at low frequencies but decreases with  $\alpha_{000010}^{\text{true Control}}$ the frequency increases. At low frequencies, the charge carriers experience higher resistance due to space charge accumulation at the grain boundaries, which leads to more energy dissipation. However, at higher frequencies, charge carriers cannot follow the fast switching of the field, and hence, the conduction loss is reduced significantly, which is consistent with Koop's phenomenological theory [64]. We also plotted loss tangent, tan  $\delta$ , as a function of frequency at various temperatures, shown in Fig. S10(h). It is the ratio of dielectric loss to dielectric constant ( $\epsilon''/\epsilon'$ ) which provides the energy dissipation caused by charge carrier conduction represented by broad loss peaks. The occurrence of this peak is because of the alignment of the hopping frequency with the frequency of the applied external field. The loss peaks also shift to higher frequencies as temperature increases because of temperatureactivated hopping phenomena.

The dielectric properties of the composites are significant for energy storage devices. A material's dielectric constant can reveal the charging capacity, while the dielectric loss feature accounts for the energy dissipation in every cycle. The dielectric nature of PCSIs is similarly affected by the addition of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> to PVDF. Figure 4(c) shows the dielectric



Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42.

BY-NC

**Figure 4:** (a) P-E loop of PVDF and PCSIs and the inset shows the zoomed PE loop of PVDF and PCSI8, (b) residual and saturation polarization as a function of weight %, (c) Variation of  $\varepsilon_r$  with frequency, (d) dielectric loss of the composites as a function of frequency, (e) The amplitude image, (f) The phase image, (g) The amplitude vs bias, (h) The phase vs bias, (i) piezo response vs bias.

permittivity ( $\varepsilon_r$ ) of all the PCSIs in the frequency range of 1 kHz to 1 MHz at ambient temperature. The  $\varepsilon_r$  values of all the composites are greater than that of pure PVDF. As the loading amount of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> is increased, the value of  $\varepsilon_r$  also increases, which may be attributed to the interfacial interaction between PVDF and some preferred terminations of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> surfaces [52]. Among all the composites, PCSI8 has the highest  $\varepsilon_r$  value, and after 8% loading of the perovskite in the PVDF matrix, it decreases because of agglomeration. The larger values

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42.

of  $\varepsilon_r$  at a low-frequency range are a cumulative effect of the ionic, interfacial, dipolar value of  $\varepsilon_r$  decreases as the frequency increases, owing electronic polarizations. However, the value of  $\varepsilon_r$  decreases as the frequency increases, owing to the weakening of interfacial/space polarization [65]. Figure 4(d) shows the dielectric loss (tan( $\delta$ )) of the composites as a function of frequency. The dielectric loss of the composites increases rapidly after the frequency of 10 kHz because of the relaxation loss. The stored energy density and the energy loss density were calculated by integrating the different parts of the P-E loop (Fig. 4(a)), using the formula [6,62]

$$U = \int E \, dP \tag{2}$$

Where U is the energy density, E is the electric field, and P is the polarization. The stored energy density and energy loss density of bare PVDF and other composites are shown in Fig. S11 (see SI). The energy values of PCSIs expectedly increased up to 8% and then started decreasing owing to the reduction in the electroactive  $\beta$  phase.

The piezoresponse force microscopy (PFM) analysis was performed to check the piezoresponse of the composite film PCSI8. The amplitude and phase images over 25  $\mu$ m × 25  $\mu$ m are shown in Fig. 4(e) and 4(f), respectively. In Fig. 4(g), the composite shows an amplitude "butterfly" loop with a maximum deformation of ~ 150 pm under ±20 V bias (OFF state). Figure 4(h) shows the phase response loop of the PCSI8 composite with ±20 V applied bias voltage. The OFF state is preferred for these experiments to reduce the effects of electrostatic interactions. The piezoelectric coefficient ( $d_{33}$ ) which is calculated using the formula  $A_{deflection} = d_{33}E_{ac}$  is ~7.48 pm/V, which is higher than that of other materials like GaN (3.1 pm/V), NaNbO<sub>3</sub> (4 pm/V), and MAPbI<sub>3</sub> [66–68]. The mechanical strain developed within the film under an applied field affirms the presence of piezo-response in the composite. The piezoresponse hysteresis loop is shown in Fig. 4(i), obtained by P<sub>r</sub> = A(E) cos[ $\phi$ (E)], where A(E)

Journal of Materials Chemistry A Accepted Manuscrip





**Figure 5:** (a) The open circuit voltage and (b) short circuit current of all the devices. (c) Voltage and current as a function of load resistance, (d) power density vs resistance, (e) voltage response in forward and reverse bias configuration, (f) rectified DC voltage of PCSI8 device, and (g) schematic representation of the working mechanism of the piezoelectric response under external mechanical deformations.

#### 4.2. Piezoelectric Nanogenerator performance for energy harvesting application

To investigate the piezoelectric response for energy harvesting applications, the nanogenerator devices of bare PVDF and PCSIs were fabricated. The schematic of the device

Page 21 of 41

configuration is shown in Fig. S13 (see SI). The effective area of the device is  $7 \times 2$  cm<sup>2/iew Adjice Online</sup> the piezoelectric effect was obtained by repeated hand hammering without any external electric polling. We recorded the open circuit voltage and the short circuit current of all the devices, as shown in Fig. 5(a) and 5(b), respectively. The open circuit voltage (Fig. 5(a)) and the short circuit current (Fig. 5(b)) of PVDF are ~ 17 V and 0.5  $\mu$ A, which increased up to ~ 85 V and ~ 2.6  $\mu$ A for PCSI8 because of the highest content of the electroactive phase (~82%) in the composite. Although the output performances for all the PCSIs are better than bare PVDF, the PCSI8 device showed the best performance. The dependence of output voltage and current as a function of load resistance was also studied. The resistance was connected in the series with the PCSI8 and varied from 1 k $\Omega$  to 10 M $\Omega$ . In Fig. 5(c), the output voltage gets saturated at high resistance values while the current follows the reverse trend of the output voltage. The variation of the output power of PCSI 8 as a function of the load resistance is shown in Fig. 5(d), yielding a maximum output power density of ~1.26  $\mu$ W/cm<sup>2</sup> across at 0.8 M $\Omega$  resistor. The power density of PVDF as a function of resistance is shown in Fig. S14 (see SI). For PCSI8, the best-performing device, with the addition of 8% Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> in the PVDF, the voltage increases by 80%, and power density increases  $\sim$ 320 times that of pure PVDF. Upon changing the polarity of the PCSI8, the output voltages in the forward and reverse bias connection are almost the same (Fig. 5(e)), confirming that the voltage is primarily due to a piezoelectric effect. Figure 5(f) shows the DC output voltage of PCSI8, obtained using a bridge rectifier circuit. A schematic in Fig. 5(g) explains the mechanism of the generation of piezoelectric potential from PCSIs under mechanical stress. The molecular dipoles are represented by strips having positive and negative charges at the end. The polarization is defined as the sum of the electric dipole moment of all the molecular dipoles per unit volume. The molecular dipoles have different dipole moments. Initially, when there is no force imparted on the composites, they are oriented randomly, making the total electric dipole moment of the system zero, and

Journal of Materials Chemistry A Accepted Manuscript

ournal of Materials Chemistry A Accepted Manuscript

hence, there is no electric signal in the external circuit. When a mechanical force is applied offer online the top surface of the PCSI, the electric dipoles get oriented in the direction of the applied force. So, the electric dipole moment occurs in the composite, and positive and negative charges are induced at the top and bottom surfaces. The applied pressure deforms the crystalline structure, which has weaker Van der Waals contact and electrostatic interaction, generating a piezo potential between the two surfaces. This piezo potential causes charges on the top and bottom electrodes, generating a positive voltage signal. On the other hand, when the pressure is released, the piezoelectric potential vanishes, and the stored electrons flow in the opposite direction, resulting in a negative or reverse voltage signal [62,69,70].

Figure S15 (see SI) illustrates the output voltage of PCSI8 under varying conditions of frequency and applied force. Figure S15(a) shows that the output voltage remains relatively consistent with different frequencies (0.5 Hz to 10 Hz). However, the number of voltage cycles increases with frequency. In Fig. S15(b), the output voltage is shown under varying applied forces, where an increase in the force from 1 N to 9 N leads to a significant rise in voltage, suggesting that the nanogenerator is responsive to applied force variations.

22

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42.

(cc)) BY-NC



*Figure 6:* The output voltage due to (a) finger bending, (b) elbow bending, (c) knee bending, (d) heel pressing, (e) toe pressing, and (f) capacitor charging by PCSI8, (g) the circuit for capacitor charging, (h) long cycle output voltage up to 10000 cycles, and (i) glowing LEDs.

Journal of Materials Chemistry A Accepted Manuscript

To show the energy harvesting capability of PCSI8 via physiological motions<sup>ViewAdjCle Online</sup> performed various human motions and observed the output voltages due to them. The output voltages corresponding to finger bending (~ 0.9 V), elbow bending (~ 0.7 V), knee bending (~ 0.8 V), heel pressing (~ 2.1 V), and toe pressing (~ 5.2 V) were recorded and shown in Fig. 6(a)-(e). Figure 6(f) shows the charging of capacitors of values 2.2  $\mu$ F, 4.7  $\mu$ F, 10  $\mu$ F, 33  $\mu$ F, 47  $\mu$ F, 470  $\mu$ F using the PCSI8 device via a bridge rectifier circuit, shown in Fig. 6(g). The



respectively; (d) and (e) show the PDOS of Sb-p and I-p orbitals, respectively in the  $Cs_3Sb_2I_9$ -PVDF composite; (f),(g) and (h) shows workfunction of  $Cs_3Sb_2I_9$ , PVDF and  $Cs_3Sb_2I_9$ -PVDF structures.

charging voltage increases exponentially and gets saturated at 2.2 V. The capacitor, with Streaged online value of capacitance gets charged much earlier. The ability to charge different capacitors in a reasonably quick time indicates that the PCSIs can be used as energy storage devices to self-power portable electronic gadgets. The device's longevity, durability, and reproducible output response are checked using a long-cycle fatigue test. The output voltage of PSCI8, shown in Fig. 6(h), remains constant during the long-cycle operation for 10000 continuous cycles. The comparison of other reported nanogenerators' performance is shown in Table S1 (see SI). Using only hand-hammering motion, the PCSI8 device also successfully illuminated an array of commercially available LEDs, shown in Fig. 6(i), the video of which is available as a video supplementary (VS1).

#### 4.3 DFT Study

In order to validate the experimental results DFT calculations were performed. We considered the orthorhombic  $\beta$ -phase of PVDF as shown in Fig. S16 (a) (see SI). The Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> crystal structure is shown in Fig. S16 (b) (see SI). Based on the XRD data, we selected the most prominent peaks associated with the (203) plane of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> to establish the composite with a long chain of polyvinylidene fluoride (PVDF). After optimizing the long chains of PVDF polymer on the surface of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> (203), we observed that PVDF forms bonds by physisorption. The optimized structure of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> PVDF is shown in Fig. S16 (c) (see SI).

Journal of Materials Chemistry A Accepted Manuscript

To understand the electronic properties, we have estimated the Density of States (DOS) for Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>, PVDF, and Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>-PVDF systems. The DOS results of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>, PVDF and Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>-PVDF systems are depicted in Fig. 7(a), 7(b), and 7(c), respectively [53,69]. It is noticeable from Fig. 7(a)-(c) that there is a symmetric behavior of the density of states for up and down spin, demonstrating the non-magnetic properties of these compounds. Further, there is a distinct separation between valence band maxima (VBM) and conduction band minima

Journal of Materials Chemistry A Accepted Manuscript

(CBM), which represents the insulating behavior of these compounds. The above Figs of Marcacone (c) clearly shows that there is a reduction in the band gap (Eg) while the Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> surfaces interact with the PVDF. The reduction in the band gap occurs due to the shift of p-orbital conduction states towards lower energy of the antimony and iodine, respectively, which is shown in Fig. 7(d) and (e). The cause of this shift can be attributed to the interaction between Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> and PVDF layers [71]. Work function calculations have been done to see how easily an electron can be removed from these materials to an external environment. Work functions for Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>, PVDF, and Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>-PVDF are depicted in Fig. 7(f)-(h). In our calculation, the work function for Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> and PVDF are determined to be 4.74 eV and 6.46 eV, respectively. For the composite material Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>-PVDF, the work function is measured at 5.27 eV. Once the composite is formed, the material exhibits a reduced work function. This suggests that electrons can readily transition from the Fermi level to the external environment, indicating the favorable electron emission characteristics of the composite material.

#### 4.4. Piezo-phototronic effect

We have further demonstrated the piezo-phototronic effect in the PCSI8 of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> and PVDF under positive and negative strain in the presence of light. The device was prepared by placing PCSI8 on a flexible substrate. Then, the silver contact for the photodetection was made using a physical vapor deposition technique, and two wires were connected at the end with silver paste with an active area of  $2.5 \times 1.6$  cm<sup>2</sup>. Figure 8(a) shows the schematic of the customized setup for investigating the piezo-phototronic effect where the orange-colored film with two electrodes between the two blue boxes is PCSI8. Here, one end was kept fixed while the other could be moved to bend the film in different curvatures, creating both positive and negative strain in the composite.

The bending strain was calculated as,

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42.

| BY-NC



**Figure 8:** (a) Schematic diagram for the measurement of piezo-phototronic effect, (b) I-V measurement PCSI8 under positive and negative strain, under illuminated condition, (c) I-V measurement PCSI8 under positive and negative strain, under dark condition, (d) Change in the current of photodetector in dark and illuminated conditions, and schematic structure and energy band diagrams of PCSI8 under (e) without strain and in dark (f) with strain and in dark condition.

$$=\frac{t}{2r}$$
View Article Online
DOI: 10.1039(3)TA08601E

Where  $\epsilon$ , t, and r are the strain, thickness of the film, and bending radius, respectively. The bending radius was calculated using,

 $\epsilon$ 

$$\sin\left(\frac{L}{2r}\right) = \frac{L - L_0}{2r} \tag{4}$$

The derivation of eqn. (4) is provided in supporting information text. Here, L and  $L - L_0$  are the initial and reduced lengths, respectively.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42.

The current-voltage data were recorded under a bias of  $\pm 10$  V, and the strain was varied from -1.37 % to +1.37 % under the irradiated condition. In Fig. 8(b), the photocurrent increases with an increment in positive strain under the light illumination, which can be ascribed to the piezo-phototronic effect in the PCSI composite [13,47,72–75]. When the positive strain is applied, a positive piezoelectric potential gets generated, which decreases the Schottky barrier height (SBH), facilitating the transportation of the electrons. This reduction of the barrier height aids the electron-hole separation and decreases the recombination of the electron-hole pairs, ultimately increasing the photocurrent. On the other hand, when the negative strain was applied to the composite, the photocurrent reduced with the increment of the negative strain. This is because the negative strain induces the negative piezo potential, leading to the increment in the Schottky barrier height, which opposes the transportation of the electron and, consequently, less photocurrent [47,73]. Further, when the positive and negative strains were applied to the PCSI in the dark, the effect of piezo potential on the dark current in both cases was negligible, [73] as shown in Fig. 8(c).

We also measured the short circuit current in dark and illuminated conditions on a photodetection-based device, similar to a piezoelectric nanogenerator. The self-powered photodetector was fabricated by depositing the solution of PCSI8 on a flexible ITO-coated PET

Page 29 of 41

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

substrate, and a top contact. In dark conditions,  $I_{sc}$  was approximately 0.47  $\mu$ A, and under the substrate online on the substrate of th light irradiation, it was ~ 1.3  $\mu$ A, leading to the enhancement in I<sub>sc</sub> by 63%, as shown in Fig 8(d). To understand the mechanism, a schematic of the energy band diagram is shown in Fig 8(e) and (f). In the Cu/PCSI/ITO architecture, the interface between Cu and PCSI is metalsemiconductor contact, while that between PCSI and ITO is ohmic contact. The schematic of the device with the energy band diagram is shown in Fig. 8(e) in unstrained and light-off conditions. When a compressive strain was applied to PCSI, the positive and negative charges merged at the surface of PCSI due to piezoelectric potential. Due to this, a change in the Schottky barrier height occurs, which determines the flow of the charge carriers through the contact. As discussed earlier, the positive and negative piezoelectric potentials will cause a change in the SBH. So, the energy band at Cu/PCSI contact goes down, and the energy band at PCSI/ITO contact goes up, as demonstrated in Fig. 8(f) [76]. When the light is irradiated on it, the charge carriers will be generated in the PCSI, and the piezoelectric potential due to strain helps in the separation of electron-hole pairs, preventing their recombination process and increasing the current density, as shown in Fig. 8(g). We also measured the output voltage in dark and irradiated conditions. In the dark condition, it was  $\sim 8.6$  V, and when the light was turned on, the output voltage decreased to ~ 6.2 V, a drop of ~ 28 %, shown in Fig. S18 (see SI). When the light is on, the photo-generated charge carriers start moving within PCSI, generating a local electromagnetic field that can prevent the movement of the charge carriers, as shown in Fig. 8(g). Due to this, there will be less flow of free electrons in the circuit, resulting in less output voltage. Thus, we successfully demonstrate the piezo-phototronic effect in PCSI, which can be used as a self-powered optoelectronic device. These composites have tremendous potential to be employed as optoelectronic sensors due to their synergistic properties encompassing enhanced biomechanical energy harvesting as well as photodetection properties.

Journal of Materials Chemistry A Accepted Manuscript

#### 5. Conclusion:

View Article Online DOI: 10.1039/D4TA08601E

In conclusion, we have successfully developed an environment-friendly, easily processable, cost-effective, flexible, mechanically robust, and self-sustaining device based on a lead-free halide perovskite - Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> and PVDF composite. Controlled incorporation of  $Cs_3Sb_2I_9$  into the PVDF matrix could enhance the nucleation of the electroactive ( $\beta$ ) phase content. The best device (obtained by loading 8% of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> into the PVDF matrix) exhibited appreciable performance with approximately  $\sim 82\%$  of  $\beta$  phase activation and a piezoelectric coefficient of ~7.48 pm/V, which is significantly higher than bare PVDF. The dielectric permittivity of the composites also increased with the addition of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub> into PVDF, making them suitable for energy storage devices. The device displayed a maximum remanent polarization of 0.026  $\mu$ C/cm<sup>2</sup> and a saturation polarization of 0.525  $\mu$ C/cm<sup>2</sup>). Further, the device generated a maximum open circuit voltage of ~85 V and, a short circuit current of ~2.6  $\mu$ A and a maximum power density of ~1.26  $\mu$ W/cm<sup>2</sup> (across a 0.8 M $\Omega$  resistor), which can sustain portable electronic gadgets and exhibited impressive durability and repeatability, withstanding up to 10000 cycles. DFT calculation was invoked to understand the interactions of the perovskite surfaces with the PVDF. It is noted from the calculations that the composite exhibited reduced work function (5.27 eV), indicating favorable electron emission characteristics. Finally, we realized the piezo-phototronic effect in the composite by combining the piezoresponse and photoexcitation processes, yielding a photocurrent increment of 63%, with prospective applications in integrated piezotronics sensing and optoelectronic devices.

Author contribution: Prabhat Kumar: Investigation; Conceptualization; Formal analysis; Writing - original draft. Tufan Paul: Conceptualization; Validation; Visualization. Aditi Sahoo: Investigation; Validation. Manoj Singh: Conceptualization; Data curation; Methodology. Arupjyoti Pathak: Data curation; Methodology. Ranjit Thapa: Software;

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

Supervision; Validation; Writing - review & editing. Rupak Banerjee: Investigation; Fund Added acquisition; Resources; Supervision; Validation; Writing - review & editing.

#### **Conflicts of interest:**

There are no conflicts to declare.

#### **Data Availability:**

The data supporting this article have been included as part of the Supplementary Information.

#### Acknowledgment:

Funding from the MoE-STARS, Govt. of India under the project MoE-STARS/STARS-1/231 and ANRF, Govt. of India under the project CRG/2022/005258 is gratefully acknowledged. We also thank the Central Instrumentation Facility at IIT Gandhinagar for facilitating several measurements.

#### **References:**

[1] I.-Y. Suh, Y.-J. Kim, P. Zhao, D.S. Cho, M. Kang, Z.-Y. Huo, S.-W. Kim, Self-powered microbial blocking textile driven by triboelectric charges, Nano Energy 110 (2023) 108343. https://doi.org/10.1016/j.nanoen.2023.108343.

[2] S.J. Kim, J.H. We, B.J. Cho, A wearable thermoelectric generator fabricated on a glass fabric, Energy Environ. Sci. 7 (2014) 1959–1965. https://doi.org/10.1039/C4EE00242C.

[3] N.H. Makani, A. Sahoo, P. Pal, T. Paul, L.S. Tanwar, M. Singh, A. Ghosh, R. Banerjee, Onset of vacancy-mediated high activation energy leads to large ionic conductivity in twodimensional layered Cs<sub>2</sub>PbI<sub>2</sub>Cl<sub>2</sub> Ruddlesden-Popper halide perovskite, Phys. Rev. Mater. 6 (2022) 115002. https://doi.org/10.1103/PhysRevMaterials.6.115002. [4] R.J. Sutton, G.E. Eperon, L. Miranda, E.S. Parrott, B.A. Kamino, J.B. Patel, New Tricle Online Hörantner, M.B. Johnston, A.A. Haghighirad, D.T. Moore, H.J. Snaith, Bandgap-Tunable Cesium Lead Halide Perovskites with High Thermal Stability for Efficient Solar Cells, Advanced Energy Materials 6 (2016) 1502458. https://doi.org/10.1002/aenm.201502458.

[5] M.T. Khan, M. Salado, A. Almohammedi, S. Kazim, S. Ahmad, Elucidating the Impact of Charge Selective Contact in Halide Perovskite through Impedance Spectroscopy, Advanced Materials Interfaces 6 (2019) 1901193. https://doi.org/10.1002/admi.201901193.

[6] N.H. Makani, P. Kumar, T. Paul, A. Sahoo, S. Maiti, R. Banerjee, Low-dimensional halide perovskite/PVDF nanocomposite with enhanced piezoelectricity as flexible biomechanical energy harvester, Chemical Physics Impact 8 (2024) 100564. https://doi.org/10.1016/j.chphi.2024.100564.

[7] M. Singh, J. Nama, T. Paul, N.H. Makani, A. Sahoo, S. Sharma, R. Banerjee, Photoelectrochemically Induced CO<sub>2</sub> Reduction Using Halide-Tunable Lead-Free Perovskites, ACS Appl. Energy Mater. 6 (2023) 3566–3578. https://doi.org/10.1021/acsaem.3c00053.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

[8] J. Xu, W. Huang, P. Li, D.R. Onken, C. Dun, Y. Guo, K.B. Ucer, C. Lu, H. Wang, S.M. Geyer, R.T. Williams, D.L. Carroll, Imbedded Nanocrystals of CsPbBr<sub>3</sub> in Cs<sub>4</sub>PbBr<sub>6</sub> : Kinetics, Enhanced Oscillator Strength, and Application in Light-Emitting Diodes, Advanced Materials 29 (2017) 1703703. https://doi.org/10.1002/adma.201703703.

[9] M.R. Leyden, L.K. Ono, S.R. Raga, Y. Kato, S. Wang, Y. Qi, High performance perovskite solar cells by hybrid chemical vapor deposition, J. Mater. Chem. A 2 (2014) 18742–18745. https://doi.org/10.1039/C4TA04385E.

[10] A. Sahoo, T. Paul, P. Pal, N.H. Makani, A. Ghosh, R. Banerjee, Dielectric Relaxation Mechanism in the Phase-Transition Region of a Chiral Hybrid Perovskite and Its Piezoelectric-Energy-Harvesting Properties, Phys. Rev. Appl. 20 (2023) 034024. https://doi.org/10.1103/PhysRevApplied.20.034024.

[11] J. Kwon, W. Seung, B.K. Sharma, S.-W. Kim, J.-H. Ahn, A high performance PZT ribbon-based nanogenerator using graphene transparent electrodes, Energy Environ. Sci. 5 (2012) 8970–8975. https://doi.org/10.1039/C2EE22251E.

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

[12] Z.L. Wang, Triboelectric Nanogenerators as New Energy Technology for Self-PowerAdicle Online Systems and as Active Mechanical and Chemical Sensors, ACS Nano 7 (2013) 9533–9557. https://doi.org/10.1021/nn404614z.

[13] Q. Lai, L. Zhu, Y. Pang, L. Xu, J. Chen, Z. Ren, J. Luo, L. Wang, L. Chen, K. Han, P. Lin, D. Li, S. Lin, B. Chen, C. Pan, Z.L. Wang, Piezo-phototronic Effect Enhanced Photodetector Based on CH<sub>3</sub>NH<sub>3</sub>PbI<sub>3</sub> Single Crystals, ACS Nano 12 (2018) 10501–10508. https://doi.org/10.1021/acsnano.8b06243.

[14] X. Chen, X. Li, J. Shao, N. An, H. Tian, C. Wang, T. Han, L. Wang, B. Lu, High-Performance Piezoelectric Nanogenerators with Imprinted P(VDF-TrFE)/BaTiO<sub>3</sub> Nanocomposite Micropillars for Self-Powered Flexible Sensors, Small 13 (2017) 1604245. https://doi.org/10.1002/smll.201604245.

[15] S. Barsiwal, A. Babu, U.K. Khanapuram, S. Potu, N. Madathil, R.K. Rajaboina, S. Mishra, H. Divi, P. Kodali, R. Nagapuri, T. Chinthakuntla, ZIF-67-Metal–Organic-Framework-Based Triboelectric Nanogenerator for Self-Powered Devices, Nanoenergy Advances 2 (2022) 291–302. https://doi.org/10.3390/nanoenergyadv2040015.

[16] Q. Zheng, M. Peng, Z. Liu, S. Li, R. Han, H. Ouyang, Y. Fan, C. Pan, W. Hu, J. Zhai,
Z. Li, Z.L. Wang, Dynamic real-time imaging of living cell traction force by piezo-phototronic light nano-antenna array, Science Advances 7 (2021) eabe7738.
https://doi.org/10.1126/sciadv.abe7738.

[17] X. Gong, M. Tong, Y. Xia, W. Cai, J.S. Moon, Y. Cao, G. Yu, C.-L. Shieh, B. Nilsson,
 A.J. Heeger, High-Detectivity Polymer Photodetectors with Spectral Response from 300 nm to
 1450 nm, Science 325 (2009) 1665–1667. https://doi.org/10.1126/science.1176706.

[18] A. Swarnkar, A.R. Marshall, E.M. Sanehira, B.D. Chernomordik, D.T. Moore, J.A. Christians, T. Chakrabarti, J.M. Luther, Quantum dot-induced phase stabilization of  $\alpha$ -CsPbI<sub>3</sub> perovskite for high-efficiency photovoltaics, Science 354 (2016) 92–95. https://doi.org/10.1126/science.aag2700.

[19] S. Mondal, T. Paul, S. Maiti, B.K. Das, K.K. Chattopadhyay, Human motion interactive mechanical energy harvester based on all inorganic perovskite-PVDF, Nano Energy 74 (2020) 104870. https://doi.org/10.1016/j.nanoen.2020.104870.

Journal of Materials Chemistry A Accepted Manuscrip

[20] A. Sultana, P. Sadhukhan, M. Alam, S. Das, T. Middya, D. Mandal, Organo FierAdicle Online Halide Perovskite Induced Electroactive β-Phase in Porous PVDF Films: An Excellent Material for Photoactive Piezoelectric Energy Harvester and Photodetector, ACS Applied Materials & Interfaces 10 (2018). https://doi.org/10.1021/acsami.7b17408.

[21] D.B. Kim, K.S. Jo, K.S. Park, Y.S. Cho, Anion-Dependent Polarization and Piezoelectric Power Generation in Hybrid Halide MAPbX<sub>3</sub> (X = I, Br, and Cl) Thin Films with Out-of-Plane Structural Adjustments (Adv. Sci. 4/2023), Adv Sci (Weinh) 10 (2023) 2370022. https://doi.org/10.1002/advs.202370022.

[22] D.B. Kim, K.H. Park, Y.S. Cho, Origin of high piezoelectricity of inorganic halide perovskite thin films and their electromechanical energy-harvesting and physiological currentsensing characteristics, Energy Environ. Sci. 13 (2020) 2077–2086. https://doi.org/10.1039/C9EE03212F.

[23] W. Liao, D. Zhao, Y. Yu, C.R. Grice, C. Wang, A.J. Cimaroli, P. Schulz, W. Meng, K. Zhu, R.-G. Xiong, Y. Yan, Lead-Free Inverted Planar Formamidinium Tin Triiodide Perovskite Solar Cells Achieving Power Conversion Efficiencies up to 6.22, Adv Mater 28 (2016) 9333–9340. https://doi.org/10.1002/adma.201602992.

[24] J. Zillner, H.-G. Boyen, P. Schulz, J. Hanisch, N. Gauquelin, J. Verbeeck, J. Küffner, D. Desta, L. Eisele, E. Ahlswede, M. Powalla, The Role of SnF<sub>2</sub> Additive on Interface Formation in All Lead-Free FASnI3 Perovskite Solar Cells, Advanced Functional Materials 32 (2022) 2109649. https://doi.org/10.1002/adfm.202109649.

[25] R. Chiara, M. Morana, L. Malavasi, Germanium-Based Halide Perovskites: Materials,
 Properties, and Applications, ChemPlusChem 86 (2021) 879–888.
 https://doi.org/10.1002/cplu.202100191.

[26] Y. Raoui, S. Kazim, Y. Galagan, H. Ez-Zahraouy, S. Ahmad, Harnessing the potential of lead-free Sn–Ge based perovskite solar cells by unlocking the recombination channels, Sustainable Energy Fuels 5 (2021) 4661–4667. https://doi.org/10.1039/D1SE00687H.

[27] P. Chandra, S. Saha, S.K. Mandal, A dielectric study of Br-doped lead-free methylammonium bismuth chloride (CH<sub>3</sub>NH<sub>3</sub>)<sub>3</sub>Bi<sub>2</sub>Br<sub>x</sub>Cl<sub>9-x</sub>, Appl. Phys. A 128 (2022) 541. https://doi.org/10.1007/s00339-022-05677-9. [28] H. Lei, D. Hardy, F. Gao, Lead-Free Double Perovskite Cs<sub>2</sub>AgBiBr<sub>6</sub>: Fundamental Article Online Applications, and Perspectives, Advanced Functional Materials 31 (2021) 2105898. https://doi.org/10.1002/adfm.202105898.

[29] J. Deng, L. Yang, X. Zhang, K. Wei, G. Du, G. Zhu, J. Zhang, Synergistic effects of morphological control and enhanced charge collection enable efficient and stable lead-free CsBi<sub>3</sub>I<sub>10</sub> thin film solar cells, J. Mater. Chem. A 10 (2022) 9384–9392.
https://doi.org/10.1039/D1TA10808E.

[30] Y. Yang, C. Liu, M. Cai, Y. Liao, Y. Ding, S. Ma, X. Liu, M. Guli, S. Dai, M.K. Nazeeruddin, Dimension-Controlled Growth of Antimony-Based Perovskite-like Halides for Lead-Free and Semitransparent Photovoltaics, ACS Appl Mater Interfaces 12 (2020) 17062–17069. https://doi.org/10.1021/acsami.0c00681.

[31] W. Guo, Y. Zhu, M. Zhang, J. Du, Y. Cen, S. Liu, Y. He, H. Zhong, X. Wang, J. Shi, The Dion–Jacobson perovskite CsSbCl<sub>4</sub>: a promising Pb-free solar-cell absorber with optimal bandgap ~1.4 eV, strong optical absorption ~105 cm–1, and large power-conversion efficiency above 20%, J. Mater. Chem. A 9 (2021) 16436–16446. https://doi.org/10.1039/D1TA02969J.

[32] Z.-H. Lin, Y. Yang, J.M. Wu, Y. Liu, F. Zhang, Z.L. Wang, BaTiO<sub>3</sub> Nanotubes-Based Flexible and Transparent Nanogenerators, J. Phys. Chem. Lett. 3 (2012) 3599–3604. https://doi.org/10.1021/jz301805f. Journal of Materials Chemistry A Accepted Manuscript

[33] S. Xu, B.J. Hansen, Z.L. Wang, Piezoelectric-nanowire-enabled power source for driving wireless microelectronics, Nat Commun 1 (2010) 93. https://doi.org/10.1038/ncomms1098.

[34] F. Wu, W. Cai, Y.-W. Yeh, S. Xu, N. Yao, Energy scavenging based on a single-crystal PMN-PT nanobelt, Sci Rep 6 (2016) 22513. https://doi.org/10.1038/srep22513.

[35] J.H. Jung, M. Lee, J.-I. Hong, Y. Ding, C.-Y. Chen, L.-J. Chou, Z.L. Wang, Lead-Free NaNbO3 Nanowires for a High Output Piezoelectric Nanogenerator, ACS Nano 5 (2011) 10041–10046. https://doi.org/10.1021/nn2039033.

[36] K.Y. Lee, D. Kim, J. Lee, T.Y. Kim, M.K. Gupta, S. Kim, Unidirectional High-Power Generation via Stress-Induced Dipole Alignment from ZnSnO3 Nanocubes/Polymer Hybrid Piezoelectric Nanogenerator, Adv Funct Materials 24 (2014) 37–43. https://doi.org/10.1002/adfm.201301379. [37] Y. Hu, C. Xu, Y. Zhang, L. Lin, R.L. Snyder, Z.L. Wang, A Nanogenerator for EnterArticle Online Harvesting from a Rotating Tire and its Application as a Self-Powered Pressure/Speed Sensor, Advanced Materials 23 (2011) 4068–4071. https://doi.org/10.1002/adma.201102067.

[38] Y.-F. Lin, J. Song, Y. Ding, S.-Y. Lu, Z.L. Wang, Piezoelectric nanogenerator using CdS nanowires, Applied Physics Letters 92 (2008) 022105. https://doi.org/10.1063/1.2831901.

[39] J.M. Wu, C.C. Kao, Self-powered pendulum and micro-force active sensors based on a ZnS nanogenerator, RSC Adv. 4 (2014) 13882–13887. https://doi.org/10.1039/C3RA47435F.

[40] L. Lin, C.-H. Lai, Y. Hu, Y. Zhang, X. Wang, C. Xu, R.L. Snyder, L.-J. Chen, Z.L.
Wang, High output nanogenerator based on assembly of GaN nanowires, Nanotechnology 22 (2011) 475401. https://doi.org/10.1088/0957-4484/22/47/475401.

[41] S. Mohammadpourfazeli, S. Arash, A. Ansari, S. Yang, K. Mallick, R. Bagherzadeh, Future prospects and recent developments of polyvinylidene fluoride (PVDF) piezoelectric polymer; fabrication methods, structure, and electro-mechanical properties, RSC Adv. 13 (2023) 370–387. https://doi.org/10.1039/D2RA06774A.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

[42] X. Cai, T. Lei, D. Sun, L. Lin, A critical analysis of the  $\alpha$ ,  $\beta$  and  $\gamma$  phases in poly(vinylidene fluoride) using FTIR, RSC Advances 7 (2017) 15382–15389. https://doi.org/10.1039/c7ra01267e.

[43] N. Soin, P. Zhao, K. Prashanthi, J. Chen, P. Ding, E. Zhou, T. Shah, S.C. Ray, C. Tsonos, T. Thundat, E. Siores, J. Luo, High performance triboelectric nanogenerators based on phaseinversion piezoelectric membranes of poly(vinylidene fluoride)-zinc stannate (PVDF-ZnSnO<sub>3</sub>) and polyamide-6 (PA6), Nano Energy 30 (2016) 470–480. https://doi.org/10.1016/j.nanoen.2016.10.040.

[44] D. Mandal, K. Henkel, D. Schmeißer, Improved performance of a polymer nanogenerator based on silver nanoparticles doped electrospun P(VDF–HFP) nanofibers, Phys. Chem. Chem. Phys. 16 (2014) 10403–10407. https://doi.org/10.1039/C3CP55238A.

[45] A. Sultana, Md.M. Alam, P. Sadhukhan, U.K. Ghorai, S. Das, T.R. Middya, D. Mandal, Organo-lead halide perovskite regulated green light emitting poly(vinylidene fluoride) electrospun nanofiber mat and its potential utility for ambient mechanical energy harvesting application, Nano Energy 49 (2018) 380–392. https://doi.org/10.1016/j.nanoen.2018.04.057.

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

[46] N. Meng, X. Ren, G. Santagiuliana, L. Ventura, H. Zhang, J. Wu, H. Yan, M.J. Reer Article Online E. Bilotti, Ultrahigh  $\beta$ -phase content poly(vinylidene fluoride) with relaxor-like ferroelectricity for high energy density capacitors, Nat Commun 10 (2019) 4535. https://doi.org/10.1038/s41467-019-12391-3.

[47] J. Sun, Q. Hua, R. Zhou, D. Li, W. Guo, X. Li, G. Hu, C. Shan, Q. Meng, L. Dong, C.
 Pan, Z.L. Wang, Piezo-phototronic Effect Enhanced Efficient Flexible Perovskite Solar Cells,
 ACS Nano 13 (2019) 4507–4513. https://doi.org/10.1021/acsnano.9b00125.

[48] J. Nie, Y. Zhang, L. Li, J. Wang, Piezo-phototronic effect enhanced photodetectors based on MAPbI<sub>3</sub> perovskite, J. Mater. Chem. C 8 (2020) 2709–2718. https://doi.org/10.1039/C9TC05721H.

[49] A. Sahoo, T. Paul, N. Hiralal Makani, S. Maiti, R. Banerjee, High piezoresponse in lowdimensional inorganic halide perovskite for mechanical energy harvesting, Sustainable Energy & Fuels 6 (2022) 4484–4497. https://doi.org/10.1039/D2SE00786J.

[50] G. Kresse, D. Joubert, From ultrasoft pseudopotentials to the projector augmentedwave method, Phys. Rev. B 59 (1999) 1758–1775. https://doi.org/10.1103/PhysRevB.59.1758.

[51] P.E. Blöchl, Projector augmented-wave method, Phys. Rev. B 50 (1994) 17953–17979.
 https://doi.org/10.1103/PhysRevB.50.17953.

[52] J.P. Perdew, K. Burke, M. Ernzerhof, Generalized Gradient Approximation Made Simple, Phys. Rev. Lett. 77 (1996) 3865–3868. https://doi.org/10.1103/PhysRevLett.77.3865.

[53] B. Saparov, F. Hong, J.-P. Sun, H.-S. Duan, W. Meng, S. Cameron, I.G. Hill, Y. Yan,
 D.B. Mitzi, Thin-Film Preparation and Characterization of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>: A Lead-Free Layered
 Perovskite Semiconductor, Chem. Mater. 27 (2015) 5622–5632.
 https://doi.org/10.1021/acs.chemmater.5b01989.

[54] S. Grimme, J. Antony, S. Ehrlich, H. Krieg, A consistent and accurate ab initio parametrization of density functional dispersion correction (DFT-D) for the 94 elements H-Pu, The Journal of Chemical Physics 132 (2010) 154104. https://doi.org/10.1063/1.3382344.

[55] P.K. Santra, Degradation Studies of Cs<sub>3</sub>Sb<sub>2</sub>I<sub>9</sub>: A Lead-Free Perovskite, (2019).
 https://doi.org/10.1021/acsaem.9b01899.

[56] K. Momma, F. Izumi, VESTA 3 for three-dimensional visualization Of crystatrice Online volumetric and morphology data, J Appl Cryst 44 (2011) 1272–1276. https://doi.org/10.1107/S0021889811038970.

[57] V. Jella, S. Ippili, J.-H. Eom, J. Choi, S.-G. Yoon, Enhanced output performance of a flexible piezoelectric energy harvester based on stable MAPbI<sub>3</sub>-PVDF composite films, Nano Energy 53 (2018) 46–56. https://doi.org/10.1016/j.nanoen.2018.08.033.

[58] K. Maity, S. Garain, K. Henkel, D. Schmeißer, D. Mandal, Self-Powered Human-Health Monitoring through Aligned PVDF Nanofibers Interfaced Skin-Interactive Piezoelectric Sensor, ACS Appl. Polym. Mater. 2 (2020) 862–878. https://doi.org/10.1021/acsapm.9b00846.

[59] A. Sultana, P. Sadhukhan, Md.M. Alam, S. Das, T.R. Middya, D. Mandal, Organo-Lead Halide Perovskite Induced Electroactive β-Phase in Porous PVDF Films: An Excellent Material for Photoactive Piezoelectric Energy Harvester and Photodetector, ACS Appl. Mater. Interfaces 10 (2018) 4121–4130. https://doi.org/10.1021/acsami.7b17408.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

[60] P. Martins, A.C. Lopes, S. Lanceros-Mendez, Electroactive phases of poly(vinylidene fluoride): Determination, processing and applications, Progress in Polymer Science 39 (2014) 683–706. https://doi.org/10.1016/j.progpolymsci.2013.07.006.

[61] B. Saravanakumar, S. Soyoon, S.-J. Kim, Self-Powered pH Sensor Based on a Flexible Organic–Inorganic Hybrid Composite Nanogenerator, ACS Appl. Mater. Interfaces 6 (2014) 13716–13723. https://doi.org/10.1021/am5031648.

[62] A. Sahoo, T. Paul, A. Nath, S. Maiti, P. Kumar, P. Ghosh, R. Banerjee, Preferential perovskite surface-termination induced high piezoresponse in lead-free in situ fabricated Cs<sub>3</sub>Bi<sub>2</sub>Br<sub>9</sub> -PVDF nanocomposites promotes biomechanical energy harvesting, Nanoscale 15 (2023) 11603–11615. https://doi.org/10.1039/D3NR01517C.

[63] M. Singh, T. Paul, P. Pal, A. Sahoo, L.S. Tanwar, N.H. Makani, A. Ghosh, R. Banerjee,
High Ionic Conduction and Polarity-Induced Piezoresponse in Layered Bimetallic
Rb<sub>4</sub>Ag<sub>2</sub>BiBr<sub>9</sub> Single Crystals, J. Phys. Chem. C 126 (2022) 21810–21824.
https://doi.org/10.1021/acs.jpcc.2c06844.

Open Access Article. Published on 06 5 2025. Downloaded on 2025-05-12 8:45:42

[64] C.G. Koops, On the Dispersion of Resistivity and Dielectric Constant of StewAdicle Online Semiconductors at Audiofrequencies, Phys. Rev. 83 (1951) 121–124. https://doi.org/10.1103/PhysRev.83.121.

[65] N.P. Maria Joseph Raj, N.R. Alluri, G. Khandelwal, S.-J. Kim, Lead-free piezoelectric nanogenerator using lightweight composite films for harnessing biomechanical energy, Composites Part B: Engineering 161 (2019) 608–616.
 https://doi.org/10.1016/j.compositesb.2018.12.129.

[66] N.H. Langton, D. Matthews, The dielectric constant of zinc oxide over a range of frequencies, Br. J. Appl. Phys. 9 (1958) 453–456. https://doi.org/10.1088/0508-3443/9/11/308.

[67] T.-Y. Ke, H.-A. Chen, H.-S. Sheu, J.-W. Yeh, H.-N. Lin, C.-Y. Lee, H.-T. Chiu, Sodium Niobate Nanowire and Its Piezoelectricity, J. Phys. Chem. C 112 (2008) 8827–8831. https://doi.org/10.1021/jp711598j.

[68] Y. Rakita, O. Bar-Elli, E. Meirzadeh, H. Kaslasi, Y. Peleg, G. Hodes, I. Lubomirsky, D. Oron, D. Ehre, D. Cahen, Tetragonal CH<sub>3</sub>NH<sub>3</sub>PbI<sub>3</sub> is ferroelectric, Proceedings of the National Academy of Sciences 114 (2017) E5504–E5512. https://doi.org/10.1073/pnas.1702429114.

[69] T. Paul, A. Sahoo, S. Maiti, D.S. Gavali, R. Thapa, R. Banerjee, Halide Tunablility Leads to Enhanced Biomechanical Energy Harvesting in Lead-Free Cs<sub>2</sub>SnX<sub>6</sub>-PVDF Composites, ACS Appl Mater Interfaces 15 (2023) 34726–34741. https://doi.org/10.1021/acsami.3c04031.

[70] Y. Xue, T. Yang, Y. Zheng, E. Wang, H. Wang, L. Zhu, Z. Du, X. Hou, K.-C. Chou, The mechanism of a PVDF/CsPbBr3 perovskite composite fiber as a self-polarization piezoelectric nanogenerator with ultra-high output voltage, J. Mater. Chem. A 10 (2022) 21893–21904. https://doi.org/10.1039/D2TA03559F.

[71] A. Torabi, V.N. Staroverov, Band Gap Reduction in ZnO and ZnS by Creating Layered ZnO/ZnS Heterostructures, J Phys Chem Lett 6 (2015) 2075–2080.
 https://doi.org/10.1021/acs.jpclett.5b00687.

[72] L. Zhu, Y.-C. Wang, D. Li, L. Wang, Z.L. Wang, Enhanced Spin–Orbit Coupled Photoluminescence of Perovskite CsPbBr3 Quantum Dots by Piezo-Phototronic Effect, Nano Lett. 20 (2020) 8298–8304. https://doi.org/10.1021/acs.nanolett.0c03470.

Journal of Materials Chemistry A Accepted Manuscrip

[73] Q. Yang, X. Guo, W. Wang, Y. Zhang, S. Xu, D.H. Lien, Z.L. Wang, Enhanger Adjust Online Sensitivity of a Single ZnO Micro-/Nanowire Photodetector by Piezo-phototronic Effect, ACS Nano 4 (2010) 6285–6291. https://doi.org/10.1021/nn1022878.

[74] L. Zhu, Q. Lai, W. Zhai, B. Chen, Z.L. Wang, Piezo-phototronic effect enhanced polarization-sensitive photodetectors based on cation-mixed organic–inorganic perovskite nanowires, Materials Today 37 (2020) 56–63. https://doi.org/10.1016/j.mattod.2020.02.018.

 [75] L. Zhu, Z.L. Wang, Piezotronic effect on Rashba spin-orbit coupling based on MAPbI<sub>3</sub>/ZnO heterostructures, Applied Physics Letters 117 (2020).
 https://doi.org/10.1063/5.0011280.

[76] W. Wu, Z.L. Wang, Piezotronics and piezo-phototronics for adaptive electronics and optoelectronics, Nature Reviews Materials 1 (2016). https://doi.org/10.1038/natrevmats.2016.31. Page 41 of 41

## Data Availability Statement:

The data supporting this article have been included as part of the Supplementary Information.