

Showcasing research from Professor Seung Hwan Ko's laboratory, Department of Mechanical Engineering, Seoul National University, Seoul, Korea.

Tattoo electrodes in bioelectronics: a pathway to next-generation wearable systems

We present a comprehensive review of tattoo-based electronics, emphasizing recent progress in fabrication strategies, materials, and applications. Tattoo electronics enable ultrathin, skin-conformal platforms with unique advantages over conventional wearable electronics. We highlight key challenges, including durability, biodegradability, multifunctionality, and system-level integration, and discuss strategies to overcome them. This work aims to guide future research toward autonomous, versatile tattoo electronics for next-generation bioelectronic systems.

Image reproduced by permission of Jinwoo Lee from *Nanoscale Horiz.*, 2025, **10**, 1501.





rsc.li/nanoscale-horizons

Nanoscale Horizons

REVIEW

Check for updates

Cite this: *Nanoscale Horiz.*, 2025, **10**, 1501

Received 24th March 2025, Accepted 23rd May 2025 DOI: 10.1039/d5nh00175g

rsc.li/nanoscale-horizons

1. Introduction

Various types of soft and stretchable electrodes have been studied, attracting substantial attention in wearable bioelectronics. By utilizing flexible substrates and materials, researchers have progressed in acquiring biosignals from the human skin, heart, and other internal organs.¹ These biosignals are subsequently processed using computational technologies, including machine learning and deep learning technologies, to extract valuable information.^{2–4} However, electrodes based on flexible substrates still face some limitations in terms of conformality, user convenience, permeability, and biocompatibility, which hinder long-term use of the electrodes.^{5,6}

As a promising alternative, tattoo electrodes offer several universal advantages due to their ultrathin, substrate-free configurations.⁷ Their intimate conformality minimizes motion artifacts and enhances signal fidelity. In addition, their low mechanical modulus, comparable to that of biological tissues,

Tattoo electrodes in bioelectronics: a pathway to next-generation wearable systems

Jinwoo Lee^a and Seung Hwan Ko^(b)*^{abc}

Tattoo-based electronics have emerged as a transformative platform for next-generation wearable bioelectronics. Unlike conventional wearable devices, which rely on substrates, tattoo electrodes are directly formed or transferred onto the skin or internal organs, ensuring superior comfort, breathability, and long-term usability. This intimate interface minimizes motion-induced artifacts and enables reliable biosignal acquisition across diverse physiological and anatomical regions. However, the absence of a supporting substrate imposes unique challenges in fabrication and material design. The fabrication processes must be tailored to accommodate direct skin application, and the selection of functional materials is more constrained. Materials must not only be biocompatible and flexible but also capable of maintaining performance under the dynamic conditions of the human body. This review presents a comprehensive overview of tattoo electrode technology, beginning with fabrication strategies, including direct and indirect patterning methods. We then discuss a range of materials, such as metallic networks, carbon-based materials, polymers, and materials recently being studied. Finally, we explore the diverse applications of tattoo electrodes in strain and electrophysiological sensing, temperature and humidity detection, biochemical monitoring, and energy harvesting and storage. Through this review, we aim to highlight the potential and future directions of tattoo-based electronic systems.

improves mechanical compatibility with the human body (Table 1).⁸ Tattoo electrodes also reduce the risk of irritation and inflammation, particularly when implemented using breathable, porous materials that preserve natural skin functions such as sweating and thermoregulation. These features make them suitable for long-term, unobstructive wearable electronics.⁹ However, extreme manufacturing processes, such as high temperature, high pressure, or chemically reactive methods that can be harmful, are generally avoided, since the electrodes are intended for direct contact with the human body.

This review addresses challenges that tattoo electrodes encounter and investigates fabrication methods and materials. It also outlines future directions for tattoo electrodes to expand their applications into a wider range of fields (Fig. 1).

2. Fabrication

Tattoo electrodes differ from many conventional electrodes not merely due to their substrate-free nature, but because they are designed for direct, conformal contact with the human body. This imposes unique constraints on fabrication, as harsh processing conditions such as high temperature, vacuum environment, or chemical treatments cannot be applied directly to the body without risking adverse physiological effects.¹⁰ To address these challenges, a variety of manufacturing techniques have been developed to enable the efficient formation of skin-conformal



View Article Online

^a Wearable Soft Electronics Lab, Department of Mechanical Engineering, Seoul National University, 1, Gwanak-ro, Gwanak-gu, Seoul 08826, Republic of Korea. E-mail: maxko@snu.ac.kr

^b Institute of Engineering Research/Institute of Advanced Machinery and Design (SNU-IAMD), Seoul National University, 1, Gwanak-ro, Gwanak-gu, Seoul 08826, Republic of Korea

^c Interdisciplinary Program in Bioengineering, Seoul National University, 1 Gwanak-ro, Gwanak-gu, Seoul, Korea

Table 1 Elastic modulus ranges of biological tissues

Tissue name	Elastic modulus range	Ref.
Skin	0.4–2 MPa	109
Brain	0.1–10 kPa	110
Heart	10–600 kPa	111
Liver	0.5–5 kPa	112
Lung	5–15 kPa	113
Spinal cord	0.5–60 kPa	114
Peripheral nerve	100–500 kPa	115
Blood vessel	0.1–1 MPa	116
Skeletal muscle	10–45 kPa	117
Retina	0.01–1 kPa	118

electrodes under biocompatible conditions. This section discusses these fabrication methods in detail.

2.1. Direct patterning

Direct patterning refers to the process of creating electrode patterns directly on the human body without the use of an intermediate substrate. Due to the absence of a supporting substrate, there are stringent constraints on fabrication conditions, particularly regarding the tolerance to harsh processing environments. Additionally, inevitable movements such as breathing and pulse activity lead to distortion of the pattern, even when user motion is minimized. Nevertheless, direct patterning offers an intuitive and highly effective approach, particularly for rapid prototyping.

Among the methods for direct patterning, spray-coating stands out as a simple fabrication technique that requires few processing steps. Typically, the areas where electrode deposition is unwanted are covered using a physical mask; thus, it is crucial to ensure the mask and body make close contact to prevent any gaps. Any gaps can lead to unwanted electrode deposition, therefore contaminating unintended areas. For example, Kim et al. developed a substrate-less nanomesh receptor for strain sensing, employing silver-gold core-shell nanowires as the electrode material to ensure biocompatibility (Fig. 2a).¹¹ They created a lightweight and portable printing machine and used a stencil mask to cover the unwanted areas so that mass production could be available in a scalable and transportable manner. One of the key advantages of spraycoating is its ability to pattern electrodes over large areas, which makes it highly suitable for rapid prototyping.

Another approach for direct patterning involves printing or drawing directly onto the target area. In printing-based methods, the three-dimensional geometry of the application site should be scanned while restraining user movement, allowing for precise electrode deposition that conforms to the body's contours.^{12,13} Drawing methods, on the other hand, utilize a brush or a similar tool to create customized electrode patterns manually (Fig. 2b).¹⁴ During the subsequent transition from the liquid to the solid phase, either through solvent evaporation or temperature-induced phase change, the adhesion between the electrode and the body is enhanced. Although these methods



Jinwoo Lee

Jinwoo Lee is a PhD student in the Wearable Soft Electronics (WSE) Lab, led by Prof. Seung Hwan Ko's group at Seoul National University, South Korea. He received his BS from the Department of Mechanical Engineering of Seoul National University in 2023. His research focuses on soft wearable electronics.



Seung Hwan Ko

Seung Hwan Ko is a professor at the Wearable Soft Electronics (WSE) Lab, Mechanical Engineering Department at Seoul National University, South Korea. Before joining Seoul National University, he was a faculty member at KAIST, South Korea, since 2009. He received his PhD degree in mechanical engineering from UC Berkeley in 2006. He worked as a postdoctoral researcher at UC Berkeley until 2009. His current research interests include stretch-

able/flexible electronics, transparent electronics, soft robotics, wearable electronics, and laser-assisted nano/microfabrication. Nanoscale Horizon has been the major source of references for nanoscience in our lab. Our first publication on Biomimetic reconstruction of butterfly wing scale nanostructures for radiative cooling and structural coloration in Nanoscale Horizon was selected as a Nanoscale Horizons Outstanding Articles 2022 and Nanoscale Horizons Most Popular 2022 Articles. Nanoscale Horizon was one of the most effective outlets to disseminate our recent research results. I strongly recommend Nanoscale Horizon to our peer researchers. Congratulations on the 10th anniversary and best wishes to the Nanoscale Horizons.



may result in lower pattern resolution than mask-assisted techniques, they offer significant advantages: electrodes can uniformly cover the entire target surface without shaded regions caused by mask misalignment, and desired patterns can be produced more rapidly and flexibly.

Additionally, to acquire biosignals from the deeper regions of the body, conductive materials can be injected beneath the dermis with a tattoo needle.¹⁵ In contrast to the electrodes deposited on the surface, which collect signals only from the exterior of the skin or organs, this technique enables capturing signals from deeper layers, allowing for more accurate and varied data collection. While most tattoo electrodes have been primarily used for electrical signal detection and a limited range of chemical sensing, this method extends their functionality to diverse chemical sensing. Utilizing specific reactive materials can collect biological data, enabling the tracking of glucose levels, proteins, inflammation markers, and other biochemical signals.^{16,17} Nevertheless, user discomfort and challenges in complete tattoo removal still pose significant obstacles.

In conclusion, improving the resolution without harsh manufacturing procedures is required to enable fine electrode patterning for tattoo electrodes made using the direct patterning method to be used efficiently. Additionally, the electrodes must also have a high degree of adhesion to the body surface to ensure long-term stability and prevent delamination. When these issues are properly addressed, the direct patterning method is highly beneficial for mass manufacturing, rapid prototyping, and a simplified fabrication process, which makes it a good choice for wearable electronics.

2.2. Indirect patterning

Unlike direct patterning, indirect patterning involves patterning the electrode on an external substrate before transferring it onto the body. Water-soluble substrates, which act as a temporary medium for depositing conductive materials, are the mainstay of such production procedures. The utilization of harsh fabrication techniques like laser processing, UV curing, and chemical reactions is made possible by the greatly decreased fabrication limitations resulting from the patterning process occurring on a substrate rather than directly on the human body.¹⁸ Furthermore, the accurate application of inkjet printing, which necessitates a steady and motionless environment, is made possible by the lack of movement during

Review



Fig. 2 Diverse types of fabrication methods to generate tattoo electrodes. (a) (i) Photographs of the portable printing machine. (ii) Schematic illustration of a nanomesh receptor mimicking a cutaneous receptor, with wireless measurement of resistance changes. Adapted with permission from ref. 11 Copyright 2022, Springer Nature. (b) (i) Photographs of the *in situ* biogel applied and squeezed on skin. (ii) Photographs of the biogel undergoing rapid *in situ* gelation. (iii) Photographs demonstrating the biogel's skin adhesion and mechanical toughness. Adapted with permission from ref. 14 Copyright 2025, Springer Nature. (c) (i) Schematic illustration of nanomesh conductors and their deposition onto skin, along with an optical image on skin (scale bar: 1 mm) and an SEM image on a skin replica (scale bar: 5 μm). (ii) Photographs of nanomesh conductors attached to the finger when the hand is opened and closed. Adapted with permission from ref. 22 Copyright 2017, Springer Nature. (d) (i) Schematic illustration of reversible selective laser-induced redox enabling monolithic patterning of CuNW, Cu₂ONW, and CuONW networks. (ii) Optical images of CuNW, Cu₂ONW, and CuONW networks (iii) Optical images showing laser-induced drawing, conversion, and erasing. Adapted with permission from ref. 26 Copyright 2022, Springer Nature.

processing.¹² This method is especially useful for rapid production while preserving the inherent properties of both the substrate and the electrode.

One approach for indirect patterning employs water-soluble substrates.¹⁹ In this method, the conductive material only

remains on the body after the substrate dissolves in water. It is important to set the temporary substrate to an appropriate thickness. If the substrate is too thick, forming precise electrode patterns on intricate surfaces like fingerprints or extremely curved and wrinkled areas may become difficult since conformal contact between the skin and substrates becomes challenging. On the other hand, an excessively thin substrate makes it difficult to work with; for best results, a balance in thickness is needed. Furthermore, the substrate material should also be readily detachable and biocompatible to guarantee safe application on the body. Among many choices, polyvinyl alcohol (PVA) is frequently utilized as a substrate material since it is highly water-soluble and biocompatible, making removal simple without causing any harm to humans.^{20,21}

For example, Miyamoto *et al.* employed a PVA electrospun membrane as a substrate that dissolves in water (Fig. 2c).²² After applying a gold nanomesh solution, the membrane is placed on the skin. Then, the membrane is dissolved in water, and only the gold nanomesh is left on the skin, providing remarkable conformality even in highly dynamic regions like finger joints, where adhesion is difficult. Additionally, the gold nanomesh electrode demonstrated high stretchability due to its ability to repeatedly and reversibly split and repair, while its high permeability enabled seamless exchange of sweat and air through the electrode.

Moreover, indirect patterning reduces process constraints, allowing for the adoption of a wide range of fabrication techniques. Specifically, laser direct writing can achieve high resolution and induce photothermal chemical reactions with patterning materials.²³ For instance, when polyimide undergoes a photothermal chemical reaction, it transforms into graphene, which can serve as electrodes due to its high conductivity.^{24,25} Similarly, copper can be reduced and subsequently oxidized *via* wet oxidation to form Cu₂O, a semiconducting material suitable for optoelectronic applications (Fig. 2d).²⁶ Additionally, photolithography can be employed, in which photoresist layers are patterned through light exposure and subsequently developed using chemicals to achieve fine and precise structures.^{27,28}

Thus, in indirect patterning, patterns can be easily transferred by dissolving water-soluble substrates. Alternatively, laser direct patterning and photolithography can also be used to improve resolution, enabling the formation of accurate and fine patterns. These methods provide distinct approaches for achieving precise patterning in different contexts.

3. Materials

Tattoo electrodes rely significantly on the selection of electrode materials, which must satisfy several requirements: mechanical compliance to match soft biological tissues, high electrical conductivity for efficient signal transmission, biocompatibility to ensure safety during prolonged contact with the body, and, in many cases, permeability to preserve natural skin functions.^{29,30} Traditionally, metallic, carbon-based, and polymeric materials have been widely used as tattoo electrode materials. Recent developments have additionally brought liquid metals and MXene family as alternative materials with improved characteristics for specific applications. Table 2 summarizes the typical materials, electrode structure, electrical characteristics, and electrical failure

strain of various tattoo electrodes. The components and construction of tattoo electrodes will be discussed in this part, highlighting both conventional and newly developed materials under ongoing research.

3.1. Metallic materials

Metallic materials have been widely used in bioelectronics due to their high electrical conductivity and ease of patterning. Ensuring conformal contact is essential for tattoo electrodes to accurately collect signals from the highly textured and nonuniform surfaces of the human body. However, bulk metals are inherently brittle and have low stretchability, making it difficult for them to conform to the body. Therefore, structural modifications and solution-processed metals have been employed to overcome these limitations.

Structurally engineered electrode patterns exhibit greater stretchability while maintaining significant conductivity under strain.³¹ Additionally, when metal films are patterned into serpentine or other porous structures by laser processing or etching, permeability is also enhanced, making them highly beneficial for strain sensing applications.^{32,33} Furthermore, research has demonstrated that depositing gold onto shapememory polymers can further improve stretchability and mechanical resilience.³⁴

On the other hand, metal nanowires in solution form have been extensively explored for tattoo electrode applications. Depending on their structural arrangement, nanowires can form either a dense nanomesh structure or a nano-percolation network. In the nanomesh structure, individual nanowires rearrange under strain while maintaining electrical connection without fracture.²² In contrast, nanowires create a porous structure that can be integrated with a polymer matrix when a percolation network is formed. By embedding metal nanowires into stretchable polymer matrices, a conductive composite can be formed that intrinsically combines mechanical deformability with electrical conductivity (Fig. 3a).³⁵ This approach eliminates the need for post-deposition processing and enables conformal contact with dynamic surfaces. The polymer matrix provides elasticity and structural support, while the embedded nanowires establish percolated conductive pathways that remain stable under strain, offering excellent performance for stretchable tattoo electronics.³⁶ Furthermore, chemical stability and biocompatibility are also critical factors for direct contact with the body. Therefore, gold nanowires, copper nanowires, and silver-gold core-shell nanowires are commonly used in tattoo electrodes.37-39

On the other hand, liquid metal-based tattoo electrodes, such as eutectic gallium–indium (EGaIn), have recently gained great attention. EGaIn is the most well-known liquid metal, capable of being directly patterned in a liquid state, as it remains in a liquid phase until exposed to external stimuli.⁴⁰ However, EGaIn particles, mechanically fractured from bulk EGaIn, are typically employed instead since bulk EGaIn lacks intrinsic stretchability.⁴¹ When EGaIn particles are deposited into a desired pattern, oxide layers rapidly form on their surface. These layers can be mechanically fractured through

Table 2	Summary of materials,	electrode structure,	electrical	characteristics and	electrical	failure strain	of tattoo	electrodes
---------	-----------------------	----------------------	------------	---------------------	------------	----------------	-----------	------------

Material class	Material name	Electrode structure	Electrical characteristics	Electrical failure strain	Ref.
Metallic	Ag-Au	Nanomesh	$\sim 1.4 \ \Omega \ sq^{-1}$	>30%	11
	Au		$5.3 imes10^{-7}~\Omega~{ m m}$	$\sim 50\%$	22
		Serpentine	—	$\sim 100\%$	91
		Wrinkled thin film	66–88 Ω sq ⁻¹	> 200%	34
	Cu	Serpentine	$R/R_0 < 1.01$	>300%	90
	Ag	Nanomesh	7.62 Ω sq ⁻¹	> 80%	38
	Au/Ti	Hollow-carved structure	4–12 kΩ cm	> 100%	39
	Ni/EGaIn	Intrinsically stretchable	Na⁺ sensitivity ∼56.8 mV per decade	10-30%	40
Carbon-based	Graphene	Serpentine	Skin-electrode impedance $\sim 200-300 \text{ k}\Omega$ at 10 kHz	10-30%	50
			$\sim 2 \text{ k}\Omega \text{ sq}^{-1}$	> 25%	51
		Multi-stacking	\sim 0.55 \pm 0.25 k Ω sq $^{-1}$	> 30%	52
		C	Skin-electrode impedance $\sim 1-10 \text{ k}\Omega$ at 10 kHz	10-30%	53
Polymeric	ETE-COONa/PVA	Intrinsically stretchable	$\sim 0.25 \text{ S cm}^{-1}$	>30%	13
	Polyacrylamide/ polypyrrole PEDOT:PSS	·	$R/R_0 < 1.06$	>200%	66
			Skin-electrode impedance −72 kΩ at 50 Hz	10-30%	85
			100–200 $\Omega \mathrm{sq}^{-1}$	10-30%	94
	PVA/PEDOT:PSS		$0.6-1.8 \text{ S} \text{ m}^{-1}$	>349%	57
			2.3 S m^{-1}	> 100%	59
	WPU/PEDOT:PSS		11 S cm^{-1}	>400%	61
	Poly(aniline)	Stencil pattern	—	10-30%	97
Hybrid	EGaIn/CNT	Intrinsically stretchable	$< 100 \Omega \text{ sq}^{-1}$	$>\!40\%$	45
	CNT/PDMS		$\sim 10^{-2} \text{ S m}^{-1}$	$\sim 200\%$	55
	Ag/TPU		38% increase in sheet resistance over 4 days	$\sim 100\%$	92
Others	Mo_2C	Ultrathin film	60–150 Ω sq ⁻¹	10-30%	89
	$Ti_3 \tilde{C}_2 T_x / EGaIn$	Intrinsically stretchable	$2.2 \ \Omega \ \mathrm{sq}^{-1}$	>50%	78

mechanical force or laser sintering, allowing the particles to connect and restore electrical conductivity.⁴² However, once these EGaIn particles reconnect, they behave similarly to bulk EGaIn, which easily fractures under strain. To address this limitation, elastomeric materials or metal flakes are often incorporated to enhance stretchability.^{43,44} Additionally, Lee *et al.* demonstrated the enhanced mechanical robustness of liquid metal-based tattoo electrodes by attaching Pt-decorated carbon nanotubes (CNTs) onto EGaIn, further expanding the potential of metallic tattoo electrode materials (Fig. 3b).⁴⁵

As a result, metallic electrodes can be effectively utilized by engineering their structures or incorporating liquid-state metals, enabling them to be applied even on highly dynamic areas subjected to frequent movements.

3.2. Carbon-based materials

Carbon-based materials have unique bonding structures that enable their high electrical conductivity. In well-packed carbon materials, such as carbon nanotubes (CNTs) and graphene, the sp² hybridized structure creates delocalized π -electron networks, facilitating electron transport.^{46,47} The carbon materials exhibit metallic behavior with an electron bandgap close to 0 eV, and their conductivity is further enhanced.⁴⁸ Additionally, carbon-based tattoo electrodes have been developed to employ carbon black ink with conductive polymers, broadening the variety of carbon-based materials for tattoo applications.⁴⁹ Overall, their high conductivity, mechanical flexibility, and chemical stability make them ideal for skin-conformal and stretchable electronic applications. For these reasons, carbon-based materials, such as graphene and carbon nanotubes (CNTs), are among the most commonly utilized materials for tattoo electrodes.

Graphene, a one-atom-thick 2D material, comprises carbon atoms arranged in a honeycomb lattice. Graphene has been widely used in flexible displays and wearable sensors owing to its high flexibility and mechanical strength. Although the material is not inherently stretchable and is prone to break under tensile strain, strategies have been developed to overcome this limitation.⁵⁰ Kabiri Ameri et al. developed filamentary serpentine graphene electrodes, improving the stretchability to over 40%, whereas straight-line graphene electrodes rupture at strains below 20% (Fig. 3c).⁵¹ Another strategy developed to enhance the resilience of graphene-based tattoo electrodes is multilayer stacking, in which graphene is stacked into multilayers to maintain electrical conductivity and function as a backup when a layer breaks under strain.52 Multilayer stacking enables greater stretchability and durability, making it suitable for generating stretchable and transparent electrodes for wearable applications.

Review



Fig. 3 Metallic and carbon-based materials that can be utilized for the formation of tattoo electrodes. (a) (i) Schematic illustrations depicting the manufacturing process of a nanowire-embedded polymer. (ii) Photograph of the nanowire-embedded polymer for EMG sensing. Adapted with permission from ref. 35 Copyright 2025, Springer Nature. (b) (i) Schematic illustration depicting the assembly of a Pt-decorated CNT on liquid metal particles (CMPs) on the skin. (ii) Photographs showing diverse applications of CMPs, including ECG sensing, electrical stimulation, biosensing, and photothermal heating. (iii) Schematic illustration of a CMP-based electrical stimulator applied to a rat. Adapted with permission from ref. 45 Copyright 2022, Wiley-VCH. (c) (i) Photographs of graphene electronic tattoo (GET) on the skin under 25% compression and stretching. (ii) Demonstration of the GET used for skin hydration and temperature sensing. Adapted with permission from ref. 51 Copyright 2017, American Chemical Society. (d) (i) Photographs of the CNT/PDMS composite sensor for EEG monitoring from top and bottom views. (ii) Sensor attached behind the ear. (iii) FFT spectrogram of EEG signals before and after eye closure. Adapted with permission from ref. 54 Copyright 2023, Springer Nature.

CNTs, on the other hand, are composed of cylindrical carbon structures and exhibit great flexibility. However, the material also lacks stretchability, limiting its uses to low-strain regions.⁵³ This limitation can be improved by blending the material with an elastomer, such as polydimethylsiloxane (PDMS), to form CNT-elastomer composites (Fig. 3d).⁵⁴ These composites can withstand strains exceeding 100%, enabling their use in high-strain sensor applications. Furthermore, a

high gauge factor is another characteristic that makes CNT-based electrodes ideal for ultra-sensitive strain sensors in tattoo electronics. 55

Given their high electrical conductivity, biocompatibility, and outstanding mechanical strength, carbon-based materials remain one of the most promising candidates for tattoo electrodes. They also have immense potential for wearable bioelectronics and next-generation flexible devices.

3.3. Polymeric materials

Review

The most prevalent polymer-based material for tattoo electrodes is poly(3,4-ethylenedioxythiophene):poly(styrene sulfonate) (PEDOT:PSS). This material exhibits high electrical conductivity, excellent biocompatibility, and strong processability. However, pristine PEDOT:PSS exhibits very low intrinsic stretchability (2% before mechanical failure), which makes it prone to delamination under body movements.⁵⁶ Moreover, in humid environments, the hydrophilic nature of the PSS component leads to excessive swelling and redispersion of the film, limiting its applicability in wearable bioelectronics without further engineering.

To address these challenges, network engineering strategies have been employed, incorporating PEDOT:PSS into polymer matrices such as poly(vinyl alcohol) (PVA), poly(acrylic acid) (PAA), and gelatin.57-59 These networks improve mechanical stretchability and suppress water-induced degradation (Fig. 4a).⁶⁰ Alternatively, phase separation approaches have been explored. For instance, the addition of dimethyl sulfoxide induces the formation of reconfigured PEDOT:PSS.⁶¹ Other methods use additives like polyurethane to decouple mechanical and electrical phases, creating distinct PEDOT:PSS conductive pathways within mechanically robust matrices.^{60,62} Recently, Won et al. introduced a laser treatment technique that spatially separates PEDOT and PSS phases (Fig. 4b).⁶³ Upon hydration, the PEDOT-rich domains form continuous electrical pathways, while the PSS-rich domains act as ionic conductors, collectively suppressing water-induced degradation. Moreover, the use of laser processing enables high-resolution, selective patterning on targeted regions.

In addition, conductive pathways can be embedded within hydrogel matrices to fabricate tattoo-like sensors and interfaces.^{64,65} For example, Zhuo and colleagues developed a reusable hydrogel-based tattoo sensor, in which polypyrrole was incorporated to enable monitoring of skin temperature and hydration levels (Fig. 4c).⁶⁶ Owing to their extremely low mechanical modulus, hydrogels offer exceptional mechanical conformity with biological tissue, making them ideal for bioelectronic interfaces and wearable sensors. Unlike conventional polymers, hydrogels exhibit high water retention within their internal matrix, which prevents dehydration-related failures and ensures stable performance in humid or sweaty environments that often degrade other tattoo electrode materials. Their inherently porous structure also enables the incorporation of ionic components, allowing internal ions to migrate freely under mechanical strain and maintain stable current flow even during deformation.⁶⁷ Additionally, their high viscosity allows hydrogels to be processed into printable inks, thereby facilitating patterning via 3D printing and other additive manufacturing techniques.68,69

Overall, polymeric materials strike a crucial balance between flexibility, biocompatibility, and conductivity in tattoo electrodes. Hydrogel-based systems, in particular, offer superior ionic conductivity and mechanical softness, enabling advanced functionalities for sensing and human–machine interfaces in nextgeneration wearable biomedical devices.

3.4. Other materials

The previously discussed materials – metallic, carbon-based, and polymeric – have long been employed as electrode materials. To enhance their suitability for tattoo electrodes, researchers have explored combining them with elastomers or forming composites that leverage the advantages of each material.^{43,55,70,71}

Lately, the MXene family has been receiving significant interest as possibly useful materials for tattoo electrodes. MXenes are a family of 2D nanomaterials with remarkable electrical properties, high ionic conductivity, and great flexibility that make them ideal materials for skin-conformal bioelectronics.⁷² MXenes can be derived from MAX phases through chemical or mechanical exfoliation.⁷³ Early production techniques, however, suffered from scalability, limiting their general deployment. However, large-scale synthesis techniques have made it feasible to generate consistent, high-quality MXenes, and hence, their use has expanded greatly in various research fields, including energy storage and wearable bio-electronics.⁷⁴

MXene-based electrodes' capacity to be processed into ultrathin films, allowing their use in biosignal sensing and energy storage, is one of their main advantages.^{75,76} Their unique combination of conductivity, flexibility, large surface area and biocompatibility further expands the potential of tattoo electrodes in wearable and implantable bioelectronics, thus opening the path for next-generation soft electronic systems.⁷⁷ However, MXenes suffer from their intrinsic structural brittleness under tension. To overcome this, Wang et al. developed a composite by incorporating a liquid metal to enhance its mechanical resilience and stretchability (Fig. 4d).⁷⁸ Under strain, the oxide layer of the liquid metal nanocapsules mechanically breaks, allowing the liquid metal within to flow and re-establish electrical pathways, thereby effectively solving the brittleness issue. MXene films produced in this work demonstrated outstanding resistance to mechanical stress and water exposure while allowing high-fidelity biosignal acquisition.

In addition to MXenes, transition metal dichalcogenides (TMDs) such as MoS₂ and WS₂ are also gaining interest in the context of tattoo electrodes.^{79,80} TMDs are two-dimensional semiconductor materials with layered structures similar to graphene.⁸¹ They exhibit several attractive properties, including strong exciton binding energies, fast charge transport, and intense light–matter interactions.⁸² Furthermore, TMDs allow for tunable electronic and optical properties through phase engineering, doping, or strain modulation. These characteristics make TMDs promising candidates not only for conformable sensors, but also for next-generation optoelectronic devices, transistors, and catalysts.⁸³ Their atomic thinness enables excellent skin conformality, while their semiconducting nature provides diverse functionalities in bio-integrated systems.

In summary, MXenes and TMDs represent promising emerging materials for tattoo electrodes, offering exceptional electrical, mechanical, and optical properties that enable multifunctionality in wearable bioelectronics. Their unique characteristics,



Fig. 4 Polymeric and alternative materials that can be utilized to form tattoo electrodes. (a) (i) Schematic illustrations of composites integrating PEDOT:PSS and hydrophilic polyurethane. (ii) Photographs of the bioelectronic interface on a fingertip demonstrating its stretchability. (iii) Photograph of the bioelectronic interface on a rat sciatic nerve. Adapted with permission from ref. 60 Copyright 2023, Springer Nature. (b) (i) PEDOT:PSS pattern fabricated *via* laser processing, demonstrating strong adhesion to the substrate under wet conditions, and SEM image of the dried PEDOT:PSS hydrogel cross-section on a PET substrate. (ii) Comparison of wet adhesion to the substrate under shear force. Top: Only EG-treated. Bottom: Laser-treated. Adapted with permission from ref. 63 Copyright 2024, Springer Nature. (c) (i) Schematic illustrations of fabrication steps for a hydrogel-based electronic tattoo sensor. (ii) Photographs of different hydrogel electronic tattoo sensors. HSHS, HRTD, and HEPS represent hydrogel-based hydration sensors, hydrogel-based resistance temperature sensors, and hydrogel-based electrophysiological sensors, respectively (scale bar: 1 cm). (iii) SEM image showing its microstructural morphology. Adapted with permission from ref. 66 Copyright 2024, Springer Nature. (d) (i) Schematic illustrations of a sprayable liquid metal–MXene composite electronic tattoo sensor applied onto the skin. (ii) Top: Photographs of the nanocomposite along different strains (0–50%) (scale bar: 200 μm). Bottom: Schematic illustration of the self-healing mechanism of the cracked nanocomposite. (iii) Demonstrations of LEDS in a tattoo circuit maintaining stable operation on the skin during compression, stretching, and twisting. Adapted with permission from ref. 78 Copyright 2024, Elsevier.

such as skin conformability, conductivity, and tunable behavior, open new possibilities for next-generation bio-integrated systems beyond conventional materials.

4. Applications

Tattoo electrodes, leveraging their skin-conformal structure and material versatility, have found wide-ranging applications in wearable bioelectronics. Their intimate contact with the body enables highly accurate strain and electrophysiological signal acquisition, supporting diverse use cases such as motion tracking, facial expression monitoring, and real-time cardiac or neural assessments. In addition, tattoo electrodes are being employed for temperature and humidity sensing through responsive materials, providing valuable data for both virtual reality systems and clinical diagnostics. Their adaptability also extends to chemical and pH sensing, where electrochemical mechanisms enable non-invasive detection of biochemical markers. Beyond sensing, tattoo electrodes are emerging energy harvesting and storage platforms, particularly through sweatpowered biofuel cells, capacitive systems, and wireless power transfer, paving the way for self-sustaining, wire-free wearable systems. This section explores the expanding role of tattoo electrodes in health monitoring, human-machine interaction (HMI), and the development of fully integrated, next-generation wearable electronics.

4.1. Strain sensors

The exceptional performance of tattoo electrodes in strain sensing is one of their significant advantages in biosignal monitoring. Conventional strain sensors fabricated on flexible substrates often struggle to maintain intimate contact with the body, especially over highly contoured, wrinkled, or dynamic surfaces such as joints or facial regions.⁸⁴ This imperfect interface can compromise signal fidelity and accuracy. In contrast, tattoo electrodes are directly deposited onto the skin or tissue surface, achieving gap-free, conformal adhesion without the need for adhesives or an external support. This ultra-thin, substrate-free architecture provides a skin-like interface that ensures precise transduction of mechanical deformations into electrical signals, thereby significantly enhancing the accuracy and reliability of strain sensing.⁸⁵

Tattoo electrodes are frequently employed to monitor various forms of body movement, including finger motion, facial expressions, and micro-strains from skin deformation (Fig. 5a).^{11,86,87} Beyond cutaneous applications, they can also be integrated with internal organs such as the heart and lungs, owing to their soft mechanical properties.¹³ This mechanical compatibility minimizes inflammation and delamination, enabling stable long-term *in vivo* operation without triggering adverse immune responses.

The strain signals collected by tattoo sensors are typically processed using machine learning algorithms, allowing for high-level interpretation and classification.^{3,4} Applications such as hand gesture recognition, facial expression detection,

and non-verbal communication interfaces have been successfully demonstrated, paving the way for advanced HMI and neuroprosthetic control systems.

In summary, the ultra-conformal, substrate-free design of tattoo electrodes offers a distinct advantage in strain sensing by enabling seamless integration with both external skin and internal organs. This intimate interface ensures high-fidelity signal acquisition even on complex, dynamic surfaces, while minimizing mechanical mismatch and immune responses. Coupled with machine learning-based signal processing, tattoo strain sensors have demonstrated strong potential in diverse applications.

4.2. Electrophysiological sensors

Electrophysiological signals, including electromyography (EMG), electrocardiography (ECG), electroencephalography (EEG), and electrooculography (EOG), are essential for monitoring neuromuscular activities, cardiac rhythms, brain function, and ocular motion.⁸⁸ However, traditional electrodes, often composed of rigid metal components or gel-based adhesives, face inherent limitations in long-term and dynamic monitoring. One major issue is their susceptibility to motion artifacts, which arises from poor mechanical conformity and unstable contact with the skin during body movement. Additionally, the imperfect interface between the electrode and skin often leads to high interfacial impedance, degrading the quality and fidelity of acquired signals.

Tattoo electrodes address these limitations by forming a conformal, ultra-thin interface that adheres intimately to the skin's microtopography.⁸⁹ Unlike conventional electrodes, they do not require bulky adhesives or conductive gels, minimizing the risk of delamination or contact variation. This configuration effectively reduces motion-induced signal distortion and ensures low-impedance coupling, even under continuous or dynamic conditions. As a result, tattoo electrodes enable reliable acquisition of high-fidelity electrophysiological signals suitable for both clinical and wearable applications. A representative example is polysomnography, where simultaneous monitoring of multiple physiological parameters during sleep is critical (Fig. 5b).⁹⁰ Conventional setups often involve cumbersome electrodes and wiring that can interfere with natural sleep. Tattoo electrodes offer a lightweight and unobtrusive solution, enabling continuous, high-resolution sleep monitoring without compromising user comfort or signal integrity.

Thanks to their skin-like mechanical properties and stable electrical interface, tattoo electrodes are particularly well-suited for electrophysiological sensing in biomedical applications. Their ability to acquire high-fidelity EMG, ECG, EEG, and EOG signals over extended periods enables continuous monitoring of muscular, cardiac, neurological, and ocular functions in a non-invasive and patient-friendly manner. This makes them highly attractive for use in neurological disorder diagnosis, cardiac health tracking, sleep studies, and assistive technologies. By enabling accurate and long-term bioelectrical monitoring, tattoo sensors hold great potential to advance personalized medicine, adaptive neuroprosthetics, and realtime health feedback systems.



Fig. 5 Various types of applications achieved with tattoo-based electronic systems. (a) Applications implemented by tattoo strain sensors for (i) finger motion, (ii) facial expressions, and (iii) micro-strains from skin deformation. Adapted with permission from ref. 11, 86 and 87 Copyright 2022, Springer Nature, 2024, The American Association for the Advancement of Science, and 2022, Springer Nature. (b) Implementation of polysomnographic techniques using tattoo electrophysiological sensors. Adapted with permission from ref. 90 Copyright 2023, The American Association for the Advancement of Science. (c) Optical and infrared images of temperature sensors integrated into the skin. Adapted with permission from ref. 91 Copyright 2013, Springer Nature. (d) (i) Schematic illustration of a tattoo-based humidity sensing system and (ii) current response measured before, during, and after exercise. Adapted with permission from ref. 96 Copyright 2024, Springer Nature. (e) Schematic illustrations of the manufacturing process of a pH-responsive tattoo sensor. Adapted with permission from ref. 98 Copyright 2021, Wiley-VCH. (f) Sensing mechanisms of tattoo-based electrodes for detecting (i) glucose and (ii) alcohol. Adapted with permission from ref. 16 and 17 Copyright 2014, American Chemical Society and 2016, American Chemical Society. (g) Schematic illustrations of thermoelectric generation using tattoo-like wearable devices. Adapted with permission from ref. 104 Copyright 2024, Wiley-VCH. (h) Photographs of the tattoo electrode system for energy harvesting and storage. Adapted with permission from ref. 106 Copyright 2017, Wiley-VCH.

4.3. Temperature and humidity sensors

In addition to mechanical and electrophysiological sensing, tattoo electrodes can be engineered to detect temperature and humidity by incorporating materials that exhibit temperaturedependent or hygroscopic electrical properties. Their ultra-thin, conformal form allows for precise and continuous monitoring of skin temperature and moisture levels with minimal interference to the user. This is particularly valuable in scenarios where subtle thermal changes reflect underlying physiological conditions, such as inflammation, infection, fever onset, or wound healing dynamics.

One notable work by Webb et al. demonstrated ultrathin, conformal temperature sensors capable of continuous thermal mapping of the skin with clinical-grade accuracy (Fig. 5c).⁹¹ Such systems can act as early indicators of localized physiological abnormalities, enabling timely intervention in medical settings. Furthermore, skin-integrated tattoo thermosensors can be seamlessly combined with other tattoo-based sensors to create multimodal diagnostic platforms that monitor biochemical and biophysical parameters in real-time. Beyond healthcare, temperature-sensitive tattoo electrodes also show strong potential in virtual and augmented reality environments, where realistic thermal feedback can enhance immersion and interaction.92-94 By providing location-specific temperature changes in sync with digital stimuli, tattoo sensors enable more lifelike tactile experiences, thereby expanding the possibilities for next-generation human-machine interfaces. In addition, humidity-sensing tattoo electrodes, often based on materials like graphene oxide or MXene-based composites, can track perspiration levels to infer the hydration status, stress response, or metabolic activity (Fig. 5d).^{95,96} When integrated into wearable systems, they support continuous sweat analysis, athletic performance monitoring, and thermal regulation studies.

Overall, tattoo-based temperature and humidity sensors offer a compelling combination of wearability, sensitivity, and application diversity, making them valuable tools in clinical diagnostics and interactive technology platforms.

4.4. Chemical and pH sensors

Tattoo electrodes can be functionalized to detect chemical biomarkers and pH levels in biofluids such as sweat, blood, and urine, providing a powerful platform for non-invasive, continuous health monitoring. These biofluids contain physiologically relevant analytes, including electrolytes, metabolites, and protons (pH), which can indicate the hydration status, metabolic conditions, and localized inflammation.

One effective approach for tattoo-based chemical sensing involves the use of electrochemical mechanisms, in which chemical reactions at the sensor surface produce measurable electrical signals.⁹⁷ A representative example is the temporary tattoo pH sensor developed using a pH-responsive hydrogel (Fig. 5e).⁹⁸ In this system, the hydrogel swells or contracts in response to local pH, altering the electrical double layer at the electrode interface. This change is transduced into an electrochemical signal, enabling real-time tracking of skin pH. Such devices demonstrate excellent mechanical conformity, reversibility, and stability, all while maintaining user comfort.

Beyond pH, tattoo-based chemical sensors have been developed to monitor glucose, lactate, sodium, potassium, and cortisol levels using enzyme-functionalized electrodes or ionselective membranes (Fig. 5f).^{16,17,99,100} These sensors typically utilize potentiometric or amperometric mechanisms to convert ion concentration or redox reactions into voltage or current signals.

Unlike rigid chemical sensors that may require bulky instrumentation or invasive sampling, tattoo sensors are ultra-thin, breathable, and skin-conformal, allowing for unobtrusive operation over extended periods. These features make tattoo chemical and pH sensors ideal for early disease detection, sports performance monitoring, and personalized health diagnostics, especially in decentralized healthcare settings.¹⁰¹ They also show strong potential for emerging applications such as pet health monitoring and ingestible or edible sensors with guaranteed biodegradability.^{102,103}

4.5. Energy harvesting and storage

Tattoo electrodes are not only capable of transmitting bioelectrical and externally applied signals but also hold great potential for on-skin energy harvesting and storage. Their ultra-thin, breathable, and highly conformal architecture enables efficient energy interaction with the skin and surrounding environment, opening up new opportunities for developing self-powered wearable systems.

Recent studies have demonstrated the feasibility of such systems using tattoo-based platforms. For instance, a thermoelectric tattoo system has been developed that harvests energy from the temperature gradient between the human body and ambient air, enabling continuous temperature mapping without an external power source (Fig. 5g).¹⁰⁴ In another example, a fully untethered and battery-free electronic tattoo was realized using near-field communication-based wireless energy harvesting to support real-time biosignal monitoring.¹⁰⁵ These examples highlight how tattoo electrodes can serve not only as sensing interfaces but also as integral components of autonomous energy systems, advancing the development of next-generation self-powered bioelectronics.

Moreover, tattoo electrodes can also function as energy storage components, particularly in the form of capacitors. A typical configuration consists of two conductive layers separated by a dielectric material, enabling the system to store and release electrical energy (Fig. 5h).¹⁰⁶ In capacitive coupling systems, the stratum corneum can act as the dielectric medium, allowing tattoo electrodes to relay signals or charge through the skin without direct electrical contact.¹⁰⁷ Furthermore, triboelectric nanogenerators have been demonstrated by sandwiching elastic dielectric layers, such as electrospun fibers, between conductive tattoo electrodes.¹⁰⁸ This configuration enables energy harvesting through motion-induced contact

Nanoscale Horizons

and separation, creating self-powered systems suitable for dynamic body movements.

Collectively, these developments in energy harvesting and storage enable tattoo electronics to function as fully independent systems with sustained operation. Therefore, tattoo-integrated energy solutions can contribute significantly to the development of next-generation autonomous bioelectronic systems by providing compact, eco-friendly, and non-invasive power sources.

5. Conclusion and perspectives

This review has explored fabrication methods, materials, and diverse applications of tattoo-based electronics. While traditional substrate-based wearables often struggle with issues of conformality, user comfort, and mechanical compatibility, tattoo electronics offer a promising alternative through their seamless integration with the skin. Building on these advantages, tattoo-based electronics are now redefining the landscape of wearable technology by enabling ultrathin and conformal platforms for health monitoring, HMI, and energy systems. However, to fully realize their potential, several unresolved challenges must still be addressed, along with the exploration of new technological directions.

First, enhancing long-term durability and mechanical robustness remains critical. Tattoo electrodes often suffer from delamination, mechanical failure, or degradation under repeated strain, especially under humid or dynamic skin conditions. Strategies involving self-healing materials, moisturetolerant encapsulation, and stretchable interconnects are needed to ensure consistent long-term performance. Second, the development of biodegradable tattoo electronics is an emerging direction with high relevance for both medical and environmental applications. Biodegradable tattoo sensors can offer transient wound healing or drug delivery monitoring without requiring removal, minimizing environmental impact and improving user comfort. Third, incorporating a wider range of materials can allow tattoo sensors to detect multiple types of signals simultaneously, enabling more compact and lightweight designs. Incorporating 2D materials, bioresorbable composites, and biocompatible nanostructures can drive progress in this area. Finally, integrating data processing and wireless communication in ultrathin formats is essential to create fully autonomous systems. Advanced machine learning approaches and power-efficient circuitry can enable real-time analysis and feedback in decentralized healthcare or immersive HMI environments.

Therefore, addressing these frontiers will shape tattoo-based electronics into truly autonomous, versatile platforms for nextgeneration bioelectronic systems.

Data availability

No primary research results, software or code have been included and no new data were generated or analysed as part of this review.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by the National Research Foundation of Korea (grant number RS-2025-11092968, RS-2022-NR068144) and the Air Force Office of Scientific Research under award number FA2386-24-1-4089.

References

- 1 Y. Liu, H. Wang, W. Zhao, M. Zhang, H. Qin and Y. Xie, *Sensors*, 2018, **18**, 645.
- 2 M. Jafari, G. Marquez, H. Dechiraju, M. Gomez and M. Rolandi, *Cell Rep. Phys. Sci.*, 2023, 4, 101535.
- 3 J. Xie, Y. Zhao, D. Zhu, J. Yan, J. Li, M. Qiao, G. He and S. Deng, *ACS Appl. Mater. Interfaces*, 2023, **15**, 12551–12559.
- 4 Q. Yang, W. Jin, Q. Zhang, Y. Wei, Z. Guo, X. Li, Y. Yang, Q. Luo, H. Tian and T.-L. Ren, *Nat. Mach. Intell.*, 2023, 5, 169–180.
- 5 W. Heng, S. Solomon and W. Gao, *Adv. Mater.*, 2022, 34, e2107902.
- 6 Y. Yuan, B. Liu, H. Li, M. Li, Y. Song, R. Wang, T. Wang and H. Zhang, *Biosensors*, 2022, **12**, 1069.
- 7 A. J. Bandodkar, W. Jia and J. Wang, *Electroanalysis*, 2015, 27, 562–572.
- 8 K. Lim, H. Seo, W. G. Chung, H. Song, M. Oh, S. Y. Ryu, Y. Kim and J.-U. Park, *Commun. Mater.*, 2024, 5, 49.
- 9 A. Spanu, A. Mascia, G. Baldazzi, B. Fenech-Salerno,
 F. Torrisi, G. Viola, A. Bonfiglio, P. Cosseddu and
 D. Pani, *Front. Bioeng. Biotechnol.*, 2022, 10, 820217.
- 10 Y. Wang, L. Yin, Y. Bai, S. Liu, L. Wang, Y. Zhou, C. Hou, Z. Yang, H. Wu, J. Ma, Y. Shen, P. Deng, S. Zhang, T. Duan, Z. Li, J. Ren, L. Xiao, Z. Yin, N. Lu and Y. Huang, *Sci. Adv.*, 2020, 6, eabd0996.
- 11 K. K. Kim, M. Kim, K. Pyun, J. Kim, J. Min, S. Koh, S. E. Root, J. Kim, B.-N. T. Nguyen, Y. Nishio, S. Han, J. Choi, C. Y. Kim, J. B. H. Tok, S. Jo, S. H. Ko and Z. Bao, *Nat. Electron.*, 2022, 6, 64–75.
- 12 L. W. Lo, J. Zhao, H. Wan, Y. Wang, S. Chakrabartty and C. Wang, *ACS Appl. Mater. Interfaces*, 2021, 13, 21693–21702.
- 13 X. Strakosas, H. Biesmans, T. Abrahamsson, K. Hellman, M. S. Ejneby, M. J. Donahue, P. Ekström, F. Ek, M. Savvakis, M. Hjort, D. Bliman, M. Linares, C. Lindholm, E. Stavrinidou, J. Y. Gerasimov, D. T. Simon, R. Olsson and M. Berggren, *Science*, 2023, **379**, 795–802.
- 14 T. Li, H. Qi, C. Zhao, Z. Li, W. Zhou, G. Li, H. Zhuo and W. Zhai, *Nat. Commun.*, 2025, **16**, 88.
- B. Wei, Z. Wang, H. Guo, F. Xie, S. Cheng, Z. Lou, C. Zhou, H. Ji, M. Zhang, X. Wang, X. Jiao, S. Ma, H.-M. Cheng and X. Xu, *Cell Rep. Phys. Sci.*, 2023, 4, 101335.
- 16 J. Kim, I. Jeerapan, S. Imani, T. N. Cho, A. Bandodkar, S. Cinti, P. P. Mercier and J. Wang, ACS Sens., 2016, 1, 1011–1019.

- 17 A. J. Bandodkar, W. Jia, C. Yardimci, X. Wang, J. Ramirez and J. Wang, *Anal. Chem.*, 2015, **87**, 394–398.
- 18 M. Kim, J. J. Park, C. Cho and S. H. Ko, Adv. Funct. Mater., 2023, 33, 2303286.
- 19 T. W. Kang, J. Lee, Y. Kwon, Y. J. Lee and W. H. Yeo, *Adv. NanoBiomed Res.*, 2024, 4, 2300169.
- 20 L. M. Ferrari, U. Ismailov, J.-M. Badier, F. Greco and E. Ismailova, *npj Flexible Electron.*, 2020, **4**, 4.
- 21 X. Zhou, A. Rajeev, A. Subramanian, Y. Li, N. Rossetti, G. Natale, G. A. Lodygensky and F. Cicoira, *Acta Biomater.*, 2022, **139**, 296–306.
- 22 A. Miyamoto, S. Lee, N. F. Cooray, S. Lee, M. Mori, N. Matsuhisa, H. Jin, L. Yoda, T. Yokota, A. Itoh, M. Sekino, H. Kawasaki, T. Ebihara, M. Amagai and T. Someya, *Nat. Nanotechnol.*, 2017, **12**, 907–913.
- 23 C. Cho, W. Shin, M. Kim, J. Bang, P. Won, S. Hong and S. H. Ko, *Small*, 2022, **18**, e2202841.
- 24 J. Zhu, Y. Xiao, X. Zhang, Y. Tong, J. Li, K. Meng, Y. Zhang, J. Li, C. Xing, S. Zhang, B. Bao, H. Yang, M. Gao, T. Pan, S. Liu, F. Lorestani, H. Cheng and Y. Lin, *Adv. Mater.*, 2024, 36, e2400236.
- 25 F. M. Vivaldi, A. Dallinger, A. Bonini, N. Poma, L. Sembranti, D. Biagini, P. Salvo, F. Greco and F. Di Francesco, ACS Appl. Mater. Interfaces, 2021, 13, 30245–30260.
- 26 J. Bang, Y. Jung, H. Kim, D. Kim, M. Cho and S. H. Ko, *Nano-Micro Lett.*, 2022, 14, 49.
- 27 I. Byun, A. W. Coleman and B. Kim, *J. Micromech. Micro-eng.*, 2013, 23, 085016.
- 28 K. J. Lee, K. A. Fosser and R. G. Nuzzo, *Adv. Funct. Mater.*, 2005, **15**, 557–566.
- 29 S. Wang, J. Y. Oh, J. Xu, H. Tran and Z. Bao, Acc. Chem. Res., 2018, 51, 1033–1045.
- 30 K. Zhao, Y. Zhao, R. Qian and C. Ye, *Chem. Eng. J.*, 2023, 477, 147109.
- 31 L. Yin, R. Kumar, A. Karajic, L. Xie, J. M. You, D. Joshuia, C. S. Lopez, J. Miller and J. Wang, *Adv. Mater. Technol.*, 2018, 3, 1800013.
- 32 S. Yin and L. Dong, Adv. Mater. Technol., 2024, 9, 2302073.
- 33 T. Widlund, S. Yang, Y.-Y. Hsu and N. Lu, *Int. J. Solids* Struct., 2014, **51**, 4026–4037.
- 34 J. Kim, S. J. Park, T. Nguyen, M. Chu, J. D. Pegan and M. Khine, *Appl. Phys. Lett.*, 2016, **108**, 061901.
- 35 Y. Jung, K. R. Pyun, S. Yu, J. Ahn, J. Kim, J. J. Park, M. J. Lee,
 B. Lee, D. Won, J. Bang and S. H. Ko, *Nano-Micro Lett.*,
 2025, 17, 127.
- 36 Y. Chen, R. S. Carmichael and T. B. Carmichael, ACS Appl. Mater. Interfaces, 2019, 11, 31210–31219.
- 37 S. J. Joo, S. H. Park, C. J. Moon and H. S. Kim, ACS Appl. Mater. Interfaces, 2015, 7, 5674–5684.
- 38 J. S. Oh, J. S. Oh and G. Y. Yeom, *Nanomaterials*, 2020, 10, 633.
- 39 H. Wang, J. Wang, D. Chen, S. Ge, Y. Liu, Z. Wang, X. Zhang,
 Q. Guo and J. Yang, *IEEE Sens. J.*, 2022, 22, 3817–3827.
- 40 W. Zhao, C. Liu, Y. Wang, K. Li, Z. He, S. Zhou, J. Zeng, O. O. Ibrahim, S. Zhang and Q. Wang, *Sens. Actuators, B*, 2025, 428, 137245.

- 41 G.-H. Lee, H. Kim, J. Lee, J.-Y. Bae, C. Yang, H. Kim, H. Kang, S. Q. Choi, S. Park, S.-K. Kang, J. Kang, Z. Bao, J.-W. Jeong and S. Park, *Mater. Today*, 2023, **67**, 84–94.
- 42 W. Ge, R. Wang, X. Zhu, H. Zhang, L. Sun, F. Wang, H. Li, Z. Li, X. Du, H. Chen, F. Zhang, H. Shi, H. Hu, Y. Xi, J. He, L. Hu and H. Lan, *J. Mater. Chem. A*, 2024, **12**, 657–689.
- 43 M. Reis Carneiro, C. Majidi and M. Tavakoli, *Adv. Eng. Mater.*, 2021, 24, 2100953.
- 44 S. Kim, B. Yoo, M. Miller, D. Bowen, D. J. Pines and K. M. Daniels, *Sens. Actuators, A*, 2022, 342, 113659.
- 45 G. H. Lee, H. Woo, C. Yoon, C. Yang, J. Y. Bae, W. Kim,
 D. H. Lee, H. Kang, S. Han, S. K. Kang, S. Park, H. R. Kim,
 J. W. Jeong and S. Park, *Adv. Mater.*, 2022, 34, e2204159.
- 46 M. J. Allen, V. C. Tung and R. B. Kaner, *Chem. Rev.*, 2010, 110, 132–145.
- 47 K. J. Hughes, K. A. Iyer, R. E. Bird, J. Ivanov, S. Banerjee, G. Georges and Q. A. Zhou, *ACS Appl. Nano Mater.*, 2024, 7, 18695–18713.
- 48 Z. Zhai, L. Zhang, T. Du, B. Ren, Y. Xu, S. Wang, J. Miao and Z. Liu, *Mater. Des.*, 2022, **221**, 111017.
- 49 L. Bareket, L. Inzelberg, D. Rand, M. David-Pur, D. Rabinovich, B. Brandes and Y. Hanein, *Sci. Rep.*, 2016, 6, 25727.
- 50 D. Kireev, S. K. Ameri, A. Nederveld, J. Kampfe, H. Jang, N. Lu and D. Akinwande, *Nat. Protoc.*, 2021, **16**, 2395–2417.
- 51 S. Kabiri Ameri, R. Ho, H. Jang, L. Tao, Y. Wang, L. Wang, D. M. Schnyer, D. Akinwande and N. Lu, *ACS Nano*, 2017, 11, 7634–7641.
- 52 D. Kireev, J. Kampfe, A. Hall and D. Akinwande, *npj 2D Mater. Appl.*, 2022, **6**, 46.
- 53 D. Kireev, K. Sel, B. Ibrahim, N. Kumar, A. Akbari, R. Jafari and D. Akinwande, *Nat. Nanotechnol.*, 2022, **17**, 864–870.
- 54 J. E. Jin, S. Kim, H. Yu, K. N. Lee, Y. R. Do and S. M. Lee, *Biomed. Eng. Lett.*, 2023, 13, 495–504.
- 55 L. Liu, X. Zhang, D. Xiang, Y. Wu, D. Sun, J. Shen, M. Wang, C. Zhao, H. Li, Z. Li, P. Wang and Y. Li, *Prog. Nat. Sci.: Mater. Int.*, 2022, **32**, 34–42.
- 56 H. Li, J. Cao, R. Wan, V. R. Feig, C. M. Tringides, J. Xu,
 H. Yuk and B. Lu, *Adv. Mater.*, 2025, 37, e2415151.
- 57 J. Yu, R. Wan, F. Tian, J. Cao, W. Wang, Q. Liu, H. Yang, J. Liu, X. Liu, T. Lin, J. Xu and B. Lu, *Small*, 2024, 20, e2308778.
- 58 J. Jin, S. Wang, Z. Zhang, D. Mei and Y. Wang, *Soft Sci.*, 2023, **3**, 8.
- 59 Q. Gao, C. Li, M. Wang, J. Zhu, D. R. Munna, P. Wang, C. Zhu, J. Gao and C. Gao, *J. Mater. Chem. C*, 2022, 10, 6271–6280.
- 60 T. Zhou, H. Yuk, F. Hu, J. Wu, F. Tian, H. Roh, Z. Shen, G. Gu, J. Xu, B. Lu and X. Zhao, *Nat. Mater.*, 2023, 22, 895–902.
- 61 B. Lu, H. Yuk, S. Lin, N. Jian, K. Qu, J. Xu and X. Zhao, *Nat. Commun.*, 2019, **10**, 1043.
- 62 N. Kim, S. Lienemann, I. Petsagkourakis, D. Alemu Mengistie, S. Kee, T. Ederth, V. Gueskine, P. Leclere, R. Lazzaroni, X. Crispin and K. Tybrandt, *Nat. Commun.*, 2020, **11**, 1424.

- 63 D. Won, H. Kim, J. Kim, H. Kim, M. W. Kim, J. Ahn, K. Min, Y. Lee, S. Hong, J. Choi, C. Y. Kim, T.-S. Kim and S. H. Ko, *Nat. Electron.*, 2024, 7, 475–486.
- 64 H. Cao, L. Duan, Y. Zhang, J. Cao and K. Zhang, Signal Transduction Targeted Ther., 2021, 6, 426.
- 65 E. M. Ahmed, J. Adv. Res., 2015, 6, 105-121.
- 66 S. Zhuo, A. Tessier, M. Arefi, A. Zhang, C. Williams and S. K. Ameri, *npj Flexible Electron.*, 2024, 8, 49.
- 67 S. Correa, A. K. Grosskopf, H. Lopez Hernandez, D. Chan, A. C. Yu, L. M. Stapleton and E. A. Appel, *Chem. Rev.*, 2021, 121, 11385–11457.
- 68 M. Song, C. Gong and X. Liu, *J. Polym. Mater.*, 2025, 42, 111-123.
- 69 J. Yu, F. Tian, W. Wang, R. Wan, J. Cao, C. Chen, D. Zhao, J. Liu, J. Zhong, F. Wang, Q. Liu, J. Xu and B. Lu, *Chem. Mater.*, 2023, 35, 5936–5944.
- 70 J. H. Kim, J. Y. Hwang, H. R. Hwang, H. S. Kim, J. H. Lee, J. W. Seo, U. S. Shin and S. H. Lee, *Sci. Rep.*, 2018, 8, 1375.
- 71 Y. Ding, Y. Shi, D. Yu and W. Wang, *Colloids Surf.*, *A*, 2023, **675**, 132060.
- 72 M. Shekhirev, C. E. Shuck, A. Sarycheva and Y. Gogotsi, *Prog. Mater. Sci.*, 2021, **120**, 100757.
- 73 A. VahidMohammadi, J. Rosen and Y. Gogotsi, *Science*, 2021, 372, eabf1581.
- 74 N. A. Koshi, A. K. Mandia, B. Muralidharan, S. C. Lee and S. Bhattacharjee, *Nanoscale*, 2023, 15, 10254–10263.
- 75 C. J. Zhang, B. Anasori, A. Seral-Ascaso, S. H. Park, N. McEvoy, A. Shmeliov, G. S. Duesberg, J. N. Coleman, Y. Gogotsi and V. Nicolosi, *Adv. Mater.*, 2017, 29, 1702678.
- 76 Y. Dong, S. S. K. Mallineni, K. Maleski, H. Behlow, V. N. Mochalin, A. M. Rao, Y. Gogotsi and R. Podila, *Nano Energy*, 2018, 44, 103–110.
- 77 M. Salauddin, S. M. S. Rana, M. Sharifuzzaman, M. T. Rahman, C. Park, H. Cho, P. Maharjan, T. Bhatta and J. Y. Park, *Adv. Energy Mater.*, 2021, **11**, 2002832.
- 78 L. Wang, Y. Lin, C. Yang, Q. Wang, T. Fang, C. Bai, J. Wang and D. Kong, *Chem. Eng. J.*, 2024, **500**, 157504.
- 79 J. Y. Oh, J. H. Lee, S. W. Han, S. S. Chae, E. J. Bae, Y. H. Kang, W. J. Choi, S. Y. Cho, J.-O. Lee, H. K. Baik and T. I. Lee, *Energy Environ. Sci.*, 2016, 9, 1696–1705.
- 80 Z. Xie, S. Yu, X. Ma, K. Li, L. Ding, W. Wang, D. A. Cullen,
 H. M. Meyer, H. Yu, J. Tong, Z. Wu and F.-Y. Zhang, *Appl. Catal.*, *B*, 2022, 313, 121458.
- 81 S. Manzeli, D. Ovchinnikov, D. Pasquier, O. V. Yazyev and A. Kis, *Nat. Rev. Mater.*, 2017, 2, 17033.
- 82 Q. Zhang, E. Linardy, X. Wang and G. Eda, *ACS Nano*, 2020, 14, 11482–11489.
- 83 S. Joseph, J. Mohan, S. Lakshmy, S. Thomas,
 B. Chakraborty, S. Thomas and N. Kalarikkal, *Mater. Chem. Phys.*, 2023, 297, 127332.
- 84 T. Zhang, Y. Wang, X. Feng, Y. Zuo, H. Yu, H. Bao, F. Jiang and S. Jiang, *iScience*, 2024, 27, 110707.
- 85 R. Vikhe, S. Masure, M. K. Das, A. Mishra, E. Sreehari, U. Kulhari, B. D. Sahu, L. N. Sharma, S. Loganathan and S. Kumar, ACS Appl. Electron. Mater., 2025, 7, 1611–1621.

- 86 S. Liu, T. Fawden, R. Zhu, G. G. Malliaras and M. Bance, *Sci. Adv.*, 2024, **10**, eado9576.
- 87 H. Jang, K. Sel, E. Kim, S. Kim, X. Yang, S. Kang, K. H. Ha,
 R. Wang, Y. Rao, R. Jafari and N. Lu, *Nat. Commun.*, 2022,
 13, 6604.
- 88 S. Shustak, L. Inzelberg, S. Steinberg, D. Rand, M. David Pur, I. Hillel, S. Katzav, F. Fahoum, M. De Vos, A. Mirelman and Y. Hanein, *J. Neural Eng.*, 2019, 16, 026024.
- 89 S. Wang, X. Wang, W. Zhang, X. Shi, D. Song, Y. Zhang, Y. Zhao, Z. Zhao and N. Liu, *Nano Res.*, 2023, 16, 4100–4106.
- 90 S. Kwon, H. S. Kim, K. Kown, H. Kim, Y. S. Kim, S. H. Lee, Y. T. Kown, J. W. Jeong, L. M. Trotti, A. Duarte and W. H. Yeo, *Sci. Adv.*, 2023, 9, eadg9671.
- 91 R. C. Webb, A. P. Bonifas, A. Behnaz, Y. Zhang, K. J. Yu, H. Cheng, M. Shi, Z. Bian, Z. Liu, Y. S. Kim, W. H. Yeo, J. S. Park, J. Song, Y. Li, Y. Huang, A. M. Gorbach and J. A. Rogers, *Nat. Mater.*, 2013, **12**, 938–944.
- 92 Y. Zheng, Y. Li, Y. Zhao, X. Lin, S. Luo, Y. Wang, L. Li, C. Teng, X. Wang, G. Xue and D. Zhou, *Nano Energy*, 2023, 107, 108092.
- 93 H. Yuan, Y. Li, J. Yang, H. Li, Q. Yang, C. Guo, S. Zhu and X. Shu, *Micromachines*, 2021, **12**, 1521.
- 94 M. Galliani, F. Greco, E. Ismailova and L. M. Ferrari, ACS Appl. Electron. Mater., 2025, 7, 1408–1414.
- 95 R. Park, H. Kim, S. Lone, S. Jeon, Y. W. Kwon, B. Shin and S. W. Hong, *Sensors*, 2018, **18**, 1857.
- 96 T. Li, T. Zhao, H. Zhang, L. Yuan, C. Cheng, J. Dai, L. Xue, J. Zhou, H. Liu, L. Yin and J. Zhang, *npj Flexible Electron.*, 2024, 8, 3.
- 97 A. J. Bandodkar, V. W. Hung, W. Jia, G. Valdes-Ramirez, J. R. Windmiller, A. G. Martinez, J. Ramirez, G. Chan, K. Kerman and J. Wang, *Analyst*, 2013, 138, 123–128.
- 98 K. Unger, F. Greco and A. M. Coclite, *Adv. Mater. Technol.*, 2021, 7, 2100717.
- 99 A. J. Bandodkar, D. Molinnus, O. Mirza, T. Guinovart, J. R. Windmiller, G. Valdes-Ramirez, F. J. Andrade, M. J. Schoning and J. Wang, *Biosens. Bioelectron.*, 2014, 54, 603–609.
- 100 N. K. Singh, S. Chung, A. Y. Chang, J. Wang and D. A. Hall, Biosens. Bioelectron., 2023, 227, 115097.
- 101 D. Kim, J. Lee, M. K. Park and S. H. Ko, *Commun. Mater.*, 2024, 5, 41.
- 102 G. E. Bonacchini, C. Bossio, F. Greco, V. Mattoli, Y. H. Kim,G. Lanzani and M. Caironi, *Adv. Mater.*, 2018, 30, e1706091.
- 103 W. T. Fonseca, T. Parra Vello, G. C. Lelis, A. V. Ferreira Deleigo, R. K. Takahira, D. S. T. Martinez and R. F. de Oliveira, ACS Sens., 2025, 10, 3222–3238.
- 104 M. A. S. Almeida, A. L. Pires, J. L. Ramirez, S. B. Malik, S. de la Flor, E. Llobet, A. T. Pereira and A. M. Pereira, *Adv. Sci.*, 2025, **12**, e2403775.
- 105 J. Alberto, C. Leal, C. Fernandes, P. A. Lopes, H. Paisana,A. T. de Almeida and M. Tavakoli, *Sci. Rep.*, 2020, 10, 5539.
- 106 S. Hong, J. Lee, K. Do, M. Lee, J. H. Kim, S. Lee and D. H. Kim, Adv. Funct. Mater., 2017, 27, 1704353.

Review

- 107 L. M. Ferrari, U. Ismailov, F. Greco and E. Ismailova, *Adv. Mater. Interfaces*, 2021, **8**, 2100352.
- 108 N. Gogurla and S. Kim, Adv. Energy Mater., 2021, 11, 2100801.
- 109 A. Wahlsten, A. Stracuzzi, I. Luchtefeld, G. Restivo, N. Lindenblatt, C. Giampietro, A. E. Ehret and E. Mazza, *Acta Biomater.*, 2023, **170**, 155–168.
- S. Budday, R. Nay, R. de Rooij, P. Steinmann, T. Wyrobek,
 T. C. Ovaert and E. Kuhl, *J. Mech. Behav. Biomed. Mater.*, 2015, 46, 318-330.
- 111 R. Emig, C. M. Zgierski-Johnston, V. Timmermann,A. J. Taberner, M. P. Nash, P. Kohl and R. Peyronnet, *Biophys. Rev.*, 2021, 13, 587–610.
- 112 A. E. Samir, M. Dhyani, A. Vij, A. K. Bhan, E. F. Halpern, J. Méndez-Navarro, K. E. Corey and R. T. Chung, *Radiology*, 2015, 274, 888–896.

- 113 S. R. Polio, A. N. Kundu, C. E. Dougan, N. P. Birch, D. E. Aurian-Blajeni, J. D. Schiffman, A. J. Crosby and S. R. Peyton, *PLoS One*, 2018, 13, e0204765.
- 114 A. Karimi, A. Shojaei and P. Tehrani, *J. Chem. Neuroanat.*, 2017, **86**, 15–18.
- 115 G. H. Borschel, K. F. Kia, W. M. Kuzon, Jr. and R. G. Dennis, *J. Surg. Res.*, 2003, **114**, 133–139.
- 116 D. B. Camasao and D. Mantovani, *Mater. Today Bio*, 2021, **10**, 100106.
- 117 G. Nakao, T. Kodesho, T. Kato, Y. Yokoyama, Y. Saito, Y. Ohsaki, K. Watanabe, M. Katayose and K. Taniguchi, *J. Med. Ultrason.*, 2023, 50, 275–283.
- 118 M. Ferrara, G. Lugano, M. T. Sandinha, V. R. Kearns,
 B. Geraghty and D. H. W. Steel, *Eye*, 2021, 35, 1818–1832.