



Nanoscale

**Improved Electronic Uniformity and Nanoscale Homogeneity
in Template-Grown CsPbBr₃ Nanorods**

Journal:	<i>Nanoscale</i>
Manuscript ID	NR-ART-12-2023-006682.R1
Article Type:	Paper
Date Submitted by the Author:	16-Mar-2024
Complete List of Authors:	Avila-Lopez, Eduardo; California State University Bakersfield Liang, Shuang; University of Minnesota Twin Cities, Department of Chemistry & Department of Chemical Engineering and Materials Science Elias, Isaac; California State University Bakersfield Lin, Zhiqun; National University of Singapore, Chemical and Biomolecular Engineering; Georgia Institute of Technology, Li, Yize; California State University Bakersfield,

SCHOLARONE™
Manuscripts

Improved Electronic Uniformity and Nanoscale Homogeneity in Template-Grown CsPbBr₃ Nanorods

Eduardo Avila-Lopez,^a Shuang Liang,^b Isaac Elias,^a Zhiqun Lin,^{*b,c} and Yize Stephanie Li^{*a}

^a School of Natural Sciences, Mathematics, and Engineering, California State University, Bakersfield, California 93311, United States. E-mail: yli11@csub.edu

^b School of Materials Science and Engineering, Georgia Institute of Technology, Atlanta, Georgia 30332, United States

^c Department of Chemical and Biomolecular Engineering, National University of Singapore, Singapore 117585, Singapore. E-mail: z.lin@nus.edu.sg

Abstract:

One-dimensional metal halide perovskites are among the most promising candidate materials for optoelectronic devices. The heterogeneity and fast degradation of perovskite nanowires (NWs) and nanorods (NRs) synthesized by conventional approaches, nevertheless, impose a bottleneck for their optoelectronic applications. Recently, all-inorganic perovskite CsPbBr₃ NRs with tailored dimensions, crafted using amphiphilic bottlebrush-like block copolymer (BBCP) as nanoreactors, demonstrated enhanced stabilities. Herein, we report the electronic investigation into these template-grown CsPbBr₃ NRs using a contactless, nondestructive imaging technique, dielectric force microscopy (DFM). All freshly prepared CsPbBr₃ NRs exhibited ambipolar behaviors which remained up to two months after sample synthesis. A transition from ambipolar to p-type behaviors occurred after two months, and nearly all NRs completed the transition within two weeks. Moreover, template-grown CsPbBr₃ NRs displayed better nanoscale electronic homogeneity compared to their conventional counterparts. The improved electronic uniformity and nanoscale homogeneity places template-grown CsPbBr₃ NRs a unique advantageous position for optoelectronic applications.

1 Introduction

With recent advances in metal halide perovskite-based materials and devices over the past decade,^{1–12} particularly ample success in synthesis of perovskite nanocrystals (NC) with controlled shapes,^{13–18} crafting and investigation into one-dimensional (1D) perovskite nanorods (NRs) and nanowires (NWs) have attracted significant attention.^{19–23} Colloidal synthesis^{18,24} and surfactant-free substrate-assisted growth^{8,25,26} have been the prevailing approaches to synthesize perovskite NRs and NWs. Perovskite NWs synthesized by the hot-injection method possess well-controlled, uniform morphology.¹⁸ Our recent electronic characterization using contactless dielectric force microscopy (DFM) technique, nevertheless, unraveled the electronic heterogeneity and inhomogeneity in individual CsPbBr₃ NWs synthesized via the hot-injection method.²⁷ In a very recent work, we developed a general approach to synthesize a library of 1D perovskite NRs with controllable dimensions, compositions and enhanced stabilities, by using amphiphilic bottlebrush-like block copolymer (BBCP) as nanoreactors.²⁸ NRs synthesized by this new approach are termed as template-grown NRs or templated NRs. The electronic transport properties of template-grown CsPbBr₃ NRs, which are highly relevant to device applications, are the focuses of this work.

The conventional approach to study electronic transport properties, including the majority carrier type, of a semiconductor requires fabrication of a field effect transistor (FET) before electronic transport measurements could be performed. Due to experimental challenge of FET device fabrication on individual NRs or NWs, few studies in the literature reported the majority carrier type in individual NRs/NWs. Meng *et al.* fabricated an FET device on a CsPbBr₃ NW that had a diameter of ~150 nm and measured its transfer characteristic, revealing an ambipolar behavior.^{29,30} In addition to the challenge in device fabrication, the interpretation of data from transport measurements could be complicated with

the influence of metal-nanomaterial contacts.³¹ It has been shown in our prior work that DFM is a powerful tool to probe the electronic properties in perovskite NWs.²⁷

In this work, we report the investigation of the electronic properties in template-grown CsPbBr₃ NRs using contactless dielectric force microscopy. CsPbBr₃ NRs with lengths of 60–130 nm and with diameters of 5–12 nm were examined. All templated CsPbBr₃ NRs were identified as ambipolar semiconductor NRs with both electrons and holes as majority carriers. Their ambipolar behaviors lasted for two months, after which a transition to p-type behaviors occurred and was completed in about two weeks. In addition, DFM characterizations revealed good longitudinal and transverse nanoscale electronic homogeneities.

2 Experimental

2.1 Synthesis of Templated CsPbBr₃ Nanorod Samples

The synthesis of templated CsPbBr₃ NR samples used in this work is schematically illustrated in Fig. 1a. Amphiphilic bottlebrush-like block copolymers of poly(acrylic acid)-block-polystyrene (denoted PAA-*b*-PS) were firstly synthesized, which were then used as nanoreactors for the growth of PS-ligated CsPbBr₃ NRs. As reported previously,²⁸ the template synthetic approach, featured by using amphiphilic bottlebrush-like block copolymers as nanoreactors, enabled formation of uniform perovskite NRs with precisely controlled dimensions and compositions, as well as enhanced stabilities owing to the presence of hydrophobic PS chains. The enhanced stabilities ensure that template-grown CsPbBr₃ NRs maintain good 1D morphology and thus provide well defined electronic transport path, after an extended period of time.

2.2 CsPbBr₃ Nanorod Storage and Preparation for Electronic Characterization

As-synthesized CsPbBr₃ NRs were remained in liquid Hexane at room temperature in ambient air, until they were ready for electronic characterizations. In preparation for each electronic characterization, CsPbBr₃ NRs were spin-cast onto a degenerately doped p-type Si wafer with a 300-nm-thick thermal oxide layer. The wafer was then stored in a vacuum desiccator overnight to ensure that the surface was free of liquid droplets before electronic characterization.




Fig. 1 (a) Schematic illustration of the synthetic route to amphiphilic bottlebrush-like poly(acrylic acid)-block-polystyrene (denoted PAA-*b*-PS) block copolymers and subsequent PS-ligated perovskite nanorods using the former as nanoreactors. (b) Schematic illustration of a DFM experiment. (c) Schematic

illustration on how positive, zero, and negative V_{DC} modulates the distribution of majority carriers (i.e. electrons) in an n-type nanorod.

2.3 Electronic Characterization Using Dielectric Force Microscopy

The study of the electronic properties of template-grown CsPbBr₃ NRs was achieved by employing a novel contactless scanning force microscopy (SFM)-based imaging tool, dielectric force microscopy. As reported in our prior work, DFM allowed identification of semiconducting and metallic nanomaterials and determination of the majority carrier type in a semiconductor, without the need of making metal contacts.^{27,32–34} DFM signals from nanomaterials were found to highly correlated with their electronic transport properties.³¹ Moreover, the inherent nanoscale spatial resolution of DFM, as an SFM-based technique, enabled contactless detection of local electronic inhomogeneities, including point defects, grain boundaries, and complex defect patterns.^{27, 31}

The DFM setup was built with a Park NX-10 atomic force microscope (AFM) and conductive AFM probes (MikroMasch NSC19/Cr-Au) were used for the experiments. A double-pass imaging process, as illustrated in Fig. 1b, was used. Following acquisition of a topographic scan line in the first pass, the oscillation of the cantilever at resonance frequency was turned off and the tip was lifted up to a height (typically 10 – 15 nm in this work), and a bias voltage $V = V_{DC} + V_{AC} \sin(\omega t)$ was applied to the conductive AFM tip only in the second pass. The AC bias is to polarize the sample, resulting in an attractive dielectric force that oscillates in a 2ω frequency. The DC bias acts as a local gate, similar to a top gate in a field effect transistor, which modulates the carrier distribution in the sample. Fig. 1c illustrates the modulation of the majority carrier distribution in the presence of a positive, zero, and negative V_{DC} , using an n-type NR as an example. The accumulation (depletion) of majority carriers, i.e. electrons, below the conductive AFM tip under a positive (negative) V_{DC} leads to a stronger (weaker) DFM

response, compared to that under zero V_{DC} . For a p-type NR where holes are majority carriers (not shown), on the other hand, the DFM response is strongest under a negative V_{DC} and is weakest under a positive V_{DC} . For an ambipolar NR where both electrons and holes are majority carriers (not shown), the DFM responses at both positive and negative V_{DC} are stronger than zero V_{DC} . The 2ω component of the cantilever deflection signal is sampled by a lock-in amplifier and recorded as a DFM image. A comparison of DFM images at a positive, zero, and negative V_{DC} allows determination of the majority carrier type in a semiconductor NR.

3 Results and discussion

3.1 Uniform Ambipolar Behaviors and Nanoscale Electronic Homogeneity

Fig. 2a shows the topography and DFM images of a template-grown CsPbBr_3 NR, labeled as NR 1, measured 14 days after a sample was synthesized. The NR had well-defined morphology and a nearly uniform diameter of 8 ± 1 nm along the NR. The DFM responses of NR 1 at $V_{DC} = 3$ V and -3 V were both stronger compared to $V_{DC} = 0$ V, signifying an ambipolar NR. Fig. 2b shows the topography and DFM images of another template-grown CsPbBr_3 NR, NR 2, measured 21 days after a different sample was synthesized. The diameter of NR 2 was 5 ± 1 nm which remained uniform along the NR. Same as NR 1, NR 2 was an ambipolar NR with the weakest DFM response at $V_{DC} = 0$ V. DFM signals, extracted from the DFM images, as a function of V_{DC} are shown in Fig. 2c for NRs 1 – 2, which further confirmed quantitatively that both were ambipolar NRs. Notably, all template-grown CsPbBr_3 NRs in freshly prepared samples exhibited ambipolar behaviors which remained up to two months after the samples were synthesized (see Fig. 3 and discussions below). In a prior work, we reported the electronic heterogeneity of CsPbBr_3 NWs, synthesized using a conventional hot-injection approach, where ambipolar, n-type, and p-type NWs co-existed.²⁷ The remarkable electronic uniformity in templated

CsPbBr₃ NRs, benefited from the template growth approach using BBCP as nanoreactors, makes them particularly competitive for optoelectronic applications that requires uniform electronic performance from individual NRs.




Fig. 2 (a) Topographical images and dielectric response images of a templated CsPbBr₃ nanorod, NR 1 (diameter: 8±1 nm), 14 days after a sample was synthesized, and another templated CsPbBr₃ nanorod, NR 2 (diameter: 5±1 nm), 21 days after synthesis. (b) DFM signal as a function of V_{DC} for NR 1 and NR 2. (c) X–Y coordinate system whose origin is located at the top end of the NR and illustration of the area selection for the extraction of DFM signal as a function of X (top) and Y (bottom), respectively (using the DFM image for NR 1 at V_{DC} = -3 V as an example). (d) DFM signal as a function of X extracted from the dielectric response images for NR 1 and NR 2 at V_{DC} = -3 V. (e) DFM signal as a function of Y extracted from the dielectric response images for NR 1 and NR 2 at V_{DC} = -3 V, where the boundaries of the Y-range with nearly constant DFM signals are indicated by dashed lines.

In addition to consistent electronic properties from different NRs, another electronic characteristic that is important for utilizing NRs as building blocks for optoelectronic devices is the nanoscale electronic

homogeneity of individual NRs. We extracted the longitudinal and transverse dielectric response profiles of template-grown CsPbBr₃ NRs, as illustrated in Fig. 2c. DFM signals as a function of X, *i.e.* longitudinal dielectric response profiles, for NR 1 and NR 2 at $V_{DC} = -3$ V, as shown in Fig. 2d, revealed good nanoscale longitudinal electronic homogeneity with small variations along the NRs. The relative standard deviation (*i.e.* the ratio between the standard deviation and the mean) of the longitudinal dielectric response profile for NR 1 and NR 2 is 5.8% and 11.6%, respectively. Similar level of longitudinal electronic homogeneity was also found at $V_{DC} = 3$ V and 0 V, respectively (see Supplementary Information). Fig. 2e shows DFM signals as a function of Y, *i.e.* transverse dielectric response profiles, for NR 1 and NR 2 at $V_{DC} = -3$ V, which were representative of transverse dielectric response profiles at $V_{DC} = 3$ V and 0 V as well (see Supplementary Information). For each DFM signal vs. Y trace, boundaries of the Y-range with nearly constant (or slowly varying) DFM signals were indicated by dashed lines to guide an eye. The Y-range within boundaries was generally consistent with the diameter of the NR, as determined from the height of the NR topography. Within the boundaries, DFM signals exhibited small variations for NR 1 (with a relative standard deviation of 3.7%) and were almost constant for NR 2 (with a relative standard deviation of 3.3%). Beyond the boundaries (corresponding to locations beyond the physical boundaries of the NR), DFM signals dropped rapidly, as expected. In our prior work, outstanding longitudinal and transverse electronic inhomogeneities were unveiled in conventional CsPbBr₃ NWs which inevitably imposed challenges in utilizing them for optoelectronic applications.²⁷ The significant improvement of nanoscale electronic homogeneity in template-grown CsPbBr₃ NRs, along both longitudinal and transverse directions, further elevates the feasibility of templated CsPbBr₃ NRs for optoelectronic applications.

3.2 Persistency of Ambipolar Behaviors up to Two Months

As a result of the enhanced stabilities in template-grown CsPbBr₃ NRs,²⁸ their uniform ambipolar behaviors remained up to two months after sample synthesis. Fig. 3a shows topography and DFM images of a 0.5 μm x 0.5 μm area with four NRs. The measurement was carried out 56 days after the sample was synthesized. Only the ones close to the top and bottom edges the scan area, labeled as NR 3 and NR 4, respectively, were scrutinized, because DFM responses of the other two NRs were superposed due to their close proximity. Both NR 3 and NR 4 displayed ambipolar behaviors as revealed from DFM images and quantitative DFM signals at $V_{DC} = 3$ V, 0 V, and -3 V (Fig. 3b). Their longitudinal and transverse dielectric response profiles, as shown in Fig. 3c–d for $V_{DC} = 3$ V as an example, indicated that the nanoscale electronic homogeneities in template-grown CsPbBr₃ NRs persisted, along with the enhanced stabilities²⁸ and consistent ambipolar behaviors. The relative standard deviations of the dielectric response profiles in the longitudinal direction were 6.6% and 9.0%, and in the transverse direction were 4.0% and 1.0%, for NR3 and NR 4, respectively. Although variations in the dielectric response profiles were visible for some NRs (for example, for NR 3), they were much less conspicuous compared to those uncovered in conventional CsPbBr₃ NWs.²⁷




Fig. 3 (a) Topographical image and dielectric response images of an area with two well-separated CsPbBr_3 nanorods, NR 3 (diameter $12 \pm 1\text{ nm}$) and NR 4 (diameter $10 \pm 1\text{ nm}$), 56 days after a sample was synthesized. (b) DFM signal as a function of V_{DC} for NR 3 and NR 4. (c) DFM signal as a function of X extracted from the dielectric response images for NR 3 and NR 4 at $V_{DC} = 3\text{ V}$. (d) DFM signal as a function of Y extracted from the dielectric response images for NR 3 and NR 4 at $V_{DC} = 3\text{ V}$, where the boundaries of the Y-range with nearly constant DFM signals (or the Y-range in which the DFM signals changed slower) are indicated by dashed lines.

3.3 Transition to p-type Behaviors

A transition from ambipolar to p-type behaviors occurred approximately two months after a sample was synthesized. Fig. 4a shows topography and DFM images of a $0.6\text{ }\mu\text{m} \times 0.6\text{ }\mu\text{m}$ area with a number of NRs, measured 62 days after sample synthesis. Two representative NRs, labeled as NR 5 and NR 6, were studied. Similar to NR 1 – 4 shown in figures above, NR 5 exhibited an ambipolar behavior with the weakest DFM response at $V_{DC} = 0\text{ V}$. NR 6, on the other hand, had the strongest DFM response at $V_{DC} = -3\text{ V}$ and the weakest DFM response at $V_{DC} = 3\text{ V}$, revealing a p-type NR. Fig. 4b shows the contrasting

DFM signal vs. V_{DC} characteristics for NR 5 and NR 6. Although NRs were in transition from ambipolar to p-type in Day 62, they still maintained well-defined morphologies and displayed generally good nanoscale electronic homogeneities, as uncovered in Fig. 4c–d for NR 5 and NR 6 at $V_{DC} = -3$ V. The relative standard deviations of the dielectric response profiles in the longitudinal direction were 17.3% and 20.2%, and in the transverse direction were 5.6% and 2.2%, for NR 5 and NR 6, respectively.




Fig. 4 (a) Topographical image and dielectric response images of an area with multiple well-separated CsPbBr₃ nanorods, including NR 5 (diameter 10±1 nm) and NR 6 (diameter 11±1 nm), 62 days after a sample was synthesized. (b) DFM signal as a function of V_{DC} for NR 5 and NR 6. (c) DFM signal as a function of X extracted from the dielectric response images for NR 5 and NR 6 at $V_{DC} = -3$ V. (d) DFM signal as a function of Y extracted from the dielectric response images for NR 5 and NR 6 at $V_{DC} = -3$ V, where the boundaries of the Y-range with nearly constant DFM signals are indicated by dashed lines.

Although the ambipolar to p-type transition did not occur exactly the same day for all NRs, nearly all NRs completed the transition within two weeks. Fig. 5a shows topography and DFM images of a 0.5 μm x 0.5

μm area with multiple NRs. The measurement was conducted 74 days after sample synthesis. All NRs displayed the strongest DFM response at $V_{\text{DC}} = -3\text{ V}$ and the weakest DFM response at $V_{\text{DC}} = 3\text{ V}$, signifying p-type behaviors. Quantitative DFM signals were also extracted for two representative NRs, labeled as NR 7 and NR 8. Fig. 5b shows their DFM signals as a function of V_{DC} , confirming their completion of the transition to p-type NRs. Even after the ambipolar to p-type transition, the NRs maintained well-defined morphology without any sign of degradation, as evident from the topographical image. Moreover, longitudinal and transverse dielectric response profiles, as shown in Fig. 5c–d for NR 7 and NR 8 at $V_{\text{DC}} = 3\text{ V}$ as examples, unveiled reasonably good nanoscale electronic homogeneity despite the transition of their polarity from ambipolar to unipolar p-type. The relative standard deviations of the dielectric response profiles in the longitudinal direction were 9.2% and 6.7%, and in the transverse direction were 1.7% and 5.7%, for NR 7 and NR 8, respectively.




Fig. 5 (a) Topographical image and dielectric response images of an area with multiple well-separated CsPbBr₃ nanorods, including NR 7 (diameter: 12±1 nm) and NR 8 (diameter 10±1 nm), 74 days after a sample was synthesized. (b) DFM signal as a function of V_{DC} for NR 7 and NR 8. (c) DFM signal as a function of X extracted from the dielectric response images for NR 7 and NR 8 at $V_{DC} = 3$ V. (d) DFM signal as a function of Y extracted from the dielectric response images for NR 7 and NR 8 at $V_{DC} = 3$ V, where the boundaries of the Y-range with nearly constant DFM signals are indicated by dashed lines.

The transition to p-type could be induced by the presence of oxygen in air. In a recent study, Shin *et al.* achieved reversible diffusion of oxygen into MAPbI₃ thin films and their photoemission experiments revealed that oxygen diffusion led to pronounced p-doping in MAPbI₃ which was attributed to oxygen substitution of iodine vacancies.³⁵ Similar oxygen substitution of bromide vacancies could occur in template-grown CsPbBr₃ NRs, after allowing sufficient time for oxygen to diffuse into PS-ligated CsPbBr₃ NRs. Indeed, the degradation of PS-ligated PbSe nanoparticles (NPs), induced by oxygen/moisture diffusion, has been reported.³⁶ The underlying mechanism for the ambipolar to p-type transition in template-grown CsPbBr₃ NRs deserves a thorough investigation, which could potentially lead to controllable electronic doping and highly desirable uniform p-type CsPbBr₃ nanocrystals.³⁷

4 Conclusions

In summary, we crafted perovskite CsPbBr₃ NRs using amphiphilic bottlebrush-like block copolymer as nanoreactors and performed contactless DFM characterizations on as-synthesized NRs to study their electronic properties. We found that all template-grown CsPbBr₃ NRs exhibited ambipolar behaviors within two months after sample synthesis. A transition from ambipolar to p-type behaviors occurred afterwards and within a transition window of about two weeks, nearly all NRs completed the transition to p-type. Moreover, our experiments revealed good longitudinal and transverse nanoscale electronic homogeneity in template-grown CsPbBr₃ NRs before and after the transition. The remarkable

improvement of electronic uniformity and nanoscale homogeneity in templated CsPbBr₃ NRs, over conventional CsPbBr₃ NWs, opens a new avenue of device applications utilizing one-dimensional perovskite nanocrystals with uniform electronic properties and minimum defects.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work is supported by the National Science Foundation through grants DMR-1904042 and DMR-1903990.

References

- 1 S. Kazim, M. K. Nazeeruddin, M. Grätzel and S. Ahmad, *Angew. Chem. Int. Ed.*, 2014, **53**, 2812–2824.
- 2 S. D. Stranks and H. J. Snaith, *Nat. Nanotechnol.*, 2015, **10**, 391–402.
- 3 D. Zhang, Y. Yang, Y. Bekenstein, Y. Yu, N. A. Gibson, A. B. Wong, S. W. Eaton, N. Kornienko, Q. Kong, M. Lai, A. P. Alivisatos, S. R. Leone and P. Yang, *J. Am. Chem. Soc.*, 2016, **138**, 7236–7239.
- 4 J. Kang, and L. W. Wang, *J. Phys. Chem. Lett.*, 2017, **8**, 489–493.
- 5 E. Oksenberg, E. Sanders, R. Popovitz-Biro, L. Houben and E. Joselevich, *Nano Lett.*, 2018, **18**, 424–433.
- 6 Q. Zhang and Y. Yin, *ACS Cent. Sci.*, 2018, **4**, 668–679.
- 7 T. Ma, S. Wang, Y. Zhang, K. Zhang and L. Yi, *J. Mater. Sci.*, 2020, **55**, 464–479.
- 8 A. B. Wong, M. Lai, S. W. Eaton, Y. Yu, E. Lin, L. Dou, A. Fu and P. Yang, *Nano Lett.*, 2015, **15**, 5519–5524.
- 9 D. Zhang, Y. Yu, Y. Bekenstein, A. B. Wong, A. P. Alivisatos and P. Yang, *J. Am. Chem. Soc.*, 2016, **138**, 13155–13158.
- 10 J. Deng, J. Li, Z. Yang and M. Wang, *J. Mater. Chem. C.*, 2019, **7**, 12415–12440.
- 11 S. W. Eaton, M. Lai, N. A. Gibson, A. B. Wong, L. Dou, J. Ma, L. W. Wang, S. R. Leone and P. Yang, *Proc. Natl. Acad. Sci. USA*, 2016, **113**, 1993–1998.
- 12 G. Xu, Y. Li, J. Yan, X. Lv, Y. Liu and B. Cai, *Mat. Res. Lett.*, 2019, **7**, 203–209.
- 13 J. Shamsi, A. S. Urban, M. Imran, L. De Trizio and L. Manna, *Chem. Rev.*, 2019, **119**, 3296–3348.
- 14 A. Pan, B. He, X. Fan, Z. Liu, J. J. Urban, A. P. Alivisatos, L. He, and Y. Liu, *ACS Nano*, 2016, **10**, 7943–7954.
- 15 J. Shamsi, P. Rastogi, V. Caligiuri, A. L. Abdelhady, D. Spirito, L. Manna and R. Krahne, *ACS Nano*, 2017, **11**, 10206–10213.
- 16 J. Shamsi, Z. Dang, P. Bianchini, C. Canale, F. Di Stasio, R. Brescia, M. Prato and L. Manna, *J. Am. Chem. Soc.*, 2016, **138**, 7240–7243.
- 17 M. Gao, H. Liu, S. Yu, S. Louisia, Y. Zhang, D. P. Nenon, A. P. Alivisatos and P. Yang, *J. Am. Chem. Soc.*, 2020, **142**, 8871–8879.
- 18 D. Zhang, S. W. Eaton, Y. Yu, D. Dou and P. Yang, *J. Am. Chem. Soc.*, 2015, **137**, 9230–9233.
- 19 Y. Dou, F. Cao, T. Dudka, Y. Li, S. Wang, C. Zhang, Y. Gao, X. Yang, A. L. Rogach, *ACS Mater. Lett.*, 2020, **2**, 814–820.

- 20 Y. Li, H. Huang, Y. Xiong, A. F. Richter, S. V. Kershaw, J. Feldmann, A. L. Rogach, *ACS Nano*, 2019, **13**, 8237–8245.
- 21 J. Li, Q. Jing, S. Xiao, Y. Gao, Y. Wang, W. Zhang, X. W. Sun, K. Wang, and T. He, *J. Phys. Chem. Lett.*, 2020, **11**, 4817–4825.
- 22 D. Yang, P. Li, Y. Zou, M. Cao, H. Hu, Q. Zhong, J. Hu, B. Sun, S. Duhm and Y. Xu, *Chem. Mater.*, 2019, **31**, 1575–1583.
- 23 Q. Li, Y. Yang, W. Que and T. Lian, *Nano Lett.*, 2019, **19**, 5620–5627.
- 24 M. Imran, F. Di Stasio, Z. Dang, C. Canale, A. H. Khan, J. Shamsi, R. Brescia, M. Prato and L. Manna, *Chem. Mater.*, 2016, **28**, 6450–6454.
- 25 J. He, A. Towers, Y. Wang, P. Yuan, Z. Jiang, J. Chen, A. J. Gesquiere, S. T. Wu, and Y. Dong, *Nanoscale* 2018, **10**, 15436–15441.
- 26 H. Zhou, S. Yuan, X. Wang, T. Xu, X. Wang, H. Li, W. Zheng, P. Fan, Y. Li and L. Sun, *ACS Nano*, 2017, **11**, 1189–1195.
- 27 Y. S. Li, S. Liang, T. Trieu, R. R. Bautista and Z. Lin, *ACS Appl. Energy Mater.*, 2022, **5**, 4431–4438.
- 28 S. Liang, M. Zhang, S. He, M. Tian, W. Choi, T. Lian and Z. Lin, *Nat. Synth.*, 2023, **2**, 719–728.
- 29 Y. Meng, C. Lan, F. Li, S. Yip, R. Wei, X. Kang, X. Bu, R. Dong, H. Zhang and J. C. Ho, *ACS Nano*, 2019, **13**, 6060–6070.
- 30 Y. Meng, Z. Lai, F. Li, W. Wang, S. Yip, Q. Quan, X. Bu, F. Wang, Y. Bao, T. Hosomi, T. Takahashi, K. Nagashima, T. Yanagida, J. Lu and J. Ho, *ACS Nano*, 2020, **14**, 12749–12760.
- 31 Y. S. Li, J. Ge, J. Cai, J. Zhang, W. Lu, J. Liu, L. Chen, *Nano Res.*, 2014, **7**, 1623–1630.
- 32 W. Lu, J. Zhang, Y. S. Li, Q. Chen, X. Wang, A. Hassanien and L. Chen, *J. Phys. Chem. C*, 2012, **116**, 7158–7163.
- 33 J. Zhang, W. Lu, Y. S. Li, D. Lu, T. Zhang, X. Wang and L. Chen, *Acc. Chem. Res.*, 2015, **48**, 1788–1796.
- 34 T. Stabile and Y. S. Li, *Mater. Today Adv.*, 2021, **12**, 100189.
- 35 D. Shin, F. Zu, A. V. Cohen, Y. Yi, L. Kronik and N. Koch, *Adv. Mater.*, 2021, **33**, 2100211.
- 36 S. Liang, M. Zhang, Y. He, Z. Kang, M. Tian, M. Zhang, H. Miao and Z. Lin, *Chem. Mater.*, 2021, **33**, 6701–6712.
- 37 J. T. Mulder, I. du Fossé, M. A. Jazi, L. Mann and A. J. Houtepen, *ACS Energy Lett.*, 2021, **6**, 2519–2525.